DOE/PC/80011-T8

1001

DOE/PC/80011--T8

DE92 016987

DEVELOPMENT AND PROCESS EVALUATION OF
IMPROVED FISCHER-TROPSCH SLURRY CATALYSTS

g h

QUARTERLY TECHNICAL PROGRESS REPORT
FOR THE PERIOD 1 JULY TO 30 SEPTEMBER 1988

by

Howard P. Withers

Air Products and Chemicals, Inc.

Allentown, PA 18195

DOE/PC/80011-T8

and

Dragomir B. Bukur and Michael P. Rosynek

Departments of Chemical Engineering and Chemistry

Texas A&M University

College Station, TX 77843

WORK PERFORMED UNDER DOE CONTRACT NO. DE-AC22-85PC80011

FOR THE UNITED STATES DEPARTMENT OF ENERGY

THE PITTSBURGH ENERGY TECHNOLOGY CENTER

PITTSBURGH, PENNSYLVANIA

MASTER

1001

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Project Manager - George Cinquegrane
Liquid Fuels Division
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

Program Manager - John Shen
Office of Coal Preparation & Liquefaction
Department of Energy
Washington, DC

TABLE OF CONTENTS

I. Abstract	1
II. Objective and Scope of Work	2
III. Summary of Progress	3
IV. Detailed Description of Technical Progress	5
Task 1 – Project Work Plan	5
Task 2 – Slurry Catalyst Improvement	5
Task 3 – Process Evaluation Research	5
3.1. Slurry Reactor Catalyst Studies	5
3.1.1. Slurry Reactor Wax Withdrawal	5
3.1.2. Run SB-27-2168 (100 Fe/3.0 Cu/0.5 K)	6
3.1.3. Run SB-66-2468 (100 Fe/5.0 Cu/4.2 K/24 SiO ₂)	8
3.2. Fixed Bed Catalyst Studies	12
3.2.1. Run FA-15-1768 (100 Fe/1.0 Cu/0.2 K)	12
3.2.2. Runs FB-27-2438/FA-27-2518 (100 Fe/3.0 Cu/0.5 K)	14
3.2.3. Run FB-66-1948 (100 Fe/5.0 Cu/4.2 K/24 SiO ₂)	16
Tables	19
Figures	37

I. ABSTRACT

A larger internal filter was fabricated and successfully tested for wax withdrawal and then used in the two slurry runs. It was used for all wax withdrawals in the second slurry run, and there appears to be no catalyst in the wax removed. However, some wax had to be returned to the reactor following most withdrawals to flush catalyst adhering to the reactor walls and the filter element. Two slurry runs were made to test catalyst stability. In the first run, the unsupported 100 Fe/3.0 Cu/0.5 K catalyst was tested. The catalyst deactivated rapidly due to operational problems during the change over from helium to syngas. Following reduction with CO the catalyst was inadvertently exposed to CO for an additional 27 hours. The second test was made using the supported 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst. This catalyst was found to be fairly stable, however, operational problems related to wax withdrawal lead to a gradual loss in activity. Hydrocarbon selectivity for this catalyst was similar to that for the Ruhrchemie LP 33/81 catalyst, although our catalyst was more active.

A stability run of unsupported 100 Fe/1.0 Cu/0.2 K catalyst was completed. This run was a retest of a previous stability run of the same catalyst, and in both there was strong deactivation. No operational problems were encountered in either run, and it appears that this catalyst is not stable. Two stability runs using unsupported 100 Fe/3.0 Cu/0.5 K catalyst, which was activated with CO at ambient pressure using a different temperature and duration for each run (280 °C, 12 h and 335 °C, 24 h). Catalyst reduced at higher temperature was less stable and produced more gaseous hydrocarbons than catalyst reduced at the lower temperature. A stability run using supported 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst has also been completed. This catalyst was found to be very stable. Catalyst selectivity was similar to the Ruhrchemie LP 33/81 catalyst, but our catalyst was more active and stable.

II. OBJECTIVE AND SCOPE OF WORK

The objective of this contract is to develop a consistent technical data base on the use of iron-based catalysts in Fischer-Tropsch (F-T) synthesis reactions. This data base will be developed to allow the unambiguous comparison of the performance of these catalysts with each other and with state-of-the-art iron catalyst compositions. Particular attention will be devoted to generating reproducible kinetic and selectivity data and to developing reproducible improved catalyst compositions. To accomplish these objectives, the following specific tasks will be undertaken.

TASK 1 - Project Work Plan

The objective of this task is to establish a detailed project work plan covering the entire period of performance of the contract. This includes estimated costs and manhours expended by month for each task.

TASK 2 - Slurry Catalyst Improvement

The primary purpose of this task is to develop improved iron-based catalysts, both precipitated and supported, that show enhanced activity and selectivity in slurry phase testing. This will be accomplished by gaining systematic understanding of the role of promoters, binders, supports and activation procedures in determining the activity and selectivity of iron-based catalysts. The catalyst development program will incorporate extensive physical and chemical characterization of these materials with the objective to establish correlations between the physical/chemical properties of these catalysts and the corresponding catalytic behavior for synthesis gas conversion.

TASK 3 - Process Evaluation Research

The purpose of this task is to subject the most improved catalysts (based on activity and selectivity) to a thorough process evaluation. This involves long term stability studies, investigation of a wide range of process variables, and determination of kinetic parameters.

Task 4 - Economic Evaluation

The aim of this task is to develop the relative economic impact for each improved catalyst composition and compare these economics with the economics of using the base case catalyst.

II. SUMMARY OF PROGRESS

A cylindrical 20 μm filter element (1.0-cm OD and 3.8-cm long) was used to conduct wax withdrawal studies in the slurry reactor. The tests showed that it was possible to remove wax from the reactor without removing any catalyst and without interfering with the run itself. The procedure was then used during the second slurry run to withdraw wax. It was possible to remove wax within a reasonable amount of time, although, some of the catalyst accumulated in the vicinity of the filter and on the reactor wall following the withdrawal. Some wax had to be returned to the reactor to flush the walls and the filter element and restore the drop in activity caused by the removal of some catalyst from the synthesis zone.

Two stability runs in the slurry reactors were completed during the past quarter. The first run was conducted using the unsupported 100 Fe/3.0 Cu/0.5 K catalyst (run SB-27-2168) and the second using the supported 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst. The catalyst deactivated rapidly in the first run, possibly due to prolonged exposure of the catalyst to CO. Following the reduction of the catalyst with CO, helium was accidentally diverted to the reactor through the H₂ mass flow meter, resulting in an additional 27 hours of exposure of the catalyst to a mixture of CO and He. Following relatively high initial catalyst activity (at 260 °C, 1.48 MPa, 2.0 NI/g-cat·h, H₂/CO = 0.67), the catalyst deactivated and the run was terminated after only four mass balances (after 339 hours on stream). In the second run, the supported 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst was activated using CO and tested at 250 °C, 1.48 MPa, 2 NI/g-cat·h and H₂/CO = 0.67. Five mass balances were conducted at these conditions and two more balances were conducted at space velocities of 4 and 1 NI/g-cat·h, respectively. Catalyst activity declined gradually with time on stream during the first five balances and hydrocarbon selectivity shifted toward lighter products. Some of the deactivation was possibly due to disturbances caused by the wax withdrawal/addition procedure that was repeated several times during the run. Hydrocarbon selectivities during this were comparable to those for the Ruhrchemie LP 33/81 catalyst. Catalyst activity was superior to

the Ruhrchemie catalyst although it declined with time on stream and was comparable to that for the Ruhrchemie catalyst towards the end of the run. The activity was lower than that obtained in the fixed bed reactor with the same catalyst.

Four stability runs in fixed bed reactors have been completed during the past quarter. In a test of unsupported 100 Fe/1.0 Cu/0.2 K catalyst (run FA-15-1768), which was begun during the previous period, catalyst deactivation occurred rapidly with time. Similar deactivation occurred in a previous stability run using this catalyst. Two stability runs using unsupported 100 Fe/3.0 Cu/0.5 K catalyst (FB-27-2438, FA-27-2518) were made. The difference between the two runs was the reduction procedure used to activate the catalyst: CO, ambient pressure, 280 °C, 12 h for run FB-27-2438, and CO, ambient pressure, 335 °C, 24 h for run FA-27-2518. After activation, the catalyst was tested at 260 °C, 1.48 MPa, 2.0 *Nl/g-cat·h* using an $H_2/CO = 0.67$ feed gas. The catalyst deactivated during both runs, however the catalyst reduced at 335 °C deactivated more strongly than the catalyst activated at 280 °C. The higher reduction temperature also shifted the hydrocarbon selectivity towards lower molecular weight products.

A fixed bed stability run using supported 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst has also been completed (run FB-66-1948). A process variables study was conducted as part of this run in the later mass balances (235-265 °C, 1.0-4.0 *Nl/g-cat·h*, $H_2/CO = 0.67$ and 1.0). This silica containing catalyst was found to be very stable, with a slight decrease in ($H_2 + CO$) conversion from 68.7 to 64.3 % over 457 h on stream. Catalyst selectivity did not change significantly with time. Varying the process conditions accelerated deactivation, but the loss in activity was not severe. This catalyst was more active and stable than Ruhrchemie LP 33/81 catalyst, and gave a similar product selectivity. Compared to our catalyst containing 8 parts SiO₂, the 24 parts SiO₂ catalyst was less active and favored lower molecular weight products. However, the higher silica content significantly improved catalyst stability.

III. DETAILED DESCRIPTION OF TECHNICAL PROGRESS

TASK 1 — Project Work Plan

The project work plan was completed during the first quarter of this project and the detailed work plan was submitted to APCI.

TASK 2 — Slurry Catalyst Improvement

No work has been performed on this task during this reporting period.

TASK 3 — Process Evaluation Research

3.1. Slurry Reactor Catalyst Studies.

3.1.1. Slurry Reactor Wax Withdrawal.

A 20 μm cylindrical filter element (1.0-cm OD, 3.8-cm long) was attached to the dipleg in the slurry reactor and was used to withdraw wax in the slurry run SB-27-2168. However, the filter cracked during the run and could not be used to withdraw wax. It was replaced with a new element following the completion of the run SB-27-2168 and tested. The filter element was positioned horizontally near the reactor wall at a static volume of 370 cc. 200 g of fresh FT-300 wax was added to the slurry remaining in the reactor from run SB-27-2168. Experiments were conducted at 260 °C, 1.48 MPa and 2 $\text{Ni/g-cat}\cdot\text{h}$ (assuming 30 g of catalyst) using a stirring speed of 1250 rpm, i.e. under typical synthesis conditions. A pressure differential of 10 psi was maintained across the filter element, i.e. between the reactor and the receiving vessel. During the first experiment a total of 220.6 g of slurry was withdrawn over a 7 h period and the withdrawal line was backflushed several times. The slurry was virtually free of solids (0.09 g). In the second experiment 189 g of the wax was returned to the reactor, and after 9.5 h of filtration (and no backflushing) a total of 195 g of slurry (0.02 g of solids) was withdrawn. These tests showed good filter performance and fairly good reproducibility and we decided to implement this procedure in the next slurry run SB-66-2468.

3.1.2. Run SB-27-2168 (100 Fe/3.0 Cu/0.5 K).

Slurry run SB-27-2168 was a long term test of a precipitated 100 Fe/3.0 Cu/0.5 K catalyst reduced *in situ* using CO as the reductant (280 °C, 0.79 MPa, 12 h). The reactor was charged with 45.2 g catalyst (270–325 mesh) and 295 g of purified *n*-octacosane to obtain a 13 weight % catalyst slurry. The slurry withdrawal dipleg, attached to a cylindrical 20 μ m filter element (1.0-cm OD by 3.8-cm long), was preset to give a static slurry volume of 370 cc. Four mass balances were performed during the run, and the run was voluntarily terminated after 339 hours on stream. The process conditions used during the run were: 260 °C, 1.48 MPa, (H_2/CO) = 0.67–1.0, 2.0–3.0 $Nl/g\text{-cat}\cdot h$. The major events occurring during run SB-27-2168 are summarized in Table 1, and the wax and solids inventory for the run is shown in Table 2. The results obtained from the mass balances are summarized in Table 3.

Following catalyst reduction, the reactor was cooled down with flowing helium to 260 °C and excess wax withdrawn through the filter. The slurry withdrawn was very dark in color and subsequently it has been determined that 6 g of catalyst was removed together with 42 g of wax. After increasing the pressure to 1.48 MPa, syngas with an H_2/CO feed ratio of 0.7 was introduced at a space velocity of 0.5 $Nl/g\text{-cat}\cdot h$ while maintaining the helium flow at 4 $Nl/g\text{-cat}\cdot h$. During the next 27 hours the syngas flow rate was gradually increased to 2 $Nl/g\text{-cat}\cdot h$ and helium flow was phased out. However, the gas contraction was very low, and the feed and tail gas sample analyses showed only CO in the former and no hydrocarbon products in the latter. At this point it was discovered that the helium purge from the slurry A reactor system was accidentally diverted through the H_2 mass flow meter. This means that the catalyst was exposed to a mixture of CO and He at 260 °C and 1.48 MPa for 27 hours, in addition to 12 h activation with pure CO at 280 °C and 0.79 MPa. After the problem was corrected, gas contraction showed an increase with time on stream. Slurry was again withdrawn through the filter element after 22 hours at the process conditions. The 101 g of slurry withdrawn was found to contain 8.7 g of catalyst, providing further

evidence of filter malfunction, possibly due to a leak in the filter element (at the end of the run, it was found that the filter had cracked due to its proximity to the stirring shaft in the reactor). All subsequent withdrawals were made through the external settling tank system described in the Technical Progress Report for 1 January–31 March 1988. No further operational problems were encountered during the remainder of the run.

A stability plot, ($\text{H}_2 + \text{CO}$) conversion versus time on stream, is shown in Fig. 1. The initial activity of the catalyst was relatively high with a ($\text{H}_2 + \text{CO}$) conversion of 68.3% at 46 hours on stream, however, the catalyst activity declined rapidly with time on stream, and the ($\text{H}_2 + \text{CO}$) conversion dropped to 13.6% at 333 hours on stream. During this period, the hydrocarbon distribution shifted toward higher molecular weight products. At 46 hours on stream the hydrocarbon fractions were 3.8 (CH_4), 15.1 ($\text{C}_2 - \text{C}_4$), 20.3 ($\text{C}_5 - \text{C}_{11}$) and 60.7% ($\text{C}_{12} +$), whereas at 237 hours on stream they were 2.89 (CH_4), 11.6 ($\text{C}_2 - \text{C}_4$), 9.46 ($\text{C}_5 - \text{C}_{11}$) and 76.1% ($\text{C}_{12} +$). For the same catalyst in the fixed bed reactor (run FB-27-2438, Section 3.2.2), the deactivation was slower and the hydrocarbon distribution shifted toward lower molecular weight products. In general, more light hydrocarbons were produced in the fixed bed test than in the slurry run under similar operating conditions. Hydrocarbon selectivity during the first mass balances for the two runs were 3.8 and 6.4 (CH_4), 15.1 and 25.4 ($\text{C}_2 - \text{C}_4$), 20.3 and 32.3 ($\text{C}_5 - \text{C}_{11}$), and 60.7 and 35.8% ($\text{C}_{12} +$) for the slurry and fixed bed tests, respectively. When syngas with $\text{H}_2/\text{CO} = 1.0$ was used in the slurry run (in balance 4), more light products were produced. The rapid deterioration of catalyst activity in the slurry run was probably due to the prolonged exposure of the catalyst to CO. Following the completion of the run, solids were separated from the slurry remaining in the reactor by filtering the slurry. The carbon was then burnt to recover the catalyst (in the oxidized form). Image analysis was used to determine particle size distribution for this catalyst and it was found that almost all of the catalyst was less than $15\mu\text{m}$ compared to the $45\text{--}53\mu\text{m}$ size cut for the original catalyst that was charged to the reactor.

3.1.3. Run SB-66-2468 (100 Fe/5.0 Cu/4.2 K/24 SiO₂).

Run SB-66-2468 was made as a long term stability test of the 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst. Results from this run will also be used to compare the performance of the catalyst in slurry and fixed bed reactor tests (Run FB-66-1948, Section 3.2.3). The catalyst was reduced *in situ* using CO as the reductant (280 °C, 0.79 MPa, 12 h). The reactor was charged with 35.1 g catalyst (270-325 mesh) and 282 g of purified n-octacosane. The first five mass balances (up to 460 h on stream) were made at 250 °C, 1.48 MPa, 2.0 Nl/g-cat·h, H₂/CO = 0.67 to determine catalyst stability. These conditions were repeated following balance 7. The effect of space velocity was studied in balances 6 (4.0 Nl/g-cat·h) and 7 (1.0 Nl/g-cat·h). The run was voluntarily terminated after 582 hours on stream. The major events occurring during the run are summarized in Table 4, and the wax and solids inventory for the run is shown in Table 5. The results obtained from the seven mass balances made during the run are summarized in Table 6.

Following reduction the reactor was cooled to 230 °C with flowing helium and the excess wax was withdrawn through a cylindrical filter element (1.0-cm OD by 3.8-cm long). The withdrawal of 65 g of wax took only 5 minutes and the clarity of the wax confirmed successful operation of the filter. After increasing the pressure to 1.48 MPa, syngas with H₂/CO = 0.67 was introduced at a gas space velocity of 2 Nl/g-cat·h and the reactor temperature was gradually raised to 250 °C. These conditions were maintained for 19 days (455 hours). Over this period of time, five mass balances and twelve wax withdrawals (through the internal filter) were made. The durations for the wax withdrawals ranged between 5 and 40 minutes, depending on the quantity of wax withdrawn. It was possible to withdraw as much as 150 g of wax in 30-40 minutes without the need to backflush the filter.

The activity plot for this catalyst (gas contraction versus time on stream) is shown in Figs. 2 (0-240 h TOS) and 3 (241-460 h TOS). Also shown on these plots are the instances when wax was withdrawn from or added to the reactor together with the respective amounts. Catalyst activity

initially increased and the contraction reached 40.4% at 33 hours on stream at which point in time 142 g of wax was withdrawn from the reactor through the internal filter. Immediately following the wax withdrawal, contraction dropped sharply from 40.4% to 14.7% (corresponding to a drop in $(\text{H}_2 + \text{CO})$ conversion from 56.6% to 17.9%). There appeared to be no catalyst present in the wax withdrawn from the reactor, therefore the sudden loss in activity was probably due to the removal of a large portion of the catalyst from the synthesis zone. Accumulation of the catalyst in the vicinity of the filter element was suspected and corrective measures were taken. During the withdrawal of the wax through the filter, the catalyst must have been left on the reactor wall (as the slurry level dropped gradually) and some of it must have collected in the narrow space between the filter element and the reactor wall. Backflushing of the filter with a small quantity of hexane (20 cc) did not improve the contraction significantly (contraction increased from 14.7% to 21.3%). We then added 98 g of wax back to the reactor through the external settling tank (described in the Technical Progress Report for 1 January-31 March 1988). The activity was restored to pre-withdrawal level within 18 hours following the addition of the wax (contraction reached 40.5%). The addition of the wax increased the slurry volume and the agitation was sufficient to flush the accumulated catalyst back into the slurry. Following the first mass balance (TOS = 76 h), wax was again withdrawn from the reactor, however, the withdrawal procedure was stopped short of complete withdrawal of all excess wax. The contraction did not change following this withdrawal, probably because the slurry level was sufficiently above the filter element to prevent any catalyst accumulation. However, following the majority of the subsequent wax withdrawals, a drop in contraction was observed and wax had to be returned to the reactor. Also, following each wax addition to the reactor, an equivalent amount of wax was withdrawn from the reactor 24 hours following the addition, i.e. after enough wax was produced to cover the filter element. Using this procedure, it was possible to prevent any significant wax withdrawal related losses in catalyst activity. No other operating problems were encountered during the entire run.

The 100 Fe/5.0 Cu/4.2 K/24 SiO₂ catalyst was fairly stable in comparison to slurry tests with other catalysts, with some loss in activity over the first 19 days (constant conditions). The stability plot for the run over this period is shown in Fig 4. Also included are the (H₂+CO) conversion values obtained following the seventh mass balance, when the initial conditions were repeated. Catalyst activity increased initially and reached a maximum at 107 hours on stream (H₂+CO conversion of 58.7%), thereafter it steadily declined and the (H₂+CO) conversion at 460 hours on stream was 44% (a 25% loss in activity). The deactivation of the catalyst over this period could possibly have been caused by the introduction of small quantities of air into the reactor during the wax addition process. The wax addition procedure involved the addition of molten wax to the external settling tank, following which the tank was purged with helium. The wax was then forced into the reactor using a slight over pressure in the settling tank. Any air dissolved in the wax, or present in the settling tank would be introduced into the reactor and would have a detrimental effect on catalyst activity. When the same conditions were repeated after mass balance 7, the (H₂+CO) conversion was 35.4% (at 558 hours on stream), which represents a 20% drop in activity in comparison to balance 5 conducted at 453 hours on stream. The accelerated catalyst deactivation is probably due to the combined effects of frequent changes in process conditions and the repeated introduction of small quantities of air into the reactor during the wax addition procedure. As discussed earlier, we had suspected that some of the catalyst was accumulating in the vicinity of the filter element and on the reactor wall following each withdrawal of wax. During these periods, it is likely that the concentrated catalyst regions might result in localized hot spots, which would be detrimental to catalyst performance, leading to a further loss in activity with time on stream. Inspection of the reactor, following the completion of the run, showed that a layer of slurry was adhering to the reactor wall above the slurry level, and it is likely that any catalyst entrained in this layer would have deactivated fairly rapidly. When the same catalyst was tested in the fixed bed reactor (Run FB-66-1048, section 3.2.3), the catalyst was very stable and more active than in the slurry

reactor. ($\text{H}_2 + \text{CO}$) conversion in the fixed bed was 68.7% initially and declined to 64.3% after 457 hours on stream, a drop of only 6.4% in activity. Catalyst activity in the slurry test was superior to that of the Ruhrchemie LP 33/81 catalyst (similar composition to our catalyst 100 Fe/4 Cu/4 K/25 SiO_2), whose stability plot for the slurry run SA-99-0888 (Technical Progress Report for 1 April-30 June 1988) is also included in Fig. 4. The initial activity of the Ruhrchemie catalyst was lower (with $\text{H}_2 + \text{CO}$ conversion of around 46%) compared to our catalyst (having $\text{H}_2 + \text{CO}$ conversion of around 56%) at the start of the run. However, at 336 hours on stream the differences in activities for the two catalysts were smaller, with an ($\text{H}_2 + \text{CO}$) conversion of around 45% for the Ruhrchemie catalyst and around 51% for our catalyst. Activities for the two catalysts at the end of the respective runs were the same ($\text{H}_2 + \text{CO}$ conversions of around 35%), following some deactivation of the two catalysts.

With a decline in catalyst activity over the first 19 days (constant conditions), the hydrocarbon selectivity shifted slightly towards lighter products. At 69 hours on stream (balance 1) the hydrocarbon fractions were 3.9 (CH_4), 17.9 ($\text{C}_2 - \text{C}_4$), 20.7 ($\text{C}_5 - \text{C}_{11}$) and 57.5% ($\text{C}_{12} +$), whereas at 453 hours on stream (balance 5) they were 6.3 (CH_4), 21.8 ($\text{C}_2 - \text{C}_4$), 23.5 ($\text{C}_5 - \text{C}_{11}$) and 48.3% ($\text{C}_{12} +$). During the same period, the olefin/paraffin ratios decreased for all carbon numbers (Table 6). A similar, although weaker, trend was observed when the same catalyst was tested in the fixed bed reactor, where at 71 hours on stream (balance 1) the hydrocarbon fractions were 5.8 (CH_4), 21.9 ($\text{C}_2 - \text{C}_4$), 21.4 ($\text{C}_5 - \text{C}_{11}$) and 50.9% ($\text{C}_{12} +$), whereas at 477 hours on stream (balance 5) they were 6.5 (CH_4), 25.5 ($\text{C}_2 - \text{C}_4$), 24.8 ($\text{C}_5 - \text{C}_{11}$) and 43.2% ($\text{C}_{12} +$). However, over this period in the fixed bed, the olefin/paraffin ratios for all carbon numbers, either remained the same or showed a marginal increase with time on stream. In general, more light products were produced in the fixed bed than in the slurry test. For the Ruhrchemie catalyst, hydrocarbon selectivity had a trend that was similar to that for the 100 Fe/5.0 Cu/4.2 K/24 SiO_2 catalyst: at 49 hours on stream (balance 1) the hydrocarbon fractions were 4.3 (CH_4), 17.8 ($\text{C}_2 - \text{C}_4$), 22.1 ($\text{C}_5 - \text{C}_{11}$) and 55.8% ($\text{C}_{12} +$),

whereas at 336 hours on stream (balance 5) they were 4.6 (CH₄), 21.3 (C₂-C₄), 29.5 (C₅-C₁₁) and 44.6% (C₁₂+). The olefin/paraffin ratios for the Ruhrchemie catalyst also showed a decline with time on stream over the same period. In balances 6 and 7 of the present run, the effect of space velocity (1 and 4 *Nl/g-cat·h*) on the catalyst activity and product selectivity was studied. Conversion decreased with higher space velocity, as would be expected, with an (H₂+CO) conversion of 26.2% at 4 *Nl/g-cat·h* at 500 *h* (balance 6) compared to 44.3% at 2 *Nl/g-cat·h* at 453 *h* (balance 5). Hydrocarbon selectivity shifted toward lighter products with an increase in space velocity: 7.8 (CH₄), 27.7 (C₂-C₄), 21.8 (C₅-C₁₁) and 42.7% (C₁₂+). The olefin/paraffin ratios for most carbon numbers increased at the same time. When a lower space velocity was used (1 *Nl/g-cat·h* in balance 7), hydrocarbon selectivities were comparable to those obtained in balance 5 at 2 *Nl/g-cat·h*, but the olefin/paraffin ratios showed a significant decrease for all carbon numbers (Table 6). The shift in hydrocarbon selectivity toward lighter products as the catalyst aged has also been shown for other catalysts tested.

3.2. Fixed Bed Catalyst Studies.

3.2.1. Run FA-15-1768 (100 Fe/1.0 Cu/0.2 K).

The fixed bed stability test of the 100 Fe/1.0 Cu/0.2 K catalyst that began in the previous reporting period and was made as a repeat of run FA-15-1698 (Technical Progress Report for 1 April-30 June 1988) has been completed. In both of these runs, the catalyst (30/60 mesh) was reduced at 280 °C for 16 *h* using CO. Following the activation treatment, the catalyst was tested at a fixed set of operating conditions (235 °C, 1.48 *MPa*, 2.0 *Nl/g-cat·h*, H₂/CO = 0.71). Rapid deactivation occurred during both runs. Only a single mass balance was completed in run FA-15-1698 before it was terminated due to the deactivation. During the retest, run FA-15-1768, 6 mass balances were completed. The first two mass balances (up to 175 *h*) were made at the conditions above, and balances 3 and 4 (up to 367 *h*) were made using H₂/CO = 1.03 feed gas. During balances 5 and 6 (up to 511 *h*), the temperature was increased to 250 °C and a H₂/CO = 0.71 feed

gas was used. The results for both runs FA-15-1698 and FA-15-1768 are summarized in Table 7.

With the exception of run FA-15-2097, the 100 Fe/1.0 Cu/0.2 K catalyst deactivated quickly during catalyst testing, as discussed in the previous progress report (Technical Progress Report for 1 April-30 June 1988). In the recent tests, the initial activity of the catalyst was high, but decreased with time. The stability plot for the two runs is shown in Fig. 5. In run FA-15-1768, the (H₂+CO) conversion dropped from 59.1 % at 25.5 h to 31.2 % at 175 h. Switching to an H₂/CO = 1.03 synthesis gas increased conversion slightly to 33.7 % at 191 h, but the catalyst continued to deactivate. At these same nominal conditions (235 °C, 1.48 MPa, 2.0 Nl/g-cat·h, H₂/CO = 1.0) during the successful run FA-15-2097, the H₂/CO conversion was 72.9 %. The increase in temperature to 250 °C at about 392 h increased the conversion to only 34.5 %.

Catalyst selectivity for the two recent tests (FA-15-1698/FA-15-1768) of the 100 Fe/1.0 Cu/0.2 K catalyst is compared in Fig. 6 (235 °C, H₂/CO = 0.71). The selectivity during the first stability test was towards more lighter hydrocarbons than the retest and the C₁₂+ weight percent decreased from 63 % to 49 % (balance 1) between the two runs. A comparison of the selectivity for run FA-15-1768 and the two previous runs (FA-15-2097, Technical Progress Report for 1 July-30 September 1987; FA-15-0278, Technical Progress Report for 1 January-31 March 1988) is shown in Fig. 7 (235 °C, H₂/CO = 1.0, nominal). The recent test shows higher selectivity to high molecular weight products with a substantially greater C₁₂+ fraction of hydrocarbons. The olefin/paraffin ratios are also higher than in previous tests, although this may be due to the deactivation of the catalyst. The (H₂+CO) conversions for the four balances shown in Fig. 7 were 29.8 (balance 3) and 26.5 % (balance 4) in run FA-15-1768, 72.9 % in run FA-15-2097, and 44.7 % in run FA-15-0278, and the differences in conversion may have affected the olefin/paraffin ratios. There was no significant effect of time on stream on the weight percent hydrocarbon distribution during FA-15-1768 at any of the 3 sets of conditions used.

3.2.2. Runs FB-27-2438/FA-27-2518 (100 Fe/3.0 Cu/0.5 K).

Runs FB-27-2438 and FA-27-2518 were intended as long term stability tests of the 100 Fe/3.0 Cu/0.5 K catalyst. This catalyst was tested previously during the Promoter Effect Research portion of this investigation in run FA-27-2557 (Technical Progress Report for 1 July-30 September 1988). The two recent runs differed in the procedure used to activate the catalyst. In both runs, the reductant used was CO at ambient pressure, and the catalyst was ground to 30/60 mesh and diluted with glass beads before loading the reactor in our usual fashion. In run FB-27-2438, the catalyst was reduced at 280 °C for 12 h, our usual method of activation. After the 12 h pretreatment, the reactor was cooled to 260 °C in helium (4.0 $Nl/g\text{-cat}\cdot h$), and the reactor pressure was increased to 1.48 MPa. Synthesis gas ($H_2/CO = 0.69$) was then introduced while continuing to feed He, and the syngas flow rate was gradually increased from 0.5 to 2.0 $Nl/g\text{-cat}\cdot h$ over a 4 h period. After the full syngas flow was established, the He flow was phased out over a 2.5 h period. A hot spot (280 °C) developed about 15 cm below the top of the bed after the He flow was discontinued, and He was reintroduced at 0.7 $Nl/g\text{-cat}\cdot h$ to cool the reactor. After 17 h at these conditions, the He was again discontinued and the stability run was begun (260 °C, 1.48 MPa, $H_2/CO = 0.69$, 2.0 $Nl/g\text{-cat}\cdot h$). In run FA-27-2518, the catalyst was reduced at 335 °C for 24 h, which is similar to the optimum procedure studied by Pichler (Emmett, P. H., ed., *Catalysis*, v. IV, 1956, pp 176-180). This procedure was reported to give high activity and stability over a long period of time.

Three mass balances were performed during run FB-27-2438 and the results are summarized in Table 8. The results for the two mass balances performed during run FA-27-2518 are summarized in Table 9. All balances were performed at 260 °C, 1.48 MPa, 2.0 $Nl/g\text{-cat}\cdot h$, using an $H_2/CO = 0.67$ (nominal) feed gas. The stability plot for both runs is shown in Fig. 8. The catalyst activated at 335 °C for 24 h (FA-27-2518) deactivated rapidly, with the (H_2+CO) conversion dropping from an initial 74.2 % to 47.2 % at 143 h at conditions. The conversion for catalyst activated at 280 °C

for 12 h (FB-27-2438) initially increased to a maximum 88.2 % at 7.5 h at conditions, then began deactivating. The deactivation was less severe than during run FA-27-2518 and the conversion was still 72 % at 143 h. After 265 h, the ($\text{H}_2 + \text{CO}$) conversion dropped to 66.7 %.

The hydrocarbon selectivity and olefin/paraffin ratios as a function of time are compared in Fig. 9 for both runs. During run FB-27-2438, the weight percent hydrocarbon distribution shifted towards lower molecular weight products as the catalyst deactivated with time. We have noticed this trend during other stability tests. The shift to lighter products was not significant during run FA-27-2518, although the catalyst was already deactivated during both balances (the average conversions were 57.5 and 47.3 %, respectively, during the two balances). No strong trend in the olefin/paraffin ratios occurred for either catalyst test. While it is difficult to distinguish between the effects of deactivation and reduction procedure in these two runs, it appears that the higher reduction temperature (335 °C, FA-27-2518) causes the catalyst to produce more lower molecular weight products. For example, the lowest methane percentage, 9.3 % (FA-27-2518, balance 2, 166 h), for the high temperature reduction was greater than the highest methane percentage, 8.0 % (FB-27-2438, balance 3, 240 h), for the lower reduction temperature. In our activation/reduction studies using 100 Fe/3.0 Cu/0.2 K catalyst, we found that higher reduction temperatures produced catalyst which favored high molecular weight products.

The high reduction temperature does not follow trends obtained during the Activation/Reduction procedure tests with a similar catalyst (100 Fe/3.0 Cu/0.2 K, Technical Progress Report for 1 October-31 December 1987). In those tests, we found that with 24 h reductions, higher reduction temperature favored increased stability, however in runs FB-27-2438 and FA-27-2518 deactivation occurred very rapidly. The strong deactivation may be due to the high reaction temperature (260 °C) and low feed ratio ($\text{H}_2/\text{CO} = 0.67$ nominal) used in these more recent runs. These two tests show that the standard reduction procedure produces a more active and stable catalyst than the procedure used by Pichler for our catalyst. Our reduction procedure also produces a catalyst with

a more favorable hydrocarbon selectivity (less CH_4 , more $\text{C}_{12}+$).

3.2.3. Run FB-66-1948 (100 Fe/5.0 Cu/4.2 K/24 SiO_2).

Run FB-66-1948 was made as a long term stability test of the 100 Fe/5.0 Cu/4.2 K/24 SiO_2 catalyst. The first 5 mass balances (up to 457 h) were made at 250 °C, 1.48 MPa, 2.0 $\text{Nl/g-cat}\cdot\text{h}$, $\text{H}_2/\text{CO} = 0.69$, which were held constant to determine catalyst stability. Balance 10 was a repeat of these conditions. The effect of space velocity was studied in balances 6 (4.0 $\text{Nl/g-cat}\cdot\text{h}$) and 7 (1.0 $\text{Nl/g-cat}\cdot\text{h}$), and the effect of feed ratio was studied in balances 8 and 9 ($\text{H}_2/\text{CO} = 1.03$). With an $\text{H}_2/\text{CO} = 0.70$ feed, temperature was varied in balances 11 (265 °C) and 12 (235 °C). The twelve mass balances completed during this run are summarized in Table 10.

The 100 Fe/5.0 Cu/4.2 K/24 SiO_2 catalyst was very stable, and the stability plot for the run (up to 457 h) is shown in Fig. 10. The (H_2+CO) conversion decreased from an initial 68.7 % to 64.3 % after 457 h. In the repeat of conditions (balance 10, 765 h) the conversion was still high, 57.7 %, although it is clear that varying the process conditions accelerated the rate of deactivation. The activity was superior to that of the Ruhrchemie LP 33/81 catalyst, whose stability plot for run FB-99-1588 (Technical Progress Report for 1 April-30 June 1988) is also shown in Fig. 10. The initial activity of both catalysts was approximately equal, but at about 340 h, the Ruhrchemie catalyst gave an (H_2+CO) conversion of 44.2 % while our 100 Fe/5.0 Cu/4.2 K/24 SiO_2 catalyst gave a conversion of 65.5 %. The 24 parts SiO_2 catalyst is also more stable, but less active, than our catalyst containing only 8 parts SiO_2 . The (H_2+CO) conversions at 235 °C ($\text{H}_2/\text{CO} = 1.0$) obtained with the 8 parts SiO_2 catalyst, shown in Fig. 10, are higher initially than for either the 24 parts SiO_2 catalyst or Ruhrchemie LP 33/81 at 250 °C ($\text{H}_2/\text{CO} = 0.69$). However, the catalyst containing 8 parts SiO_2 deactivated rapidly, in spite of being operated at milder conditions (235 °C).

The effect of time on catalyst selectivity is shown in Fig. 11. There was a very mild shift towards lighter products as the catalyst aged, a trend which has also been seen with other catalysts.

Between 71 (balance 1) and 477 h (balance 5), methane increased from 5.8 to 6.5 % while the $C_{12}+$ products decreased from 50.9 to 41.0 %. There was no effect of time on the olefin/paraffin ratios measured during the stability portion of the run. In balances 6-9, 11 and 12, the conditions were varied to study catalyst activity and selectivity at different sets of process conditions. The (H_2+CO) conversions and weight percent hydrocarbon distribution at the different process conditions used in these balances are shown in Fig. 12. In this figure, the average results from balances 1-5 (250 °C, 2.0 $Nl/g\text{-cat}\cdot h$, $H_2/CO = 0.69$) and balances 8 and 9 (250 °C, 2.0 $Nl/g\text{-cat}\cdot h$, $H_2/CO = 1.0$) are shown. The hydrocarbon distribution is shown as a series of bars and the (H_2+CO) conversion is shown as symbols connected by a line. Conversion increases with temperature, which is expected, and the hydrocarbon distribution shifts towards lower molecular weight products. The selectivity trend is weak between 235 (balance 12) and 250 °C (balances 1-5), however the first five balances do not reflect the effect of deactivation on selectivity. Deactivation causes more methane to be formed. For example, in balances 12, 10, and 11 at 235, 250, and 265 °C, respectively, CH_4 increases from 6.1 to 6.5 and 8.6 % while $C_{12}+$ decreases from 48.5 to 45.2 and 37.3 %. The space velocity was varied at 250 °C in balances 7, 1-5, and 6 at 1.0, 2.0, and 4.0 $Nl/g\text{-cat}\cdot h$. Conversion decreased with higher space velocity, and there was no clear effect on the hydrocarbon distribution. The CH_4 and C_2-C_4 fractions remained fairly constant, while shifting occurred between the C_5-C_{11} and $C_{12}+$ products. The conversion using a higher H_2/CO feed ratio was lower than the initial conversion, decreasing from an average 66 % (balances 1-5, $H_2/CO = 0.69$) to 60.6 % (balances 8-9, $H_2/CO = 1.0$), but this may be due to catalyst deactivation. The (H_2+CO) conversion obtained in balance 10 at the same conditions with $H_2/CO = 0.70$ was only 57.7 %. Less $C_{12}+$ products and more gaseous hydrocarbons were produced using the $H_2/CO = 1$ feed ratio than in any of the balances (1-5, 10) using the lower feed ratio, which we have also observed in tests using other catalysts.

The selectivity obtained during the stability test of the 24 parts SiO_2 catalyst is compared to the stability tests for our 8 parts SiO_2 catalyst and Ruhrchemie LP 33/81 (runs FA-63-1308

and FB-99-1588, Technical Progress report for 1 April-30 June 1988) in Fig. 13. Lower silica concentration improves production of $C_{12}+$ products and decreases the fractions of CH_4 and C_2-C_4 . We obtained similar results during the initial tests of these catalysts. The 8 parts SiO_2 catalyst also has higher initial activity, but the catalyst deactivates more rapidly than the catalyst with 24 parts SiO_2 . The selectivities of our catalyst and Ruhrchemie catalyst are very similar, while our catalyst is more stable.

Task 4 - Economic Evaluation

No work on this task was scheduled during this quarter.

Table 1. Major events occurring in run SB-27-2168.

TOS (h)	Event
- 44	Catalyst pretreatment: CO, 280 °C, 0.79 MPa, 12 h
- 27	Cooled to 260 °C, pressurized to 1.48 MPa with He
- 25	Began blending synthesis gas with He
- 24	Wax plug in high pressure unsteady state trap repaired
- 20	First attempt to initiate run
- 18	Reactor exit gas showed no H ₂ peak
- 2	Feed gas difficulty corrected (He, instead of H ₂ , was flowing into inlet line)
0	Run initiated
2.0	Achieved desired operating conditions: 260 °C, 1.48 MPa, (H ₂ /CO) = 0.67, 2.3 NI/g-cat·h
46.0	Conditions stable, (H ₂ +CO) conversion = 68.2 %
141.0	Conditions stable, (H ₂ +CO) conversion = 31.3 %
238.0	Conditions stable, (H ₂ +CO) conversion = 15.8 %
246.0	Changed process conditions: 260 °C, 1.48 MPa, (H ₂ /CO) = 1.00, 2.0 NI/g-cat·h
339.0	Voluntary termination of run SB-27-2168

Table 2. Wax and solids inventory for run SB-27-2168.

TOS (h)	Description
- 68	Reactor charged with 295 g-wax, 45.2 g-cat
- 27	Slurry withdrawal using internal filter: 42.0 g-wax, 6 g-cat removed after reduction
- 21	Slurry withdrawal using internal filter: 1.0 g-wax, 0 g-cat
22	Slurry withdrawal using internal filter: 92.0 g-wax, 8.7 g-cat
46	Began using external settling tank withdrawals due to failure of internal filter
52	Slurry withdrawal using settling tank: 163 g-wax, 3.2 g-cat
123	Slurry withdrawal using settling tank: 150 g-wax, 1.3 g-cat
243	Slurry withdrawal using settling tank: 174 g-wax, 0.6 g-cat
339	Slurry withdrawal using settling tank: 76.0 g-wax, 0.3 g-cat
341	258 g-wax, 18.4 g-cat removed at end of run, 103 % wax recovery, 83 % solids recovery

Table 3. Summary of results for slurry run SB-27-2168.

Catalyst: 100 Fe/3.0 Cu/0.5 K
 Reactor volume: 370 cc^b
 Slurry liquid: n-octacosane

Period	1	2	3	4
Date	08/06/88	08/10/88	08/14/88	08/18/88
Time on Stream (h)	45.5	141.0	236.3	333.0
Balance Duration (h)	6.0	6.0	6.2	6.2
Average Temperature (°C)	260.	260.	260.	260.
Pressure (MPa)	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.67	.67	.67	1.00
Space Velocity (NI/g-cat-h) ^a	2.96	2.34	2.34	2.01
Space Velocity (NI/g-Fe-h)	4.37	3.45	3.45	2.96
GHSV (h ⁻¹) ^b	244.	165.	165.	138.
CO Conversion (%)	72.7	33.5	16.7	13.6
H ₂ +CO Conversion (%)	68.3	31.2	15.9	10.8
H ₂ /CO Usage	.57	.56	.58	.59
STY (mols H ₂ +CO/g-cat-h) ^a	.090	.033	.017	.010
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	21.0	8.1	4.9	2.6
Weight % of Outlet				
H ₂	1.77	3.32	3.96	6.24
H ₂ O	.97	.87	.59	1.25
CO	26.3	63.7	80.1	81.4
CO ₂	53.6	23.9	10.3	7.33
Hydrocarbons	9.30	4.99	2.64	1.83
Oxygenates	.27	.19	.09	.11
Wax ^c	7.78	3.04	2.36	1.82
Yield (g/Nm ³ H ₂ + CO Converted)				
CH ₄	7.46	6.16	7.10	11.6
C ₂ -C ₄ Hydrocarbons	29.4	28.5	28.4	36.3
C ₅ -C ₁₁ Hydrocarbons	39.6	36.1	23.2	20.1
C ₁₂ + Hydrocarbons	118.	130.	187.	156.
Wax ^c	88.6	76.1	116.	112.
Oxygenates	3.06	4.87	4.21	6.79
Total	198.	206.	250.	231.
1+2 Olefins/n-Paraffin Ratio				
C ₂	2.57	4.40	4.50	2.12
C ₃	7.12	6.16	4.77	3.41
C ₄	5.79	4.97	4.12	2.92
C ₈	5.16	4.33	4.19	1.92
C ₁₀	4.33	3.85	3.18	2.39

^a Based on unreduced catalyst^c Unanalyzed wax withdrawn from reactor^b Based on static slurry volume

Table 3'(cont'd). Summary of results for slurry run SB-27-2168.

Weight % of Hydrocarbons	Period			
	1	2	3	4
CH ₄	3.84	3.07	2.89	5.17
Ethane	1.30	.86	.63	1.59
Ethylene	3.11	3.26	2.63	3.14
Propane	.68	.72	.69	1.24
Propylene	4.63	4.21	3.16	4.04
n-Butane	.74	.81	.80	1.42
1+2 Butenes	4.16	3.87	3.18	4.01
C ₄ Isomers	.48	.53	.48	.74
n-Pentane	.92	1.00	.81	1.23
1+2 Pentenes	3.27	3.05	2.18	2.59
C ₅ Isomers	.19	.21	.18	.27
n-Hexane	.49	.53	.32	.56
1+2 Hexenes	2.50	2.37	.64	1.54
C ₆ Isomers	.50	.73	.30	.00
n-Heptane	.43	.39	.21	.53
1+2 Heptenes	2.10	1.76	.98	1.13
C ₇ Isomers	.37	.49	.15	.00
n-Octane	.36	.31	.13	.25
1+2 Octenes	1.82	1.30	.54	.48
C ₈ Isomers	.26	.09	.02	.00
n-Nonane	.37	.30	.17	.03
1+2 Nonenes	1.71	1.14	.52	.06
C ₉ Isomers	.15	.10	.04	.00
n-Decane	.42	.37	.23	.04
1+2 Decenes	1.81	1.41	.72	.09
C ₁₀ Isomers	.19	.17	.08	.01
n-Undecane	.45	.39	.21	.04
1+2 Undecenes	1.81	1.57	.90	.11
C ₁₁ Isomers	.22	.26	.11	.01
C ₂ -C ₄	15.1	14.2	11.6	16.2
C ₅ -C ₁₁	20.3	17.9	9.46	8.97
C ₁₂ +	60.7	64.8	76.1	69.7
Wax ^c	45.5	37.9	47.2	49.8

^c Unanalyzed wax withdrawn from reactor

Table 4. Major Events occurring in run SB-66-2468.

TOS (h)	Event
- 14	Catalyst Pretreatment: CO, 280°C, 0.79 MPa, 12 h
- 2	Cooled to 260°C and pressurized to 1.48 MPa using He
0	Run initiated
5	Achieved desired operating conditions: 260°C, 1.48 MPa, H ₂ /CO = 0.69, 2 Nl/g-cat·h
33	Sharp drop in catalyst activity following wax withdrawal
61	Activity recovered following addition of wax to reactor
69	Conditions stable, H ₂ +CO conversion = 56.1%
165	Conditions stable, H ₂ +CO conversion = 51.9%
171	Sharp drop in catalyst activity following wax withdrawal
201	Activity recovered following addition of wax to reactor
261	Conditions stable, H ₂ +CO conversion = 53.2%
269	Sharp drop in catalyst activity following wax withdrawal
271	Activity recovered following addition of wax to reactor
357	Conditions stable, H ₂ +CO conversion = 49.3%
364	Small drop in catalyst activity following wax withdrawal
384	Activity recovered following addition of wax to reactor
453	Conditions stable, H ₂ +CO conversion = 44.3%
460	Changed operating conditions: 260°C, 1.48 MPa, H ₂ /CO = 0.69, 4 Nl/g-cat·h
509	Changed operating conditions: 260°C, 1.48 MPa, H ₂ /CO = 0.69, 1 Nl/g-cat·h
555	Small drop in catalyst activity following wax withdrawal
557	Activity recovered following addition of wax to reactor
558	Changed operating conditions: 260°C, 1.48 MPa, H ₂ /CO = 0.69, 2 Nl/g-cat·h
582	Voluntary termination of run SB-66-2468

Table 5. Wax and Solid Inventory for run SB-66-2468.

TOS (h)	Event
-- 24	Slurry loading: 282 g-wax, 35.1 g-cat
- 0	Slurry withdrawal using internal filter: 65 g-wax, 0 g-cat removed after reduction
33	Slurry withdrawal using internal filter: 142 g-wax, 0 g-cat
52	Slurry returned to reactor: 98 g-wax, 0 g-cat
76	Slurry withdrawal using internal filter: 150 g-wax, 0 g-cat
101	Slurry withdrawal using internal filter: 46 g-wax, 0 g-cat
124	Slurry withdrawal using internal filter: 88 g-wax, 0 g-cat
148	Slurry withdrawal using internal filter: 71 g-wax, 0 g-cat
171	Slurry withdrawal using internal filter: 60 g-wax, 0 g-cat
194	Slurry returned to reactor: 94 g-wax, 0 g-cat
223	Slurry withdrawal using internal filter: 88 g-wax, 0 g-cat
269	Slurry withdrawal using internal filter: 191 g-wax, 0 g-cat
270	Slurry returned to reactor: 100 g-wax, 0 g-cat
338	Slurry withdrawal using internal filter: 96 g-wax, 0 g-cat
364	Slurry withdrawal using internal filter: 172 g-wax, 0 g-cat
366	Slurry returned to reactor: 95 g-wax, 0 g-cat
438	Slurry withdrawal using internal filter: 101 g-wax, 0 g-cat
555	Slurry withdrawal using internal filter: 101 g-wax, 0 g-cat
557	Slurry returned to reactor: 49 g-wax, 0 g-cat
582	Slurry withdrawal using internal filter: 56 g-wax, 0 g-cat
590	174 g-wax, 21.3 g-cat removed at end of run, 80 % wax recovery, 61 % solids recovery.

Table 6. Summary of results for slurry run SB-66-2468.

Catalyst: 100 Fe/5.0 Cu/4.2 K /24 SiO₂ Slurry liquid: n-octacosane
 Reactor volume: 312 cc^b

Period	1	2	3	4	5	6	7
Date	09/06/88	09/10/88	09/14/88	09/18/88	09/22/88	09/24/88	09/24/88
Time on Stream (h)	69.0	165.0	261.0	357.0	453.0	500.0	549.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0	7.0	6.0
Average Temperature (°C)	250.	250.	250.	250.	250.	250.	250.
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.69	.69	.69	.69	.69	.69	.75
Space Velocity (NI/g-cat·h) ^a	2.00	2.00	2.00	2.00	2.00	4.00	1.01
Space Velocity (NI/g-Fe·h)	3.57	3.57	3.57	3.57	3.57	7.13	1.80
GHSV (h ⁻¹) ^b	225.	225.	225.	225.	225.	450.	113.
CO Conversion (%)	54.6	49.4	51.7	47.2	42.3	22.3	61.0
H ₂ +CO Conversion (%)	56.1	51.9	53.2	49.3	44.3	26.2	61.1
H ₂ /CO Usage	.74	.78	.75	.77	.78	.99	.76
STY (mols H ₂ +CO/g-cat·h) ^a	.050	.046	.047	.044	.040	.047	.027
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	2.5	1.7	2.0	1.9	1.5	.9	2.7
Weight % of Outlet							
H ₂	2.02	2.20	2.15	2.29	2.54	3.32	1.95
H ₂ O	3.60	4.35	4.23	4.04	4.38	3.26	4.51
CO	44.1	49.9	46.5	50.8	55.5	75.6	36.2
CO ₂	35.0	29.8	32.8	29.2	25.4	11.7	40.0
Hydrocarbons	8.79	8.46	9.90	9.91	9.43	5.17	12.4
Oxygenates	.19	.51	.36	.50	.50	.24	.70
Wax ^c	6.25	4.88	3.99	3.25	2.24	.74	4.23
Yield (g/Nm ³ H ₂ + CO Converted)							
CH ₄	7.89	7.57	8.87	11.3	12.8	13.4	15.5
C ₂ -C ₄ Hydrocarbons	36.5	34.6	40.5	44.6	44.1	47.4	51.1
C ₅ -C ₁₁ Hydrocarbons	42.2	40.6	50.1	49.9	47.6	37.3	49.0
C ₁₂ + Hydrocarbons	117.	109.	100.	98.9	97.7	73.0	93.5
Wax ^c	84.6	70.3	57.3	50.6	38.8	21.5	53.2
Oxygenates	2.56	7.33	5.17	7.79	8.68	7.00	8.87
Total	206.	200.	205.	213.	211.	178.	218.
1+2 Olefins/n-Paraffin Ratio							
C ₂	1.83	2.10	1.58	1.18	1.08	1.81	.44
C ₃	7.34	7.34	6.58	5.50	5.02	5.38	3.54
C ₄	5.97	6.03	5.40	4.48	4.82	4.53	3.05
C ₈	4.29	2.52	3.16	2.46	1.96	2.56	1.42
C ₁₀	3.09	3.07	2.49	1.81	1.63	2.10	1.15

^a Based on unreduced catalyst^c Unanalyzed wax withdrawn from reactor^b Based on static slurry volume

Table 6'(cont'd). Summary of results for slurry run SB-66-2468.

Period		1	2	3	4	5	6	7
Weight % of Hydrocarbons								
C ₁₁ 4		3.88	3.94	4.44	5.53	6.32	7.82	7.40
Ethane		1.85	1.81	2.60	3.38	3.73	3.53	5.47
Ethylene		3.16	3.54	3.83	3.72	3.74	5.95	2.23
Propane		.84	.83	1.02	1.26	1.42	1.62	2.08
Propylene		5.87	5.82	6.39	6.62	6.79	8.33	7.01
n-Butane		.84	.81	.95	1.17	1.04	1.42	1.77
1+2 Butenes		4.86	4.72	4.96	5.07	4.86	6.22	5.21
C ₄ Isomers		.51	.48	.53	.57	.23	.66	.66
n-Pentane		1.16	1.17	1.32	1.52	1.65	1.86	2.12
1+2 Pentenes		4.35	4.30	5.48	5.00	4.99	5.56	4.05
C ₅ Isomers		.27	.31	.58	.63	.42	.73	.54
n-Hexane		.77	.68	.96	1.06	.84	1.13	1.00
1+2 Hexenes		2.15	2.11	3.01	2.69	2.13	3.11	1.59
C ₆ Isomers		.62	.47	.68	.66	.52	.81	.44
n-Heptane		.39	.45	.53	.85	.65	.77	.75
1+2 Heptenes		1.64	1.48	1.92	1.86	1.59	1.62	1.28
C ₇ Isomers		.44	.36	.54	.37	.40	.58	.28
n-Octane		.33	.60	.50	.58	.63	.34	.88
1+2 Octenes		1.41	1.48	1.56	1.41	1.21	.85	1.23
C ₈ Isomers		.44	.28	.35	.27	.13	.17	.20
n-Nonane		.37	.42	.50	.61	.76	.26	1.12
1+2 Nonenes		1.33	1.42	1.34	1.23	1.36	.60	1.32
C ₉ Isomers		.14	.23	.28	.18	.17	.07	.25
n-Decane		.52	.58	.67	.83	1.04	.44	1.31
1+2 Decenes		1.60	1.76	1.65	1.48	1.68	.90	1.48
C ₁₀ Isomers		.25	.30	.41	.37	.32	.15	.46
n-Undecane		.63	.65	.74	.93	1.16	.59	1.37
1+2 Undecenes		1.63	1.73	1.61	1.44	1.59	1.09	1.40
C ₁₁ Isomers		.31	.31	.46	.42	.39	.19	.39
C ₂ -C ₄		17.9	18.0	20.3	21.8	21.8	27.7	24.4
C ₅ -C ₁₁		20.7	21.1	25.1	24.4	23.5	21.8	23.5
C ₁₂ +		57.5	57.0	50.2	48.3	48.3	42.7	44.7
Wax ^c		41.6	36.6	28.7	24.7	19.2	12.6	25.4

^c Unanalyzed wax withdrawn from reactor

Table 7. Summary of results for fixed bed runs FA-15-1698 and FA-15-1768.

Catalyst: 100 Fe/1.0 Cu/0.2 K, 4.50 g^a (FA-15-1698), 3.40 g^a (FA-15-1768)

Diluent: Glass beads, 35.5 g (FA-15-1698), 36.0 g (FA-15-1768)

Catalyst volume: 3.60 cc (FA-15-1698), 3.00 cc (FA-15-1768) Diluent Volume: 23.0 cc (FA-15-1698), 24.0 cc (FA-15-1768)

Run	FA-15-1698		FA-15-1768					
	1		1	2	3	4	5	6
Period								
Date	6/19/88		6/27/88	7/1/88	7/5/88	7/9/88	7/13/88	7/15/88
Time on Stream (h)	39.5		72.0	168.0	263.5	359.0	456.0	505.0
Balance Duration (h)	7.5		6.8	7.5	7.1	7.8	7.0	7.2
Average Temperature (°C)	235.		234.	235.	235.	235.	250.	250.
Maximum Δ Temperature (°C) ^b	2.10		3.30	3.30	2.90	2.60	1.60	2.10
Pressure (MPa)	1.48		1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.712		.712	.712	1.03	1.03	.712	.712
Space Velocity (Nl/g-cat.h) ^a	2.01		2.00	2.00	2.00	2.00	2.00	2.00
Space Velocity (Nl/g-Fe.h)	2.91		2.89	2.89	2.89	2.89	2.89	2.89
GHSV (h ⁻¹) ^c	336.		252.	252.	252.	252.	252.	252.
CO Conversion (%)	52.3		38.2	29.5	31.8	29.0	34.0	32.3
H ₂ +CO Conversion (%)	52.6		41.1	31.3	29.8	26.5	32.7	31.6
H ₂ /CO Usage	.720		.840	.820	.900	.860	.650	.670
STY (mols H ₂ +CO/g-cat.h) ^a	.047		.037	.028	.027	.024	.029	.028
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	2.50		1.30	1.20	1.70	1.90	3.40	3.60
Weight % of Outlet								
H ₂	2.30		2.70	3.24	5.04	5.33	3.41	3.40
H ₂ O	4.06		4.64	4.03	4.49	3.71	2.10	1.87
CO	45.4		59.3	67.4	64.1	67.2	63.4	64.6
CO ₂	35.1		23.2	17.0	17.5	15.9	23.1	22.4
Hydrocarbons	7.19		6.19	4.89	5.45	5.13	5.00	5.21
Oxygenates	0.48		0.58	0.40	0.51	0.38	0.25	0.25
Wax ^d	5.42 ^e		3.43	2.97	2.88	2.34	2.68	2.31
Yield (g/Nm ³ H ₂ + CO Converted)								
CH ₄	8.67		7.18	6.54	8.29	8.56	10.5	10.5
C ₂ -C ₄ Hydrocarbons	39.4		32.7	29.4	34.0	34.3	36.5	36.2
C ₅ -C ₁₁ Hydrocarbons	45.7		37.5	34.9	33.9	31.4	31.0	33.2
C ₁₂ + Hydrocarbons	90.1		101.	121.	106.	108.	101.	102.
Wax ^d	79.0 ^e		63.5	72.3	63.2	57.3	62.3	56.0
Oxygenates	7.07		10.7	9.84	11.2	9.21	5.90	6.17
Total	191.		189.	201.	194.	192.	185.	188.
1+2 Olefins/n-Paraffin Ratio								
C ₂	2.37		3.15	3.09	2.30	2.24	1.79	1.80
C ₃	8.02		8.00	7.49	6.22	6.18	7.32	7.62
C ₄	6.74		6.33	6.18	5.24	5.20	6.56	6.89
C _n	5.02		4.90	5.15	4.14	4.31	5.17	5.35
C ₁₀	4.75		4.00	4.65	3.60	3.98	4.80	4.52

^a Based on unreduced catalyst^b Maximum axial temperature difference^c Based on catalyst volume^d Unrecovered products from wax analysis^e Unanalyzed products collected from hot trap

Table 7 (cont'd). Summary of results for fixed bed runs FA-15-1698 and FA-15-1768.

Run	FA-15-1698		FA-15-1768					
	1		1	2	3	4	5	6
Weight % of Hydrocarbons								
CH ₄	4.72		4.03	3.42	4.54	4.68	5.87	5.78
Ethane	1.89		1.37	1.21	1.83	1.91	2.40	2.31
Ethylene	4.17		4.01	3.49	3.93	3.98	4.01	3.88
Propane	.93		.78	.69	1.00	1.00	.93	.88
Propylene	7.12		5.98	4.90	5.91	5.90	6.47	6.39
n-Butane	.89		.80	.67	.90	.91	.80	.75
i+2 Butenes	5.80		4.89	3.98	4.54	4.56	5.09	4.97
C ₄ Isomers	.61		.51	.41	.50	.51	.73	.70
n-Pentane	1.40		1.24	1.03	1.25	1.27	1.26	1.21
i+2 Pentenes	5.37		4.65	3.78	4.11	4.13	4.65	4.57
C ₅ Isomers	.30		.25	.22	.29	.31	.31	.29
n-Hexane	.64		.58	.54	.65	.56	.48	.56
i+2 Hexenes	3.24		3.01	2.78	2.88	2.54	2.37	3.20
C ₆ Isomers	.68		.61	.56	.69	.54	.67	.73
n-Heptane	.48		.38	.37	.41	.37	.29	.31
i+2 Heptenes	2.33		1.94	1.83	1.76	1.55	1.34	1.68
C ₇ Isomers	.49		.41	.50	.35	.31	.54	.67
n-Octane	.41		.26	.24	.36	.22	.16	.17
i+2 Octenes	2.03		1.24	1.22	1.45	.93	.82	.91
C ₈ Isomers	.36		.09	.05	.15	.06	.07	.16
n-Nonane	.36		.31	.18	.21	.16	.17	.16
i+2 Nonenes	1.78		1.31	.94	.81	.77	.89	.77
C ₉ Isomers	.20		.11	.05	.05	.05	.07	.06
n-Decane	.40		.41	.31	.31	.30	.25	.23
i+2 Decenes	1.85		1.69	1.42	1.11	1.18	1.20	1.01
C ₁₀ Isomers	.29		.24	.12	.10	.11	.12	.11
n-Undecane	.35		.42	.35	.34	.35	.28	.25
i+2 Undecenes	1.58		1.57	1.55	1.17	1.29	1.23	1.07
C ₁₁ Isomers	.31		.29	.20	.14	.15	.19	.15
C ₁₂ -C ₄	21.4		18.3	15.3	18.6	18.8	20.4	19.9
C ₅ -C ₁₁	24.9		21.0	18.2	18.6	17.2	17.4	18.3
C ₁₂ +	49.0		56.6	63.0	58.3	59.4	56.3	56.1
Wax ^d	43.0 ^e		35.6	37.8	34.6	31.3	34.9	30.7

^d Unrecovered products from wax analysis

^e Unanalyzed wax collected from hot trap

Table 8. Summary of results for fixed bed run FB-27-2438. Catalyst reduced using CO at 280 °C for 12 h, 3.0 *Nl/g-cat·h*.

Catalyst: 3.80 *g*^a, 100 Fe/3.0 Cu/0.5 K
Catalyst volume: 3.40 *cc*

Diluent: 38.1 *g*, Glass beads
Diluent Volume: 25.0 *cc*

Period	1	2	3
Date	09/02/88	09/06/88	09/10/88
Time on Stream (<i>h</i>)	72.0	167.0	264.0
Balance Duration (<i>h</i>)	6.8	7.0	6.8
Average Temperature (°C)	260.	260.	260.
Maximum Δ Temperature (°C) ^b	3.00	2.00	2.00
Pressure (<i>MPa</i>)	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.704	.704	.704
Space Velocity (<i>Nl/g-cat·h</i>) ^a	2.01	2.01	2.01
Space Velocity (<i>Nl/g-Fe·h</i>)	2.95	2.95	2.95
GHSV (<i>h</i> ⁻¹) ^c	268.	268.	268.
CO Conversion (%)	83.3	76.5	72.3
H ₂ +CO Conversion (%)	78.4	72.1	67.8
H ₂ /CO Usage	.604	.606	.598
STY (<i>mols H₂+CO/g-cat·h</i>) ^a	.070	.065	.061
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	15.2	12.8	17.5
Weight % of Outlet			
H ₂	1.36	1.63	1.84
H ₂ O	1.97	1.81	1.23
CO	15.7	22.2	26.2
CO ₂	60.8	55.6	53.7
Hydrocarbons	14.4	15.0	14.4
Oxygenates	.408	.302	.236
Wax ^d	5.37	3.47	2.41
Yield (<i>g/Nm³ H₂ + CO Converted</i>)			
CH ₄	12.6	14.4	15.4
C ₂ -C ₄ Hydrocarbons	49.8	53.7	55.3
C ₅ -C ₁₁ Hydrocarbons	63.4	74.2	74.3
C ₁₂ + Hydrocarbons	70.2	56.8	47.7
Wax ^d	53.3	37.4	27.7
Oxygenates	4.05	3.25	2.71
Total	200.	202.	195.
1+2 Olefins/ <i>n</i> -Paraffin Ratio			
C ₂	1.25	.974	1.00
C ₃	8.31	7.04	7.28
C ₄	7.27	6.01	6.11
C ₅	4.58	3.18	3.09
C ₁₀	3.74	2.40	2.25

^a Based on unreduced catalyst

^c Based on catalyst volume

^b Maximum axial temperature difference

^d Unanalyzed products collected from hot trap

Table 8 (cont'd). Summary of results for fixed bed run FB-27-2438. Catalyst reduced using CO at 280 °C for 12 h, 3.0 NI/g-cat·h.

Period	1	2	3
Weight % of Hydrocarbons			
CH ₄	6.41	7.25	7.99
Ethane	3.34	3.83	4.06
Ethylene	3.90	3.48	3.79
Propane	1.10	1.35	1.38
Propylene	8.74	9.04	9.56
n-Butane	.951	1.25	1.32
1+2 Butenes	6.68	7.23	7.77
C ₄ Isomers	.709	.780	.826
n-Pentane	1.55	1.90	2.04
1+2 Pentenes	5.82	6.22	6.74
C ₅ Isomers	.440	.610	.680
n-Hexane	.622	.918	.807
1+2 Hexenes	3.41	4.03	3.48
C ₆ Isomers	.726	.814	.693
n-Heptane	.591	1.000	.864
1+2 Heptenes	2.96	3.50	3.06
C ₇ Isomers	.842	1.17	.629
n-Octane	.644	.997	1.15
1+2 Octenes	2.90	3.12	3.50
C ₈ Isomers	.785	.696	.706
n-Nonane	.659	1.03	1.30
1+2 Nonenes	2.66	2.75	3.35
C ₉ Isomers	.706	.587	.679
n-Decane	.639	1.05	1.30
1+2 Decenes	2.35	2.47	2.87
C ₁₀ Isomers	.795	.643	.701
n-Undecane	.608	1.04	1.20
1+2 Undecenes	1.97	2.09	2.22
C ₁₁ Isomers	.668	.620	.589
C ₂ -C ₄	25.4	27.0	28.7
C ₅ -C ₁₁	32.3	37.3	38.6
C ₁₂ +	35.8	28.5	24.8
Wax ^d	27.2	18.8	14.4

^d Unanalyzed wax collected from hot trap

Table 9. Summary of results for fixed bed run FA-27-2518. Catalyst reduced using CO at 335 °C for 24 h, 3.0 NI/g-cat·h.

Catalyst: 3.45 g^a, 100 Fe/3.0 Cu/0.5 K
Catalyst volume: 2.50 cc

Diluent: 37.2 g, Glass beads
Diluent Volume: 24.5 cc

Period	1	2
Date	09/10/88	09/14/88
Time on Stream (h)	77.0	166.0
Balance Duration (h)	6.5	6.8
Average Temperature (°C)	260.	260.
Maximum Δ Temperature (°C) ^b	1.80	1.70
Pressure (MPa)	1.48	1.48
H ₂ /CO Feed Ratio	.639	.639
Space Velocity (NI/g-cat·h) ^a	2.00	2.00
Space Velocity (NI/g-Fe·h)	2.95	2.95
GHSV (h ⁻¹) ^c	256.	256.
CO Conversion (%)	57.6	46.5
H ₂ +CO Conversion (%)	57.5	47.3
H ₂ /CO Usage	.637	.667
STY (mols H ₂ +CO/g-cat·h) ^a	.051	.042
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	5.76	3.53
Weight % of Outlet		
H ₂	1.87	2.26
H ₂ O	1.92	2.31
CO	40.5	51.0
CO ₂	42.1	32.3
Hydrocarbons	10.1	8.91
Oxygenates	.274	.265
Wax ^d	3.25	2.95
Yield (g/Nm ³ H ₂ + CO Converted)		
CH ₄	18.2	18.7
C ₂ -C ₄ Hydrocarbons	48.7	53.9
C ₅ -C ₁₁ Hydrocarbons	51.4	58.4
C ₁₂ + Hydrocarbons	66.3	70.0
Wax ^d	45.0	50.0
Oxygenates	3.79	4.48
Total	188.	205.
1+2 Olefins/n-Paraffin Ratio		
C ₂	1.27	1.40
C ₃	7.84	8.11
C ₄	7.08	7.41
C ₈	4.67	5.51
C ₁₀	4.13	4.59

^a Based on unreduced catalyst

^c Based on reactor volume

^b Maximum axial temperature difference

^d Unanalyzed products collected from hot trap

Table 9 (cont'd). Summary of results for fixed bed run FA-27-2518. Catalyst reduced using CO at 335 °C for 24 h, 3.0 NI/g-cat·h.

Period	1	2
Weight % of Hydrocarbons		
CH ₄	9.86	9.29
Ethane	3.91	3.98
Ethylene	4.63	5.20
Propane	1.13	1.10
Propylene	8.47	8.51
n-Butane	.959	.900
1+2 Butenes	6.55	6.43
C ₄ Isomers	.722	.707
n-Pentane	1.46	1.41
1+2 Pentenes	5.93	7.00
C ₅ Isomers	.459	.807
n-Hexane	.586	.475
1+2 Hexenes	3.57	3.53
C ₆ Isomers	.660	.805
n-Heptane	.479	.434
1+2 Heptenes	2.66	2.53
C ₇ Isomers	.489	.514
n-Octane	.482	.402
1+2 Octenes	2.21	2.18
C ₈ Isomers	.511	.497
n-Nonane	.469	.405
1+2 Nonenes	1.97	1.95
C ₉ Isomers	.387	.349
n-Decane	.476	.448
1+2 Decenes	1.94	2.02
C ₁₀ Isomers	.502	.530
n-Undecane	.451	.439
1+2 Undecenes	1.73	1.84
C ₁₁ Isomers	.425	.491
C ₂ -C ₄	26.4	26.8
C ₅ -C ₁₁	27.8	29.1
C ₁₂ +	35.9	34.8
Wax ^d	24.4	24.9

^d Unanalyzed products collected from hot trap

Table 10. Summary of results for fixed bed run FB-66-1948.

Catalyst: 3.40 g^a, 100 Fe/5.0 Cu/4.2 K/24 SiO₂
Diluent: 36.4 g, Glass beads
Catalyst volume: 4.60 cc Diluent Volume: 24.0 cc

Period	1	2	3	4	5	6
Date	07/15/88	07/19/88	07/23/88	07/27/88	08/01/88	08/03/88
Time on Stream (h)	71.0	167.5	263.5	356.0	476.5	524.0
Balance Duration (h)	6.5	6.5	6.5	7.0	6.8	6.5
Average Temperature (°C)	250.	250.	250.	250.	250.	250.
Maximum Δ Temperature (°C) ^b	2.10	2.00	3.00	3.00	3.00	4.00
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.686	.686	.686	.686	.712	.712
Space Velocity (NI/g-cat.h) ^a	2.01	2.01	2.01	2.01	2.01	4.02
Space Velocity (NI/g-Fe.h)	3.58	3.58	3.58	3.58	3.58	7.16
GIHSV (h ⁻¹) ^c	239.	239.	239.	239.	239.	477.
CO Conversion (%)	69.4	68.8	67.7	67.9	66.1	40.3
H ₂ +CO Conversion (%)	67.9	67.1	65.6	65.5	64.0	41.5
H ₂ /CO Usage	.650	.643	.634	.628	.657	.764
STY (mols H ₂ +CO/g-cat.h) ^a	.061	.060	.059	.059	.057	.074
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	3.41	3.09	3.17	3.98	3.96	1.93
Weight % of Outlet						
H ₂	1.61	1.70	1.78	1.79	1.91	2.76
H ₂ O	4.45	4.82	4.68	3.94	3.91	3.85
CO	29.1	30.2	31.0	30.7	32.4	56.6
CO ₂	48.2	46.6	45.6	47.3	46.1	26.8
Hydrocarbons	11.0	11.5	11.5	11.4	9.26	7.20
Oxygenates	.715	.769	.581	.649	.563	.398
Wax ^d	4.99	4.32	4.89	4.21	5.80 ^e	2.36
Yield (g/Nm ³ H ₂ + CO Converted)						
CII ₄	10.5	10.5	10.8	11.4	11.6	12.3
C ₂ -C ₄ Hydrocarbons	40.1	40.8	43.1	43.0	45.9	47.4
C ₅ -C ₁₁ Hydrocarbons	39.3	40.5	45.6	44.4	44.6	45.0
C ₁₂ + Hydrocarbons	93.2	88.9	92.7	83.2	77.7	72.8
Wax ^d	57.2	49.3	57.5	49.7	69.2 ^e	43.8
Oxygenates	8.20	8.77	6.83	7.67	6.71	7.39
Total	191.	190.	199.	192.	186.	185.
1+2 Olefins/n-Paraffin Ratio						
C ₂	2.12	2.38	2.50	2.31	2.29	2.46
C ₃	7.98	8.11	8.10	8.29	8.26	7.96
C ₄	6.47	6.48	6.48	6.57	6.57	6.50
C ₈	4.64	4.83	5.14	4.88	4.72	5.17
C ₁₀	3.92	4.16	4.34	4.13	4.14	4.35

^a Based on unreduced catalyst

^b Maximum axial temperature difference

^c (Unanalyzed) products collected from hot trap

^d Based on catalyst volume

^e (Unanalyzed) products collected from hot trap

Table 10 (cont'd). Summary of results for fixed bed run FD-66-1948.

Period	7	8	9	10	11	12
Date	08/05/88	08/08/88	08/11/88	08/13/88	08/15/88	08/17/88
Time on Stream (h)	572.0	644.5	715.5	764.5	812.5	860.0
Balance Duration (h)	8.0	6.5	7.0	6.8	6.2	6.7
Average Temperature (°C)	250.	250.	250.	250.	265.	235.
Maximum Δ Temperature (°C) ^b	3.00	4.00	3.00	4.00	5.00	2.00
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.712	1.03	1.03	.704	.704	.704
Space Velocity (Nl/g-cat.h) ^a	1.01	2.01	2.01	2.01	2.01	2.01
Space Velocity (Nl/g-Fe.h)	1.79	3.58	3.58	3.58	3.58	3.58
GIISV (h ⁻¹) ^c	120.	239.	239.	239.	239.	239.
CO Conversion (%)	86.4	68.5	68.3	57.7	77.7	32.4
H ₂ +CO Conversion (%)	82.3	60.6	60.6	57.7	74.1	35.5
H ₂ /CO Usage	.631	.800	.802	.702	.626	.862
STY (mols H ₂ +CO/g-cat.h) ^a	.037	.054	.054	.052	.066	.032
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	10.1	3.38	3.78	2.94	5.95	.958
Weight % of Outlet						
H ₂	1.14	3.22	3.24	2.04	1.51	2.88
H ₂ O	3.03	7.85	7.12	3.92	3.71	5.23
CO	12.8	29.1	29.4	40.1	21.5	63.7
CO ₂	60.9	42.2	43.0	40.0	55.4	19.5
Hydrocarbons	16.3	12.8	12.4	9.44	12.8	5.39
Oxygenates	.672	1.02	.907	.513	.781	.625
Wax ^d	5.17	3.84	3.87	4.02	4.31	2.66
Yield (g/Nm ³ H ₂ + CO Converted)						
CH ₄	12.1	14.7	14.3	11.7	15.1	10.7
C ₂ -C ₄ Hydrocarbons	47.9	53.6	51.8	43.8	49.6	42.9
C ₅ -C ₁₁ Hydrocarbons	58.6	45.8	45.0	43.4	45.5	37.3
C ₁₂ + Hydrocarbons	83.0	68.1	67.0	81.6	65.4	85.7
Wax ^d	48.6	42.2	42.3	53.9	44.2	58.4
Oxygenates	6.32	11.2	9.91	6.88	8.01	13.7
Total	208.	193.	188.	187.	184.	190.
1+2 Olefins/n-Paraffin Ratio						
C ₂	1.70	2.11	2.28	2.57	1.56	3.17
C ₃	8.38	6.91	6.99	8.15	8.54	7.18
C ₄	6.67	5.55	5.61	6.62	7.04	5.94
C ₈	4.80	4.04	4.08	4.67	4.80	4.60
C ₁₀	3.87	3.12	3.54	4.14	3.72	3.56

^a Based on unreduced catalyst

^c Based on catalyst volume

^b Maximum axial temperature difference

^d Unrecovered products from wax analysis

Table 10 (cont'd). Summary of results for fixed bed run FB-66-1948.

Period		1	2	3	4	5	6
Weight % of Hydrocarbons							
CH ₄		5.75	5.80	5.63	6.20	6.45	6.91
Ethane		2.19	2.07	1.98	2.25	2.34	2.39
Ethylene		4.33	4.61	4.61	4.86	5.00	5.49
Propane		.975	.985	.975	1.04	1.09	1.16
Propylene		7.43	7.62	7.54	8.20	8.56	8.79
<i>n</i> -Butane		.893	.933	.937	1.03	1.08	1.13
1+2 Butenes		5.58	5.84	5.86	6.51	6.85	7.10
C ₄ Isomers		5.23	5.33	5.36	5.86	6.11	6.36
<i>n</i> -Pentane		1.28	1.36	1.31	1.48	1.53	1.64
1+2 Pentenes		4.79	5.19	5.03	5.74	5.89	6.31
C ₅ Isomers		.279	.292	.296	.323	.336	.361
<i>n</i> -Hexane		.461	.462	.541	.569	.591	.721
1+2 Hexenes		2.63	2.61	2.90	3.06	3.18	3.95
C ₆ Isomers		.545	.526	.577	.628	.609	1.01
<i>n</i> -Heptane		.366	.345	.409	.411	.479	.526
1+2 Heptenes		1.85	1.78	2.04	2.11	2.36	2.74
C ₇ Isomers		.353	.310	.313	.372	.433	.762
<i>n</i> -Octane		.371	.396	.426	.415	.424	.341
1+2 Octenes		1.69	1.88	2.15	1.99	1.96	1.73
C ₈ Isomers		.272	.369	.253	.338	.534	.293
<i>n</i> -Nonane		.474	.407	.426	.398	.386	.254
1+2 Nonenes		1.54	1.74	1.92	1.69	1.64	1.21
C ₉ Isomers		.225	.237	.166	.208	.237	.127
<i>n</i> -Decane		.410	.411	.443	.398	.382	.290
1+2 Decenes		1.58	1.69	1.90	1.62	1.56	1.24
C ₁₀ Isomers		.244	.274	.201	.247	.285	.187
<i>n</i> -Undecane		.417	.395	.437	.398	.342	.266
1+2 Undecenes		1.44	1.48	1.76	1.45	1.31	1.17
C ₁₁ Isomers		.238	.254	.224	.258	.267	.211
C ₂ -C ₄		21.9	22.6	22.4	24.5	25.5	26.7
C ₅ -C ₁₁		21.4	22.4	23.7	24.1	24.8	25.3
C ₁₂ +		50.9	49.2	48.2	45.2	43.2	41.0
Wax ^d		31.2	27.3	29.9	27.0	38.5 ^e	24.7

^d Unrecovered products from wax analysis

^e Unanalyzed wax collected from hot trap

Table 10 (cont'd). Summary of results for fixed bed run FB-66-1948.

Period		7	8	9	10	11	12
Weight % of Hydrocarbons							
CH ₄		5.98	8.07	8.03	6.50	8.62	6.07
Ethane		2.66	2.97	2.83	2.25	3.57	1.91
Ethylene		4.22	5.86	6.01	5.39	5.19	5.66
Propane		1.03	1.49	1.46	1.05	1.19	1.15
Propylene		8.23	9.85	9.76	8.17	9.68	7.91
n-Butane		.953	1.35	1.31	.928	1.02	1.05
1+2 Butenes		6.14	7.23	7.07	5.93	6.95	6.04
C ₄ Isomers		.541	.659	.642	.548	.627	.584
n-Pentane		1.37	1.74	1.69	1.34	1.52	1.49
1+2 Pentenes		5.14	6.00	5.85	5.11	5.74	5.38
C ₅ Isomers		.334	.422	.405	.304	.370	.317
n-Hexane		.587	.786	.700	.605	.606	.715
1+2 Hexenes		3.20	3.45	3.14	3.25	3.44	3.49
C ₆ Isomers		.574	.715	.673	.640	.805	.833
n-Heptane		.531	.575	.497	.459	.474	.524
1+2 Heptenes		2.70	2.38	2.09	2.27	2.32	2.47
C ₇ Isomers		.416	.557	.434	.431	.543	.584
n-Octane		.604	.464	.489	.424	.455	.376
1+2 Octenes		2.85	1.84	1.96	1.95	2.14	1.70
C ₈ Isomers		.348	.182	.500	.343	.489	.400
n-Nonane		.646	.427	.466	.380	.410	.161
1+2 Nonenes		2.67	1.46	1.71	1.61	1.66	.593
C ₉ Isomers		.305	.237	.198	.251	.373	.0564
n-Decane		.657	.430	.469	.405	.422	.197
1+2 Decenes		2.51	1.32	1.63	1.65	1.54	.691
C ₁₀ Isomers		.351	.275	.239	.348	.420	.110
n-Undecane		.657	.415	.431	.377	.406	.188
1+2 Undecenes		2.27	1.23	1.41	1.48	1.33	.728
C ₁₁ Isomers		.331	.257	.273	.410	.419	.133
C ₂ -C ₄		23.8	29.4	29.1	24.3	28.2	24.3
C ₅ -C ₁₁		29.1	25.2	25.2	24.0	25.9	21.1
C ₁₂ +		41.2	37.4	37.7	45.2	37.3	48.5
Wax ^d		24.1	23.2	23.8	29.9	25.2	33.1

^d Unrecovered products from wax analysis

Figure 1. Stability plot, (H₂+CO) conversion versus time on stream, for run SB-27-2168.
 (260 °C, 1.48 MPa, 2.3-3.0 NI/g-cat.h).

Figure 2. Catalyst activity for run SB-66-2468 (weights indicate amount of wax withdrawn (-) or added (+)). 0 to 240 h on stream. (250 °C, 1.48 MPa, 2.0 NI/g cat-h, H₂/CO = 0.67 nominal).

Figure 3. Catalyst activity for run SB-66-2468 (weights indicate amount of wax withdrawn (-) or added (+)). 240 to 480 h on stream. (250 °C, 1.48 MPa, 2.0 NI/g-cat-h, H₂/CO = 0.67 nominal).

Figure 4. Stability plot, ($H_2 + CO$) conversion versus time on stream, for run SB-66-2468. (250 °C, 1.48 MPa, 2.0 NI/g-cat.h, $H_2/CO = 0.67$ nominal).

Figure 5. Stability plot, ($H_2 + CO$) conversion versus time on stream, for runs FA-15-1698 and FA-15-1768 (100 Fe/1.0 Cu/0.2 K catalyst, 235 °C, 1.48 MPa, 2.0 NL/g cat·h).

Figure 6. Comparison of catalyst selectivity in runs FA-15-1698 and FA-15-1768 (100 Fe/1.0 Cu/0.2 K catalyst, 235 °C, 1.48 MPa, 2.0 Nl/g-cat·h, H₂/CO = 0.71).

Figure 7. Selectivity comparison for fixed bed tests of 100 Fe/1.0 Cu/0.2 K catalyst (235 °C, 1.48 MPa, 2.0 Nl/g-cat·h. H₂/CO = 1.0).

Figure 8. Stability plot, (H₂+CO) conversion versus time on stream, for runs FB-27-2438 and FB-27-2518 (100 Fe/3.0 Cu/0.5 K catalyst, 260 °C, 1.48 MPa, 2.0 NL/g cat-h, H₂/CO = 0.67 nominal).

Figure 9. Effect of time on stream on catalyst selectivity for runs FB-27-2438 and FB-27-2518 (100 Fe/3.0 Cu/0.5 K catalyst, 260 °C, 1.48 MPa, 2.0 Nl/g-cat.h, H₂/CO = 0.67 nominal).

Figure 10. Stability plot, (H_2+CO) conversion versus time on stream, for run FB-66-1948 (100 Fe/5.0 Cu/4.2 K/24 SiO₂) and comparison to runs FB-99-1588 (Ruhrchemie LP 33/81) and FA-63-1308 (100 Fe/5.0 Cu/4.2 K/8 SiO₂).

Figure 11. Effect of time on stream on catalyst selectivity for run FB-66-1948 (100 Fe/5.0 Cu/4.2 K/24 SiO₂). (250 °C, 1.48 MPa, 2.0 NI/g-cat·h, H₂/CO = 0.69).

Figure 12. Effect of process conditions on catalyst activity and selectivity for run FB-66-1948 (100 Fe/5.0 Cu/4.2 K/24 SiO₂).

Figure 13. Comparison of catalyst selectivity for 100 Fe/5.0 Cu/4.2 K/8 and 24 SiO₂ catalysts and Ruhrchemie LP 33/81. (2.0 Nl/g-cat·h, 1.48 MPa, H₂/CO = 0.67 nominal).

END

**DATE
FILMED
8/21/92**