WSRC-RP--89-1277

DE92 015064

SARM
SAFETY ANALYSIS
AND RISK MANAGEMENT

keywords: SEISMIC ANALYSIS
BURIED PIPING
FRAGILITY
REACTOR COOLING
NIL DUCTILITY

SEISMIC FRAGILITY ANALYSIS OF BURIED STEEL PIPING AT P,
L, AND K REACTORS (U)

by

H. E. WINGO

ISSUED: OCTOBER, 1989

SRL

SAVANNAH RIVER LABORATORY, AIKEN, SC 29808
Westinghouse Savannah River Company
Prepared for the U. S. Department of Energy under
Contract DE-AC09-88SR18035

D A Sharp
D. A. Sharp, Authorized Derivative Classifier

10/27/89

Date

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SEISMIC FRAGILITY ANALYSIS OF BURIED STEEL PIPING
AT P, L, AND K REACTORS

INTRODUCTION

Analysis of seismic strength of buried cooling water piping in reactor areas is necessary to evaluate the risk of reactor operation because seismic events could damage these buried pipes and cause loss of coolant accidents. This report documents analysis of the ability of this piping to withstand the combined effects of the propagation of seismic waves, the possibility that the piping may not behave in a completely ductile fashion, and the distortions caused by relative displacements of structures connected to the piping. Not included was the effect of relative settlement of buildings from soil consolidation and liquefaction. The analysis was done in a probabilistic manner using methods developed for the NRC to assess safety margins at nuclear power plants with respect to seismic events⁽¹⁾. Capacity of the underground piping is expressed in terms of a HCLPF value, which is the earthquake level at which it is extremely unlikely that damage will occur. Mathematically the HCLPF value is the earthquake level that produces a 95 percent confidence of not exceeding a 5 percent probability of failure. The analysis was done by the consulting engineering firm of Jack R. Benjamin & Associates, Inc. under contract AX-781257. The appendix shows the complete study.

SUMMARY

The analysis indicated seismic strength, HCLPF value, of the underground piping is adequate to withstand an earthquake having a peak ground acceleration of up to 0.37 g. This strength translates to a margin from failure of 1.85 at the design basis earthquake of 0.2g. The HCLPF values were evaluated for failures in a brittle, ductile or a mixed brittle/ductile state. Values of HCLPF ranged up to 1.82 g for small diameter buried piping with water temperatures in the range that would permit piping to fail only in a ductile manner (piping failure without temperature effects), as shown in the following table.

SEISMIC CAPACITY OF BURIED CARBON STEEL PIPING FOR P, L, AND K REACTORS

COMPONENT	HCLPF, peak ground acceleration capacity
30" to 42" pipes with temperature effects ⁽¹⁾	0.37
4" pipes with temperature effects ⁽²⁾	0.39
30" to 42" pipes without temperature effects ⁽³⁾	1.17
4" pipes without temperature effects ⁽²⁾	1.82

(1)Applicable to cooling water inlet and cooling water bypass pipes.

(2)Applicable to small-diameter pipes (4 inch diameter and less)

(3)Applicable to cooling water effluent and recirculation water pipes.

DISCUSSION

The analysis indicated adequate seismic strength of the buried carbon steel piping under the conditions evaluated. However the analysis did not account for stresses in piping from relative building settlements caused by soil consolidation. Settlement from soil consolidation may be an important contributor to piping stresses. Preliminary calculations indicate piping between the reactor building and the Building 107 effluent sump will be most severely affected. This report will be revised to include the effects of soil consolidation on piping stresses when the analysis is completed.

REFERENCES

1. Budnitz, R. J. P. J. Amico, C. A. Cornell, W. J. Hall, R. P. Kennedy, J. W. Reed, and M. Shinozuka, "An Approach to the Qualification of Seismic Margins in Nuclear Power Plants," NUREG/CR-4334, UCID-20444 (August 1985).

APPENDIX

SEISMIC FRAGILITY ANALYSIS OF BURIED STEEL PIPING AT THE SAVANNAH RIVER SITE REACTORS

Prepared by

John W. Reed
Martin W. McCann, Jr.
Auguste C. Boissonnade

Prepared for

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

May 19, 1989

Executive Summary

This report presents the results of the seismic fragility analysis for the underground carbon steel piping at the L, K, and P Reactors at the Savannah River Site (SRS). The seismic capacities of the underground piping were evaluated for the effects of propagating seismic waves and the distortions caused by the relative displacements of connecting structures. The effects of water temperature on the type of failure mode were also considered. Potential pipe failure associated with settlement due to soil consolidation or liquefaction was not considered in the analysis.

The objective of the analysis was to develop seismic fragility values for the underground steel piping at SRS reactors and to verify that the piping capacity is adequate for the evaluation earthquake level of 0.20 g peak ground acceleration (PGA).

The following table lists the fragility parameters for the underground steel piping. Two sizes of carbon steel piping are considered: large-diameter piping, 30- to 42-inch, and small-diameter pipe lines, 4-inch and smaller. For each pipe size, two sets of fragility parameters were evaluated. The first set considers piping for which service water temperatures vary during the year and may cause the pipe to fail in a brittle, ductile or a mixed brittle/ductile state. The second set considers piping where the service water temperatures are in the range that would cause piping to fail in a ductile manner (i.e., piping without temperature effects). The table also lists the High Confidence of a Low Probability of Failure (HCLPF) capacities for the underground piping. The lowest HCLPF capacity was found to be 0.37 g. This capacity is large enough so that the piping is adequate for the evaluation earthquake of 0.20 g PGA with a margin of at least 1.85.

The effects on buried piping of relative building motions associated with soil-structure interaction were found to be insignificant.

Seismic Fragility Parameters For Underground Piping

Component	Median Peak Ground Acceleration Pipe Capacity (g)	β_r^4	β_u	β_c	HCLPF (g)
30" to 42" ¹ pipes with temperature effects	2.00	0.42	0.60	0.73	0.37
4" pipes with ² temperature effects	2.00	0.52	0.47	0.70	0.39
30" to 42" ³ pipes without temperature effects	3.60	0.23	0.45	0.51	1.17
4" pipes ² without temperature effects	4.43	0.27	0.27	0.38	1.82

¹ Applicable to Cooling Water Inlet and Cooling Water Bypass Pipes

² Applicable to small-diameter pipes (i.e., 4-inch in diameter and smaller)

³ Applicable to Cooling Water Effluent and Recirculating Water Pipes

⁴ β_r = Logarithmic standard deviation for randomness

β_u = Logarithmic standard deviation for uncertainty

$$\beta_c = \sqrt{\beta_r^2 + \beta_u^2}$$

HCLPF = High confidence of a low probability of failure capacity

Table of Contents

<u>Section</u>	<u>Page</u>
Executive Summary	ii
1. Introduction	1
2. Identification of Underground Pipe Lines	2
3. Screening Analysis	4
3.1 Seismic Wave Passage Effects	4
3.2 Relative Building Motion Effects	5
4. Seismic Fragility Analysis of Underground Piping	6
4.1 Seismic Capacity Estimates For Brittle and Ductile Failure Modes	10
4.2 Seismic Capacity Estimates With Temperature Effects	14 - -
5. Summary and Conclusions	19
6. References	21

1. Introduction

This report presents the results of the seismic fragility analysis for the underground carbon steel piping at the L, K, and P Reactors at the Savannah River Site (SRS) (Ref. 1). The seismic capacities of the underground piping were evaluated for the effects of propagating seismic waves and the distortions caused by the relative displacements of connecting structures. The effects of water temperature on the type of failure mode were also considered. Potential pipe failure associated with settlement due to soil consolidation or liquefaction was not considered in the analysis.

The objective of the analysis was to develop seismic fragility values for the underground steel piping at the SRS reactors and to verify that the capacity of the piping is adequate for the evaluation earthquake level of 0.20 g peak ground acceleration (PGA).

Seismic fragility values define the fraction of seismically-induced failures of the underground piping as a function of PGA. As part of the fragility analysis an assessment was also made of the uncertainty in the piping capacity. The calculated fragility values will be used in the seismic probabilistic risk assessment (PRA) of the SRS reactors. The seismic fragility results are also used to determine the High Confidence of a Low Probability of Failure (HCLPF) capacities which are compared with the evaluation earthquake.

In developing seismic fragility values, the following tasks were performed: 1) identification of underground pipe lines, 2) screening analysis, and 3) fragility evaluation. The following sections discuss the results of these three tasks. The last section presents the conclusions of the report.

2. Identification of Underground Pipe Lines

The purpose of this study was to evaluate the seismic capacity of underground steel piping at the L, K and P Reactors. Based on a review of the piping at each reactor, it was concluded that similarities between the underground piping at the L, K and P Reactors exist and that an evaluation of the L Reactor buried pipe lines is applicable to all three reactors.

The piping analyzed for the L Reactor consists of the following lines:

- East and West Cooling Water Inlet pipes (190-L Building to 105-L Reactor)
- Cooling Water Effluent pipe (105-L Reactor to 107-L Sump)
- Cooling Water Bypass pipe (190-L Building to 105-L Reactor)
- Recirculating Water pipe (107-L Sump to 186-L Cooling Water Reservoir)

In addition, a generic, shallow-buried 10 foot-long cantilevered pipe 4 inches in diameter was analyzed. The assessment of the seismic capacity of the 4-inch pipe is used to represent the capacity of a general class of small-diameter piping (i.e., 4-inch in diameter and smaller) that exists at each of the reactor sites.

Figure 1 shows the location of the large buried pipe lines at the L Reactor. Table 1 gives a summary of the pipe properties. The piping is made of carbon steel and is buried between 4 and 25 feet below the ground surface. Soil properties for the site are based on data reported in References 2 to 4.

Figure 1 Pipe Lines Analyzed

Table 1
Underground Piping Properties

Pipe Lines*	Diameter (inches)	Thickness (inches)	Operating Pressure (psi)
Cooling Water Inlet Pipes	42	0.5	55
Cooling Water Effluent Pipe	42	0.5	25
Cooling Water Bypass Pipe	30, 36	0.312, 0.375	9
Recirculating Water Pipe	30	0.312	9
Small-Diameter Pipes, (Generic)	4	all schedules	N/A

* Material reported to be ASTM A53, API 5L, ASTM A139, ASTM 106 or ASTM A285 (Refs. 10, 11)

3. Screening Analysis

A screening analysis was performed for the four large pipes listed above. The purpose of this task was to determine which seismic hazards (i.e., relative displacements of buildings and/or wave passage effects) required consideration in the fragility analysis and to identify the pipe sections with the lowest seismic capacity. Seismic forces in the piping caused by wave passage and relative building displacements were analyzed as part of the screening process.

3.1 Seismic Wave Passage Effects

The principle consideration in determining the effects of seismic wave passage is the relative axial displacement that occurs between the pipe and soil. Because there are limited friction forces between the soil and pipe, the pipe movement can not match the seismically-induced soil movement. This leads to relative motions between pipe sections at angles to each other (e.g., non-straight sections of pipe), causing axial

and bending strains. The maximum relative displacement is controlled by the friction force and the predominant seismic wave length (Ref. 9).

The potential for buckling caused by seismic wave passage was also investigated and found to be relatively insignificant. The methods documented in References 6 through 9 were used to evaluate stresses in bends and straight sections of pipe. From the analysis, the controlling limit state was found to be bending at the intersection of pipes at 90 degrees. A review of the L Reactor underground piping identified two critical locations:

- Cooling Water Inlet pipe at the 90 degree bend, 10 feet from the 190-L Building.
- Recirculating Water pipe at the 90 degree bend between the 1209-foot straight leg and the 133-foot leg which ultimately connects to the 186-L Cooling Water Reservoir.

Because the stresses in the Cooling Water Inlet pipe was found to be slightly above the stresses found in the Recirculating Water pipe, a seismic fragility analysis was performed on the Cooling Water Inlet pipe. The results of this analysis are used to represent the seismic fragility of all large pipe lines (i.e., 30- to 42-inch pipes).

Effects of corrosion of steel piping on the seismic capacity was investigated. A recent inspection of the 42-inch Cooling Water Inlet pipes concluded that there has been no significant pitting (Ref. 5). In all cases pitting is less than 0.05 inch. Because of the limited amount of observed pitting relative to the original wall thickness of 0.50 inches, it was concluded that corrosion of this magnitude does not impact the pipe seismic capacity.

3.2 Relative Building Motion Effects

Reference 2 reports the results of a dynamic seismic analysis for the L Reactor buildings corresponding to an evaluation earthquake with a

0.2 g PGA. As part of this analysis, soil-structure interaction was considered. The computed displacements of the soil in the vicinity of the buildings were found to be very small (e.g., relative displacement of 0.01 inches over a distance of 10 feet). Because this displacement is small compared to pipe displacements resulting from seismic wave passage, the effect of relative building displacement was not considered further.

4. Seismic Fragility Analysis of Underground Piping

Seismic wave passage may cause failure of steel underground pipes at high strain values. Carbon steel pipe can fail in a ductile, brittle or a mixed brittle/ductile state depending on the steel temperature. Ductile failure is preceded by large plastic deformations, whereas brittle failure occurs with little or no plastic deformation. The transition from one type of failure to the other occurs with changes in temperature.

The effect of temperature on steel is determined by Charpy V-Notch (CVN) impact test results. Figure 2 shows schematically an example of a CVN curve. The notch toughness value, corresponding to the nil ductility transition (NDT) temperature, defines the upper limit of brittle behavior of steel (T_y on Fig. 2). A higher temperature value (T_d on Fig. 2) defines the lower limit of the plastic behavior of steel.

Based on CVN test results performed on the Cooling Water pipes at the SRS (Refs. 11 and 12), the NDT temperature was found to be in the range of -20°C to 15°C (-4°F to 59°F) and the upper shelf temperature, T_d , was found to be in the range of 9°C to 53°C (48°F to 127°F). Figures 3 and 4 show curves for samples taken from Cooling Water piping at the SRS constructed of A285 and A53 materials, respectively.

From Reference 13, the yearly average temperature of the Savannah River is about 17°C (63°F) with temperatures as low as 5°C (41°F) and

Figure 2 Schematic Of A Charpy V-Notch Impact Test Data

Figure 3 Plots Of Charpy V-Notch Impact Test Data For A285 Piping At The Savannah River Site (Ref. 11)

Figure 4 Plots Of Charpy V-Notch Test Data For A53 Piping At The Savannah River Site (Ref. 11)

as high as 26° C (79° F). Therefore, the Cooling Water Inlet and Bypass pipes could fail in a brittle, ductile or a mixed brittle/ductile state depending on the temperature at the time of the earthquake. In comparison, the Cooling Water Effluent pipe and Recirculating Water pipe for which service water temperature is greater than 180° F are assumed to respond in a fully ductile manner. Consequently, two types of fragility analyses were performed.

In the first analysis, seismic capacities of underground piping were estimated for brittle failure (i.e., service temperature at or below the NDT temperature) which is assumed to occur at the yield level, and for ductile failures for which inelastic capacity of the pipe can be fully developed (i.e., assumes that the service temperature is at or above the upper-shelf temperature).

In the second analysis, seismic capacities of underground piping were obtained for the case where the temperature of the service water varies during the year. In this case, since the earthquake may occur at random during the year, the temperature could be between the NDT temperature and the upper-shelf temperature. Thus, failure could occur in a brittle, ductile or a mixed brittle/ductile state. The following two sections present the approach used and the results for the two analyses.

4.1 Seismic Capacity Estimates For Brittle and Ductile Failure Modes

The seismic capacity of a pipe for either failure mode (e.g., brittle or ductile) is expressed in terms of a double-lognormal model, for which the parameters are:

- Median capacity defined in terms of peak ground acceleration, $\bar{A}$
- Logarithmic standard deviation for capacity due to randomness, β_r

- Logarithmic standard deviation of the median capacity due to uncertainty, β_u

The first lognormal distribution quantifies the fraction of times failure occurs as a function of the earthquake ground motion level (e.g., PGA) with a known median pipe capacity. The second lognormal distribution quantifies the uncertainty in the estimate of the median pipe capacity.

The two logarithmic standard deviations, β_r and β_u , quantify the two sources of variability that exist in predicting the pipe capacity. Parameter β_r quantifies the randomness and β_u represents uncertainty. Randomness corresponds to the inherent (or irreducible) variability associated with the component response to the earthquake ground motion. Uncertainty is that part of the variability associated with model uncertainties and limited data. This variability could be reduced in principal by additional testing or analysis.

The seismic capacity of underground piping is determined by the relative axial displacements between the pipe and soil due to the effect of seismic wave passage. The axial pipe forces induce axial strains in straight pipe sections. Because of the relative motions between pipe sections at angles to each other bending distortions occur that could lead to potential failure. Offsets in the pipes are affected, but pipes with 90° elbows are generally the critical elements.

Earthquake ground motion is comprised of compression- and shear-type body waves and surface waves. From an engineering perspective, strong ground motion is dominated by shear-type body waves. Their amplitude and frequency content pose the greatest hazard to engineered facilities. Axial strains in the pipe depend on the seismic wave characteristics (ground velocity, peak acceleration, and wave velocity). Simplified relations are used to relate these strains to parameters of the seismic waves (Ref. 7).

The relations in Reference 7 can be used to express the PGA capacity of a pipe in terms of axial strain in the soil and seismic wave characteristics as:

$$A = \frac{\epsilon}{V_g \Phi_g} \frac{1}{\frac{\alpha}{2C_s} + \frac{1-\alpha}{C_p}} \quad (1)$$

where,

- A = pipe PGA capacity (g)
- ϵ = axial strain in soil at pipe capacity (dimensionless)
- V_g = peak ground velocity (fps) for an earthquake level of 1.0 g
- Φ_g = ground motion input variability factor (dimensionless)
- C_s = shear-wave velocity (fps)
- C_p = compression- (or surface-) wave velocity (fps)
- α = participation factor of shear-wave induced strain to the total strain (dimensionless)

Each random variable in Equation 1 is defined by a lognormal distribution. The parameters of each distribution are listed in Table 2. Note that the randomness value of 0.23 for parameter Φ_g includes both the effects of peak-to-valley variability of the ground response spectrum (β_r equal to 0.20) and the variability between the reference acceleration for a given horizontal direction and the average of the reference accelerations for the two orthogonal horizontal directions (β_r equal to 0.12). The median acceleration capacity (PGA) is assumed to be expressed in terms of the average reference acceleration in the seismic PRA.

The median capacity, $\bar{X}$, and variability due to randomness and uncertainty, β_r and β_u , were estimated for the brittle and ductile failure levels using Equation 1 in a probabilistic manner. The first and second moment of the pipe capacity distribution is derived using the

Table 2
Fragility Analysis Parameters For 30- To 42-inch Pipe

Parameter	Median Value	β_r	β_u
ϵ at yield level	7.31×10^{-4}	0.00	0.08
ϵ at ultimate level	2.45×10^{-3}	0.00	0.22
V_g	4 fps	0.00	0.19
Φ_g	1.0	0.23	0.00
C_s	3000 fps	0.00	0.42
C_p	6560 fps	0.00	0.38
α	0.7	0.34	0.00

Table 3
Pipe Fragility Parameters For Different Failure Modes

Component	Failure Mode	Median Peak Ground Acceleration Pipe Capacity (g)	β_r^1	β_u	β_c	HCLPF (g)
30" to 42" pipes	Brittle	1.07	0.23	0.40	0.46	0.38
30" to 42" pipes	Ductile	3.60	0.23	0.45	0.51	1.17
4" pipe	Brittle	1.10	0.27	0.20	0.34	0.51
4" pipe	Ductile	4.43	0.27	0.27	0.38	1.82

¹ β_r = Logarithmic standard deviation for randomness

β_u = Logarithmic standard deviation for uncertainty

$$\beta_c = \sqrt{\beta_r^2 + \beta_u^2}$$

HCLPF = High confidence of a low probability of failure capacity

"second moment" method with first and second order terms (Ref. 14). The pipe fragility parameters and HCLPF values are given in Table 3 for the brittle and ductile failure modes. Note that substituting the parameter values from Table 2 directly into Equation 1 will give slightly higher capacity values when compared to Table 3. Because the terms in Equation 1 are not in a pure multiplicative relationship, the median values based on the second moment approach are lower.

Table 3 also lists the fragility parameter estimates for the small diameter, 4-inch shallow buried pipe. The fragility results for this pipe were estimated by neglecting the soil restraint effect on a 10-foot cantilevered-pipe segment. This is conservative, even for pipes buried at depth, where soil restraint becomes significant.

4.2 Seismic Capacity Estimates With Temperature Effects

For piping that is exposed to service temperature variations during the year, failure due to an earthquake could occur in a brittle, ductile or mixed brittle/ductile state. Consequently the pipe seismic fragility must take into account the fact that the service water temperature varies throughout the year.

The CVN tests (see Figs. 3 and 4) provide an indication of the expected carbon steel behavior as a function of temperature. The CVN tests define two temperature levels, T_y and T_d (see Fig. 2), at which steel behavior changes. For temperatures lower than T_y (the nil ductility transition temperature), the steel exhibits brittle behavior. For temperatures higher than T_d , steel behavior is ductile. The transition from one type of behavior to the other occurs as temperature increases from T_y to T_d . Depending on the service water temperature, T , the fraction of times piping failure occurs is estimated for a ground motion intensity, A_g , as:

$$\begin{aligned}
(P_f|A_g)_y &= \Phi \left\{ \frac{\ln(A_g/\bar{X}_y)}{\beta_y} \right\} & T \leq T_y \\
(P_f|A_g)_d &= \Phi \left\{ \frac{\ln(A_g/\bar{X}_d)}{\beta_d} \right\} & T \geq T_d \\
(P_f|A_g) &= (P_f|A_g)_y + \frac{(P_f|A_g)_d - (P_f|A_g)_y}{T_d - T_y} (T - T_y) & T_y < T < T_d
\end{aligned} \quad (2)$$

where $\bar{X}_y$, β_y , and $\bar{X}_d$, β_d are the parameters of the piping seismic capacities for the brittle (i.e., subscript y) and ductile (i.e., subscript d) failure modes. The peak acceleration is denoted as A_g , and $\Phi(\cdot)$ is the cumulative normal distribution. Note that in the procedure to calculate the combined piping capacity (i.e., reflecting temperature), β_y or β_d was assigned either β_c or β_r (see Table 3). Also, $\bar{X}_y$ and $\bar{X}_d$ used in the analysis are the corresponding median capacities for each failure mode (see Table 3). In the first case when β_c is used, the resulting distribution includes the effects of both randomness and uncertainty. In the second case when only β_r is used, the resulting distribution reflects only the effects of randomness. The variability due to uncertainty for the combined fragility curve, β_u , was found by the square root of the sum of the squares (SRSS) procedure (i.e., $\beta_u^2 = \beta_c^2 + \beta_r^2$).

Service water temperature varies during the year and was considered to be uniformly random because an earthquake may occur any time during the year. The temperature data at the Jackson station given in Reference 13 were used in the analysis. An earthquake was assumed to occur equally likely in any month, and the temperature in a given month was assumed to be governed by the temperature distribution for that month. The behavior of steel as a function of temperature is characterized by the CVN tests. However, there are several test results for the same material (see Figs.

3 and 4). Differences in results suggest there is uncertainty in determining the behavior of steel for a given temperature.

To characterize the variability in the service water temperature and steel behavior, alternative events and hypotheses were assigned. In the analysis, service water temperature is dependent on the time of the year that the earthquake occurs. The earthquake is assumed to occur at random during any month of the year. The statistical distributions on monthly temperature are used to determine the probability on service water temperature.

Equal weight is subjectively assigned to each CVN test result, expressing the belief that the test results are equally likely to provide the "true" measure of the steel behavior as a function of temperature. Plant specifications require that piping between 30 and 60 inches in diameter be fabricated from A285 carbon steel, thus it is likely that the buried piping was constructed of A285 steel. Therefore, only the CVN test results for A285 was used in the buried pipe analysis. This is conservative for the 4-inch pipe where it is likely that a tougher steel was used.

The NDT (T_y) and upper-shelf (T_d) temperature values used in the analysis are listed in Table 4. These values were obtained from the four curves shown in Figure 3. In addition, two curves were added (Curves No. 5 and 6 in Table 4) after discussion with E. I. du Pont de Nemours and Company personnel to more fully represent the uncertainty in material properties.

The logic diagram in Figure 5 illustrates for each source of variability (i.e., time of earthquake occurrence, water temperature, and the CVN test results) the alternative possibilities and the likelihood assigned to each. Along a branch of the model, a conditional frequency of failure curve for the pipe $(P_f)_n$ is defined, using Equation 2, based

Table 4
Nil Ductility Transition And Upper Shelf Temperatures For A285 Steel

Curve No.	Nil Ductility Transition Temperature T_y ($^{\circ}\text{F}$)	Upper Shelf Temperature T_d ($^{\circ}\text{F}$)
1	23	86
2	59	94
3	39	84
4	49	80
5	40	85
6	-5	40

on the water temperature and CVN test results. The product of the individual event probabilities (p_n , q_n , r_n) gives the weight assigned to the conditional frequency of failure.

The final product is a family of conditional frequency of failure curves and associated weights that express the probability that the calculated frequency is the "true" frequency of failure. A mean (i.e., weighted average) conditional frequency of failure curve was then determined, from which the parameters for the seismic capacity of the pipe were obtained by fitting a lognormal distribution.

The results of the analysis are summarized in Table 5.

Figure 5 Logic Diagram Illustrating The Variability Analysis Considering Temperature Effects

Table 5
Pipe Fragility Parameters Including Temperature Effects

<u>Component</u>	<u>Median Peak Ground Acceleration Pipe Capacity (g)</u>	<u>β_r</u>	<u>β_u</u>	<u>β_c</u>	<u>HCLPF (g)</u>
30" to 42" pipes	2.0	0.42	0.60	0.73	0.37
4" pipe	2.0	0.52	0.47	0.70	0.39

5. Summary and Conclusions

Table 6 lists the fragility parameters for the underground steel piping. Two classes of piping are considered. The first class considers piping for which service water temperatures vary during the year and may cause the pipe to fail under seismic wave action either in a brittle, ductile or mixed brittle/ductile state (piping with temperature effects). The second class of piping includes those for which service water temperatures are in the range that would cause piping to fail in a ductile manner (piping without temperature effects). Table 6 also lists the 95 percent confidence of 5 percent or less probability of failure (HCLPF) capacities for the underground piping. The lowest HCLPF capacity was found to be 0.37 g. This capacity is large enough so that the piping is adequate for the evaluation earthquake of 0.20 g PGA with a margin of at least 1.85.

The seismic fragility results for the 30- to 42-inch diameter pipe lines are based on the analysis of the Cooling Water Inlet pipes which were found to have the lowest seismic capacity (not considering temperature effects). The fragility results listed in Table 6 for the 4-inch diameter pipe were obtained using a shallow-buried 10-foot long cantilevered pipe. These results are conservative because it was assumed

Table 6
Seismic Fragility Parameters For Underground Piping

Component	Median Peak Ground Acceleration Pipe Capacity (g)	β_r	β_u	β_c	HCLPF (g)
30" to 42" ¹ pipes with temperature effects	2.00	0.42	0.60	0.73	0.37
4" pipes with temperature effects	2.00	0.52	0.47	0.70	0.39
30" to 42" ² pipes without temperature effects	3.60	0.23	0.45	0.51	1.17
4" pipes without temperature effects	4.43	0.27	0.27	0.38	1.82

¹ Applicable to Cooling Water Inlet and Cooling Water Bypass Pipes

² Applicable to Cooling Water Effluent and Recirculating Water Pipes

in the analyses that there is no friction between the soil and pipe. Piping smaller than 4 inches in diameter is more flexible and thus have even higher capacities.

The effects on buried piping of relative building motions associated with soil-structure interaction were found to be insignificant.

This report does not address the effects on buried piping of relative ground movements or building settlements associated with soil consolidation or liquefaction.

6. References

1. Boissonnade, A. C. and J. W. Reed, "Seismic Fragility Analysis of Underground Piping at L Reactor, Savannah River Plant," Calculation Package, Jack R. Benjamin and Associates, Project No. 153-040, January, 1989.
2. "Seismic Analysis of 'L' Area Buildings at the Savannah River Plant Site," Appendix Volume I, Quadrex Corporation, QUAD-1-85-016.
3. "Update of Seismic Criteria for the Savannah River Plant," URS/John A. Blume and Associates, September 1982.
4. "Seismic Response of Buried Pipes and Structural Components," ASCE Nuclear Structures and Materials Committee, 1983.
5. Mittelberg, R. F., "L-Area Reactor Startup Inspections 13 Years After Retirement," E. I. du Pont de Nemours and Company, Savannah River Plant, February 1983.
6. Shah, H. H. and Chu, S. L., "Seismic Analysis of Underground Structural Elements," Journal of the Power Division, ASCE, Volume 100, No. P01, July 1974, pp. 53-62.
7. Goodling, E. C., Jr., "Buried Piping - An Analysis Procedure Update," PVP-77, Proceedings International Symposium on Lifeline Earthquake Engineering, Portland, Oregon, ASME, 1983, pp. 225-237.
8. American Society of Civil Engineers, "Seismic Analysis of Safety-Related Nuclear Structures and Commentary on Standard for Seismic Analysis of Safety Related Structures," ASCE 4-86, September 1986.
9. American Society of Civil Engineers, "Guidelines for the Seismic Design of Oil and Gas Pipeline Systems," 1984.
10. du Pont Specification No. 4482, issued 05/02/72, revised 09/14/83.
11. "Reactor Carbon Steel Piping Material Study for Savannah River Plant 100 Area; Carbon Steel Reactor Piping Assessment," Volume I of II, E. I. du Pont de Nemours and Company, Engineering Department Design Division, Atomic Engineering Division, December 1983.

12. Louthan, M. R., Jr., "Fracture of 100 Area Carbon Steel Piping: A Lower-Bound Analysis," Savannah River Laboratory, Aiken, SC, DPST-88-353, February 25, 1988.
13. United States Geological Survey, "Savannah River Temperatures," Prepared for E. I. du Pont de Nemours and Company, VEGP-FSAR-2.
14. Benjamin, J. R., and Cornell, C. A., Probability, Statistics, and Decision for Civil Engineers, McGraw-Hill Book Company, 1970.

END

DATE
FILMED

8/04/92