**MODELING OF INTEGRATED
ENVIRONMENTAL CONTROL SYSTEMS
FOR COAL-FIRED POWER PLANTS:
Conventional Froth Flotation for
the IEC Coal Cleaning Plant Model**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Quarterly Progress Report

To

Pittsburgh Energy Technology Center
U.S. Department of Energy
Pittsburgh, Pennsylvania 15236

From

Center for Energy and Environmental Studies
Carnegie Mellon University
Pittsburgh, Pennsylvania 15213

Prepared by

E.S. Rubin, Principal Investigator
J.S. Salmento, Research Associate

January 1989

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Nomenclature

A	= Ash content coal (fraction)
AC	= Annual operating cost (78\$/dry ton of clean coal)
c_k	= Chemical cost for k^{th} level plant (78\$/dry ton of cleaned coal)
CS	= Concentration of solids (fraction)
DC	= Direct capital cost (78\$)
DCC	= Cost coefficient for cleaning equipment (78\$/dry ton of raw coal)
e_k	= Electricity cost for k^{th} level plant (78\$/dry ton of cleaned coal)
E_d	= Energy needed for thermal drier (Btu/lb of dry coal)
f	= Weight fraction of coal (fraction)
HHV	= Average higher heating value of coal (Btu/lb)
K_{specie}	= Rate constant of specie (min^{-1})
l_k	= Labor cost for k^{th} level plant (78\$/dry ton of cleaned coal)
LHV	= Lower heating value of coal (Btu/lb)
m'	= Total moisture content of coal (fraction)
m_i'	= Inherent moisture content of coal (fraction)
m_s'	= Surface moisture content of coal (fraction)
m	= Dry mass flow rate of coal (tons/hr)
MIBC	= MIBC consumption of froth flotation circuit (lb/raw dry ton)
O	= #2 fuel oil consumption of froth flotation circuit (lb/raw dry ton)
r_{specie}	= Recovery of species (fraction)
R_{specie}	= Ultimate recovery constant of species (fraction)
S	= Sulfur content of coal (fraction)
T	= Residence time of flotation vessels (minutes)
v	= Volume of flotation cells (ft^3)
V_{ef}	= Effective volume of flotation equipment (fraction)
w'	= Weight of water evaporated in thermal drier per pound of dry coal processed (fraction)
w'_e	= Weight of water evaporated in thermal drier (tons/hr)
w_k	= Water cost for k^{th} level plant (78\$/dry ton of cleaned coal)
Y_d	= Mass yield of the thermal drier (fraction)
Y_p	= Mass yield of coal cleaning plant excluding the thermal drier yield (fraction)
Y_t	= Mass yield of the entire coal cleaning plant (fraction)
Y_{od}	= Ratio of coal mass exiting wash streams to coal mass exiting plant (fraction)

Greek Letter Symbols

ϵ	= Efficiency of thermal drier (fraction)
δ_i	= Equals 0 if wash stream i is not thermally dried and 1 if it is thermally dried.
ρ_c	= density of coal (lb/ft^3)
ρ_w	= density of water (lb/ft^3)

Subscripts:

c = clean coal exiting wash streams
d = thermal drier
i = (1) coarse, (2) medium, or (3) fine streams
in = entering thermal drier
j = oil or MIBC
k = level of plant (2,3,4, or 5)
l = clean, thermal, raw, refuse, sample
o = clean coal exiting plant
out = exiting thermal drier
ref = refuse coal
ROM = raw coal

species:

a = ash
afc = ash-free coal
s = sulfur content

1. Introduction

This report describes the addition of a conventional froth flotation circuit into the FORTRAN coal cleaning module of the Integrated Environmental Control (IEC) model [1]. The purpose of this modification is to include froth flotation as an option to clean the fine fine. The current model has three beneficiation: levels (2, 3, and 4) in which different streams are washed by specific gravity equipment. Level 2 washes only the coarse stream. Level 3 washes the coarse and medium streams. Level 4 washes the coarse, medium, and fine streams. This modification adds a fifth level, which uses specific gravity equipment to wash the coarse and medium streams and froth flotation equipment for the fine stream. The specific size fractions in each stream are specified by the model user. As before, the model optimizes the yield of each circuit in order to achieve a target coal quality for the cleaned coal product.

2. Process Description

This section only briefly describes froth flotation of coal. For a more detailed descriptions of froth flotation see References 2,3,4, 5, and 6. Most coal cleaning processes use the difference between the specific gravity of coal, ash, and pyrite to separate the coal from the ash and pyrite [4]. Froth flotation, however, uses the difference between the adhesion of small air bubbles to coal, ash, and pyrite to achieve separation. Usually small air bubbles are passed through a fine coal slurry stream. Air attaches itself to coal and floats to the surface, where it is removed. Since the air does not attach itself to the ash it remains in the slurry and is carried off. Particles which stick to air bubbles are called hydrophobic, while those which are easily wetted are called hydrophilic.

Coal is inherently hydrophobic, but the degree of floatability depends upon a number of parameters, including particle size, pulp density, coal rank, extend of oxidation, quantity and type of chemicals used, slurry pH, aeration and agitation, retention time. Three theories which try to broadly predict the floatability of coal are the carbon-hydrogen ratio theory, the carbon content theory, and the surface-components theory. All three theories have advantages and disadvantages

in predicting the floatability of coal; however, none of the theories predicts the quality and yield of coal for a specific set of flotation parameters. Therefore, they are not applicable for this model; however, they can be used to estimate the performance of a new coal from existing floatability data.

Usually chemicals, called frothers, are added to the coal slurry to prolong the life of the air bubbles, which enhances the stability of the froth. MIBC (methyl isobutyl carbinol) is a common frother used for coal froth flotation. Collectors increase the adhesion of air to coal and are needed for highly oxidized or lower rank coals. A common collector used for froth flotation of coal is fuel oil. Other chemicals can be added which perform a variety of functions. The most common are depressing agents, activating agents, pH regulators, dispersing agents, and protective colloids.

Figure 2-1 shows the a process diagram for a conventional coal cleaning plant with froth flotation for the fine size stream. Although it is widely used, the process is not understood as well as specific gravity based beneficiation. Because less is known about froth flotation, it is difficult to predict full scale performance from laboratory batch data. Although there are algorithms for scaling up laboratory data [7], they have not been implemented in this model until they can be further evaluated. It is also generally accepted that flotation washability data cannot be predicted from specific gravity washability data [8,9].

3. Froth Flotation Performance Model

A complete description of the conventional coal cleaning model is found in Reference [1]. This report only discusses the improvements that have been added. The model uses a Lagrange multiplier technique to maximize the yield (mass or energy) for a given coal and plant configuration. The algorithm needs discrete data points of the yield and coal quality at different specific gravities for three wash streams (coarse, medium, fine). For froth flotation of the finesize stream, the user can specify washability data in one of three different ways:

- Actual yield and quality data at different residence times
- Rate and ultimate recovery constants for ash-free yield, ash, and sulfur content
- Mass yield and coal quality of the cleaned coal for the flotation circuit.

Figure 2-1: Coal Cleaning Plant with Froth Flotation of Fine Stream

For all three options the following information is also needed:

- The quantity of MIBC and #2 fuel oil,
- Inlet slurry concentration, and
- Effective volume of the cells.

For option one the froth flotation data is substituted for the conventional fine stream data and the model optimizes the yield for all three streams as usual. Data in this form can be found in Reference 9; however, this is batch data and has not been scaled to full size. The only difference is that the residence time is determined instead of a specific gravity for the fine stream. The only restriction currently is that the number of coal quality data points for froth flotation must equal the number of specific gravity data points.

For the second option, the rate and ultimate recovery constants are used in the Klimpel model (Equation 3.1) to predict the recovery of ash-free coal, ash, and sulfur at different residence times [7,8]:

$$r_i = R_i \left[1 - \frac{1}{K_i T} (1 - e^{-K_i T}) \right] \quad (3.1)$$

The total mass yield is equal to the sum of the ash-free coal and ash recovered (Equation 3.2). The ash content of the cleaned coal is equal to the recovery of ash times the raw coal ash content divided by the mass yield (Equation 3.3). The sulfur content of the cleaned coal is determined similarly (Equation 3.4). The higher heating value is estimated by Equation 3.5.

$$Y_{p,3} = (1 - A_{ROM}) r_{afc} + A_{ROM} r_a \quad (3.2)$$

$$A_{o,3} = \frac{A_{ROM} r_a}{Y_{p,3}} \quad (3.3)$$

$$S_{o,3} = \frac{S_{ROM} r_s}{Y_{p,3}} \quad (3.4)$$

$$HHV_{o,3} = HHV_{ROM} \left(\frac{1 - A_{o,3}}{1 - A_{ROM}} \right) \quad (3.5)$$

The coal yield and quality in the froth circuit at different residence time interval can be

determined with Equations 3.2 - 3.5. The residence times intervals is determined by specifying a maximum residence time and dividing by the number of specific gravity data points.¹ This data is then substituted into the fine size washability data and the model proceeds as usual.

For the third option, the yield and quality of the froth flotation circuit is specified at a given residence time. This data is passed into the optimization algorithm, where the model optimizes the mass yields of the coarse and medium streams to achieve the overall target coal quality.

For all three options, once the residence time is determined the total volume of the cells can be determined from Equation 3.6:

$$v = m_{\text{ROM}} f_{\text{ROM},3} T \frac{2000 \text{ lb/ton}}{60 \text{ min/hr}} \left[\frac{1}{r_c} + \left(\frac{1}{CS} - 1 \right) \frac{1}{r_w} \right] \frac{1}{V_{\text{ef}}} \quad (3.6)$$

The density of water and coal are assumed to be 84 and 62 lb/ft³, respectively. The effective volume, V_{ef} , is used to account for the volume occupied by the air-ingestion equipment and air bubbles.

4. Process Economics Model

The general coal cleaning plant economic model is based on several studies [10,11,12,13,14,15] and is described in Reference [1]. All cost are computed in 1978 dollars then escalated to a current year using a plant cost index. The same method is used to estimate the cost of the new level five plant with froth flotation. The capital cost is divided into five different sections: (1) raw coal handling, (2) cleaning equipment, (3) thermal drying, (4) refuse handling, and (5) coal sampling system. The direct capital cost of each section other than the coal sampling system is related to its characteristic mass flow, and is assumed to have an economy of scale of 0.7 for plant sizes in the range of 500 to 2000 clean tons per hour (tph) [11]. Only the cost of the cleaning equipment section is assumed to vary with different levels of coal cleaning. The capital cost related to clean coal handling (which includes the cost of conveyors, storage, and loading equipment) is included in the raw coal handling cost since the cleaning plant is assumed to be at the

¹ This will be changed to the maximum number of data points possible in the next version of the model.

mine site. It is assumed that the cost of the coal sampling system does not vary with plant capacity.

The economics of froth flotation depend on the residence time, chemical usage, and process yield. The direct capital for the cleaning equipment for a level 5 plant is estimated by Equation 4.1:

$$DC_{\text{clean}} = DCC_5 m_{\text{ROM}}^{0.7} + 6780 v^{0.4} \quad (4.1)$$

where $DCC_5 = 43,700$

The first term of Equation 4.1 is the capital cost of the cleaning equipment excluding the flotation cells. The second term is the capital cost of the flotation cells. The value for the first term was obtained from Reference [10]. It represents the average cost of all cleaning equipment excluding the flotation cells scaled to the raw coal mass flow rate. The direct capital cost for the froth flotation equipment is scaled to the total volume of the vessels [10,15]. An exponential scaling factor of 0.4 is used as the best fit to available data [10,15].

The indirect and annualized capital costs are calculated as shown in Reference [1]. The operating and maintenance costs of a level five plant are calculated in a similar manner to the other levels. The cost factors for labor, maintenance, refuse, and taxes are the same as a level four plant [10]. The cost factor for chemicals (excluding oil and MIBC), electricity, and water are, respectively, 0.064, 0.15, and 0.0015 in 1978\$/ton of raw coal [10]. The amounts of MIBC and #2 fuel oil used are input parameters in the model. Therefore the cost per ton of cleaned coal is estimated by the following equations:

$$AC_{\text{oil}} = \frac{0.072 O f_{\text{ROM},3}}{Y_t} \quad (4.2)$$

$$AC_{\text{MIBC}} = \frac{0.60 \text{ MIBC } f_{\text{ROM},3}}{Y_t} \quad (4.3)$$

5. Other Model Enhancements

5.1 Level 4 Plant Cost

After reviewing the economics for a level four plant, several cost coefficients were modified to more accurately represent level four plants which use hydrocyclones. These changes are minor

and do not change the cost of cleaning a given coal significantly. The new cost coefficients were modified for the direct capital cost, chemicals, electricity, and water are:

$$DCC_4 = 45,700 \quad (5.1a)$$

$$c_4 = 0.065 \quad (5.1b)$$

$$e_4 = 0.158 \quad (5.1c)$$

$$w_4 = 0.0041 \quad (5.1d)$$

5.2. Moisture Content of Cleaned Coal

Another improvement to the coal cleaning model is that it now more accurately calculates the moisture content of the cleaned and refuse coal. Previously the model did not explicitly calculate the moisture content of the cleaned or refuse coal, and it did not adjust the final quality of the coal to account for the thermal drier. These assumptions made the model less sensitive to the effects of the different moisture content associated with different size wash streams.

The revised model assumes that the total moisture content of the raw coal is composed of two components: the inherent moisture and the surface moisture. The inherent moisture is assumed to remained constant even if the coal is washed or thermally dried. The surface moisture of the coal changes if it is washed or thermally dried. The model requires that the surface moisture associated with each wash stream be entered as an input parameter. The value should be typical of the surface moisture associated with the wash size stream after it has been through mechanical dewatering. In other words, as the wash stream size decreases the surface moisture should increase. For example, 28x0 mesh coal would have a surface moisture of approximately 20%, while 1.375"x0.25" would have a value of approximately 4%.

The total moisture content of each wash stream is equal to the inherent moisture content of the raw coal plus the surface moisture of either the wash stream (if the stream was washed) or the raw coal (Equation 5.2).

$$\text{If } Y_i < 1 \text{ then} \quad (5.2)$$

$$m'_i = m_{i,ROM} + ms'_i$$

else

$$m'_i = m_{i,ROM} + ms'_{ROM}$$

In order to calculate the average properties of the coal entering the thermal drier, the fraction of coal to be thermally dried needs to be determined. Equation (5.3) calculates the weight fraction of the coal exiting the washing equipment, while Equation (5.4) calculates the fraction of coal to be thermally dried. The input parameter, δ_i , is used to determine which streams should be thermally dried. It is set to 1 if the stream is to be thermally dried; otherwise, it is 0. This allows any combination of wash streams to be sent to the thermal drier.

$$f_{c,i} = \frac{f_{ROM,i} Y_i}{Y_p} \quad (5.3)$$

$$f_d = \sum_{i=1}^3 f_{c,i} \delta_i \quad (5.4)$$

The surface moisture associated with a wash stream, ms'_i , is an input parameter. Equations 5.5 and 5.6 show the equations for the average moisture content and higher heating value of the coal entering the thermal drier.

$$m'_{in} = \frac{\sum_{i=1}^3 \frac{m'_i f_{c,i} \delta_i}{(1 - m'_i)}}{\sum_{i=1}^3 \frac{f_{c,i} \delta_i}{(1 - m'_i)}} \quad (5.5)$$

$$HHV_d = \frac{\sum_{i=1}^3 HHV_i f_{c,i} \delta_i}{f_d} \quad (5.6)$$

The moisture content of the refuse streams is equal to the inherent moisture content of the raw coal plus surface moisture associated with the washed streams. Therefore the average moisture content of the refuse coal is estimated with Equation 5.7.

$$m'_{ref} = \frac{\sum_{i=1}^3 \frac{(mi'_{ROM} + ms'_i) (1 - Y_i) f_{ROM,i}}{(1 - mi'_{ROM} - ms'_i)}}{\sum_{i=1}^3 \frac{(1 - Y_i) f_{ROM,i}}{(1 - mi'_{ROM} - ms'_i)}} \quad (5.7)$$

With the moisture content and higher heating value of the coal entering the thermal drier determined, it is possible to calculate the performance of the thermal drier. Since the model explicitly calculates the moisture content of the coal entering the thermal drier, m'_{in} , it is possible for that coal to be drier than the specified moisture content of the coal exiting the thermal drier, m'_{out} . Thus, the thermal drier is used only if the coal entering the drier has a moisture content above a certain level. If the thermal drier is not used the thermal drier yield is set to 100 percent and the fraction of coal dried and water evaporated are set to zero. If it is used the fraction of coal dried is the same as calculated above (Equation 5.4) and the other parameters are calculated as follows.

$$m'_{out} = m'_{iROM} + m'_{s'out} \quad (5.8)$$

If $m'_{in} < m'_{out}$ then

$$w' = 0.0 \quad (5.9a)$$

$$E_d = 0.0 \quad (5.10a)$$

$$LHV = 0.0 \quad (5.11a)$$

$$Y_d = 1.0 \quad (5.12a)$$

$$Y_{O_d} = 1.0 \quad (5.13a)$$

$$w'_c = 0.0 \quad (5.14a)$$

$$f_d = 0.0$$

$$\delta_l = 0$$

else

$$w' = \frac{m'_{in} - m'_{out}}{(1 - m'_{in})(1 - m'_{out})} \quad (5.9b)$$

$$E_d = \frac{1020m'}{\epsilon} \quad (5.10b)$$

$$LHV = 0.96 HHV_d - \frac{1020 m'_{out}}{1 - m'_{out}} \quad (5.11b)$$

$$Y_d = 1 - \frac{E_d}{LHV} \quad (5.12b)$$

$$Y_{O_d} = (1 - f_d) + f_d Y_d \quad (5.13b)$$

$$w'_c = w' \frac{m_o f_d}{Y_{O_d}} \quad (5.14b)$$

The ratio of the coal exiting the washing equipment to the coal leaving the plant is defined by

Equation 5.13. This parameter is needed to calculate the amount of coal leaving the wash streams based upon the out capacity of the plant.

The thermal drier does not change the quality of the coals; however, it does change the weight fraction of coal in each stream. Therefore, the mass yield and weight fraction of each stream must be adjusted to account for the losses of water and coal in thermal drier. At this point it is more appropriate to describe the drier yield by individual stream even though the streams to be dried are combined before entering the thermal drier and the yield is the same across both streams.

$$\begin{aligned} \text{If } \delta_i = 1 \text{ then} \\ Y_{d,i} = Y_d \\ \text{else} \\ Y_{d,i} = 1 \end{aligned} \quad (5.15)$$

With the thermal drier yield described as above, the weight fraction and mass yield of each stream can be calculated as follows:

$$f_{o,i} = \frac{f_{c,i} \delta_i}{Y_{o,d}} \quad (5.16)$$

$$Y_{t,i} = Y_i Y_{d,i} \quad (5.17)$$

With the new weight fraction data it is possible to calculate the quality of the coal leaving the coal cleaning plant. The moisture content of the final product depends upon whether any stream was thermally dried. From this, the higher heating value, ash, and sulfur content on a wet basis can be calculated with Equations 5.20 to 5.22.

$$\begin{aligned} \text{If } \delta_i = 1 \text{ then} \\ m'_{o,i} = m'_{out} \\ \text{else} \\ m'_{o,i} = m'_{in,i} \end{aligned} \quad (5.18)$$

$$m'_o = \frac{\sum_{i=1}^3 \frac{m'_{o,i} f_{o,i}}{1 - m'_{o,i}}}{\sum_{i=1}^3 \frac{f_{o,i}}{1 - m'_{o,i}}} \quad (5.19)$$

$$\text{HHV}_o = (1 - m'_o) \sum_{i=1}^3 \text{HHV}_{o,i} f_{o,i} \quad (5.20)$$

$$A_o = (1 - m'_o) \sum_{i=1}^3 A_{o,i} f_{o,i} \quad (5.21)$$

$$S_o = (1 - m'_o) \sum_{i=1}^3 S_{o,i} f_{o,i} \quad (5.22)$$

The quality of the final product after the thermal drier may differ slightly from the target quality specified because the optimization algorithm is based on dry coal properties. The difference should not be very large since the thermal drier usually has a mass yield well above 98%. Also note, that if all the streams are picked to be thermally dried, the model will only attempt to dry to coal if the moisture content exceeds a specified value.

6. Future Research

The improved coal cleaning models documented in this report have been implemented in the CMU Integrated Environmental Control (IEC) computer model used for analyzing alternative power plant systems. Future documentation will include a detailed numerical example illustrating the use of the froth flotation model, plus case studies involving typical power plant application. Appropriate documentation for computer model users also will be prepared in the next reporting period.

7. References

1. Rubin, E.S., J.S. Salmento, J.G. Barrett, C.N. Bloyd, H.C. Frey. *Modeling and Assessment of Advanced Processes for Integrated Environmental Control of Coal-Fired Power Plants*. Final Report of Contract No. DE-FG22-83PC60271 from Carnegie Mellon University, Pittsburgh, PA to U.S. Department of Energy, Pittsburgh, PA, July, 1986. NTIS No. DE86014712/WEP, Springfield, VA.
2. Brown, D.J. "Coal Flotation," Fuerstenau, D.W., Ed., *Froth Flotation - 50th Anniversary Volume*, AIME, New York, 1962, pp. 518 - 538.
3. Aplan, F.F. "Coal Flotation," Fuerstenau, M.C., Ed., *Flotation, A.M. Gaudin Memorial Volume, Vol. II*, AIME, New York, 1976, pp. 1235 - 1265.
4. Leonard, J.W., Ed. *Coal Preparation, 4th edition*. The American Institute of Mining, Metallurgical, and Petroleum Engineers, Inc., New York, 1979.
5. Miller, K.J. and A.W. Deurbrouck. "Froth Flotation to Desulfurize Coal," Liu, Y.A., Ed., *Physical Cleaning of Coal Present and Developing Methods*. Marcel Dekker, Inc., 1982.
6. Leja, J. *Surface Chemistry of Froth Flotation*. Plenum Press, New York, 1982.
7. Olson, T.J. *Froth Flotation for Fine-Coal Cleaning*. Final Report of Research Project 1852-4 from WEMCO, Sacramento, California to Electric Power Research Institute, Palo Alto, California, December, 1985. CS-4383.
8. Arnold, B.J. *A Practical View of Rate and Residence Time in Industrial Coal Froth Flotation Circuits*. EPRI Coal Quality Development Center, Homer City, PA. Prepared for the 5th Annual International Pittsburgh Coal Conference, Pittsburgh, PA, September, 1988.
9. Cavallaro, J.A., and A.W. Deurbrouck. *Froth Flotation Washability Data of Various Appalachian Coals using the Timed Release Analysis Technique*. United States Department of the Interior, Bureau of Mines, Report of Investigations 6652, 1965.
10. Onursal, B., B. Chenz and L. McCandless. *Cost, Energy and Environmental Sensitivity Analysis of Coal Cleaning Technology for Industrial Boiler Applications*. Prepared under Contract No. EPA-68-02-3136, Versar, Inc., June, 1980.
11. Bechtel Corporation. *Coal Preparation and Cleaning Assessment Study*. ANL/ECT-3, Appendix A (Part 1), Argonne National Laboratory, December, 1977.
12. Buroff, J. et al. *Technology Assessment Report for Industrial Boilers: Coal Cleaning and Low Sulfur Coal*. EPA-600/7-79-178c, Versar, Inc., December, 1979.
13. Hoffman-Muntner Corporation. *Engineering/Economic Analyses of Coal Preparation with SO₂ Cleanup Processes*. Report EPA-600/7-78-002, Interagency Energy-Environment Research and Development Program Report, January, 1978.

14. Molburg, J.C. *Mathematical Models for Integrated Environmental / Economic Analysis of the Coal-To-Electricity System*. Ph.D. Thesis, Carnegie Mellon University, May, 1982.
15. Holt, E.C., Jr. *An Engineering / Economic Analysis of the Coal-Pyrite Flotation Process*. Final Report of Contract DE-AC22-80PC30149, U.S. Department of Energy, Hoffman-Holt, Incorporated, Silver Spring, MD, July 1981. NTIS No. DE82013450.

**DATE
FILMED**
8/11/92