11

Quarterly Technical Progress Report No. 11
For Period
August 1, 1990 through October 31, 1990

SURFACE MAGNETIC ENHANCEMENT FOR COAL CLEANING

Submitted to:

U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Contract Number: DE-AC22-88PC88856

Technical Program Officer: McMahan L. Gray

Prepared by:

Project Manager and Principal Investigator
J. Y. Hwang
Program Manager - Minerals

Institute of Materials Processing
Michigan Technological University
Houghton, Michigan 49931

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

SUMMARY AND FUTURE WORK

The fundamental chemistry for selective adsorption of magnetizing reagent on coal-associated minerals to enhance the magnetic susceptibilities of minerals have been established in Phase I study. The application of the results to study the feasibility for coal cleaning has been completed in the Phase II study. The most effective approach to clean Illinois No. 6, Ohio Lower Kittanning, and West Virginia Pocahontas coals using the magnetizing method has been determined. The results show that the best separation performance is obtained on finely ground coals. Up to 91% ash reduction (from 22% to 3.3% ash content) and 93% pyritic sulfur reduction at 70% BTU recovery can be obtained for Illinois No. 6 coal. Similar or better results are obtained for Lower Kittanning and Pocahontas coal due to better liberation.

Phase III study is in progress during this quarter. Experimental work includes the determination of various separation parameters, including the separator and matrix selection, magnetic reagent dosage, particle size, magnetic field intensity, and retention time.

Complete data evaluation and economic analysis will be carried out in the next quarter. A draft of the final report will also be prepared in the next quarter.

INTRODUCTION

This research studies the surface enhancement of magnetic susceptibility of minerals for coal cleaning. The enhancement is achieved by adsorbing magnetizing reagent on minerals. The objectives of the study include: (i) to define the optimal conditions for adsorption selectivity and magnetic enhancement using magnetizing reagent approach, (ii) to determine the effect of such magnetic enhancement on the coal cleaning efficiency with magnetic separations, and (iii) to evaluate where this method can be adapted to the existing coal processing schemes for maximum effectiveness.

Three phases of work are included in this research: a fundamental study, an application study, and an industrial laboratory study. The fundamental study investigates the basic chemistry involved in the interactions of magnetizing reagents and minerals. The application study employs the basic chemistry for coal cleaning under various process schemes. The industrial laboratory study investigates the effects of parameters of industrial laboratory magnetic separators.

The work performed during this reporting period is focused on the selection of magnetic separators and the determination of separation parameter effects (Task 12) in the Phase III study.

PROGRESS BY WORK BREAKDOWN STRUCTURE

Task 1. Magnetizing Reagent Preparation

Thirty five magnetizing reagents with various surfactant functional groups have been prepared for this study. The properties of these reagents were documented in the previous reports. Five reagents, selected from different cationic, anionic, and nonionic categories, were investigated for their shelf life. The results show that magnetizing reagents are stable for long term storage. This task is completed.

Task 2. Mineral/Reagent Interactions

The interactions of magnetizing reagents and minerals under various conditions have been investigated. The conditions include pH, kinds and dosages of magnetizing reagents, mineral activator, coal depressant, oxidation effect, and slurry regulators. All of the experimental results have been described in the previous reports. This task is completed.

Task 3. Magnetite Size Effect

The particle size of magnetite and its effects on the properties of magnetizing reagents were studied. The experiments show that smaller magnetite particles provide better metallurgical results. This task is completed.

Task 4. Phase I Data Evaluation

All of the results in Phase I study have been evaluated. The most promising conditions for selective magnetic enhancement of

coal-associated minerals have been selected.

Task 5. Phase I Report and Review

The reports documenting the progress in Phase I study have been completed and reviewed.

Task 6. Coal Selection, Preparation, and Characterization

Three coals are selected for the Phase II study. They are Illinois No. 6, Ohio Lower Kittanning, and West Virginia Pocahontas No. 3 seams. Each 400 pound sample was prepared simulating the commercial operations to yield the feed for this study. The circuits include heavy media, tabling, and froth flotation separations. Characterization study includes coal analysis, grindability, washability, mineralogy, and maceral and pyrite distributions. The results were described in the previous reports. This task is completed.

Task 7. Optimization of Magnetizing Conditions

Eleven promising conditions to yield selective adsorption of magnetizing reagent on coal-associated minerals have been evaluated on the basis of magnetic separations. The three coals at -48 mesh prepared in Task 6 were utilized in these tests. The results show that enhanced separation is particularly successful with an approach which uses a hydrophilic modifier for coal depressing and a cationic magnetizing reagent for minerals magnetic enhancement. A reduction of 92% ash and 83% pyrite can be achieved. In addition, flotation concentrates of these coals at -48 mesh were also examined with this approach. The results show that the magnetic enhancement approach performs better than the recleaning

flotation approach. At the same extent of pyrite reduction, the magnetic enhancement approach gains 12% additional coal yield than the recleaning flotation approach does for Illinois No. 6 coal. The better selectivity on removing the unliberated pyrite from coal particles is believed the reason. This task is completed.

Task 8. Process Adaptation Testing

This task is to determine the best way to adopt the magnetizing method to the existing coal preparation and utilization scenarios. Three options are included. The first option is to condition the coal concentrates with the magnetizing reagent at the preparation plant, dry pulverize the coal at power plant, and conduct dry magnetic separation before combustion. The second option is to process the preparation plant middlings. The third option is in the area of fine coal cleaning, which is found most promising.

Option 1.1. Table Concentrate Processing. Experiments show that adsorbed magnetic reagent is not smeared away from mineral surface during pulverizing. Wet magnetic separation can remove residual pyrite and ash effectively, but dry magnetic separation is ineffective.

Option 1.2. Heavy Media Concentrate Processing. Experimental results agree with Option 1.1 that only wet magnetic separation is effective.

Option 1.3. Flotation Concentrate Processing. Dry magnetic separation is still ineffective.

Option 2. Heavy Media Middlings Processing. The middlings are very difficult to liberate. The concentrate obtained from the middlings after processing contains higher ash content than that obtained from processing the ROM coals directly.

Option 3.1. Fine Coal processing for Illinois No. 6. Ash content reduced from 22% to 3.3% with 70% coal recovery can be obtained. Pyritic sulfur is reduced from 2.18% to 0.28% (93% rejection). Similar separation results are obtained in the range of 90% passing 200 mesh to 90% passing 500 mesh.

Option 3.2. Fine Coal Processing for Lower Kittanning. Ash content can be reduced from 6.9% to 1.3% at 79% coal recovery. Pyritic sulfur can be reduced from 1.76% to 0.48% (81% rejection). The effect of particle sizes in the range of 90% passing 200 mesh to 90% passing 500 mesh on magnetic enhanced separation is not significant.

Option 3.3. Fine Coal Processing for Pocahontas. The ash content can be reduced from about 30% to about 5% (90% ash rejection) at about 59% yield (80% coal recovery). Pyritic sulfur is reduced from 0.40% to 0.07% (93% rejection).

Task 9. Phase II Data Evaluation

All of the results in Phase II study have been evaluated. The most promising approach for direct utilization of the magnetic reagent technology on coal cleaning is in the fine coal cleaning area. However, the combination of flotation and magnetic reagent technology may offer the best separation efficiency.

Task 10. Phase II Report and Review

The reports documenting the results in Phase II study have been completed and submitted during this reporting period.

A paper entitled "Fine Coal Cleaning With Advanced Magnetic Enhancement Technology" has been prepared and presented on the Sixth Annual Coal Preparation, Utilization, and Environmental Control Contractors Conference at Pittsburgh. The paper was well received. Many research institutions have approached for the details of this innovative technology and expressed their interests to cooperate on the development of this new technology.

Task 11. Sample Preparation and Delivery

The reserved samples of Phase II study, including 206 pounds Illinois No. 6, 210 pounds Lower Kittanning, and 256 pounds Pocahontas, have been processed during this reporting period for the Phase III study. The reserved samples at 4" top size have been stored under argon gas for a period of 12 to 15 months. These samples were crushed and ground to minus 48 mesh. Samples were then riffled and bagged in plastic bags under argon atmosphere. Each bag contains 300 grams charge. The samples were carried to Erie, Pennsylvania, for the testing work at Eriez Magnetics.

Task 12. Separator Selection and Parameter Determination

Separator Selection. The results of Phase II study have been discussed with the technical staff of Eriez Magnetics, led by Dan Norrgran, Technical Manager. High intensity magnetic separator, Eriez Model L-4-20, was selected as the most appropriate separator for this study based on both technical and economical concerns.

Particle Size and Matrix Selection. Based on the experience of Eriez Magnetics, potential candidates for the separator matrix may include expanded metal, coarse screen, chicken wire, and stainless steel balls. Stainless steel wool matrix can only be utilized for minus 270 mesh coal and may cause serious mechanical entrapment for the magnetic reagent approach. The matrix selection has to be carried out experimentally for coal ground to various sizes.

Two coal particle sizes are selected in this study: -48 mesh and 90% passing 200 mesh. The former one avoids costly grinding requirement. The latter one investigates fine coal cleanability. Results in Phase II study show that there is no significant difference for coals processed in the range of 90% passing 200 mesh to 90% passing 500 mesh. Coarser grinding provides the grinding cost advantage.

Figure 1 shows the effects of matrix on coal cleaning at -48 mesh particle size. Experiments were conducted by feeding a slurry of Illinois No. 6 through a matrix at 10 kilogauss magnetic field intensity. Three periods of retention time were involved for each matrix testing, which are 1, 2, and 3 seconds. Longer retention time provides a higher extent of ash reduction. Coarse screen matrix obviously can remove more ash forming minerals than the other matrices. However, the ball matrix can provide the best recovery. From the factor of separation efficiency, the ball matrix also performs the best. Thus, ball matrix is selected for the processing of -48 mesh coal.

Figure 2 shows the results of matrix selection for 90% passing 200 mesh coal, using the same experimental procedures as described above. Ball matrix performs slightly better than coarse screen matrix in respect of recovery and separation efficiency. However, coarse screen matrix is much better on the extent of ash reduction. Coarse screen matrix is therefore, selected for -200 mesh coal processing. Expanded metal and chicken wire matrices are not competitive.

Reagent Dosage. Four dosages of magnetic reagents are studied for Illinois No. 6 coal at -48 mesh particle size. These dosages are 0, 3, 5, and 10 pounds per ton of coal. Ball matrix with 10 kilogauss applied magnetic field strength is utilized. Without magnetic reagent, only a small amount of ash can be removed. The best separation is achieved at 3 lbs/ton magnetic reagent dosage. Further increase in magnetic reagent dosage results in serious loss of coal recovery, although the extent of ash reduction is improved. Each dosage test includes separations at three periods of retention time, which are 1, 2, and 3 seconds. All of the results are shown in Figure 3.

The effects of magnetic reagent dosage for Illinois No. 6 coal at 90% passing -200 mesh particle size have been studied at five dosage levels: 0, 4, 6, 8, and 10 pounds per ton of coal. Experiments were carried out with coarse screen matrix under 10 kilogauss applied magnetic field strength for 1, 2, and 3 seconds of retention time. Figure 4 shows the results. Without magnetic reagent, poor separation with very little ash reduction

was obtained. When magnetic reagent was added, separation results under different conditions generally form a curve. The optimum dosage can thus be selected freely based on the extent of coal cleaning required.

Magnetic reagent dosage for Lower Kittanning coal and Pocahontas coal at 48 mesh and 200 mesh particle sizes has been studied using the same experimental procedures. The results agree closely with that of the Illinois No. 6 coal. Figure 5 shows the dosage effect for the Lower Kittanning -48 mesh coal. Good separation can again be obtained with about 3 lb/ton reagent. Higher dosage, however, improves the separation slightly. Figure 6 shows the results of Lower Kittanning coal at 90% passing 200 mesh. Drastic improvements in separation after adding magnetic reagent are again observed. A dosage of less than 4 lb/ton is probably sufficient. Figure 7 demonstrates the results for the Pocahontas coal at -48 mesh. The extremely high ash content (32%) in this coal does not change the nature of the magnetic reagent approach. Improvements in coal cleaning with the addition of magnetic reagent is still obvious. Figure 8 shows the results for Pocahontas coal at 90% passing 200 mesh. Reduction of ash content from 32% to about 3% can be obtained.

Magnetic Field Strength. One advantage that the magnetic reagent approach can offer is the capability to conduct magnetic separation at low magnetic field strength. Magnetic separation at low magnetic field strength has benefits of low capital costs and

low energy consumption (low operation cost). Matrix materials are usually saturated at about 6 kilogauss of applied magnetic field strength. Conventional magnetic separation frequently requires higher magnetic field strength in order to increase the magnetization of desired particles. However, the energy consumption for magnetic field higher than 8 kilogauss increases exponentially. The amounts of coil materials and the cooling of coils are additional. Thus, high intensity magnetic separation is not favored in many applications. Since magnetic reagent can yield strong particle magnetization at low magnetic field strength, new applications become possible.

Experiments to determine the effects of magnetic field strength on separation after the addition of magnetic reagent have been conducted in this period. The range of field intensity in this study is from 2 to 10 kilogauss, which is much lower than the conventional approach. The conventional approach frequently utilizes magnetic field strengths up to 20 or 50 kilogauss. Figure 9 shows the separation results of Illinois No. 6 coal at -48 mesh. Significant ash reduction can be observed even at 2 kilogauss. Above 5 kilogauss, separation results are almost identical in all retention time. Figure 10 displays the results for Illinois No. 6 coal at 90% passing 200 mesh. Again, the difference among the separation results at 6, 8, and 10 kilogauss is very small. Figure 11 and Figure 12 demonstrates the results for Lower Kittanning coal at -48 mesh and -200 mesh, respectively. Figure 13 and Figure 14 are for Pocahontas coal at -48 mesh and -200 mesh,

respectively. Consistently, all of the results show that effective separation can be readily achieved at about 6 kilogauss. Further increase of the magnetic field intensity is unnecessary when magnetic reagent is utilized.

Figure 1.

Figure 2.

Figure 3.

Figure 4.

Figure 5.

Figure 6.

Figure 7.

**Reagent Dosage Effect
Pocanhontas -48 mesh
Ball Matrix; 10 K. Gauss**

MR Dosage (lb/t) 0.0 3.0 5.0 10.0
 □ △ ○ *

Figure 8.

Figure 9.

Figure 10.

Figure 11.

Figure 12.

Figure 13.

**Field Strength Effect
Pocahontas -48 mesh
Ball; MR 10 lb/t**

Figure 14.

END

**DATE
FILMED
8 / 19 / 92**