NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DOE/PC/88856-T3

DOE/PC/88856--T3

DE92 016136

Quarterly Technical Progress Report No. 3

For Period

August 1, 1988 thru October 31, 1988

SURFACE MAGNETIC ENHANCEMENT FOR COAL CLEANING

Submitted to

U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

3

Contract Number: DE-AC22-88PC88856

Technical Program Officer: McMahan L. Gray

Prepared by:

Project Manager

Tom E. Scott
Director

Principal Investigator

J.Y. Hwang
Sr. Research Scientist

Institute of Materials Processing
Michigan Technological University
Houghton, Michigan 49931

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SUMMARY AND FUTURE WORK

The progress achieved during this quarter includes the reagent shelf life study, the evaluation and selection of magnetizing reagents, an experimental database for activating and depressing the adsorption of magnetizing reagents in the presence of various chemicals, an adsorption regulator investigation, the establishment of a coal surface controlling theory, and a magnetite size effect study for the separation of magnetic enhanced minerals. The work is on schedule with the original plan. Modifications include the addition of a regulator study to help proving the selectivity controlling theory.

The fundamentals for applying the magnetizing reagent technology on coal cleaning are generally established during this quarter. Selective magnetic enhancement of minerals through the adsorption of magnetizing reagents has been experimentally proved. The work for the next quarter will be mainly on optimizing the selective adsorption conditions and the continuation on magnetite size effect study.

INTRODUCTION

This research is formulated for coal cleaning by enhancing the magnetic properties of minerals in coal. The enhancement is achieved through the adsorption of "magnetizing reagents" --- recently developed at Michigan Tech --- on the surface of minerals. The objectives of the research are: (i) to define the conditions for optimal selectivity and magnetic property enhancement of minerals by magnetizing reagents; (ii) to determine the effect of such magnetic enhancement on the efficiency of coal cleaning by magnetic separations; and (iii) to evaluate where this method can be adapted to existing coal preparation process schemes to achieve maximum effectiveness.

Three phases of work are included in this research: a fundamental study, an application study, and an industrial laboratory study. The fundamental study investigates the basic chemistry involved in the interactions of magnetizing reagents and minerals. The work performed during this reporting period is part of the fundamental study, which includes the preparation of magnetizing reagents (Task 1), mineral-reagent interactions (Task 2), magnetite size effect (Task 3), and Phase I Data Evaluation (Task 4). The progress in these tasks is reported below.

PROGRESS BY WORK BREAKDOWN STRUCTURE

Task 1. Magnetizing Reagent Preparation.

Reagent Preparation.

Thirty five magnetizing reagents with various surfactant functional groups have been prepared for this study. These reagents have been

described in the Quarterly Technical Report No. 2. This work will use the same MR-number designated in that report for these reagents.

Shelf Life of Reagents.

Five magnetizing reagents, selected from different cationic, anionic, and nonionic categories, were investigated for their activities at various shelf age. The activity was determined by the magnetic susceptibility enhancement of calcite after the interactions of magnetizing reagents and calcite at various pHs. Calcite is utilized for this experiment because of its stability to oxidation and good adsorbability at the reaction conditions. The results are shown in Table 1. For all of the five magnetizing reagents, there is no significant change of the activity in the seven month period of study. Slight increase in activity was found in four of the five reagents. Only one reagent shows a slight decrease in activity. Therefore, it is concluded that the magnetizing reagents are basically stable for long term use.

Task 2. Mineral/Reagent Interactions.

Mineral Preparation.

Research grade mineral samples of pyrite, kaolinite, calcite, and quartz were prepared by washing and grinding to -325 mesh. The procedures of preparation to avoid magnetic contamination and oxidation have been described in the previous report.

Selection of Reagent Dosage.

Magnetizing reagent dosage for standard mineral/reagent interaction tests was determined by the experiments in the previous quarter. The dosage was selected at 0.002 g magnetite per gram of mineral. This dosage was still utilized for the standard tests in this quarter.

Effect of pH on Mineral/Reagent Interactions.

Experiments to establish the pH effect on the interactions of minerals and coals with the thirty five magnetizing reagents were completed in the last quarter. The results have been documented in the previous report. Many magnetizing reagents were found capable to increase the magnetic susceptibilities of minerals over a wide pH range. However, these reagents also show strong reactivity with coal. To achieve selective adsorption of magnetizing reagents on minerals, coal depressant and mineral activator have to be identified. A major part of the effort during this quarter was to investigate the coal depressant and mineral activator effects.

Selection of Magnetizing Reagent.

It was proposed in the Test Plan to select eight magnetizing reagents for activator study and six magnetizing reagents for depressant study. Since there are many promising magnetizing reagents found from the pH effect study, the selection process becomes a difficult issue. The method to select the reagents in this study includes the considerations on pH, the extent of magnetic enhancement on minerals (especially pyrite), and the functional group of magnetizing reagents. Because pH is not a very strong factor to control the adsorption of magnetizing reagents on most coal-associated minerals and it is preferable to process coal at a near neutral pH, the first step of this selection is to compare all of the magnetizing reagents on the basis of their performance at pH 7. As shown in Table 2, the enhanced magnetic susceptibilities of minerals and coal by reacting with various magnetizing reagents at pH 7 were listed. Those magnetizing reagents which were effective on pyrite were picked. Then, the magnetizing reagents with the same or similar functional group were examined to select the one which was most effective on all the minerals. Four anionic (MR-30,

MR-60, MR-33, MR-58), three cationic (MR-1, MR-3, MR-89), and two nonionic (MR-45, MR-73) magnetizing reagents were selected from this process. MR-30 and MR-60 are actually with the same functional group. This duplication is utilized to assure that the trend of reaction is determined by the functional group.

Activator Investigation.

It is well known that inorganic salts can modify the surface charge and surface species of minerals. This modification process is also pH related. These effects were investigated to determine if minerals can be activated to the magnetizing reagent adsorption through the surface modification process. Two cationic salts, ferrous sulfate and calcium chloride, and two anionic salts, sodium silicate and sodium tripolyphosphate (STPP), were utilized as the surface modifying chemicals. The dosage of each salt was fixed at 300 ppm in solution. After conditioning the minerals in solution at a pH, magnetizing reagent was added. The treated minerals were then filtered, dried, and analyzed for magnetic susceptibility. The results are demonstrated in Table 3.

As predicted, cationic salts activate the adsorption of anionic magnetizing reagents on minerals. Anionic salts generally depress the minerals from the adsorption of anionic magnetizing reagents. The extents of activation and depression are specifically related to the individual chemical and mineral system. For example, sodium silicate strongly depress the silicate minerals (quartz and kaolinite) but it is less or not effective on calcite and pyrite. The unexpected is that coal is activated and depressed by the inorganic salts along with the same trend of minerals. For example, coal can be activated to adsorb MR-30 by ferrous and calcium ions but it can also be depressed from MR-30 adsorption by sodium silicate and

sodium tripolyphosphate. From this point, coal behaves in a similar way as the clays.

For the cationic magnetizing reagent, the adsorption on minerals is expected to be activated by the anionic salt and be depressed by the cationic salt from the electrokinetic theory. The experimental results indicate that this is only partially true. For example, sodium silicate may activate the adsorption of MR-3 on minerals but depress the adsorption of MR-1 on quartz and kaolinite. Ferrous sulfate depress calcite and pyrite for MR-3 but show little or no activation effect on the two minerals for MR-1. Sodium tripolyphosphate depress pyrite significantly from the adsorption of MR-1 and MR-3. From the tripolyphosphate test, coal behaves somewhat similar to pyrite.

Based on the nonionic magnetizing reagents, coal again shows a property similar to the mixture of kaolinite, pyrite, and calcite. Coal is well activated at the presence of calcium and ferrous ions. On the other hand, coal is depressed when the metals of minerals are at the depressed state (e.g. calcium of calcite, aluminum of kaolinite, and iron of pyrite).

Depressant Investigation.

After screening a large number of chemicals, five coal depressants were selected for this study. They are: humic acid, sodium sulfide, lignin sulfonate, dextrin, Aero 633 of American Cyanamid, and molasses. Coal was first conditioned in a solution of these chemicals. Then magnetizing reagent was added to the slurry with stirring. After the treatment, coal was filtered, dried, and measured for magnetic susceptibility. Minerals were tested under the same procedures when necessary.

Table 4 shows the results of humic acid. This chemical apparently can depress coal from adsorbing all types of magnetizing reagent, although it is

more effective on anionic and nonionic types than on cationic type, especially at low pH. Quartz and kaolinite are also strongly depressed by the humic acid. Pyrite and calcite begin to be depressed at high pH. Apparently the existing theory can hardly explain all of these phenomena. For example, coal is a hydrophobic material. The adsorption of humic acid will modify the surface to more hydrophillic. In addition, the carboxylic group of humic acid can strongly interact with the amines. Thus the humic acid should activate the adsorption of hydrophillic cationic magnetizing reagents, which is contrary to the experimental results.

A dosage experiment was conducted to determine if a significant magnetizing reagent adsorption selectivity can be obtained at various humic acid dosages. The results of magnetic susceptibility measurements are demonstrated in Table 5. For each 0.05 ml dosage of 2% humic acid in 30 ml deionized water, the solution contains about 33 ppm humic acid. In terms of the chemical/solid ratio, this is equivalent to 2 lb/ton. The results show that the optimum dosage of humic acid to depress coal is different for each magnetizing reagent. Pyrite is rarely affected by the humic acid. The selectivity between the two is significant. Kaolinite and calcite are both depressed to some degrees. MR-1 and MR-60 may be the favorable candidates for separation tests.

The results of utilizing sodium sulfide to depress coal are shown in Table 6. The trend of magnetizing reagent/coal interactions in the presence of sodium sulfide is basically the same as in the presence of humic acid. Sodium sulfide is unstable at pH below 7 by forming H_2S or elemental sulfur. Therefore, comparison can only be made at pH 7 or higher. At these pHs, all types of magnetizing reagents were again depressed from the adsorption on coal. Reaction of dilute sodium sulfide with organics at room

temperature can hardly be believed as a reason to cause these depressing effects, especially to the cationic magnetizing reagents.

The selectivity of magnetizing reagent adsorption between minerals and coal is quite significant in the presence of sodium sulfide. As shown in Table 6, minerals are not depressed at all. If this selectivity holds under the plant operation conditions, clean separation between coal and minerals can be expected. To prove that sodium sulfide is such an ideal reagent, it is also necessary to determine that sodium sulfide will not increase the sulfur content of coal.

The dosage of sodium sulfide is another issue of concern. As shown in Table 7, it is necessary to use about 10 lb/ton of sodium sulfide to reach the coal depressing state. Although sodium sulfide is a cheap chemical, this dosage is still rather large. In addition, this dosage is only representative to the DI water condition. If tap water is utilized and if the pyrite in coal has been seriously oxidized, the dosage can be much higher.

Sodium lignosulfonate can depress coal (see Table 7) in exactly the same fashion as the previous two coal depressants. Unfortunately, large dosage is still required (about 5 lb/ton). Calcite, quartz, and kaolinite are also depressed at the same time, as shown in Table 8. Since lignosulfonate can be adsorbed on coal, the large dosage will inevitably increase the organic sulfur content of coal. Therefore, this coal depressant will not be seriously considered in the future.

Dextrin is a compound identified useful in the reverse flotation of pyrite. Our preliminary tests showed that very large amount of dosage was required to depress coal from magnetizing reagent adsorption. The experimental results at 80 lb/ton of dextrin dosage are reported in

Table 9. This chemical shows that it can selectively depress coal. Minerals are depressed by dextrin only at very high pHs (near 11), probably through the adsorption of hydrolysis product of dextrin. Using MR-3 and dextrin at pH 5 to 7 may yield promising separation. But the economics of dextrin may be a problem.

Depressing coal by Aero 633 is effective at about pH 9, as shown in Table 10. Cationic magnetizing reagents are less affected. Clay and calcite are partially depressed by Aero 633, too. A dosage of about 10 lb/ton is required. This reagent is not the ideal coal depressant, but it is still worth consideration.

Molasses can depress coal more effectively than dextrin, as shown in Table 11. Probably the dyestuff in molasses is more effective than the carbohydrates. The depressing occurs in a wide pH range. Minerals are generally not affected. Good separation selectivity is thus very possible. The dosage requirement is in the range of 20 to 50 lb/ton. Therefore, the economics will be a critical issue.

Regulator Investigation.

The regulator investigations were not included in the original Test Plan. This study was performed since some fundamental problems on the coal surface property needed to be answered. We believe that the knowledge on these fundamental coal properties will open the door for the development of the most effective coal cleaning method.

A hypothesis was developed on the basis of the results of mineral activator and coal depressant investigations. This hypothesis assumes that there is no or very little direct interaction between the coal surface and the functional group of magnetizing reagent (or surfactant). All of adsorptions of magnetizing reagent on coal are thru indirect way. The

indirect adsorption is achieved with a bridge, which is metal ion or its hydroxyls. When the hydrophobic coal is immersed in water, large amounts of ions may be concentrated at the interface to reduce the interfacial surface energy. Thus, a bridge for the adsorption of magnetizing reagent (or surfactant) at the functional group end is formed. Since coal contains a lot of soluble mineral matters, such as calcite and iron salts (from oxidized pyrite), the supply of metal ions will not be deficient. If the divalent or multivalent metal species can be removed from the interface, coal should be depressed. Monovalent metal ions, such as sodium, is not surface potential determining species and, thus, will not serve as the bridge. The anionic ions will not react with the functional group.

If this hypothesis is true, then it is possible to control the adsorption by controlling the bridge. Three regulators are utilized to testify this hypothesis. They are: sodium pyrophosphate (SPP), trisodium phosphate, and sodium carbonate. Sodium pyrophosphate forms complexes or precipitates with most metal ions. Trisodium phosphate and sodium carbonate can also precipitate most metal ions. However, the dissociation constants of the three regulators are different. It is expected that a solution may have the least amount of free metal ions in the presence of sodium pyrophosphate and have the highest amount of free metal ions in the presence of sodium carbonate. Therefore, the coal depressing effect should be sodium pyrophosphate > trisodium phosphate > sodium carbonate. Silicon is the only metal of significant content in coal which will not react with these regulators. However, silicon is only reactive to the cationic surfactants. Therefore, only the adsorption of cationic magnetizing reagents may deviate from the proposed trend.

The experimental results are shown in Table 12. For the anionic and nonionic magnetizing reagents, the depressing trend at the presence of

regulators is almost identical with the prediction of our hypothesis. The depressing effect on cationic magnetizing reagent appears at high pHs where the regulators are most reactive with the metal ions.

Task 3. Magnetite Size Effect.

The objective of the magnetite size effect study is to reduce the surfactant consumption by increasing the magnetite size of magnetizing reagent. The surfactant cost may constitute the major portion of the total magnetizing reagent cost. However, the increase of magnetite size may reduce the collision rate between the magnetizing reagent and mineral and may cause unhomogeneous adsorption of magnetizing reagent on mineral. Experiments were performed to determine the optimum magnetite size.

Four magnetizing reagents, designated as MR58-11, MR58-12, MR58-13, and MR58-14, were prepared. The average magnetite sizes of these reagents were expected to be 100, 159, 191, and 252 Angstroms, respectively. However, the real magnetite size has to be determined under the TEM (Transmitted Electron Microscope). Several TEMs located at the MTU and the JEOL Inc. have been utilized for the determination, but no conclusive results have been obtained. Indirect evidence from the surfactant consumption, as shown in Table 13, shows that the magnetite size has been increased by our crystal growth technology. The surfactant consumption can be reduced to about half of the original magnetizing reagent. Further reduction of the surfactant consumption has not been achieved.

To determine whether the magnetite size would change the magnetic separation performance, a series of magnetic separation tests was conducted. In each test, calcite was conditioned with a magnetizing reagent at pH 7 for two minutes. Then the slurry was fed through a magnetic separator with ball matrix. The speed valve control was fully open to allow

the maximum flow speed (near free falling). The magnetic and nonmagnetic fractions were then collected, filtered, dried, and weighed to determine the weight percentage of calcite reported to the magnetic fraction. The results are also shown in Table 13. When the dosage of magnetite is 6 pounds per ton of calcite (probably 1.2 lb per ton of coal if coal contains 20% calcite), a magnetic field strength at as low as 2 kilogauss may collect 96% calcite using MR58-11. Magnetizing reagents with larger magnetite cause a decrease of magnetic collection at the same field. When the magnetic field strength increases, the magnetic collection rate increases, too. This indicates that there is probably an unhomogeneous adsorption at large magnetite size. Table 13 also shows the results of calcite collection at various magnetite dosages. These tests demonstrate that the 6 lb/ton dosage may be appropriate. MR58-11 and MR58-12 may compete with each other at the same cost range. The cost advantage of MR58-13 and MR58-14 may not compensate the technical performance.

Task 4. Data Evaluation.

All data generated from Task 1 through Task 3 has been examined in detail. The evaluation results, including the reagents and conditions selection and fundamental discussions, have been described in the previous sections.

CONCLUSIONS AND RECOMMENDATIONS

The fundamentals for applying the magnetizing reagent technology on coal cleaning are generally established during this quarter. Several conditions which can provide selective magnetic enhancement for minerals in coal have been identified. From the activator and depressant studies, a

theory for controlling the selectivity on the basis of coal surface chemistry was developed. A regulator study was added to this project to help prove this theory, since this action may lead to the development of ideal separation conditions for this project.

Magnetizing reagent was found a very effective tool for investigating the coal surface properties. It may have a lot of potential on determining the true surface behavior of coal in water. However, this is beyond the scope of this study.

Table 1. Enhanced magnetic susceptibility of calcite by fresh and aged magnetizing reagent.

		AGE	FRESH	7 MONTHS
MR-1	pH	5	51.3	73.9
	pH	7	50.9	57.9
	pH	9	55.6	57.6
	pH	11	51.2	52.9
MR-3	pH	5	49.9	73.6
	pH	7	47.4	54.0
	pH	9	49.6	52.2
	pH	11	49.0	53.2
MR-30	pH	5	38.0	59.3
	pH	7	35.4	44.4
	pH	9	36.7	41.7
	pH	11	35.3	42.4
MR-45	pH	5	56.4	63.5
	pH	7	47.4	49.6
	pH	9	45.7	51.4
	pH	11	45.0	50.8
MR-52	pH	5	65.5	56.2
	pH	7	60.6	45.1
	pH	9	60.1	45.2
	pH	11	59.2	42.0

Table 2. Magnetic enhancement of minerals and coal by various magnetizing reagents at pH 7.

Changed Magnetic Susceptibility at pH=7

Reagent #	Type	Calcite	Quartz	Kaolin	Pyrite	Coal
MR-33	A	40.2	4.5	39.9	39.6	43.3
MR-53	A	31.7	1.8	36.0	32.7	44.1
MR-60	A	16.9	5.8	24.1	16.3	21.1
MR-53	A	60.6	62.6	64.5	75.7	62.0
MR-20	A	33.4	1.2	30.5	36.4	40.5
MR-35	A	43.4	0.3	39.9	43.2	44.0
MR-27	A	35.3	12.6	42.3	38.1	39.0
MR-31	A	37.2	0.1	40.9	37.0	40.2
MR-55	A	45.4	44.1	44.7	45.4	39.8
MR-59	A	9.2	1.6	11.0	3.6	9.5
MR-61	A	20.1	2.2	31.0	32.1	18.0
MR-90	A	38.3	34.1	41.9	33.4	52.9
MR-60	A	58.9	4.9	58.9	57.2	63.0
MR-83	A	44.6	1.3	45.8	47.6	50.8
MR-01	C	50.9	50.4	54.9	43.1	53.1
MR-80	C	36.6	32.9	40.2	40.6	35.9
MR-06	C	25.6	25.4	32.8	31.5	17.0
MR-07	C	22.1	24.7	30.7	23.0	23.1
MR-19	C	25.0	25.2	29.1	24.4	31.0
MR-20	C	23.9	24.4	31.1	24.1	35.0
MR-5	C	11.9	9.2	14.8	10.4	13.0
MR-03	C	42.4	44.3	47.0	52.3	42.5
MR-06	C	16.4	18.9	13.6	20.0	22.1
MR-04	C	36.5	40.8	41.1	38.6	41.8
MR-1	C	47.0	40.9	33.4	32.1	31.1
MR-99	C	47.1	47.5	49.2	57.0	32.3
MR-74	N	21.6	24.1	23.3	35.7	18.1
MR-77	N	13.9	14.1	17.5	15.3	21.9
MR-45	N	47.4	27.6	49.5	49.1	60.0
MR-73	N	29.3	31.9	37.6	36.9	37.1
MR-48	N	43.9	1.6	44.0	46.6	42.0
MR-22	I	13.5	17.5	22.5	22.3	22.8
MR-50	I	36.7	0.0	41.5	32.5	33.1
MR-51	N	25.3	17.2	32.2	35.5	40.1
MR-16	I	19.1	31.9	40.6	34.4	23.0

A Anionic magnetizing reagents
 C Cationic magnetizing reagents
 N Nonionic magnetizing reagents

Table 3. Magnetic susceptibility of minerals and coal in the presence of activator and magnetizing reagent.

MR-30

	pH	0.0	FeSO ₄	CaCl ₂	NaSiO ₃	STPP
Calcite	3.0					
	5.0	53.0	70.1	84.9	52.6	59.2
	7.0	55.4	55.3	60.7	51.1	22.7
	9.0	36.7	63.3	60.0	41.8	6.7
	11.0	35.3	64.1	22.6	42.2	6.2
Quartz	3.0	26.6	56.5	69.8	33.8	18.8
	5.0	3.0	53.7	36.2	1.6	0.9
	7.0	1.2	59.6	41.5	0.5	0.4
	9.0	0.8	43.6	73.9	0.3	0.4
	11.0	17.5	18.8	80.6	0.7	0.6
Halite	3.0	35.8	74.3	43.3	56.2	45.5
	5.0	36.6	53.2	31.3	48.8	8.5
	7.0	37.5	57.3	47.3	25.6	8.7
	9.0	25.4	60.9	44.9	3.9	6.2
	11.0	34.7	55.9	55.2	6.4	6.7
Pyrite	3.0	34.7	60.0	48.8	50.2	49.2
	5.0	32.2	51.3	44.3	52.6	56.2
	7.0	36.4	55.6	43.2	52.5	42.9
	9.0	34.3	36.4	47.0	52.5	4.4
	11.0	37.9	97.2	47.2	44.9	2.5
Coal	3.0	18.4	52.2	51.6	37.5	33.2
	5.0	31.5	61.7	60.9	57.9	24.9
	7.0	40.5	64.5	57.4	3.5	3.2
	9.0	27.9	65.0	55.7	2.3	2.7
	11.0	22.3	3.3	50.0	1.7	1.2

Table 3 continued.

MR-60

	pH	O ₂	FeSO ₄	CaCl ₂	NaSiO ₃	STPP
Calcite	3.0					
	5.0	59.4	83.7	78.9	72.4	74.1
	7.0	58.9	77.6	76.2	57.0	70.6
	9.0	61.7	84.6	75.7	53.0	9.1
	11.0	59.0	86.3	76.7	40.1	9.3
Quartz	3.0	56.0	67.5	76.6	56.8	64.4
	5.0	7.6	79.4	50.1	2.8	1.2
	7.0	4.9	73.9	76.6	0.7	0.4
	9.0	31.5	69.2	73.8	0.8	.0
	11.0	58.8	23.4	62.8	0.6	0.3
Feldspar	3.0	60.9	63.3	76.1	92.0	53.5
	5.0	50.2	58.3	78.9	61.5	6.6
	7.0	53.4	94.4	71.1	21.0	7.1
	9.0	46.3	57.3	75.1	9.5	9.8
	11.0	59.6	60.9	68.0	9.7	9.6
Pyrite	3.0	46.4	66.0	72.7	79.3	62.4
	5.0	55.2	77.0	69.6	65.5	73.7
	7.0	57.3	75.3	73.6	93.1	49.6
	9.0	60.0	76.2	67.5	81.3	3.4
	11.0	67.5	94.6	84.0	96.1	45.5
Glauber	3.0	61.7	43.3	81.1	56.5	66.2
	5.0	63.2	75.6	64.0	80.5	8.3
	7.0	63.0	35.8	62.9	3.1	9.4
	9.0	65.6	75.0	72.1	7.9	3.2
	11.0	52.6	37.8	63.3	4.0	1.3

Table 3 continued.

MR-58						
	pH	0.0	FeSO ₄	CaCl ₂	Na ₂ SiO ₃	STPP
Calcite	3.0					
	5.0	65.5	56.9	41.2	46.6	46.2
	7.0	60.6	52.8	32.5	45.4	35.0
	9.0	66.1	48.5	30.5	40.2	17.0
	11.0	59.8	48.3	34.5	13.6	17.2
Quartz	3.0	60.2	37.5	35.9	42.6	7.2
	5.0	61.4	41.6	38.3	29.4	4.5
	7.0	62.6	46.3	32.7	4.7	2.6
	9.0	58.6	37.9	40.7	1.9	2.5
	11.0	59.3	39.9	41.2	3.0	2.4
Kearf	3.0	65.3	41.2	39.4	59.1	44.3
	5.0	56.0	48.9	40.7	56.9	27.3
	7.0	64.3	43.6	44.3	52.5	11.3
	9.0	66.6	53.8	42.1	31.6	11.1
	11.0	62.7	44.1	44.0	19.7	13.3
Pyrite	3.0	45.3	55.3	45.3	48.0	29.3
	5.0	69.8	44.2	52.1	44.0	42.7
	7.0	75.7	44.5	55.8	54.2	41.3
	9.0	69.0	42.7	57.8	51.7	21.3
	11.0	78.1	41.3	56.1	47.7	14.3
Oxal	3.0	65.7	39.3	50.2	45.5	21.1
	5.0	65.1	60.3	52.8	44.4	31.2
	7.0	62.0	42.3	56.0	45.9	21.7
	9.0	61.0	47.5	52.1	2.5	21.6
	11.0	61.4	41.4	48.3	2.5	21.5

Table 3 continued.

MR-33

	pH	ClO	FeSO ₄	CaCl ₂	NaSiO ₃	ETAP
Calcite	3.0					
	5.0	44.1	53.2	51.9	39.0	30.5
	7.0	40.2	57.0	49.2	35.3	8.5
	9.0	39.4	53.9	47.5	11.9	7.9
	11.0	38.1	52.8	47.6	9.3	6.1
Quartz	3.0	20.1	31.2	32.1	23.5	19.8
	5.0	45.6	13.9	24.7	7.7	6.7
	7.0	4.5	39.0	22.6	5.6	6.8
	9.0	3.5	4.7	2.0	6.7	1.0
	11.0	2.3	6.4	19.0	2.2	0.4
Naolite	3.0	38.9	42.4	50.7	46.3	39.2
	5.0	35.2	50.1	41.7	33.5	6.9
	7.0	37.7	53.7	53.3	28.6	11.6
	9.0	29.1	26.7	22.3	10.2	11.2
	11.0	25.2	34.1	17.8	18.0	12.3
Pyrite	3.0	51.8	40.7	41.4	40.7	43.4
	5.0	34.9	31.3	53.6	45.5	21.6
	7.0	31.6	52.7	53.1	50.5	11.1
	9.0	34.7	37.2	53.2	47.2	2.3
	11.0	25.4	101.9	57.7	43.1	5.2
Coal	3.0	42.9	52.0	51.7	38.6	38.1
	5.0	27.2	57.5	52.1	45.1	14.5
	7.0	48.5	34.1	54.2	25.8	5.3
	9.0	14.6	10.7	26.6	20.5	3.1
	11.0	15.8	15.2	29.4	19.3	4.5

Table 3 continued.

MR-02

	pH	0.0	FeSO4	CaCl2	NaSiO3	STPS
Calcite	3.0					
	5.0	49.9	10.2	56.0	70.3	52.4
	7.0	47.4	14.2	46.4	51.1	53.3
	9.0	49.6	10.1	46.5	53.0	47.6
	11.0	49.0	23.0	47.3	45.1	44.9
Quartz	3.0	37.4	55.8	45.8	49.9	50.4
	5.0	45.1	51.9	52.6	52.3	50.6
	7.0	44.3	46.6	46.7	55.0	56.0
	9.0	41.3	53.5	51.6	46.3	42.7
	11.0	42.3	50.1	53.2	50.2	46.4
Selenite	3.0	46.3	46.5	50.4	50.3	42.2
	5.0	46.1	60.2	54.2	62.4	26.2
	7.0	47.0	33.2	52.5	30.5	41.1
	9.0	48.7	50.2	45.9	60.1	34.1
	11.0	39.0	58.2	59.0	56.0	41.3
Selenite	3.0	45.1	18.7	45.7	42.9	34.6
	5.0	44.9	20.9	55.4	49.1	31.5
	7.0	52.3	26.4	55.8	60.3	37.4
	9.0	59.7	30.7	60.2	53.2	30.4
	11.0	55.1	70.4	58.7	64.7	21.4
Cosi	3.0	52.0	42.3	52.4	46.6	52.2
	5.0	47.2	54.2	52.4	59.6	46.5
	7.0	52.6	49.0	53.2	57.9	16.6
	9.0	60.0	49.2	49.5	55.2	7.7
	11.0	52.1	25.2	61.6	30.4	30.4

Table 3 continued.

MR-B9

	pH	0.0	FeSO4	CaCl2	NaSiO3	STPP
Calcite	3.0					
	5.0	54.0	53.0	47.2	51.0	50.6
	7.0	47.4	52.0	53.9	50.6	37.0
	9.0	47.6	51.2	47.4	51.4	38.7
	11.0	47.9	46.5	46.1	48.6	17.8
Quartz	3.0	46.4	47.0	58.2	44.5	21.6
	5.0	41.3	53.1	48.6	48.7	10.6
	7.0	47.5	52.9	58.8	35.0	28.5
	9.0	48.5	43.3	50.4	28.0	32.3
	11.0	48.2	35.6	49.6	47.5	31.9
Kaolin	3.0	50.8	42.9	49.3	49.3	35.1
	5.0	51.6	49.7	24.7	32.4	10.9
	7.0	49.2	51.5	56.1	33.6	23.0
	9.0	52.3	77.6	48.1	34.2	21.4
	11.0	47.2	51.1	44.0	41.7	31.8
Pyrite	3.0	44.5	37.2	46.3	41.7	21.7
	5.0	53.7	38.2	58.5	52.2	29.7
	7.0	57.0	53.0	56.3	47.4	22.3
	9.0	50.5	62.7	56.2	49.5	23.2
	11.0	53.0	107.1	58.3	72.6	21.3
Coal	3.0	48.7	43.6	46.3	51.3	53.5
	5.0	54.3	44.7	54.7	61.3	60.7
	7.0	53.3	31.1	57.3	44.3	36.4
	9.0	57.4	51.8	60.4	34.0	42.3
	11.0	63.4	24.5	53.2	49.0	36.2

Table 3 continued.

MR-01

	pH	CaO	FeSO4	CaCl2	NaSiO3	STPP
Calcite	3.0					
	5.0	61.3	63.0	54.2	62.0	56.7
	7.0	50.9	62.5	59.9	52.7	51.3
	9.0	55.6	59.5	60.4	49.8	56.5
	11.0	51.2	57.1	57.1	53.3	40.9
Quartz	3.0	56.2	47.2	49.1	52.1	44.8
	5.0	53.1	56.6	53.2	7.5	53.0
	7.0	50.4	57.1	55.0	5.7	47.1
	9.0	47.0	53.9	53.8	4.6	15.0
	11.0	30.3	35.0	46.5	1.9	20.4
Naclite	3.0	50.0	56.7	52.1	47.5	36.6
	5.0	51.2	56.7	53.4	47.8	39.0
	7.0	54.0	57.2	51.5	46.6	33.7
	9.0	53.1	54.7	57.1	14.3	33.1
	11.0	43.2	57.5	55.7	19.9	24.5
Pyrite	3.0	41.8	53.3	51.4	42.5	36.7
	5.0	48.1	51.1	58.4	53.6	43.2
	7.0	48.5	53.0	41.8	59.7	41.4
	9.0	45.6	66.4	55.9	55.6	13.3
	11.0	24.6	96.1	57.1	33.9	16.6
Oxal	3.0	53.9	60.4	56.6	49.3	54.2
	5.0	61.3	67.9	54.3	64.3	53.5
	7.0	53.8	55.0	57.4	65.4	35.2
	9.0	60.9	69.3	73.5	41.9	7.8
	11.0	60.5	45.1	59.3	18.3	9.3

Table 3 continued.

MR-45

	pH	O.0	FeSO4	CaCl2	NaSiO3	STPP
Calcite	3.0					
	5.0	56.4	66.5	66.3	65.0	54.9
	7.0	47.4	63.0	67.5	52.9	9.4
	9.0	45.9	65.3	62.9	6.5	3.2
	11.0	46.0	65.9	66.7	6.1	5.2
Quartz	3.0	45.0	57.2	56.8	20.3	54.2
	5.0	44.5	63.0	50.5	1.9	50.3
	7.0	27.6	7.5	34.1	1.2	5.2
	9.0	0.4	1.9	5.7	0.7	0.3
	11.0	0.1	4.8	4.1	0.7	0.7
Feldspar	3.0	46.9	67.9	54.4	50.1	46.6
	5.0	46.7	75.0	53.0	51.2	47.2
	7.0	49.2	65.2	50.7	42.1	10.4
	9.0	36.3	54.2	42.2	6.0	3.0
	11.0	39.7	45.1	50.9	7.4	11.7
Fluorite	3.0	46.2	54.3	52.3	45.2	55.5
	5.0	49.7	50.1	56.5	56.2	54.7
	7.0	49.1	68.1	51.4	59.6	55.4
	9.0	39.1	61.7	61.3	56.2	11.3
	11.0	20.2	37.4	61.3	53.7	2.1
Goshite	3.0	52.2	52.2	62.1	59.3	54.2
	5.0	54.5	60.2	62.1	61.3	52.5
	7.0	50.2	68.9	71.9	66.7	32.7
	9.0	59.9	67.7	66.5	11.5	7.2
	11.0	56.8	53.3	75.7	42.2	6.1

Table 3 continued.

MR-73

	pH	ClO	FeSO4	CaCl2	NaSiO3	STPP
Calcite	3.0					
	5.0	33.5	55.0	56.3	60.4	55.8
	7.0	29.5	49.4	50.6	43.8	52.2
	9.0	34.2	45.9	45.6	47.4	52.7
	11.0	31.3	46.5	47.7	45.1	49.4
Quartz	3.0	27.5	43.0	42.7	42.6	42.5
	5.0	32.3	47.8	42.0	44.5	48.1
	7.0	31.9	48.1	42.4	41.4	47.4
	9.0	34.2	44.2	42.6	44.1	50.3
	11.0	27.7	40.9	42.1	34.3	44.3
Feldspar	3.0	36.5	44.5	40.3	46.5	37.2
	5.0	33.7	43.3	40.2	36.2	34.1
	7.0	37.5	52.5	44.1	32.3	36.4
	9.0	36.9	43.9	45.4	38.6	46.3
	11.0	32.4	47.8	48.8	45.1	32.3
Pyrite	3.0	35.6	40.2	40.8	41.7	45.3
	5.0	37.4	43.4	47.6	42.0	50.7
	7.0	38.9	52.5	53.0	34.3	33.5
	9.0	32.3	58.5	45.2	53.2	22.1
	11.0	35.2	117.3	51.3	31.0	38.7
Glauberite	3.0	20.3	42.1	42.5	45.1	45.4
	5.0	32.9	47.1	45.4	34.4	42.0
	7.0	33.1	49.0	50.8	52.1	13.3
	9.0	32.5	52.3	48.9	42.0	19.0
	11.0	32.5	22.2	45.8	34.1	30.9

Table 4. Magnetic susceptibility of minerals and coal
in the presence of humic acid and magnetizing
reagent.

Humic Acid Depressing Effect

	pH	Calcite	Quartz	Magnetite	Pyrite	Coal	Coal*
MR-50	3.0		1.6		51.0	32.5	65.7
	5.0	27.9	1.0	9.2	49.9	8.1	65.1
	7.0	25.1	0.4	9.5	46.7	7.0	62.0
	9.0	3.9	2.4	11.2	4.2	5.2	61.0
	11.0		1.2		11.9	4.0	61.4
MR-01	3.0					52.7	53.6
	5.0	42.0	9.1	11.9	51.1	54.9	61.5
	7.0	34.3	8.0	20.2	51.2	12.2	51.9
	9.0	1.1	3.7	22.4	41.7	7.6	50.9
	11.0					6.4	60.5
MR-30	3.0					46.0	48.7
	5.0					56.3	54.3
	7.0					13.3	52.3
	9.0					22.7	51.4
	11.0					10.3	63.4
MR-10	3.0					47.7	62.9
	5.0	39.5		9.2	46.6	7.2	57.3
	7.0	37.1		9.2	33.0	5.7	53.7
	9.0				3.2	4.0	51.6
	11.0					7.3	56.4
MR-48	3.0					29.0	52.9
	5.0	41.4	1.6	3.0	58.8	3.2	54.6
	7.0	22.4		6.4	61.9	5.9	60.2
	9.0				2.7	4.0	51.6
	11.0					4.3	56.1
MR-11	3.0			25.3	13.0	57.5	61.7
	5.0	43.4		7.3	57.0	23.4	53.2
	7.0	22.1		5.0	56.9	2.7	52.6
	9.0	1.5		5.5	1.2	2.7	65.6
	11.0	1.2		1.8	4.7	1.6	62.6
MR-30	3.0					24.1	53.4
	5.0	29.7		6.4	16.5	7.1	51.5
	7.0	23.4		7.4	39.3	1.7	40.3
	9.0				6.3	3.4	57.9
	11.0					2.2	52.3
MR-01	3.0					21.1	51.0
	5.0	41.6	9.2	13.9	49.0	10.0	47.2
	7.0	25.1	1.5	20.0	47.9	6.7	52.1
	9.0	6.1	5.8	22.2	24.7	9.3	50.0
	11.0					6.3	52.1

Table 5. The dosage effect of humic acid.

Total Magnesium Susceptibility at Different Humic Acid Dosage

Humic acid dosage (mg/L)	MF-01 pH 7	MF-02 pH 7	MF-45 pH 7	MF-08 pH 7	MF-50 pH 7	MF-10 pH 7	MF-11 pH 7
0.000	50.5	50.5	50.5	50.5	50.5	49.5	49.5
0.020			50.5	44.1	42.7	41.1	39.5
0.050	50.5	51.0	20.5	17.5	8.5	5.5	10.5
0.100	12.5	10.7	3.4	3.0	5.1	4.1	3.1
0.200	3.2	3	1.1	1.5	2.2	2.5	1.5
0.500	1.2	11.2	3.0	2.1	1.9	2.3	2.5
1.000	12.5	5.5	0.5	0.5	3.7	3.1	3.1

Mineral Magnesium Susceptibility at Different Humic Acid Dosage

Humic acid dosage (mg/L)	MF-01	MF-02	MF-45	MF-08	MF-50	MF-10	MF-11
0.000	0.15	0.21	0.10	0.10	0.05	0.03	0.12
0.020	0.15	0.14	0.1	0.1	0.1	0.1	0.1
0.050	0.1	0.1	0.1	0.1	0.1	0.1	0.1
0.100	0.1	0.1	0.1	0.1	0.1	0.1	0.1
0.200	0.1	0.1	0.1	0.1	0.1	0.1	0.1
0.500	0.1	0.1	0.1	0.1	0.1	0.1	0.1
1.000	0.1	0.1	0.1	0.1	0.1	0.1	0.1

Table 6. Magnetic susceptibility of minerals and coal in the presence of sodium sulfide and magnetizing reagent.

Sodium Sulfide Depressing Effect							
MF #2	pH	Calcite	Quartz	Kaolin	Pyrite	Coal	Clay *
	1.0		21.7	42.6	36.6	35.7	15.7
	5.0	40.1	36.3	37.2	42.6	31.0	36.1
	7.0	38.0	3.4	39.4	42.6	2.6	32.6
	9.0	33.2	36.3	36.9	42.6	2.0	61.0
	11.0	30.1	3.0	37.4	33.7	3.0	61.6
MF #30	3.0					13.2	11.4
	5.0					11.1	21.7
	7.0	35.1		40.3	13.0	2.1	10.5
	9.0					0.1	1.0
	11.0					1.1	21.0
MF #60	1.0					11.2	7.1
	5.0					41.1	11.0
	7.0	44.1		11.0	11.0	1.1	11.0
	9.0					1.1	2.1
	11.0					0.1	11.4
MF #120	1.0		11.0	31.3	11.0	11.0	11.0
	5.0	11.0	2.0	47.1	11.0	18.0	1.1
	7.0	40.0	2.6	11.1	10.7	11.1	18.0
	9.0	10.1	1.1	20.0	11.0	1.1	11.0
	11.0	13.1	3.0	11.0	20.5	1.0	21.0
MF #240	1.0		11.0	10.0	10.0	11.0	11.0
	5.0	50.0	1.0	10.0	11.0	41.0	11.0
	7.0	12.0	0.0	14.0	10.0	1.0	11.0
	9.0	40.4	0.0	11.0	32.0	1.0	11.0
	11.0	10.0	1.0	8.0	10.0	1.0	11.0
MF #480	1.0		10.0	11.0	10.0	11.0	12.0
	5.0	50.1	10.0	14.0	11.0	11.0	11.0
	7.0	56.0	0.1	50.0	56.3	1.1	51.2
	9.0	41.0	1.0	40.0	10.0	1.0	1.0
	11.0	53.0	0.8	22.5	27.7	1.0	51.0

Table 6 continued.

na Gulf de Cap-Henry Strait

	10	20	30	40	50	60	70
45-50	31.0		39.2	31.1	47.2	31.6	31.9
	31.1	31.0	44.0	41.2	57.1	31.1	31.2
	31.0	33.2	53.7	33.3	50.1	31.0	33.2
	31.0	61.6	50.1	39.0	30.1	30.0	50.1
	31.0	30.1	33.7	32.6	49.0	30.1	30.1
45-55	31.0		30.0	45.9	41.7	41.1	45.1
	31.0	55.0	47.2	31.3	31.8	41.6	34.1
	31.0	50.2	35.0	34.0	35.1	30.1	31.1
	31.0	50.0	53.2	32.3	37.5	31.0	37.4
	31.1	37.8	47.6	46.1	31.1	30.1	30.1
45-60	31.0					31.0	31.1
	31.1					31.1	31.1
	31.0					30.1	31.0
	31.0	31.1	30.1	31.1	30.1	31.1	31.1
	31.0					31.0	31.1

Gulf of Cap-Henry Strait using 100 percent

Table 7. The dosage effect of sodium sulfide.

Coal Magnetic Susceptibility at Different Sodium Sulfide Dosage

The results of the experiment are shown in Table 7. The results of the experiment are shown in Table 7.

Dosage (g)	MR-01 pH 2	MR-03 pH 9	MR-45 pH 7	MR-55 pH 7
0.00	50.3	50.0	50.2	50.0
0.05	50.4	49.0	50.0	49.0
0.50	11.2	3.1	13.5	24.3
1.00	10.0	11.0	6.5	2.5

Dosage g/l	MR-33 pH 7	MR-60 pH 7	MR-33 pH 7	MR-30 pH 7
0.00	50.3	50.0	43.5	40.5
0.05	50.2	40.5	23.5	13.5
0.10	1.0	13.1	0.5	0.0
1.00	1.0	3.6	0.5	2.5

Table 8. Magnetic susceptibility of minerals and coal in the presence of sodium lignosulfonate and magnetizing reagent.

Total magnetic susceptibility at different NaLig dosage
Using NaLig as Depressant

PH	MR-01	MR-03	MR-43	MR-53	MR-60	MR-73	MR-80
0.00	0.0	0.0	0.0	4.5	2.0	0.0	0.0
0.00	10.1	4.4	4.6	5.5	2.3	3.2	1.1
0.00	5.1	3.0	3.0	4.0	1.9	4.0	2.0

Total magnetic susceptibility at different NaLig dosage

Dosage	MR-01 PH-2	MR-03 PH-2	MR-43 PH-2	MR-53 PH-2	MR-60 PH-2	MR-73 PH-2	MR-80 PH-2
0.00	03.3	00.0	00.0	00.0	00.0	4.3	0.0
0.00	00.0	00.0	40.4	40.0	40.5	19.0	04.7
0.00	00.0	00.0	5.0	3.2	0.0	0.0	0.0
0.00	0.0	0.0	0.0	0.0	0.0	0.0	0.0
0.00	10.1	4.4	4.0	0.3	0.0	0.0	0.0

Table 9. Magnetic susceptibility at different NaLig dosage

Dosage	MR-01	MR-03	MR-43	MR-53	MR-60	MR-73	MR-80
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.00	00.0	00.0	00.7	40.0	00.0	0.0	00.0
0.00	00.0	0.1	0.0	0.0	0.0	0.0	0.0
0.00	00.0	00.4	00.0	00.0	00.4	00.0	00.0
0.00	00.0	00.0	00.0	40.0	00.0	00.0	00.0

Table 9. Magnetic susceptibility of minerals and coal in the presence of dextrin and magnetizing reagent.

Dextrin Deaggregating Effect

	MP	Calcite	Quartz	Wadlin	Synite	Coal	Coal
MR-01	3.0		52.4	50.3	51.0	59.5	55.5
	5.0	53.1	47.0	50.0	52.0	12.6	51.5
	7.0	54.6	52.5	55.4	50.3	23.4	51.2
	9.0	55.0	55.7	50.8	51.0	35.0	50.5
	11.0	57.9	52.1	23.7	23.7	11.4	50.5
MR-10	3.0		58.6	52.8	41.0	55.6	48.7
	5.0	51.1	53.8	53.4	47.0	15.1	54.0
	7.0	56.0	47.0	60.1	51.0	49.0	51.3
	9.0	54.1	37.2	43.6	53.0	35.7	51.1
	11.0	50.0	47.8	30.0	34.0	11.6	51.4
MR-13	3.0		45.5	46.3	47.8	13.7	52.0
	5.0	49.6	41.0	40.0	54.0	7.5	47.2
	7.0	44.6	45.3	44.0	61.0	11.0	50.5
	9.0	46.3	45.1	44.1	51.1	50.4	51.0
	11.0	18.0	37.2	39.1	45.5	14.0	52.1
MR-40	3.0		17.8	39.1	31.1	42.5	52.1
	5.0	52.2	18.0	43.3	30.3	52.0	54.2
	7.0	54.5	11.7	40.0	52.1	45.7	51.2
	9.0	23.0	30.1	13.1	41.1	12.0	50.1
	11.0	11.1	11.1	11.1	11.1	11.1	50.1
MR-30	3.0						18.1
	5.0					43.1	51.1
	7.0	11.0		5.0	41.0	12.2	50.5
	9.0					2.2	50.1
	11.0					5.2	52.1
MR-12	3.0		15.1	45.0	37.1	51.0	52.1
	5.0	40.1	11.1	35.7	42.7	41.3	51.1
	7.0	11.6	11.1	30.2	43.0	12.0	51.1
	9.0	11.0	11.0	11.0	39.9	11.5	54.5
	11.0	11.1	11.0	10.3	33.0	5.7	50.5
MR-15	3.0		35.3	41.0	40.2	34.4	51.7
	5.0	33.1	11.0	31.9	41.5	41.5	51.1
	7.0	30.0	3.0	34.6	37.4	30.4	51.0
	9.0	14.1	11.2	14.0	33.7	4.2	51.0
	11.0	9.2	11.6	9.4	31.0	2.7	51.4

Values are without dextrin deaggregant

Table 10. Magnetic susceptibility of minerals and coal in the presence of Aero 633 and magnetizing reagent.

Table 10. Magnetic susceptibility at pH 10. Present in
Aero 633 as Dispersant

pH	MR-01	MR-03	MR-45	MR-50	MR-55	MR-65	MR-80
1.0	58.3	45.0	31.5	40.3	55.0	22.0	30.0
2.0	22.0	31.0	30.1	45.0	22.0	2.1	24.0
3.0	25.7	20.0	5.1	19.0	6.2	0.9	3.0

Table 10. Magnetic susceptibility at different Aero 633 dosage

dosage (ml)	MR-01 pH 10	MR-03 pH 10	MR-45 pH 10	MR-50 pH 10	MR-55 pH 10	MR-65 pH 10	MR-80 pH 10
1.00	58.3	45.0	31.5	40.3	55.0	22.0	30.0
2.00	22.0	31.0	30.1	45.0	22.0	2.1	24.0
3.00	25.7	20.0	5.1	19.0	6.2	0.9	3.0
4.00	22.7	21.3	5.1	9.1	3.0	0.9	0.0

Table 10. Magnetic susceptibility at pH 10. Aero 633 1.0 ml

100.00	20.0	17.0	40.5	44.0	50.1	11.5	25.0
200.00	21.0	12.0	3.8	3.8	16.0	2.1	1.0
300.00	21.0	24.1	10.0	27.5	26.0	2.1	1.0
400.00	20.7	33.0	50.0	41.0	50.5	41.4	41.0

Table 11. Magnetic susceptibility of minerals and coal in the presence of molasses and magnetizing reagent.

Coal Magnetic Susceptibility at Different pH
Using Molasses as Depressant

pH	MF-01	MF-01	MF-40	MF-60	MF-80	MF-100	MF-300
5.0	41.0	21.9	34.5	3.2	3.6	3.1	4.6
7.0	9.2	7.7	14.2	3.0	4.0	2.1	4.6
9.0	12.1	9.6	13.8	2.6	2.9	4.6	2.3

Coal Magnetic Susceptibility at Different Molasses Dosage

Dosage (ml)	MF-01 pH 7	MF-01 pH 7	MF-40 pH 7	MF-60 pH 7	MF-80 pH 7	MF-100 pH 7	MF-300 pH 7
0.00	21.2	21.2	20.1	22.1	13.0	40.0	12.1
0.02	23.2	4.3		43.4	27.0	1.5	21.7
0.04	41.0	21.2		4.2	2.8	1.1	1.3
0.30	1.4	6.1		2.1	6.0	3.1	2.0
1.00	2.0	7.7	14.2	6.0	4.2	8.5	1.1

Coal Magnetic Susceptibility at Different Molasses Dosage at pH 7

Dosage	MF-01	MF-03	MF-18	MF-30	MF-33	MF-30
	1.00	0.00	0.25	0.01	0.10	1.2
1	41.0	30.8	45.1	34.6	34.2	22.3
2	9.2	7.2	1.2			
3	24.3	46.3	43.4	40.6	26.0	22.1
4	58.0	50.2	52.1	52.1	45.4	11.5

Table 12. Coal magnetic susceptibility in the presence of various regulators and magnetizing reagents.

Coal Regulator Test

	Type	0.0	0.0	3FF	MS2004	MS2003
MR-00	A	1.0	65.7	3.2	48.4	48.7
		5.0	65.1	3.7	31.9	43.3
		7.0	62.6	3.0	2.0	40.1
		9.0	61.0	2.8	1.8	50.9
		11.0	61.4	3.2	1.0	14.1
MR-00	A	1.0	61.7	69.0	42.1	41.3
		5.0	60.2	61.6	38.7	43.6
		7.0	63.0	0.3	4.7	11.1
		9.0	60.6	0.3	4.5	22.1
		11.0	58.3	0.4	5.3	15.2
MR-00	A	1.0	12.4	8.9	42.0	43.1
		5.0	3.5	19.0	34.0	40.8
		7.0	40.1	1.0	1.9	43.3
		9.0	37.0	1.2	1.0	26.1
		11.0	21.1	1.8	2.1	11.7
F-00		1.0	40.9	44.1	47.1	42.1
		5.0	1.1	19.6	43.0	51.2
		7.0	43.5	1.8	14.5	43.0
		9.0	1.6	3.7	10.5	11.4
		11.0	65.3	10.3	3.3	11.1
F-00		1.0	12.1	48.2	32.1	11.1
		5.0	14.3	47.2	49.3	16.1
		7.0	30.2	0.3	21.3	66.1
		9.0	29.9	0.9	0.4	16.1
		11.0	60.3	3.0	2.6	17.3

Table 12 continued.

Load Regulator Test

.2.

Type	PH	0.0	3PP	NA3P04	NA3P03
MR 01	3.0	55.0	41.0	51.6	50.1
	5.0	61.5	45.0	50.4	46.2
	7.0	63.8	29.7	39.7	61.3
	9.0	60.9	18.5	21.1	52.4
	11.0	60.6	23.2	12.6	71.0
MR 03	3.0	52.0	41.8	49.0	48.6
	5.0	47.2	44.0	46.3	51.5
	7.0	52.6	46.7	45.8	34.1
	9.0	60.0	12.6	16.3	49.8
	11.0	52.1	34.6	14.6	34.7
MR 04	3.0	40.1	31.9	23.1	52.6
	5.0	54.3	59.1	31.3	50.2
	7.0	61.2	61.4	21.1	41.1
	9.0	37.4	33.3	42.0	34.4
	11.0	11.4	14.1	11.1	11.1

A. Alkaline Reagent

B. Alkaline Reagent

C. Alkaline Reagent

Table 13. Magnetizing reagents with various magnetite sizes and their effects on magnetic separation at various magnetic field strengths.

Magnetite Size Effect on the Recovery of Calcite at Different Field Strength (Dosage Magnetite 5.0 lb/ton)

Field Strength (Gauss)	58-11	58-12	58-13	58-14
2000	96.20	91.48	93.85	95.71
3500	98.14	97.31	97.57	98.87
5000	99.97	98.99	97.60	98.93
3000	97.15	99.52	98.60	98.67

Magnetite Size Effect on the Recovery of Calcite at Different Dosage Field Strength 3500 Gauss

Dosage lb/ton	58-11	58-12	58-13	58-14
1.0	95.44	95.44	98.77	98.79
4.0	95.02	95.30	98.92	98.03
8.0	96.03	98.07	94.93	98.84
12.0	98.14	97.31	98.57	98.87

Magnetite Size Effect on the Recovery of Calcite at Different Dosage Field Strength 5000 Gauss

Dosage lb/ton	58-11	58-12	58-13	58-14
2.0	94.21	98.73	97.23	95.39
4.0	93.34	97.16	91.94	91.33
8.0	98.54	98.93	95.05	98.16
12.0	98.79	98.93	97.60	98.39

Surfactant
(g/g Mt)

Calculated Magnetite Size
Expect to Reach

58-11	0.364	100(A) reference
58-12	0.425	159(A)
58-13	0.497	131(A)
58-14	0.493	252(A)

END

**DATE
FILMED**

8 / 24 / 92