RESONANCE RAMAN AND PHOTOPHYSICAL STUDIES OF
TRANSITION METAL COMPLEXES IN SOLUTION AND
ENTRAPPED IN ZEOLITES

Progress Report
for Period Aug. 1, 1991 - Mar. 31, 1992

James R. Kincaid

Chemistry Department
Marquette University
Milwaukee, WI 53233

Report Date: Mar. 31, 1992

Prepared for: The U.S. Department of Energy
Agreement No. DE-FG02-86ER13619

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

In the seven months during which this phase of the program has been underway, progress has been made in several areas. As described in Part I of the report (Polypyridine Complexes of Ruthenium(II)), we now have obtained convincing evidence for localization of the optical electron on a single-ring fragment of a chelated "bipyridine-like" ligand (ie., pyridylpyrazine or 4-Methyl-bipyridine) (manuscript submitted). In addition we have completed studies of $\text{Ru}(\text{bipyrazine})_3^{2+}$ in aqueous sulfuric acid (0-98% by weight) and find clear evidence for sequential addition of six-protons to the six peripheral nitrogen atoms (manuscript submitted).

Studies of zeolite-entrapped complexes are continuing and a series of homo- and heteroleptic complexes have been prepared and characterized (manuscript in preparation). Finally, the synthesis of zeolite-entrapped metallophthalocyanines has now been developed and the copper and cobalt analogues synthesized. The characterization of these materials is now in progress.

I. Studies of Polypyridine Complexes

A. Solutions of Free Complexes

1. Inherently Asymmetric Ligands

During the past year studies of the RR spectra of the ground and $^3\text{MLCT}$ states of ruthenium complexes of inherently asymmetric ligands have been completed for two cases; pyridylpyrazine (pypz) and 4-methyl-2,2'bipyridine (4Mebpy). A manuscript describing the first species is in preparation, while final experiments involving the second case (specifically, using selectively deuteriated 4-Mebpy) are in progress. Briefly summarizing, the G-S and $^3\text{MLCT}$ state RR spectra provide convincing evidence that optical electron density in the $^3\text{MLCT}$ states of these complexes is localized to a large extent on one fragment of the chelate ring (ie., on the pyrazine fragment of pypz and on the unsubstituted pyridyl ring of 4Mebpy).

2. Tris-bipyrazine ruthenium $[\text{Ru}(\text{bpz})_3^{2+}]$ in Solutions of Sulfuric Acid

The RR spectra of $\text{Ru}(\text{bpz})_3^{2+}$ in solutions of H_2SO_4 and $^2\text{H}_2\text{SO}_4$ having varying acid concentrations between 0 and 98% have been acquired. The spectra are readily interpreted in terms of sequential protonation steps at the six peripheral nitrogen atoms. In this case also, clear evidence is obtained for vibrational isolation of individual fragments, the mono-protonated bpz (ie, the $\text{Ru}(\text{bpzH}^+)$ fragments exhibiting vibrational features ascribable to pyz-pyz^+ . A manuscript describing this work has been submitted for publication.

3. Position Dependent Deuterium Effects on Lifetimes of $\text{Ru}(\text{bpy})_3^{2+}$

We have now completed an intensive investigation of the effect of specific deuteration of $\text{Ru}(\text{bpy})_3^{2+}$ on lifetimes of the $^3\text{MLCT}$ state. As had been reported by previous workers, perdeuteration causes an increase of the lifetime from 580 ns to 690 ns. We find that

deuteration at the 3,3'- or 4,4' positions has a small effect on lifetime while deuteration at the 5,5'- or 6,6'- positions increases the lifetime significantly (to ~620 ns). Other (d4- and d6-) analogues exhibit lifetimes between 620 and 670 ns. We have also determined lifetimes of all of these deuterated compounds in D₂O and H₂O/D₂O mixtures as well as ethanol. As was mentioned in the proposal, our effort is now focussed on providing a structural dynamics interpretation of this behavior in terms of normal mode compositions of the ground and ³MLCT vibrations of each analogue.

B. Zeolite-Entrapped Complexes of Ruthenium Polypyridine Complexes

We have now completed a detailed study of the preparation and spectroscopic characterization of various homoleptic and heteroleptic complexes of ruthenium(II). While a manuscript describing this work is now in preparation, the results can be briefly summarized as follows.

The six different zeolite-entrapped complexes which were studied are Z-Ru(bpy)₃²⁺, Ru(bpy)₂(DMB)²⁺, Z-Ru(bpz)₃²⁺, Z-Ru(bpy)₂(bpz)²⁺, Z-Ru(bpy)₂(bpm)²⁺, and Z-Ru(4-MMB)₃²⁺ and (where: bpy=2,2'-bipyridine; DMB=4,4'-dimethyl-2,2'-bipyridine; 4-MMB=4-monomethyl-2,2'-bipyridine; bpz=2,2'-bipyrazine; bpm=2,2'-bipyrimidine).

In all cases except one a decrease in the ³MLCT state lifetime (compared to aqueous solution) was observed for the zeolite entrapped species. This decreased lifetime cannot be explained simply on the basis of decreased energy gap inasmuch as both red- and blue- shifts in the emission maxima are observed. The most dramatic effects (changes in lifetimes) are observed for those complexes which possesses peripheral nitrogen atoms (ie., complexes of bpz and bpm) and, in fact, in the case of Z-Ru(bpy)₂(bpz)²⁺ an increase in the ³MLCT state lifetime (from 122 to 324 ns) was observed.

For all complexes the absorption, emission, RR and TR³ spectra were obtained and lifetimes (at various temperatures) were measured. The detailed discussion of these results will be presented in the forthcoming manuscript.

II. Zeolite Entrapped Metal Phthalocyanines

Earlier efforts in our laboratory to repeat the reported synthesis of zeolite entrapped FePc were hampered by prior oxidation of Fe²⁺ loaded zeolite to the ferric form. Turning our attention to more oxidatively stable metals, the syntheses of Z-CuPc and Z-CoPc were attempted. Difficulty was encountered in removal of surface deposited MPc using the solvent prescribed in the originally reported work (pyridine). This difficulty was overcome by employing chloronaphthalene which is a much better solvent for Pc and MPc.

The resulting products, Z-CuPc and Z-CoPc, were characterized by reflectance spectroscopy and x-ray powder diffraction. The results from both methods are consistent with formation of super-cage entrapped MPc and no detectable surface species. That is, the electronic spectra are distinctly different from those of surface-coated materials and the x-ray powder diffraction pattern indicates replacement of super-cage sodium ions with "guest" molecules. The RR spectra of both materials are now being studied in order to investigate possible distortions of the relatively rigid MPc molecule which may be induced by incorporation into the sterically demanding zeolite supercage.

**DATE
FILMED**

8/12/92