TECHNICAL PROGRESS REPORT #3

Title: Non-Intrusive Measurement of Particle Charge:
Electrostatic Dry Coal Cleaning (DE-FG22-91PC91290)

Organization: Center for Applied Energy Research
University of Kentucky
3572 Iron Works Pike
Lexington, KY 40511-8433

Report Period: 01/01/92 - 03/31/92

Grant Period: 8/29/91 - 8/28/94

1. **Grant Objective:** No change
2. **Technical Approach Changes:** No changes
3. **Progress Report by Task:**

Task 1. Sample acquisition and Preparation

To evaluate the charging characteristics of pure carbon, 40 - 80 micron vitreous carbon spherical particles have been ordered from Atomergic Chemetals Co. in Plainview, New York.

Task 2. PDPA - Charge Measurement

After initial testing of the integrated particle charging/separation equipment, it was discovered that results from the Phase Doppler Particle Analyzer were not repeatable. Two weeks of troubleshooting, with phone assistance from the manufacturer, led to an on site visit from a technical representative of Aerometrics. It was ultimately decided to return the instrument to the manufacturer for diagnosis and repair. After replacing an integrated circuit card on the motor controller board and a frequency shift motor in the laser transmitter (both replaced components affect the velocity component measurements), the instrument was returned. The total time lost as a result of the instrument malfunction was approximately 6 weeks.

Shakedown tests using the repaired instrument with silica spheres showed repeatable particle velocity results. Tests were then conducted to collect data for particle charge determinations. Particle velocity and relative density data was collected for two different electric field strengths. Figures 1 and 2 show velocity and density maps for 20 kV and 40 kV electric potentials respectively. The velocity vectors indicate relative magnitude and direction. The thickness of the vectors is an indication of the relative particle number density at that location. These values were determined

MASTER

by factoring in the time required to collect a constant number of samples at each measurement location.

Figure 1: 20 kV

Figure 2: 40 kV

As in the experiments described in the last report, charged silica spheres exited the transport tube and entered the electric field where they were attracted to the positive copper plate electrode. The silica particles were transported and charged under the same conditions so that any change in particle trajectory in Figures 1 and 2 is a result of changing electric field strength. Dry nitrogen was used as the transporting, charging, and separation chamber gas.

From Figures 1 and 2, individual particle trajectories were determined. It was assumed that any particle travelling on a given trajectory has the same charge/mass ratio. These trajectories were determined by visually evaluating the data, interpolating between vectors and maintaining trajectory slopes parallel to adjacent velocity vectors.

The equations which describe the charged particle motion through the electric field are given in Equations 1 - 5. Forces which affect particle motion in the horizontal direction are due to the electric field F_{Ex} , drag F_{Dx} , and particle interactions F_{Px} . These forces are equated to the product of the particle mass m and its horizontal acceleration a_x in Equation 1.

$$\sum F_x = ma_x = F_{Ex} - F_{Dx} + F_{Px} \quad (1)$$

$$a_x = \frac{\Delta (V_x^2)}{2 \Delta x} \quad (2)$$

$$F_{E_x} = q E_x \quad (3)$$

$$F_{D_x} = C_{D_x} \frac{\pi d^2}{4} \frac{\rho V_x^2}{2} \quad (4)$$

$$\text{where: } C_{D_x} = \frac{24}{R_e} \quad \text{for } R_e < 2$$

$$\text{and: } R_e = \frac{\rho d V_x}{\mu}$$

$$\therefore F_{P_x} = 3 \pi d \mu v_x$$

$$F_{P_x} = f(x, z) q \quad (5)$$

The force due to the electric field is defined as the product of the particle charge q and the field strength in the horizontal direction E_x as shown in Equation 3. Assuming laminar conditions, the drag force, as shown in Equation 4, is a function of the particle projection area (which is related to the particle diameter d), the gas viscosity μ , and the particle horizontal velocity V_x . Equation 5 describes the interaction force as a function of the particle charge and its relative position (x, y) with respect to surrounding particles.

All of the variables in Equations 1 - 5 can either be calculated or measured with the exception of the interaction force. By subjecting particles of similar charge and mass to two different electric fields (E_{x1} and E_{x2}), the change in particle motion can be described as:

$$m(a_{x_2} - a_{x_1}) = q(E_{x_2} - E_{x_1}) - c(V_{x_2} - V_{x_1}) + [f(x_2, z_2) - f(x_1, z_1)] q \quad (6)$$

Where $c = 3\pi d$ and is defined as the drag coefficient. If Equation 6 is evaluated at the same horizontal coordinate ($x_1 = x_2$) then the change in the particle interaction force becomes small (provided the difference in the particle vertical positions (x, z) and (x, z_2) is small. Under these conditions, the change in particle interaction term can be ignored and Equation 6 becomes:

$$m(a_{x_2} - a_{x_1}) = q(E_{x_2} - E_{x_1}) - c(V_{x_2} - V_{x_1}) \quad (7)$$

With data from Figures 1 and 2, particle charge was calculated using Equation 7 and tabulated in Table 1. The average particle diameter was 60μ , the average mass was determined to be 2.78×10^{-10} kg, and the drag coefficient was 1.04×10^{-8} .

Table 1.

$E_{x1} = 2 \times 10^5$ (VDC)		$E_{x2} = 4 \times 10^5$ (VDC)		
(x, z) mm	V_{x1} (m/s)	(x, z) mm	V_{x2} (m/s)	q (coulombs)
(-10, -25)	0.53	(-10, -10)	0.71	
(-15, -30)	0.62	(-15, -15)	0.84	2.40×10^{-14}
(-20, -34)	0.70	(-20, -18)	0.85	
(-25, -37)	0.76	(-25, -21)	0.95	2.17×10^{-14}
(-30, -40)	0.77	(-30, -22.5)	1.00	2.24×10^{-14}
(-35, -42)	0.76	(-35, -24.5)	1.04	2.67×10^{-14}
(-40, -45)	0.75	(-40, -25.5)	1.05	2.01×10^{-14}

The acceleration and average velocity were determined from adjacent data points along the presumed charged particle trajectory for each electric field. This data was in turn used to calculate particle charge. The results of Table 1 yield the particle charge for a single particle trajectory as it traverses the separator chamber. If charge dissipation occurred, the charge magnitude would have decreased as the particle distance from the transport tube increased. Inspection of the data does not clearly show this trend. It is possible however that the rate of charge dissipation for silica particles in a nitrogen environment is not high. This trend will be followed for other particle and gaseous compositions during future tests.

To determine the sensitivity of the particle charge to the interaction force, another set of data was collected. Figures 3 and 4 show the velocity and density maps for this data collected at electric potentials of 20 kV and 40 kV respectively. This data was evaluated using Equation 8 in which the particle interaction force is ignored. The results of the evaluation are displayed in Table 2. The average

$$ma_x = qE_x - cV_x \quad (8)$$

Figure 3: 20kV

Figure 4: 40kV

particle mass and drag coefficient remained the same as those used in the previous evaluation.

Table 2.

$E_x = 2 \times 10^5$ (VDC)			$E_x = 4 \times 10^5$ (VDC)		
(x, z) mm	V_x m/s	q (coul.)	(x, z) mm	V_x m/s	q (coul.)
(-4, -20)	0.32	2.44×10^{-14}	(-4, -15)	0.31	1.74×10^{-14}
(-6, -25)	0.35		(-6, -20)	0.38	
(-8, -20)	0.52	3.34×10^{-14}	(-10, -15)	0.71	2.54×10^{-14}
(-12, -25)	0.55		(-16, -20)	0.78	
(-12, -20)	0.65	3.76×10^{-14}	(-12, -15)	0.79	2.73×10^{-14}
(-18, -25)	0.67		(-20, -20)	0.87	
(-14, -20)	0.70	3.94×10^{-14}	(-14, -15)	0.87	2.87×10^{-14}
(-22, -25)	0.72		(-24, -20)	0.95	
(-16, -20)	0.74	4.24×10^{-14}	(-16, -15)	0.94	2.79×10^{-14}
(-26, -25)	0.77		(-28, -20)	0.99	
			(-18, -15)	0.99	3.02×10^{-14}
			(-32, -20)	1.06	

The horizontal acceleration was determined by using the V_x measurement at two adjacent PDPA measurement locations along the previously determined particle trajectory. The acceleration was then used in calculating the particle charge (q).

Table 2 particle charge results were determined for different particle trajectories (hence different charge/mass ratios) along a horizontal slice of the separator chamber. If it is assumed that all particles have the same mass then the highest charged particles should be closest to the copper plate electrode at any horizontal section. The results of Table 2 verify this assumption with particle charge increasing as the absolute horizontal coordinate increases.

Evaluating the two sets of data indicate that the affect of particle interactions on charge determination, at least with silica spheres, may not be significant. This evaluation also shows consistent V_x measurements and q calculations as a function of (x , z). An effort is currently underway to quantify the electric, drag, and particle interaction forces, and to determine there relative orders of magnitude.

Task 3. Sample Characterization

No further sample characterizations have been conducted.

Task 4. Reports/Publications

A quarterly report for the period spanning 10/01/91 - 12/31/91 was submitted on January 30, 1992.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

**DATE
FILMED**

8/20/92