DOE/PC/89783--T5

RECEIVED
GENERAL INVESTIGATIVE
DIVISION
APR 11 1990

DOE/PC/89783--T5

DE92 018316

Quarterly Progress Report for the period 1/1/90 - 03/31/90

to US Department of Energy

Project title: "Fundamental Studies of Catalytic Processing of Synthetic Liquids"

Project number: DE-FG22-89PC89783

Principal Investigator: Prof. Philip R. Watson
Department of Chemistry and Center for
Advanced Materials Research
Oregon State University
Gilbert Hall 153
Corvallis, OR 97331-4003
(503)-737-2081

Date of report: 04/10/90

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

1. Background

This project revolves around understanding the fundamental processes involved in the catalytic removal of harmful oxygenated organics present in coal liquids. We will model the complex type of sulfided Mo catalyst proposed for these reactions with a simple single crystal surfaces that display a controlled range and number of reaction sites and can be extensively characterized by surface science techniques.

2. Summary

The second quarter of this project has been spent in building up our knowledge of Mo/S surface chemistry to the point where we can reproducibly obtain a variety of surface surfaces of known composition and probable structure. The equipment has also been modified to permit the adsorption of O-containing reactants onto the surface in a controlled manner.

3. Work performed

The prime initial objective of this project is to discover how to reliably and reproducibly produce S overlays on a Mo(100) surface of known composition. This has been achieved. Figure 1 shows the raw Auger electron spectroscopy (AES) data that illustrate our ability to make i) a clean Mo surface, free from surface C and O, and ii) using an in-situ electrochemical chlorine source, to cover this surface with a monolayer of S atoms. This sulfur can then be removed in stages by heating as shown in Figure 2. After heating to 1800K, a clean S-free surface is recovered.

We can convert raw AES S/Mo signal ratios into surface coverages via a formalism suggested by Salmeron et al [1]:

$$\theta_s = \frac{r^2 [-Mo(0)^2\alpha] + r [Mo(0)S(1)]}{r^2 [\alpha^2 Mo(0)^2 - \alpha Mo(0)^2] + r [Mo(0)S(1) - 2\alpha Mo(0)S(1)] + S(1)^2}$$

to produce the calibration curve shown in Figure 3.

We observe a number of ordered surface phases via low-energy electron diffraction (LEED) as a function of surface coverage (Figure 4 and Table 1). These are in good agreement with previous studies [1-3]; in common with Clarke [2] and Maurice et al [3] we find that the (2x1) LEED patterns are a high coverage phenomenon, rather than relatively low coverage phase as suggested by Salmeron et al [1]. Recent conversations with Salmeron and Somorjai [4] suggest that they now agree with our assignment. From previous studies and experience we can formulate reasonable models for the structure of these surfaces. The likely structures corresponding to the above phases are shown in Figure 5 [1-3]. These structures assume that the top layer Mo atoms are not rearranged upon S adsorption. This assumption is probably untrue, but the displacements are likely to be rather small [4].

4. Future studies

We are now in a position to begin oxygenate adsorption and reaction experiments. To this end we have modified the gas introduction system to allow the vapor of thoroughly degassed organic liquids e.g. furans and phenols to be introduced into the vacuum system via a leak valve and capillary doser. Such an arrangement allows relatively high adsorbate pressures to be maintained at the sample surface, while not saturating the whole vacuum chamber with organic vapors that are difficult to remove.

5. References

1. M. Salmeron, G.A. Somorjai and R.R. Chianelli, Surface Sci. 127 526 (1983).
2. L.J. Clarke, Surface Sci. 102 331 (1981).
3. V. Maurice, L. Peralta, Y. Berthier and J. Oudar, Surface Sci. 148 623 (1984).
4. M. Salmeron and G.A. Somorjai, personal communication.

Table I. LEED patterns reported for Mo(100)/S system at various S coverages.

	LEED patterns			
	c(2x2)	$\begin{pmatrix} 2 & -1 \\ 1 & 1 \end{pmatrix}$	c(4x2)	p(2x1)
Salmeron et al [1]	0.3 - 0.5	0.54 - 0.69	0.6 - 0.77	0.47 - 0.63
Clark [2]	0.5	0.65	0.8	1.0
Maurice et al [3]	0.5	0.66	0.7 - 0.8	0.8 - 1.0
This work	0.5	0.66	0.8	1.0

Figure 1. AES spectra of a) clean Mo(100)
b) S covered

Figure 2. S desorption from Mo(100) _S

Figure 3. S adsorption on Mo(100) measured by AES

Figure 4. LEED patterns observed at various S coverages

Figure 5. Possible surfaces structures of S on Mo(100)

Department of
Chemistry

Corvallis, Oregon 97331-4003

(503) 754-2081

2/5/90

Norey B. Laug
Contract Specialist
Ad-22, 921-165
US Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

RECEIVED
USDOE/PETC
90 FEB 12 AM 10:59
AUGUSTIN J. ROBERTS, JR.

Dear Ms. Laug:

Please find enclosed the first quarterly report for my grant "Fundamental Studies of Catalytic Processing of Synthetic Liquids", project number DE-FG22-89PC89783.

Sincerely,

A handwritten signature in dark ink, appearing to read "P. R. Watson", written in a cursive style.

Philip R. Watson
Assistant Professor

**DATE
FILMED
8/26/92**