DOE/PC/89868--4

DE92 016724

Development of Improved Iron Fischer-Tropsch Catalysts

Quarterly Technical Progress Report
for the Period 1 July 1990 – 30 September 1990

Prepared by: Dragomir B. Bukur

Contributors: R. Manne, S. Ledakowicz, D. Wang, J. Zheng

Texas A&M University
Department of Chemical Engineering
College Station, Texas 77843

October 29, 1990

Prepared for the Pittsburgh Energy Technology Center,
the United States Department of Energy Under Contract No. DE-AC22-89PC89868
V. Udaya Rao, Project Manager (PETC)

"U.S. Department of Energy Patent Clearance not required
prior to publication of this document"

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

NOTICE

MAY 07 1992

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States nor any agency thereof, nor any of their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for any third party's results of such use of any information, apparatus, product or process disclosed in this report, or represents that its use by such a third party would not infringe privately owned rights.

PATENT STATUS

U.S./DOE Patent Clearance is not required prior to the publication of this document.

TECHNICAL STATUS

This technical report is being transmitted in advance of DOE review and no further dissemination or publication shall be made of the report without prior approval of the DOE Project/Program Manager.

TABLE OF CONTENTS

I.	Executive Summary	1
II.	Objective and Scope of Work	2
III.	Detailed Description of Technical Progress	4
III-1.	Task 2. Catalyst Pretreatment Research	4
III-1.1	Run FB-1920 (Ruhrchemie LP33/81 Catalyst)	4
III-1.2	Run FB-2290 (Ruhrchemie LP33/81 Catalyst)	5
III-2.	Task 3. Improved Iron/Silica Catalysts	5
III-2.1	Run FA-2080 (100 Fe/3 Cu/2 K/8 SiO ₂)	5
III-2.2	Run FA-2500 (100 Fe/3Cu/4K/8 SiO ₂)	6
III-2.3	Run SB-1910 (100 Fe/5Cu/4.2K/8 SiO ₂)	6
III-2.4	Run SB-2270 (100 Fe/5Cu/4.2K/16 SiO ₂)	10
III.3	Catalyst Synthesis	12
	Tables	13
	Figures.	25

I. EXECUTIVE SUMMARY

Two different pretreatment procedures were employed in tests of the Ruhrchemie LP 33/81 catalyst in a fixed bed reactor, namely reduction with H_2 at $280^\circ C$ for 1 h (Run FB-1920), and activation with syngas ($H_2:CO = 2:1$) at $310^\circ C$ for 6 h (Run FB-2290). After the pretreatment the catalyst was tested at $250^\circ C$, 200 psig, $2(Nl/g\text{-cat}/h)$, and $(H_2/CO) = 0.67$. The (H_2+CO) conversion increased with time on stream (62.9-70.9%) in the run FB-1920 (H_2 reduction), whereas it decreased slightly with time (61.1-57.9%) in the Run FB-2290 (pretreatment with syngas). The catalyst activated with syngas produced less methane and more high molecular weight products, than the catalyst reduced in H_2 . The average hydrocarbon distribution in the Run FB-2290 was: $(CH_4) = 7.0$; $(C_2-C_4) = 23.0$; $(C_5-C_{11}) = 23.1$; and $(C_{12}^+) = 46.9\%$, whereas in the Run FB-1920 the hydrocarbon distribution was: $(CH_4) = 9.3$; $(C_2-C_4) = 24.1$; $(C_5-C_{11}) = 43.4$, and $(C_{12}^+) = 23.2\%$.

Two screening tests of iron/silica catalysts with nominal compositions 100 Fe/3 Cu/2 K/8 SiO_2 (Run FA-2080) and 100 Fe/3 Cu/2 K/8 SiO_2 (Run FA-2500) were made in a fixed bed reactor. There were some operational problems (plugging of lines with high molecular weight products) in both of these tests. A hot spot developed in the reactor during the Run FA-2500, resulting in (H_2+CO) conversion of 90%, and methane selectivity of 61%. The methane selectivity during the Run FA-2080 was between 3.3 and 3.7%.

Two silica containing catalysts with nominal compositions 100 Fe/5 Cu/4.2 K/x SiO_2 (where $x=8$ or 16), were evaluated in runs SB-1910 and SB-2270, respectively. Both tests were terminated voluntarily after 400 h on stream. Initially, catalysts deactivated slowly with time on stream, but the rate of deactivation increased after each wax withdrawal. In both tests the deactivation rate was greater than the target rate of 1% per day. Hydrocarbon selectivity of the 100 Fe/5 Cu/4.2 K/8 SiO_2 catalyst (Run SB-1910) was within the DOE target, i.e. $(C_1+C_2) \leq 7$ wt%.

Seventeen catalysts have been synthesized by continuous coprecipitation method for future testing in fixed bed and slurry reactors.

II. OBJECTIVE AND SCOPE OF WORK

The objective of proposed research is development of catalysts with enhanced slurry phase activity and better selectivity to fuel range products, through a more detailed understanding and systematic studies of the effects of pretreatment procedures and promoters/binders (silica) on catalyst performance. In order to accomplish this objective, the work shall be divided into several tasks which are described in the following subsections.

Task 1 – Project Management

Within 60 days of project initiation, the contractor shall prepare and submit to the DOE Project Manager a detailed project work plan covering the entire period of performance of the project. The plan shall present, in detail, all activities that will be performed to successfully complete proposed research and its shall consist of the following: (1) detailed description of the methods and technical approach that shall be used to achieve the objectives of this project; (2) a detailed project schedule for each task or other logical segment of work to be performed; (3) graphs reflecting cumulative estimated costs and person-hours expended by month for each task or other logical segment of work, and for the total project effort; (4) a project work chart showing the key personnel/groups planned to work on each task and percentage of their time devoted to the tasks; and (5) a Work Breakdown Structure (WBS) dictionary to establish the framework for contract execution and to report cost schedule and technical performance.

All project status, milestone schedule, and cost management reports, as well as topical reports, if any, shall be submitted in accordance with the DOE reporting requirements.

Task 2 – Catalyst Pretreatment Research

This task is aimed at developing optimal pretreatment conditions for precipitated unsupported (1 catalyst) and supported (or silica containing; 1-2) iron catalysts, and at providing a better understanding of the role of pretreatment on subsequent catalyst activity, selectivity and longevity during Fischer-Tropsch (F-T) synthesis. This shall be accomplished by examining the effect of various activation conditions on physical and chemical properties of the catalyst as well as on catalytic behavior in fixed and slurry bed reactors. Parameters such as type of reductant (H_2 vs. CO vs. syngas), reductant flow rate, temperature and duration shall be studied. Selected catalysts shall be extensively characterized using a variety of physical, chemical and instrumental techniques with the objective to establish correlations between the physical/chemical properties of the catalysts and their observed catalytic behavior during F-T synthesis.

Task 3 – Improved Iron/Silica Catalysts

The objective of this task is to determine optimal concentrations of silica and K_2O in a catalyst with composition $100 Fe/x Cu/yK_2O/zSiO_2$ (in parts per weight). The effect of SiO_2 and K_2O on catalytic activity, selectivity and stability shall be determined to arrive at promoter/binder concentrations for an improved catalyst performance. The screening tests shall be conducted in fixed bed reactors to obtain preliminary indication of F-T activity and selectivity at different process conditions. Catalysts which show enhanced activity and/or selectivity towards transportation fuels shall be tested in slurry reactors up to 30 days on stream. Selected catalysts shall be extensively characterized, to determine relations between the physico-chemical properties of catalyst and their catalytic behavior during F-T synthesis.

III. DETAILED DESCRIPTION OF TECHNICAL PROGRESS

III-1. Task 2. Catalyst Pretreatment Research

III-1.1 Run FB-1920 with the Ruhrchemie Catalyst

This run was made as retest of the unsuccessful run FB-99-0750, to study the effect of pretreatment conditions (H_2 reduction at $280^\circ C$, ambient pressure, superficial gas velocity of 1.5 m/s for 1 h) on catalyst performance in a fixed bed reactor. The results of the run FB-99-0750 were reported in Quarterly Technical Progress Report for the period 1 January 1990 – 31 March 1990. Throughout the current test average reaction temperature, pressure, space velocity and H_2/CO feed ratio were maintained at $250^\circ C$, 200 psig, 2 Nl/g-cat/h and 2:3, respectively. The run was voluntarily terminated after about 220 h on stream. The results from three mass balances are summarized in Table 1.

Catalyst Activity and Stability

Catalyst activity, measured by volumetric gas contraction as well as (H_2+CO) conversion, is shown in Figures 1 and 2, respectively. Both contraction and conversion increased slightly with time on stream (TOS) during the entire test period, which is not unusual for catalysts reduced in hydrogen.

Catalyst Selectivity

This test confirms our hypothesis that high methane selectivity (26-44%) in the previous fixed bed run, FB-99-0750, was unusual and may have been caused by hot spots in the reactor. Methane selectivity varied between 8 and 10% during this test.

The average hydrocarbon distribution during the entire test was: 9.3 (CH_4), 24.1 (C_2-C_4), 43.4 (C_5-C_{11}) and 23.2 wt% (C_{12}^+). A high yield of (C_5-C_{11}) products results in a relatively high yield of methane and comparatively low yield of C_{12}^+ hydrocarbons.

III-1.2 Run FB-2290 with the Ruhrchemie Catalyst

The purpose of this run was to study the effect of pretreatment conditions, on catalyst activity, selectivity and stability. The catalyst was reduced using synthesis gas with $H_2:CO = 2:1$ at $310^\circ C$, ambient pressure and total gas flow rate of 1200 cc/min for 6 hours. The process conditions employed throughout this test were: $250^\circ C$, 200 psig, 2.0 Nl/g-cat/h and $H_2:CO = 2:3$ feed gas. The run was voluntarily terminated after about 160 hours on stream. The results from three mass balances are given in Table 2.

Catalyst Activity and Stability

The catalyst activity was fairly stable during 160 hours of testing (Figures 3 and 4). The ratio of partial pressures ($P_{CO_2} P_{H_2}/P_{CO} P_{H_2O}$) which is one of the ways to quantify water-gas-shift (WGS) activity was about 2.1 in this test. This is markedly lower in comparison to values obtained in tests where H_2 reduction was employed. For the run FB-1920 (H_2 reduction at $280^\circ C$) the ratio of partial pressures was approximately ~23.0 (balances 1 and 3) and for the run FA-3509 (H_2 reduction at $220^\circ C$) it was about 6.

Catalyst Selectivity

Methane selectivity was lower than in the fixed bed run FB-1920 (7.0% as opposed to 9.2% in the run FB-1920). The average hydrocarbon distribution during the run was: 7.0 (CH_4), 23.0 (C_2-C_4), 23.1 (C_5-C_{11}), and 46.9 wt% (C_{12}^+).

A typical carbon number product distribution is shown in Figure 5 in the form of Anderson-Shulz-Flory (ASF) plot. Solid product (wax) collected from the high pressure trap was not analyzed.

III-2. Task 3. Improved Iron/Silica Catalysts

III-2.1 Run FA-2080 with the 100 Fe/3 Cu/2 K/16 SiO_2 Catalyst

This was a screening test of a silica containing catalyst in a fixed bed reactor. The catalyst was reduced in H_2 at $220^\circ C$ for 1 h before exposure to synthesis gas with $H_2:CO$ feed ratio of 2:3. The test was terminated voluntarily after 140 h on stream. Results from two mass balances are summarized in Table 3.

Initially, the process conditions were: $250^\circ C$, 200 psig, 2 NI/g-cat/h and $H_2/CO = 0.67$. The first mass balance was made after 70h on stream and the (H_2+CO) conversion was about 54%, whereas the hydrocarbon selectivity was: $(CH_4) = 3.7$; $(C_2-C_4) = 15.4$; $(C_5-C_{11}) = 21.0$; $(C_{12}^+) = 59.9\%$. After the mass balance, reaction pressure and gas space velocity were changed to 300 psig, and 3 NI/g-cat/h, respectively, and the second mass balance begun at about 94h on stream. The (H_2+CO) conversion was 48.4%, and the hydrocarbon selectivity was: $(CH_4) = 3.3$; $(C_2-C_4) = 14.1$; $(C_5-C_{11}) = 18.4$, and $(C_{12}^+) = 64.2\%$. Total mass balance closures in both of the two mass balances were significantly lower in comparison to values that are normally obtained in our laboratory (i.e. $100 \pm 3\%$). Also, problems with plugging of lines by high molecular weight products were experienced throughout the test.

III-2.2 Run FA-2500 with the 100 Fe/3Cu/4K/8 SiO₂ Catalyst

The screening test of this catalyst was terminated voluntarily after 80 h on stream, due to plugging of the reactor. Following reduction with H_2 at $220^\circ C$, the catalyst was exposed to synthesis gas with $H_2:CO=2:3$ at $250^\circ C$, 200 psig and 2 NI/g-cat/h. The (H_2+CO) conversion was high: 90%, but the methane selectivity was 61%. This indicates that a hot spot was present in the reactor, which had caused carbonization of high molecular weight products, and consequently plugging of the reactor. We plan to retest this catalyst during the next quarter.

III-2.3 Run SB-1910 with the 100 Fe/5 Cu/4.2 K/8 SiO₂ Catalyst

This was the first slurry reactor test of one of the most active catalysts synthesized in our laboratory during the DOE Contract No. DE-AC22-85PC80011. This catalyst was evaluated in a

fixed bed reactor (Runs FA-63-0418 and FA-63-1308), and results from these tests were reported previously (Final Report for the above referenced contract). In both of these tests the catalyst was very active, and had excellent hydrocarbon selectivity (low methane yield and high yield of C_{12}^+ hydrocarbons) but its deactivation rate was higher than the target rate of 1% per day.

The catalyst was tested initially (first 160 h) at 250°C, 200 psig (1.48 MPa), 2NI/g-cat/h using the synthesis gas with H_2 to CO molar ratio of about 0.7 (0.65-0.75). Two mass balances were made during this time period, but the (H_2 +CO) conversion and volumetric gas contraction (VC) were monitored more frequently. After the second mass balance, the reaction temperature was increased to 258°C (160-270 h) in order to achieve higher (H_2 +CO) conversion (mass balances 3 and 4). At 273 h on stream the gas flow rate was decreased to give the gas space velocity of 1.5 (NI/g-cat/h) based on the initial amount of catalyst charged to the reactor. These operating conditions were maintained over next 94 h, and two additional mass balances were made (balances 5 and 6). At 365 h on stream the baseline conditions were established again to check the catalyst activity (365-397h). The run was terminated voluntarily after 400 h on stream. Results from all six mass balances are summarized in Table 4.

Catalyst Activity and Stability

The catalyst activity was very stable between 30 and 110 h on stream, as shown in Figures 6 (contraction vs. TOS) and 7 (conversion vs. TOS). During this time period the volumetric contraction (VC) was between 36 and 38%, whereas the (H_2 +CO) conversion varied between 53.6 and 56.4%. After slurry withdrawal through a dipleg tube at about 110 h, the VC and (H_2 +CO) values decreased by about 10%, but remained fairly stable during the next fifty hours (TOS = 110-160 h). This decrease may be attributed in part to loss of catalyst with wax removed from the system (1.7 g catalyst, or about 6% of the total amount of the catalyst left in the reactor after the reduction and slurry sample withdrawal for catalyst characterization - see Table 5).

At about 162 h on stream, the temperature was increased to 258°C, and during the next 44

hours (162-206 h on stream) the volumetric contraction and the (H_2+CO) conversion declined slightly with time (see Figures 6 and 7). During the mass balance period 3 (201-207 h) the volumetric contraction varied between 41 and 43%, whereas after withdrawal of about 154 g of wax and 1.4 g of catalyst from the reactor the contraction decreased to 37.1% (see Fig. 6). Further drop in activity occurred at about 230 h on stream, $VC = 32.6\%$, after a temporary stoppage (~2h) of syngas flow due to plugging of the reactor inlet line. The contraction continued to decrease slowly with time (TOS = 230-258 h), but another sharp decline occurred after the slurry withdrawal from the reactor (134 g of wax, and 1.5 g of catalyst) at about 270 h on stream ($VC = 25.4\%$). At this time the feed flow rate was changed to 750 (cc/min), corresponding to the gas space velocity of $1.5(Nl/g\text{-cat}/h)$ based on the initial amount of catalyst charged to the reactor. During the next fifty hours (TOS = 272-322 h) the volumetric contraction and the (H_2+CO) conversion were fairly stable, i.e. $VC = 33.4\text{-}37\%$ and (H_2+CO) = $49.7\text{-}51.9\%$. After the slurry withdrawal (122 g of wax, and 1.2 g of catalyst) at 324 h, a marked decrease in activity was observed again. The volumetric contraction was 29.1% at 328 h on stream, and is remained fairly stable during the next 24 hours. After another slurry withdrawal at 354-364h, the contraction decreased to 26.5%. At this point the reaction temperature was decreased to $250^\circ C$, whereas the syngas flow rate was increased to 1000 cc/min (baseline conditions), and these conditions were maintained during the next 30 h. During this period the volumetric contraction varied between 20 and 21.7%, and the (H_2+CO) conversion between 29.2 and 31%.

Wax and Catalyst Inventories

Two methods of wax (slurry) withdrawal were employed during this run, i.e. wax withdrawal through a $10\text{ }\mu m$ vertical cylindrical element and slurry withdrawal to an external settler via a dipleg tube followed by wax removal and return of concentrated slurry to the reactor. Results from all wax (slurry) withdrawals are summarized in Table 5.

At the end of the reduction period 65 g of wax was removed from the reactor through the

filter. The withdrawn wax was clear in appearance, and contained trace amounts of solids only. At 62 h on stream about 17.5 g of wax was withdrawn through the filter. This wax had a black color, and it was suspected that the filter element had developed a crack. At this point it was decided to change the method of wax withdrawal, and slurry withdrawal through a dipleg tube was employed throughout the remainder of the test. At the end of the run the filter element was inspected and no cracks were found. This means that the catalyst particles had disintegrated to size smaller than 10 μm during the first 60 h of synthesis (The catalyst particles charged to the reactor were between 43 and 53 μm ; 270/325 mesh particles).

The wax transferred from the settling vessel was of black color. The amount of catalyst in the wax was determined by filtration, and subsequent burning of the solids material retained on the filter. As can be seen from results in Table 5, the catalyst content in the wax was about 1%. Therefore, the amount of catalyst remaining in the reactor was decreasing with each slurry withdrawal. The gas space velocities reported in Table 4, are based on the estimated amount of catalyst in the reactor.

At the end of the run, the catalyst content in the slurry was determined by the above procedure. The overall wax and catalyst recoveries were: 113 and 77.3%, respectively. (% Recovery = (Amount out)/(Amount in) x 100).

Hydrocarbon Product Distribution

Hydrocarbon selectivities were similar in all six mass balances, even though the process conditions were not constant throughout the test ($T = 250\text{-}258^\circ\text{C}$, $SV = 1.9\text{-}2.4 \text{ NI/g-cat/h}$, $(\text{H}_2/\text{CO}) = 0.64\text{-}0.82$). Methane selectivity varied between 3.1 and 3.8%, and selectivity of light hydrocarbons ($\text{C}_2\text{-C}_4$) varied between 12.9 and 13.7%. Fraction of C_{12}^+ hydrocarbons decreased slightly with time on stream (TOS), whereas fraction of hydrocarbons in the gasoline range ($\text{C}_5\text{-C}_{11}$) increased with time (see Table 4).

Overall the performance of this catalyst was very good. It is evident that loss of catalyst from the reactor had contributed to decrease in (H_2+CO) conversion with time on stream. The hydrocarbon selectivity of the catalyst was within the DOE target, i.e. $(C_1+C_2) \leq 7$ wt%.

III-2.4 Run SB-2270 with the 100 Fe/5 Cu/4.2 K/16 SiO₂ Catalyst

This run was made to study the effect of the amount of silica at constant promoter levels. Also, this catalyst was tested previously in a fixed bed reactor (Run FA-1580, April 1–June 30, 1990 Quarterly Technical Progress Report).

The catalyst was tested initially (first 230 h) at 260°C, 200 psig (1.48 MPa), 1.4 NI/g-cat-h using the synthesis gas with H_2 to CO molar feed ratio of 0.69, and three mass balances were made during this time period. Following this the reaction pressure and the gas space velocity were changed to 300 psig (2.17 MPa) and 2.3 (NI/g-cat/h), respectively. At 300 h on stream the catalyst was regenerated in-situ with H_2 at 220°C, and 200 psig for 2 hours. Two mass balances were made at these process conditions, one before and the other one after the regeneration with H_2 . The test was terminated voluntarily after 400 h on stream. Results from all five mass balances are summarized in Table 6.

Catalyst Activity and Stability

The catalyst activity, expressed in terms of volumetric contraction and (H_2+CO) conversion, declined slowly with time during the first 180 h on stream, as shown in Figures 8 and 9. After the wax withdrawal at 184 h, the volumetric contraction decreased markedly from 41% to 31%, whereas the (H_2+CO) conversion decreased from about 64% to 45%. During the next 40 hours, the volumetric contraction remained fairly stable (29-31%). Although, the reasons for this sharp drop in activity are not known, we suspect that it might have been caused by removal of the catalyst particles from the slurry. After withdrawal of approximately 280 cm³ of wax, a significant portion of the catalyst remained above the slurry level (e.g. deposited on the reactor wall or on the

internal filter element), and it appears that this catalyst is not as active as the one in the slurry.

At about 230 h on stream the reaction pressure and the gas space velocity were increased to 300 psig (2.17 MPa) and 2.3 (Nl/g-cat/h); respectively. During the next 60 hours, the activity remained fairly constant (VC=21-23%; (H₂+CO) = 33-34%). At 250 h on stream an attempt was made to increase the activity, by adding 65 g of wax to raise the liquid level in the slurry reactor. However, this did not result in increased catalyst activity.

At about 300 h on stream the catalyst was regenerated in-situ with H₂ at 220°C and 200 psig for two hours. After the regeneration, the catalyst activity increased markedly. At 311 h on stream the values of volumetric contraction and (H₂+CO) conversion were: 33.8 and 47.6%, respectively. However, the activity declined with time and at 400 h the volumetric contraction was only 23.5% .

The WGS activity was rather high throughout the entire test, e.g. the H₂/CO usage ratio varied between 0.6 and 0.7, whereas the approach to equilibrium was between 0.1 and 0.3 (see Table 6).

Wax and Catalyst Inventories

The reactor was charged initially with 10 g of catalyst and 289 g of purified n-octacosane. We have deliberately chosen to add only a small amount of catalyst for this test, in order to minimize the need for wax withdrawals throughout the run. Wax withdrawals result in disturbance of the system and may have adverse effect on the rate of catalyst deactivation (Bukur et al., Final Report for DOE Contract, No. DE-AC22-85PC80011, August 1989). Only three wax withdrawals were made through a 2 µm cylindrical filter element placed vertically in the reactor. Results from all withdrawals are summarized in Table 7.

There were no operational problems during wax withdrawals, and the collected wax was clear in appearance. At the end of the run 8.9 g of catalyst was recovered in the reactor, after separation from wax by filtration and burning in the air to convert the used catalyst into Fe₂O₃. It

is estimated that about 0.3 g of catalyst was removed from the reactor with the slurry sample withdrawn at the end of reduction. The catalyst recovery was 92.6%, whereas the wax recovery was 78%.

Hydrocarbon Product Distribution

Hydrocarbon selectivities were similar in balances 2-5, and the average values for methane and product group lumps by carbon numbers were: $(\text{CH}_4) = 4.2$; $(\text{C}_2\text{-C}_4) = 17.7$; $(\text{C}_5\text{-C}_{11}) = 17.7$, and $(\text{C}_{12}^+) = 60.4\%$.

During the first mass balance the fraction of high molecular weight products was markedly higher, and the methane yield was markedly lower in comparison to selectivities obtained in balances 2 to 5 (see Table 6).

III-3. Catalyst Synthesis

We have synthesized 17 additional catalysts, using the controlled – pH continuous precipitation, during the current reporting period. Total number of catalysts synthesized during the past two quarters is 21, and breakdown according to the composition is as follows: 13 catalysts of the type $\text{Fe}/x\text{Cu}/y\text{K}/z\text{SiO}_2$; 4 catalysts – $\text{Fe}/x\text{Cu}/y\text{SiO}_2$; and 4 catalysts without silica, i.e. $\text{Fe}/x\text{Cu}/y\text{K}$.

Table 1. Summary of results for fixed bed run FB-99-1920 .

Catalyst: 3.49 g^a, Ruhrchemie
 Catalyst volume: 5.40 cc
 Diluent: 35.12 g, Glass beads
 Diluent Volume: 23.80 cc

Period	1	2	3
Date	07/15/90	07/18/90	07/19/90
Time on Stream (h)	92.7	159.3	200.1
Balance Duration (h)	12.0	12.0	12.0
Average Temperature (°C)	250.	250.	250.
Maximum Δ Temperature (°C) ^b	5.00	4.00	7.00
Pressure (MPa)	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.669	.669	.669
Space Velocity (NI/g-cat·h) ^a	2.00	2.00	2.00
Space Velocity (NI/g-Fe·h)	3.81	3.81	3.81
GHSV (h ⁻¹) ^c	248.	248.	248.
CO Conversion (%)	62.9	67.6	70.9
H ₂ +CO Conversion (%)	62.8	65.8	67.9
H ₂ /CO Usage	.668	.624	.598
STY (mols H ₂ +CO/g-cat·h) ^a	.056	.059	.061
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	25.8	11.9	22.5
Weight % of Outlet			
H ₂	1.72	1.70	1.70
H ₂ O	.463	1.27	.766
CO	35.6	31.0	27.9
CO ₂	43.5	48.3	49.9
Hydrocarbons	13.5	13.2	15.6
Oxygenates	2.30	1.31	2.17
Wax ^d	2.89	3.28	1.93
Yield (g/Nm ³ H ₂ + CO Converted)			
CH ₄	21.1	16.1	18.1
C ₂ -C ₄ Hydrocarbons	47.4	48.6	50.4
C ₈ -C ₁₁ Hydrocarbons	85.7	87.4	106.
C ₁₂ + Hydrocarbons	48.9	43.8	26.5
Wax ^d	35.9	39.1	22.2
Oxygenates	28.6	15.6	25.0
Total	232.	211.	226.
1+2 Olefins/n-Paraffin Ratio			
C ₂	.448	.397	.371
C ₃	3.84	3.78	3.72
C ₄	3.09	3.12	3.07
C ₈	1.39	1.38	1.41
C ₁₀	.988	1.21	1.22

^a Based on unreduced catalyst^c Based on reactor volume^b Maximum axial temperature difference^d Unanalyzed products collected from hot trap

Table 1 (cont'd). Summary of results for fixed bed run FB-99-1920 .

Weight % of Hydrocarbons	Period		
	1	2	3
CH ₄	10.4	8.20	9.00
Ethane	4.45	4.86	4.82
Ethylene	1.86	1.80	1.67
Propane	1.98	2.15	2.17
Propylene	7.23	7.76	7.71
n-Butane	1.85	1.95	2.07
1+2 Butenes	5.53	5.88	6.14
C ₄ Isomers	.402	.410	.413
n-Pentane	1.76	1.78	3.29
1+2 Pentenes	4.56	4.87	5.79
C ₅ Isomers	.571	.557	.607
n-Hexane	.656	.954	1.82
1+2 Hexenes	5.38	1.97	3.06
C ₆ Isomers	.413	.993	1.80
n-Heptane	1.10	3.05	2.47
1+2 Heptenes	1.42	3.68	3.45
C ₇ Isomers	.0661	.812	1.17
n-Octane	2.97	2.92	3.46
1+2 Octenes	4.05	3.97	4.80
C ₈ Isomers	.126	.859	2.48
n-Nonane	4.46	3.96	3.74
1+2 Nonenes	5.09	5.20	4.62
C ₉ Isomers	.00000	.709	.525
n-Decane	3.49	2.64	2.96
1+2 Decenes	3.40	3.15	3.57
C ₁₀ Isomers	.00000	.360	.199
n-Undecane	1.43	1.08	1.66
1+2 Undecenes	1.27	1.02	1.37
C ₁₁ Isomers	.00000	.0811	.0178
C ₂ -C ₄	23.3	24.8	25.0
C ₅ -C ₁₁	42.2	44.6	52.8
C ₁₂ +	24.1	22.4	13.2
Wax ^d	17.7	20.0	11.0

^d Unanalyzed products collected from hot trap

Table 2. Summary of results for fixed bed run FB-99-2290 .

Catalyst: 3.51 g^a, Ruhrchemie
 Catalyst volume: 5.40 cc
 Diluent: 35.35 g, Glass beads
 Diluent Volume: 24.00 cc

Period	1	2	3
Date	08/20/90	08/23/90	08/24/90
Time on Stream (h)	73.5	125.0	157.0
Balance Duration (h)	24.0	19.1	10.0
Average Temperature (°C)	250.	250.	250.
Maximum Δ Temperature (°C) ^b	7.00	7.00	7.00
Pressure (MPa)	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.692	.689	.689
Space Velocity (NI/g-cat·h) ^a	2.02	2.02	2.02
Space Velocity (NI/g-Fe·h)	3.85	3.85	3.85
GHSV (h ⁻¹) ^c	241.	241.	241.
CO Conversion (%)	61.1	59.9	57.9
H ₂ +CO Conversion (%)	63.3	61.8	60.9
H ₂ /CO Usage	.754	.742	.777
STY (mols H ₂ +CO/g-cat·h) ^a	.057	.056	.055
$P_{CO_2} \cdot \bar{P}_{H_2} / P_{CO} \cdot \bar{P}_{H_2O}$	2.28	2.14	1.71
Weight % of Outlet			
H ₂	1.61	1.74	1.68
H ₂ O	4.26	4.41	4.87
CO	37.7	39.6	41.1
CO ₂	39.9	37.8	35.9
Hydrocarbons	8.53	9.90	11.6
Oxygenates	.604	.870	.949
Wax ^d	7.42	5.68	3.88
Yield (g/Nm ³ H ₂ + CO Converted)			
CH ₄	13.5	13.9	13.2
C ₂ -C ₄ Hydrocarbons	43.6	44.8	44.9
C ₅ -C ₁₁ Hydrocarbons	43.1	59.0	61.0
C ₁₂ + Hydrocarbons	92.1	71.0	73.5
Wax ^d	89.5	68.7	48.2
Oxygenates	7.27	10.5	11.8
Total	200.	199.	204.
1+2 Olefins/n-Paraffin Ratio			
C ₂	1.39	1.38	1.38
C ₃	6.72	6.89	6.59
C ₄	5.90	5.77	6.48
C ₈	2.93	1.70	1.76
C ₁₀	2.11	1.20	1.20

^a Based on unreduced catalyst^c Based on reactor volume^b Maximum axial temperature difference^d Unanalyzed products collected from hot trap

Table 2 (cont'd). Summary of results for fixed bed run FB-99-2290 .

Weight % of Hydrocarbons	Period		
	1	2	3
CH ₄	7.00	7.35	6.88
Ethane	2.58	2.53	2.41
Ethylene	3.33	3.27	3.10
Propane	1.24	1.25	1.24
Propylene	7.96	8.25	7.80
n-Butane	1.06	1.21	1.14
1+2 Butenes	6.02	6.71	7.10
C ₄ Isomers	.490	.532	.492
n-Pentane	.990	1.14	1.38
1+2 Pentenes	5.26	5.93	6.32
C ₅ Isomers	.738	.819	.761
n-Hexane	.705	.879	.711
1+2 Hexenes	3.12	3.75	2.88
C ₆ Isomers	.872	1.01	1.16
n-Heptane	.626	1.05	.646
1+2 Heptenes	2.24	2.91	1.70
C ₇ Isomers	.638	.805	.724
n-Octane	.574	1.47	.814
1+2 Octenes	1.65	2.46	1.41
C ₈ Isomers	.809	.822	.600
n-Nonane	.387	1.65	.909
1+2 Nonenes	1.18	2.34	1.35
C ₉ Isomers	.273	.347	.138
n-Decane	.388	1.22	.671
1+2 Decenes	.806	1.44	.796
C ₁₀ Isomers	.263	.176	.0515
n-Undecane	.296	.531	8.29
1+2 Undecenes	.474	.497	.356
C ₁₁ Isomers	.108	.0397	.00461
C ₂ -C ₄	22.7	23.8	23.3
C ₅ -C ₁₁	22.4	31.3	31.7
C ₁₂ +	47.9	37.6	38.2
Wax ^d	46.5	36.4	25.0

^d Unanalyzed products collected from hot trap

Table 3. Summary of results for fixed bed run FA-2080 .

Catalyst: 3.50 g^a, 100Fe/3Cu/2K/8SiO₂
 Catalyst volume: 3.10 cc
 Diluent: 35.40 g, Glass beads
 Diluent Volume: 24.00 cc

Period	1	2
Date	07/27/90	07/28/90
Time on Stream (h)	68.5	92.5
Balance Duration (h)	6.0	6.0
Average Temperature (°C)	250.	250.
Maximum Δ Temperature (°C) ^b	5.00	8.00
Pressure (MPa)	1.48	2.17
H ₂ /CO Feed Ratio	.669	.669
Space Velocity (NI/g-cat.h) ^a	1.53	2.12
Space Velocity (NI/g-Fe.h)	2.50	3.48
GHSV (h ⁻¹) ^c	205.	285.
CO Conversion (%)	55.8	51.8
H ₂ +CO Conversion (%)	53.4	49.1
H ₂ /CO Usage	.597	.584
STY (mols H ₂ +CO/g-cat.h) ^a	.036	.047
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	172.	14.1
Weight % of Outlet		
H ₂	2.53	2.52
H ₂ O	.0671	.818
CO	46.1	46.1
CO ₂	37.0	37.0
Hydrocarbons	8.58	8.12
Oxygenates	.400	.464
Wax ^d	5.30	5.04
Yield (g/Nm ³ H ₂ + CO Converted)		
CH ₄	6.12	7.28
C ₂ -C ₄ Hydrocarbons	25.6	30.4
C ₆ -C ₁₁ Hydrocarbons	34.4	39.2
C ₁₂ + Hydrocarbons	120.	133.
Wax ^d	71.1	80.4
Oxygenates	5.37	7.41
Total	192.	217.
1+2 Olefins/n-Paraffin Ratio		
C ₂	2.52	2.52
C ₃	5.32	5.32
C ₄	4.79	4.79
C ₆	3.45	3.47
C ₁₀	2.73	2.71

^a Based on unreduced catalyst^c Based on reactor volume^b Maximum axial temperature difference^d Unanalyzed products collected from hot trap

Table 3 (cont'd). Summary of results for fixed bed run FA-2080.

Weight % of Hydrocarbons	Period	
	1	2
CH ₄	3.20	3.46
Ethane	1.14	1.20
Ethylene	2.68	2.83
Propane	.854	.900
Propylene	4.33	4.56
n-Butane	.782	.824
1+2 Butenes	3.61	3.81
C ₄ Isomers	.339	.357
n-Pentane	1.28	1.35
1+2 Pentenes	3.02	3.18
C ₅ Isomers	.808	.851
n-Hexane	.463	.487
1+2 Hexenes	2.04	2.15
C ₆ Isomers	.451	.475
n-Heptane	.273	.284
1+2 Heptenes	1.20	1.25
C ₇ Isomers	.190	.198
n-Octane	.309	.306
1+2 Octenes	1.05	1.04
C ₈ Isomers	.0321	.0306
n-Nonane	.469	.454
1+2 Nonenes	1.35	1.30
C ₉ Isomers	.252	.240
n-Decane	.618	.597
1+2 Decenes	1.66	1.59
C ₁₀ Isomers	.224	.214
n-Undecane	.717	.695
1+2 Undecenes	1.69	1.62
C ₁₁ Isomers	.363	.346
C ₂ -C ₄	13.7	14.5
C ₅ -C ₁₁	18.5	18.7
C ₁₂ +	64.5	63.4
Wax ^d	38.2	38.3

^d Unanalyzed products collected from hot trap

Table 4. Summary of results for slurry run SB-1910.

Catalyst: 29.50 g^a, 100Fe/5Cu/4.2K/8SiO₂ Slurry liquid: 330.0 g, n-C28Reactor volume: 430. cc^b

Period	1	2	3	4	5	6
Date	07/12/90	07/14/90	07/18/90	07/20/90	07/23/90	07/24/90
Time on Stream (h)	55.0	102.5	201.0	247.0	316.5	346.5
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	250.	250.	258.	258.	258.	258.
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.754	.639	.752	.754	.786	.821
Space Velocity (NI/g-cat-h) ^a	2.03	2.14	2.26	2.38	1.90	2.00
Space Velocity (NI/g-Fe-h)	3.30	3.47	3.67	3.87	3.08	3.25
GHSV (h ⁻¹) ^b	140.	140.	118.	118.	88.6	88.6
CO Conversion (%)	59.2	59.6	66.0	48.3	54.6	46.7
H ₂ +CO Conversion (%)	54.1	56.1	62.2	45.6	51.1	43.4
H ₂ /CO Usage	.602	.545	.650	.658	.671	.692
STY (mols H ₂ +CO/g-cat-h) ^a	.049	.054	.063	.048	.043	.039
P _{CO₂} · F _{H₂} /P _{CO} · F _{H₂O}	21.2	30.6	34.1	31.0	36.6	33.9
Weight % of Outlet						
H ₂	2.74	2.16	2.20	2.98	2.86	3.40
H ₂ O	.780	.467	.554	.383	.395	.367
CO	39.1	38.6	32.1	49.1	43.0	50.5
CO ₂	41.4	44.8	48.6	34.4	38.1	32.5
Hydrocarbons	8.04	7.36	9.35	8.13	10.6	9.49
Oxygenates	.937	.823	1.19	.933	1.26	1.00
Wax ^c	7.06	5.74	6.07	4.07	3.71	2.81
Yield (g/Nm ³ H ₂ + CO Converted)						
CH ₄	6.43	6.16	6.30	7.68	6.85	7.67
C ₂ -C ₄ Hydrocarbons	27.4	24.6	25.4	27.5	26.7	26.7
C ₅ -C ₁₁ Hydrocarbons	44.2	48.4	42.2	48.4	59.0	59.5
C ₁₂ + Hydrocarbons	130.	107.	113.	117.	114.	112.
Wax ^c	97.1	81.7	73.7	67.0	53.7	47.0
Oxygenates	12.9	11.7	14.5	15.4	18.2	16.7
Total	221.	198.	202.	216.	225.	222.
1+2 Olefins/n-Paraffin Ratio						
C ₂	4.28	3.92	3.79	4.89	4.30	4.44
C ₃	4.34	4.23	4.49	4.39	4.28	4.19
C ₄	3.42	3.39	3.31	3.50	3.48	3.26
C ₈	1.57	1.37	1.57	1.65	1.83	1.46
C ₁₀	1.74	1.39	1.01	2.11	1.99	1.92

^a Based on unreduced catalyst^c Unanalyzed wax withdrawn from reactor^b Based on static slurry volume

Table 4 (cont'd). Summary of results for slurry run SB-1910 .

Period	1	2	3	4	5	6
Weight % of Hydrocarbons						
CH ₄	3.10	3.30	3.36	3.83	3.32	3.73
Ethane	.707	.724	.771	.635	.680	.666
Ethylene	2.82	2.65	2.73	2.90	2.73	2.76
Propane	.952	.997	.968	1.00	.961	.984
Propylene	3.95	4.03	4.15	4.20	3.93	3.93
n-Butane	1.03	1.04	1.09	1.04	.980	1.03
1+2 Butenes	3.38	3.40	3.50	3.50	3.29	3.23
C ₄ Isomers	.349	.354	.355	.417	.367	.374
n-Pentane	1.10	1.09	1.02	1.09	1.01	1.07
1+2 Pentenes	3.12	3.10	3.12	3.18	2.90	2.88
C ₅ Isomers	.550	.555	.952	1.10	.763	1.07
n-Hexane	.599	.609	.673	.673	.731	1.02
1+2 Hexenes	2.98	1.82	1.98	1.95	1.85	1.88
C ₆ Isomers	1.06	.661	.740	.762	.982	.742
n-Heptane	.587	.716	.703	.701	.900	.932
1+2 Heptenes	1.67	.967	1.02	1.24	1.85	1.19
C ₇ Isomers	.693	.487	.593	.519	.558	.502
n-Octane	.751	.820	.620	.780	1.27	1.36
1+2 Octenes	1.16	1.10	.958	1.26	2.27	1.95
C ₈ Isomers	.178	.132	.566	.0732	.886	.164
n-Nonane	.615	1.13	.946	.888	1.49	1.68
1+2 Nonenes	1.03	1.35	.969	1.65	2.75	2.82
C ₉ Isomers	.197	.305	.248	.0781	.155	.140
n-Decane	.779	1.53	1.19	.923	1.38	1.67
1+2 Decenes	1.34	2.09	1.18	1.92	2.71	3.17
C ₁₀ Isomers	.423	2.34	1.85	2.57	.185	.261
n-Undecane	.899	.955	1.13	.744	.906	1.25
1+2 Undecenes	1.25	1.72	1.22	1.86	2.70	3.00
C ₁₁ Isomers	.307	2.49	.853	.162	.312	.218
C ₂ -C ₄	13.2	13.2	13.6	13.7	12.9	13.0
C ₅ -C ₁₁	21.3	26.0	22.5	24.1	28.6	29.0
C ₁₂ +	62.4	57.5	60.5	58.4	55.2	54.3
Wax ^c	46.7	43.8	39.3	33.4	26.0	22.9

^c Unanalyzed wax withdrawn from reactor

Table 5. Wax and solids inventory for run SB-1910

TOS (h)	Description
	Slurry loading: 330 g wax, 30 g catalyst
	Wax filtration following reduction: 65 g wax
	Slurry withdrawal for catalyst characterization: 6.05 g (5.55 g of wax, 0.5 g of catalyst)
62	Wax filtration: 16.1 g wax, 1.46 g catalyst
110	Wax removal: 137.5 g wax, 1.48 g catalyst
210	Wax removal: 154.0 g wax, 1.34 g catalyst
254	Wax removal: 134.8 g wax, 1.50 g catalyst
324	Wax removal: 122.2 g wax, 1.20 g catalyst
354	Wax removal: 125.3 g wax, 1.52 g catalyst
387	End of run: Slurry withdrawal for catalyst characterization: 10 g (9.35 g of wax, 0.65 g of catalyst)
	Slurry from the reactor: 299.5 g wax, 14.8 g catalyst
	Recoveries: 113% for wax; 77.3% for catalyst

Table 6. Summary of results for slurry run SB-2270.

Catalyst: 9.70 g^a, 100Fe/5Cu/4.2K/16SiO₂

Slurry liquid: 289.0 g, n-C28

Reactor volume: 394. cc^b

Period	1	2	3	4	5
Date	08/16/90	08/18/90	08/21/90	08/26/90	08/28/90
Time on Stream (h)	45.0	93.5	162.0	284.5	332.0
Balance Duration (h)	14.0	20.0	20.0	11.5	14.0
Average Temperature (°C)	260.	260.	260.	260.	260.
Pressure (MPa)	1.48	1.48	1.48	2.17	2.17
H ₂ /CO Feed Ratio	.689	.689	.689	.689	.661
Space Velocity (NI/g-cat-h) ^a	1.37	1.37	1.37	2.30	2.14
Space Velocity (NI/g-Fe-h)	2.40	2.40	2.40	4.04	3.75
GHSV (h ⁻¹) ^b	33.7	33.7	33.7	56.6	52.6
CO Conversion (%)	68.7	67.2	64.9	35.2	46.5
H ₂ +CO Conversion (%)	65.7	64.2	61.7	34.5	44.2
H ₂ /CO Usage	.613	.612	.604	.656	.578
STY (mols H ₂ +CO/g-cat-h) ^a	.040	.039	.038	.035	.042
P _{CO₂} · P _{H₂} / P _{CO} · P _{H₂O}	19.0	20.9	22.5	6.80	9.22
Weight % of Outlet					
H ₂	1.85	1.92	2.05	3.11	2.73
H ₂ O	.904	.786	.706	1.08	1.10
CO	30.0	31.5	33.6	61.2	51.6
CO ₂	49.1	47.3	45.8	25.4	33.7
Hydrocarbons	6.97	8.22	10.0	6.64	6.76
Oxygenates	.587	.447	.521	.296	.356
Wax ^c	10.5	9.80	7.32	2.23	2.76
Yield (g/Nm ³ H ₂ + CO Converted)					
CH ₄	6.71	8.65	9.78	9.16	8.24
C ₂ -C ₄ Hydrocarbons	25.9	32.5	39.9	39.1	37.2
C ₅ -C ₁₁ Hydrocarbons	25.7	35.5	40.6	38.1	34.5
C ₁₂ + Hydrocarbons	146.	139.	127.	115.	105.
Wax ^c	123.	118.	91.7	50.6	66.2
Oxygenates	6.88	5.36	6.53	6.70	6.26
Total	212.	221.	224.	208.	192.
1+2 Olefins/n-Paraffin Ratio					
C ₂	1.27	1.37	.846	1.38	1.55
C ₃	4.99	4.74	4.85	4.49	4.32
C ₄	4.34	4.25	4.29	4.03	3.83
C ₅	2.28	2.19	2.40	2.42	2.87
C ₁₀	1.48	2.01	1.99	2.60	2.95

^a Based on unreduced catalyst^c Unanalyzed wax withdrawn from reactor^b Based on static slurry volume

Table 6 (cont'd). Summary of results for slurry run SB-2270 .

Period	1	2	3	4	5
Weight % of Hydrocarbons					
CH ₄	3.28	4.00	4.50	4.55	4.44
Ethane	1.57	2.04	2.65	2.03	2.29
Ethylene	1.85	2.60	2.10	2.62	3.33
Propane	.854	1.03	1.32	1.53	1.62
Propylene	4.07	4.65	6.13	6.55	6.67
n-Butane	.784	.870	1.12	1.25	1.20
1+2 Butenes	3.29	3.57	4.63	4.88	4.45
C ₄ Isomers	.251	.290	.409	.582	.481
n-Pentane	.748	.791	1.00	1.07	.815
1+2 Pentenes	2.88	3.07	3.83	3.86	2.90
C ₅ Isomers	.374	.424	.604	.831	.714
n-Hexane	.414	.456	.453	.655	.684
1+2 Hexenes	1.25	1.97	1.59	2.04	2.20
C ₆ Isomers	.422	.520	.605	.976	1.08
n-Heptane	.270	.354	.496	.492	.537
1+2 Heptenes	.792	1.20	1.24	1.28	1.48
C ₇ Isomers	.210	.303	.362	.927	.969
n-Octane	.211	.451	.547	.480	.487
1+2 Octenes	.473	.971	1.29	1.14	1.37
C ₈ Isomers	.132	.393	.273	.157	.153
n-Nonane	.447	.689	.653	.620	.685
1+2 Nonenes	.749	1.14	1.42	1.24	1.41
C ₉ Isomers	.0342	.0786	.151	.101	.125
n-Decane	.626	.605	.639	.355	.339
1+2 Decenes	.916	1.20	1.25	.912	.985
C ₁₀ Isomers	.156	.111	.169	.119	.154
n-Undecane	.477	.554	.686	.499	.363
1+2 Undecenes	.682	1.000	1.21	.989	.988
C ₁₁ Isomers	.278	.130	.192	.224	.199
C ₂ -C ₄	12.7	15.0	18.4	19.5	20.1
C ₅ -C ₁₁	12.5	16.4	18.7	19.0	18.6
C ₁₂ +	71.5	64.5	58.5	57.0	56.9
Wax ^c	60.1	54.4	42.2	25.2	35.7

^c Unanalyzed wax withdrawn from reactor

Table 7. Wax and solids inventory for run SB-2270

TOS	Description
	Slurry loading: 289 g wax, 10.0 g catalyst
	Wax filtration following reduction: 70.8 g
	Slurry withdrawal for catalyst characterization: 10 g (9.7 g of wax, 0.3 g of catalyst)
184	Wax filtration: 194 g
249	Wax addition: 65 g
372	Wax filtration: 137 g
400	End of run: 170 g of wax and 9 g of catalyst were recovered from the reactor. Wax recovery: 78%; Catalyst recovery: 92.6%

Figure 1. Volumetric contraction versus time on stream for run FB-1920

Figure 2. Stability plot, (H₂+CO) conversion versus time on stream, for run FB-1920

Figure 3. Volumetric contraction versus time on stream for run FB-2290

Figure 4. Stability plot, (H₂+CO) conversion versus time on stream, for run FB-2290

Figure 5. Anderson-Schulz-Flory plot for run FB-2290 (Balance#1),
total products excluding wax

Figure 6. Volumetric contraction versus time on stream for run SB-1910
(weights indicate amount of wax withdrawn)

Figure 7. Stability plot, (H₂+CO) conversion versus time on stream for run SB-1910

Figure 8. Volumetric contraction versus time on stream for run SB-2270

(weights indicate amount of wax withdrawn (-) or added (+))

Figure 9. Stability plot, (H₂+CO) conversion versus time on stream, for run SB-2270

**DATE
FILMED**
8 / 17 / 92