DOE/CE/15433-T3

DE92 015723

IMPROVED METHODS TO MANUFACTURE ALUMINUM

FINAL REPORT

CONTRACT No. DOE-FG01-89CE15433

PERIOD COVERED

May 17, 1989 to March 16, 1992

June 15, 1992

ELECTROCHEMICAL TECHNOLOGY CORP.

1601 Dexter Ave. North

Seattle, WA 98109

Phone (206) 285-7404

MASTER

SUMMARY

A low-temperature (750°C) process to produce aluminum, employing dimensionally-stable electrodes, was investigated under this contract. Tests were carried out at a 10-ampere scale to develop a nonconsumable anode and to evaluate certain cell operating parameters. The work was carried out in conjunction with a NSF SBIR research grant to study the fundamental science aspects of the process. A scaled up 300-ampere cell was built and a preliminary test run was made with encouraging results. The new technology has the promise of producing aluminum at 5.0 kWh/lb as compared to the U.S. average of about 7.5 kWh/lb, and to produce it at lower cost. Preliminary technical discussions have been held with a major U.S. aluminum company under secrecy agreement for eventual licensing.

INTRODUCTION

At the time the proposal for this work was submitted, Electrochemical Technology Corp. (ETC) and a collaborating company, Brooks Rand Ltd. (BRL) were pursuing funding to investigate two modified technologies to produce primary aluminum metal. Both technologies would use modified molten cryolite electrolytes and operate at about 750°C or about 200°C lower temperature than the standard one-hundred year old Hall-Heroult process. We predicted higher energy efficiencies for both new technologies. The lower temperature of operation is less corrosive on materials and would permit some new cell designs.

The first modified technology was based on use of a composite anode of carbon and alumina in stoichiometric proportions. The composite anode feeds alumina directly to the site at which it is consumed, the anode-electrolyte interface, at which the alumina solubility in the electrolyte is too low for standard operation. Earlier laboratory tests made on this

technology, supported by Metallurgical Inc. in Cleveland, Ohio, showed the feasibility, but new concepts had to be demonstrated to scale up to a practical commercial cell. ETC and BRL developed some new concepts for scaleup. Metallurgical Inc. owned three basic patents on the technology (1-3) and ETC and BRL made an agreement with Metallurgical for further development and marketing.

In the meantime ETC and BRL developed concepts for an alumina-slurry electrolyte cell. Alumina particles would reach the anode-electrolyte interface from the electrolyte side instead of from the anode side, and the particles dissolve within the anode diffusion layer. A new nonconsumable cermet anode announced by Alcoa (4), combined with the low-temperature slurry electrolyte again offered the promise of higher energy efficiency. ETC and BRL obtained two patents on the slurry technology (5, 6).

ETC and BRL decided to try to obtain funding to evaluate both technologies. The composite anode was further developed than the slurry electrolyte and appeared to have lower risk. On the other hand, the slurry technology would have lower operating costs if successful.

The composite anode was pursued first with the DOE-NBS Energy Related Inventions Program (ERIP). A proviso was put in the proposal that the 300 ampere cell composite anode cell be designed so that it could be converted to slurry operation. Then an opportunity came to submit a proposal to the NSF SBIR program to work on the slurry concept. The NSF Phase I SBIR grant was awarded before the ERIP contract. It turned out that the slurry concept was eminently successful, and ETC and BRL obtained a third patent based on the Phase I SBIR work (7). Preliminary work on the ERIP contract indicated that our scaleup concepts for the composite anode were more difficult to implement than anticipated. We therefore requested and were granted a change of

the focus of the ERIP work to the slurry electrolyte concept. This report describes work on both concepts.

The budget available on the ERIP contract allowed only a limited amount of laboratory tests and building a 300 ampere pilot scale cell system. Operation of the 300 ampere cell awaits further funding from another source. We have had preliminary technical discussions with a major U.S. aluminum company under secrecy agreement, and it has shown an interest in the technology. We are pursuing other government funding to enable demonstration runs with the 300 A cell to develop a business interest in the slurry technology.

LABORATORY TESTS

Composite Anode Tests

The preliminary laboratory work was carried out at ETC. The 300 ampere cell was to be built and operated at the pilot plant facilities of BRL.

A cell and furnace were assembled and an anode pressing die was obtained. Composite anode pieces were mixed, pressed, and baked. Aluminum cladding was cast on the circular anode segments and four segments were bonded together with graphite cement to make a vertical anode stack that could be tested in the 25 ampere cell. The purpose of the initial experiments was to evaluate the integrity of the inter-segment bonding and the effectiveness of the aluminum cladding concept for conducting current to the anode and protecting it from airburn. The inter-segment bonding worked very well on this 25 A laboratory scale. The aluminum cladding concept appears to be viable, but we had to make several changes to solve a contact resistance problem.

A drawing of the anode pressing die is given in Fig. 1. Anode paste was mixed in a bowl with a spoon. The alumina was Alcoa grade A-3. The binder was UCAR Phenolic Resin Solution

- ① & ② : Tool steel
 ③, ④, ⑤, ⑥ : Mild steel
 10-32 Allen head screws

Fig. 1 Anode press.

BRL-1100. (Ultimately, coal tar pitch or petroleum pitch would be used in a plant, but the resin was much easier to use on a laboratory scale.) A Carver 12-ton press was used to apply pressure to the die. The 1"-inch thick anode segments were baked in a bed of calcined petroleum coke to a temperature of about 1000°C.

A 1/8"-thick layer of aluminum was cast around the circumference of each 2"-diameter anode segment. Some practice was required to obtain perfect casts. The segments were bonded together with Dylon Grade GC graphite cement.

The completed anode was clamped in the cell as shown in the drawing in Fig. 2 and the photograph in Fig. 3. The anode clamp could be moved down as the anode was consumed. A low-ratio cryolite containing about 7 wt% LiF, with a primary freezing point of about 660°C was used. Prior work on the NSF Phase I SBIR grant provided a background on suitable bath compositions. The cell operating temperature was about 750°C.

The first cell experiment showed that a high resistance developed between the aluminum cladding and the composite segment. Calculations showed that the aluminum band was stressed beyond its elastic limit by differential contraction compared to the composite on cooling after casting. Reheating in the cell opened the gap. This is a problem peculiar to the small laboratory anodes and not with larger scale plant cell anodes. To solve this problem a longitudinal slot was cut in the aluminum band, and it was put under greater pressure in the cell anode clamp. Tests made on contact resistance versus applied pressure showed that a satisfactorily low resistance can be achieved, as shown in Fig. 4.

Five further experiments of varying success were made with the aluminum-clad segmented anodes. No problem was had with the adhesive joint between blocks. Some airburn occurred at the

Fig. 2 Composite anode cell.

Fig. 3 Photograph of cell.

Fig. 4 Area resistivity of composite anode contact versus pressure.

joints between anode segments and at the slot, and graphite cement was painted on the surface to try to control it. The thermal balance in the anode was such that melting of the cladding occurred at a desired 1/4" above the bath as shown in Fig. 5. An unanticipated peripheral problem was that differential thermal expansion of the stainless steel can versus the graphite crucible broke electrical contact to the crucible during the runs giving voltage rises like anode effect. This problem was solved by packing petroleum coke between the can and the crucible instead of using graphite cement. Experiments continued to evaluate the aluminum cladding concept for conducting current to the composite anode and for preventing surface airburn.

Three more composite anode cell runs were made. Several problems occurred that suggested revision of the program. Airburn continued to be significant on any part of a composite anode not covered by aluminum skin. Significant dusting of carbon also occurred which fouled the bath. Our anode quality was not the problem because a piece of composite anode made by J.C. Withers in Cleveland in 1980 and successfully used by him in a laboratory cell also suffered from airburn and dusting. Another unexpected occurrence was that the one-inch thick molten aluminum cathode put on the bottom of the cell inverted and shorted to the anode. These problems may have been due to use of all-fluoride baths containing NaF-LiF-AlF₃ operated at about 750°C instead of all-chloride baths or mixed chloride-fluoride baths at about 700°C used by Withers.

A lower-melting Na₃AlF₆-LiF-NaCl eutectic with primary freezing point of 642°C was used in the last two runs at an operating temperature of 700°C. The airburn and carbon dusting problems were decreased for both the Withers anode and our aluminum clad anode. The bad effect was that the chloride-containing bath was extremely corrosive and destroyed the stainless steel can around the cell and the furnace elements. As

Fig. 5 Temperature gradient
in anode.

the bond between composite anode blocks came within 1/4 inch of the bath in the last run, the joint came apart. Although we believe we could eventually overcome these problems, they appeared to need more time and funds than were budgeted in this contract.

Fortunately we had an alternative promising approach. This is the alumina slurry electrolyte cell mentioned in our August 20, 1987, proposal to the ERIP on p 12. Subsequent to submission of the ERIP proposal and before funding, we submitted a proposal and received an NSF Phase I SBIR contract for exploratory investigation of the slurry cell concept. The slurry cell operation had many fewer problems than the composite anode cell and appeared to have better economics for an aluminum plant retrofit. The situation was discussed by phone with the then Contract Monitor, Lester Lee, and at a meeting in Washington, DC, on October 20, 1989. He thought that it was feasible to make the minor changes in the work statement and a request was sent to ERIP on November 14, which was agreed to by phone November 29, 1989.

Slurry Cell Laboratory Tests

A total of 31 runs were made in the 10-ampere slurry cell illustrated in Fig. 6. The 10-A cell tests made to evaluate materials and conditions proposed for the 300-A cell included:

- Electrode configuration
- Al_2O_3 particle size
- Limiting current density versus Al_2O_3 slurry concentration
- Bath velocity and settling of Al_2O_3 particles
- Performance of TiB_2 cathode in low temperature bath
- Performance of a new non-consumable alloy anode material

A suitable low-temperature bath composition had already been discovered during the NSF SBIR work.

Prevention of settling of the Al_2O_3 particles to form "muck" on the bottom of the cell is one of the most serious problems

a) Bottom anode

b) Annular anode

Fig. 6 10-A Slurry cells

- is TiB_2 rod

+ is Cu or non-consumable anode

with the slurry cell. This can be accomplished by use of a horizontal anode on the bottom of the cell as shown in Fig. 6a. Oxygen gas from the anode keeps the alumina fluidized in the bath. Interestingly, the aluminum metal produced at the cathode and falling to the anode does not react with the anode and destroy it. On the other hand, some current efficiency is lost by reaction of the aluminum with the small oxygen bubbles flowing around it. Calculations of flow velocities generated by oxygen from the anode for the configuration in Fig. 6b indicate that the alumina should not settle, but some muck formation did occur. Fluid dynamic design remains an important task for the slurry cell. Calculations indicate that this problem should diminish for larger cells with higher bath velocities.

Titanium diboride cathodes were used repeatedly in run after run with no problem of thermal shock. Literature data on corrosion rate in Al_2O_3 -cryolite indicate low corrosion rate at 750°C . We predict that TiB_2 cathodes will become practical in the low-temperature slurry cell. Conditions are much milder than in conventional Hall-Heroult cells at 960 - 980°C , in which they have not yet become practical.

The laboratory testing of the slurry cell under the ERIP contact was completed in January 1990. Design and building the 300 A cell was delayed until the fall of 1991 in order to obtain more laboratory experience with the slurry concept and our new metal anode under the NSF Phase II SBIR.

300 A Slurry Cell

The 300 A slurry cell design went through many iterations and the final one is shown in Fig. 7. The cell consists of a cast metal anode vessel in a firebrick insulated steel shell. The vessel is heated by ac heating elements on its four outside vertical faces. Two titanium diboride cathodes 4 in. x 5 in. x 1/2 in. were immersed in the electrolyte, with a 4 in. x 5 in. x 1/4 in. alloy anode in between them. The anode-cathode spacing

SECTION B-B

A-A
SECTION

Fig. 7

300 A CELL

1/4 SCALE

TRB 10-24-91

was 1/2-inch. Stainless steel straps conducted current to the electrodes. The bottom of the cell was sloped so that aluminum formed would collect at one end for siphoning. Alloy for the anodes was induction melted and cast in sand molds at a local foundry. Four different attempts were made to obtain sound castings with the new alloy, which delayed startup of the cell.

Views of the electrodes and anode vessel prior to cell assembly are shown in Fig. 8. Views of the assembled cell are given in Fig. 9. Continuous electrolyte temperature measurement can be made with a thermocouple in an alumina tube because the electrolyte is saturated with alumina. Continuous temperature measurement is not economically feasible in conventional Hall-Heroult cells. The insulating firebrick around the anode vessel can be seen in Fig. 9a. The fume hood and siphon for removing electrolyte are seen in Fig. 9b. A view of the fume scrubber is given in Fig. 10a. An overall view of the cell system showing the 500 A rectifier, the cell, hood, and stripchart recorder is given in Fig. 10b.

A preliminary test run was made on March 13, 1992. The electrolyte composition was the eutectic 44 mol% AlF_3 , 56 mol% NaF . Heatup to operating temperature of 750°C and complete melting of electrolyte took five hours. Two hours of electrolysis at 300 amperes followed. Cell voltage was constant at 3.5 volts. A polarization curve for the cell in Fig. 11 shows that the voltage extrapolates to about 2.3 V, the thermodynamic potential, at zero current. Unfortunately the electrolyte composition drifted to lower AlF_3 concentration during the run, and cryolite deposited on the cathodes as seen in Fig. 12. This condition, we have found in 10 A cell tests, prevents wetting of the TiB_2 cathodes, giving dropwise formation of aluminum and low current efficiency. The condition is corrected by maintaining the electrolyte composition closer to the eutectic. The current efficiency in this run was 3% compared to an average 60% for the 10 A cell runs. We predict that filmwise deposition of aluminum

a. Electrodes
(upside down)

b. Anode Vessel

Fig. 8 Electrodes and anode vessel.

a. Top of cell
showing
electrodes
and
thermocouple

b. Side view
of cell
showing
hood and
bath
siphon

Fig. 9 Views of assembled cell.

a. Fume scrubber

b. Rectifier, cell, hood,
stripchart recorder

Fig. 10 Views of cell system.

Fig. 11 Current-voltage curve for cell.

a. Electrodes

b. Anode vessel

Fig. 12 Electrodes and
anode vessel
after trial run.

on TiB_2 and continuous siphoning of aluminum should give above 95% current efficiency for the 300 A cell.

The cell voltage at the design current density of 0.5 A/cm^2 for 300 A is about a volt lower than for the best equivalent Hall-Heroult cell as shown in Fig. 11. The reasons for this result, in spite of a one-volt higher thermodynamic potential to produce O_2 rather than CO_2 , are as follows. First, the kinetic overpotential at an O_2 producing anode is about 0.5 volts lower than that for a CO_2 producing anode. Second, the approximately 0.6 volt loss in carbon anodes and cathodes in Hall-Heroult cells is eliminated. Third, the anode-cathode spacing is decreased from about 1-3/4 inches to 1/2 inch, and the actual current density is decreased by about a factor of two. Each electrode in the slurry cell has two sides versus one side each in the Hall-Heroult cell so the slurry cell can operate at half the current density of a Hall-Heroult cell. In spite of the lower conductivity of the low-ratio, low-temperature slurry-cell electrolyte, the slurry cell has a lower bath ohmic loss. The overall balance for the slurry cell is thus

ΔE°	+1.0 V
Δ overpotential	-0.6 V
Δ carbon IR	-0.6 V
<u>Δ bath IR</u>	<u>-0.8 V</u>
$\Sigma \Delta$ voltage	-1.0 V

The projected specific energy consumption for the 300 A cell at 3.5 V and 95% current efficiency is 5.0 kWh/lb, based on the formula

$$\text{kWh/lb Al} = \frac{135 \times \text{cell voltage}}{\% \text{ current efficiency}} \quad (1)$$

The average for the United States is about 7.5 kWh/lb for the Hall process and 6 kWh/lb for the most modern cells. The Hall process consumes carbon to produce polluting CO_2 .

The slurry process with the nonconsumable anodes produces oxygen.

The savings in carbon, energy, and labor for the slurry cell process could amount to a calculated 10 ¢/lb out of a mill cost today of about 60 ¢/lb. Fig. 13 shows a conceptual schematic (7) of a commercial slurry cell and Fig. 14 shows a comparison of size of a 200 kA slurry cell to a conventional 200 kA Hall-Heroult cell.

Fig. 13 Concept of vertical electrode slurry cell;
a. Plan; b. Section 2-2 (Ref. 7).

Fig. 14 Isometric comparison of size of conventional Hall-Heroult cell to slurry cell; 200 kA; 6 ft man.

CONSULTANT

The contributions of Consultant, Prof. Jomar Thonstad from Trondheim, Norway, which have helped the development are acknowledged here. In particular he has contributed to prediction of bath properties and rate of TiB_2 corrosion, and to analysis of non-consumable anode behavior.

REFERENCES

1. J.C. Withers and G.V. Upperman, Electrolytic Cell for the Production of Aluminum, U.S. Patent 4,338,177, July 6, 1982.
2. J.C. Withers and G.V. Upperman, Composite Anode for the Electrolytic Deposition of Aluminum, U.S. Patent 4,342,637, August 3, 1982.
3. J.C. Withers and G.V. Upperman, Process for the Electrolytic Deposition of Aluminum Using a Composite Anode, U.S. Patent 4,670,110, June 2, 1987.
4. J.D. Weyand, et al., "Inert Anodes for Aluminum Smelting," Final Report, DOE/CS/40158, Alcoa Laboratories, February, 1986.
5. T.R. Beck and R.J. Brooks, Method and Apparatus for Electrolytic Reduction of Alumina, U.S. Patent No. 4,592,812, 1986.
6. T.R. Beck and R.J. Brooks, "Electrolytic Reduction of Alumina," U.S. Patent No. 4,865,701, 1989.
7. T.R. Beck and R.J. Brooks, "Electrolytic Reduction of Alumina," U.S. Patent No. 5,006,209, 1991.

END

**DATE
FILMED**

7 / 27 / 92