GEOTHERMAL WASTE TREATMENT BIOTECHNOLOGY

BNL--46301

DE91 014796

Eugene T. Premuzic and Mow S. Lin

May 1991

Prepared for presentation at the International Conference - Heavy Metals in the Environment, Edinburgh, Scotland, September 16-29, 1991.

**BIOSYSTEMS AND PROCESS SCIENCES DIVISION
DEPARTMENT OF APPLIED SCIENCE
BROOKHAVEN NATIONAL LABORATORY
ASSOCIATED UNIVERSITIES, INC.
UPTON, NY 11973**

*Under Contract No. DE-AC02-76CH00016 with the
U.S. Department of Energy*

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

E.T. Premuzic*, M. Lin*

ABSTRACT

Technical feasibility of a biotechnology based on biochemical reactions for detoxification of geothermal brines has been demonstrated. Laboratory-scale studies have shown that the emerging biotechnology is versatile and is applicable to a variety of geothermal sludges and materials with similar geochemical properties. Materials suitable for treatment are those which may contain few or many metals in concentrations exceeding those allowed by regulatory agencies. Comparison of several possible types of bioreactors and processes have led to the conclusion that a number of variables have to be considered in the design and development of a biochemical plant for the detoxification of geothermal type sludges. These include reactor size, effects of agitation, mixed cultures, state of the biomass, pH and dissolved oxygen, concentration of residual sludge, residence time, and temperature. Under optimum conditions, high rates of metal removal can be achieved. For example, 80-90% removal efficiency has been reached for metals such as chromium, copper, and manganese. Some recent studies, dealing with the process variables and their optimization, will be discussed.

INTRODUCTION

For the past several years the geothermal research and development effort in this laboratory has been aimed at the development of biochemical processes for the treatment of wastes and by-products generated in the production of geothermal power (ref 1-3). The ultimate goal is to develop an environmentally acceptable, economically and technically feasible biotechnology for the removal and concentration of toxic metals present in the residual sludges associated with the power production. Such biotechnology is particularly useful when large quantities of wastes are present which contain low, however environmentally significant concentration of metals, disposal of which is regulated. It has been shown that a number of process variables are essential and have to be considered in the design of biotreatment processes. For example, mixtures of selected strains of acidophilic bacteria in certain proportions are more efficient than each strain alone (ref 4). In addition to the increased efficiency of mixed cultures, several other parameters have to be considered. These include reactor size and type, mode of mixing, addition of biomass, pH and dissolved oxygen, sludge concentration and temperature. Development of thermoadapted acidophilic microorganisms has allowed to consider a process operating at 50-60°C and pH 1-2. Under these operating conditions fast and highly efficient metal solubilization kinetics can be achieved. Currently two types of bioreactors, an agitated tank and a fluidized bed, are being considered and their applications optimized.

OUTLINE OF STUDY AND MATERIALS

Experimental procedures have been reported elsewhere (ref 3). In the present work analyses have been carried out in triplicate, both in solid and liquid phases. Two types of bioreactors have been constructed out of plastic materials (Plexiglas) for ambient and out of glass for elevated temperature studies. For sake of expedience, atomic adsorption was used in routine kinetic studies and limited to four representative metals, copper, zinc, manganese and lead. Detailed multielement analyses have also been carried out with an Induced Coupled Plasma Mass Spectrometer (ICP-MS) VG-Plasma Quad 2 instrument. Four different concentrations of geothermal sludge, 10%, 20%, 30% and 40% have been used in the studies reported in this paper.

RESULTS

Interaction between microbial biomass and geothermal sludge involves an attachment of microorganisms to the substrate (ref 3) followed by enzymatic solubilization of metal salts. Therefore, for an efficient process, good mixing of the solid and liquid phases during the residence time is critical. Further, the biomass is pregrown and then mixed with the substrate in a bioreactor. In the present work two waste treatment plants have been considered, one using a fluidized bed and the other an agitated bioreactor. A process flow diagram for an agitated tank bioreactor system is shown in fig. 1. In this process, agitated tank and fluidized bed bioreactor are interchangeable. Processes using either bioreactor are similar, except that the fluidized bed bioreactor when replaced by an agitated tank allows for a process which requires a much smaller air supply. This is a significant cost-efficiency factor, because a large air compressor needed in the fluidized bed is replaced by a cheaper stirrer used in the agitated tank. Details of the cost analyses have been discussed elsewhere (ref 5). The process shown in fig 1 is designed to handle 80,000 lb/day of geothermal waste contained in a 65% filter press cake generated by a 50 MW double flash plant. The initial sludge is sent from a brine solid separation plant to the bioreactor via a conveyor belt at an average rate of 123,000 lb/day. Preliminary analyses of the processes shown in fig 1 have shown that the biotreatment is economically and technically feasible (ref 5). In the process, stream 1 and 2 are mixed in the bioreactor. The bioreactor outflow (stream 4) is sent to a filter press where it is concentrated into a solid cake which is the non-hazardous solid waste product. At this stage, if the solid product still exceeds regulated concentrations of toxic metals, it can be recycled to the geothermal sludge holding tank (stream 5) and reprocessed. The liquid which passes through the filter press (stream 3) can be

*Department of Applied Science, Brookhaven National Laboratory, Upton, New York 11973

BIOLOGICAL WASTE-TREATMENT PLANT USING AGITATED TANK BIOREACTOR

Fig. 1 Process flow diagram for biochemical waste-treatment plant.

recycled or be sent to a neutralization drum (stream 6) at pH ~4. The liquid is then pumped through another filter to collect any precipitated solids and bacteria from the neutralization step. The filtrate from press 2 is then pumped down a re-injection well (stream 9). The solids at filter press 2 may be sent to a metal recovery plant.

The effects of sludge loading and temperature on residence time are shown in fig 2 for copper. An 80% removal of copper is achieved in 25 hours in either the fluidized bed or agitated tank bioreactor. The overall efficiency applies to other metals as shown in fig 3. The results of kinetic studies show

Fig. 2 Rates of removal of copper using fluidized and tank type bioreactors at 55° and different sludge concentration.

Fig. 3 ICP-MS analysis of mercury and lead contents in geothermal sludge. A untreated, B treated.

Fig. 3 ICP-MS analysis of rubidium and strontium contents in geothermal sludge. A untreated, B treated.

that there is an initial rapid removal of metals, followed by a drop, suggesting that several biochemical mechanisms are involved. From a process design point of view the initial rapid phase is important because it removes most metals to levels below the total regulated threshold limiting concentrations (ref 6) within a biotreatment period of 25 hours. Concurrent studies in this laboratory are also considering the metal option recovery (ref 5) which may become an integral part of the detoxification process, both for environmental and economic reasons. The emerging biotechnology is promising and is sufficiently flexible that it may be applied to similar materials of geological origin. Optimization of process variables will further improve on the efficiency of metal removal. Because of temperature and acidity factors, materials to be used in the construction of bioreactors and other key components of a biotreatment plant are being considered in the continuing phases of this R&D effort.

ACKNOWLEDGMENTS

This work has been sponsored by the U.S. Department of Energy, Division of Geothermal Technology, under Contract No. AM-35-10 and by Brookhaven National Laboratory and the U.S. Department of Energy under Contract No. DE-AC02-76CH00016.

REFERENCES

1. E T Premuzic, M Lin, The Role of Biotechnology in the Treatment of Geothermal Residual Sludges, Seventh International Conference on "Heavy Metals in the Environment," Proceedings, 2, 60-63 (1989).
2. E T Premuzic, M S Lin and S K Kang, Developments in Geothermal Waste Treatment Biotechnology, Proceeding VIII, Geothermal Program Review, CONF-9004131, 41-47 (1990).
3. E T Premuzic, M S Lin, L E Kukacka, and R D Sproull, Applications of Biotechnology in the Removal of Toxic Metals from Geothermal Residual Sludges, Geothermal Sci. & Tech. 2(3), 139-160 (1990).
4. E T Premuzic and M S Lin, Patent Pending 1991.
5. E T Premuzic, M S Lin, S Kang, Advances on Geothermal Waste Treatment Biotechnology, in press, Conference Proceedings, Geothermal Program Review IX, CONF-913105, 77-84 (1991).
6. B A Royce, An Analysis of Environmental Regulations Governing the Disposal of Geothermal Waste in California, BNL Report 37577 (1985).

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.