Report for the period 10/1/91 to 12/31/91

DoE Grant DE-FG22-91PC91302

HYDROTHERMAL REACTIONS OF FLY ASH

Paul W. Brown

168 MRL

DOE/PC/91302--1

Penn State University

DE92 013719

University Park PA 16802

ABSTRACT

The reactions which occur when fly ash is treated under hydrothermal conditions will be investigated. This will be done for two primary reasons. The first of these is to determine the nature of the phases that form, to assess the stabilities of these phases in the ambient environment and, finally, to assess whether these phases are capable of sequestering hazardous species. The second reason for undertaking this proposed study is that, depending on the composition of the ash and the presence of selected additives, it may be possible under hydrothermal conditions to form compounds which have cementitious properties.

Formation of four classes of compounds, which bracket likely fly ash compositional ranges, have been selected for study. These are calcium silicate hydrates, calcium silicosulfates, calcium aluminosulfates, and alkali aluminosilicates. The specific compounds fabricated will be determined and their stability regions assessed. As a part of stability assessment, the extent to which selected hazardous species are sequestered will be determined. Finally, the cementing properties of these compounds will be established.

US/DOE Patent Clearance is not required prior to the publication of this document.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PROGRESS

This is the initial report for this program.

During this period two fly ashes, one high lime and one low lime, were acquired and analyzed. The results of chemical analyses are attached.

An initial study to determine the intrinsic reactivity of these ashes has been carried out. This was done by isothermal calorimetry. In the method used a known amount of ash (typically 3 grams) is placed in a gold plated copper calorimetric sample holder. This is then thermally equilibrated to the temperature of reaction. An aqueous reactant is separately equilibrated to the same temperature. Once equilibrium has been achieved, the liquid is inoculated onto the solid and the heat of reaction measured. These experiments were carried out at 25, 38, and 60°C on the two ash samples.

Results of calorimetric tests on two types of fly ashes with and without alkaline activators at different temperatures are reported. The technique is used to identify and monitor the progress of reaction of two types of fly ash reacted with various alkaline activators. The results showed that there are distinct differences in the manner in which the different ash pastes hydrated at different conditions. Using alkaline activators, it may be possible to produce a fly ash based material with the desirable chemical reactions and physical properties.

1. Reactivity of raw materials

Figure 1. shows the heat evolved during hydration for raw materials at 38°C. It can be seen that the high-lime fly ash has direct cementitious activity between the ash and water and shows pozzolanic reactivity, but the low-lime ash tested here shows poor reactivity.

2. Effect of temperature

The sample measured at elevated temperature (60°C) followed the same trend as the one at lower temperature (38°C in Fig. 1) as shown in Figure 2. For the low-lime ash, three different temperatures used were: 25°C, 38°C and 60°C, and samples were measured for 24 hours. It was found that no peaks could be observed during this period of time no matter how high the temperature was (A small peak appeared between 3~5 minutes for all samples is treated just as a mixing peaks as shown in Figure 3). For the high-lime ash, however, the sample with high temperature has faster reaction rates (Figure 4) and higher total evolved heat (Figure 5) than sample with low temperature.

PLANNED WORK

In the next quarter, the effects of alkaline activators and calcium sulfate will be evaluated.

LOW LIME ASH

SiO_2	50.2%
Al_2O_3	27.0
TiO_2	1.40
Fe_2O_3	13.8
MgO	0.84
CaO	1.82
MnO	0.034
Na_2O	0.24
K_2O	2.45
P_2O_5	0.49
Totals	98.27%

Ba 1250 ppm

Sr 900

HIGH LIME ASH

SiO_2	36.9%
Al_2O_3	17.5
TiO_2	1.17
Fe_2O_3	5.90
MgO	5.05
CaO	26.14
MnO	0.038
SrO	0.43
BaO	0.62
Na_2O	1.91
K_2O	0.45
P_2O_5	0.97
SO_3	2.10
L.O.I. (1000°)	0.39
TOTAL	99.6%

Reporting Checklist

Marilyn Keane
PM-01, MS 922-206
U.S. Department of Energy
Pittsburgh Energy Technology Center
P. O. Box 10940
Pittsburgh, PA 15236

Norey B. Laug
Contract Specialist
AD-22, MS 921-118
U.S. Department of Energy
Pittsburgh Energy Technology Center
P. O. Box 10940
Pittsburgh, PA 15236

Office of Technology Transfer
Attn: Kay Downey
Mail Stop 58-M217
U.S. Department of Energy
Pittsburgh Energy Technology Center
P. O. Box 10940
Pittsburgh, PA 15236

END

**DATE
FILMED**

7 / 7 / 92