CONF - 300402-15
MASTER

ELECTRONIC STRUCTURE OF NONSTOICHIOMETRIC CUBIC HYDRIDES*

A. C. Switendick
Sandia National Laboratories†
Albuquerque, New Mexico 87185

ABSTRACT

Using the supercell approach we have calculated the electronic structure of Y_4H_8 , Y_4H_9 , Y_4H_{11} , and Y_4H_{12} as prototypic of nonstoichiometric cubic di- and trihydrides. The nature of the interaction between the yttrium and the octahedral and tetrahedral hydrogens is shown by the relative amount of charge contained in the crystal spheres. Each added hydrogen lowers one band which was already partially filled. The charge on both the octahedral and tetrahedral sites is very similar and significantly more than is contained in a comparable atomic sphere.

*This work was supported by the U. S. Department of Energy, DOE, under Contract DE-AC04-76-DP00789.

†A U. S. Department of Energy facility.

DISCLAIMER

This document contains information which is the property of the U. S. Government and is loaned to you by the U. S. Department of Energy. It is to be used for the specific purpose for which it is loaned and is not to be distributed outside your organization. It is to be returned to the U. S. Department of Energy when it is no longer needed. This document is not to be used for any other purpose without the express written permission of the U. S. Department of Energy.

INTRODUCTION

The transition and rare earth di- and trihydrides are perhaps the simplest examples of interstitial compounds with hydrogen occupying an empty region in the filled metal lattice. The dihydride is formed by occupying the tetrahedral site in the face-centered cubic (fcc) lattice and usually forms with a change from the elemental metal structure [1]. The trihydride forms by further occupying the octahedral sites. Except for the light rare earths La, Ce, Pr, and Nd, trihydride formation further engenders a metal lattice change to a hexagonal (hex) one allowing a larger hydrogen-hydrogen separation. Ever since the first proposal [2] there has been increasing evidence of partial octahedral site occupancy before full tetrahedral site occupancy of the ideal dihydride stoichiometry from electron spin resonance [3] neutron diffraction [4] nuclear magnetic resonance [5] and spectroscopic studies [6,7]. Fractional site occupancies are thus observed giving rise to compositions RH_x where R is a rare earth metal and $1.6 \leq x \leq 3.0$. The value of x may span this regime continuously as in the case of the rare earths cited above or may have excluded ranges as in the case of gadolinium where $2.0 < x \leq 2.25$ and $2.8 < x$. For intermediate values of x a two-phase mixture of hyperstoichiometric fcc dihydride and substoichiometric hcp trihydride is found. The specific compositional ranges are rare earth and temperature dependent. Although yttrium falls in this latter category, we shall ignore the specifics of the phase diagram and extend our examination [8] of the electronic structure of this system as a prototypic fcc

hydride system, particularly in view of the experimental work on this system [3-7], using the same potentials and techniques as before [8].

Our approach will be that of the large supercell which has proven useful in studies of the Pd-H [9] and Ni-H [10] systems. We shall investigate the stoichiometric compositions YH_2 and YH_3 and deviations therefrom by this approach.

RESULTS

In order to understand our results for the two nonstoichiometric cases Y_4H_9 and Y_4H_{11} , it is instructive to relate the supercell results for the stoichiometric di- and trihydrides, Y_4H_8 and Y_4H_{12} respectively. The results for YH_2 in the primitive unit cell are given schematically in Fig. 1a. The bands are given in more detail in reference 8. The results of the supercell calculation for Y_4H_8 are given in panel 1b. The fourfold increase of the unit cell volume results in a fourfold decrease in the Brillouin zone volume with a four-to-one mapping of k-space. Thus, the three fcc points $X(2,0,0)$, $X(0,2,0)$ and $X(0,0,2)$ map upon Γ with a threefold degeneracy (multi-dimensionality is indicated in parenthesis) $X1 \rightarrow \Gamma 1$, $\Gamma 12(2)$; $X3 \rightarrow \Gamma 25'(3)$; $X4' \rightarrow \Gamma 15(3)$ and the four points $L(1,1,1)$, $L(\bar{1},1,1)$, $L(1,\bar{1},1)$, $L(1,1,\bar{1})$ become fourfold degenerate R's; $L1 \rightarrow R1, R25'(3)$; $L2' \rightarrow R2'$, $R15(3)$; etc. These degeneracies exist because we have not chosen the primitive unit cell in this case. The Fermi energy is determined by filling these bands with $4 \times (3+2) = 20$ valence electrons, but since each band contains two electrons (one of spin up and one of spin down) and we have just four times as many bands as before, the Fermi energy falls at the

same place as for YH_2 . Thus, the first eight bands are full and the remaining four electrons go into the states above Γ_2' which arise largely out of the d-states of the yttrium. The first bands are the so-called hydrogen associated bonding/antibonding states. However, as Table I shows these states have substantial charge associated with each yttrium (0.73e) as well as outside the spheres $1.27e/Y$ and within each hydrogen sphere (0.97e). Of the 0.73e on the yttrium over half of it is d-like with the remainder sp-like. As we further fill to the Fermi energy the remaining added electrons are about 0.34e yttrium d-like with 0.59e occupying the interstitial region with only slight addition on the tetrahedral hydrogens. The density of states and component densities of states are shown in Fig. 1c-e.

On adding a hydrogen at the octahedral site, $a\left(\frac{1}{2}, \frac{1}{2}, \frac{1}{2}\right)$ the unit cell now contains nine hydrogens -- the formula Y_4H_9 is the primitive unit and the cubic unit cell (zone) is now appropriate. The effect of this addition is to lower states near the bottom of the d-band having s-like character about this hydrogen eg Γ_1 , X_4' and R_2' as shown in Fig. 2a. There are now nine low-lying bands below the second R_2' . This state is lowered 5 eV and has been shown to be due to a second nearest neighbor octahedral hydrogen-hydrogen interaction [8-11]. Since some of these states were filled in Y_4H_8 , (Γ_1 , X_4' , etc.) the Fermi energy rises by about one half an electron volt to accommodate 0.47 electron in states (the third X_4' , etc.) at the Fermi energy (above that of Y_4H_8) with the remaining 0.53 electron being accommodated in lowered states such as R_2' . The added

potential not only lowers states but changes their character from largely yttrium d-like to hydrogen (octahedral) s-like as Table II shows in the comparison of that band for Y_4H_8 which contains the most octahedral s-character with the corresponding unperturbed states of Y_4H_8 . Charge has left the interstitial region and yttrium d-character and become tetrahedral and octahedral in nature, with half an electron shared among the eight tetrahedral neighbors and half an electron being associated with the octahedral site. Table I shows the total charge on the tetrahedral hydrogens, the yttrium, and in the interstitial region changes very little with a total of about $0.97e$ being associated with the octahedral hydrogen sphere. Although one band is pulled down the charge is distributed throughout the region from -2.0 eV to 3.0 eV as shown in Fig. 2e. A three-peaked structure with peaks at -1.0 , 0.75 and 2.5 eV is displayed by this octahedral hydrogen as contrasted with the single peak at 1.5 eV associated with the tetrahedral hydrogens in Fig. 2d.

If we now remove this hydrogen and add three octahedral hydrogens at the sites $a(\frac{1}{2}, 0, 0)$, $a(0, \frac{1}{2}, 0)$, $a(0, 0, \frac{1}{2})$ which retains cubic symmetry, we now lower three bands as shown schematically in Fig. 3a. Some of these were previously filled in Y_4H_8 [e.g., Γ_1 , $\Gamma_{12}(2)$, X_2 , X_4'] and some were empty [X_1 , $R_{15}'(3)$]. Again the lowering of R_{15}' is large and represents the three independent second nearest neighbor octahedral hydrogen-hydrogen interactions. Again not enough states are lowered to accommodate the three added electrons and the Fermi energy goes up over 0.70 eV to accommodate 1.0 electrons at the Fermi level (above Y_4H_8). There

is now approximately 1.03e associated with each tetrahedral sites. Some net charge has been lost from each of the yttrium - about 0.10e with most of it of d-character. Some of the charge at the octahedral sites, 0.07e, was already there in the interstitial region. Again the octahedral hydrogen is three peaked in nature with peaks at 0.0, 2.5 and 3.5 eV adding structure above the fairly characterless tetrahedral hydrogen density of states as shown in Fig. 3e and d, respectively.

Finally, as we add the original octahedral hydrogen to achieve the composition Y_4H_{12} with the fcc trihydride structure the states $X4'$, Γ_1 , R_2' etc. are again pulled down and a gap develops between the hydrogen manifold and the Fermi level as shown in Fig. 4a. This can account for the semiconducting properties of these trihydrides. Again degeneracies [Γ_1 , $\Gamma_{12}(2)$] develop reflecting the nonprimitive nature of the Y_4H_{12} unit cell. The correspondence between the cubic structure and the primitive trihydride structure is shown schematically in Figs. 4a and 4b. The Fermi energy drops 1.5 eV (below Y_4H_{11}) reflecting the lowering of a whole band and the addition of only one electron. The charge in the octahedral (tetrahedral) spheres is 1.04e (1.04e). Again charge leaves the d-states and flows onto the hydrogens. The interstitial charge density increases reflecting the smaller interstitial volume. Comparing Figs. 3e and 4f, charge is added in the low-energy peak and in a new high energy peak below the Fermi energy. The tetrahedral distribution (3d and 4e) is virtually unchanged.

CONCLUSIONS

Addition of octahedral hydrogen has significant influence up on the band structure. The enhancement of the higher lying hydrogen structure is in agreement with the interpretation of references 6 and 7. Surprisingly enough there is very little difference in charge between the octahedral and tetrahedral sites. In both cases the H-sphere charge is significantly larger than the associated atomic value and we cannot concur with the conclusion of protonic hydrogen of Dekytyar et al. [12]. Hopefully our results will serve in the further interpretation of octahedral occupancy and nonstoichiometric hydrides and as a benchmark until more realistic solutions to these problems are advanced.

REFERENCES

1. W. H. Mueller, J. P. Blackledge, and G. G. Libowitz, Metal Hydrides, Academic Press, New York, 1968.
2. D. S. Schreiber and R. M. Cotts, Phys. Rev. 131, 1118 (1963).
3. E. L. Venturini, proceedings this conference.
4. D. Khatamian, W. A. Kamitakahara, R. G. Barnes and D. T. Peterson, Phys. Rev. B 21, 2622 (1980).
5. D. L. Anderson, R. G. Barnes, D. T. Peterson and D. R. Torgeson, Phys. Rev. B 21, 2625 (1980).
6. J. H. Weaver, R. Rosei and D. T. Peterson, Phys. Rev. B 19, 4855 (1979).
7. D. J. Peterman, B. H. Harmon, J. Marchiando and J. H. Weaver, Phys. Rev. B 19, 4867 (1979).
8. A. C. Switendick, Solid State Commun., ilid. 2. Phys. Chemie N.F. 117, 89-112 (1979).
9. A. C. Switendick, Tran. J. Inst. Metals, Supplement to Vol. 21, p. 57.
10. A. C. Switendick, unpublished work.
11. A. C. Switendick, Ber Bunsenges Physik Chemie, 76, 535 (1972).
12. I. Ya. Dekhtyar and V. I. Shevchenko, Phys. Stat. Sol. (b), 83, 323 (1977).

TABLE I

CHARGE DISTRIBUTION FOR Y_4H_n CALCULATIONS

Charges are computed by summing contributions to include indicated states and energies. Y, t and o, indicate yttrium, tetrahedral and octahedral hydrogen spheres respectively.

System	Energy(Ryd)	States	Int. (/Y)	Charge (Electrons/Atom Sphere)						
				s_Y	p_Y	d_Y	s_t	p_t	s_o	p_o
Y_4H_8	0.288	$\leq t_2$	1.27	0.13	0.21	0.39	0.97	0.00		
	0.452	$\leq F_F$	1.86	0.14	0.23	0.73	0.98	0.02		
Y_4H_9	0.486	$\leq F_F$	1.87	0.13	0.23	0.71	0.99	0.02	0.96	0.01
Y_4H_{11}	0.508	$\leq F_F$	1.86	0.13	0.23	0.65	1.01	0.02	0.99	0.02
Y_4H_{12}	0.436	$\leq F_F$	1.87	0.12	0.23	0.58	1.03	0.01	1.02	0.02
Atom				0.16	--	1.34	0.57			
XTAL				1.99						
YH_2			1.74						0.70	

TABLE II
CHARGE DISTRIBUTION FOR BAND NINE

<u>Int. (/Y)</u>		<u>Charge/(Electrons/Band)</u>						
		$\underline{s}_Y$	P_Y	$\underline{d}_Y$	$\underline{s}_t$	P_t	$\underline{s}_O$	P_O
Y_4H_8	1.15	0.02	0.06	0.68	0.02	0.06		
Y_4H_9	0.68	0.02	0.04	0.21	0.50	0.02	0.50	0.00

FIGURE CAPTIONS

- Figure 1 Electronic Structure of Y_4H_8 : a) Schematic band structure for YH_2 , b) Schematic band structure for Y_4H_8 indicating foldings along Γ , remappings of $X-\Delta$ to $\Gamma-X$ and $4L \rightarrow R$; densities of states, c) total, d) yttrium d-like, e) tetrahedral hydrogen s-like.
- Figure 2 Electronic Structure of Y_4H_9 : a) Schematic band structure; densities of states, b) total, c) yttrium d-like, d) tetrahedral hydrogen s-like, e) octahedral hydrogen s-like.
- Figure 3 Electronic structure of Y_4H_{11} : a) Schematic band structure; densities of states, b) total, c) yttrium d-like, d) tetrahedral hydrogen s-like, e) octahedral hydrogen s-like.
- Figure 4 Electronic structure of Y_4H_{12} : a) Schematic band structure, b) schematic band structure for equivalent YH_3 ; densities of states, c) total, d) yttrium d-like, e) tetrahedral hydrogen s-like, f) octahedral hydrogen s-like.

Fig. 2

Fig. 3

Fig. 4