RECEIVED
ACQUISITION SERVICE
02 MAR -2 PM 3:30

MEASUREMENT AND MODELING OF ADVANCED COAL CONVERSION PROCESSES

21st Quarterly Report #523043-67
October 1, 1991 to December 31, 1991

By
Peter R. Solomon
Michael A. Serio
David G. Hamblen

L. Douglas Smoot
B. Scott Brewster

Work Performed Under Contract No. DE-AC21-86MC23075

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia
Dr. Richard Johnson
COTR

By
Contractor

Advanced Fuel Research, Inc.
87 Church Street
East Hartford, CT 06108
(203) 528-9806

Program Director

Peter R. Solomon
President

Subcontractor

Brigham Young University
Provo, Utah 84602
(801) 378-4326

Program Director

L. Douglas Smoot
Dean and Professor

DISCLAIMER

DE92 012186

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PATENT STATUS

This technical report is being transmitted in advance of DOE patent clearance and no further dissemination or publication shall be made of the report without prior approval of the DOE patent Counsel.

ABSTRACT

The overall objective of this program is the development of predictive capability for the design, scale up, simulation, control and feedstock evaluation in advanced coal conversion devices. This technology is important to reduce the technical and economic risks inherent in utilizing coal, a feedstock whose variable and often unexpected behavior presents a significant challenge. This program will merge significant advances made at Advanced Fuel Research, Inc. (AFR) in measuring and quantitatively describing the mechanisms in coal conversion behavior, with technology being developed at Brigham Young University (BYU) in comprehensive computer codes for mechanistic modeling of entrained-bed gasification. Additional capabilities in predicting pollutant formation will be implemented and the technology will be expanded to fixed-bed reactors.

The foundation to describe coal-specific conversion behavior is AFR's Functional Group (FG) and Devolatilization, Vaporization and Crosslinking (DVC) models, developed under previous and on-going METC sponsored programs. These models have demonstrated the capability to describe the time dependent evolution of individual gas species, and the amount and characteristics of tar and char. The combined FG-DVC model will be integrated with BYU's comprehensive two-dimensional reactor model, PCGC-2, which is currently the most widely used reactor simulation for combustion or gasification. The program includes: i) validation of the submodels by comparison with laboratory data obtained in this program, ii) extensive validation of the modified comprehensive code by comparison of predicted results with data from bench-scale and process scale investigations of gasification, mild gasification and combustion of coal or coal-derived products in heat engines, and iii) development of well documented user friendly software applicable to a "workstation" environment.

Success in this program will be a major step in improving the predictive capabilities for coal conversion processes including: demonstrated accuracy and reliability and a generalized "first principles" treatment of coals based on readily obtained composition data.

The progress during the twenty-first quarter of the program is summarized below.

For Subtask 2.a., the next step in the development of the reactivity model is to use the model developed for the low temperature (kinetic regime) to predict the high temperature reactivity in the pore diffusion regime. In the case of the higher temperature data, a Thiele modulus approach was used to predict the reaction rates. Good agreement was obtained for low rank coals but only fair agreement for the high rank coals. These differences and the extension of the model to gasification conditions will be the subject of future work. The current version of the model was delivered to BYU in order to be included in PCGC-2.

Work continued on the sulfur and nitrogen submodel. The FG-DVC model code was modified to include the additional pools that will be needed for the sulfur and nitrogen submodel. The results for the post oxidation experiments in the TG-FTIR with the Argonne coals show two main peaks for SO_2 . Experiments are now being done on demineralized coals and at different heating rates in order to better resolve the different contributions and to determine kinetic parameters.

Work continued on the swelling model. Our approach is as follows. Using the single bubble model described in previous reports, we are able to predict (a) whether or not swelling will occur (slow heating); (b) if swelling occurs, what the volume ratio is for the swollen to the original coal, and (c) whether the bubbles will burst.

For Subtask 2.b., the high-pressure, controlled-profile (HPCP) reactor, including the char, tar and gas separation and collection system has been successfully operated in coal devolatilization, char preparation and char oxidation experiments. Minor modifications or repairs to the HPCP were completed. Work on an uncooled injection probe to reduce the influence on the particle temperature profile in the reactor was initiated. The optical pyrometer and particle-imaging system were completed and verified with sample particles.

For Subtask 2.c., discussions continued with BYU on implementation of the soot oxidation and particle ignition submodels. Several strategies were outlined at the semi-annual review meeting held at AFR in November.

For Subtask 2.d., no work was scheduled.

For Subtask 2.e., a study was made of literature data on tar yields from fixed-bed gasifiers which were compiled in a recent EPRI report (Thimsen and Maurer, 1990). This was done in an effort to understand the relatively low tar yields from these systems. Plots were made of tar yield data versus flow rate at fixed pressure and tar yield versus pressure at fixed residence time. In the first case, it was found that the tar yield increased with flow rate at fixed pressure, which was expected. In the second case, it was found that the tar yield decreased with pressure at fixed residence time. A possible explanation for the gasifier results is that the increased total pressure leads to increased partial pressures of CO_2 and H_2O and an increased loss of tar from gasification reactions.

For Subtask 2.f., it is planned to design and construct a cantilever beam balance unit to be placed in the HPCP facility of Subtask 2b. This facility will permit measurement of the rates of char oxidation at pressures up to 17 atm. and temperatures up to 1700 K. For the principal purposes of providing experience in experimental procedures associated with large coal particles, and for providing reliable data at atmospheric pressure, several sets of large particles of a Utah bituminous coal were devolatilized and oxidized in platinum crucibles in air. Later these measurements were extended to additional coals. Analysis of these data has been made by graphing the data with different functional relationships based on thick and thin ash layer models of the oxidation of large coal and char particles. The observations are consistent with oxidation being controlled by diffusion of oxygen through the ash layer.

For Subtask 2.g., a sensitivity study and mass balance were performed for the SO_x /sorbent submodel. The results are internally consistent and in agreement with the trends in the literature.

For Subtask 3.a., a new version of FG-DVC with swelling was received from AFR. A char reactivity submodel was also received. Incorporation into PCGC-2 will depend on availability of resources. The Montana Rosebud coal flame ("fast flow" conditions) in the TWR was simulated with 100 percent feedback of enthalpy from volatiles combustion to the particles. Eleven new cases were simulated for the ABB Combustion Engineering drop-tube reactor. A coal combustion case was

simulated for the BYU/ACERC controlled-profile reactor. The effect of swirl number on flowfield predictions for the Imperial College reactor was investigated. Development of code graphics continued.

For Subtask 3.b., work continued on developing and evaluating the fixed-bed model, FBED-1. Work was initiated to improve the FBED-1 predictions. The study of the individual submodels was started to justify their inclusion in the final version of the code. Work was initiated also to consolidate the input data for the final simulations of a high-pressure, Lurgi gasifier and an atmospheric-pressure, Wellman-Galusha gasifier. An overview of the fixed-bed code development was presented at the METC/AFR/BYU contract review meeting. A paper was submitted for publication (Hobbs et al., 1991).

For Subtask 3.c., no work was performed on this subtask during the quarter.

For Subtask 4.a., work continued on collecting information for simulating the two application cases: the Coal Tech cyclone combustor and the Texaco gasifier (with dry coal feed).

For Subtask 4.b., work continued on collecting fixed-bed design and test data from organizations and individuals involved in fixed- or moving-bed gasification or combustion research or in research on non-reacting fixed- or moving beds. No new data sets were obtained. Work also continued on collecting fixed-bed experimental data from the open literature. No new cases were simulated.

"MEASUREMENT AND MODELING OF COAL CONVERSION PROCESSES"

Contract No. DE-AC21-86MC23075

Table of Contents

DISCLAIMER	i
ABSTRACT	ii
I. INTRODUCTION	1
I.A. Program Background and Description	1
I.B. Objectives	1
I.C. Approach	2
I.D. Critical Technical Issues	2
I.E. Twenty-First Quarter Progress	3
II. TASK 2 - SUBMODEL DEVELOPMENT AND EVALUATION	8
II.A. Subtask 2.a. - Coal to Char Chemistry Submodel	9
II.B. Subtask 2.b. - Fundamental High-Pressure Reaction Rate Data	31
II.C. Subtask 2.c. - Secondary Reaction of Pyrolysis Product and Burnout Submodels	35
II.D. Subtask 2.d. - Ash Physics and Chemistry Submodel	36
II.E. Subtask 2.e. - Large Particle Submodels	37
II.F. Subtask 2.f. - Large Char Particle Oxidation at High Pressures	55
II.G. Subtask 2.g. - SO _x -NO _x Submodel Development	58
III. TASK 3 - COMPREHENSIVE MODEL DEVELOPMENT AND EVALUATION	63
III.A. Subtask 3.a. - Integration of Advanced Submodels into Entrained-Flow Code, with Evaluation and Documentation	64
III.B. Subtask 3.b. - Comprehensive Fixed-Bed Modeling Review, Development Evaluation and Implementation	77
III.C. Subtask 3.c. - Generalized Fuels Feedstock Submodel	84
IV. TASK 4 - APPLICATION OF INTEGRATED CODES	85
IV.A. Subtask 4.a. - Application of Generalized Pulverized Coal Comprehensive Code	86
IV.B. Subtask 4.b. - Application of Fixed-Bed Code	87
V. REFERENCES	88
APPENDIX A - "The Variations in Char Combustion Reactivity with Pyrolysis Conditions and Coal Type"	
APPENDIX B - "The Prediction of Coal Char Reactivity Under Combustion Conditions"	
APPENDIX C - "Sulfur Balance for SO _x /Sorbent Submodel Evaluation and Results of Sensitivity Study"	

SECTION I. INTRODUCTION

I.A. PROGRAM BACKGROUND AND DESCRIPTION

During the past several years, significant advances have been made at Brigham Young University (BYU) in comprehensive two-dimensional computer codes for mechanistic modeling of entrained-bed gasification and pulverized coal combustion. During the same time period, significant advances have been made at Advanced Fuel Research, Inc. (AFR) in the mechanisms and kinetics of coal pyrolysis and secondary reactions of pyrolysis products. This program presents a unique opportunity to merge the technology developed by each organization to provide detailed predictive capability for advanced coal characterization techniques in conjunction with comprehensive computer models to provide accurate process simulations.

The program will streamline submodels existing or under development for coal pyrolysis chemistry, volatile secondary reactions, tar formation, soot formation, char reactivity, and SO_x - NO_x pollutant formation. Submodels for coal viscosity, agglomeration, tar/char secondary reactions, sulfur capture, and ash physics and chemistry will be developed or adapted. The submodels will first be incorporated into the BYU entrained-bed gasification code and subsequently, into a fixed-bed gasification code (to be selected and adapted). These codes will be validated by comparison with small scale laboratory and PDU-scale experiments. The validated code could then be employed to simulate and to develop advanced coal conversion reactors of interest to METC.

I.B. OBJECTIVES

The objectives of this study are to establish the mechanisms and rates of basic steps in coal conversion processes, to integrate and incorporate this information into comprehensive computer models for coal conversion processes, to evaluate these models and to apply them to gasification, mild gasification and combustion in heat engines.

I.C. APPROACH

This program is a closely integrated, cooperative effort between AFR and BYU. The program consists of four tasks: 1) Preparation of Research Plans, 2) Submodel Development and Evaluation, 3) Comprehensive Model Development and Evaluation, and 4) Applications and Implementation.

I.D. CRITICAL TECHNICAL ISSUES

To achieve the goals of the program, the computer models must provide accurate and reliable descriptions of coal conversion processes. This will require the reduction of very complicated and interrelated physical and chemical phenomena to mathematical descriptions and, subsequently, to operational computer codes. To accomplish this objective, a number of technical issues must be addressed as noted below. The status of each of these tasks is also included:

- A Separation of Rates for Chemical Reaction, Heat Transfer, and Mass Transfer
- A Particle Temperature Measurements Using FT-IR E/T Spectroscopy
- A Functional Group Description of Coal, Char and Tar
- A Tar Formation Mechanisms
- A Char Formation Mechanisms
- A Viscosity/Swelling
- A Intraparticle Transport
- I Pyrolysis of Volatiles and Soot Formation
- I Secondary Reaction of Tar
- I Particle Ignition
- A Char Reactivity
- I Ash Chemistry and Physics
- A Particle Optical Properties
- I Coupling of Submodels with Comprehensive Codes
- I Comprehensive Code Efficiency
- I Turbulence
- I SO_x and NO_x
- I Generalized Fuels Models
- I Fixed-Bed Model

(o) to be addressed; (I) initiated; (A) almost completed; (C) completed.

These technical issues are addressed in the three Tasks as described in Sections II-IV.

I.E. TWENTY-FIRST QUARTER PROGRESS

Subtask 2.a. Coal to Char Chemistry Submodel Development and Evaluation

The next step in the development of the reactivity model is to use the model developed for the low temperature (kinetic regime) to predict the high temperature reactivity in the pore diffusion regime. In the case of the higher temperature data, a Thiele modulus approach was used to predict the reaction rates. Good agreement was obtained for low rank coals but only fair agreement for the high rank coals. There are several possible reasons: 1) uncertain knowledge of char physical parameters used in Thiele modulus calculations (tortuosity, mean pore radius, effective diffusivity); 2) the high temperature data are usually based on calculated temperatures which may be in error. These differences and the extension of the model to gasification conditions will be the subject of future work. The current version of the model was delivered to BYU in order to be included in PCGC-2.

Work continued on the sulfur and nitrogen submodel. The FG-DVC model code was modified to include the additional pools that will be needed for the sulfur and nitrogen submodel. The results for the post oxidation experiments in the TG-FTIR with the Argonne coals show two main peaks for SO_2 . The low temperature peak is from tar sulfur and organic H_2S evolution while the high temperature peak is primarily H_2S from pyrite decomposition. Experiments are now being done on demineralized coals and at different heating rates in order to better resolve the different contributions and to determine kinetic parameters. An 11 ppm HCN in Helium cylinder was obtained to better calibrate the TG-FTIR for HCN and further verify the high NH_3/HCN ratio.

Work continued on the swelling model. Our approach is as follows. Using the single bubble model described in previous reports, we are able to predict (a) whether or not swelling will occur (slow heating); (b) if swelling occurs, what the volume ratio is for the swollen to the original coal, and (c) whether the bubbles will burst. These predictions are being compared with experimental observations to determine whether a consistent set of parameters can be obtained.

Subtask 2.b. Fundamental High-Pressure Reaction Rate Data

The high-pressure, controlled-profile (HPCP) reactor, including the char, tar and gas separation and collection system has been successfully operated in coal devolatilization, char preparation and char oxidation experiments. Minor modifications or repairs to the HPCP were completed. Work on an uncooled injection probe to reduce the influence on the particle temperature profile in the reactor was initiated. The optical pyrometer and particle-imaging system were completed and verified with sample particles.

Coal particle classification in two ranges of particle diameters for all five coals under study was completed during the reporting period.

Subtask 2.c. Secondary Reaction of Pyrolysis Products and Char Burnout

Discussions continued with BYU on implementation of the soot oxidation and particle ignition submodels. Several strategies were outlined at the semi-annual review meeting held at AFR in November.

Subtask 2.d. Ash Physics and Chemistry Submodel

No work scheduled.

Subtask 2.e. Large Particle Submodels

According to the predictions of the FBED-1 model, the tar evolution occurs in a relatively small region near the top of the reactor where the gas and particle temperatures are changing rapidly. While the coal particles are entering at room temperature, the exit gas temperature is close to 1000 K and is 1300 K in the region where tar evolves. Consequently, the contribution of tar cracking and tar gasification (by CO_2) must also be accounted for and could be the dominant mode of tar loss under some conditions. In order to address this question, a study was made of literature data on tar yields from fixed-bed gasifiers which were compiled in a recent EPRI report (Thimsen and Maurer, 1990). This was done in an effort to understand the relatively low tar yields from these systems. Plots were made of tar yield data versus flow rate at fixed pressure and tar yield versus pressure at fixed residence time. In the first case, it was

found that the tar yield increased with flow rate at fixed pressure, which was expected. In the second case, it was found that the tar yield decreased with pressure at fixed residence time. A possible explanation for the gasifier results is that the increased total pressure leads to increased partial pressures of CO_2 and H_2O and an increased loss of tar from gasification reactions.

Subtask 2.f. Large Char Particle Oxidation at High Pressure

The overall objective is to provide data for reaction rates of large char particles of interest to fixed-bed gasification and oxidation systems operating at pressures above atmospheric pressure. The need for this study centers on the fact that most of the time required for the conversion of a large coal particle is in the char reaction step. Therefore accurate rate data are needed to model the reaction processes in fixed-bed combustion and gasification. A significant number of industrial fixed-bed processes operate at elevated pressure under which conditions the reactivity of char has hardly been addressed in the available literature.

The plan of Subtask 2f is the design and construction of a cantilever beam balance unit to be placed in the HPCP facility of Subtask 2b. This facility will permit measurement of the rates of char oxidation at pressures up to 17 atm. and temperatures up to 1700 K.

For the principal purposes of providing experience in experimental procedures associated with large coal particles, and for providing reliable data at atmospheric pressure, several sets of large particles of a Utah bituminous coal were devolatilized and oxidized in platinum crucibles in air. Later these measurements were extended to additional coals. Because of the availability of chunks of a Colorado coal, a set of three particles was oxidized in air with Mekker burners. Further tests were performed on large particles of North Dakota lignite, Wyoming subbituminous and Illinois #6 coals. A set of three particles, one from each of these, was oxidized in air with Mekker burners. An additional run was made with a large particle pressed from a sample of pulverized Pittsburgh #8 coal. The rationale for measurements of pressed pulverized coal particles is to be able to prepare large particles of the same composition of a single coal or char if needed.

Analysis of these data has been made by graphing the data with different functional relationships based on thick and thin ash layer models of the oxidation of large coal and char particles. Test variables were coal type, oxidation temperature, and initial char particle mass. The cube root of particle mass declined linearly with time in all tests. Ash layers formed and usually remained in place around the coal particle. Average mass reactivities increased with decreasing initial char particle mass and possibly with decreasing char ash percentage. Increasing furnace temperature had little impact on char reactivity. Observations are consistent with oxidation being controlled by diffusion of oxygen through the ash layer. Values of burning rate coefficient are inferred from measurements and compared among coals.

Subtask 2.g. SO_x - NO_x Submodel Development

A sensitivity study and mass balance were performed for the SO_x /sorbent submodel. The results are internally consistent and in agreement with the trends in the literature.

Subtask 3.a. Integration of Advanced Submodels into Entrained-Flow Code, with Evaluation and Documentation

A new version of FG-DVC with swelling was received from AFR. A char reactivity submodel was also received. Incorporation into PCGC-2 will depend on availability of resources. The Montana Rosebud coal flame ("fast flow" conditions) in the TWR was simulated with 100 percent feedback of enthalpy from volatiles combustion to the particles. Eleven new cases were simulated for the ABB Combustion Engineering drop-tube reactor. A coal combustion case was simulated for the BYU/ACERC controlled-profile reactor. The effect of swirl number on flowfield predictions for the Imperial College reactor was investigated. Development of code graphics continued.

Subtask 3.b. Comprehensive Fixed-Bed Modeling Review, Development, Evaluation, and Implementation

During the last quarter, work continued on developing and evaluating the fixed-bed model, FBED-1. Work was initiated to improve the FBED-1 predictions. The study of the individual submodels was started to justify their inclusion in

the final version of the code. Work was initiated also to consolidate the input data for the final simulations of a high-pressure, Lurgi gasifier and an atmospheric-pressure, Wellman-Galusha gasifier. An overview of the fixed-bed code development was presented at the METC/AFR/BYU contract review meeting. A paper was submitted for publication (Hobbs et al., 1991).

Subtask 3.c. Generalized Fuels Feedstock Submodel

No work was performed on this subtask during the quarter.

Subtask 4.a. Application of Generalized Pulverized Coal Comprehensive Code

Work continued on collecting information for simulating the two application cases: the Coal Tech cyclone combustor and the Texaco gasifier (with dry coal feed).

Subtask 4.b. Application of Fixed-Bed Code

During the past quarter, work continued on collecting fixed-bed design and test data from organizations and individuals involved in fixed- or moving-bed gasification or combustion research or in research on non-reacting fixed- or moving beds. No new data sets were obtained. Work also continued on collecting fixed-bed experimental data from the open literature. No new cases were simulated.

SECTION II. TASK 2. SUBMODEL DEVELOPMENT AND EVALUATION

Objectives

The objectives of this task are to develop or adapt advanced physics and chemistry submodels for the reactions of coal in an entrained-bed and a fixed-bed reactor and to validate the submodels by comparison with laboratory scale experiments.

Task Outline

The development of advanced submodels for the entrained-bed and fixed-bed reactor models will be organized into the following categories: a) Coal Chemistry (including coal pyrolysis chemistry, char formation, particle mass transfer, particle thermal properties, and particle physical behavior); b) Char Reaction Chemistry at high pressure; c) Secondary Reactions of Pyrolysis Products (including gas-phase cracking, soot formation, ignition, char burnout, sulfur capture, and tar/gas reactions); d) Ash Physics and Chemistry (including mineral characterization, evolution of volatile, molten and dry particle components, and ash fusion behavior); e) Large Coal Particle Effects (including secondary reactions within the particle and in multiple particle layers; f) Large Char Particle Effects (including oxidation); g) SO_x - NO_x Submodel Development (including the evolution and oxidation of sulfur and nitrogen species); and h) SO_x and NO_x Model Evaluation.

II.A. SUBTASK 2.a. - COAL TO CHAR CHEMISTRY SUBMODEL DEVELOPMENT AND EVALUATION

Senior Investigators - David G. Hamblen and Michael A. Serio
Advanced Fuel Research, Inc.
87 Church Street, East Hartford, CT 06108
(203) 528-9806

Objective

The objective of this subtask is to develop and evaluate, by comparison with laboratory experiments, an integrated and compatible submodel to describe the organic chemistry and physical changes occurring during the transformation from coal to char in coal conversion processes.

Accomplishments

The next step in the development of the reactivity model is to use the model developed for the low temperature (kinetic regime) to predict the high temperature reactivity in the pore diffusion regime. The latter regime is of most interest in entrained combustion and gasification. The model was tested against data from the literature in which both low temperature (TGA) and high temperature (drop tube) data were available and for which information on the char physical properties (porosity, surface area) and elemental analysis was provided. Good agreement was obtained for low temperature TGA data for both low and high rank coals. In the case of the higher temperature data, a Thiele modulus approach was used to predict the reaction rates. Good agreement was obtained for low rank coals but only fair agreement for the high rank coals. There are several possible reasons: 1) uncertain knowledge of char physical parameters used in Thiele modulus calculations (tortuosity, mean pore radius, effective diffusivity); 2) the high temperature data are usually based on calculated temperatures which may be in error. These differences and the extension of the model to gasification conditions will be the subject of future work. The current version of the model was delivered to BYU in order to be included in PCGC-2.

Work continued on the sulfur and nitrogen submodel. The FG-DVC model code was modified to include the additional pools that will be needed for the sulfur and nitrogen submodel. This includes products from organic sulfur evolution (SO_2 , COS , CS_2 , H_2S -Loose, H_2S -tight, char-S) pyrite decomposition (FeS , plus same pools as above) and organic nitrogen evolution (NH_3 , HCN -loose, HCN -tight, NO_2 , Char-N).

The results for the post oxidation experiments in the TG-FTIR with the Argonne coals show two main peaks for SO_2 . The low temperature peak is from tar sulfur and organic H_2S evolution while the high temperature peak is primarily H_2S from pyrite decomposition. Experiments are now being done on demineralized coals and at different heating rates in order to better resolve the different contributions and to determine kinetic parameters.

Demineralization of Illinois #6 using the Bishop and Ward technique was not effective in removing pyrites. The ASTM D-2492 for removing sulfates and pyrites was subsequently employed. Post oxidation experiments are presently being done to determine the effectiveness of this procedure. Pittsburgh #8 was pyrolyzed at 10 °C/min, 30 °C/min and 100 °C/min with post oxidation of volatiles. The higher the heating rate, the higher the temperature of both SO_2 peaks. Also, the higher the heating rate, the higher the peak 1: peak 2 ratio. The SO_2 kinetics experiments will be repeated for reproducibility and the remaining char will be combusted for a complete sulfur balance.

An 11 ppm HCN in Helium cylinder was obtained to better calibrate the TG-FTIR for HCN and further verify the high NH_3/HCN ratio. Both NO and NO_2 were qualitatively identified in the TG-FTIR during post-oxidation of Pittsburgh #8. During combustion of the Pittsburgh #8 char however, NO proved to be the predominant specie.

Work continued on the swelling model. Our approach is as follows. Using the single bubble model described in previous reports, we are able to predict (a) whether or not swelling will occur (slow heating); (b) if swelling occurs, what the volume ratio is for the swollen to the original coal, and (c) whether the bubbles will burst. These predictions are being compared with experimental observations to determine whether a consistent set of parameters can be obtained.

For an initial radius of 30 μm , it was determined that Pittsburgh seam coal (excluding inertinite and extinite components) particles swell for a holding temperature of 510 $^{\circ}\text{C}$, but do not swell for 500 $^{\circ}\text{C}$. This boundary between swelling and non-swelling was investigated using the model. A value of diffusivity of between 7.5×10^{-5} and 9×10^{-5} c.g.s units, at 510 $^{\circ}\text{C}$ would be deduced from this data. Using values of the parameters determined in the manner described above, we will continue to model particle swelling properties, and to compare predictions with observations, as we "tune" the model.

Char Reactivity

Two papers on char reactivity were submitted to the 24th Symposium (International) on Combustion. These are included as Appendices A and B. The main objective of the work during the past quarter was to develop a char reactivity submodel that could be used in a comprehensive code for entrained coal combustors and gasifiers. A char reactivity submodel for incorporation into PCGC-2 was delivered during the past quarter. Appendix B presents in detail the model developed for all reaction regimes (pore diffusion and kinetic regime). The approach used in the kinetic regime has been described previously in the Fifth Annual Report. In the pore diffusion regime, the model follows the approach of Smith (1982) who used the Thiele Modulus to calculate the reaction rate as a function of the intrinsic rate and char properties such as porosity, tortuosity and mean pore radius. In this case, it is assumed that the reaction occurs near the external surface with little penetration of the reactive gas inside the particle. It can be derived that, under those conditions, the value of apparent activation energy is half the value of intrinsic activation energy, and that $n=(m+1)/2$ where n = apparent reaction order and m = intrinsic reaction order (Frank-Kamenetskii, 1969).

The Thiele modulus approach was tested against low temperature TGA data of a lignite coal for different particle sizes. The data showed the transitions between the kinetic regime (zone I) and the pore diffusion regime (zone II) for different particle sizes. A value of the mean pore radius r_p of 10 $\text{\AA}$ (which is the value usually taken in the literature) led to an underestimation of the reactivity at high temperature, i.e. predicted the switch between Zone I and Zone II too early. A reasonable fit was obtained using an adjusted value of $r_p = 100 \text{\AA}$. Similarly, predictions of literature data from TGA (low temperature) and drop

tube (high temperature) experiments obtained for the same chars were greatly improved using a value of $r_p = 100 \text{ \AA}$. Additional literature data will be investigated in the same manner to check if this trend is consistent.

The Thiele Modulus approach necessitates the knowledge of char properties (porosity, tortuosity and mean pore radius) which can be difficult to estimate, especially for inhomogeneous structures. While for low rank coals with high porosity the predictions were found to be fairly good, for cenospheric chars the reactivity was underpredicted. This may indicate that the effects of pore connectivity and large pores probably need to be taken into account. In that case, discrete simulations and percolation theory may be a better approach than theories using a continuum description of transport.

Sulfur and Nitrogen Evolution

A complete set of pyrolysis data has been obtained for the Argonne coals using a 60 mg sample size and a wide band MCT detector. The lower wave number limit of the detector is 500 cm^{-1} and hereby allows detection of HCN which has a sharp absorbance peak at 713 cm^{-1} .

Both the HCN and NH_3 evolution curves displayed in Figures II.A-1 and II.A-2, respectively, show a consistent variation with rank. While HCN shows one broad evolution peak, NH_3 has two distinct evolution peaks. The low temperature NH_3 peak is believed to result from decomposition of amine groups. The source of the high temperature NH_3 peak is unknown, but it could be a secondary reaction product resulting from ring decomposition and condensation reactions since it occurs in the temperature range where hydrogen is evolved.

The HCN and NH_3 weight percents (as-received basis) for the Argonne set are presented in Table II.A-1. The relatively large amount of NH_3 was quite surprising since HCN is the dominant product in high heating rate experiments. The calibrations for NH_3 were redone and an 11 ppm HCN in Helium cylinder has been obtained to redo the HCN calibrations and verify these data. It is possible that the HCN found in the high heating rate experiments may be a secondary product from tar cracking. An experiment employing a post-pyrolysis zone was done to check this idea. Figure II.A-3 shows that additional HCN was formed from tar cracking while the NH_3 evolution was relatively unchanged. Due to the

Figure II.A-1. NH_3 Evolutions for Argonne Coals.

Figure II.A-2. HCN Evolutions for Argonne Coals.

Figure II.A-3. Utah Blind Canyon HCN and NH_3 Evolutions: Pyrolysis Vs. Post Pyrolysis.

importance of the NH_3/HCN question with respect to the pollutant submodels in PCGC-2, additional experiments will be done to control the opportunity for secondary reactions.

Table II.A-1 Results for HCN and NH_3 Evolution from Argonne Coals

	<u>Weight Percent</u> (as-received basis)	
	HCN	NH_3
Pocahontas	0.016	0.27
Upper Freeport	0.012	0.42
Pittsburgh #8	0.019	0.47
Upper Knawha	0.025	0.45
Utah Blind Canyon	0.052	0.53
Illinois #6	0.033	0.45
Wyodak	0.019	0.28
Zap	0.040	0.40

Preliminary qualitative work was done on NO and NO_2 species. Both a Pittsburgh #8 post-oxidation run and a Pittsburgh #8 char combustion run were reprocessed for NO and NO_2 (Figures II.A-4 and II.A-5 respectively). In the post-oxidation run, both NO and NO_2 are seen evolving with two distinct peaks. These peaks occur at the same temperature as NH_3 evolved during Pittsburgh #8 pyrolysis (Figure II.A-2). The first peaks for NO and NO_2 are much larger than that of NH_3 during pyrolysis because they contain the tar nitrogen. In the combustion run, NO proved to be the most abundant specie.

A complete set of pyrolysis data has been obtained for the Argonne coals using a post-oxidizer. The post-oxidizer, which is positioned in-line between the furnace and gas cell and effectively oxidizes all pyrolysis products, allows for the measurement of tar sulfur and H_2S .

Figure II.A-4. NO and NO₂ Evolutions During Pyrolysis of Pittsburgh No. 8.

Figure II.A-5. NO and NO₂ Evolutions During Combustion of Pittsburgh No. 8.

The SO_2 evolution curves obtained in the post-oxidation experiments are displayed in Figure II.A-6. All the coals show two main evolution peaks for SO_2 which are consistent with rank variation. The low temperature peak is thought to be from the tar sulfur and organic H_2S while the high temperature peak is thought to be primarily from pyrite decomposition.

To better resolve the different sulfur contributions, an Illinois #6 coal sample was demineralized according to the Bishop and Ward technique and subjected to a post-oxidation experiment. The results displayed in Figure II.A-7 strongly suggest that this demineralization procedure was ineffective in removing pyrites.

In a second attempt to remove pyrites from Illinois #6, a sample was subjected to ASTM D-2492 for determining sulfur forms in coal. In this procedure the sulfate sulfur was extracted from the coal with dilute hydrochloric acid and the pyrite was extracted using dilute nitric acid. Post-oxidation experiments are currently being done to resolve the pyrite contribution to sulfur evolution.

To determine kinetic parameters, post-oxidation experiments were done on Pittsburgh #8 at three different heating rates: 10 °C/min, 30 °C/min and 100 °C/min. The evolution curves are plotted in Figure II.A-8 as a function of temperature. There is a systematic trend of an increase in both peak temperatures with an increase in heating rate. This is especially interesting for the second peaks as they are thought to be primarily from pyrite decomposition.

The relative SO_2 Peak 1/Peak 2 ratio also shows dependence on heating rate. The relative peak 1/Peak 2 ratios for 10, 30 and 100 °C/min. are 0.74, 1.72 and 1.19, respectively. Due to the importance of the heating rate/ SO_2 evolution question, the post-oxidation experiments at 10, 30 and 100 °C/min will be repeated. The system will be slightly modified to prevent possible tar condensation and the temperature profile will include a combustion cycle to allow a complete sulfur balance.

Swelling Model

An outline of the particle swelling submodel is illustrated in Figure II.A-9.

Figure II.A-6. SO₂ Evolutions for Argonne Coals with Post Oxidizer "In Line".

Figure II.A-7. SO_2 Evolutions During Pyrolysis and Oxidation of Raw and Demineralized Illinois No. 6.

Figure II.A-8. Pittsburgh No. 8 SO₂ Evolutions with Post Oxidizer "In Line".

Input

- Particle Size, r_2°
- Bubble Size, r_1°
- Time-Temp. Profile
(Heating Rate,
Final Temp.)
- Gas Yield Rate (FG-DVC)
- Viscosity (FG-DVC)

Swelling Model

Output

- Particle Size Due to Swelling
- Porosity

Model Parameters

- Initial Bubble Size
- Diffusivity
- Critical Wall Stress
- Surface Tension

Figure II.A-9. Outline of Particle Swelling Submodel.

Role of Swelling in Reactivity

It has been shown in the previous modeling that micropores ($r_p \leq 1 \mu\text{m}$) in bituminous and subbituminous coals do not swell on heating, due to the dominating effect of surface tension. For a variety of heating rates, Zygourakis showed that, when determined by microscopy with a resolution of $0.5 \mu\text{m}$, the maximum surface area density of a pyrolyzed char is $0.08 \text{ m}^2/\text{cm}^3$. This is a hundred times less than areas determined for similar chars by BET and other methods, showing that most of the area is in the micropores, with $r_p < 0.5 \mu\text{m}$, which are in a size regime not affected by gas evolution. Therefore, it is concluded that swelling does not contribute to reactivity by virtue of increasing surface area. Swelling can effect reactivity by increasing particle porosity. For these reasons, it was decided not to include surface area predictions in the swelling model. With this decision made, it was felt that a multi-bubble model would give more complexity than was warranted. Current efforts are aimed at fitting data to a single bubble model.

Determination of Parameters in Swelling Model

Parameters to be determined for the swelling model are initial bubble size, critical wall stress, diffusivity and surface tension. Also to be determined is the manner in which multi-bubble particles are to be treated.

Experimental observations at our disposal are as follows.

Heating Rate Domains - Qualitatively, for bituminous and subbituminous coals, particles react as follows to different heating rates:

Slow heating rate: no swelling

Medium heating rate: swelling

Fast heating rate: wall rupture, little swelling

Particle Size Domains - The particle size domains considered were as follows:

Small, single cenospheres ($0 < r < 25 \mu\text{m}$) (AFR)

Medium, multi-bubble particles ($30 \mu\text{m} < r < 1000 \mu\text{m}$)

Agglomerates: free swelling index (ASTM standard)

Our approach is as follows. Using the single bubble model described in previous reports, we are able to predict: (a) whether or not swelling will occur (slow heating); (b) if swelling occurs, what the volume ratio is for the swollen to the original coal; and (c) whether the bubbles will burst.

These predictions will be compared with experimental observations to determine whether a consistent set of parameters can be obtained.

Determination of Diffusivity at 500 °C - For an initial radius of $30 \mu\text{m}$ it was determined that Pittsburgh seam coal (excluding inertinite and exinite components) particles swell for a holding temperature of 510°C , but do not swell for 500°C .

This boundary between swelling and non-swelling was investigated using the model (Fig. II.A-10). A value of diffusivity of between 7.5×10^{-5} and 9×10^{-5} c.g.s units, at 510°C would be deduced from this data.

Determination of Critical Stress Parameters - Experimentally, it was determined that a Pittsburgh Seam coal particle of $30 \mu\text{m}$ radius burst when heated in an entrained flow reactor at 1000°C , but not at 800°C . This boundary will be used in conjunction with the model, to choose a value of the critical stress for melt fracture.

Choice of Initial Internal Pore Size - Predictions by the model for both volume swelling ratio (Fig. II.A-11) and liquid stress (Fig. II.A-12), as a function of initial pore size, show that this parameter is not important.

Figure II.A-10. Swelling Boundary Diagram.

Prediction:

Experiment: EFR Data, 700°C
Volume Swelling Ratio: 30

Figure II.A-11. Swelling Domain.

Figure II.A-12. Prediction of Stress within the Melt as a Function of Temperature for Initial Pore Sizes of 4,6, and 10μm.

Future Work

Using values of the parameters determined in the manner described above, we will continue to model particle swelling properties, and to compare predictions with observations, as we "tune" the model.

FG-DVC Model

A complete set of new gas pools was added to FG-DVC. These are the products of organic sulfur (SO_2 , COS, CS_2 , H_2S loose, H_2S tight and Char S), and of organic nitrogen (NO_2 and Char N). As a result, the total number of gas pools increased from 27 to 37, an increase of 10 which includes 2 empty pools. See Figure II.A-13 for a complete list of new pool settings.

Besides the organic gas pools, an independent set of pools was added for pyrite decomposition products: SO_2 , COS, CS_2 , H_2S loose and H_2S tight. Two step decomposition of pyrite was adapted:

Plans

Continue work on the models for swelling, char reactivity and the evolution of sulfur and nitrogen species.

FGDVC version 7

Major Pools

<u>Species</u>	<u>Pool Number</u>
CO	4
	10
	13
	15
CO ₂	1
	3
	12
CH ₄	32
	33
H ₂ O	8
	9
	11
NH ₃	2
HCN	6
	7
NO ₂	22
Char N	23
SO ₂	16
COS	17
CS ₂	18
H ₂ S	19
	20
Char S	21

Figure II.A-13. List of Pools.

II.B. SUBTASK 2.B. - FUNDAMENTAL HIGH-PRESSURE REACTION RATE DATA

Senior Investigators - Geoffrey J. Germane and Angus U. Blackham
Brigham Young University
Provo, Utah 84602
(801) 378-2355 and 6536

Student Research Assistants - Charles R. Monson, Ken Bateman,
Layne Pincock and Trace Salmon

Objectives

The overall objectives of this subtask are to measure and correlate fundamental reaction rate coefficients for pulverized-coal char particles as a function of char burnout in oxygen at high temperature. The effect of high-pressure will be investigated.

The specific objectives for the quarterly reporting period included:

1. Review appropriate literature in pertinent areas.
2. Complete the HPCP optical pyrometer and particle-imaging system for char preparation and oxidation studies.
3. Complete the preparation and continue characterization of chars from the coals selected for this study, using the HPCP for char production.
4. Begin oxidation tests in the HPCP reactor with chars produced from several of the coals selected for study.

Accomplishments

Three components of the subtask have been identified to accomplish the objectives outlined above: 1) design and construction of a laminar-flow, high-pressure, controlled-profile (HPCP) reactor, 2) char preparation at high temperature and high pressure, and 3) determination of the kinetics of char-oxygen reactions at high pressure.

The HPCP reactor, capable of functioning at 400 psi (27 atmospheres), has been constructed and instrumented to perform the fundamental reaction rate measurements required for the study. For the determination of kinetic

parameters, data will be included from a char oxidation study conducted with an atmospheric pressure reactor constructed under independent funding at Brigham Young University. The test program was established but not begun because of the effort required to successfully complete the optical pyrometer and particle-imaging system during the reporting period.

HPCP Reactor and Instrumentation Development

HPCP Reactor - The reactor has been essentially complete and ready for char preparation and oxidation tests since the end of the previous quarter. Some minor modifications to the preheater and the particle injection tube were initiated during the quarter. Some faulty control components were discovered and replaced. The new virtual impactor was completed and installed in the collection system. The main effort expended in this area involved completion of the particle-imaging and pyrometry system.

Optical Instrumentation - The modified optical pyrometer and particle-imaging system, described in detail in the 5th Annual Report, was completed, and operation was verified using both Spherocarb and coal char. The problem with distinguishing the trigger was resolved with the existing laser and detector. Significant effort was required to prepare the system for the upcoming char oxidation test series. Initial particle temperature, velocity and size measurements were successfully made with oxidizing coal char.

Char Preparation at High Temperature and High Pressure

The main objective of this aspect of the study is the preparation of chars from five different coals with three different reactors at atmospheric and elevated pressure. The coals are Pitt, HVA, UT Blind Canyon HVB, IL #6 HVC, Wyodak SUBC, and Beulah-Zap LIGA. These are all relatively common U.S. coals that have been used in char oxidation studies. All of the coals are included in the Penn State, the Department of Energy and the Argonne National Laboratory coal banks. They are also standard ACERC coals. The kinetics of oxidation of selected samples of these coal chars will be determined at elevated pressure and the data compared with those obtained at atmospheric pressure.

The principal facility focus of this study is the use of the HPCP reactor in the determination of the kinetics of oxidation of the chars and the preparation of selected char samples from the coals indicated. An important question to be answered is how different will the oxidation kinetics be for chars prepared under different conditions when the kinetic parameters are determined at high temperature and high pressure.

Cooperation with separately-funded researchers in ACERC at BYU continued with the selection of the UT Blind Canyon HVB coal as a primary reference coal for which char will be produced in a flat-flame burner operated by the other research group. Chemical and physical property comparisons will be available to the present study in the analysis of char reactivity in the HPCP at atmospheric and elevated pressures.

Kinetics of Char-Oxygen Reactions at High Pressure

Char oxidation experiments will be performed with five coals varying in rank from lignite to high-volatile bituminous as mentioned above. Samples of these coals have been ground and size-classified with a combination of sieving and an aerodynamic classification to produce tightly sized fractions of 64-75 μm and 37-44 μm . The size fractions were verified by scanning electron microscope and Coulter Counter measurements.

Chars for the oxidation experiments will be prepared in the HPCP furnace in a nitrogen environment. Since devolatilization conditions greatly affect char characteristics, all of the chars will be prepared at the same reactor conditions. These conditions will also be more extreme than those expected for the oxidation experiments to ensure that no further devolatilization occurs during the char oxidation tests. Char preparation conditions will be as follows: atmospheric pressure, wall and gas temperatures of 1700 K, an initial particle heating rate of 10^4 K/s (calculated using gas and wall temperature measurements), and a particle residence time of 300 ms.

In order to obtain accurate results, certain conditions must be met during the char oxidation experiments. The first of these is concerned with the particle temperature history. In the analysis of the results, it is assumed that the particle temperature is constant as it passes through the reaction zone. In order to approach this in the experiments, the gas temperature must be carefully controlled. The temperature of the gases and

the particles must also rapidly drop at the end of the reaction zone, upon entry into the collection probe. For each of the experimental conditions, the preheater temperature and the wall heater zone settings that provide the most isothermal gas temperature profile (measured with the gas suction pyrometer) will be found. Movement of the collection probe and use of an uncooled injection probe may be required to produce acceptable temperature profiles.

Char titanium analysis for carbon conversion determination has been improved with more frequent calibration of the ICP with reference samples. It is thought that sufficient accuracy and precision can be obtained with relatively small char samples if reference samples are run between every char sample.

The experimental plan remains essentially unchanged for the UT Blind Canyon HVB coal char tests. The primary coal selection may be changed, however, if reaction rates are dominated by diffusion, and chemical rates cannot be distinguished for a range of reactor conditions. A detailed description of the test plan and the char analyses and data reduction approach is contained in the 5th Annual Report for this project.

Other Activities

During the reporting period, a paper on the optical particle-imaging system was completed in cooperation with researchers from an independent research team (Cope et al., 1991). The paper was presented at the fall meeting of the Western States Section of the Combustion Institute, in Los Angeles, CA, in October, 1991.

Plans

The HPCP reactor uncooled injection probe and preheater modifications will be completed, and final alignment of the optical instrument will be accomplished with improved signal conditioning for the PMT outputs to provide stronger, noise-free signals.

The char oxidation tests for the primary reference coal will be largely completed during the next quarter. Some modification to the plan may be dictated as particular characteristics of the HPCP and the UT Blind Canyon HVB coal are discovered.

**II.C. SUBTASK 2.c. - SECONDARY REACTION OF PYROLYSIS PRODUCTS
AND CHAR BURNOUT**

SUBMODEL DEVELOPMENT AND EVALUATION

Senior Investigator - James R. Markham and Michael A. Serio
Advanced Fuel Research, Inc.
87 Church Street, East Hartford, CT 06108
(203) 528-9806

Objective

The objective of this subtask is to develop and evaluate by comparison with laboratory experiments, an integrated and compatible submodel to describe the secondary reactions of volatile pyrolysis products and char burnout during coal conversion processes. Experiments on tar cracking, soot formation, tar/gas reactions, char burnout, and ignition will continue during Phase II to allow validation of submodels.

Accomplishments

Discussions continued with BYU on implementation of the soot oxidation and particle ignition submodels. Several strategies were outlined at the semi-annual review meeting held at AFR in November.

Plans

Continue work with BYU on modeling the TWR coal flame experiments. Complete definition of submodels for ignition and soot formation.

II.D. SUBTASK 2.d. - ASH PHYSICS AND CHEMISTRY SUBMODEL

Senior Investigator - James Markham
Advanced Fuel Research, Inc.
87 Church Street, East Hartford, CT 06108
(203) 528-9806

Objective

The objective of this task is to develop and validate, by comparison with laboratory experiments, an integrated and compatible submodel to describe the ash physics and chemistry during coal conversion processes. AFR will provide the submodel to BYU together with assistance for its implementation into the BYU PCGC-2 comprehensive code. To accomplish the overall objective, the following specific objectives are: 1) to develop an understanding of the mineral matter phase transformations during ashing and slagging in coal conversion; 2) to investigate the catalytic effect of mineral matter on coal conversion processes.

Accomplishments

No work scheduled.

Plans

Continue work on submodel for ash chemistry and physics.

II.E. SUBTASK 2.e. - LARGE PARTICLE/THICK BED SUBMODELS

Senior Investigator - Michael A. Serio
Advanced Fuel Research, Inc.
87 Church Street
East Hartford, CT 06108
(203) 528-9806

Objective

The objectives of this task are to develop or adapt advanced physics and chemistry submodels for the reactions of "large" coal particles (i.e., particles with significant heat and/or mass transport limitations) as well as thick beds (multiple particle layers) and to validate the submodels by comparison with laboratory scale experiments. The result will be coal chemistry and physics submodels which can be integrated into the fixed-bed (or moving-bed) gasifier code to be developed by BYU in Subtask 3.b. Consequently, this task will be closely coordinated with Subtask 3.b.

Accomplishments

A compilation was made of literature data on tar yields from Pittsburgh seam bituminous coal as a function of heating rate, reactor type, particle size, gas flow rate, temperature and residence time. This will be used to help validate the tar destruction submodel for fixed-bed (or moving-bed) gasifiers. According to the predictions of the FBED-1 model, the tar evolution occurs in a relatively small region near the top of the reactor where the gas and particle temperatures are changing rapidly. While the coal particles are entering at room temperature, the exit gas temperature is close to 1000 K and is 1300 K in the region where tar evolves. Consequently, the contribution of tar cracking and tar gasification (by CO_2) must also be accounted for and could be the dominant mode of tar loss under some conditions.

In order to address this question, a study was made of literature data on tar yields from fixed-bed gasifiers which were compiled in a recent EPRI report (Thimsen and Maurer, 1990). This was done in an effort to understand the relatively low tar yields from these systems. Plots were made of tar yield data

versus flow rate at fixed pressure and tar yield versus pressure at fixed residence time. In the first case, it was found that the tar yield increased with flow rate at fixed pressure, which was expected. In the second case, it was found that the tar yield decreased with pressure at fixed residence time. This is consistent with the conventional wisdom that increased pressure decreases tar yields. However, this is based primarily on data from captive sample (static) systems such as grid heaters, where the pressure and residence time are not independently controlled. The review by Dryden and Sparham (1963) on pyrolysis data from flow systems concludes that the residence time is much more important than the total pressure for inert gas experiments. A possible explanation for the gasifier results is that the increased total pressure leads to increased partial pressures of CO_2 and H_2O and an increased loss of tar from gasification reactions. This hypothesis is consistent with the relatively high gas temperatures in these systems (~ 1300 K) in the region where tar evolves.

A quantitative model is being developed to describe the loss of tar by cracking and gasification reactions near the top of the gasifier. This would be supplied to BYU for input into the advanced fixed bed code.

Modeling of Tar Destruction in a Moving-Bed Gasifier

It has been observed that the tar yields from moving-bed gasifiers are much lower than those reported in laboratory-scale coal pyrolysis under inert conditions. In order to understand the cause of these tar yield differences, these two categories will be separately considered.

Results from Laboratory Studies for Inert Pyrolysis:

Tar yields (DAF) from pyrolysis under inert gas conditions of Pittsburgh Seam (or equivalent) coals under atmospheric pressure and for pulverized-sized coal particles are summarized in Table II.E-1.

Table II.E-1 Tar Yields from Pyrolysis in Laboratory Reactors at One Atmosphere

Tar Yield (DAF wt.%)	Coal	Coal Rank	Reactor Type	Particle Size (μm)	Reference
26	Pittsburgh	hvbitt	Wire-Grid	74	Suuberg (1977)
24	Pittsburgh	hvbitt	Fixed-Bed	250	Serio (1984)
30	Pittsburgh	hvbitt	Entrained Flow	60	Solomon et al. (1988)
31	Pittsburgh	hvbitt	Fluidized-Bed	75-105	Tyler (1980)
31-28	Linby	hvbitt	Fluidized Bed	100-150	Katheklakis et al. (1990)
19	Pittsburgh	hvbitt	Fixed-Bed	---	Khan (1989)
9.1-13.3	Pittsburgh	hvbitt	Fixed-Bed	2.5 cm	Kalson and Briggs (1985)

The above data reveal that coal pyrolysis performed under these conditions results in a tar yield around 20-30%, even when pyrolysis is done in a fixed-bed configuration (in the presence of a gas flow). The results of Kalson and Briggs (1985) with large coal particles show a significant reduction in the tar yield. The low tar yields of large coal particles may be attributed to the increased residence time of tar in the coal particles, which could result in cracking or repolymerization of the tars inside the particles to form low molecular weight gases and char, respectively. However, since the tar yields in Kalson's experiment were very sensitive to the external gas flow rate, it is possible that the yields were not fully optimized in this system. Consequently, the results, as far as particle size effects are concerned, must be considered inconclusive.

There have been few systematic studies of particle size effects on pyrolysis yields in the literature. Suuberg (1977) studied particles of size ranges 74 μm , 297-833 μm , and 833-991 μm in his wire grid apparatus. The observed tar (plus hydrocarbon liquids) yields were 24, 23, and 21 wt.% (as received-basis) from pyrolysis of Pittsburgh Seam coal. If only the tar yields are considered, the differences were somewhat larger between the two extreme size cuts (23 vs. 18 wt.%), which largely disappeared when the large particles were reground (in order to test for maceral enrichment effects). It is not clear whether possible heat transfer effects were completely eliminated by holding the larger particles for a longer time at higher temperature. Assuming that these

effects were not present, the work of Suuberg would suggest a reduction in tar yield of 10 to 20% from increasing the particle diameter from $< 100 \mu\text{m}$ to $\sim 1000 \mu\text{m}$ (1 mm). Studies on particle size effects on tar yields from pyrolysis in fluidized beds were done in the 3 to 11 mm size range by Stubington and Sumaryono (1984). Three different Australian coals were tested at three different reactor temperatures (750, 850, 950 °C). At the lowest temperature studied (750 °C), only one coal indicated a significant particle size effect on the tar yield in this size range. At the highest pyrolysis temperature (950 °C), the tar yields were reduced by about 1/3 over this size range for two of the coals and were unchanged for the third coal. A possible conclusion is that the intraparticle secondary reactions are more important at higher temperatures, when the primary volatiles must diffuse through a hotter char layer to escape the particle.

Pressure has also been reported to affect tar yields from coal pyrolysis. A higher pressure external to the coal particles decreases the pressure gradient produced by the creation of volatiles within the coal particle. Hence, the residence time of these reactive gases within the particle is increased, leading to a greater extent of secondary tar reactions, and a reduction in tar yields.

Suuberg (1977) has studied the pressure effects on tar yields from coal pyrolysis under inert conditions. Fig. II.E-1 presents a summary of his data obtained with a Pittsburgh No. 8 bituminous coal. It shows clearly that, as gas pressure external to a particle is increased, the yield of tar obtained during pyrolysis is decreased. The tar yield was 32 wt. % under vacuum, 23 wt. % at 1 atm and 12 wt. % at 69 atm (as-received basis). At the same time, the yield of light gases increases with increasing pressure.

There is general qualitative agreement on the role of mass transfer limitations in coal pyrolysis. If the rate of escape of the tar decreases with increasing pressure, this implies a longer residence time for tar precursors in the particle, thus allowing a large fraction of them to be repolymerized into the char structure. Once reincorporated into the solid matrix by more stable bonds, the tar precursors can yield volatiles only by reactions which involve cracking off of small side groups (hence the increased yields of gas with decreasing tar yield).

Figure II.E-1. Effect of Pressure on Pyrolysis Product Yields from Pittsburgh Seam Bituminous Coal (Suuberg, 1977. Atmosphere, helium. Average particle diameter, 74 μ m. Heating rate, 1000°C/s. Final temperature, 1000°C. Holding time at final temperature, 2 to 10 s).

The concept of repolymerization of tar precursors into the char structure is supported by Suuberg's results, which show that the char yield was 48 wt.%, at vacuum, 53 wt.% at 1 atm and 62 wt.% at 69 atm (as-received basis). However, the above pressure effect results were obtained for coal pyrolysis carried out in static systems, in which the coal is heated in a captive sample reactor and the volatiles are evolved from the coal, through a hot screen and into a cold gas. It is possible that the observed pressure effect is primarily due to inhibition of diffusion of tar away from the hot screen.

The papers that have been published on pyrolysis of coals under pressure in flow systems are primarily in the German and Russian literature. Several of these papers have been summarized in the review of Dryden and Sparham (1963). Even though this review is fairly old, it is not dated since little else has been done since that time. This review also covered work on high pressures of reactive atmospheres (H_2 , H_2O).

The authors have distinguished between two different cases: a) increasing pressure at constant volatile residence time and b) volatile residence time increasing in direct proportion to pressure. The essential conclusion of their work was that increases in pressure at constant volatile residence time were not that important. There was slight effect of polymerization and condensation reactions and to retard decomposition reactions among the primary products; an increase in pressure also promoted reactions between gases in the primary products and the semicoke (e.g., auto-hydrogenation). Volatile (tar and gas) residence time, the value of which was proportional to pressure, was a more important factor in influencing the yield and composition of products. The major effect of increasing volatile residence time was to increase the decomposition reactions of the primary volatiles.

Thus, although pressure has some direct effects on the secondary reactions of volatiles, its major effects appear to be due to corresponding changes in volatile residence time.

The effects of volatile residence time in a fixed or moving bed reactor can be explained as follows: 1) increased residence time allows increased time for gas phase secondary reactions which remove tar; 2) the corresponding reduced carrier gas flow rate would reduce the mass transfer rate of tar from the

particle surface, thus increasing the opportunity for tar repolymerization reactions. The secondary gas phase reactions could either be the cracking or gasification (reaction with oxygenated volatiles) type. The latter would be more important for low rank coals.

The only criticism that can be made of the Dryden and Sparham (1963) review is that the volatile residence times (20-100 sec.) were longer than those in a real moving bed gasifier (~ 1 sec.), the particle sizes (powdered to 1 cm) were somewhat smaller, and the heating rates (1-10 °C/min) much lower. If their conclusions are correct about the lack of a significant true pressure effect, a corollary conclusion would be the lack of a significant particle size effect.

Results from Gasifier Systems

Some examples of tar yields of bituminous coal from coal gasifiers are shown in Tables II.E-2 and II.E-3. All of the results in this section were taken from the compilation by Thimsen and Maurer (1990).

Table II.E-2. Tar Yields from Atmospheric Pressure
(Wellman Galusha) Gasifier (AR wt.%)

Coal	Tar Yield
Jetson	12.9±5.4
Ill 6	14.4±4.2

Table II.E-3. Tar Yields from Pressurized Gasifiers (AR wt.%)

Gasifier	Coal	Ox/Coal Ratio	Steam/Coal Ratio	Tar Yield	Pressure (psig)
British Gas	Pitt 8	0.5	0.3	6.4±3.1	335
METC	Pitt 8	2.8	0.5	4.4±4.6	~150
GE	Ill 6	2.4	0.9	3.4±1	~300

Table II.E-2 presents the results from atmospheric pressure gasifiers, and Table II.E-3 presents results from pressurized gasifiers. It can be seen that the tar yield of a pressurized gasifier is much lower than that of an atmospheric gasifier. It has been concluded in the inert-pyrolysis discussion that increasing residence time in the reactor should decrease the yield of tar. In a gasifier, at identical oxygen-steam rates, increasing operating pressure will increase residence time. Therefore, the low tar yield in the pressurized reactor may be due to the increase in residence time which causes more tar secondary reactions. On the other hand, if the pressure in the reactor is kept constant, increasing the gas flow rate will decrease the residence time and, therefore, the tar yield should increase with the gas flow rate. This is supported by the results in Figs. II.E-2 to II.E-7 for atmospheric pressure gasification. However, the results of Jetson coal in Figs. II.E-8 and II.E-9 show an opposite trend. This will be discussed later.

It is likely that tar gasification reactions resulting from the reactions of tar with CO_2 and/or H_2O cannot be neglected, since the gas phase temperature is 200 - 300 °C higher than the solid phase temperature in the volatilization zone of a gasifier, and gasification or cracking of tar can occur once the tar is released from the solid to the gas phase.

Figs. II.E-10 to II.E-17 show the tar yield results for pressurized gasifiers. In every case, pressure was increased in direct proportion to gas flow rate, implying constant residence time. The results show a reduction in tar yield due to the pressure increase. Since Dryden and Sparham (1963) concluded that pressure has little effect on tar yields under inert pyrolysis conditions, the reduction of tar yields due to the pressure increase in gasifiers has to be attributed to the corresponding increase of CO_2 and/or H_2O partial pressure, if this conclusion is correct. The results for Jetson coal in an atmospheric gasifier shown in Figs. II.E-8 and II.E-9 may reflect the increasing oxygen-steam flow rate resulting in higher concentrations of H_2O and CO_2 in the volatilization zone to enhance the gasification of tar.

The particle size effect on tar yields in atmospheric pressure gasification is revealed in Table II.E-4.

Figure II.E-2. Tar Yield from a GE Gasifier, Illinois No. 6 Coal, 300 psig Pressure over a Range of Gas Flow Rates.

Figure II.E-3. Tar Yield from an Elkhorn Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 1/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-4. Tar Yield from an Elkhorn Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 3/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-5. Tar Yield from an Illinois No. 6 Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 1/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-6. Tar Yield from an Illinois No. 6 Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 3/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-7. Tar Yield from a Utah Blind Canyon Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 1/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-8. Tar Yield from Jetson Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 1/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-9. Tar Yield from Jetson Bituminous Coal, Wellman Galusha Gasifier, 1 atm Pressure + 3/4 Inch Particle Size, Over a Range of Gas Flow Rates.

Figure II.E-10. Tar Yield from Upper Freeport Bituminous Coal, METC Gasifier, 122-210 psig Pressure, Over a Range of Gas Flow Rates.

Figure II.E-11. Tar Yield from Upper Freeport Bituminous Coal, METC Gasifier, Over a Range of Pressures.

Figure II.E-12. Tar Yield from Pittsburgh No. 8 Bituminous Coal, METC Gasifier, 88-210 psig Pressure, Over a Range of Gas Flow Rates.

Figure II.E-13. Tar Yield from Pittsburgh No. 8 Bituminous Coal, METC Gasifier, Over a Range of Pressures.

Figure II.E-14. Tar Yield from Kentucky No. 9 Bituminous Coal, METC Gasifier, Over a Range of Gas Flow Rates.

Figure II.E-15. Tar Yield from Kentucky No. 9 Bituminous Coal, METC Gasifier, Over a Range of Pressures.

Figure II.E-16. Tar Yield from an Akwright Bituminous Coal, METC Gasifier, Over a Range of Gas Flow Rates.

Figure II.E-17. Tar Yield from an Akwright Bituminous Coal, METC Gasifier, Over a Range of Pressures.

Table II.E-4. Particle Size Effect on Tar Evolution in an Atmospheric Pressure Gasifier

Test #	Coal	Coal Flow	Dry Gas Flow	Particle Size	Tar Yield
007-02	Ill #6	2025	6471	+3/4	13.4
007-11	Ill #6	1983	6511	+1/4	8.6
007-04	Ill #6	2042	6357	+3/4	14.1
007-10	Ill #6	2067	6361	+1/4	14.7
007-06	Ill #6	3861	12314	+3/4	15.6
007-13	Ill #6	4142	12258	+1/4	13.7
008-03	Elkhorn (hvAb)	2355	7893	+3/4	15.6
008-09	Elkhorn	2315	7501	+1/4	15.6
008-04	Elkhorn	2574	8718	+3/4	14.3
008-10	Elkhorn	2554	8505	+1/4	14.6
008-05	Elkhorn	2990	9828	+3/4	15.6
008-11	Elkhorn	2900	9596	+1/4	14.5

* The above results were all obtained at 1 atm.

According to the results in Table II.E-4, particle size has little effect on the tar yield, which implies that intra-particle and boundary layer mass transfer does not control the tar yield in these gasifiers. This result is consistent with Dryden and Sparham's (1963) conclusion that pressure has little effect on tar yield in a flowing system under inert gas pressure, implying no intra-particle and boundary layer mass transfer limitation. It is also consistent with results discussed previously for inert gas pyrolysis which show little effect of particle size under conditions where the particles devolatilize (isothermally) at low temperatures.

The conclusions can be summarized as follows:

1. Tar residence time is the essential parameter in determining the tar yield. Increasing the residence time increases the cracking and gasification of tar.
2. In the case where the tar residence time is increased by a reduction in the gas flow rate, this will have a further detrimental effect on tar yields in fixed beds by reducing the mass transfer rate from a particle surface.
3. It is likely that the observed pressure effects are due to changes in volatile residence time and/or changes in the partial pressures of tar gasification agents (CO_2 , H_2O).
4. The existence of a significant particle size effect on yields has not been definitively established. This conclusion is consistent with the lack of an observed pressure effect in inert gas systems.

Based on the above conclusions, both the secondary pyrolysis and tar gasifications reactions should be incorporated into the FG-DVC model in order to predict the tar yield in a gasifier. This will be done in the next quarter.

Plans

Complete development of tar destruction submodel. Continue development of single particle model with BYU.

II.F. SUBTASK 2.F. - LARGE PARTICLE OXIDATION AT HIGH PRESSURES

Senior Investigators: Angus U. Blackham and Geoffrey J. Germane
Brigham Young University
Provo, Utah 84602
(801) 378-2355 and 6536
Student Research Assistant: Ken Bateman

Objectives

The overall objective for this subtask is to provide data for the reaction rates of large char particles of interest to fixed-bed coal gasification and combustion systems operating at pressure.

The specific objectives for this year include:

1. Design and start the construction of the cantilever beam balance unit.
2. Conduct additional preliminary oxidation experiments.

Accomplishments

The two components of this subtask that have been suggested earlier for accomplishing the overall objective are: 1) reactor design, fabrication, and preliminary data; 2) experimental reaction rate data for chars from five coals. Construction of a cantilever beam balance unit to be connected to an optical access port of the HPCP reactor has continued during this quarter.

Analysis of the previous preliminary oxidation runs of the coal and char particles in platinum crucibles is continuing. The data are being graphed with different functional relationships and possible models are being tested to fit these relationships. These data and relationships have been organized and correlated into a manuscript to be submitted for publication.

Reactor Design

Cantilever Beam Balance Unit - The cantilever beam balance unit was designed to give mass loss readings and to precisely locate the sample during oxidation experiments using 0.5-1.0 cm char particles. The three components of the cantilever beam balance unit are: a) a balance unit; b) a two-axis

slide; and c) a heat-shielded, water-cooled valve. The entire assembly will be bolted directly to the HPCP reactor of Subtask 2b.

The balance unit measures the mass loss of the particles as they oxidize in the HPCP reactor. It consists of a force transducer, a ceramic cantilever beam and a platinum wire mesh sample basket. The basket is secured to the cantilever beam and extends into the reactor tube through one of the optical access ports of the HPCP reactor.

In order to test multiple samples during each run, a mechanism has been designed to insert and retract the samples from the reactor tube. The balance unit is mounted on a mobile platform. This platform is capable of moving along two axes. First, the entire platform moves toward and away from the reactor tube. This motion, accurate to + or - 0.001 in, allows for sample insertion into and retraction from the reactive environment. The second motion is perpendicular to the first and in the vertical direction. With this capability, the particle can be moved while being oxidized, thus permitting several temperature readings along the surface of the particle. Both movements will be accomplished through the use of motor-driven ball screws.

An aluminum, water-cooled gate valve will be mounted between the HPCP reactor and balance unit housing. With the valve in the open position, the cantilever beam and platinum mesh basket can extend through the opening.

The construction of this cantilever beam balance unit is now underway.

Oxidation Measurements

Preliminary Large Particle Oxidation Measurements - For the principal purpose of providing experience in experimental procedures associated with large coal particles, a series of sets of large particles of a Utah bituminous coal have been devolatilized and oxidized in platinum crucibles in air. These results were given in the Fourth Annual Report (Solomon, et. al, 1990). A lump of coal was crushed to provide some particles with dimensions of about 0.5-1.0 cm on a side. The first set (six particles) were heated with Mekker burners. A second set (six particles) were heated in a muffle furnace. Then four sets of samples (four particles in each set) were heated at different temperatures in the muffle furnace.

Later, as reported in the Fifth Annual Report (Solomon, et. al 1991), similar measurements were extended to additional coals. A set of three particles of a Colorado coal was devolatilized and oxidized in air with Mekker burners. A set of three particles, one from each of North Dakota lignite, Wyoming subbituminous and Illinois #6 coals, was devolatilized and oxidized in air with Meker burners. An additional run was made with a large particle pressed into a thick disk about 1 cm in diameter and .5 cm high from a sample of pulverized Pittsburgh #8 coal. The rationale for measurements of pressed pulverized coal particles is to be able to prepare large particles of somewhat uniform composition of a single coal or char if needed. Some difficulty was experienced while removing the disk from the die, and it cracked. However, a piece of sufficient size was obtained to devolatilize it to a swollen char particle for the oxidation run.

During this quarter, analysis of these preliminary oxidation runs was continued. The data were graphed with different functional relationships based on thick and thin ash layer models of the oxidation of large coal and char particles. Test variables were coal type, oxidation temperature, and initial char particle mass. Surprisingly, the cube root of particle mass declined linearly with time in all tests. Ash layers formed and usually remained in place around the coal particle. Average mass reactivities increased with decreasing initial char particle mass and possibly with decreasing char ash percentage. Increasing furnace temperature had little impact on char reactivity. Observations are consistent with oxidation being controlled by diffusion of oxygen through the ash layer. Values of burning rate coefficient are inferred from measurements and compared among coals.

Plans

During the next quarter, the construction of the cantilever beam balance unit will be completed and tested for its accuracy and reproducibility in positioning the sample char particle in the reactor. The rates of oxidation of the selected coals will then be made at pressures above atmospheric pressure.

Additional preliminary oxidation runs will be made in air in platinum crucibles to resolve some of the issues raised with the previous preliminary experiments.

II.G. SUBTASK 2.G. - SO_x/NO_x SUBMODEL DEVELOPMENT

Senior Investigators: L. Douglas Smoot and B. Scott Brewster
Brigham Young University
Provo, Utah 84602
(801) 378-4326 and (801) 378-6240

Research Assistant: Richard D. Boardman

Objectives

The objectives of this subtask are 1) to extend an existing pollutant submodel in PCGC-2 for predicting NO_x formation and destruction to include thermal NO, 2) to extend the submodel to include SO_x reactions and SO_x-sorbent reactions, and 3) to consider the effects of fuel-rich conditions and high pressure on sulfur and nitrogen chemistry in pulverized-fuel systems.

Accomplishments

SO₂/Sorbent Capture Submodel Evaluation

An evaluation of the sulfation model parameters has been completed for a Wyoming subbituminous coal combustion case. The combustor and conditions for this case correspond to an experimental case investigated by Asay (1982) and are contained in the PCGC-2 Databook. For this model simulation, the reactor length was increased to 3 meters to allow greater residence time of the sorbent particles in the reactor. PCGC-2 was first converged and restart files were used to complete parametric runs using the SO_x/sorbent capture submodel.

A base case was first established using the submodel parameters given in Table II.G-1. The sorbent particles were injected into the combustor, along with the pulverized coal, through the primary tube. While the common practice is to inject sorbent downstream in order to avoid the high flame temperatures which cause the sorbent to lose its effectiveness, the sorbent was injected with the coal in this case because the code was not yet modified to allow particle injection in sidewall inlets. A future test case will consider sidewall injection. The sorbent particle trajectories for the present case were shown in the 5th Annual Report (Solomon et al., 1991).

Mass Balance Closure - A mass balance comparing the moles of SO_2 captured with the moles of CaO reacted is shown in Appendix A. The predicted coal burnout for the baseline case was 68 %. This conversion is rather low, detracting from the usefulness of this case for submodel evaluation. The reason for the low conversion is being investigated, and future test cases will have higher conversion. The coal contains 7.0% ash and 0.56% (daf) sulfur. Integrated SO_2 profiles at the reactor exit indicated that 49% of the gas-phase SO_2 was captured, giving a total molar capture of 2.4×10^{-5} kmol SO_2/kg air. The average conversion of the three sorbent particles was 6.5%. This also translates to a capture of 2.4×10^{-5} kmol SO_2/kg air. Hence, the mass of sulfur captured by the reacting sorbent particles matches the mass of sulfur removed from the gas phase. Despite the low sorbent conversion, a large percent of the gas SO_2 is captured. This is due to a significant amount of sulfur remaining in the unburned coal.

Sensitivity to Ca/S Ratio - Figure II.G-1 shows SO_2 capture increases with Ca/S mole ratio over the range of 0.15 to 3.17. The Ca/S ratio plotted in Fig. II.G-1 is based on the sulfur which was released to the gas phase. Since the coal burnout was 67.5 percent, the Ca/S ratio of 2.14 in Table II.G-1 corresponds to a value of 3.17 in Fig. II.G-1. The magnitude and trend of sulfur capture displayed in Figure II.G-1 are similar to trends measured by Newton, et al (1986).

Figure II.G-2 plots the predicted sorbent particle conversion as the particle size was varied from 2 to 40 μm . The conversion decreases with increasing particle diameter. This correctly reflects the resistance of mass transfer in the sorbent particle pores.

Sensitivity to BET Surface Area - The sorbent conversion should increase with increasing particle surface area. This trend is shown for the submodel predictions given in Figure II.G-3. The nominal BET surface area ranges from 10-50 m^2/g for carbonate-derived calcine and 20-150 m^2/g for hydrate-derived calcine. Since the BET surface area is an important model parameter, it was added to the input data file and must be specified by the code user. Figure II.G-3 illustrates the model sensitivity to BET surface area.

TABLE 1. Baseline Case Parameters

Parameter	Variable Value
BET surface Area	100 m ² /g
*Ca/S	2.14 (mole Ca)/(mole S)
particle diameter	8.0 mm
first order reaction rate constant (cm/s)	291. exp(-7510/T)
solid-state diffusion coef.	0.012. exp(-12,200/T)

*Ratio based on inlet amount of Ca and S.

Figure III.G-1. Dependence of predicted SO₂ capture on sorbent loading.

Figure III.G-2. Dependence of sorbent particle conversion on initial particle size.

Figure III.G-3. Dependence of sorbent particle conversion on BET surface area.

Sensitivity to Kinetic Parameters - The sensitivity of sorbent particle conversion to the chemical reaction rate constant and to the solid-state diffusion coefficient was investigated by independent variation of these two parameters over four orders of magnitude. Figure II.G-4 shows that the predicted conversion is more sensitive to the reaction rate constant than to the solid-state diffusion coefficient for this case. This result is contrary to some experimental investigations (e.g. Gopalakrishnan and Seehra, 1990) which determined that solid-state diffusion was the controlling resistance to particle conversion. Predictions for large particle sizes revealed that solid-state diffusion was controlling. Thus, sensitivity to other factors, including BET surface area, temperature, and particle diameter should also be considered.

Sensitivity to Gas-Phase Variables - The sorbent particle reaction is sensitive to the gas phase temperature through the kinetic parameters. At low temperatures, the reaction rate is too slow for appreciable reaction. At higher temperatures, the sorbent particles will sinter due to rapid reaction of the grains near the particle surfaces. Figure II.G-5 shows the increase in particle reaction rate as the gas phase temperature was varied. The conversion increased with increasing gas temperature.

The sorbent conversion fell approximately 35% with a 50% artificial reduction of the gas-phase SO₂ concentration. Similarly, the conversion increased by 25% for a 33% increase in SO₂ concentrations. Figure II.G-6 shows the sensitivity of conversion to the baseline-case relative SO₂ concentration. The demonstrates the dependence of the particle conversion of the partial pressure of SO₂ in the gas. It illustrates that longer residence time is required to capture diminishing SO₂ concentrations.

Plans

Depending on availability of resources, development and implementation of an H₂S capture subroutine will be considered.

Figure. II.G-4. Dependence of sorbent particle conversion on independent variation in the chemical reaction rate constant and solid-state diffusion coefficient. The variation factor was multiplied by the values given in Table II.G-1.

Figure. II.G-5. Dependence of sorbent particle conversion on the gas-phase temperature.

Figure. II.G-6. Dependence of sorbent particle conversion on the partial pressure of SO_2 in the gas.

**SECTION III. TASK 3. COMPREHENSIVE MODEL DEVELOPMENT
AND EVALUATION**

Objectives

The objective of this task is to integrate advanced chemistry and physics submodels into a comprehensive two-dimensional model of entrained-flow reactors (PCGC-2) and to evaluate the model by comparing with data from well-documented experiments. Approaches for the comprehensive modeling of fixed-bed reactors will also be reviewed and evaluated and an initial framework for a comprehensive fixed-bed code will be employed after submission of a detailed test plan (Subtask 3.b).

Task Outline

This task is being performed in three subtasks. The first covers the full 72 months of the program and is devoted to the development of the entrained-bed code. The second subtask is for fixed-bed reactors and is divided into two parts. The first part (12 months) was devoted to reviewing the state-of-the-art in fixed-bed reactors. This led to the development of the research plan for fixed-bed reactors, which was approved. The code development is being done in the remaining 60 months of the program. The third subtask is to generalize the entrained-bed code to fuels other than dry pulverized coal and will be performed during the last 36 months of the program.

III.A. SUBTASK 3.A. - INTEGRATION OF ADVANCED SUBMODELS INTO ENTRAINED-FLOW CODE, WITH EVALUATION AND DOCUMENTATION

Senior Investigators - B. Scott Brewster and L. Douglas Smoot
Brigham Young University
Provo, UT 84602
(801) 378-6240 and 4326

Research Assistants - Ziaul Huque and Susana K. Berrondo

Objectives

The objectives of this subtask are 1) to integrate the FG-DVC submodel into PCGC-2, 2) incorporate additional submodels and improvements developed under Task 2, 3) evaluate the improved code, 4) improve user-friendliness and robustness, and 5) document the code.

Accomplishments

Submodel Integration

A new version of the FG-DVC submodel, with sulfur and nitrogen pools and swelling, was received from AFR. Integration into PCGC-2 was initiated at AFR. A char reactivity submodel was also received. Integration of these submodels will be completed at BYU, based on availability of resources. Since the project is nearing completion, the first priority will be given to producing a user-friendly, robust, well-documented code.

Code Evaluation

Transparent Wall Reactor (TWR) - A description of the TWR was given in the 1st Annual Report (Solomon et al., 1987). Experimental data for three coal flames were presented in the 4th Annual Report (Solomon et al., 1990). The results of calculations investigating the effect of direct enthalpy feedback from volatiles combustion on model predictions for the Rosebud coal flame ("fast flow" conditions) were presented in the 5th Annual Report (Solomon et al., 1991). Predicted particle temperature and char fraction for a devolatilizing, 60- μ m particle in a uniform, inert gas flowfield were presented for conditions of no feedback, 50 percent feedback,

and 100 percent feedback. Predicted gas and particle temperatures for the flame simulations were also presented for no feedback and for 50 percent feedback. For completeness, predicted particle and gas temperature for 100 percent feedback in the flame are presented here, as shown in Fig. III.A-1. Predictions for the other two conditions (no feedback and 50 percent feedback) are also shown for comparison.

The trends observed previously for the conditions of no feedback and 50 percent feedback are continued with the simulation of 100 percent feedback. Including feedback increases the heating rate of the particles and reduces the spread in particle temperature. However, even with 100 percent feedback, the model does not predict the "jump" in particle temperature of approximately 1000 K at ignition that was observed experimentally. Also, the discrepancy in predicted and measured gas temperatures in the pre-ignition zone is even greater with the increased feedback.

The predicted temperature is well over 1000 K higher than measured at a radius of 2-4 mm when the enthalpy feedback is 100 percent. This discrepancy is probably due to neglecting the intracellular mixing and combustion kinetics of the volatiles. Particle weight loss is predicted to begin at approximately 6 cm, in good agreement with experimental data. The model assumes that the volatiles mix with the bulk gas and react to equilibrium instantaneously. Shaw et al. (1991) measured global kinetics of volatiles combustion. Taking average values of 11.5 kcal/mol and 12.85 for activation energy and $\ln k_0$ (k_0 is in $\text{m}^3\text{kg}^{-1}\text{s}^{-1}$), respectively, the time constant (time for the concentration to decay to e^{-1} of the original concentration) for the first-order decomposition of volatiles (oxygen concentration remains constant) is 0.01 s at 1000 K. For a gas velocity of 1.4 m/s, this time constant represents a distance of 1.4 cm for the volatiles concentration to decay to e^{-1} of its original value. If the mixing delay were also considered, the distance from volatiles evolution to the resulting temperature increase from combustion would be even greater. Hence, in the region of volatiles evolution, the predicted gas temperature rises instantaneously, but the measured gas temperature rise is delayed and more gradual. At 10.5 cm, when volatiles evolution is essentially complete, the predicted and measured gas temperatures agree quite closely.

ABB Combustion Engineering (CE) Reactor - A description of the ABB CE drop tube facility system (DTFS) was given by Nsakala et al. (1986).

a) no feedback

b) 50% feedback

c) 100% feedback

Measured:

- Gas
- ◆— Unignited particles
- Ignited particles

Predicted:

- - Gas
- 45-μm particles
- 52.5-μm particles
- ◇ 60-μm particles
- × 67.5-μm particles
- + 75-μm particles

Figure III.A-1. Effect of direct volatiles flame enthalpy feedback on measured and predicted particle and gas temperatures for combustion of Rosebud subbituminous coal ("fast flame" conditions) in the transparent wall reactor.

A schematic diagram of the reactor was shown in the 5th Annual Report (Solomon et al., 1991) and is repeated here in Fig. III.A-2 to add a detail not shown previously. Rather than being entrained in primary gas and fed through a 0.27-cm-diameter tube as shown in the previous figure, the coal is injected on the centerline of the 0.27-cm-diameter tube through a 0.084-cm-i.d. hypodermic tube. Sheath gas is fed at room temperature through the annulus between the hypodermic tube and the larger tube. The coal injection was simulated with two starting locations, one of which was in the annular region of the injection nozzle; the difference in predicted burnout between the two starting locations was insignificant.

Eleven new cases were simulated during the past quarter as shown in Table III.A-1. Gas flowrates were constant, while coal flowrate varied. The sheath and carrier gas streams were both the same as the secondary reactant gas. The secondary gas was 6.5 percent oxygen in argon at 1755 K. The single-step kinetics of Solomon et al. (1986) were used for devolatilization. Coal C cases were also simulated with the full PCGC-2/FG-DVC model. Char kinetics were supplied by ABB CE for Coals A and B. For Coal C, the kinetics reported by Smith and Smoot (1989) obtained from refitted ABB CE kinetic data (Goetz et al., 1982) were used. The Field et al. (1967) kinetics were also tested. The kinetics of de Soëte (1975), Wendt and coworkers (Wendt et al., 1989; Bose et al., 1988), and Mitchell and Tarbell (1982) were used for fuel NO formation. Coal nitrogen was assumed to partition equally between HCN and NH₃ upon devolatilization for all three coals, although a value of unity is probably more appropriate for bituminous coals (Boardman, 1990). Convergence was difficult to achieve as the partitioning factor approached pure HCN and the predictions moved farther away from the data.

Figure III.A-3 shows the predicted and measured NO_x concentrations at the reactor exit. Since the inlet gas mixture is argon and oxygen, the NO_x is formed from fuel nitrogen. The Coal C predictions were obtained with the single-step devolatilization kinetics and the char kinetics reported by Smith and Smoot (1989) for subbituminous coal. The latter gave results which agreed more closely with the experimental data than the kinetics of Field et al. (1967). The char kinetic rates are compared in Fig. III.A-4a for all three coals. Fuel NO was predicted with the de Soëte kinetics in all three cases. The predictions are strongly dependent on the assumptions of HCN/NH₃ partitioning and the fuel NO kinetics. Convergence was marginal with the

Table III.A-1. Measured and predicted NO_x concentration at the exit of the ABB CE drop tube furnace.

Coal type	Coal feed rate (g/min)	O ₂ /coal ratio	Measured NO _x (ppm)	Predicted NO _x (ppm)	% difference
Coal A (Bituminous)	0.91	1.59	115	93	19
	0.62	2.35	131	109	17
	0.44	3.30	152	122	20
	0.26	5.59	151	133	12
Coal B (Bituminous)	0.92	1.57	156	108	31
	0.68	2.12	219	138	37
	0.48	2.99	274	166	39
	0.27	5.35	251	205	18
Coal C (Subbituminous)	0.77	1.88	79	97	-23
	0.61	2.39	86	112	-27
	0.39	3.69	95	122	-28

Figure III.A-2. ABB Combustion Engineering drop-tube reactor.

Figure III.A-3. Predicted (—) and measured (▲) NO_x at the outlet of the ABB CE drop tube furnace for three coal types.

Figure III.A-4. Predictions for coal combustion in the ABB CE drop tube reactor.

Wendt kinetics and not achieved with the Mitchell and Tarbell kinetics. Further work is needed to improve robustness with the various kinetics options and to correlate the HCN/NH₃ partitioning factor with coal type, heating rate, etc.

As shown by both the predictions and the data, the effluent concentration of NO_x increases at a decreasing rate with decreasing coal flowrate. The data for Coal B even indicate a decrease in NO_x concentration at low coal flowrate. This trend may be explained as follows: Predicted fractional burnout of the coal increases with decreasing coal flowrate (Fig. III.A-4b). However, the product of burnout and coal flowrate (total amount of coal that has reacted) decreases with decreasing coal flowrate (Fig. III.A-4c). Since nitrogen evolution is proportional to the coal mass loss, the total nitrogen in the exit gas should also decrease with decreasing coal flowrate, and this is indeed the case (Fig. III.A-4c). Therefore, total nitrogen in the effluent gas decreases with decreasing coal flowrate, but NO_x concentration increases. The reason can be seen in Fig. III.A-4d. The formation of NO depends on the availability of oxygen. As coal flowrate is increased, oxygen is depleted for an increasingly longer distance at the reactor centerline, due to char combustion. Although less nitrogen is evolved at lower coal flowrate, more NO is formed because of the increased availability of oxygen. At sufficiently high coal flowrate, the availability of fuel nitrogen becomes the limiting factor, and NO_x decreases. This explanation was tested theoretically with the model, which predicted a maximum in NO_x concentration at an O₂/coal ratio of approximately 12.

BYU/ACERC Controlled-Profile Reactor (CPR) - A diagram of the CPR and results of gas flame simulations were given in the 5th Annual Report (Solomon et al., 1991). During the last quarter, a simulation was performed for combustion of Utah Blind Canyon (high volatile bituminous) coal. Conditions are shown in Table III.A-2. Results are shown in Fig. III.A-5. No comparisons have yet been made with experimental data.

Imperial College Reactor - A description of available datasets for the axisymmetric, Imperial College reactor was given in the 5th Annual Report (Solomon et al., 1991). A schematic diagram of the reactor is shown in Fig. III.A-6.

a) U-V velocity vectors & representative particle trajectories

b) Gas temperature isotherms

c) Radially integrated particle burnout

Figure III. A-5. Predictions for combustion of coal in the CPR.

Figure III.A-6. Cross-sectional diagram of the Imperial College reactor (Costa et. al., 1991).

Table III.A-2. Input parameters for CPR coal combustion.

	<u>Primary gas</u>	<u>Secondary gas</u>
Composition:	Air	Air
Flow rate (kg/sec):	0.00412	0.03528
Temperature (K):	298.0	423.0
Swirl number:	0.0	1.4
Coal feed rate (kg/sec):	0.00315	0.0
Wall temperature (K):		1373.0

In the 5th Annual Report, it was reported that the directions of both the internal and external recirculation zones are incorrectly predicted. This results in the coal particles traveling along the front wall to the sidewall and completely burning within a very short axial distance. This problem was investigated further during the last quarter by making predictions for the conditions of Case A in Table III.A-2 of the 5th Annual Report, except that the inlet gas streams were at room temperature and there were no particles. Predicted velocity vectors for three secondary inlet swirl numbers are shown in Fig. III.A-7. The experimental swirl number of Case A is 0.78.

As shown in Fig. III.A-7, the predicted velocities are sensitive to the swirl number. For non-swirling flow (swirl no. = 0), the external recirculation zone (ERZ) should be counter-clockwise, and there should be no internal recirculation zone (IRZ). The correct pattern is predicted by the model as shown in Fig. III.A-7a. As swirl is increased, a critical point is reached where flow reversal occurs at the reactor centerline, and a clockwise internal recirculation zone is established. The model does not predict this flow reversal on the centerline with the corresponding IRZ. Instead, a clockwise recirculation zone begins in the corner, within the ERZ, as shown in Fig. III.A-7b at a swirl number of 0.25. As swirl number is further

a) Secondary swirl no. = 0.0

b) Secondary swirl no. = 0.25

c) Secondary swirl no. = 0.5

Figure III.A-7. Predicted U-V velocity vectors for the Imperial College reactor conditions.

increased, this recirculation zone grows in size and pushes the ERZ toward the centerline. A clockwise IRZ is not predicted. These predictions are inconsistent with predictions reported by Costa et al. (1991) for the same reactor. The problem is being investigated by comparing these predictions with simulations of the CPR, which is very similar in geometry to the Imperial College reactor. The predicted flowfields have recently been found to be sensitive to grid density, and the role of grid density in these predictions is being investigated.

User-Friendliness and Robustness

Work was initiated during the last quarter to convert the graphical user interface (GUI) for preparing code input from the OPEN LOOK™ windowing system to Movie.BYU. The former was developed by Sun Microsystems and is available only on Sun workstations. The latter runs under X Windows and is available on many different platforms. A portion of the window for specifying primary stream data is shown in Fig. III.A-8.

A plotting program that reads data in spreadsheet format (PV Wave) was evaluated for use with PCGC-2. This program has some powerful macro and real-time plotting capabilities, but it was decided to use the Movie.BYU software instead. The latter approach is consistent with the direction being taken for the developing 3-D code (PCGC-3) at BYU and allows this project to benefit from the considerable on-going effort on graphics in ACERC. Movie.BYU is widely distributed around the world and is available on many different platforms. Maintenance of the DISSPLA graphics will also continue.

Plans

During the next quarter, work will continue on evaluating the code and preparing the final code product. Depending on availability of resources, the version of FG-DVC with swelling and the newly received char reactivity submodel will be integrated into PCGC-2. Simulations will be performed for the final two TWR flames. Experimental data will be compared with predictions for coal combustion in the CPR when they become available. Work will continue to correctly predict recirculation in the Imperial College reactor. Preparation of a code user's manual will be initiated. Work will continue on the code graphics, namely the Movie.BYU-based versions of the pre- and post-processors and the DISSPLA graphics.

PRIMARY

INCSWP: ☒ Swirl in primary stream ☒ No swirl in primary stream

Units

Mass flow rate of gas in primary:

Swirl number for the primary:

Turbulence for the primary stream:

Temperature of inlet stream: ☒ K ☒ C ☒ F ☒ R

Species Name	Composition	Basis		Species Name	Composition	Basis
<input type="text" value="CO2"/>	<input type="text" value="0.016252"/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value="CH4"/>	<input type="text" value="0.800761"/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value="C2H6"/>	<input type="text" value="0.120040"/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value="C3H8"/>	<input type="text" value="0.054172"/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value="N2"/>	<input type="text" value="0.008775"/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value=""/>	<input type="text" value=""/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value=""/>	<input type="text" value=""/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole
<input type="text" value=""/>	<input type="text" value=""/>	☒ mole	☒ mass	<input type="text" value=""/>	<input type="text" value=""/>	☒ mole

Figure III A-8. Graphical User Interface window for specifying primary stream data.

III.B. SUBTASK 3.B. - COMPREHENSIVE FIXED-BED MODELING REVIEW, DEVELOPMENT, EVALUATION, AND IMPLEMENTATION

Senior Investigators - Predrag T. Radulovic and L. Douglas Smoot
Brigham Young University
Provo, Utah 84602
(801) 378-3097 and (801) 378-4326

Research Assistant - M. Usman Ghani

Objectives

The objectives of this subtask are: 1) to develop an advanced fixed-bed model incorporating the advanced submodels being developed under Task 2, particularly the large-particle submodel (Subtask 2.e.), and 2) to evaluate the advanced model.

Accomplishments

During the last quarter, work continued on developing and evaluating the fixed-bed model, FBED-1. Work was initiated to improve the FBED-1 predictions. A study of the individual submodels was started to justify their inclusion in the final version of the code. Work was initiated also to prepare the input data for the final simulations of a high-pressure, Lurgi gasifier and an atmospheric-pressure, Wellman-Galusha gasifier. An overview of the fixed-bed code development was presented at the METC/AFR/BYU contract review meeting. A paper was submitted for publication (Hobbs et al., 1991).

FBED-1

The FBED-1 and MBED-1 predictions for the Wellman-Galusha gasifier fired with Jetson bituminous coal were compared. The comparisons of predictions with the Wellman-Galusha data for the Jetson coal case are currently better when computed with the MBED-1 code. The current version of the fixed-bed model, FBED-1, predicts solid temperatures which are considerably higher than the experimental values and the predictions of MBED-1 model. The gas and solid phase temperature gradients predicted by FBED-1, in the devolatilization zone, are also extremely steep. Other problems include higher particle and gas peak temperatures, dips in temperatures, a

jump in oxygen between the ash and the oxidation zone, a jump in nitrogen in the oxidation zone etc. These problems are probably numerical in origin. Work was initiated to resolve these problems.

A study of the individual submodels was started to improve the results and to obtain a better agreement between the predicted and the experimental temperature profiles. The effect of input parameters for the FG-DVC submodels on the FBED-1 predictions was studied. The effect of particle internal pressure differential, defined as the difference between the particle interior pressure and average surface pressure, on devolatilization rates and potential tar-forming fraction was studied first. A decrease in the particle internal pressure differential yields a higher value for the tar-forming fraction, which is consistent with the experimental observations. However, FBED-1 did not yield a converged solution at low values of particle pressure drop (one atmosphere and less). The evolution of tar from the individual mass bins was found to occur in a very localized zone and in large spikes as shown in Figure III.B-1A.

FG-DVC

The above-noted observations prompted a thorough analysis of the FG-DVC submodel. The mathematical models forming the basis of the FG-DVC submodel were studied. Portions of the code which may be further improved were flagged. The results of the stand-alone FG-DVC model, while simulating the laboratory experimental data, did not show devolatilization to occur in large spikes. This was attributed to the low heating rates corresponding to the particle time-temperature history attained in the laboratory experiments. The stand-alone FG-DVC, after minor changes, was executed, then, with the particle time-temperature history typical of an industrial scale fixed-bed process. This time-temperature history was generated from the FBED-1 simulation of the Wellman-Galusha gasifier fired with Jetson bituminous coal. The simulation was performed using the LSODE integrator to run in "one step" mode, thereby, providing a complete time-temperature history. In the one step mode, time and temperature values were obtained after each successful step taken by LSODE with internally computed step size. The stand-alone FG-DVC model with this specified time-temperature history predicted the tar evolution from the individual mass bins to occur in large spikes in a very localized zone (Figure III.B-1B). The bridge population profiles also showed steep gradients. The labile bridge population, in particular, showed some

Figure III.B-1 Tar evolution rate from individual mass bins A) FBED-1. B) FG-DVC stand-alone with FBED-1 generated time temperature history.

chaotic behavior and attained small negative values after devolatilization had been completed. Even though the source of these problems has not been identified yet, new insights were obtained from these simulations. The following conclusions were drawn:

1. The extremely high devolatilization rates and steep temperature gradients are coupled. This indicates the importance of including transport processes within the particle during devolatilization, which should be accounted for in the final version of the fixed-bed code.
2. The predictions for the tar yields are higher when compared with the experimental data (see the 4th Annual Report, Solomen et al., 1990). This is attributed to the repolymerization of tar to form char, which decreases the experimental tar yield. Hence, a tar repolymerization model should be included in the final formulation.

The results of these simulations were sent to AFR for their review, analysis and recommendations.

Contract Review Meeting

A METC/AFR/BYU contract review meeting was held at AFR on November 14 and 15. An overview of the fixed-bed code development was presented. The devolatilization and tar repolymerization submodels were analyzed with Drs. David Hamblen and Michael Serio. The schedule, milestones, and graphics were discussed with METC and AFR. Input data to be used for the development of a tar repolymerization was requested by AFR, and was subsequently sent to them.

Study of Individual Modules

A study of individual submodels was initiated to justify their inclusion in the final version of the fixed-bed code. The char gasification and oxidation submodel was thoroughly analyzed. The assumption of same char and ash densities in the shell progressive and ash segregation models was relaxed and new equations for the particle diameter and particle number density were derived. The kinetic rate constants for combustion and gasification reactions were reconsidered and a number of improvements were made. The O_2 rate constants for lignite and the CO_2 rate constants for average coal were added. New rate constants were selected for the H_2O and H_2 reactions. These

improvements will be incorporated in the final version of the code. The study of additional modules is still in progress. Work also continued on rewriting portions of the code to make it more robust and user-friendly.

Parametric Simulations

Additional simulations were made with FBED-1 to understand better the effect of various input parameters. First, to understand the effect of functional group composition, a simulation was made for the Wellman-Galusha gasifier fired with Jetson HVBB coal. The composition data from MBED-1 for the original 19 functional groups were used along with the FG-DVC submodel. The contents of the additional eight functional groups were set to zero. The results did not show any improvement when compared with the experimental data for temperature. The solid and gas temperatures in the ash zone were substantially higher than the previous simulations and did not compare well with the data. The predictions were also found to be sensitive to the ultimate analysis of the coal. The input values for the functional group composition are taken for a coal in the database which is closest but not the same as the coal being used in the simulation. This leads to a discrepancy and clearly indicates a need for proper closure of elemental mass balances between the functional group composition and the ultimate analysis of feed coal. The procedure, implemented in MBED-1, to adjust the functional group composition to match the ultimate analysis of feed coal was reviewed. An extended procedure for twenty-seven functional groups was requested from AFR.

Additional simulations were made also with MBED-1, to study the effect of reactor operating pressure on the drying, devolatilization, gasification and oxidation rates, the relative lengths of these zones in the fixed-bed, and on the potential tar-forming fraction. The results for the Jetson bituminous coal for the Wellman-Galusha gasifier operated at 101.3 kPa (1 atm) and 2533.1 kPa (25 atms) are shown on Figures III.B-2A and B, respectively. An increase in the operating pressure significantly shortens the gasification and oxidation zones. The devolatilization zone increases and extends to the beginning of the oxidation zone. No significant effect is observed on the drying zone. The volumetric rates for devolatilization decrease, whereas, the volumetric rates for gasification increase. At low char flow rates, both oxidation and gasification rates show an increase before decaying to zero. The potential tar-forming fraction decreases with an increase in the operating pressure, which is as expected.

Figure III.B-2 MBED-1 predicted sensitivity of volumetric rates for drying, devolatilization, gasification and oxidation to operating pressure A) 101.3 kPa, B) 2533.1 kPa.

Data Preparation

The preparation of the input data for the final simulations with FBED-1 of Wellman-Galusha and Lurgi gasifiers used in MBED-1 simulations was initiated. Corrections were made for any inconsistent data found. A procedure to calculate the wall heat losses from the available experimental data was finalized. New wall heat losses were calculated for all the cases. The new heat loss calculations for the Lurgi cases are based on jacket steam and blowdown heat losses. For the Wellman-Galusha cases, the heat loss calculations are now based on jacket steam and cooling water heat losses. The zero-dimensional simulations were repeated with the corrected values for wall heat loss. Substantial improvements in exit temperature were observed. However, the effluent dry gas composition still does not compare well with the experimental values. In particular, CO and CO₂ showed major discrepancies when compared with the experimental data. Furthermore, for some cases better agreement between the predicted and experimental exit temperatures was obtained when the gases in the drying and devolatilization zones were allowed to go to equilibrium, while for some other cases better agreement was obtained when the gases were kept out of equilibrium. The choice of a single option for all the cases, based on the predictions is, as yet, inconclusive. An analysis of the equilibrium module was initiated and options to improve the effluent predictions were considered. The new options being considered for inclusion in the final version of the code are: 1) to allow total equilibrium for tar and gases, 2) to keep the gas phase compositions chemically frozen throughout the reactor bed, and 3) to allow gases to go to equilibrium in the gasification and oxidation zones and to remain chemically frozen in the drying and devolatilization zone.

Plans

During the next quarter, work will continue to complete the final version of the comprehensive fixed-bed model FBED-1. Additional portions of the code will be rewritten to further improve the structure, modularity and user-friendliness. The iteration method will be further modified to improve the convergence and the robustness of the code. After completion, the code will be validated and a sensitivity analysis will be performed. Work will start on modifications to support spreadsheet graphics. Preparation of the FBED-1 user's manual will be initiated.

SUBTASK 3.C. - GENERALIZED FUELS FEEDSTOCK SUBMODEL

Senior Investigators - B. Scott Brewster and L. Douglas Smoot
Brigham Young University
Provo, UT 84602
(801) 378-6240 and 4326

Objective

The objective of this subtask is to generalize PCGC-2 to include sorbent injection, as outlined in the Phase II Research Plan.

Accomplishments

No work was performed on this subtask during the quarter.

Plans

Test the previous code modifications for particle injection in additional (sidewall) inlets.

SECTION IV. TASK 4. APPLICATION OF INTEGRATED CODES

Objective

The objectives of this task are to evaluate the integrated comprehensive codes for pulverized coal and fixed-bed reactors and to apply the codes to selected cases of interest to METC.

Task Outline

This task will be accomplished in two subtasks, one for the entrained-bed lasting 57 months and one for the fixed-bed lasting 48 months. Each of these subtasks will consist of three components: 1) Simulation of demonstration cases on BYU computers; 2) Implementation on a work station at AFR; and 3) Simulations of demonstration cases on the workstation.

IV.A. SUBTASK 4.A. - APPLICATION OF GENERALIZED, PULVERIZED-COAL
COMPREHENSIVE CODE

Senior Investigators - B. Scott Brewster and L. Douglas Smoot
Brigham Young University
Provo, UT 84602
(801) 378-6240 and 4326

Research Assistant - Ziaul Huque

Objectives

The objectives of this subtask are to 1) demonstrate application of the code by simulating reactors of interest to METC and 2) implement the code at METC and conduct training.

Accomplishments

Work continued on collecting information for simulating the two application cases: the Coal Tech cyclone combustor (a Clean Coal Technology project) and the Texaco gasifier with dry-coal feed. The final report on the Clean Coal project "The Demonstration of an Advanced Cyclone Coal Combustor, with Internal Sulfur, Nitrogen, and Ash Control for the Conversion of a 23 MMBtu/hour Oil Fired Boiler to Pulverized Coal" was ordered and received from Coal Tech Corp.

Plans

Initiate simulation of Coal Tech. combustor and Texaco gasifier.

IV.B. SUBTASK 4.B. - APPLICATION OF FIXED-BED CODE

Senior Investigators - Predrag T. Radulovic and L. Douglas Smoot
Brigham Young University
Provo, Utah 84602
(801) 378-3097 and (801)378-4326

Research Assistant - M. Usman Ghani

Objectives

The objective of this subtask is to apply the advanced fixed-bed code developed in task 3.b. to simulate fixed-bed gasifiers of interest to METC.

Accomplishments

Fixed-Bed Data Collection

During the past quarter, work continued on collecting fixed-bed design and test data from organizations and individuals involved in fixed- or moving-bed gasification or combustion research or in research on non-reacting fixed- or moving beds. No new data sets were obtained. Work also continued on collecting fixed-bed experimental data from the open literature.

Application of Fixed-Bed Code

No new cases were simulated.

Plans

During the next quarter, work will continue on collecting fixed-bed design and test data. Efforts will continue to identify additional test cases for simulation, and the code will be applied to the cases of interest to METC.

REFERENCES

Asay, B. W., "Effects of coal type and moisture content on burnout and nitrogenous pollutant formation," Ph.D. dissertation, Brigham Young University, Provo, UT, (1982).

Boardman, R. D., "Development and evaluation of a combined thermal and fuel nitric oxide predictive model," Ph.D. dissertation, Brigham Young University, Provo, UT, (1990).

Bose, A. C., Dannecker, K. M. and Wendt, J. O. L., "Coal composition effects on mechanisms governing the destruction of NO and other nitrogenous species during fuel-rich combustion," *Energy & Fuels*, 2, 301 (1988).

Cope, R.F., Monson, C.R., Hecker, W.C., and Germane, G.J., "Improved Temperature, Velocity and Diameter Measurements for Char Particles in Drop-Tube Reactors," Western States Section of the Combustion Institute, Los Angeles, CA, October, 1991.

Costa, M., Costen, P., Lockwood, F. C. and Mahmud, T., "Detailed measurements in and modelling of an industry-type pulverised-coal flame," *Twenty-Third Symposium (International) on Combustion*, The Combustion Institute, Pittsburgh, PA, 973-980 (1990).

de Soete, G. G., "Overall reaction rates of NO and N₂ from fuel nitrogen," *Fifteenth Symposium (International) on Combustion/The Combustion Institute*, Pittsburgh, PA, 1093 (1975).

Dryden, I.G.C., and Sparham, G.A., "Carbonization of Coals Under Gas Pressure", *B.C.U.R.A. Monthly Bull.*, 27, 1 (1963).

Field, M. A., Gill, D. W., Morgan, B. B. and Hawksley, P. G. W., *Combustion of pulverized coal*, The British Coal Utilisation Research Association, Leatherhead, Surrey, England (1967).

Frank-Kamenetskii, D.A., *Diffusion and Heat Transfer in Chemical Kinetics*, p. 103, Plenum Press, New York, 1969.

Goetz, G. J., Nsakala, N. Y., Patel, K. L. and Lao, T. C., "Combustion and gasification kinetics of chars from four commercially significant coals of varying rank," *Second Annual Conference on Coal Gasification*, EPRI, Palo Alto, CA, October, (1982).

Gopalakrishnan, R. and Seehra, M.S., "Kinetics of the high temperature reaction of SO₂ with CaO particles using gas-phase fourier transform infrared spectroscopy," *Energy & Fuels*, 4, 226-230 (1990).

Hobbs, M.L., Radulovic, P.T., and Smoot, L.D., "Dependence of Fixed-Bed Reaction Processes on Bed Void Distribution," submitted to the Twenty-Fourth Symposium (International) on Combustion, the Combustion Institute, Pittsburgh, PA, (1991).

Kalson, P.A., and Briggs, D.E., *AIChE J.*, 31, 1047 (1985).

Kathelakis, I.E., Shi-Lin, L., Bertle, K.D., and Kandiyoti, R., *Fuel*, 69, 172 (1990).

Khan, M.R., Serio, M.A., Malhotra, R., and Solomon, P.R., A Comparison of Liquids Produced from Coal by Rapid and Slow Heating Pyrolysis Experiments, ACS Div. of Fuel Chem. Preprints, 34, (4), 1054, (1989).

Mitchell, J. W. and Tarbell, J. M., "A kinetic model of nitric oxide formation during pulverized coal combustion," AIChE J., 28, 302-311 (1982).

Newton, G. H., Harrison, D. J., Silcox, G. D. and Pershing, D. W., "Control of SO_x emissions by in-furnace sorbent injection: Carbonates vs. hydrates," Environ. Prog., 5, 140-144 (1986).

Nsakala, N., Patel, R., and Borio, R., "An advanced methodology for prediction of carbon loss in commercial pulverized coal-fired boilers," 1986 JPGC, Portland, OR, October 19-23, 1986.

Serio, M.A., "Secondary Reactions of Tar in Coal Pyrolysis", Ph.D Thesis, Dept. of Chemical Engineering, Mass. Inst. of Tech., Cambridge, MA (1984).

Solomon, P.R., Hamblen, D.G., Carangelo, R.M., Serio, M.A., and Deshpande, G.V., "A General Model of Coal Devolatilization", Energy and Fuel, 2, 405, (1988).

Smith, P. J. and Smoot, L. D., Brigham Young University, "Detailed model for practical pulverized coal furnaces and gasifiers. Volume 1. General technical report," Brigham Young University, Provo, UT, (1989).

Solomon, P. R., Serio, M. A., Hamblen, D. G., Smoot, L. D. and Brewster, B. S., Measurement and modeling of advanced coal conversion processes, 5th Annual Report, DOE-METC Contract No. DE-AC21-86MC23075, Advanced Fuel Research, Hartford, CT, (1991).

Solomon, P. R., Serio, M. A., Hamblen, D. G., Smoot, L. D. and Brewster, B. S., Measurement and modeling of advanced coal conversion processes, 4th Annual Report, Solomon, P. R. et al., DOE-METC Contract No. DE-AC21-86MC23075, U.S. Dept. of Energy, Advanced Fuel Research, Hartford, CT, (1990).

Solomon, P. R., Hamblen, D. G., Serio, M. A., Smoot, L. D. and Brewster, B. S., Measurement and modeling of advanced coal conversion, First annual report, DOE-METC Contract No. DE-AC21-86MC23075, Advanced Fuel Research, Hartford, CT, (1987).

Solomon, P. R., Serio, M. A., Carangelo, R. M. and Markham, J. R., "Very rapid coal pyrolysis," Fuel, 65, 182-194 (1986).

Stubington, J.F. and Sumaryono, Fuel, 63, 1013 (1984).

Suuberg, E.M., "Rapid Pyrolysis and Hydropyrolysis of Coal", Sc.D. Thesis, Dept. of Chemical Engineering, Mass. Inst. of Tech., Cambridge, MA (1977).

Thimsen, D.P., and Maurer, R.E., "Coal Devolatilization in a Moving Bed Gasifier" Research Project 2225-14 Final Report (October, 1990).

Tyler, R.J., Fuel, 59, 218 (1980).

Wendt, J. O. L., Bose, A. C. and Hein, K. R. G., "Fuel nitrogen mechanisms governing NO_x abatement for low and high rank coals," 1988 Joint Symposium on Stationary Combustion NO_x Control, San Francisco, CA, March 609, (1989).

APPENDIX A

"THE VARIATIONS IN CHAR COMBUSTION REACTIVITY WITH PYROLYSIS
CONDITIONS AND COAL TYPE"

THE VARIATIONS IN CHAR COMBUSTION REACTIVITY WITH PYROLYSIS CONDITIONS AND COAL TYPE

Michael A. Serio*
Peter R. Solomon
Sylvie Charpenay
and
Eric M. Suuberg**

Advanced Fuel Research, Inc.
87 Church Street, East Hartford, CT 06108

** Division of Engineering
Brown University, Providence, RI 02912

Subject Matter:

- (1) Coal and Organic Solids Combustion
- (2) Combustion in Practical Systems
- (8) Kinetics

Submitted for Presentation at the Twenty-Fourth International
Symposium on Combustion

Length of Paper:	Text	3,988
	Equations	* included in word count
	Nomenclature =	$X 7 = 0$
	Figures & Tables =	$7 X 200 = 1,400$
	TOTAL	5,388

* To whom correspondence should be addressed
(tel. 203-528-9806; fax 203-528-0648)

THE VARIATIONS IN CHAR COMBUSTION REACTIVITY WITH PYROLYSIS CONDITIONS AND COAL TYPE

Michael A. Serio, Peter R. Solomon, Sylvie Charpenay and Eric M. Suuberg*
Advanced Fuel Research, Inc., 87 Church Street, East Hartford, CT 06108
*Brown University, Division of Engineering, Providence, RI 02912

Subject Matter: (1) Coal and Organic Solids Combustion; (2) Combustion in Practical Systems;
(8) Kinetics

ABSTRACT

The intrinsic reactivity of the char is important in combustion experiments since most studies indicate that the char combustion at high temperatures occurs at less than the external diffusion limit. The effects of coal pyrolysis conditions on intrinsic combustion reactivity have not been studied over a wide range of conditions. One problem is the difficulty in making these measurements accurately at high temperatures. A convenient experiment for measuring intrinsic reactivity is a thermogravimetric analyzer (TGA). A new TGA technique was developed in which the weight loss was measured while the sample was heated at a constant heating rate in the presence of the reactive gas. This method has the advantage that the same conditions can be used for chars of widely varying reactivity. The method was applied to study the dependence of reactivity on coal properties and pyrolysis conditions. The combustion reactivity of a set of chars from five different coals prepared by pyrolysis at heating rates between 0.5 and 20,000°C/sec to temperatures between 400 and 1600°C was studied. Reactivities are seen to decrease dramatically with decreasing aromatic hydrogen concentration. Reactivities were insensitive to heating rate for a lignite but were sensitive to heating rate for a bituminous coal. Mineral catalytic effects explain most of the rank variations. The test provides a measure of the reaction rate which agrees well with literature data for chars from similar coals. The measured intrinsic reactivities also extrapolate well to high temperature measurements if an activation energy of 35 kcal/mole is used. The test can also predict the reactivity differences between coals in a laminar coal flame experiment.

INTRODUCTION

Understanding char reactivity is important since the consumption of char is the slowest and, therefore, the controlling process in combustion or gasification. Reviews of char reactivity^{1,2} demonstrate that there is a wide variation in observed reactivities. Work described by Wells et al.³ highlights the very large variations (two orders of magnitude) in char reactivity with method of formation. Similarly, Ashu et al.⁴ found an enhanced reactivity of char caused by rapid heating of the precursor coal. In work done in a vertical tunnel furnace, Essenhigh and Farzan⁵ measured very rapid burnout times for small coal particles. They ascribed this to the firing condition which gave rates of heating in the 10^6 K/s regime, compared with the more usual value of 10^4 K/s in slower burning flames. Nsakala has reported a wide variation in reactivity associated with rank⁶.

The intrinsic reactivity of the char is important in combustion experiments since most studies indicate that the char combustion at high temperatures occurs at less than the external diffusion limit⁷⁻¹². It has also been observed that char combustion exhibits a negative temperature coefficient,¹ which may be due to annealing which occurs during combustion at high temperatures. The effects of coal pyrolysis conditions on intrinsic combustion reactivity have not been studied over a wide range of conditions. One problem is the difficulty in making these measurements accurately at high temperatures. These experiments usually require a fairly complex apparatus and large quantities of coal, and the effects of heat and mass transport must be considered to back out intrinsic reactivity. A convenient experiment for measuring intrinsic reactivity is a thermogravimetric analyzer (TGA). However, two problems must be considered.

One is how to develop a TGA test which can make measurements over a wide range of reactivities. The second problem is how to relate the low temperature reactivity measurements to the high temperature conditions of interest in pulverized fuel (p.f.) or fluidized bed combustion.

This paper reports on a study of the combustion (oxidation) reactivity of a set of chars from five different coals prepared by pyrolysis at heating rates between 0.5 and 20,000°C/sec to temperatures between 400 and 1600°C. A new TGA technique was developed in which the weight loss was measured while the sample was heated at a constant heating rate in the presence of the reactive gas. The results for the present paper are for reactivity in air. This method has the advantage that the same conditions can be used for chars of widely varying reactivity. The paper will also show that these low temperature measurements give reasonable predictions of high temperature char reactivities.

EXPERIMENTAL PROCEDURE

Char Preparation - Chars for this study were prepared from the 200 x 325 mesh sieved fractions ($\sim 60 \mu\text{m}$ mean diameter) of coals and lignites listed in Table I. The chars were prepared by pyrolysis in an inert atmosphere in one of four reactors: 1) an atmospheric pressure entrained flow reactor (EFR)^{13,14} with coal particle temperatures between 650 and 1600°C at heating rates of $\sim 10,000^\circ\text{C}/\text{sec}$; 2) a heated tube reactor¹⁵ with coal particle temperatures between 650°C and 950°C at heating rates of $\sim 20,000^\circ\text{C}/\text{sec}$; 3) a thermogravimetric analyzer (TGA) with coal particle temperatures of 450°C to 900°C at heating rates of $0.5^\circ\text{C}/\text{sec}$; and 4) a high pressure entrained flow reactor (HPR) with coal temperatures of 600°C to 1400°C at heating rates of $\sim 10,000^\circ\text{C}/\text{sec}$ and pressures up to 200 psig.¹⁶

Reactivity Measurements - Initial char reactivity measurements were made using the isothermal measurement technique developed at Pennsylvania State University.¹⁷ In this method, the char is heated in a TGA in nitrogen to the desired temperature, usually 400-500°C. The temperature level is chosen to make sure no oxygen diffusion limitations are present, i.e., by varying the flow rate, bed depth and particle size. After the weight of the sample has stabilized at the selected temperature level, the nitrogen flow is switched to air and the weight loss is monitored. The time for 50% burnoff, $\tau_{0.5}$, is used as the reactivity index. Another group at Penn State has used the maximum rate of weight loss as a reactivity index, which is determined in a similar isothermal experiment¹⁸. In our char characterization work, we had difficulty applying the isothermal techniques to chars formed over a wide range of conditions. A temperature level selected for one char was inappropriate for another. The temperature was either too high for the rate to be chemically controlled or too low for the $\tau_{0.5}$ to be reached in a reasonable time period.

In order to overcome this difficulty, a non-isothermal technique was developed. A Perkin-Elmer TGA 2 was initially used for this method. Recent measurements have been made using a Bomem TG/plus, which couples a Dupont 951 TGA with a Bomem Michelson 100 FT-IR spectrometer¹⁹. The sample size is about 1.5 mg. The sample is heated in air at a rate of 30 K/min until a temperature of 900°C is reached. The TGA records the sample weight continuously and, at the end of the experiment, the weight and derivative are plotted. Some representative curves for chars from the North Dakota (Zap) lignite and the Pittsburgh Seam bituminous coal are shown in Fig. 1. The Zap and Pittsburgh chars were prepared in the EFR, in which it was calculated that the particles were heated at about 7000 K/s to 700°C before being quenched. The samples were oxidized with an air flow of 40 cc/min and a nitrogen purge flow of 400 cc/min. The derivative curve for the Zap lignite coal (Fig. 1a) shows a sharp downward spike, indicating

that the particle ignited. The Zap lignite also indicates burnout of several components of the char of different reactivity, while the Pittsburgh coal shows a more homogeneous burnout at higher temperatures.

The characteristics of the weight loss curve can be understood as follows: 1) At low temperature, there is an initial weight loss as moisture is removed, then a small weight gain due to oxygen chemisorption; 2) As the temperature is raised, the reactivity of the char increases until the fractional weight loss rate is sufficiently large to be observed. The sample size and oxygen flows are chosen so that the initial ~ 10-15% of the oxidation weight loss occurs under intrinsic reactivity control; 3) As the temperature continues to increase, the reactivity increases until eventually all the oxygen reaching the sample bed is consumed and the weight loss is controlled by the oxygen supply to the sample bed alone. Then the fractional weight loss rate becomes constant for all samples; 4) When the char has components of different reactivity, the weight loss can switch between being oxygen supply limited and being intrinsic reactivity limited as each component is consumed.

Figure 2 compares the weight loss curves for the same char sample but with different sample sizes. The curves are identical for the initial weight loss which is controlled by the intrinsic reactivity. This is the region in which the reactivity measurements are made. As expected, the fractional rate of weight loss $df/dt = (1/m_o) (dm/dt)$ decreases with increasing sample size in the oxygen supply limited regime.

THEORETICAL ANALYSIS

Comparison of Isothermal and Constant Heating Rate Reactivity Tests - The temperature (T_{cr}) at which the derivative of the fractional weight loss with respect to time reaches

a value of 0.065 wt. fraction/min $\approx$ 0.001 wt. fraction/s was chosen as an index of reactivity to be compared with the $\tau_{0.5}$ values measured by the isothermal technique. The actual critical slope used is arbitrary. A value is chosen which is large enough to be unambiguously determined, but small enough so that reaction occurs in the chemically controlled regime. Values of $\ln \tau_{0.5}$ were plotted against $1/T_{cr}$ and a good correlation was observed.

It was subsequently decided that a comparison to $\tau_{0.1}$ (time for 10% burnoff) would be more relevant since the initial reactivity indicated by T_{cr} would be measured, rather than an integral reactivity over a large extent of conversion which could be affected by reactivity variations due to changes in the pore structure or sample inhomogeneity. A plot of $\ln \tau_{0.1}$ vs $1/T_{cr}$ is shown in Fig. 3. This plot includes data for chars from three different coals (Lignite, Subbituminous, Bituminous) in four reactors. The experimental conditions covered the following ranges: heating rate = 0.5 to 20,000 K/sec; temperature = 400 to 1600°C; residence time = .020 s to 30 min; pressure = 0 to 1400 kPa.

It can be shown that a plot of $\ln \tau_{0.1}$ vs $1/T_{cr}$ will be linear with a slope equal to E/R , where E is the global activation energy for the intrinsic oxidation rate and R is the gas constant. For the reaction

the initial fractional rate of disappearance of mass (under the condition of chemical reaction control) can be represented as follows²⁰:

$$df/dt = 6 R_g / (d_o \rho_o) \quad (2)$$

where df/dt is the fractional loss of mass per particle in unit time (1/sec), R_o is the reaction rate based on external surface area (g/cm²s), d_o is the initial particle diameter (cm), and ρ_o is the initial particle density. Following the treatment by Smith², the relationship between the intrinsic and external reaction rate is as follows:

$$R_o = d_o \rho_o A_g R_i / 6 \quad (3)$$

where R_i is the "intrinsic" reaction rate based on the internal surface area and A_g is the specific surface area in cm²/g for the reaction. The parameter A_g can be thought of as the product of (βA_a), where β is the ratio of active area per unit accessible surface area (cm²/cm²) and A_a is the accessible surface area in cm² per gram. By making the above substitutions, one can arrive at a new expression for the initial fractional weight loss rate.

$$df/dt = A_g R_i = [\beta A_a] R_i \quad (4)$$

In the isothermal experiment, the fractional burn-off rate is nearly constant up to ~ 10% weight loss:

$$df/dt \approx \Delta f / \Delta t \approx - 0.1 / \tau_{0.1} \quad (5)$$

Substituting Eq. 4 for df/dt :

$$[\beta A_a] R_i = 0.1 / \tau_{0.1} \quad (6)$$

$$R_i = k_i C_s^m = k_i (T_o) C_s^m \quad (7)$$

where T_o is the temperature of the experiment and C_s is the surface oxygen concentration.

Therefore:

$$[\beta A_g] k_i(T_o) C_s^m = 0.1/\tau_{0.1} \quad (8)$$

Solving for $\tau_{0.1}$:

$$\tau_{0.1} = 0.1/[k_i(T_o) C_s^m] \cdot [1/[\beta A_a]] \quad (9)$$

$$= K_1 [1/\beta A_a] \quad (10)$$

The quantities in the first set of brackets in Eq. 9 are nearly constant for a given isothermal experiment (temperature = T_o) at low conversions and independent of coal type, while the second set of brackets contain quantities which vary with coal type and char formation conditions.

For the non-isothermal experiment, the relative rate of mass loss is constant at some critical temperature, T_{cr} :

$$df/dt = -0.001 = [\beta A_a] k_i(T_{cr}) C_s^m \quad (11)$$

$$k_i(T_{cr}) = -0.001/[C_s^m] \cdot [1/[\beta A_a]] \quad (12)$$

$$= K_2 [1/[\beta A_a]] \quad (13)$$

The result obtained is that $k_i(T_{cr})$ is proportional to an experimental constant and inversely proportional to char properties.

For data collected on the same char sample, $[\beta A_a]$ can be eliminated between Eqs. 9 and 12:

$$\tau_{0.1} = [0.1/[k_i(T_o) C_s^m]] \cdot [k_i(T_{cr}) C_s^m / -0.001] \quad (14)$$

or

$$\tau_{0.1} = 100 \exp [-E/R [1/T_{cr} - 1/T_o]] \quad (15)$$

assuming that k_i can be expressed as an Arrhenius expression $k_i(T) = k_o \exp(-E/RT)$.

Consequently, a plot of $\ln \tau_{0.1}$ vs $1/T_{cr}$ will have a slope equal to $-E/R$ of the intrinsic global oxidation rate. In the absence of catalytic effects, the value of E should be the same for chars from all coals and chars from the same coal prepared under a wide variety of conditions. The nearly linear data in Fig. 3 appears to support this conclusion. A problem may arise if T_{cr} and T_o are significantly different. The mechanism of the oxidation reaction probably changes with temperature, as indicated by the wide range of activation energies and reaction orders reported for the char oxidation reaction in the literature²¹. The best fit value of about 35 kcal/mole determined from Fig. 3 is intermediate in reported values and close to the value of ~ 31 kcal/mole determined by Radovic et al.²² and Wells et al.³ for a wide range of chars from U.S. coals in TGA experiments. It also agrees with the value of 34 kcal/mole determined by Smith² for the intrinsic global activation energy of several U.S. coals.

The formation conditions for the Montana Rosebud Chars which are labeled in Fig. 3 are given in Table II. This provides an indication of the range of pyrolysis conditions required to provide the variation of $\tau_{0.1}$ and T_{cr} observed in Fig. 3.

RESULTS

Reactivity vs. Extent of Pyrolysis - Figure 4 summarizes the results for chars from T_{cr} measurements on five coals produced over a wide range of pyrolysis conditions. The critical

temperature (T_{cr}), which varies inversely with reactivity, is plotted as a function of the (daf) hydrogen content, which is used as a measure of the extent of pyrolysis. For each char type, there is a trend for increasing T_{cr} (decreasing reactivity) with decreasing hydrogen. Most of the change occurs below 2.5% hydrogen, after the evolution of aliphatic hydrogen is complete. That is, T_{cr} appears to vary primarily with the concentration of aromatic hydrogen. This variation could be due to a variation in the active site concentration (β), possibly correlated with the ring condensation accompanying the elimination of aromatic hydrogen. There does not appear to be any drastic effects due to heating rate for low rank coals containing minerals, as chars for a wide range of conditions all fell along the same curve. The results for bituminous coals and demineralized low rank coals do not show the same heating rate independence²³. It should be noted that there is also ring oxygen in the char which is removed at about the same rate as the hydrogen and which may be related to the reactivity changes. Similar correlations were observed with oxygen concentration for chars produced from a single coal, i.e., the reactivity decreases with decreasing char oxygen concentration¹⁶. However, it is thought that the hydrogen is a better indicator of reactivity, since it is present at about five times the level of oxygen on an atomic basis and can be more easily and accurately measured.

The upper solid line in Fig. 4 is a "best fit" line drawn through the data for Kentucky No. 9 and Pittsburgh Seam bituminous chars. The lower solid line is a best fit line drawn through the Zap lignite chars. The differences in the values of T_{cr} with the extent of pyrolysis allows one to assess the importance of this parameter on reactivity. In the case of the Zap lignite, the range of T_{cr} from about 350°C to 525°C corresponds to a factor of ~ 500 in reactivity (assuming the 35 kcal/mole activation energy). In the case of the two bituminous coals, the range of T_{cr} from about 450°C to 575°C corresponds to a factor of ~ 40 in reactivity. Using the same method, one can track the maximum difference in reactivities with coal types as being a factor of 120 (350°C, 475°C) while the minimum difference is about a factor of 4 (525°C, 575°C).

Reactivity vs. Mineral Content - It is known that the vertical displacement of the curves in Fig. 4. is at least partly due to the variations in catalytic activity of minerals. This effect has been observed in previous studies which have been reviewed by Mahajan and Walker²⁴. The most reactive chars are for the Zap lignite which are known to have a high Na and Ca content. The results for T_{cr} versus daf hydrogen content for chars produced from demineralized Zap by the Bishop and Ward technique¹⁰ are similar to chars from bituminous coals²³.

Reactivity vs. Surface Area - Our previous work has suggested that the rank differences in reactivity in Fig. 4 are primarily due to differences in mineral content and not from differences in surface area^{19,23,26}. Similarly, the trends with the hydrogen concentration are due to changes in the molecular order (active site concentration) and not from changes in surface area.

The fact that reactivities differences between chars from different coals do not correlate well with BET surface area is not surprising. As discussed by Walker and coworkers²², it is the active surface area (ASA) as measured by oxygen chemisorption which is important. However, the utility of oxygen chemisorption as a technique for measuring the ASA of "young" chars in question²⁵. In this work, we have not attempted to measure ASA's.

Reactivity vs. Burnout - Measurements have been made of T_{cr} versus the extent of burnout for chars from a Montana Rosebud and a Pittsburgh Seam coal²⁶. In this case, the values of T_{cr} must be corrected for the increase in the ash content. The value of T_{cr} increases systematically with increasing burnout for both coals, which indicates that more reactive components are removed first (or that the burnout process anneals the remaining material).

Correlation of T_{cr} Measurements with High Temperature Combustion Reactivities - Of course the measurement of T_{cr} would not be of much good to those interested in p.f. combustion

unless it can be shown that these measurements correlate with intrinsic reactivities measured at high temperatures. The T_{cr} measurement provides a temperature at which $df/dt = 0.001 \text{ s}^{-1}$. For a $\sim 60 \text{ }\mu\text{m}$ mean diameter fraction of Montana Rosebud coal, the measured T_{cr} was 429°C (702K) while the measured initial CO_2 BET surface area was $152 \text{ m}^2/\text{g}$. The problems of using the BET surface area as a correlating parameter have been discussed previously²³. However, since the intrinsic reactivity data in the literature have been derived using such measurements, this approach is consistent. The CO_2 area varies the least over a wide range of burnoffs, for most coal chars, and is used here. Using equation 4, one would calculate $R_i = 1.1 \times 10^{-10} \text{ g/cm}^2\text{s}$ at $T_p = 702\text{K}$. The most comprehensive compilation of intrinsic reactivity data for a range of carbons is that provided by Smith². The correlation of Smith would predict a value of $R_i = 1.0 \times 10^{-11} \text{ g/cm}^2\text{s}$. However, this correlation underpredicts the data for brown coal chars and lignites in this temperature range, so the agreement is actually within a factor of 2 of the relevant data in Fig. 9 of Reference 2. The extrapolation to high temperatures can be done by using $E = 35 \text{ kcal/mole}$ which gives $R_i = 2 \times 10^{-4} \text{ g/cm}^2\text{s}$ at $T_p = 1650\text{K}$. This estimate is about a factor of two lower than Smith's correlation and about a factor of two higher than his data for brown coal chars. A similar agreement is observed for the other chars that were studied. Consequently, it appears that the T_{cr} measurement is capable of giving meaningful results when extrapolated to high temperatures using an activation energy of $E = 35 \text{ kcal/mole}$.

Recent work in our laboratory with a laminar coal flame experiment has shown a correlation of T_{cr} with the ignition point above the nozzle²⁷ and with the interval of time required to achieve 100% burnout²⁸.

Correlation of T_{cr} Measurements for Reactivity Modeling - Recent work has involved using the T_{cr} database to develop a char reactivity submodel for use in a comprehensive entrained gasification and combustion code²⁹. Since T_{cr} is inversely proportional to the reactivity, $1/T_{cr}$ was found to be a more appropriate quantity to use to develop correlations. Good linear correlations of $1/T_{cr}$ vs. the char hydrogen concentration were obtained for all of the coals examined, as shown in Fig. 5. This includes some additional data which is not included in Fig. 4. The points which fall below the bottom line for the Pittsburgh Seam coal are from chars which were produced at low heating rate in a TGA. For fluid coal, the pyrolysis heating rate can affect the reactivity by at least one order of magnitude.

CONCLUSION

A new reactivity test has been developed which allowed relative rates of reactivity to be determined for chars of widely varying reactivity. The method was applied to study the dependence of reactivity on coal properties and pyrolysis conditions. Reactivities are seen to decrease dramatically with decreasing aromatic hydrogen concentration. Reactivities were insensitive to pyrolysis heating rate for a lignite but were sensitive to heating rate for a bituminous coal. Mineral catalytic effects explain most of the rank variations. The test provides a measure of the reaction rate which agrees well with literature data for chars from similar coals. The measured intrinsic reactivities also extrapolate well to high temperature measurements if an activation energy of 35 kcal/mole is used. The test can also predict the reactivity differences between coals in a laminar coal flame experiment.

ACKNOWLEDGEMENTS

The authors are grateful for the support of the United States Army under contract DACA88-85-C-0020 in the development of the constant heating rate reactivity test and the support of the Morgantown Energy Technology Center of the United States Department of Energy under contracts DE-AC21-84MC21004, DE-AC21-85MC22050 and DE-AC21-86MC23075, for support of the study of char reactivity.

REFERENCES

1. Essenhigh, R.H., Chemistry of Coal Utilization, (M.A. Elliott, Ed.), John Wiley & Sons, 1981, 2nd Supplementary Vol., p. 1162.
2. Smith, I.W., 19th Symposium (Int) on Combustion, The Combustion Institute, 1982, pp. 1045-1065.
3. Wells, W.F., S.K. Kramer, L.D. Smoot, and A.U. Blackham, 19th Symposium (Int) on Combustion, The Combustion Institute, 1982, pp. 1539-1546.
4. Ashu, J.T., Nsakala, N.Y., Mahajan, O.P., and Walker, P.L., Jr.: Fuel, **57**, 251, (1978).
5. Essenhigh, R.H. and Farzan, H.: Nineteenth Symposium (International) on Combustion, pp. 1105-111, The Combustion Institute, 1982.
6. Nsakala, N.Y., Patel, R.L., and Lao, T.C.: Final Report, Electric Power Research Institute, Report No. 1654-6, 1982.
7. Field, M.A., Combust. Flame, **14**, 237, (1970).
8. Smith, I.W, Combust. Flame, **17**, 421, (1971).

9. Mitchell, R.E. and J.W. McLean, 19th Symposium (Int) on Combustion, The Combustion Institute, 1982, pp. 1113-1122.
10. Tichenor, D.A., R.E. Mitchell, K.R. Hencken, and S. Niksa, 20th Symposium (Int) on Combustion, The Combustion Institute, 1985, pp. 1213-1221.
11. Waters, B.J., R.E. Mitchell, R.G. Squires, and N.M. Laurendeau, 22nd Symposium (Int) on Combustion, The Combustion Institute, 1988, pp. 17-27.
12. Leslie, I.H., M. Jost, and C.H. Kruger, *Combust. Flame*, **78**, 195, (1989).
13. Solomon, P.R., Hamblen, D.G., Carangelo, R.M., and Krause, J.L.: *Nineteenth Symposium (International) on Combustion*, pp 1139-1149, The Combustion Institute, 1982.
14. Solomon, P.R. and Hamblen, D.G.: *Chemistry of Coal Conversion*, (R.H. Schlosberg, Ed.), Ch. 5, p. 121, Plenum Press, 1985.
15. Solomon, P.R., Serio, M.A., Carangelo, R.M., and Markham, J.R.: *Fuel*, **65**, 182, (1986).
16. Solomon, P.R., Hamblen, D.G., and Carangelo, R.M.: *Analytical Pyrolysis*, (K.J. Voorhees, Ed.), Ch. 5, p. 121, Butterworths, 1984.
17. Mahajan, O.P., R. Yarzab, and P.L. Walker, Jr., *Fuel*, **57**, 643, (1978).
18. Jenkins, R.G., S.P. Nandi, and P.L. Walker, Jr., *Fuel*, **52**, 288, (1973).

19. Solomon, P.R., M.A. Serlo, R.M. Carangelo, and R. Bassilakis, International Conference of Coal Science Proceedings, p. 67, IEA, Japan, (1989a).
20. McKenzie, A., I.W. Smith, and G.A.D. Szpindler, J. Inst. Fuel, **47**, 75, (1974).
21. Larandea, N.M., Prog. Eng. Combust. Sci., **4**, 221, (1978).
22. Radovic, L.R., P.L. Walker, Jr., and R.G. Jenkins, Fuel, **62**, 849, (1983).
23. Serlo, M.A., P.R. Solomon, R. Bassilakis, and E.M. Suuberg, ACS Div. of Fuel Chem. Prepr., **34**(1), 9, (1989).
24. Mahajan, O.P., and Walker, P.J., Jr.: *Analytical Methods for Coal and Coal Products*, (C. Karr, Ed.), Vol. II, Ch. 32, pp. 465-492, Academic Press, 1978.
25. Suuberg, E.M., Calo, J.M., and Mojtownicz, M.: ACS Div. of Fuel Chem. Prepr., **31**(3), 186, (1986).
26. Solomon, P.R., M.A. Serlo, D.G. Hamblen, J.R. Markham, P.E. Best, and R. Bassilakis, DOE/METC Final Report under Contract No. DE-AC21-85MC22050, (1988).
27. Solomon, P.R., P.L. Chlen, R.M. Carangelo, P.E. Best, and J.R. Markham, 22nd Symposium (Int) on Combustion, The Combustion Institute, 1988, pp. 211-221.
28. Solomon, P.R., M.A. Serlo, D.G. Hamblen, L.D. Smoot, and B.S. Brewster, DOE/METC 3rd Annual Report under Contract No. DE-AC21-86MC23075, (1989).

29. Charpenay, S., Serlo, M.A., Solomon, P.R., "The Prediction of Coal Char Reactivity Under Combustion Conditions", paper submitted to 24th Symposium (Int) on Combustion, The Combustion Institute, (1991).

TABLE I

SAMPLE PROPERTIES

WT% DAF

	Zap, North Dakota Lignite	Montana Rosebud Subbituminous	Illinois #6 Bituminous	Pittsburgh Seam Bituminous	Kentucky #9 Bituminous
Carbon	66.5	72.1	73.6	82.1	81.7
Hydrogen	4.8	4.9	4.7	5.6	5.6
Nitrogen	1.1	1.2	1.4	1.7	1.9
Sulfur	1.1	1.2	3.8	2.4	2.4
Oxygen (Diff.)	26.5	20.3	16.5	8.2	8.4
Ash (Dry Wt.%)	7.1	10.0	11.0	9.2	14.1

TABLE II
KEY TO MONTANA ROSEBUD DATA IN FIGURE 3

Datum No.	Reactor	Heating Rate ^a °C/s	Maximum Temperature °C	Residence Time ^b (s)	Pressure (psig)
1	TGA	0.5	900	---	0
2	EFR	10,000	1300	0.2	0
3	HPR	10,000	817	0.3	100
4	HTR	20,000	800	0.2	0
5	HPR	10,000	817	0.3	26
6	HTR	20,000	800	0.1	0
7	HTR	20,000	800	---	0
8	HTR	20,000	600	---	0

Notes:

TGA Thermogravimetric Analyzer
EFR Atmospheric Pressure Entrained Flow Reactor
HPR High Pressure Entrained Reactor
HTR Heated Tube Reactor
a Heating rates are nominal
b Residence time at final temperature

Figure 1. Non-Isothermal TGA Reactivity Tests at 400 cc/min Air Flow; Heated at 30°C/min. a) High Reactivity Zap Lignite Char, b) Low Reactivity Pittsburgh Seam Bituminous Char.

Figure 2. TGA Weight Loss Curves for Zap Lignite Char at 3 Sample Weights.

Figure 3. $\tau_{0.1}$ (time for 10% burnoff) vs. $1/T_{cr}$. T_{cr} is the Temperature at which the Weight Loss Rate Equals $-0.001 \text{ wt. Fraction/sec.}$

Figure 4. Comparison of Reactivity for Chars from Five Various Ranks as a Function of Hydrogen Concentration. T_{cr} Varies Inversely with Reactivity.

Figure 5. Correlation of $1/T_{crit}$ with the Percent (daf) Hydrogen Content of the Char (H_{char}) for Zap, Rosebud, Illinois No. 6 and Pittsburgh No. 8 Coals.

APPENDIX B

"THE PREDICTION OF COAL CHAR REACTIVITY UNDER COMBUSTION CONDITIONS"

THE PREDICTION OF COAL CHAR REACTIVITY UNDER COMBUSTION CONDITIONS

Sylvie Charpenay
Michael A. Serio*
Peter R. Solomon

Advanced Fuel Research, Inc.
87 Church Street
East Hartford, CT 06108

Subject Matter:

- (1) Coal and Organic Solids Combustion
- (2) Combustion in Practical Systems
- (8) Kinetics

Submitted for Presentation at the Twenty-Fourth International
Symposium on Combustion

Length of Paper:

Text = 1	3,326
Equations =	* included in word count
Nomenclature = 27	X 7 = 187
Figures & Tables = 9	X 200 = 1,800
TOTAL	5,313

* To whom correspondence should be addressed
(tel. 203-528-9806; fax 203-528-0648)

THE PREDICTION OF COAL CHAR REACTIVITY UNDER COMBUSTION CONDITIONS

Sylvie Charpenay, Michael A. Serio and Peter R. Solomon

Advanced Fuel Research, Inc.
87 Church Street, East Hartford, CT 06108

The main objective of the current work was to develop a char reactivity submodel that could be used in a comprehensive code for entrained coal combustors and gasifiers. The requirement of a char reactivity submodel is to predict the reactivity of chars from a wide range of coals over a wide range of temperatures (i.e., in all reaction regimes) and burnoff levels. In order to predict intrinsic reactivity, correlations of reactivity with char hydrogen content, coal oxygen content, coal mineral content and pyrolysis heating rate were used. A random pore model (high rank coals) and a volumetric model (low rank coals) were used to predict variations of reactivity with burnoff in the kinetic regime. In the pore diffusion regime the model follows the approach of Smith¹ to calculate the reaction rate as a function of the intrinsic rate and char properties such as porosity, tortuosity and mean pore radius. In this case, it is assumed that the reaction occurs near the external surface with little penetration of the reactive gas inside the particle. The correlations associated with the random pore model or volumetric model gave good predictions of reactivity and reactivity variations in the kinetic regime. The fit of data in the diffusion regime led to a good agreement for high porosity, low rank coals, while underpredicting reactivity for low porosity cenospheric coals. However, in the case of cenospheric coals, the continuum description of transport may not be appropriate.

¹ Smith, I.W., Nineteenth Symposium (Int) on Combustion, The Combustion Institute, 1982, pp. 1045-1065.

INTRODUCTION

The objective of a char reactivity model is to predict the reactivity of various coals and chars over a wide range of temperatures (i.e., in all reaction regimes) and at various degree of burnoff. The burnout of the char often dictates the overall time scale for many practical combustion and gasification systems. In the case of a fixed-bed gasifier, the char reactivity will dictate the location of the maximum temperature in the combustion zone. For mild gasification of coal, the production of a highly reactive char for subsequent combustion can be critical to the success of a process.

Intrinsic reaction rates (regime I) can be measured at low temperature in a TGA apparatus. However pore diffusion effects (regime II) are important under many practical combustion and gasification conditions and need to be accounted for. External diffusion (regime III) can also be important, but was not included in the present model since several studies¹⁻³ indicate that it is not usually the rate limiting step, except for fluidized bed combustion. The main objective of the current work was to develop a char reactivity submodel that could be used in a comprehensive code for entrained coal combustors and gasifiers.

A model which can be used in regimes I or II must include a description of intrinsic char reactivity and how it varies with temperature, coal type, and char formation conditions. In order to predict intrinsic reactivity, the measurement and evaluation of the number of active sites on chars surfaces have been the object of extensive work^{4,5}. However, the current methods (TPD, TGA, transient kinetics, etc...) do not allow a direct measurement of the number of active sites. In the absence of such a method, our approach has been to develop correlations of reactivity with known parameters of coals and chars. Correlations of reactivity with the concentrations of minerals and oxygen in the starting coal and hydrogen in the char as well as pyrolysis heating rate

have been observed. Those correlations reflect the fact that the amount of active sites is dependent on the following: 1) The degree of pyrolysis of the char, which can be characterized by the hydrogen content of the char; 2) The degree of disorder of the char, which varies with the heating rate at which it has been produced during pyrolysis (valid for fluid coals only); 3) The coal rank, which can be characterized by the oxygen content; 4) The amount of catalytic impurities present in the starting coal, which can be characterized by the dispersed mineral content (Calcium in particular).

For high rank coals, variations in reactivity with burnoff (in the kinetic regime) have been associated with changes in internal surface area⁶. Consequently, reactivity predictions will require a description of the char morphology. For this purpose, the Random Pore Model derived for the kinetic regime by Bhatia and Perlmutter⁷ and Gavalas⁸ was used, which calculates surface area changes during reaction. For low rank coals, the intrinsic reactivity is primarily dependent on catalytic effects and a simple volumetric model was used.

In order to predict reactivity at high temperatures (regime II), one has to account for pore diffusion limitations. The model follows the approach of Smith⁹, who used the Thiele modulus¹⁰ to derive the value of the global reaction rate as a function of the intrinsic reaction rate and char properties such as char porosity, tortuosity and mean pore radius. In this case, it is assumed that the reaction occurs mainly on the external surface, with little penetration of the reactive gas inside the particle. The reaction rate is then proportional to the external surface area.

The transition region from kinetic to pore diffusion control was not explicitly investigated, since numerical solutions are usually necessary to calculate the reactive gas concentration profile in the particle. However, this region is relatively narrow and most of the available data can be considered to fall in either the kinetic or pore diffusion regime.

EXPERIMENTAL

T_{crit} Measurements - Correlations have been developed using an extensive database of "Critical Temperature" (T_{crit}) measurements obtained in our laboratory. The value of T_{crit} is an index of char reactivity which is related to the concentration of accessible active sites^{11,12}. The determination of T_{crit} relies on a TGA technique in which the weight loss is measured while the sample is heated at a constant heating rate in the presence of the reactive gas. The temperature (T_{crit}) at which the rate of weight loss reaches a value of 0.065 g/g-min (~ 0.001 g/g-s) is recorded and gives an indication of the reactivity of the char. The value of the reaction rate used for measurement of T_{crit} was chosen to be high enough to be easily measurable but low enough so that it is still in the kinetic regime, based on a Thiele modulus calculation¹⁰. In practice, T_{crit} has been observed to occur usually at the end of the kinetic regime, when pore diffusion limitations start to appear. The chars used for the development of correlations were produced in several different reactors and under widely different pyrolysis conditions¹².

TG-FTIR Measurements - The reaction rates at low temperature were measured isothermally using a TG-FTIR instrument which couples a Dupont 951 TGA with a Bomem Michelson 100 FT-IR spectrometer¹³. The reaction rate is constantly monitored during the entire burnoff process. In addition, since this technique allows the simultaneous measurement of weight loss and the evolution of carbon oxides, it eliminates potential errors in interpretation due to effects of oxygen adsorption. All experiments were performed using a partial pressure of oxygen of 0.13 atm (13.2 kPa), and a coal sample size of 10 mg, which corresponds to a char amount of 4 to 7 mg. The chars were prepared by heating at 30°C/min in nitrogen up to the pyrolysis temperature, followed by immediate cooling to the temperature at which the isothermal reactivity measurements were done.

MODEL DEVELOPMENT FOR KINETIC REGIME

Reactivity Model - Following the approach from Smith⁹ the reaction rate in the kinetic regime is given by:

$$r_p = S k_i v M_p C_s \quad \text{with} \quad k_i = A \exp\left(-\frac{E}{RT}\right), \quad C_s = \frac{P}{RT} \quad (1)$$

where S = Internal surface area of remaining char, k_i = Intrinsic rate coefficient, v = stoichiometric factor, M_p = molecular weight of carbon, and C_s = oxidant concentration. For simplicity, a reaction order of 1 was assumed.

For high rank coals, the value of S is given by the Random Pore Model^{7,8}:

$$S = S_o (1-X) (1-\Psi \ln(1-X))^{0.5} \quad (2)$$

where S_o = internal surface area of original char, Ψ = structural parameter, X = char burnoff.

For low rank coals, the volumetric model is used and S becomes:

$$S = S_o (1-X) \quad (3)$$

The preexponential factor, A , of the intrinsic rate coefficient, k_i , includes the number of active sites. The variations of A with coal type and pyrolysis conditions can be estimated with correlations based on T_{crit} measurements, and can be written for high rank coals (HRC) as:

$$A = A_{HRC} f(H_{char}) g(O_{coal}) \quad (4)$$

where $f(H_{char})$ and $g(O_{coal})$ are char hydrogen and coal oxygen correlation functions, respectively, which represent the changes in active site concentration, and A_{HRC} is the baseline frequency factor for high rank coals. The corresponding factor for low rank coals (LRC) is given by:

$$A = A_{LRC} f(H_{char}) g(O_{coal}) h(Ca_d) \quad (5)$$

where $h(Ca_d)$ is a correlation function based on the dispersed calcium concentration and A_{LRC} is the baseline frequency factor for low rank coals.

Development of Correlations - Since T_{crit} measurements occur at the end of the kinetic regime, before pore diffusion limitations start to dominate, correlations derived from T_{crit} measurements can be directly used to calculate intrinsic reactivity. A factor of 1.2 was, however, introduced in the preexponential to account for the slight effect of diffusion limitations. The functions f , g and h are expected to be positive functions of the char hydrogen content, coal oxygen content and coal mineral content, respectively. Since T_{crit} is inversely proportional to the reactivity (the higher T_{crit} , the less reactive the coal), $1/T_{crit}$ was found to be a more appropriate quantity to use to develop correlations.

H_{char} -Correlation - Good linear correlations of $1/T_{crit}$ vs the char hydrogen concentration (H_{char}) were obtained for all coals. The curves all showed very similar slopes, which implies that the influence of the degree of pyrolysis of the char is similar for all coals (Fig. 1). The data also seem to show a plateau for values higher than 3.5% H_{char} , which was included in the modeling. The initial loss of hydrogen during pyrolysis is primarily aliphatic, which does not have the annealing

effect of the loss of aromatic hydrogen during the latter stages of pyrolysis^{11,12}.

O_{coal} Correlation - For similar values of H_{char} , the value of $1/T_{crit}$ for different coals gives an idea of the influence of coal rank on reactivity, and should be roughly correlated with oxygen and/or mineral content. Plots of $1/T_{crit}$ (using 900° C chars) as a function of the coal oxygen content also showed a reasonable correlation (Fig. 2).

Mineral Correlation - Since mineral concentration and especially dispersed calcium is important only for low rank coals, a correlation was obtained using coals of oxygen content higher than 13%. Dispersed calcium was found to be the main mineral responsible for reactivity enhancement¹² and was used to develop this correlation. The amount of dispersed calcium was obtained by difference between the total amount of calcium measured by SEM/x-ray analysis minus the amount of calcium carbonate measured with FT-IR. As in the case of the other correlations, a linear fit of $1/T_{crit}$ vs. dispersed calcium gave a good representation of the data (Fig. 3). For low rank coals, the influence of calcium needs to be clearly separated from the effect of coal rank as measured by oxygen content. Since demineralized low rank coals show a reactivity similar to that of medium rank coals (of oxygen content approximately 13%), the dispersed calcium content is a more reliable parameter than coal rank to define reactivity for these coals. In order to account for this in the model, the value of O_{coal} is kept constant and set equal to 13% for coals of oxygen content higher than 13%.

Other second order effects include the combined effect of fluidity and pyrolysis heating rate on char reactivity. This can be important for fluid coals, and has been included in our model by obtaining separate $1/T_{crit}$ vs H_{char} correlations for different heating rates. The data points for Pittsburgh No. 8 coal (as well as other coals) in Fig. 1 which fall well below the lowest correlation line are from low heating rate experiments.

The correlations of $1/T_{crit}$ with H_{char} , O_{coal} and Ca_d (the dispersed calcium content) gave the equations:

$$1/T_{crit} = a \cdot H_{char} + b \cdot O_{coal} + d \quad \text{for high rank coals} \quad (6)$$

$$1/T_{crit} = a \cdot H_{char} + c \cdot Ca_d + e \quad \text{for low rank coals} \quad (7)$$

with $a=9.3 \times 10^{-5}$ ($a=4.5 \times 10^{-5}$ for low heating rates for fluid coals), $b=1.58 \times 10^{-5}$, $c=1.03 \times 10^{-4}$, $d=1.00 \times 10^{-3}$ and $e=1.26 \times 10^{-3}$, and where T_{crit} is in K and H_{char} , O_{coal} and Ca_d are in wt. % (daf).

Individual correlation plots (shown in Figs. 1-3) gave an accuracy range in T_{crit} of about $\pm 20^\circ\text{C}$. A parity plot of the results from the simultaneous correlations using H_{char} , O_{coal} , and Ca_d is shown in Fig. 4. The range of accuracy can be estimated as $\pm 40^\circ\text{C}$. Using the correlation based on the hydrogen content only (which is equivalent of having one adjustable parameter to represent coal rank and mineral effects), led to a much better prediction of the data, with a range of accuracy of $\pm 20^\circ\text{C}$ as shown in Fig. 5. This range of T_{crit} represents approximately a factor of 2 in rate. It should also be noted that the precision of the measurement of T_{crit} is $\pm 10^\circ\text{C}$.

To overcome potential shortcomings of using several correlations simultaneously, it is reasonable to assume one adjustable parameter. However for the cases presented below, the correlations were used without an adjustable parameter.

Intrinsic Rate Predictions - At T_{crit} , the rate of weight loss r_p reaches the value of 0.065/min $\sim$ 0.001/sec. By replacing the values of $1/T_{crit}$ and r_p in equation (1), the form of the correlation functions f , g and h used in equations (4) and (5) can be derived. It is implicitly assumed that $1-X$ is constant and equal to 0.85 at the point where T_{crit} is measured. S_o is also kept constant and was taken as 300 m^2/g . The value of the activation energy, E , has been calculated from

experimental data and was found to be approximate 30 kcal/mol for all chars and coals studied.

For high rank coals ($O_{\text{coal}} < 13\%$), equation (1) becomes:

$$r_p = 8.33 \times 10^2 \exp \frac{-15000}{T} \exp (1.4 H_{\text{char}}) \exp (0.237 O_{\text{coal}}) S_o (1-X) (1-\Psi \ln (1-X))^{0.5} \quad (8)$$

For low rank coals ($O_{\text{coal}} > 13\%$), the equivalent of equation (1) is:

$$r_p = 4.1 \times 10^4 \exp \frac{-15000}{T} \exp (1.4 H_{\text{char}}) \exp (1.54 Ca_d) S_o (1-X) \quad (9)$$

Those reaction rates correspond to the case where the oxygen partial pressure is 0.13 atm (13.2 kPa).

Predictions of reactions rate (for $X=0$) using equations (8) and (9) have been compared with data obtained in our laboratory (Pittsburgh No. 8 and Zap lignite chars) as well as literature data from Wells et al.¹⁴ (FMC, Occidental and Toscoal chars). The parameters used are indicated in Table I. The parameters for the literature chars were directly taken from reference 14. Figures 6 and 7 show the very good agreement obtained between the theory and the low temperature TGA data for all coals and chars studied.

Predictions of reaction rate as a function of burnoff are presented in Fig. 8 for Pittsburgh No. 8 (high rank coal) 600 °C char and Zap lignite (low rank coal) 900 °C char using the random pore

model and volumetric model respectively. The predictions were done by adjusting the reactivity amount (without using the correlations) in order to demonstrate the adequacy of the models chosen. The good fit obtained in the full range of burnoff justifies the use of these models.

MODEL DEVELOPMENT FOR PORE DIFFUSION REGIME

Calculation of Reaction Rate - Following Smith,⁹ the reaction rate in the diffusion regime can be expressed as a function of the intrinsic reaction rate:

$$r_p = \eta S_o k_i \nu M_p C_s \quad (10)$$

where η = effectiveness factor. η is equal to 1 in the kinetic regime, and is much smaller than 1 for the pore diffusion regime. Following the treatment by Mehta and Aris,¹⁵ the effectiveness factor can be determined using the relations between η and $\eta\phi^2$ where ϕ is the Thiele modulus¹⁰. In the diffusion regime the term $\eta\phi^2 \rightarrow 1/\eta$ which is equivalent to $\eta = 1/\phi$.

The Thiele modulus is given by:

$$\phi = \frac{d}{6} \left(\frac{\sigma S_o k_i}{D_e \nu M_p / M_o} \right)^{0.5} \quad (11)$$

with d = particle diameter, σ = density, D_e = effective diffusivity, M_o = molecular weight of oxidant. From the simple pore-structure model of Wheeler¹⁶, D_e can be calculated:

$$D_e = 9.7 \cdot 10^2 \cdot r_{pore} \left(\frac{T}{M_o} \right)^{0.5} \frac{e_o}{\tau_o}$$

(12)

where r_{pore} = mean pore radius in m, e_o = porosity, τ_o = tortosity.

The global reaction rate can be written:

$$r_p = \frac{6}{d} \left(D_e \cdot \frac{M_p}{M_o} \frac{S_o k_f}{\sigma} \right)^{0.5} C_s$$

(13)

The reaction rate depends on char properties such as the tortuosity, porosity and the mean pore radius. The tortuosity parameter has been introduced to account for the connectivity of pores. Its value has generally been taken between 1.5 and 10, usually equal to 2. The porosity and the mean pore radius can be measured. However their determination may be difficult in the case of a non-uniform pore size distribution.

Since the reaction occurs primarily near the particle surface, variations of reaction rate with burnoff are included into the particle size variations. In that case, the relationship between burnoff and particle size is given by: $d = d_o (1-X)^{1/3}$ where d_o = initial particle size.

Comparison of Predictions with Data - Using parameters indicated in Table I and kinetic parameters derived earlier, predictions in the diffusion regime for 600 °C and 900 °C Pittsburgh No. 8 chars and 900 °C Zap lignite chars in the pore diffusion regime are shown in Fig. 6. For low rank coals we used a "deactivation" function to account for the fact that catalysts have less impact on reactivity at high temperatures^{11,12}. At high temperatures, the reactivity of a low rank coal is forced to be equal to the reactivity of a coal of 13% oxygen. Although the number of data

points in the diffusion regime is limited, the transition between kinetic and diffusion control is fairly well represented by the theory. However, a TGA experiment is not optimal for measurement of high temperature rates since bed effects and mass transfer resistances become important under these conditions.

The model predictions for chars used in Ref. 14 (FMC, OCCIDENTAL and TOSCOAL) are presented in Fig. 7 (solid lines) together with literature correlations based on experimental data obtained from a drop tube reactor (symbols). As predicted by the Thiele modulus calculation, the apparent activation energy in the diffusion regime is well described by half the intrinsic activation energy. However, predictions of the reaction rate of the FMC char (whose parent coal is a Pittsburgh No. 8) give much lower values than the correlations based on the literature data. A similar comparison for the OCCIDENTAL char (which was produced from a Wyodak coal) and TOSCOAL char (from a Utah coal) leads to a fairly good agreement (within a factor of 5) between the predictions and the data. The lower value of the predicted reactivity for the low rank OCCIDENTAL coal char may be due to uncertainties on the "deactivation" process which could be much slower than represented. To resolve this problem, more data is necessary. It can also be noticed that differences in experimental combustion reactivity (as measured in the drop tube reactor) between low rank coals and high rank coals appear to be smaller at high temperature than at low temperature. However, mainly because of very different values of porosity, the model predicts a similar difference in reactivity at low and high temperature. This may indicate that the Thiele calculation (and the Wheeler's model) may be unsuitable to describe the behavior of cenospheric fluid coals with low porosity. More comprehensive models, which are not based on a continuum description of transport, but on discrete simulations and percolation theory may be more appropriate to represent the effect of large pores and pore connectivity.¹⁷

CONCLUSIONS

It was shown that correlations developed at low temperatures using the char hydrogen content, coal oxygen content, coal mineral content and pyrolysis heating rate have given good predictions of intrinsic reactivity for different coals and chars. With the simultaneous utilization of a random pore model for high rank coals and volumetric model for low rank coals, reactivity and reactivity variations with burnoff can be predicted.

The reactivity in the pore diffusion regime was calculated using the Thiele modulus. This approach necessitates the knowledge of char properties such as porosity, tortuosity and mean pore radius which can be difficult to obtain. However for low rank coals with high porosity the predictions were found to be fairly good. For cenospheric chars, the effect of pore connectivity and large pores probably needs to be taken into account. In that case, discrete simulations and percolation theory may be a better approach than theories using a continuum description of transport.

ACKNOWLEDGEMENTS

The authors are grateful for the support of the Morgantown Energy Technology Center of the United States Department of Energy under contract DE-AC21-86MC23075, for support of the study of char reactivity. The authors wish to acknowledge the contributions of Hsisheng Teng and Marie DiTaranto of Advanced Fuel Research, Inc. to the experimental work.

REFERENCES

1. Field, M.A., Combust. Flame, 14, 237, (1970).
2. Smith, I.W., Combust. Flame, 17, 421, (1971).
3. Mitchell, R.E. and J.W. McLean, Nineteenth Symposium (Int) on Combustion, The Combustion Institute, 1982, pp. 1113-1122.
4. Radovic, L.R., Walker, P.L., Jenkins, R.G., Fuel, 62, 849, (1983).
5. Suuberg, E.M., Calo, J.M., and Wojtowicz, M., ACS Div. of Fuel Chem. Preprints, 31, (3), 186, (1986).
6. Su, J.L., Perlmutter, D.D., AIChE J., 31, 6, 973 (1985).
7. Bhatia, S.K., Perlmutter, D.D., AIChE J., 26, 379 (1980).
8. Gavalas, G.R., AIChE J., 26, 577, (1980).
9. Smith, I.W., Nineteenth Symposium (Int) on Combustion, The Combustion Institute, 1982, pp. 1045-1065.
10. Thiele, E.W., Ind. Eng. Chem., 31, 916 (1939).
11. Solomon, P.R., Serio, M.A., Heninger, S.G., ACS Div. of Fuel Chem. Preprints, 31, (3), 200, (1986).
12. Serio, M.A., Solomon, P.R., Charpenay, S. and Suuberg, E.M. to be submitted to the Twenty-Fourth Symposium (International) on Combustion (1992).
13. Solomon, P.R., Serio, M.A., Carangelo, R.M., and Bassilakis, R., Energy & Fuels, 4, 319, (1990).
14. Wells, W.F., Kramer, S.K., Smoot L.D., Twentieth Symposium (International) on Combustion, p. 1539, The Combustion Institute, 1984.
15. Mehta, B.N., and Aris, R., Chem. Eng. Sci., 26, 1699 (1971).
16. Wheeler, A., Adv. Catal., 3, 249 (1951).
17. Sahu, R., Flagan, R. and Gavalas G., Combust. Flame, 77, 337 (1989).

NOMENCLATURE

A = pre-exponential factor, m/s

C_s = reactant concentration, mol/m³

Ca_d = % (daf) dispersed calcium in coal

d = particle diameter, m

d_o = initial particle diameter, m

D_e = diffusivity, m²/s

E = activation energy, kcal/mol

H_{char} = % (daf) hydrogen in char

k_i = reaction rate coefficient, m/s

M_o = molecular mass of reactive gas, g/mol

M_p = molecular mass of carbon, g/mol

O_{coal} = % (daf) oxygen in coal

P = partial pressure of reactive gas, atm

R = gas constant, m³ atm/(g mol K)

r_{pore} = mean pore radius, m

r_p = reaction rate, 1/s

S = internal surface area of remaining char, m²/g

S_o = internal surface area of initial char, m²/g

T = particle temperature, K

X = burnoff

GREEK SYMBOLS

η = effectiveness factor

ϵ_o = porosity

τ_o = tortuosity

σ = particle density, g/m³

Φ = Thiele modulus

ν = stoichiometric factor

Ψ = structural parameter

TABLE I
PARAMETERS USED IN REACTIVITY CALCULATIONS

Char	PIT 900 °C Char	PIT 600 °C Char	ZAP 900 °C Char	FMC	OCC	TOS
Parent Coal	Pittsburgh #8	Pittsburgh #8	Zap	Pittsburgh #8	Wyodak	Utah
Pyrolysis Heating Rate (°C/s)	0.5	0.5	0.5	10 ³	10 ⁴	10 ³
ϵ_o	0.1*	0.1*	0.3*	0.1	0.55	0.11
τ_o	2*	2*	2*	2*	2*	2*
d (μm)	70	70	70	90	63	55
r_{pore} (Å)	10*	10*	10*	10*	10*	10*
S_o (m ² /g)	300*	300*	300*	300*	300*	300*
σ_o (g/cm ³)	1.3*	1.3*	1.3*	1.52	0.86	1.43
O _{coal} (%)	8	8	21	9	21	11.8
H _{char} (%)	1.2	3.17	0.74	2	2	3.18
Ca _d (%)	0	0	1	0	1*	0

NOTES: 900 °C and 600 °C Pittsburgh No. 8 chars and 900 °C Zap lignite char have been produced in our laboratory.
FMC, Occidental and Toscoal are chars from Reference 14.

*estimated from measured values for similar chars or coals

Figure 1. Correlation of $1/T_{crit}$ with the percent (daf) hydrogen content of the char (H_{char}) for Zap, Rosebud, Illinois No. 6 and Pittsburgh No. 8 coals.

Figure 2. Correlation of $1/T_{crit}$ with the percent (daf) coal oxygen content (O_{coal}).

Figure 3. Correlation of $1/T_{crit}$ with the percent (daf) of dispersed calcium (Ca_d).

Figure 4. Measured T_{crit} vs. predicted T_{crit} using the three correlations simultaneously for Zap, Rosebud, Illinois No. 6 and Pittsburgh No. 8 coals.

Figure 5. Measured T_{crit} vs. predicted T_{crit} using the H_{char} correlation only for Zap, Rosebud, Illinois No. 6 and Pittsburgh No. 8 coals.

Figure 6. Comparison of predicted reactivity vs. TGA data for 600 °C and 900 °C Pittsburgh No. 8 chars and 900 °C Zap lignite chars.

Figure 7. Comparison of predicted reactivity (solid lines) vs. correlations (symbols) derived from experimental data from Wells et al.¹⁴ The low temperature data was measured using TGA. The high temperature data was obtained in a drop tube reactor. The symbols do not correspond to actual data points, but serve to identify the different correlations.

Figure 8. Comparison of TGA data (symbols) and model predictions (solid lines) for the reaction of a) 600 °C char from Pittsburgh No. 8 at 500 °C using the random pore model; b) 900 °C char from Zap Ignite combusted at 380 °C using the volumetric model.

APPENDIX C

SULFUR BALANCE FOR SO_x/SORBENT SUBMODEL EVALUATION AND RESULTS OF SENSITIVITY STUDY

A mass balance comparing the moles of SO₂ captured with the moles of CaO reacted was calculated. The coal burnout for the baseline case was 67.5 %. The coal contains 7.0% ash and 0.56% sulfur. Integrated SO₂ profiles at the reactor exit indicated that 48.8% of the gas-phase SO₂ was captured, giving a total molar capture of 2.4x10⁻⁵ kg.mole.SO₂/kg.air.

$$0.675(1 - 0.07)0.0056 \left(\frac{\text{kg} \cdot \text{S}}{\text{kg} \cdot \text{coal}} \right) 0.455 \left(\frac{\text{kg} \cdot \text{coal}}{\text{kg} \cdot \text{air}} \right) (0.488) \left(\frac{\text{kgmol} \cdot \text{SO}_2}{32.06 \text{ kg} \cdot \text{S}} \right) = 2.4 \times 10^{-5} \left(\frac{\text{kgmol} \cdot \text{SO}_2}{\text{kg} \cdot \text{air}} \right)$$

The average conversion of the three sorbent particles was 6.5%. This also translates to a capture of 2.4x10⁻⁵ kg.mole.SO₂/kg.air.

$$0.021 \left(\frac{\text{kg} \cdot \text{CaO}}{\text{kg} \cdot \text{air}} \right) 0.065 \left(\frac{\text{kgmol} \cdot \text{CaO}}{56.08 \cdot \text{kg} \cdot \text{CaO}} \right) \left(\frac{1 \text{ mol} \cdot \text{SO}_2}{1 \text{ mol} \cdot \text{CaO}} \right) = 2.4 \times 10^{-5} \left(\frac{\text{kgmol} \cdot \text{SO}_2}{\text{kg} \cdot \text{air}} \right)$$

Hence, the mass of sulfur captured by the reacting sorbent particles matches the mass of sulfur removed from the gas phase.

The sensitivity analysis results used to obtain the curves shown in Figs. II.G-1 through 6 are shown in the attached table.

Table C-1. Prediction Results Obtained for Parametric Runs of the PCGC-2 SO_x Submodel.

Values for parameters being held constant are given in Table II.G-1.

<u>Case No.</u> <u>%</u>	<u>Parameter Varied</u>	<u>Parameter Value</u>	<u>Sorbent</u> <u>Conversion</u>	<u>% SO₂</u> <u>Captured</u>
1.	none (baseline case)	see Table 1		5.87
2.	Ca/S (gas phase)	0.15		13.0
3.	Ca/S (gas phase)	0.34		19.2
4.	Ca/S (gas phase)	0.844		30.2
5.	Ca/S (gas phase)	1.29		38.6
6.	Ca/S (gas phase)	1.78		46.3
7.	Ca/S (gas phase)	3.17		59.4
8.	particle diameter	2.0	8.55	
9.	particle diameter	20.0	2.59	
10.	particle diameter	40.0	1.53	
11.	BET surface area	10.0	1.61	
12.	BET surface area	25	3.05	
13.	BET surface area	50	4.45	
14.	BET surface area	75	5.29	
15.	BET surface area	150	6.68	
16.	first order reaction	100*k _{first}	8.90	
17.	first order reaction	0.01*k _{first}	2.24	
18.	solid-state diffusion	100*D _{sp}	6.04	
19.	solid-state diffusion	0.01*D _{sp}	3.61	
20.	gas temperature	T+200 K	7.62	
21.	gas temperature	T-200 K	3.55	
22.	SO ₂ gas concentration	[SO ₂]*1.5	7.19	
23.	SO ₂ gas concentration	[SO ₂]*0.5	3.86	

END

**DATE
FILMED**

6 / 1 / 92