CATALYST DISPERSION AND ACTIVITY UNDER CONDITIONS OF TEMPERATURE-STAGED LIQUEFACTION

**Technical Progress Report for the Period
October to December 1991**

by

Alan Davis, H.H. Schobert, G.D. Mitchell

and L. Artok

PENNSTATE

Energy & Fuels Research Center

(814) 865-6544

**Pennsylvania State University
University Park, PA 16802**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. References herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

Two coals, a high volatile A bituminous coal from Utah and a subbituminous coal from Texas, were subjected to temperature-staged liquefaction in hydrogen and hydrogen/hydrogen sulfide atmospheres. Addition of H_2S to the reaction gas increased the conversion of both coals, through higher asphaltene yields from the bituminous coal and higher yields of all liquid products from the subbituminous coal. Generally the addition of ferrous sulfate to the coals, followed by liquefaction in hydrogen, had about the same effect as addition of H_2S to the gas, though the systems with added FeSO_4 had lower yields of preasphaltenes than obtained by use of $\text{H}_2:\text{H}_2\text{S}$. The addition of H_2S to the gas combined with impregnation with FeSO_4 provided significant enhancement of conversion of both coals. For both coals the effect of using the two additives together was to enhance the asphaltene yields. The results of this work suggest the possibility of selectively tailoring the behavior of the catalyst in different stages of the liquefaction process by selecting the appropriate gaseous atmosphere.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	iii
PROGRAM OBJECTIVES	1
PROGRAM OUTLINE	1
Catalyst Transformation	1
Catalysts and Their Dispersion	2
Coal Pretreatment	3
Evaluation of Impregnated Coals and Residual Materials from Other DOE Programs	4
DESCRIPTION OF TECHNICAL PROGRESS	6
1. THE EFFECT OF CATALYST PRECURSOR AND ATMOSPHERE ON LIQUEFACTION OF COALS	6
TEMPERATURE-STAGED LIQUEFACTION OF COALS IMPREGNATED WITH FERROUS SULFATE	7
1.1. <u>Introduction</u>	7
1.2. <u>Experimental</u>	9
1.3. <u>Results and Discussion</u>	12
1.3.1. Reaction Chemistry of Ferrous Sulfate	12
1.3.2. Reactions of Coals Impregnated with Ferrous Sulfate	17
1.4. <u>Implications for Liquefaction Processing</u>	23
References	25

PROGRAM OBJECTIVES

The general objectives of this research are 1) to investigate the use of highly dispersed catalysts for the pretreatment of coal by mild hydrogenation, 2) to identify the active forms of the catalysts under reaction conditions and 3) to clarify the mechanisms of catalysis. The ultimate objective is to ascertain if mild catalytic hydrogenation resulting in very limited or no coal solubilization is an advantageous pretreatment for the transformation of coal into transportable fuels. The experimental program will focus upon the development of effective methods of impregnating coal with catalysts, evaluating the conditions under which the catalysts are most active and establishing the relative impact of improved impregnation on conversion and product distributions obtained from coal hydrogenation.

PROGRAM OUTLINE

Catalyst Transformation

Four catalyst materials have been selected for this investigation: ammonium tetrathiomolybdate, ferrous sulfate, molybdenum hexacarbonyl, and iron pentacarbonyl. Insofar as it is possible, these catalysts will be evaluated by TGA in order to determine 1) the temperature at which a chemical change occurs in the catalyst precursor, 2) the holding time at that temperature needed to reach completion of the transformation, and 3) and effects of heating rate on catalyst precursor transformation. Experiments will be performed for each catalyst for a matrix of conditions, as follows: 1) three heating rates: 5°, 50°, and about 125°C/min; 2)

three final temperatures: 275°, 350°, and 425°C; 3) two atmospheres, namely nitrogen and hydrogen; and 4) one "soak time" at temperature (1 h). Also, in order to define the heating regimes over which both catalysts and coals decompose, each of the two test coals will be evaluated in the TGA under the same reaction conditions employed with the catalysts.

Each of the catalyst precursors will be tested in 25 ml microautoclaves (tubing bombs) in order to prepare larger quantities of the transformed materials for subsequent characterization. The time-temperature regimes used in these experiments will be selected based on results from the TGA study. Three atmospheres will be used: 1) nitrogen, 2) hydrogen, and 3) 95:5 hydrogen:hydrogen sulfide. In each of these experiments the tubing bomb will be pressurized to 1000 psi (cold).

Catalysts and Their Dispersion

The purpose of this portion of the research effort is to investigate methods of impregnating coal with catalysts prior to liquefaction. A variety of techniques that are best suited for a particular catalyst will be explored. Those planned include:

- a) using the ammonium tetrathiomolybdate or ferrous sulfate in aqueous solution; the coals will be slurried with the solution of catalyst precursor and then freeze-dried;
- b) these same precursors will be applied to coal in solvents that are known to swell coal structures; THF, pyridine, methanol and tetrabutylammonium hydroxide. However, the catalyst materials must be either soluble or form a fairly stable suspension in the appropriate solvent in order to promote access of catalyst to interior surfaces of the coal;
- c) iron pentacarbonyl and molybdenum hexacarbonyl will be applied to coal in hydrocarbon or other organic solvents that may promote coal swelling;

- d) ion exchange of iron, as ferrous sulfate, onto the lignite selected for this project will also be investigated.

With some basic information with respect to solvent and catalyst interactions, both individual large particles and fine particulate samples of each coal will be impregnated or ion-exchanged with the catalyst, and the dried sample prepared and observed under the SEM to determine the extent of impregnation and dispersion of the catalyst.

Coal Pretreatment

Two coals, a lignite and an hvCb, will be selected from the Penn State Sample Bank in consultation with DOE. Each coal will possess high vitrinite and low sulfur contents and ash yields, and will have been thoroughly characterized by proximate and ultimate analyses, maceral and reflectance analyses, as well as major and trace elements.

The principal objective of this work is to explore the influences of catalyst presence, dispersion and chemistry on coal pretreatment. All experiments will be carried out in 25 Ml microautoclave reactors, under 1000 psi (cold) pressure and using a nominal 5 g of coal and 5 g of vehicle. The time-temperature regimes will be defined on the basis of results obtained from the catalyst transformation investigations.

Temperature-staged liquefaction consists of two distinct steps, the low-temperature pretreatment and the high-temperature liquefaction reaction.

The main focus of this work is on pretreatment, and therefore most of the experiments will be carried out in the range of 275°-350°C. In order to assure that the pretreatment stage has been effective in converting the starting coal into an "active coal" intermediate, a limited number of

experiments will be performed incorporating the second, high-temperature stage (425°C) as well. The gas atmosphere will be hydrogen. If tests from the catalyst transformation work are encouraging, additional experiments will be performed in 95:5 H₂:H₂S atmospheres.

Experiments will be run without catalyst to obtain baseline data and with each of the four catalyst precursors. The level of catalyst loading will be chosen to ensure that the amount of metal left in the residue is detectable by the planned characterization techniques. Also, catalyst loading will be adjusted so that the same loading on a gram-atom basis is achieved for the iron and molybdenum. Furthermore, the experiments will be run with and without a hydrogen-donor vehicle. It is planned to use phenanthrene as a non-donor vehicle and dihydrophenanthrene as a donor vehicle.

Following liquefaction, a variety of conventional techniques will be used to characterize gaseous, liquid and solid products. Gases will be routinely analyzed by gas chromatography. Oils and asphaltenes will be routinely analyzed by GC, GC/MS, and ¹H NMR, and by FTIR and ¹³C (solution) NMR for selected samples. Selected samples of the solid residue will be characterized by DRIFT, ¹³C (solid) NMR and optical and electron optical microscopy.

Evaluation of Impregnated Coals and Residual Materials from Other DOE Programs

Impregnated coals and liquefaction residues will be solicited from DOE and its contractors for microscopic study of materials generated in larger scale experiments than ours, and through other novel approaches to

hydrogenation. Samples also will be sought from projects that are developing unique techniques for the impregnation of catalyst into coals for liquefaction. It is expected that many of these samples will come from PETC and the Advanced Research program to assess the degree of catalyst dispersal and to assess the relative extent of hydrogenation and condensation reactions.

DESCRIPTION OF TECHNICAL PROGRESS

1. THE EFFECT OF CATALYST PRECURSOR AND ATMOSPHERE ON LIQUEFACTION OF COALS

All of the experimental work concerning catalyst transformation, coal pretreatment and product work-up has been completed during this reporting period. Much of the assembly and synthesis of the data for the final project report has also been accomplished. As part of the technology transfer process, we have continued the preparation of several manuscripts for publication in the peer-reviewed professional literature. The draft of one of these papers is incorporated in this report; it deals with the effect of catalyst precursor addition and of reactor atmosphere (H_2 ; H_2/H_2S) on temperature-staged liquefaction. Included was a study of the catalyst chemistry and crystallographic state during reaction. This paper will be submitted to *Fuel Processing Technology*. Another manuscript entitled "Swelling Pretreatment of Coals for Catalytic Temperature-Staged Liquefaction" is being prepared. It deals with the results of experiments in which the effects of swelling pretreatment upon reaction in the higher temperature stage are investigated. This manuscript will be submitted for publication to *Energy & Fuels*.

The modified draft of the first of these two papers follows. It forms a comparison to the paper "Swelling Pretreatment of Coals for Improved Liquefaction" which was included in the previous Quarterly Technical Progress Report.

TEMPERATURE-STAGED LIQUEFACTION OF COALS IMPREGNATED WITH FERROUS SULFATE

1.1. Introduction

Iron compounds are attractive catalysts for coal liquefaction due to their relatively low cost, hydrogenation activity and the potential of soluble iron compounds to be dispersed on or impregnated into the coal. One of the earliest large-scale direct liquefaction operations, the Bergius - IG Farben process, used a disposable iron oxide catalyst [1]. In many liquefaction systems it appears that the addition of sulfur, or the sulfiding of the iron catalyst, improves the activity of the iron [2]. The active form of iron catalyst is considered to be an iron sulfide [3]. The non-stoichiometric iron sulfide, pyrrhotite, plays an especially important role in coal liquefaction [4-6]. The Fe/S atomic ratio which provides maximum conversion in liquefaction is in the range 0.5 to 1.0 [7]. In addition, a synergism exists between pyrrhotite and H_2S for coal hydrol liquefaction [8]; indeed, in some cases it is thought that pyrrhotite is catalytically active only in the presence of H_2S [9].

It is now generally appreciated that beneficial effects can be obtained in liquefaction by achieving good dispersion of the catalyst on the surface of the coal particles. Catalyst dispersion provides an increase in the number of catalyst particles in close proximity to sites at which reaction is occurring, and, furthermore, the dispersion of catalyst as fine particles increases the amount of active catalyst surface area available in the reactor (relative to using the same quantity of catalyst, but in larger, less dispersed particles). An approach to achieving catalyst dispersion is to employ a liquid vehicle as the medium for

dispersing the catalyst. Unfortunately, several of the compounds of interest as liquefaction catalysts, such as pyrrhotite, pyrite, and molybdenum disulfide, are insoluble in all common solvents. Consequently, a strategy of using "catalyst precursors" has been developed, in which the precursor is a soluble compound that may not itself be catalytically active, but transforms at elevated temperature into an active catalyst. As an example, the moderately soluble ammonium tetrathiomolybdate, which decomposes to molybdenum disulfide at typical liquefaction reaction temperatures, has been used as a precursor to obtain a good dispersion of the disulfide.

A variety of iron compounds are soluble in water or organic solvents, and have been investigated as prospective catalyst precursors for direct liquefaction and for co-processing. The compounds used in this application have included iron(II) acetate [10], iron pentacarbonyl [11-15], dithiodiiron hexacarbonyl [12], iron(III) acetylacetonate [16], and iron(III) nitrate [17]. The compound used in the present work is iron(II) sulfate, or ferrous sulfate. Watanabe et al. [18] and Suzuki et al. [19] reported results of using ferrous sulfate as a catalyst precursor in liquefaction. In their work, it appears that addition of ferrous sulfate did not promote conversion of low sulfur-content coals. It is likely that ferrous sulfate did not completely transform to the active catalyst during liquefaction reaction. Rahimi and co-workers examined the effect of H_2S , FeSO_4 , and both H_2S and FeSO_4 together on coprocessing of coals with heavy oils [20]. They showed that an $\text{H}_2\text{S}:\text{H}_2$ atmosphere is superior to the addition of FeSO_4 in a H_2 atmosphere at low and moderate severity

conditions, but that at high severity the FeSO_4 addition is superior to use of H_2S . Their results may reflect the transformation of FeSO_4 to the catalytically active pyrrhotite at high-severity reaction conditions.

The work reported in this paper is part of a broader investigation of catalytic pre-treatments in temperature-staged liquefaction [21]. The concept of temperature-staging involves reaction first at a low temperature, e.g. 275–350°C, followed by a second reaction at a higher temperature more typical of direct liquefaction processing, e.g., 375–450°C. It has been well established that this technique can provide significant benefits, particularly in conversion to soluble oil products [22,23]. It was not a goal of the present work to optimize reaction conditions, but rather to explore the changes in product distribution resulting from impregnation of two coals of different rank with the precursor of interest, FeSO_4 . Hence we selected a temperature-staging regime of 275°/425° mainly to insure commonality with prior work and collateral work in progress in our laboratory, eventually to develop comparisons of the benefits of using this catalyst precursor with those obtained from other precursors at comparable reaction conditions.

1.2. Experimental

The coals used for this work were Blind Canyon (Utah) high volatile A bituminous coal and Big Brown (Texas) subbituminous C coal. Proximate and ultimate analyses of these coals are given in Table 1. The coals were impregnated with $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ (0.59% iron, expressed as elemental iron, not the ferrous sulfate salt, on a daf coal basis) in the following way: the

Table 1. Proximate and Ultimate Analyses of Coals

A. Proximate Analysis (Wt%, Dry Basis)		
	Blind Canyon	Big Brown
Ash	5.84	15.81
Volatile	44.50	47.40
Fixed Carbon	49.66	36.79
B. Ultimate analysis (Wt%, daf)		
Carbon	81.28	74.27
Hydrogen	8.24	5.64
Nitrogen	1.55	1.46
Sulphur	0.42	1.18
Oxygen (Diff.)	10.50	17.45

iron salt was dissolved in sufficient distilled water to give an approximate water-to-coal ratio of 1:1 (v/w). Usually a single batch of 30 grams of coal was impregnated at a time, enough for several experiments. The solution was added to coal in a flat-bottom flask and the mixture was stirred for 30 min, then excess water was removed in vacuum at room temperature. The mixture was continuously being stirred during this procedure. While the coal was still wet with water, the mixture was quenched in dry ice-acetone bath until it became frozen and was then freeze dried, followed by vacuum drying at room temperature. This low-temperature drying of the coal-catalyst slurry has been shown to improve conversion, presumably by an improvement in catalyst dispersion [24]. In the case of thermal hydrogenation, the coals were dried overnight at 100°C.

Liquefaction experiments were carried out using horizontal microautoclave reactors (tubing bombs) with a 25 mL capacity. Five grams

of each prepared sample and five grams of phenanthrene were placed in the tubing bomb and mixed with a spatula. Then the reactor was sealed and air was removed by repetitive pressurizing to 7 MPa, once with nitrogen, twice with hydrogen. Subsequently, the reactor was pressurized to 7 MPa (cold) with H_2 or $H_2S:H_2$ (5:95). The reactor was immersed in a preheated sand bath. Temperature-staged reaction conditions were 275°C for 30 min and at 425°C for 30 min. Hydrogen pressures were in the range 10.5–14 MPa at reaction temperature. The reactor was oscillated vertically through 2.5 cm at 350 cycles min^{-1} . At the end of the each stage, reactor was plunged into cold water to quench the reaction, then the volume of the product gas was measured by water displacement. The water was saturated with NaCl in order to prevent CO_2 dissolution. Gas samples were collected for analysis. The CO , CO_2 , C_1 – C_2 analyses of the gas were performed using a packed Carbosieve column with thermal conductivity detector. The C_1 – C_5 analyses of the gas were performed using a Chemipack C18 column (connected to a flame ionization detector) on a Perkin Elmer model gas chromatograph. Details of the separation and calculation of yields were given elsewhere [8]. Briefly, preasphaltenes are THF-soluble, toluene-insoluble; asphaltenes are toluene-soluble, hexane-insoluble; and oils are hexane-soluble. Total conversion is determined from the weight of THF-insolubles. Hydrogen absorption was calculated as the difference between the amount of hydrogen initially charged to the reactor and that found by gas chromatographic analysis of the gas after reaction.

To determine the fate of ferrous sulfate itself at these reaction conditions, the salt was reacted in microautoclaves at 7 MPa (cold) N_2 , H_2

or $\text{H}_2\text{S}:\text{H}_2$ (5:95) at temperatures of 275, 350 and 425°C for one hour. X-ray diffraction (XRD) measurements of the products were made using $\text{Cu-K}\alpha$ radiation with Rigaku equipment and operated at 40 kV and 20 mA. Sulfur and iron analyses were performed by Galbraith Laboratories, Inc. Thermogravimetric analysis of $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ was performed using a Perkin Elmer model TGA-7 in a nitrogen atmosphere.

1.3. Results and Discussion

1.3.1. Reaction Chemistry of Ferrous Sulfate

Thermal analysis of ferrous sulfate in nitrogen indicated three regions of decomposition (Figures 1-2). First, a decomposition takes place around 140°C and represents loss of water of hydration. The product in this stage is $\text{FeSO}_4 \cdot \text{H}_2\text{O}$. The second decomposition begins at 230°C and is completed at 260°C. The product of this stage is FeSO_4 . Final decomposition of the anhydrous ferrous sulfate is effected at temperatures > 575°C, and the product of this stage is hematite (Fe_2O_3). In each of these cases, the identity of the product was verified by XRD. By examining the products obtained in microautoclave reactions of ferrous sulfate in N_2 , H_2 and $\text{H}_2\text{S}:\text{H}_2$, it was determined that ferrous sulfate is stable at 425°C in nitrogen and is stable at least to 350°C in either H_2 and $\text{H}_2\text{S}:\text{H}_2$ (5:95). However, it decomposed at 425°C in H_2 and $\text{H}_2\text{S}:\text{H}_2$ (5:95). XRD of the product obtained at 425°C in H_2 showed the presence of troilite and pyrrhotite phases (Figure 3), whereas only the pyrrhotite phase was observed when ferrous sulfate reacted in a mixture of H_2S and H_2 at 425°C (Figure 4). The elemental composition of the stoichiometric ferrous

Figure 1. Thermogravimetric Decomposition of Ferrous Sulfate Heptahydrate in the Temperature Range 50 - 400°C, Nitrogen Atmosphere

Figure 2. Thermogravimetric Decomposition of Ferrous Sulfate Heptahydrate in the Temperature Range 100 - 800°C, Nitrogen Atmosphere

Figure 3. X-Ray Diffractogram of Products Obtained from Reaction of Ferrous Sulfate in Hydrogen Atmosphere at 425°C

Figure 4. X-Ray Diffractogram of Products Obtained from Reaction of Ferrous Sulfate in 5:95 $\text{H}_2\text{S}:\text{H}_2$ Atmosphere at 425°C

sulfide is 63.6 Fe, 36.4 S. By comparing the elemental composition of the products (50.0 Fe, 32.8 S in H_2 and 57.5 Fe, 37.8 S in $H_2S:H_2$ at $425^\circ C$), it can be seen that the $H_2S:H_2$ gas mixture is superior for the transformation of ferrous sulfate to pyrrhotite.

1.3.2. Reactions of Coals Impregnated with Ferrous Sulfate

A comparison of conversion data from liquefaction of the Blind Canyon and the Big Brown coals in H_2 and $H_2S:H_2$ (5:95) with and without $FeSO_4$ is given in Tables 2 and 3. For reaction without added $FeSO_4$, hydrogen sulfide addition to the reaction gas increased the total conversion of both coals. The increased conversion came mainly via greater formation of asphaltenes for the Blind Canyon coal. The yields of all liquid products - oil, asphaltenes, and preasphaltenes - was increased for the Big Brown coal, but the most significant increase was in the oils. Absorption of hydrogen from the gas phase also increased by addition of hydrogen sulfide. These findings are in agreement with the well-known observation that H_2S is beneficial for the liquefaction of coals due to enhancing of hydrogen transfer reactions (hydrogen shuttling), to cleavage of certain types of bonds, and to sulfiding iron species which are already present in coal, producing iron sulfide active for hydrogenation of coal [8,25-29].

The use of $FeSO_4$ (in H_2) slightly increases total conversion from 48.0 % (daf basis) to 52.4% for the Blind Canyon, and from 53.1% to 61.2% for the Big Brown coal. In the liquefaction of the Blind Canyon coal, the major increase in total conversion with added $FeSO_4$ is a result of

Table 2. Conversion and product yields from liquefaction of Blind Canyon bituminous coal with and without FeSO_4 catalyst precursor in different atmospheres

Gas Atm.	Catalyst	H_2 Abs. from Gas mg. and (% daf)		Conversion % (daf)					
				Total	P.asph	Asph	Oil	CO_x	$\text{C}_1\text{-C}_5$
H_2	No	26.0	(0.56)	48.0	12.3	8.5	21.9	3.1	2.2
$\text{H}_2\text{S}:\text{H}_2$	No	45.4	(0.97)	58.2	12.1	17.2	22.3	2.8	3.8
H_2	Yes	37.2	(0.83)	52.4	10.2	15.4	21.0	3.3	2.5
$\text{H}_2\text{S}:\text{H}_2$	Yes	71.2	(1.58)	78.5	15.5	29.2	27.5	2.9	3.4

Table 3. Conversion and product yields from liquefaction of Big Brown subbituminous coal with and without FeSO_4 catalyst precursor in different atmospheres

Gas Atm.	Catalyst	H_2 Abs. from Gas mg. and (% daf)		Conversion % (daf)					
				Total	P.asph	Asph	Oil	CO_x	$\text{C}_1\text{-C}_5$
H_2	No	25.3	(0.61)	53.1	8.2	10.9	21.2	9.9	2.9
$\text{H}_2\text{S}:\text{H}_2$	No	47.0	(1.17)	66.7	11.2	13.9	28.1	10.0	3.5
H_2	Yes	50.6	(1.26)	61.2	6.7	13.0	27.2	12.0	2.3
$\text{H}_2\text{S}:\text{H}_2$	Yes	57.4	(1.43)	71.5	5.1	24.4	27.7	10.2	4.1

increased asphaltene yield; in contrast, the major increase in conversion of Big Brown is via increased oil yield. In this respect, impregnation of coal with FeSO_4 followed by temperature-staged liquefaction in a hydrogen atmosphere has nearly the same effect as liquefaction of the same coal at the same conditions in a $\text{H}_2\text{S}:\text{H}_2$ atmosphere but without added ferrous sulfate. For both coals, the principal distinction of reaction in the $\text{FeSO}_4:\text{H}_2$ system relative to the $\text{H}_2\text{S}:\text{H}_2$ case is that the ferrous sulfate addition provides a lower yield of preasphaltenes than does reaction in $\text{H}_2\text{S}:\text{H}_2$.

Although the two coals provided similar conversions when liquefied in H_2 atmosphere without added catalyst, the improvement in total conversion obtained by addition of $FeSO_4$ is much greater for the Big Brown subbituminous than for the Blind Canyon bituminous coal. We attribute this difference to the higher oxygen content of the former coal. Iron catalysts have been shown in several investigations to facilitate carbon-oxygen bond cleavage [e.g., 30,31]. Furthermore, the hydrogen uptake nearly doubles in the case of the Big Brown coal (from 25.3 mg without added $FeSO_4$ to 50.6 mg with $FeSO_4$), whereas a much smaller increase (26.0 mg to 37.2 mg) was observed in the comparable experiments with Blind Canyon coal. Previous workers have indicated that iron catalysts facilitate conversion of coal to asphaltene, but do not significantly improve hydrogen uptake [10,14]. Our work substantiates this observation for the bituminous coal, but certainly not so for the subbituminous.

The $H_2S:H_2$ atmosphere in combination with impregnated $FeSO_4$ was quite beneficial for conversion of these coals. Addition of H_2S to the reaction gas atmosphere combined with impregnation with ferrous sulfate significantly promoted conversion of both coals. In the case of Blind Canyon coal, enhancement of the conversion in $H_2S:H_2$ with impregnated ferrous sulfate is mainly via greater formation of asphaltenes. For this coal, treatment with either H_2S or $FeSO_4$ used singly produced, in both cases, a near doubling of the asphaltene yield (that is, from 8.5% to 17.2% by addition of H_2S to the reactive gas atmosphere, and from 8.5% to 15.4% by impregnation with $FeSO_4$). The use of the two additives together appeared to have a synergistic effect, resulting in a greater than three-

fold increase in asphaltene yield. It is also noteworthy that use of H_2S and FeSO_4 in combination increased the oil yield as well. The observed hydrogen absorption increased from 37.2 mg for reaction in a hydrogen atmosphere to 71.2 mg for reaction in $\text{H}_2\text{S}:\text{H}_2$ (5:95) with FeSO_4 . In the case of Big Brown subbituminous, addition of H_2S or ferrous sulfate singly increased the yields of all of the liquid products, relative to liquefaction only in H_2 , but the most significant increase was in the oil yield. The use of these two additives together had no additional effect on oil yield, but produced a marked increase in asphaltenes. Hydrogen uptake increased from 50.6 mg to 57.4 mg, compared to the reaction which was performed in H_2 with FeSO_4 . When comparing the amounts of hydrogen consumed for the two coals, it is important to recognize that there is less carbonaceous coal substance in the reactor with the Big Brown coal than with Blind Canyon, because of the higher mineral matter content of the former. To compare the results of one coal with respect to the other, we show in Tables 2 and 3 the hydrogen consumptions corrected to a daf basis.

When the coals are impregnated with FeSO_4 and liquefied in a H_2 atmosphere (with no added H_2S), there is little increase in total conversion relative to the reaction without FeSO_4 . However, there is a marked shift in the product slate toward lighter products. For example, the asphaltene/preasphaltene ratio for Blind Canyon liquefaction increases from 0.69 without impregnated FeSO_4 to 1.51 with FeSO_4 . Thus a major effect of the addition of FeSO_4 to Blind Canyon coal is the catalysis of the hydrogenation of preasphaltenes to asphaltenes. The corresponding change for the Big Brown coal is 1.33 to 1.94, again demonstrating that the

preasphaltene-to-asphaltene conversion has been facilitated by addition of FeSO_4 . Even though the initial product slate (that is, as obtained for liquefaction by H_2 without either FeSO_4 or H_2S addition) is different for the two coals, as indicated for example by the significantly different asphaltene/preasphaltene ratios, the added FeSO_4 appears to intervene in exactly the same way for both coals. A distinction between the behavior of the two coals impregnated with FeSO_4 and reacted in H_2 is the significant difference in hydrogen utilization. For the Blind Canyon coal, hydrogen absorption increased from 26.0 to 37.2 mg upon addition of FeSO_4 . However, for Big Brown coal, the hydrogen uptake doubled, from 25.3 to 50.6 mg, accompanied by an increase in asphaltenes and a significant increase in oils. Big Brown subbituminous has about three times the sulfur content of Blind Canyon coal (1.18% vs. 0.42%), and this difference in coal behavior may reflect an *in situ* sulfiding of the FeSO_4 by H_2S generated from the coal.

The data in Tables 2 and 3 has been plotted as Figure 5, showing the total conversion, asphaltene yield, and oil yield as functions of the hydrogen consumption. Results for both coals, reaction with and without catalyst, and in both H_2 and $\text{H}_2\text{S}:\text{H}_2$ atmospheres are incorporated as a single data set. It is noteworthy that the lines (obtained by linear least squares regression) have similar slopes for the total conversion and asphaltene yields as functions of hydrogen consumption, while the slope of the oil yield vs. hydrogen consumption line is closer to zero. This observation suggests that the principal role of hydrogen absorbed from the gas phase is to participate in the depolymerization of the coal to

Figure 5. The Dependence of Total Conversion, Asphaltene Yield and Oil Yield on Hydrogen Absorption from the Gas

The data plotted include the results for both coals, with and without FeSO_4 impregnation and in H_2 and 5:95 $\text{H}_2\text{S}:\text{H}_2$ atmospheres.

relatively heavy products (i.e., asphaltenes) and not in the hydrogenation of the asphaltenes to oils.

It must be recognized that a possible side reaction in this liquefaction system is the hydrogenation of the liquid vehicle, phenanthrene. Suzuki and co-workers have demonstrated the use of pyrrhotite to hydrogenate phenanthrene [15]. Thus some of the observed hydrogen uptake in our experiments could reflect the hydrogenation of phenanthrene. The hydrogenation product, 9,10-dihydrophenanthrene, is a very good hydrogen donor. Thus it was of concern to check the possibility that our conclusions of the behavior of added H_2S , FeSO_4 , or both, were not confounded by the hydrogenation of phenanthrene and the reaction of the resulting 9,10-dihydrophenanthrene with the coal. Gas chromatographic analysis of the hexane-soluble products showed that less than 2% of the phenanthrene was hydrogenated in our system. Hence we consider that hydrogen uptake by phenanthrene and reaction of the 9,10-dihydrophenanthrene with the coal are negligible in this system. Furthermore, since the same quantities of phenanthrene, H_2S , and FeSO_4 were used in all experiments, and since the reaction conditions were kept the same, the differences in the extent of hydrogen uptake from one experiment to another must incorporate at least some coal-specific effects.

1.4. Implications for Liquefaction Processing

We have recently shown that the effect of sulfided catalysts in temperature-staged liquefaction is mainly to increase total conversion via formation of relatively heavy liquids (asphaltenes and preasphaltenes),

whereas hydrogenation catalysts have little effect on the total conversion, but rather facilitate conversion of those liquids which do form into lighter products [32]. Collateral work in this laboratory has shown that the efficacy of impregnated nickel sulfate in total conversion, liquids yield, and hydrodesulfurization of Mequinenza (Spanish) lignite is directly related on the extent to which NiSO_4 has transformed to NiS under a given set of reaction conditions [33].

The results communicated in this paper suggest a strategy for tailoring the activity of impregnated FeSO_4 for temperature-staged liquefaction. Liquefaction in H_2 with FeSO_4 provides little improvement in conversion but rather increased yields of lighter products. For a coal which undergoes facile decomposition to liquids even in the absence of catalysts, the H_2 - FeSO_4 combination improves the product slate. On the other hand, for those coals which require a dissolution catalyst to facilitate decomposition to liquids, the addition of small amounts of H_2S to the gas phase, in concert with impregnated FeSO_4 , can significantly improve conversion relative to that obtained with $\text{H}_2\text{S}:\text{H}_2$ or with FeSO_4 alone. The effect of H_2S is not only to promote liquefaction itself; it is also effective to transform catalyst precursors to active forms. FeSO_4 is quite a stable compound, and it can not be decomposed up to 540°C in nitrogen. A hydrogen atmosphere is not enough to transform it completely to pyrrhotite at typical liquefaction temperatures. The additional sulfur made available to the reaction system from the added H_2S may be necessary

to transform FeSO_4 completely to pyrrhotite, which is believed to be the active catalyst for the liquefaction of coals, at these conditions.

Because processing improvements (that is, increases in total conversion and in asphaltene or oil yield) clearly result from addition of FeSO_4 in either a H_2 or $\text{H}_2\text{S}:\text{H}_2$ atmosphere, the FeSO_4 precursor converts to a catalytically active species in either case. However, the specific behavior of the resulting catalytically active species is different, depending on the chosen gas atmosphere. Thus with a H_2 atmosphere, large increases in conversion are not obtained, but there seems to be a shift in the product slate to favor lighter materials: asphaltenes rather than preasphaltenes, or oils rather than asphaltenes. It becomes possible for an investigator to consider at what point (i.e., breakdown of the coal or hydrogenation of the products) in the liquefaction of *a given coal* it is most useful to have the catalyst intervene, and then, by selection of the reactive atmosphere, convert the catalyst precursor into a species active for catalysis of the desired step. The ability to tailor the effect of impregnated FeSO_4 by sulfiding, or not sulfiding as the case may be, suggests that some benefits might also be realized by having the catalyst in different forms in the different stages (i.e., low- or high-temperature) of liquefaction.

References

1. Probstein, R.F. and Hicks, R.E., 1982. Synthetic Fuels. McGraw-Hill, New York, Chapter 6.
2. Jackson, W.R. and Larkins, F.P. , 1991. In: Durie, R.A. (Ed.), The Science of Victorian Brown Coal. Butterworth-Heinemann, Oxford, Chapter 10.

3. Garg, D. and Givens, E.N., 1982. Ind. Eng. Chem. Process Des. Devel., 21:113.
4. Montano, P.A. and Granoff, B., 1980. Fuel, 59:214.
5. Brooks, D.G., Guin, J.A., Curtis, C.W. and Placek, T.D., 1983. Ind. Eng. Chem. Process Des. Devel., 22:343.
6. Bommanavar, A. and Montano, P.A., 1983. Fuel, 62:932.
7. Yokoyama, S., Yoshida, R., Narita, H., Kodaira, K and Maekawa, Y., 1986. Fuel, 65:164.
8. Baldwin, R.M. and Vinciguerra, S., 1983. Fuel, 62:498.
9. Narain, N., Cillo, D.L., Steigel, G.J. and Tischer, R.E., 1987. In: Volborth, A. (Ed.), Coal Science and Chemistry. Elsevier, Amsterdam, Chapter 4.
10. Cook, P.S. and Cashion, J.D., 1987. Fuel, 66:669.
11. Suzuki, T., Osamu, Y., Takahashi, Y., and Watanabe, Y., 1985. Fuel Process. Technol. 10:33.
12. Hirschon, A.S. and Wilson, R.B., Jr., 1991. In: Schobert, H.H., Bartle, K.D., and Lynch, L.J. (Eds.), Coal Science II, American Chemical Society, Washington, Chapter 21.
13. Herrick, D.E., Tierney, J.W., Wender, I., Huffman, G.P. and Huggins, F.E., 1990. Energy Fuels, 4:231.
14. Pradhan, V.R., Herrick, D.E., Tierney, J.W. and Wender, I., 1991. Energy Fuels, 5:712.
15. Suzuki, T., Yamada, H., Sears, P.L. and Watanabe, Y., 1989. Energy Fuels, 3:707.
16. Kamiya, Y., Nobusawa, Y. and Futamura, S., 1988. Fuel Process. Technol., 18:1.
17. Yamashita, H., Ohtsuka, Y., Yoshida, S. and Tomita, A., 1989. Energy Fuels 3:686.
18. Watanabe, Y., Yamada, O., Fujita, K., Takegami, Y. and Suzuki, T., 1984. Fuel, 63:752.
19. Suzuki, T., Yamada, O., Fujita, K., Takegumi, Y. and Watanabe, Y., 1984. Fuel, 63:1707.

20. Rahimi, P.M., Fouda, S.A. and Kelly, J.F., 1986. Prepr. Pap. Amer. Chem. Soc. Div. Fuel Chem., 31(4):192.
21. Artok, L., Davis, A., Mitchell, G.D., and Schobert, H.H., 1992. Fuel, (In press).
22. Derbyshire, F.J., Davis, A., Epstein, M. and Stansberry, P.G., 1986. Fuel, 65:1233.
23. Derbyshire, F.J., Davis, A., Lin, R., Stansberry, P.G., and Terrer, M.T., 1986. Fuel Process. Technol., 12:127.
24. Stansberry, P.G. and Derbyshire, F.J., 1988. A Study of the Molybdenum Catalyzed Hydrogenation of Coals in the Absence of Solvent. U.S. Dept. of Energy Report DE-FE22-83PC60811.
25. Murakami, K., Yokono, T. and Sanada, Y., 1986. Fuel, 65:1079.
26. Anderson, R.R. and Bockrath, C., 1984. Fuel, 63:329.
27. Satterfield, C.N. and Gultekin, S., 1981. Ind. Eng. Chem. Process Des. Devel., 20:62.
28. Willson, W.G., Hei, R., Riskedahl, D. and Stenberg, V.I., 1985. Fuel, 64:128.
29. Trewhella, M.J. and Grint, A., 1987. Fuel, 66:1315.
30. Larkins, F.P., Jackson, W.R., Rash, D., Hertan, P.A., Cassidy, P.J., Marshall, M. and Watkins, I.D., 1984. In: Schobert, H.H. (Ed.), The Chemistry of Low-Rank Coals, American Chemical Society, Washington, Chapter 18.
31. Cebolla, V.L., Diack, M., Oberson, M., Bacaud, R., Cagniant, D., and Nickel-Pepin-Donat, B., 1991. Fuel Process. Technol., 28:183.
32. Burgess, C.E., Artok, L. and Schobert, H.H., 1991. Prepr. Pap. Amer. Chem. Soc. Div. Fuel Chem., 36:462.
33. Garcia, A. and Schobert, H.H., 1991. Coal Preparation, 9:185.

END

**DATE
FILMED**

7 / 13 / 92