NMR AND OPTICAL STUDIES OF PIEZOELECTRIC POLYMERS

ANNUAL PERFORMANCE REPORT

Grant No. DE-FG06-87ER45292

For The Period April 1, 1991 - March 31, 1992

by

Co-Principal Investigator Professor V. Hugo Schmidt

and

Co-Principal Investigator George F. Tuthill

Department of Physics
Montana State University
Bozeman, Montana 59717

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

9/1/1992
JMS
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TECHNICAL PROGRESS

for Grant year 1 April 1991 to 31 March 1992

DOE Grant DE-FG06-87ER45292

ELECTROACTIVE POLYMERS AND LIQUID CRYSTALS

Principal Investigator: V. Hugo Schmidt
Principal Investigator: George F. Tuthill

Department of Physics
Montana State University
Bozeman, MT 59717

Submitted Dec. 26, 1991

This report covers the middle year of this three-year grant. Our most notable breakthrough from the financial point of view was the funding by DOE of our equipment proposal, which with the MSU match comes to over \$110,000. With this money we are buying an HP Apollo work station which will speed up the polymer modelling greatly. We also bought and just received a Tecmag Taurus Real-Time NMR Station which will improve our NMR capabilities. We also bought and ordered apparatus which will extend considerably our dielectric apparatus speed of operation and frequency range. For the audio range we bought a Wayne-Kerr 6425 Precision Component Analyzer which we use as a dielectric bridge which covers the 20 Hz to 300 kHz frequency range. At the high-frequency end, we have ordered an HP 4191A which covers the 1 to 1000 MHz range, while at the low frequency end we are getting a frequency synthesizer and electrometer which will bring us into the fractional Hz range.

We were fortunate to have Stuart Hutton visit us and show us how to automate the taking of dielectric data and control of temperature. He got experience at Mainz, Germany in working with the 1 to 1000 MHz HP bridge, and when he returns for two months this winter he will help in setting it up. We also recently set up hysteresis loop measuring system, which will be used to study our piezoelectric (ferroelectric) copolymer samples. All of the above measurements are (or will be) available over the temperature range 4 K to 500 K.

As to scientific progress, the last paper reporting Zhimin Liu's Ph.D thesis work was published, dealing with Brillouin scattering from the 80/20 mol% vinylidene fluoride / trifluoroethylene random copolymer. A graduate student, Greg Pastalan, is interested in continuing this work. One particular problem we wish to investigate is ways of increasing the transition temperature T_c out of the ferroelectric state, thus enhancing the practical range of the copolymer for piezo- and pyroelectric applications. Seymour Preis, a consulting chemist who has been very helpful to us, has a patent for increasing T_c by various heat

treatments, and Brillouin scattering is one way of monitoring T_c . Our goal is to understand the microscopic basis of the improvements he achieved.

Another graduate student, Nick Pinto, has made a preliminary NMR (nuclear magnetic resonance) study of a lithium stearate liquid crystal sample. ^7Li NMR was carried out in the temperature range 21 to 178 $^{\circ}\text{C}$. This liquid crystal has a series of transitions as temperature increases. At 114 $^{\circ}\text{C}$ there is a crystalline-crystalline phase transition. At 140 $^{\circ}\text{C}$ there is a crystalline-smectic phase transition and at 174 $^{\circ}\text{C}$ the sample becomes an isotropic liquid. Lineshape measurements need to be made again because of lack of proper Fourier transform software, which we now have. Spin-lattice relaxation time (T_1) measurements up to 140 $^{\circ}\text{C}$ indicate the presence of more than one relaxation time constant, while above this temperature these time constants merge into one. Clear indication of the various transitions is seen when T_1 is plotted against temperature, where an abrupt drop in T_1 indicates the phase transition. In subsequent reruns of this experiment the ^7Li signal decreased considerably above 114 $^{\circ}\text{C}$, making it hard to perform any set of measurements with accuracy. We will investigate whether this is caused by sample deterioration or by equipment problems. With the new computer controlled NMR apparatus we plan on studying lineshapes on the above samples. It will also be possible to measure $T_{1\rho}$. This will enable us to study slow motions in the liquid crystal.

Graduate student Tim Tu learned the NMR technique and made T_1 measurements of the E7 liquid crystal. He found evidence for the phase transition at the clearing point at 61 $^{\circ}\text{C}$. He also made some calculations for the Freedericksz transition (see Fig. 1 below) which are helpful in analyzing our results discussed below.

A graduate student new to our group, Greg Pastalan, has built up an apparatus for measuring thermal conductivity and specific heat by an ac temperature wave technique. The device is now based on two Melcor thermoelectric devices, one acting as the wave generator and the other as the temperature sensor. This will be useful for measuring thermal properties of polymers and liquid crystals.

Another graduate student, Phil Himmer, is measuring the Freedericksz transition in E7 liquid crystal, using a laser and our 15" Varian electromagnet which is no longer needed for NMR since we got our superconducting magnet. The liquid crystal director is originally perpendicular to the field. As the magnetic field increases past a critical value, the director suddenly starts turning to align with the field, changing the optical properties. The critical value depends on the magnetic susceptibility anisotropy, the volume elastic constant, and for thin samples the surface anchoring strength. Our goal is to determine the surface anchoring strength, a parameter which is necessary in determining elastic constants in PDLC (polymer-dispersed liquid crystal) experiments as discussed below.

We submitted a proposal to NSF for a joint US/France project on neutron scattering and NMR of piezoelectric polymers. Unfortunately, the Grenoble (ILL) reactor where we planned to do the neutron work under the direction of Jeff Legrand is out of commission for three years because of cracks in both the main and the backup cooling systems. We tried to modify the proposal after this happened, but the referees and the NSF personnel said the scope of the work was too greatly changed, so we have to resubmit May 1, 1992.

Jeff Legrand was here this spring for a few days, and we made quite a bit of progress with the polymer model. Also, we submitted an abstract for the March 1992 APS Meeting.

Profs. Arnold Craig and Bradford Mundy of our Chemistry Department are preparing a new material, based on dye molecules with which Prof. Craig had experience at Kodak, which we hope will have liquid crystalline properties. If it does, the next step will be to polymerize it onto a silicon backbone to obtain a liquid crystalline polymer.

Hugo Schmidt is working on a paper to explain the results of measurements on PDLIC materials, in which the various bulk and surface elastic constants are important. He is also investigating the role of the k_{11} elastic constant. A graduate student, Hua Zhao, is beginning work with George Tuthill on the theory for these interactions.

George Tuthill and his collaborator and students have continued statistical mechanical studies of models of linear polymers using both analytical and numerical (simulation) techniques:

(1). We have further pursued studies of the statistical mechanics of the $n=0$ vector model for polymers. In work published in June 1991 we have shown, based on Monte Carlo simulation results, that contrary to recent speculation this model fails to undergo a percolation-like transition in the dense phase limit. The context of this study is as follows: The n -vector model of magnetism, where n is the number of components of the local magnetic moments has long provided physics with a framework for discussing a wide variety of phase transitions. The $n=0$ limit of this model was shown by de Gennes, and des Cloizeaux, to yield information about the behavior of a system of (idealized) polymer chains. In the $n=0$ model, which in our work is realized on a lattice, the length and number distribution of chains are controlled by fugacities for polymer links and polymer end-points. On the basis of scaling arguments the $n=0$ vector model for a many-polymer system has been predicted to undergo a percolation-like transition to a phase in which a single chain occupies the lion's share of the system (an "infinite chain", in the thermodynamic limit). During the past year we completed a Monte Carlo examination of this suggestion on lattices in both two and three dimensions. Extrapolation was used to infer infinite-system behavior from our studies of a sequence of

finite-sized samples. Our work indicates that a percolation-type transition can occur only in the limit of vanishing statistical weight for chain end-points. We also show that the correct scaling arguments are consistent with the results of our simulations. The implication for real polymers is that free energy for flexible chains should be "smooth" in the melt, apart from any transition due to crystallization.

(2) We have solved exactly a model for the biased and interacting self-avoiding walk (SAW), on a lattice which is a deterministic fractal, the 4-simplex lattice. SAWs on lattices serve as simple models for linear polymers in dilute solution, particularly when one is interested in such properties as the scaling of the radius of gyration or end-to-end distance with chain length. A lattice SAW is a coarse-grained model of a real polymer, but it can incorporate not only the excluded-volume constraint (through self-avoidance) but other intra- and inter molecular effects as well. For example, it can include chain bias (resistance to bending) and monomer-solvent interaction (solvent quality). The first of these effects can arise from an energy difference between trans and gauche bonds in a polyethylene-type chain, while the second -- which can be modeled by an attractive interaction between adjacent, non-consecutive monomers -- can lead to a collapse transition, where the chain adopts a tightly coiled configuration.

Despite extensive study, there are few cases in which the properties of SAWs on regular lattices have been calculated exactly. Recently, however, there has arisen interest in finitely ramified fractal lattices. For such cases SAW statistics can be analyzed exactly on a sequence of successively larger lattices. Such lattices are not uniform, since there is a great variety in the structure neighborhoods of different lattice sites. They therefore serve as crude models for real amorphous materials where local environments are non-uniform and fluctuate randomly. We have concentrated our efforts on the 4-simplex lattice (with Hausdorff dimension $d = 2$), since SAWs on it can represent polyethylene-like polymer chains on a fractal subset of the diamond lattice. The bends of a SAW on the 4-simplex correspond to gauche bonds of the polymer into which the walk is mapped. Thus the current model pertains in a rudimentary way to an ensemble of polymers.

Together with W.A. Schwalm (University of North Dakota) we have completed and submitted for publication the first study for SAWs on the 4-simplex lattice in which both chain stiffness and monomer-monomer interactions are accounted for exactly. This represents a significant extension of work begun last year in which only stiffness was included. We are able to describe the conditions under which collapse can take place, and show that chain antistiffness (bias favoring chain bends) is insufficient to cause collapse. The full phase diagram has been mapped in the space of three fugacities -- for SAW steps, bends, and nearest-neighbor monomer-monomer interactions. We have found critical amplitudes (as well as critical exponents) in semianalytic fashion. We have also treated fully the scaling properties of very stiff SAWs which are rod-like at short lengths but flexible on long length scales.

(3) We have developed, and are now analyzing results from, Monte Carlo simulations of chains of electrically active PVF2 and PVF2/TrFE copolymers. In this work our object is to model the conformational order/disorder transition within the chain that underlies the ferroelectric/paraelectric phase transition. In particular we are assessing the role of inter- and intrachain dipole-dipole forces in this process. So that we may use relatively rapid Monte Carlo methods in this study, we confine the monomers to the sites of a diamond lattice. In this scheme an all-trans chain lies along the lattice 110 direction, and the important kink-3-bond defect can be naturally accommodated. Our initial results suggest that in fact electrical forces do play a dominant role determining chain conformations, as compared to torsional (trans/gauche) energies at temperatures near the transition. We will report on this work at the March APS meeting in Indianapolis.

(4) In a second phase of these PVF2/TrFE simulations we are developing a molecular dynamics simulation of linear chains in the crystalline phase. This is a multi-chain model in free space (rather than on a lattice) for which the equations of motion of the monomers are numerically integrated. Dynamic properties such as relaxation and time-dependent response, as well as time-averaged behavior can thereby be studied. This work is being carried out with Maureen Grigereit, a graduate student; portions of the code are presently being tested and we expect preliminary results during the coming semester.

Fig.1 The Freederikse's transition for a nematic slab under a magnetic field $\vec{H}$

$$\left(\frac{d}{2} - z\right) = \int \left[F(\phi/\theta_M) - F(\phi_0/\theta_M) \right]$$

where $F(\phi/\theta_M) = \int_0^\phi \frac{d\phi'}{\sqrt{1 - \sin^2 \phi' \sin^2 \theta_M}}$

$$F(\phi_0/\theta_M) = \int_0^{\phi_0} \frac{d\phi'}{\sqrt{1 - \sin^2 \phi' \sin^2 \theta_M}}$$

$$\theta_0 = \theta(z = d/2)$$

$$\sin \phi = \frac{\sin \theta}{\sin \theta_M}$$

$$\sin \phi_0 = \frac{\sin \theta_0}{\sin \theta_M}$$

$$H_c = \text{critical field} = \frac{\pi}{2} \sqrt{\frac{K}{\epsilon}}$$

Publications and Abstracts Appearing or Submitted in 1991

1. "Deuteron NMR Study of Ferroelectric Transition in VF_2/TrFE Copolymer", V.H. Schmidt, C. Perry, E.A. Dratz, and Y. Ke, invited talk at US-USSR Seminar on Ferroelectrics, Boulder, July 1989 Ferroelectrics 117, 149 (1991).
2. "Search for a Percolation Transition in a Lattice Polymer Model", G.F. Tuthill and D.G. Glover, Bull. Am. Phys. Soc. 36, 793 (1991).
3. "Biased Self-Avoiding Walks on the 4-Simplex Lattice", W.A. Schwalm and G.F. Tuthill, Bull Am. Phys. Soc. 36, 693 (1991).
4. "Search for a Percolation Transition in a Lattice Polymer Model", G.F. Tuthill and D.J. Glover, J. Chem. Phys. 94, 8408 (1991).
5. "Studies of 80/20 Mol% Vinylidene Fluoride-Trifluoroethylene Copolymer by Brillouin Scattering", Z. Liu and V.H. Schmidt, Ferroelectrics 119, 9 (1991).
6. "Ferroelectric Soft Mode in $\text{P}(\text{VDF-TrFE})$ Copolymers as Revealed by a Neutron Spin Echo Study," J. F. Legrand, E. M. Amalric, and V. H. Schmidt, Bull. Am. Phys. Soc. 37 (to appear March, 1992).
7. "Interacting, Biased SAWs on the 4-Simplex Lattice," G. F. Tuthill and W. A. Schwalm, Bull. Am. Phys. Soc. 37 (to appear March, 1992).
8. "Monte Carlo Simulation of PVF_2/TrFE Chains on a Lattice," D. J. Glover and G. F. Tuthill, Bull. Am. Phys. Soc. 37 (to appear March, 1992).
9. "Biased Interacting Self-Avoiding Walks on the 4-Simplex Lattice," G. F. Tuthill and W. A. Schwalm (submitted to Phys. Rev. B).
10. "Normal Distortion Mode Description of Periodic Distortions in Nematic Liquid Crystals and Proposed Method to Measure Saddle Elastic Constant k_{44} ", V.H. Schmidt (to be resubmitted to Molec. Cryst. - Liq. Cryst.).

END

**DATE
FILMED**

7 / 8 / 92