**Final Report on UHM/HNEI EV Test and Evaluation Program
USDOE Contract No. DE-FC08-79NV10031**

**By the Hawaii Natural Energy Institute
University of Hawaii at Manoa**

1. Program Objectives

The electric vehicle (EV) program of the University of Hawaii's Hawaii Natural Energy Institute (HNEI) focuses primarily on the field testing of promising EV/traction batteries. HNEI is located on the island of Oahu in the state of Hawaii. The island setting provides a unique opportunity for testing batteries and EVs in an environment of limited range requirements and moderate climate. The intent of this program is to utilize typical driving cycles to develop information that verifies or refutes what is obtained in the laboratory.

Three different types of battery were assigned by the U.S. Department of Energy (DOE) for testing in this program:

- ◇ Sonnenschein Dryfit 6V-160
- ◇ Exide GC-5
- ◇ Trojan T-145

For comparison we added the following battery to the test program:

- ◇ ALCO 2200

2. Vehicle Survey and Application

No new vehicles were purchased in this program. Instead, HNEI's existing EVs were utilized as test beds. After careful inspection, the following EVs were chosen from the many EVs in our program and were used as follows:

- ◇ Converted Ford Escort station wagon, Vehicle No. 4356; for commuting and other general use (typical daily driving distance, 25-30 miles)
- ◇ Converted Ford Escort two-door sedan, Vehicle No. 4386; for commuting and other general use (typical daily driving distance, 10 miles)
- ◇ Converted Ford Escort two-door sedan, Vehicle No. 4387; for commuting and other general use (typical daily driving distance, 10 miles)
- ◇ Converted Dodge van, Vehicle No. 159; for commuting between campus and transportation in other HNEI projects (typical daily driving distance, 10 miles)

3. Instrument Calibration

3.1. Odometer Calibration

The odometers of the four EVs were calibrated by carefully driving the EVs on the highway and comparing the odometer readings with the mileage markers on the highway. The odometers for all four EVs were accurate to within 1.0 percent (see table below).

EV Number	Marker Readings (miles)	Odometer Readings (miles)	Disparity (%)
4356	20	20.16	+ 0.8
159	20	19.82	-0.9
4386	20	19.94	-0.3
4387	20	20.10	+ 0.5

3.2. Kilowatt-Hour Meter Calibration

To obtain reliable data, the kWh meters for the chargers of the four EVs were compared with an Electro Industries' solid state digital kW/kWh Meter with a resolution of 0.001 kWh and 0.25 percent accuracy. The kWh meters for all four EVs were accurate to within 2.0 percent (see table below).

EV Number	4356	4386	4387	159
KWh Meter Type	General Electric 1-70-S	SANGAMO J4S	Westinghouse D4S	SANGAMO J4S
Disparity	0.12%	0.80%	1.80%	1.14%

4. Battery Installation

Battery installation were as follows:

EV Number	4356	4386	4387	159
EV Type	Station Wagon	2-Door sedan	2-Door Sedan	Van
Battery Type	Sonnenschein Dryfit 6V-160	Trojan T-145	Exide GC-5	ALCO 2200
No. of Modules	18	16	16	20
Installation Date	6/19/89	11/2/89	12/27/90	12/6/89

Immediately following installation of the batteries, the following data for all of the batteries except the Alco 2200 were recorded:

- ◇ Initial module weight
- ◇ Initial module open circuit voltage
- ◇ Module number (the module number consecutively starting from the most positive pack connection)

The initial data for the Trojan T-145, Exide GC-5, and Sonnenschein Dryfit 6V-160 battery packs, are presented in Table 1, Table 2, and Table 3, respectively.

5. Daily Data Record

5.1. Daily Log Sheet

Hard copies of the daily log sheets were sent on a monthly basis to DOE's Idaho EV operational office using the Demonstration Operator's Daily Operation Report form provided by DOE's Electric and Hybrid Vehicle Test and Evaluation Project. Table 4 summarizes the accumulated mileage and accumulated charging kWh for the four test batteries.

5.2. Charging Pattern

The charging patterns for the four test batteries are shown in Figures 1 through 4. The charging pattern of Sonnenschein battery pack (Fig. 1) is typical for Hawaii, with most charge cycles being about 10 kWh per charging. For that particular vehicle/battery combination, 10 kWh corresponds to about 30 miles of driving. The normal driving range needed on Oahu to and from work (round trip) on Oahu is 20-30 miles.

6. Capacity Test

Capacity tests were performed on each battery pack once every quarter. The battery capacity was determined by discharging the battery pack at 75 amps after a prolonged charge. The battery pack was charged and the EV parked at ambient temperature (20-30°C) for at least 8 hours prior to beginning the capacity test. The manufacturer's recommended minimum discharge voltage was used as the cut-off voltage (5.25 V per module) for the test.

The capacity tests were performed with an Abler battery test system which can continuously monitor and record the discharging current, overall battery pack voltage, and individual module voltage in the battery pack. The capacity test results are shown in Figures 5 through 8. Seventy-five ampere discharging curves for the four battery packs are plotted in those figures. Table 5 summarizes the capacity tests.

7. Battery Maintenance

7.1. Battery Equalization Charge

Because of high vibrational operating conditions, unbalanced temperatures between modules, and differences in terminal and interconnect cable resistance, repeated charge/discharge cycling gradually increases the differences in the capacity of the modules. This continually increasing capacity difference among modules is extremely harmful to the life of the battery pack. That is why equalization charge is advisable in the maintenance of battery packs.

Since EV batteries are connected in series, the decline in performance of one battery cell affects the performance of the entire battery pack. To equalize the performance of the battery pack, equalization charges were conducted every 1000 miles or before a capacity test, whichever came first. During the equalization charge, the battery pack was charged with a small current over an extended period. Battery cells that declined in performance were expected to be restored to full capacity without excessive gassing from sound cells because of the low charging current level.

7.2. Additional Charge Method

Although an equalization charge was performed on the battery pack every time before a capacity test, some modules were still found to be weaker than average. Experiments were performed to correct the problem. After capacity tests, weaker battery modules were recharged individually using an off-board charger (hence the designation, "Additional Charge Method"). The entire battery pack was then given an equalization charge with the hope of bringing the capacity of weaker batteries to an acceptable level. The results have been quite promising; based on our experiments, it appears that equalization charges can have a very significant impact on the life of the battery pack.

Fig. 5 shows the effect of applying additional charge to three weak modules, No. 6, 17, and 18, of the Sonnenschein battery pack; Fig. 9, 10, and 11 show discharge curves for the respective modules. After about 1,000 miles of driving, we re-examined those modules and verified that modules No. 17 and 18 had recovered, but module No. 6 seemed to be permanently damaged. Similar experiments were also performed on other battery packs, such as the Trojan batteries. The results have been encouraging. Based on our experiments, we feel that the quality of the equalization charge can have a significant impact on the life of a battery pack. When an equalization charge is unsatisfactory, an additional charge was found to be very beneficial.

7.3. Battery Watering and Cleaning

Sonnenschein Dryfit 6V-160 batteries are maintenance-free. The other three battery packs, Trojan T-145, Exide GC-5, and Alco 2200, are flooded lead/acid type. Battery water levels in these three pack were checked monthly. Water levels also were checked before each capacity test.

When the water level was checked, the battery surfaces and terminal connections were also cleaned.

7.4. Battery Connection Terminal Soldering

Because of acid corrosion and vehicle vibration, the battery terminal connection should be carefully checked after a prescribed interval of use. To investigate the effect of the terminal connection quality on the energy output capability of the battery pack, capacity tests were conducted on the Sonnenschein, Trojan, and Alco battery packs before and after soldering of terminals. At the time of testing, accumulated mileage on the Sonnenschein pack was 8784; Trojan, 2047; and Alco, 728. The test showed a 9% increase in output energy from the Sonnenschein pack after soldering the connections (Fig. 12); however, very limited improvements were observed on the Trojan and Alco packs. It seems that the higher accumulated mileage with the Sonnenschein pack resulted in poor terminal connections.

Based on terminal soldering tests, we suggest that the battery terminal connections be readjusted after a prescribed period of operation, e.g., every 2,000–3,000 miles.

8. Regeneration Effect of the EVcort

EV No. 4356 with the Sonnenschein Dryfit 6V-160 battery pack is equipped with a Soleq electronic regeneration brake system. To evaluate the effect of regeneration on charging of the battery pack, the energy generated by the regeneration system was measured and compared with the total energy consumed in driving. The results are summarized in Fig. 13. Driving in this test was performed on city roads in Honolulu. During the test, the regenerated energy was about 6 percent of the total energy consumed.

9. Battery Remaining Energy Monitor

A digital voltmeter that locks battery voltage reading when the traction current increases to 100 A was designed and fabricated. It was installed on the EVcort which has the Sonnenschein battery. Although several improvements could be made, it worked quite well. We believe it is a step in the right direction in developing an effective "fuel gauge."

10. Summary

Based on our operation experiences, we conclude:

1. Capacity testing is a very effective way of monitoring the status of battery modules. Based on capacity tests, corrective action such as battery replacement, additional charging, adjusting terminal connections, etc., may be taken to maintain good performance.
2. About 15500 miles and 600 cycles have been accumulated on the Sonnenschein Dryfit 6V-160 battery pack. Five of its 18 modules have been changed. Based on DOE's standard, the battery has reached the end of its useful life. Nevertheless, the battery pack is still operational and its operating range is still greater than 40 miles per charge.

3. It is too early to evaluate the life expectancy of the other three batteries, the Trojan T-145, Exide GC-5, and Alco 2200. No module has been replaced in these three packs. The Trojan T-145 battery is a very promising EV traction battery in terms of quality and reliability versus price. HNEI will keep the Trojan and Exide battery packs in operation. The Alco 2200 batteries will be transferred to another vehicle.
4. The Additional Charging Method, which was introduced by this program, seems to be an effective way of restoring weak modules.
5. The "Smart Voltmeter" developed by HNEI is a promising way of monitoring the remaining range for an EV. HNEI remains interested in pursuing the development of an effective EV "fuel gauge."

Publications

The following publications were prepared in this program.

Neill, D.R., J. Bac, S. Yano, and C. Xue. "Electric Vehicle Program in Hawaii," in Proceedings of the Society of Automotive Engineers International Congress and Exposition; Detroit, Michigan, February 1990.

Neill, D.R., S. Yano, Y. Li, and J. Lu. "Renewable Transportation Alternatives," Solar Today, July/August 1990; and presented at American Solar Energy Society Solar '90 Conference; Austin, Texas, March 1990.

Neill, D.R., C. Yu, and J. Lu. "Report on Hawaii's EV Program," presented at Electric Vehicle Symposium X; Hong Kong, December 1990.

STATISTICS OF KWh PER CHARGING SONNENSCHEN DRYFIT 6V-160 BATTERY PACK

FIG. 1 CHARGING STATISTICS OF SONNENSCHEN DRYFIT 6V-160

STATISTICS OF KWh PER CHARGING ALCO 2200 BATTERY PACK

FIG. 2 CHARGING STATISTICS OF ALCO 2200

STATISTICS OF KWh PER CHARGING TROJAN T-145 BATTERY PACK

FIG. 3 CHARGING STATISTICS OF TROJAN T-145

STATISTICS OF KWh PER CHARGING Exide GC-5 BATTERY PACK

FIG. 4 CHARGING STATISTICS OF EXIDE GC-5

SONNENSCHNEIN 6V-160 CAPACITY TESTS **18 MODULES, 75 Amp, CUTOFF 5.25V/MODULE**

----- 6/1/1990 9/28/1990 ——— 12/10/1990
 7311 miles 10442 miles 11731 miles

FIG. 5 SUMMARY OF SONNENSCHNEIN DRYFIT 6V-160 CAPACITY TESTS

TROJAN T-145 CAPACITY TESTS 16 MODULES, 75 A, CUTOFF 5.25 V/MODULE

3/19/9 791 m 6/22/9 1538 10/2/9 2341 1/10/1 3078 3/28/1 3422

FIG. 6 SUMMARY OF TROJAN T-145 CAPACITY TESTS

EXIDE GC-5 CAPACITY TEST
CUTOFF 5.25 V/CELL, 75 Amp, 16 MODULES

— 12/26/1990
Miles: 0

FIG. 7 SUMMARY OF EXIDE GC-5 CAPACITY TESTS

ALCO 2200 CAPACITY TESTS
20 MODULES, 75 Amp, CUTOFF 5.25V/MODULE

FIG. 8 SUMMARY OF ALCO 2200 CAPACITY TESTS

EFFECT OF ADDITIONAL CHARGING SONNENSCHIEEN DRYFIT PACK, MODULE #6

FIG. 9 ADDITIONAL CHARGING ON MODULE #6 OF SONNENSCHIEEN PACK

**EFFECT OF ADDITIONAL CHARGING
SONNENSCHINE DRYFIT 6V-160, MODULE #17**

FIG. 10 ADDITIONAL CHARGING ON MODULE #17 OF SONNENSCHNEIN PACK

EFFECT OF ADDITIONAL CHARGING **SONNENSCHINE DRYFIT 6-160, MODULE #18**

— 9/28/1990 10422 - - - - 12/10/1990 11731

FIG. 11 ADDITIONAL CHARGING ON MODULE #18 OF SONNENSCHNEIN PACK

SOLDERING EFFECT ON SONNENSCHN EIN PACK **18 MODULES, 75 Amp, CUTOFF 5.25V/MODULE**

FIG. 12 SOLDERING EFFECT ON SONNENSCHN EIN PACK

FIG. 13 RE-GENERATION EFFECT OF EVcort, EV #4356

Table 1 Trojan T-145 Pack/EV #4387 Initial installation Data

Installation Date: 11/02/8

Battery NO.	Weight (Lb)	Open Circuit Voltage (Volt)
1	71.0	6.32
2	70.0	6.32
3	70.0	6.30
4	70.0	6.30
5	70.0	6.31
6	70.0	6.31
7	70.0	6.30
8	70.0	6.31
9	70.0	6.29
10	72.0	6.32
11	70.0	6.31
12	70.0	6.30
13	70.0	6.30
14	70.0	6.29
15	70.0	6.29
16	70.0	6.30

Table 2 Exide GC-5 Pack/EV #4387 Initial installation Data

Installation Date: 12/27/1990

Battery NO.	Weight (Lb)	Open Circuit Voltage (Volt)
1	70.0	6.30
2	67.8	6.31
3	65.0	6.30
4	65.0	6.29
5	65.0	6.29
6	65.0	6.31
7	67.0	6.30
8	65.0	6.28
9	68.2	6.29
10	66.5	6.29
11	66.0	6.30
12	65.3	6.29
13	64.5	6.29
14	64.2	6.29
15	67.0	6.30
16	67.5	6.30

Table 3 Sonnenschein Pack/EV #4356 Initial installation Data

Installation Date: 6/19/89

Battery NO.	Weight (Lb)	Open Circuit Voltage (Volt)
1	72.0	6.32
2	72.0	6.30
3	72.0	6.31
4	72.0	6.21
5	72.0	6.31
6	72.0	6.30
7	72.0	6.23
8	72.0	6.29
9	72.0	6.31
10	72.0	6.32
11	72.0	6.32
12	72.0	6.30
13	72.0	6.32
14	72.0	6.31
15	72.0	6.31
16	72.0	6.29
17	72.0	6.25
18	72.0	6.30

Table 4 Summary of Accumulated Mileage and Charging kWh
(As end of July of 1991)

Battery Pack	Vehicle NO.	Accumulated Mileage	Accumulated kWh *
Sonnenschein Dryfit 6V160	4356	15420	5779
Trojan T-145	4386	4243	2499
Exide GC-5	4387	1093	550
Alco 2200	159	1982	1820

* The accumulated kWh includes the charging kWh for capacity tests.

TABLE 5. SUMMARY OF CAPACITY TESTS

BATTERY TYPE	TROJAN T-145					SONNENSCHEN DRIFT 5V 160					EXIDE CC-5					ALCO 2200				
RATED CAPACITY	145 minutes at 75 Amperes					160 AH @ 5 hour rate					105 minutes at 75A rate					105-106 minutes at 75 A 80F				
MODULE NUMBER	16					15					16					20				
SEQUENCE OF CAPACITY TESTS	First	Second	Third	Fourth	Fifth	First	Second	Third	Fourth	Fifth	First	Second	Third	Fourth	Fifth	First	Second	Third	Fourth	Fifth
TEST DATE	3/19/90	5/22/90	10/2/90	1/10/91	3/28/91	3/5/90	6/1/90	9/28/90	12/18/90	4/08/91	12/26/90	4/11/91	9/27/90	12/28/90	4/2/91	4/3/90	6/28/90	9/27/90	12/28/90	4/2/91
TOTAL WRELDGE OF THE BATTERY	791	1583	2577	3078	3422	5591	7311	10422	11731		0	684	259	612	1956	259	612	1011	1490	1956
TOTAL CHARGING kWh	465	908	1517	1738	1964	2079	2844	3951	4452		0	358	247	605	1677	247	605	961	1313	1677
Dis. capa test																				
TOTAL NUMBER OF REPLACED MODULE	0	0	0	0	0	4	4	5	5	6	0	0	0	0	0	0	0	0	0	0
DISCHARGING CURRENT (A)	75	75	75	75	75	75	75	75	75	75	75	75	75	75	75	75	75	75	75	75
TOTAL DISCHARGE TIME (minutes)	118	118	104	100	124	82.6	96	84	88	60 [1]	106	50 [2]	97	102	100	97	102	108	108	100
Amper-Hour CAPACITY	147	147	130	125	155	103.5	122.5	105	110		132.5		119.8	127.5	125	119.8	127.5	135	135	125
kWh CAPACITY	13.34	13.50	11.60	11.40	14.20	10.7	12.97 *	11.21	11.53		12.13		13.65	14.57	14.36	13.65	14.57	15.53	15.53	14.36
PANEL TEMPERATURE (F)	79	79	81	81	85	78.5	80	82	75		77		80	76	86	80	76	85	76	86
* kWh CAPACITY DECREASE		-1.19%	12.58%	3.4%	-24.56%		-17.50%	13.57%	-3.75%					-6.74%	7.4%		-6.74%	-5.86%	0.0%	7.4%

* This was measured after the battery connections were soldered.

* Comparing with last time.

[1] When discharging at 75 A to 60 minutes, the weakest module already reversed

[2] When discharging at 75 A to 50 minutes, two modules already got too weak to continue the test.

TABLE 5. SUMMARY OF CAPACITY TESTS

END

**DATE
FILMED**

6 105/92