10/6/16/92 *Jim* ①

ORNL/CON-338

**OAK RIDGE
NATIONAL
LABORATORY**

MARTIN MARIETTA

**Numerical Analysis of Heat
Transfer by Conduction and
Natural Convection in Loose-Fill
Fiberglass Insulation—Effects
of Convection on
Thermal Performance**

Agnès A. Delmas
Kenneth E. Wilkes

MANAGED BY
MARTIN MARIETTA ENERGY SYSTEMS, INC.
FOR THE UNITED STATES
DEPARTMENT OF ENERGY

ALL INFORMATION CONTAINED HEREIN IS UNCLASSIFIED

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ORNL/CON--338

DE92 014938

Energy Division

**NUMERICAL ANALYSIS OF HEAT TRANSFER BY CONDUCTION
AND NATURAL CONVECTION IN LOOSE-FILL FIBERGLASS INSULATION—
EFFECTS OF CONVECTION ON THERMAL PERFORMANCE**

Agnès A. Delmas
Kenneth E. Wilkes
Oak Ridge National Laboratory

Manuscript completed
December 1991

Published
April 1992

Prepared by
OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6285
managed by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
U.S. DEPARTMENT OF ENERGY
under Contract No. DE-AC05-84OR21400

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EB

CONTENTS

	Page
LIST OF FIGURES	v
LIST OF TABLES	vii
ABSTRACT	ix
EXECUTIVE SUMMARY	xi
NOMENCLATURE	xiii
1. INTRODUCTION	1
2. A PRELIMINARY APPROACH TO THE PROBLEM	4
2.1 OBJECTIVES	4
2.2 A SIMPLE DESCRIPTION OF THE REAL SYSTEM	5
2.2.1 The Facilities: ATM and LSCS	5
2.2.2 The Physical Attic Insulation Problem	5
2.3 THEORETICAL APPROACH AND SCHEMATIZATION	11
2.3.1 Theoretical Approach	11
2.3.2 The Horizontal Porous Layer	11
2.3.3 The Wood Joists	13
3. NATURAL CONVECTION IN POROUS MEDIA	14
3.1 THE TYPICAL EQUATIONS FOR HEAT TRANSFER IN POROUS MEDIA	14
3.1.1 Mass Conservation	15
3.1.2 Heat Transfer Description - The Different Models	15
3.1.3 The General Darcy's Law	16
3.2 THE COMPLETE SET OF EQUATIONS FOR THE PRESENT PROBLEM	17
3.2.1 Nondimensional Equations and Parameters	17
3.2.2 The Boundary Conditions	19
4. NUMERICAL ANALYSIS	21
4.1 THE CONVECTIVE CODE DARCY	21
4.1.1 Code DARCY Features	21
4.1.2 Onset of Convection Within a Porous Medium	23
4.2 FIVE TYPICAL CONFIGURATIONS	26
4.2.1 Closed Configuration: The Small-Scale Test	26
4.2.2 Open Configuration - Various Thermal Boundary Conditions	26
4.3 THERMAL AND DYNAMIC PROPERTIES OF FIBERGLASS INSULATION	27
4.3.1 Thermal Conductivity, k^*	28
4.3.2 Thermal Resistance, R	29
4.3.3 Air Permeability, K	30

CONTENTS (continued)

	Page
5. RESULTS AND DISCUSSION	33
5.1 THE FIVE CONFIGURATIONS	33
5.1.1 Criteria for the Onset of Convection	33
5.1.2 The Effects of the Wood Joists	38
5.2 CONSEQUENCES OF VARIABLE PERMEABILITY AND THICKNESS	45
5.2.1 Variable Permeability for a Fixed Thickness	47
5.2.2 Performance of a Double Layer	49
5.2.3 Gradient of Permeability Within the Insulation	51
5.3 THE ATTIC CONFIGURATION	58
6. GENERAL CONCLUSIONS AND PERSPECTIVES	62
6.1 CONCLUSIONS	62
6.2 PERSPECTIVES	64
REFERENCES	66
APPENDIX A. VELOCITIES AND ISOTHERMS IN THE FIVE CONFIGURATIONS	69
APPENDIX B. CONVECTIVE MOTIONS IN AN INCLINED POROUS LAYER	81

LIST OF FIGURES

	Page
2.1 Attic test module	6
2.2 Large scale climate simulator	7
2.3 The physical attic insulation problem: schematization	8
2.4 The horizontal porous layer with and without joists	12
4.1 Convection in porous media and air spaces - code PENALTY	22
4.2 Nusselt number vs Rayleigh number in closed and open configurations with and without joists	25
4.3 Thermal resistance vs temperature difference in closed and open configurations with and without joists	31
5.1 Thermal resistance vs temperature difference without joists: the five configurations	37
5.2 Closed configuration: velocities, isotherms, stream functions, and isobars	39
5.3 Thermal resistance vs temperature with joists: the five configurations	43
5.4 Permeability vs density for one type of loose-fill fiberglass insulation	44
5.5 Geometrical characteristics	46
5.6 Thermal resistance vs temperature difference for one thickness [$E = 31.75$ cm (12.5 in.)] and four densities [6.4, 8, 9.6, or 11.2 kg/m^3 (0.4, 0.5, 0.6, or 0.7 lb/ft^3)] : the effect of various permeabilities	48
5.7 Thermal resistance vs temperature difference for three thicknesses [$E = 20.95$, 31.75, or 39.40 cm (8.25, 12.5, or 15.5 in.)] and one density [8 kg/m^3 (0.5 lb/ft^3)] : the effect of joists at various insulation thicknesses	50
5.8 Thermal resistance vs temperature difference for three thicknesses [$E = 20.95$, 31.75, or 39.40 cm (8.25, 12.5, or 15.5 in.)] and their respective densities [7.7 , 8, or 8.2 kg/m^3 (0.48 , 0.5, or 0.515 lb/ft^3)] : the effect of joists at various insulation thicknesses	52
5.9 Nusselt number vs Rayleigh number: comparison of Nu^* for $E = 40.64$ cm (16 in.) with constant permeability and with a gradient of permeability within the insulation	56
5.10 Thermal resistance vs temperature difference: comparison of R-value for $E = 40.64$ cm (16 in.) with constant permeability and with a gradient of permeability within the insulation	57
5.11 Thermal resistance vs temperature difference: model predictions and data from the attic test module used in the large-scale climate simulator	59
A.1 Air velocities within the insulation: the closed configuration for $Ra^* = 40$ and 48—comparison of velocities with and without joists	71
A.2 Isotherms within the insulation: the closed configuration for $Ra^* = 40$ and 48—comparison of isotherms with and without joists	72
A.3 The open configuration: velocities and isotherms in the whole medium without joists for $Ra^* = 27$ —isothermal boundaries	73
A.4 The open configuration: velocities and isotherms in the whole medium without joists for $Ra^* = 48$ —isothermal boundaries	74
A.5 Air velocities within the insulation: the open configuration for $Ra^* = 27$ and 48— isothermal boundaries; comparison of velocities with and without joists ...	75
A.6 Isotherms within the insulation: the open configuration for $Ra^* = 27$ and 48— isothermal boundaries; comparison of isotherms with and without joists ...	76

LIST OF FIGURES (continued)

		Page
A.7	Air velocities within the insulation: the open configuration for $Ra^* = 27$ and 48—isothermal bottom boundary, nonuniform temperature on top; comparison of velocities with and without joists	77
A.8	Isotherms within the insulation: the open configuration for $Ra^* = 27$ and 48—isothermal bottom boundary, nonuniform temperature on top; comparison of isotherms with and without joists	78
A.9	Isotherms within the insulation: the open configuration for $Ra^* = 8, 27$, and 48—imposed uniform heat flux on bottom and isothermal top	79
A.10	Isotherms within the insulation: the open configuration for $Ra^* = 8, 27$, and 48—imposed uniform heat flux on bottom and nonuniform temperature on top	80
B.1	Diagram of the principal convective motions observed by S. Bories and M. Combarnous in an inclined porous layer with large aspect ratio ($A = 13$; $B = 9$)	83

LIST OF TABLES

	Page
5.1 The five configurations without joists: Ra^* , Nu^* , and the corresponding values of the temperature difference and thermal resistance of the insulation	34
5.2 The five configurations with joists: Ra^* , Nu^* , and the corresponding values of the temperature difference and thermal resistance of the insulation	35
5.3 Open configuration for one density and three thicknesses: Ra^* , Nu^* , and ΔT , and R-values of R-19, R-30, and R-38	41
5.4 Open configuration for three thicknesses and a small density variation: Ra^* , Nu^* , and ΔT , and R-values of R-19, R-30, and R-38	53
5.5 Comparison of the evolution of thermal resistance over temperature difference for R-19 and R-38 with the same permeability and for R-38 with a gradient of permeability within the insulation	55

**NUMERICAL ANALYSIS OF HEAT TRANSFER BY CONDUCTION
AND NATURAL CONVECTION IN LOOSE-FILL FIBERGLASS INSULATION—
EFFECTS OF CONVECTION ON THERMAL PERFORMANCE**

Agnès A. Delmas
Kenneth E. Wilkes

ABSTRACT

A two-dimensional code for solving equations of convective heat transfer in porous media is used to analyze heat transfer by conduction and convection in the attic insulation configuration. The particular cases treated correspond to loose-fill fiberglass insulation, which is characterized by high porosity and air permeability.

The effects of natural convection on the thermal performance of the insulation are analyzed for various densities, permeabilities, and thicknesses of insulation. With convection increasing the total heat transfer through the insulation, the thermal resistance was found to decrease as the temperature difference across the insulating material increases. The predicted results for the thermal resistance are compared with data obtained in the large-scale climate simulator at the Roof Research Center using the attic test module, where the same phenomenon has already been observed. The way the wood joists within the insulation influence the start of convection is studied for differing thermophysical and dynamic properties of the insulating material. The presence of wood joists induces convection at a lower temperature difference.

EXECUTIVE SUMMARY

BACKGROUND

Heat transfer by natural convection in fiberglass insulation has in many cases been considered negligible compared with the heat transfer by conduction and radiation. This is true for most of the high density fiberglass insulations; however, some previous experimental studies have shown that convection can be a significant transfer mechanism in low-density material having a high air permeability, such as some loose-fill insulations.

In 1990, a series of tests were performed in an Attic Test Module with several types of insulation to measure the thermal resistance of the insulation in an attic configuration. This module was used in the Large Scale Climate Simulator at the ORNL Roof Research Center. Testing with a loose-fill fiberglass insulation clearly showed that, under realistic cold winter conditions, thermal performance of the insulation was reduced considerably because of convective motion developing within the insulation.

OBJECTIVE

To verify by a numerical approach, the criteria for the onset of natural convection in a porous medium under specific conditions; to study how convection effects change with the thickness of insulation and with the density, thermal conductivity, air permeability of the type of insulation; to look at how wood joists within the insulation affect the criteria for the onset of convection for various types of insulation; and to compare the thermal resistance obtained using the model for a configuration similar to the existing small-scale apparatus with that obtained using configurations closer to real problem of attic insulation.

APPROACH

A two-dimensional code solving equations of convective heat transfer in porous media is used to analyze heat transfer by convection in the attic insulation configuration. The particular cases treated correspond to loose-fill fiberglass insulation, which is characterized by high porosity and air permeability. The effects of natural convection on the thermal performance

of the insulation are analyzed for various densities, air permeabilities, and thickness of insulation. The predicted results in terms of thermal resistance are compared with data obtained in the Attic Test Module. The influence of wood joists within the insulation on the start of convection is studied for differing thermophysical and dynamic properties of the insulating material.

RESULTS

Global heat transfer through a horizontal porous layer heated from below has been predicted under different thermal boundary conditions with a two-dimensional convective code. Using the thermal conductivity and air permeability of one type of loose-fill fiberglass insulation, thermal resistance has been deduced from these calculations. In the closed configuration which model the small-scale apparatus used to test the performance of the insulation, calculations showed no evidence of convection. The configurations with an open top appear to be a good approximation to the real system; numerical analysis confirmed the phenomena already observed in experiments, such as a decrease in the performance of loose-fill fiberglass insulation when natural convection is occurring inside the insulation under conditions and for permeabilities typical of some existing insulation. Calculations performed with wood joists within the insulation showed a decrease in the critical temperature difference for the start of convection.

CONCLUSIONS

The numerical analysis confirms that the small-scale apparatus is not a good indicator of the in-service thermal resistance of all types of insulation within which natural convection may occur and be a significant mode of heat transfer. For given air permeability and thermal conductivity, the predicted thermal resistance as a function of the temperature difference across the insulation, agrees with measured values in the Attic Test Module. However, a major uncertainty remains in the determination of air permeability. Numerical analyses shows that, to correctly predict convection effects, the in-service value of this parameter must be determined. A definite need exists to develop a tester that would provide reliable and repetitive values for this key parameter.

NOMENCLATURE

Latin

a^*	thermal diffusivity
A	aspect ratio
C	specific heat
e	thickness of wood joists
E	thickness of porous layer
E_i	emittance of surface
F	coefficient, function of density, extinction coefficient, and thickness
g	gravitational constant
h	height of wood joists heat transfer coefficient of surface
k	thermal conductivity
K	air permeability
L	length of the medium
p'	pressure
Q	heat flux
R	thermal resistance
S	surface area
T	temperature
T_0	indoor temperature
T'_0	ceiling temperature
T_m	mean temperature (absolute)
U'	horizontal component of velocity
V'	vertical component of velocity
$\underline{V'}$	vector velocity

Greek

α	amplitude of perturbation for highest temperature
β	thermal expansion coefficient (K^{-1})
ϵ	porosity
ν	kinematic viscosity
μ	dynamic viscosity
ρ	density
σ	Stefan-Boltzmann constant ($5.67 \times 10^{-8} \cdot w \cdot m^{-2} \cdot K^{-4}$)

Subscript

cd	conductive quantities
cr	critical values
cv	convective quantities
eff	effective
f	relative to the fluid
m	averaged values

NOMENCLATURE (continued)

r	radiative quantities
s	relative to the solid

Superscript

* quantities relative to the porous medium
, nondimensional

Nondimensional parameters

$$\text{Bi} = \frac{h L}{k^*} \quad \text{Biot number}$$

$$\text{Da} = \frac{K}{L^2} \quad \text{Darcy number}$$

$$\text{Nu}^* = \frac{(Q_{cd} + Q_{cv})}{Q_{cd}} \quad \text{Nusselt number}$$

$$\text{Pr} = \frac{v(\rho C)_f}{k^*} \quad \text{Prandtl number}$$

$$Ra^* = \frac{g \beta (\rho C)_f \Delta T K E}{\nu k^*} \quad \text{Rayleigh number}$$

1. INTRODUCTION

Heat transfer by natural convection within fiberglass insulation has in many cases been considered negligible compared with the heat transfer by radiation and conduction. However, some previous experimental studies have shown that, in the presence of a low-density material having a high air permeability, convection can be a significant transfer mechanism under certain conditions [1-5].

Free convection in porous media is caused by buoyant forces created by density gradients. The presence of a temperature gradient perpendicular to the gravity vector always induces fluid motion. The only case where a temperature gradient does not induce a natural convection flow is for a horizontal porous layer subjected to a temperature gradient parallel to the gravity vector. Under this condition, however, the system may be unstable. The configuration is stable when the top side is hot and the bottom is cold (low-density fluid on the top and heavy fluid at the bottom); the configuration is unstable when the temperature gradient is in the opposite direction, with the high-density fluid on the top. For this last case, fluid motion exists when the temperature difference exceeds a critical value. The warm fluid then tends to move from the bottom to the top. This minimum temperature difference required to create the fluid motion is a function of different parameters; among them are the thermophysical characteristics of the saturating fluid (viscosity and thermal conductivity) and the characteristics of the porous medium (thickness and fluid flow permeability).

Natural convection in porous media represents a very important phenomenon which can occur in many applications. In building insulation, the principal objective is to reduce heat flow by using insulating materials like fiberglass, rock wool, or other aggregates that have open pores. The problem, then, is to strike a balance between the cost of the insulation and its performance.

In 1990, a series of tests were performed in an attic test module with several types of insulation. One of the objectives was to measure the thermal resistance of the insulation in an attic configuration. This module was used in the large-scale climate simulator at the ORNL Roof Research Center [6].

Testing with a loose-fill fiberglass insulation clearly showed that, under realistic cold winter conditions, thermal performance of the insulation was reduced considerably.

Thermal resistance decreased as the temperature difference across the tested material increased. The change in R-value was attributed to convective motion within the insulation [7].

Many experimental and theoretical studies have been performed on the subject of natural convection in porous media [7–12], leading to predictions of the conditions under which convection occurs within a porous medium. The criteria for the onset of convection, however, correspond to particular geometric, thermal, and dynamic conditions. Some previous studies have shown that the real problem of thermal insulation in buildings is more complex and cannot always be studied under these simplifying assumptions [13].

In particular, tests of fiberglass insulation with a small-scale heat flowmeter apparatus have never shown any evidence of convective motion. This small-scale apparatus is currently used as a standard method to test insulation, but it appears not to be sensitive to natural convection. The objective, then, is to determine the conditions under which this existing test method might become a good indicator of in-service performance.

The research reported here is a numerical approach for calculating heat transfer by conduction and convection in a horizontal layer of porous insulation. Because the real configuration of a residential attic with a wide air space above the insulation cannot be treated numerically, a series of typical configurations is studied to characterize the coupling mechanisms between heat transfer inside the insulation and that in the surrounding air. The equations of convection (motion and energy) are solved in a horizontal porous layer heated from below under several dynamic and thermal conditions.

Numerical tests are performed for five different types of boundary conditions. For each type, the criterion for the onset of convection is determined in terms of a critical Rayleigh number (Ra_c), and compared with data in the bibliography [8]. The thermal resistance of the insulation is calculated under these particular boundary conditions over a range of temperature gradient less than the critical temperature gradient (conductive mode) and greater than the critical value (convective and conductive mode). The effects of convection on the performance of horizontal insulation are compared with actual thermal resistances obtained from the LSCS.

The ATM is made with nominal 2 × 4 in. wood rafters and joists. A 1.3-cm (0.5-in.)-thick gypsum board is attached to the bottom of the joists. The thermal

conductivity of the wood is higher than the thermal conductivity of the insulation at a normal temperature of 21°C (70°F). The conductive transport through the joists is greater than that through the surrounding insulation, so the wood studs will create warmer areas. These perturbations in the thermal field within the insulation can be expected to have an influence on the onset of convection.

For the numerical analysis of this effect, some impermeable areas with high conductivity are included in the porous medium. The calculations are performed for the same five configurations previously used for the homogeneous porous medium. The thermal fields for the five systems with joists are compared with the thermal fields of the five systems without joists. The effects of convective changes with the type of insulation (density and permeability) and the geometric characteristics (thickness of insulation relative to the dimensions of the joists) are analyzed and presented in the last section of this report.

2. A PRELIMINARY APPROACH TO THE REAL SYSTEM

2.1 OBJECTIVES

The purpose of this study is not to model the heat transfer in the complete system (indoor chamber + ceiling + attic + roof), but to look specifically at the heat loss through the ceiling. However, to characterize the heat transfer mechanisms inside the layer of insulation in the attic, one needs to know the influence of the "outside" conditions that are the boundary conditions of the studied system. The insulation inside the attic is lying on the floor, and it is surrounded by a large air space for which the fluid motion is hard to characterize because the flow may be turbulent.

The effect of the exchange by radiation between the inside surfaces of the roof and the top surface of the insulation is also a complex problem, depending on the emittances of the various surfaces involved in this heat exchange process. If a system of ventilation exists, mixing of the air inside the attic may also change the inside roof temperatures and the temperature on the top of the insulation.

The approach adopted here consists of studying the porous layer alone, looking for appropriate thermal and dynamic boundary conditions to apply at the interface between the fluid in the attic space and the layer of insulation.

The purpose is also to try to characterize the outdoor conditions (outside temperature) under which heat transfer by convection can occur within the insulation and be a significant mode of transport for given properties of the insulating material (density, thermal conductivity, and permeability).

First, a simplified description of the real system is presented for the residential ATM used in the Roof Research Center. The objectives here are

- to verify, by a numerical approach, the criteria for the onset of convection in a porous medium under specific conditions;
- to study how convection effects change with the thickness of insulation and with the density, conductivity, and permeability of the type of insulation;
- to look at how wood joists within the insulation affect the criteria for the onset of convection for various types of insulation; and

- to compare the thermal resistance obtained using the model for a configuration similar to the existing small-scale apparatus with that obtained using configurations closer to a real system.

2.2 A SIMPLE DESCRIPTION OF THE REAL SYSTEM

2.2.1 The Facilities: ATM and LSCS

Figure 2.1 shows the ATM used in the LSCS. This module is made with wood rafters and joists. Gypsum board is attached to the bottoms of the joists, and 1.3-cm (0.5-in.)-thick plywood is attached to the tops of the rafters. The plywood roof sheathing is covered with roofing paper and medium gray asphalt shingles. The gables are constructed with plywood of the same thickness.

The LSCS is shown in Fig. 2.2. The upper portion of the LSCS constitutes the environmental chamber (climate chamber), which can be operated over an ambient temperature range of -40°C (-40°F) to 65.5°C (150°F). An array of infrared heating lamps is mounted on the ceiling of the Climate Chamber to simulate solar radiation.

The lower part is composed of guard and metering chambers designed to simulate a wide range of indoor temperatures from 7.2°C (45°F) to 65.5°C (150°F). Reference 6 contains a detailed presentation of the facilities.

This study deals only with winter conditions under which the inside of the house loses heat to the attic space (heat flows upward). The metering chamber is a guarded hot box maintained at 21°C (70°F) for every outside temperature.

2.2.2 The Physical Attic Insulation Problem

The geometry of the physical attic insulation problem is shown in Fig. 2.3. This section briefly describes the heat transfer behavior for winter conditions for the four principal parts of the system: the metering chamber, the ceiling (gypsum board), the attic insulation, and the attic space. Under winter conditions, the house loses heat through the ceiling, which, in turn, loses heat to the attic insulation. The primary modes of transport involved in this mechanism are analyzed here.

Fig. 2.1. Attic test module.

ORNL-DWG 92-4568

Fig. 2.2. Large-scale climate simulator.

Fig. 2.3. The physical attic insulation problem: schematization.

2.2.2.1 The metering chamber

The indoor temperature T_0 is controlled by a thermocouple and is kept constant. The bottom temperature of the ceiling, T'_0 , results from convective exchange between the gypsum board and the warmer air in the metering chamber. The value of the resistance R_0 created by the air film close to the surface depends on the exchange coefficient h . If Q is the total flux lost through the ceiling, h can be evaluated as follows:

$$Q = h S (T'_0 - T_0) \quad (2.1)$$

This convective exchange coefficient can be found in the literature [14]. The thermal resistance R_0 is then calculated

$$R_0 = 1/h \quad (2.2)$$

A thermal balance on the metering chamber gives the total heat flux Q through the ceiling.

2.2.2.2 The ceiling and the insulation layer

The temperature on the top of the gypsum board is T_l . It is the reference for the bottom of the insulation and one of the thermal boundary conditions of the system, because the gypsum board is not included in the system chosen for the numerical analysis. T_l will depend on h and the thermal resistance R_l of the gypsum board in which heat transfer occurs by conduction (see Fig. 2.3).

The nature of the heat transfer through the insulation has an effect on this temperature: as soon as convective loops develop in the insulation, T_l is no longer uniform and depends on the number of cells and the temperature difference through the insulation.

Heat transfer inside fiberglass insulation can have three primary transport modes: conduction, free convection, and volumetric radiation [15]. *Conduction* through fiberglass is caused by conduction in gas (static air), fiber contact, and fiber lengthwise conduction. *Convection* can occur in fiberglass under certain conditions of the temperature gradients. *Radiant* heat in fiberglass insulation can be scattered, absorbed, and emitted. To perform an analytical prediction of the radiative transport, knowledge of the radiative properties of

the material (scattering and absorption coefficient) as well as the phase function is necessary. Various ways to determine these properties have been developed [15–18].

Heat transfer by radiation within fiberglass insulation is an important mode of transfer, and it has been shown that, in low-density material, it can represent 40% of the total heat transfer for some fiberglass batts and 60% for some loose-fill fiberglass insulation [19–21].

2.2.2.3 The attic air space

The cold top surface of the insulation is open to the attic air space. Convective motion may occur simultaneously above and within the insulation. When the top surface of the insulation is permeable, the flows in the insulation and in the attic are coupled. The dynamic and thermal conditions at the fluid-porous medium interface result from this interaction. If the insulation is covered with an impermeable film, the flow inside the porous layer is *confined*. This facing allows one to dynamically uncouple the porous medium from the air space. However, thermal interaction still exists, as convection in the above air creates variations in the interface temperature.

A strong attic ventilation rate would permit mixing of the cold air in the attic space and produce a fairly isothermal surface on the top of the insulation [5]. This configuration may be compared with the *confined porous layer*, where the insulation is inside an enclosure with isothermal impermeable plates on the bottom and on the top (see Sect. 4.2.1).

Because the real configuration described previously is complex and involves coupled heat transfer mechanisms and interactions among several media, some approximations and simplifications are required for a numerical analysis of the problem.

In the following chapter, different existing approaches are presented. The simplified geometry and the method that has been chosen to treat this configuration are described.

2.3 THEORETICAL APPROACHES AND SCHEMATIZATION

2.3.1 Theoretical Approaches

As described previously, a layer of insulation offers a permeable surface to the surrounding attic air space. To characterize the interaction between the porous layer and the external medium, data on dynamic and thermal conditions are required. Several approaches can be used to solve the problem [4, 5, 12]. One approach considers the complete system of porous medium and fluid in contact where the laws of conservation of mass and energy are applied. With this method, approximations of the boundary conditions at the interface are avoided.

A nonglobal approach is to solve the coupled mass, momentum, and energy balance equations in the porous medium alone with appropriate boundary conditions at the interface. Although it is difficult to write realistic boundary conditions on the top permeable surface, this method allows one to treat numerically the configuration of the layer of insulation in an attic in which the porous layer is very thick and temperature differences are very large (see Sect. 3.1.2). This approach was used for this study.

2.3.2 The Horizontal Porous Layer

The configuration chosen to model heat transfer by conduction and convection in the layer of insulation is the horizontal porous layer presented in Fig. 2.4. The bottom surface is impermeable, while the top surface is open to the surrounding air. The sides are assumed to be adiabatic. The thermal boundary conditions are presented in detail in Sect. 3.

One calculation was also performed with a closed top surface to model the conditions of the small-scale test in which different insulating materials are tested. The insulation is then confined between two impermeable isothermal plates. The criterion for the onset of convection in the closed configuration is very different from the open one because there is no coupling mechanism with the environment. Both the top temperature and the bottom temperature of the insulation are isothermal.

Fig. 2.4. The horizontal porous layer with and without joists.

The effects of the wood joists in the previous configurations were studied with the same boundary conditions.

2.3.3 The Wood Joists

Most residential attics are made with wood rafters and joists. The insulation is then installed between the joists on the ceiling. This configuration is presented in Fig. 2.4.

The thermal conductivity of wood (k_o) is greater than that of the insulation (k_i). For the range of mean temperatures in which the tests are performed, k_o is close to twice k_i .

In winter conditions, when the house loses heat through the ceiling to the layer of insulation, the wood creates warmer areas within the insulation. The air that is close to the joists is then subjected to a horizontal temperature gradient. Because of this perturbation phenomenon in the conductive temperature field, this air may start to move from the bottom to the top of the insulation along each joist. Then, convection within the insulation may occur for a lower temperature gradient than the one required for the onset of convection in a homogeneous medium.

For this study, the calculations were performed assuming that the rafters are nominally 5.1×10.2 cm (2×4 in.) [actually 3.8 cm $\times$ 8.9 cm (1.5 in. $\times$ 3.5 in)]. The distance between the centers of two joists is 61 cm (24 in.). The importance of the joists' effect on convection is studied for several values of insulation thickness and permeability.

3. NATURAL CONVECTION IN POROUS MEDIA

3.1 THE TYPICAL EQUATIONS FOR HEAT TRANSFER IN POROUS MEDIA

A knowledge of the exact fluid flow inside a static porous substratum (pore scale) is almost impossible to characterize for a real porous medium, and only a few specific applications exist in which it is useful. This is why models of equations are introduced to obtain a macroscopic description of the heat transfer phenomena in a *local volume average* (LVA) for the porous medium.

If Ω represents a porous volume bounded by the surface Σ , the solid static substratum has a heat capacity $(\rho C)_s$ and a thermal conductivity (k_s) and is characterized by its porosity (ϵ) and permeability (K). The saturating fluid has a heat capacity $(\rho C)_f$, a thermal conductivity (k_f) , a thermal expansion coefficient (β), and a kinematic viscosity (ν). The porous medium is then characterized by the heat capacity $(\rho C)^*$, calculated as follows:

$$(\rho C)^* = \epsilon (\rho C)_f + (1 - \epsilon) (\rho C)_s \quad (3.1)$$

The "apparent" thermal conductivity (k^*) for the porous medium is a complex function of the conductivities of the solid matrix and the saturating fluid but also of other parameters, such as the texture of the porous medium. The determination of the exact value of k^* for a given porous medium is not easy, and very often the best way consists of approaching this conductivity by experimental measurements under "in-service" conditions; the obtained thermal conductivity is then more a "system" characteristic rather than the specific value of the material.

The thermophysical characteristics of the porous medium having been introduced, the integral equations of balances can be written, and then the assumption of a local balance within the porous medium can be used. However, this local equilibrium will exist only for an LVA larger than the volume of one pore.

3.1.1 Mass Conservation

The mean velocity of the fluid $\underline{V}$ in pores is called the interstitial velocity; the velocity defined in the absence of solid substratum ($\underline{V}$) is called the filtration velocity. The relation between these two variables is

$$\underline{V} = \epsilon \underline{V}_i . \quad (3.2)$$

The integral mass balance equation for an LVA is

$$\epsilon \frac{\partial \rho}{\partial t} + \nabla \cdot (\rho \underline{V}) = 0 . \quad (3.3)$$

3.1.2 Heat Transfer Description—the Different Models

To describe the heat transfer phenomena at a macroscopic scale within the porous medium, two models should be introduced.

The first (the simpler model) uses the concept of one fictitious fluid with a heat capacity $(\rho C)^*$ and a thermal conductivity (k^*) , but only the fluid with the heat capacity $(\rho C)_f$ moves within the solid substratum.

A more elaborate model allows one to globally consider heat exchanges between phases.

3.1.2.1 The hypothetical fluid model

This model leads to the assumption that, at one point, the temperatures of the solid phase and the fluid phase are the same ($T_s = T_f = T$); the heat exchange between the two phases is characterized by an infinite exchange coefficient.

The energy balance equation for an LVA is

$$(\rho C)^* \frac{\partial T}{\partial t} + (\rho C)_f \underline{V} \cdot \nabla T = \nabla \cdot (k^* \nabla T) . \quad (3.4)$$

3.1.2.2 The two-equation model

This model was introduced by M. Combarnous and S. Bories [22]; it uses a more precise description of the heat transfer and distinguishes between the temperatures T_s and T_f of the solid and fluid phases. The heat exchange between phases occurs by natural convection and is characterized by a finite heat exchange coefficient, h .

Here, the energy equation is split into two equations in which the variables are the temperatures T_s and T_f of the two phases that are assumed to be isotropic and homogeneous:

$$\epsilon (\rho C)_f \frac{\partial T_f}{\partial t} + (\rho C)_f \underline{V} \cdot \nabla T_f = \nabla \cdot (k_f^* \nabla T_f) - h (T_f - T_s) , \text{ and} \quad (3.5)$$

$$(1 - \epsilon) (\rho C)_s \frac{\partial T_s}{\partial t} = \nabla \cdot (k_s^* \nabla T_s) - h (T_s - T_f) . \quad (3.6)$$

The equivalent thermal conductivity (k^*) for the whole system composed of the two phases is

$$k^* = k_f^* + k_s^* . \quad (3.7)$$

By summing up, term by term, the two previous energy equations and assuming that the temperatures of the two phases are equal, the final equation corresponds to the first model of a hypothetical fluid.

This elaboration of the two-equation model leads to a more realistic description of the heat transfer in porous media and provides results that usually agree better with experimentation. However, it has been shown that, for steady convection, this description does not fundamentally change the results. This model is necessary when the Rayleigh number (Ra^*) becomes large.

3.1.3 The General Darcy's Law

Filtration velocity is related to the pressure gradient and gravity by an experimental law, called Darcy's law:

$$\underline{V} = K \mu^{-1} (-\nabla P + \rho \underline{g}), \quad (3.8)$$

where K is the permeability of the porous medium, $\mu = \rho \nu$ is the fluid dynamic viscosity, and $\underline{g}$ is the gravity vector.

By analogy with the Navier-Stokes equation, a general Darcy's Law can be obtained by adding inertial terms and a transient term. However, the effects of inertial terms can be neglected for thermoconvective flows. Also, the exact expression of these inertial terms is not very well known and may depend on the texture of the medium [23].

The general Darcy's Law can then be written as follows:

$$\frac{\rho}{\epsilon} \frac{\partial \underline{V}}{\partial t} = -\nabla P + \rho \underline{g} - \frac{\mu}{K} \underline{V}. \quad (3.9)$$

The first description corresponding to one hypothetical fluid was chosen to model the problem of natural convection in fiberglass insulation.

3.2 THE COMPLETE SET OF EQUATIONS FOR THE PRESENT PROBLEM

3.2.1 Nondimensional Equations and Parameters

In addition to the local balances for the conservation of mass, momentum, and energy, a state equation for the saturating fluid is necessary. For the classic Darcy's model, the complete set of equations for our problem is as follows:

$$\epsilon \frac{\partial \rho}{\partial t} + \nabla \cdot (\rho \underline{V}) = 0, \quad (3.10)$$

$$(\rho C)^* \frac{\partial T}{\partial t} = \nabla \cdot (k^* \nabla T) - (\rho C)_f \underline{V} \cdot \nabla T, \quad (3.11)$$

$$\frac{\rho}{\epsilon} \frac{\partial \underline{V}}{\partial t} = -\nabla P + \rho \underline{g} - \frac{\mu_f}{K} \underline{V}, \text{ and} \quad (3.12)$$

$$\rho = \rho_1 [1 - \beta (T - T_1)], \quad (3.13)$$

where ρ_1 is the fluid density at the temperature T_1 , and β is the thermal expansion coefficient.

For gases and liquids, β is small and, if the temperature differences in the system are small, one can neglect the variation of density with the temperature in Eqs. 10–12, except in the term ρg in Darcy's equation, which is the driving force for natural convection.

The other characteristics—viscosity, heat capacity, and conductivity—are assumed to be constant for this range of temperatures. All these simplifications are called the Boussinesq approximation.

Under this approximation and assuming that the fluid is incompressible, the mass conservation equation becomes

$$\nabla \cdot \underline{V} = 0 \quad (3.14)$$

The geometric configuration of the system under study allows the use of a characteristic dimension that can be, for example, the distance E between the two horizontal surfaces for the porous layer (top and bottom surfaces of the insulation). Using this dimension, a nondimensional variable can be associated with each variable. The nondimensional variables are noted with the symbol "" and are calculated as follows:

$$\begin{aligned} X' &= X / E, & U' &= U E / a^*, & P' &= P K / \mu_f a^*, & A &= L / E, \\ Z' &= Z / E, & V' &= V E / a^*, & T' &= (T - T_m) / \Delta T, & t' &= t a^* / E^2. \end{aligned}$$

If T_1 and T_2 are the temperatures at the boundaries of the system, the mean temperature T_m and the temperature difference ΔT are

$$T_m = (T_1 + T_2)/2 \quad \text{and} \quad \Delta T = T_1 - T_2.$$

Substituting these new variables into Eqs. 11–14, the set of nondimensional equations is then

$$\nabla \cdot \underline{V}' = 0, \quad (3.15)$$

$$\frac{\partial T'}{\partial t'} = \nabla^2 T' - \underline{V}' \cdot \nabla T', \text{ and} \quad (3.16)$$

$$\epsilon^{-1} \text{Pr}^{-1} M \text{Da} \frac{\partial \underline{V}'}{\partial t'} = -\nabla P' + \text{Ra}^* \underline{z} T' - \underline{V}', \quad (3.17)$$

where

$\text{Pr}^* = k^*/(\rho c)_f$ is the Prandtl number,

$M = (\rho C)_f / (\rho C)^*$,

$\text{Da} = K/E^2$ is the Darcy number,

$\text{Ra}^* = g \beta (\rho c)_f K E \Delta T / \nu k^*$ is the filtration Rayleigh number.

The Nusselt number (Nu^*) is a characteristic of the heat exchange in the global system in a steady state. Nu^* is a function of Ra^* and, evaluated at any horizontal plane, it is calculated as follows:

$$\text{Nu}^* = \frac{1}{L} \frac{\int_0^L \left(k^* \frac{\partial T}{\partial z} - (\rho C)_f V T \right) dx}{\frac{-\Delta T}{E / k^*}}. \quad (3.18)$$

Nu^* represents the ratio of the effective heat flux to the heat flux in the absence of convection:

$$\text{Nu}^* = \frac{Q(\text{cond} + \text{conv})}{Q(\text{cond})}. \quad (3.19)$$

3.2.2 The Boundary Conditions

To solve the previous set of equations, a formulation of the hydrodynamic and thermal boundary conditions is necessary.

The thermal boundary conditions often used in heat transfer problems are

- imposed temperature (Dirichlet condition): $T = T_1$ on S_1 ,
- imposed heat flux (Neumann condition): $-k^* \underline{n} \cdot \nabla T + q = 0$ on S_2 , and
- mixed conditions (Fourier): $-k^* \underline{n} \cdot \nabla T + q + h(T-T_f) = 0$ on S_3 .

Usually, the surfaces that limit the porous medium have a greater thermal conductivity than the porous medium itself, and these surfaces are most often isothermal. For the open configuration, which corresponds to the porous layer surrounded by air, the condition at the interface is different when it characterizes a thermal coupling phenomenon between the convection within the porous medium and motion in air. This specific condition is presented in detail in Sect. 4.3.

The following hydrodynamic conditions are applied to the filtration velocity ($\underline{V}'$):

- On an impermeable wall, the perpendicular component of the velocity must be 0:

$$\underline{n} \cdot \underline{V}' = 0 \quad .$$

- On a free surface, the pressure is constant:

$$P' = \text{constant} \quad .$$

One fundamental difference between fluid media and porous media is in the way we write the tangential component of the velocity, which is not zero on impermeable surfaces.

In the case of an open surface, the dynamic condition depends on the motion in the surrounding air (Sect. 4.3).

4. NUMERICAL ANALYSIS

4.1 THE CONVECTIVE CODE DARCY

The two-dimensional code used for this work was fully developed in the laboratory Modélisations Avancées des Systèmes Thermiques et Ecoulements Réels (MASTER)/Ecole Nationale Supérieure de Chimie et Physique de Bordeaux (ENSCPB), Université de Bordeaux I, France. It has already been used for several collaborative works between the MASTER and industries and, more specifically, for research on loose-fill insulation, which involved the American company CertainTeed Corporation (Blue Bell, Pennsylvania), the Centre de Recherche Industrielle de Rantigny-Isover St. Gobain (Rantigny, France), and MASTER [4-5].

DARCY is a particular version of the two-dimensional convective code PENALTY, which solves equations of convection in enclosed porous media and air spaces, horizontal or inclined. These several configurations are shown in Fig. 4.1. DARCY runs in the third configuration presented in Fig. 4.1. It is not the intent of this paper to present a description of the numerical method used to solve the equations. This information will be given later in a complete user's manual. This program remains the total property of the laboratory MASTER/ENSCPB.

4.1.1 Code DARCY Features

DARCY solves the equations of convection (mass conservation, motion, and energy) in a porous medium only, with special boundary conditions on the interface to characterize the interaction with the air motion above. The transient equations are solved to obtain a steady-state solution.

Differential Eqs. 15-17 are discretized in space and time using a finite volume method. In the initial conditions for temperature and pressure, perturbations are introduced to start the calculation. For example, the initial temperature field is the one obtained in pure conduction with the addition of a perturbation.

In the following section, the " " is omitted on nondimensional quantities to simplify the notations, $T^{(0)}(x,z) = 0.5 - z + \alpha \cos(ax) \sin(bz)$.

Configuration 1. Natural convection in enclosure partially filled with porous medium.

Configuration 2. Forced convection over a porous layer.

Configuration 3. Natural convection in a porous layer

Fig. 4.1. Convection in porous media and air spaces—code PENALTY.

The code calculates air velocities, temperatures, pressure, stream functions, and heat fluxes at each point of a regular grid. It can model different parameters such as permeabilities, insulation thicknesses, and temperature differences.

The temperature difference on the boundaries of the system is imposed through the Rayleigh number Ra^* introduced previously. The characteristics of the porous medium [permeability (K), thermal conductivity (k^*), and thermal diffusivity (a^*)], as well as the characteristics of the saturating fluid [density (ρ) and kinematic viscosity (ν)] also are included in this parameter.

Viscosity and thermal conductivity are assumed to be independent of the temperature in the calculation. The permeability and thermal conductivity can be variable in the domain, which allows one to consider a nonhomogeneous medium and, for example, to take into account enclosed solid areas, such as the joists, or a layer of insulation with variable permeability from bottom to top.

$$K = K(x,z), \text{ and } k^* = k^*(x,z).$$

For each Rayleigh number (Ra^*), the code calculates the Nusselt number (Nu^*), which allows determination of the onset of convection and, more specifically, the derivation of a critical Rayleigh number (Ra_c^*) for specific configurations.

The variation of the Nusselt number as a function of the Rayleigh number is presented in the following section for very specific boundary conditions.

4.1.2 Onset of Convection Within the Porous Medium

Both experimentation and theory clearly show the influence of boundary conditions on the onset of convection within porous media. A critical Rayleigh number can be established only for specific idealized boundary conditions

4.1.2.1 Closed configuration

If the porous medium is bounded by two isothermal impermeable plates, $Ra_c^* = 4\pi^2$. When the cold top surface of the porous medium (still sealed) is in contact with an air layer, as shown in Fig. 4.1, this top surface is not always isothermal. The

temperature at the interface depends on the convective and radiative heat transfer mechanism within the air layer.

4.1.2.2 Open configuration

When the impermeable bottom surface and the fluid above the cold top surface of the porous medium are both absolutely isothermal, $Ra_c^* = 27.1$. If this isothermal condition is not fulfilled, convection occurs for a smaller Ra^* [5].

The variation of the Nusselt number versus the Rayleigh number, as calculated by DARCY, is shown in Fig. 4.2 for the closed configuration without an air layer (isothermal top and bottom surfaces) and for the open configuration with an isothermal interface (isothermal impermeable bottom surface). This graph points out the importance of the boundary conditions. Recall the definition of the Rayleigh number presented earlier:

$$Ra^* = f(T_m) \Delta T K E, \quad (4.1)$$

$$\text{where: } f(T_m) = g \beta (\rho C)_f / \nu k^*.$$

If the thermal performance of the insulation is tested in an apparatus that corresponds to the closed box, since the critical Rayleigh number is greater ($Ra_c^* = 40$) than in the open configuration, a higher temperature difference is required to start convection for the same material with the same thickness.

In Fig. 4.2, notice that the critical Rayleigh number predicted by the model for the two previous configurations (open and closed) under the same boundary conditions agrees with theory ($Ra_{cr} = 27.1$ and $4\pi^2$). These curves also point out the earlier onset of convection in the presence of joists. This phenomenon will be discussed more specifically in Sect. 5.1.2.

Because the real configuration described in Sect. 2 is very different from that of the closed box in terms of convection, five typical configurations were studied with the model as approaches to the attic insulation problem.

Fig. 4.2. Nusselt number vs Rayleigh number in closed and open configurations with and without joists.

4.2 FIVE TYPICAL CONFIGURATIONS

4.2.1 Closed Configuration: The Small-Scale Test

In this system, the porous medium (i.e., the insulation) is bounded by two impermeable isothermal plates in contact with the top and bottom surface of the insulation. No air gap exists, and the sides are assumed to be adiabatic.

4.2.2 Open Configuration with Various Thermal Boundary Conditions

As a first simplifying hypothesis to model the interaction between the insulation and the attic air, a partial coupling of the internal and external flow is considered. Partial coupling is the case where normal velocity or a pressure distribution is assumed on the open top of the insulation. This approximation supposes that the flow dynamics outside the porous medium are known. Because this approach ignores thermal interactions and only partially takes into account dynamic coupling, it is not completely satisfactory for most situations. However, it constitutes a good first approach for the attic insulation problem.

A distribution of temperature $T(x)$ can also be assumed at the interface, depending on the external flow.

On the bottom of the insulation, two different types of thermal boundary conditions are applied; the first type assumes an isothermal bottom surface (Dirichlet condition) and the second is a Neumann condition (imposed heat flux).

The four systems that were studied for the open configuration are recalled here:

- Open System 1:

$$\begin{aligned} z = 0, \quad T = T_1 = \text{constant}, \quad V = 0 \\ z = 1, \quad T = T_2 = \text{constant}, \quad P = \text{constant} \quad (U = 0) \end{aligned}$$
- Open System 2:

$$\begin{aligned} z = 0, \quad T = T_1 = \text{constant}, \quad V = 0 \\ z = 1, \quad T = T_2(x), \quad P = \text{constant} \quad (U = 0) \end{aligned}$$

- Open System 3: $z = 0, Q = \text{constant}, V = 0$
 $z = 1, T = T_2 = \text{constant}, P = \text{constant} (U = 0)$
- Open System 4: $z = 0, Q = \text{constant}, V = 0$
 $z = 1, T = T_2(x), P = \text{constant} (U = 0)$

T_1 represents the temperature on the bottom surface of the insulation, and T_2 is the temperature on the top surface. U and V are, respectively, the horizontal and vertical components of the velocity ($\underline{V}$).

All calculations were conducted with the same aspect ratio, $A = L/E = 2.5$, which would correspond to 24.4-cm (9.6-in.)-thick insulation, to compare the calculated results with the first set of data from the LSCS. The distance (L) between joists was 61 cm (24 in.).

HSL (see Tables 5.1 and 5.2) is the parameter of perturbation introduced in the initial condition; it actually represents the assumed number of convective cells chosen to start the calculation.

Two different Nusselt numbers are used here. According to the definition given in Eq. (3.18), Nu^* in a homogeneous medium is equal to 1 when no convection exists. With joists, $Nu^* > 1$ in the conduction mode, because the joists' conductivity is greater than the conductivity of the surrounding medium. To evaluate the effect of convection only, a second Nusselt number has been introduced: Nu' , the ratio of the effective value of Nu^* to the value of Nu^* in a conduction mode.

4.3 THERMAL AND DYNAMIC PROPERTIES OF FIBERGLASS INSULATION

The thermal and dynamic properties of the fiberglass are as important as the boundary conditions of the system in analyzing heat transfer through the insulation.

Until now, the notion of radiative heat transfer within the insulation has only been suggested; this study does not treat the coupling of radiation-convection mechanisms. In the first part of this section, the definition of an "effective" thermal conductivity is introduced.

For low-density materials, such as loose-fill insulation and some fiberglass batt in which convection may be a significant mode of heat transport, it is necessary to know the accurate value of the permeability.

In the last part of this section, using the definition of conductivity, the notion of thermal resistance is introduced.

4.3.1 Thermal Conductivity, k^*

The thermal conductivity of fiberglass insulation used here includes radiation. The value of k^* is calculated using a semi-empirical expression [24]. Under the assumption that the heat transfer by conduction and radiation are not coupled, the *effective* conductivity k^* can be calculated as follows:

$$k^* = k_{cd} + k_r \quad (4.2)$$

The conductive transfer is represented by the thermal conductivity $k_{cd} = k_g + k_s$, where k_g is the conductivity of static air and k_s is the conductivity of the solid phase [24]:

$$k_g = k_1 T_m^{a_1} \quad (4.3)$$

$$k_s = k_2 \rho^{a_2} (1 + b_2 T_m) \quad (4.4)$$

Using an analogy with an air layer bounded by two isothermal plates, the radiative heat transfer can be characterized by a thermal conductivity, k_r . This approach is available for high-porosity material, which includes most fiberglass insulation, particularly low-density loose-fill insulation.

$$k_r = \frac{4 \sigma T_m^3 E}{\frac{1}{E_1} + \frac{1}{E_2} - 1 + F} \quad (4.5)$$

Some experiments performed on one type of loose-fill insulation [3] showed that the *effective* conductivity for a temperature difference lower than 44.4°C (80°F) follows the equation

$$k^* = k_0 \exp \left[\alpha (T_m - T_0) \right] . \quad (4.6)$$

4.3.2 Thermal Resistance, R

The thermal performances of various insulating materials are compared in terms of thermal resistance, or R-value.

If a layer of insulation is subjected to a temperature difference ΔT , and if Q is the global heat flux through this layer, the R-value is calculated as follows:

$$R = \frac{\Delta T}{Q} . \quad (4.7)$$

This general definition is valid even when convection occurs within the insulation. In the absence of convection (conduction-radiation mode), the total heat flux through a layer of insulation of thickness E is

$$Q = k^* \frac{\Delta T}{E} . \quad (4.8)$$

If $R_0(T_m)$ is the thermal resistance of the insulation in the absence of convection,

$$R_0(T_m) = \frac{E}{k_m^*} . \quad (4.9)$$

The *nominal* R-value, then, is the thermal resistance for $T_m = 24^\circ\text{C}$ (75°F). For our system, the reference for the R-value will be the thermal resistance at 21°C (70°F), which corresponds to the state in which no temperature difference exists throughout the insulation.

$$R_0(70^\circ\text{F}) = \frac{E}{k_0^*} . \quad (4.10)$$

According to the definition of the Nusselt number (Nu^*) given previously, the R-value is

$$R(T_m) = \frac{R_0(T_m)}{Nu^*} \quad (4.11)$$

For each given value of Ra^* , the model provides the corresponding Nu^* . If the properties of the insulation (k^* , K) and the thickness (E) are known, a value of ΔT can be calculated from Ra^* . The results of the calculation can be presented in terms of Nu^* as a function of Ra^* (Fig. 4.2) or, as shown in Fig. 4.3, thermal resistance (R-value) versus temperature difference. Here, the calculation was performed for an aspect ratio $A = 2.5$, which corresponds to $E = 24.4$ cm (9.6 in.).

Notice the increase in thermal resistance as the temperature difference increases. This is the effect of decreasing mean temperature on conductivity. As soon as convection occurs in the porous layer, the Nusselt number becomes greater than 1. The corresponding R-value starting from $R_0(T_m)$ decreases.

Just as a critical Rayleigh number was introduced previously as a criterion for the onset of convection, a critical temperature difference ΔT_c can be calculated from Ra^* to predict the climate conditions under which convective motion may start within the insulation and be responsible for a degradation in thermal performance.

The curves presented in Fig. 4.3 demonstrate the influence of boundary conditions on the critical temperature difference ΔT_c , which is much lower in the open configuration than in the closed configuration.

If loose-fill insulation is tested in a hot box under temperature gradients lower than ΔT_c , no evidence of convection exists, and the heat transfer modes are then conduction and radiation only.

Note that all these calculations were performed for a given permeability $K = 9.3 \times 10^{-8} \text{ m}^2$ ($1 \times 10^{-6} \text{ ft}^2$); small variations in permeability can modify the shape of the curve and the critical temperature difference.

4.3.3 Permeability, K

As described previously, air permeability, (K), is one of the most significant parameters for the study of convection.

Fig. 4.3. Thermal resistance vs temperature difference in closed and open configurations with and without joists.

The air permeability of a porous medium in laminar flow is defined as

$$K = \frac{(\text{flow rate} \times \text{viscosity} \times \text{thickness})}{(\text{area} \times \text{pressure drop})} \quad (4.12)$$

Some permeability measurements performed on batt fiberglass insulation show that the perpendicular and parallel permeabilities can vary by about a factor of two from one to the other [25]. This is caused by the orientation of the fibers, which creates a nonisotropic medium and produces a higher permeability in the direction of the fibers. Usually, a mean permeability is used for the analysis of convection in batts.

Loose-fill insulation constitutes a more isotropic medium; however, it can be compressed, and its homogeneity is not always well controlled.

5. RESULTS AND DISCUSSION

5.1 THE FIVE CONFIGURATIONS

In the five systems previously described, calculations were made for a range of Rayleigh numbers that spans both the conductive and the convective regimes for the different configurations. The critical Ra^* (i.e., the ΔT_c) was evaluated for each boundary condition. The thermal resistance was calculated with Eq. 4.11 in Sect. 4. All calculations were performed for one thickness of the insulation, $E = 24.4$ cm (9.6 in.), corresponding to an aspect ratio of $A = 2.5$, and for one permeability, $K = 9.3 \times 10^{-8}$ m² (10^{-6} ft²). Again, the values of E , A , and K were chosen to model the geometry of the experimental configuration and the property of the tested material to compare predicted and measured R-values. The results for the attic system without joists are presented in Table 5.1, and those for the system with joists are presented in Table 5.2.

5.1.1 Criteria for the Onset of Convection

The nominal R-value was calculated using Eqs. 4.6 and 4.10, assuming that the thermal resistance of the insulation is $R_0(70) = 3.9$ m² · K/W (22 h · ft² · °F/Btu) with wood joists.

The critical Rayleigh number found in the literature [8] is shown Table 5.1 in the column under Ra_{cr} on the first line for each configuration; on the next lines are values estimated by the model. In the second column for each Ra^* , the corresponding temperature difference is calculated using the parameters introduced previously and the definition of Ra^* . For configurations 1, 2, and 4, the critical Rayleigh number is compared with results given in the literature [8]; they agree. For open configurations 3 and 5, when a top cold temperature is assumed [$T_2 = T_2(x)$], derivation of a critical Rayleigh number is more complex; in fact, the nonisothermal condition imposed at the interface characterizes the coupling mechanism between the inside and outside flows. Note that, for the same Ra^* , the configurations with variable interface temperature have a higher global heat transfer (i.e., a higher Nu^*).

Table 5.1. The five configurations without joists: Ra^* , Nu^* , and the corresponding values of the temperature difference and thermal resistance of the insulation

	$Ra(\alpha)$	Ra^*	DT	DTeff	Nu^*	Nu'	RO	R	HSL	A
1 CLOSED $T_1=0.5$ $T_2=-0.5$	$4\pi^2$	0	0	1.00	1.000	1.000	22.3	22.3	2	2.5
	≈ 40	27	41	1.00	1.000	1.000	23.7	23.7	2	2.5
		40	55	1.00	1.000	1.000	24.3	24.3	2	2.5
		45	61	1.00	1.157	1.157	24.4	21.0	2	2.5
		48	64	1.00	1.278	1.278	24.6	19.2	2	2.5
		50	66	1.00	1.353	1.353	24.7	18.2	2	2.5
2 OPEN $T_1=0.5$ $T_2=-0.5$	27.1	0	0	1.00	1.000	1.000	22.3	22.3	2	2.5
		08	14	1.00	1.000	1.000	22.8	22.8	2	2.5
		20	32	1.00	1.000	1.000	23.4	23.4	2	2.5
	>27	27	41	1.00	1.000	1.000	23.7	23.7	2	2.5
	<30	30	45	1.00	1.190	1.190	23.9	20.1	2	2.5
		48	64	1.00	1.950	1.950	24.6	12.6	2	2.5
3 OPEN $T_1=0.5$ $T_2=T_2(X)$	—	0	0	1.00	1.000	1.000	22.3	22.3	2	2.5
	≈ 08	08	14	1.00	1.008	1.008	22.8	22.6	2	2.5
		20	32	1.00	1.116	1.116	23.4	20.9	2	2.5
		27	41	1.00	1.428	1.428	23.7	16.6	2	2.5
		30	45	1.00	1.594	1.594	23.9	15.0	2	2.5
		48	64	1.00	2.366	2.366	24.6	10.4	2	2.5
4 OPEN $QO=CT$ $T_2=-0.5$	17.5	0	0	1.00	1.000	1.000	22.3	22.3	2	2.5
	>08	08	14	1.00	1.000	1.000	22.8	22.8	2	2.5
	<20	20	32	0.98	1.000	1.000	23.4	22.9	2	2.5
		27	41	0.81	1.000	1.000	23.7	19.2	2	2.5
		30	45	0.76	1.000	1.000	23.9	18.1	2	2.5
		48	64	0.59	1.000	1.000	24.6	14.5	2	2.5
5 OPEN $Q(Z=0)=CT$ $T_2=T_2(X)$	—	0	0	1.00	1.000	1.000	22.3	22.3	2	2.5
	≈ 08	08	14	0.96	1.000	1.000	22.8	21.9	2	2.5
		20	32	0.91	1.000	1.000	23.4	18.9	2	2.5
		27	41	0.67	1.000	1.000	23.7	15.9	2	2.5
		30	45	0.63	1.000	1.000	23.9	15.0	2	2.5
		48	64	0.47	1.000	1.000	24.6	11.5	2	2.5

Table 5.2. The five configurations with joists: Ra^* , Nu^* , and the corresponding values of the temperature difference and thermal resistance of the insulation

	Ra^*	DT	D_{Teff}	Nu^*	Nu'	RO	R	HSL	A
1 CLOSED $T_1=0.5$ $T_2=-0.5$	0	0	1.00	1.016	1.000	22.0	22.0	2	2.5
	30	45	1.00	1.026	1.009	23.5	23.3	2	2.5
	38	54	1.00	1.047	1.031	23.8	23.1	2	2.5
	40	55	1.00	1.069	1.053	23.9	22.6	2	2.5
	48	64	1.00	1.298	1.278	24.2	18.9	2	2.5
	50	66	1.00	1.364	1.342	24.3	18.1	2	2.5
2 OPEN $T_1=0.5$ $T_2=-0.5$	0	0	1.00	1.016	1.000	22.0	22.0	2	2.5
	08	14	1.00	1.016	1.000	22.4	22.4	2	2.5
	20	32	1.00	1.024	1.007	23.1	22.9	2	2.5
	27	41	1.00	1.088	1.071	23.4	21.8	2	2.5
	30	45	1.00	1.230	1.211	23.5	19.4	2	2.5
	48	64	1.00	1.949	1.918	24.2	12.6	2	2.5
3 OPEN $T_1=0.5$ $T_2=T_2(X)$	0	0	1.00	1.016	1.000	22.0	22.0	2	2.5
	08	14	1.00	1.033	1.017	22.4	22.1	2	2.5
	20	32	1.00	1.151	1.132	23.1	20.4	2	2.5
	27	41	1.00	1.447	1.424	23.4	16.4	2	2.5
	30	45	1.00	1.604	1.578	23.5	14.9	2	2.5
	48	64	1.00	2.353	2.316	24.2	10.4	2	2.5
4 OPEN $Q_0=CT$ $T_2=-0.5$	0	0	0.98	1.000	1.000	22.0	21.5	2	2.5
	08	14	0.98	1.000	1.000	22.4	21.9	2	2.5
	20	32	0.97	1.000	1.000	23.1	22.4	2	2.5
	27	41	0.81	1.000	1.000	23.4	18.9	2	2.5
	30	45	0.76	1.000	1.000	23.5	17.8	2	2.5
	48	64	0.59	1.000	1.000	24.2	14.2	2	2.5
5 OPEN $Q(Z=0)=CT$ $T_2=T_2(X)$	0	0	0.98	1.000	1.000	22.0	21.5	2	2.5
	08	14	0.96	1.000	1.000	22.4	21.5	2	2.5
	20	32	0.80	1.000	1.000	23.1	18.4	2	2.5
	27	41	0.67	1.000	1.000	23.4	15.6	2	2.5
	30	45	0.63	1.000	1.000	23.5	14.8	2	2.5
	48	64	0.47	1.000	1.000	24.2	11.3	2	2.5

However, it is difficult, even impossible, to separate the part caused by convection within the insulation itself from that caused by penetration of the outside flow.

In these cases, the significance of Ra_{cr} is different from the traditional definition of critical Rayleigh (the value for which natural convection starts within the insulation). Here, it corresponds to the value of the Rayleigh number for which Nu^* begins to increase (i.e., the thermal resistance begins to decrease), and one part of this phenomenon is caused by "induced" convection from interaction at the air space–insulation interface.

The function used for the variable top cold temperature should model the presence of two convective cells inside the medium. This distribution was chosen according to observation of the top surface of the insulation in the ATM with an infrared camera in the presence of convection [7]. The infrared camera clearly showed hexagonal patterns on the top surface, and the characteristic dimension of the cell appeared to be the distance between two joists.

$$T_2(x) = T_2 + a \cdot \cos\left(\pi \cdot x \cdot \frac{HSL}{A}\right) \quad (5.1)$$

The coefficient a then characterizes the temperature gradient between the cold spots in the center and the warmer areas on the edges. HSL is the number of cells in the domain; here, $HSL = 2$.

In the configurations where a constant heat flux is maintained on the bottom, (configurations 4 and 5), the Nusselt number obtained with the model is 1 for all values of Ra^* as the flux is imposed. Because the bottom temperature is not uniform, an *effective* temperature difference, ΔT_{eff} , is calculated. The R-value is then:

$$R(T_m) = R_0(T_m) \cdot \Delta T_{eff} \quad (5.2)$$

To impose a constant temperature on a surface is a stronger thermal stress for the system than to impose a constant heat flux. While a temperature imposed on the bottom surface of the system is "more stable," the temperature difference required for the onset of convection is greater than the one under a constant flux boundary condition. The consequence is that convection occurs for a smaller value of the Rayleigh number with the Neumann boundary condition in configuration 4 ($Ra_{cr}^* = 17.6$) than with an isothermal bottom surface ($Ra_{cr}^* = 27.1$), as in configuration 2.

The variation of thermal resistance (R-value) with temperature difference is shown in Fig. 5.1 for the previous boundary conditions. These curves clearly show the effects of

Fig. 5.1. Thermal resistance vs temperature difference without joists: the five configurations.

the boundary conditions on the value of the critical temperature difference and on the shape of the curves. The variation of the R-value for the closed configuration shows a very high critical temperature difference: $\Delta T_{cr} \approx 30.5^\circ \text{C}$ (55°F).

Air velocities, isotherms, stream functions, and isobars for $Ra^* = 40$ and 48 in half of the medium are shown in Fig. 5.2.

5.1.1.1 Closed Configuration with $Ra^* = 40$

No fluid motion exists for this configuration. The isotherms are horizontal, parallel, and equidistant, which is typical of the conductive mode with adiabatic sides:

$$T(x,z) = T(z) = 0.5 - z \quad (5.3)$$

The pressure is a solution of the equation:

$$\frac{\partial P}{\partial z} = Ra^* \cdot T \quad (5.4)$$

5.1.1.2 Closed Configuration with $Ra^* = 48$

Figure 5.2 shows a comparison (for velocities, temperatures, pressure, and stream functions) between a conductive mode ($Ra^* = 40$) and a convective mode ($Ra^* = 48$).

The same calculations were performed with joists within the insulation, and the effect of these perturbations on the criteria for the onset of convection is presented in the following section.

5.1.2 The Effect of the Wood Joists

The calculations with joists are presented in Table 5.2.

5.1.2.1 Changes in the Critical Rayleigh Number

Because the air near the joists is subjected to a horizontal temperature gradient, it begins to move for Rayleigh numbers lower than the critical Rayleigh numbers predicted in Table 5.1 for a homogeneous medium. In Fig. 4.2, the effects of the joists on the start

Fig. 5.2. Closed configuration: velocities, isotherms, steam functions, and isobars.

of convection are shown for both configurations (closed and open) with constant top temperature in terms of Nusselt number. Three phases can be distinguished on these curves:

1. If Ra^* is lower than 27.1 for the open top or lower than 40 for the closed box, some small velocities appear in the bottom of the insulation near the wood studs, increasing the total heat transfer ($Nu' > 1$). The Nusselt number (Nu') plotted in Fig. 4.2 represents the ratio of the effective heat transfer Nu^* to the heat transfer for $Ra^* = 0$. In this way, the effect of conduction in the wood is eliminated, and the increase in Nu' is caused only by convection. This can be verified by looking at the air velocities within the insulation presented in Fig. 5.12 (closed top) and Fig. 5.16 (open top).
2. When Ra^* reaches the critical values of 27.1 or 40, the "real" convection starts, and the variations of Nu' versus Ra^* for closed and open configurations are very similar.
3. For higher Rayleigh numbers, when convection is very "active," the joists become an obstacle to air motion, which explains why the curves intersect at one point. In Figs. 5.12 and 5.16, the velocities for $Ra^* = 48$ are shown to illustrate this configuration.

Note that these calculations were performed for only one thickness, $E = 24.4$ cm (9.6 in.). The effect of insulation thickness relative to the joist dimension was also studied. Several tests were conducted for the same density [$\rho = 8$ kg/m³ (0.5 lb/ft³)] with variable thicknesses [$E = 21, 32$, or 39.4 cm (8.25, 12.5, or 15.5 in.)] in the open configuration with constant top temperature. These results are shown in Table 5.3, where it is evident that the effect of the joists on the start of convection decreases as thickness increases. Note that Nu' remains equal to 1 for larger Ra^* , when the thickness is larger. For $E = 39.4$ cm (15.5 in.), no velocity exists in the insulation for $Ra^* < Ra_{cr}$, and when convection starts, the joists do not constitute an obstacle to air motion.

Table 5.3. Open configuration for one density and three thicknesses: Ra^* , Nu^* , ΔT , and R-values of R-19, R-30, and R-38

E (in.)	Density (lb/ft ³)	R-value (h · ft ² · °F)	Permeability (m ²)
8.25	0.50	19.0	$3.42 \cdot 10^{-8}$
12.50	0.50	30.0	$3.42 \cdot 10^{-8}$
15.50	0.50	38.0	$3.42 \cdot 10^{-8}$

E (in.)	Ra^*	Nu^*	DT (°F)	RO (T _m)	R (T _m)
8.25	0.0	1.000	0	18.69	18.69
	8.5	1.001	41	19.91	19.77
	15.0	1.002	64	20.58	20.37
	20.0	1.004	79	21.08	20.77
	27.0	1.055	97	21.62	20.28
	32.0	1.220	109	22.02	17.82
	40.0	1.427	> 120	—	—
12.50	0.0	1.000	0	29.75	29.75
	8.5	1.000	28	31.02	31.02
	15.0	1.000	45	31.82	31.82
	20.0	1.001	56	32.35	32.31
	27.0	1.022	70	33.04	32.32
	32.0	1.231	80	33.54	27.24
	40.0	1.683	93	34.20	20.32
	50.0	2.135	107	34.92	16.35
15.50	0.0	1.000	0	37.69	37.69
	8.5	1.000	23	39.11	39.11
	15.0	1.000	37	39.94	39.94
	20.0	1.000	47	40.54	40.54
	27.0	1.002	59	41.28	41.19
	32.0	1.010	67	41.78	41.36
	40.0	1.304	79	42.54	32.62
	50.0	1.867	92	43.37	23.23

5.1.2.2 Thermal Resistance

Because the conductivity (k_1) of wood is twice the conductivity (k_0^*) of the insulation, including joists in the insulation decreases the nominal R-value. If R' and R are, respectively, the thermal resistance with joists and without joists, and assuming that $k_1 = 2 k_0$, R' can be calculated as follows:

$$R'(T_m) = \frac{12}{k^*(T_m)} \cdot \frac{1}{\frac{1.5}{2E-3.5} + \frac{22.5}{2E}} = \frac{R'_0(T_m)}{Nu'} \quad (5.5)$$

For example: for $E = 24.4$ cm (9.6 in.),

$$R'(70) = 3.87 \text{ m}^2 \cdot \text{K/W} \text{ (22 h} \cdot \text{ft}^2 \cdot ^\circ\text{F/Btu) ,}$$

$$R(70) = 3.93 \text{ m}^2 \cdot \text{K/W} \text{ (22.35 h} \cdot \text{ft}^2 \cdot ^\circ\text{F/Btu) , and}$$

$$R/R' = 1.016 = Nu^*/Nu' .$$

The decrease in the nominal R-value caused by the presence of joists here corresponds to 1.6%. The variation of thermal resistance over temperature difference for the five basic configurations is shown in Fig. 5.3. The permeability used in these calculations was measured by CertainTeed Corporation (Fig. 5.4) [25].

When a constant flux is imposed on the bottom of the insulation, the temperature on this surface in the conduction regime is not uniform. The joists then create cool areas decreasing the temperature on the bottom surface (i.e., decreasing the *effective* temperature difference, ΔT_{eff} , through the insulation).

5.1.2.3 Structure and Location of Convective Cells

Observation of the top surface of the loose-fill insulation with an infrared camera [6] clearly showed the hexagonal patterns typical of the structure of convective motion in the horizontal porous layers heated from below for $Ra^* \geq 40$.

Fig. 5.3. Thermal resistance vs temperature difference with joists: the five configurations.

Fig. 5.4. Permeability vs density for one type of loose-fill fiberglass insulation.

The locations of the cells and their dimensions relative to the distance between two joists are not easy to deduce from this observation, since the joists do not appear clearly from the top surface. The infrared camera was used to observe the ceiling from the metering chamber side. This experience seemed to show that the hexagonal cell was located between the joists, as shown in Fig. 5.5.

In the numerical calculation, a perturbation must be introduced on the temperature and velocities for the convection to start. The code used to solve the equations of convection in a porous medium can be more or less sensitive to this initial condition and may have an influence on the final solution. In the nonhomogeneous configuration, the joists constitute a perturbation, and the calculation can be performed using the conduction regime as the initial condition. This allows no assumption about the size and number of cells in the domain.

The natural evolution of the solution, then is two semirolls between two joists, for an aspect ratio of $A = 2.5$ [i.e., $E = 24.4$ cm (9.6 in.)]; this solution was used as the initial solution for the homogeneous configuration.

The numerical analyses tend to show a correlation between the dimensions of the cells and the distance between joists. However, this observation should be verified experimentally.

5.2 CONSEQUENCES OF VARIABLE PERMEABILITY AND THICKNESS

Permeability being a significant parameter for the analysis of convection, another objective of this study was to characterize the influence of changes in density on thermal performance. Usually, an empirical correlation between density and permeability is given. However, uncertainty remains in the relationship between density and thickness, mainly because it depends on the process used to blow the loose-fill insulation, but also because it seems to be difficult to control the uniformity of the installed material. To approach this problem, different calculations were performed for three cases. The first case assumes that, for the same thickness, insulation with several densities can be installed. In the second case, the objective was to compare the thermal resistance of loose-fill insulation when thickness is doubled and density is uniform. In the third case, a vertical gradient of permeability is assumed within the insulation, and its consequences on convection are

studied. In each configuration reported in this section, joists were included in the calculations.

5.2.1 Variable Permeability for a Fixed Thickness

Insulation thickness is assumed to be $E = 32 \text{ cm}$ (12.5 in.). With this fixed thickness, the calculation is performed with a range of densities, starting with a light product [$\rho = 6.4 \text{ kg/m}^3$ (0.4 lb/ft³)] and including more compacted material [$\rho = 11.2 \text{ kg/m}^3$ (0.7 lb/ft³)]. The values of air permeability used for the calculation (see Fig. 5.4) were provided by CertainTeed Corporation for one type of loose-fill fiberglass insulation.

The objective of this calculation is to study the influence of variable permeability on the evolution of a given R-value over the temperature difference. The thermal resistance (R-value) with joists is calculated for four values of density (i.e., permeability); the results are presented in Fig. 5.6. In these calculations, the top and bottom surfaces of the insulation are assumed to be isothermal.

Critical temperature differences for the densities 6.4, 8.0, and 9.6 kg/m³ (0.4, 0.5, 0.6 lb/ft³) are, respectively, $\Delta T = 22.2, 36, \text{ and } 52.7^\circ \text{C}$ (40, 65, 95° F) for the permeabilities given in Fig. 5.4. For a density greater than or equal to 11.2 kg/m³ (0.7 lb/ft³) (i.e., $K \leq 1.19 \times 10^{-8} \text{ m}^2$ ($1.29 \times 10^{-7} \text{ ft}^2$)), no convection occurs in the insulation for a temperature difference lower than 66.6° C (120° F).

If we suppose that, in reality, the temperature difference does not exceed 44.4° C (80° F) in the loose-fill insulation blown at 32 cm (12.5 in.) with a density at least equal to 9.6 kg/m³ (0.6 lb/ft³), no evidence exists of convection in the insulation. However, the critical temperature difference for 6.4 kg/m³ (0.4 lb/ft³) remains low : $\Delta T_{\text{cr}} = 22.2^\circ \text{C}$ (40° F).

The density of 8 kg/m³ (0.5 lb/ft³) seems to give a good result, considering that it is still a light density, but convection starts only for $\Delta T \geq 39^\circ \text{C}$ (70° F), which corresponds to a very cold outside temperature : $T_{\text{out}} \leq -18^\circ \text{C}$ (0° F).

Fig. 5.6. Thermal resistance vs temperature difference for one thickness
 $[E = 31.75 \text{ cm (12.5 in.)}]$ and four densities $[6.4, 8.0, 9.6, \text{ and } 11.2 \text{ kg/m}^3 (0.4, 0.5, 0.6, \text{ and } 0.7 \text{ lb/ft}^3)]$: the effect of various permeabilities.

5.2.2 Performance of a Double Layer

In many cases, to obtain better insulation performance (i.e., a higher R-value), insulation thickness is increased; for example, R-19 can be obtained with 20.3 cm (8 in.) of loose-fill insulation, and R-38 can be obtained with 40.6 cm (16 in.). While this better performance remains in effect when heat transfer occurs only by conduction, the thicker insulation may induce convection at a lower temperature difference.

In fact, this can be explained by looking at the expression for the Rayleigh number given in Sect. 4 and recalled as follows:

$$Ra^* = f(T_m) \cdot \Delta T \cdot K \cdot E \quad (5.6)$$

It has been shown that the critical Rayleigh number Ra_{cr}^* is equal to 27.1 in the open configuration with isothermal top temperature. If R-19 and R-38 are blown with the same density, they must have the same permeability. In a first approximation, assuming that the thermal characteristics included in $A(T_m)$ are the same in the two configurations (i.e., they do not vary with the mean temperature), the critical temperature difference required to initiate convection in the 40.6-cm (16-in.)-thick layer is one-half the critical ΔT for 20.3 cm (8 in.) because $\Delta T_{cr} \cdot E = \text{constant}$.

Three calculations were performed for one density [$\rho = 8 \text{ kg/m}^3$ (0.5 lb/ft³)] and for three thicknesses [$E_1 = 21 \text{ cm}$ (8.25 in.), $E_2 = 32 \text{ cm}$ (12.5 in.), and $E_3 = 39.4 \text{ cm}$ (15.5 in.)] with insulation characteristics corresponding to R-19, R-30, and R-38, respectively, with the characteristics chosen previously. The variation of thermal resistance with temperature difference was deduced from the calculations. The results are presented in Fig. 5.7 and Table 5.3.

As explained previously, these curves show an increase in ΔT_{cr} with a decrease in thickness for a fixed density. However, the gap between the ΔT_{cr} for E_1 and E_3 is not as great as expected; according to Eq. (5.6), thicknesses and critical temperature differences should be related by

$$\frac{E_i}{E_j} = \frac{\Delta T_{crj}}{\Delta T_{cri}} \quad (5.7)$$

Figure 5.7 shows that $E_i/E_j > \Delta T_{crj} / \Delta T_{cri}$. More specifically, when we look at R-19 and R-38, $E_3 / E_1 = 1.8$, but $\Delta T_{cr1} / \Delta T_{cr3} = 1.4$. In fact, Eq. (5.7) is valid

Fig. 5.7. Thermal resistance vs temperature difference for three thicknesses [$E = 20.95, 31.75, \text{ and } 39.40 \text{ cm (} 8.25, 12.5, \text{ and } 15.5 \text{ in.)}$] and one density [$8 \text{ kg/m}^3 (0.5 \text{ lb/ft}^3)$]: the effect of joists at various insulation thicknesses.

under the assumption that the thermal characteristics of the insulation were the same in the three configurations. In reality, the mean temperatures in these two layers are not the same when $Ra^* = 27.1$; then $\Delta T_{cr} \cdot E$ is not constant but is a function of the mean temperature. This explains why the critical temperature differences in Fig. 5.7 are closer to each other than expected.

In the information given by the manufacturer, a small variation of the density with thickness sometimes appears. Density is determined by the quantity of material used to fill a certain volume and the process used to blow the insulation. However, for an assumed density, the thicker layer is always a bit compacted.

The calculations previously presented and discussed were performed including this small variation in density. The results are plotted in Fig. 5.8 and reported in Table 5.4. Here, it appears that ΔT_{cr1} , ΔT_{cr2} , and ΔT_{cr3} are very similar.

Some experiments performed on loose-fill insulation [3] showed that the critical temperature differences for a 21.6-cm (8.5-in.)-thick layer and a 43.2-cm (17-in.)-thick layer were nearly the same. One test recently performed at the LSCS in the ATM (full of loose-fill insulation) showed the same result [26].

For the LSCS test, the hot temperature in the metering chamber was fixed so that the mean temperature within the insulation changed with the temperature difference. In ref. [3], the mean temperature was fixed, and both hot and cold temperatures changed. One explanation for this phenomenon is that a vertical gradient of permeability may exist within the insulation.

The last objective was to study the coupling effect of the mean temperature and a vertical permeability difference in the critical ΔT .

5.2.3 Gradient of Permeability Within the Insulation

When loose-fill insulation is blown to form a thick layer, insulation in the bottom of the layer is compacted under the weight of the insulation above, so density through the layer may vary from bottom to top.

Some tests were performed by Yarbrough on one type of loose-fill fiberglass insulation to characterize the ability of the material to be compacted under a certain weight [27]. This information was used to estimate a density variation, hence, a variation in permeability.

Fig. 5.8. Thermal resistance vs temperature difference for three thicknesses [$E=20.95$, 31.75 , and 39.40 cm (8.25 , 12.5 , and 15.5 in.)] and their respective densities [7.7 , 8.0 , 8.2 kg/m³ (0.480 , 0.500 , 0.515 lb/ft³)] the effect of joists at various insulation thicknesses.

Table 5.4. Open configuration for three thicknesses and a small density variation: Ra^* , Nu^* , ΔT , and R-values of R-19, R-30, and R-38

E (in.)	Density (lb/ft ³)	R-value (h · ft ² · °F)	Permeability (m ²)
8.25	0.480	19.0	$3.85 \cdot 10^{-8}$
12.50	0.500	30.0	$3.42 \cdot 10^{-8}$
15.50	0.515	38.0	$3.28 \cdot 10^{-8}$

E (in.)	Ra^*	Nu^*	DT (°F)	RO (T _■)	R (T _■)
8.25	0.0	1.000	0	18.69	18.69
	8.5	1.001	38	19.79	19.77
	15.0	1.002	59	20.42	20.37
	20.0	1.004	73	20.86	20.77
	27.0	1.055	90	21.40	20.28
	32.0	1.220	101	21.75	17.82
	40.0	1.427	116	22.25	15.59
12.50	0.0	1.000	0	29.75	29.75
	8.5	1.000	28	31.02	31.02
	15.0	1.000	45	31.82	31.82
	20.0	1.001	56	32.35	32.31
	27.0	1.022	70	33.04	32.32
	32.0	1.231	80	33.54	27.24
	40.0	1.683	93	34.20	20.32
15.50	0.0	1.000	0	37.69	37.69
	8.5	1.000	24	39.07	39.07
	15.0	1.000	38	39.90	39.90
	20.0	1.000	48	40.50	40.50
	27.0	1.002	61	41.30	41.21
	32.0	1.010	69	41.80	41.38
	40.0	1.304	81	42.56	32.63
15.50	50.0	1.867	95	43.46	23.27

Using these characteristics, a calculation was performed with the model on 40.6-cm (16-in.)-thick insulation divided into four layers with different permeabilities as follows:

$$0.0 \leq z < 0.25, K(z) = K_0 / 1.55 \text{ .}$$

$$0.25 \leq z < 0.50, K(z) = K_0 / 1.35 \text{ .}$$

$$0.50 \leq z < 0.75, K(z) = K_0 / 1.18 \text{ .}$$

$$0.75 \leq z < 1.0, K(z) = K_0 \text{ .}$$

Here, the top layer should have the permeability K_0 of the uncompacted material.

Considering two thicknesses of insulation, $E_1 = 20.3$ cm (8 in.) and $E_2 = 40.6$ cm (16 in.), a comparison of the three following configurations is presented in Table 5.5:

$$\text{" } \blacklozenge \text{" } E = E_1, K = K_0 \text{ .}$$

$$\text{" } \blacksquare \text{" } E = E_2, K = K_0 \text{ .}$$

$$\text{" } + \text{" } E = E_2, K = K(z) \text{ .}$$

The results of the calculations for these cases are presented in Fig. 5.9 (Nusselt number versus Rayleigh number). This graph shows the different influences of the joists at the onset of convection for the single and the double layer, previously mentioned. For $E = E_2$, the critical Rayleigh number is near the theoretical 27.1. For the configuration with the gradient of permeability, Ra_{cr} is close to 40.

From the preceding values of Nu' and Ra^* , R-values are calculated and presented in Fig. 5.10. A comparison between " $\blacklozenge$ " and " $\blacksquare$ " shows the influence of the mean temperature on ΔT_{cr} .

Configuration "+" shows the combination of mean temperature and a gradient of permeability within the insulation. The variation of the R-value for 1 and 3 clearly shows the same critical temperature difference for the single and double layers.

Coincidentally, the critical temperature differences are exactly the same for these configurations. The conclusion of this calculation is that a permeability gradient may exist within the insulation and have a positive effect against convection since the permeability gradient delays the start of convection in thick layers.

Table 5.5. Comparison of the evolution of thermal resistance over temperature difference for R-19 and R-38 with the same permeability and for R-38 with a gradient of permeability within the insulation

E (in.)	R-value ($\text{h} \cdot \text{ft}^2 \cdot ^\circ\text{F}$)	Permeability (ft^2)
8.0	19.0	$6.915 \cdot 10^{-7}$
16.0	38.0	$6.915 \cdot 10^{-7}$
16.0	38.0	K(z)

E (in.)	Ra*	Nu*	DT ($^\circ\text{F}$)	RO (T_{m})	R (T_{m})
8.0	0.0	1.000	0	18.68	18.68
	8.5	1.001	24	19.36	19.34
	15.0	1.002	39	19.80	19.76
	20.0	1.004	50	20.13	20.04
	27.0	1.055	63	21.53	19.45
	32.0	1.220	71	20.77	17.02
	40.0	1.427	83	21.15	14.82
	50.0	1.747	97	21.60	12.36
16.0	0.0	1.000	0	37.72	37.72
	8.5	1.000	13	38.46	38.46
	15.0	1.000	21	38.92	38.92
	20.0	1.000	28	39.33	39.33
	27.0	1.002	36	39.81	39.73
	32.0	1.010	41	40.11	39.71
	40.0	1.304	49	40.59	31.13
	50.0	1.867	59	41.21	22.07
16.0	0.0	1.000	0	37.72	37.72
	8.5	1.000	13	38.46	38.46
	15.0	1.000	21	38.92	38.92
	20.0	1.000	28	39.33	39.33
	27.0	1.002	36	39.81	39.73
	32.0	1.002	41	40.11	40.03
	40.0	1.009	49	40.59	40.22
	45.0	1.096	54	40.90	37.32
	50.0	1.297	59	41.21	31.77
	60.0	1.698	67	41.70	24.56
	70.0	2.223	79	42.46	19.10

Fig. 5.9. Nusselt number vs Rayleigh number: comparison of Nu^* for $E = 16$ in. with constant permeability and with a gradient of permeability within the insulation.

Fig. 5.10. Thermal resistance vs temperature difference: comparison of R-value for $E = 16$ in. with constant permeability and with a gradient of permeability within the insulation.

5.3 THE ATTIC CONFIGURATION

One objective of this work was to find boundary conditions to apply in the numerical analysis that would reflect the in-service configuration. For this purpose, the thermal resistances calculated in five systems with wood joists presented previously were compared with data from the ATM fitted with one type of loose-fill fiberglass insulation [7] (specimen 2).

This material was installed in a 24-cm (9.5-in)-thick layer with a density of 6.4 kg/m^3 (0.40 lb/ft^3), and the nominal R-value was estimated to be $3.3 \text{ m}^2 \text{ K/W}$ ($19 \text{ h} \cdot \text{ft}^2 \cdot ^\circ\text{F/Btu}$). To compare the model with the data, the nominal R-value is taken as the LSCS value at the lowest temperature difference [$R = 3.0 \text{ m}^2 \text{ K/W}$ ($17.0 \text{ hr} \cdot \text{ft}^2 \cdot ^\circ\text{F/Btu}$)].

The experimental thermal resistance was obtained for six values of outdoor temperature. The temperature difference across the insulation varied from 11°C (20°F) to 41.6°C (75°F). The estimated error on the measured R-value was $\pm 5\%$. These results are presented in Fig. 5.11 with the predicted R-value for the following three boundary conditions on the top surface of the insulation:

- closed configuration with the top isothermal plate in contact with the layer of insulation (+);
- open configuration with an isothermal temperature on the top surface of the insulation (■); and
- open configuration with a variable temperature on the top surface of the insulation (▲).

Only two tests were conducted for temperature differences lower than the critical ΔT [7]. The thermal resistance obtained under these conditions was smaller than the R-19 expected:

$$\Delta T = 11.5^\circ\text{C} (20.7^\circ\text{F}), R = 3.0 \text{ m}^2 \text{ K/W} (17 \text{ h} \cdot \text{ft}^2 \cdot ^\circ\text{F/Btu});$$

$$\Delta T = 18.0^\circ\text{C} (32.6^\circ\text{F}), R = 3.1 \text{ m}^2 \text{ K/W} (17.7 \text{ h} \cdot \text{ft}^2 \cdot ^\circ\text{F/Btu}).$$

Fig. 5.11. Thermal resistance vs temperature difference: model predictions and data from the attic test module used in the large-scale climate simulator.

The difference between the expected nominal R-value and the R-value obtained in the experiments may be caused by variability of material, type of blowing machines, etc. Also, the predicted R-value for the closed configuration presented in Fig. 5.11 does not reflect the in situ thermal performance of the tested material.

The shape of the experimental curve seems to agree with the predicted R-value for the open configuration, considering that an uncertainty exists in the permeability and the "apparent" thermal conductivity of the insulation. However, to determine the critical temperature difference for the start of convection, the isothermal boundary condition should be used rather than the variable top temperature. This is so because, before convection starts, the top surface should be nearly isothermal. The nonuniform top temperature is the result of convection; imposing this condition may then be more realistic when convection is very active within the insulation, which explains the hexagonal patterns observed in the experiment [7]; but this condition artificially produces convection in a range of temperature difference in which the transfer should occur only by conduction.

The calculations performed for configurations 4 and 5 (see Table 5.2), with a constant flux imposed on the bottom of the insulation, overestimate the heat flux through the insulation. The bottom temperature of the insulation is not directly maintained at a constant temperature, as explained in Sect. 2. However, the materials used to build the ceiling very often have a high conductivity compared with the insulation (in this example, gypsum board), so they can be assumed to be isothermal.

The number that characterizes exchanges between an outside fluid (air in the metering chamber) and a solid (ceiling = gypsum board + insulation) is called the Biot number (Bi):

$$Bi = \frac{h \cdot L}{k_s} \quad (5.8)$$

The symbol h represents the exchange coefficient introduced in Sect. 2, L represents a characteristic dimension of the solid, and k_s represents the thermal conductivity of the solid.

The Biot number suggests the type of boundary condition to apply at the surface of the solid that is in contact with the fluid, so that:

- if Bi is small ($Bi < 0.1$), the boundary condition is a constant flux at the surface; and
- if Bi is large, the boundary condition is similar to an isothermal surface.

In the numerical analyses, these two types of boundary condition are represented by $Bi \rightarrow 0$ and $Bi \rightarrow \infty$.

For the attic problem, Bi can be calculated at the bottom surface of the gypsum board (metering chamber side) or at the bottom of the insulation. Using the notation presented in Fig. 2.3, these numbers can be calculated as follows:

- At the bottom surface of the gypsum board (metering chamber side),

$$Bi = (R_1 + R_2)/R_0 = 21 \text{ .}$$

- On the top surface of the gypsum board (insulation side),

$$Bi = R_2 / (R_0 + R_1) = 11 \text{ .}$$

This calculation shows that the real boundary condition is between imposed constant flux and imposed constant temperature. However, the isothermal bottom temperature is a good approximation and gives satisfactory results.

A graphic program was used to represent the velocity (V) at each point of the grid under the five previous configurations. A comparison of the homogeneous system and the configuration with joists is presented. The isotherms also are represented under the same conditions. These graphs are presented in Fig(s). A.1–A.10 in Appendix A.

The velocity graphs show the motion already present in the system with joists for a Rayleigh number smaller than the one predicted by the theory for a homogeneous medium (without joists).

By looking at the isothermal lines, one can see the development of the convective cells and the increase of the "effective" total thermal conductivity when motion is present within the insulation.

6. GENERAL CONCLUSIONS AND PERSPECTIVES

6.1 CONCLUSIONS

Global heat transfer through a horizontal porous layer heated from below has been predicted under different boundary conditions with a two-dimensional convective code. Using the thermal conductivity and air permeability of one type of loose-fill fiberglass insulation, thermal resistance has been deduced from these calculations.

When the bottom and top of the insulation are in contact with two isothermal plates, the variation of the R-value in a closed configuration did not show evidence of convection under realistic temperature differences. This configuration should model the small-scale apparatus currently used to test the performance of insulation. Numerical analysis confirms that this apparatus is not a good indicator of the in-service thermal resistance of all types of insulation within which natural convection may occur and be a significant mode of heat transfer.

The fact that the small-scale heat meter does not appear to be sensitive to natural convection can be explained mostly by the difference in boundary conditions. In a closed configuration, the insulation is confined between two isothermal plates; in the attic, the top surface of the insulation is opened to the air space and, because of the coupling mechanism between heat transfer in the air space and through the insulation, a lower temperature difference across the insulation is required to start convection.

The configuration with an open and isothermal top temperature appeared to be a good approximation of the real system. It can be used to determine the critical temperature difference for which convection will start within insulation. For given permeability and thermal conductivity, the predicted R-value agrees with measured values.

However, a better approximation would involve assuming a pressure field at the interface between the air and the insulation and a more realistic variable top temperature, both deduced from the experiments. In this way, the dynamic and thermal coupling phenomena will be totally characterized.

Numerical analysis confirmed the phenomena already observed in experiments, such as a decrease in the performance of loose-fill fiberglass insulation when natural

convection is occurring inside the insulation under realistic winter conditions and for permeabilities typical of some existing insulation.

Small, rectangular, nonpermeable elements with a higher conductivity than the surrounding medium have been included in the porous domain to model the effect of the wood joists usually present within the insulation. Calculations in this configuration showed a decrease in the critical temperature difference for the start of convection because of the presence of joists.

Some complementary calculations run for different insulation thicknesses revealed that the effect of the joists decreases with an increase of insulation thickness and may disappear totally. In particular, for one type of loose-fill insulation, it has been shown that no evidence exists of any effect of the joists for a 16-in.-thick layer, which corresponds to a thermal resistance of R-38.

To characterize the thermal performance of loose-fill insulation, air permeability and "apparent" thermal conductivity appeared to be the key parameters. Any changes in permeability modify not only the critical temperature difference but also the function that characterizes the variation of thermal resistance with temperature difference.

A major uncertainty seems to remain in the determination of air permeability. Numerical analyses showed that, to correctly predict convection effects, the in-service value of this parameter must be determined.

The main difficulty is to measure the permeability from a sample of insulation that has the same characteristics (e.g., density, thickness, degree of homogeneity) as the insulation installed in the attic.

Some experiments conducted in the ATM on a 9.5-in.-thick layer and an 18-in.-thick layer of the same type of insulation blown with the same machine showed that the critical temperature difference was nearly the same for both. In theory, if the single layer and the double layer have the same permeability (i.e., density), convection should start earlier in the thicker layer. Observation of the experiment leads one to conclude that a gradient of permeability (i.e., density) exists within the insulation.

A calculation was performed with a vertical gradient of permeability across a layer of 40.6-cm (16-in.)-thick insulation. The permeability on the top was K_0 , and the permeability on the bottom was $1.55 K_0$. The variation of the thermal resistance in this configuration was compared with the evolution of thermal resistance for a 20.3-cm (8 in.)-thick layer with a permeability of K_0 . This test confirmed that, in the presence of a

gradient of permeability in the thicker layer, convection is delayed and may occur for the same critical temperature difference as the single layer.

Because, for thick layers, insulation is compressed by its own weight, a variable permeability must be considered in the calculation of the critical temperature difference. However, this significant phenomenon, already observed experimentally and with numerical analysis, cannot be transported to insulation of another type than that already tested without experimental validation, because the structure of the loose-fill insulation varies by manufacturer and the insulation may be more or less compacted under the same weight. This phenomenon may be amplified in some types of loose-fill insulation and may be insignificant in others.

6.2 PERSPECTIVES

It is impractical to use a large-scale test apparatus like the attic test module as a standard method for testing the performance of loose-fill insulation.

To approach in-service conditions, the small-scale apparatus may be modified. In particular, if the open "infinite" air space above the insulation cannot be achieved, this boundary condition can be approached by introducing an air layer between the top surface of the insulation and the isothermal plate. If this introduced air layer is thick enough to allow natural convection to occur, this configuration can be a good first approximation of the real boundary condition in the attic. This system also can be used to characterize the coupling mechanism at the interface by using various types of surfaces (permeable or impermeable) between the air and the insulation. Experimentation with an air layer on top of the insulation already has been conducted with loose-fill fiberglass insulation in guarded hot boxes [4].

The validated model could be used along with the ASTM test methods, leading to a better understanding of the performance of loose-fill insulation in attics.

Meanwhile, as discussed previously, other critical input besides the boundary conditions to apply in the numerical analyses must be known precisely. For a parameter such as air permeability, a large uncertainty remains when determining a value for in situ configuration. A definite need exists to develop a tester that would provide reliable and repetitive values for this key parameter.

Combining laboratory measurements of air permeability and thermal conductivity would provide the necessary parameters for predicting the performance of insulation in an attic. Model predictions then could be compared with experimental results obtained for different insulations tested in the attic test module in the large-scale climate simulator. These complementary numerical and experimental research works should help manufacturers better understand the behavior of existing insulating material and develop future products.

REFERENCES

1. D. Fournier and S. Klarsfeld, "Utilisation d'un Appareil Orientable à Plaque Chaude Gardée pour la Mise en Evidence du Transfert de Chaleur par Convection Naturelle en Milieu Poreux dans des Conditions Simulées," pp. 53-61 in *Proceedings of the XIIIth International Congress of Refrigeration*, Vol. 2, ed. W. T. Pentzer et al., Washington, 1971.
2. C. G. Bankvall, "Mechanisms of Heat Transfer in Permeable Insulation and Their Investigation in Special Guarded Hot Plate," pp. 34-38 in *Heat Transmission Measurements in Thermal Insulation*, ASTM STP 554, American Society for Testing and Material, Philadelphia, 1975.
3. K. E. Wilkes and J. L. Rucker, "Thermal Performance of Residential Attic Insulation," pp. 263-277 in *Energy and Buildings*, Vol. 5, 1983.
4. C. Langlais, E. Arquis, and D. J. McCaa, "A Theoretical and Experimental Study of Convective Effects in Loose Fill Thermal Insulation," pp. 290-318 in *Insulation Material Testing and Applications*, ASTM STP 1030, American Society for Testing and Material, Philadelphia, 1990.
5. A. Silberstein, C. Langlais, and E. Arquis, "Natural Convection in Light Fibrous Insulating Materials with Permeable Interfaces: Onset Criteria and Its Effect on the Thermal Performances of the Product," *J. Therm. Insul.* **14**, 22-42 (July 1990).
6. W. R. Huntley, *Design Description of the Large Scale Climate Simulator*, ORNL/TM-10675, Oak Ridge National Laboratory, Oak Ridge, Tenn., 1989.
7. K. E. Wilkes, R. L. Wendt, A. Delmas, and P. W. Childs, "Attic Testing at the Roof Research Center - Initial Results, ORNL/CON-313, Oak Ridge National Laboratory, Oak Ridge, Tenn., 1991.
8. D. A. Nield, "Onset of Thermohaline Convection in Porous Medium," *Water Resour. Res.* **4**, 553-560 (1968).
9. J. P. Caltagirone, *Instabilités Thermoconvectives en Milieu Poreux*, Thèse de Doctorat d'Etat, Université Pierre et Marie Curie Paris VI, France, 1976.
10. T. W. Tong and E. Subramanian, "Natural Convection in Rectangular Enclosures Partially Filled with a Porous Medium," pp. 331-338 in *Proceedings of the ASME-JSME Thermal Engineering Joint Conference*, ed. Yasuo Mori and Wen-Jei Yang, Vol. 1, American Society of Mechanical Engineers, N.Y., 1983.

11. C. Beckermann, S. Ramadhyani, and R. Viskanta, "Natural Convection Flow and Heat Transfer Between a Fluid Layer and a Porous Layer Inside a Rectangular Enclosure," *ASME J. Heat Transfer* **109**, 363-370 (1987).
12. E. Arqis and J. P. Caltagirone, "Interacting Convection Between Fluid and Open Porous Layer," presented at the ASME Winter Annual Meeting, Boston, December 13-18, 1987.
13. J. G. N. Lecompte, "The Influence of Natural Convection in an Insulated Cavity on the Thermal Performance of a Wall," pp. 397-420 in *Insulation Material Testing and Applications*, ASTM STP 1030, American Society for Testing and Material, Philadelphia, 1990.
14. *ASHRAE Handbook*, American Society of Heating, Refrigerating and Air-Conditioning Engineers, Atlanta, 1989.
15. Heng-Yau Yeh, *Radiative Properties and Heat Transfer Analysis of Fibrous Insulations*, Ph.D. dissertation, The University of Mississippi, 1986.
16. J. D. Verschoor, P. Greebler, and N. J. Mainville, "Heat Transfer by Gas Conduction and Radiation in Fibrous Insulation," *ASME Trans.* **74**, 961-968 (1952).
17. C. Bankvall, "Heat Transfer in Fibrous Materials," *J. Test. Eval.* **1**(3), 235-243 (May 1973).
18. C. L. Tien and K. Vafai, "Statistical Upper and Lower Bounds of Effective Thermal Conductivity of Fibrous Insulation," presented at the Second AIAA/ASME Thermophysics and Heat Transfer Conference, AIAA-78-874, Palo Alto, Calif., May 24-26, 1978.
19. G. Lauriat, "A Numerical Study of a Thermal Insulation Enclosure: Influence of the Radiative Transfer," pp. 63-71 in *Natural Convection in Enclosures*, ASME HTD, Vol. 8, American Society for Testing and Material, Philadelphia, 1980.
20. T. W. Tong, R. C. Birkebak, and I. E. Enoch, "Thermal Radiation Convection and Conduction in Porous Media Contained in Vertical Enclosures," *ASME J. Heat Transfer* **105**, 414-418 (1983).

21. C. Bouallou, *Modélisation Bidimensionnelle des Transferts Couplés Rayonnement-Convection Naturelle dans les Milieux Semi-transparents*, Thèse de Doctorat, INSA de Lyon, France, 1989.
22. M. Combarnous and S. Bories, "Modélisation de la convection naturelle au sein d'une couche poreuse horizontale à l'aide d'un coefficient de transfert solide-fluide," *Int. J. Heat Mass Transfer* 17, 505-515 (1974).
23. J. L. Beck, "Convection in a Box of Porous Material Saturated with Fluid," *Phys. Fluids* 15(8), 1377-1383 (1972).
24. M. Degenne, J. Boulant, and S. Klarsfeld, "Mesures des Caractéristiques Thermiques des Isolants à Basses Températures à l'Aide d'Une Méthode Fluxmétrique," presented at the XVI^{ième} Congrès International du Froid, Paris, 1983.
25. J. Beckwith, *Air Permeability*, internal report, CertainTeed Corporation, Insulation Group, 1991.
26. K. E. Wilkes, *Attic Testing at the Roof Research Center: Initial Results*, ORNL/CON-313, to be published at Oak Ridge National Laboratory, Oak Ridge, Tenn., 1991.
27. D. Yarbrough, *Reduction in the Thermal Resistance (R-value) of Loose-Fill Insulation and Fiberglass Batts Due to Compression*, ORNL/Sub-7715/2, Oak Ridge National Laboratory, Oak Ridge, Tenn., 1991.

Appendix A
VELOCITIES AND ISOTHERMS IN THE FIVE CONFIGURATIONS

Fig. A.1. Air velocities within the insulation: the closed configuration for $Ra^* = 40$ and 48—comparison of velocities with and without joists.

Fig. A.2. Isotherms within the insulation: the closed configuration for $Ra^* = 40$ and 48—comparison of isotherms with and without joists.

Fig. A.3. The open configuration: velocities and isotherms in the whole medium without joists for $Ra^* = 27$ —isothermal boundaries.

Fig. A.4. The open configuration: velocities and isotherms in the whole medium without joists for $Ra^* = 48$ —isothermal boundaries.

Fig. A.5. Air velocities within the insulation: the open configuration for $Ra^* = 27$ and 48—iso-thermal boundaries; comparison of velocities with and without joists.

ORNL-DWG 92-4588

Fig. A.6. Isotherms within the insulation: the open configuration for $Ra^* = 27$ and 48—isothermal boundaries; comparison of isotherms with and without joists.

VELOCITIES, NO JOIST

 $Ra^* - 27$

VELOCITIES BETWEEN 2-JOISTS

 $Ra^* - 27$

VELOCITIES, NO JOIST

 $Ra^* - 48$

VELOCITIES BETWEEN 2-JOISTS

 $Ra^* - 48$

Fig. A.7. Air velocities within the insulation: the open configuration for $Ra^* = 27$ and 48—iso-thermal bottom boundary, non-uniform temperature on top; comparison of velocities with and without joists.

Fig. A.8. Isotherms within the insulation: the open configuration for $Ra^* = 27$ and 48—isothermal bottom boundary, non-uniform temperature on top; comparison of isotherms with and without joists.

ISOTHERMS

 $Ra^* - 8$

ISOTHERMS

 $Ra^* - 8$

ISOTHERMS

 $Ra^* - 27$

ISOTHERMS

 $Ra^* - 27$

ISOTHERMS

 $Ra^* - 48$

ISOTHERMS

 $Ra^* - 48$

Fig. A.9. Isotherms within the insulation: the open configuration for $Ra^* = 8, 27$, and 48—imposed uniform heat flux on bottom and isothermal top.

ISOTHERMS
 $Ra^* - 08$

ISOTHERMS
 $Ra^* - 08$

ISOTHERMS
 $Ra^* - 27$

ISOTHERMS
 $Ra^* - 27$

ISOTHERMS
 $Ra^* - 48$

ISOTHERMS
 $Ra^* - 48$

Fig. A.10. Isotherms within the insulation: the open configuration for $Ra^* = 8$, 27, and 48—imposed uniform heat flux on bottom and non-uniform temperature on top.

Appendix B
CONVECTIVE MOTION IN AN INCLINED POROUS LAYER

Fig. B.1. Diagram of the principal convective motions observed by S. Bories and M. Combarous in an inclined porous layer with large aspect ratio ($A = 13$; $B = 9$).*

*M. Combarous and S. Bories, "Hydrothermal Convection in Saturated Porous Media," pp. 231-307 in *Advances in Hydrosience*, Vol. 10, Academic Press, N.Y., 1975.

INTERNAL DISTRIBUTION

1-10.	A. A. Delmas	33.	M. B. Gettings
11-20.	K. E. Wilkes	34.	J. O. Kolb
21.	J. E. Christian	35.	T. G. Kollie
22.	W. R. Mixon	36.	M. A. Kuliasha
23.	G. E. Courville	37.	P. M. Love
24.	R. B. Shelton	38.	G. M. Ludtka
25.	C. L. Brown	39.	D. L. McElroy
26.	R. S. Carlsmith	40.	H. A. McLain
27.	K. W. Childs	41.	A. Zaltash
28.	P. W. Childs	42.	ORNL Patent Office
29.	J. W. Cooke	43.	Central Research Library
30.	F. A. Creswick	44.	Document Reference Section
31.	A. O. Desjarlais	45-47.	Laboratory Records
32.	S. K. Fischer	48.	Laboratory Records - RC

EXTERNAL DISTRIBUTION

49. Henry Amistadi, Scientific Computing, RR2, Box 2191C, Brunswick, ME 04011
50. Terry Applegate, Applegate Insulation Mfg., P.O. Box 292, Okemos, MI 48805
51. Erv Bales, New Jersey Institute of Technology, Newark, NJ 07102
52. James Beck, Engineering Bldg., A-231, Dept. of Mechanical Engineering, Michigan State University, East Lansing, MI 48824
53. Bruce E. Bolton, 184 Pinecrest Drive, Pittsburgh, PA 15237
54. Mark Bomberg, National Research Council Canada, Building Performance Section, Ottawa, Ontario, Canada K1A 0R6
55. J. Boone, Wichita Insulation, 12727 E. Kellogg, Wichita, KS 67207
56. Jeffrey R. Brisley, Knauf Fiberglass, 240 Elizabeth Street, Shelbyville, IN 46176
57. Barton W. Bromley, American Rockwool, Inc., P.O. Box 880, Spring Hope, NC 27882
58. William C. Brown, National Research Council Canada, Bldg. M-24, Montreal Road, Ottawa, Ontario, Canada K1A 0R6
59. Bruce G. Buchanan, Computer Science Dept., University of Pittsburgh, 206 Mineral Industries Building, Pittsburgh, PA 15260
60. E. F. Cusick, Jr., Rock Wool Mfg. Co., P.O. Box 506, Leeds, AL 35094
61. W. M. Edmunds, Owens-Corning Fiberglas, 2790 Columbus Road, Bldg. 72-1, Granville, OH 43023-1200
62. P. W. Fairey, Florida Solar Energy Center, 300 State Road 401, Cape Canaveral, FL 32920

63. P. R. Fisette, Room 126, Holdsworth Hall, University of Massachusetts, Amherst, MA 01003
64. Robert Gardner, Knauf Fiber Glass, 240 Elizabeth Street, Shelbyville, IN 46176
65. L. Glicksman, Mass. Institute of Technology, Rm. 4-209, Cambridge, MA 02139
66. Frank C. Gorham, Roofing Services, Inc., 6106 Roxbury Avenue, Springfield, VA 22152-1621
67. Brent Griffith, Lawrence Berkeley Laboratory, 90-3111, Berkeley, CA 94720
68. David Harris, National Institute of Building Sciences, 1201 L Street, N.W., Suite 400, Washington, D.C. 20005
69. B. F. Harshaw, Central Fiber Corp., P.O. Box 749, Fiberlane Road, Wellsville, KS 66092
70. Donna Hawkins, Dept. of Energy, CE-40, FORSTL, 1000 Independence Ave., S.W., Washington, D.C. 20585
71. Phil Hendrickson, Dow Chemical, USA, P.O. Box 515, Granville, OH 43023
72. Allan Hirsch, Midwest Research Institute, 5109 Leesburg Pike, Suite 414, Falls Church, VA 22041
73. Bion Howard, Alliance to Save Energy, 1725 K Street, N.W., Suite 509, Washington, D.C. 20006-1401
74. Helen M. Ingram, Udall Center for Studies in Public Policy, The University of Arizona, 803/811 East First Street, Tucson, AZ 85719
75. Julian L. Ius, HQ AFCESA/ENC, Stop 21, Tyndall AFB, FL 32403-6001
76. Walter Kromer, Rensselaer Polytechnic Institute, Center for Arch. Research, Greene 103, 110 8th Street, Troy, NY 12180-3590
77. M. B. Lacher, Certainteed Corp., P.O. Box 860, Valley Forge, PA 19482
78. Gene Leger, Leger Designs, 256 Middle Branch Road, New Boston, NH 03070
79. Dick Leuthold, Advanced Fiber Technology, P.O. Box 5016, Bucyrus, OH 44820
80. Dan Ley, Cellulose Industry Standards Enforcement Program, 1315 Talbott Tower, Dayton, OH 45402
81. Fran W. Lichtenberg, The Society of the Plastics Industry, Polyurethane Division, 355 Lexington Avenue, Suite 1100, New York, NY 10017
82. M. D. Lyberg, SIB, P.O. Box 785, Gavle, Sweden, S-80129
83. Calvin D. MacCracken, Calmac Manufacturing Corporation, 101 West Sheffield Avenue, P.O. Box 710, Englewood, NJ 07631
84. Merle F. McBride, Owens-Corning Fiberglas, 2790 Columbus Road, Granville, OH 43023-1200
- 85-87. David McCaa, CertainTeed, 1400 Union Meeting Road, Blue Bell, PA 19422
88. E. Gerry Miller, Jim Walter Research Corp., 10301 9th Street, N., St. Petersburg, FL 33716
89. Thomas J. Miller, Box 435, Delphos, OH 45833
90. M. Millspaugh, Reflectix, Inc., P.O. Box 108, Markleville, IN 46056
91. John R. Mumaw, Owens Corning Fiberglas, 2790 Columbus Road, Granville, OH 43023-1200
92. Bruce D. Nelson, Minn. Dept. of Public Service, 150 E. Kellogg Blvd, #790, St. Paul, MN 55101
93. Ned Nisson, Energy Design Update, P.O. Box 1709, Ansonia Station, New York, NY 10023
94. T. J. Ohlemiller, National Institute of Standards and Technology, Bldg. 226, Gaithersburg, MD 20899
95. Frank J. Powell, 12218 Cattail Lane, Jacksonville, FL 32223
- 96-97. Richard Ray, Manville Corp., P.O. Box 625005, Littleton, CO 80162-5005

98. Paul Remmele, Morton Buildings, Inc., 252 W. Adams, P.O. Box 399, Morton, IL 61550-0399
99. Paul Robinson, 10 Twin Dolphin Drive, Suite B230, Redwood City, CA 94065
100. Walter Rossiter, National Institute of Standards and Technology, Building 226, Gaithersburg, MD 20899
101. Peter Scofield, Department of Energy, CE-421, FORSTL, 1000 Independence Ave., S.W., Washington, D.C. 20585
102. Max Sherman, Jim Walter Corporation, 6723 14th Avenue, North, St. Petersburg, FL 33710-5405
103. Jacqueline B. Shrago, Office of Technology Transfer, 405 Kirkland Hall, Vanderbilt University, Nashville, TN 37240
104. A. T. Skinner, Roofing Service Assoc., Inc., 6500 Papermill Road, #209, Knoxville, TN 37919
105. David R. Smith, 853.07, National Institute of Standards and Technology, 325 Broadway, Boulder, CO 80303-3328
106. S. E. Smith, Physical Sciences Group, 48 Chester Street, Somerville, MA 02144
107. Tom Smith, National Roofing Contractors Assoc., O'Hare International Center, 10255 W. Higgins Road, Suite 600, Rosemont, IL 60018-5607
108. E. E. Stansbury, 5800 Woodburn Drive, Knoxville, TN 37919
109. Raymond L. Sterling, Underground Space Center, 500 Pillsbury Drive, S.E., Minneapolis, MN 55455
110. M. Stranathan, National Insulation, 3601 Calvert, Lincoln, NE 68506
111. Stephen S. Szoke, National Concrete Masonry Assoc., 2302 Horse Pen Road, Herndon, VA 22071-3406
112. S. Tewes, Small Homes Council, One East Saint Mary's Road, Champaign, IL 61820
113. Timothy Tong, Dept. of Mech. & Aerospace Engr., Arizona State University, Tempe, AZ 85287
114. Adrian Tuluca, Steven Winter Associates, Inc., 50 Washington Street, Norwalk, CT 06854
115. R. P. Tye, 292 Jerusalem Road, Cohasset, MA 02025
116. Carl R. Vander Linden, Vander Linden & Assoc., 5 Brassie Way, Littleton, CO 80123
117. Martha Van Geem, Construction Technology Labs, Portland Cement Assoc., 5420 Old Orchard Road, Skokie, IL 60077
118. Martin Williams, Department of Economics, Northern Illinois University, DeKalb, IL 60115
119. David W. Yarbrough, Tennessee Technological University, Box 5013, Cookeville, TN 38505
120. Robert R. Zarr, National Institute of Standards and Technology, Bldg. 226, B320, Gaithersburg, MD 10899
121. Office of the Assistant Manager for Energy Research and Development, DOE-ORO, P.O. Box 2001, Oak Ridge, TN 37831-8600
- 121-161. BTE SM Library, Oak Ridge National Laboratory, P.O. Box 2008, Bldg. 3114, Oak Ridge, TN 37831-6070
- 162-171. OSTI, U.S. Dept. of Energy, P.O. Box 62, Oak Ridge, TN 37831

END

**DATE
FILMED**

7 / 13 / 92