Progress Report

DOE/ER/45332--T1

DE92 012572

**Continuation Application for
'PREPARATION AND CHARACTERIZATION OF
SUPERLATTICES'**

**RESEARCH GRANT
DE-FG03-90ER-45332**

(3/15/91 - 3/14/92)

Principal Investigator: Professor Ivan K. Schuller

**Institution: Physics Department-0319
University of California, San Diego
La Jolla, California 92093-0319
Phone: (619) 534-2540
FAX: (619) 534-0173**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

A. SUMMARY OF SCIENTIFIC PROGRESS

During this last year we were involved in a number of studies geared towards understanding the relationship between interfacial disorder and X-ray diffraction from superlattices. In addition, we have performed a number of physical properties studies in order to relate structure to physical properties. These studies include magnetism and superconducting studies in a variety of different thin film systems. A major development was the implementation of a structural refinement program capable of determining the important structural parameters in superlattices and thin films. This program is being supplied to many research groups for the study of related problems.

We are currently devoted to detailed, comparative studies of magnetic samples prepared by Molecular Beam Epitaxy and sputtering. The unique facilities available to us not only allow preparing samples by the two different methods but also are capable of determining interfacial structure using *in-situ* characterization techniques such as Reflection High Energy Electron Diffraction (RHEED), Low Energy Electron Diffraction (LEED) and Auger Electron Spectroscopy (AES). We have developed a data acquisition system capable of acquiring electron diffraction in real time during growth.

Part of the work done here is a good example of a collaboration between a University (UCSD), a national lab (ANL) and industrial organizations (Amoco, IBM).

1. STRUCTURAL REFINEMENT

The structure of thin films is the key determining factor in their physical properties. A large number of examples exist in which changes in structural parameters such as grain sizes, interfacial roughness, interdiffusion, changes in lattice parameters, etc. may strongly modify and change physical properties. Examples of these types include changes in the Curie temperature of magnetic thin films, variations of the transport properties and modifications of the superconducting properties. Because of this, it is important to determine with high accuracy crystallographic and chemical parameters in order to relate these with physical properties. Thin films and superlattices are usually prepared by vapor phase deposition techniques and are not in thermodynamic equilibrium. Therefore, the structure is strongly dependent on growth conditions.

X-ray diffraction is a technique that is well suited for studying the structure of thin films and superlattices. It is non-destructive and can provide structural information on the atomic scale. Because the scattered x-ray intensity is measured, the phase information is lost and it is impossible to directly convert the intensities to obtain the structure. Modeling of the superlattice is required to compare the calculated intensity of the modeled superlattice with the measured intensity. By fitting the measured intensity profiles with model calculations, it is possible to obtain the structure. This type of structural characterization is commonly used in x-ray and neutron diffraction from bulk powder crystals using the Rietveld refinement procedure. In Rietveld refinement, the structure of a single unit cell is modeled and the relative intensity of the diffraction peaks is determined from the structure factor of the unit cell. The difference with the present refinement technique is that here the relative intensities and line profiles are used to determine the average cell and the deviations from this average.

The characteristic length scales in superlattices are i) the modulation wavelength, Λ , defined as the repeat distance of the layering, ii) the lattice spacing of the constituent material, and iii) the structural coherence length, ξ , which is the distance over which the atomic positions are

quantitatively correlated and can be estimated from the full width at half maximum of diffraction peaks using Scherrer's equation. In many superlattices, ξ is limited to only a few times Λ due to structural disorder. The type and amount of structural disorder can greatly affect the relative intensity of the diffraction peaks. Since many types of disorder can be present in a superlattice including layer thickness fluctuations, interface disorder, crystalline disorder, and interdiffusion, a large number of model parameters have to be included. This makes a refinement procedure much more difficult.

We developed a general kinematic diffraction model that includes both the average atomic structure of the layers and structural disorder for fitting measured x-ray diffraction profiles. By fitting the measured profiles, it is possible to *quantitatively* determine both lattice constants and disorder parameters of a wide variety of superlattices. To illustrate the need to include lattice deviations and structural disorder in superlattice calculations, Fig. 1 shows the measured x-ray diffraction profile (open circles) of a sputtered Mo/Ni superlattice compared to two model calculations. The thin line is calculated assuming a perfect superlattice with bulk lattice parameters for the Mo and Ni. The thick line is the result of the refinement procedure developed here, which quantitatively fits the measured diffraction profile over three orders of magnitude in intensity.

Of course, since the refinement described here relies on a multivariate fit, it is very important to ascertain the reliability of the method. For this we have spent considerable amount of time and effort to compare the results obtained from the structural refinement to results obtained independently from other measurements.

Figure 1: Measured x-ray diffraction profile of a $[\text{Mo}(20\text{\AA})/\text{Ni}(22\text{\AA})]_{130}$ superlattice (circles) and calculated spectra (thin line) using formalism described in the text assuming bulk Mo and Ni lattice spacing and integer number of atomic layers. Thick line is the result of refinement procedure described in text.

To check the roughness values obtained by the refinement procedure, a series of Mo/Ni and Nb/Cu superlattices were prepared in which the layer thicknesses were varied during growth in a known random fashion. These values were very well reproduced by the refinement. Internal consistency was obtained by checking values obtained from various orders of reflections and from model independent average quantities.

Excellent agreement is obtained between the refinement results for the lattice parameters of Ag/Mn, as compared to Extended X-Ray Absorption Fine Structure (EXAFS) and X-Ray Photoelectron Diffraction (XPD). Figure 2 shows the measured (circles) and fitted (line) diffraction

profiles of a 3 and 5 monolayer (ML) Mn in Ag/Mn superlattices. Best fit results for the Mn and Ag distances from fitting the diffraction profiles about the Ag[002] and Ag[004] reflections are given in Table 1. Included in Table 1, are the Mn lattice spacings estimated from the c/a ratio determined from EXAFS on the same superlattice and XPD results on MBE grown Ag/Mn/Ag trilayers. Excellent agreement is obtained between the two techniques for the Mn distance in the superlattices and for the lattice spacing in the trilayers. In particular, both techniques determine that there is a large change in lattice spacing from 3 to 5 ML of Mn. The additional information which is obtained from these refinements is the interfacial roughness and the variations in thicknesses which are not available otherwise.

Other comparisons include determination of the relative thickness of the layers from X-ray diffraction refinement and chemical analysis for Cu/Ni, calibrated sputtering rate for W/Ni, and low angle profile for Mo/Ni.

The methodology developed here has applications in all fields which use thin films as the basic materials. We are currently applying the same methods to study property-structure relationships in superconducting, magnetic, elastic and transport properties of thin films and superlattices.

Figure 2: Experimental (o) and calculated (full line) high angle x-ray diffraction profiles for (a) $[\text{Ag}(33\text{\AA})/\text{Mn}(6\text{\AA})]_{101}$ and (b) $[\text{Ag}(31\text{\AA})/\text{Mn}(8\text{\AA})]_{20}$ superlattices. The refined parameters are given in Table 1. The arrows indicate the position of the additional Ag(002) buffer layer peak.

Two independent versions of this program have been written, one using TURBOPASCAL and the other FORTRAN, in order to assure further the correctness of the methodology. As a service to the community, both of these versions are now supplied in a user friendly version together with users manuals to other researchers interested in similar problems. To date we have

received a large number of requests only based on talks given at various conferences. The results are summarized in two major papers and two Ph.D. theses.

Table 1

Thickness (ML)		Roughness ($\text{\AA}$)			Lattice Spacings ($\text{\AA}$)			
N_{Ag}	N_{Mn}	S_{Ag}	S_{Mn}	c	X-Ray d_{Ag}	d_{Mn}	EXAFS d_{Mn}	XPD d_{Mn}
15	5	2	1	0.23	2.046 ± 0.003	1.68 ± 0.04	1.64 ± 0.08	1.65
16	3	1	1	0.08	2.051 ± 0.003	1.90 ± 0.04	2.03 ± 0.15	1.80
13	2	2	0.5	0.04	2.052 ± 0.003	1.92 ± 0.04	—	1.85

Table 1: Refined roughness and lattice parameters for MBE grown Ag/Mg superlattices. The Mn lattice spacings are estimated from the c/a ratio determined in EXAFS on the same superlattice and XPD results are obtained for comparable MN layer thicknesses Ag/Mn/Ag trilayers.

2.- SUPERCONDUCTIVITY

An important application of our preparation methods has been geared towards the study of model systems, such as superconducting-normal superlattices. One particularly interesting problem relates to the H-T phase diagram of superconducting multilayers. A number of theoretical models have been developed, specifically geared towards the study of ceramic superconductors which however only rely on the layered nature of the material.

We have performed a number of extensive studies of the structure and superconducting properties of Pb/Ge superlattices to investigate the H-T phase diagram of layered superconductors. This system has a major advantage over ceramic superconductors for studies of these type of problems since we can control independently all relevant parameters, such as layer thicknesses and pinning. We discovered a novel transition, in the H-T phase diagram which is signaled by a very unusual dependence of the critical current (J_c) as a function of these parameters. Figure 3 shows the dependence of J_c as a function of angle, in a fixed magnetic field for a Pb(220 $\text{\AA}$)/Ge(50 $\text{\AA}$) superlattice. Fig 4 shows the dependence of J_c as a function of perpendicular field for the same superlattice. Both of these, dependences are quite unusual, unlike ever observed in any superconductor. Note that the critical current in a certain range of magnetic field, increases with increasing field which is totally unexpected from any conventional theoretical ideas. The detailed studies of these material show that the unusual temperature dependence is related to some sort of melting or decoupling of the vortex lattice, which was predicted theoretically for ceramic superconductors.

Figure 3: Critical current density at 4.2K for a Pb/Ge (220Å/50Å) multilayer as a function of the angle between an applied magnetic field of 1000 Gauss and the layers. The inset shows the geometrical configuration.

Figure 4: Critical current density at 4.2K for a Pb/Ge (220Å/50Å) multilayer as a function of perpendicular magnetic field.

3.- MAGNETISM

Magnetism in superlattices has received a renewed attention due the discovery of giant magnetoresistance (change in resistance with field, ΔR normalized by the resistance, R) in Fe/Cr superlattices. These studies have also important implications for the development of media and heads for magnetic recording. The connection of the giant magnetoresistance (GMR) to the antiferromagnetic coupling, the presence of oscillations in the coupling and the GMR, and the dependence of these phenomena on various magnetic and separator elements has received considerable attention. However, not much work was done in trying to understand the connection between the GMR and the physical structure.

We have combined our growth and structural methods with detailed magnetic and transport studies to try understanding the connection between structure and magnetoresistance in Fe/Cr superlattices. These studies were performed by varying growth parameters in a systematic fashion and combining these measurements with detailed structural, magnetic and transport measurements.

Fig. 5a shows standard low angle θ - 2θ X-ray diffraction spectra of $[\text{Fe}(30\text{\AA})/\text{Cr}(19\text{\AA})]_{10}$ superlattices, where the subscript is the number of bilayers. The samples were deposited under similar conditions except for the pressure of the Ar sputtering gas, which was changed from 4 mTorr to 12 mTorr. The 4 mTorr samples exhibit clear superlattice Bragg peaks up to the 2nd

order, a shoulder at the position corresponding to the 4th order peak and clean cut finite size peaks between the Bragg peaks (the 3rd order peak is expected to be suppressed because the ratio of Fe to Cr is almost 2:1). The finite size peaks result from interference of X-ray reflections from the film surface and the film-substrate interface with the periodicity of the peaks determined by the total film thickness. The Bragg and finite size peaks in the 12 mTorr samples have a considerably reduced intensity and are visibly broadened. The immediate qualitative conclusion is that the 4 mTorr sample exhibits layers which are considerably flatter than the 12 mTorr sample. An inspection of the magnetoresistance ratio $\Delta R/R$ versus magnetic field in Fig 5b shows that the maximum value of $\Delta R/R$ increases substantially with increasing roughness of the layers.

Similar results were obtained by varying the roughness using other sputtering parameters. All these lead to the unequivocal conclusion that roughness strongly affects the GMR and that increasing roughness increases the GMR. Theories available to date fail to explicitly calculate the dependence of the GMR on roughness and consequently it is hard at the present time to make definite theoretical conclusions. Nevertheless these results clearly indicate that structural measurements combined with physical properties produce interesting, sometimes unexpected new physics.

Figure 5: (a) Low angle θ - 2θ X-ray diffraction spectra and (b) $\Delta R/R$ vs. applied field at 4K for selected representative $[\text{Fe}(30\text{\AA})/\text{Cr}(18\text{\AA})]_{10}$ superlattices sputtered at various Ar pressures. X-ray spectra are offset by two decades for clarity.

B. RESEARCH PLANS FOR THE COMING YEAR

1. INTERFACIAL STRUCTURE AND PHYSICAL PROPERTIES

We will apply our Superlattice Refinement Code (SUPREF) to a variety of interesting problems to study structure-property relationships. These studies include research on the structure of high T_c superlattices and the relationship of interdiffusion to the properties of single unit cell layers. We will also apply these techniques to further investigate the connection between structure and GMR in magnetic superlattices. We will also compare samples prepared by the two commonly prepared techniques: MBE and sputtering in order to ascertain the role that preparation method and crystallographic orientation has on these properties.

2. METAL-INSULATOR EPITAXY

We will continue our detailed studies of the MBE growth of ferromagnetic Ni on antiferromagnetic NiO in order to study questions regarding roughness and the important problem of displaced hysteresis loops ("exchange-bias") in ferro-antiferromagnetic layers. The structure of the NiO single crystal surface is being characterized using *ex-situ* X-ray diffraction and *in-situ* RHEED and LEED. Once the surface of NiO is characterized we prepare a thin film of Ni of various thicknesses to study the magnetic properties and its dependence on the interfacial structure. Preliminary results indicate that interfacial roughness plays an important role on the exchange bias. We are presently trying to quantify this statement i.e. to ascertain to what level we can affect the exchange bias by varying the interfacial roughness. As a further check on this problem we will also explore the growth of Co on single crystal CoO. This work is done in collaboration with Dr. V. Speriosu from the IBM Almaden Research Center.

3. QUANTITATIVE RHEED

An important ingredient on the structural characterization of interfaces is to understand RHEED during growth or at various stages of interrupted growth. For this purpose we developed a data acquisition system to acquire RHEED data in a digital fashion. In this way we are able to perform detailed quantitative analysis of the intensities and the line shapes of the RHEED diffraction spectrum. This is applied to the various systems described in the sections above and to prototype systems specially grown to check the theoretical approach used for the quantitative RHEED analysis. We are currently developing model calculations for RHEED images which eventually will be included in a refinement program similar to the SUPREF. This will hopefully allow the quantitative determination of interfacial structure from RHEED measurements.

As an additional technical development we are in the process of installing an *in-situ* Scanning Tunneling Microscope (STM) which will allow cross checking our RHEED and LEED measurements with direct space measurements.

APPENDIX I

PUBLICATIONS UNDER THE SECOND FUNDING PERIOD OF THIS GRANT (3/15/91-3/14/92)

A. Papers Published in Refereed Journals

1. **Anisotropy and Magnetic Field Dependence of Critical Currents in Pb/Ge Multilayers**
D. Neerincx, K. Temst, M. D'Halle, C. Van Haesendonck, Y. Bruynseraede, A. Gilabert, Ivan K. Schuller, T. Krekels, G. Van Tendeloo
Physica B 165 & 166, 473 (1990).
2. **Quantitative X-ray Structure Determination Superlattices and Interfaces**
Ivan K. Schuller, Eric E. Fullerton, H. Vanderstraeten and Y. Bruynseraede, in
"Structure/Property Relationships for Metal/Metal Interfaces", A.D. Romig, Jr., D.E. Fowler and P.D. Bristowe, editors
(Materials Research Society) Vol. 229, 1991, pg. 41.

B. Papers Submitted to Refereed Journals (Not Yet Published)

1. **Roughness and Giant Magnetoresistance in Fe/Cr Superlattices**
Eric E. Fullerton, D.M. Kelly, J. Guimpel, Ivan K. Schuller and Y. Bruynseraede
Phys. Rev. Lett., Submitted.
2. **Structural Refinement of Superlattices from X-ray Diffraction**
Eric E. Fullerton, Ivan K. Schuller, H. Vanderstraeten and Y. Bruynseraede
Phys. Rev. B., Submitted.
3. **Subsurface Bonding of Hydrogen in Transition Metals: Dependence on Surface Orientation**
J. Rogan, M. Lagos and Ivan K. Schuller
Rap. Comm. - Phys. Rev. B., Submitted.

C. Invited Talks at National and International Meetings

1. **X-Ray Structure Determination of Superlattices and Interfaces**
Ivan K. Schuller, Eric E. Fullerton, H. Vanderstraeten and Y. Bruynseraede
Materials Research Society
Anaheim, CA
April 39-May 4, 1991.
2. **Superconducting Properties of Percolating Multilayers**
K. Temst, D. Neerincx, M. Baert, C. Van Haesendonck, Y. Bruynseraede, A. Gilabert and Ivan K. Schuller
11th General Conference of the Condensed Matter Division of the European Physical Society
Exeter, U.K.
April 8-11, 1991.

3. **Structure and Magnetism in Metallic Superlattices**
Ivan K. Schuller and Y. Bruynseraede
Workshop in "Magnetism, Surfaces, Films and Multilayers"
Rio de Janeiro, Brazil
July 15-17, 1991.
4. **Structure and Magnetism in Metallic Superlattices**
Ivan K. Schuller, E. Fullerton, D. Kelly, J. Guimpel, P. Belien and Y. Bruynseraede
International Workshop on Spin-Valve Layered Structures
Madrid, Spain
September 9-12, 1991.

D. Doctoral Theses

1. **Quantitative Structural and Elastic Characterization of Superlattices**
Eric E. Fullerton, University of California - San Diego
September, 1991.
2. **Characterization of Structural Disorder in Multilayers and Superlattices Using X-Ray Diffraction**
H. Vanderstraeten, Katholieke Universiteit - Leuven
June, 1991.

E. Contributed Talks

1. **Structural and Magnetic Properties of Fe/Cr Superlattices**
Eric E. Fullerton, D. Kelly, J. Guimpel, F.T. Parker, Ivan K. Schuller and Y. Bruynseraede
Bull. Am. Phys. Soc. 36, 785 (1991).
2. **Anomalous Parallel FMR Mode in Fe/Cu Multilayers**
Michael J. Pechan, Jiansheng Xu, Ivan K. Schuller and Eric Fullerton
Bull. Am. Phys. Soc. 36, 785 (1991)
3. **Structural Refinement of Superlattices from X-ray Diffraction**
H. Vanderstraeten, Y. Bruynseraede, Eric E. Fullerton and Ivan K. Schuller
Bull. Am. Phys. Soc. 36, 958 (1991).
4. **Magneto-transport Properties of Fe/Cu Multilayer Films**
Jeff M. Florczak, E. Dan Dahlberg, Eric E. Fullerton and Ivan K. Schuller
Bull. Am. Phys. Soc. 36, 1045 (1991).
5. **Structural Refinement of Superlattices from X-ray Diffraction**
Eric E. Fullerton, Ivan K. Schuller, H. Vanderstraeten and Y. Bruynseraede
Materials Research Society
Anaheim, CA
April 29-May 4, 1991.

6. **Structural and Magnetic Properties of Fe/Cr Multilayers**
D.M. Kelly, Eric E. Fullerton, J. Guimpel, F.T. Parker, Ivan K. Schuller
and Y. Bruynseraede
Materials Research Society
Anaheim, CA
April 29-May 4, 1991.
7. **Connection Between Structure and Giant Magnetoresistance in Sputtered
and MBE Grown Fe/Cr Superlattices**
David M. Kelly, J. Guimpel, Ivan K. Schuller, P. Belien and Y. Bruynseraede
March 1992 Meeting of The American Physical Society
Indianapolis, IN
March 16-20, 1992.

APPENDIX II

Students and Postdoctoral Fellows Supported by This Grant

Mr. Eric Fullerton was supported by this grant, and received his Ph.D. in September, 1991. Currently, Mr. I. Chan and S. Kim are graduate students supported by this grant. One postdoctoral fellow (J. Guimpel) is partially supported by this grant.

END

**DATE
FILMED**

6 / 11 / 92