EGG-MS-9879
October 1991

**Idaho
National
Engineering
Laboratory**

*Managed
by the U.S.
Department
of Energy*

INFORMAL REPORT

MAR 26 1992

TECHNICAL ASSESSMENT OF PROCESSES TO ENABLE
RECYCLING OF LOW-LEVEL CONTAMINATED METAL
WASTE

G. A. Reimann

*Work performed under
DOE Contract
No. DE-AC07-76ID01570*

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights. References herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

EGG-MS--9879

DE92 010488

TECHNICAL ASSESSMENT OF PROCESSES TO ENABLE
RECYCLING OF LOW-LEVEL CONTAMINATED METAL WASTE

G. A. Reimann

Published October 1991

EG&G Idaho, Inc.
Idaho Falls, ID 83415

Prepared for the
U.S. Department of Energy
Office of Environment Restoration
and Waste Management
Under DOE Field Office, Idaho
Contract DE-AC07-76ID01570

MASTER

ABSTRACT

Accumulations of metal waste exhibiting low levels of radioactivity (LLCMW) have become a national burden, both financially and environmentally. Much of this metal could be considered as a resource. The Department of Energy was assigned the task of inventorying and classifying LLCMW, identifying potential applications, and applying and/or developing the technology necessary to enable recycling. One application for recycled LLCMW is high-quality canisters for permanent repository storage of high-level waste (HLW). As many as 80,000 canisters will be needed by 2035. Much of the technology needed to decontaminate LLCMW has already been developed, but no integrated process has been described, even on a pilot scale, for recycling LLCMW into HLW canisters. This report reviews melting practices for removal of radionuclides and for producing low carbon stainless steel. Contaminants that readily form oxides may be reduced to below *de minimis* levels and combined with a slag. Most of the radioactivity remaining in the ingot is concentrated in the inclusions. Radionuclides that chemically resemble the elements that comprise stainless steel can not be removed effectively. Slag compositions, current melting practices, and canister fabrication techniques were reviewed.

CONTENTS

INTRODUCTION	1
CANISTER REQUIREMENTS	4
Required Quantities	4
Canister Design	5
Canister Material Specification	7
Canister Tests	9
ICPP Canister Requirements	10
MELTING OF CONTAMINATED STAINLESS STEEL	12
Steel Melting, General	12
Electric Arc Furnace	12
Induction Melting	12
Nature of Activity in Scrap	15
Scrap Criteria	16
Removing/Decreasing Scrap Contamination	20
Decontamination by Melting	22
Removal of Uranium from Steels	22
Removal of Transuranics from Steels	24
Removal of Fission Products from Steels	27
Removal of Activation Products from Steels	32
SLAGS	34
Decontaminating Slags	36
Industrial Refining Slags	40
APPLICATION OF CURRENT MELTING TECHNOLOGY	44
Induction Melting Under Vacuum and Inert Gas	44
Bottom Pouring	46
Induction Melting in the Ladle	47
PLANS FOR FUTURE WORK	49
Preliminary Studies	49
Cooperative Agreement Studies	49
REFERENCES	54

FIGURES

1. Sketch of HLW canister.	5
2. Comparison of EAF and induction furnace cross sections.	13
3. Schematic of slide gate bottom pouring system.	48

TABLES

1.	Summary of allowable nuclide concentrations in low-level waste . .	18
2.	Examples of non-removable isotopes	33
3.	Slag composition vs. melt decontamination	37
4.	Compositions of stainless steels	42

INTRODUCTION

A growing accumulation of low-level contaminated metal waste (LLCMW) has been a major cause for concern for at least two decades. As quantities of LLCMW continue to increase while the space available for disposal continues to decrease, this concern is changing to alarm. LLCMW will accumulate at an increasing rate as reactors built in the 1950s reach the end of their useful life, as nuclear-powered ships become obsolete or unneeded, and as various weapons plants and fuel processing facilities are dismantled or modernized. LLCMW represents a substantial resource, yet little technology has been developed domestically that would enable recycling this waste. The Department of Energy (DOE) was chartered to investigate recycling of LLCMW generated at various nuclear facilities, and EG&G Idaho Inc.'s Waste Management Research and Development Unit was commissioned to identify, research, and develop alternate uses for LLCMW generated by DOE, Nuclear Regulatory Commission (NRC), and Department of Defense (DOD) facilities in the United States.

It has been demonstrated that much of the LLCMW is amenable to decontamination by melt refining. Large quantities of LLCMW are stored at various DOE, Department of Defense (DOD), and commercial sites under the control of the Nuclear Regulatory Commission (NRC). In its present configuration, this waste represents a considerable storage volume as well as a significant cost, since it must be maintained and monitored in secure storage, including retrievable shallow land burial, to minimize the chance of spreading radioactive contamination. Waste, especially nuclear waste, is also a political problem. A number of states have or are developing compacts in a cooperative effort to control movement of all types of waste across their borders and disposal of waste within their borders. Many older landfills are approaching capacity and too few new landfills are opening to replace them. The issue is surrounded by overheated political controversy, particularly with regard to nuclear waste, and any resolution of problems will likely be accompanied by greatly increased disposal costs.

An imperative exists for permanently disposing of an accumulating store of high-level waste (HLW) that is a by-product of the many facets of nuclear activities. Current plans for disposal of this material include conversion of HLW into a non-leachable glass or ceramic and loading it into 304L stainless

steel canisters for permanent disposal in a secure repository. The tonnage of stainless steel needed to produce the required number of canisters is considerable, but could be met by the LLCMW inventory, provided that successful technologies can be developed to convert this waste into acceptable canisters. Nearly 26,000 tons of stainless steel will be needed^a to produce the canisters currently deemed necessary to accommodate current and projected quantities of HLW.

The substantial supply of contaminated stainless steel waste could meet the demand for the large number of waste canisters without placing an additional burden on our natural resources, strategic materials, or the balance of trade. Further, if the stainless steel that is classified as LLCMW could be converted into a product that is suitable for the requirements of the HLW storage canisters, the cost of storing and monitoring this LLCMW would be eliminated. The technology reviewed and/or developed during the course of this study may enable cleanup of some LLCMW to the extent that it may be allowed to enter the commercial scrap recycling system, although this currently is not a goal of this effort.

In the event that an outer container, a pedestal, a bore-hole liner, and a shield plug are required to ensure satisfactory permanent repository disposal of HLW, the tonnage of LLCMW to be processed will be much larger than that required for the canisters alone. Such requirements have not yet been defined but will likely involve substantial quantities of mild steel. This review will concentrate on the canisters, as this component must meet the most stringent requirements.

The technical objectives of the LLCMW Program are:^b

1. Conduct a needs assessment to establish potential applications for the recycled LLCMW.
2. Conduct a survey that will establish the quantity and availability of LLCMW at DOE, DOD, and NRC controlled facilities.

a. K. E. Rosenberg and N. D. Stucki, *Canister Work Scope Report* (Unpublished Pre-Decisional Draft), EG&G Idaho, Inc., Idaho Falls, ID, October 1989.

b. Canister Fabrication Technical Task Plan, May 1990.

3. Conduct performance assessment and material characterization studies on the remelted LLCMW scrap.
4. Design and manufacture prototypes of the applications that are demonstrated to be economically viable.
5. Provide processing equipment information and canister fabrication design criteria for the design and construction of a manufacturing facility."

This report addresses items 3, 4, and 5, above, in terms of using LLCMW for canisters for storage of HLW, with emphasis on a review of the literature to determine melting techniques most applicable to decontaminating and refining and on the suitability of these techniques to newly-developed or emerging melting and manufacturing technologies.

The Savannah River Plant (SRP) will begin filling canisters in 1992 and the Hanford Waste Vitrification Plant (HWVP) in the year 2000. Since back-extruded containers using recycled LLCMW have not been qualified for this application, these canisters must be produced from formed and welded plate obtained from the commercial sector.

If DOE is to recycle LLCMW into canisters and meet the current schedule for treatment and disposal of existing and anticipated HLW inventories, the technology development and demonstration activity necessary for construction of a pilot plant should begin as soon as possible, not 20 years hence. A full-scale manufacturing facility for conversion of LLCMW into the required quantities of back-extruded canisters will require a substantial capital investment.

CANISTER REQUIREMENTS

Required Quantities

The quantity of canisters required to accommodate current and anticipated radioactive waste inventories have been projected through the year 2035. The three facilities and their estimated canister requirements are as follows:^a SRP, 5689 canisters, years 1992 to 2022; HWVP, 2800 canisters, years 2000 to 2007; Idaho Chemical Processing Plant (ICPP), 24,500 canisters, years 2011 to 2035. If a decision is made to vitrify the "single tank" waste at HWVP, an additional 8000 canisters will be required after 2008. Based on these estimates, a total of about 41,000 canisters may be needed.

The Idaho National Engineering Laboratory (INEL) has a growing accumulation of HLW, the ICPP calcines, which eventually must be retrieved, processed, packaged, and stored in a permanent repository. The 24,500 canisters plus 73,500 inner cans will be required to receive the current ICPP production as well as to work off the stored backlog by the year 2035, provided that the calcining process proposed by ICPP produces an acceptable waste form. Otherwise, nearly 64,000 canisters (but not the inner cans) will be needed if the borosilicate glass (BSG) waste form must be used. Using the smaller figure will require an annual production rate of 1000 canisters, or 550 tons per year of decontaminated, finished product just to satisfy the minimal ICPP requirements. If the BSG waste form must be used, the potential total number of canisters needed for the three facilities swells to nearly 80,500.

While processing of the INEL high level waste and loading into canisters is not scheduled to begin until 2011, the SRP is presently purchasing canisters produced from formed and welded 304L plate, using stainless steel obtained from the commercial sector, because the technology for utilizing decontaminated LLCMW has not been developed. It is likely that canisters produced from contaminated scrap will be ready to receive the high-level waste from the HWVP if efforts begin immediately to develop the technology.

a. K. E. Rosenberg and N. D. Stucki, *Canister Work Scope Report* (Unpublished Pre-Decisional Draft), EG&G Idaho, Inc., Idaho Falls, ID, October 1989.

Canister Design

No "standard" waste canister design exists at present, although the Defense Waste Processing Facility (DWPF) reference canister design, shown in Figure 1, is expected to become the standard as it has been tested and qualified for the SRP waste. This canister is 2 ft in diameter, about 10 ft tall, and has a $\frac{3}{8}$ in. (or 1 cm) wall thickness and an internal volume of 26 ft³. The empty canister weight is 1100 lb; when filled to 85% of its capacity (22 ft³) with BSG ($d \approx 2.70$) it will weigh 4800 lb. The SRP and the HWVP have tentatively adopted the reference design shown in Figure 1. These two facilities will use the approved BSG waste form, which will be loaded with

Figure 1. Sketch of HLW canister.

30 to 60% radioactive waste and poured into the canisters at 1050-1100°C. The ICPP will utilize a different waste form [a hot isostatically-pressed (HIPped) calcine] and as a consequence will likely use a somewhat different canister design. This will be covered in more detail later in this report.

The vessel has a relatively thin wall as the waste is not expected to produce significant internal pressure and no external (hydrostatic or lithostatic) pressure is anticipated in the repository. The cylindrical body of the design depicted is fabricated by roll-forming commercial stainless steel plate and welding along the longitudinal seam (this seam is not shown in Figure 1). Hot-formed top and bottom heads are welded to the body and a filler neck is welded to the top head to complete the assembly. The filler neck serves as access for pouring in molten BSG and is subsequently sealed by remote welding. The neck must be rugged enough to serve as a handle or pintle for remote manipulation of the filled canister.

The process proposed for fabricating canisters from LLCMW, back extrusion, involves driving a punch into a cylindrical blank that is restrained from lateral flow by a heavy-walled, closed-bottom container. Sufficient force is applied to cause the metal to flow through the clearance between the container and the descending punch. In conventional extrusion, plastic flow through the orifice (extrusion die) moves in the same direction as the punch, while in back extrusion the orifice is the clearance between the container and the punch so metal flows in the direction opposite to punch motion. Aluminum beverage cans are back extruded as is a variety of other items, including artillery projectiles. The metal structure in the walls of the back-extruded part resembles that encountered in seamless tubing. The canisters will be formed from two back extrusions, trimmed, weld-prepped, and joined at the center with a single girth weld. Two major advantages of back-extruded containers are: only a single girth weld is needed to join the halves, and, when the technology is developed to back extrude a cast blank, the process will not require an expensive rolling and forming facility dedicated to processing decontaminated stainless steel ingots. Back-extruded canisters are expected to have the same configuration as the roll-formed canisters. The properties of back-extruded canisters must be verified by testing of prototypes to ensure that they are equal to or better than the reference canister for the loading, transport, and interim and long-term

storage requirements before they may be considered to be qualified for use with HLW.

Canister Material Specification

The requirements to be met for the canister material are somewhat vague: "The waste form canister and any secondary containers applied by the producer shall be fabricated from austenitic stainless steel. The ASTM alloy specification and the composition of the canister material, the secondary canister material, and any filler material used in welding shall be included in the Waste Form Compliance Plan (WCP)."¹ The material currently specified for SRP canisters is 304L stainless steel. If the canisters are to be made from LLCMW, the product form would be required to conform to the specifications for AISI Type 304L stainless steel.

The HLW canisters must conform to the requirements imposed by 40CFR191 in order to comply with radionuclide release limits for geological repositories. In this case the repository is assumed to be the Yucca Mountain site and environmental conditions unique to this location will determine what must be done to meet canister performance objectives. This task is complicated by frequent revisions of 40CFR191 and related chapters that may change canister performance objectives. Presently, in the context of 40CFR191, storage means the retention of HLW with the intent and capability to readily retrieve such waste, while disposal means permanent isolation of HLW with no intent of recovery. The canister is simply a barrier; it is a temporary impediment that must prevent or substantially delay movement of radionuclides. The canisters must be retrievable within the first 50 years after emplacement at the Yucca Mountain Site. As a barrier, the canister must contain radionuclides without any migration for 1000 years from the date of closure of the repository. Releases after the 1000 year period must be "substantially controlled" for up to 10,000 years. This requirement anticipates that some of the canisters will be breached by corrosion after 1000 years but that leakage of radionuclides will be minimal. The rate of leakage will be influenced greatly by the leachability of the contained waste form. Movement of radionuclides beyond the borehole will depend on how long the secondary container, if used, protects the canister, the borehole liner (which is used primarily to assure easy retrieval), and other barrier materials such as clays and zeolites.

The decay heat of the contained radionuclides will make it easier to meet the minimum barrier requirement by assuring a dry canister for several hundred years. Aqueous corrosion will not be a factor in canister deterioration until the wall temperature drops to the boiling point at the repository elevation (96°C). Some oxidation will result from exposure to air and steam at the maximum wall temperature (270°C), and the potential of alloy phase instability in austenitic steels should be considered for the protracted times at the elevated canister temperatures.

A variety of austenitic stainless steels is available that could meet the canister requirements, considering cost, mechanical properties, weldability, and corrosion resistance. Commercial 304L stainless steel was used in the container prototypes² and samples have been corrosion tested in a simulated Yucca Mountain repository environment using a variety of likely conditions.³ This alloy met the current canister requirements satisfactorily, and none of the other austenitic grades demonstrated performance that was clearly superior, with the possible exception of the 825 alloy. For the purpose of simplifying the task at hand, 304L stainless steel will be considered as the primary candidate alloy for the canister and this report will concentrate on recycling stainless steel waste into an alloy that conforms to the chemical and physical requirements of ASTM specifications for Type 304L plus other requirements specific to the repository.

Current ASTM specifications, and documents referenced in these specifications, provide for satisfactory mechanical properties for 304L stainless steel plate to be used for fabrication of the canisters. This specification does not address a corrosion resistance requirement for repository storage and/or disposal. Presently, it is not possible to assure that the desired performance may be obtained, as no data base exists for such an extended period that would enable giving such assurance; however, melting practices are in use that could enhance the long-term corrosion resistance of 304L stainless steel and these practices appear to be compatible with techniques that may be used to decontaminate the steel. This technology combination remains to be demonstrated.

Based on autoclave testing in solutions representative of those expected in the repository environment, stainless steel specimens with the lowest

carbon contents and the fewest inclusions will fare best. If conditions favoring pitting and stress corrosion are avoided, the uniform corrosion rate is estimated at $<1 \mu\text{m}$ per year.³ At this rate, with environmental conditions remaining constant, the 1.0 cm the canister wall would have dissolved and the radionuclides would no longer be contained after 10,000 years. Unfortunately, uniform corrosion is not the only mode, nor will the conditions around the canister remain constant. Processing parameters may be tailored to enhance resistance to stress, crevice, inter- and transgranular, and pitting corrosion in austenitic stainless steels to increase durability beyond the 30 to 50 years normally expected for lifetimes of industrial plants. Imposing such requirements will demand processing controls more stringent than those imposed by the specifications presently used in commerce.

Canister Tests

Reference design canisters (Figure 1) were compared to centrifugally-cast canisters made to approximately the same configuration.² These canisters were filled with "SRP 165 black frit", which is the equivalent to BSG except for the radioactive waste content. Using operating conditions considered representative of those anticipated at the DWPF, the canisters were filled with BSG poured at 1050°C, using a fill rate of 220 lb/h. Fifteen hours were required to fill the canister with 3250 lb of glass. Thermocouples placed on the canister wall to obtain temperature profiles showed that the wall reached about 450°C and remained above 350°C for several hours. The stainless steel wall contracts more than the glass on cooling, so the wall is stressed at yield upon reaching ambient temperature.⁴ This condition is unfavorable in terms of susceptibility to stress corrosion cracking.

Several of the filled canisters were sectioned, examined metallographically, and subjected to corrosion testing.⁴ Other canisters were subjected to drop testing.⁵ The major purpose of this activity was to compare the performance of centrifugally-cast canisters of the CF-3 alloy (the as-cast equivalent of 304L) to those produced by the conventional form-and-weld process dictated by the reference design. The canister types performed about equally well in the corrosion tests and the drop tests. The drop tests entailed two 30-ft drops onto an unyielding surface so as to impact the bottom corner and the fill neck, and a 40-in. drop onto vertical steel

steelcylinder 6 in. in diameter as a puncture test. No canister ruptures occurred as a result of these tests nor were any leaks or cracks detected.

ICPP Canister Requirements

The ICPP canisters will contain hot-isostatically-pressed (HIPped) cans of a calcine-ceramic mix rather than BSG. While the reference canister design is presently under consideration for the ICPP calcines, it is likely that this design will be modified somewhat to better accommodate the HIPped cans.

The glass-ceramic route was selected by ICPP because of the higher waste loading achievable. A calcine-additive mix has been formulated that provides leach resistance equal or superior to that exhibited by BSG,^a and the higher waste loading means that fewer canisters will be needed to contain the HLW and dispose of it in the repository. At least 2600 canisters per year would be needed if the BSG waste form were used, while 1000 canisters per year will be needed if the glass-ceramic is used, resulting in an estimated cost reduction of \$560,000,000 per year.^a The production rate will require an average of 4 acceptable canisters per day, 250 days per year, which translates into at least a 5000 lb per day capability for waste processing, melting, and fabricating.

The calcine is primarily Al_2O_3 , ZrO_2 , and CaF_2 , but calcine compositions vary with the type of fuel and the process used. After treatment to remove volatiles, the calcines are blended with a "silica-based additive", fed into metal cans, and densified by vibratory and/or pressure compaction. The cans are then evacuated, sealed by welding, decontaminated, and HIPped for conversion into the glass-ceramic. The size of the cans is such that three of them will fit into the reference canister (Figure 1). The cans are thin-walled (10 ga., 0.135 in., or 3.4 mm) and will likely be fabricated from commercial sheet. HIPping will deform these cans, so an allowance must be made for dimensional variations of misshapen cans to ensure that they may be inserted into the canisters.

a. W. A. Freeby, unpublished work on preliminary description of bases for development of an ICPP glass-ceramic processing facility, Westinghouse Idaho Nuclear Company, Inc., Idaho Falls, ID, November, 1988.

At present, development of the glass-ceramic waste form remains at a primitive stage, as only miniature (≈ 1 in. dia. x 3 in. long) specimens have been HIPped to produce samples for testing. Full-size production HIPs are expensive and cycle times will be long, so a battery of remotely operated units will be needed to sustain a production rate that will fill the equivalent of four of the reference canisters each day. A substantial investment in research and development will be necessary before design and construction of a pilot plant and a production facility may be considered.

Using the BSG waste form permits fabrication of the canister and inspection of the welds prior to filling. When calcine-loaded HIPped cans are used the canister must be welded after the cans are in place. Weld inspection on a 270°C canister that reads 10^5 R/h or more may be difficult. While the canister wall will not be stressed in tension due to the difference in contraction coefficient on cooling, it will not be supported against impact damage as it was when the BSG solidified because of the extra clearance needed to permit misshapen cans to be inserted into the canister.

MELTING OF CONTAMINATED STAINLESS STEEL

If contaminated stainless steel waste is to be recycled into canisters, technologies must be developed to enable smelting and refining to remove the contamination, or at least to reduce it to very low levels. The melting process must also enable efficient production of a low carbon, high quality 304 stainless steel extrusion blank to produce a back-extruded canister that will endure storage and/or disposal in the repository environment.

Since the need for the greatest number of canisters is at the INEL, it follows that the technology to convert scrap into canisters would be developed at the INEL, as would the facility for full-scale conversion of scrap into canisters, particularly in view of the INEL mission and the expertise and equipment resources already available.

Steel Melting, General

Electric Arc Furnace

The majority of the stainless steel in the U.S. is produced in three-phase direct electric arc furnaces (EAF). The EAF process also accounts for about a third of the total raw steel production in this country, and has achieved this prominence as a result of an increasing availability of low-cost electric power and because of the versatility of the EAF. It is effective in producing carbon steels, low-alloy steels, tool steels, and stainless steels. The geometry of the furnace is such that it contains a large diameter, shallow melt with a large surface area which facilitates charging of scrap and the evolution of gases. The large surface area also contributes to increased bath oxidation. The general shape of EAF interiors is shown in Figure 2. Larger arc furnaces have internal diameters of 30 feet or more and capacities of over 350 tons.

Induction Melting

The induction melting technique is accounting for increasing tonnages of steel as improvements in solid-state frequency converters have increased operating efficiencies of the smaller units and, in the case of foundries,

N91 0415

Figure 2. Comparison of EAF and induction furnace cross sections.

where energy costs and air quality standards have caused obsolescence of other melting techniques. An induction furnace produces about 20% of the effluent dust generated by an EAF of similar capacity. Induction melting has some unique characteristics that may present advantages or handicaps, depending on the application.

A coreless induction furnace contains a crucible or a refractory lining surrounded by a water-cooled power coil through which the electrical energy is applied. The metal charge contained within the refractory vessel is heated by the reversing magnetic field produced by the passage of alternating current through the coil. Very rapid heating and high melting rates are obtainable because the pieces of the scrap charge are heated from within instead of relying on radiant heat from an external source which must be conducted from the surface to the interior. Also, the induction currents stir the bath vigorously, which assures more uniform composition and temperature. Furnace capacities may range from a few pounds to 75 tons or more, with higher frequencies being required for the smaller furnaces.

While the coreless induction furnace is well-suited for melting scrap, its geometry is not well-suited for certain refining operations where large volumes of gas are generated as a result of refining reactions. The melt is contained as a long vertical cylinder for efficient coupling with the coil and as a consequence only a relatively small surface area is available at the top of the melt for evolution of gases. This situation could lead to boilover if CO is generated too rapidly when oxygen is injected for decarburization. On the other hand, the restricted bath surface minimizes heat loss as well as oxidation of the melt by the atmosphere. A representative configuration for the induction furnace is shown in Figure 2, where it may be compared to the EAF.

Induction melting is frequently employed for melting of scrap. The chemistry of the final melt is closely related to the chemistry of the scrap and usually no major refining or metallurgical activity is involved, so the scrap is carefully segregated to avoid introducing unwanted alloying elements, particularly those that are troublesome to remove from the melt. The usual reactions occur at elevated temperatures between the melt, slag, refractories, and the atmosphere, however, and must be taken into account if successful

results are to be achieved. Major refining and melt conditioning operations, if any, are usually done after the furnace is emptied into a preheated ladle.

Three major problems must be confronted when melting contaminated stainless steel waste for recycling into waste containers: (1) the removal and control of the radioactive contamination, (2) achieving the desired stainless steel composition, and (3) controlling the nonmetallic inclusion content to achieve the long term corrosion resistance. These problems are discussed in more detail in the following sections.

Nature of Activity in Scrap

Stainless steel scrap will be contaminated by radioactive isotopes that originate from three major sources: (1) fission, (2) activation, and (3) transmutation. Fission products are elements that are by-products of the nuclear reaction and result from the splitting of the original nuclei. Splitting into two equal parts is not the most probable mode; the asymmetric mode most commonly yields isotopes with atomic mass numbers between 95 and 138. Activation products result when neutrons from the nuclear reaction penetrate the fuel cladding, the structural internals of the reactor, and the reactor pressure vessel, and collide with nuclei of the atoms that make up these components, changing the atoms to unstable isotopes of the original element or splitting the impacted nuclei to form unstable isotopes of new elements. The resulting radioactivity level depends upon the chemical composition of the material, the energies of the incident neutrons, and the duration of the exposure period. Transmutation generates the transuranic (TRU) elements, which are defined as elements with atomic numbers above 92. Transmutation occurs within the nuclear fuel itself as a result of neutron capture. TRUs characteristically have long half lives. Some of them may be used as reactor fuel or for nuclear weapons after recovery from spent fuel rods.

The piping that carries the primary reactor coolant becomes contaminated on the inside surface when the fuel cladding is breached and leaks some of the fuel reaction product into the primary coolant. Those fuel products that are soluble are readily circulated throughout the primary system. Fortunately, the TRU elements are essentially insoluble in the primary coolant and remain

with the fuel. Stainless steel scrap may be TRU-contaminated if it has been used in fuel processing or reprocessing equipment.

Activation products are not mobile as they are contained more or less homogeneously within the bulk of the structures in which they were formed; however, activation products may be transported as a corrosion residue and deposited in other parts of the primary coolant system.

The by-products of a nuclear reactor will include isotopes of all the elements in the periodic table. Many of these isotopes are generated in minuscule quantities and/or have such short half-lives that they disappear in a matter of hours, days, or weeks as a result of natural decay. Other elements are produced in greater abundance, have longer half-lives, are toxic, and will be encountered in sufficient quantities when processing scrap stainless steel from nuclear applications that safe procedures must be devised to deal with these elements.

Scrap Criteria

The normal life expectancy of a nuclear power plant is about 40 years, so those plants that began operation in the 1950s will be reaching the ends of their lives in the 1990s, and additional plants are scheduled for shutdown through the year 2020. Each 1000 MWe class plant will produce 40,000 to 50,000 tons of metal waste when dismantled.⁶ Substantial additional quantities of LLCMW is or will become available from DOD sources with the retirement of nuclear-powered naval vessels and weapons-related facilities. Essentially all of the metal waste from such installations must be surveyed and much of it will be found to be uncontaminated, or contaminated with such low levels of radionuclides that it could be recycled through commercial scrap channels. On-site decontamination procedures may place additional waste in these categories. The remaining waste will range from LLCMW suitable for recycling to highly-activated reactor internals. Procedures for categorizing and recycling this waste have not yet been established.

The current inventory of LLCMW in DOE facilities includes 1870 tons of stainless steel waste contaminated at less than 10 mR/h and 1408 tons of such waste contaminated to levels between 10 and 100 mR/h.^a In addition, large quantities of LLCMW from these sources have not been characterized in terms of the above contamination level criteria.

If a facility is to be operated at the INEL for recycling LLCMW into canisters, criteria need to be established for accepting LLCMW from the various DOE, DOD, and commercial facilities. In the absence of such criteria, EG&G Radiological Engineering recommended that average beta/gamma radiation fields on contact shall not exceed 10 mR/h (up to 50 mR/h may be acceptable in certain cases), and that localized radiation fields (hot spots) up to 100 mR/h be considered on a case-by-case basis. Surface alpha contamination shall not exceed 20 dpm/100 cm². Smearable beta/gamma contamination shall be less than 40,000 dpm/100 cm². Induced radioactivity shall be less than 0.2 mR/h and internal transuranic contamination exceeding 0.1 nCi/g would be unacceptable.^a

It is apparent that the stainless steel waste to be considered as candidate material for recycling into canisters has not been well-defined and the criteria established by EG&G Radiological Engineering may not be generally accepted as they are not species-specific. It is expected that this waste will conform generally to the requirements that define low-level waste (LLW), and this effort will proceed under this assumption.

LLW is subdivided into three classes, A, B, and C,⁷ depending on the nature of the material and the degree of contamination, with Class A being the least noxious and Class C being the most. If the radionuclide concentration exceeds the limit for Class C, the waste is not considered suitable for near-surface (within 30 m of the surface) disposal, although it may still be considered as LLW. Table 1 lists the maximum quantities of radionuclides in Class C waste. If the waste does not include any of the radionuclides listed Table 1, or if the concentration of long-lived radionuclides is less than 10% of the values given in Table 1, it is Class A. Class B waste contains only the short-lived radionuclides listed in Table 1 in quantities less than those

a. K. E. Rosenberg and N. D. Stucki, *Canister Work Scope Report* (Unpublished Pre-Decisional Draft), EG&G Idaho, Inc., Idaho Falls, ID, October 1989.

Table 1. Summary of allowable nuclide concentrations in low-level waste^a

Radionuclide	Concentration		
	Ci/m ³	ppm ^b	g/m ³
¹⁴ C	8	1.8	2.2
¹⁴ C in activated metal	80	18	22
⁵⁹ Ni in activated metal	220	2750	3300
⁶⁰ Co	c	c	c
⁶³ Ni	700	11.3	13.6
⁶³ Ni in activated metal	7000	113	136
⁹⁰ Sr	7000	142	170
⁹⁴ Nb in activated metal	0.2	1.1	1.3
⁹⁹ Tc	3	150	180
¹²⁹ I	0.08	500	600
¹³⁷ Cs	4600	53	64
²⁴¹ Pu	3500 ^d	0.03	0.037
²⁴² Cm	20000 ^d	0.006	0.007
α-emitting TRU nuclides with half-life >5 yr	100 ^d	---	---
Total, all nuclides with half life <5 yr	c	c	c

a. Data extracted from 10CFR61, 1-1-88 ed., §61.55, Tables 1 and 2.

b. ppm calculated from specific activity and estimated weight of stainless steel in 1 m³ of scrap, using equation from ref. 10 and half life data from Reference 11. 1 ppm = 1 g/metric ton.

c. No limits established for these radionuclides in Class C waste. Practical considerations such as the effects of external radiation and internal heat generation on transportation, handling, and disposal will limit the concentration of these wastes.

d. Units are nanocuries per gram.

given. Generally, the radionuclides permitted in Class A and Class B waste will have decayed in 100 years or less, while Class C waste will require a longer decay time and thus requires deeper burial and/or intruder barriers that will last 500 years or more.

From a practical standpoint, when LLW is prepared for disposal, it is packaged and the isotopic content is estimated from readings taken at the exterior surface of the package. Hence, the values given in 10CFR61 are based for units of volume, rather than weight. A useful working number for the bulk density of stainless steel scrap is 75 lb/ft^3 , which converts to 1201 lb/m^3 , about 15% of the density expected were the alloy cast into a solid 1 m^3 block. Using the value of 1200 kg for a cubic meter of stainless steel waste, the allowable concentrations of radionuclides were converted into g/m^3 based on the specific activities⁸ and these values are given in the last column of Table 1.

The values given in the table should be considered as a "worst case" situation; they are given here to establish an estimate of an upper boundary for what is possible to encounter in stainless steel classified as LLW. Also, the table lists the maximum allowable quantities of individual radionuclides. These maximums would be reduced for mixtures based on the "sum of the fractions rule", where the fractions present of the allowable concentrations cannot exceed 1.0 when totaled.

One major objective of this program is to avoid the various costs and complications of shallow land burial by separating radioactive contaminants from the stainless steel waste classified as LLW to the extent that this steel would be satisfactory for use as HLW canisters. But it is apparent that the maximum radionuclide loadings that could be encountered in LLW would exceed the limits for exposure of personnel during facility dismantling, scrap preparation, and the various melt shop activities. The recommended maximums given by EG&G Radiological Engineering are orders of magnitude below the upper limits established for Class C waste, but the figures given by Radiological Engineering for incoming LLCMW do not translate readily into specific nuclide loadings. In any case, some remote operations will be necessary if the most contaminated LLW is to be processed and such operations would result in astronomical recycling costs.

Removing/Decreasing Scrap Contamination

Much of the LLCMW recovered during decommissioning of a nuclear reactor will be in the form of pipe and tubing ranging in size from 1 to 4 in. in diameter. Larger and smaller diameters will also be encountered. When present, most of the contamination will be part of a corrosion product coating that adheres tightly to internal surfaces. The simplest approach would seem to be to decontaminate this waste simultaneously with the decontamination and decommissioning (D&D) of the facility, as the temporary containment structures (decon rooms) will be in place, and trained personnel and monitoring equipment will be available. The packaging and shipping requirements will be much simpler for those items that exhibit no contamination. This approach may be applicable also to dismantling of unneeded, obsolete, or failed processing equipment for nuclear fuel and its by-products. However, the additional permitting requirements and the generation of a new waste stream may add sufficient new complications and costs to this approach to outweigh other advantages that seem apparent.

Decontamination procedures would become more difficult with the increasing complexity of components. Large components and those with convoluted shapes and internal crevices will be particularly challenging. The scrap that must be cut apart on the scene should be reduced to a size suitable for direct charging into a melting furnace so as not to require further handling for size reduction. Also, components made up of dissimilar alloys should be disassembled to avoid unnecessary contamination of the scrap with heavy metals and the production of a slag or baghouse dust that will be classified as a mixed waste. All of this effort will be labor-intensive and costly, and will increase personnel exposure to radiation. Whether the LLCMW is to be cut up and decontaminated at the facility undergoing D&D or whether some of these operations will be done at the melting facility depends on the total cost of contamination control, packaging, shipping, and personnel exposure.

It would appear that components that are surface-contaminated only would be the best candidates for recycling. Surface treatment to remove ^{60}Co would be important because this element cannot be removed by melt refining and will become homogeneously dispersed in the castings. After such dispersion has

occurred, the only means currently available for ^{60}Co removal is to allow it to decay naturally, a process that will require more than 50 years if at least 10 half-lives remains the criterion for small amounts of a radioisotope to decay into insignificance. On the other hand, in the surface contamination the Co is relatively concentrated in a coating that may be easily dislodged, enabling the contamination to spread. Melting such surface-contaminated waste will result in considerable dilution of the Co, and self shielding by the host metal will reduce the effect of the contained Co even more, especially in thick sections.

Several techniques have been investigated for treatment of surface contaminated metal waste. Regardless of the technique, a radioactive or mixed waste will be generated which will require disposal, and the nature of this waste and the difficulty of converting it into a stable waste form may be the factors that decide which surface cleaning process, if any, is selected.

A variety of proprietary compounds are available to clean contaminated surfaces, even surfaces covered with a very adherent layer of corrosion deposit. These compounds are mixed with water (6 to 32 oz/gal) to form acid or alkaline solutions that are heated to 140 to 250°F (60 to 120°C); the parts to be decontaminated are submerged in these solutions for an hour or more. Considerable solution volume is required, with occasional spot scrubbing needed by operating personnel. Large components are difficult to clean if a 1-in immersion is required. The quantity of solution is substantial, and added to this is rinse water. The product of this effort will be cleaner scrap, a mixed waste sludge, and a substantial volume of radioactive solution that will require treatment before discharge.

Perhaps the most effective on-site decontamination is by electrochemical means.⁹ This process uses the piece to be cleaned as the anode and the passage of electric current causes the surface to go into solution, leaving a very smooth surface. Phosphoric acid was the preferred electrolyte in concentrations of 40 to 80% at 40 to 80°C, using electrode potentials of 8 to 12 V, and current densities of 50 to 250 A/ft². Decontamination times ranged from 5 to 30 min and between 0.3 and 2 mils were removed from the surface. Frequently, the contamination level was reduced to background.

Normally, the phosphoric acid solution can operate satisfactorily until the metal loading reaches about 6%. Criticality limits dictate the maximum fissile material content. Procedures are available to extend electrolyte life, such as liquid-liquid solvent extraction and/or ion exchange, but eventually the electrolyte must be treated as are other decon solutions prior to disposal.

Other methods for decontaminating surfaces include shot blasting and blasting with dry ice particles. The shot is easily separated from the debris and reused. The dry ice method has the advantage of the blasting agent subliming into CO₂ which may be exhausted, leaving only the residue, but neither of these mechanical methods can decontaminate cracks and crevices or small parts with convoluted shapes.

Decon treatment at the D&D site will not eliminate the need for decon facilities at the foundry. D&D site decon may only be sufficient to remove (or cover) smearable contamination, and LLCMW retrieved from shallow land burial, or from the INEL, may require treatment at the foundry before charging it into a melting furnace. In some cases, reduction of contamination by the melt refining step itself may be more effective than prior treatment of the scrap.

Decontamination by Melting

Interest in decontamination of steels began in the 1950s when the accumulation of uranium-contaminated scrap at some locations became so large as to be burdensome. The early reports on this activity gave the results of the ingot analyses with little apparent regard for the uranium concentration in the scrap or the composition of the slag, when one was used. For purposes of comparison and to establish a baseline, some heats of carbon steel produced before 1942 were analyzed and the uranium content averaged 0.06 ppm.¹⁰ Stainless steel produced before 1942 averaged 0.23 ppm uranium.¹¹

Removal of Uranium from Steels

The first production-scale steel decontamination project described in the literature was undertaken by the National Lead Co. of Ohio and involved

6,000 tons of LLCMW.¹² The scrap consisted of discarded uranium extraction equipment and baled drums; these drums had been used for shipping uranium concentrate. A commercial steel mill agreed to perform the task using an electric arc furnace. Their efforts focused on monitoring the exposures of foundry personnel that resulted from processing this waste, and no analytical data were given for residual uranium in the ingots or in the slag. Mautz, *et al.*,¹³ learned through personal communication that the ingots averaged <3 ppm uranium while the slag contained 2.12% uranium. The slag weight constituted 8.5% of the weight of the steel melted, so that by calculation the average original uranium content of the scrap was 0.2% or 2000 ppm. The level of contained uranium in the ingots was below regulatory concern and they were sold on the commercial scrap market, while the slag was shipped to Oak Ridge for disposal.

In a related effort, the process described above was applied in 1958 to 350 tons of LLCMW that was contaminated by shipping and processing radium concentrates.¹⁴ The same mill was used for this work. After smelting, the ingots averaged 9.0×10^{-13} g Ra/g steel and the slag averaged 1.47×10^{-9} g Ra/g slag. The concentration of Ra in the ingots was 0.06% of that in the slag, or the concentration ratio, slag/ingot, was 1633:1.

The Y-12 plant at Oak Ridge supervised the melting of a 20-year accumulation of LLCMW in a 10-ton electric arc furnace.¹³ This campaign processed 27,000 tons of scrap, requiring 2037 heats for the carbon steel scrap and 218 heats for the stainless steel scrap. Analytical data show the mild steel ingots averaged 0.4 ppm, with 94.3% of the heats containing 1.0 ppm or less, while the stainless heats averaged 0.6 ppm, with 79.8% of the heats containing 1.0 ppm or less. No data were reported on the content of the scrap before melting, but the slags (compositions unspecified) for the carbon steel heats averaged 2630 ppm (0.26%) uranium. The final disposition of the ingots and the slags was not mentioned, but it is presumed that the residual activity in these ingots was considered to be below regulatory concern and that the ingots were disposed of through commercial scrap channels.

Removal of Transuranics from Steels

Processing of spent nuclear fuel to separate useful isotopes from waste material is producing LLCMW containing a variety of radioactive contaminants, including isotopes of plutonium and other transuranics. Recent experimental work dealing with this problem has been more definitive than the works cited previously in terms of the melting parameters vs. the results, but few of the recent works have dealt with decontamination of LLCMW on a production scale.

UO₂ has been used as a "stand-in" for PuO₂¹⁵ because of their very similar chemical behaviors in the environment produced by melt-refining, and for this reason UO₂ will be included with the transuranics in the discussions of decontamination by melt refining. In contrast to earlier works, the more recent studies investigated the effectiveness of various slag compositions, slag-refractory interactions, melt temperatures and times, and distribution of the isotopes as a result of refining processes. In all instances involving the melting of scrap, a major uncertainty is the scrap assay, as no method has been devised as yet to sample heterogeneous scrap and obtain a reliable and accurate value for the isotope content. This is analogous to the age-old problem of sampling ores to obtain a reliable value for the precious metal content. For the sake of experimental accuracy, adding a known quantity of the contaminant to an uncontaminated heat of metal is the preferred approach.

Experimental metal decontamination programs at Argonne^{15,16} and Oak Ridge^{17,18,19} investigated the removal of uranium, plutonium, and americium from ferrous and non-ferrous melts using small (50 to 500 g) heats and bench scale equipment. These studies investigated in some detail the thermodynamics of the systems, slag compositions, slag-melt interactions, slag-refractory interactions, extraction ratios, etc., with emphases in these programs on reducing the volume of material requiring disposal, converting scrap into a readily-assayable form, and reducing the mobility of the contaminants, rather than attempting to decontaminate for recycling. The processes studied were to be suitable for up-scaling in order to treat the ever-increasing volumes of accumulated contaminated scrap and permit maximum utilization of shallow land burial with possible subsequent retrieval. If the total transuranic content could be reduced to <10 nCi/g (equivalent to about 0.1 ppm Pu) or less, the potential hazards would be reduced to the extent that retrievable shallow land

burial would not be required and the metal castings could be disposed of in commercial landfills without concern for retrievability according to the regulations in effect at that time. No figure is presently available for TRU concentrations considered to be "below regulatory concern," which would enable sale of decontaminated ingots for recycling through commercial scrap channels.

The Argonne program used a Brew furnace with a tungsten mesh resistance element that would enable the charge to be heated to 1800°C in "any desired atmosphere" (presumably excluding those containing any oxygen; otherwise the tungsten element would have been destroyed). The furnace was evacuated and backfilled to 400 mm Hg pressure with dry helium and the crucible contents were heated to 1500°C and held at temperature for 1 h. The melts were allowed to solidify in their crucibles and the resulting ingots and slags were analyzed by autoradiography and/or a fission track analysis technique. TRU contents as low as 0.002 ppm of ^{239}Pu equivalent could be detected by autoradiography, while the detection limit for Pu and Am using aqueous dissolution and radiochemical determination was 0.001 ppb. The fission track analysis technique also exhibited excellent sensitivity (to 0.04 ppb Pu). The radiography and fission track techniques would pinpoint localized concentrations while the dissolution technique would provide information on the average concentration in the bulk sample.

Most of the melts in the Argonne study were done using 200 g of mild steel with about 20 g of slag, or a slag/metal ratio of 0.10. Alumina crucibles of 100 mL were used. Melts were generally contaminated with 400 ppm Pu (as PuO_2), although as much as 1.4% (14,000 ppm) Pu was added in one instance. The PuO_2 was added to a cavity machined into the bottom of the sample to be melted, which was then sealed with a metal plug, or it was blended with the slag so that the slag would contaminate the melt. No differences in results were noted that could be traced to the method of adding the PuO_2 . A majority of the melts used a borosilicate slag^a, but CaSiO_3 and $\text{CaMgSi}_2\text{O}_6$ slags were used also. The results of this effort were similar to those achieved with the production-scale melting campaigns to reduce uranium and radium in contaminated scrap in that the contaminants in the steel were

a. A Dow Corning 7740 glass, 81.0% SiO_2 , 13.0% B_2O_3 , 4.0% Na_2O , 2.0% Al_2O_3 , and 0.5% K_2O , by weight.

reduced to very low levels and were concentrated in the slags. It was interesting to note that the Pu remaining in the ingots was concentrated at or near the ingot surface, apparently in adhering or entrained slag, or in non-metallic inclusions in the ingot interior. Except for the Pu content, no analysis of the inclusions was given; however, it may be assumed that the composition of the inclusions was fairly close to that of the slag. In some instances, the Pu was concentrated in "clusters" within the ingot. The nature of these clusters was not clearly defined but it was speculated that they resulted from precipitation of PuO_2 which may have had a finite solubility in the molten steel. Where no inclusions or clusters were found, the Pu content of the metal was reported to be as low as 0.04 ppb. The dissolution and counting technique showed higher Pu contents than the autoradiography or fission track method on the metal matrix of the same samples because the dissolution technique averaged-in the inclusions, clusters, and any other casting defects in which Pu may have been concentrated.

In the cases where more than 400 ppm Pu was added to the melt, the Pu content and distribution in the ingot were about the same, even when the Pu additions ranged between 660 and 13,700 ppm. These melts weighed only 11 to 13 g. The Argonne reports did not specify how the Pu was added to these small melts, but it seems likely in these cases that the Pu was added to the slag and allowed to equilibrate with the molten steel rather than being sealed into the bottom of the cold metal charge as was done with the 200 g melts. In theory the end result should have been the same, however, complications occur in practice that are not accounted for by the assumptions in the theory.

"Staged melting" was done on one heat where portions of two previously-melted ingots were remelted using a clean slag. The result of this experiment was an even greater reduction in Pu content. The initial content of the charge was reported as "about 0.1 ppm" Pu, while the ingot resulting from this melt averaged 0.002 ppm Pu. Based on what was reported previously, the cleanup must have resulted from a significant reduction of Pu-containing inclusions, since the dissolution and counting technique employed for analyses includes the Pu contained in these defects. It is possible that a similar result could have been obtained by a longer holding time in the crucible to allow time for the oxide particles suspended in the melt to coalesce and float into the slag. This is more easily done in the resistance furnace employed

for this work as the melt agitation developed by induction heating is absent and only convection currents are operative. The inclusions still trapped in the first melt had an additional hour to float to the surface in the second melt. The total melting time for both heats of the double melt was 2 h. Two other single melts held for this much time under a borosilicate slag yielded similarly low Pu contents, leading to a conclusion that longer holding times may be nearly as effective as staged melting.

Copeland and coworkers at Oak Ridge performed experiments similar to those done at Argonne, but studied a wider range of metals and slags and relied more heavily on a thermodynamic approach to metal-slag interaction. The Oak Ridge study used UO_2 and PuO_2 as contaminants, adding them to the flux and assuming that equilibration during melting would produce the same result as would adding it to the metal charge. Both mild steel and stainless steel (type unspecified) were melted with induction being the primary melting method. Metal weights between 50 and 500 g were employed, with 100 g melts predominating. Flux was added so that it equalled 10% (5% in a few instances) of the metal weight, and UO_2 or PuO_2 was thoroughly mixed with the flux so that it would be equivalent to 500 ppm (≈ 440 ppm U or Pu) in the metal. Melting times ran between $\frac{1}{2}$ and 1 h and melts were allowed to solidify in the crucible. Ingots assaying between 0.01 to 0.1 ppm U and <1 ppm Pu were obtained for both mild and stainless steel melts. The results for mild steel were not as low as those obtained by Argonne even though similar dissolution and counting analytical techniques were used. Halving the slag weight had no apparent effect on the refining capability, but double melting reduced the Pu level to 0.1 ppm, which was a goal of their effort. The Oak Ridge study concluded that halving the slag weight and double-refining was an effective approach and could reduce the quantity of waste requiring disposal by retrievable shallow land burial.

Removal of Fission Products from Steels

Relatively few studies as detailed as the investigations by Argonne and Oak Ridge have been done for removal of fission product contamination from steels by melt refining. The most abundant long-lived fission products, ^{137}Cs and ^{90}Sr , readily form stable oxides as do U and Pu and they should be removed readily and effectively by the slag. Cs_2O has a relatively high vapor

pressure at the temperatures used for melting steel and will evaporate from the slag, so accumulations in the exhaust system must be anticipated. Chemically, Sr behaves similarly to Ca and should be retained in the slag in the same manner. Removal of other fission products has not been studied in great detail as most of them have short half-lives and have decayed to insignificance by the time scrap steel is available for processing. Some fission products that are common enough to be encountered in scrap stainless steel are listed below, along with their half-lives (in years):

^{144}Ce	0.78	^{154}Eu	16.0
^{106}Ru	1.00	^{90}Sr	28.1
^{155}Eu	1.80	^{137}Cs	30.2
^{134}Cs	2.05	^{99}Tc	2.1×10^5
^{125}Sb	2.70	^{129}I	1.7×10^7

For LLCMW that has been in storage for about 30 years, small quantities of the isotopes in the left column will have decayed to insignificance, 25% of the ^{154}Eu , and about half of the ^{90}Sr and ^{137}Cs will remain. The ^{99}Tc and the ^{129}I will be present in essentially their original quantities. If these two isotopes are in the scrap, melting will remove the volatile iodine but the technetium will be about as difficult to remove selectively as molybdenum. Tc contaminated scrap should be avoided unless melting is to be done for volume reduction only.

A six-ingot scoping study was performed at Hanford²⁰ using an induction furnace to make 2.27 kg (5 lb) melts. The charge for each melt consisted of five uncontaminated stainless steel bars, two of which were then contaminated. One was painted with a slurry containing PuO_2 so that the bar contained 0.8 to 1.0 g of Pu (an addition to the total melt of 350 to 440 ppm), and another bar was dipped into an acidified solution of beta-gamma source from Hanford "tank waste" and was coated with up to 7 μCi of ^{60}Co , 640 μCi of ^{137}Cs , and 42 μCi of ^{155}Eu . The analytical techniques used for these experiments were mostly qualitative, using a "C. P." instrument for comparative surface readings, and autoradiography. Such measurements made comparison with the Argonne and Oak Ridge studies difficult. A flux resembling the borosilicate glass composition was used, but the high SiO_2 content caused attack of the MgO crucibles. The autoradiographs showed that the ingot contamination was concentrated on the

surface and in inclusions, and ingot analyses (by wet chemistry) showed levels of residual Pu in the 0.1 to 0.085 ppm range. Residual quantities of Cs, Sr, and Eu were not indicated.

Previous work at the INEL in melting contaminated stainless steel scrap was concerned primarily with reducing the volume of the scrap to conserve a dwindling waste storage capacity at the Radioactive Waste Management Complex (RWMC). The Waste Experimental Reduction Facility (WERF) was established to process a variety of low-level beta/gamma-contaminated waste. A 750 kW induction furnace was used to demonstrate that melting the scrap and casting it into 680 kg (1500 lb) ingots was a safe and effective method for achieving at least a 10-fold reduction in volume, converting the scrap into a readily assayable form, and stabilizing any radioisotopes remaining in the ingots.

The contaminated scrap was generated by various INEL facilities and consisted mostly of salvaged reactor and test support components that were surface contaminated only. The contaminants were ^{60}Co , ^{90}Sr , and ^{137}Cs , although small amounts of other isotopes may have been present in some cases.

The WERF induction furnace has converted many tons of contaminated stainless steel waste into ingots since it began operation in July of 1983 with a primary objective of volume reduction. The maximum isotope content in any of these ingots was estimated to be about 10 μCi in 680 kg. Based on the specific activity, if this 10 μCi were entirely ^{60}Co , it would be equivalent to 8.8×10^{-9} g in 680 kg, or 1.3×10^{-8} ppm, or 0.013 parts per trillion. Thus the radioactivity in the ingots had been so low that no basis existed for predicting the dispersion of isotopes that resulted from melting nor for developing a rationale for modifying the melting practice in order to control isotopes carried on more highly-contaminated scrap.

Three "spiked melts" using sub-sized heats were made in order to resolve these questions.^a Known quantities of ^{60}Co , ^{85}Sr , and ^{137}Cs were added to uncontaminated stainless steel; the melt sizes ranged between 230 and 320 kg

a. M. M. Larsen, G. A. Reimann, and C. D. Reno, unpublished work on spiked melt tests at the waste experimental reduction facility, Idaho National Engineering Laboratory, Idaho Falls, ID, February, 1985.

(510 and 700 lb). ^{85}Sr was used instead of ^{90}Sr because it is a gamma emitter (^{90}Sr is a beta emitter) and is therefore easier to detect in the minute quantities used for this work. The 200 to 300 kg melt size was selected because it was the smallest amount that could be coupled effectively in the 700 kg induction furnace and poured into a representative casting using the existing ingot molds.

Contaminants were added to the charge by wrapping the desired addition in metal foil and sheet metal to form a package that could be placed in the bottom of the cold crucible before adding a charge of uncontaminated stainless steel. The quantities of isotopes added to the charge for the 230 kg melt were 50 μCi of ^{60}Co , 5 μCi of ^{85}Sr , and 5 μCi of ^{137}Cs . The quantities were adjusted proportionately upward for the 320 kg melt. The amounts of each isotope, as calculated from their specific activities, were: 1.9×10^{-7} ppm ^{60}Co , 9.1×10^{-10} ppm ^{85}Sr , and 2.5×10^{-7} ppm ^{137}Cs . These are minuscule additions compared to what might be encountered in LLCMW or in comparison to the 400 ppm quantities added in previously-described bench-scale experiments. The flux used for this work was "Slag Gel 160", which was described as "100% perlite ore,"^a the nominal composition of which is given as: 72% SiO_2 , 13% Al_2O_3 , 4.5% Na_2O , 5.0% K_2O , and 0.7% CaO . For the three melts in question, between 0.3 and 1.0 kg of flux was employed. The flux charge constituted between 0.09 and 0.44% of the metal charge compared to the 10% used by workers cited previously. This amount was considered sufficient to combine with the oxides of Fe and Cr generated during heat up and melting to ensure they remained liquid and did not bridge over the melt, which would prevent monitoring temperature, adding charge, or pouring. The slags resulting from 0.3 to 1.0 kg of flux weighed between 3.6 and 4.5 kg, indicating they were quite high in Fe and Cr oxide content, which would reduce their ability to capture Sr and Cs.

The results of this effort showed that 91 to 100% of the Co, 0 to 15% of the Cs and 0 to 4% of the Sr remained in the ingots. Most of the Sr was collected in the slag, while most of the Cs went to the baghouse. An accurate materials balance was not easy to obtain. The amounts of added contaminants were so small that minimal sample contamination could seriously skew the

a. Personal Communication, P. Devlin, Asbury Graphite, Rodeo, CA, Feb. '90.

results. The uncontaminated feed metal showed a trace of ^{85}Sr (half life: 64 days) at a level of about 1% of what was found in the ingot. In the case of the slag, the distributions were difficult to measure not only because so little isotope was present but also because sampling was imprecise. For example, it was difficult to account for all the slag since some was attached to the ingot and the dipping tools, while some reacted with the furnace refractory and remained in the furnace. Also, the slag entrained some metal and the metal entrained some slag. As a rough estimate, 0.1 to 0.3% of the Co, 36 to 66% of the Sr, and 14 to 17% of the Cs was found in the slag.

The material charged for the three heats was 776 kg and the resulting ingots weighed 746 kg. Averaging the three heats and compensating for the melting losses, the total residual activity in the ingots was 164.7 μCi . This value compares with 196 μCi added to the charge. At first glance the net change seems unimpressive; however, while the ^{60}Co content remained essentially unchanged, only 7.8% of the ^{137}Cs and 0.8% of the ^{85}Sr remained in the ingots. It was not expected that significant Co removal would be achieved, but the reduction in Cs and Sr should be considered excellent in view of the very small original contents and the small quantity of oxide-laden slag that resulted from air melting the stainless steel.

The Europeans have been active in treating radioactive scrap by melting techniques for both volume reduction and recycling. Translations are not yet available for many of their reports. Some of these studies have been done using full-scale production equipment.

One such study in France²¹ entailed melting of portions of a rejected heat exchanger from the Chinon A power plant that had a total activity between 10 and 20 mCi per metric ton, which was more than 75 times the activity, on a per ton basis, than that used for the INEL spiked melt tests. The electric arc furnace selected for this work had a capacity of 4 to 5 metric tons and was equipped with an effective exhaust and filter system. The 3.8 metric tons of scrap was flame cut into pieces not exceeding 1 meter in length (221 man-hours were required). Oxygen was injected after the charge was melted, followed by deoxidation with "manganese salt". The metal was poured into previously-prepared sand molds to produce four castings with a combined weight of 3660 kg. The slag weighed 200 kg (5.3% of the metal charge weight) and

collected dust weighed 30 kg. Of the total activity involved, 76 mCi was found in the ingots (99.7% as ^{60}Co , 0.2% as ^{54}Mn , and 0.1% as ^{65}Zn), while the balance of the activity was found in the slag (217 μCi , 0.3%), the filter dust (148 μCi , 0.2%), and the molding sand (38 μCi , 0.005%). A "fairly high amount" of cesium was found in the filter dust, but the quantity was not disclosed. Measurements outside the plant failed to reveal any radionuclides other than those considered as background. Checks inside the plant in the vicinity of the furnace during operation showed activities that did not exceed the maximum permissible concentration level of 10 pCi/m^3 . The report concluded that the dose rates involved are insignificant enough to permit achievement of a large-scale (4000 mt) operation in complete safety. Such an operation would be three orders of magnitude larger than the test just described, and it appears likely that after 1000 heats had been melted in the 4-ton electric arc furnace the radiation levels in the melting area and on the downwind side of the plant would be substantially higher than the levels observed after a single melt if the operations were conducted in the same manner as described.

Removal of Activation Products from Steels

Some radionuclides have chemical characteristics that are the same as or very similar to those of the major components in stainless steel. In a melting and refining operation, these isotopes will behave chemically in the same manner as the major alloy components. Other isotopes, while being quite different in chemical characteristics from the major alloying components, have fairly high vapor pressures and are resistant to oxidation, but will readily alloy with steel. The noble metals fall into this group. In effect, these isotopes cannot be removed, so LLCMW heavily laden with them is to be avoided except when the sole purpose for melting is for volume reduction prior to disposal. Since most of these isotopes are produced as a result of activation, a restriction on the quantity of activation products, as recommended by EG&G Radiological Engineering, provides a remedy for this problem. Some examples of these radioisotopes and their half-lives²² are listed in Table 2.

Table 2. Examples of non-removable isotopes

<u>Isotope</u>	<u>Half Life</u>	<u>Isotope</u>	<u>Half Life</u>	<u>Isotope</u>	<u>Half Life</u>
⁵¹ Cr	27.8 d	⁵⁷ Co	270.0 d	⁹⁹ Tc	2.12x10 ⁵ y
⁵⁴ Mn	303.0 d	⁶⁰ Co	5.27 y	¹¹⁰ Ag	253.0 d
⁵⁵ Fe	2.6 y	⁵⁹ Ni	8x10 ⁴ y	¹⁹⁵ Au	183.0 d
⁵⁹ Fe	45.1 d	⁶³ Ni	92.0 y		

SLAGS

Many impurities associated with iron ores are difficult to melt and would seriously interfere with the smelting process if they remained unfused. A flux is added to combine with these impurities and form a slag, which has a lower melting point and is readily fusible in the temperature range used by the process of interest. Selecting the proper flux to produce the desired slag is a chemical problem that requires a knowledge of the composition and properties of all the materials that come into contact with the slag at the operating temperatures. Many elements in the ore are reduced with the iron and remain in solution, or are in chemical combination, so a secondary purpose of a flux is to form a liquid in which the undesired elements may combine in preference to the iron. Such a liquid is a refining slag and this study will deal with the effectiveness of refining slags in treating LLCMW.

In ferrous melts, silica is the ubiquitous slag component. Silicon's small radius and high charge result in tightly-bound tetrahedral SiO_4 which, when joined to adjacent tetrahedra, forms a three-dimensional network that persists without dissociation at temperatures well beyond the melting point of silica. The tetrahedra are joined at the corners so that the oxygen atom at each corner is shared by two tetrahedra. In a pure silica melt, the tetrahedra remain cross-linked with one another above the melting point to form a semi-rigid structure. The shear stress required to cause flow is high because many primary bonds must be broken when shear occurs. Viscosity decreases with increasing temperature as larger numbers of bonds are broken by the increased thermal energy.

When a metal oxide such as CaO is added to a silica melt, an excess of oxygen ions is introduced which interrupts the bridging necessary to maintain bonding between the SiO_4 tetrahedra. The double oxygen bond that constituted the shared corner of two tetrahedra becomes a single oxygen bond so that the tetrahedra corners are no longer joined. The Ca ion must remain in the structure for charge balance. The face-to-face linkage of tetragonal units becomes arranged hexagonally (or into rings). As depolymerization progresses with added metal oxide, the rings themselves break apart and form linear chains of tetrahedral units.^{23,24} At constant temperature, viscosity

decreases as a function of depolymerization, particularly as the polymer network becomes less complex.

Slags are characterized as "acid" or "basic" according to the silicate degree or the basicity, depending on the slag's tendency to react with the containing refractories as well as the slag's ability to refine the underlying metal by selectively removing impurities. Slags high in silica are acid slags, while those high in metal oxides are basic slags. The terms "acid" and "basic" are rooted in alchemic observations of similarities in the behavior of aqueous solutions and oxide melts. Various rationales have developed to define acid-base phenomena. An acid is any chemical species that can accept an electron or an electron pair, while a base is any species that may donate an electron or electron pair. The terminology is useful for understanding the nature of chemical reactions, as nearly all reactions may be explained in terms of acid-base behavior. For aqueous solutions a uniform quantitative scale has been devised so that the concentration of H^+ or OH^- may be expressed as pH or pOH. Presently, no analogous system is available to characterize oxide melts.

The process to be used for smelting contaminated stainless steel for conversion into canisters will begin with a cold charge of scrap. The processing required will resemble what is considered to be "standard" foundry practice for producing stainless steel castings by induction melting. (Induction melting was chosen because of its versatility and its suitability for the melt sizes under consideration, and because its basic configuration appears to lend itself better to the control of effluent.) The slag functions in the induction furnace will resemble what would be expected from refining slags, although in the usual foundry practice melt refining is seldom performed in the induction furnace itself.

Induction furnaces in the size range contemplated for pilot plant work use rammed refractory linings rather than crucibles. High purity alumina is frequently used for induction furnace linings because its durability in a variety of melting environments compensates for its additional cost. As refractories go, alumina is considered neutral (that is, neither acid or basic); however, aluminosilicates will form with highly siliceous slags, so alumina behaves as a base under such conditions, while calcium aluminates will

form with very basic slags and alumina behaves as an acid. Also, alumina is vulnerable to fluorides (as are most other refractories), which are frequently added to the flux to decrease slag viscosity.

The flux is added to the charge to combine with the oxides that form when the charge is brought to the melting temperature. While these fluxes (coagulants) are highly siliceous, the SiO_2 content is diluted by the metal oxides (mostly Cr_2O_3 , FeO , and MnO) by the time the crucible is fully charged. When air melting is done and only a small amount of flux is used, oxidation may be substantial, and if the quantity of oxide generated is more than can be liquified by the amount of flux added, bridging may occur. Bridging results when oxides solidify above the melt surface to form a very strong crust that resists penetration by mechanical methods. The crust prevents monitoring of melt temperature, charging more scrap, and even may prevent pouring the heat. If it is not allowed to become too thick and become cold due to heat loss, the crust may be liquified by the addition of silica which will reform fayalite (Fe_2SiO_4 , m.p. 1205°C). In smaller furnaces, the high oxide slag may be dipped out manually before pouring; with larger furnaces this method becomes a time-consuming chore. A substantial quantity of oxide inclusions in a steel ingot is of little consequence if radioactively-contaminated steel is being melted solely for volume reduction, but the inclusions will be a source of defects and a cause for product rejection when high quality material is specified for the canisters.

When melting is done under an inert atmosphere or in a vacuum, the formation of large quantities of oxide is avoided, and the FeO and Fe_2O_3 normally formed due to exposure to air is unavailable to convert the siliceous flux into a fluid slag. Additions of lime (CaCO_3), dolomite (Ca,MgCO_3), soda ash (Na_2CO_3), borax ($\text{Na}_2\text{B}_4\text{O}_7$), fluorite or fluorspar (CaF_2), etc., will compensate. Magnesia (MgO) refractories are employed when high lime slags are used for sulfur and phosphorus reduction.

Decontaminating Slags

A variety of slag compositions was tried for the removal of uranium and transuranics in the bench scale tests conducted at Argonne and Oak Ridge^{16,18,19} and by others.^{25,26} Unfortunately, the various laboratory studies were

concerned with U and Pu removal, and little attention was paid to removal of Sr and Cs.

The slag compositions employed and the results obtained are shown in Table 3. In the Oak Ridge work, the flux compositions were considered to be the same as the slag compositions. The desired quantities of U and Pu were added to the flux before melting began, assuming that when the melt cycle was completed the slag would have contaminated the melt to the same level as it would have been had the contaminant been added to the metal and extracted into the slag. This assumption is valid only when equilibrium is achieved, which

Table 3. Slag composition vs. melt decontamination

Composition, wt %								Slag Weight, % ^a	Contaminant (ppm)			
SiO ₂	CaO	Al ₂ O ₃	Fe ₂ O ₃	Na ₂ O	K ₂ O	CaF ₂	Other		Ingot	Slag	Ref.	
81	--	2	--	4	0.5	--	13 B ₂ O ₃	10	Pu	0.003	3000	17
80	--	2	--	4	1	--	13 B ₂ O ₃	10	Pu	0.6	1120	20
80	--	2	--	4	1	--	13 B ₂ O ₃	5	Pu	0.75	3680	20
75	25	--	--	--	--	--	--	10	U	<0.01	2260	19
60	--	40	--	--	--	--	--	10	U	2.53	346	19
60	30	10	--	--	--	--	--	10	Pu	0.42	2240	20
60	30	10	--	--	--	--	--	5	Pu	0.21	2640	20
52	48 ^b	--	--	--	--	--	--	10	Pu	0.6 ^c	1900	17
52	48 ^b	--	--	--	--	--	--	15	Pu	0.016 ^{c,d}	37000	17
40	30	20	--	--	--	10	--	10	U	0.10	e	28
35	65	--	--	--	--	--	--	10	U	0.28	73	19
30	50	10	5	--	--	5	--	10	U	0.05	507	19
30	40	10	15	--	--	5	--	10	Pu	0.30	1700	20
30	40	10	15	--	--	5	--	5	Pu	0.50	4880	20
10	60	25	--	--	--	5	--	10	U	2.39	231	19
10	40	40	--	--	--	--	10 NiO	10	U	0.005 ^c	e	28

a. Slag weight as a percentage of metal weight.

b. Actual composition given as CaMgSi₂O₆.

c. Mild steel ingot.

d. 7100 ppm Pu added to 13 g charge.

e. Slag not analyzed.

seldom occurs. Other investigators inserted contaminants into a cavity in the base of the melt stock, or covered the surface of the melt stock with a contaminated coating. The latter methods are preferred as they more closely resemble conditions that will be encountered in practice. In most studies a complete slag analysis was not reported, only the level of contamination, assuming that the slag would have essentially the same composition as the flux.

No clear trends are discernable from the above table as to whether any slag compositions are superior to others with regard to uranium and plutonium removal. Some experimenters obtained fair decontamination of stainless steel simply by melting without any flux. In such cases, oxides of contaminants combined with the crucible refractory and/or dissolved in the oxides that normally float to the top of the melt.

Lower decontamination efficiencies were associated with the high silica slags²⁰, and this observation is confirmed by Abe, *et al.*, who claimed that better decontamination was achieved when the basicity was 1.5, that is, the ratio of metal oxide (CaO) to $\text{SiO}_2 + \text{Al}_2\text{O}_3$ was 1.5:1.²⁶ In this case, alumina was considered as an acid component of the flux. The decontamination effect was additionally improved by maintaining the given basicity ratio and adding either CaF_2 or NiO. None of the flux formulations listed by Abe, *et al.*, showed a specific composition of 60% CaO, balance silica and alumina. The ternary phase equilibrium diagram²⁷ for these compounds reveals melting points well beyond the reach of the equipment (1800 to 1950°C) for some combinations of 60% CaO plus silica and alumina, with usable melting points (about 1500°C) occurring only below the 10% SiO_2 level. Therefore, we would assume that the most efficient slag for this effort had a composition approximating 10% SiO_2 , 60% CaO, and 30% Al_2O_3 . Whatever the actual composition of the slag, a decontamination to 0.04 ppm U was obtained. Adding 10% of CaF_2 or NiO to this mix reduced the contamination level to 0.02 ppm. Abe, *et al.*, also reported better U decontamination at 1700°C than at lower or higher temperatures, and estimated that 0.1 h was sufficient time at this temperature for the reaction to go to completion (with 100 g melts).

Apparent anomalies are evident in Table 3, which was compiled from the data of several investigations. The table concentrates on stainless steel

melts, although a large amount of data was accumulated and a wider variety of slag compositions was used with mild steel. In the table, the poorest decontaminations were obtained with both very high and very low silica slags. The poor results were attributed to contamination of the slag due to attack of the magnesia and zirconia crucibles as well as absorption into the crucible wall,¹⁸ but no analyses of the resulting slag compositions were given. Also, it should be observed that examples of the most effective decontamination for U and Pu were obtained with the slags highest in silica. Melting without any flux at all reduced the U contamination from 500 to 0.65 ppm,¹⁸ and between 85 and 100 ppm.²⁵ The disparity in these values could be related to the method of applying the contamination to the melt stock.

Seitz, et al.,¹⁶ found that some of the slags were inhomogeneous, notably the borosilicate slags which sometimes exhibited a mottled or marbled appearance. Analyses disclosed higher Pu concentrations in regions of higher alumina content; higher concentrations of chromium were also found in the higher alumina phase. Seitz, et al. concluded that the higher silica slags were less effective in decontaminating steel melts. They also found that a major source of residual contamination in the ingots was incomplete separation of the slag from the ingots (producing radioactive inclusions in an otherwise "clean" ingot) and demonstrated that "staged extraction" (remelting a decontaminated ingot) resulted in significant additional decontamination.

The presence of inclusions in which the radioisotopes are concentrated is likely a major cause of the variability in the decontamination results reported. The analytical techniques reported by Seitz clearly showed very clean metal containing radioactive casting defects, many of which were identified as inclusions. Analyses of the same ingots by the dissolution and counting method dissolved and averaged-in the inclusions, and therefore consistently showed higher levels of contamination. Other investigators analyzed drill samples of the interior of the castings after discarding chips from the ingot exterior to eliminate the high levels of surface contamination known to be present. In spite of this precaution, drill chips, inclusions and all, were considered as representative of the decontaminated metal and the reported results may have been influenced as much by the ability of the melting technique employed to remove inclusions as by the composition of the slag.

Industrial Refining Slags

Translating laboratory data into industrial scale, or even pilot scale, operations is difficult. The cited laboratory studies were performed in a closely-controlled environment, usually in a chamber that was evacuated and backfilled with an inert gas. These conditions may be difficult to duplicate on a large scale. Electric arc furnaces cannot duplicate these atmospheres unless the entire system is enclosed, although inert gas has been used in these furnaces to decrease electrode consumption and to provide better melt chemistry control. Induction furnaces, even though vacuum or inert gas may be used above the melt surface, must suffer some melt oxidation when the cover is removed periodically to permit charging until the furnace is at capacity. When melting stainless steels, $\text{FeO} \cdot \text{Fe}_2\text{O}_3$, Cr_2O_3 , and MnO_2 will be components of the slag whether or not they are beneficial to decontamination of the melt and any decontamination study should (or should have) included these components as well as others that are used in industry to improve slag fluidity. Also compositional shifts will occur in the slag as a result of degassing, decarburizing, and desulfurizing operations that are normally performed during melt refining operations.

Large melt sizes (500 kg or more) offer advantages over bench-scale melts in that holding times may be prolonged at minimum power input to permit reactions to approach completion, to allow non-metallics trapped in the melt time to float to the top and enter the slag, and to allow metal shot trapped in the slag to settle into the melt. In addition, in larger furnaces, inert gas may be injected into the melt and the units may be equipped for bottom pouring. The latter feature enables the cleaned metal to be poured from under the contaminated slag. It may be poured into another ladle containing a clean slag, obtaining the advantages of staged extraction, mentioned earlier, and enabling production of several heats with the same slag thereby reducing the quantity of radioactive material requiring disposal. Investigating the benefits of these options would not be feasible in the 100 to 500 g melts used for the bench scale furnaces, and could only be done with some difficulty in furnaces with 20 to 30 kg capacity.

For the purpose of removing various impurities from the melt, the refining slag may be compared to solvent extraction processes used in

hydrometallurgy. Most of the various radioactive metals that contaminate the melt are in the form of oxides that dissolve much more readily in the oxide slag if they contact it than in the metal bath in which they are suspended. Oxides of U and Pu are denser than the molten steel, and when very small particles that can remain in suspension agglomerate into particles large enough to settle, these dense contaminants will tend to accumulate on the bottom of the melt, away from the slag. Melt stirring imparted by the induction field tends to keep the heavier oxide particles in suspension, increasing opportunities to enter the slag. Also, other particles in the melt such as the aluminosilicates may collide with the dense oxides and combine with them, producing particles with sufficient buoyancy to float toward the slag layer.

When melting contaminated stainless steel scrap for the purpose of recycling the material into canisters for long-term interment, other factors may dominate processing to ensure that the decontaminated steel has properties suitable for the intended application. The recycled product will be equivalent to a low-carbon, low-inclusion 304L stainless steel, free of a tendency to sensitize, and with superior long term corrosion resistance. This objective may be difficult to achieve even with scrap that is considered to be well-characterized because, even though the scrap has been sorted, cleaned, and freed of non-ferrous metals and other extraneous material, several types of stainless steel may be encountered that would be difficult to distinguish using routine testing techniques. Compositions of various types of stainless steels that will likely be in the LLCMW stream are listed in Table 4. Other heat and corrosion resistant alloys (Inconels, Incolloys, Hastelloy, etc., and precipitation-hardening stainless steels) may be encountered in small quantities.

The only standard stainless steel alloy in Table 3 that would cause compositional problems in meeting the specification of 304L alloy is the 316 alloy, due to its molybdenum content. The molybdenum will resist removal, even in an oxidizing environment which would remove most of the chromium first. Alloying elements in the other stainless grades could be removed by the routine melting operations and captured by the refining slag. The required chromium, nickel, and manganese adjustments would be made in the usual manner before the heat was poured.

Table 4. Compositions of stainless steels

	304L	316L	321	348 ^a
C, max	0.03 ^b	0.03 ^c	0.08	0.08
Cr	18.00-20.00	16.00-18.00	17.00-19.00	17.00-19.00
Ni	8.00-12.00	10.00-14.00	9.00-12.00	9.00-13.00
Mo	--	2.00-3.00	--	--
Mn, max	2.00	2.00	2.00	2.00
Si, max	1.00	1.00	1.00	1.00
P, max	0.045	0.045	0.045	0.045
S, max	0.030	0.030	0.030	0.030
Ti	--	--	5x%C min	--
Cb	--	--	--	10x%C min

a. 348 is restricted to Ta 0.10 max. and Co 0.02 max.; otherwise it is the same as 347.

b. 304, C = 0.08 max

c. 316, C = 0.08 max

It appears that for the purposes of this work, the decontaminating and refining slags could be one and the same, with possible adjustments in the composition of the flux in order to achieve the composition most suitable for the dual capacity. The applicability of industrial refining slags to the removal of radioactivity from stainless steels is clearly an area that requires more study. A suggested flux composition for examination would be: 30% SiO₂, 40% CaO, 10% Al₂O₃, 15% Fe₂O₃, and 5% Ca₂B₆O₁₁.^{a,28} This mix should have a melting point of 1250°C or less, it approximates the composition of effective decontamination and refining slags, and it should not be aggressive to the alumina induction furnace refractories. During the course of decontaminating a heat of stainless steel, the slag will become enriched in Cr₂O₃, MnO, and likely Fe₂O₃, in addition to the radioisotopes of interest. Since the conclusions of several investigations would seem to be ambiguous as far as the relative decontaminating effectiveness of different slag

a. Colemanite, a fluidizer substitute for borax or fluorite.

compositions is concerned, this area needs more study, provided that analytical tools are now available with the required sensitivity.

Decontaminating a heat of stainless steel will produce a radioactive slag as a waste form. In some cases, the isotopes collected in the slag will be enriched to the extent that isotope recovery may be economically feasible.²⁹ In this regard, such slags may be a source for weapons grade isotopes and their custody becomes a security problem. Otherwise, the slag should be mechanically strong and resistant to leaching, so that it will not deteriorate in the disposal environment. Heat treatment of some slag compositions will cause devitrification (formation and growth of crystals), which usually results in increased mechanical strength and better leach resistance.³⁰

APPLICATION OF CURRENT MELTING TECHNOLOGY

The coreless induction furnace has been developed into a rapid, clean, economic melter of quality steels. With the rapid development of high capacity, solid-state circuitry, manufacturers of induction melting power supplies can produce very efficient units capable of 97% electrical efficiency with the ability to draw 100% of the rated power for the entire melt cycle. With regard to the present application, the induction furnace has advantages over the electric arc furnace, not only in terms of overall efficiency, but in the avoidance of the large amount of fume (EAF dust) resulting from the emission of aerosols from the melt. A large capacity exhaust system and a large, efficient air filtration system would be needed over the EAF unit to control the spread of radioactive aerosols, especially cesium. EAF dust has become a disposal problem for the industry, and the problem would be compounded seriously by the addition of radioactive components.

Induction Melting Under Vacuum and Inert Gas

The entire induction melting unit may be enclosed in an evacuated chamber. Very low pressures (10^{-3} torr or less) may be achieved and a slag is not necessary, or even desirable (except to reduce radiant heat loss from the melt surface) as it would be a source of inclusions in the melt. The dissolved gas content of the melt becomes very low by the time it is ready to pour. If the chamber is large enough, pouring may be done in a vacuum as well, so the melt is never exposed to the atmosphere. The induction coil must be operated at a considerably lower voltage in a vacuum to avoid arcing across the coils, so in order to maintain the required power input to the melt, the amperage must be correspondingly increased and much larger conductors are necessary. This adds considerably to the cost of the unit. Only when premium-grade alloys for high performance applications are required can the added cost of high vacuum induction melting be justified.

A simpler approach is to seal the melting cavity itself with a tight-fitting cover containing a heat-resistant seal. Access ports enable sampling and alloy additions, but the cover is usually removed for charging. Consequently, no attempt is made to maintain a high vacuum with this design, although the pressure over the melt may be maintained at 1 torr, sometimes

less. This pressure enables decarburization, the production of gas-free steel, and close compositional control without the large cost of more conventional vacuum equipment and the heavy conductors required for operating the induction coil *in vacuo*. Also, when melting steel that is radioactively contaminated, the vacuum system is inherently superior for preventing the spread of contamination, although a filtered exhaust hood over the furnace plume will be necessary when charging the furnace.

As an alternative to melting under a vacuum, decarburization and deoxidation may be performed with an inert gas, usually argon. Large quantities of argon may be required to keep the melt protected from startup to pouring, and this may become costly. Decarb and deox functions may be performed by injecting an argon-oxygen mix into the melt with a lance, or through the bottom using a gas line and a porous plug cemented into the melting cavity lining. As decarburization proceeds, the proportion of oxygen in the mix is steadily reduced until, near the end of the heat, the melt is deoxidized with undiluted argon. The advantages, if any, of argon-oxygen decarburization (AOD) over accomplishing the same objective under a vacuum (VOD), or a combination of AOD and VOD, for the purposes of removing the radioactive contamination and refining stainless steel have not been demonstrated. Carbon levels as low as 0.004 to 0.006% (40 to 60 ppm) may be achieved with vacuum systems that can provide about 1 Torr pressure over the melt, while the best that can be expected from AOD under optimum conditions are carbon levels between 0.008 and 0.010%.^a The 0.010% carbon level will be satisfactory for the waste canisters, as this level is low enough to avoid sensitization adjacent to welds.

The major justification for blowing oxygen into steel melts is to remove carbon. The Bessemer and the Basic Oxygen Furnace converted the blast furnace product into fabricable steel by blowing the carbon from about 4.3 to 0.3% or less. Also, carbon was added to open hearth melts to save fuel by reducing the melting temperature. As the heat approached completion, this carbon had to be removed. With induction melting, if the scrap is carefully selected, the carbon level should be less than 0.08%, and if 0.01% is the objective it

a. Private communication, R. U. Swaney, Inductosteel Corp., Pittsburgh, PA, May 17, 1990.

should be achieved without the addition of oxygen. The question still remaining is whether argon or vacuum is more effective.

In more conventional foundry operations, the stirring effect of the inert gas bubbling through the melt has been shown to be beneficial in terms of agglomerating the fine particles and hastening the natural rise of oxides toward the slag layer³¹ as well as performing the expected decarb and deox functions. If the desired carbon levels can be obtained, AOD may be preferred to VOD if it can be shown that it will produce a lower inclusion count in the castings. The low inclusion count will reduce pitting corrosion as well as residual radioactive contamination.

Bottom Pouring

The simplest method for pouring an induction-melted heat is to tilt the furnace so the melt flows over the lip into the receiving container, which frequently is a ladle that enables additional metallurgical treatment (secondary metallurgy) prior to pouring the finished castings or that is used for transporting the molten metal directly to the molds without additional treatment. Major refining operations are usually not done in the furnace itself because its geometry is not suited to such activity, especially when gas may be evolved. When ladle refining is to be used, the induction furnace is used only for melting, so the small quantity of slag needed in the furnace to protect the melt from air and to reduce heat loss may be dipped out before the melt is poured into the ladle. Even though ladles are preheated to avoid vapor generation, thermal shock, and to keep from chilling the charge of molten steel, ladle metallurgy is limited to larger melts to assure a sufficient heat reservoir so that the treatment operations may be performed before the heat freezes. Supplementary ladle heaters are available to increase the time available for treatment operations, if necessary. Traditionally, large gas burners were used for ladle preheating, but they are being replaced by more efficient resistance heaters or plasma torches.

Argon or vacuum treatment in the induction furnace will be largely nullified if the melt is poured into the ladle through air at the completion of the melting phase. A bottom pouring induction furnace overcomes this difficulty by enabling an evacuated and/or purged ladle to be placed beneath

the furnace, the joint sealed between the two, and the furnace charge poured into the ladle without exposure to the atmosphere. A metal foil membrane protects the ladle interior from air and is melted through by the pour from the furnace. A similar approach may be used to pour the ladle-refined heat into the mold. While a stopper rod may be used in the ladle to control the flow, this rod would not survive well in the induction furnace as it would be damaged or broken when the furnace was charged with cold scrap and melted when the induction field was applied to the charge. A slide-gate valve at the bottom of the furnace avoids such problems. A thin pouring stream is easily degassed as it passes through the evacuated or inert atmosphere of the ladle and is stripped of many of the remaining entrained contaminated oxide particles as it passes through the clean ladle slag. A new refining opportunity is available as the ladle slag may be a radically different composition than that used in the furnace. While silica was described previously as the "ubiquitous slag component," its presence is not really mandatory and synthetic slags that contain no silica may be very useful in this application. Bottom pouring can prevent contamination of the ladle slag by the melt slag by shutting off the flow before this slag reaches the orifice. The slag and metal remaining behind in the furnace may then be drained into a separate slag pot and separated when cold, or simply left in the furnace to become part of the next charge. A schematic of a bottom-pour furnace with a slide gate is shown in Figure 3.

Induction Melting in the Ladle

Placing a ladle within the induction coil and attempting to melt the contained charge without melting the ladle shell would seem, at first consideration, to be as impractical as trying to melt a charge situated around a stopper rod without melting the rod. The Inductive Ladle was developed by the Inductotherm Corporation of Rancocas, New Jersey.³² A critical ingredient of this concept is the non magnetic, austenitic stainless steel ladle shell which is permeable to the electromagnetic field but not heated by it when using less than line-frequency power. The power supply was designed to match frequency, kilowatts, and coil configuration for this special purpose. This technology has progressed to where a 2000 lb ladle was constructed and operated successfully.³³ A different alloy was used for this

N91 0416

Figure 3. Schematic of slide gate bottom pouring system.

ladle shell. Frequencies between 50 and 250 Hz have been applied. The ladle shell temperatures rise only slightly above those observed in conventional foundry practice, but do not exceed the 425°C design limit.

Inductosteel calls their arrangement the "Power Window Ladle Refiner" (PWLR). The advantages of applying this unique concept in the foundry industry are obvious in that all the melting and refining functions may be performed in one vessel, the ladle, without concern for heat loss during these operations because the induction coil is present to compensate for any heat loss. Further, while this has not yet been tried, the inductive ladle may be fitted with a cover that permits operation under vacuum or an inert gas, or both. It is capable of modification to incorporate inert gas injection and a slide-gate bottom pouring mechanism. This concept seems so well-suited to removing the radioactive contamination from stainless steel, in addition to the usual melting and refining functions, that the INEL discussed a cooperative agreement with Inductosteel to further develop the process to better enable comparisons with more conventional foundry approaches.

PLANS FOR FUTURE WORK

Preliminary Studies

The Physics and Radiological Science Unit at the INEL can perform bench scale experiments using a small (5 kg) furnace in the hot lab, or a hot cell. The hot cell would be used because of convenient connection to the efficient exhaust and filter system rather than the need for remote operation. This melting study would be conducted to confirm the data and conclusions in the literature as well as to resolve the ambiguities encountered with regard to the most effective slag compositions. These studies would also include activation and fission products. Staged melting could be done, if desired, to assess the benefits of melting under a second slag of a different composition in order to provide guidance for selection of slag chemistry for the refining ladle.

Analytical equipment is on hand that was unavailable to researchers of more than a decade ago, which will greatly extend the capabilities of this effort. This equipment can analyze the individual inclusions and detect transuranics in the ppm range. The proximity of the analytical equipment to the melting unit favors more accurate results and a quicker turnaround.

Data obtained from this work will establish a technical basis for: (a) identification of stainless steel waste that is unsuitable for melt refining, (b) selection of slag compositions [the choice would be based on thermo-chemical analyses of metal-slag interactions that would not be possible to investigate offsite (i.e., in the Cooperative Agreements) or would be too costly to study on a pilot plant scale], and (c) radiological safety requirements for controlling effluent, as well as other waste stream controls that will be necessary to obtain a permit for construction and operation of a pilot plant at the INEL.

Cooperative Agreement Studies

Inductosteel has two 2000 lb ladles at their research facility near Pittsburgh, permitting the use of a two-ladle system with a single induction coil and power supply. This arrangement should provide the benefits noted

previously for the second melt with a clean slag while allowing bottom pouring of clean metal from beneath contaminated slags. The process should be able to produce cast blanks needed for developing a back extrusion process and for material for characterization studies.

Specific objectives to be met in a cooperative agreement with Inductosteel were as follows:

1. To demonstrate that the double-melt/double-slag concept is an effective approach for removing radioactive contamination (by using surrogate additions when necessary) and for producing low-carbon, inclusion-free 304L stainless steel ingots (or cast extrusion blanks) from contaminated scrap.
2. To demonstrate that bottom pouring from the ladle can be applied successfully to the Inductosteel PWLR concept and that it will enable pouring a heat from under a loaded slag through a clean slag in a second ladle that is also capable of bottom pouring. (The ladles should be interchangeable.)
3. To demonstrate that vacuum degassing can be applied successfully to the bottom-pour ladles, that the carbon content may be reduced in 304L stainless steel to 0.01% or less without significant chromium depletion, and that the degassed/decarburized heat may be poured into the refining ladle without significant reintroduction of oxygen or inclusions. Argon melt covers may be investigated in this phase in order to enable comparisons.
4. To demonstrate that sampling for heat analyses and melt additions, when necessary, may be performed with either ladle.
5. To demonstrate that ingots may be poured from the second refining ladle without reintroduction of oxygen or inclusions, and that cast blanks suitable for back extrusion into waste containers may be produced.

A tentative experimental plan was devised for evaluating the processing of simulated contaminated stainless steel waste on a pilot plant scale using the PWLR concept. The individual evaluations of the areas listed below will constitute the process evaluation. No significance should be attached to the order of listing.

1. Vacuum vs Inert Gas Evaluation - This would be done by taking melt and slag chemistry samples just as the charge becomes completely molten but before the argon or vacuum treatment is applied, taking similar samples part way through the melt, and additional samples at the end of treatment before pouring into the refining ladle. The vacuum and/or argon pressure and temperatures during the course of the melt will be recorded.
2. Single vs Double Pour Evaluation - Take same measurements as above, but pour a sample ingot from part of the first melt before pouring into the refining slag ladle. Section this ingot and obtain samples to compare the inclusion counts and chemistry.
3. Carbon Reduction Evaluation - determined from chemistry samples under (1).
4. Chemistry Control Evaluation - determined from chemistry samples under (1). A rapid melt analysis system may not be available in the early stages of this work to enable making alloy additions after the refining step to meet the chemistry specification.
5. Flux Matrix Evaluation - Three flux mixes are anticipated, with emphasis on those that are supposed to be better at capturing radionuclides according to the literature and the results of preliminary studies at the INEL. No radionuclides will be used for this series of melts.
6. Scrap Contamination Evaluation - This effort will study the consequences of using the "dirty" (scale, rust, paint, etc.) scrap from the INEL and test the capabilities of the process and equipment

to at least partially overcome problems encountered when using such scrap.

7. Pour Solidification Evaluation - This aspect will be most important to the user of the cast extrusion blank and the evaluation may be mostly his after working with these blanks.
8. Mold Shape and Size Evaluation - This concern is related to (7), but it presently includes making small (up to 50 lb) slab castings for rolling the cast material into plate for characterization of the wrought material, including corrosion studies. The slab castings will not be necessary if back-extruded material is available for evaluation in a timely manner.
9. Chemistry Sampling Evaluation - This is related not only to the samples themselves but to ensuring that the samples are representative of whatever is being measured. Much of the analytical work will be done at the INEL.
10. Process Control Evaluation - The most important consideration here is repeatability. Once a process is developed to produce a clean heat of 304L stainless steel that is decontaminated to acceptable levels, can this be done on a routine basis? The acceptable tolerances for the process must be established.

In addition to the studies being planned with Inductosteel, we discussed another Cooperative Agreement with NI Industries, Los Angeles, CA, to develop a process to back-extrude the waste canisters from cast blanks. NI uses blanks cut from plate and has no experience using cast blanks, although it appears at this stage that such blanks would be satisfactory. Inductosteel would produce cast blanks sized for NI's existing back-extrusion tooling, which can produce a 12-in. diameter canister that requires about the same extrusion ratio as would the equivalent full-size canister. The blanks must be cast somewhat oversize to allow machining to remove surface defects that would otherwise produce laps and seams in the canister wall. The extrusion step is a severe metalworking operation, and the wall structure would resemble seamless tubing rather than rolled plate. Samples will be cut from the first

back extrusions to provide specimens for material characterization studies, which would include samples physical property, welding, and corrosion tests.

Depending on the outcome of the effort with the 12-in. canisters, NI would procure tooling and accessory equipment to produce full size canister prototypes. These will require cast blanks weighing at least 600 lb. Inductosteel's 2000 lb PWLR heats can produce as many as three of these blanks per melt. A prototype qualification effort may begin when these canisters are produced.

Successful completion of the work under the Cooperative Agreements should generate enough information to enable a decision with regard to constructing a pilot plant at the INEL to apply the process, as it has been developed to this point, to the treatment of stainless steel with radionuclide contamination. At this juncture, all of the data will have been collected with minimal investment in capital equipment at the INEL, and the technology should have been developed to where material characterization studies would show whether the back-extruded canister material can be equal to or better than the material presently used for the reference canister.

Qualification of back-extruded HLW canisters will be a time-consuming, costly task. Construction of a full-scale production facility to produce canisters for HLW will not be warranted until the pilot plant can produce prototypes that will survive the various tests when loaded with cans containing the equivalent of the ICPP HIPped glass-ceramic waste form. At present, not only is the technology for recycling LLCMW into canisters at the primitive stage, but so is the development technology for the glass-ceramic waste form. If this waste form is not developed and qualified to justify construction of a glass-ceramic production facility, then using the BSG waste form will require a canister production facility with 2.6 times the capacity presently contemplated.

REFERENCES

1. Waste Acceptance Preliminary Specifications for the Defense Waste Processing Facility High-Level Waste Form (OGR/B-8), DOE/RW-0125, Rev. 3, June 1988.
2. J. M. Beeston, et al., Canister Material Test Program, EGG-WM-6707, August 1984.
3. R. D. McCright, W. G. Halsey, and R. A. Van Konynenburg, Progress Report on the Results of Testing Advanced Conceptual Design Metal Barrier Materials Under Relevant Environmental Conditions for a Tuff Repository, UCID-21044, December 1987.
4. A. K. Agrawal, et al., "A Comparison of the Properties of CF-3 Centrifugal Castings and AISI Type 304L Stainless Steel for Storage of High-Level Waste," Appendix B in Canister Material Test Program, EGG-WM-6707, August 1984.
5. M. E. Peterson and J. M. Alzheimer, "A Report Submitted to EG&G Idaho, Inc, in Partial Fulfillment of Contract #D1414 21876," 7H35-84-11, March 1984. Appendix C in Canister Material Test Program, EG&G-WM-6707, August 1984.
6. M. Tanaka and H. Nakamura, "Research Program of Decommissioning Material Reuse in JAERI," Proc. 1989 Joint International Waste Management Conference, Kyoto, Japan, October 22-28, 1989, pp. 213-217.
7. Code of Federal Regulations, 10CFR61, §61.55, 1-1-88 ed.
8. Radiological Health Handbook, Compiled and edited by Division of Radiological Health, U.S. Department of Health, Education and Welfare, Washington D.C. 1960 p. 103.
9. R. P. Allen, H. W. Arrowsmith, and W. C. Budke, "Electropolishing as a Large Scale Decontamination Technique," 70th AIChE Annual Meeting, Session 109, Paper No. 109C, New York, November 13-17, 1977.
10. H. Blatz, J. H. Harley, and M. Eisenbud, Investigation of the Potential Hazard in Releasing Scrap Steel Contaminated with Uranium to Commercial Channels, USAEC NYO-1558, June 1951.
11. P. B. Klevin and W. B. Harris, "Remelting May Permit Reclaiming Uranium-Contaminated Metals," Nucleonics, 14, 4, pp. 93-96, April 1956.
12. R. H. Starkey, et al., "Health Aspects of the Commercial Melting of Uranium-Contaminated Ferrous Metal Scrap," Ind. Hygiene. J., 21, 1960, pp. 178-181.
13. E. W. Mautz et al., Uranium Decontamination of Common Metals by Smelting - A Review, NCLO-1113, February 1975.

14. R. H. Starkey, J. A. Quigley, and J. W. Kelvey "Health Aspects of the Commercial Melting of Radium Contaminated Ferrous Metal Scrap," Ind. Hygiene Journal, 22, 1961, pp. 489-493.
15. N. Levitz, et al., "Volume Reduction and Salvage Considerations for Plutonium-Contaminated Ferrous Metal," AIChE Symposium Series, R. E. Tomilson, (ed.), 72, 154, 1976, pp.86-89.
16. M. G. Seitz, T. J. Gerding, and M. J. Steindler, Decontamination of Metals Containing Plutonium and Americium, ANL-78-13, June 1979.
17. G. L. Copeland, R. L. Heestand, and R. S. Mateer, Volume Reduction of Low-Level Contaminated Metal Waste by Melting, ORNL/TM-6388, June 1978.
18. B. Heshmatpour and G. L. Copeland, The Effect of Slag Composition and Process Variables on Decontamination of Metallic Wastes by Melt Refining, ORNL/TM-7501, 1981.
19. B. Heshmatpour, G.L. Copeland, and R.L. Heestand, Decontamination of Transuranic Waste Metal by Melt Refining, ORNL/TM 7951, 1981.
20. C. W. Hobbick, D. R. Schatz, and G. D. Aden, Distribution and Removal of Radionuclides in Molten Stainless Steel, RHO-CD-1444, June 1981.
21. J. P. Lacroix and M. Tailliez, "STMI's Industrial Experience in Low Activity Steel Waste Processing by Melting," Waste Management '86, 3, R. G. Post (ed.) 1986, pp. 547-552.
22. R. C. Weast (ed.), CRC Handbook of Chemistry and Physics, 59th edition., CRC Press, Inc., 1978, pp. B-276 - B-360.
23. R.G. Ward, An Introduction to the Physical Chemistry of Iron and Steel Making, London: Edward Arnold Ltd., 1962, pp. 10-21.
24. D. R. Gaskell, "The Role of Slags in Steelmaking. The Physical and Chemical Origins of the Behavior of Slags," Part 1. Iron and Steelmaker, 10, 5, May 1983, pp. 60-62.
25. T. Uda, H. Tsuchiya, and H. Iba, "Decontamination of Uranium-Contaminated Iron by Smelting," Trans. American Nuclear Society, 41, June 1982, pp. 102-103.
26. M. Abe, T. Uda, and H. Iba, "Melt Refining Method for Uranium-Contaminated Steels and Copper," Waste Management '85: Waste Isolation in the U.S. (conf.), March 24-28, 1985.pp. 375-379.
27. E. M. Levin, C. R. Robbins, and H. F. McMurdie, Phase Diagrams for Ceramists, Compiled by National Bureau of Standards, 1964, (w 1969 and 1975 supplements), American Ceramic Society.
28. R. H. Nafziger and G. W. Elger, "Fluorspar Substitutes in Steelmaking," New Steelmaking Technology from the Bureau of Mines, IC 9195, 1988, pp. 23-27.

29. R. L. Miller, J. M. Welch, and J. E. Flinn, "Uranium Recovery from a Nuclear Fuel Waste Form," Min. and Met. Processing, February 1985, p. 51.
30. J. M. Welch, et al., Iron-Enriched Basalt as a Waste Form for High-Level Nuclear Wastes, EGG-FM-5758, October 1982.
31. J. K. Cotchen, "Ladle Metallurgy and the Foundry," 1987 Electric Furnace Proceedings, ISS-AIME, 45, 1987.
32. R. U. Swaney, "Induction Ladle Metallurgy: An Alternative to the Arc," 1987 Electric Furnace Proceedings, ISS-AIME, 45, 1987, pp. 325-327.
33. N. P. Cignetti and R. U. Swaney, "Development of a Small Sized Ladle Metallurgy System," 1989 Electric Furnace Conference Proceedings, ISS-AIME, 47, 1989, pp. 219-227.

END

**DATE
FILMED**

5 / 29 / 92