DOE/PC/90287--T6

NOV 13 1992

**OXIDATION OF COAL AND COAL PYRITE
MECHANISMS AND INFLUENCE ON SURFACE CHARACTERISTICS
DE-FG22-90PC90287**

**Fiona M. Doyle
University of California at Berkeley
Dept. Materials Science and Mineral Engineering**

DOE/PC/90287--T6

DE92 014111

TECHNICAL PROGRESS REPORT (3/31/92)

RESEARCH OBJECTIVES

The objective of this research is to develop a mechanistic understanding of the oxidation of coal and coal pyrite, and to correlate the intrinsic physical and chemical properties of these minerals, along with changes resulting from oxidation, with those surface properties that influence the behavior in physical coal cleaning processes. The results will provide fundamental insight into oxidation, in terms of the bulk and surface chemistry, the microstructure, and the semiconductor properties of the pyrite.

During the sixth quarter, oxidized samples of Upper Freeport coal from the Troutville #2 Mine, Clearfield County, Pennsylvania were studied by ion-exchange methods. Film flotation tests were done to characterize the flotability of as-received coal, and samples subjected to different oxidation procedures. In addition, electrochemical studies were started on electrodes prepared from coal pyrite samples.

EXPERIMENTAL METHODS AND RESULTS

a. Sample preparation

Monosized fractions of the Upper Freeport coal were prepared using a mortar and pestle, followed by sieving. Both grinding and sieving were done in an argon-filled glove box, to prevent oxidation.

b. Dry oxidation studies

5 g samples of -75 +63 μ m Upper Freeport coal, spread to a depth of about 1 mm, were oxidized in a convection oven at 100, 150, 200 and 230°C for 24 hours, to investigate the effect of oxidation temperature. Samples were also oxidized at 230°C for 1, 2, 4, 8 and 24 hours, to investigate the oxidation rate.

As-received coal, and samples that had been oxidized for 24 hours, was analyzed by the sodium acetate ion-exchange method to determine the surface carboxylate species, and by the barium hydroxide ion-exchange method to determine the total acidic species (carboxylate and phenolic). Both methods are described in detail by Brooks and Sternhell (J.D. Brooks and S. Sternhell, *Aust. J. Appl. Sci.*, Vol. 8, pp. 206-221, 1957).

MASTER

DM

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

In the sodium acetate ion-exchange method, one gram of sample is purged with nitrogen, and shaken with 100 ml of 3.0M sodium acetate for 24 hours. The method assumes that all the surface carboxylic acid groups will be converted to their sodium salts on exposure to sodium acetate, releasing hydrogen ions into solution:

In the barium hydroxide ion-exchange method, one gram of sample is purged with nitrogen, and shaken with 100 ml of 0.3 N $\text{Ba}(\text{OH})_2$ for 24 hours. The method assumes that Ba^{2+} exchanges with H^+ in the carboxylic and phenolic groups, forming insoluble compounds on the coal surface and releasing hydrogen ions into the solution:

where (s) denotes a surface species. The phenolic group concentration is found by difference from the carboxylic and total acid concentrations.

Figure 1 shows that the majority of the acidic oxygen groups are phenolic in the as-received coal and coal oxidized at temperatures up to 150°C. At higher oxidation temperatures there is a dramatic increase in the total number of acid groups, but the majority of these are the more highly oxidized carboxylic groups. Figure 2 shows that coal samples oxidized at 230°C for less than 5 hours have a majority of phenolic groups, whereas the concentration of carboxylic acid groups increases steadily with oxidation time, exceeding that of phenolic groups after five hours. It is possible that Figures 1 and 2 reflect an increase in surface area, or opening up of internal surfaces already containing acidic groups, due to softening and volatilization at 200 and 230°C. However, the results of the film flotation tests discussed below indicate that there is a real increase in surface oxidation during prolonged heating.

c. Film flotation tests

The wettability of as-received coal, and samples oxidized for 24 hours under different conditions was tested by the film flotation method described in detail by Fuerstenau and Williams (*D.W. Fuerstenau and M.C. Williams, Colloids and Surfaces, Vol. 22, pp. 87-91, 1987*). Closely sized coal particles are gently sprinkled onto the surface of solutions with different surface tensions. At any given surface tension, those particles that do not sink into the wetting liquid are called lyophobic, whereas those that are imbibed into the liquid are called lyophilic. The weight percentage of each fraction is determined gravimetrically, and the percentage of lyophobic particles is plotted as a function of the surface tension of the solutions. The mean critical surface tension of each coal sample (the surface tension at which 50% of the sample is lyophobic) can be obtained from this curve. It should be emphasized that this method provides information on the averaged surface properties of individual particles. Each particle has a critical surface tension, which depends on the relative concentration of lyophobic and lyophilic groups on the particle surface. Film

flotation tests reveal the distribution of critical surface tensions. These tests are directly relevant to the behavior that could be expected during coal cleaning by flotation techniques.

All the film flotation experiments were carried out at room temperature using aqueous methanol solutions. The surface tensions ranged from 22.5 mN/m (pure methanol) to 72.8 mN/m (pure water) and the amount of coal used in each test varied from 0.03g to 0.1g.

Figure 3 shows the film flotation partition curves of raw coal and coal oxidized at 200 and 230°C, and Figure 4 shows the mean critical surface tensions derived from these curves. For the sample oxidized at 230°C, the mean critical surface tension was obtained by extrapolation, and hence is only approximate. The surface tension increased dramatically with increasing oxidation temperature, corresponding to a decrease in the hydrophobicity of the coal samples with oxidation. Less coal would be floated during cleaning with increasing extent of oxidation. Figure 5 shows that at 230°C, the partition curves shifted to higher surface tension values with increasing oxidation times. Figure 6 shows that at 230°C there is a dramatic increase in the mean critical surface tension for oxidation times of less than 5 hours. After 5 hours, the mean critical surface tension appears to increase more slowly, although there is less certainty in these values, since they are extrapolated; it would be expected that the surface tension would reach a maximum value, corresponding to complete surface oxidation to carboxylic groups. As more and more particles approach complete surface oxidation, the film flotation curves would become increasingly sharp. Figure 7 shows that the mean critical wetting surface tension of coal samples (including extrapolated values) appears to be directly related to the total concentration of acidic group oxygen, and that complete surface oxidation has not been achieved, even after twenty four hours at 230°C.

Figure 8 shows the film flotation partition curves for coal samples oxidized by 0.1M and 3.0M HNO₃ solutions (the oxidation procedures were reported in or 12/31/91 report). As expected, the surface tension shifted to higher values with increasing nitric acid concentration. Table I shows the mean critical surface tension after both treatments.

Table I. Mean critical surface tension of coal samples oxidized by nitric acid

Coal Treatment	Mean Critical Surface Tension, mN/m
As received coal	40.00
0.1M HNO ₃ , 24 hrs	51.00
3.0M HNO ₃ , 24 hrs	65.00

d. Rest Potential Measurements

Coal pyrite samples were hand picked from broken coal, and cleaned first with hot dilute hydrochloric acid, to remove acid-soluble impurities, then with pyridine, to remove coal impurities. Electrodes were constructed from the larger pieces of pyrite. Copper wires 1 mm in diameter were connected to the pyrite samples using silver epoxy, then the copper wire was shrouded in an insulating plastic capillary tube. The sample and base of the plastic tube were then encased in cold-setting resin, to expose only the bottom of the pyrite sample. Before each electrochemical experiment a fresh pyrite surface was produced by wet grinding, using deoxygenated water on a 600 grit silicon carbide paper under a nitrogen atmosphere in a glove box. The surface was etched for 1 minute in a 2:1:1 HNO_3 :HF: CH_3COOH mixture, to dissolve any oxidized layers or surface debris. The sample was transferred to the electrochemical cell inside the glove box, to prevent oxidation. The electrolytes were deoxygenated by sparging with 99.7% nitrogen, followed by 99.995% argon, for 1.0 hour each. Residual oxygen and carbon dioxide were removed from the argon by passing over an activated catalyst heated to 100°C in a tubular furnace, and a CO_2 absorbent. Potentials were measured against a saturated calomel reference electrode (SCE), using an EG&G Model 273 potentiostat, and then converted to the SHE scale.

The potential of pyrite electrodes was measured as a function of time in 0.1M H_2SO_4 solution, while continuously sparging the electrolyte with argon, to prevent oxidation of the pyrite. Typical plots of the potential as a function of time are shown in Figures 9 and 10; there was an initial, rapid decrease, with the potential stabilizing after about 20.0 hours. The final potentials from Figures 9 and 10 were 311.0 mV and 313.0 mV respectively, indicating good reproducibility, although these values are slightly higher than the thermodynamic rest potentials of pyrite in equilibrium with a sulfate solution at this pH value.

PLANS FOR NEXT QUARTER

During the next quarter we will continue studying the oxidation of Upper Freeport coal using different procedures, focussing on characterization techniques that reveal more about the mechanisms of oxidation. Diffuse reflectance infrared Fourier transform (DRIFT) analysis will be done. The electrokinetic behavior of as-received coal and oxidized coal will be studied as a function of pH and electrolyte concentration. Electron microscopy of the coal, and coal pyrite, is planned. Coal pyrite electrodes will be studied to determine anodic and cathodic polarization behavior, and cyclic voltammetry will be done in different potential ranges. In addition, long-term oxidation tests will be started on high-sulfur coal samples from the Pennsylvania State Coal Bank, to compare their oxidation behavior at ambient temperatures. Samples will be analyzed periodically over the final six quarters of this project.

UPPER FREEPORT COAL

200 x 250 mesh
OXIDIZED FOR 24 HOURS

Figure 1. Effect of oxidation temperature on weight percent oxygen in the form of carboxylic and phenolic groups on the surfaces of Upper Freeport coal oxidized for 24 hours

UPPER FREEPORT COAL

200 x 250 mesh
OXIDIZED AT 230 °C

Figure 2. Effect of oxidation time on weight percent oxygen in the form of carboxylic and phenolic groups on the surface of Upper Freeport coal oxidized at 230°C

UPPER FREEPORT COAL

200 x 250 mesh

Figure 3. Film flotation partition curves of Upper Freeport coal as-received and oxidized for 24 hours at 200° and 230°C

UPPER FREEPORT COAL

200 x 250 mesh

Figure 4. The effect of oxidation temperature on the mean critical surface tension of Upper Freeport coal as-received and oxidized for 24.0 hours

UPPER FREEPORT COAL

200 x 250 mesh
OXIDIZED AT 230 °C

Figure 5. Film flotation partition curves of Upper Freeport coal oxidized at 230°C for different time periods

UPPER FREEPORT COAL

200 x 250 mesh
OXIDIZED AT 230 °C

Figure 6. The effect of oxidation time on the mean critical surface tension of Upper Freeport coal oxidized at 230°C

UPPER FREEPORT COAL

200 x 250 mesh
OXIDIZED AT 230 °C

Figure 7. Correlation between the mean critical surface tension and weight percent oxygen in the form of acidic functional groups on the surfaces of Upper Freeport coal oxidized at 230°C

UPPER FREEPORT COAL

200 x 250 mesh
NITRIC ACID OXIDATION

Figure 8. Film flotation partition curves of Upper Freeport coal oxidized by 3.0 and 0.1 M HNO₃ for 24 hours

Figure 9. Potential of coal pyrite sample as a function of time, in 0.1 M H₂SO₄

Figure 10. Potential of coal pyrite sample as a function of time, in 0.1 M H₂SO₄

**DATE
FILMED**

7/17/92