**Development of An Advanced, Continuous Mild Gasification
Process for the Production of Co-Products
(Tasks 2, 3, and 4.1 to 4.6), Volume II**

Final Report

**R.A. Knight
J.L. Gissy
M. Onischak
S.P. Babu
R.H. Carty
R.G. Duthie (Bechtel Group, Inc.)
J.M. Wootten (Peabody Holding Co. Inc.)**

September 1991

Work Performed Under Contract No.: DE-AC21-87MC24266

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia**

**By
Institute of Gas Technology
Chicago, Illinois**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, ~~DDC-635-0101~~.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**Development of An Advanced, Continuous Mild Gasification
Process for the Production of Co-Products
(Tasks 2, 3, and 4.1 to 4.6), Volume II**

Final Report

**R.A. Knight
J.L. Gissy
M. Onischak
S.P. Babu
R.H. Carty
R.G. Duthie (Bechtel Group, Inc.)
J.M. Wootten (Peabody Holding Co. Inc.)**

Work Performed Under Contract No.: DE-AC21-87MC24266

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Institute of Gas Technology
IIT Center, 3424 S. State Street
Chicago, Illinois 60616**

September 1991

Volume I

Project Summary

Literature Survey of Mild Gasification Processes,
Co-Product Upgrading and Utilization, and Market
Assessment (Program Task 1)

Volume II

Mild Gasification Technology Development:
Process Research Unit Tests Using Slipstream Sampling
(Program Task 2)

Bench-Scale Char Upgrading Study
(Program Task 3)

Mild Gasification Technology Development:
System Integration Studies
(Program Tasks 4.1 to 4.6)

Volume III

Mild Gasification Technology Development:
24 Ton Per Day Process Development Unit Design
and Cost Estimates (Program Task 4.7)

TABLE OF CONTENTS

	<u>Page</u>
MILD GASIFICATION TECHNOLOGY DEVELOPMENT: TASK 2. PROCESS RESEARCH UNIT TESTS USING SLIPSTREAM SAMPLING	II-1
Objectives	II-1
Introduction	II-1
Project Approach	II-2
Description of the Process Research Unit	II-3
Description of the Mild Gasification Tests and PRU Modifications	II-10
Test Coals	II-10
Shakedown Operations	II-10
Mild Gasification Tests	II-16
Discussion of PRU Test Results	II-33
Introduction	II-33
Material Balances	II-33
Temperature Effects	II-77
Effects of Steam	II-88
Chemical Properties of Oils/Tars	II-88
Reproducibility of Data	II-97
Reactor/Process Configuration	II-99
Conclusions	II-101
References Cited	II-103
TASK 3. BENCH-SCALE UPGRADING STUDY	II-105
Objective	II-105
Introduction	II-105
Project Approach	II-106
Summary of Potential Markets for Mild Gasification Char Co-Products	II-108
Form Coke	II-109
Smokeless Fuel	II-110
Activated Char	II-110
Char Upgrading Studies	II-112
Form Coke	II-112
Smokeless Fuel	II-119
Activated Char	II-122

TABLE OF CONTENTS, Cont.

	<u>Page</u>
Conclusions	II-142
References Cited	II-143
TASKS 4.1 TO 4.6. SYSTEM INTEGRATION STUDIES	II-144
Objective	II-144
Introduction	II-144
Project Approach	II-145
System Integration Tests	II-148
Description of Tests	II-148
Test Results	II-159
Introduction	II-159
Test Coals	II-159
Material Balances	II-161
Co-Product Yields	II-162
Properties of Char	II-175
Properties of Oils/Tars	II-188
Oils/Tars From Full-Stream Condensate System	II-196
Properties of Fuel Gas	II-201
Impact of Data on Scale-Up Design	II-203
Impact of Data on Marketing of Co-Products	II-203
Conclusions	II-204
References Cited	II-205

LIST OF FIGURES

<u>Figure No.</u>		<u>Page</u>
II-1	Schematic Diagram of PRU System	II-4
II-2	Isometric View of PRU System	II-5
II-3	Slipstream Sampling System	II-7
II-4	Control Room Panel With Data Acquisition/Control System	II-9
II-5	Fluidization Grid Modifications	II-26
II-6	Effect of Mild Gasification Temperature on Co-Product Yields	II-78
II-7	Effect of Mild Gasification Temperature on the Boiling-Point Fractions of Oils/Tars	II-79
II-8	Effect of Mild Gasification Temperature on the Heteroatoms in Oils/Tars	II-80
II-9	Effect of Mild Gasification Temperature on the H/C Atomic Ratio in Oils/Tars	II-81
II-10	Effect of Mild Gasification Temperature on Ash, Volatile Matter, and Sulfur Content of Char	II-82
II-11	Effect of Mild Gasification Temperature on Gas Composition	II-83
II-12	FIMS Spectrum of Test MG-3 Solvent Quench Tar	II-84
II-13	FIMS Spectrum of Test MG-3 THF Wash Tar	II-92
II-14	Vacuum Distillation Curve for Test MG-3 Solvent Quench Tar	II-93
II-15	Vacuum Distillation Curve for Test MG-3 THF Wash Tar	II-94
II-16	H-NMR Spectrum of Test MG-25 Oils/Tars	II-96
II-17	Isometric of PRU System	II-107
II-18	Comparison of Domestic Fuels	II-111
II-19	Diametral Compression Tests for Tensile Strength	II-114
II-20	Form Coke Reactivity Tests	II-116
II-21	Schematic Process Flow Diagram of Hot Briquetting Installation	II-118

LIST OF FIGURES, Cont.

<u>Figure No.</u>		<u>Page</u>
II-22	Sulfur Forms in Combusted Smokeless Fuel	II-121
II-23	Schematic Diagram of the 2-inch-ID Fluidized-Bed Reactor	II-123
II-24	Schematic Diagram of the Fluidized-Bed Steam Treatment Apparatus	II-124
II-25	Surface Area and Iodine Numbers of Activated Carbons	II-132
II-26	Surface Area and Iodine Numbers as a Function of Activation Time	II-133
II-27	Adsorption Properties of Char Versus Carbon Burn-Off	II-134
II-28	Char Adsorption Optimization for Iodine Number and Surface Area	II-135
II-29	Micropore Distribution of Selected Activated Chars and Carbons	II-136
II-30	3,5-Dichlorophenol Isotherms	II-138
II-31	3,5-Dimethylphenol Isotherms	II-139
II-32	3,5-Dichlorophenol Adsorption Rates	II-140
II-33	3,5-Dimethylphenol Adsorption Rates	II-141
II-34	Schematic Diagram of PRU System	II-146
II-35	Isometric of PRU System	II-147
II-36	Schematic Diagram of Full-Stream Condensate System	II-150
II-37	Co-Product Yields From Task 2 and Task 4 PRU Tests	II-174

LIST OF TABLES

<u>Table No.</u>		<u>Page</u>
II-1	Properties of Coals and Coke Breeze Diluents	II-11
II-2	Summary of PRU Shakedown Tests	II-13
II-3	Summary of Mild Gasification PRU Tests	II-17
II-4	Analyses of Solids From Test SD-6	II-34
II-5	Analyses of Solids From Test MG-3	II-35
II-6	Analyses of Solids From Test MG-5	II-36
II-7	Analyses of Solids From Test MG-11	II-37
II-8	Analyses of Solids From Test MG-12	II-38
II-9	Analyses of Solids From Test MG-14	II-39
II-10	Analyses of Solids From Test MG-15	II-40
II-11	Analyses of Solids From Test MG-16	II-41
II-12	Analyses of Solids From Test MG-18	II-42
II-13	Analyses of Solids From Test MG-19	II-43
II-14	Analyses of Solids From Test MG-21	II-44
II-15	Analyses of Solids From Test MG-22	II-45
II-16	Analyses of Solids From Test MG-25	II-46
II-17	Analyses of Solids From Test MG-28	II-47
II-18	Analyses of Solids From Test MG-30	II-48
II-19	Oils/Tars Elemental Analyses and Simulated Distillation	II-49
II-20	Component Analyses of Full-Range Oils and Tars	II-53
II-21	Gas Compositions	II-57
II-22	Test SD-6 (1300°F) Material Balances	II-61
II-23	Test MG-3 (1325°F) Material Balances	II-62
II-24	Test MG-5 (1100°F) Material Balances	II-63
II-25	Test MG-11 (1390°F) Material Balances	II-64

LIST OF TABLES, Cont.

<u>Table No.</u>		<u>Page</u>
II-26	Test MG-12 (1252°F) Material Balances	II-65
II-27	Test MG-14 (1084°F) Material Balances	II-66
II-28	Test MG-15 (1034°F) Material Balances	II-67
II-29	Test MG-16 (1183°F) Material Balances	II-68
II-30	Test MG-18 (1178°F) Material Balances	II-69
II-31	Test MG-19 (1102°F) Material Balances	II-70
II-32	Test MG-21 (1109°F) Material Balances	II-71
II-33	Test MG-22 (1147°F) Material Balances	II-72
II-34	Test MG-25 (1134°F) Material Balances	II-73
II-35	Test MG-28 (1149°F) Material Balances	II-74
II-36	Test MG-30 (1050°F) Material Balances	II-75
II-37	Comparison of PAH Contents of Mild Gasification Tar and a Typical Coke Oven Tar	II-89
II-38	Comparison of Co-Product Yields With Coke Oven By-Product Yields	II-90
II-39	Comparison of PAH Production Levels Between Mild Gasification and a Typical Coke Oven Tar	II-90
II-40	FIMS Data on Test MG-3 Oils and Tars	II-95
II-41	Hydrogen Atom Distribution in Test MG-25 Oils and Tars	II-97
II-42	Heating Value Comparison of Smokeless Fuel With Solid Fuels	II-112
II-43	Analyses of Limestones Used in Smokeless Fuel Briquettes	II-120
II-44	Standard Tests for Activated Carbon	II-125
II-45	Summary of Results From Char Activation and Adsorption Tests	II-127
II-46	Fischer Assay of Illinois No. 6 Coal Used in Adsorbent Studies	II-131
II-47	Adsorbents Compared in DCP and DMP Isotherm Tests	II-137

LIST OF TABLES, Cont.

<u>Table No.</u>		<u>Page</u>
II-48	Summary of Mild Gasification Tests Conducted in Task 4	II-151
II-49	Analyses of Coals Tested in Task 4	II-160
II-50	Test IST-5 Material Balances	II-163
II-51	Test IST-7 Material Balances	II-164
II-52	Test IST-8 Material Balances	II-165
II-53	Test IST-9 Material Balances	II-166
II-54	Test IST-10 Material Balances	II-167
II-55	Test IST-11 Material Balances	II-168
II-56	Test IST-12 Material Balances	II-169
II-57	Test IST-13 Material Balances	II-170
II-58	Test IST-14 Material Balances	II-171
II-59	Test IST-15 Material Balances	II-172
II-60	Test IST-17 Material Balances	II-173
II-61	Analyses of Solids From Test IST-5	II-176
II-62	Analyses of Solids From Test IST-7	II-177
II-63	Analyses of Solids From Test IST-8	II-178
II-64	Analyses of Solids From Test IST-9	II-179
II-65	Analyses of Solids From Test IST-10	II-180
II-66	Analyses of Solids From Test IST-11	II-181
II-67	Analyses of Solids From Test IST-12	II-182
II-68	Analyses of Solids From Test IST-13	II-183
II-69	Analyses of Solids From Test IST-14	II-184
II-70	Analyses of Solids From Test IST-15	II-185
II-71	Analyses of Solids From Test IST-17	II-186
II-72	Diluent-Free Char Properties With Normalization	II-187

LIST OF TABLES, Cont.

<u>Table No.</u>		<u>Page</u>
II-73	Oils/Tars Elemental Analyses and Simulated Distillations	II-189
II-74	Component Analyses of Full-Range Condensate System	II-192
II-75	Oils/Tars Data From Full-Stream Condensate System	II-197
II-76	Partitioning of Full-Stream Quench Components in Distillation (Test IST-5)	II-199
II-77	Evaluation of Tar Samples by Reilly Industries	II-200
II-78	Gas Compositions	II-202

7WP/61089pre2/RPP

VOLUME II. EXECUTIVE SUMMARY

Mild Gasification Technology Development: Process Research Unit Tests Using Slipstream Sampling (Program Task 2)

The IGT mild gasification process was designed to handle all coals and incorporates an integrated fluidized/entrained-bed reactor supplying heat indirectly by a combination of char and gas recycle. The use of mild operating conditions (1000° to 1500°F), low pressures (<50 psig), and continuous operation in closed reactors, combined with the sale of value-added co-products, offer an environmentally sound and economical approach to advanced coal utilization.

The mild gasification process research unit (PRU) that was designed and built consists of an 8-inch-ID x 8-foot-long fluidized-bed reactor closely coupled to a 4-inch-ID x 13-foot-long entrained-bed reactor. The PRU test results have demonstrated process performance, including the effect of coal type and temperature on mild gasification co-product yields and their properties. The fates of the heteroatoms have also been analyzed.

Data analysis from the successful PRU tests with Peabody's Illinois No. 6 and West Virginia coals show that, in the temperature range of 1035° to 1390°F, coal conversion ranged from 24% to 46%, resulting in 54% to 76% char, 13% to 29% oils/tar, and 5% to 19% fuel gas. The test data with the Illinois coal show that increasing reaction temperature increases coal conversion, with decreasing char yield. The oils/tar yields appear to maximize around 1100°F, while the gas yield increases steadily with increasing temperature, primarily due to increasing secondary thermal cracking reactions. The highly aromatic oils and tars were characterized to estimate the light oil (<350°F), middle oil (350° to 590°F), heavy oil (590° to 750°F), and pitch (>750°F) distillation fractions. The predominance of secondary reactions is also evident in the effect of temperature on the amounts of various oils/tars produced. It was determined that with increasing mild gasification temperature, the pitch fraction decreased with a corresponding increase in lighter fractions, particularly the light oil.

The fuel gas from mild gasification is rich in hydrogen and methane and it also contains other light hydrocarbons, carbon oxides, and hydrogen sulfide. Increasing temperature reduces methane and increases hydrogen

content, which effects are also attributable to secondary cracking and reforming reactions and to gas-phase C/H/O equilibria.

The char volatile matter content was in the range of 7% to 12%, reduced from the 37% volatile matter content of the dry Illinois No. 6 coal.

Analysis of the fate of sulfur with increasing reaction temperature showed that the sulfur content in char and gases decreased while the sulfur content of oils/tars increased. In general, for Illinois coal, the char contained 36% to 54% of the sulfur, oils and tars contained 9% to 15% of the sulfur, and the fuel gas contained 31% to 52% of the sulfur in the coal.

The implications of these observations, and conclusions on process evaluation, scale-up, and marketability of the co-products have been considered for the preliminary conceptual design of the 24 ton per day process development unit.

Bench-Scale Char Upgrading Study (Program Task 3)

Three value-added solid co-products from mild gasification were identified in Volume I "Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization and Market Assessment." These co-products are a metallurgical form coke, a smokeless fuel, and an activated adsorbent char.

The chars from the mild gasification PRU and from a laboratory fluidized bed were evaluated with bench-scale performance tests specific for each of the three products. The investigation indicated that a form coke briquette made from metallurgical grade coal can be made of sufficient strength and in the proper range of coke reactivity. Larger scale tests will be required to prove the performance of the form coke in industrial equipment, but the major factors of strength and reactivity should not be a technical barrier.

Briquettes of smokeless fuel do not have to be as strong as the form coke briquettes. Limestone, which can be easily blended into the char briquettes, has been shown to capture 88% of the sulfur from the char of an Illinois No. 6 coal in simple combustion tests. The coal sulfur was found to be completely converted to calcium sulfate in the combusted ash residue.

A good-quality, low-cost activated adsorbent char was prepared from Illinois No. 6 char by optimizing the carbon burn-off with steam. The

adsorbent char was comparable in performance characteristics to a commercial bituminous coal-based activated char and was found to be particularly well-suited for adsorption of low-molecular-weight species.

Mild Gasification Technology Development:
System Integration Studies (Program Tasks 4.1 to 4.6)

The (PRU) tests conducted in the task on System Integration Studies, operated with a full-stream product gas condensate system that was added to the IGT mild gasification process research unit. The process conditions for these tests were identified in the task on Process Research Unit Tests Using Slipstream Sampling, to produce the maximum amount of valuable liquids. The tests were operated for steady-state periods of up to 12 hours, and were conducted with four different coals.

In these tests, the use of recycle char from previous PRU tests mixed with the caking coal feed to the fluidized bed simulated the scaled-up adiabatic process development unit (PDU) that will use recycled hot char. Also, one test was performed to evaluate the effect of carbon dioxide in the inlet fluidization gas, as would be present in the PDU design using heated recycled product gas for fluidization.

Co-product yields and quality were compared with previous data and related to sequential char recycle, fluidization gas, and coal type. Oils/tars yields from Illinois and West Virginia bituminous coals were consistently over 25% by weight of maf coal, and were not adversely affected either by replacement of coke diluent with mild gasification char or by the use of 19% CO₂ in the fluidization gas. The steady operation of the IGT mild gasification PRU with 100% non-caking coal at 102 lb/h was also demonstrated showing the versatility of the reactor design.

Condensable co-products from the PRU tests were evaluated by Reilly Industries for the production of chemicals and pitch binders, and recommendations for liquids upgrading for incorporation into the 24-ton/day PDU were made. Larger batches of char were generated for preparation of form coke and smokeless fuel briquettes to be tested in the Bench-Scale Char Upgrading Study.

MILD GASIFICATION TECHNOLOGY DEVELOPMENT: TASK 2. PROCESS RESEARCH
UNIT TESTS USING SLIPSTREAM SAMPLING

Objectives

The overall objective of this program is to develop mild gasification technology and co-product utilization with Eastern bituminous coal feedstocks. Specifically, the objective of Task 2 is to develop a technical data base for mild gasification technology through the operation of a 100-lb/h process research unit (PRU) with slipstream sampling. The operational data thus obtained can be used for the design of an integrated PRU with a total quench system and a design of a larger (1-ton/hour) process development unit (PDU), ultimately leading to scale-up and commercialization of the process.

Introduction

The U.S. Department of Energy (DOE) is supporting the development of mild gasification technology to produce coal-derived fuels and value-added products such as chemical feedstocks. Mild gasification may be the most affordable route to increasing coal utilization in the present economic climate. This technology uses operating conditions of 1000° to 1500°F, near-atmospheric pressure, and inexpensive reactants to convert coal to a slate of co-products.

Mild gasification could be considered as an advanced low-temperature coal carbonization process. Low-temperature carbonization of coal was popular in the U.S. until natural gas became abundantly available, and it is still used on a commercial scale in some foreign countries. The old technology, however, has been improved to produce value-added co-products through the application of technical and scientific knowledge about coal conversion that has been developed over the past twenty-five years. Improvements in reactor and process design are being applied to significantly enhance the yield and quality of the co-products as well as the overall economics of the technology. Because of the mild operating conditions and process simplicity, mild gasification can use available materials of construction and conventional engineering design and construction practices. As a result, the capital and operating costs are expected to be low. In this context, by successfully developing and marketing the co-products to derive the value-added benefits, it should be possible to commercialize the technology within the next ten years.

With support of the U.S. DOE, a project team consisting of the Institute of Gas Technology, Peabody Holding Company, Inc., and Bechtel Group is developing a mild gasification process that uses a fluidized-/entrained-bed reactor. This reactor is designed to process caking bituminous coals over a wide range of particle sizes without oxidative pretreatment, and also without the use of oxygen or air as reactants. Process heat, in the conceptual commercial reactor, would be provided by recycled hot char or high-temperature fuel or flue gases derived from burning a portion of the process-derived fuel gases. The addition of an in-bed sulfur-capture agent such as calcium oxide to capture the hydrogen sulfide released during coal conversion is an option for processing high-sulfur coals. The co-product streams, consisting of char, fuel gas, water, and condensables, would be separated by conventional means such as cyclones, staged condensers, and recycle-oil scrubbers.

An isothermal process research unit (PRU) has been built at IGT, consisting of an 8-inch-ID, 8-foot-long fluidized-bed section and a 4-inch-ID, 13-foot-long entrained-flow section, externally heated by electrical heaters. The coal feed capacity is 100 lb/h, and the coal can be fed either to the fluidized bed or to the freeboard region above the fluidized bed and below the entrained section. The stainless steel reactor vessel is designed for operation at a maximum temperature and pressure of 1500°F and 50 psig, respectively.

This report, Volume II, summarizes the technology development work that has been performed in the PRU with slipstream sampling of the devolatilization products, using Illinois No. 6 and West Virginia coals. Operational data and extensive characterization data on oils and tars are discussed in the sections to follow along with information developed on char upgrading leading to the process scale-up design to an adiabatic PDU, presented as Volume III.

Project Approach

The mild gasification project consists of four major tasks:

- Task 1. Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment
- Task 2. Bench-Scale Mild Gasification Study
- Task 3. Bench-Scale Char Upgrading Study
- Task 4. System Integration Studies

The approach to the development of an advanced, mild gasification process was based, in Task 1 of this project, on a detailed literature survey and review of the state-of-the-art technology for coal conversion to readily saleable co-products. A market survey, conducted concurrently with the literature survey, identified the value-added priority end uses of the co-products. Based on this information, the basis for design of the reactor, the process operating conditions, and the methods of co-products upgrading were determined.

The results of the above approach were presented in Volume I of this report. In Task 2 of the project, Bench-Scale Mild Gasification, IGT was directed by U.S. DOE to design, build, and operate an isothermal 100-lb/h bench-scale process research unit (PRU) to determine process performance and to obtain design information on the mild gasification of coals for process scale-up. Subsequently, a part of the work for Task 4, System Integration Studies, was directed to prepare a conceptual preliminary process design including material and energy balances for a 24-ton/day (1-ton/h) adiabatic process development unit (PDU).

Description of the Process Research Unit

As a part of Task 2, a 100-lb/h isothermal process research unit (PRU) system was designed, built, and operated. The PRU was designed to operate at temperatures up to 1500°F and pressures up to 50 psig, and was also designed to provide mechanical flexibility in reconfiguration of the feed locations, the inlet gas supply, and the char discharge locations. Figure II-1 shows the components of the PRU reactor system in a block diagram and Figure II-2 shows an isometric view of the installed PRU in an existing high-bay at IGT.

The reactor vessel consists of an 8-inch-ID fluidized bed that is 8 feet long with a 4-inch-ID entrained bed section above it that is 13 feet long. The reactor and piping is constructed of 316H, a high-carbon stainless steel suitable for temperatures above 1000°F. Several zones of split-shell electrical heaters surround the reactor vessel to maintain isothermal test conditions. Inlet fluidization gases are heated to the test temperature in electrically heated tubing coils. The fluidization gas, with or without the addition of steam, enters the bottom of the fluidized bed through a conical gas distribution grid. A portion of the inlet fluidization gas also enters

A9001018P

Figure II-1. SCHEMATIC OF PRU SYSTEM

Figure II-2. ISOMETRIC OF PRU SYSTEM

through a center jet at the bottom of the conical grid to promote good mixing in the fluidized bed.

The coal feed is held in a large hopper with a capacity of 800 lb of feed. The coal is fed by a screw conveyor to either of two feed nozzle locations on the reactor. The coal can be fed to the mid-region, or freeboard, of the 8-inch-ID reactor or to the fluidized bed near the gas distribution grid. The entire feed hopper is supported from three load cells that continuously monitor the weight of the hopper and its contents. The feed screw is controlled by a variable-speed drive that is calibrated for each feed material before the test.

The mild gasification char in the fluidized bed can be discharged either from the bottom of the fluidized bed or from an overflow position about two feet above the gas distribution grid. The fluidized-bed height can be adjusted by controlling the rotational rate of a char discharge screw that conveys the char to the char lockhopper vessel. The finer mild gasification char is entrained from the reactor along with the product gas, and is separated by two cyclones installed in series. The cyclones are enclosed in an electrical split-shell furnace that maintains a temperature of about 1000°F to avoid condensation of any of the liquid co-products.

A slipstream consisting of approximately 5% of the hot product gas stream is sampled downstream of the cyclones prior to passing through the pressure letdown valves and entering the combustor. The sampling system withdraws a flow-controlled slipstream of hot gas that is filtered at 1000°F and then passes through a series of condensers. A schematic diagram of the dual-train sampling system is shown in Figure II-3. One train is used from the beginning of the test at low flow for continuous on-line gas analysis, and the other train is activated only for the steady-state portion of the test, with the flow regulated to approximate isokinetic conditions for accurate entrained dust recovery. To capture tar aerosols, which are difficult to condense, a solvent injection and recovery system was devised. The solvent, methylene chloride, is pumped into the sample stream after it exits from the hot sintered-metal filters. Condensables-laden solvent (solvent quench) and condensed steam are recovered in water-cooled, ice-cooled, and dry ice/solvent-cooled traps. Any remaining tar aerosols are removed by a final coalescing filter.

Figure II-3. SLIPSTREAM SAMPLING SYSTEM

Following each test, tar-laden solvent and aqueous condensate are drained from the system, and the vessels and lines are thoroughly washed with unstabilized tetrahydrofuran (THF) to complete the recovery of oils/tars and condensed water. Filters are cooled, and the collected dust is removed for determination of fines carryover. The oils/tars dispersed in methylene chloride (solvent quench) and the remaining oils/tars dispersed in THF (THF wash) are analyzed separately, and the data are combined to define the chemical characteristics of the entire oils/tars product.

The operation of the PRU system is controlled by an IBM-compatible PC-based process control and data acquisition software package called "Paragon Control", made by Intel Controls Corporation in Waltham, MA. Two CRT monitors installed in the control panel display multiple screens of real-time information about each system component during the startup, operation, and shutdown of the PRU system. All of the data from the field units are recorded and available for run-time or post-test viewing by the operator. Figure II-4 shows the control room panel with the data acquisition/control system in operation.

Key operating data and calculated values -- such as fluidization and entrainment velocities at the test temperature and pressure, fluidized-bed height, individual and average temperatures in the reactor, differential pressure values in the fluidized bed, and the weight of feed remaining in the feed hopper -- are presented every 10 seconds. Various data values that deviate from specified ranges can trigger visual and audible alarms on the monitors, to allow operator action. The available graphics from this process control software system offer the operator simple and direct control of the operational and process parameters selected for the test. The three lockhoppers in the PRU system, one for the fluidized-bed char and two for the cyclones, are controlled by a separate programmable logic controller panel in the control room. The controller operates the main lockhopper solids-flow valves, the venting valves, and the repressurization valves. Either automatic or manual operation of the lockhoppers can be selected. The timed, sequenced operations of each lockhopper, with safety interlocks, can be programmed or changed as necessary.

An on-line gas chromatograph (GC) analyzes the dry gas composition every 12 minutes from startup to shutdown. The data from the GC are displayed on a

Figure II-4. CONTROL ROOM PANEL WITH DATA ACQUISITION/CONTROL SYSTEM

separate dedicated monitor in the control room. This information is normalized and plotted against the time of the test to give the operator a view of the steady-state test period. Any deviation from steady-state conditions, such as a feed rate change or interruption, can be easily seen.

Description of Mild Gasification Tests and PRU Modifications

Test Coals

Two coals were tested in the PRU operations: A -12 mesh Illinois No. 6 coal obtained from the Peabody Coal Company Randolph Preparation Plant in Baldwin, Illinois, and a metallurgical-grade blended coal consisting of 55% No. 2 Gas Seam and 45% Campbell's Creek Seam from the Peabody Coal Company Wells Complex in Wharton, West Virginia. The Illinois coal had a size consist of 60% below 40 mesh, and the West Virginia coal had a size consist of 90% below 40 mesh. Both of these coals were selected to be representative of high-moisture fines streams from the preparation plants. In most of the tests, the coal was also blended with coke breeze obtained from Mid-Continent Coal & Coke in Gary, Indiana. Two separate batches of the coke breeze were used, designated as Batch 1 and Batch 2. The analytical and physical property data obtained at IGT on the coals and coke breeze batches, following drying in a rotary drum dryer, are shown in Table II-1.

Shakedown Operations

The design and procurement of the PRU system components were started in February 1988. Construction of the PRU system began in September 1988 and was completed in February, 1989, and a series of system proving tests was begun. Seven shakedown tests were conducted with coke breeze and Illinois No. 6 coal, and these tests are summarized in Table II-2. The series of shakedown tests provided a variety of information on the PRU system operation, proving the operation and control of the system, validating certain design features, and demonstrating the quality of the data collected for the elemental and material balances. Various system modifications were identified in these tests to improve the PRU operation. The most important information acquired for control of the mild gasification process was identification of the values of key PRU parameters that must be monitored and regulated to control fluidization and, hence, the conversion of the coal particles. These parameters included: values of various input gas flow rates, temperatures of different

Table II-1. PROPERTIES OF COALS AND COKE BREEZE DILUENTS

	<u>Illinois No. 6^a</u>	<u>West Virginia^b</u>	<u>Coke Breeze</u> <u>Batch 1^c</u>	<u>Batch 2^d</u>
<u>Proximate</u>	----- wt % as fed to reactor -----			
Moisture	5.3	1.4	1.1	0.4
Volatile Matter	34.7	30.6	3.4	4.9
Ash	15.0	6.4	11.4	7.4
Fixed Carbon	<u>45.0</u>	<u>61.6</u>	<u>84.1</u>	<u>87.3</u>
Total	100.0	100.0	100.0	100.0
<u>Ultimate</u>	----- wt % dry basis -----			
Ash	15.8	6.4	11.6	7.4
Carbon	64.3	80.2	85.1	87.3
Hydrogen	4.2	5.0	0.4	1.2
Nitrogen	1.4	1.7	1.2	1.3
Sulfur	3.9	1.3	0.7	2.0
Oxygen (by diff)	<u>10.4</u>	<u>5.4</u>	<u>1.0</u>	<u>0.1</u>
Total	100.0	100.0	100.0	100.0
<u>Sulfur Forms</u>	----- wt % of total sulfur -----			
Pyritic	33.3	33.0	5.9	1.7
Sulfate	3.3	<1.0	3.5	1.1
Sulfide	0.0	0.0	6.8	1.7
Organic	<u>63.4</u>	<u>67.0</u>	<u>83.8</u>	<u>95.5</u>
Total	100.0	100.0	100.0	100.0
HHV, Btu/lb (dry)	11,599	14,535	12,504	13,385
Free Swelling Index	1½	5½	0	0

^a Baldwin No. 1, Marissa and River King No. 6 Mines; proximate and ultimate analyses are averages of 4 samples; sulfur forms are from analysis of Test MG-16 feed coal.

^b 55% No. 2 Gas Seam/45% Campbell's Creek Seam; proximate and ultimate analyses are averages of 3 samples; sulfur forms are "typical" values from supplier.

^c Proximate and ultimate analyses, average of 3 samples; sulfur forms, 1 sample; used in tests up to and including Test MG-30.

^d Proximate and ultimate analyses, average of 4 samples; sulfur forms, 1 sample; used in Test MG-31.

Table II-1, Cont. PROPERTIES OF COALS AND COKE BREEZE DILUENTS

	<u>Illinois No. 6</u>	<u>West Virginia</u>	<u>Coke Breeze</u>	
			<u>Batch 1</u>	<u>Batch 2</u>
<u>Proximate</u>				
U. S. Screen Size	wt % retained on screen			
12	3.88	0.00	21.30	19.40
20	17.50	0.32	26.90	25.30
40	40.50	9.83	20.80	21.20
60	25.30	14.40	11.90	13.60
80	8.87	12.10	6.26	7.46
100	2.11	7.09	2.68	3.80
140	1.00	13.60	3.58	4.39
200	0.33	7.73	2.46	2.49
230	0.11	1.29	0.67	0.58
270	0.11	3.55	0.89	0.58
325	0.11	3.06	0.67	0.29
Pan	0.18	27.03	1.89	0.91
Total	100.00	100.00	100.00	100.00

PRU sections, differential pressures indicating the height and stability of the fluidized bed, hot fluidized-bed char discharge rates, overhead char rates collected by the cyclones, and minimum operating pressure to provide a sufficient gas flow through the slipstream sampling system. Also, improvements were made to maintain non-condensing conditions in the hot filtration and connective piping sections of the slipstream sampling system and to improve quantitative recovery of co-product samples.

The system modifications that were made to the PRU were evaluated after each successive shakedown test. Physical modifications to the PRU system were relatively minor. Routine post-test inspection and cleanup procedures were also learned and implemented for all vessels to assure operational success and satisfactory material balances. A fiber optic probe was found to be very useful to quickly inspect the PRU vessels and shorten the turnaround time.

The modifications made to the PRU system during the shakedown tests included the following:

- A pressure equalizing line was installed between the feedhopper and the reactor, replacing the automatic system for feedhopper pressure and purge control which, during periods of pressure imbalance, caused occasional surges in the feed rate.

Table II-2. SUMMARY OF MILD GASIFICATION SHAKEDOWN TESTS

	Test No.			
	SD-1	SD-2	SD-3	SD-4
Purpose of Test	To verify solids split between entrained and fluidized beds	To achieve stable operation with coal mixture feed	To achieve stable test with coal mixture at lower fluidization	Repeat SD-3 with pressure equalizing line installed
Feed Material	coke	1:1 mixture coal ^a /coke	coal ^a	1:1 mixture coal ^a /coke
Feed Rate, lb/h	63.0/122.0	10.0	50.0	50.0
N ₂ Rate, lb/h ^b	64.0	112.3	50.1	42.9
Steam Rate, lb/h	0.0	22.1	0.0	0.0
Steam/Coal Ratio	0.00	4.42	0.00	0.00
Temperature, °F ^c	1100	1200	1350	1350
Pressure, psig	0.5	10	5	5
Feed Location	Freeboard	Freeboard	Freeboard	Freeboard
Fluidized-Bed Height, ft	--	--	--	--
Superficial Gas Velocity, ft/s	2.0	3.0	1.4	1.2
Solids Residence Time, min	--	--	--	--
Steady-State Period, h	--	--	--	--
Remarks	Solids carry-over and underflow split achieved	Fines blocked combustor inlet mixer	Pressure control upset of feed rate	Inadequate mixing in low-velocity fluidized bed

^a Illinois No. 6 coal.

^b Not including purge nitrogen.

^c Average of four thermocouples.

Table II-2, Cont. SUMMARY OF MILD GASIFICATION SHAKEDOWN TESTS

	Test No.		
	SD-5	SD-6	SD-7
Purpose of Test	To establish fluidized bed without starter coke in bed	To test feed to fluidized bed directly	Repeat SD-6 with coal
Feed Material	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	coal ^a
Feed Rate, lb/h	50.0	34.0	50.0
N ₂ Rate, lb/h ^b	41.1	91.4	115.6
Steam Rate, lb/h	0.0	12.4	0.0
Steam/Coal Ratio	0.00	0.73	0.00
Temperature, °F ^c	1275	1300	1225
Pressure, psig	5	10	10
Feed Location	Freeboard	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	--	3.3	--
Superficial Gas Velocity, ft/s	1.1	2.4	2.4
Solids Residence Time, min	--	40	--
Steady-State Period, h	--	3.0	--
Remarks	High purge gas flow reduced char discharge from underflow	Good test with char underflow from fluidized bed	Low feed gas flow with feed, agglomerate growth under feed nozzle

^a Illinois No. 6 coal.

^b Not including purge nitrogen.

^c Average of four thermocouples.

- Nitrogen blast taps were added to the continuously purged pressure differential taps in the fluidized bed and were used periodically to clear the ends of the taps.
- A similar blast tap was installed in the center char discharge pipe below the reactor to maintain a uniform flow of solids from the fluidized bed to the char discharge screw.
- A continuous nitrogen purge was added to the "fire eye" combustor controller that keeps the flame free of dust accumulation.
- The threaded fittings on the frequently disassembled hot gas line to the conical gas distributor were replaced with the more durable "Graylok" fittings with a single seal-ring gasket.
- The ranges on all of the instrumentation transmitters were precisely calibrated after one certified transmitter was found to be mis-set from the factory.

To improve operator control and data quality, computer software parameters controlling the frequency of data acquisition were changed to more accurately collect and display critical test data and calculated values. Although this required about twice the amount of data storage capacity for each test, disk storage space was available. Two additional graphic screens of information, devoted entirely to the critical calculated fluidized-bed parameters and other system values, were created for display. The cycle times for the operation of the system's lockhoppers were shortened to 20 minutes so that more char samples could be obtained at shorter intervals during each test.

Another purpose of the series of shakedown tests was to identify the values of superficial gas and entrainment velocities required to achieve different fractional splits of the various particle sizes of the coal feed when the feed was introduced into the freeboard region above the fluidized bed. The PRU entrainment velocity could be adjusted with an auxiliary nitrogen input to the freeboard section, to increase the velocity in the 4-inch-ID entrained section while maintaining an ideal superficial gas velocity in the fluidized bed. This feature was installed on the reactor to test different material size splits for different coal types and sizes tested in the same mild gasification reactor.

The process options of either feeding to the freeboard or splitting the coal feed between the fluidized bed and the entrained section both depend on a stable fluidized bed operation. Shakedown Test SD-6 was the first PRU test

operated with feeding to the fluidized bed. The test continued for 3 hours of steady-state operation with a 1:1-weight-ratio mixture of Illinois No. 6 coal and coke breeze.

The coal feed material used in the shakedown tests was the Illinois No. 6 coal. This coal was also tested in all of the mild gasification tests up to MG-26. Tests MG-27 through MG-31 were performed with the West Virginia metallurgical-grade coal. The mild gasification tests in the PRU operated satisfactorily with the Illinois No. 6 coal when blended in a 1:1 weight ratio with a non-caking non-reacting coke breeze. A key operational fact-learned about the 8-inch-ID PRU was that the amount of devolatilized char present in the fluidized bed is very important for the dilution and distribution of the incoming caking coal until the coal loses its caking tendency through devolatilization. Previous experience at IGT in operating the 3-foot-ID U-GAS coal gasification pilot plant showed that caking coals could be fed without blending if the ratio of the feed rate of caking coal to the weight of char in the fluidized bed is equal to or less than 1:1. Blending the feed coal with coke breeze assures that this ratio is maintained in the 8-inch-ID PRU.

This information learned from PRU operations is important for process scale-up of the mild gasification process with caking coals. Fluidized beds larger than the 8-inch-ID PRU would be expected to have a sufficient char inventory so that the feed blending practiced in the PRU tests may not be necessary in larger reactors. That information, however, has to be developed further in Task 4, studying system integration and process scaleup. In a scaled-up reactor, blending of the feed coal with a hot recycled char may be required to supply heat for the mild gasification process.

Mild Gasification Tests

The mild gasification tests began after the seven shakedown tests. Thirty-one tests were conducted, and these are summarized in Table II-3. A brief description of the test purpose and results follows. The operational performance of the test coals was determined under a variety of mild gasification test conditions and several modifications were made to the PRU to improve its performance.

The first mild gasification tests were planned to use fluidized-bed freeboard feeding of 100% Illinois No. 6 coal, and subsequent tests were

Table II-3, Part 1. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-1	MG-2	MG-3	MG-4
Purpose of Test	Test feed nozzle extended 2 inches into fluidized bed	Test ½-inch screen over gas distributor to stop blockage	Test lime-stone as diluent with coal	Test with coke diluent and lower fluidized-bed height
Feed Material	coal ^a	coal ^a	1:1 mixture coal ^a /lime-stone	1:1 mixture coal ^a /coke
Feed Rate, lb/h	50.0	50.0	62.5	50.0
N ₂ Rate, lb/h ^b	91.6	89.1	136.4	110.9
Steam Rate, lb/h	14.2	15.8	0.0	16.4
Steam/Coal Ratio	0.57	0.63	0.00	0.66
Temperature, °F ^c	1325	1325	1325	1325
Pressure, psig	10	10	10	10
Feed Location	Freeboard	Freeboard	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	--	--	2.5	1.3
Superficial Gas Velocity, ft/s	2.5	2.5	3.0	3.0
Solids Residence Time, min	--	--	15	--
Steady-State Period, h	--	--	4	--
Remarks	Char lump blocked underflow discharge	Inadequate mixing in fluidized bed	Successful test, but no steam due to faulty transmitter	Small clumps formed on screen over grid

a Illinois No. 6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table II-3, Part 2. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-5	MG-6	MG-7	MG-8
Purpose of Test	Test center gas jet for better mixing 1.6-inch jet diameter	Repeat test MG-5 with 100% coal	Repeat test MG-6 with smaller jet diameter of 0.875-inch	Test raised gas grid and center jet, use -40 mesh sized coal
Feed Material	1:1 mixture coal ^a /coke	coal ^a	coal ^a	coal ^a
Feed Rate, lb/h	109.0	70.0	25.0	29.4
N ₂ Rate, lb/h ^b	216.7	129.3	119.5	51.0
Steam Rate, lb/h	11.2	11.2	17.5	5.3
Steam/Coal Ratio	0.21	0.32	1.40	0.36
Temperature, °F ^c	1100	1200	1200	1320
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	2.0	2.0	2.0	1.25
Superficial Gas Velocity, ft/s	4.5	3.0	3.0	1.3
Solids Residence Time, min	10	--	--	--
Steady-State Period, h	3	--	--	--
Remarks	Successful test operation	Poor mixing, coal found on top of bed	Inlet gas superheater shorted, still poor mixing	High fines carryover, plugged lines, cyclone inlet velocity too low

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table II-3, Part 3. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-9	MG-10	MG-11	MG-12
Purpose of Test	Test -40 mesh coal feed with fine coke breeze starter bed	Test -12 mesh feed with larger central jet diameter	Repeat MG-10 at higher temperature	Repeat MG-11 at lower temperature
Feed Material	coal ^a	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	22.1	23.9	20.5	22.7
N ₂ Rate, lb/h ^b	60.0	156.7	154.9	150.9
Steam Rate, lb/h	5.4	10.7	12.4	12.4
Steam/Coal Ratio	0.49	0.90	1.21	1.09
Temperature, °F ^c	1320	1320	1390	1252
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	1.25	1.25	1.25	1.25
Superficial Gas Velocity, ft/s	1.5	3.8	4.0	3.6
Solids Residence Time, min	--	--	32	29
Steady-State Period, h	--	--	3.25	3.25
Remarks	Fines plugged sample system, lost starter bed before coal feed	Reactor heat element short uneven thermal expansion	Successful test operation	Successful test operation

^a Illinois No.6 coal

^b Not including purge nitrogen

^c Average of four thermocouples

Table II-3, Part 4. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-13	MG-14	MG-15	MG-16
Purpose of Test	Test higher coal-to-coke ratio	Repeat MG-12 at lower temp and relocated pressure taps	Repeat MG-12 at about 1000 °F	Test deeper fluidized bed with higher feed rate
Feed Material	2:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	14.0	23.2	19.5	32.4
N ₂ Rate, lb/h ^b	146.7	173.1	172.2	153.2
Steam Rate, lb/h	12.4	14.1	14.0	12.4
Steam/Coal Ratio	1.32	1.22	1.44	0.77
Temperature, °F ^c	1260	1084	1034	1183
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	1.25	1.25	1.25	2.0
Superficial Gas Velocity, ft/s	3.5	3.7	3.6	3.5
Solids Residence Time, min	--	28	33	20
Steady-State Period, h	--	2.25	3.0	3.0
Remarks	Cake buildup on reactor wall covered pressure taps	Successful test operation	Successful test operation	Successful test operation

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table II-3, Part 5. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-17	MG-18	MG-19	MG-20
Purpose of Test	Test -40 mesh feed to entrained bed	Operate with deeper bed, greater char inventory, higher steam rate	Greater bed height, higher feed rate, higher steam rate	High feed rate test
Feed Material	coal ^a fines (-40 mesh)	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	20.0	48.2	90.8	93.8
N ₂ Rate, lb/h ^b	149.4	162.8	189.7	221.9
Steam Rate, lb/h	12.4	23.4	23.7	15.9
Steam/Coal Ratio	1.24	0.97	0.52	0.34
Temperature, °F ^c	1200	1178	1102	1120
Pressure, psig	10	10	10	10
Feed Location	Freeboard	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	--	2.5	3.0	1.8
Superficial Gas Velocity, ft/s	(entrained vel = 13.8)	4.0	4.4	4.8
Solids Residence Time, min	0.02	28	14	--
Steady-State Period, h	3.0	2.0	2.0	--
Remarks	Char found in bed, velocity too low	Successful test operation	Successful test operation	Start test at 100 lb/h, bed defluidized at 200 lb/h

^a Illinois No.6 coal

^b Not including purge nitrogen

^c Average of four thermocouples

Table II-3, Part 6. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-21	MG-22	MG-23	MG-24
Purpose of Test	Repeat of Test MG-19 with reduced steam rate	Operate test without steam	Use recycled MG-21 char as diluent	Entrained test, feed in bed nozzle, residence time longer
Feed Material	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /MG char	coal ^a fines (-40 mesh)
Feed Rate, lb/h	94.0	95.2	77.0	27.7
N ₂ Rate, lb/h ^b	230.0	233.1	194.1	372.6
Steam Rate, lb/h	8.5	0.0	15.7	18.2
Steam/Coal Ratio	0.18	0.00	0.41	1.31
Temperature, °F ^c	1109	1147	1100	1180
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed Nozzle
Fluidized-Bed Height, ft	2.0	1.8	2.3	--
Superficial Gas Velocity, ft/s	4.7	4.6	4.2	(entrained vel = 8.1)
Solids Residence Time, min	10	8	--	--
Steady-State Period, h	3.5	2.5	--	--
Remarks	Successful test operation	Successful test operation	Bed defluidized 15 minutes after start	Discharge from feed hopper restricted

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table II-3, Part 7. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-25	MG-26	MG-27	MG-28
Purpose of Test	Repeat MG-23 conditions using MG-21 char as diluent	Feed coal mixed with calcium oxide	First test with West Virginia coal	Repeat MG-27 with feed sweep gas at lower temp and higher flow
Feed Material	1:1 mixture coal ^a /MG char	1:1 mixture coal ^a /lime	1:2 mixture coal ^b /coke	1:2 mixture coal ^b /coke
Feed Rate, lb/h	100.3	83.0	64.1	51.9
N ₂ Rate, lb/h ^c	223.1	140.5	160.7	173.4
Steam Rate, lb/h	11.1	7.5	8.2	8.2
Steam/Coal Ratio	0.22	0.18	0.38	0.47
Temperature, °F ^d	1134	1140	1225	1149
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	3.0	1.9	2.2	1.4
Superficial Gas Velocity, ft/s	4.7	3.0	3.6	3.7
Solids Residence Time, min	8	--	--	15
Steady-State Period, h	2.0	--	1.0	3.5
Remarks	Successful test operation	Bed defluidized 15 min after start	Plug at end of feed nozzle to bed	Successful test operation

a Illinois No. 6 coal

b West Virginia coal

c Not including purge nitrogen

d Average of four thermocouples

Table II-3, Part 8. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.		
	MG-29	MG-30	MG-31
Purpose of Test	Repeat MG-28 at lower temperature	Repeat MG-28 at lower temperature	Repeat MG-30 with 1:1 feed mixture
Feed Material	1:2 mixture coal ^a /coke	1:2 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	54.3	67.2	70.6
N ₂ Rate, lb/h ^b	183.2	183.4	181.6
Steam Rate, lb/h	8.2	8.2	8.2
Steam/Coal Ratio	0.45	0.37	0.23
Temperature, °F ^c	990	1050	1048
Pressure, psig	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	2.4	2.4	3.75
Superficial Gas Velocity, ft/s	3.5	3.7	3.6
Solids Residence Time, min	--	17	19
Steady-State Period, h	--	3.0	2.75
Remarks	Feed line plug at reactor stopped test	Successful test operation	Successful test but char overflow interruption

^a West Virginia coal

^b Not including purge nitrogen

^c Average of four thermocouples

planned for feeding into the fluidized bed. In Tests MG-1 and MG-2, 100% Illinois No. 6 coal was fed to the freeboard. Small, lightly agglomerated clumps of material formed and blocked the char discharge pipe located in the bottom-center of the gas distribution grid. The contributing cause identified in these tests was a lack of good mixing in the fluidized bed with the freeboard-fed coal floating at the top of the bed and preventing sufficient feed penetration into the fluidized bed. Also, a downward growing "beard" aggregation formed on the reactor wall in the freeboard just under the feed nozzle. A higher feed nozzle gas injection velocity prevented the formation of the growth in subsequent tests. In Test MG-3, Illinois No. 6 coal blended with dolomitic limestone was fed to the fluidized bed. The test operated successfully for a 4-hour steady-state period. The purpose of the limestone used in Test MG-3 was to investigate the fluidization-mixing-reaction dynamics with a non-carbonaceous diluent, and limestone was readily obtainable.

Test MG-4 was an attempt to repeat Test MG-3 conditions using diluent coke instead of limestone. Small clumps of material formed at the bottom of the fluidized bed on the one-half-inch screen added over the center char discharge nozzle, which was placed to prevent the blockage of the char discharge nozzle. The screen was removed after Test MG-4.

Various diameters of the center gas jet were tried in Tests MG-5, MG-6, and MG-7, with coal/coke mixtures and coal alone, to see if mixing in the fluidized bed could be improved. Following these tests, a significant modification was made to promote better mixing and dispersal of the incoming coal particles to the fluidized bed. The distance between the feed inlet nozzle and the fluidized bed conical gas distributor grid was shortened to 3 inches from the previous 12 inches, as indicated in Figure II-5. The grid assembly and its associated piping were modified to allow a portion of the hot fluidization gas to enter the fluidized bed through a center pipe, along with the fluidization gas entering through the holes in the conical grid itself. As shown in Figure II-5, the coal feed nozzle was relocated 12 inches below the char overflow port and 3 inches above the outer edge of the conical gas distributor. This arrangement introduces the coal deep into the bed in a zone of high turbulence, thus increasing the mixing of the incoming coal particles in the fluidized bed. With the particles dispersed quickly throughout the fluidized bed, the frequency of collisions between the sticky particles is reduced and fluidization stability is increased.

Figure II-5. FLUIDIZATION GRID MODIFICATIONS

In conjunction with the grid modification to improve mixing in the fluidized bed, tests with smaller coal particles, without the diluent coke, were attempted to see if the higher heat-up rate of the smaller particles and subsequent rapid devolatilization would lead to improvements in fluidization stability and coal conversion. Test MG-8 was conducted to test the operation of the reactor with the relocated gas distributor. Also, the 100% Illinois No. 6 coal feed was screened to -40 mesh to facilitate rapid particle heat-up. During this test, system pressure upsets eventually led to fluidized bed instability and early shutdown. The cause of the upset was found to be an excessive carry-over of char fines that led to plugging in the pressure equalizing line between the reactor and the feed hopper, together with the malfunction of a pressure letdown valve actuator mechanism. Ultimately, the excessive fines carry-over resulted from the fact that the lower superficial gas velocity necessary for fluidizing the -40-mesh coal particles caused the cyclones to operate at a low collection efficiency.

Test MG-9 was conducted, again with the -40 mesh coal, but with a start-up fluidized bed of coke breeze screened to -40 mesh to match the superficial gas velocity of the fine feed coal in the startup and steady-state periods. The test was stopped as fines plugged the slipstream condensate sampling system in the line to the hot gas filter. A high entrainment rate of the fine coke breeze from the starter fluidized bed was also evident from the observation of fluidized bed differential pressure values before the coal feed was begun.

In Test MG-10, the feed size was returned to -12 mesh, and the 1:1 coal-to-coke weight ratio mixture was used. For this test, the diameter of the central jet in the gas distributor was increased from 0.5 to 1 inch. The test had to be aborted when a reactor heating element in the fluidized-bed zone grounded against a pressure tap fitting, causing a loss of temperature control in the fluidized-bed section. The feedopper load cells at this time also gave a false reading of the feed weight, indicating an incorrect feed rate. It was determined that both problems were the results of an unbalanced thermal expansion between the feed system and the reactor. The impact of this situation in subsequent tests was eliminated by welding additional steel supports to immobilize the feed screw housing and by adding a guide to the vertical feed line to prevent lateral movement.

Following the repair of the heater and the feed line support modifications, Test MG-11 was operated successfully at conditions similar to Test MG-10, but at a temperature of 1390°F. Test MG-12 was conducted at conditions similar to Test MG-11, but at a lower temperature of 1252°F.

Test MG-13 was conducted with a feed mixture containing a 2:1 ratio of coal to coke breeze to increase the coal input to the PRU. The test was interrupted prior to the steady-state period because of a buildup of caked coal on the reactor walls, which covered the pressure taps and blocked the feed and overflow discharge ports. The pressure taps were relocated away from the feed inlet region for subsequent tests.

Test MG-14 was conducted successfully with the 1:1 coal-to-coke mixture at 1084°F. Test MG-15 was a repeat of the same test operation at a lower temperature of 1034°F. Test MG-16 was successfully conducted with a higher feed rate and a deeper fluidized bed of about 24 inches. The bed height in this test was increased to a point above the 15-inch location of the char overflow nozzle by reducing the speed of the char discharge screw, thus allowing the bed to build up above the discharge opening. The Illinois No. 9 coal feed was screened to remove the -40 mesh fines fraction. This was done to restrict mild gasification to the fluidized-bed section by minimizing the entrainment of coal. The test temperature was 1183°F.

Test MG-17 was then conducted, using only the -40 mesh feed coal fines, to investigate the performance of the entrained reaction zone separately from the fluidized bed. The -40 mesh fraction represents about one-third of the -12 mesh size coal stream from the Peabody coal preparation plant. Therefore, the 1:1 mixture of -40 mesh coal and coke was fed to the freeboard at 20 lb/h at a test temperature of 1200°F. The test achieved steady operation and was voluntarily shut down. After the test, about 36 lb (60%) of the total feed was found to have collected in the fluidized-bed region rather than having elutriated from the reactor.

Test MG-18 was operated with a higher steam rate and a higher fluidized-bed height to increase the char inventory in the fluidized bed. The char was discharged successfully as in Test MG-16, but shortly after the conclusion of the one-hour slipstream sampling period, a small one-inch plug of material blocked the feed line to the reactor.

Test MG-19 was conducted to repeat the higher feed rate conditions of Test MG-5, but with a deeper fluidized bed of 36 inches. This test also ran smoothly and parametric data were obtained in completing about two hours of operation until another pressure upset occurred during the repressurization of the first cyclone's lockhopper. The cause of the pressure upsets was found to be a plugged instrumentation line to a differential pressure switch that allows operation of the lockhopper solids dump valve after the lockhopper is sufficiently vented. During repressurization, the system over-pressurized the lockhopper and the pulse affected the fluidized-bed operation. All of the system tubing lines for venting, pressurization, and pressure equalization were inspected and cleaned prior to the following test.

The goal for Test MG-20 was to increase the feed rate to 200-lb/h, to achieve the design coal feed rate of 100-lb/h. The test began normally with a smooth startup and steady operation at an initial feed rate of 93.8-lb/h for 45 minutes. At that time, the feed rate was increased to about 200-lb/h. After ten minutes at this rate, the fluidized bed became defluidized and char stopped discharging from the bed. After the test, a clump of material was found in the fluidized-bed, indicating that too much feed coal was entering the fluidized-bed reactor compared to the volume of bed char.

Test MG-21 and MG-22 were conducted at the same conditions as Test MG-19 but with different steam inputs to the fluidized bed. These three tests were designed to analyze the effects of steam upon mild gasification and the production and quality of the co-products. For these three comparative tests, the feed rate was maintained from 91 to 95 lb/h and the temperature from 1100° to 1150°F.

Test MG-23 was conducted with the purpose of reducing the amount of inert coke diluent used in the feed mixture for the tests. This was achieved by blending the feed coal with fluidized-bed char collected from Test MG-21. An equal amount of Illinois No. 6 coal was blended with char from Test MG-21 to reduce the weight percentage of coke in the feed mixture from 50% to an estimated 32%. In this way, the Illinois No. 6 coal-derived char in the feed mixture more closely simulates mild gasification with a recycle char stream. The char collected from this test was intended for subsequent blending with coal in later tests to further reduce the amount of coke in the feed mixture; however, about one half-hour after feeding of the mixture was begun, a heater

zone in the fluidized-bed zone failed and the fluidized-bed temperature declined, leading to test shutdown.

Test MG-24 was conducted to investigate entrained-flow mild gasification while waiting for a replacement heater element for the fluidized bed. In this test, the -40 mesh fines fraction of the coal was fed to the fluidized-bed nozzle rather than to the freeboard nozzle, to gain additional solids residence time. The entraining gas velocity in the 8-inch section was set at 8-ft/s and, based on a gas-solids flow correlation, the solids residence time in the 8-inch-ID, 8-foot-long entrained section was calculated to be about 1.2 seconds. The 4-inch piping above the 8-inch zone added another 0.4 second for a total solids residence time of 1.6 seconds.

This arrangement of the fines feed location was designed to improve upon Test MG-17, in which the coal fines were fed to the 8-inch-ID freeboard section above the fluidized bed. The fluidization velocity in Test MG-17 had been 3-ft/s in the 8-inch section. This was too low to entrain the fines and thus they fell on the top of the fluidized bed and did not mix into it. In Test MG-24, however, the feedhopper stopped discharging the fine particles after 35 minutes of feeding. Inspection after the test showed that fine particles were plugging the pressure equalizing line between the feedhopper and the reactor and two instrumentation lines connected to the cyclone-lockhopper system.

Test MG-25 was conducted to repeat the aborted Test MG-23, using the coal and recycle char from Test MG-21 to reduce the amount of diluent coke in the feed mixture. The blended feed mixture was fed at 100-lb/h for two hours and the steady-state sampling period was completed before the feed was interrupted from the feedhopper. A plug in the feed line prevented the resumption of feeding and the test was stopped.

Test MG-26 investigated the addition of calcium oxide to the feed to react with hydrogen sulfide in the product gas and possibly to reduce the sulfur content of the condensables. The coal and calcium oxide were mixed in a 1:1 weight ratio without any diluent coke material to simplify analysis of the data. The feed rate was 85-lb/h and the fluidized-bed temperature was set at 1140°F. Calcium oxide is known to be reactive with moisture and it has a high heat of hydration. Thus, the mixture for Test MG-26 was prepared one hour before the test to avoid a temperature rise or change in physical

characteristics of the mixture. In spite of this, the temperature of the mixture in the drum did rise to about 250°F in the center and the mixture was difficult to pour out of the drum. The test ran for 15 minutes when the bed began to de-fluidize. After 50 minutes of trying to fluidize the bed, the feed rate of the mixture from the hopper could not be maintained uniformly.

Batch premixing of the 5%-moisture coal and calcium oxide could be avoided in the PRU system with the addition of a second hopper and screw feeder for the calcium oxide or other additive. Mixed in small quantities and introduced quickly to the PRU, the effect of the hydration reaction can be minimized. Prior to Test MG-26, a five-gallon bucket of coal and calcium oxide was prepared and tested in a 6-inch cold flow fluidization test column, and then stored for 48 hours afterwards. In this small quantity, no temperature rise was noted and the mixture was free-flowing and easy to pour after 48 hours. This suggests that mixing at the point of feeding would be successful.

Test MG-27 was the first test conducted to evaluate the mild gasification performance of the metallurgical-grade coal obtained from Peabody's preparation plant in West Virginia. The coal as received had a finer size consist than the Illinois No. 6 coal, as shown in Table II-1. The coal was mixed with diluent coke for the first set of tests in a 1:2 weight ratio, because of its higher fines content and higher free swelling index compared to the Illinois No. 6 coal. This was done with the intent of increasing the coal/coke ratio for subsequent tests. The test proceeded well through two hours, after which the sampling period began; however, five minutes into the sampling period, the feed line into the reactor became blocked. The blockage was temporarily relieved by isolating the feedhopper and increasing the feed sweep gas flow through the nozzle. The blockage, however, developed again and the test was stopped. Inspection of the reactor, cyclones, and piping showed that everything was clean and the blockage was restricted to a one-half inch plug in the feed line at the point where it enters the reactor. To eliminate this occurrence in the next test, the feed sweep gas temperature was reduced from 690° to 500°F and the sweep gas velocity was increased.

Test MG-28 was conducted to repeat the conditions of Test MG-27. The temperature was 1170°F and the feed rate was 51.9 lb/h. The test operated well for over 3.5 hours with a very steady flow of fluidized-bed char

discharge and steady fluidized-bed differential pressure values. Solids recovered from the reactor after the test were free-flowing.

Test MG-29 was operated with West Virginia coal under conditions similar to those of MG-28, but at a lower temperature of 990°F. In spite of the reduced feed sweep gas temperature, a small plug in the coal feed line at the entrance to the reactor occurred one hour after the start of coal feeding. The 1/2-inch-thick blockage in the one-inch pipe caused a shutdown of the test prior to steady state. The solids drained from the reactor after the test were free-flowing. The material from the feed line plug was composed of very fine coal particles that had agglomerated and built up in that area. Following the test, a movable rod-probe was installed in the feed pipe using a packing-gland fitting for a seal. This probe was designed to clear feed line blockages if required during subsequent tests.

Test MG-30 was successfully operated with the West Virginia coal at 1050°F, using the 1:2 coal/coke feed mixture, repeating the conditions of Test MG-29. The mixture feed rate was 67.2 lb/h. Steady-state operation was maintained for 3 hours, and slipstream samples were collected after the second hour. Solids drained from the reactor after the test were free-flowing. About 200 grams of material agglomerated around the thermocouples that protrude into the reactor.

In Test MG-31, the ratio of coal to coke was increased to 1:1. An erroneous reading from one of the bed thermocouples, which was later traced to agglomeration of coal on the thermocouple, showed a bed temperature of 600°F. The readings from the remaining three bed thermocouples indicated an average bed temperature of 1050°F, which was reported for the test. Interruptions in the overflow char discharge during the sampling period occurred, resulting in a fluctuating bed height and difficulties in obtaining representative char samples and determining a char discharge rate. Although the system continued to operate until a voluntary shutdown, post-test examination of the material balance data led to the conclusion that the lack of steady-state conditions during sampling rendered the data from this test unacceptable. The char discharged from the fluidized bed was noticeably larger, about 1/8-inch particle diameter, and more nearly uniform in size than bed material from previous tests.

These tests were beneficial in identifying several mechanical design and operational modifications for successful processing of caking bituminous coals.

Integrated PRU tests conducted while preparing this report have identified a very important problem in feeding the coal/coke mixture into the 8-foot-tall feedhopper. The long drop of the mixture was observed to promote segregation of coal at the bottom of the feedhopper, thus increasing the chance of feeding coal-rich mixtures at the beginning of a test. This increases the probability of feed agglomeration and early termination of the test, and may also have significant impact upon the material and elemental balance data for tests that continue to completion. This issue will be discussed further in the following section on PRU test results. The operational modifications implemented to avoid segregation of coal in the feed, and its effect on PRU operation, will be presented in subsequent project reports.

Discussion of PRU Test Results

Introduction

Analyses of char, oils and tars, and gas from the PRU reactor and slipstream sampling system were completed for the successful Illinois No. 6 coal Tests SD-6, MG-3, MG-5, MG-11, MG-12, MG-14, MG-15, MG-16, MG-18, MG-19, MG-21, MG-22, MG-25, and the West Virginia coal Tests MG-28 and MG-30. The data from these tests were used to construct material balances and to examine the effects of mild gasification system temperature and fluidizing gas steam content on the yield and quality of co-products. The analyses of solids are given in Tables II-4 through II-18. Oils and tars analyses are shown in Tables II-19 and II-20, and gas analyses are given in Table II-21. The normalized material balances for the tests listed above are tabulated, and a description of the data normalization procedure is given in the following section.

Material Balances

The raw and adjusted material balances for successful PRU tests are presented in Tables II-22 through II-36. These balances have been normalized in a logical fashion to provide a consistent basis for comparison of the tests. The major measurable streams of carbon and ash were usually better than 90% in balance from the raw data.

Table II-4. ANALYSES OF SOLIDS FROM TEST SD-6
(Test Temperature = 1300°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	3.08	5.33	1.12	0.24	0.52	0.76	ND
Volatile matter	20.83	34.71	3.44	5.09	6.42	7.43	ND
Ash	13.76	15.01	11.44	17.45	14.88	14.63	ND
Fixed carbon	<u>62.33</u>	<u>44.95</u>	<u>84.00</u>	<u>77.22</u>	<u>78.18</u>	<u>77.18</u>	ND
Total	100.00	100.00	100.00	100.00	100.00	100.00	ND
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	73.72	64.33	85.12	78.56	79.79	79.31	ND
Hydrogen	2.61	4.22	0.35	0.37	0.93	1.03	ND
Sulfur	2.21	3.90	0.70	1.35	1.81	1.90	ND
Nitrogen	1.37	1.37	1.21	1.32	1.64	1.65	ND
Oxygen (by diff.)	5.89	10.35	1.05	0.91	0.87	1.37	ND
Ash	<u>14.20</u>	<u>15.83</u>	<u>11.57</u>	<u>17.49</u>	<u>14.96</u>	<u>14.74</u>	ND
Total	100.00	100.00	100.00	100.00	100.00	100.00	ND
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	3.88	21.30	--	--	--	--
20	--	17.50	26.90	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	--	--	--	--
60	--	25.30	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	--	--	--	--
100	--	2.11	2.68	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	--	--	--	--
230	--	0.11	0.67	--	--	--	--
270	--	0.11	0.89	--	--	--	--
325	--	0.11	0.67	--	--	--	--
PAN	--	<u>0.18</u>	<u>1.89</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND - analysis not done

Table II-5. ANALYSES OF SOLIDS FROM TEST MG-3
(Test Temperature = 1325°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.72	5.33	NA ^a	0.28	1.02	1.07	ND
Volatile matter	41.40	34.71	NA	34.60	22.08	29.02	ND
Ash	36.24	15.01	NA	43.75	25.67	34.41	ND
Fixed carbon	<u>19.64</u>	<u>44.95</u>	NA	<u>21.37</u>	<u>51.23</u>	<u>35.50</u>	ND
Total	100.00	100.00	NA	100.00	100.00	100.00	ND
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	37.67	64.33	NA	33.60	60.43	49.23	ND
Hydrogen	1.51	4.22	NA	0.17	1.04	0.71	ND
Sulfur	1.64	3.90	NA	0.82	1.56	1.37	ND
Nitrogen	0.66	1.37	NA	0.52	1.31	1.09	ND
Oxygen (by diff.)	21.27	10.35	NA	21.02	9.73	12.82	ND
Ash	<u>37.25</u>	<u>15.83</u>	NA	<u>43.87</u>	<u>25.93</u>	<u>34.78</u>	ND
Total	100.00	100.00	NA	100.00	100.00	100.00	ND
Heating Value, Btu/lb	5036	11,599	NA	3429	8903	6753	ND
Particle Density, g/cm ³	ND	1.46	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	--	0.00	ND	0.09	--	--	ND
12	1.92	3.88	--	7.00	--	0.25	--
20	8.55	17.50	--	20.40	--	--	--
30	--	--	--	--	--	--	--
40	33.90	40.50	--	47.60	0.66	--	--
60	26.80	25.30	--	20.00	5.25	0.25	--
70	--	--	--	--	--	--	--
80	13.70	8.87	--	3.69	7.55	1.24	--
100	6.09	2.11	--	0.65	6.57	1.24	--
120	--	--	--	--	--	--	--
140	6.09	1.00	--	0.46	14.10	4.98	--
170	--	--	--	--	--	--	--
200	1.66	0.33	--	0.11	15.30	55.70	--
230	0.37	0.11	--	--	6.24	11.70	--
270	0.21	0.11	--	--	8.05	5.72	--
325	0.11	0.11	--	--	6.73	7.21	--
PAN	<u>0.60</u>	<u>0.18</u>	--	--	<u>29.55</u>	<u>11.71</u>	--
	100.00	100.00	--	100.00	100.00	100.00	--

ND = analysis not done

NA = not applicable

a The diluent in this test was limestone

Table II-6. ANALYSES OF SOLIDS FROM TEST MG-5
(Test Temperature = 1100°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	4.95	5.33	1.12	0.59	0.94	1.70	6.01
Volatile matter	18.92	34.71	3.44	18.24	9.08	13.54	21.03
Ash	12.71	15.01	11.44	18.50	13.21	29.25	35.96
Fixed carbon	<u>63.42</u>	<u>44.95</u>	<u>84.00</u>	<u>62.67</u>	<u>76.77</u>	<u>55.51</u>	<u>37.00</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	75.20	64.33	85.12	70.26	79.34	60.40	54.19
Hydrogen	2.45	4.22	0.35	2.18	1.17	1.53	0.95
Sulfur	2.17	3.90	0.70	2.72	1.57	1.90	3.15
Nitrogen	1.47	1.37	1.21	1.37	1.54	1.78	1.37
Oxygen (by diff.)	5.34	10.35	1.05	4.86	3.04	4.63	2.08
Ash	<u>13.37</u>	<u>15.83</u>	<u>11.57</u>	<u>18.61</u>	<u>13.34</u>	<u>29.76</u>	<u>38.26</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	--	--	--	ND
12	--	3.88	21.30	7.36	0.12	--	--
20	--	17.50	26.90	26.00	3.44	--	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	46.58	15.85	0.45	--
60	--	25.30	11.90	15.00	23.05	0.45	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	3.30	16.00	0.45	--
100	--	2.11	2.68	0.88	8.60	0.45	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.66	10.70	6.79	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.22	7.62	4.82	--
230	--	0.11	0.67	--	2.46	1.90	--
270	--	0.11	0.89	--	2.95	2.26	--
325	--	0.11	0.67	--	2.21	4.07	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>--</u>	<u>7.00</u>	<u>1.36</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table II-7. ANALYSES OF SOLIDS FROM TEST MG-11
(Test Temperature = 1390°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.21	3.30	1.12	0.24	0.41	1.57	2.95
Volatile matter	19.09	34.73	3.44	3.82	5.62	8.09	13.91
Ash	13.28	15.12	11.44	15.87	15.80	16.55	44.28
Fixed carbon	<u>65.42</u>	<u>46.85</u>	<u>84.00</u>	<u>80.07</u>	<u>78.17</u>	<u>73.79</u>	<u>38.86</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	75.05	64.98	85.12	81.08	79.41	76.54	47.47
Hydrogen	2.37	4.38	0.35	0.31	0.70	1.24	0.73
Sulfur	2.33	3.95	0.70	1.15	1.57	1.58	6.28
Nitrogen	1.36	1.51	1.21	1.32	1.43	1.64	1.18
Oxygen (by diff.)	5.31	9.59	1.05	0.23	1.03	2.19	0.00
Ash	<u>13.58</u>	<u>15.59</u>	<u>11.57</u>	<u>15.91</u>	<u>15.86</u>	<u>16.81</u>	<u>44.34</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.30	0.00	0.00	--
12	--	3.88	21.30	35.10	0.00	0.00	--
20	--	17.50	26.90	37.50	0.22	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	22.35	5.64	0.83	--
60	--	25.30	11.90	3.75	23.95	3.31	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	0.42	16.65	9.09	--
100	--	2.11	2.68	0.12	8.92	1.65	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.12	12.50	5.79	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.00	10.50	5.79	--
230	--	0.11	0.67	0.00	3.75	0.83	--
270	--	0.11	0.89	0.00	4.27	1.65	0.00
325	--	0.11	0.67	0.12	3.56	1.65	25.00
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.22</u>	<u>10.04</u>	<u>69.41</u>	<u>75.00</u>
	--	100.00	100.00	100.00	100.00	100.00	100.00

ND = analysis not done

Table II-8. ANALYSES OF SOLIDS FROM TEST MG-12
(Test Temperature = 1252°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.22	3.32	1.12	0.58	0.91	2.14	7.54
Volatile matter	19.34	35.23	3.44	5.20	6.51	12.41	31.28
Ash	12.78	14.11	11.44	16.33	14.54	18.97	42.96
Fixed carbon	<u>65.66</u>	<u>47.34</u>	<u>84.00</u>	<u>77.89</u>	<u>78.04</u>	<u>66.48</u>	<u>18.22</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	75.28	65.43	85.12	80.60	80.06	74.44	53.54
Hydrogen	2.39	4.43	0.35	0.39	0.87	1.35	NA
Sulfur	2.26	3.81	0.70	1.27	1.64	1.49	NA
Nitrogen	1.25	1.28	1.21	1.29	1.44	1.41	NA
Oxygen (by diff.)	5.75	10.49	1.05	0.02	1.32	1.93	NA
Ash	<u>13.07</u>	<u>14.56</u>	<u>11.57</u>	<u>16.43</u>	<u>14.67</u>	<u>19.38</u>	<u>46.46</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.00	0.00	0.00	ND
12	--	3.88	21.30	15.70	0.00	0.00	--
20	--	17.50	26.90	43.40	0.19	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	31.60	2.64	0.00	--
60	--	25.30	11.90	6.82	19.20	1.59	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	1.14	17.50	1.59	--
100	--	2.11	2.68	0.45	9.62	0.00	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.45	14.20	1.59	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.23	12.10	1.59	--
230	--	0.11	0.67	0.00	4.42	0.00	--
270	--	0.11	0.89	0.00	5.19	1.59	--
325	--	0.11	0.67	0.00	3.65	0.00	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.21</u>	<u>11.29</u>	<u>92.05</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND - analysis not done

Table II-9. ANALYSES OF SOLIDS FROM TEST MG-14
(Test Temperature = 1084°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.36	3.60	1.12	0.91	0.86	2.37	7.79
Volatile matter	19.62	35.80	3.44	6.34	7.42	10.30	26.27
Ash	13.48	15.52	11.44	16.99	13.89	18.22	46.60
Fixed carbon	<u>64.54</u>	<u>45.08</u>	<u>84.00</u>	<u>75.76</u>	<u>77.83</u>	<u>69.11</u>	<u>19.34</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	74.42	63.72	85.12	77.31	79.13	73.53	ND
Hydrogen	2.34	4.33	0.35	0.66	1.05	1.19	ND
Sulfur	2.25	3.80	0.70	1.45	1.74	1.42	ND
Nitrogen	1.17	1.13	1.21	1.19	1.33	1.16	ND
Oxygen (by diff.)	6.01	10.97	1.05	2.24	2.74	4.04	ND
Ash	<u>13.81</u>	<u>16.05</u>	<u>11.57</u>	<u>17.15</u>	<u>14.01</u>	<u>18.66</u>	<u>50.54</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.98	0.00	0.00	ND
12	--	3.88	21.30	34.60	0.00	0.00	--
20	--	17.50	26.90	34.80	0.07	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	20.60	1.85	0.30	--
60	--	25.30	11.90	5.39	18.05	1.56	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	1.23	19.10	1.56	--
100	--	2.11	2.68	0.49	10.75	0.97	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.74	14.85	2.32	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.25	11.80	3.00	--
230	--	0.11	0.67	0.25	4.20	0.97	--
270	--	0.11	0.89	0.25	4.72	1.94	--
325	--	0.11	0.67	0.25	3.53	1.94	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.17</u>	<u>11.15</u>	<u>85.44</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND - analysis not done

Table II-10. ANALYSES OF SOLIDS FROM TEST MG-15
(Test Temperature = 1034°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	1.98	2.84	1.12	0.46	0.70	1.59	4.54
Volatile matter	17.85	32.26	3.44	5.31	7.98	11.18	26.68
Ash	12.27	13.09	11.44	14.71	13.17	19.08	64.57
Fixed carbon	<u>67.90</u>	<u>51.81</u>	<u>84.00</u>	<u>79.52</u>	<u>78.15</u>	<u>68.15</u>	<u>4.21</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	76.56	67.99	85.12	80.28	79.91	73.09	32.36
Hydrogen	2.38	4.40	0.35	0.65	1.21	1.24	ND
Sulfur	1.99	3.28	0.70	1.32	1.68	1.21	ND
Nitrogen	1.34	1.46	1.21	1.34	1.52	1.37	ND
Oxygen (by diff.)	5.21	9.41	1.05	1.63	2.42	3.70	ND
Ash	<u>12.52</u>	<u>13.46</u>	<u>11.57</u>	<u>14.78</u>	<u>13.26</u>	<u>19.39</u>	<u>67.64</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.00	0.00	0.00	ND
12	--	3.88	21.30	18.90	0.00	0.00	--
20	--	17.50	26.90	50.76	0.14	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	23.00	2.63	0.00	--
60	--	25.30	11.90	4.61	14.42	0.88	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	1.03	15.62	0.88	--
100	--	2.11	2.68	0.43	10.21	0.88	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.51	16.32	0.88	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.26	13.42	0.88	--
230	--	0.11	0.67	0.08	4.85	0.00	--
270	--	0.11	0.89	0.18	5.40	0.88	--
325	--	0.11	0.67	0.08	3.88	0.88	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.16</u>	<u>13.11</u>	<u>93.84</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND - analysis not done

Table II-11. ANALYSES OF SOLIDS FROM TEST MG-16
(Test Temperature = 1183°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	----- wt% -----						
Moisture	2.44	3.36	1.12	0.33	0.58	1.36	2.48
Volatile matter	18.28	33.12	3.44	4.76	6.06	10.55	23.17
Ash	14.58	15.60	11.44	18.76	13.47	14.99	74.35
Fixed carbon	<u>64.70</u>	<u>47.92</u>	<u>84.00</u>	<u>76.15</u>	<u>79.89</u>	<u>73.10</u>	<u>0.00</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	----- dry wt% -----						
Carbon	74.49	63.86	85.12	78.36	82.12	77.27	23.74
Hydrogen	2.17	3.99	0.35	0.36	1.05	1.39	ND
Sulfur	2.15	3.60	0.70	1.22	1.68	1.39	ND
Nitrogen	1.27	1.33	1.21	1.15	1.53	1.63	ND
Oxygen (by diff.)	6.06	11.07	1.05	1.85	0.47	3.29	ND
Ash	<u>13.86</u>	<u>16.15</u>	<u>11.57</u>	<u>17.06</u>	<u>13.15</u>	<u>15.03</u>	<u>76.26</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	----- wt% retained on screen -----						
6	0.00	0.00	0.00	0.00	0.00	ND	ND
12	11.30	3.88	21.30	20.80	0.00	--	--
20	26.90	17.50	26.90	59.10	0.25	--	--
30	--	--	--	--	--	--	--
40	36.70	40.50	20.80	17.60	8.17	--	--
60	17.60	25.30	11.90	1.73	17.10	--	--
70	--	--	--	--	--	--	--
80	4.64	8.87	6.26	0.16	7.18	--	--
100	1.19	2.11	2.68	0.16	3.71	--	--
120	--	--	--	--	--	--	--
140	0.83	1.00	3.58	0.16	7.92	--	--
170	--	--	--	--	--	--	--
200	0.24	0.33	2.46	0.16	8.17	--	--
230	0.12	0.11	0.67	0.00	4.46	--	--
270	0.12	0.11	0.89	0.00	5.69	--	--
325	0.12	0.11	0.67	0.00	4.70	--	--
PAN	<u>0.24</u>	<u>0.18</u>	<u>1.89</u>	<u>0.13</u>	<u>32.65</u>	--	--
	100.00	100.00	100.00	100.00	100.00	--	--

ND = analysis not done

Table II-12. ANALYSES OF SOLIDS FROM TEST MG-18
(Test Temperature = 1178°F)

	<u>Feed</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u>	<u>1st</u>	<u>1st</u>	<u>Carry</u>
	<u>Mixture</u>			<u>Bed</u>	<u>Cyclone</u>	<u>Cyclone</u>	<u>Over</u>
				<u>Char</u>	<u>Char</u>	<u>Char</u>	<u>Char</u>
<u>Proximate Analysis</u>							
	----- wt% -----						
Moisture	3.59	6.53	0.65	0.21	0.77	1.29	0.00
Volatile matter	17.36	31.05	3.67	5.50	7.25	11.34	43.03
Ash	11.83	11.44	12.22	15.71	15.64	16.22	17.58
Fixed carbon	<u>67.22</u>	<u>50.98</u>	<u>83.46</u>	<u>78.58</u>	<u>76.34</u>	<u>71.15</u>	<u>39.39</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	----- dry wt% -----						
Carbon	77.07	70.27	83.87	80.44	78.21	74.36	70.81
Hydrogen	2.26	4.08	0.44	0.49	1.09	1.85	1.20
Sulfur	1.98	3.21	0.75	1.15	1.92	2.19	1.53
Nitrogen	1.36	1.49	1.23	1.28	1.44	1.66	1.28
Oxygen (by diff.)	5.06	8.71	1.41	0.90	1.58	3.51	7.60
Ash	<u>12.27</u>	<u>12.24</u>	<u>12.30</u>	<u>15.74</u>	<u>15.76</u>	<u>16.43</u>	<u>17.58</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	----- wt% retained on screen -----						
6	0.00	0.00	0.00	0.00	0.00	0.00	0.00
12	14.90	3.88	19.30	8.32	0.14	0.00	0.00
20	30.30	17.50	31.40	35.90	2.43	0.65	0.00
30	--	--	--	--	--	--	--
40	33.20	40.50	37.00	50.40	23.20	4.58	0.00
60	14.70	25.30	11.90	4.85	27.20	11.10	0.00
70	--	--	--	--	--	--	--
80	4.27	8.87	0.17	0.17	5.00	3.92	0.00
100	1.20	2.11	0.00	0.00	2.57	1.31	0.00
120	--	--	--	--	--	--	--
140	0.68	1.00	0.00	0.17	4.46	3.92	0.00
170	--	--	--	--	--	--	--
200	0.34	0.33	0.00	0.00	5.68	3.27	0.00
230	0.17	0.11	0.17	0.00	2.84	0.65	0.00
270	0.00	0.11	0.00	0.00	3.78	1.31	0.00
325	0.00	0.11	0.00	0.00	3.51	1.96	0.00
PAN	<u>0.34</u>	<u>0.18</u>	<u>0.06</u>	<u>0.19</u>	<u>19.19</u>	<u>67.33</u>	<u>100.00</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00

ND = analysis not done

Table II-13. ANALYSES OF SOLIDS FROM TEST MG-19
(Test Temperature = 1102°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	4.02	6.92	1.12	0.57	0.92	ND	3.93
Volatile matter	18.29	33.14	3.44	5.99	12.63	--	31.43
Ash	12.17	12.90	11.44	15.00	16.53	--	61.07
Fixed carbon	<u>65.52</u>	<u>47.04</u>	<u>84.00</u>	<u>78.44</u>	<u>69.92</u>	--	<u>3.57</u>
	100.00	100.00	100.00	100.00	100.00	--	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	77.18	69.24	85.12	80.09	73.27	ND	36.43
Hydrogen	2.43	4.51	0.35	0.81	1.97	--	ND
Sulfur	2.04	3.38	0.70	1.43	2.68	--	ND
Nitrogen	1.39	1.57	1.21	1.41	1.51	--	ND
Oxygen (by diff.)	4.28	7.51	1.05	1.17	3.89	--	ND
Ash	<u>12.68</u>	<u>13.79</u>	<u>11.57</u>	<u>15.09</u>	<u>16.68</u>	--	<u>63.57</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.00	0.00	ND	ND
12	11.30	3.88	21.30	20.80	0.00	--	--
20	26.90	17.50	26.90	59.10	0.25	--	--
30	--	--	--	--	--	--	--
40	36.70	40.50	20.80	17.60	8.17	--	--
60	17.60	25.30	11.90	1.73	17.10	--	--
70	--	--	--	--	--	--	--
80	4.64	8.87	6.26	0.16	7.18	--	--
100	1.19	2.11	2.68	0.16	3.71	--	--
120	--	--	--	--	--	--	--
140	0.83	1.00	3.58	0.16	7.92	--	--
170	--	--	--	--	--	--	--
200	0.24	0.33	2.46	0.16	8.17	--	--
230	0.12	0.11	0.67	0.00	4.46	--	--
270	0.12	0.11	0.89	0.00	5.69	--	--
325	0.12	0.11	0.67	0.00	4.70	--	--
PAN	<u>0.24</u>	<u>0.18</u>	<u>1.89</u>	<u>0.13</u>	<u>32.65</u>	--	--
	100.00	100.00	100.00	100.00	100.00	--	--

ND - analysis not done

Table II-14. ANALYSES OF SOLIDS FROM TEST MG-21
(Test Temperature = 1109°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	3.46	5.79	1.12	0.38	0.74	1.23	7.46
Volatile matter	17.34	31.24	3.44	6.03	13.15	13.59	25.42
Ash	11.39	11.34	11.44	14.40	13.98	15.28	51.31
Fixed carbon	<u>67.81</u>	<u>51.63</u>	<u>84.00</u>	<u>79.19</u>	<u>72.13</u>	<u>69.90</u>	<u>15.81</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	77.70	70.27	85.12	80.09	74.75	73.93	44.55
Hydrogen	2.27	4.19	0.35	0.74	2.21	2.14	ND
Sulfur	1.89	3.07	0.70	1.39	2.49	2.07	ND
Nitrogen	1.51	1.81	1.21	1.50	1.79	1.88	ND
Oxygen (by diff.)	4.83	8.64	1.05	1.82	4.68	4.51	ND
Ash	<u>11.80</u>	<u>12.02</u>	<u>11.57</u>	<u>14.46</u>	<u>14.08</u>	<u>15.47</u>	<u>55.45</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.00	0.00	0.00	ND
12	16.30	3.88	19.30	18.20	0.00	0.00	--
20	29.80	17.50	31.40	54.20	0.00	0.00	--
30	--	--	--	--	--	--	--
40	34.00	40.50	37.00	23.60	5.36	0.57	--
60	14.00	25.30	11.90	2.40	11.10	2.27	--
70	--	--	--	--	--	--	--
80	3.51	8.87	0.17	0.40	5.16	1.70	--
100	0.84	2.11	0.00	0.20	3.37	1.14	--
120	--	--	--	--	--	--	--
140	0.70	1.00	0.00	0.20	7.94	2.27	--
170	--	--	--	--	--	--	--
200	0.28	0.33	0.00	0.20	11.30	3.41	--
230	0.14	0.11	0.17	0.20	5.16	2.27	--
270	0.14	0.11	0.00	0.20	7.74	4.55	--
325	0.14	0.11	0.00	0.00	6.75	2.27	--
PAN	<u>0.15</u>	<u>0.18</u>	<u>0.16</u>	<u>0.20</u>	<u>36.12</u>	<u>79.55</u>	--
	100.00	100.00	100.00	100.00	100.00	100.00	--

ND - analysis not done

Table II-15. ANALYSES OF SOLIDS FROM TEST MG-22
(Test Temperature = 1147°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	----- wt% -----						
Moisture	3.49	5.86	1.12	0.25	0.54	0.69	1.76
Volatile matter	17.88	32.31	3.44	5.88	12.17	12.52	30.88
Ash	11.89	12.33	11.44	15.56	15.56	14.61	64.92
Fixed carbon	<u>66.74</u>	<u>49.50</u>	<u>84.00</u>	<u>78.31</u>	<u>71.73</u>	<u>72.18</u>	<u>2.44</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	----- dry wt% -----						
Carbon	76.63	68.14	85.12	78.90	73.66	74.54	33.92
Hydrogen	2.26	4.16	0.35	0.73	1.89	2.12	NA
Sulfur	2.00	3.30	0.70	1.45	2.51	2.49	NA
Nitrogen	1.38	1.55	1.21	1.39	1.65	1.70	NA
Oxygen (by diff.)	5.41	9.79	1.05	1.93	4.66	4.44	NA
Ash	<u>12.32</u>	<u>13.06</u>	<u>11.57</u>	<u>15.60</u>	<u>15.63</u>	<u>14.71</u>	<u>66.08</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	----- wt% retained on screen -----						
6	0.00	0.00	0.00	0.14	0.00	0.00	ND
12	15.05	3.88	19.30	16.13	0.00	0.00	--
20	29.70	17.50	31.40	59.97	0.10	0.00	--
30	--	--	--	--	--	--	--
40	34.05	40.50	37.00	20.23	7.39	1.87	--
60	14.80	25.30	11.90	1.79	17.00	7.46	--
70	--	--	--	--	--	--	--
80	3.98	8.87	0.17	0.38	7.39	4.10	--
100	1.06	2.11	0.00	0.19	4.43	3.36	--
120	--	--	--	--	--	--	--
140	0.71	1.00	0.00	0.26	9.15	4.85	--
170	--	--	--	--	--	--	--
200	0.30	0.33	0.00	0.32	10.90	11.90	--
230	0.00	0.11	0.17	0.13	5.17	1.49	--
270	0.12	0.11	0.00	0.20	6.75	7.84	--
325	0.00	0.11	0.00	0.07	6.19	2.99	--
PAN	<u>0.23</u>	<u>0.18</u>	<u>0.16</u>	<u>0.19</u>	<u>25.53</u>	<u>54.14</u>	--
	100.00	100.00	100.00	100.00	100.00	100.00	--

ND - analysis not done

Table II-16. ANALYSES OF SOLIDS FROM TEST MG-25
(Test Temperature = 1134°F)

	Feed			Fluid	1st	1st	Carry
	Mixture	Coal	Diluent	Bed	Cyclone	Cyclone	Over
				Char	Char	Char	Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.86	5.34	0.38	0.27	0.38	0.34	0.67
Volatile matter	16.27	26.51	6.03	7.44	15.33	14.80	22.72
Ash	12.92	11.44	14.40	16.63	17.34	16.36	22.29
Fixed carbon	<u>67.95</u>	<u>56.71</u>	<u>79.19</u>	<u>75.66</u>	<u>66.95</u>	<u>68.50</u>	<u>54.32</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	76.21	72.33	80.09	76.56	69.67	70.89	77.56
Hydrogen	2.16	3.58	0.74	1.05	2.38	2.35	ND
Sulfur	2.09	2.79	1.39	1.84	2.99	3.04	ND
Nitrogen	1.38	1.26	1.50	1.44	1.67	1.64	ND
Oxygen (by diff.)	4.86	7.90	1.82	2.43	5.88	5.66	ND
Ash	<u>13.30</u>	<u>12.14</u>	<u>14.46</u>	<u>16.68</u>	<u>17.41</u>	<u>16.42</u>	<u>22.44</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	3.88	19.30	--	--	--	--
20	--	17.50	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	37.00	--	--	--	--
60	--	25.30	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	0.17	--	--	--	--
100	--	2.11	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	0.00	--	--	--	--
230	--	0.11	0.17	--	--	--	--
270	--	0.11	0.00	--	--	--	--
325	--	0.11	0.00	--	--	--	--
PAN	--	<u>0.18</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table II-17. ANALYSES OF SOLIDS FROM TEST MG-28
(Test Temperature = 1149°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	0.80	0.16	1.12	0.17	0.19	0.02	1.58
Volatile matter	9.23	20.81	3.44	3.94	7.92	17.37	13.46
Ash	11.55	11.77	11.44	12.77	16.10	31.56	8.31
Fixed carbon	<u>78.42</u>	<u>67.26</u>	<u>84.00</u>	<u>83.12</u>	<u>75.79</u>	<u>51.05</u>	<u>76.65</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	83.02	78.82	85.12	83.51	77.05	57.54	91.56
Hydrogen	1.49	3.77	0.35	0.64	1.83	2.24	ND
Sulfur	0.98	1.54	0.70	0.95	1.52	0.18	ND
Nitrogen	1.29	1.45	1.21	1.36	1.34	1.40	ND
Oxygen (by diff.)	1.58	2.64	1.05	0.75	2.13	7.07	ND
Ash	<u>11.64</u>	<u>11.78</u>	<u>11.57</u>	<u>12.79</u>	<u>16.13</u>	<u>31.57</u>	<u>8.44</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	14,535	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	ND	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	0.00	19.30	--	--	--	--
20	--	0.32	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	9.83	37.00	--	--	--	--
60	--	14.40	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	12.10	0.17	--	--	--	--
100	--	7.09	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	13.60	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	7.73	0.00	--	--	--	--
230	--	1.29	0.17	--	--	--	--
270	--	3.55	0.00	--	--	--	--
325	--	3.06	0.00	--	--	--	--
PAN	--	<u>27.03</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table II-18. ANALYSES OF SOLIDS FROM TEST MG-30
(Test Temperature = 1050°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	0.88	0.40	1.12	0.23	0.53	0.59	0.59
Volatile matter	9.88	22.76	3.44	4.55	9.04	21.84	19.77
Ash	11.23	9.85	11.44	12.21	14.70	43.20	4.62
Fixed carbon	<u>78.01</u>	<u>66.99</u>	<u>84.00</u>	<u>83.01</u>	<u>75.73</u>	<u>34.37</u>	<u>75.02</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	82.15	76.21	85.12	82.71	77.40	44.02	95.47
Hydrogen	1.51	3.83	0.35	0.82	1.78	2.23	ND
Sulfur	0.96	1.48	0.70	0.94	1.40	1.01	ND
Nitrogen	1.34	1.60	1.21	1.39	1.35	0.98	ND
Oxygen (by diff.)	3.03	6.99	1.05	2.17	3.49	10.79	ND
Ash	<u>11.01</u>	<u>9.89</u>	<u>11.57</u>	<u>11.97</u>	<u>14.58</u>	<u>40.97</u>	<u>4.53</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	14,535	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	ND	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	0.00	19.30	--	--	--	--
20	--	0.32	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	9.83	37.00	--	--	--	--
60	--	14.40	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	12.10	0.17	--	--	--	--
100	--	7.09	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	13.60	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	7.73	0.00	--	--	--	--
230	--	1.29	0.17	--	--	--	--
270	--	3.55	0.00	--	--	--	--
325	--	3.06	0.00	--	--	--	--
PAN	--	<u>27.03</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table II-19, Part 1. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	<u>SD-6</u>	<u>MG-3</u>	<u>MG-5</u>	<u>MG-11</u>
Test Temperature, °F	1300	1325	1100	1390
Elemental Analysis of				
<u>Oils and Tars^a</u>	----- dry wt% -----			
Ash ^b	0.57	0.09	0.17	0.53
Carbon	78.71	80.98	78.18	82.29
Hydrogen	6.87	6.17	7.32	6.08
Nitrogen	ND	1.32	0.96	1.26
Sulfur	2.28	2.21	1.99	3.21
Oxygen (by diff.)	<u>ND</u>	<u>9.23</u>	<u>11.38</u>	<u>6.63</u>
Total	ND	100.00	100.00	100.00
H/C Atomic Ratio	1.04	0.91	1.12	0.88
Simulate Distillation				
by Gas Chromatography ^c				
<u>Cumulative Wt% Recovered</u>	----- Boiling Point, °F -----			
5	435	365	367	340
10	498	416	440	390
15	540	462	498	437
20	575	506	550	482
30	637	590	645	568
40	693	672	735	652
50	747	758	826	739
60	802	856	926	831
70	864	995	1057	939
EP (end point) ^d	1093	1068	1068	1093
% Residue at EP	13.7	27.6	29.4	20.3

- a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.
- b Corrected for THF-soluble FeCl₃ which was determined to be a contaminant from corrosion of stainless steel exposed to the hot methylene chloride quench solvent.
- c Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.
- d Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-19, Part 2. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	MG-12	MG-14	MG-15	MG-16
Test Temperature, °F	1252	1084	1034	1183
Elemental Analysis of Oils and Tars ^a	----- dry wt% -----			
Ash ^b	0.36	0.25	0.65	0.42
Carbon	75.74	77.97	73.86	74.24
Hydrogen	6.21	6.76	6.85	6.74
Nitrogen	1.27	0.98	0.79	0.78
Sulfur	2.03	1.83	1.57	1.60
Oxygen (by diff.)	<u>14.39</u>	<u>12.21</u>	<u>16.28</u>	<u>16.22</u>
Total	100.00	100.00	100.00	100.00
H/C Atomic Ratio	0.98	1.03	1.11	1.08
Simulate Distillation by Gas Chromatography ^c	----- Boiling Point, °F -----			
<u>Cumulative Wt% Recovered</u>				
5	353	388	351	343
10	433	487	408	404
15	506	576	466	459
20	573	661	525	510
30	705	840	652	610
40	844	--	810	713
50	1023	--	--	833
60	--	--	--	--
70	--	--	--	--
EP (end point) ^d	1093	1093	1093	1093
% Residue at EP	47.6	60.6	53.4	41.4

a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

b Corrected for THF-soluble FeCl₃ which was determined to be a contaminant from corrosion of stainless steel exposed to the hot methylene chloride quench solvent.

c Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

d Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-19, Part 3. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	MG-18	MG-19	MG-21	MG-22
Test Temperature, °F	1178	1102	1109	1147
Elemental Analysis of				
<u>Oils and Tars^a</u>				
	----- dry wt% -----			
Ash ^b	0.29	0.00	0.47	0.00
Carbon	76.57	77.98	77.57	77.56
Hydrogen	6.71	7.06	6.88	6.90
Nitrogen	1.00	0.92	1.00	0.85
Sulfur	1.74	1.93	1.93	1.84
Oxygen (by diff.)	<u>13.68</u>	<u>12.11</u>	<u>12.15</u>	<u>12.84</u>
Total	100.00	100.00	100.00	100.00
H/C Atomic Ratio	1.04	1.08	1.06	1.06
Simulate Distillation				
by Gas Chromatography ^c				
<u>Cumulative Wt% Recovered</u>	<u>----- Boiling Point, °F -----</u>			
5	358	351	359	359
10	418	438	430	425
15	475	509	492	484
20	530	572	550	541
30	644	690	661	650
40	771	810	776	765
50	960	954	912	909
60	--	--	--	--
70	--	--	--	--
EP (end point) ^d	1068	1068	1068	1068
% Residue at EP	48.3	44.9	43.0	44.7

- a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.
- b Corrected for THF-soluble FeCl₃ which was determined to be a contaminant from corrosion of stainless steel exposed to the hot methylene chloride quench solvent.
- c Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.
- d Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-19, Part 4. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	MG-25	MG-28	MG-30
Test Temperature, °F	1134	1149	1050
Elemental Analysis of			
<u>Oils and Tars^a</u>	----- dry wt% -----		
Ash	0.17	1.14	0.77
Carbon	78.45	79.60	82.04
Hydrogen	7.09	7.09	7.34
Nitrogen	0.85	0.86	0.82
Sulfur	2.18	0.83	0.74
Oxygen (by diff.)	<u>11.26</u>	<u>10.48</u>	<u>8.29</u>
Total	100.00	100.00	100.00
H/C Atomic Ratio	1.08	1.06	1.07
Simulate Distillation			
by Gas Chromatography^b			
<u>Cumulative Wt% Recovered</u>	----- Boiling Point, °F -----		
5	374	376	313
10	449	465	428
15	511	542	516
20	567	615	593
30	672	754	730
40	776	904	861
50	897	1068	995
60	--	--	--
70	--	--	--
EP (end point) ^c	1068	1068	1068
% Residue at EP	41.6	51.8	45.0

- a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.
- b Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.
- c Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-20, Part 1. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	<u>SD-6</u>	<u>MG-3</u>	<u>MG-5</u>	<u>MG-11</u>
Test Temperature, °F	1300	1325	1100	1390
<u>Component</u>	----- Wt% of total oils/tars ^a -----			
Benzene	1.7	2.2	0.9	8.7
Toluene	2.0	0.2	1.6	5.5
Xylenes	1.8	1.1	1.4	2.8
Ethylbenzene	0.2	0.1	0.3	2.2
Indene	1.4	1.3	0.2	2.0
Styrene	0.8	0.6	0.3	1.2
Other Light Oils	<u>2.2</u>	<u>4.8</u>	<u>1.3</u>	<u>1.4</u>
Total Light Oil ^b	10.1	10.2	6.0	23.8
Phenol	4.4	2.3	2.0	2.8
Cresols	6.4	3.1	2.8	2.0
Xylenols	3.1	1.7	0.8	0.6
Naphthalene	1.2	1.2	0.3	2.0
Other Middle Oils	<u>2.1</u>	<u>15.7</u>	<u>13.3</u>	<u>13.6</u>
Total Middle Oil ^c	17.2	24.0	19.2	21.0
Heavy Oil ^d	26.5	17.9	17.4	15.3
Pitch ^e	<u>46.2</u>	<u>47.9</u>	<u>57.4</u>	<u>39.9</u>
Total Oils and Tars	100.0	100.0	100.0	100.0

^a Includes light oils that are not included in the oils and tars of Table II-19.

^b Atmospheric boiling point <360°F; estimated from simulated distillation data.

^c Atmospheric boiling point 360° to 590°F.

^d Atmospheric boiling point 590° to 750°F.

^e Atmospheric boiling point >750°F.

Table II-20, Part 2. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	MG-12	MG-14	MG-15	MG-16
Test Temperature, °F	1252	1084	1034	1183
<u>Component</u>	----- Wt% of total oils/tars ^a -----			
Benzene	1.2	0.9	0.5	0.6
Toluene	1.3	1.5	0.8	0.9
Xylenes	0.8	0.5	0.5	0.6
Ethylbenzene	0.6	0.1	0.1	0.1
Indene	0.4	0.2	0.1	0.2
Styrene	0.3	0.2	0.2	0.1
Other Light Oils	<u>4.3</u>	<u>6.0</u>	<u>5.4</u>	<u>6.0</u>
Total Light Oil ^b	8.9	9.4	7.6	8.5
Phenol	1.0	1.2	0.3	0.9
Cresols	1.4	1.7	1.7	2.2
Xylenols	0.6	1.4	1.3	2.1
Naphthalene	0.5	0.1	0.1	0.1
Other middle oils	<u>11.8</u>	<u>6.9</u>	<u>15.7</u>	<u>15.9</u>
Total Middle Oil ^c	15.3	11.3	19.1	21.2
Heavy Oil ^d	11.7	8.8	11.1	15.0
Pitch ^e	<u>64.1</u>	<u>70.5</u>	<u>62.2</u>	<u>55.3</u>
	100.0	100.0	100.0	100.0

a Includes light oils that are not included in the oils and tars of Table II-19.

b Atmospheric boiling point <360°F; estimated from simulated distillation data.

c Atmospheric boiling point 360° to 590°F.

d Atmospheric boiling point 590° to 750°F.

e Atmospheric boiling point >750°F.

Table II-20, Part 3. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	<u>MG-18</u>	<u>MG-19</u>	<u>MG-21</u>	<u>MG-22</u>
Test Temperature, °F	1178	1102	1109	1147
<u>Component</u>				
	----- Wt% of total oils/tars ^a -----			
Benzene	0.7	0.1	0.5	0.8
Toluene	0.8	0.3	0.4	0.7
Xylenes	0.5	0.2	0.3	0.4
Ethylbenzene	0.1	0.04	0.1	0.1
Indene	0.3	0.1	0.1	0.2
Styrene	0.2	0.1	0.1	0.1
Other Light Oils	<u>4.8</u>	<u>5.4</u>	<u>4.8</u>	<u>4.7</u>
Total Light Oil ^b	7.4	6.2	6.3	7.0
Phenol	0.8	0.6	0.6	0.8
Cresols	2.1	1.6	1.6	2.1
Xylenols	1.9	1.6	1.9	2.3
Naphthalene	0.5	0.3	0.1	0.4
Other Middle Oils	<u>14.4</u>	<u>11.8</u>	<u>14.1</u>	<u>13.4</u>
Total Middle Oil ^c	19.7	15.9	18.3	19.0
Heavy Oil ^d	12.9	13.5	14.1	14.0
Pitch ^e	<u>60.1</u>	<u>64.4</u>	<u>61.3</u>	<u>60.0</u>
Total Oils and Tars	100.0	100.0	100.0	100.0

^a Includes light oils that are not included in the oils and tars of Table II-19.

^b Atmospheric boiling point <360°F; estimated from simulated distillation data.

^c Atmospheric boiling point 360° to 590°F.

^d Atmospheric boiling point 590° to 750°F.

^e Atmospheric boiling point >750°F.

Table II-20, Part 4. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	<u>MG-25</u>	<u>MG-28</u>	<u>MG-30</u>
Test Temperature, °F	1134	1149	1050
<u>Component</u>	----- Wt% of total oils/tars ^a -----		
Benzene	0.3	0.5	0.3
Toluene	0.5	0.7	0.6
Xylenes	0.4	0.5	0.6
Ethylbenzene	0.1	0.1	0.1
Indene	0.1	0.2	0.1
Styrene	0.1	0.05	0.1
Other Light Oils	<u>4.2</u>	<u>7.3</u>	<u>8.7</u>
Total Light Oil ^b	5.7	9.3	10.5
Phenol	0.8	0.4	0.4
Cresols	1.9	1.0	1.0
Xylenols	3.8	1.6	1.3
Naphthalene	0.1	0.6	0.1
Other Middle Oils	<u>11.0</u>	<u>9.7</u>	<u>9.7</u>
Total Middle Oil ^c	17.6	13.3	12.5
Heavy Oil ^d	15.2	10.8	11.2
Pitch ^e	<u>61.5</u>	<u>66.6</u>	<u>65.8</u>
Total Oils and Tars	100.0	100.0	100.0

a Includes light oils that are not included in the oils and tars of Table II-19.

b Atmospheric boiling point <360°F; estimated from simulated distillation data.

c Atmospheric boiling point 360° to 590°F.

d Atmospheric boiling point 590° to 750°F.

e Atmospheric boiling point >750°F.

Table II-21, Part 1. GAS COMPOSITIONS

Test Number	<u>SD-6</u>	<u>MG-3</u>	<u>MG-5</u>	<u>MG-11</u>
Test Temperature, °F	1300	1325	1100	1390
<u>Component</u>	----- Mol % in gas, nitrogen-free -----			
H ₂	52.1	30.3	17.8	44.3
CO	15.3	18.0	15.1	17.0
CO ₂	8.1	8.6	16.0	9.1
CH ₄	19.3	29.9	31.4	18.8
C ₂ H ₄	1.7	5.9	7.5	6.0
C ₂ H ₆	2.7	3.0	5.1	1.1
C ₃ H ₆	0.6	3.6	5.0	1.2
C ₃ H ₈	0.2	0.7	2.1	0.1
H ₂ S	<u>NA</u>	<u>NA</u>	<u>NA</u>	<u>2.4</u>
Total	100.0	100.0	100.0	100.0
Molecular Weight	13.6	18.7	23.4	16.0
Higher Heating Value, Btu/scf	508	712	810	546

Table II-21, Part 2. GAS COMPOSITIONS

Test Number	<u>MG-12</u>	<u>MG-14</u>	<u>MG-15</u>	<u>MG-16</u>
Test Temperature, °F	1252	1084	1034	1183
<u>Component</u>	----- Mol % in gas, nitrogen-free -----			
H ₂	37.5	28.4	29.5	33.6
CO	16.1	13.0	10.6	12.7
CO ₂	8.7	10.3	12.9	10.1
CH ₄	23.3	28.1	28.1	28.1
C ₂ H ₄	6.3	6.5	5.8	4.7
C ₂ H ₆	2.5	4.3	4.7	3.7
C ₃ H ₆	2.1	2.7	2.5	2.5
C ₃ H ₈	0.2	1.0	0.6	1.5
H ₂ S	<u>3.3</u>	<u>5.7</u>	<u>5.3</u>	<u>3.1</u>
Total	100.0	100.0	100.0	100.0
Molecular Weight	17.5	19.9	19.9	18.4
Higher Heating Value, Btu/scf	626	719	694	689

Table II-21, Part 3. GAS COMPOSITIONS

Test Number	<u>MG-18</u>	<u>MG-19</u>	<u>MG-21</u>	<u>MG-22</u>
Test Temperature, °F	1178	1102	1109	1147
<u>Component</u>	----- Mol % in gas, nitrogen-free -----			
H ₂	40.4	17.1	18.6	23.1
CO	11.5	13.4	13.6	13.1
CO ₂	9.5	9.5	10.0	7.5
CH ₄	26.0	40.2	38.3	37.1
C ₂ H ₄	4.8	5.7	5.9	5.7
C ₂ H ₆	3.2	7.4	6.7	5.9
C ₃ H ₆	2.2	3.0	3.0	3.8
C ₃ H ₈	0.5	1.3	1.4	1.3
H ₂ S	<u>1.9</u>	<u>2.4</u>	<u>2.5</u>	<u>2.5</u>
Total	100.0	100.0	100.0	100.0
Molecular Weight	16.5	21.2	21.1	19.8
Higher Heating Value, Btu/scf	640	841	823	824

Table II-21, Part 4. GAS COMPOSITIONS

Test Number	<u>MG-25</u>	<u>MG-28</u>	<u>MG-30</u>
Test Temperature, °F	1134	1149	1050
<u>Component</u>	----- Mol % in gas, nitrogen-free -----		
H ₂	17.4	27.1	18.9
CO	15.1	3.8	1.9
CO ₂	11.3	8.2	8.9
CH ₄	34.9	45.2	51.3
C ₂ H ₄	4.7	5.3	5.9
C ₂ H ₆	5.4	5.4	6.6
C ₃ H ₆	3.0	2.6	2.9
C ₃ H ₈	1.1	1.0	2.0
H ₂ S	<u>7.1</u>	<u>1.4</u>	<u>1.6</u>
Total	100.0	100.0	100.0
Molecular Weight	22.2	17.6	19.3
Higher Heating Value, Btu/scf	769	830	922

Table II-22. TEST SD-6 (1300°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	24.17	0.86	1.93	0.45	0.72	4.66	32.79
Steam + Moisture	--	<u>1.52</u>	<u>12.08</u>	--	--	--	<u>13.60</u>
Total	24.17	2.38	14.01	0.45	0.72	4.66	46.39
<u>Output</u>							
Char Mixture	21.13	0.12	0.26	0.37	0.39	4.55	26.82
Product Gas	1.32	0.46	1.02	--	NA	--	2.80
Oils/Tars	2.19	0.17	0.20	0.03	0.03	0.00	2.62
Aqueous Condensate	--	<u>0.87</u>	<u>6.87</u>	<u>0.00</u>	<u>0.00</u>	--	<u>7.74</u>
Total	24.64	1.62	8.35	0.40	0.42	4.55	39.98
Out/In	1.02	0.68	0.60	0.89	0.59	0.98	0.86
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	24.17	0.86	1.93	0.45	0.72	4.66	32.79
<u>Output</u>							
Char Mixture	21.64	0.13	0.26	0.38	0.40	4.66	27.47
Product Gas	1.31	0.46	1.03	--	0.29	--	3.09
Oils/Tars	2.19	0.17	0.20	0.02	0.04	0.00	2.62
Aqueous Condensate	--	<u>-0.05</u>	<u>-0.39</u>	<u>0.05</u>	<u>0.00</u>	--	<u>-0.39</u>
Total	25.14	0.71	1.10	0.45	0.73	4.66	32.79
Out/In	1.04	0.83	0.57	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	66.7	59.8
Gas	19.4	23.3
Oils/Tars	16.4	19.8
Water	<u>-2.5</u>	<u>-2.9</u>
Total	100.0	100.0

Table II-23. TEST MG-3 (1325°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	22.50	0.90	13.13	0.39	0.97	22.98	60.87
Steam + Moisture	--	<u>0.18</u>	<u>1.45</u>	<u>0.00</u>	<u>0.00</u>	--	<u>1.63</u>
Total	22.50	1.08	14.58	0.39	0.97	22.98	62.50
<u>Output</u>							
Char Mixture	18.82	0.19	10.67	0.34	0.57	22.62	53.21
Product Gas	1.79	0.35	0.82	--	0.37	--	3.33
Oils/Tars	2.37	0.18	0.28	0.04	0.06	0.00	2.93
Aqueous Condensate	--	<u>0.43</u>	<u>3.37</u>	<u>0.00</u>	<u>0.00</u>	--	<u>3.80</u>
Total	22.98	1.15	15.14	0.38	1.00	22.62	63.27
Out/In	1.02	1.06	1.04	0.98	1.03	0.98	1.01
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	22.50	0.89	13.13	0.39	0.97	22.98	60.87
<u>Output</u>							
Char Mixture	19.11	0.19	10.84	0.35	0.58	22.97	54.04
Product Gas	1.79	0.35	0.82	--	0.33	--	3.29
Oils/Tars	2.37	0.18	0.27	0.04	0.06	0.01	2.93
Aqueous Condensate	<u>0.00</u>	<u>0.07</u>	<u>0.56</u>	<u>0.00</u>	<u>0.00</u>	--	<u>0.63</u>
Total	23.27	0.79	12.49	0.39	0.97	22.98	60.89
Out/In	1.03	0.89	0.95	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	76.9	71.7
Gas	11.1	13.6
Oils/Tars	9.9	12.1
Water	<u>2.1</u>	<u>2.6</u>
Total	100.0	100.0

Table II-24. TEST MG-5 (1100°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	77.91	2.54	5.53	1.52	2.25	13.85	103.60
Steam + Moisture	--	<u>1.86</u>	<u>14.74</u>	--	--	--	<u>16.60</u>
Total	77.91	4.40	20.27	1.52	2.25	13.85	120.20
<u>Output</u>							
Char Mixture	60.06	1.24	3.00	1.15	1.66	13.20	80.31
Product Gas	1.26	0.28	0.82	0.00	0.15	--	2.51
Oils/Tars	3.97	0.37	0.58	0.05	0.10	0.01	5.08
Aqueous Condensate	<u>0.00</u>	<u>2.05</u>	<u>16.25</u>	<u>0.00</u>	<u>0.00</u>	--	<u>18.30</u>
Total	65.29	3.94	20.65	1.20	1.91	13.21	106.20
Out/In	0.84	0.90	1.02	0.79	0.85	0.95	0.88
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	77.91	2.54	5.53	1.52	2.25	13.85	103.60
<u>Output</u>							
Char Mixture	62.97	1.30	3.15	1.21	1.74	13.84	84.21
Product Gas	1.26	0.28	0.82	0.00	0.16	--	2.52
Oils/Tars	13.67	1.29	2.00	0.18	0.36	0.03	17.5
Aqueous Condensate	<u>0.00</u>	<u>-0.09</u>	<u>-0.71</u>	<u>0.14</u>	<u>0.00</u>	<u>0.00</u>	<u>-0.66</u>
Total	77.90	2.78	5.26	1.53	2.26	13.87	103.60
Out/In	1.00	1.09	0.95	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	63.0	56.4
Gas	4.8	5.7
Oils/Tars	33.5	39.3
Water	<u>-1.3</u>	<u>-1.4</u>
Total	100.0	100.0

Table II-25. TEST MG-11 (1390°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	15.04	0.47	1.07	0.27	0.46	2.73	20.04
Steam + Moisture	--	<u>1.44</u>	<u>11.42</u>	--	--	--	<u>12.85</u>
Total	15.04	1.92	12.48	0.27	0.46	2.73	32.89
<u>Output</u>							
Char Mixture	14.36	0.08	0.09	0.24	0.26	2.95	17.98
Product Gas	0.81	0.22	0.61	0.00	0.07	--	1.71
Oils/Tars	1.02	0.08	0.07	0.01	0.04	0.01	1.23
Aqueous Condensate	<u>0.00</u>	<u>0.70</u>	<u>5.55</u>	<u>0.00</u>	<u>0.00</u>	--	<u>6.25</u>
Total	16.19	1.08	6.32	0.25	0.37	2.96	27.17
Out/In	1.08	0.57	0.51	0.93	0.81	1.08	0.83
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	15.04	0.47	1.07	0.27	0.47	2.72	20.04
<u>Output</u>							
Char Mixture	13.12	0.08	0.09	0.22	0.24	2.72	16.47
Product Gas	0.81	0.23	0.61	0.00	0.19	--	1.84
Oils/Tars	1.11	0.08	0.08	0.02	0.04	0.00	1.34
Aqueous Condensate	<u>0.00</u>	<u>0.04</u>	<u>0.33</u>	<u>0.03</u>	<u>0.00</u>	--	<u>0.40</u>
Total	15.04	0.43	1.11	0.27	0.47	2.72	20.04
Out/In	1.00	0.92	1.04	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	63.9	57.3
Gas	18.6	22.0
Oils/Tars	13.5	15.9
Water	<u>4.0</u>	<u>4.8</u>
Total	100.0	100.0

Table II-26. TEST MG-12 (1252°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	8.91	0.28	0.68	0.14	0.26	1.54	11.81
Steam + Moisture	--	0.77	6.14	--	--	--	6.91
Total	8.91	1.05	6.82	0.14	0.26	1.54	18.72
<u>Output</u>							
Char Mixture	7.01	0.05	0.04	0.12	0.12	1.49	8.83
Product Gas	0.35	0.09	0.21	0.00	0.03	--	0.68
Oils/Tars	0.88	0.07	0.16	0.01	0.02	0.00	1.14
Aqueous Condensate	0.00	0.42	3.37	0.00	0.00	0.00	3.79
Total	8.24	0.63	3.78	0.13	0.17	1.49	14.45
Out/In	0.92	0.60	0.55	0.94	0.65	0.97	0.77
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	8.91	0.28	0.68	0.14	0.26	1.54	11.81
<u>Output</u>							
Char Mixture	7.26	0.06	0.04	0.12	0.12	1.54	9.14
Product Gas	0.35	0.09	0.21	0.00	0.12	--	0.77
Oils/Tars	1.30	0.10	0.24	0.02	0.02	0.00	1.68
Aqueous Condensate	0.00	0.02	0.19	0.00	0.00	--	0.21
Total	8.91	0.27	0.68	0.14	0.26	1.54	11.81
Out/In	1.00	0.96	1.00	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	54.3	46.4
Gas	13.1	15.4
Oils/Tars	28.9	33.8
Water	3.7	4.4
Total	100.0	100.0

Table II-27. TEST MG-14 (1084°F) MATERIAL BALANCES

	UNADJUSTED						Total
	C	H	O	N	S	Ash	
<u>Input</u>							
Feed Mixture	15.45	0.48	1.24	0.25	0.47	2.87	20.76
Steam + Moisture	--	1.50	11.94	--	--	--	13.45
Total	15.45	1.98	13.18	0.25	0.47	2.87	34.21
<u>Output</u>							
Char Mixture	13.03	0.13	0.39	0.21	0.26	2.77	16.79
Product Gas	0.41	0.10	0.22	0.00	0.07	--	0.80
Oils/Tars	1.01	0.09	0.15	0.01	0.02	0.00	1.28
Aqueous Condensate	0.00	0.84	6.66	0.00	0.00	0.00	7.50
Total	14.45	1.16	7.39	0.22	0.35	2.77	26.37
Out/In	0.94	0.58	0.56	0.88	0.74	0.97	0.77
	ADJUSTED						Total
	C	H	O	N	S	Ash	
<u>Input</u>							
Feed Mixture	15.45	0.49	1.25	0.24	0.47	2.87	20.76
<u>Output</u>							
Char Mixture	13.45	0.13	0.41	0.21	0.26	2.87	17.34
Product Gas	0.41	0.11	0.22	0.00	0.17	--	0.90
Oils/Tars	1.59	0.14	0.24	0.02	0.04	0.00	2.03
Aqueous Condensate	0.00	0.05	0.42	0.01	0.00	--	0.49
Total	15.45	0.43	1.29	0.24	0.47	2.87	20.76
Out/In	1.00	0.89	1.04	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	66.6	60.2
Gas	8.8	10.5
Oils/Tars	19.9	23.6
Water	4.7	5.7
Total	100.0	100.0

Table II-28. TEST MG-15 (1034°F) MATERIAL BALANCES

	UNADJUSTED						<u>Total</u>
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	
<u>Input</u>							
Feed Mixture	14.63	0.46	1.00	0.26	0.38	2.40	19.13
Steam + Moisture	--	<u>1.61</u>	<u>12.77</u>	--	--	--	<u>14.38</u>
Total	14.63	2.07	13.77	0.26	0.38	2.40	33.51
<u>Output</u>							
Char Mixture	13.53	0.14	0.32	0.24	0.24	2.54	17.01
Product Gas	0.41	0.11	0.25	0.00	0.08	--	0.85
Oils/Tars	1.20	0.11	0.26	0.01	0.02	0.01	1.61
Aqueous Condensate	<u>0.00</u>	<u>0.95</u>	<u>7.53</u>	<u>0.00</u>	<u>0.00</u>	<u>0.00</u>	<u>8.48</u>
Total	15.14	1.31	8.36	0.25	0.34	2.55	27.95
Out/In	1.03	0.63	0.61	0.97	0.89	1.06	0.83
	ADJUSTED						<u>Total</u>
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	
<u>Input</u>							
Feed Mixture	14.63	0.45	1.00	0.26	0.38	2.39	19.11
<u>Output</u>							
Char Mixture	12.64	0.13	0.30	0.22	0.22	2.37	15.89
Product Gas	0.41	0.11	0.25	0.00	0.12	--	0.89
Oils/Tars	1.58	0.15	0.34	0.02	0.03	0.01	2.13
Aqueous Condensate	<u>0.00</u>	<u>0.02</u>	<u>0.16</u>	<u>0.02</u>	<u>0.00</u>	--	<u>0.20</u>
Total	14.63	0.41	1.05	0.26	0.38	2.39	19.11
Out/In	1.00	0.90	1.05	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	66.0	60.9
Gas	9.4	10.9
Oils/Tars	22.4	25.8
Water	<u>2.2</u>	<u>2.4</u>
Total	100.0	100.0

Table II-29. TEST MC-16 (1183°F) MATERIAL BALANCES

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	23.60	0.68	1.92	0.40	0.68	4.39	31.67
Steam + Moisture	--	1.47	11.70	--	--	--	13.17
Total	23.60	2.15	13.62	0.40	0.68	4.39	44.84
<u>Output</u>							
Char Mixture	18.91	0.11	0.39	0.29	0.31	4.03	24.04
Product Gas	0.67	0.18	0.37	0.00	0.07	--	1.29
Oils/Tars	1.35	0.12	0.29	0.01	0.03	0.01	1.81
Aqueous Condensate	0.00	0.78	6.21	0.00	0.00	0.00	6.99
Total	20.93	1.19	7.26	0.30	0.41	4.04	34.13
Out/In	0.89	0.55	0.53	0.75	0.60	0.92	0.76
	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	23.59	0.69	1.92	0.40	0.68	4.39	31.67
<u>Output</u>							
Char Mixture	20.52	0.12	0.43	0.31	0.33	0.38	26.11
Product Gas	0.67	0.19	0.37	0.00	0.29	--	1.52
Oils/Tars	2.39	0.22	0.52	0.02	0.05	0.01	3.22
Aqueous Condensate	0.00	0.09	0.69	0.06	0.00	--	0.84
Total	23.59	0.62	2.01	0.40	0.68	4.40	31.69
Out/In	1.00	0.90	1.05	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	64.4	57.6
Gas	9.7	11.6
Oils/Tars	20.5	24.4
Water	5.4	6.4
Total	100.0	100.0

Table II-30. TEST MG-18 (1178°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	26.86	0.79	1.76	0.47	0.69	4.28	34.85
Steam + Moisture	--	2.11	16.75	--	--	--	18.86
Total	26.86	2.90	18.51	0.47	0.69	4.28	53.71
<u>Output</u>							
Char Mixture	22.96	0.18	0.32	0.38	0.38	4.53	28.75
Product Gas	0.75	0.22	0.43	0.00	0.05	--	1.45
Oils/Tars	1.41	0.12	0.25	0.02	0.03	0.01	1.84
Aqueous Condensate	0.00	1.43	11.36	0.01	0.00	0.00	12.80
Total	25.12	1.95	12.36	0.41	0.46	4.54	44.84
Out/In	0.94	0.67	0.67	0.87	0.67	1.06	0.83
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	26.86	0.79	1.76	0.47	0.69	4.28	34.85
<u>Output</u>							
Char Mixture	21.54	0.17	0.30	0.36	0.35	4.25	26.97
Product Gas	0.75	0.22	0.43	0.00	0.24	--	1.64
Oils/Tars	4.57	0.39	0.81	0.06	0.10	0.03	5.96
Aqueous Condensate	0.00	0.02	0.21	0.05	0.00	0.00	0.28
Total	26.86	0.80	1.75	0.47	0.69	4.28	34.85
Out/In	1.00	1.02	0.99	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	53.3	47.0
Gas	9.7	11.0
Oils/Tars	35.3	40.1
Water	<u>1.7</u>	<u>1.9</u>
Total	100.0	100.0

Table II-31. TEST MG-19 (1102°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	67.26	2.12	3.73	1.21	1.78	11.05	87.15
Steam + Moisture	--	<u>3.06</u>	<u>24.25</u>	--	--	--	<u>27.31</u>
Total	67.26	5.18	27.98	1.21	1.78	11.05	114.46
<u>Output</u>							
Char Mixture	54.63	0.64	1.02	0.98	1.08	10.57	68.92
Product Gas	1.40	0.34	0.59	0.00	0.09	--	2.42
Oils/Tars	6.26	0.57	0.96	0.07	0.15	0.00	8.01
Aqueous Condensate	<u>0.00</u>	<u>1.60</u>	<u>12.71</u>	<u>0.01</u>	<u>0.00</u>	<u>0.00</u>	<u>14.32</u>
Total	62.29	3.15	15.28	1.06	1.32	10.57	93.67
Out/In	0.93	0.61	0.55	0.88	0.74	0.96	0.82
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	67.26	2.12	3.73	1.21	1.78	11.05	87.15
<u>Output</u>							
Char Mixture	57.14	0.67	1.04	1.02	1.12	11.05	72.04
Product Gas	1.40	0.36	0.59	0.00	0.44	--	2.79
Oils/Tars	8.72	0.79	1.35	0.10	0.21	0.00	11.17
Aqueous Condensate	<u>0.00</u>	<u>0.12</u>	<u>0.95</u>	<u>0.09</u>	<u>0.00</u>	--	<u>1.16</u>
Total	67.26	1.94	3.93	1.21	1.78	11.05	87.16
Out/In	1.00	0.92	1.05	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	64.2	58.5
Gas	6.6	7.7
Oils/Tars	26.4	30.7
Water	<u>2.8</u>	<u>3.1</u>
Total	100.0	100.0

Table II-32. TEST MG-21 (1109°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	59.94	1.75	3.74	1.16	1.46	9.09	77.14
Steam + Moisture	--	<u>1.11</u>	<u>8.83</u>	--	--	--	<u>9.94</u>
Total	59.94	2.86	12.57	1.16	1.46	9.09	87.08
<u>Output</u>							
Char Mixture	50.33	0.57	1.34	0.96	0.94	9.61	63.75
Product Gas	1.32	0.32	0.529	0.00	0.09	--	2.32
Oils/Tars	5.65	0.50	0.87	0.07	0.14	0.03	7.26
Aqueous Condensate	<u>0.00</u>	<u>0.56</u>	<u>4.43</u>	<u>0.00</u>	<u>0.00</u>	<u>0.00</u>	<u>4.99</u>
Total	57.30	1.95	7.23	1.03	1.17	9.64	78.32
Out/In	0.96	0.68	0.57	0.89	0.80	1.06	0.90
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	59.94	1.75	3.74	1.16	1.46	9.09	77.14
<u>Output</u>							
Char Mixture	47.31	0.54	1.26	0.90	0.88	9.03	59.92
Product Gas	1.32	0.32	0.59	0.00	0.30	--	2.53
Oils/Tars	11.31	1.00	1.74	0.14	0.28	0.06	14.53
Aqueous Condensate	<u>0.00</u>	<u>0.00</u>	<u>0.03</u>	<u>0.12</u>	<u>0.00</u>	<u>0.00</u>	<u>0.15</u>
Total	59.94	1.86	3.62	1.16	1.46	9.09	77.13
Out/In	1.00	1.06	0.97	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	54.3	48.2
Gas	6.7	7.6
Oils/Tars	38.6	43.7
Water	<u>0.4</u>	<u>0.5</u>
Total	100.0	100.0

Table II-33. TEST MG-22 (1147°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	70.40	2.07	4.98	1.26	1.84	11.31	91.86
Steam + Moisture	--	0.37	2.96	--	--	--	3.33
Total	70.40	2.44	7.94	1.26	1.84	11.31	95.19
<u>Output</u>							
Char Mixture	57.74	0.64	1.67	1.04	1.16	11.72	73.97
Product Gas	2.01	0.51	0.78	0.00	0.14	--	3.44
Oils/Tars	6.25	0.56	0.99	0.07	0.14	0.00	8.01
Aqueous Condensate	0.00	0.24	1.90	0.00	0.00	0.00	2.14
Total	66.00	1.95	5.34	1.11	1.44	11.72	87.56
Out/In	0.94	0.80	0.67	0.88	0.78	1.04	0.92
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	70.40	2.07	4.98	1.26	1.84	11.31	91.86
<u>Output</u>							
Char Mixture	55.72	0.62	1.61	1.00	1.12	11.31	71.38
Product Gas	2.01	0.51	0.78	0.00	0.14	0.00	3.74
Oils/Tars	12.67	1.14	2.01	0.14	0.28	0.00	16.24
Aqueous Condensate	0.00	0.05	0.36	0.12	0.00	0.00	0.53
Total	70.40	2.32	4.76	1.26	1.84	11.31	91.89
Out/In	1.00	1.12	0.96	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	54.3	47.4
Gas	8.3	9.6
Oils/Tars	36.2	41.7
Water	<u>1.2</u>	<u>1.3</u>
Total	100.0	100.0

Table II-34. TEST MG-25 (1134°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	61.88	1.75	3.95	1.12	1.69	10.80	81.19
Steam + Moisture	--	1.30	10.35	--	--	--	11.65
Total	61.88	3.05	14.30	1.12	1.69	10.80	92.84
<u>Output</u>							
Char Mixture	55.44	0.86	2.01	1.06	1.42	12.26	73.05
Product Gas	1.57	0.37	0.84	0.00	0.32	--	3.10
Oils/Tars	6.68	0.60	0.92	0.07	0.18	0.01	8.46
Aqueous Condensate	0.00	1.09	8.66	0.02	0.00	0.00	9.77
Total	63.69	2.92	12.43	1.15	1.92	12.27	94.38
Out/In	1.03	0.96	0.87	1.03	1.14	1.14	1.02
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	61.88	1.75	3.95	1.12	1.69	10.80	81.19
<u>Output</u>							
Char Mixture	48.76	0.76	1.77	0.93	1.25	10.78	64.25
Product Gas	1.57	0.37	0.84	0.00	0.13	0.00	2.91
Oils/Tars	11.55	1.04	1.59	0.12	0.31	0.02	14.63
Aqueous Condensate	0.00	-0.08	-0.61	0.07	0.00	0.00	-0.62
Total	61.88	2.09	3.59	1.12	1.69	10.80	81.17
Out/In	1.00	1.19	0.91	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	57.2	51.3
Gas	7.4	8.4
Oils/Tars	37.0	42.0
Water	-1.5	-1.7
Total	100.0	100.0

Table II-35. TEST MG-28 (1149°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	42.74	0.77	0.82	0.66	0.51	5.99	51.49
Steam + Moisture	--	<u>0.97</u>	<u>7.66</u>	--	--	--	<u>8.63</u>
Total	42.74	1.74	8.48	0.66	0.51	5.99	60.12
<u>Output</u>							
Char Mixture	42.59	0.32	0.40	0.69	0.48	6.52	51.00
Product Gas	0.82	0.24	0.25	0.00	0.03	--	1.34
Oils/Tars	2.89	0.26	0.36	0.03	0.03	0.00	3.57
Aqueous Condensate	<u>0.00</u>	<u>0.37</u>	<u>2.92</u>	<u>0.00</u>	<u>0.00</u>	<u>0.00</u>	<u>3.29</u>
Total	46.30	1.19	3.93	0.72	0.54	6.52	59.20
Out/In	1.08	0.68	0.46	1.09	1.06	1.09	0.98
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	42.74	0.77	0.82	0.66	0.51	5.99	51.49
<u>Output</u>							
Char Mixture	39.10	0.30	0.35	0.64	0.44	5.99	46.82
Product Gas	0.82	0.24	0.25	0.00	0.03	--	1.34
Oils/Tars	2.82	0.25	0.35	0.03	0.03	0.00	3.48
Aqueous Condensate	<u>0.00</u>	<u>-0.02</u>	<u>-0.12</u>	<u>-0.01</u>	<u>0.00</u>	--	<u>-0.15</u>
Total	42.74	0.77	0.83	0.66	0.50	5.99	51.49
Out/In	1.00	1.00	1.02	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	73.0	69.4
Gas	7.8	8.8
Oils/Tars	20.1	22.8
Water	<u>-0.9</u>	<u>-1.0</u>
Total	100.0	100.0

Table II-36. TEST MG-30 (1050°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	54.72	1.00	2.02	0.90	0.64	7.34	66.62
Steam + Moisture	--	<u>0.98</u>	<u>7.81</u>	--	--	--	<u>8.79</u>
Total	54.72	1.98	9.83	0.90	0.64	7.34	75.41
<u>Output</u>							
Char Mixture	47.30	0.47	1.24	0.79	0.55	6.85	57.20
Product Gas	0.73	0.21	0.19	0.00	0.03	--	1.16
Oils/Tars	3.58	0.32	0.35	0.03	0.03	0.00	4.31
Aqueous Condensate	<u>0.00</u>	<u>0.84</u>	<u>6.68</u>	<u>0.01</u>	<u>0.00</u>	<u>0.00</u>	<u>7.53</u>
Total	51.61	1.84	8.46	0.83	0.61	6.85	70.20
Out/In	0.94	0.93	0.86	0.92	0.95	0.93	0.93
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	54.72	1.01	2.02	0.89	0.64	7.34	66.62
<u>Output</u>							
Char Mixture	50.66	0.50	1.33	0.85	0.58	7.34	61.26
Product Gas	0.73	0.21	0.19	0.00	0.03	--	1.16
Oils/Tars	3.58	0.32	0.35	0.03	0.03	0.00	4.31
Aqueous Condensate	<u>0.00</u>	<u>-0.01</u>	<u>-0.11</u>	<u>0.01</u>	<u>0.00</u>	--	<u>-0.11</u>
Total	54.97	1.02	1.76	0.89	0.64	7.34	66.62
Out/In	1.00	1.02	0.87	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	76.0	73.4
Gas	5.2	5.7
Oils/Tars	19.3	21.4
Water	<u>-0.5</u>	<u>-0.5</u>
Total	100.0	100.0

For material balance calculations, the coke breeze used as diluent was assumed to be non-reacting, based on the initial on-line gas analyses during start-up with coke breeze only. The stepwise data normalization procedure that was applied is summarized as follows:

1. The ash in the output streams was balanced with ash in the input feed by adjusting the weight of fluidized-bed char collected during the test.
2. The carbon in the output streams was balanced by adjusting the amount of oils and tars collected, assuming that the heavy components coating pipes in the slipstream sampling system cannot be quantitatively collected, and also that the sintered metal filter used to separate char from the gas stream provides an active surface that promotes thermal cracking of a portion of the heavier tars, resulting in deposition of tar-based carbon in the filter pores. In cases where the carbon balance after step 1 was in excess of 100%, no adjustment was made.
3. Sulfur gases react reversibly with stainless steel system components, thus introducing a random error in PRU sulfur balances; unaccounted sulfur was balanced by assuming its presence as hydrogen sulfide.
4. Unaccounted nitrogen from the coal was assumed to form ammonia in the condensate stream. An analysis was performed for ammonia, but the volatility of that species at the low pH of the aqueous condensate makes it probable that a significant portion is lost during sampling and sample transport and storage.
5. The net chemical water make was determined by difference from a 100% total material balance. In some tests, the net water make is a negative number. It is unlikely that steam is actually consumed in the test, and the negative value for net water is probably the result of an accumulation of experimental error.

In five of the 15 successful tests (MG-5, MG-18, MG-21, MG-22, and MG-25), the required adjustments for the ash and carbon balances were in opposing directions. Consequently, the forcing of the ash balance caused the required adjustment to oils/tars for the carbon balance to be very large. The reason for this situation may lie in the question of feed material homogeneity during the course of the test, which was discussed earlier in the section describing PRU operations. For these tests, the material balances are considered to be less reliable, and, although reported for completeness, the data will be marked separately for purposes of interpretation in subsequent sections. Aside from material balances, the characterization data from these tests are used for interpretation of test parameters on co-product quality.

Temperature Effects

With the available analyzed data for the PRU tests described above, an evaluation of the effect of temperature on the co-product yields and other selected properties has been completed. These data are presented graphically in Figures II-6 to II-12.

Figure II-6 shows the effect of mild gasification temperature on the yields of char, gas, oils and tars, and net water from the fifteen tests listed at the beginning of this section, with the exception of Test MG-3. Test MG-3 was omitted because the use of limestone as a diluent constitutes a significantly different system condition, and thus the MG-3 data should not be included in a discussion of temperature effects using coal-derived diluents. Best-fit regression curves for Illinois No. 6 coal tests were constructed through the data points selected for the quality of the material balance data, shown as solid circles. Those tests (MG-5, MG-18, MG-21, MG-22, and MG-25) which required large adjustments to the char and/or oils and tars yields, based on the material balance normalization procedure, are shown as open circles on the plots, and were not included in calculation of the regression curves. This approach gives a conservative interpretation of oils/tars yields, and is consistent with accepted practice in statistical data analysis which allows rejection of data points that deviate substantially from the main body of the data. As shown, the gas yield increases with temperature, whereas the maximum oils/tars yield appears between 1100° and 1200°F. Char yield decreases as expected with increasing temperature, and the chemical water production appears fairly constant. Also shown on these plots for comparison are data from the two tests with West Virginia coal, displayed as asterisks. For the two test temperatures studied, this coal produced more char and less of oils/tars, gas, and water, on a dry-coal basis. This difference should be interpreted cautiously, however, because the West Virginia coal had substantially more fines, which may have affected the fluidization behavior and residence time in the fluidized bed. West Virginia coal will be used more extensively in Task 4 integrated system tests.

Also shown for comparison in Figure II-6 are pilot-plant data from the COED² and Occidental Flash Pyrolysis³ processes and laboratory data from CSIRO.⁴ The COED data was obtained with Illinois No. 6 coal, the Occidental data with Kentucky No. 9 coal, and the CSIRO data with Australian Liddell B

- IGT PRU data, Illinois coal; ○ IGT PRU data, Illinois coal (not included in regression curve);
- * IGT PRU data, West Virginia coal; △ Occidental Flash Pyrolysis (ref. 5);
- COED 2nd stage (ref. 7); CSIRO fluidized bed, Liddell B coal (ref. 6).

Figure II-6. EFFECT OF MILD GASIFICATION TEMPERATURE ON CO-PRODUCT YIELDS
(Based on Adjusted Material Balances)

closed points = Illinois coal, open points = West Virginia coal

Figure II-7. EFFECT OF MILD GASIFICATION TEMPERATURE ON THE BOILING-POINT FRACTIONS OF OILS/TARS

Figure II-8. EFFECT OF MILD GASIFICATION TEMPERATURE ON HETEROATOMS IN OILS/TARS

closed points = Illinois coal, open points = West Virginia coal

Figure II-9. EFFECT OF MILD GASIFICATION TEMPERATURE
ON H/C ATOMIC RATIO IN OILS/RATIO

closed points = Illinois coal; open points = West Virginia coal

Figure II-10. EFFECT OF MILD GASIFICATION TEMPERATURE ON ASH, VOLATILE MATTER, AND SULFUR CONTENT OF CHAR

Figure II-11. EFFECT OF MILD GASIFICATION TEMPERATURE ON GAS COMPOSITION

Figure II-12. FIMS SPECTRUM ON TEST MG-3 SOLVENT QUENCH TAR

bituminous coal. Both of the latter coals are similar in ash and volatile matter content and in swelling/caking behavior to the Illinois No. 6 coal used in the PRU tests.

Citations in the literature have generally shown, in laboratory studies, increasing oils/tars yields with temperatures up to at least 1500°F; however, these data were usually obtained in experimental systems that minimized the extent of secondary reactions.⁵⁻⁷ Pilot-plant data from the entrained-flow Occidental Flash Pyrolysis process with Kentucky bituminous coal showed higher oils/tars yields than in our tests in three out of ten of their test runs, but the diluent solid used was a low-surface-area non-reactive petroleum coke.³ Occidental data with recycled pyrolysis char gave much lower liquid yields, and even with the petroleum coke, seven of their ten reported tests gave oils/tars yields similar to those from the mild gasification PRU. Pyrolysis in fluidized beds, while providing rapid particle heating, cannot avoid secondary reactions, and thus there is a temperature at which the equilibrium between condensables production and destruction reactions results in a decreasing yield. The PRU liquid yield data shown in Figure II-6 is in good agreement with the CSIRO fluidized-bed data, from which the maximum oils/tars yields were reported to be at about 1100°F, regardless of the coal rank.⁴ The mild gasification liquid yields are slightly higher than those reported for Illinois No. 6 coal in the first two stages of the COED process, which operated at a lower temperature of 800°F and required oxidative pretreatment and the use of multiple staged reactors.²

The use of a fluidized/entrained reactor rather than a simple fluidized bed was designed to allow fine particles that would normally elutriate from the bed to undergo devolatilization in the entrained section. The data from the PRU tests are not conclusive regarding the role of the entrained section on the co-product yields. Nevertheless, the observed yields of oils and tars are comparable to those obtained from the Occidental entrained reactor, and greater than those reported by COED, suggesting that the PRU reactor configuration may have some positive influence on oils/tars yields.

Figure II-7 shows the effect of the process temperature on the cumulative boiling-range distribution of the oils and tars. It appears from these data that the principal change in the volatility of the condensables with an increasing mild gasification temperature consists of an increase in light oils

fraction (b.p. <360°F) at mild gasification temperatures above 1300°F, accompanied by a more gradual decrease in the pitch fraction (b.p. >750°F) beginning at a process temperature of about 1150°F. A maximum in the heavy oil fraction (b.p. 590° to 750°F) occurs between 1150° and 1300°F, but no significant change was seen in the middle oils fraction (b.p. 360° to 590°F) with an increasing mild gasification temperature. These results are contrary to trends reported for fixed-bed or moving-bed carbonizers, which utilize slow heating rates and report an increasing pitch content in the liquids at higher process temperatures. This indicates that the IGT mild gasification process produces not only higher oils/tars yields than conventional fixed-bed or moving-bed carbonizers, but that the physicochemical nature of the condensables is also significantly different.

Figure II-8 shows the manner in which the heteroatom content of the condensables (not including light oils) changes with the process temperature. Comparison of sulfur content with the coal composition shown in Table II-1 indicates that the sulfur content of oils/tars from the Illinois No. 6 coal is lower than the sulfur content of the coal. In contrast with the results on boiling-fraction distribution, this trend is similar to that reported for slow-heating processes, such as in a recent paper by Khan, based on fixed-bed mild gasification of a variety of coals at 932°F.⁸ Nitrogen and sulfur levels increase slightly, whereas the oxygen content decreases sharply with an increasing mild gasification temperature. The decrease in oxygen content signals the loss of oxygen functionalities, such as phenolic -OH groups, and may partially explain the decrease in pitch content at higher temperatures, whereby the removal of oxygen functional groups reduces the boiling point and shifts some pitch components into the lower boiling fractions. The slight increase in N and S content with process temperature may indicate an increasing incorporation of these heteroatoms into polycondensed aromatic rings.

The H/C ratio of the condensables, shown in Figure II-9, also changes with process temperature. The decrease in the H/C ratio is consistent with an increase in aromaticity with process temperature. This can result from dealkylation and dehydroxylation reactions of existing aromatic nuclei or from the cyclization and dehydrogenation of aliphatic constituents. In slow-heating low-temperature carbonization processes, which produce liquids with

substantial aliphatic content, the latter pathway may be significant, explaining the increase in pitch content with increasing temperature in those processes. In rapid-heating processes such as the IGT mild gasification process, the presence in low-temperature oils/tars of primarily aromatic structures with abundant aliphatic side chains and phenolic hydroxyl groups shows that the former pathway may be more significant. This is also consistent with the observation of loss of oxygen from the oils/tars at increasing mild gasification temperatures. The quality of binder pitches is closely correlated with high aromaticity.

Figure II-10 shows the ash, volatile matter, and sulfur content of the mild gasification char with process temperature. These data quantify the increasing devolatilization and carbon conversion of the feed coal as mild gasification temperature increases. Sulfur content is 20% to 35% lower than that of the feed coal, and decreases slowly with increasing temperature.

The product gas composition is also affected by process temperature, as shown in Figures II-11a and II-11b. In these plots, the West Virginia coal data have been omitted for clarity. The Illinois No. 6 coal data for hydrogen, methane, and C₂ hydrocarbons (ethane + ethylene) are shown in Figure II-11a, and have been grouped into "low-steam" (steam/coal weight ratio of 0.0 to 0.5) and "high-steam" (steam/coal weight ratio of 0.7 to 1.4) tests, in order to illustrate the effects of steam and temperature on these components. A similar treatment of carbon monoxide, carbon dioxide, and hydrogen sulfide is shown in Figure II-11b. Best-fit regression curves were calculated for these data, and are shown as solid lines for the high-steam tests and dotted lines for the low-steam tests.

The dry, nitrogen-free concentrations of hydrogen and carbon monoxide increase with temperature, whereas carbon dioxide and hydrocarbon gases decrease. These trends are consistent with well-known devolatilization and gas-phase equilibrium data. The hydrogen sulfide content of the gas also decreases with temperature, at least for the high-steam tests, and it appears that, even when the increased gas yield at higher temperature is taken into account, the amount of sulfur released as hydrogen sulfide decreases with temperature. The effects of steam on the gas composition are discussed in more detail below.

Effects of Steam

PRU mild gasification Tests MG-19, MG-21, and MG-22 were conducted at similar conditions ($1125 \pm 23^\circ\text{F}$, 10 psig, 4.55 ± 0.15 ft/s gas velocity, 93.0 ± 2.2 lb/h feed rate of 1:1 Illinois No. 6 coal and coke breeze) except for steam input rates. The steam rates varied from zero in Test MG-22 to 23.7 lb/h (steam/coal ratio of 0.522) in Test MG-19. The intermediate steam rate in Test MG-21 was 8.5 lb/h (steam/coal ratio of 0.180). Some previous Illinois No. 6 coal tests were conducted at even higher steam/coal ratios; Tests SD-6, MG-11, MG-12, MG-14, MG-15, MG-16, and MG-18 used steam rates which resulted in steam/coal weight ratios of 0.7 to 1.4. The highest steam/coal ratio was 1.44 in Test MG-15.

Gas compositions were affected by steam, as indicated by the data in Figures II-11a and II-11b. The hydrogen concentration is seen to be consistently lower in the low-steam than in high-steam tests, while the hydrocarbon and CO levels are higher in the low-steam tests. The CO_2 and H_2S concentrations do not appear to be significantly affected by steam rate. These observations can be explained by the thermodynamics and kinetics of competing gas-phase reactions (steam-carbon, shift, and steam-methane reforming). An increase in the steam content of the fluidizing gas drives all three of these reactions toward the direction of hydrogen production, while tending to consume hydrocarbons via reforming. The steam-carbon reaction produces carbon monoxide, which in turn reacts with additional steam to make carbon dioxide. No attempt was made to compare the gas compositions with equilibrium compositions since, in fact, it is unlikely that the products were at equilibrium at the reactor exit.

The effect, if any, of the steam/coal ratio on the overall co-product yield structure could not be determined from these tests. Examination of oils/tars quality did not show any identifiable differences among Tests MG-19, MG-21, and MG-22 with respect to boiling-point fraction distribution, sulfur content, nitrogen content, oxygen content, or H/C ratio. No effects on char ash, volatile matter, or sulfur content were observed for these three tests.

Chemical Properties of Oils/Tars

Other properties of the oils and tars are of interest, and have been investigated for selected tests. Table II-37 shows a comparison of selected

Table II-37. COMPARISON OF PAH CONTENT OF MILD GASIFICATION TAR
WITH A TYPICAL COKE OVEN TAR⁹

	Mild Gasification (Test MG-25) ----- wt % of tar -----	Coke Oven -----
Biphenyl	0.010	0.420
Acenaphthene	0.011	1.280
Fluorene	0.027	2.560
Phenanthrene/Anthracene	0.066	2.870
2-Methylphenanthrene	0.083	0.700
1-Methylphenanthrene	0.064	0.750
Fluoranthene	0.003	0.531
Pyrene	0.015	0.520
Benz(a)anthracene	0.019	0.304
Chrysene/Triphenylene	not detected	0.221
Benzo(b,k)fluoranthene	not detected	0.354
Benzo(a)pyrene	0.017	0.293
Dibenzo(a,h)anthracene	0.009	0.039
Benzo(g,h,i)perylene	not detected	0.171

polyaromatic hydrocarbons, determined by capillary GC-MS, in the tar from Test MG-25 (process temperature of 1130°F) with a typical coke oven tar.⁹ As seen, the mild gasification tar contains at least an order of magnitude less of these compounds, some of which are known carcinogens and environmentally sensitive, compared to conventional coke oven tar.

In Table II-38, a comparison of the co-product yields from mild gasification and a typical coking process shows the major expected difference in the yield of oils/tars. Combining the values in Tables II-37 and II-38 reveal that the absolute quantities of environmentally sensitive PAH compounds, as well as their percentages in the total liquids, are lower in the mild gasification oils/tars. This is shown in Table 39 expressed as pounds per ton of dry coal.

Other methods of analysis that were applied to PRU oils/tars samples included field ionization mass spectroscopy (FIMS) and H-NMR (hydrogen nuclear magnetic spectroscopy).

The FIMS analysis was applied early in the program to the +360°F fraction from the Test MG-3 slipstream oils/tars samples collected in methylene chloride during the test (solvent quench condensate) and in tetrahydrofuran by post-test rinsing of the sample vessels and lines (THF wash). This method characterizes the components in the liquid with minimal molecular fracture,

Table II-38. COMPARISON OF CO-PRODUCT YIELDS WITH COKE OVEN
BY-PRODUCT YIELDS⁹

	<u>Mild Gasification</u>	<u>Coke Oven</u>
	----- wt % maf coal -----	-----
Product Gas	11.6	13.9
Oils/Tars	24.4	4.5
Water	6.4	14.1
Char or Coke	57.6	67.5

Table II-39. COMPARISON OF PAH PRODUCTION LEVELS BETWEEN
MILD GASIFICATION AND A TYPICAL COKE OVEN TAR

	<u>Mild Gasification</u>	<u>Coke Oven</u>
	(Test MG-25)	
	----- lb/ton dry coal -----	-----
Biphenyl	0.049	0.378
Acenaphthene	0.055	1.152
Fluorene	0.128	2.304
Phenanthrene/Anthracene	0.315	2.583
2-Methylphenanthrene	0.398	0.630
1-Methylphenanthrene	0.306	0.675
Fluoranthene	0.015	0.478
Pyrene	0.070	0.468
Benz(a)anthracene	0.091	0.274
Chrysene/Triphenylene	0.000	0.199
Benzo(b,k)fluoranthene	0.000	0.319
Benzo(a)pyrene	0.079	0.264
Dibenzo(a,h)anthracene	0.044	0.035
Benzo(g,h,i)perylene	0.000	0.154

unlike standard MS which breaks down large molecules into smaller fragments. Consequently, the FIMS method can identify the parent molecules and derive a molecular weight distribution for a major part of the high-boiling oils and tars. It can also show important structural data. Test MG-3 was performed in the PRU at 1325°F with Illinois No. 6 coal and limestone as a diluent. The two oils/tars samples from the test were analyzed in a FIMS device at SRI International, and interpretation of the data was provided by Dr. Ripudaman Malhotra of SRI. In this device, the sample is volatilized under vacuum using a programmed temperature ramp ranging from -58° to 842°F.

Figures II-12 and II-13 show, respectively, the FIMS spectra of the Test MG-3 oils/tars in methylene chloride, representing the condensables dissolved in the run-time quench solvent, and of the Test MG-3 oils/tars washed from the sample lines with THF. Figures II-14 and II-15 show the vacuum evaporation curves from the apparatus, and indicate that the quantities of the oils/tars represented by the FIMS spectra are approximately 95% and 88% of the total oils/tars mass for the two samples. Therefore, the FIMS data represent the majority of each sample, with a minimal loss of high-boiling unrecovered material. As indicated by the spectra, the bulk of the material falls in the 100 to 500 molecular weight range, with the THF wash containing a higher proportion of high-molecular weight compounds. Table II-40 lists some of the major components (up to molecular weight 246) in the two FIMS spectra by molecular weight, their relative ion intensities, and some overall characteristics of the samples. From these data, it is seen that the oils/tars are composed primarily of aromatic nuclei, but the C₁- and C₂-alkyl derivatives of many of the components (e.g., phenol, naphthol, fluorene, anthracene/phenanthrene) are more abundant than the parent aromatic. This is reflective of the low temperature of mild gasification, and is in general agreement with the standard GC analyses of the co-products that were performed at IGT. The ratio of odd/even ions in the spectra is an indication of the relative nitrogen content of the sample, because nitrogen, at mass 7, is the usual source of an odd-numbered ion molecular weight. Based on this interpretation, the THF wash, which contains a higher proportion of higher-molecular-weight components, also contains more nitrogen. This is corroborated by the elemental analyses of the samples.

Figure II-13. FIMS SPECTRUM OF TEST MG-3 THF WASH TAR

Figure II-14. VACUUM DISTILLATION CURVE OF TEST MG-3 SOLVENT QUENCH TAR

Figure II-15. VACUUM DISTILLATION CURVE OF TEST MG-3 THF WASH TAR

Table II-40. FIMS DATA ON TEST MG-3 OILS AND TARS

Mol wt	Major Peaks		THF Wash
	Possible compound(s)	CH ₂ Cl ₂ Quench	
94	phenol	407	473
108	cresols	1056	1498
122	xlenols	653	1008
142	naphthols	774	874
156	C ₁ -naphthols	886	865
166	fluorene	1157	984
168	dibenzofuran	550	527
170	C ₂ -naphthols	683	627
178	anthracene/phenanthrene	762	667
180	C ₁ -fluorenes	1378	1027
182	C ₁ -dibenzofurans	964	805
184	dibenzothiophene	571	524
192	C ₁ -anthracenes/phenanthrenes	1505	994
196	C ₂ -dibenzofurans	918	732
202	pyrene	661	415
204	phenylnaphthalene	987	591
206	C ₂ -anthracenes/phenanthrenes	1645	895
216	C ₁ -pyrenes	1751	834
218	C ₁ -phenylnaphthalenes	1369	789
230	C ₂ -pyrenes	1861	894
232	C ₂ -phenylnaphthalenes	1611	917
244	C ₃ -pyrenes	1301	697
246	C ₃ -phenylnaphthalenes	1349	738
Number average molecular weight		261	275
Weight average molecular weight		289	315
Ratio of odd/even mass peaks		0.228	0.324

The FIMS analysis confirms the aromatic nature of the mild gasification oils/tars and its potential to produce pitch that is a high-market-value product. In contrast, the low-temperature carbonization tars from conventional slow-heating processes (Coalite, Disco, etc.) were not considered suitable for production of binder pitches because of their high aliphatic content. The mild gasification liquid does not show any significant quantities of aliphatic parent compounds. Virtually all of the aliphatic content is comprised of short alkyl side chains on aromatic nuclei. If desired, a simple thermal treatment may be adequate to remove these aliphatic constituents and increase the aromaticity of the resulting pitch to acceptable levels for use as electrode binders.

H-NMR analysis was applied to the mild gasification tar from Test MG-25 (test temperature 1134°F). The NMR spectrum is shown in Figure II-16, and

ONE-PULSE SEQUENCE

P2= 10.00 USEC
A DE= 312 USEC
D2= AT
D3= 5.00 SEC
NS = 800
SIZ = 0192
AT = 1.28 SEC
ADL ON OPD ON =
ADC = 10 BITS AT =
SW = +/- 1602.56 DW =
F2 = 200.059001
DF = 1188.42
SF = 200.059001
EM = .90
FA = 272.9
PD = 98.6

SCALE: 94.25 HZ/CM
4711 PPM/CM

Figure II-16. H-NMR SPECTRUM OF TEST MG-25 OILS/TARS

shows the following distribution of H-atoms in the combined oils/tars (combined solvent quench and THF wash samples).

Table II-41. HYDROGEN ATOM DISTRIBUTION IN TEST MG-25 OILS AND TARS

<u>Hydrogen Functional Type</u>	<u>Percent of Total Hydrogen</u>
Aromatic + phenolic	35
Hydrogen on C α - to two rings	5
Hydrogen on C α - to one ring	35
Naphthenic methylene (hydroaromatic) + methane	5
Methylene β - or more remote from ring + methyl β - to ring	14
Methyl Γ - or further from ring	4

These data show that the hydrogen in the mild gasification liquids is contained largely in alkyl groups, primarily methyl, attached to aromatic rings. The methyl, ethyl, and propyl or longer chain hydrogen can be estimated to be in the ratio of 5.25:2.5:1. Only a small amount, 5%, of hydrogen is in methylene bridges between rings, and a similarly small percentage is associated with hydroaromatic structures. These characteristics are typical of a rapid-heating low-temperature carbonization liquid, and are consistent with the FIMS data discussed above, which showed that alkyl derivatives of aromatic nuclei were abundant in the Test MG-3 oils/tars.

Reproducibility of Data

Most of the PRU tests conducted under Task 2 were performed at different temperatures to evaluate the effect of temperature. The reproducibility can thus be evaluated from the degree of scatter of the data from the regression curves derived therefrom. Of all the PRU tests, Tests MG-5, MG-19, and MG-21 were conducted at essentially the same system temperature ($1104 \pm 5^\circ\text{F}$), but varied in other respects, as system modifications were implemented primarily to increase the coal feed rate and improve gas-solids mixing. Test MG-14 was operated at a similar temperature, 1084°F , but at a much higher steam/feed ratio, a lower superficial gas velocity, and a longer coal residence time than the other tests, and thus is not included in the assessment of reproducibility.

In view of these considerations, it can be stated that the unadjusted co-product yields for these three tests covered the following ranges: char, 58.7 ± 4.1 wt %; oils/tars, 16.0 ± 4.4 wt %; and gas, 5.5 ± 0.5 wt % of dry coal. The error limits given are simple standard deviations. The relative standard deviations based on these data are 6.9%, 27.5%, and 9.8% for char, oils/tars, and gas yields, respectively. The low standard deviation in char yield indicates that the degree of devolatilization is controlled primarily by temperature. The scatter in the oils/tars yield data is probably because the oils/tars sample recovery techniques were steadily improved over the course of the investigation, resulting in a greater percentage of the produced condensables accounted for in the later tests (19.0 wt % and 19.3 wt % of dry coal unadjusted in Tests MG-19 and MG-21, compared to 9.8 wt % in Test MG-5). The relatively large standard deviation in gas yield may reflect the differences in steam rate, superficial gas velocity, and other process conditions which varied among the three tests. The effect of steam rate on gas composition has already been discussed, and was shown graphically in Figure II-7.

From the adjusted material balance data, the following ranges of yields were observed for the three tests: char, 60.5 ± 4.4 wt %; oils/tars, 32.8 ± 5.0 wt %; and gas, 6.0 ± 0.9 wt % of dry coal, respectively. The relative standard deviations for these co-products were, in the order just given, 7.3%, 15.2%, and 14.9%. The reproducibility of char yield was essentially unchanged, while the deviation was lower for oils/tars and higher for gases, compared to the unadjusted data.

Properties of oils/tars for the three tests were assessed for reproducibility. The distribution of oils/tars boiling-range fractions showed the following ranges and standard deviations: light oils, 6.2 ± 0.1 wt %; middle oils, 17.8 ± 1.4 wt %; heavy oils, 15.0 ± 1.7 wt %; and pitch, 61.0 ± 2.9 wt % of the total oils/tars. The relative standard deviations ranged from 2.0% to 11.4%. Sulfur content of the oils/tars was 1.9 ± 0.04 wt %, nitrogen content was 1.0 ± 0.05 wt %, and oxygen content was 11.9 ± 0.4 wt % of the total condensables. These data show relative standard deviations of 2.4% to 4.9%. The H/C atomic ratio for the oils/tars from the three tests was 1.09 ± 0.02 , giving a relative standard deviation of 2.3%.

These analyses show that, for the limited number of tests operated under similar conditions, the reproducibility of data was quite acceptable, especially with respect to the oils/tars quality. More comprehensive reproducibility data will be available following the completion of Task 4, System Integration Studies, because long-duration tests at constant reactor conditions will have been performed and that data will be integrated with the data already obtained under Task 2.

Reactor/Process Configuration

The operational flexibility designed into the fluidized/entrained bed isothermal PRU allows different process conditions and configurations to be evaluated. The resulting "preferred" process conditions identified from PRU data must be further evaluated in an adiabatic process development unit (PDU) that --

- Has no limiting hydrodynamic or wall effects on the fundamental conversion, heat, and mass transfer processes
- Provides a practical heat supply for adiabatic operation.

The main limitations of the IGT PRU is associated with its 8-inch inside diameter and the effects associated with the process heat coming through the metal walls of the reactor. This is especially important when caking coals are processed in the reactor. The relationship of the hydrodynamic characteristics of the PRU fluidized bed to those of larger units is also in the forefront of scale-up decisions, in terms of achieving proper mixing, gas distribution, and solids residence times.

Fluidized-Bed Section: For caking coals, the size of the PRU fluidized bed does not provide a sufficiently large volume of bed char to maintain the agglomerates in motion until they dissipate, avoiding their buildup in the bed or on the reactor walls. It is understood that low feed rates of caking coal will be quickly dispersed into a bed of devolatilized coal char and diminish the size of caked agglomerates. In the U-GAS project, IGT operated a 3-ft-ID fluidized bed that successfully fed caking Illinois No. 6 and Kentucky No. 9 coals. From this experience, a mathematical relationship of coal feed rate to fluidized-bed char volume was developed. This information was applied in the mild gasification PRU test operations, but agglomerates that still formed in the PRU did not have enough space or bed volume to dissipate before contacting

other sticky groups of particles or the reactor wall. Rather than considering any form of coal pretreatment such as air oxidation, we selected to operate the PRU with caking coal by mixing a surrogate bed char (coke breeze) with the incoming coal feed to achieve the required dilution of sticky particles to allow their complete devolatilization. Coal was also mixed with limestone in one test in the PRU, achieving non-agglomerating operation.

This approach allowed the PRU to operate and obtain material-balanced process data over a temperature range of 1035° to 1390°F, as previously discussed. Furthermore, upon analysis of the process for scale-up to an adiabatic PDU, coal feeding with hot recycled char and gas was determined to be economically beneficial. Therefore, operation of the PDU or larger reactors with caking coals will not be limited by the agglomeration tendency of the coal, because of the sufficiently large diameter and volume of char to promote rapid dispersion and mixing of the feed coal.

Entrained-Bed Section: The PRU feed point for the entrained-bed feed was located in the 8-inch-ID freeboard section with the intent of adding auxiliary hot nitrogen just below the freeboard feed point. The operational results showed that a significant amount of the feed coal particles were not entrained and fell into the fluidized bed. It was determined that the particles formed agglomerates as they entered the 8-inch-ID section, and could not be entrained at the employed gas velocities. The auxiliary hot gas flow for entrainment was distributed in the 8-inch diameter of the PRU through 12 holes drilled through the reactor wall. These radial jets of gas caused turbulence just below the feed point. The length of the entrained section from the feed point to the auxiliary nitrogen feed point was not sufficient to establish a well-distributed gas flow for proper entrainment. In addition, agglomerates from softening coal particles stuck to the hot metal walls of the reactor, resulting in a solid buildup on the walls.

To refine the design of the entrained bed, two steps should be taken:

- The PRU feed point should be relocated to the 4-inch-ID section where the flow velocity will be higher and can be properly established, and
- The feed nozzle should direct the injected particles in an upward direction with the gas stream, rather than downward and counter to the gas stream.

The key operation, however, of the IGT mild gasification process is the operation of the fluidized bed. The fluidized bed has operated with a caking Illinois No. 6 coal and a higher fluidity West Virginia coal. The successful operation involves superficial gas velocities higher than those traditionally used, and requires a gas distribution cone arrangement with a central gas jet to promote solids mixing near the coal feed point. In the IGT PRU, a higher fraction of particles were therefore elutriated from the fluidized bed. As revealed in Tables II-4 through II-18, the fine char from the system cyclones was less extensively devolatilized than the bed char, which increases the desirability of recycling the fine char to the fluidized bed. The less-devolatilized char could also be suitable for forming briquettes.

Maintaining the present reactor configuration and splitting the feed between the fluidized bed and the entrained bed in the adiabatic PDU design will capitalize on these observations. The discussion of a detailed PDU reactor configuration and its operational flexibility will be continued in the Topical Report for Task 4, System Integration Studies. The equipment design choices and advantageous processing refinements will be discussed.

Conclusions

The isothermal PRU system consisting of the fluidized/entrained bed reactor system was designed, constructed, installed and successfully shaken down. Two bituminous coals obtained from the Peabody Holding Co., Inc. (-12 mesh Illinois No. 6 coal and a -40 mesh West Virginia coal fines) were tested in the PRU to develop the process performance data for engineering evaluation and scale-up purposes. The PRU test data are obtained from slip-stream sampling of the condensable and gaseous products while the bulk of the co-products are disposed of in a combustor.

In the initial tests, dried coal fines were fed to the mid-region of the reactor, anticipating a size separation by the fluidizing nitrogen and subsequent mild gasification of coarse particles in the fluidized bed and of fines in the entrained bed section. The wall effects of the 8-inch ID reactor and the externally heated hot metal walls promoted caking of coal, leading to involuntary test shutdown. The caking problem was solved by mixing the coal with a diluent char and feeding the mixture into the fluidized-bed reactor section. Based on previous gasification studies with bituminous coals in process research and process development units, it is expected that caking

coals can be successfully processed in large diameter reactors that contain an adequate proportion of well-mixed devolatilized char that limits the agglomeration of coal and ensures uninterrupted operation of the reactor. Feeding a mixture of coal and char could also be interpreted as a simulation of supplying energy for the endothermic mild gasification reactions by char recycle.

In the PRU tests, preheated nitrogen was used as the fluidizing medium. The superficial gas velocity was maintained at about 4 ft/s in the fluidized section and about 16 ft/s in the entrained section. Data analysis from the successful PRU tests show that, in the temperature range of 1035° to 1390°F, Illinois No. 6 coal conversion ranged from 33% to 46%, resulting in 54% to 67% char, 14% to 29% oils/tar, and 7% to 19% fuel gas. The test data with the Illinois coal show that increasing the reaction temperature increased coal conversion with a decreasing char yield. The oils/tar yields appear to reach a maximum in the region of 1100° to 1200°F, while the gas yield increased steadily with increasing temperature, partially because of the increasing secondary thermal cracking reactions. From the limited data with West Virginia coal, it appears that the gas, oils/tars, and water yields were lower, and the char yield higher, than for the Illinois No. 6 coal. It is not known at this time whether the difference in particle size distribution may have played a role in the different results from the two coals, because of the difference in fluidization/entrainment behavior.

The highly aromatic oils and tars were characterized to estimate the light oil (<350°F), middle oil (350° to 590°F), heavy oil (590° to 750°F), and pitch (>750°F) fractions. The predominance of secondary reactions is also evident in explaining the effect of temperature on the distribution of oil fractions. It was determined that with an increasing mild gasification temperature, the pitch fraction decreased with a corresponding increase in light oils. There was no significant change in the yield of middle or heavy oils with temperature. With respect to the heteroatom content in the oils/tars, sulfur and nitrogen increased slightly with process temperature, while oxygen in the liquids decreased rapidly with increasing temperature. This indicates that deoxygenation reactions may play a role in the change in distribution of boiling-range fractions in the oils/tars. The aromaticity also increased with process temperature, as indicated by the decreasing atomic

H/C ratio in the condensables. Trends were similar for the two coals tested, although the West Virginia coal tests did not cover as wide a range of temperatures, and thus these conclusions can only be tentatively applied to that coal at present.

Characterization of the diluent-free char from the PRU tests showed a monotonically increasing ash content accompanied by a decrease in volatile matter content. The char volatile matter content was in the range of 7% to 12% compared to the 37% volatile matter content of the dry Illinois No. 6 coal. The decrease in volatile matter was approximately linear with respect to process temperature. Sulfur content in the char showed a very slight decrease with mild gasification temperature, and was approximately 33% lower than the sulfur content of the parent coal for Illinois No. 6 coal. For West Virginia coal, the sulfur content of the char was not significantly lower than that of the coal, but the trends in ash and volatile matter content were similar to those for the Illinois coal.

The fuel gas from mild gasification is rich in hydrogen and methane and also contains other light hydrocarbons, carbon oxides, and hydrogen sulfide. Increasing temperature reduces methane and increases hydrogen content, which are also attributable to the secondary cracking and reforming reactions.

Analysis of the fate of sulfur with an increasing reaction temperature showed that the sulfur content in both char and gases decreased while the sulfur content of oils and tars increased. In general for Illinois coal, the char retained 36% to 54% of the sulfur, oils and tars contained 9% to 15% of the sulfur, and the fuel gas contained 31% to 52% of the sulfur from the coal.

The implications of these observations and conclusions on process evaluation, scale-up and the marketability of the co-products will be analyzed and presented in subsequent project reports.

References Cited

1. Wootten, J. M., Nawaz, M., Duthie, R. G., Knight, R.A., Onischak, M., Babu, S. P. and Bair, W. G., "Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products," DOE Contract No. DE-AC21-87MC24266; Topical Report on Task 1, August 1988.
2. Scotti, L. J. et al., "Char Oil Energy Development Interim Report No. 5", Dept. of Energy Report No. FE-1212-5, August 1975.

3. Che, S. C. et al., "Flash Pyrolysis Coal Liquefaction Process Development", Final Report for July 1976 -- June 1978, Dept. of Energy Report No. FE-2244-26, 1978.
4. Tyler, R. J., "Flash Pyrolysis of Coals. Devolatilization of Bituminous Coals in a Small Fluidized Bed Reactor", Fuel, 59:4, 218-226, April 1980.
5. Solomon, P. R. and Colket, M. B., "Coal Devolatilization", Proc. of 17th Int'l Symp. on Combustion, Leeds, U.K., 131-143, 1979.
6. Suuberg, E. M. et al., "A Comparison of the Rapid Pyrolysis of a Lignite and a Bituminous Coal", ACS Div. of Petr. Chem. Preprints, 23:1, 175-182, 1978.
7. Knight, R. A., Koncar, G. J., Martin, K. A., Babu, S.P. and Chao, S. S. "Mild Gasification Studies with Illinois Coals", Annual Report to Center for Research on Sulfur in Coal (September 1988 -- August 1989), CRSC Subgrant Agreement No. 88-139, September 1989.
8. Khan, M. R., "Prediction of Sulphur Distribution in Products During Low Temperature Coal Pyrolysis and Gasification", Fuel 68:11, 1439-49, 1989.
9. McNeil, D., "High-Temperature Coal Tar", Chemistry of Coal Utilization, 2nd Suppl. Vol., Chap. 17, 1003-1082, 1981

7WP/61089-II/RPP

TASK 3. BENCH-SCALE UPGRADING STUDY

Objective

The overall objective of this program is to develop mild gasification technology and co-product utilization. The objective of Task 3, Bench-Scale Char Upgrading Study, was to investigate the necessary steps for upgrading the mild gasification char into potential high-market-value solid products. Recommendations of the Task 1 market survey section formed the basis for selecting three value-added solid products from mild gasification char: form coke, smokeless fuel, and activated adsorbent char.

Specifically, the objective of Task 3 was to evaluate the upgraded samples of the char products with standard bench-scale tests to determine and compare the properties and performance of the char products with comparable commercial products.

Introduction

The U.S. Department of Energy (DOE) is supporting the development of mild gasification technology to produce coal-derived fuels and chemical feedstocks. Mild gasification may be the most affordable route to increase coal utilization in the present economic climate. This technology uses operating conditions of 1000° to 1500°F, near-atmospheric pressure, and inexpensive reactants to convert coal to a slate of co-products.

Mild gasification could be considered an advanced low-temperature coal carbonization process. Low-temperature carbonization of coal was popular in the United States until natural gas became abundantly available, and it is still used on a commercial scale in some foreign countries; however, the old technology has been improved to produce value-added co-products through the application of technical and scientific knowledge about coal conversion that has been developed over the past twenty-five years. Improvements in reactor and process design are being applied to significantly enhance the yield and quality of co-products as well as the overall economics of the technology. Because of the mild operating conditions and process simplicity, mild gasification can use available materials of construction and conventional engineering design and construction practices. As a result, the capital and operating costs are expected to be low. In this context, by successfully developing and marketing the co-products to derive the value-added benefits, it should be possible to commercialize the technology within the next ten years.

With support of the U.S. DOE, a project team consisting of the Institute of Gas Technology, Peabody Holding Company, Inc., and Bechtel Group is developing a mild gasification process that uses a fluidized/entrained-bed reactor. This reactor is designed to process all types of coal over a wide range of particle sizes without oxidative pretreatment, and also without the use of oxygen or air as reactants. Process heat, in the conceptual commercial reactor, would be provided by recycled hot char or high-temperature fuel or flue gases derived from burning a portion of the process-derived fuel gases. The co-product streams consisting of char, fuel gas, water, and oils/ tars would be separated by conventional methods employing cyclones, staged condensers, and recycle-oil scrubbers.

An isothermal process research unit (PRU) has been built at IGT as shown schematically in Figure II-17. It consists of an electrically heated 8-inch-ID, 8-foot-long fluidized-bed section and a 4-inch-ID, 13-foot-long entrained flow section. Both sections are enclosed in clam-shell electrical heaters. The design coal feed capacity is 100 lb/h, and the coal can be fed either to the fluidized bed or the freeboard region above the fluidized bed and below the entrained section. The stainless steel reactor vessel is designed for operation at a maximum temperature and pressure of 1500°F and 50 psig, respectively. The reactor details have been presented earlier in this volume.

Project Approach

The mild gasification project consists of four major tasks:

- Task 1. Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment
- Task 2. Bench-Scale Mild Gasification Study
- Task 3. Bench-Scale Char Upgrading Study
- Task 4. System Integration Studies.

The approach to the development of an advanced mild gasification process was based, in Task 1 of this project, on a detailed literature survey and review of the state-of-the-art technology for coal conversion to readily saleable co-products. A market survey, conducted concurrently with the literature survey, identified the value-added priority end uses of the co-products. This information was used to determine the basis for design of the type of reactor, the process operating conditions, and the methods of co-products upgrading.

Figure II-17. ISOMETRIC OF PRU SYSTEM

The results of the above approach were presented in Volume I of this report. The objective of Task 2 of the project, Bench-Scale Mild Gasification, was to design, build, and operate an isothermal 1.2-ton/day (100-lb/h) process research unit (PRU) with slip stream sampling to determine process performance and to obtain design information for process scale-up. The objective of Task 3, Bench-Scale Char Upgrading, was to evaluate the performance of upgraded samples of potential high-market value solid products. In Task 4, System Integration Studies, a full-stream product gas condenser was designed, built, and operated to obtain the integrated PRU system performance data. Included in this task is the preparation of a process design, including material and energy balances, for a 24-ton/day adiabatic process development unit (PDU) to be erected at Southern Illinois University-Carbondale.

Summary of Potential Markets for Mild Gasification Char Co-Products

The Volume I report for Task 1 of this program identified several large potential markets for value-added mild gasification char co-products. These large markets are as follows:

- Metallurgical form coke (about 30×10^6 ton/yr)
- Smokeless fuel (about 50 to 100×10^6 ton/yr)
- Activated char (about 1 to 2×10^6 ton/yr).

The identification of these co-products was also guided by the technical considerations for the development of the mild gasification process and its integration with coal preparation technology. In addition, the impact of a wide variety of upstream solid processing steps and downstream processing steps were considered for the production of commercial quality liquid and solid co-products. As a result, the mild gasification process that evolved favored a minimum of processing steps.

Developmental work will be required to prepare commercially acceptable products identified from the mild gasification char. The mild gasification process along with downstream processing could be integrated with a coal preparation plant. The feed coals tested in this program came from the high moisture fines ($-1/4$ inch) stream from Peabody's coal preparation plants that normally mix these fines with the lump coal shipments.

The use of the mild gasification char co-product for the large steam or utility fuel market is technically possible, but because the char as a utility fuel may not have a significant value-added advantage, that market was not evaluated in detail at this time.

Form Coke

A form coke product from the mild gasification char has two sub-markets. The larger of the two markets for form coke is in blast furnace production of iron with a current annual consumption of about 27 million tons of coke per year. A smaller market of about 1.8 million tons per year exists for foundry coke used in cupolas for re-melting and alloying iron to make special steels. The cost of coke from various suppliers is currently about \$150 per ton.³ Consequently, a suitable form coke from mild gasification would present an excellent value-added product. In addition, the mild gasification process offers continuous form coke production with superior environmental control that is difficult and costly to achieve in existing coke oven batteries.

The existing coking plants in the United States are also aging, and environmentally acceptable methods to rapidly produce supplementary supplies of coke are urgently needed. The replacement coke could come from imports, although this source would not be assured as a long-term supply. The U.S. foundry industry is in a similar situation with lost coking capacity. An assured domestic supply of form coke from a continuous, environmentally safe process would have significant benefits for the steel and coal companies and the nation.

Form coke made from mild gasification char can meet the requirements for coke properties. In general, coke needs a strength sufficient to support the burden in the blast furnace and also has to provide a certain bulk porosity for gas, liquid metal, and flux flows. In addition to these properties, the coke must also meet a reactivity criterion based on its reaction with carbon dioxide, and its sulfur and ash contents should be low. Blast furnace coke is usually produced in the coke oven by selectively blending several coking coals, usually a high volatile and a low volatile coal, to make a strong structure with a desired reactivity. Mild gasification chars can be produced and blended in a similar manner with better control of the process conditions and emissions than attainable in coke ovens.

The properties of foundry coke differ from blast furnace coke, but the char from mild gasification could be processed to satisfy the required criteria. A higher porosity and reactivity are more important than strength in a cupola because the foundry coke is a source of both heat and carbon for transfer into the iron melt to make various steels. A form coke for foundry applications could also incorporate metallic fines such as silicon and manganese that are normally added in the cupola for alloying with the steel. This would enhance the value of foundry form coke significantly by providing a secondary benefit in improving cupola operations.

Smokeless Fuel

The low, yet ignitable volatile matter content of about 10% makes mild gasification char a suitable feedstock for producing briquettes of smokeless fuel. In the case of higher sulfur coals, limestone can be incorporated into the briquette to control the sulfur emissions during combustion. Domestically, the smokeless fuel could be used in place of firewood or, in some localities, anthracite coal. Figure II-18 compares the relative ranges of costs of various domestic fuels with the estimated cost of a smokeless fuel product. The smokeless fuel cost is comparable to that of anthracite coal. The heating value comparison of the solid fuels is given in Table II-42.

When calculated on a heating value basis, the domestic consumption of firewood would be equivalent to about 50 million tons of smokeless fuel. There is no current domestic use of smokeless fuel but demand could materialize if restrictions are imposed on the use of firewood for environmental protection. Additionally, the present export market for smokeless fuel could be significant. Countries with a shortage of firewood, anthracite, or natural gas are candidate markets. Another possible market is represented by countries with district heating central boilers. Korea has imported anthracite from the United States at a cost of about \$100 per ton, which includes about \$30 per ton for shipping. Smokeless fuel in the United Kingdom was recently being sold for \$170 per ton from the Rexco process. This market presents a good potential for a smokeless fuel co-product from mild gasification.

Activated Char

Mild gasification chars could be steam-treated to produce a low-cost activated char product in a powdered or granular form. Commercial adsorbent

WCTR302

¹ Priced competitively with anthracite depending on market conditions

Figure II-18. COMPARISON OF DOMESTIC FUELS

Table II-42. HEATING VALUE COMPARISON OF SMOKELESS FUEL
WITH SOLID FUELS

	Heating Value (million Btu/ton)
Wood (15% moisture)	14.6
Utility Bituminous Coal	21.1
Anthracite	21.6
Charcoal Briquettes	30.0
Smokeless Fuel With Limestone	20.0

carbons are made from a variety of carbonaceous materials, including coal, and sell for up to \$2000 per ton. Powdered adsorbent forms are generally mixed directly with a contaminated liquid streams for purification; the granular forms are used in packed-bed applications. Currently, major uses of activated carbon include treatment of effluent streams in the paper and pulp industry and treatment of refinery activated sludge. The demand for activated carbon will increase if stricter clean water standards are imposed, and with the probable appearance of natural gas-fueled urban vehicles, which would use active carbon for fuel storage. The market size is small at present, but with stricter water standards or other events and a competitively priced absorbent carbon, the demand could increase suddenly. A mild gasification process could provide a potentially lower-cost activated char for these applications.

Char Upgrading Studies

Form Coke

The suitability of the granular char from the mild gasification process to be made into form coke was investigated in two bench-scale briquetting studies followed by a pilot-scale production of pillow-shaped briquettes. The investigation was limited to the production of briquettes using only coal as the source of the binder material rather than the higher market-value pitch co-product. First, small 1-inch-diameter by 3/8-inch-thick briquettes were made with the mild gasification chars and tested for strength and coke reactivity. Several 3-inch diameter by 1-inch thick briquettes were then made in a larger mold, focusing on the best conditions to produce a strong briquette. Lastly, a large quantity of 1 by 1.75-inch pillow briquettes were made at a rate of one ton per hour with equipment at a test facility of a manufacturer of roll briquetting equipment.

The first test briquettes were made in a one-inch diameter cylindrical mold with chars from the 8-inch-ID mild gasification process research unit (PRU) tests performed in Task 2 of this program. The chars from Illinois No. 6 coal in PRU Tests MG-9 and MG-17 were mixed in a 1:1 weight ratio with the parent coal and pressed in a one-inch diameter mold at 1000°F. Two briquetting pressures, 4,000 and 10,000 psi, were selected to produce the approximately 3/8-inch-thick briquettes. The briquettes were removed from the mold and calcined in an oven under nitrogen up to 1800°F to remove the remaining volatile matter and complete the form coke briquetting process. To test the physical strength of these briquettes, a diametral compression test apparatus was used. The test actually measures the tensile strength up to fracture. The tensile strength tests were conducted on an Instron (Model 101) compression-tension measuring machine following the procedure of ASTM Test B-485-76.

The range of values of the measured tensile strengths of the various briquettes that were made under various conditions are shown in Figure II-19, along with the value measured on a similar sized sample of metallurgical coke obtained from Inland Steel Company and literature values for commercial metallurgical coke and foundry coke. As indicated in Figure II-19, the initial briquettes that were made under non-optimized conditions do approach the values for commercial cokes. With optimization of the steps in the briquetting process, it is expected that mild gasification char can be briquetted using coal as a binder material to meet the required physical strength.

In addition to the physical strength, another property of coke important to blast furnace operation is its reactivity value. The reaction rate of the carbon in the coke with the carbon dioxide present in the blast furnace gases is directly related to the iron production rate, because this reaction generates the reductant carbon monoxide. This reactivity value was measured with a briquette made from the mild gasification char using the West Virginia coal. A reactivity test procedure obtained from the Bethlehem Steel Company⁴ specifies grinding the coke to 18 x 40 mesh and placing a weighed sample in a quartz tube. The sample is heated to 1825°F under nitrogen and then the nitrogen is replaced with carbon dioxide and held at temperature for 2 hours. The percent weight loss of the coke after 2 hours is correlated with acceptable blast furnace performance.

<u>SAMPLE NO.</u>	<u>DESCRIPTION</u>	<u>BRIQUETTING PRESSURE (PSI)</u>
1	COMMERCIAL COKE A	---
2	COMMERCIAL COKE B	---
3	FOUNDRIY COKE	---
4	INLAND STEEL COKE SAMPLE	---
5	HOT BRIQUETTE (-6 MESH MG-9 CHAR)	4000
6	HOT BRIQUETTE (-6 MESH MG-9 CHAR)	10000
7	HOT BRIQUETTE (20x60 MESH MG-17 CHAR)	4000
8	HOT BRIQUETTE (20x60 MESH MG-17 CHAR)	10000
9	HOT BRIQUETTE (-20 MESH MG-9 CHAR)	4000

COKE STR

Figure II-19. DIAMETRAL COMPRESSION TESTS FOR TENSILE STRENGTH

This procedure was applied and was calibrated with a coke sample obtained from Inland Steel Company that was known as a low-reactivity coke. The resulting value is plotted in Figure II-20, which also shows the ranges of industry-accepted low, medium, and high reactivity coke values. The test briquette made with the West Virginia char yielded a medium reactivity value. Current practice of coke production involves blending different coals to achieve the required coke properties and thus, coke reactivity values could be adjusted by blending different coals.

Tailoring of the properties of the form coke briquettes will be an important feature of any candidate char-producing and briquetting process. The major factors that affect both the strength and reactivity of form coke are the density, porosity, voidage, and the type of metallurgical coal or coals. Foundry coke for iron and steel remelting, for example, requires different properties than blast furnace coke. Foundry coke has to be a source of heat for melting iron and also a source of carbon for solution into the iron. Consequently, the rate of reaction with carbon dioxide is not as important as in blast furnaces. Blending of fine particles of alloying materials into the foundry coke would increase its value. In another application, coke for rock wool cupola melting is required to be strong to support its burden, but the coke combustion rate, with minimum generation of fines, controls the production rate of the melt, which is spun into fibers.

To make practical sizes of form coke for proof-of-concept testing, a 3-inch diameter mold was machined to make larger briquettes from the West Virginia char. A hydraulic press with heated platens was used to apply the heat and force to the mold. Slight variations to the procedure of heating up to 1000°F, holding at temperature to allow volatiles to leave, and pressing the hot char-coal mixture were practiced until conditions were found to make a strong, dense briquette. The critical step that was identified was the time required for a portion of the volatilized products from the binder coal to leave. If the products do not leave, then the briquette will expand too much upon subsequent calcination. Also, compaction pressures of only about 1000 psi were found to be sufficient for this hot, partially devolatilized plastic mixture. Compression values up to or greater than 20,000 psi have been indicated in some briquetting operations but may not be necessary. The 3-inch briquettes were as strong as the Inland Steel Company sample, and the

● BETHLEHEM CO₂ REACTIVITY TEST CONDUCTED ON FORM
COKE MADE FROM WV CHAR CALCINED AT 1800°F

▲ COMPARATIVE TEST CONDUCTED WITH COKE
SAMPLE OBTAINED FROM INLAND STEEL

A8007104P

Figure II-20. FORM COKE REACTIVITY TESTS

briquette density was measured as approximately 65 lb/cubic foot, which is comparable to the density measured for the Inland Steel Company coke sample, 62 lb/cubic foot.

With the experience of making the test briquettes, arrangements were made for the production of a large quantity of form coke briquettes from approximate 700 pounds of West Virginia char that was available from the longer-duration mild gasification tests conducted in Task 4 of the program. The char, when blended with about 700 pounds of West Virginia coal, could provide about 1000 pounds of calcined briquettes.

A manufacturer of roll briquetting equipment with a hot briquetting test system that could make pillow briquettes at a rate of about one ton per hour was located. A schematic of the equipment, which is located at K. R. Komarek Research in Anniston, AL, is shown in Figure II-21. The pre-mixed char and coal were fed to the buffer hopper, and then pneumatically conveyed up the flash dryer-heater section to the cyclone and fed directly to the roll briquetting press. The roll briquetting press had dies to make 1- by 1.75-inch pillow briquettes.

Prior to the operation of the briquetting test unit, several batch briquetting tests were conducted in other similar roll briquetting machines to identify settings for the required roll compaction pressure and the feed rate to the rolls. One variation of the coal-to-char mix ratio, from 1:1 to 0.75:1 by weight coal to char, was investigated. The ratio with less coal seemed to produce an equally strong briquette, but available time precluded more detailed investigation of the mix ratio. The mixtures could only be batch-heated in an oven to about 400°F in these preliminary trials, but briquettes of good green strength were produced that survived a six-foot drop test intact. Although the mixture temperature was below the approximately 900°F that is required to release volatile matter for maximum briquette compaction and strength, these tests scoped out the operating parameters for the roll briquetting system shown in Figure II-21.

After the operating parameters were defined, the 700 pounds of West Virginia char was mixed with 700 pounds of the coal to begin feeding to the hot briquetting system. However, the test system heater could only achieve a mixture temperature of about 550°F at the entrance to the rolls because of excessive heat losses. Efforts to increase the temperature were not success-

Figure II-21. SCHEMATIC PROCESS FLOW DIAGRAM OF HOT BRIQUETTING INSTALLATION

ful, and about 600 pounds of briquettes were made before the operation was stopped. A screw conveyor used in the equipment to transport the briquettes to the receiving box broke about one-third of the briquettes in half. A screen belt conveyor would be the preferred conveyor for the briquettes.

About 200 of these pillow briquettes were heated to 1000°F to release the volatile matter in the coal binder. The temperature was then raised to 1800°F to complete the calcination. Because the volatiles were not released prior to briquetting, the briquettes expanded, nearly doubling their volume. The measured density of the briquettes was 22.5 lbs/cubic foot, which is about one-third of that of the good 3-inch briquettes. The pillow briquettes did not fracture in a six-foot drop test, and showed a 3% weight attrition in an ASTM-D-3038-83 drop shatter test for coke. However, about 75% of the briquettes crumbled in a ASTM D-3402-81 tumbler test for coke which tumbles the coke for 1400 revolutions.

Measurement of the carbon dioxide reactivity of the calcined briquettes indicated a 40% weight loss in the Bethlehem Steel coke reactivity procedure, which places the briquettes near the high reactivity range of coke values on Figure II-20. The low density and high porosity of the calcined pillow briquettes contributed to an increase in the weight loss as measured by the two-hour carbon dioxide reaction test.

These studies have shown that the crucial step in the briquetting process for form coke production is the char and coal mixing step at a temperature from 800 to 1000°F, depending on the time required for the release of a portion of the volatile matter, and not the actual briquette formation in the rolls. The single 3-inch-diameter briquettes were made in a near-optimum way and were as strong as the coke sample from Inland Steel. However, where this strength level is not required, such as in smokeless fuel briquettes, the key step would involve blending of additives to control the release of sulfur and assurance of a minimal volatile matter content for ignitability.

Smokeless Fuel

The bench-scale tests to evaluate the production of smokeless fuel involved preparation of briquettes from mixtures of Illinois No. 6 coal char, limestone, and about 12% pitch. Binderless briquetting could also be performed without pitch addition. The briquettes were made in the one-inch

diameter mold under briquetting pressures of 4000 and 10,000 psi. Pitch was used for these briquettes as an expedient procedure to make the smokeless fuel samples. Two different limestones were used, a pure grade of limestone and a dolomitic limestone. The analyses of these additives are shown in Table II-43. These were added to the char mixture to provide a calcium-to-sulfur molar ratio of 2:1 in the briquettes. The briquettes were then subjected to a low temperature curing step at 400°F to polymerize and harden the binder.

Table II-43. ANALYSES OF LIMESTONES USED IN SMOKELESS FUEL BRIQUETTES

<u>Component, wt%</u>	<u>Pure Limestone</u>	<u>Dolomitic Limestone</u>
Calcium	39.1	34.0
Magnesium	0.55	3.7
Potassium	0.5	0.33
Iron	0.09	0.16
Aluminum	0.05	<0.1
Silicon	0.1	0.78
Strontium	0.016	0.021
Carbon Dioxide	44.6	43.5
Oxygen (by difference)	<u>14.994</u>	<u>17.409</u>
Total	100.000	100.000

In the combustion tests, the briquettes were stacked in a small pile and combusted in a muffle furnace at about 1560°F. The 10 to 15% volatile matter content of the char was sufficient for ignition and combustion of the briquettes. The ash residues from the top of the pile and from the center of the pile were analyzed for calcium sulfate and other sulfur forms to assess sulfur retention. The test results show that the two limestones retained nearly the same quantity of sulfur in this simple combustion test.

Figure II-22 shows the various sulfur forms and retention levels before and after combustion with 84 and 88% of the sulfur being captured from the center and top of the pile, respectively. Of the sulfur retained, 99% is in the form of calcium sulfate, which is suitable as a non-leachable landfill material.

The heating values of the smokeless fuel briquettes from Illinois No. 6 coal-derived char with limestone were compared in Table II-42 in the previous section with the heating value of other possible solid fuels. It is apparent

FORM

Figure II-22. SULFUR FORMS IN COMBUSTED SMOKELESS FUEL

that the heating value of smokeless fuel from mild gasification char compares favorably with the heating values of common domestic heating fuels.

Activated Char

The potential for producing a low-cost activated adsorbent char was explored by steam-treating a number of mild gasification char samples from Illinois No. 6 coal and measuring their physical and adsorbent properties. The mild gasification char was produced in the 8-inch-ID process research unit (PRU) and also in a 2-inch-ID laboratory-scale reactor. The char activation was accomplished in a separate 2-inch-ID activation reactor. The chars were activated using steam for varying periods of time to determine the effects of the extent of activation on the resulting char properties and performance.

Char Sample Preparation Procedure

Because the mild gasification char samples from the PRU contained a portion of the coke breeze diluent used in the feed, a 2-inch-ID fluidized bed reactor as shown in Figure II-23 was constructed to prepare the char samples used for the adsorbent char studies. The following procedure was used to prepare the char to simulate the mild gasification PRU. Approximately 200 grams of coal was loaded into the feed hopper which was fed to the reactor fluidized with nitrogen. When the reactor achieved 1200°F, the entire contents of the feed hopper was fed to the reactor and fluidized for 15 minutes to simulate the residence time in the PRU. The resulting char was transferred into the char collection hopper.

The 2-inch-ID reactor has a slanting gas distribution cone. A high center-jet velocity is maintained to maximize agitation to prevent agglomeration and de-fluidization with the caking Illinois No. 6 coal. However, agglomeration occurred in the operation of this unit with 100% coal feed, as expected. For the purpose of this task to study the upgrading of the char, the coal was subjected to a light air-oxidation treatment at 300°F prior to mild gasification. This reduced the agglomeration in the reactor so that char samples could be produced for further tests.

Char Activation Procedure

The fluidized-bed steam-treatment apparatus used to activate the char samples is shown in Figure II-24. The activation temperature of 1560°F was chosen based on work by Klose and Born⁵ who found that iodine adsorption

Figure II-23. SCHEMATIC DIAGRAM OF THE 2-INCH-ID FLUIDIZED-BED REACTOR

Figure II-24. SCHEMATIC DIAGRAM OF THE FLUIDIZED-BED STEAM TREATMENT APPARATUS

numbers of activated carbons peak at an activation temperature of about 1470°F, while surface areas peak at a higher activation temperature of about 1650°F. The activation temperature of 1560°F was selected as a midway point. The char activation procedure involved placing about 100 grams of char in the reactor and heating it to temperature under a purge flow of nitrogen. A flow of nitrogen and steam sufficient to fluidize the char was then maintained for different periods ranging from 45 to 240 minutes for varying degrees of carbon conversion.

Adsorbent Characterization Methods

The performance of an activated carbon depends upon a number of different parameters which include surface area, hardness, pH, apparent density, particle size, pore size distribution, adsorptive capacity of standard chemicals, and kinetic/mass transfer coefficients. Table II-44 lists the tests and methods used to analyze selected activated char properties. ASTM standard methods were used whenever applicable to characterize the char. There is no ASTM method to characterize extractable material from the activated carbon, so the standard extraction procedure (EP) was used.

Table II-44. STANDARD TESTS FOR ACTIVATED CARBON

<u>Property</u>	<u>ASTM Test Method</u>
Char, Ash, Sulfur	D 3172-73, D 3176-84
Apparent Density	D 2854-70
Hardness	D 3807-79
Iodine Number	D 4607-86
pH	D 3838-80
Particle Size Distribution	D 2862-70
EP Toxicity	N/A

The surface area and porosity of the adsorbents were determined using the standard BET method with a Micrometric Model 2100 D surface area and pore-volume analyzer. This test equipment uses both nitrogen and mercury to measure the range of pore diameters from 10 to over 200 Angstroms.

Adsorption isotherms were measured with a procedure of washing, drying, and grinding the chars before contacting various amounts of char from 0.01 to

2 grams with a solution of 3,5-dichlorophenol (DCP) or 3,5-dimethylphenol (DMP) for a period of six hours. The char was then separated by filtration and the concentration of the solutions were determined by a UV absorption apparatus.

For batch kinetic tests measuring adsorption rates, similar quantities of char were placed in the solutions and stirred. Solution samples were periodically withdrawn and the concentrations were measured with the UV absorption apparatus. The solutions of DCP and DMP were chosen to represent phenols in wastewater from many types of industrial plants. In these tests, an activated carbon was purchased from Calgon Company (Type OL bituminous coal based) and tested for comparison to the char samples.

Discussion of Test Results

The objective of these tests was to investigate the method of producing an adsorbent from mild gasification char that has the maximum adsorptive capacity, as determined by iodine adsorption and surface area values, with the minimum amount of activation in terms of carbon burnoff. Once the optimum activation procedure was identified, a larger batch of char was prepared for the selected adsorbent performance tests. A number of evaluation tests were first conducted with the mild gasification chars from the PRU and from the 2-inch reactor to determine the optimum activation conditions before specific performance tests were made. Table II-45 lists the test char samples and resulting search data.

The first two tests listed in Table II-45 used char from PRU Test MG-6. In Test 1-23A the char was steam-treated at 1652°F and in Test 1-28 the treatment temperature was 1562°F. The iodine adsorption numbers measured for these activated chars, each with a similar degree of carbon burnoff, were 525 and 596, respectively. Commercial grade adsorbents are expected to achieve iodine numbers up to about 1000. The next two tests were conducted with char from PRU Test MG-9. The carbon burnoff amounts achieved in Tests 1-40 and 1-45 were different and iodine numbers of 464 and 348 were measured for the MG-9 char with 47 and 30 percent carbon burnoff, respectively. One difference between the MG-9 char and the MG-6 char was that the MG-9 char had a lower carbon content and a higher ash content than the MG-6 char, resulting from a greater degree of conversion in the PRU.

Table II-45, Part 1. SUMMARY OF RESULTS FROM CHAR ACTIVATION
AND ADSORPTION TESTS

Test Number	1-23A	1-28	1-40	1-45
Char Source	MG-6	MG-6	MG-9	MG-9
Feed Char Composition (Dry), wt %				
Carbon	68.30	68.30	62.93	62.93
Sulfur	2.67	2.67	3.53	3.53
Ash	21.64	21.64	28.46	28.46
Activation Temperature, °F	1650	1560	1560	1560
Duration of Activation, min	60	100	150	127
Activation Gas Composition, vol %				
Nitrogen	71.7	71.8	79.7	79.7
Steam	28.3	28.2	20.3	20.3
Percent Carbon Burn-Off	43	40	47	30
Activated Char Properties				
Ultimate Analysis, wt %				
Ash	ND	31.24	ND	ND
Carbon	ND	63.83	ND	ND
Hydrogen	ND	0.38	ND	ND
Nitrogen	ND	1.06	ND	ND
Sulfur	ND	1.69	ND	ND
Oxygen	ND	1.80	ND	ND
Ball Pan Hardness Number	52.2	51.1	46.1	--
Apparent Density, g/ml	0.27	0.27	0.32	0.29
Sieve Analysis, mesh				
+6	--	--	--	--
-6+12	13.3	ND	22.82	ND
-12+20	29.4	ND	15.72	ND
-20+40	32.8	ND	14.28	ND
-40+60	19.8	ND	18.74	ND
-60+80	3.2	ND	18.81	ND
-80	1.6	ND	9.81	ND
Surface Area, m ² /g	--	563	--	--
Iodine Number	525	597	464	348

ND = Not determined.

Table II-45, Part 2. SUMMARY OF RESULTS FROM CHAR ACTIVATION
AND ADSORPTION TESTS

Test Number	<u>1-50A</u>	<u>2-11</u>	<u>2-29A</u>	<u>2-29B</u>
Char Source	P-1A	P-1B	P-2	P-2
Feed Char Composition (Dry), wt %				
Carbon	70.20	61.53	73.52	73.52
Sulfur	2.87	2.88	2.38	2.38
Ash	22.06	28.99	17.89	17.89
Activation Temperature, °F	1560	1560	1560	1560
Duration of Activation, min	120	120	45	90
Activation Gas Composition, vol %				
Nitrogen	74.2	76.5	63.6	63.4
Steam	25.8	23.5	36.4	36.6
Percent Carbon Burn-Off	58	41	21	40
Activated Char Properties				
Ultimate Analysis, wt %				
Ash	31.62	ND	23.15	28.68
Carbon	64.15	ND	72.17	66.91
Hydrogen	0.32	ND	0.37	0.34
Nitrogen	1.07	ND	1.43	1.18
Sulfur	1.59	ND	2.23	1.95
Oxygen	1.26	ND	0.65	0.94
Ball Pan Hardness Number	88.1	45.6	--	--
Apparent Density, g/ml	0.43	0.25	--	--
Sieve Analysis, mesh				
+6	--	--	--	--
-6+12	2.06	--	--	--
-12+20	10.89	36.57	20.6	20.59
-20+40	38.94	36.87	40.46	42.36
-40+60	35.80	19.63	26.90	26.95
-60+80	8.19	4.66	8.21	6.49
-80	4.12	2.27	3.83	3.61
Surface Area, m ² /g	825	--	611	8.15
Iodine Number	804	537	602	782

ND = Not determined.

Table II-45, Part 3. SUMMARY OF RESULTS FROM CHAR ACTIVATION
AND ADSORPTION TESTS

Test Number	2-29C	2-30A	2-40A
Char Source	P-2	P-2	P-2
Feed Char Composition (Dry), wt %			
Carbon	73.52	73.52	73.52
Sulfur	2.38	2.38	2.38
Ash	17.89	17.89	17.89
Activation Temperature, °F	1560	1560	1560
Duration of Activation, min	135	180	95
Activation Gas Composition, vol %			
Nitrogen	63.0	64.2	65.1
Steam	37.0	35.8	34.9
Percent Carbon Burn-Off	58	71	43
Activated Char Properties			
Ultimate Analysis, wt %			
Ash	36.99	45.62	23.61
Carbon	59.67	52.16	71.24
Hydrogen	0.23	0.29	0.31
Nitrogen	0.87	0.87	1.16
Sulfur	1.71	1.22	1.56
Oxygen	0.53	0	2.12
Ball Pan Hardness Number	--	--	75.9
Apparent Density, g/ml	--	--	0.47
Sieve Analysis, mesh			
+6	--	--	--
-6+12	--	--	--
-12+20	19.78	13.58	27.42
-20+40	40.14	40.55	41.07
-40+60	28.50	32.14	23.65
-60+80	7.60	8.75	5.78
-80	3.98	4.98	2.08
Surface Area, m ² /g	1000	1070	8.53
Iodine Number	832	896	763

The remainder of the test chars in Table II-45 were prepared in the 2-inch reactor after a minimum air-oxidation pretreatment step and steam treated at 1562°F for different lengths of time. The char for Test 1-50a was air-oxidized overnight at 300 °F for a greater degree of pre-treatment. The resulting activated char in Test 1-50a shows a high iodine number but also a high carbon burnoff value compared to the other test chars. The char in Test 2-29c was made from a less oxidized coal with a similar carbon burnoff level. It resulted in an iodine number similar to that of the highly pretreated coal used in Test 1-50a, but a lower surface area value than that of the more oxidized coal. An air oxidation pretreatment of caking coals is not desired for mild gasification, as the liquid yields are adversely affected. It is employed here as an experimental expedient for the preparation of controlled property chars.

The char in Test 2-11 was prepared from non-oxidized Illinois No. 6 coal. The batch of Illinois No. 6 coal without air oxidation that was fed to the 2-inch reactor sintered into one mass in the reactor. This mass was removed and ground and then steam activated at 1562°F. Its iodine number is comparable to those of the chars obtained from the PRU although it was not produced under the same fluidized-bed conditions.

The difference due to air oxidation pretreatment of the coal was assessed with a Fisher assay of the liquids from the oxidized and non-oxidized coal samples. The values in Table II-46 show the expected differences due to air oxidation. However, the char properties for steam activation should not be significantly affected.

Iodine Numbers and Surface Area of Chars

The measured values of the iodine adsorption numbers and the surface areas of the prepared chars listed in Table II-46 are presented in Figure II-25. The reported values of a commercial adsorbent from Calgon Company and a typical bituminous coal-based adsorbent are included in the figure. The chars in this study compare favorably with the commercial adsorbents. The effect of steam activation on the iodine number and surface area of the chars is illustrated in Figure II-26. Both the iodine number and the surface area increase with the activation time but the iodine number does not increase at the same rate as the surface area. This is probably due to increase in diameter of the small pores which contribute to the surface area

Table II-46. FISCHER ASSAY OF ILLINOIS NO. 6 COAL USED
IN ADSORBENT STUDIES

<u>Assay, wt %</u>	<u>Un-oxidized Coal as Char No. 1-50b</u>	<u>Oxidized As Char No. 2-28</u>	<u>Oxidized Overnight as Char No. 1-49</u>
Oil	15.1	9.6	1.6
Water	4.6	7.2	6.8
Residue	73.9	75.2	80.0
Gas + loss	<u>6.4</u>	<u>8.0</u>	<u>11.6</u>
Total	100.0	100.0	100.0
Oil Yield (gal/ton)	34.6	21.4	3.8
Water Yield (gal/ton)	11.0	17.3	16.2
Specific Gravity Oil at 60/60°F	1.046	1.068	1.023
API Gravity of Oil at 60°F	3.8	1.0	6.8

but not the overall iodine uptake. This difference in rate is depicted in the plot in Figure II-27 which shows the iodine number and surface area increasing with the carbon burnoff levels up to about 70%.

As the iodine numbers and surface area continue to increase with the increasing amount of carbon burnoff, there will be smaller amounts of carbon structure available for adsorptive capacity. Hence, the results were normalized by reporting the iodine uptake and the surface area per unit weight of char used in the activation. The iodine uptake and the surface area per gram of feed char is illustrated in Figure II-28 as a function of carbon burnoff amount. It is seen that the net adsorptive values reach a maximum at 40% carbon burnoff.

Pore Size Distribution

The pore size distribution is important in adsorbents because it is related to the amount of surface area available for adsorbates of a specific size range. The pore size distributions of the micropores were determined for four selected chars in this study by the standard BET nitrogen adsorption isotherms. The adsorption isotherm of the Calgon commercial adsorbent was also evaluated. Figure II-29 shows the commercial adsorbent to have a fairly even distribution of pores in the range of 10 to 500 Angstroms. The chars

SAMPLE NO.	DESCRIPTION
1	TYPICAL COMMERCIAL BITUMINOUS-BASED CARBON
2	CALGON TYPE OL
3	MG-6 CHAR - 100 MIN ACTIVATION
4	ILLINOIS NO. 6 CHAR - 45 MIN ACTIVATION
5	ILLINOIS NO. 6 CHAR - 90 MIN ACTIVATION
6	ILLINOIS NO. 6 CHAR - 95 MIN ACTIVATION
7	ILLINOIS NO. 6 CHAR - 135 MIN ACTIVATION
8	ILLINOIS NO. 6 CHAR - 180 MIN ACTIVATION
9	OXIDIZED ILLINOIS NO. 6 - 120 MIN ACTIVATION

SACIN

Figure II-25. SURFACE AREA AND IODINE NUMBERS OF ACTIVATED CARBONS

Figure II-26. SURFACE AREA AND IODINE NUMBERS AS A FUNCTION OF ACTIVATION TIME

Figure II-27. ADSORPTION PROPERTIES OF CHAR VERSUS CARBON BURN-OFF

• Adjusted to one gram of the original feed char.

Figure II-28. CHAR ADSORPTION OPTIMIZATION FOR IODINE NUMBER AND SURFACE AREA

Figure II-29. MICROPORE DISTRIBUTION OF SELECTED ACTIVATED CHARS AND CARBONS

have a concentration of pores in the size range of 10 to 60 Angstroms. Increasing the extent of steam treatment increases the micropore volume and the percentage of larger pores as would be expected. For the adsorption of color bodies in effluent streams and high molecular weight organic materials, pores in the range of 20 to 500 Angstroms are considered to be best suited. Odor and low molecular weight organic species are best adsorbed with pores under 30 Angstroms in diameter. It appears that the chars may be well-suited for adsorption of low-molecular-weight organics.

Adsorption Performance With DCP and DMP

The char denoted 2-40a in Table II-46 and the Calgon Type OL carbon were evaluated for the uptake of DCP and DMP. The characteristics of the sample char and the commercial adsorbent used in these tests are summarized in Table II-47. The adsorption isotherm results are presented in Figures II-30 and II-31 for DCP and DMP adsorption, respectively.

Table II-47. ADSORBENTS COMPARED IN DCP AND DMP ISOTHERM TESTS

<u>Adsorbent</u>	<u>Raw Material Source</u>	<u>Iodine Number</u>	<u>Surface Area, (m²/g)</u>	<u>USS Mesh</u>
Char 2-40a	Illinois No. 6	763	853	20 x 50
Calgon Type OL	Bituminous Coal	1050	1100	20 x 60

Each carbon adsorbent showed similar isotherm slopes for DMP adsorption and the low slope of these lines indicate that the carbon adsorbents react similarly to changes in adsorbate concentrations. The DCP isotherm lines look quite different. At high concentrations, the Calgon adsorbent showed an equilibrium capacity for DCP about 1.5 times that of the char adsorbent. At lower concentrations of the adsorbate, the char adsorption capacity for DCP decreases significantly compared to the Calgon adsorbent. Depending on the adsorbate concentration, the Calgon adsorbent has an equilibrium concentration from 1.5 to 7.5 times the char adsorbent.

Single-solute batch kinetic tests were also conducted with both char and the Calgon activated carbon for both DCP and DMP adsorption. The measured uptake of these organic species versus time is shown in Figures II-32 and II-33. The char and the Calgon activated carbon behaved similarly in terms of the rate of uptake of both the DCP and DMP species with the rates leveling off

Figure II-30. 3,5-DICHLOROPHENOL ISOTHERMS

Figure II-31. 3,5-DIMETHYLPHENOL ISOTHERMS

Figure II-32. 3,5-DICHLOROPHENOL ADSORPTION RATES

Figure II-33. 3,5-DIMETHYLPHENOL ADSORPTION RATES

after about 60 minutes. The char showed a higher uptake rate initially than did the Calgon adsorbent and overall a lower quantity adsorbed as measured in the equilibrium isotherms.

Conclusions

The three solid co-products made from mild gasification char with high value-added benefits were evaluated in Task 3 of this program. These co-products are a metallurgical form coke, an adsorbent char carbon, and a smokeless fuel.

The formation and testing for the form coke co-product involved an evaluation of its briquette strength and reactivity. An amount of coal equal to that of the char was used as the binder for form coke briquettes. The measured tensile strength and reactivity of the form coke sample briquettes were in the range of commercial coke, and development tests on a larger scale are recommended. The reaction rate of the form coke carbon with carbon dioxide at 1825°F was measured using the standard procedure specified by Bethlehem Steel Company. Various other tests and specifications have to be met to assess the potential success of form coke from mild gasification char, but the initial results are encouraging.

Three-inch-diameter briquettes were successfully made with their density and strength equal to a coke sample obtained from a steel company. About 1000 pounds of form coke were produced, using char from Task 4 PRU tests, in hot briquetting equipment at the research facility of a roll briquetting equipment manufacturer. However, the coal and char mixture temperature in the equipment could not be brought to the necessary value and, consequently, the briquettes were not of optimum strength after calcination due to expansion. Briquetting process variables need to be defined for each coal type and char product to tailor the processing to optimize physical and chemical properties necessary for form coke, foundry coke, or smokeless fuel.

A smokeless fuel briquette with limestone added to control sulfur can be made from mild gasification char in a simple manner. Test results have shown that briquettes with limestone have a heating value comparable to other solid fuels and the limestone can retain up to 88% of the sulfur during combustion in a simple bench-scale combustion test, almost all of it as a stable calcium sulfate. The production of smokeless fuel from mild gasification char,

particularly from high sulfur coals, is recommended for further development both for indigenous and export markets.

Adsorbent char carbon from mild gasification represents another potential co-product with a high probability of technical acceptance and a probable lower production cost compared to present commercial adsorbents. Char samples were prepared with a standard steam activation procedure and tested for a variety of pertinent property and performance values. These were compared with a commercially available adsorbent. After identifying optimum activation levels, we found that the mild gasification chars performed well. Such adsorbents may be better suited for use in some areas, such as the adsorption of low-molecular-weight substances, because of the smaller pore sizes measured in the char.

References Cited

1. Wootten, J. M., Duthie, R. G., Nawaz, M., Knight, R. A., Onischak, M., Babu, S. P. and Bair, W. G., "Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products, Topical Report for Task 1, Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment," for U.S. DOE Contract No. DE-AC21-87MC24266, August 1988.
2. Wootten, J. M., Duthie, R. G., Knight, R. A., Gissy, J. L., Onischak, M. and Babu, S. P., "Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products, Topical Report for Task 2, Mild Gasification Technology Development, Process Research Unit Tests Using Slipstream Sampling," for U.S. DOE Contract No. DE-AC21-87MC24266, May 1990.
3. Private communication, Weirton Steel Corporation, 1990.
4. Private communication, Bethlehem Steel Company, 1989.
5. Klose, E. and Born, M., "Partial Gasification of Lignite Coke with Steam in a Rotary Kiln for Activated Carbon Production," Fuel, 64:1313-1316, 1985.

19WP/RPP/61089-IIb

TASKS 4.1 TO 4.6. SYSTEM INTEGRATION STUDIES

Objective

The overall objective of this program is to develop mild gasification technology and co-product utilization with all types of coal. The objective of Task 4, System Integration Studies, is to obtain test data and develop the design information necessary for the scale-up of the IGT mild gasification process to an adiabatic PDU.

Introduction

The U.S. DOE is supporting the development of mild gasification technology to produce coal-derived fuels and chemical feedstocks. Mild gasification may be the most affordable route to increase coal utilization in the present economic climate. This technology uses operating conditions of 1000° to 1500°F, near-atmospheric pressure, and inexpensive reactants to convert coal to a slate of co-products.

Mild gasification could be considered an advanced low-temperature coal carbonization process. Low-temperature carbonization of coal was popular in the U.S. until natural gas became abundantly available, and it is still used on a commercial scale in some foreign countries. However, the old technology has been improved to produce value-added co-products through the application of technical and scientific knowledge about coal conversion that has been developed over the past 25 years. Improvements in reactor and process design are being applied to significantly enhance the yield and quality of co-products as well as the overall economics of the technology. Because of the mild operating conditions and process simplicity, mild gasification can use available materials of construction and conventional engineering design and construction practices. As a result, the capital and operating costs are expected to be low. In this context, by successfully developing and marketing the co-products to derive the value-added benefits, it should be possible to commercialize the technology within the next 10 years.

With support of the U.S. DOE, a project team consisting of IGT, Peabody Holding Company, Inc., and Bechtel Group is developing a mild gasification process which uses a fluidized/entrained-bed reactor. This reactor is designed to process caking bituminous coals over a wide range of particle sizes without oxidative pretreatment, and also without the use of oxygen or

air as reactants. Process heat, in the conceptual commercial reactor, would be provided by recycled hot char and/or by high-temperature flue gases derived from burning a portion of the process-derived fuel gases. The co-product streams, consisting of char, fuel gas, water, and oils/tars, would be separated by conventional methods employing cyclones, staged condensers, and recycle-oil scrubbers.

An isothermal PRU has been built at IGT. The PRU is shown schematically in Figures II-34 and II-35. It consists of an electrically heated 8-inch-ID, 8-foot-long fluidized-bed section and a 4-inch-ID, 13-foot-long entrained flow section. Both sections are enclosed in clam-shell electrical heaters. The design coal feed capacity is 100 lb/h, and the coal can be fed either to the fluidized bed or the freeboard region above the fluidized bed and below the entrained section. The stainless steel reactor vessel is designed for operation at a maximum temperature and pressure of 1500°F and 50 psig, respectively. The reactor details have been presented earlier in this volume.

Project Approach

The mild gasification project consists of four major tasks:

- Task 1. Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment
- Task 2. Bench-Scale Mild Gasification Study
- Task 3. Bench-Scale Char Upgrading Study
- Task 4. System Integration Studies

The approach to the development of an advanced mild gasification process was based, in Task 1 of this project, on a detailed literature survey and review of the state-of-the-art technology for coal conversion to readily saleable co-products. A market survey, conducted concurrently with the literature survey, identified the value-added priority end uses of the co-products. Based on this information, the bases for design of the type of reactor, the process operating conditions, and the methods of co-products upgrading were determined. The results of the above approach were presented in Volume I of this report. That report identified several large potential markets for value-added mild gasification char co-products. These potential large markets for the char are:

A8001016P

Figure II-34. SCHEMATIC DIAGRAM OF PRU SYSTEM

Figure II-35. ISOMETRIC OF PRU SYSTEM

- Metallurgical form coke (about 30×10^6 ton/yr)
- Smokeless fuel (about 50 to 100×10^6 ton/yr)
- Activated char (about 1 to 2×10^6 ton/yr).

The identification of these co-products was also guided by the technical considerations for the development of the mild gasification process and its integration with coal preparation technology. In addition, the impact of a wide variety of upstream solid processing steps and downstream processing steps were considered for the production of commercial quality liquid and solid co-products. As a result, the resultant mild gasification process that evolved favored a minimum of processing steps.

Developmental work will be required to prepare the identified commercially acceptable products from mild gasification char, and to integrate the mild gasification process and downstream processing with a coal preparation plant. The feed coals tested in this program came from the high-moisture fines (<1/4-inch) streams from Peabody's coal preparation plants. These fines are normally mixed with the lump coal shipments. The use of the mild gasification char co-product for the steam or utility fuel market is technically possible, but that large market was not evaluated in detail because the char as a utility fuel may not have a significant value-added advantage at this time.

The objective of Task 2 of the project, Bench-Scale Mild Gasification, was to design, build, and operate an isothermal 1.2-ton/day (100-lb/h) PRU with slipstream sampling to determine process performance and to obtain design information on mild gasification of coals for process scale-up.

The objective of Task 3, Bench-Scale Char Upgrading, was to evaluate the performance of upgraded samples of potential high-market value solid products. In Task 4, System Integration Studies, a full-stream product gas condenser was designed, built, and operated to obtain the integrated PRU system performance data.

System Integration Tests

Description of Tests

After the completion of the operational and parametric tests in the IGT mild gasification PRU in Task 2 of this program, the PRU system was modified

by installing a full-flow product gas stream condensation system. A schematic diagram of the full-stream condensate system is shown in Figure II-36. The system consists of a quench spray tower vessel, a quench liquids collection vessel, a heat exchanger, and a recirculating quench liquid pump. The quench spray tower vessel has four spray nozzles that spray recirculated quench liquid countercurrent to the product gas flow. The quench liquid in turn, is cooled by flowing through a tube and shell heat exchanger. The condensable liquids can be drained from four nozzles located at different elevations on the quench collection vessel or from the bottom of the vessel.

The hot product gas from the cyclones can be directed, as desired, either to the quench system or to the existing combustor. During startup and shutdown, the reactor gases are directed to the combustor, bypassing the full-stream condensate system, until steady mild gasification conditions are achieved. The single-stage condensation system was designed to collect the middle- and high-boiling fractions of the condensable liquids. The low-boiling fraction is not collected, but passes through the condenser and is incinerated in the combustor to avoid discharge to the atmosphere. The low-boiling fraction can be determined from the total analysis of the sample of product gas and condensable liquids available from the hot gas slip-stream sampling system, which operates independently of the full-stream condensate system.

A summary of the 17 tests conducted in this task is given in Table II-48. The first test, Test IST-1, was conducted with the full-stream quench system in place, using water as the quench liquid. The West Virginia coal studied in Task 2 was the feed coal. The test conditions were selected to repeat those of a successful test at a mild gasification temperature of about 1180°F and a feed rate of about 60 lb/h. Test IST-1 began smoothly, but after a half hour of coal feed, the system pressure began to fluctuate and the test was stopped. Tar deposits in the pressure letdown valves were restricting the operation of the valve to control the system pressure. It was determined that tar aerosols were formed that were not being coalesced in the quench tower.

A second test, Test IST-2, was conducted under the same process conditions to estimate the amount of uncondensed tar leaving the quench spray tower and to determine system changes to trap the aerosols. When the system pressure began to fluctuate after about 40 minutes of coal feeding, the test

Figure II-36. SCHEMATIC DIAGRAM OF FULL-STREAM CONDENSATE SYSTEM

Table II-48, Part 1. SUMMARY OF MILD GASIFICATION TESTS CONDUCTED IN TASK 4

	Test No.			
	IST-1	IST-2	IST-3	IST-4
Purpose of Test	Quench system operation	To estimate extent of tar aerosols escaping quench system	Operate with changes to quench system	Quench shake-down, xylene solvent and relocated pressure let-down valve
Feed Material	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^b /coke	1:1 mixture coal ^b /coke
Feed Rate, lb/h	59.6	50.5	62.3	48.7
Steam Rate, lb/h	0.0	0.0	0.0	0.0
Steam/Coal Ratio	0.0	0.0	0.0	0.0
Temperature, °F	1180	1165	1150	1045
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized Bed Height, ft	2.1	1.9	2.1	2.3
Superficial Gas Velocity, ft/s	4.4	4.2	4.0	3.4
Solids Residence Time, min	--	--	--	--
Steady-State Period, h	--	--	--	--
Remarks	Lost system pressure control after 30 min of feed	Stopped after 40 min of feed to estimate tar in system	Determined control valve to be moved, solvent quench liquid to replace water	Plug in feed line after 45 min of feed

^a West Virginia coal.^b Illinois No. 6 coal.

Table II-48, Part 2. SUMMARY OF MILD GASIFICATION TESTS CONDUCTED IN TASK 4

	Test No.			
	IST-5	IST-6	IST-7	IST-8
Purpose of Test	Repeat of IST-4	Replace coke diluent in feed using IST-5 char	Repeat of IST-6 with IST-5 char	Test with 19% CO ₂ in fluidization gas inlet
Feed Material	1:1 mixture coal ^b /coke	1:1 mixture coal ^b /char	1:1 mixture coal ^b /char	1:1 mixture coal ^b /coke
Feed Rate, lb/h	66.6	61.7	57.6	57.6
Steam Rate, lb/h	0.0	0.0	0.0	0.0
Steam/Coal Ratio	0.0	0.0	0.0	0.0
Temperature, °F	1110	1170	1115	1105
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized Bed Height, ft	2.25	1.9	1.9	2.4
Superficial Gas Velocity, ft/s	4.5	4.6	4.5	4.5
Solids Residence Time, min	12	--	10	13
Steady-State Period, h	4.5	--	4.5	4.0
Remarks	Successful test operation	Feed line plug after 15 min of feed	Successful test operation	Successful test operation

^b Illinois No. 6 coal

Table II-48, Part 3. SUMMARY OF MILD GASIFICATION TESTS CONDUCTED IN TASK 4

	Test No.			
	IST-9	IST-10	IST-11	IST-12
Purpose of Test	Reduce coke diluent in feed further using IST-7 char	Conduct WV coal test, reduce coke by using MG-31 char diluent	Reduce coke content further using IST-10 char diluent	Conduct 12-hour steady-state test
Feed Material	1:1 mixture coal ^b /char	50% coal ^a /33% char/17% coke	1:1 mixture coal ^a /char	1:1 mixture coal ^a /coke
Feed Rate, lb/h	50.6	53.5	74.1	63.0
Steam Rate, lb/h	0.0	0.0	0.0	0.0
Steam/Coal Ratio	0.0	0.0	0.0	0.0
Temperature, °F	1105	1110	1110	1100
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized Bed Height, ft	1.75	1.9	2.25	1.6
Superficial Gas Velocity, ft/s	4.5	4.5	4.4	4.4
Solids Residence Time, min	9	13	9	10
Steady-State Period, h	4.8	4.5	3.5	12
Remarks	Successful test operation	Successful test operation	Successful test operation	Successful test operation

^a West Virginia coal.^b Illinois No. 6 coal.

Table II-48, Part 4. SUMMARY OF MILD GASIFICATION TESTS CONDUCTED IN TASK 4

	Test No.			
	IST-13	IST-14	IST-15	IST-16
Purpose of Test	Reduce coke in feed by using IST-12 char diluent	Obtain higher temp data, feed using IST-12 char	Conduct test with Western coal	Conduct test with second Illinois coal
Feed Material	1:1 mixture coal ^a /char	1:1 mixture coal ^a /char	100% coal ^c	1:1 mixture coal ^e /coke
Feed Rate, lb/h	61.4	60.6	73.1 ^d	52.3
Steam Rate, lb/h	0.0	0.0	0.0	0.0
Steam/Coal Ratio	0.0	0.0	0.0	0.0
Temperature, °F	1084	1275	1062	1288
Pressure, psig	10	12	12	12
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized Bed Height, ft	2.3	1.6	1.4	2.2
Superficial Gas Velocity, ft/s	4.5	4.5	3.5	4.3
Solids Residence Time, min	11	9	8	--
Steady-State Period, h	5.0	7.0	11.3	--
Remarks	Successful test operation	Successful test operation	Successful test operation	Feed line plug 30 min into test

^a West Virginia coal.^c Rochelle sub-bituminous coal.^d Feed rate raised to 102 lb/h for last 6-hour period.^e Illinois No. 6 (Sesser seam) coal.

Table II-48, Part 5. SUMMARY OF MILD GASIFICATION TESTS CONDUCTED IN TASK 4

	<u>Test No.</u> <u>IST-17</u>
Purpose of Test	Repeat test with second Illinois coal type
Feed Material	1:1 mixture coal ^e /char
Feed Rate, lb/h	59.0
Steam Rate, lb/h	0.0
Steam/Coal Ratio	0.0
Temperature, °F	1288
Pressure, psig	12
Feed Location	Fluidized Bed
Fluidized Bed Height, ft	2.4
Superficial Gas Velocity, ft/s	4.5
Solids Residence Time, min	13
Steady-State Period, h	5.0
Remarks	Successful test operation

^e Illinois No. 6 (Sesser seam) coal.

was stopped and an estimate obtained of tar deposited in the valves and piping compared to the tar collected in the quench vessel. The tar aerosol deposit was about 10% of the tar that was collected in the quench vessel. Alterations to the quench system were made for the next test to try to reduce the carry-over tar amount. A stainless steel demister was installed at the top exit of the spray tower and only three of the four spray nozzles were used to increase the water spray pressure to the others for better atomization.

Test IST-3 began smoothly and operated about an hour before the system pressure began to fluctuate, and the test was terminated. To solve the tar aerosol carryover, the water quench liquid was replaced with a solvent and the pressure let-down valves were relocated upstream of the quench system. A search for a candidate recirculating solvent identified xylene as a safe-to-handle liquid that could be separated from the quenched liquids by distillation, and would minimize interference with chemical analysis of the liquids. Other modifications necessitated by these changes involved increasing the exit piping size from the quench tower, since the system would operate at near atmospheric pressure instead of 10 psig due to the relocation of the pressure let-down valve. A refrigeration chiller was installed to provide cold ethylene glycol to the recirculating xylene heat exchanger, and a pump capable of handling xylene was substituted. With these modifications to eliminate the tar aerosol, the full-stream quench system operated well, and 11 of the remaining 14 tests were successful. All but two of the remaining tests were conducted under similar conditions of temperature, fluidized-bed height, and char residence time that were identified in Task 2 as being favorable to the maximum production of oils and tars. The major differences among the tests were that four different types of coal were evaluated, char from previous tests was recycled to replace the coke feed diluent, and two extended-duration tests with 12-hour steady-state periods were conducted. The four coals include the Illinois No. 6 coal and the West Virginia coal used in the tests conducted in Task 2, and, in addition, a low-sulfur Illinois No. 6 (Sesser seam) coal, and a Western subbituminous coal (Rochelle coal near Gillette, Wyoming). The analyses and descriptions of these coals are given in the section presenting the test data.

Tests IST-4 and IST-6 were conducted with Illinois No. 6 coal, and both experienced a blockage of the feed in the feed injection nozzle just before

the entrance to the reactor. These tests were stopped before the steady-state period. Tests IST-5 and IST-7, however, were operated steadily for about 4.5 hours until the feed mixture in the feed hopper was exhausted. Test IST-7 used char recycled from Test IST-5 instead of the diluent coke breeze, and the only notable difference observed as a result of the substitution was that the fluidized-bed density was lower, as expected with the lower density diluent char. The sample system flow controller malfunctioned in Test IST-7, which resulted in a low sample gas flow, and may have introduced an error into the material balance data for that test. This is discussed more fully in a later section.

Test IST-8 was conducted with Illinois No. 6 coal and an inlet fluidization gas containing about 19 volume % carbon dioxide. This concentration of carbon dioxide is about the level expected in the conceptual design of the 24-tpd adiabatic PDU using heated recycled product gas. The test was successful.

Test IST-9 used recycled char from two successive tests as a feed diluent. The test was conducted with the char from Test IST-7 which used the char from Test IST-5, this reducing the coke content of the char from Test IST-9 to an estimated 15% by weight. The test operated smoothly for 4.5 hours until the feed was exhausted from the feed hopper indicating that the mixing and fluidization of the recycle char in the conceptual process design is practical.

West Virginia coal was tested in Tests IST-10 through IST-14. Tests IST-10 and IST-11 were conducted with the purpose of using recycled char from previous tests to produce a char with reduced coke content in the char diluent. Each test operated successfully until the feed mixture in the hopper was exhausted. Some of the char from Test IST-10 was used to prepare single briquettes of form coke. A 3-inch diameter mold was machined to hot-press the char and parent coal as a binder in a large, heated hydraulic press. A 1:1 by weight mixing ratio was used to make the 3-inch diameter by about 1-inch thick briquettes. These were then calcined at 1800°F under a nitrogen atmosphere. The making of these single briquettes showed that a strong briquette can be made using coal as the binder. The chars from subsequent tests will be used to make briquettes of form coke in a roll briquetting machine for evaluation in Task 3 of this program.

Test IST-11 used the char from Test IST-10 in its feed mixture. The test operated until the feed was exhausted from the feed hopper after about 4 hours. At the last half hour of the test, a trace heater burned out just upstream of the pressure letdown valve. Tars began to accumulate in the valve and the system pressure began to rise from 10 to 11.7 psig. The entire PRU system after the reactor was disassembled, inspected, and cleaned before the next scheduled test, a 12-hour steady-state duration test.

Test IST-12 was successfully conducted in the PRU for a 12-hour steady-state period. The fluidization, as indicated by the constant readings of the fluidized-bed differential pressure taps converted into fluidized-bed density and height, was very smooth during the entire test. The feed was a 1:1 by weight mixture of the West Virginia coal and the diluent coke breeze. The test ended when the 730 pounds of feed was exhausted from the feed hopper. Only the small tubing lines of the slip-stream sampling system experienced some blockage of tars and fine material about 5 hours into the steady-state period. These lines were isolated from the system during the test, cleaned, and returned to service. The single-stage quench system also operated well and about 55 gallons of liquids were collected for distillation of the xylene solvent.

Test IST-13 was performed with recycle char in place of coke breeze as the feed diluent to produce char with reduced coke content for the production of form coke briquettes for Task 3 evaluation. Char from Test IST-12 was used and the test operated smoothly for 5 hours. Operation of the PRU with recycle char simulates the expected mild gasification process conditions with char recycle and improves confidence in the configuration of the 24-tpd PDU design.

Test IST-14 was conducted at a higher fluidization temperature of about 1275°F to evaluate the co-product distribution from the West Virginia coal at this process temperature. Char from IST-12 was used in the feed mixture and the test operated smoothly for 7 hours. In this test, the slipstream sampling system was operated for about 2.6 hours instead of the usual 1-hour sampling period. This was done to collect a larger total condensate sample for analysis by a tar processing company.

Test IST-15 was conducted with a sub-bituminous western coal obtained from Peabody's Rochelle mine in the Powder River basin near Gillette, Wyoming. The purpose of this test was to evaluate the PRU mild gasification performance

with a lower-rank noncaking coal. The subbituminous coal was fed directly to the reactor with no diluent material. The feed rate was set at 73.1 lb/h for a 5-hour steady-state period, then raised to 102 lb/h for a 6-hour operation period. This test defined the differences expected between a caking coal and a noncaking coal in the mild gasification process. Analysis of the values of key operating parameters will be useful for the PDU scale-up design for added process flexibility. Values such as the feed rate per unit fluidized-bed area, the fluidization velocity, the fluidized-bed density, and fluidized-bed height are important design considerations.

Tests IST-16 and IST-17 were conducted with a second coal from Illinois that is very low in sulfur and ash, identified as an Illinois No. 6 (Sesser seam) coal. One of the uses for this coal is as a blending coal in metallurgical coke-making to achieve the desired coke strength and reactivity values. A quantity of this coal was obtained from the storage supply of the coking operations at Inland Steel Company in Indiana. Test IST-16 started smoothly with a 1:1 mixture of the coal and coke diluent. A half hour after the start of coal feeding, a large gas leak developed in the feed metering screw's shaft seal. The test was stopped to repair the seal and a repeat of the test conditions was scheduled.

Test IST-17 was completed successfully with the Sesser seam coal. The feed rate was 59 lb/h and the test temperature was 1288°F over the 5-hour test period.

Test Results

Introduction

The results of the Task 4 PRU tests are presented and interpreted in this section. The test coals will be described, the co-product yields and properties will be interpreted and compared to those presented in Task 2,¹ the results of oils/tars recovery from the full-stream quench system will be discussed, and the impact of these findings on scale-up design considerations and co-product markets will be discussed.

Test Coals

As described in the previous section, four coals were tested in the mild gasification PRU under Task 4, two of which were previously tested in Task 2. In addition, a noncaking subbituminous coal from Rochelle, Wyoming, and a low-

sulfur Illinois No. 6 seam coal from Sesser, Illinois were each used in one successful test. The proximate and ultimate analyses of samples of the four coals are shown in Table II-49, and the coals are described below.

Table II-49. ANALYSES OF COALS TESTED IN TASK 4

	<u>Illinois No. 6^a</u> <u>Randolph P. P.</u>	<u>West Virginia^b</u> <u>Wells Complex</u>	<u>Subbituminous</u> <u>Rochelle Mine</u>	<u>Illinois No. 6</u> <u>Sesser Seam</u>
<u>Proximate</u>	----- Wt % as fed to reactor -----			
Moisture	5.3	1.4	16.2	6.6
Volatile Matter	34.7	30.6	35.9	31.6
Ash	15.0	6.4	4.6	4.2
Fixed Carbon	<u>45.0</u>	<u>61.6</u>	<u>43.3</u>	<u>57.5</u>
Total	100.0	100.0	100.0	100.0
<u>Ultimate</u>	----- Wt % dry basis -----			
Ash	15.8	6.4	5.5	4.5
Carbon	64.3	80.2	68.3	78.2
Hydrogen	4.2	5.0	4.2	5.0
Nitrogen	1.4	1.7	1.1	2.0
Sulfur	3.9	1.3	0.14	1.1
Oxygen (by diff)	<u>10.4</u>	<u>5.4</u>	<u>20.8</u>	<u>9.3</u>
Total	100.0	100.0	100.0	100.0

^a Baldwin No. 1, Marissa and River King No. 6 Mines.

^b 55% No. 2 Gas Seam/45% Campbell's Creek Seam.

The Illinois No. 6 coal was from the high-moisture fines (<1/8-inch) stream of the Peabody Coal Company Randolph Preparation Plant. This coal is from three mines: Baldwin No. 1, Marissa, and River King No. 6, and is a typical high-sulfur, high-ash Illinois coal used primarily as utility fuel. The West Virginia coal is also from the high-moisture fines stream of a Peabody Preparation plant at the Wells Complex in Boone County near Wharton, West Virginia. This metallurgical blending coal is a blend from two mines: 55% Lightfoot No. 1 (No. 2 Gas Seam) and 45% Harris No. 2 (Campbell's Creek Seam). The West Virginia coal is a more highly caking coal (FSI 5 to 8) than the Illinois No. 6, and is typical of Eastern medium-sulfur (~1%) low-ash (~6%) coals. The Rochelle subbituminous coal is a low-sulfur utility coal from the Powder River Basin, and is fairly typical of Western coals, having very low sulfur (0.14%), low ash (5.5%), and a high oxygen content (~20%).

The moisture content of this coal is also typically high (~16%). The second Illinois No. 6 coal is an atypical low-sulfur, low-ash variety from a mine in Sesser, Illinois, which is used for coke blending. The moderate caking properties of the coal are typical of Illinois No. 6 bituminous coals.

Material Balances

The normalization procedure used to present the Task 4 data differs from that used in the Task 2 Topical Report. Previously, ash, carbon, sulfur, nitrogen, and water were forced by adjusting the char, oils/tars, H_2S , NH_3 , and aqueous condensate output values. This was done partially to produce fully balanced output streams for the preliminary PDU design, and also because of a difficulty in obtaining a consistent measured water balance. The water balance problem was solved by analyzing the slipstream sampling system tetrahydrofuran (THF) wash sample for water content, which showed that a significant part of the condensed water was not collecting in the condensate pots, but was apparently adhering to the pipe and vessel surfaces in the sampling system. Water is soluble in THF, and can be determined by the Karl Fischer method. In most cases, satisfactory water recovery was obtained by the simple procedural change.

The simplified material balance procedure presented here, which does not make any attempt to force any of the elemental or ash balances, consists of adjusting the oils/tars yield to force the overall mass balance to 100% on a moisture- and ash-free basis. Previous co-product yield data from Task 2 was also recalculated on a moisture- and ash-free basis for comparison. The ash content of the diluent coke breeze showed much less variability, and thus was used as a basis for calculating the coal composition based on the feed mixture analysis from several samples taken during the steady-state period of each test.

In addition to this procedure, a correction to product gas and diluent output was made to account for the small but significant devolatilization of the various diluent materials. In each test, 50 pounds of diluent coke or char was fed to the reactor over a 1-hour period prior to the actual coal feed, and the on-line gas analyses were used to calculate this correction based on the mass fraction of diluent in the test feed mixture.

All of the material balance and co-product characterization data were based on slipstream sampling and processed via a dedicated Lotus 1-2-3™ spreadsheet. The raw and adjusted material balances for Tests IST-5, IST-7 through IST-15, and IST-17 are shown in Tables II-50 to II-60. Data from the full-stream quench system samples will be discussed separately in a later section.

In general, the mass balances closures for the major elements were close to 100% both before and after adjustment. The carbon balance closure ranged from 93% to 101%, and the ash balance closure from 92% to 112% before adjustments were made. The hydrogen closure ranged from 97% to 110%, and the oxygen closure from 83% to 122%. Oxygen is difficult to balance since it is determined by difference in standard analyses, and thus tends to accumulate random errors in the measurement of other elements. The sulfur balance closure ranged from 85% to 100% for the bituminous coals, which is expected because sulfur gases can react reversibly with stainless steel surfaces, removing some of the sulfur from the products. The nitrogen balance closure for all of the coals, not including nitrogen gas used for fluidization, ranged from 80% to 96%. Unaccounted nitrogen can be assumed to represent a partial loss of volatile ammonia from the aqueous condensate during sample recovery, transfer, and processing.

Co-Product Yields

The char, gas, oils/tars, and water yields from the Task 4 PRU tests are also given in Tables II-50 to II-60, and are shown graphically in Figure II-37, along with the yield curves generated for Illinois No. 6 coal in Task 2, represented by the dotted lines. The open circles represent Illinois No. 6 coal tested in Task 4; the closed circles, West Virginia coal; the triangles, Illinois Sesser coal; and the asterisks, Rochelle subbituminous coal. Except for Test IST-7, which gave unusually high oils/tars and water yields and a low char yield, the data for both Illinois coals and the West Virginia coal were fairly close to the previous data. The IST-7 results may have been skewed due to an accumulation of char fines in the cyclone crossover tee together with a malfunction in the slipstream sample system flow controller, which was acknowledged in the test description given earlier. The gas yields were consistently lower in the Task 4 data for all three bituminous coals, which may be partly because of the fact that the correction was not

Table II-50. TEST IST-5 MATERIAL BALANCES

Coal: Illinois No. 6
 Fluidization Gas: 100% N₂
 Temperature: 1111°F

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed	22.40	1.61	2.81	0.48	1.51	3.32	32.13
Diluent	27.97	0.13	0.38	0.40	0.25	3.80	32.93
Steam + Moisture	--	<u>0.17</u>	<u>1.37</u>	--	--	--	<u>1.54</u>
Total	50.37	1.91	4.56	0.88	1.76	7.12	66.60
<u>Output</u>							
Char + Diluent	40.73	0.57	0.86	0.74	1.19	7.33	51.42
Product Gas	0.99	0.25	0.46	0.00	0.16	--	1.86
Oils/Tars	5.05	0.46	0.69	0.05	0.14	0.02	6.41
Aqueous Condensate	<u>0.00</u>	<u>0.29</u>	<u>2.30</u>	<u>0.00</u>	<u>0.00</u>	--	<u>2.59</u>
Total	46.77	1.57	4.31	0.79	1.49	7.35	62.28
Out/In	0.93	0.82	0.95	0.90	0.85	1.03	0.94

	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed	22.40	1.61	2.81	0.48	1.51	3.32	32.13
Diluent	27.97	0.13	0.38	0.40	0.25	3.80	32.93
Steam + Moisture	--	<u>0.17</u>	<u>1.37</u>	--	--	--	<u>1.54</u>
Total	50.37	1.91	4.56	0.88	1.76	7.12	66.60
<u>Output</u>							
Char + Diluent	40.73	0.57	0.86	0.74	1.19	7.33	51.42
Product Gas	0.99	0.25	0.46	0.00	0.16	--	1.86
Oils/Tars	8.43	0.77	1.17	0.09	0.23	0.04	10.73
Aqueous Condensate	<u>0.00</u>	<u>0.38</u>	<u>2.30</u>	<u>0.00</u>	<u>0.00</u>	--	<u>2.59</u>
Total	50.15	1.89	4.79	0.83	1.58	7.37	66.60
Out/In	1.00	0.98	1.08	0.94	0.90	1.04	1.00

Diluent-Free Co-Product Yields, wt % coal

	<u>dry</u>	<u>maf</u>
Char	58.3	52.8
Gas	5.8	6.5
Oils/Tars	33.4	37.1
Water	<u>3.3</u>	<u>3.6</u>
Total	100.8	100.0

Table II-51. TEST IST-7 MATERIAL BALANCES

Coal: Illinois No. 6
 Fluidization Gas: 100% N₂
 Temperature: 1117°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	17.69	1.24	3.34	0.37	1.06	3.58	27.28
Diluent	22.68	0.34	0.56	0.41	0.68	4.10	28.77
Steam + Moisture	--	0.17	1.37	--	--	--	1.54
Total	40.37	1.75	5.27	0.78	1.74	7.68	57.59
<u>Output</u>							
Char + Diluent	30.09	0.49	1.09	0.58	1.14	7.21	40.60
Product Gas	1.06	0.25	0.67	0.00	0.11	--	2.09
Oils/Tars	9.21	0.83	1.42	0.08	0.24	0.05	11.83
Aqueous Condensate	0.02	0.59	4.72	0.03	0.00	--	5.37
Total	40.38	2.16	7.90	0.69	1.49	7.25	59.89
Out/In	1.00	1.23	1.50	0.89	0.86	0.95	1.04

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	17.69	1.24	3.34	0.37	1.06	3.58	27.28
Diluent	22.68	0.34	0.56	0.41	0.68	4.10	28.77
Steam + Moisture	--	0.17	1.37	--	--	--	1.54
Total	40.37	1.75	5.27	0.78	1.74	7.68	57.59
<u>Output</u>							
Char + Diluent	30.09	0.49	1.09	0.58	1.14	7.21	40.60
Product Gas	1.06	0.25	0.67	0.00	0.11	--	2.09
Oils/Tars	7.15	0.65	1.07	0.06	0.18	0.04	9.15
Aqueous Condensate	0.02	0.59	4.72	0.03	0.00	--	5.36
Total	38.32	2.05	7.55	0.67	1.43	7.25	57.20
Out/In	0.95	1.17	1.43	0.86	0.83	0.95	0.99

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	43.3	36.7
Gas	7.7	8.8
Oils/Tars	33.5	38.4
Water	14.0	16.1
Total	98.5	100.0

Table II-52. TEST IST-8 MATERIAL BALANCES

Coal: Illinois No. 6
 Fluidization Gas: 19% CO₂, 81% N₂
 Temperature: 1102°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	17.70	0.92	2.82	0.35	0.68	4.89	27.36
Diluent	24.97	0.36	0.29	0.38	0.58	2.20	28.78
Steam + Moisture	--	0.18	1.48	--	--	--	1.66
Total	42.67	1.46	4.59	0.73	1.26	7.09	57.80
<u>Output</u>							
Char + Diluent	38.60	0.39	1.00	0.65	0.85	7.66	49.15
Product Gas	0.79	0.17	0.42	0.00	0.18	--	1.56
Oils/Tars	3.70	0.35	0.54	0.02	0.09	0.00	4.70
Aqueous Condensate	0.01	0.18	1.49	0.01	0.00	--	1.69
Total	43.10	1.09	3.45	0.68	1.12	7.66	57.10
Out/In	1.01	0.75	0.75	0.92	0.89	1.08	0.99

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	17.70	0.92	2.82	0.35	0.68	4.89	27.36
Diluent	24.97	0.36	0.29	0.38	0.58	2.20	28.78
Steam + Moisture	--	0.18	1.48	--	--	--	1.66
Total	42.67	1.46	4.59	0.73	1.26	7.09	57.80
<u>Output</u>							
Char + Diluent	38.60	0.39	1.00	0.65	0.85	7.66	49.15
Product Gas	0.79	0.17	0.42	0.00	0.18	--	1.56
Oils/Tars	4.75	0.45	0.71	0.03	0.11	0.01	6.06
Aqueous Condensate	0.01	0.18	1.49	0.01	0.00	--	1.69
Total	44.15	1.19	3.62	0.69	1.14	7.67	58.46
Out/In	1.03	0.82	0.79	0.93	0.90	1.08	1.01

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	75.3	67.3
Gas	5.7	6.9
Oils/Tars	21.1	25.7
Water	0.1	0.1
Total	102.2	100.0

Table II-53. TEST IST-9 MATERIAL BALANCES

Coal: Illinois No. 6
 Fluidization Gas: 100% N₂
 Temperature: 1107°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	15.61	0.95	2.21	0.29	0.85	4.11	24.02
Diluent	18.64	0.32	0.72	0.36	0.71	4.47	25.22
Steam + Moisture	--	0.15	1.21	--	--	--	1.36
Total	34.25	1.42	4.14	0.65	1.56	8.58	50.60
<u>Output</u>							
Char + Diluent	29.78	0.51	1.49	0.51	1.28	9.62	43.19
Product Gas	0.59	0.15	0.34	0.00	0.14	--	1.22
Oils/Tars	3.44	0.34	0.58	0.03	0.08	0.01	4.48
Aqueous Condensate	0.01	0.22	1.74	0.01	0.00	--	1.98
Total	33.82	1.22	4.15	0.55	1.50	9.63	50.87
Out/In	0.99	0.84	1.00	0.85	0.96	1.12	1.01

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	15.61	0.95	2.21	0.29	0.85	4.11	24.02
Diluent	18.64	0.32	0.72	0.36	0.71	4.47	25.22
Steam + Moisture	--	0.15	1.21	--	--	--	1.36
Total	34.25	1.42	4.14	0.65	1.56	8.58	50.60
<u>Output</u>							
Char + Diluent	29.78	0.51	1.49	0.51	1.28	9.62	43.19
Product Gas	0.59	0.15	0.34	0.00	0.14	--	1.22
Oils/Tars	3.91	0.39	0.66	0.04	0.09	0.01	5.10
Aqueous Condensate	0.01	0.22	1.84	0.01	0.00	--	1.98
Total	34.29	1.27	4.23	0.56	1.51	9.63	51.49
Out/In	1.00	0.89	1.02	0.86	0.97	1.12	1.02

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	75.4	65.2
Gas	5.1	6.1
Oils/Tars	21.2	25.6
Water	2.6	3.1
Total	104.3	100.0

Table II-54. TEST IST-10 MATERIAL BALANCES
 Coal: West Virginia
 Fluidization Gas: 100% N₂
 Temperature: 1108°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	21.20	1.11	1.15	0.39	0.33	2.01	26.19
Diluent	22.45	0.43	0.64	0.40	0.44	2.34	26.70
Steam + Moisture	--	0.06	0.54	--	--	--	0.60
Total	43.65	1.60	2.33	0.79	0.77	4.35	53.49
<u>Output</u>							
Char + Diluent	35.18	0.69	1.04	0.59	0.68	4.19	42.37
Product Gas	1.11	0.31	0.21	0.00	0.04	--	1.67
Oils/Tars	5.04	0.47	0.63	0.04	0.05	0.02	6.25
Aqueous Condensate	0.00	0.15	1.29	0.00	0.00	--	1.44
Total	41.33	1.62	3.17	0.63	0.77	4.21	51.73
Out/In	0.95	1.01	1.36	0.80	1.00	0.97	0.97
	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	21.20	1.11	1.15	0.39	0.33	2.01	26.19
Diluent	22.45	0.43	0.64	0.40	0.44	2.34	26.70
Steam + Moisture	--	0.06	0.54	--	--	--	0.60
Total	43.65	1.60	2.33	0.79	0.77	4.35	53.49
<u>Output</u>							
Char + Diluent	35.18	0.69	1.04	0.59	0.68	4.19	42.37
Product Gas	1.11	0.31	0.21	0.00	0.04	--	1.67
Oils/Tars	6.21	0.58	0.78	0.05	0.06	0.02	7.70
Aqueous Condensate	0.00	0.15	1.29	0.00	0.00	--	1.44
Total	42.50	1.73	3.32	0.64	0.78	4.21	53.18
Out/In	0.97	1.08	1.42	0.81	1.01	0.97	0.99

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	60.4	57.8
Gas	6.4	6.9
Oils/Tars	29.4	31.8
Water	3.2	3.5
Total	99.4	100.0

Table II-55. TEST IST-11 MATERIAL BALANCES

Coal: West Virginia
 Fluidization Gas: 100% N₂
 Temperature: 1110°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	28.06	1.59	1.37	0.56	0.30	2.55	34.43
Diluent	28.99	0.58	0.86	0.49	0.56	3.45	34.93
Steam + Moisture	--	0.11	0.84	--	--	--	0.95
Total	57.05	2.28	3.07	1.05	0.86	6.00	70.31
<u>Output</u>							
Char + Diluent	47.36	1.11	1.44	0.93	0.67	6.05	57.56
Product Gas	1.18	0.33	0.32	0.00	0.03	--	1.86
Oils/Tars	5.28	0.47	0.68	0.05	0.03	0.00	6.51
Aqueous Condensate	0.00	0.21	1.60	0.00	0.00	--	1.81
Total	53.82	2.12	4.04	0.98	0.73	6.05	67.74
Out/In	0.94	0.93	1.32	0.93	0.85	1.01	0.96

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	28.06	1.59	1.37	0.56	0.30	2.55	34.43
Diluent	28.99	0.58	0.86	0.49	0.56	3.45	34.93
Steam + Moisture	--	0.11	0.84	--	--	--	0.95
Total	57.05	2.28	3.07	1.05	0.86	6.00	70.31
<u>Output</u>							
Char + Diluent	47.36	1.11	1.44	0.93	0.67	6.05	57.56
Product Gas	1.18	0.33	0.32	0.00	0.03	--	1.86
Oils/Tars	7.27	0.65	0.96	0.08	0.05	0.01	9.02
Aqueous Condensate	0.00	0.21	1.60	0.00	0.00	--	1.81
Total	55.81	2.30	4.32	1.01	0.75	6.06	70.25
Out/In	0.98	1.01	1.41	0.96	0.87	1.01	1.00

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	66.1	63.2
Gas	5.4	5.8
Oils/Tars	26.2	28.3
Water	2.5	2.7
Total	100.2	100.0

Table II-56. TEST IST-12 MATERIAL BALANCES
 Coal: West Virginia
 Fluidization Gas: 100% N₂
 Temperature: 1100°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	23.34	1.49	1.51	0.46	0.30	1.73	28.83
Diluent	24.98	0.09	0.12	0.31	0.16	3.48	29.14
Steam + Moisture	--	0.06	0.47	--	--	--	0.53
Total	48.32	1.64	2.10	0.77	0.46	5.21	58.50
<u>Output</u>							
Char + Diluent	39.97	0.49	0.65	0.64	0.34	5.68	47.77
Product Gas	1.12	0.34	0.08	0.00	0.01	--	1.55
Oils/Tars	7.47	0.70	0.92	0.08	0.07	0.07	9.31
Aqueous Condensate	0.00	0.28	2.17	0.00	0.00	--	2.45
Total	48.56	1.81	3.82	0.72	0.42	5.75	61.08
Out/In	1.00	1.10	1.82	0.94	0.91	1.10	1.04

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	23.34	1.49	1.51	0.46	0.30	1.73	28.83
Diluent	24.98	0.09	0.12	0.31	0.16	3.48	29.14
Steam + Moisture	--	0.06	0.47	--	--	--	0.53
Total	48.32	1.64	2.10	0.77	0.46	5.21	58.50
<u>Output</u>							
Char + Diluent	39.97	0.49	0.65	0.64	0.34	5.68	47.77
Product Gas	1.12	0.34	0.08	0.00	0.01	--	1.55
Oils/Tars	5.69	0.53	0.68	0.06	0.05	0.05	7.06
Aqueous Condensate	0.00	0.28	2.18	0.00	0.00	--	2.46
Total	46.78	1.64	3.59	0.70	0.40	5.73	58.84
Out/In	0.97	1.00	1.71	0.91	0.87	1.10	1.01

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	65.3	61.3
Gas	5.4	5.7
Oils/Tars	24.5	25.9
Water	6.7	7.1
Total	101.9	100.0

Table II-57. TEST IST-13 MATERIAL BALANCES

Coal: West Virginia
 Fluidization Gas: 100% N₂
 Temperature: 1084°F

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed	24.56	1.48	1.75	0.49	0.34	1.61	30.23
Diluent	25.52	0.30	0.50	0.42	0.21	3.51	30.46
Steam + Moisture	--	0.08	0.62	--	--	--	0.70
Total	50.08	1.86	2.87	0.91	0.55	5.12	61.39
<u>Output</u>							
Char + Diluent	41.50	0.77	1.19	0.77	0.42	5.13	49.78
Product Gas	0.99	0.30	0.11	0.00	0.04	--	1.44
Oils/Tars	6.37	0.58	0.71	0.07	0.05	0.00	7.78
Aqueous Condensate	0.00	0.18	1.43	0.00	0.00	--	1.61
Total	48.86	1.83	3.44	0.84	0.51	5.13	60.61
Out/In	0.98	0.98	1.20	0.92	0.93	1.00	0.99

	-----			ADJUSTED	-----		
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed	24.56	1.48	1.75	0.49	0.34	1.61	30.23
Diluent	25.52	0.30	0.50	0.42	0.21	3.51	30.46
Steam + Moisture	--	0.08	0.62	--	--	--	0.70
Total	50.08	1.86	2.87	0.91	0.55	5.12	61.39
<u>Output</u>							
Char + Diluent	41.50	0.77	1.19	0.77	0.42	5.13	49.78
Product Gas	0.99	0.30	0.11	0.00	0.04	--	1.44
Oils/Tars	6.94	0.63	0.77	0.07	0.06	0.00	8.47
Aqueous Condensate	0.00	0.18	1.43	0.00	0.00	--	1.61
Total	49.43	1.88	3.50	0.84	0.52	5.13	61.30
Out/In	0.99	1.01	1.22	0.92	0.95	1.00	1.00

Diluent-Free Co-Product Yields, wt % coal

	<u>dry</u>	<u>maf</u>
Char	64.2	62.2
Gas	4.8	5.0
Oils/Tars	28.0	29.6
Water	3.0	3.2
Total	100.0	100.0

Table II-58. TEST IST-14 MATERIAL BALANCES

Coal: West Virginia
 Fluidization Gas: 100% N₂
 Temperature: 1275°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	24.35	1.35	1.52	0.58	0.34	1.64	29.78
Diluent	25.24	0.30	0.40	0.41	0.21	3.59	30.15
Steam + Moisture	--	0.08	0.59	--	--	--	0.67
Total	49.59	1.73	2.51	0.99	0.55	5.23	60.60
<u>Output</u>							
Char + Diluent	43.46	0.56	0.73	0.91	0.40	5.45	51.51
Product Gas	1.68	0.56	0.37	0.00	0.04	--	2.65
Oils/Tars	3.77	0.30	0.28	0.04	0.03	0.00	4.42
Aqueous Condensate	0.00	0.12	0.91	0.00	0.00	--	1.03
Total	48.91	1.54	2.29	0.95	0.47	5.45	58.91
Out/In	0.99	0.89	0.91	0.96	0.85	1.04	0.97

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	24.35	1.35	1.52	0.58	0.34	1.64	29.78
Diluent	25.24	0.30	0.40	0.41	0.21	3.59	30.15
Steam + Moisture	--	0.08	0.59	--	--	--	0.67
Total	49.59	1.73	2.51	0.99	0.55	5.23	60.60
<u>Output</u>							
Char + Diluent	43.46	0.56	0.73	0.91	0.40	5.45	51.51
Product Gas	1.68	0.56	0.37	0.00	0.04	--	2.65
Oils/Tars	4.71	0.38	0.36	0.06	0.03	0.00	5.54
Aqueous Condensate	0.00	0.12	0.91	0.00	0.00	--	1.03
Total	49.85	1.62	2.37	0.97	0.47	5.45	60.73
Out/In	1.01	0.94	0.94	0.98	0.85	1.04	1.00

Diluent-Free Co-Product Yields, wt % coal

	<u>dry</u>	<u>maf</u>
Char	72.1	69.6
Gas	8.9	9.4
Oils/Tars	18.6	19.7
Water	1.2	1.3
Total	100.8	100.0

Table II-59. TEST IST-15 MATERIAL BALANCES

Coal: Rochelle Subbituminous

Fluidization Gas: 100% N₂

Temperature: 1062°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	83.70	5.09	25.42	1.38	0.17	6.74	122.50
Diluent	--	--	--	--	--	--	--
Steam + Moisture	--	2.65	21.05	--	--	--	23.70
Total	83.70	7.74	46.47	1.38	0.17	6.74	146.20
<u>Output</u>							
Char + Diluent	62.93	1.87	6.35	1.18	0.17	6.53	79.03
Product Gas	6.18	0.87	8.80	0.00	0.06	--	15.91
Oils/Tars	7.44	0.75	0.96	0.07	0.02	0.02	9.26
Aqueous Condensate	0.11	2.91	23.10	0.05	0.00	--	26.17
Total	76.66	6.40	39.21	1.30	0.25	6.55	130.37
Out/In	0.92	0.83	0.84	0.94	1.47	0.97	0.89

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	83.70	5.09	25.42	1.38	0.17	6.74	122.50
Diluent	--	--	--	--	--	--	--
Steam + Moisture	--	2.65	21.05	--	--	--	23.70
Total	83.70	7.74	46.47	1.38	0.17	6.74	146.20
<u>Output</u>							
Char + Diluent	62.93	1.87	6.35	1.18	0.17	6.53	79.03
Product Gas	6.18	0.87	8.80	0.00	0.06	--	15.91
Oils/Tars	17.42	1.77	2.44	0.17	0.06	0.04	21.90
Aqueous Condensate	0.12	3.26	25.86	0.06	0.00	--	29.30
Total	86.65	7.77	43.45	1.41	0.29	6.57	146.14
Out/In	1.04	1.00	0.94	1.02	1.71	0.97	1.00

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	64.5	62.6
Gas	13.0	13.7
Oils/Tars	17.9	18.9
Water	4.6	4.8
Total	100.0	100.0

Table II-60. TEST IST-17 MATERIAL BALANCES

Coal: Illinois Sesser Seam

Fluidization Gas: 100% N₂

Temperature: 1288°F

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	21.66	1.27	2.53	0.50	0.31	1.32	27.59
Diluent	26.00	0.09	0.12	0.40	0.22	2.58	29.41
Steam + Moisture	--	0.22	1.78	--	--	--	2.00
Total	47.67	1.58	4.43	0.90	0.53	3.90	59.00
<u>Output</u>							
Char + Diluent	40.22	0.30	0.22	0.75	0.38	3.76	45.63
Product Gas	1.29	0.42	0.48	0.00	0.06	--	2.25
Oils/Tars	3.57	0.31	0.44	0.05	0.03	0.00	4.40
Aqueous Condensate	0.00	0.13	1.10	0.00	0.00	--	1.23
Total	45.08	1.16	2.24	0.80	0.47	3.76	53.51
Out/In	0.95	0.73	0.51	0.89	0.87	0.96	0.91

	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed	21.66	1.27	2.53	0.50	0.31	1.32	27.59
Diluent	26.00	0.09	0.12	0.40	0.22	2.58	29.41
Steam + Moisture	--	0.22	1.78	--	--	--	2.00
Total	47.66	1.58	4.43	0.90	0.53	3.90	59.00
<u>Output</u>							
Char + Diluent	40.21	0.30	0.20	0.75	0.38	3.79	45.63
Product Gas	1.29	0.42	0.48	0.00	0.06	--	2.25
Oils/Tars	5.08	0.44	0.64	0.07	0.04	0.00	6.27
Aqueous Condensate	0.01	0.52	4.16	0.01	0.00	--	4.70
Total	46.59	1.68	5.48	0.83	0.48	3.79	58.85
Out/In	0.98	1.06	1.24	0.92	0.89	0.97	1.00

Diluent-Free Co-Product Yields, wt % coal

	dry	maf
Char	58.8	57.2
Gas	8.2	8.6
Oils/Tars	22.7	23.9
Water	9.8	10.3
Total	99.5	100.0

Figure II-37. CO-PRODUCT YIELDS FROM TASK 2 AND TASK 4 PRU TESTS

made for gas production by diluent devolatilization in Task 2, which may have resulted in slightly overestimated gas yields. For the bituminous coal tests conducted around 1100°F, the oils/tars yields were consistently above 25%, and in some cases exceeded 30%.

The data for the subbituminous coal show the expected lower oils/tars and higher gas yields compared to the bituminous coals. The subbituminous coal data in Table II-59 also show a relatively high carbon content in the aqueous condensate, reflecting the presence of water-soluble organic species which are expected from lower-rank coals.

The effect of CO₂ atmosphere on char, oils/tars, and gas yields from Illinois No. 6 coal (Test IST-8, Table II-52) does not appear to be significant. A suppression of chemical water make seems to be shown by the yield data, but the low hydrogen and oxygen closures cast doubt on the validity of the water yield. The product gas composition, however, is significantly affected by CO₂ in the fluidization medium, as will be discussed later.

Properties of Char

The analytical data on the solid feed materials and char samples from the PRU are given in Tables II-61 through II-71. To show how the char properties were affected by sequential recycle of char, test temperature, and gas atmosphere, the volatile matter, ash, and sulfur contents of the diluent-free chars are given in Table II-72. To normalize these properties to those in the feed coal for each particular test, Table II-72 also shows the volatile matter, ash, and sulfur content of each char expressed as a ratio to the same property of the parent coal used in that test.

Expressed on this basis, the data show that the volatile matter and ash content of the char, reflecting the overall degree of devolatilization, do not change significantly as the coke content of the bed material decreases for Illinois No. 6 coal (Tests IST-5, IST-7, and IST-9). With West Virginia coal, the volatile matter did show some variation with sequential char recycle from Tests IST-10 and IST-11, but the ash ratios did not change. The sulfur content of the char did show some reduction for the Illinois No. 6 coal series, with the char/coal sulfur ratio dropping from 1.13 to 0.95 in Tests IST-5 and IST-7, and further to 0.91 in Test IST-9. The significance of

Table II-61. ANALYSES OF SOLIDS FROM TEST IST-5
(Test Temperature = 1111°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	2.31	3.50	1.12	0.08	0.27	0.45	0.82
Volatile Matter	18.79	34.14	3.44	6.29	11.69	11.98	21.48
Ash	10.70	9.96	11.44	14.25	12.32	12.08	8.20
Fixed Carbon	<u>68.20</u>	<u>52.40</u>	<u>84.00</u>	<u>79.38</u>	<u>75.72</u>	<u>75.49</u>	<u>69.50</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	77.42	69.72	85.12	79.21	77.87	ND	ND
Hydrogen	2.68	5.01	0.35	1.10	2.17	ND	ND
Sulfur	2.71	4.72	0.70	2.31	2.25	ND	ND
Nitrogen	1.35	1.49	1.21	1.44	1.66	ND	ND
Oxygen (by diff.)	4.89	8.73	1.05	1.68	3.70	ND	ND
Ash	<u>10.95</u>	<u>10.33</u>	<u>11.57</u>	<u>14.26</u>	<u>12.35</u>	<u>12.13</u>	<u>8.27</u>
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	3.88	19.30	--	--	--	--
20	--	17.50	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	37.00	--	--	--	--
60	--	25.30	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	0.17	--	--	--	--
100	--	2.11	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	0.00	--	--	--	--
230	--	0.11	0.00	--	--	--	--
270	--	0.11	0.00	--	--	--	--
325	--	0.11	0.00	--	--	--	--
PAN	--	<u>0.18</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done.

Table II-62. ANALYSES OF SOLIDS FROM TEST IST-7
(Test Temperature = 1117°F)

	<u>Feed Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid Bed Char</u>	<u>1st Cyclone Char</u>	<u>2nd Cyclone Char</u>	<u>Carry Over Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	2.68	5.28	0.08	0.30	ND	ND	ND
Volatile Matter	21.48	36.67	6.29	8.12	ND	ND	ND
Ash	13.32	12.39	14.25	17.70	ND	ND	ND
Fixed Carbon	62.52	45.66	79.38	73.88	ND	ND	ND
Total	100.00	100.00	100.00	100.00			
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	72.02	64.83	79.21	74.12	ND	ND	ND
Hydrogen	2.83	4.56	1.10	1.20	ND	ND	ND
Sulfur	3.09	3.87	2.31	2.80	ND	ND	ND
Nitrogen	1.40	1.36	1.44	1.44	ND	ND	ND
Oxygen (by diff.)	6.97	12.26	1.68	2.69	ND	ND	ND
Ash	13.69	13.12	14.26	17.75	ND	ND	ND
Total	100.00	100.00	100.00	100.00			
HHV, Btu/lb	ND	11,599	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	0.00	ND	ND	ND	ND	ND
12	--	3.88	--	--	--	--	--
20	--	17.50	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	--	--	--	--	--
60	--	25.30	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	--	--	--	--	--
100	--	2.11	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	--	--	--	--	--
230	--	0.11	--	--	--	--	--
270	--	0.11	--	--	--	--	--
325	--	0.11	--	--	--	--	--
PAN	--	0.18	--	--	--	--	--
	--	100.00	--	--	--	--	--

ND = analysis not done.

Table II-63. ANALYSES OF SOLIDS FROM TEST IST-8
(Test Temperature = 1102°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	2.87	5.32	0.42	0.34	0.59	1.28	0.00
Volatile Matter	18.63	32.34	4.92	6.16	12.89	11.24	61.96
Ash	12.26	17.14	7.38	15.54	12.21	13.08	31.52
Fixed Carbon	<u>66.24</u>	<u>45.20</u>	<u>87.28</u>	<u>77.96</u>	<u>74.31</u>	<u>74.40</u>	<u>6.52</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	76.01	64.69	87.33	78.53	76.79	ND	ND
Hydrogen	52.28	3.36	1.20	0.80	2.11	ND	ND
Sulfur	2.24	2.49	1.99	1.72	2.13	ND	ND
Nitrogen	1.31	1.29	1.33	1.33	1.65	ND	ND
Oxygen (by diff.)	5.54	10.30	0.78	2.03	5.04	ND	ND
Ash	<u>12.62</u>	<u>17.87</u>	<u>7.37</u>	<u>15.59</u>	<u>12.28</u>	13.25	31.52
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	11,599	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	0.00	ND	ND	ND	ND	ND
12	--	3.88	--	--	--	--	--
20	--	17.50	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	--	--	--	--	--
60	--	25.30	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	--	--	--	--	--
100	--	2.11	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	--	--	--	--	--
230	--	0.11	--	--	--	--	--
270	--	0.11	--	--	--	--	--
325	--	0.11	--	--	--	--	--
PAN	--	<u>0.18</u>	--	--	--	--	--
	--	100.00	--	--	--	--	--

ND = analysis not done.

Table II-64. ANALYSES OF SOLIDS FROM TEST IST-9
(Test Temperature = 1107°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
	-----			wt %	-----		
Moisture	2.68	5.06	0.30	0.20	0.61	1.46	2.77
Volatile Matter	19.49	30.86	8.12	9.65	13.22	14.29	20.92
Ash	16.97	16.24	17.70	22.23	14.85	12.18	42.23
Fixed Carbon	<u>60.86</u>	<u>47.84</u>	<u>73.88</u>	<u>67.92</u>	<u>71.32</u>	<u>72.07</u>	<u>33.08</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	-----			dry wt %	-----		
Carbon	69.55	64.98	74.12	68.95	73.94	ND	ND
Hydrogen	2.58	3.96	1.20	1.19	2.32	ND	ND
Sulfur	3.16	3.52	2.80	2.96	2.41	ND	ND
Nitrogen	1.33	1.22	1.44	1.19	1.68	ND	ND
Oxygen (by diff.)	5.94	9.19	2.69	3.44	4.71	ND	ND
Ash	<u>17.44</u>	<u>17.13</u>	<u>17.75</u>	<u>22.27</u>	<u>14.94</u>	<u>12.36</u>	<u>44.46</u>
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	11,599	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh	-----			wt % retained on screen	-----		
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	3.88	19.30	--	--	--	--
20	--	17.50	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	37.00	--	--	--	--
60	--	25.30	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	0.17	--	--	--	--
100	--	2.11	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	0.00	--	--	--	--
230	--	0.11	0.00	--	--	--	--
270	--	0.11	0.00	--	--	--	--
325	--	0.11	0.00	--	--	--	--
PAN	--	<u>0.18</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done.

Table II-65. ANALYSES OF SOLIDS FROM TEST IST-10
(Test Temperature = 1108°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
	-----			wt %	-----		
Moisture	1.13	2.11	0.15	0.64	0.42	ND	ND
Volatile Matter	16.61	26.44	6.78	7.04	10.05	ND	ND
Ash	8.14	7.50	8.78	9.90	10.10	ND	ND
Fixed Carbon	<u>74.12</u>	<u>63.95</u>	<u>84.29</u>	<u>82.42</u>	<u>79.43</u>	ND	ND
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
<u>Ultimate Analysis</u>							
	-----			dry wt %	-----		
Carbon	82.52	80.95	84.09	83.03	81.12	ND	ND
Hydrogen	2.92	4.24	1.60	1.63	2.32	ND	ND
Sulfur	1.46	1.26	1.66	1.60	1.21	ND	ND
Nitrogen	1.49	1.50	1.48	1.39	1.59	ND	ND
Oxygen (by diff.)	3.38	4.38	2.38	2.45	3.62	ND	ND
Ash	<u>8.23</u>	<u>7.67</u>	<u>8.79</u>	<u>9.90</u>	<u>10.14</u>	ND	ND
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	14,317	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh	-----			wt % retained on screen	-----		
6	ND	0.00	ND	ND	ND	ND	ND
12	--	0.00	--	--	--	--	--
20	--	45.50	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	42.50	--	--	--	--	--
60	--	11.60	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	0.33	--	--	--	--	--
100	--	0.00	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	0.00	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.00	--	--	--	--	--
230	--	0.00	--	--	--	--	--
270	--	0.00	--	--	--	--	--
325	--	0.00	--	--	--	--	--
PAN	--	<u>0.00</u>	--	--	--	--	--
	--	100.00	--	--	--	--	--

ND = analysis not done.

Table II-66. ANALYSES OF SOLIDS FROM TEST IST-11
(Test Temperature = 1110°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	1.34	2.04	0.64	0.98	1.63	2.24	ND
Volatile Matter	16.88	26.72	7.04	8.68	10.23	11.08	ND
Ash	8.53	7.16	9.90	10.41	8.69	7.93	ND
Fixed Carbon	73.25	64.08	82.42	79.93	79.45	78.75	ND
Total	100.00	100.00	100.00	100.00	100.00	100.00	ND
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	82.26	81.49	83.03	82.27	82.35	ND	ND
Hydrogen	3.12	4.61	1.63	1.93	2.43	ND	ND
Sulfur	1.24	0.88	1.60	1.17	1.14	ND	ND
Nitrogen	1.51	1.63	1.39	1.61	1.62	ND	ND
Oxygen (by diff.)	3.22	3.99	2.45	2.51	3.63	ND	ND
Ash	8.65	7.40	9.90	10.51	8.83	ND	ND
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	14,317	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	0.00	ND	ND	ND	ND	ND
12	--	0.00	--	--	--	--	--
20	--	45.50	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	42.50	--	--	--	--	--
60	--	11.60	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	0.33	--	--	--	--	--
100	--	0.00	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	0.00	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.00	--	--	--	--	--
230	--	0.00	--	--	--	--	--
270	--	0.00	--	--	--	--	--
325	--	0.00	--	--	--	--	--
PAN	--	0.07	--	--	--	--	--
	--	100.00	--	--	--	--	--

ND = analysis not done.

Table II-67. ANALYSES OF SOLIDS FROM TEST IST-12
(Test Temperature = 1100°F)

	<u>Feed Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid Bed Char</u>	<u>1st Cyclone Char</u>	<u>2nd Cyclone Char</u>	<u>Carry Over Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	0.90	1.44	0.36	0.50	1.27	ND	ND
Volatile Matter	17.49	33.15	1.83	4.56	9.86	ND	ND
Ash	8.90	5.89	11.91	11.88	10.20	ND	ND
Fixed Carbon	<u>72.71</u>	<u>59.52</u>	<u>85.90</u>	<u>83.06</u>	<u>78.67</u>	ND	ND
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	83.35	80.96	85.74	83.74	81.60	ND	ND
Hydrogen	2.73	5.17	0.29	0.98	2.35	ND	ND
Sulfur	0.80	1.03	0.57	0.70	1.02	ND	ND
Nitrogen	1.33	1.58	1.08	1.34	1.53	ND	ND
Oxygen (by diff.)	2.81	5.25	0.37	1.30	3.17	ND	ND
Ash	<u>8.98</u>	<u>6.01</u>	<u>11.95</u>	<u>11.94</u>	<u>10.33</u>	ND	ND
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	13,540	14,372	12,534	12,749	13,182	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	0.00	0.00	--	--	--	--
20	--	45.50	38.60	--	--	--	--
30	--	--	--	--	--	--	--
40	--	42.50	43.30	--	--	--	--
60	--	11.60	17.20	--	--	--	--
70	--	--	--	--	--	--	--
80	--	0.33	0.30	--	--	--	--
100	--	0.00	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	0.00	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.00	0.30	--	--	--	--
230	--	0.00	0.00	--	--	--	--
270	--	0.00	0.00	--	--	--	--
325	--	0.00	0.00	--	--	--	--
PAN	--	<u>0.07</u>	<u>0.60</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done.

Table II-68. ANALYSES OF SOLIDS FROM TEST IST-13
(Test Temperature = 1084°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	1.15	1.52	0.78	0.56	1.23	1.38	3.28
Volatile Matter	16.82	28.84	4.80	6.78	13.17	12.94	20.66
Ash	8.32	5.20	11.44	10.24	8.90	8.27	56.14
Fixed Carbon	<u>73.71</u>	<u>64.44</u>	<u>82.98</u>	<u>82.42</u>	<u>76.70</u>	<u>77.41</u>	<u>19.92</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	82.52	81.26	83.78	83.38	79.90	ND	ND
Hydrogen	2.93	4.88	0.98	1.54	2.75	ND	ND
Sulfur	0.91	1.12	0.70	0.85	1.37	ND	ND
Nitrogen	1.50	1.63	1.37	1.54	1.66	ND	ND
Oxygen (by diff.)	3.72	5.80	1.64	2.39	5.31	ND	ND
Ash	<u>8.42</u>	<u>5.31</u>	<u>11.53</u>	<u>10.30</u>	<u>9.01</u>	<u>8.39</u>	<u>58.04</u>
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	14,372	12,749	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	0.00	ND	ND	ND	ND	ND
12	--	0.00	--	--	--	--	--
20	--	45.50	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	42.50	--	--	--	--	--
60	--	11.60	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	0.33	--	--	--	--	--
100	--	0.00	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	0.00	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.00	--	--	--	--	--
230	--	0.00	--	--	--	--	--
270	--	0.00	--	--	--	--	--
325	--	0.00	--	--	--	--	--
PAN	--	<u>0.07</u>	--	--	--	--	--
	--	100.00	--	--	--	--	--

ND = analysis not done.

Table II-69. ANALYSES OF SOLIDS FROM TEST IST-14
(Test Temperature = 1275°F)

	<u>Feed</u>			<u>Fluid</u>	<u>1st</u>	<u>2nd</u>	<u>Carry</u>
	<u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Bed</u>	<u>Cyclone</u>	<u>Cyclone</u>	<u>Over</u>
				<u>Char</u>	<u>Char</u>	<u>Char</u>	<u>Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	1.10	1.70	0.50	0.87	1.20	2.22	1.99
Volatile matter	15.32	26.08	4.56	5.30	9.83	11.20	14.01
Ash	8.62	5.36	11.88	10.49	7.86	5.77	11.68
Fixed carbon	<u>74.96</u>	<u>66.86</u>	<u>83.06</u>	<u>83.34</u>	<u>81.11</u>	<u>80.81</u>	<u>72.32</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	82.75	81.76	83.74	84.38	83.26	ND	ND
Hydrogen	2.76	4.54	0.98	1.08	2.22	ND	ND
Sulfur	0.92	1.14	0.70	0.77	1.14	ND	ND
Nitrogen	1.65	1.96	1.34	1.77	2.15	ND	ND
Oxygen (by diff.)	3.20	5.10	1.30	1.42	3.27	ND	ND
Ash	<u>8.72</u>	<u>5.50</u>	<u>11.94</u>	<u>10.58</u>	<u>7.96</u>	<u>5.90</u>	<u>11.92</u>
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	14,372	12,749	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
<u>U.S. Mesh</u>				wt % retained on screen			
6	ND	0.00	ND	ND	ND	ND	ND
12	--	0.00	--	--	--	--	--
20	--	45.50	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	42.50	--	--	--	--	--
60	--	11.60	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	0.33	--	--	--	--	--
100	--	0.00	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	0.00	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.00	--	--	--	--	--
230	--	0.00	--	--	--	--	--
270	--	0.00	--	--	--	--	--
325	--	0.00	--	--	--	--	--
PAN	--	<u>0.07</u>	--	--	--	--	--
	--	100.00	--	--	--	--	--

ND = analysis not done.

Table II-70. ANALYSES OF SOLIDS FROM TEST IST-15
(Test Temperature = 1062°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
				wt %			
Moisture	16.21	16.21	--	0.56	0.74	1.55	6.77
Volatile matter	35.91	35.91	--	18.97	22.09	11.76	15.37
Ash	4.61	4.61	--	8.37	7.22	6.75	21.51
Fixed carbon	43.27	43.27	--	72.10	69.95	79.94	56.35
Total	100.00	100.00	--	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
				dry wt %			
Carbon	68.33	68.33	--	80.16	78.38	ND	ND
Hydrogen	4.15	4.15	--	2.28	2.64	ND	ND
Sulfur	0.14	0.14	--	0.26	0.06	ND	ND
Nitrogen	1.13	1.13	--	1.51	1.47	ND	ND
Oxygen (by diff.)	20.75	20.75	--	7.37	10.18	ND	ND
Ash	5.50	5.50	--	8.42	7.27	6.86	23.07
Total	100.00	100.00	--	100.00	100.00	ND	ND
HHV, Btu/lb	11,219	11,219	--	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh				wt % retained on screen			
6	ND	ND	ND	ND	ND	ND	ND
12	--	--	--	--	--	--	--
20	--	--	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	--	--	--	--	--	--
60	--	--	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	--	--	--	--	--	--
100	--	--	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	--	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	--	--	--	--	--	--
230	--	--	--	--	--	--	--
270	--	--	--	--	--	--	--
325	--	--	--	--	--	--	--
PAN	--	--	--	--	--	--	--

ND = analysis not done.

Table II-71. ANALYSES OF SOLIDS FROM TEST IST-17
(Test Temperature = 1288°F)

	<u>Feed</u> <u>Mixture</u>	<u>Coal</u>	<u>Diluent</u>	<u>Fluid</u> <u>Bed</u> <u>Char</u>	<u>1st</u> <u>Cyclone</u> <u>Char</u>	<u>2nd</u> <u>Cyclone</u> <u>Char</u>	<u>Carry</u> <u>Over</u> <u>Char</u>
<u>Proximate Analysis</u>							
	-----			wt %	-----		
Moisture	3.39	6.47	0.31	0.42	0.82	2.26	2.35
Volatile matter	15.87	30.24	1.50	2.71	6.66	8.71	16.07
Ash	6.61	4.36	8.86	9.04	6.51	5.82	11.89
Fixed carbon	<u>74.13</u>	<u>58.93</u>	<u>89.33</u>	<u>87.83</u>	<u>86.01</u>	<u>83.21</u>	<u>69.69</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	-----			dry wt %	-----		
Carbon	83.62	78.49	88.75	88.20	87.94	ND	ND
Hydrogen	2.38	4.59	0.17	0.34	1.33	ND	ND
Sulfur	0.94	1.14	0.74	0.82	0.87	ND	ND
Nitrogen	1.58	1.83	1.33	1.47	1.99	ND	ND
Oxygen (by diff.)	4.64	9.16	0.12	0.09	1.31	ND	ND
Ash	<u>6.84</u>	<u>4.79</u>	<u>8.89</u>	<u>9.08</u>	<u>6.56</u>	<u>5.95</u>	<u>12.18</u>
Total	100.00	100.00	100.00	100.00	100.00	ND	ND
HHV, Btu/lb	ND	ND	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U.S. Mesh	-----			wt % retained on screen	-----		
6	ND	ND	ND	ND	ND	ND	ND
12	--	--	--	--	--	--	--
20	--	--	--	--	--	--	--
30	--	--	--	--	--	--	--
40	--	--	--	--	--	--	--
60	--	--	--	--	--	--	--
70	--	--	--	--	--	--	--
80	--	--	--	--	--	--	--
100	--	--	--	--	--	--	--
120	--	--	--	--	--	--	--
140	--	--	--	--	--	--	--
170	--	--	--	--	--	--	--
200	--	--	--	--	--	--	--
230	--	--	--	--	--	--	--
270	--	--	--	--	--	--	--
325	--	--	--	--	--	--	--
PAN	--	--	--	--	--	--	--

ND = analysis not done.

Table II-72. DILUENT-FREE CHAR PROPERTIES WITH NORMALIZATION

Test Number	<u>IST-5</u>	<u>IST-7</u>	<u>IST-8</u>	<u>IST-9</u>
Feed Coal	IL No. 6	IL No. 6	IL No. 6	IL No. 6
Test Temperature, °F	1111	1117	1102	1107
	----- dry wt % -----			
Volatile Matter	11.4	13.4	8.0	11.8
VM _{char} /VM _{coal}	0.32	0.35	0.23	0.36
Ash	19.3	24.9	29.0	30.5
Ash _{char} /Ash _{coal}	1.87	1.90	1.60	1.79
Sulfur	5.3	3.7	1.2	3.2
S _{char} /S _{coal}	1.13	0.95	0.49	0.91

Test Number	<u>IST-10</u>	<u>IST-11</u>	<u>IST-12</u>	<u>IST-13</u>
Feed Coal	WV	WV	WV	WV
Test Temperature, °F	1108	1110	1100	1084
	----- dry wt % -----			
Volatile Matter	7.6	11.4	9.3	10.0
VM _{char} /VM _{coal}	0.28	0.42	0.28	0.34
Ash	11.5	11.4	11.7	8.3
Ash _{char} /Ash _{coal}	1.51	1.57	1.96	1.58
Sulfur	1.5	0.5	0.9	1.1
S _{char} /S _{coal}	1.19	0.58	0.89	0.96

Test Number	<u>IST-14</u>	<u>IST-15</u>	<u>IST-17</u>
Feed Coal	WV	Rochelle	IL Sesser
Test Temperature, °F	1275	1062	1288
	----- dry wt % -----		
Volatile Matter	6.4	19.8	8.7
VM _{char} /VM _{coal}	0.24	1.02	0.27
Ash	8.5	8.3	7.5
Ash _{char} /Ash _{coal}	1.56	1.50	1.60
Sulfur	0.9	0.2	1.0
S _{char} /S _{coal}	0.76	1.50	0.83

this observation is difficult to interpret, since the situation is complicated by the fact that the starting coke diluent and subsequent char diluents contain sulfur, and the coal sulfur content shows significant variation from test to test. It is not possible to determine the individual fates of sulfur from the feed coal and the diluents. However, the observation is worth making, since the sulfur content of the char can be important in determining char upgrading requirements. The char/coal sulfur ratio also decreased with sequential char recycle for the West Virginia coal in Tests IST-10 and IST-11.

Perhaps of greater significance is the observed effects of 19% CO_2 in the fluidization gas in Test IST-8. Compared to Test IST-5 which was conducted under similar conditions except for the use of 100% nitrogen in the gas, Test IST-8 yielded a diluent-free char with less than half the sulfur content, based on the normalized char/coal sulfur ratios. As will be shown, the co-product fuel gas also contained more H_2S from Test IST-8, which is consistent with a lower char sulfur content. This finding, while interesting, does not suggest a mechanism for the reduction of char sulfur in the presence of CO_2 . Further investigations in this area are recommended.

Properties of Oils/Tars

Tables II-73 and II-74 show the properties of oils/tars from the slipstream sampling system for the Task 4 PRU tests. Table II-73 gives the elemental analyses of the oils/tars and the simulated distillation results, which are related to the boiling curves and, consequently, the degree of cracking and/or degradation of the liquids. The aromaticity of Illinois No. 6 oils/tars, reflected by the atomic H/C ratio, showed some decrease (1.09 to 1.18) with sequential char recycle (Tests IST-5, IST-7, and IST-9), and the distillation curve also showed a marginally lighter product from the test with increased char content in the diluent. Table II-74 supports these data by showing more light and middle oils and less pitch in the IST-9 oils/tars compared to IST-5. This indicates that recycled mild gasification char may have some effect on the properties of the co-product liquids, which had been a recognized possibility based on the previous observations of Tyler.³ However, this effect does not seem to be very great, and may be within analytical error. In any case, there does not appear to be the very large loss of oils/tars that was reported by Tyler at CSIRO. With the West Virginia coal, the sequential char recycle in Tests IST-10 and IST-11 did not show any

Table II-73, Part 1. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	IST-5	IST-7	IST-8	IST-9
Feed Coal	Ill No. 6	Ill No. 6	Ill No. 6	Ill No. 6
Test Temperature, °F	1111	1117	1102	1107
Elemental Analysis of				
<u>Oils and Tars^a</u>	dry wt %			
Ash	0.37	0.46	0.09	0.22
Carbon	78.14	76.44	77.83	76.06
Hydrogen	7.17	6.92	7.44	7.53
Nitrogen	0.85	0.76	0.54	0.72
Sulfur	2.22	2.24	1.97	1.94
Oxygen (by diff.)	<u>11.25</u>	<u>13.18</u>	<u>12.13</u>	<u>12.53</u>
Total	100.00	100.00	100.00	100.00
H/C Atomic Ratio	1.09	1.08	1.14	1.18
Simulate Distillation				
by Gas Chromatography ^b				
<u>Cumulative Wt % Recovered</u>	Boiling Point, °F			
5	399	ND	ND	334
10	482	--	--	393
15	555	--	--	453
20	622	--	--	515
30	752	--	--	646
40	891	--	--	792
50	--	--	--	971
60	--	--	--	--
70	--	--	--	--
EP (end point) ^c	1040	--	--	1040
% Residue at EP	51.75	--	--	46.90

^a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

^b Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

^c Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-73, Part 2. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	IST-10	IST-11	IST-12	IST-13
Feed Coal	WV	WV	WV	WV
Test Temperature, °F	1108	1110	1100	1084
Elemental Analysis of Oils and Tars ^a	----- dry wt % -----			
Ash	0.33	0.08	0.79	0.04
Carbon	79.93	80.18	79.36	81.50
Hydrogen	7.45	7.17	7.40	7.34
Nitrogen	0.73	0.90	0.89	0.89
Sulfur	0.88	0.53	0.83	0.72
Oxygen (by diff.)	10.68	11.14	10.73	9.51
Total	100.00	100.00	100.00	100.00
H/C Atomic Ratio	1.11	1.07	1.11	1.07
Simulate Distillation by Gas Chromatography ^b	----- Boiling Point, °F -----			
Cumulative Wt % Recovered				
5	357	ND	344	354
10	436	--	426	451
15	508	--	514	558
20	575	--	607	673
30	703	--	813	902
40	827	--	1040	--
50	956	--	--	--
60	--	--	--	--
70	--	--	--	--
EP (end point) ^c	1040	--	1040	1040
% Residue at EP	43.88	--	60.02	63.22

^a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

^b Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

^c Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-73, Part 3. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	IST-14	IST-15	IST-17
Feed Coal	WV	Rochelle	Ill Sesser
Test Temperature, °F	1275	1062	1288
Elemental Analysis of Oils and Tars ^a	----- dry wt % -----		
Ash	0.00	0.20	0.00
Carbon	84.14	78.98	80.46
Hydrogen	6.58	8.04	6.87
Nitrogen	1.20	0.82	1.23
Sulfur	0.67	0.27	0.71
Oxygen (by diff.)	7.41	11.69	10.73
Total	100.00	100.00	100.00
H/C Atomic Ratio	0.93	1.21	1.02
Simulate Distillation by Gas Chromatography ^b	----- Boiling Point, °F -----		
Cumulative Wt % Recovered			
5	323	329	288
10	388	364	314
15	458	402	342
20	535	440	372
30	706	523	437
40	890	618	511
50	--	733	596
60	--	904	697
70	--	--	814
EP (end point) ^c	1040	1040	1040
% Residue at EP	51.54	36.93	12.85

^a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

^b Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

^c Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table II-74, Part 1. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	IST-5	IST-7	IST-8	IST-9
Feed Coal	Ill No. 6	Ill No. 6	Ill No. 6	Ill No. 6
Test Temperature, °F	1111	1117	1102	1107
<u>Component</u>				
	-----	Wt % of total oils/tars ^a		-----
Benzene	0.7	1.3	0.2	0.6
Toluene	0.5	0.6	0.6	0.4
Xylenes	0.4	0.4	0.4	0.4
Ethylbenzene	0.1	0.1	0.1	0.1
Indene	0.2	0.2	0.02	0.02
Styrene	0.1	0.1	0.1	0.1
Other Light Oils	<u>5.5</u>	ND	ND	<u>9.9</u>
Total Light Oil ^b	7.5	ND	ND	11.5
Phenol	0.8	0.8	0.8	0.6
Cresols	1.9	1.5	1.8	1.4
Xylenols	2.3	2.3	2.0	1.7
Naphthalene	0.4	0.6	0.1	0.1
Other Middle Oils	<u>8.5</u>	ND	ND	<u>14.0</u>
Total Middle Oil ^c	13.9	ND	ND	17.8
Heavy Oil ^d	11.7	ND	ND	10.9
Pitch ^e	<u>66.9</u>	ND	ND	<u>59.9</u>
Total Oils and Tars	100.0	ND	ND	100.0

^a Includes light oils that are not included in the oils and tars of Table 26.

^b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

^c Atmospheric boiling point 360° to 590°F.

^d Atmospheric boiling point 590° to 750°F.

^e Atmospheric boiling point > 750°F.

Table II-74, Part 2. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	<u>IST-10</u>	<u>IST-11</u>	<u>IST-12</u>	<u>IST-13</u>
Feed Coal	WV	WV	WV	WV
Test Temperature, °F	1108	1110	1100	1084
<u>Component</u>	Wt % of total oils/tars ^a			
Benzene	0.7	0.1	0.1	0.4
Toluene	0.5	0.5	0.4	0.4
Xylenes	0.4	0.5	0.3	0.5
Ethylbenzene	0.1	0.1	0.1	0.1
Indene	0.04	0.1	0.1	0.1
Styrene	0.1	0.1	0.1	0.1
Other Light Oils	<u>9.1</u>	ND	<u>11.9</u>	<u>7.9</u>
Total Light Oil ^b	10.9	ND	13.0	9.5
Phenol	0.4	0.1	0.3	0.3
Cresols	0.8	0.9	1.0	0.8
Xylenols	1.2	1.1	1.5	1.2
Naphthalene	0.1	0.2	0.4	0.1
Other Middle Oils	<u>12.5</u>	ND	<u>8.9</u>	<u>8.2</u>
Total Middle Oil ^c	15.0	ND	12.1	10.6
Heavy Oil ^d	11.9	ND	7.4	6.6
Pitch ^e	<u>62.2</u>	ND	<u>67.5</u>	<u>73.3</u>
Total Oils and Tars	100.0	ND	100.0	100.0

^a Includes light oils that are not included in the oils and tars of Table 26.

^b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

^c Atmospheric boiling point 360° to 590°F.

^d Atmospheric boiling point 590° to 750°F.

^e Atmospheric boiling point > 750°F.

Table II-74, Part 3. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	<u>IST-14</u>	<u>IST-15</u>	<u>IST-17</u>
Feed Coal	WV	Rochelle	Ill Sesser
Test Temperature, °F	1275	1062	1288
<u>Component</u>	--- Wt % of total oils/tars ^a ---		
Benzene	2.1	1.4	1.3
Toluene	1.3	1.4	1.1
Xylenes	0.8	0.9	0.7
Ethylbenzene	0.1	0.2	0.1
Indene	0.4	0.2	0.3
Styrene	0.2	0.1	0.2
Other Light Oils	<u>15.6</u>	<u>14.4</u>	<u>19.2</u>
Total Light Oil ^b	20.5	18.6	22.9
Phenol	0.5	2.1	1.4
Cresols	1.1	2.1	3.0
Xylenols	1.7	2.1	3.1
Naphthalene	0.3	0.3	0.3
Other Middle Oils	<u>9.8</u>	<u>18.4</u>	<u>21.6</u>
Total Middle Oil ^c	13.4	25.0	29.4
Heavy Oil ^d	7.8	12.6	14.5
Pitch ^e	<u>58.3</u>	<u>43.7</u>	<u>33.2</u>
Total Oils and Tars	100.0	100.0	100.0

^a Includes light oils that are not included in the oils and tars of Table 26.

^b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

^c Atmospheric boiling point 360° to 590°F.

^d Atmospheric boiling point 590° to 750°F.

^e Atmospheric boiling point > 750°F.

significant effects, but a noticeable difference in the distillation curves between Tests IST-10 and IST-12 (the 12-hour test to generate char for form coke testing) and also between Tests IST-10 and IST-13, which used recycled char from Test IST-12 as a diluent, are also shown in Table II-73. The oils/tars from Test IST-12 are considerably heavier, with a 60% residue at end point compared to 44% in Test IST-10. The oils/tars from Test IST-13 were even heavier, with a 63% residue at the 1040°F distillation end point. The difference in distillation behavior between Tests IST-10 and IST-12 was not accompanied by a change in aromaticity, and thus it seems unlikely that it can be attributed to any difference in reactor conditions. These tests were also conducted at the same fluidized-bed temperatures. These observation may be an indication of the sensitivity of the oils/tars to aging and/or exposure to air, although precautions were taken in sample handling and storage to minimize air exposure. The high oxygen content of these liquids can be taken as an indication of phenolic groups which tend to promote changes in the liquid properties upon storage. The oils/tars from Test IST-14, conducted at a higher temperature of 1275°F, showed a higher aromaticity (H/C ratio of 0.93) and a lower oxygen content, but actually was lower-boiling compared to the Test IST-12 liquids.

As expected, the oils/tars from the subbituminous coal (Test IST-15) were much lighter (residue at end point = 37%) and less aromatic (H/C ratio = 1.21) than the bituminous coal liquids. The condensables from Test IST-15 were also observed to be much more fluid than the oils/tars from the bituminous coals, which were virtually solid at room temperature.

The oils/tars from the Illinois Sesser coal were also quite different from those observed with either the Illinois No. 6 or the West Virginia coal, in that they were very light, leaving only 13% residue at the distillation end point of 1040°F. This liquid was also reported to be quite fluid at ambient conditions, although the aromaticity (H/C ratio = 1.02) was similar to that of oils/tars from the other bituminous coals. This underscores the variability of co-products from different feedstocks, even within the same coal seam, since the Sesser coal is considered to be contiguous with the No. 6 seam, although it has unusually low sulfur and ash contents.

Oils/Tars From Full-Stream Condensate System

The oils/tars collected in xylene quench solvent from the full-stream condensate system in Tests IST-5, IST-7, and IST-9 through IST-12 were subjected to distillation to remove the xylene solvent. The tar-laden solvent was filtered to remove char solids, which were washed with fresh xylene. The filtrate was then distilled to an overhead temperature of 307°F, with a maximum pot temperature of about 500°F. The boiling range of xylenes is from 280° to 291°F. The undistilled filtrate, the overheads, and the pot residue were all analyzed for major components by GC, and the residue was also subjected to elemental analysis. Table II-75 shows the results of these analyses, which can be compared with slipstream sampling data shown in Tables II-73 and II-74.

In general, the full-stream condensate system condenses only a minor fraction of the light oils (b.p. <360°F), and those light oils that do condense are mostly removed with the xylene solvent in the distillation. Consequently, the distillation residues, as shown in Table II-75, consist primarily of heavy oils and pitch (b.p. >590°F). In the process of distillation of the xylene, the middle oils are partitioned between the distillate (overheads) and the tar (residue). This partitioning is shown in Table II-76 for Test IST-5. As shown, the point at which a tar species distributes equally between the distillate and the residue comes at about the C₂-phenols, which boil in the range of 397° to 441°F. Thus, the tar residue contains less than half of the original components which boil below this temperature range, which includes most of the monoaromatic phenols. This explains the reduced oxygen in the tar residues, compared to slipstream oils/tars from the same tests shown in Table II-73. Another notable difference is seen in the phenolic species content of the full-stream quench tars from the Illinois No. 6 coal tests and the West Virginia coal tests. The West Virginia coal liquids consistently contain lower levels of phenols.

A preliminary evaluation was made of xylene quench tars from Tests IST-9 (Illinois No. 6 coal) and IST-10 (West Virginia coal) by Reilly Industries. The samples, which were black glassy solids at room temperature, were subjected to the following key analyses: distillation (ASTM D20), quinoline insolubles (QI) (ASTM D2318), coking value (ASTM D2416), "aliphaticity"* via

* Indicator of aliphatic vs. aromatic C-H bonds.

Table II-75. OILS/TARS DATA FROM FULL-STREAM CONDENSATE SYSTEM

Test Number	IST-5	IST-7	IST-9	IST-10
Feed Coal	Ill No. 6	Ill No. 6	Ill No. 6	WV
Test Temperature, °F	1111	1117	1107	1108
Total sample, lb	149.2	147.3	308.4	261.8
Solids, lb	5.5	5.4	4.9	8.1
Distillate (overhead), lb	138.2	139.1	251.0	236.5
Tar (residue), lb	10.9	8.1	9.3	17.1
Loss, lb	0.1	0.1	0.4	0.2
Adjusted Oils/Tars ^a , lb	10.9	8.3	9.8	17.7
<u>Elemental Analysis^b</u>	----- dry wt % -----			
Ash	0.0	0.1	0.0	0.0
Carbon	83.2	82.3	82.5	87.0
Hydrogen	7.1	7.0	7.5	7.3
Nitrogen	0.8	0.9	0.8	0.8
Sulfur	2.4	2.2	2.2	0.8
Oxygen (by diff)	6.5	7.5	7.0	4.1
Total	100.0	100.0	100.0	100.0
H/C Atomic Ratio	1.01	1.01	1.08	1.01
HHV, Btu/lb (calc)	15665	15454	15751	16564
<u>Component Analysis^c</u>	----- Wt % of total oils/tars -----			
Benzene	0.05	0.03	0.01	0.02
Indene	0.06	0.08	0.00	0.05
Other <360°F	0.46	0.24	0.93	1.55
Phenol ^d	0.23	0.21	0.20	0.07
o-Cresol	0.46	0.54	0.65	0.35
m,p-Cresols	1.39	1.56	1.84	0.65
C ₂ -phenols	2.09	2.44	2.28	1.51
Naphthalene	0.11	0.14	0.16	0.15
C ₁ -Naphthalenes	0.65	0.76	0.13	0.61
Other 360°-590°F	7.43	8.12	6.23	7.04
590°-750°F	10.09	11.00	7.28	11.73
>750°F	76.98	74.88	80.29	76.27

^a Calculated from chromatographable tar in overhead + tar residue - retained solvent.

^b Distillation residue only.

^c Toluene, xylenes, ethylbenzene, and styrene are obscured by xylene solvent.

^d Phenol in distillate is obscured by C₃-benzene peak in xylene solvent; value reported is from tar residue only.

Table II-75, Cont. OILS/TARS DATA FROM FULL-STREAM CONDENSATE SYSTEM

Test Number	IST-11	IST-12
Feed Coal	WV	WV
Test Temperature, °F	1110	1100
Total Sample, lb	232.7	350.2
Solids, lb	2.0	5.9
Distillate (overhead), lb	158.7	292.5
Tar (residue), lb	18.2	51.7
Loss, lb	0.1	0.0
Adjusted Oils/Tars ^a , lb	24.1	57.8
<u>Elemental Analysis^b</u>	----- dry wt % -----	
Ash	0.0	ND
Carbon	87.0	ND
Hydrogen	7.4	ND
Nitrogen	0.1	ND
Sulfur	0.8	ND
Oxygen (by diff)	4.7	ND
Total	100.0	ND
H/C Atomic Ratio	1.01	ND
HEV, Btu/lb (calc)	16530	ND
<u>Component Analysis^c</u>	- Wt % of total oils/tars -	
Benzene	0.01	0.10
Indene	0.06	0.08
Other <360°F	0.73	0.50
Phenol ^d	0.08	0.19
o-Cresol	0.26	0.29
m,p-Cresols	0.38	0.41
C ₂ -phenols	1.01	1.30
Naphthalene	0.07	0.10
C ₁ -Naphthalenes	0.44	0.51
Other 360°-590°F	8.37	9.38
590°-750°F	24.93	20.02
>750°F	63.66	67.12

^a Calculated from chromatographable tar in overhead + tar residue - retained solvent.

^b Distillation residue only.

^c Toluene, xylenes, ethylbenzene, and styrene are obscured by xylene solvent.

^d Phenol in distillate is obscured by C₃-benzene peak in xylene solvent; value reported is from tar residue only.

Table II-76. PARTITIONING OF FULL-STREAM QUENCH COMPONENTS IN DISTILLATION
(Test IST-5)

<u>Component</u>	<u>B.P., °F</u>	<u>Distillate</u>	<u>Residue</u>
Indene	360	88.2	11.8
o-Cresol	376	81.9	18.1
m,p-Cresols	396-397	75.4	24.6
C ₂ -Phenols	397-441	53.7	46.3
Naphthalene	424	59.0	41.0
C ₁ -Naphthalenes	464-469	18.1	81.9

IR index, and GC/MS analyses for major components. Later, a THF extract of entrained char particles filtered from the Test IST-13 xylene quench and a sample of 360°F+ oils/tars from slipstream sampling in Test IST-14 were subjected to the QI and IR index tests, along with a determination of the fraction of aromatic H (f_a) by NMR. The distillation was not performed with the latter two samples.

The results from all of these analyses are shown in Table II-77. In the ASTM distillation, the Tests IST-9 and IST-10 samples both underwent coking/decomposition at 360°C with evolution of water and gas, thus negating the opportunity for a softening point determination. This is considered typical behavior for low-temperature pitch which has not been upgraded by conventional (thermal) processing. The IR index, which is a ratio of peak areas for aliphatic C-H and aromatic C-H bands, showed a low aromatic C-H content (high index) compared to a specification-grade coke-oven tar pitch. The WV coal mild gasification tar had a higher aromaticity than the Illinois coal xylene-quench tar. Quinoline insolubles (QI) were very low (0.01%) for the WV xylene-quench tar, and was not determined for the Illinois tar, but this was attributed to the xylene quench solvent, which could not adequately recover the QI resins from the product stream. The slipstream oils/tars from Test IST-14 contained an order of magnitude more QI, indicating that the stronger THF solvent used to clean out the slipstream system can dissolve or disperse more of the QI present in the mild gasification liquids, and confirming the underestimation of QI based on the xylene quench liquids. This also suggests that additional QI may be recoverable in the neat tar. The present PRU setup requires a quench solvent, and thus does not allow for recovery of a neat tar. The conceptual design for the 24-ton/day PDU, however, would include provisions for condensing the heavier fractions of the mild gasification oils/tars

Table II-77. EVALUATION OF TAR SAMPLES BY REILLY INDUSTRIES

	Xylene		Xylene		Quench		Slipstream		Coke Oven
	Quench Tar Test IST-9	Quench Tar Test IST-10	Solids	THF Extract Test Ist-13	Oils/Tars Test IST-14	Tar			
Distillation (ASTM D20)									
0-170°C	1.3	0.0	ND	ND	ND	2.0			
210	3.7	1.9	--	--	--	6.0			
235	6.6	3.7	--	--	--	13.0			
270	14.9	8.6	--	--	--	24.0			
300	24.8	13.6	--	--	--	29.0			
315	29.1	17.6	--	--	--	38.0			
360	53.9	28.9	--	--	--	NA			
400	ND	49.1	--	--	--	NA			
Residue	46.1	50.9	--	--	--	62.0			
QI (ASTM D2318)	ND	0.01	0.002	0.002	0.23	2.0			
Coking Value (ASTM D2416)	28.61	34.87	ND	ND	ND	30.0			
IR Index (aliphaticity)	7.4	4.8	10.2	10.2	3.0	-0.5*			
f _a by NMR (aromaticity)	ND	ND	0.71	0.71	0.79	-0.95*			
GC Analysis									
Phenol	1.34	1.11	3.47	3.47	3.02	2.0			
C ₁ -phenols	2.73	1.50	4.92	4.92	5.49				
C ₂ -phenols	3.68	2.65	7.28	7.28	7.59	8.0			
Naphtahlene	0.61	0.96	1.63	1.63	2.81				
C ₁ -naphthalenes	2.35	2.98	6.72	6.72	7.14	ND			
C ₂ -naphthalenes	0.59	ND	ND	ND	ND	ND			
Fluorene	0.59	1.08	ND	ND	ND	ND			
Phenanthrene	0.42	1.23	ND	ND	ND	ND			
Anthracene	1.06	1.31	ND	ND	ND	ND			
Pyrene	3.79	3.83	ND	ND	ND	ND			

ND = not determined.

* Value shown is for binder pitches derived from coke-oven tar.

without a quench solvent, thus allowing recovery of all of the QI present in the liquids. For electrode binder pitch, a QI content of 4% to 12% is considered suitable, but a lower QI-content pitch is desirable as an impregnation pitch for graphite articles. The coking value of the West Virginia tar was 34.9%, which is satisfactory for binders, but the Illinois coal tar coking value was low at 28.6%.

On the positive side, both of the tars had virtually no ash. The sulfur content of the WV tar was 0.88 weight percent, which is not far from the 0.5 weight percent considered acceptable for an electrode binder pitch. The tar from the high-sulfur Illinois coal contained 1.94 weight percent sulfur.

It is apparent from these data that the mild gasification pitch would require post-treatment to increase aromaticity and remove heteroatoms in order to be acceptable for electrode binders. Mr. W. Roder of Reilly Industries suggests that an on-stream thermal upgrading step prior to tar condensation has the potential to render mild gasification liquids acceptable for binder pitch production. A liquids recovery system design that condenses the higher-boiling fraction of the oils/tars neat would maximize the QI content of the pitch and thus may reduce the upgrading requirement for meeting electrode binder pitch specifications.

Properties of Fuel Gas

The gas compositions from the Task 4 PRU tests were determined both by on-line and off-line gas chromatography. The average nitrogen-free compositions are shown in Table II-78.

For Test IST-8, which was conducted under 19% CO₂ atmosphere, a different correction was used. Since the fluidization gas contains about two orders of magnitude more CO₂ than would be expected from coal devolatilization in the PRU, the coal-generated CO₂ in the product gas was assumed to be equal to that in Test IST-5, which was conducted under similar conditions except for the fluidization gas. The H₂ content of the gas from this test was comparatively low, and the CO content comparatively high. This can be attributed to the water-gas shift equilibrium, which is affected by the large excess of CO₂ in the mild gasification atmosphere. The CO₂ drives the reaction in the direction that produces CO and H₂O, reducing the concentration of H₂. The other major difference in the gas from Test IST-8 is the high level of H₂S,

Table II-78. GAS COMPOSITIONS

Test Number	IST-5	IST-7	IST-8	IST-9	IST-10	IST-11	IST-12	IST-13	IST-14	IST-15	IST-17
Test Temperature, °F	1111	1117	1102	1107	1108	1110	1100	1084	1275	1062	1288
Component	Mol % in gas, nitrogen-free										
H ₂	22.1	22.8	4.4	25.7	17.0	22.0	26.5	21.4	42.9	21.5	42.4
CO	15.1	13.5	20.2	12.6	5.6	5.3	1.9	3.1	7.1	17.1	12.3
CO ₂	8.5	14.3	11.4	12.2	4.8	7.3	2.2	2.8	2.4	37.8	3.3
CH ₄	33.4	33.6	38.7	27.4	53.0	47.2	48.5	52.4	34.5	16.7	31.4
C ₂ H ₄	4.6	4.8	5.1	5.0	6.3	5.4	7.5	7.0	5.7	2.5	4.3
C ₂ H ₆	6.6	5.1	7.7	6.3	7.4	7.4	7.2	6.6	3.4	2.1	3.3
C ₃ H ₆	2.9	1.8	2.3	2.7	3.1	3.0	4.2	3.3	2.8	1.5	1.5
C ₃ H ₈	1.3	0.7	1.2	0.7	1.4	1.5	1.6	2.0	0.6	0.5	0.4
H ₂ S	5.5	3.4	9.0	7.4	1.4	0.9	0.4	1.4	0.6	0.3	1.1
Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Molecular Weight	20.7	21.0	25.3	21.1	18.9	18.7	16.7	17.6	13.8	26.8	14.2
Higher Heating Value, Btu/SCF	781	702	826	718	956	895	968	971	744	419	672

which, combined with the observed low sulfur content of the char, indicates that mild gasification in the presence of CO_2 may increase the release of sulfur into the gas phase. The possible mechanism for this effect is not known.

The co-product gas from the subbituminous coal, Test IST-15, shows the expected higher level of CO_x and lower level of H_2 , which result in a lower heating value for the gas. The H_2S content is also very low, because of the low sulfur content of the feed coal.

Impact of Data on Scale-Up Design

Five significant results of the Task 4 PRU tests have been identified as having an impact on the scale-up design for the 24-ton/day PDU:

- The batchwise char recycle for both Illinois No. 6 coal and West Virginia coal confirms that mild gasification char, in a 1:1 ratio to coal, is effective as a diluent for processing caking coals in the mild gasification reactor without causing significant destruction of valuable co-products (oils/tars).
- The mild gasification reactor system can process low-rank noncaking coals for extended periods without the need for a diluent.
- The use of recycled flue gases, containing up to 19% CO_2 , from combustion of co-product fuel gas as a heat carrier and fluidization medium is technically feasible without causing any adverse effects on the yield and quality of co-products.
- The physical properties of the oils/tars, which are important for design of condensables recovery equipment, are greatly dependent on the feed coal properties; the Illinois Sessler coal, while similar in rank and elemental composition to Illinois No. 6, yielded a much less viscous condensable product than the Illinois No. 6 or West Virginia coals.
- It has been concluded that mild gasification oils/tars may require on-stream upgrading prior to cooling and condensation in order to render them suitable for production of binder pitches; the final PDU design should address this factor by including the necessary equipment to thermally and/or catalytically alter the condensables to meet the industrial requirements for these feedstocks.

These findings will be factored into the Task 4 scale-up design.

Impact of Data on Marketing of Co-Products

The upgrading of the principal co-product, char, is being concurrently studied under Task 3, Bench-Scale Char Upgrading Study. Char from the Task 4 PRU tests with West Virginia coal will be converted to form coke briquettes

for evaluation of key physical and chemical properties. The results of that testing will be reported separately in the Task 3 Topical Report.

Another important finding which relates to the marketing of co-products concerns the suitability of mild gasification oils/tars for electrode binder pitch. It was determined in consultation with the Industrial Products Advisory Group (IPAG) that the untreated mild gasification oils/tars would not meet the specifications for premium electrode binder pitches, due to low aromaticity, high heteroatom content, and insufficient high-molecular-weight β -resin (QI) content. A possible approach to on-stream upgrading consists of a downstream exposure of condensables-laden product gas to high temperatures ($\sim 1800^\circ\text{F}$) to convert the oils/tars into forms favorable to binder pitch production. The effects of such treatment on the yields of other valuable chemicals, such as BTX and phenols, must also be investigated. It is expected that thermal treatment of oils/tars will reduce the heteroatom content and increase the aromaticity, primarily by dealkylation of aromatic centers in the high-boiling organic species.

Conclusions

The Task 4 investigations in the mild gasification PRU have confirmed the technical viability of the process in several areas. Recycled mild gasification char has been substituted for the coke breeze diluent previously used to process caking coals, and the products have been characterized showing no adverse effects of char recycle. Oils/tars yields in excess of 25% maf coal were consistently obtained from high-volatile bituminous coals. Two Illinois bituminous coals and a West Virginia bituminous coal have been successfully processed for steady-state test periods of up to 12 hours using a 1:1 char diluent, which simulates the char recycle that is indicated in the scale-up design of the mild gasification reactor. The use of a simulated flue gas (19% CO_2 /81% N_2) based on combustion of mild gasification co-product fuel gas as a fluidization medium was also demonstrated.

The ability of the fluidized-bed/entrained reactor to process 100% non-caking subbituminous coal for extended periods at the design feed rate of 100 lb/h was confirmed, and co-products were compared with those from caking coals.

A full-stream quench system for collection of large batches of oils/tars was successfully operated in the Task 4 tests, producing batches of heavy oil/pitch fractions of up to 52 pounds from a single test. Large batches of mild gasification char were also produced for upgrading to form coke and/or smokeless fuel briquettes in Task 3.

The evaluation of co-products for industrial utilization has continued throughout the program, and important information for upgrading of oils/tars to produce premium binder pitches were obtained from examination of the full-stream quench oils/tars by an IPAG member tar processing company. These discussions have led to a decision to include an on-stream tar upgrading step in the mild gasification PDU design.

References Cited

1. Wootten, J. M., Duthie, R. G., Knight, R. A., Gissy, J. L., Onischak, M. and Babu, S. P., "Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products -- Task 2, Mild Gasification Technology Development, Process Research Unit Tests Using Slipstream Sampling," Topical Report for U.S. DOE, Contract No. DE-AC21-87MC24266, May 1990.
2. Wootten, J. M., Duthies, R. G., Nawaz, M., Knight, R. A., Onischak, M., Babu, S. P. and Bair, W. G., "Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products -- Task 1, Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment," Topical Report for U.S. DOE, Contract No. DE-AC21-87MC24266, August 1988.
3. Tyler, R. J., "Flash Pyrolysis of Coals. Devolatilization of Bituminous Coals in a Small Fluidized Bed Reactor," Fuel 59:4, 218-226, April 1980.

59WP/61089-IIc/RPP

END

**DATE
FILMED**
6/18/92