FINAL REPORT
9/1/88-8/31/91
"Superconductivity and Magnetism in Rapidly Solidified Perovskites"
DE-FG02-84ER45174

R.C. O'Handley
Gretchen Kalonji
Department of Materials Science and Engineering
Massachusetts Institute of Technology

DOE/ER/45174--T4

DE92 014081

Program Objectives and Summary

Our DoE grant "Superconductivity and Magnetism in Rapidly Solidified Perovskites" (9/1/88-8/31/91) grew out of an earlier program "Rapidly Solidified Ceramic Ferrites: Microstructure and Magnetic Properties" (9/1/84 - 8/31/88).

During the first four years of the program (9/1/84-8/31/88) we developed techniques for rapid solidification processing (RSP) of ceramics. Some use was made of splat quenching^{1,2} and twin roller quenching. The main experimental technique developed there was gas atomization of ferrites³ which required much higher temperatures than metals. The work on R.S. ceramic ferrites led to a new understanding of phase equilibrium⁴ and cation site selection and of the strong dependence of cooling rates on droplet size.⁵ Great strides were made in our ability to control these by R.S. We made extensive use of Mossbauer spectroscopy to determine cation distributions in R.S. cobalt ferrites.⁶

With the announcement of high- T_c superconductivity in La-Sr-Cu-O in November 1986, and in $Y_1Ba_2Cu_3O_{8-x}$ in early 1987, it was a natural extension of our work to shift from spinels to perovskites. This redirection proved to be extremely productive. The funding provided by DoE for this work (a one-year extension of the existing program 9/1/87 - 8/31/88, and a new program in superconductivity and magnetism of R.S. perovskites, 9/1/88 - 8/31/91) has formed a solid core around which we were able to build a larger effort by attracting a Fullbright Scholar, a postdoc from India, a postdoc plus further support from Mitsui Mining and Smelting, a visiting professor from Yugoslavia and an MPC summer fellow (see Table I).

MASTER

We will make brief reference to our achievements in that earlier program on magnetic ferrites to the extent that they form a basis for our continuation in the present program on superconducting and magnetic oxides. This report is divided into six parts, reflecting major thrusts of our work since 1987:

1. Molecular orbital theory of high T_c superconductivity,
2. Rapid solidification processing of oxide superconductors
3. Time dependent magnetic and superconducting properties of these inhomogeneous materials
4. Excess Gd in $Gd_{1+x}Ba_{2-x}Cu_3O_{7-\delta}$ perovskites
5. Rapid solidification and directional annealing to achieve high J_c .
6. Mossbauer studies of T = Fe, Co and Ni site selection in $YBa_2(CuT)_3O_{7-\delta}$ and $GdBa_2(CuT)_3O_{7-\delta}$

Table I summarizes the personnel involved and additional support brought to bear on these problems.

1. Molecular Orbital Theory of High T_c Superconductivity

Molecular orbital (M.O.) theory of superconductivity had been developed in the early 1980's by K.H. Johnson. It combined the essential ingredient of B.C.S. theory couched in M.O. terms (e.g. the electron phonon interaction became a Jahn-Teller effect) which are more suitable for describing properties of the new high T_c superconductors than for the earlier metallic ones.

Our calculations provided a clear first principles picture of the correct orbitals involved in superconductivity, emphasizing before the band theorists, the important role of oxygen hole states and of Cu-O hybridization.⁷⁻⁹ We were able to predict the dependence of the sign and magnitude of the isotope effect on T_c in various compounds, corrections born out by later measurements.⁷

2. R.S. Processing of Oxide Superconductors

We developed a crucibleless technique for melting oxide superconductors in an oxygen-rich atmosphere.¹⁰⁻¹³ This allowed droplets of molten $\text{Y}_1\text{Ba}_2\text{Cu}_3\text{O}_{7-5}$ or other compositions,¹⁴ to be directed between the twin rollers of a rapid quenching apparatus. Rapid solidification of Y-Ba-Cu oxides led to the production of cubic and tetragonal phases which could be heat treated in oxygen to give the superconducting orthorhombic 1:2:3 phase.^{12,13}

The resulting material showed higher density and greater resistance to environmental degradation than our conventionally processed superconducting ceramics. (The techniques we developed for superconducting ceramics led to novel processing of iron/silica composites as precursor magnetic storage media¹⁵).

We identified the twin boundaries as playing a role in the flux pinning of 1:2:3 superconductors¹⁶ and made early contributions to understanding anomalies in the susceptibility data of these materials.¹⁷ Specifically, the role of superimposed paramagnetic susceptibility and of flux penetration and trapping were clarified.

We also studied superconductivity in the Bi-Sr-Ca-Cu-O compounds by crystallization at 400° C and higher from a rapidly solidified, glassy precursor. The 2201 phase crystallizes first followed by 2212 ($T_c = 85\text{K}$) and for $T_a \approx 840^\circ\text{C}$, the 2223 ($T_c = 106\text{K}$) compositions.¹⁸ The 2223 phase is the most difficult to grow by this method. These three phases have one, two and three Cu-O planes, respectively, per unit cell. The superconducting properties were examined by a SQUID magnetometer.

Extensive use has been made of quenching to control transition element site selection and properties in 1:2:3 superconductors. See Sec. 6.

3. Flux Flow

It was natural for us to study flux flow in high T_c superconductors because of our experience with sensitive magnetic measurements.

We first observed that flux flow was limited by a flux pinning

energy spectrum which peaked at higher temperatures (higher energies) for RS, than for conventionally processed high T_c superconductors.¹⁹⁻²²

We found that flux ~~penetration into~~ the zero-field cooled material was characterized by different kinetics than flux ~~expulsion from~~ a field-cooled sample. We explained this in terms of the random coupling of superconducting grains.²³ We published the first accurate measurements of the activation barrier in polycrystalline 1:2:3 superconductors.²³

The dependence of flux flow upon external field was found to follow well defined empirical laws which were consistent with the Beasley, Labusch, Webb theory of thermally activated, field assisted flux creep.²⁴

Most recently we have studied flux flow in our directionally annealed (DA), high J_c materials.²⁵ Unlike random polycrystalline materials, the flux flow in the DA materials is highly anisotropic and shows little difference between field cooled and zero-field cooled states. These observations are consistent with the strongly coupled, textured grains observed in these samples (see Sec. 5).

4. Excess Gd in $Gd_{1+x}Ba_{2-x}Cu_3O_{7-\delta}$

In the proposal for this project we outlined four compositional series related to $GdBa_2Cu_3O_{7-\delta}$ (Gd 1:2:3) which were expected to show the transition from superconductivity in Gd 1:2:3 to magnetism in $GdFeO_3$ and elucidate the important structural and chemical limits on high T_c oxide superconductivity in Gd 1:2:3.

We began by considering the proposed branch $3[GdCuO_3] - Gd$ 1:2:3. We found that putative perovskite $GdCuO_3$ is not the stable end member of this series, instead Gd_2CuO_4 is. It is related to the La_2CuO_4 structure but differs in the Cu coordination by oxygen. The Cu environment in Gd_2CuO_4 is square planar as in the Gd 1:2:3 chains; in La_2CuO_4 Cu is six-fold coordinated with oxygen. Pure Gd_2CuO_4 is not superconducting nor is it superconducting when doped with Ba, Sr or Ca.

We have also studied the disappearance of superconductivity with increasing x in $Gd_{1+x}Ba_{2-x}Cu_3O_{7-\delta}$ which is the Gd 1:2:3 end of the quasibinary series mentioned above. Substitution of excess Gd for Ba in Gd 1:2:3 is expected first to populate Ba sites in the 1:2:3 structure

with Gd ions then lead to a three phase regime: Gd 1:2:3 plus Gd₂ Ba Cu O₅ (2:1:1) and Cu O. The first effect is of interest because, as x increases, moment-bearing Gd³⁺ ions will occupy sites closer to the CuI, chain sites, the presumed locus of superconductivity in these materials. The second effect is interesting because it allows us to study a granular oxide superconductor with an increasing volume fraction of normal phases (2:1:1 and Cu O) between the superconducting 1:2:3 regions.²⁶

Gd substitutions at Ba sites in the orthorhombic 1:2:3 structure have a small effect on the intragranular critical temperature T_{co} suppressing it by about 10 K from 93 K for x = 0.2 in Gd_{1+x} Ba_{2-x} Cu₃ O_{7-δ}. For x = 0.3, 0.4, and 0.5 mixed phase materials are made and the resistivity does not drop to zero at T_{co} but has a plateau down to a lower temperature T_c at which the Josephson links between the isolated grains begin to superconduct. We focussed on the electrical properties of these granular materials and described them using conventional theory for inhomogeneous superconductors. The main result is that the temperature dependence of the resistivity for x = 0.5 in the regime $T \geq T_c$, where the grains begin to couple across the weak Josephson links, approaches the relation

$$\rho \sim (T - T_c)^{2/3}$$

The exponent 2/3 implies three dimensional behavior.²⁶

Other work focussed on the proper interpretation of superconducting flux creep, in the presence of magnetic ordering²⁷ and on the significance of the irreversibility line.²⁸

5. Processing for High J_c

We were fortunate to have a visiting postdoc supported by Mitsui attracted to our group from Kitazawa's group because of the opportunity to exploit R.S. processing of high T_c superconductors. Dr. T. Yamamoto saw R.S. as a means of preparing highly homogeneous precursors for later directional annealing to develop controlled 2:1:1 phase volume fraction (for flux pinning) and for developing large oriented grains of 1:2:3 phase.

This work (supported mostly by Mitsui) was done in collaboration with Mr. Prasanna and used some of the facilities supported by DoE.

Dr. Yamamoto first demonstrated an ability to carefully control the volume fraction of 2:1:1 phase in Y 1:2:3 by high temperature annealing of R.S. precursor material.²⁹ The heating cycle was modified to include a steep temperature gradient (40°C/cm) near the temperature critical for 2:1:1 phase formation. The steep gradient promoted growth of large grains with their a-b planes (high J_c) containing the temperature gradient vector (i.e., c-axes of grains normal to sample rod length). In this way grain sizes approaching a few millimeters were achieved with a high degree of texture.³⁰

Transport critical current measurements using both d.c. and pulsed current sources have shown our samples to sustain extremely high current densities:^{31, 32} $J_c = 2000 \text{ A/cm}^2$ at 15T and $J_c = 60,000 \text{ A/cm}^2$ in $H = 2T$, both at 77K. These are record high values for ceramic superconductors and reflect the fact that the processing has resulted in highly textured microstructure with very clean grain boundaries (strongly coupled grains).

SQUID magnetometer measurements on some of these samples²⁵ show a 100% anisotropy $(\chi_{||} - \chi_{\perp})/\chi_{\perp}$ and an M-H loop hysteresis indicative of a critical current density $J_c = 30 \Delta M/R \approx 6 \times 10^4 \text{ Acm}^2$ at $H = 4T$, $T = 70 \text{ K}$. This is consistent with the transport measurements. These data also suggest that the grains are strongly coupled, i.e. R is given by the macroscopic sample radius, not by the grain radius. Further, SQUID measurements at $T = 5 \text{ K}$ indicate that $J_c (4T)$ is 300 times greater than at 70 K, i.e. $J_c = 1.8 \times 10^7 \text{ A/cm}^2$. This remarkably high current density could not be confirmed by transport measurements because of the magnitude of the current required.

A patent has been applied for on this process, listing DoE as a partial sponsor³³, and the results of our work have been reported in a feature article in *Superconductor Week*.³⁴ A fuller description of this work has been submitted to Phys. Rev. B.³⁵ That paper interprets the difference between J_c measured by pulse and d.c. current methods as arising from sample heating by thermal conduction from the normal current leads in the d.c. case. Thus the higher J_c values obtained by the pulse technique are believed to be more accurate than the dc values. TEM studies show clearly the 2:1:1 precipitates which play a central role in flux pinning.

6. Mossbauer studies of FeCo and Ni site selection in Y or Gd Ba Cu_{3-x}Fe_xO_{7-δ}.

With the increased confidence in our ability to control quench rates after years of research and development in this area, we set out to learn more about the Fe Co and Ni site preference in $Y_1Ba_2Cu_{3-x}Fe_xO_{7-\delta}$ superconductors. In the equilibrium state Fe prefers to occupy the Cu I chain sites. There it is known to strongly suppress T_c . We decided to upset this equilibrium site selection by quenching these compositions from various temperatures (900° to 1000°C) to allow entropy to increase the Cu II (plane) site occupation by Fe. After recharging with oxygen at 450°C (which does not alter the Fe site distribution) we found that T_c was increased relative to the equilibrium case. The reason, however, for the suppressed T_c for Fe (or Co) at Cu I sites is not what we anticipated. At the four-fold coordinated chain sites Fe attracts excess oxygen into the system trapping mobile holes to reduce T_c . At the five-fold oxygen coordinated plane sites, Fe does not behave the same way.^{36,37}

We found these quenching experiments to be much more repeatable in $GdFe_x 1:2:3$ compositions. But in this case driving Fe from Cu I to Cu II sites further reduces T_c , just the opposite of the $YFe_x 1:2:3$ observations. We attributed this to a magnetic interaction between Gd and Fe(II) and now have Mossbauer evidence in support of that model.³⁸ The excess oxygen phenomenon evident in $YFe 1:2:3$ for Fe(I) still operates in $GdFe 1:2:3$ for Fe(I) but is dominated by the magnetic exchange effect in $GdFe 1:2:3$. We believe the exchange may be of the Anderson (superexchange) type: Fe-O-Gd which decreases the Cu-O-Cu bonding, essential for superconductivity as shown by our early M.O. calculations and by more recent band structure results.

Similar quenching experiments have been completed for $GdNi_x$ and $GdCo_x$ samples. Ni unlike Fe and Co occupies Cu II sites in equilibrium. The mechanisms controlling T_c while the same as for $GdFe_y$, are separable here. For Ni the entropy-driven shift to Cu I sites occurs for quenching from 700°C to 800°C and it is separable from the return of Ni to the plane sites by loss of chain-site oxygen which occurs for quenching from 900°C to 1000°C. This separation is possible for Ni because these effects work opposite each other.^{36,37}

REFERENCES

1. "Spinel Ferrite-Silica Glass Obtained by Splat Quenching," M.R. De Guire, R.C. O'Handley, and G. Kalonji, *J. Non. Cryst. Sol.* **81**, 351 (1986).
2. "Magnetic Ordering in Splat-Quenched Spinel-Ferrite-Silica Compositions," M.R. De Guire, M.D. Dyar, R.C. O'Handley and G. Kalonji, *J. Magn. Magn. Mater.* **54-57**, 1337 (1986).
3. "Gas Atomization of Cobalt Ferrite-Phosphate Melts," M.R. DeGuire, R.C. O'Handley, and G. Kalonji, *J. Mat. Sci.* **24**, 590 (1989).
4. "Phase Equilibria in the Iron Oxide-Cobalt Oxide-Phosphorous Oxide System," M.R. De Guire, T.R.S. Prasanna, G. Kalonji and R.C. O'Handley, *J. of Amer. Ceram. Soc.* **70**, 831 (1987).
5. "The Cooling rate dependence of cation distribution in CoFe_2O_4 ," M.R. De Guire, G. Kalonji, and R.C. O'Handley, *J. Appl. Phys.* **65**, 3167 (1989).
6. "Cation Distributions in Rapidly Solidified Cobalt Ferrites," M.R. De Guire, G. Kalonji and R.C. O'Handley, accepted for publication, *J. Amer. Ceram. Soc.*, **73** 3002 (1990).
7. "Electronic Structure of High T_c Superconductors," M.E. McHenry, C. Counterman, G. Kalonji, K.H. Johnson, A. Collins, M.M. Donovan and R.C. O'Handley, *Adv. Ceram. Mater.* **2**, 719 (1987).
8. "Molecular Orbital Basis for Superconductivity with Applications to High- T_c Materials," K.H. Johnson, M.E. McHenry, C. Counterman, A. Collins, M.M. Donovan, R.C. O'Handley and G. Kalonji, *Novel Superconductivity*, ed. S.A. Wolf and V.Z. Kresin (Plenum Press, NY, 1987) p. 563.

9. "Quantum Chemistry and High- T_c Superconductivity," K.H. Johnson, M.E. McHenry, C. Counterman, A. Collins, M.M. Donovan, R.C. O'Handley and G. Kalonji, *Physica B* 153-155, 1165 (1988).
10. "Rapid Solidification of Oxide Superconductors in the Y-Ba-Cu-O System," J. McKittrick, L.-Q. Chen, S. Sasayama, M.E. McHenry, G. Kalonji and R.C. O'Handley, *Adv. Ceram. Mater.* 2, 353 (1987).
11. "Melting and solidification behavior of $YBa_2Cu_3O_{7-\delta}$," J.M. McKittrick, S. Sasayama, M.E. McHenry, G. Kalonji and R.C. O'Handley, *J. Appl. Phys.* 65, 3662 (1989).
12. "Rapid Solidification Processing of High- T_c Superconductors: Microstructural Features and Phase Relationships," J. McKittrick, M.E. McHenry, C. Heremans, P. Standley, T.R.S. Prasanna, G. Kalonji, and R.C. O'Handley, *Physica B* 153-155, 369 (1988).
13. "Microstructural Studies of Rapidly Solidified Oxide Superconductors," J. McKittrick, M.E. McHenry, C. Heremans, P. Standley, T.R.S. Prasanna, G. Kalonji and R.C. O'Handley, *Trans. Japan Inst. Metals*, Sept. 1988.
14. "Rapid Solidification of $YBa_2Cu_3O_{7-\delta}$, $EuBa_2Cu_3O_{7-x}$ and $GdBa_2Cu_3O_{7-x}$," J. McKittrick, M.E. McHenry, P. Standley, C. Heremans, T.R.S. Prasanna, G. Kalonji and R.C. O'Handley, in *High Temperature Superconductors*, eds. M.B. Brodsky, R.C. Dynes, K. Kitazawa and H.L. Tuller (Mater. Res. Soc., Pittsburgh, PA, 1988) p. 567.
15. "Magnetic Properties and Morphologies of Rapidly-Solidified Iron-Oxides with Silica," L. Henderson, R.C. O'Handley and B.L. Averbach, *J. Magn. Magn. Mater.* 89, 245 (1990).
16. "Magnetism and Microstructure of $YBa_2Cu_3O_{7-x}$ Superconductors Produced by Rapid Solidification," M.E. McHenry, J. McKittrick, S. Sasayama, V. Kwapong, R.C. O'Handley and G. Kalonji, *Phys. Rev. B* 37, 623 (1988).

17. "Magnetic Susceptibility of Rapidly Solidified $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductors," M.E. McHenry, J. McKittrick, S. Sasayama, V. Kwapong, R.C. O'Handley and G. Kalonji, *J. Appl. Phys.* **63**, 4229 (1988).
18. C. Heremans, "Processing of BiSrCaCuO Hi-T_c Superconductors," S.M. Thesis, MIT, 9/'89.
19. "Time Dependent Magnetic Response in a $\text{GdBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductor: Flux Creep or Superconducting Glass State?," M.E. McHenry, M. Foldeaki, J. McKittrick, R.C. O'Handley and G. Kalonji, *Physica B* **153-155**, 310 (1988).
20. "Temperature and Field Dependent Magnetic Relaxation in $\text{REBa}_2\text{Cu}_3\text{O}_{7-\delta}$," M. Foldeaki, M.E. McHenry, J. McKittrick, R.C. O'Handley and G. Kalonji, International Symposium on Non-equilibrium Solid Phases of Metals and Alloys, Kyoto, March (1988), *Trans. Japan Inst. Metals*, Sept. 1988.
21. "Local moments, diamagnetism and time dependent magnetic response of high temperature superconductors," M. Foldeaki, M.E. McHenry, G. Kalonji and R.C. O'Handley, *J. Appl. Phys.* **64**, 5812 (1988).
22. "Local moments, Diamagnetism and Pinned Flux in $\text{RBa}_2\text{Cu}_3\text{O}_{7-\delta}$ High Temperature Superconductors," M. Foldeaki, M.E. McHenry and R.C. O'Handley, *Physica C* **161**, 403 (1989).
23. "Flux expulsion and penetration in superconducting $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$," M. Foldeaki, M.E. McHenry, and R.C. O'Handley, *Phys. Rev. B* **39**, 2883 (1989).
24. "Flux Creep in $\text{Y}(\text{Gd})\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$: Magnetic Field Dependence," M. Foldeaki, M.E. McHenry and R.C. O'Handley, *Phys. Rev. B* **39**, 11,475 (1989).
25. M. Foldeaki, H. Ledbetter, R.C. O'Handley and T. Yamamoto.
26. "Superconductivity through percolation in $\text{Gd}_{1-x}\text{Ba}_{2-x}\text{Cu}_3\text{O}_{7-\delta}$," R. Chatterjee, T.R.S. Prasanna, J. Moodera and R.C. O'Handley, *Physica C* **158**, 485 (1989).

27. "Time Dependent Magnetic Response in $\text{RBa}_2\text{Cu}_3\text{O}_{7-d}$: Effect of Magnetic Ordering," M. Foldeaki, R.A. Dunlap, M.E. McHenry and R.C. O'Handley, *IEEE Trans. MAG.* **25**, 3509 (1989).
28. "Time Dependent Response to the de-Almeida-Thouless Line in R 1:2:3 Superconductors," M. Foldeaki, M.E. McHenry, L. Koszegi, R.C. O'Handley and R.A. Dunlap, *J. Appl. Phys.* **67**, 5058 (1990).
29. " $\text{YBa}_2\text{Cu}_3\text{O}_7$ Ceramics Prepared by Rapid Solidification Processing," T. Yamamoto, S.K. Chan, M. Stubicar, T.R.S. Prasanna and R.C. O'Handley, *Materials Letters* **10**, 243 (1990).
30. "Phase Control of Y_2BaCuO_5 in High T_c Superconducting $\text{YBa}_2\text{Cu}_3\text{O}_7$ Ceramics Prepared by Rapid Solidification Processing," T. Yamamoto, S.K. Chan, M. Stubicar, T.R.S. Prasanna and R.C. O'Handley, *Materials Letters* **10**, 243 (1990).
31. "High T_c Superconductors Prepared by Rapid Quenching and Directional Annealing," T. Yamamoto, M. Stubicar, S.K. Chan, J.G. Lu, T.R.S. Prasanna, and R.C. O'Handley, submitted to *Materials Science and Engineering A* **133**, 127 (1991).
32. "High- J_c Superconducting Y-Ba-Cu-O Prepared by Rapid Quenching (RQ) and Directional Annealing (DA)," T. Yamamoto, R.S. Prasanna, S.K. Chan, J.G. Liu, and R.C. O'Handley, submitted to the Proceedings of 2nd World Congress on Superconductivity, Sept. 10-13, 1990, Houston, Texas.
33. U.S. Patent Application, Serial No. 566,212, filed Aug. 10, 1990.
34. *Superconductor Week*, Dec. 24, 1990, **4**, P1.
35. "Enhanced high-field transport critical current density of superconducting bulk Y-Ba-Cu-O prepared by rapid solidification and directional annealing," T. Yamamoto, S.K. Chan, J.G. Lu, T.R.S. Prasanna, R.C. O'Handley, Lourdes Salamanca-Riba, and S. Nahm. Submitted to *Phys. Rev. B*.

36. T.R.S. Prasanna, "Transition Metal Redistribution in High Temperature Superconductors: Site Preference and Magnetic Interaction," PhD thesis, MIT 9/91.

37. "Transition metal redistribution in $\text{Gd}(\text{Y})\text{Ba}_2\text{Cu}_{3-x}\text{Fe}_x\text{O}_{7-8}$: (M = Fe, Co, Ni) Evidence for Gd-Fe(2) magnetic interaction," T.R.S. Prasanna, R. Chatterjee, R.C. O'Handley and G. Kalonji, accepted by Phys. Rev.

38. "Fe-Gd Magnetic Interactions in $\text{GdBa}_2\text{Cu}_{2-7}\text{Fe}_3\text{O}_{7-8}$," T.R.S. Prasanna, G. Papaephthimiou, and R.C. O'Handley, in preparation.

**DATE
FILMED**

7 / 13 / 92