MASTER

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PROGRESS REPORT

Contract No. DE-AS02-76ER03166

ENVIRONMENT AND FRACTURE

Submitted to

Division of Materials Sciences
Office of Basic Energy Sciences
Department of Energy

Attn: Dr. S. Wolf, ER-15
Division of Materials Sciences

by

Herbert H. Johnson, Professor

Department of Materials Science and Engineering
Cornell University
Ithaca, New York 14853

March 1979

EB
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Introduction

The present research program is directed in the main to investigations of hydrogen trapping in iron and iron-base alloys. Both chemical and physical trapping phenomena are under study. Chemical trapping of hydrogen is found in the hydrogen attack of plain carbon and alloy steels. Diffusing hydrogen reacts with carbon to form methane, which leads to carbide dissolution and deterioration of the microstructure, along with a substantial degradation in mechanical properties. Hydrogen attack is encountered at temperatures above approximately 600 K and at elevated hydrogen pressures.

Physical trapping of hydrogen is evident at lower temperatures and hydrogen pressures. Hydrogen transport through the microstructure is hindered, and measured apparent diffusion coefficients are significantly smaller than would be expected on the basis of purely lattice diffusion. Experimental programs in both of these areas are supplemented by analytical efforts, built around the construction and analysis of models to interpret the experimental results.

An experimental approach which is unique to this program is the particular way in which permeation techniques are used to obtain information on trapping characteristics. Time lag measurements as a function of hydrogen pressure and temperature may be used to establish the operative trapping mechanism, and to determine values for trap densities and binding energies. Gas phase permeation experiments may be carried out to temperatures less than 273°K with iron or steel membranes coated with thin layers of palladium. Surface impedance problems are thereby eliminated, as the palladium acts as a perfect transmission medium for hydrogen transport from the gas phase to the

membrane specimen. Hydrogen fluxes are monitored by the electrochemical technique, which is sufficiently sensitive that measurements may be carried out at lattice hydrogen concentration of the order of one hydrogen atom for every 10^8 iron atoms.

Progress in 1979/80 in the various areas of investigation is summarized in the following pages.

Physical Trapping

Isotope Effects - Hydrogen and its isotopes have always attracted attention in the context of diffusion theory. The light mass of the hydrogen atom suggests the possibility of non-classical and perhaps quantum effects, and the availability of three isotopes suggests that a complete experimental picture can be attained. Indeed, substantial deviations from the square-root-of mass scaling relation have been reported in recent years for hydrogen and its isotopes in Nb, V, Ta, and Pd.

In this program we have measured the permeability, lattice diffusivity, and lattice solubility of hydrogen and deuterium in iron over the temperature range from 280K to 797K. Very nearly square root of mass behavior was observed over this range, with a reproducible trend toward a slightly higher ratio than $(2)^{1/2}$ in the lower temperature measurements. This behavior is distinctly different from that reported for Nb, Va, Ta and to some extent Pd.

In the past year we have extended this portion of the program to a comparison of the trapping behavior of H and D in iron. Representative permeation flux and time lag data are reported in Figs. 1-5. Present and previous H and D steady state flux data are shown in Fig. 1, while Fig. 1 and Fig. 2 both show that the steady state fluxes are not influenced by the traps introduced during plastic deformation. Figs. 3-5 show representative time lag data, from which trap densities and binding energies were extracted by techniques described in

previous reports. Good agreement between experimental data and calculated curves is evident.

Tables 1 and 2 below summarize the trap density and binding energy data for H and D in four pass zone refined and annealed Ferrovac E iron. For the data in Table 1, all of the H runs were carried out before the D runs, while for Table 2 the H and D runs were alternated at each measuring temperature. It is evident that both measurement procedures give sensibly the same results.

Table 1
Binding Energy (E_b) and Trap Density (N_t)
for H and D in Annealed Iron*

Temp °C	H_2		D_2	
	$E_b \left(\frac{\text{kcal}}{\text{mol H}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$	$E_b \left(\frac{\text{kcal}}{\text{mol D}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$
15	-	-	13.3	4×10^{14}
25	13.0	4.86×10^{14}	13.0	4.23×10^{14}
	13.4	8.72×10^{14}		
45	13.4	8.47×10^{14}	12.8	8.61×10^{14}
57	13.1	1.28×10^{15}	12.9	1.07×10^{15}
70	12.3	4.15×10^{15}	11.6	6.97×10^{15}

* All H runs completed before D runs.

Table 2
Binding Energy (E_b) and Trap Density (N_t)
for H and D in Annealed Iron*

Temp °C	H_2		D_2	
	$E_b \left(\frac{\text{kcal}}{\text{mol H}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$	$E_b \left(\frac{\text{k cal}}{\text{mol D}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$
25	13.0	7.73×10^{14}	12.5	9.6×10^{14}
45	12.9	1.55×10^{15}	12.7	1.43×10^{15}
57	12.4	3.9×10^{15}	12.4	2.7×10^{15}
70	12.6	5.88×10^{15}	11.9	7.9×10^{15}

* H and D runs were alternated at each temperature.

It is evident from these data that H and D display identical trapping characteristics in iron. For comparable conditions the trap densities and binding energies are identical within the limits established by the inevitable experimental errors. The trap densities and binding energies were obtained from data such as is reported in Figures 3-5 by an optimized two parameter least squares fitting technique.

There is one aspect of the data in Tables 1 and 2 which remains puzzling. The inferred trap densities increase with temperature, by about an order of magnitude over the temperature range investigated. This has been noticed previously for data obtained from annealed iron, but not for cold-worked iron, where the trap densities are substantially greater. It is not clear at present whether the apparent increase in trap density is real or just an artifact of the data fitting process. Some further measurements will be made to try and resolve this point.

A substantially complete set of data for iron cold worked by rolling

to two levels is summarized in Tables 3 and 4.

Table 3
Binding Energy (E_b) and Trap Density (N_t)
for H and D in 30% Cold-Worked Iron

Temp °C	H_2		D_2	
	$E_b \left(\frac{k \text{ cal}}{\text{mol H}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$	$E_b \left(\frac{k \text{ cal}}{\text{mol D}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$
5	12.6	3.2×10^{16}	12.2	3.81×10^{16}
25	13.3	4.22×10^{16}	13.1	6.92×10^{16}
45	—	—	13.3	7.23×10^{16}
56	13.9	4.38×10^{16}	—	—
20	14.1	7.25×10^{16}	13.8	8.03×10^{16}

Table 4
Binding Energy (E_b) and Trap Density (N_t)
for H and D in 60% Cold-Worked Iron

Temp °C	H_2		D_2	
	$E_b \left(\frac{k \text{ cal}}{\text{mol H}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$	$E_b \left(\frac{k \text{ cal}}{\text{mol H}} \right)$	$N_t \left(\frac{\#}{\text{cm}^3} \right)$
25	13.1	1.12×10^{17}	12.9	1.02×10^{17}
45	—	—	13.2	1.00×10^{17}
			13.4	8.21×10^{16}
20	—	—	13.7	1.42×10^{17}

These data reinforce the present conclusion that H and D show identical trapping behaviors, and the previous conclusion that the trap binding energies are the same in annealed and deformed iron. The micro-structural conditions differ in that cold worked iron has a substantially higher trap density than

than annealed iron.

We anticipate tidying up this portion of the program with a few more measurements in the coming month, and then preparing the material for publication during 1980/81. This will probably conclude the major effort in isotope effects.

Edge/Screw Dislocation Trapping Capacity - In another portion of the present program, we are collaborating with H. Müghrabi of Stuttgart, in a series of measurements designed to establish whether or not edge and screw dislocations have the same trapping capacity for hydrogen. The collaboration brings together Müghrabi's experience in preparing and characterizing iron single crystals of known purity and dislocation structure, and our ability to determine trapping parameters from time lag measurements. To prepare for these measurements, it was necessary to down-size the permeation apparatus, so that single crystal specimens, inevitably of smaller area, could be accommodated.

In a first experiment, Fig. 6, time lag measurements were carried out on a single crystal specimen deformed 5% at 293K, and compared with measurements on a crystal deformed 5% at 293K, and then deformed a further 0.5% at 195K. In both instances the (T01) plane was parallel to the specimen surface. On the basis of Müghrabi's past work, 5% of deformation at 295K should introduce predominantly edge dislocations, while the additional 0.5% deformation should introduce approximately 10^8 cm^{-2} of additional screw dislocations. Thus, the two specimens should have rather different ratios of edge to screw dislocations.

From Fig. 6 it is evident that the two specimens have identical trap binding energies, but rather different trap densities. The differences in trap density are probably outside the range that could be attributed to experimental errors. On the basis of this data alone, and assuming that the dislocation structures are what was anticipated, it would be tentatively concluded that

screw dislocations have a substantial capacity for trapping of hydrogen. However, much more experimentation will be necessary before this initial conclusion can be substantiated or refuted.

The dislocation structures for the specimens tested in this portion of the program will be characterized with respect to morphology and density by Mughrabi at Stuttgart.

Deformation and Hydrogen Transport - First results are presented here from a newly initiated study of the influence of both elastic and plastic strains upon hydrogen (and deuterium) transport. This study was undertaken because of the continuing interest in dislocation transport of hydrogen, and the rather unsettled experimental picture that exists in this area at present.

These initial experiments have been carried out with 1020 steel, as it allows a larger range of elastic stresses than can be obtained with a reasonably pure iron. The gas phase permeation apparatus was adapted to an Instron testing machine.

The steady state fluxes of both H and D were dependent upon stress in the manner predicted by thermodynamics, Figs. 7 and 8. The phenomenological partial atomic volumes of H and D, $\bar{V}_H$ and $\bar{V}_D$, may be computed from the slopes of the measured $\log \frac{J_\sigma}{J_0}$ vs σ curves. The values obtained are $\bar{V}_H = 2.665 \frac{\text{cm}^3}{\text{mol H}}$, and $\bar{V}_D = 2.651 \frac{\text{cm}^3}{\text{mol D}}$. $\bar{V}_H$ is in good agreement with the one previously measured value, while $\bar{V}_D$ has not been measured before. Once again it is evident that H and D behave in a similar fashion, in this case with respect to the influence of elastic stress upon solubility.

When loading is continued into the plastic range, a sharp increase in apparent measured flux — a "spike" in the curve — is observed upon pressing through the yield point, Fig. 9. If the deformation is continued, the apparent measured flux behaves in an erratic fashion. If the load is released, the flux

decreases to well below the previous steady state value in the absence of load, remains low for a significant time, and eventually rises to a value somewhat above the previous steady state. The extent and duration of the depression in flux increases with the amount of deformation. Upon reloading, Fig. 9b, the apparent measured flux again shows a spike as plastic deformation re-commences.

These are preliminary observations, which may will be clarified or modified as further measurements are carried out. Nevertheless, it is of interest to speculate on possible interpretations. Let us consider first the "spike" that is observed in the flux vs time curves when the specimen first undergoes plastic deformation, which has also been seen by at lease one previous investigator, using a different measurement system. Figure 10a indicates that the "spike" is spurious, an artifact of the measuring system. When a specimen is loaded with the flux measuring system operative, but with no hydrogen supplied to the input side of the membrane, a "spike" is observed when plastic deformation commences. Thus, it is not associated with hydrogen transport from the input side of the membrane.

The subsequent drop in flux, when the stress is removed, may be interpreted in a straight forward if still tentative fashion as resulting from an increase in trap density during deformation, and the consequent redistribution of hydrogen lattice to trap sites. This is consistent with the fact that the extent and duration of the flux drop is related to the amount of deformation. However, it remains to be seen if this interpretation can be put on a quantitative basis.

Lastly, the permeation transients observed when an elastic stress is applied to a specimen already in the steady state permeation condition may be considered, as is outlined schematically in Fig. 10b. When the increment in integrated flux, after application of stress, delineated as the shaded region

in Fig. 10b, is plotted vs time, the typical results are as indicated in Fig. 11. This demonstrates that the time lag for re-establishment of the steady state is independent of stress, and hence of the solubility increase caused by the stress, which is just what would be expected of a lattice diffusion process without trapping. Further, when effective diffusivities are determined for the stress-induced portion of the permeation process, from time lag data such as in Fig. 11, Table 5 is the result.

Table 5
Comparison of Effective Diffusivities for Stress-Free
and Stress-Induced Hydrogen Permeation .1020 Steel

<u>Condition</u>	<u>Effective Diffusivity</u>
Annealed; stress-free permeation	$9.6 \times 10^{-6} \frac{\text{cm}^2}{\text{s}}$
Annealed; stress-induced permeation after stress-free steady state established	$8.6 \times 10^{-5} \frac{\text{cm}^2}{\text{s}}$
12% deformation; stress-induced permeation after stress-free steady state established	$8.6 \times 10^{-5} \frac{\text{cm}^2}{\text{s}}$
20% deformation; stress-induced permeation after stress-free steady state established	$7.5 \times 10^{-5} \frac{\text{cm}^2}{\text{s}}$

Table 5 shows that the effective diffusivities for a stress-induced transient after the steady state is established, are nearly an order of magnitude larger than the diffusivity which describes the establishment of the original steady state. Further the stress-induced diffusivity is sensibly independent of both the stress level, Fig. 11, and the microstructural condition of the specimen.

These facts almost surely admit of only one interpretation, which is

that the hydrogen step-function caused by the stress propagates through a specimen in which the traps have already been filled by the establishment of the prior steady state. This interpretation is consistent with quantitative application of the McNabb-Foster formalism to the stress free time lag data, which predicts that the traps are essentially saturated. Thus, the diffusivity associated with a stress-induced hydrogen step function is sensibly equivalent to the lattice diffusivity, for which indeed the best estimates are about $8 \times 10^{-5} \frac{\text{cm}^2}{\text{s}}$.

It is expected that this portion of the program will be continued, with studies of the effects of both elastic and plastic strains upon hydrogen transport.

Trapping Models and Parameters - Many previous investigative studies have indicated the existence of hydrogen trapping through measurements of an effective diffusivity, by a variety of techniques, as a function of temperature. When plotted as the logarithm of the effective diffusivity versus the reciprocal of temperature, a drop in effective diffusivity at low temperatures below the values associated with lattice diffusion is commonly taken as evidence of trapping. Various previous investigators have in effect used data in this form to explore trapping models.

In Figs. 12-14 various models and associated trap parameters are compared with a summary of literature data for $\ln D_{\text{eff}}$ vs $\frac{1}{T}$. The "Alefeld envelope" is the outline of all measured $\ln D_{\text{eff}}$ vs $\frac{1}{T}$ data from the literature; what emerges from these plots is that a variety of models and trapping parameters can be fitted to data presented in this form. For example, Figs. 12 and 13 utilize a diffusivity equation recently presented by McLellan. In his calculation he fitted his equation to the data with a binding energy of 6.5 kcal/mol and trap densities of the order of 10^{19} cm^{-3} . Figures 12 and 13 show that an equally good fit may be obtained with the higher binding energies and lower trap

densities found by the methods of this program. Thus with respect to fitting $\ln D_{\text{eff}}$ vs $\frac{1}{T}$ data, there is a trade off between trap density and binding energy. The same behavior is evident for Oriani's equation, developed some years ago, in that it fits the envelope of measured data with two sets of trapping parameters.

A wholly different model, void trapping, is shown in Fig. 14 to be capable of fitting the assembled literature data. In this model hydrogen is assumed to be trapped as molecules in interval voids, in contrast to the single atom trapping contemplated in Figures 12-13.

It may be safely concluded that the fitting of models and trap parameters to the literature data for $\ln D_{\text{eff}}$ vs $\frac{1}{T}$ is not a satisfactory procedure for evaluating models of hydrogen trapping. It must be done by the experimental methods and data analysis procedures developed and applied during the course of this program.

We expect to publish soon a short note on these and related calculations, and the inferences that may be drawn from them.

Chemical Trapping (Hydrogen Attack)

We have initiated a combined experimental and analytical study of hydrogen attack in low alloy Cr-Mo steels. As was described in last year's report, this effort has evolved from an earlier study of hydrogen attack in a plain carbon 1020 steel, and a Ferrovac E iron.

This earlier effort led to the development of two rather unique capabilities, which are now being applied to the more important case of low-alloy Cr-Mo steels. The first is the development of an analytic model for hydrogen attack which can reproduce in a semiquantitative fashion the main features of the well known "Nelson curves" for plain carbon steels, when reasonable values are selected for the physical parameters of the model.

The second new capability is a technique for measuring the actual average methane pressure in internal voids developed by hydrogen attack under different exposure condition. The total amount of methane in the voids is determined by vacuum degassing of the attacked steel at an elevated temperature. During this treatment the methane dissociates and the hydrogen diffuses out of the steel and may be collected. The associated quantity of methane, when combined with an equation of state and a measurement of the void density, allows a calculation of the methane pressure. There is an obvious interplay between the experimental measurements and the model calculations.

In the past year we have begun to apply these capabilities to the hydrogen attack of Cr-Mo low alloy steels. With respect to materials, we have acquired a series of plain C steels, with which to test certain features of the analytical model, and a .5 Mo, a 0.1 Mo - 0.5 Cr., and a $2\frac{1}{4}$ Cr - 1 Mo steel. The equipment used for exposure to high temperature, high pressure hydrogen has been upgraded and rebuilt. This was necessary since the Cr-Mo alloy steels require, for development of hydrogen attack, exposure to significantly higher pressures than are needed for plain carbon steels. This rebuilding phase of the effort is largely completed, and meaningful experiments are now in progress.

In the modelling phase of the effort calculations are now underway to see if the model can be extended to the Cr-Mo low alloy steels. A first result is shown in Figs. 15 and 16 which shows the effect of diminishing matrix carbon contents on the model calculations of incipient hydrogen attack. This simulates in an approximate way this case of the Cr-Mo alloy steels, since the thermodynamic consequence of the more stable alloy carbides in these steels is that the matrix carbon concentration is less than in plain carbon steels. These results are promising in that the trends are in the right direction, and of a magnitude to be consistent with practical experience.

Miscellaneous

1) In anticipation of a study of solute trapping of hydrogen, four Fe-Ti alloys of varying titanium concentration have been obtained. They are now undergoing specimen preparation procedures, after which time lag measurements will be undertaken in the gas phase-electrochemical detection permeation system.

2) The vacuum permeation system originally developed by Quick has been substantially rebuilt and upgraded. A first effort was made to study hydrogen permeation through silicon with a sputter deposited coating of palladium, but so far thermal stresses in the silicon have led to cracking before meaningful measurements could be undertaken. The experimental design of this experiment is under reconsideration. At present we are attempting a measurement with aluminum with a sputter-deposited palladium layer.

3) The study of generator end-ring steels, described in last year's report, has for the moment at least been terminated. The student, an hourly employee, has had less time available than anticipated, and other aspects of the program have become more exciting, and hence have received a higher priority.

Personnel

Hydrogen Trapping Studies - This portion of the program is currently being carried out by R. W. Lin, who is nearing the completion of his Ph.D. thesis.

Hydrogen Attack Studies - H. H. Wang is carrying out this project as the major part of his Ph.D. thesis. He has passed the Ph.D. qualifying exam, and is now devoting full time to thesis research.

Palladium Overlay Experiments - D. M. Kuhn is responsible for these activities. He is expected to take his Ph.D. qualifying examination this spring.

Publication/Talks

One paper was published during 1979/80.

A. J. Kumnick and H. H. Johnson, "Deep Trapping States for Hydrogen in Deformed Iron", Acta Metallurgica 28 (1980) 33-39. The measurements described in this paper have attracted much attention. Two other manuscripts based on past work by Kumnick and Quick are in preparation. Quick's work on surface impedance (presumably an oxide film) to hydrogen transport in stainless steels is in a final draft, while a paper on trapping in annealed iron, based on work of both Quick and Kumnick is well along.

With respect to talks, I participated in a three day internal meeting at Sandia Livermore in February, and will

- 1) Give a seminar at MIT in May
- 2) present the lead-off talk at the Troiano Festschrift in early June,
and
- 3) present an invited paper at the Jackson, Wyoming meeting in August.

Fig. 1 Steady State Permeability Φ_{∞} versus Reciprocal Temperature, 30% Cold Worked Ferrovac E, Hydrogen and Deuterium

Fig. 2. Steady State Permeability of Deuterium Φ_{∞} versus Reciprocal Temperature, Ferrovac E Cold-Worked 30% and 60%.

Fig. 3. Time Lag Function versus Reciprocal Square Root of Hydrogen Pressure, Annealed Iron Tested at 298K.

Fig. 4. Time Lag Function versus Reciprocal Square Root of Deuterium Pressure. Annealed Iron Tested at 330K.

Fig. 5. Time Lag Function versus Reciprocal Square Root of Deuterium Pressure. Annealed Iron Tested at 343K.

Fig. 6. Time Lag Function at 293K versus Reciprocal Square Root of Hydrogen Pressure, Annealed and Purified Iron Deformed 5% at 293K, and Deformed 5% at 293K followed by 0.5% at 195K.

Fig. 7. Steady State Flux as a Function of Stress, Annealed 1020 Steel
Tested in Hydrogen at 298K.

Fig. 8. Steady State Flux as a Function of Stress, Annealed 1020 Steel Tested in Deuterium at 298K.

Fig. 9. Schematic of Measured Flux when 1020 Steel is Stressed into Plastic Region and Unloaded. a) Single Load and Unload. b) Double Load and Unload Sequence.

Fig. 10. a) Comparison of Measurement System Response During Plastic Deformation With and Without Hydrogen.
 b) Schematic of Steady State Flux Increase When Elastic Stress is Applied to 1020 Steel in Steady State.

Fig. 11. Stress-Induced Integrated Flux vs Time For 1020 Steel in Steady State

Fig. 12. Comparison of McLellan's Effective Diffusivity with Literature Data, Using Trapping Parameters Measured in this Program.

Fig. 13. Further Comparison of McLellan's Equation with Literature Data Using Trapping Parameters Measured in this Program.

Fig. 14. Comparison of an Apparent Diffusivity with Temperature for a Void Trapping Model.

Fig. 15. Model Calculations of Incipient Hydrogen Attack for Different Matrix Carbon Concentrations, Comparison with Nelson's Curve.

Fig. 16. Model Calculations of Incipient Hydrogen Attack for Different Matrix Carbon Concentrations, Comparison with Nelson's Curves.