FINAL TECHNICAL REPORT

DOE GRANT NO. DE-FGO2-84ER45109

FATIGUE OF FERRITIC AND AUSTENITIC STEELS

PREPARED FOR THE U. S. DEPARTMENT OF ENERGY

Attn. Dr. Joseph Darby
Division of Materials Sciences
Office of Basic Energy sciences

Principal Investigator:

Prof. A. J. McEvily
Metallurgy Department
University of Connecticut
Storrs, CT 06269

Period Covered

June 1, 1984-July 31, 1991

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe upon privately-owned rights.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

pr

SYNOPSIS OF RESULTS

One aim of this research program has been to increase our understanding of the mechanisms of fatigue crack growth as influenced by such parameters as the specific material, crack length, R-ratio, overloads, temperature and the environment. A second objective has been to utilize this understanding in the development of semi-empirical quantitative methods for the prediction of fatigue crack growth behavior. Although there are still many questions remaining concerning fatigue crack growth, we feel that some significant progress in meeting these two objectives has been made as indicated in the following synopsis of the major areas investigated.

A. Crack Closure.

During the course of this DOE-sponsored research program the importance of fatigue crack closure has developed into a dominant theme. The reason for this interest in crack closure stems from the following observations*:

1. Aspects of the anomolous behavior of short fatigue cracks can be understood if crack closure is considered [1, 10].
2. Crack closure plays a dominant role in the transient fatigue crack growth that accompanies an overload, a change in ΔK or the load ratio, R [5,12, 19, 20].
3. Crack closure is importantly involved in the mechanism of fatigue crack growth in silicon nitride [24].
4. Crack closure is responsible for crack arrest under compressive cycling of notched specimens [17].
5. Crack closure is responsible for the notch size-effect in fatigue [9].

*The numbers in brackets [ ] refer to the papers listed in the section entitled "Publications".

6. Constitutive relationships for the prediction of the rate of fatigue crack growth can be developed if crack closure is taken into account [14, 18, 21-23].

B. Role of Temperature and Environment

7. At elevated temperature in vacuum crack closure may not be present, and as a result there is no R-effect on the rate of fatigue crack growth [3, 6, 8]. No creep-fatigue interaction occurs in vacuum at frequencies as low as 0.3 Hz at 538° C. Oxidation can increase the fatigue crack growth rate but also increase the threshold level at elevated temperatures.

8. In Type 304 stainless steel at room temperature more stress-induced transformation occurs at a fatigue crack tip in vacuum than in air, and the closure level in air is higher in a ΔK -decreasing as compared to a ΔK -increasing test [13].

9. The crack closure level at room temperature for steels is similar in vacuum and in air except in the near-threshold region where oxidation and fretting can increase the closure level in air relative to that in vacuum [4].

Plane stress vs. plane strain

10. The level and nature of crack closure differs in the plane stress and plane strain regions of a fatigue cracked specimen, and improved instrumentation and test techniques are needed to be able to detect the different opening loads [19].

DISCUSSION

In Figure 1 the line labeled ΔK_{eff} indicates the fatigue crack growth rate under closure free conditions. The line labeled ΔK indicates the growth rate under conditions wherein closure has fully developed in the wake of the crack. When a fatigue crack is initiated there is no wake at first, and hence no closure and the growth rate is found on the ΔK_{eff} curve. However, as the crack lengthens, the wake increases and the closure level also increases up to the level of a macroscopic crack, with the growth rate given by ΔK . Under constant applied amplitude of stress loading conditions the calculated rate of growth from an initial crack length of 0.1 mm for stress ranges of 190, 200, and 320 MPa are shown by the dashed lines. These

Figure 1

anomalous growth patterns correspond to those which have been observed for small cracks. It is noted that in the case of curve A, a non-propagating crack was formed. In making the calculations a constitutive relation is needed, and the following was used:

$$\frac{da}{dN} = A(\Delta K_{eff} - \Delta K_{effth})^2 \quad (1)$$

where A is a material constant and ΔK_{effth} is the threshold value of ΔK_{eff} . In addition an expression to describe the rate of closure development with increase in crack length, λ , from the initial flaw is needed. The following relation was used:

$$K_{op} = (1 - e^{-k\lambda})K_{opmax} \quad (2)$$

where K_{op} represents the opening level in the transition region, K_{opmax} is the opening level of a macroscopic crack, and k is a material constant of dimensions mm^{-1} .

Fig. 2a shows the effect of an overload on the rate of fatigue crack growth of an aluminum alloy. Of principal interest here is the retardation in growth rate that occurs as the crack penetrates the overload affected zone. The dashed line indicates that if the plane stress, surface layers are removed the retardation effect is largely eliminated. The corresponding crack opening behavior is shown in Fig. 2b. The closure level is highest where the crack growth rate is a minimum, i.e., ΔK_{eff} is a minimum, but when the surface layers are removed the closure level drops and the growth rate increases. It is also noted that plane stress closure controls the retardation phenomenon over the full range of baseline ΔK s investigated, from the threshold level on up. In addition a semi-empirical method has been developed for predicting the number of delay cycles as a function of the extent of overload. This method includes consideration of specimen thickness and yield strength. In accord with experimental observations the number of delay cycles for a given percentage of baseline overload is at a minimum at an intermediate ΔK baseline level.

(a)

(b)

Figure 2

Figure 3

Fig 3 shows the effect of a change in ΔK at a constant R value on the rate of fatigue crack growth. The transients in this case are associated with a change in mean stress, with a decrease in mean stress leading to a transient increase in closure, and with an increase

Figure 4

in ΔK resulting in a transient decrease in closure. In contrast to the overload situation, the closure effects referred to are through-thickness in nature, and are located quite close to the crack tip, i.e., within 50 μm of the tip, so that observation by a replica technique may be required to determine the opening level. A similar situation exists if the R value is changed while holding ΔK constant as shown in Fig. 4. In this case the transition in the opening level is also shown.

Figure 5

Fig. 5 shows the variation in the crack opening level in silicon nitride at two R levels as a function of crack length. It was observed that as the cracks grew longer ΔK_{eff} actually decreased because of the large rise in the opening level, and yet the rate of fatigue crack growth increased. This indicates that a fatigue crack growth mechanism quite different from that found in metals is operative in this case. We have proposed that microcracks are created in the closing or unloading portion of the loading cycle, and that the higher the opening level the greater will be the compressive force developed to create and propagate these microcracks. On this basis we have developed the parameter shown as the abscissa in Fig. 6, which is able to correlate a wide range of fatigue crack growth data

as shown. Note that moisture plays a role in accelerating the growth of fatigue cracks in silicon nitride over the rate shown in vacuum.

Figure 6

Fig. 7 shows the rate of fatigue crack growth of short fatigue cracks as a function of crack length for two values of ΔK . Note that a variety of R levels are involved, even some which reflect cycling in the compression-compression range. By using both Eqs. 1 and 2 predictions were made and compared with experiment in Fig. 7. Crack arrest occurred whenever the closure level reached a value where ΔK_{eff} became equal to $\Delta K_{eff,th}$. It is noteworthy that the only variable introduced in going from one R level to another was the

value of K_{opmax} . The method developed therefore provides an analytical means for dealing with short crack behavior at any R ratio.

(a) $\Delta K = 16 \text{ MPa m}^{1/2}$

(b) $\Delta K = 6 \text{ MPa m}^{1/2}$

Figure 7

Figure 8

Fig. 8 shows how the development of closure at a notch leads to an increase in the stress amplitude needed to continue the propagation of a short fatigue crack at a given growth rate, here corresponding to the threshold level of 10^{-8} mm/cycle. Unless the applied stress amplitude reaches a level such as at C a non-propagating crack may form. Note that the smaller the initial notch size, c , the higher is the stress required for fatigue crack propagation, i. e., there is a size effect which is accounted for by the method of analysis. However if the initial notch size is sufficiently large as at E, then crack initiation rather than crack propagation becomes the controlling factor, and there is no longer a size effect.

Figure 9

At elevated temperatures in vacuum the closure effect can disappear. As a result there is no R-dependency as shown in Fig. 9 for R values of 0.05 and 0.5. We have also found that testing a 9Cr-2Mo steel in vacuum at frequencies between 30 and 0.3 Hz had no effect on the da/dN value, and we conclude that within this range of frequencies there was no creep-fatigue interaction. However, if the tests were carried out in air a reduction in frequency led in general to an increase in crack growth rate, an effect attributed to time-dependent oxidation processes. Oxidation can lead to an increase in the threshold level over that observed in vacuum if a tenacious oxide film is formed, as in the case of the 9Cr-1Mo alloy or titanium alloys, or if the extent of oxidation is large enough to increase significantly the closure level, as in the case of 2 1/4 Cr-1 Mo.

Figure 10

An interesting effect of the environment on the extent of strain-induced transformation at the fatigue fracture surface in austenitic stainless steels is shown in Fig. 10. Note that if the fatigue crack growth test is performed in vacuum the extent of

Figure 11

transformation is greater than if the test had been carried out in air. Further in air there is a ΔK dependency of the extent of transformation which is absent in vacuum. Fig. 11 shows how the opening level varies with ΔK . In air the opening level depends on whether ΔK is increasing or decreasing, and this phenomenon has been related to the gradient in the extent of transformation shown in Fig. 10. Recent studies have shown that the difference in the results obtained in air and in vacuum can be explained on the basis of the greater degree of plastic blunting which takes place at a fatigue crack tip in vacuum as compared to air.

Figure 12

Fig. 12 shows the variation of the closure level in air and in vacuum as a function of ΔK at an R value of 0.05 at room temperature. In the 9Cr-1Mo steel where the effects of oxidation are minimized due to the chromium content, there is little difference

between the opening levels in air and in vacuum. Further it is noted that over the range of ΔK investigated the opening level is constant. In the other two steels, both of which are more prone to oxidation near threshold there is a rise in closure level due to the formation of oxides and related fretting debris. The closure processs in vacuum is due to plane-strain, roughness-induced closure, with the additional effects noted in air being associated with oxidation.

Figure 13

Fig. 13 shows that after an overload two opening events can be detected with appropriate instrumentation as the fatigue crack penetrates the overload zone. The lower of the two opening loads occurs in the plane strain region of the crack front, and the higher of the two occurs in the plane stress regions of the crack front at the surface of the specimen. Under constant amplitude loading the difference in the two opening levels is less pronounced, and further improvements in detection capability are needed to distinguish the two opening levels.

RECOMMENDED FURTHER RESEARCH

As a logical next step in understanding the factors that govern fatigue crack growth it is recommended that the work on short cracks [14, 17, 21] and on overload effects [19] be continued. Short crack growth behavior is important because much of the fatigue lifetime can be spent in the propagation of short cracks. In addition there is little information on the effect of overloads on the propagation of short cracks. Further the effect of high R levels on short crack and overload behavior needs to be better understood in order to deal with many design problems of practical significance.

PUBLICATIONS

1. K. Minakawa, H. Nakamura and A. J. McEvily, On the Development of Crack closure with Crack Advance in a Ferritic Steel, Scripta Met., vol. 18, 1984, pp. 1371-74.
2. A. J. McEvily and K. Minakawa, On the Effect of Microstructure on Crack Closure in the Near-Threshold Region, Proc. 7th Int. Conf. on the Strength of Metals and Alloys, ed. by H. McQueen et al., Pergamon Press, New York, 1985, pp. 1385-1392.
3. H. Nakamura, K. Murali, K. Minakawa, and A. J. McEvily, Fatigue Crack Growth in Ferritic steels as Influenced by Elevated Temperature and Environment, in Proc. Int. Conf. on Microstructure and Mechanical Behavior of Materials, Xi'an, China, G. Haicheng and H. Jiawen, eds., EMAS, Warley, U. K., 1986, p. 43.
4. W. Zhu, K. Minakawa and A. J. McEvily, On the Influence of the Ambient Environment on the Fatigue Crack Growth Process in Steels, Engng. Fract. Mech., vol. 25, 1986, pp. 361-75.
5. A. J. McEvily and Z. Yang, Transients in Fatigue Crack Growth due to a Change in ΔK or R, Scripta Met., vol. 20, 1986, pp. 1781-1784.
6. A. J. McEvily, On the Influence of the Environment on Modeling the Fatigue Crack Growth Process, in Modeling Environmental Effects on Crack Growth Processes, ed. by R. H. Jones and W. W. Gerberich, Met. Soc. AIME, 1986, pp. 285-299.
7. A. J. McEvily, On Crack Closure in Fatigue Crack Growth, in ASTM STP 982, Mechanics of Fatigue Crack Closure, ed. by J. Newman and W. Elber, 1987, pp. 35-43.
8. A. J. McEvily, K. Minakawa, and H. Nakamura, Fatigue Crack Growth at Elevated Temperatures in Ferritic Steels, in Advanced Materials for Severe Service Applications, ed. by K. Iida and A. J. McEvily, Elsevier Applied Science, NY, 1987, pp. 291-301.
9. A. J. McEvily and K. Minakawa, On Crack Closure and the Notch Size Effect in Fatigue, Engng. Fract. Mech., vol. 28, 1988, pp. 519-527.

10. A. J. McEvily, An Overview of Fatigue, Keynote Lecture, Fatigue '87, ed. by R. O. Ritchie and E.A. Starke, Jr., vol III, EMAS, Warley, U. K., 1987, pp. 1503-16.
11. J. O. Bunch and A. J. McEvily, On the Behavior of Ferritic Steels Subjected to Load Controlled Cycling at Elevated Temperatures, in Low Cycle Fatigue and Elasto-Plastic Behavior of Materials, ed. by K. T. Rie, Elsevier, London, 1987, pp. 252-257.
12. A. J. McEvily and Z. Yang, On Transients in Fatigue Crack Growth, in Effects of Load and Thermal Histories, ed. by P. Liaw and T. Nicholas, AIME, Warrendale, PA, 1987, pp. 3-12.
13. A. J. McEvily, W. Zagraney, J. Gonzalez, and S. Matsuoka, Fatigue Crack Growth in Type 304 Stainless steel, in Proc. Int. Colloq. on Basic Mechanisms in Fatigue of Metals, ed. by P. Lukas and J. Polak, Elsevier Science Publishing Co., Amsterdam, 1988, pp. 271-280.
14. A. J. McEvily, On the Growth of Small/Short Fatigue Cracks, Int. J. Jap. Soc. Mech. Engrs., vol. 32, Ser. 1, 1989, pp. 181-191.
15. A. J. McEvily and Z. Yang, On Crack Closure in Fatigue Crack Growth, in Failure Analysis-Theory and Practice, (Proc. of the Seventh European Conf. on Fracture, ECF 7) ed. by E. Czoboly, EMAS, Warley, U. K., 1988, pp. 1231-1248.
16. A. J. McEvily and Z. Yang, On the Significance of Crack Closure in Fatigue Crack Growth, Proc. 7th Int. Conf. on Fracture (ICF7), Pergamon, NY, 1989, pp. 937-944.
17. A. J. McEvily and Z. Yang, Analysis of the Growth of Short Fatigue Cracks under Compressive and/or Tensile Cyclic Loading, Met. Trans., vol. 22A, 1991, pp. 1079-82.
18. A. J. McEvily, On Constitutive Relations for Fatigue Crack Growth, Proc. 19th Canadian Fracture Conf., Constitutive Laws of Plastic Deformation and Fracture, 1989, Nat. Res. Council Canada, pp. 12-1 to 12-7.
19. A. J. McEvily and Z. Yang, The Nature of the Two Opening Levels Following an Overload in Fatigue Crack Growth, Met Trans, vol 21A, 1990, pp. 2717-2727.

20. A. J. McEvily and Z. Yang, Fatigue Crack Growth Retardation Mechanisms after Single and Multiple Overloads, Keynote Lecture, Fatigue '90, ed. by H. Kitagawa and T. Tanaka, MCEP Ltd., Birmingham, U. K., pp. 23-36.
21. A. J. McEvily, D. Eifler, and E. Macherauch, 1991, An Analysis of the Growth of Short Fatigue Cracks, Engng. Fract. Mechs., in press.
22. A. J. McEvily, An Analysis of the Growth of Short Fatigue Cracks, 1991, J. Materials Sci. and Engng., in press
23. A. J. McEvily and Z. Yang, An Analysis of the Rate of Growth of Short Fatigue Cracks, J. Fatigue and Fract. of Engng. Mats. and Structures. 1991, in press.
24. M. Okazaki, A. J. McEvily, and T. Tanaka, Crack Growth in Silicon Nitride under Cyclic Loading, in Proc. Mechanical Fatigue of Advanced Materials, ed. by B. N. Cox, R. H. Dauskardt, and R. O. Ritchie, MCEP, Ltd., Birmingham, U. K., 1991, in press.
25. A. J. McEvily and I. LeMay, Hydrogen-Assisted Cracking, Materials Characterization, 1991, vol. 26, pp. 253-268.

END

**DATE
FILMED**

5/14/92