Advanced, Soluble Hydroliquefaction and Hydrotreating Catalysts

RECEIVED
MAY 1 1992

MAY 1 1992

Annual Report No. 1

For the period August 7, 1990 through August 6, 1991

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

^aRichard M. Laine, ^bThomas Stoebe

September 9, 1991

Work Performed Under Contract No.

DE-FG22-90PC90313

^aDepartment of Materials Science and Engineering

H. H. Dow Building, North Campus

University of Michigan

Ann Arbor, MI 48109-2136

^bDepartment of Materials Science and Engineering

Roberts Hall, FB-10

University of Washington

Seattle, WA 98195

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PATENT STATUS

This technical report is being transmitted in advance of DOE patent clearance and no further dissemination or publication shall be made of the report without prior approval of the DOE Patent Counsel

TECHNICAL STATUS

This technical report is being transmitted in advance of DOE review and no further dissemination of publication shall be made of the report without prior approval of the DOE Project/Program Manager

Introduction

Present efforts to convert coal to fuels by direct hydroliquefaction suffer from being two stage direct processes, requiring high temperatures ($>400^{\circ}\text{C}$) and high hydrogen pressures (≈ 2000 psia) to effectively convert coal to a liquid and then to synfuels or petrochemical feedstocks. The need for high H_2 pressures results in excessive consumption of H_2 and an over-hydrogenated (lower quality) product. For a synfuels from coal process to be economical, all facets of the process must be made as efficient as possible. Improved control of reaction temperatures, H_2 pressures and consumption can provide significant improvements in efficiency and economy. All three areas are potentially controllable through careful selection of liquefaction catalysts.

Previous work in this group has shown that, surface confined, organometallic catalysts are exceptionally effective for hydrogenation and HDN of coal model compounds such as quinoline.¹⁻⁶ Unfortunately, surface confined catalysts have not proven to be particularly effective when used with coal itself. The problem derives from the fact that: (1) liquefaction is a solid (catalyst)-liquid (coal polymer) reaction system where, (2) diffusion of coal bonds to the heterogeneous catalyst surface is mass transport limited and controls liquefaction rates. Furthermore, heterogeneous catalyst mediated liquefaction is surface area dependent, placing another constraint on reaction rates.

The purpose of the present program is to develop soluble analogs of surface confined catalysts that can be impregnated directly into the coal structure at low temperatures. This approach should avoid problems related to surface area dependence, a two phase (surface-liquid) reaction system and, mass transport limitations.

Heteropolyanions (HPAs) offer the opportunity to develop soluble forms of surface confined catalysts. HPAs, are inexpensive, well-characterized, water soluble metal oxide clusters, e.g. $[\text{EM}_{12}\text{O}_{40}]^{4-}$ where $\text{E} = \text{Si}$ or P and $\text{M} = \text{Mo}$ or W .⁷ They are easily modified to contain other transition metals such as Co , Ni or Ru and, can be made soluble in organic solvents.⁷⁻⁹ The protic forms exhibit extremely high acidities $\text{pK}_a \approx 0-2$.⁷ In addition, selectively modified HPAs can function as low temperature hydrogenation catalysts that exhibit microporosity.¹⁰ HPAs are multi-functional catalysts that could be used to promote both hydroliquefaction and hydrotreating. In theory, these functions could be employed sequentially or simultaneously and could permit exceptional control of liquefaction reactions and reaction conditions. Thus, the current research program involves efforts to evaluate HPAs as soluble liquefaction and hydrotreating catalysts, with the goal of developing soluble analogs of surface confined catalysts.

Alternately, if HPAs decompose under useful liquefaction conditions, we will explore the utility of creating bimetallic HPAs that can be impregnated into coal and then decomposed to give high surface area heterogeneous catalyst particles that may still permit us to accomplish the above described goals.

The program consists of three major tasks: (1) Preparation of candidate HPA precatalysts; (2) HDN and HDO modeling studies and, (3) Direct liquefaction studies. The following sections outline the research planned in each area.

Task 1. Initially, we will prepare, according to literature procedure, a selected set of simple monometallic heteropolyanions (HPAs) that will be screened in the Task 2 studies. Coincidentally, we will prepare more complex, bimetallic HPAs where the second metal is Ni, Co or Ru. We will prepare bimetallic HPAs wherein the cluster size, in terms of metal atoms, is varied as is the ratio of the two metals. We will also prepare trimetallic HPAs as the results in Tasks 2 and 3 warrant.

Task 2. The HPAs catalyst precursors prepared in Task 1 will be tested for HDN activities, selectivities, and H_2 consumption using quinoline as a model substrate. Solvent will be hexadecane and/or H_2O . We will further evaluate those catalysts found to have superior activity by conducting in-depth rate studies to optimize reaction conditions as a prelude to exploring their use in Task 3.

Task 3. Initially, we will test the efficiencies of selected monometallic and bimetallic HPAs to assess the value of the Task 2 screening studies. Superior HPAs will be tested for ability to promote Wyodak 2 liquefaction and to upgrade the resultant coal liquids. The effects of pressure, solvent, reducing system (H_2 or CO/H_2O) and temperatures on conversions, H_2 consumption and the quality of the coal liquids will be used to evaluate catalyst ability.

PROGRESS TO DATE

In the first year, efforts were directed towards furnishing a coal laboratory, staffing and ordering equipment and initiating a research program.

Because of a hiatus in research due to the move of Richard M. Laine from the University of Washington to the University of Michigan, progress in the first three quarters of the first year were slow. In the fourth quarter, the first detailed efforts were made to study selected HPAs as low-temperature (below $225^\circ C$) hydrogenation catalysts for the selective conversion of quinoline (Q) to tetrahydroquinoline (THQ). In particular, baseline studies were conducted with simple Mo- and W-HPAs to establish standard reaction parameters that permit detailed assessment of the potential of novel bimetallic HPA catalysts and precatalysts.

As will be discussed in the following sections, we have determined that Mo-HPA outperforms both W-HPA, a Co/Mo bimetallic HPA precatalyst, and selected simple metal oxide precatalysts, except ammonium heptamolybdate, under the hydrogenation conditions chosen. A simple bimetallic Mo-HPA/Ru precatalyst system outperforms the individual Mo-HPA and Ru precatalysts by functioning in what appears to be a synergistic manner.

In addition, we find that under the catalysis conditions chosen, the initially homogeneous precatalyst solutions are transformed into an active heterogeneous form. Results indicate that catalyst activity can be directly related to initial precatalyst solution concentration. It is concluded that the active heterogeneous catalyst has exceptionally high surface area as evidenced by the very fine particle sizes observed in scanning electron micrographs.

Experimental Section

General Methods. Quinoline (Q) was purchased from Aldrich and distilled from CaH_2 under N_2 before use. Absolute ethanol was used as received. Molybdophosphoric acid ($\text{H}_3\text{PO}_4 \cdot 12\text{MoO}_3 \cdot x\text{H}_2\text{O} \equiv \text{H}_3\text{PMo}_{12}\text{O}_{40} \cdot x\text{H}_2\text{O}$, Mo-HPA) was purchased from Strem Chemicals and used as received. $\text{RuCl}_3 \cdot x\text{H}_2\text{O}$ ($x=1-3$) was obtained from Johnson Matthey Electronics and stored in a Dri-Box under N_2 . Stoplight compound, $(\text{NH}_4)_6[\text{Co}_2\text{Mo}_{10}\text{O}_{38}\text{H}_4] \cdot 7\text{H}_2\text{O}$, was prepared as described previously.¹¹ Phosphotungstic acid ($\text{H}_3\text{PW}_{12}\text{O}_{40} \cdot x\text{H}_2\text{O}$, W-HPA), ammonium metavanadate (NH_4VO_3), and ammonium heptamolybdate [$(\text{NH}_4)_6\text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$] were purchased from Aldrich, British Drug House Ltd., and Allied Chemical Company, respectively and used as received.

Analytical Procedures. Product analyses for all the kinetic studies were performed on a temperature programmed¹² Hewlett-Packard 5890A reporting GC equipped with FID using a 5 m x 0.53 mm x 2.65 μm capillary column packed with 100 % dimethyl polysiloxane gum.

General Reaction Procedures for Kinetic Studies. Stock solutions of Mo-HPA were prepared before use by dissolving 0.1 g (5.5×10^{-2} mmol) of molybdophosphoric acid (Mo-HPA) in 50 mL of ethanol to form a 1.1×10^{-3} M solution. In a typical reaction, an amount of stock solution (e.g. 5 mL) containing up to 5.5×10^{-3} mmol of Mo-HPA or other catalyst precursor and 5 mL (42.3 mmol) of quinoline (Q) were placed in a magnetically stirred, 34-mL quartz lined bomb reactor with 50 μL of CS_2 . The reactor was sealed and degassed via three pressurization/depressurization cycles using 800 psig N_2 and H_2 and then pressurized to the desired pressure with H_2 . The reactor was heated in an oil bath thermostatted to $\pm 2^\circ\text{C}$ of the appropriate temperature, and samples were taken at selected times by cooling the reactor in cold water bath, depressurizing, and removing a 0.1-mL sample. The reaction was then restarted following the above procedure. In all of the experiments described throughout the paper, the reported H_2 gas pressures are presented as psig, at room temperature.

Procedure A. In the H_2 pressure and temperature studies, 5 mL of the stock Mo-HPA solution and 5 mL (42.3 mmol) of Q were used with 50 μL of CS_2 .

Procedure B. A slightly modified version of Procedure A was used to explore the effects of variations in Mo-HPA and Q concentrations on Q hydrogenation rates. In these studies, the amount of catalyst or Q added for each set was varied over a selected range of concentrations as discussed below.

Procedure C. In these experiments, the required quantities of precatalyst were weighed in air except

$\text{RuCl}_3 \cdot x\text{H}_2\text{O}$ and transferred to a quartz-lined reactor.

Catalyst Activity. In all instances, catalyst activity is measured as a function of the turnover frequency (TF). TF is defined as: No. moles of product (tetrahydroquinoline, THQ)/total moles of metal (not moles of precatalyst)/ hour. Activities were always determined based on less than 25% conversion of Q to THQ. Thus, no falloff effects were included in the TF calculations.

H₂ Pressure Studies. These reactions were run according to procedure A. The reactor was charged with H₂ gas using pressures from 0 to 1000 psig (at room temperature). The reaction temperature was held constant at 200°C.

Catalyst Concentration Studies. Reactions were run as described for procedure B. Experiments were conducted in ethanol using initial H₂ pressures of 600 psig. The reaction temperature was held constant at 200°C. Mo-HPA concentrations were varied between 1.1×10^{-4} M and 5.5×10^{-4} M with total reaction volumes maintained constant at 10 mL. Typically, a known volume (e.g. 1.0 mL) of the stock solution was syringed into the reactor, followed by sufficient pure ethanol (4.0 mL) to maintain constant solvent volume and then 5.0 mL of Q.

Quinoline Concentration Studies. Reactions were run as in the catalyst concentration studies with the exception that the concentration of Mo-HPA was held constant at 5.5×10^{-4} M. Q concentrations were varied from 0.85 to 7.62 M. In these instances, additional ethanol was added to maintain a 10 mL reaction volume.

Temperature Studies. Reactions were run as in the H₂ pressure studies with the exception that the initial H₂ pressure was held constant at 400 psig. Rates were recorded at 150, 175, 200, and 225°C, the range bounded at low temperature by minimal catalyst activity and at the upper temperature by the flammability/decomposition temperature of the oil baths ($\approx 250^\circ\text{C}$).

Catalyst Precursor Survey. A series of potential HPA hydrotreating catalysts were tested for Q hydrogenation activity. The catalysts were surveyed using the following procedures. Reactions were run at constant H₂ pressure (400 psig H₂ at room temperature) at 175°C as described for procedure C. Concentrations of catalyst were 5.5×10^{-4} M in Mo-HPA, 6.5×10^{-5} M for W-HPA, 1.1×10^{-2} M for $(\text{NH}_4)\text{VO}_3$, 1.5×10^{-4} M for $(\text{NH}_4)_6\text{Mo}_7\text{O}_{24} \cdot x\text{H}_2\text{O}$, and 1.8×10^{-3} M in stoplight compound. The stock solution of $\text{RuCl}_3 \cdot x\text{H}_2\text{O}$ was prepared by dissolving 0.03 g (0.11 mmoles) of solid in 20 mL of dry ethanol under N₂ atmosphere and 5 mL of the stock solution (5.7×10^{-3} M) was used for the reaction. Mo-HPA/ RuCl_3 catalyst precursor was prepared by mixing 0.05 mL (5.7×10^{-3} M, 2.87×10^{-4} mmol) of $\text{RuCl}_3 \cdot x\text{H}_2\text{O}$ stock solution with 5 mL of ethanol solution of 5.7×10^{-3} M in Mo-HPA (5.5×10^{-4} mmol).

Solvent Effect Studies. Only acetonitrile was found to be useful for dissolution of Mo-HPA and was used in place of ethanol in this study. The reaction was run as in the H₂ pressure studies (procedure

A) at 600 psig H_2 (measured at room temperature) and 200°C.

Scanning Electron Micrograph (SEM) Studies. SEM micrographs taken of the active catalyst produced when procedure A is run using two conditions (sample 1; 600 psi H_2 , 200 °C, 6 hours and sample 2; 450 psi H_2 , 200 °C, 11 hours) were recorded on a Hitachi Model S-520 scanning electron microscope. Sample 1 was aged for 56 days in air and sample 2 was fresh when SEM was taken. These micrographs are shown in Figures 7, 7A for sample 1 and 8, 8A for sample 2, respectively.

Results

H_2 Pressure Studies. The effects of variations in H_2 pressure (P_{H_2}) on catalyst activity are shown in Figure 1. Within the limits of the current studies, there appears to be an almost linear relationship between H_2 pressure and catalyst activity (turnover frequency, TF). In the absence of H_2 , no catalyst activity is observed for a procedure A reaction solution, even following 27 hours heating at 200°C. These results were anticipated from the fact that H_2 is necessary for the reduction, sulfidation and transformation of the homogeneous catalyst precursor into the active catalyst. Under the conditions studied, it was not possible to ascertain the P_{H_2} required to reach the falloff region, where the relationship TF/P_{H_2} is no longer linear.

Precatalyst Concentration Studies. Figure 2 shows the effect of total metal concentration on catalyst activity. The highest catalyst concentration used in this study (5.5×10^{-4} M) is less than 0.02 mole % of the Q concentration used. Within the range of catalyst concentrations studied, except at very low concentrations, there appears to be a linear relationship between catalyst concentration and TF. These results are extremely valuable because, as we will discuss below, the active catalyst is heterogeneous.

Quinoline Concentration Studies. The results shown in Figure 3 indicate that under the reaction conditions studied, the rate of Q hydrogenation to THQ is not linearly dependent on initial Q concentration. The turnover frequency reaches its maximum ($TF = 20$) at $[Q] = 4.23$ M at $[Mo-HPA] = 5.5 \times 10^{-4}$ M. Considering the extremely high $[Q]$ concentrations used, there are three likely explanations for the observed falloff. One is that above $[Q] = 4.23$ M, the reaction conditions are pseudo first order, with H_2 pressure being the only variable and the falloff above these concentrations resulting from experimental error. Alternately, at these high concentrations, Q competes successfully with H_2 for active catalyst sites thereby slowing the rate of hydrogenation. The third explanation is that at these high Q concentrations, the composition of the reaction solution is considerably changed--there is much less EtOH. Consequently, the solubility or the solvation of the precatalyst changes and the surface area of the active catalyst produced is diminished thereby reducing overall catalyst activity.

Temperature Studies. Initial rates of reaction were determined for each temperature from 150 to 225°C using the reaction conditions described for procedure A in the experimental section with initial H_2

Figure 1. Turnover Frequency as a Function of Initial H_2 Pressure

Figure 2. Turnover Frequency as a Function of [Mo-HPA]

Figure 3. Turnover Frequency as a Function of Changes in [Quinoline]

Figure 4. A plot of $\ln k_{\text{obs}}$ versus $1/T \text{ (K)}$

pressures of 400 psig. Raw reaction rate data are used to calculate initial TFs which are used as k_{obs} in (Figure 4).¹³ These data allow us to calculate the energy of activation, $E_a = 16.4 \pm 3$ kcal/mole.

Catalyst Activity Studies. As shown in Figure 5, the bimetallic Mo-HPA/ $\text{RuCl}_3 \cdot x\text{H}_2\text{O}$ precatalyst system exhibits the highest catalyst activity (TF ~ 10) among the precatalysts surveyed. However, the absence of catalytic activity for W-HPA and $(\text{NH}_4)\text{VO}_3$ were somewhat unexpected considering the modest activities of the polyoxomolybdate catalysts. It is also somewhat surprising that $\text{RuCl}_3 \cdot x\text{H}_2\text{O}$ alone displays such good Q hydrogenation activity (even better than Mo-HPA) as shown in Figure 6. Ruthenium was originally chosen for catalytic studies predicated on its extremely good C-N and C-C bond hydrogenolysis activities as determined in our previous efforts,¹⁻⁶ those of Massoth et al,¹⁴ Chianelli et al.^{15,16} and, Harvey and Matheson.¹⁷

Solvent Effect studies. Two solvents (ethanol and acetonitrile) were used in this study. In EtOH, only THQ was obtained as a product. In acetonitrile, two products are observed, THQ and $\text{C}_2\text{H}_5\text{-THQ}$. The Et-THQ must arise by cleavage of the C-N triple bond in CH_3CN during the hydrogenation of Q.

Discussion

The baseline studies described in the results section were conducted to: (1) develop a set of standard conditions for testing HPA precatalyst systems; (2) identify, under minimum catalyst activity conditions, promising systems for further study at higher temperatures, and (3) establish hydrogenation reactivity patterns of the prospective catalyst systems. These studies were designed to answer several important questions concerning the utility of HPAs as hydrotreating and hydroliquefaction precatalysts. The questions include: (1) Do HPA derived catalysts function as heterogeneous or homogeneous catalysts; (2) What advantages do HPAs offer over conventional catalysts; (3) Are polymetallic HPA derived catalysts better than conventional or monometallic HPA catalysts, and (4) Do the modeling studies reflect what is observed during coal liquefaction.

Minimum activity studies are catalyst activity studies wherein the reaction conditions are far from optimum. As such, many catalysts will show limited or no activity for the reaction being studied and only good to exceptional catalysts will show moderate activity. The results of such screening studies provide an immediate focus for more detailed optimization studies.

How Do HPA Derived Catalysts Function

In the original proposal, we indicated that degradation of the homogeneous HPA systems was a possibility that could only be ascertained by experimentation. We find that HPA systems do indeed produce heterogeneous catalysts; however, the initial results rather than being discouraging are quite promising. Proof of heterogeneity comes from the fact that catalyst activation requires: (1) hydrogen reduction; (2) the presence of sulfur, and (3) an induction period (10-15 min at 200°C) prior to onset of catalyst activity.

Figure 5. Initial Turnover Frequencies at 175 °C for Selected Precatalysts.

TFs calculated based on total moles of metal. Error limits are $\pm 6\%$.

Figure 6. Comparison of the Bimetallic Precatalyst System $\text{Mo-HPA}/\text{RuCl}_3$ with the Individual Monometallic Precatalysts.

*The amount of RuCl_3 in $\text{RuCl}_3/\text{Mo-HPA}$ mixture is 5.24 mole% of Mo-HPA

Without any one of these components, catalyst activation is not obtained. In addition, once the heterogeneous catalyst has been formed, removal of all of the reaction solution (by decantation in air) followed by readdition of more Q and EtOH (but not CS₂) and repressurization to the previous starting H₂ pressure, gives the same catalyst activity as that obtained initially--without an induction period.

Thus, the heterogeneous material formed by reduction, sulfidation and degradation of the HPAs is the true, active catalyst. One positive point about this system is that the active catalyst retains its initial activity after cycling and exposure to air. A second point comes from the observation that there is a direct and linear correlation between precatalyst concentration and catalyst activity (Figure 2). This linear relationship is observed despite the fact that catalysis occurs after conversion of the homogeneous precatalyst to the active, heterogeneous form.

It can be argued that increases in precatalyst concentration should lead to lower, relative catalyst surface areas (leading to lower TF/mole metal) as initially nucleated catalyst particles serve as growth sites for the decomposition of additional HPA molecules. Given that the correlation is linear, we presume that nucleation is a solution phase rather than a surface phenomena. Thus, all of the catalyst particles should be of approximately the same dimensions. The SEMs shown in Figures 7 and 8 support this idea given that the fresh catalyst particles, seen at highest magnification, are submicron and therefore offer very high surface areas.

These results are important for several reasons. First, size reproducibility in the generation of active catalyst particles from solution should be relatively facile. Second, it may be possible to control the catalyst particle size by developing an understanding of the kinetics and mechanisms of particle formation. This in turn may permit one to optimize particle size/catalyst activities. Finally, it may be possible to control many aspects of catalyst activity during HPA impregnation and activation in coal.

What Advantages Do HPAs Offer Over Conventional Catalysts

There are several potential advantages offered by HPAs relative to conventional catalysts. First, HPAs are soluble in a variety of polar and slightly polar solvents including water, MeOH, EtOH, and acetonitrile. Consequently, under liquefaction conditions, it should be possible to tailor the HPA/solvent system to optimize coal swelling and coincidentally catalyst dispersion. By comparison, conventional soluble catalysts such as ammonium heptamolybdate; which exhibits essentially the same activity as Mo-HPA (see Figure 5), is soluble only in water.

Conventional heterogeneous bimetallic catalysts are often used effectively for coal liquefaction and subsequent hydrotreating. Unfortunately, these systems are not amenable to impregnation which means that their proven catalytic advantages over monometallic systems cannot be used effectively. One approach that is potentially employable is double impregnation with two different metals either simultaneously or

Figure 7. SEM Micrograph Picture of Sample 1 (Magnification; X 350, Fresh catalyst)

Figure 7A. SEM Micrograph Picture of Sample 1 (Magnification; X 5.0 K, Fresh catalyst)

Figure 8. SEM Micrograph Picture of Sample 2 (Magnification; X 350, Aged catalyst)

Figure 8A. SEM Micrograph Picture of Sample 2 (Magnification; X 5.0 K, Aged catalyst)

consecutively. One likely drawback is that because of different coal/metal affinities, it will not be possible to conveniently control the exact metal:metal ratios and dispersities necessary to obtain optimal bimetallic catalytic activities in the coal.

Bimetallic HPAs, which offer direct control of the ratios of the two metals, should provide a method of surmounting this problem. Surprisingly, the survey results with the bimetallic "stoplight" precatalyst, $(\text{NH}_4)_6[\text{Co}_2\text{Mo}_{10}\text{O}_{38}\text{H}_4] \cdot 7\text{H}_2\text{O}$ reveal a catalyst activity that is somewhat less than that exhibited by Mo-HPA and the heptamolybdate on a per-mol of metal basis. The most likely explanation for this is that the effectiveness of bimetallic catalysts such as "CoMo" and "NiMo" derives from their ability to effect C-N bond hydrogenolysis rather than hydrogenation of Q to THQ. Indeed, one could argue from our data on Mo-HPA, Stoplight, and the heptamolybdate that hydrogenation of Q must occur almost entirely on sulfided molybdenum sites. The stoplight compound,¹ with some cobalt should generate catalyst particles with some portion of the surface "protected" by cobalt. Consequently, if sulfided molybdenum sites are indeed responsible for hydrogenation, one would expect the stoplight derived catalyst to exhibit lower TFs for Q hydrogenation, as observed. An alternate explanation is that the decomposition pattern for the stoplight compound is different from that of Mo-HPA. This represents an area of future study.

Polymetallic HPA Precatalysts vs Conventional or Monometallic HPA Precatalysts

If we were only to compare the catalytic efficiencies of Mo-HPA, Stoplight, and the heptamolybdate as catalysts for the hydrogenation of Q to THQ, then we could argue that there is no obvious difference and further investigation is not warranted. Alternately, a more valid criticism would be that we have chosen the wrong reaction conditions to test catalytic activity. That is, we should also develop standard tests for HDN catalysis. Indeed these tests will be developed in the next year as noted in the section on Future work.

Fortunately, we have conducted one set of tests based on our previous discovery that RuMo bimetallic systems were exceptionally active HDN systems.² Our previous studies were conducted with the objective of optimizing Ru/CoMo/ α -alumina catalysts for the HDN of Q to propylbenzene.² It was assumed that the major function of the ruthenium in this trimetallic system was to promote C-N bond cleavage at extremely low temperatures. No efforts were made to determine the effects of ruthenium on the individual metals (Co and Mo) or the effects of the alumina support on the overall activity of the catalysts. Furthermore, no effort was made to explore the effects of Ru on the hydrogenation activity of this catalyst system.

We have begun to assess all of these variables here to establish a more detailed understanding of the effects of Ru both on hydrogenation and HDN as a prelude to developing Ru-HPAs. As can be seen in Figure 6, the use of a soluble Ru catalyst (as $\text{RuCl}_3 \cdot x\text{H}_2\text{O}$) alone provides an exceptional heterogeneous hydrogenation catalyst. However, what is considerably more surprising is that simple mixtures of the soluble Ru catalyst with Mo-HPA, where the Ru content is ≈ 5 mole percent of the total Mo content, provide a catalyst system that is just as effective as the pure Ru catalyst and four times as effective as the simple

Mo-HPA catalyst. The results clearly point to a synergistic system. It is too early to speculate on the reasons for these results; however, it is clear that an alumina support is not necessary to promote the hydrogenation reaction; although, it may have some effect on long-term catalyst activity.

Hydrogenation Modeling Studies vs HDN Activity vs. Coal Liquefaction Behavior.

The RuMo catalyst, which shows exceptional activity for Q to THQ conversion, was explored based on the exceptional abilities of a supported RuMo material to promote THQ HDN catalysis as previously reported from these laboratories.¹⁻⁶ Although it is tempting to claim that the hydrogenation activities parallel the previously determined HDN (C-N bond hydrogenolysis) activities, we believe that the parallel is coincidental. For example, both Rh and Pd catalysts are quite effective as hydrogenation catalysts but exhibit only moderate HDN activity.^{18,19}

The use of a Ru/Mo-HPA bimetallic system in the hydrogenation studies reported above appears to work well and will be pursued in greater detail in the future; however, this system can only serve usefully as a baseline because of the method of catalyst preparation. Because hydrogenation catalysis begins with homogeneous precatalysts, it was possible to prepare a precatalyst system that consists of soluble forms of both Ru and Mo. In direct liquefaction studies, a major concern (see above) will be our ability to achieve the same bimetallic catalyst properties by impregnation of coal with the two independent, soluble species. Thus, it is clear that efforts must be directed towards the development of Ru/Mo-HPAs both for contrast purposes in the solution phase studies and for the direct liquefaction studies

Future Work

Although several details and questions remain unanswered; as discussed above, the current studies provide boundary conditions for studies on other model compounds including sulfur containing species and planned studies with coal. They also point to the need for complementary modeling studies on HDN of THQ to propylbenzene and propylcyclohexane.

For example, such studies are necessary to avoid ignoring HPAs already studied, ie. W-HPA, should they offer exceptional HDN activity. In such an event, one could envision developing trimetallic HPAs that serve as multifunctional catalysts. One metal or two doing hydrogenation and the remaining metallic species promoting HDN.

Now that the baseline, minimum activity parameters for testing HPAs have been worked out for hydrogenation of Q to THQ, we will begin synthesizing other HPAs (see original proposal for details) to test in the survey reaction. We will simultaneously begin to develop an HDN model reaction to continue the screening process. As we identify specific HPAs with exceptional properties for hydrogenation and/or HDN catalysis, we will begin efforts to liquefy coal.

We have ordered Wyodak coal samples from the Argonne repository and plan to begin liquefaction studies in the sixth quarter.⁹ We have just drawn up plans for a heater system whereby the Parr autoclaves currently used, can be heated to 350°C so that minimum activity liquefaction studies can be performed. As with the model systems, it will be necessary to develop a screening process. We plan to use reaction conditions identified previously as a starting point.^{1,6}

References

1. "New Catalysts for Hydrotreating Coal Liquids." A. S. Hirschon, R. B. Wilson Jr., and R. M. Laine, Am. Chem. Soc. Div. Fuel. Prepr. (1986) **31**, 310-317.
2. "Modeling the Hydrodenitrogenation Reaction Using Homogeneous Catalyst Model Systems." A. S. Hirschon, R. B. Wilson, Jr.; and R. M. Laine, New J. Chem., (1987) **11**, 543-547.
3. "New Approaches to Enhance Hydrodenitrogenation of Coal Liquids" A. S. Hirschon, R. B. Wilson, Jr., R. M. Laine, in Adv. in Coal Chemistry, Theophrastus Publ, Athens 1988, p 351.
4. "Ruthenium Promoted Hydrodenitrogenation Catalysts." A. S. Hirschon, R. B. Wilson Jr., and R. M. Laine, J. Appl. Cat. (1987) **34**, 311-316.
5. "Bulk Ruthenium as an HDN Catalyst", A. S. Hirschon and R. M. Laine, J. Energy and Fuels (1988) **2**, 292-295.
6. "Use of Promoters to Enhance Hydrodenitrogenation and Hydrodeoxygenation Catalysis", A. S. Hirschon, L. L. Ackerman, R. M. Laine, and R. B. Wilson, Jr. Proc. of the 1989 Internat. Conf. on Coal Science, Tokyo, Vol. II, p. 923.
7. Heteropoly and Isopoly Oxometalates, M. T. Pope, Springer-Verlag Pub., Berlin, GDR 1983.
8. R. F. Renneke and C. L. Hill, J. Am. Chem. Soc., (1988) **110**, 5461.
9. R. K.C. Ho, W. G. Klemperer, J. Am. Chem. Soc., (1978) **100**, 6774.
10. A. R. Siedle, R. A. Newmark, M. R. V. Sahyun, P. A. Lyon, S. L. Hunt, and R. P. Skarjune, JACS (1989) **111**, 8346.
11. G. Tsigdinos, Dissertation Abstract, University of Michigan, B22, 732 (1961)
12. The conditions for the GC heating program used in this study are: Initial temperature; 35°C, initial time; 30 sec., final temperature; 180°C, Final time; 1 min., Rate; 15 deg./min, oven temperature; 35°C, injection temperature; 200°C, detector temperature; 250°C, equilibrium time; 1 min.
13. k_{obs} at each temperature is obtained from the slope of the equation, $d[THQ]/dt = k_{obs}[Q]^0$, assuming zero order reaction from data obtained. The activation energy, E_a , is calculated from the expression $k_{obs} = Ae^{(-E_a/RT)}$.
14. F. E. Massoth and J. S. Shabtai, "Catalysts Possessing Augmented C-O and C-N Hydrogenolysis Activity", Progress Report No. 6, PETSC Contract No. DE-FG22-83PC60812.
15. T. A. Pecoraro and R. R. Chianelli, J. Catal. (1981) **67**, 430.
16. S. Harris and R. R. Chianelli, "Catalysis by Transition Metal Sulfides: The Relation between Calculated Electronic Trends and HDS Activity", J. Catal. (1984) **86**, 400
17. T. G. Harvey and T. W. Matheson, "Hydrodenitrogenation Catalyzed by Zeolite Supported Ruthenium", J. Chem. Soc. Chem. Comm. (1985) 188.
18. S-I. Murahashi, Y. Imada, and Y. Hirai, "Rhodium Catalyst Hydrogenation of Quinolines and Isoquinolines under Water-Gas Shift Conditions", Bull. Chem. Soc. Jpn. (1989) **62**, 2968.
19. M. J. Guttieri and W. F. Maier, J. Org. Chem. (1984) **49**, 2875.

END

**DATE
FILMED**

6 / 11 / 92