Proc. 3rd Argonne Nat'l. Lab Workshop
on Basic Problems in Nuclear Waste,
Oct. 1-2, 1981, to be published in
Nuclear Tech.

BNL 30659

Conf-8110113--3

BNL--30659

DE82 011553

RADIATION-DAMAGE STUDIES ON NATURAL ROCK SALT FROM VARIOUS GEOLOGICAL
LOCALITIES OF INTEREST TO THE RADIOACTIVE-WASTE-DISPOSAL PROGRAM*

MASTER

Paul W. Levy

Brookhaven National Laboratory

Upton, N.Y., 11973

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

*Research supported by the Department of Energy Office of Nuclear Waste Isolation (ONWI), operated by Battelle Institute, Columbus, Ohio, and the Department of Energy, Division of Basic Energy Sciences, under contract DE-AC02-76CH00016.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MCW

ABSTRACT

As part of a program to investigate radiation damage in geological materials of interest to the radioactive waste disposal program, radiation damage—particularly radiation induced sodium metal colloid formation—has been studied in 14 natural rock salt samples. All measurements were made with equipment for making optical absorption and other measurements on samples, in a temperature controlled irradiation chamber, during and after 0.5 to 3.0 MeV electron irradiation. Samples were chosen for practical and scientific purposes, from localities that are potential repository sites and from different horizons at certain localities. At room temperature and at low doses only F-centers (Cl^- ion vacancies) and a variety of "V-region" absorption bands are present. Above 100°C and at high doses intense sodium metal colloid particle absorption bands are formed. F-center formation begins immediately after the irradiation is initiated and increases monotonically to a well-defined plateau, reached at doses of $10^6 - 10^7$ rad. In natural rock salt samples, not purposely strained in the laboratory, the colloid formation is well described by classical nucleation and growth curves with the initial induction, or low growth rate nucleation region, extending to $10^6 - 10^7$ rad. In all samples measured to date, the rapid colloid growth region is well described by $C(\text{irradiation time})^n$ or $C(\text{dose})^n$ relations. Aside from the temperature dependence, at least three factors modify the colloid growth rate. 1) The induction period is shortened by straining samples prior to irradiation. For strains up to roughly 10 percent it is progressively shortened. Around 10 percent strain the induction period is negligible or zero. Strains above this value do not produce large additional effects. 2) The colloid formation rate increases as the dose rate decreases, i.e. on a unit

dose basis, lower dose rates produce more colloids than higher dose rates. 3) Colloid formation appears to be related to the salt impurity level. It is suppressed in regions of crystals containing approximately 1 percent Ca and S. Both the F-center and colloid particle formation is strongly temperature dependent. The F-center formation rate and plateau level is high at 100°C and decreases monotonically to a low or negligible level at 300°C. The colloid formation rate is low or negligible at 100-115°C, and as the radiation temperature is increased, increases to a broad maximum at 150-175°C and then decreases to a negligible level at 250-300°C. The colloid growth curve induction period is greater than 10^4 seconds at 100°C, decreases to less than 3000 seconds at 150-175°C, and is greater than 10^4 seconds at 275-300°C. Colloid formation has been carefully studied in the 14 "naturally impure" rock salt samples at a temperature where the colloid formation rate is a maximum—namely 150°C, at a dose rate of 1.2×10^8 rad/hr and to total doses of $2-4 \times 10^8$ rad. Colloid formation rates vary by a factor of 10 or more between samples from different localities. Using the $G(\text{dose})^n$ relation to estimate the colloid formed in actual repositories indicates that in 50-400 years, a dose of 10^{10} rad will convert between 0.1 and 10 percent, and 2×10^{10} rad will convert between 1 and 50 percent of the salt to colloidal sodium metal. The chemical and physical properties of rock salt containing colloid sodium metal at these levels differs markedly from that of normal rock salt and the salt is likely to interact vigorously with canisters, backfill materials, water, etc.

I. INTRODUCTION

A survey of radiation damage in natural rock salt from widely separated geological localities is the latest subject to be emphasized in a program to study radiation effects in minerals, back fill materials, and waste forms of interest to the national radioactive waste disposal program. Under study are samples from sites of purely scientific interest, from potential repository locations, from repositories such as Asse in the FRG and from different horizons at selected sites. As will be demonstrated, the principle manifestation of radiation damage is the formation of sodium metal colloid particles and, as dictated by simple material balance, an equivalent amount of chlorine. The exact disposition of the chlorine is, at the moment, one of the principal unsolved scientific questions regarding radiation damage in rock salt. The amount of colloid formed and the colloid formation rate varies greatly from site to site and depends strongly on dose rate, total dose, temperature, strain, impurities and possible undiscovered factors. This presentation can be regarded as an updated version of a review of radiation effect studies on natural and synthetic rock salt (1) or as an expanded version of a paper presented at the Materials Research Society 1981 Symposium on the Scientific Basis for Nuclear Waste Management (2).

II. A CURSORY VIEW OF RADIATION DAMAGE IN NATURAL ROCK SALT

Radiation damaged rock salt from the Lyons KS Radioactive Waste Demonstration Project (3) is shown in a black and white version of a color photograph in figure 1. The salt that was farthest from the fuel element received a gamma ray dose in the $10^3 - 10^4$ rad range and is typical of normal bedded rock salt from the horizon where the tests were made. In contrast, the salt which was closest to the fuel element and received a dose in the $10^7 - 10^8$ rad range has several

unique characteristics. It has a very dark blue-black color, is appreciably harder than unirradiated salt, and fractures quite readily. The blue-black color is attributable to the presence of sodium metal colloid particles. The samples from intervening distances grade from blue-black to greyish-white with the intermediate examples exhibiting the light blue to purple color often described in the German mineralogy literature as "blau steinsalz." Note that none of these samples exhibit the golden brown color of natural or synthetic rock salt which contains only radiation induced F-centers. This is not surprising, both melt grown synthetic NaCl crystals--especially if they have been strained--and natural rock salt samples are golden brown in color after exposures of $10^6 - 10^7$ rad at room temperature. However, such crystals develop "steinsalz blau" blue color after being stored in the dark, at room temperature, in three to six months. The samples shown in figure 1 were removed from the Lyons KS mine some months after the fuel element had been removed.

The sections that follow contain a concise description of radiation induced F-center and colloid particle formation in both natural and synthetic melt grown rock salt, a brief summary of the current information on the various factors that control irradiation damage formation in these materials, and brief sketches of applications to repository site selection, engineering, etc.

III. EXPERIMENTAL DETAILS

Almost all of the measurements described below were made with equipment at Brookhaven National Laboratory for making optical absorption, luminescence and other measurements on samples while they are being irradiated with monoenergetic electrons. The major portion of this apparatus is shown schematically in figure 2. Basically, it is a 13 meter long double beam spectrophotometer with all

equipment which might be sensitive to radiation outside of the radiation chamber. A computer is used to control the apparatus and to record data. Typically, absorption and luminescence spectra are recorded at selected intervals, as close together as every 50 seconds, during the entire irradiation. For the measurements described below they cover the 350 to 750 nm wavelength range, i.e. 1.6 to 3.0 eV photon energy. Except for dose rate studies, all measurements were made at a dose rate used was 1.2×10^8 rad/hr. The incident electron energy was 1.5 meV; an energy sufficient to ensure that the bombarding electrons completely traversed the samples. This condition must be fulfilled to prevent the build-up of internally trap charges which would lead to electrical breakdown in the crystals. Also, as is well known, gamma rays interact with solids by the formation of electron recoils. Most importantly, the interaction between the recoil electrons and solids is precisely equivalent to that produced by bombarding electrons. Thus, information obtained by electron bombardment is immediately applicable to the evaluation of gamma-ray induced damage. However, in evaluating gamma-ray induced radiation damage it is essential to include the penetrability of the gamma rays prior to the electron recoil formation event.

During each measurement a large number of absorption spectra were recorded. As described below, at large doses overlapping F-center and colloid absorption bands are present and were resolved into individual components using previously described techniques (4,5,6). For each sample studied, a sufficient number of absorption spectra were resolved into individual F and colloid band components to construct precise curves of F-center and colloid particle concentration vs. irradiation time curves, often called coloring curves.

Natural rock salt samples were obtained from the geological localities, and from different horizons at certain locations, listed in table 1. Measurements were made on single crystals, usually $8 \times 8 \times 0.75$ mm, or thinner, cleaved from individual crystallites obtained from cores or pieces of rock salt. The samples obtained from the localities in table I contain relatively few crystallites large enough to provide samples of this size which are free of voids, inclusions, etc.. Consequently, often 0.5 kg, or so, of rock had to be carefully separated before a suitable crystal is located. The samples listed in table 1 represent roughly $2/3$ of all samples received. The remaining samples do not contain crystals large enough to measure. Because of this selection process the results are biased towards samples that contain large crystallites. Methods are being developed for studying samples containing only small crystallites and/or making measurements on centimeter size samples that are representative of unseparated rock salt.

Samples were irradiated in a chamber, containing a few millimeters of helium exchange gas, whose temperature was controlled electronically. The electronic temperature control apparatus utilizes a single thermocouple in contact with the exchange gas. The sample temperature is measured independently with a second thermocouple in contact with it.

The chamber contains fused silica windows for transmitting the spectrophotometer light beams and thin Havar metal windows for transmitting the electron beam. In principle, any irradiation induced coloring in the fused silica windows is compensated for by the dual beam nature of the spectrophotometer. However, by using high purity fused silica windows it was possible to avoid radiation induced coloring in the wavelength range used for the measurements

described here. The electron beam is sufficiently intense at the dose rate used for these studies, 1.2×10^8 rad/hr, to heat the samples between 3 and 5 degrees. Consequently, prior to irradiation the temperature controlled chamber was adjusted to 3 to 5 degrees below the desired temperature. When the irradiation commences the sample temperature increases rapidly to the desired temperature and remains constant, to within a degree or so, during the remainder of the irradiation, provided that the accelerator beam current remains reasonably constant.

IV. PHENOMENOLOGY OF RADIATION DAMAGE IN NATURAL AND SYNTHETIC ROCK SALT

As described previously, radiation damage formation in both natural and synthetic rock salt occurs in a qualitatively similar fashion (1,6,7,8). When exposed to 1.5 meV electrons, at a dose rate of 1.2×10^8 rad/hr, and with the sample at room temperature, a prominent F-center band is introduced which is accompanied by several "V-region" bands. Undoubtedly, the V-region bands play a role in the F-center formation. However, they have not been studied in detail and will not be discussed here. As a function of dose or irradiation time, the F-center absorption increases monotonically to a well-defined plateau. At roughly the dose where the F-band reaches the plateau M-bands are usually observed. Colloid bands are not observed at room temperature during irradiations as large as $2-4 \times 10^8$ rad.

At temperatures between 100 and 300 degrees C, the general features of the radiation induced absorption and luminescence, in both natural and synthetic rock salt are demonstrated by figure 3. At temperatures where both F-center (negative ion vacancy) and colloid particle absorption bands are observed, between approximately 115° and 250°C, the F-center concentration vs. dose curves

increase monotonically to well-defined plateaus, which are reached in 10^7 to 10^8 rad range. The colloidal sodium metal absorption bands are well described by classical nucleation and growth curves with the transition from the induction period to the rapid growth region occurring at about the dose where the F-center concentration reaches saturation. Both the F-center growth to a plateau or saturation level and the nucleation and growth character of the colloid absorption is demonstrated clearly in figure 3. Although it will not be discussed in this paper, this figure also shows the radiation induced luminescence typically emitted by rock salt samples during electron irradiation. It is readily shown that the decrease in intensity occurring after the irradiation has commenced does not result from the absorption of luminescence by the radiation induced absorption bands. Thus, this reduction is related to the luminescence emission processes.

In both natural and synthetic rock salt the F-center and colloid growth is strongly temperature dependent. In both materials the F-center formation rate and saturation level is largest at 100-115°C and with increasing temperature decreases monotonically until it reaches a negligible level at 250-300°C. The temperature dependence of the colloid formation is qualitatively similar for both natural and synthetic rock salt. The temperature dependence of the radiation induced colloid formation for samples from the 810 m level of the WIPP site (Waste Isolation Pilot Project, Los Medanos, NM) is shown in figure 4. The heavy solid lines show the radiation induced colloid formation measured at various temperatures. These colloid absorption vs. irradiation time, or coloring curves, are well approximated by straight lines on log-log plots, at least in the high dose portions of the data curves. In other words, at high doses

the colloid formation is well approximated by Ct^n relations, where C and n are constants, and t is irradiation time. In both natural and synthetic salt C and n values are obtained which are appropriate for the temperature dependence shown in figure 4 and described below. For WIPP salt the C values are around 10^{-6} at 100-115°C, decrease with increasing temperature to 2×10^{-8} at around 180°C, and increase to roughly 10^{-6} at 225°C. In natural rock salt the n values are relatively independent of temperature and lie between 1.7 to 2.2. The n values for melt grown synthetic NaCl crystals depend markedly on temperature. At roughly 130°C the value of n is approximately 4, increases to approximately 6.5 at 190°C, and then decreases to approximately 1.8 at 230°C.

In figure 4 the solid line contours show how the colloid growth depends on temperature. The colloid growth rate is low or zero at 115°C, increase rapidly with increasing temperature to a maximum in the 150-170°C range, and as the temperature increase further decreases to a negligible level at 250°C. The dashed contour line shows that the colloid growth curve induction period is more than 10^4 seconds at 100°C, decreases with increasing temperature to a minimum of less than 3000 seconds around 150°C, and increases more than 10^4 seconds at 250°C. To repeat, the induction period dependence in synthetic NaCl is qualitatively similar. Two important observations about the induction period at room temperature should be mentioned. First, samples exposed to 10^8 rad at room temperature do not exhibit colloid absorption bands at the end of the irradiation. However, they exhibit pronounced colloid absorption bands after being stored for 3 to 6 months in darkness at room temperature. There is a marked tendency for the slowly appearing colloid coloring to lie along the $\langle 110 \rangle$ planes associated with plastic deformation induced slip systems. Second, samples irradiated at room

temperature develop appreciable concentrations of colloids when heated for 1 to 2 hrs in the 150-250°C range (9). In fact, rock salt samples irradiated at room temperature develop M-centers as they are heated initially. Additional heating produces colloid absorption bands. Prolonged heating at 250°C removes all color center bands but the colloid absorption bands remain.

V. RADIATION INDUCED COLLOID FORMATION IN NATURAL ROCK SALT FROM VARIOUS GEOLOGICAL LOCALITIES

To determine if radiation damage--especially radiation induced colloid formation--varies in salt from different geological locations, studies are being made on both bedded and dome rock salt samples from widely separated localities. Some samples were chosen for purely scientific purposes while other samples are from localities of definite interest to the National Radioactive Waste Disposal Program. For this survey of natural samples all measurements were made at 150°C and at a dose rate of 1.2×10^8 rad/hr. Samples were selected which were free as possible from voids, discolored areas, macroscopic defects and strain induced plastic deformation. For each sample numerous absorption spectra, such as shown in figure 2, were recorded and resolved into F-center and colloid absorption band components. The resulting colloid absorption band areas vs. irradiation time curves for the first 14 samples studied are shown in figure 5. The constance in the Ct^n relation, obtained by fitting this expression to the high temperature end of the data curves, are contained in table I. For the 14 samples listed the n values are between 1.6 and 2.4 and the average n is 1.85 ± 0.18 . However, the C values vary by a factor of 10^3 or more. As discussed below, this data can be used to estimate the amount of radiation damage, particularly colloid particle formation, in natural rock salt near waste canisters in repositories.

Table I

The constants, C and n, in the relation (Mole Fraction NaCl Converted to Colloidal Na) = Ct^n , where t is irradiation time in seconds. The values were obtained from the data in Figure 5 by a best fit procedure.

Sample	n	C
AEC-8, NM, USA (WIPP site)	1.87	4.50×10^{-13}
ALT AUSEE, Austria	1.98	3.60×10^{-13}
ASSE 1, FRG	1.84	2.71×10^{-12}
ASSE 4, FRG	1.77	1.34×10^{-12}
ASSE 6, FRG	2.08	1.60×10^{-13}
ASSE 8, FRG	2.17	1.86×10^{-14}
ASSE 9, FRG	2.05	6.47×10^{-14}
Avery Island, LA, USA	1.66	8.80×10^{-12}
ERDA-9, NM, USA	1.73	2.82×10^{-12}
Lyons, KS, USA	1.87	7.43×10^{-13}
Retsof, NY, USA	1.56	4.14×10^{-11}
Rocanville, SK, Canada (above ore)	1.57	2.72×10^{-11}
Rocanville, SK, Canada (with ore)	1.83	6.78×10^{-13}
Rocanville, SK, Canada (recrystallized)	2.41	6.14×10^{-15}

VI. FACTORS INFLUENCING RADIATION INDUCED COLLOID FORMATION IN NATURAL ROCK SALT

At least 3 factors influence radiation induced colloid formation in natural rock salt in addition to the pronounced temperature dependence described above.

Colloid formation in plastically deformed samples: As shown in previous publications and illustrated in figure 5, subjecting both synthetic and natural rock salt to plastic deformation, by uniaxial compression, prior to irradiation markedly reduced the colloid growth curve induction period (1,6,7,8). For strains between 1 and 10 percent the induction period decreases with increasing strain. Strains of roughly 10% reduce the induction period to zero or to very small irradiation times or doses. Strains above this value do not introduce any large additional effects. It has been shown previously (10) that straining KCl crystals during irradiation markedly increases the F-center coloring rate. Presumably, plastically deforming NaCl crystals during irradiation will have similar large effects on the F-center and colloid formation rates. Equipment for such measurements is being assembled. The reduction in induction period associated with plastic deformation clearly indicates that there is a connection between dislocations in the rock salt lattice and the colloid particle nucleation rate. Also, recently completed theoretical studies indicate that both $\langle 100 \rangle$ and $\langle 111 \rangle$ edge dislocations are likely sites for colloid particle nucleation and that they are about equally strong nucleation sites (11,12). A large number of measurements regarding colloid formation are yet to be made. For example, it should be determined if the colloid size distribution in strained samples is different from that in unstrained samples. In samples not

strained in the laboratory, colloid formation in synthetic salt differs from that in natural salt (4,5). The annealing of strained and unstrained samples containing colloid particles has not been studied, etc.

Colloid formation in rock salt irradiated at different dose rates: Radiation induced colloid formation at three different dose rates, in rock salt samples from the WIPP site, is shown in figure 7. This figure demonstrates that colloid formation increases as the dose rate decreases. In other words, on a unit dose basis, low dose rates produce more colloids than high dose rates. Very similar results are obtained with synthetic melt grown NaCl crystals (1,6,7,8). The dose rates used in these studies are 10^3 to 10^4 times larger than those expected in radioactive waste repositories. For repository engineering purposes it is essential to make additional dose rate studies. It is conceivable that the low dose rates expected in repositories will be much more efficient in producing colloids than the high dose rates used in these studies.

Lattice impurities and radiation induced colloid formation: As expected from well-known color center studies (13) both the radiation induced color center and colloid formation processes are strongly influenced by the impurity content of the sample. One, of a large number, of indications of impurity effects in colloid formation is illustrated in the data for samples from Rocanville, Sask., Canada, shown in figure 5 and table I. Colloid formation in samples from a layer of bedded salt above the ore horizon is appreciably greater than that in samples from the ore horizon which contains intermixed rock salt and potash ore. Almost certainly, salt from the upper horizon is purer than salt from the lower ore horizon. Furthermore, colloid formation in samples of recrystallized rock

salt from the ore horizon is greater than that from the usual bedded salt samples. It is reasonable to expect that the recrystallized salt--sometimes referred to as "Vug" salt--would be appreciably purer than the salt from the surrounding matrix.

Additional information on radiation damage in impure salt has been obtained from proton microprobe studies on rock salt samples that do not color uniformly. A black and white version of a color photomicrograph of natural rock salt which was not colored uniformly after irradiation is shown in figure 8. The dark areas are blue-black, indicating the presence of both F-centers and colloidal sodium metal particles. The light area is golden yellow, indicating that only F-centers are present. The center of the white area contains a line of voids, most of which are partially or entirely brine filled. In this crystal, the colloid formation has been suppressed in the region surrounding the void. Microprobe studies have not been made on samples containing light areas surrounding voids such as shown in figure 8. However such studies have been made on samples containing similar light and dark areas which may or may not contain voids (14). Typical impurity level data for the light and dark areas, obtained by proton microprobe, are shown in Table II.

The data in table II clearly shows that colloid formation is suppressed in the impure regions where the sulfur and calcium content is in the 1 percent range and additional impurities are present in the part per million range. Thus, at the moment, it appears that the presence of both voids and/or impurities inhibit colloid formation. Proton microprobe studies on samples obtaining clear regions around voids are planned for the near future.

Table II

Impurities in colloid-rich and colloid free areas in irradiated natural rock salt, obtained by proton microprobe techniques (14).

Colloid Level	Impurity Content						
	S	Ca	Fe	Co	Cu	Br	Sr
Low or zero	1.0%	1.2%	4 ppm	4 ppm	6 ppm	40 ppm	65 ppm
High	ND	ND	ND	ND	5 ppm	36 ppm	ND

ND = Not Detected

VI. APPLICATIONS TO RADIOACTIVE WASTE REPOSITORIES IN ROCK SALT

The information outlined above has important applications to the selection of sites for radioactive waste repositories in natural rock salt, the design of a repository in a specific site, the design of canisters to contain the radioactive waste form and other aspects of site selection and design.

The total amount of radiation induced colloidal sodium metal expected in the rock salt surrounding any canister can be estimated from the data in table I. More explicitly, this data can be used to extrapolate the curves in figure 5 to any irradiation time--or any total dose, subject to the following assumptions:

- 1) The Ct^n relation is valid above the total dose--or irradiation time--used to obtain the data in figure 4.
- 2) The dose rate is 1.2×10^6 rad/hr.
- 3) The surrounding rock has been heated to 150°C by the waste canisters.
- 4) The gamma-ray dose rate at the surface of the canisters is in the $2\text{--}5 \times 10^4$ rad/hr range. Actually, the dose rate data is needed only to estimate the time required for the surrounding rock salt to reach a given dose level.

From the data in table I, subject to the assumptions listed above, one obtains the colloid levels shown in table III for total doses of 10^{10} and 2×10^{10} rad, for the samples studied to date. It is worth pointing out that doubling the total dose increases the colloid content by roughly a factor of four. Two major conclusions are demonstrated by table 2:

- 1) Rock salt from certain localities and/or horizons develops appreciably less radiation damage than salt from other localities. Thus, to minimize radia-

tion effects in the surrounding salt one would choose localities and/or horizons where the damage formation rate was a minimum.

2) Appreciable amounts of colloidal sodium metal can be formed in the surrounding rock salt. Although not discussed in detail in this paper, the physical and chemical properties of rock salt containing this degree of radiation damage are appreciably different from normal rock salt. For example, such rock salt reacts strongly with water to produce a number of chemical species (15) and readily observed hydrogen gas bubbles. Physically it is different from ordinary rock salt; it is brittle--not plastic--friable, exceptionally susceptible to cleaving, and when cleaved or broken emits an odor of chlorine gas.

The estimates contained in table III can be expected to be altered by a number of known factors and possibly some that have not yet been discovered.

1) Dose rate effects may be expected to increase the colloid content of irradiated rock salt. As demonstrated above the colloid formation increases as the dose rate decreases. The dose rates used for these studies are approximately 10^4 higher than those expected in repositories. Also, the dose rates will be highest in the salt nearest the canister and diminish as the distance from the canister increases.

2) As outlined above and described in references (1), (7) and (8), plastic strain and/or deformation diminishes or eliminates the colloid growth induction period. In the currently available data there is an indication, but not an unequivocal demonstration, that the colloid formation rate is greater in strained samples than in comparable unstrained samples.

3) Impurity effects may be expected to reduce the colloid formation. However, the samples studied to date can be considered as normal "impure" natural rock salt.

4) The estimates in table 3 are for the temperature at which the colloid formation rate is a maximum at the dose rate used in the studies. If the effective temperature of the rock salt is at a lower temperature it is quite possible that the total amount of colloid formed will be reduced. However, a lower effective temperature may simply extend the colloid growth induction period. As mentioned elsewhere, colloids are formed in samples irradiated at room temperature, particularly in strained samples, but they do not appear until three or six months after irradiation. Because of the long time periods involved, data are not available on colloid formation between room temperature and 100°C.

The data on radiation damage is natural rock salt outlined above, together with any of the computer programs for calculating gamma-ray transport through solid substances, makes it possible to calculate the radiation induced sodium metal colloid concentration around each canister. As far as can be determined, this calculation has not been attempted. However, it would appear that each canister will be surrounded by an ellipsoid or "foot ball" shaped region of radiation damaged salt. The colloid concentration will be a maximum at the surface of the canister and decrease with distance from the canister surface in a fashion intermediate between a linear and exponential decrease. At roughly a meter from the canister surface the colloid concentration will be very roughly one percent of that at the canister surface. The salt adjacent to the canister will be quite brittle. Information is not available to estimate the shear strength of the most highly irradiated salt and how the strength will depend on dose. In

Table III

Percent sodium metal colloid expected in rock salt at canister interfaces for 10^{10} and 2×10^{10} rad; approximately 50 to 400 years for a dose rate at waste form surface of 2×10^4 rad/hr. See notes, 1-4 below:

Sample	Percent Colloid	
	Dose	
	10^{10} rad	2×10^{10} rad
AEC 8-810 m level (WIPP Site), NM, USA	0.78	2.87
Alt Aussee, Austria	2.54	9.93
Asse 1, FRG	3.24	11.6
Asse 4, FRG	0.66	2.25
Asse 6, FRG	3.95	16.7
Asse 8, FRG	1.43	6.43
Asse 9, FRG	1.09	4.53
Avery Island, LA, USA	1.09	3.44
ERDA-9 (WIPP Site), NM, USA	0.84	2.80
Lyons, KS, USA	1.30	4.74
Retsof, NY, USA	1.45	4.27
Rocanville, SK, Canada (above potash ore)	1.08	3.21
Rocanville, SK, Canada (with potash ore)	0.75	2.54
Rocanville, SK, Canada (recrystallized)	9.73	51.7

- 1) Measurements made at 150°C . At lower temperatures the only effect may be a lengthening of the induction period; it appears to be in the 3-6 month range at room temperature.

- 2) Impurities in the rock salt tend to reduce the colloid formation rate. Except for the Rocanville recrystallized salt, these measurements were made on "normally impure" salt.
 - 3) Strain in the salt increases the colloid formation rate. The salt used for these measurements was carefully selected to be free as possible of strain.
 - 4) The colloid formation rate increases, on a unit dose basis, as the dose rate decreases. These measurements were made at a dose rate of 1.2×10^8 rad per hour, i.e. roughly 10^4 times larger than that expected in repositories.
-

fact, there are many aspects of radiation damage in rock salt which are not understood. Some of these are discussed in the next section.

VIII. RADIATION RELATED PROPERTIES OF NATURAL ROCK SALT YET TO BE INVESTIGATED

While it can be said that many aspects of radiation damage in natural and synthetic rock salt are understood in a qualitative fashion, a surprisingly large number of radiation related properties have not been investigated. A few of these which have practical applications to radioactive waste repository site selection and engineering are listed below.

1) Chlorine gas: Simple material balance requires one atom of chlorine to be formed for each atom of sodium incorporated into a colloidal sodium metal particle. It is not known for certain if this chlorine is retained in parts of the rock salt lattice which do not contain colloid particles. There is evidence to suggest that chlorine is incorporated in the dislocation debris accompanying dislocation climb observed during electron microscope induced radiation damage (16). It is unlikely that all of the chlorine accompanying colloid formation can be accommodated in the colloid particle free portions of the rock salt lattice when the colloid concentrations exceed 0.1 to 10 percent. As mentioned above, chlorine odors are detected when highly irradiated rock salt is cleaved or broken up. Inasmuch as chlorine gas is quite reactive chemically, especially in the presence of any moisture, it is important to determine whether or not chlorine gas is released from the rock salt lattice during irradiation. Also, it is important to determine how chlorine gas evolution depends on such parameters as total dose, dose rate, sample temperature, prior strain, crystallite size, etc. A mass spectrometer type gas analyzer system, containing a temperature controlled irradiation chamber, is under construction at Brookhaven Na-

tional Laboratory. To determine how any gas evolution will depend on dose rate, this chamber can be irradiated with ^{60}Co gamma-rays at a large number of dose rates. The detection of chlorine gas is a non-trivial matter. Consequently, carrier gas can be passed through the analyzer system. Also, measurements can be made to determine what fraction of the chlorine gas evolved is trapped in the irradiation chamber and the tubing connecting the chamber to the gas analyzer system. This apparatus should be in operation during the last quarter of 1981.

2) Mechanical properties of highly irradiated natural rock salt: As far as we can determine, the mechanical properties of highly irradiated rock salt, such as compression and shear strength, creep, hardness, etc. have not been investigated in detail. Measurements should be made on individual crystals and on the multicrystallite samples (rock samples) usually used in "rock-mechanics" studies.

3) Chemical properties of irradiated rock salt: Information on some of the chemical properties of irradiated natural rock salt have been described by Jenks et al. (15) who studied the radiolysis products formed when irradiated salt was dissolved in water. However, very few studies have been carried out on systems which include irradiated salt, water, canister material, waste forms, etc.

4) Charge build-up in irradiated salt: Charge build-up was a serious problem in the thick glass windows incorporated into the original "hot-cells". It is not known if natural rock salt is a sufficiently good insulator to support an appreciable charge build-up. However, this possibility is mentioned here to illustrate radiation related properties of rock salt and other minerals which apparently have not been considered in repository site selection and design.

5) Radiation damage modelling: To extrapolate from the high dose rates, short irradiation times, rapidly applied stresses, etc., associated with laboratory radiation damage studies to the low dose rates, high total doses, low creep rates, etc. expected in an actual repository requires a reasonably complete understanding of the radiation damage formation kinetics in natural rock salt. As discussed elsewhere (1,6) the only applicable theory for radiation damage formation in rock salt, that of Jain and Lidiard, (17) adequately describes some of the data on radiation damage in salt that has been obtained to date. However, some observed radiation damage effects, in both natural and synthetic rock salt, are not included in the theory. For example: the pronounced colloid formations induction period was not considered. Colloid particles are observed at doses and dose rates less than that predicted. In addition, there are other inadequacies requiring a discussion too long to be included here. In other words, the current understanding of radiation damage kinetics, particularly colloid particle formation, in rock salt is not adequate for a reasonably reliable modelling of the radiation damage in rock salt surrounding radioactive waste canisters.

FIGURE CAPTIONS

Figure 1--A black and white version of a color photograph of natural rock salt cored from the Lyons, Kansas, Radioactive Waste Disposal Demonstration project site after the spent fuel element had been removed. The salt farthest from the fuel element received a dose of $10^3 - 10^4$ rad. It does not show any obvious radiation damage and resembles normal unirradiated rock salt in most respects. Salt from the intermediate distances show the blue-black color typical of radiation induced colloid particle formation and is appreciably harder than unirradiated salt. The salt closest to the fuel element received a dose of $5 \times 10^7 - 5 \times 10^8$ rad. It differs appreciably from normal rock salt. It is brittle, is readily fractured or cleaved, is very much harder than normal rock salt and is quite reactive chemically. When dropped into water it readily dissolves with the formation of hydrogen gas bubbles.

Figure 2--The equipment for making optical absorption and other measurements on samples while they are being irradiated with 0.5-3.0 MeV electrons. Both the measurement control and data recording functions are performed by a computer. All sensitive equipment is outside of the irradiation chamber. Measurements above room temperature are made in a temperature controlled chamber containing an exchange gas, fused silica windows to transmit the spectrophotometer beams, and thin Havar windows to transmit the electron beam.

Figure 3--Typical optical absorption and luminescence data obtained with the facility shown in figure 2. Many fewer spectra are shown than are normally recorded. The decrease in luminescence intensity with increasing radiation time

is typical of alkali halides and is not due to radiation induced absorption in the sample. The absorption data is typical of radiation induced F-center and colloid formation in natural and synthetic rock salt. The F-centers increase rapidly to a plateau and remain at a constant level throughout the remainder of the irradiation period. The colloid formation contains a pronounced induction period and follows a classical nucleation and growth curve.

Figure 4--Colloid concentration vs. irradiation time curves recorded at various temperatures for natural rock salt from the WIPP site. The dose rate was 1.2×10^8 rad/hr. The solid line contours show that the colloid formation rate is low or negligible at 100°C , increases with increasing temperature to a maximum in the $150\text{--}175^\circ\text{C}$ range, and at higher temperatures decreases to a negligible level in the $250\text{--}300^\circ\text{C}$ range. The dashed line contours show that the colloid formation induction period is longer than 10^4 seconds at 100°C , decreases to less than 3000 seconds at 150°C , and is longer than 10^4 seconds at $250\text{--}275^\circ\text{C}$. Rock salt samples--particularly strained samples--irradiated at room temperature to doses of $10^7 - 10^8$ rad usually develop colloids after standing in the dark for 3-6 months.

Figure 5--Colloid formation in 14 natural rock salt samples irradiated at 150°C at a dose rate of 1.2×10^8 rad/hr. These curves demonstrate a number of features: Colloid formation varies appreciably from site to site and between different samples from the same site. All of the colloid growth curves are well approximated by Ct^n relations at the high dose end. The doses expected at the surface of high level radioactive waste canisters in 50-400 years will cause the

colloid content in salt at the surface to reach 0.1 to 10 percent at 10^{10} rad and 1 to 50 percent at 2×10^{10} rad.

Figure 6--Colloid growth curves for natural rock salt from the WIPP site recorded after the crystals were strained the indicated amounts prior to irradiation.

Figure 7--Colloid formation in natural rock salt from the WIPP site at three dose rates. These curves demonstrate that, on a unit dose basis, the colloid formation increases as the dose rate decreases. The dose rates used for these measurements are approximately 10^4 times higher than those expected in a repository.

Figure 8--A black and white version of a colored photomicrograph of irradiated natural rock salt. The dark area is blue-black indicating that both F-centers and colloid sodium metal particles are present. The light area is golden-brown indicating that only F-centers are present. At the center of the light area is a line of voids which are empty, partially, or entirely brine filled. Proton microprobe studies on similar crystals, which may or may not contain voids, show that the light area contains approximately 1 percent Ca and S impurity, and additional lower level impurities. Thus colloid formation is suppressed in regions containing high impurity levels.

REFERENCES

- (1) P.W. Levy, J.M. Loman, K.J. Swyler, and R.W. Klaffky, Radiation Damage Studies on Synthetic NaCl Crystals and Natural Rock Salt for Radioactive Waste Disposal Applications, to be published in: Advances in the Science and Technology of the Management of High Level Nuclear Waste, P.L. Hofmann, ed.
- (2) J.M. Loman, P.W. Levy, and K.T. Swyler, Radiation Induced Sodium Metal Colloid Formation in Natural Rock Salt From Different Geological Localities, to be published in Proc. 4th Materials Res. Soc. Symp. on the Scientific Basis of Nuclear Waste Mgmt., Boston, MA, 1981.
- (3) R.L. Bradshaw and W.C. McLain, Eds., Project Salt Vault: A Demonstration of the Disposal of High Activity Solidified Waste in Underground Salt Mines, Oak Ridge National Lab. Report ORNL 4555 (1971).
- (4) R.W. Klaffky, K.J. Swyler, and P.W. Levy, Radiation Damage Studies on Synthetic NaCl Crystals and Natural Rock Salt for Waste Disposal Applications, II. Ceramics in Nuclear Waste Management, DOE Conference 790420, T.D. Chikalla and J.E. Mendel, editors (U.S. Dept. of Energy, Washington, 1979) pp. 310-314.
- (5) R.W. Klaffky, K.J. Swyler, and P.W. Levy, Properties of Radiation Induced Colloid Particles in Synthetic NaCl Crystals and Natural Rock Salt. (In preparation).
- (6) P.W. Levy, K.J. Swyler, and R.W. Klaffky, Radiation Induced Color Center and Colloid Formation in Synthetic NaCl and Natural Rock Salt, Third Europhysics Topical Conf., Lattice Defects in Ionic Crystals, J. de Physique 41, Supplement-Colloque C6, pp. 344-347 (1980).

- (7) K.J. Swyler, R.W. Klaffky, and P.W. Levy, Radiation Damage Studies on Synthetic NaCl Crystals and Natural Rock Salt for Waste Disposal Applications, Scientific Basis of Nuclear Waste Management, Vol. 1, G.J. McCarthy, editor (Plenum, New York, 1979), p. 349.
- (8) K.J. Swyler, R.W. Klaffky, and P.W. Levy, Recent Studies on Radiation Induced Color Centers and Colloid Formation in Synthetic NaCl and Natural Rock Salt for Waste Disposal Applications, Int. Sym. on the Sci. Basis for Nuclear Waste Management, Vol. II, C.J.M. Northrup, editor (Plenum, New York, 1980) p. 553.
- (9) G.E. Elgort and P.W. Levy, Thermally Induced Colloid Formation in Previously Irradiated Natural and Synthetic Rock Salt. (In preparation).
- (10) P.W. Levy, P.L. Mattern, K. Lengweiler, and M. Goldberg, The Effect of Strain Applied during Irradiation on the Gamma-ray Induced F-center Coloring of KCl at Room Temperature. Solid State Communications 9, 1907 (1971).
- (11) L.J. Teutonico, The Role of $\langle 100 \rangle$ Edge Dislocations in Nucleating Radiation-Induced Colloidal Particles in Sodium Chloride (in preparation)
- (12) L.J. Teutonics, The Role of $\langle 111 \rangle$ Edge Dislocations in Nucleating Radiation-Induced Colloidal Particles in Sodium Chloride (in preparation).
- (13) J.H. Crawford, Jr. and L.M. Slifkin, editors, Point Defects in Solids, Vols 1 and 2 (Plenum Press, New York, 1972).
- (14) C.P. Swann, J.M. Loman and P.W. Levy, Proton Microprobe Studies on Color-Center and Colloid Particle Formation in Irradiated Rock Salt (in preparation).

- (15) G.H. Jenks, E. Sonder, C.D. Bopp, J.R. Walton, S. Lindenbaum, Reaction Products and Stored Energy Released from Irradiated Sodium Chloride by Dissolution and by Heating, J. Phys. Chem. 78, p. 871 (1975).
- (16) L.W. Hobbs, Transmission Electron Microscopy of Extended Defects in Alkali Halide Crystals, Surface and Defect Properties of Solids 4, (Chem. Soc. Specialist Period. Reports, London, 1975) p. 152.
- (17) U. Jain and A.B. Lidiard, The Growth of Colloidal Centres in Irradiated Alkali Halides, Phil. Mag. 35, 245 (1977).

3

5

30

50

60

70

80

140

200

**APPROXIMATE DISTANCE
FROM FUEL ELEMENT, cm.**

FIGURE 1

FIGURE 2

OPTICAL ABSORPTION AND LUMINESCENCE
SPECTRA OF NATURAL ROCK SALT
RECORDED DURING ELECTRON IRRADIATION

FIGURE 3

NATURAL ROCK SALT - DRILL HOLE AEC-8, 810 m LEVEL
RADIATION INDUCED COLLOID FORMATION
AT VARIOUS TEMPERATURES
DOSE RATE: 1.2×10^8 rad/hr

FIGURE 4

FIGURE 5

FIGURE 6

FIGURE 7

FIGURE 8