LA-8083

DR. 759

228
2/28/80

**Microstructural Damage Produced by
Helium in Aged $^{238}\text{PuO}_2$ Fuels**

MASTER

University of California

LOS ALAMOS SCIENTIFIC LABORATORY

Post Office Box 1663 Los Alamos, New Mexico 87545

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MICROSTRUCTURAL DAMAGE PRODUCED BY HELIUM IN AGED $^{238}\text{PuO}_2$ FUELS

by

C. C. Land

ABSTRACT

Microstructural damage is produced in aged $^{238}\text{PuO}_2$ fuels used to power radioisotopic heat sources by the generation and release of the helium arising from alpha decay of the fuel. We obtained information about the nature and extent of this damage from metallographic examination of fuel pellets ranging in density from 87-94% with a grain size range of 6-30 μm that either were stored at ambient temperature for 18 months and then heated at 900, 1150, or 1350°C or were stored at 900, 1150, or 1350°C for 27 months.

Microstructural damage was not observed in the fuel pellets stored at ambient temperature and then heated at 900°C, but grain boundary bubble damage was observed in the pellets stored at ambient temperature and then heated at either 1150 or 1350°C. More extensive damage occurred in those pellets heated at 1350°C.

Four of the higher density pellets (92 and 94% dense) stored at 900°C shattered during storage and the rest appeared to be highly strained. The pellets stored at 1150°C were damaged only slightly but were somewhat strained and appeared to have released their helium inventory only partially. All pellets stored at 1350°C showed swelling and extensive void agglomeration.

These data suggest that the best fuel operating temperature, as far as helium damage is concerned, would be $\sim 1200^\circ\text{C}$ because below this temperature the fuel becomes highly strained and above this temperature the fuel swells and becomes somewhat friable. Both these situations could adversely affect the impact behavior of the fuel from the standpoint of strength and fines generation.

INTRODUCTION

Helium is produced at the rate of 0.53 $\text{cm}^3/(\text{g}\cdot\text{yr})$ in 80% enriched $^{238}\text{PuO}_2$ fuels used to power radioisotopic heat sources as a result of alpha decay of ^{238}Pu . This study examines the microstructural damage caused by the release of helium and correlates these data with the fuel behavior in systems

such as the Kilowatt Isotope Power System (KIPS), the General-Purpose Heat Source (GPHS), and the Multi-hundred Watt (MHW). One of the primary objectives was to determine the temperature at which microstructural damage first occurs in aged fuels so that we could recommend a thermal treatment that removes the helium inventory while causing a minimal amount of microstructural damage.

EXPERIMENTAL PROCEDURE

We performed two experiments during this study. The first simulated storage of the fuel for some period before it is heated to the operating temperature of a particular system. Thirty-six $^{239}\text{PuO}_2$ pellets of different grain sizes and densities (see Table I) were stored for ~18 months at ambient temperature and then heated to 900, 1150, or 1350°C, temperatures that were chosen to approximate the expected operating temperatures of KIPS, GPHS, and MHW, respectively.

The second experiment characterized the damage caused by helium release during normal fuel operation. Two pellets from each of the pellet lots shown in Table I were stored for 27 months at 900, 1150, and 1350°C. One of the pellets from each pellet lot from each storage temperature was examined upon removal from the furnace; the other was heated to 1625°C after removal. Data from the first of each pair of pellets yield information about the behavior of fuel pellets under operating conditions, whereas data from the second yield information about the behavior of fuel pellets that have been at operating temperature for 27 months and then have reentered the earth's atmosphere.

The seventy-two 7.6-mm-diam by 7.6-mm-long, ~3-g $^{239}\text{PuO}_2$ pellets used in this study were prepared from 125- μm presintered oxalate-base $^{239}\text{PuO}_2$ shards by hot pressing in a single action press with graphite dies and then sintering in an $\text{Ar-H}_2\text{O}$ mixture. By varying the sintering times and temperatures for both granules and pellets (see Table II), we had intended to achieve a range of densities and grain sizes representative of fuel forms that might be used in operating systems. As can be seen from Table I, which lists the intended and measured densities and grain sizes, the actual ranges were not as great as we had planned. All pellets used in this study contained sintering cracks.

For the elevated-temperature storage tests, each pellet was encapsulated in an iridium-lined molybdenum primary capsule. Secondary and tertiary capsules were of nickel and Hastelloy for tests at 900°C and of Ta-10W for tests at 1150 and 1350°C. All closures were TIG welds in an argon-helium atmosphere. Pellets were heat treated in tube furnaces in air for the tests at 900°C and in Brew furnaces in vacuum for the tests at 1150 and 1350°C.

The nature and extent of the helium damage were determined by microscopic examination of both

TABLE I
FUEL MATRIX FOR STORAGE TESTS
AT AMBIENT^a AND ELEVATED^b
TEMPERATURES

Pellet Lot	Pellet No.	No. of Pellets	Density (%)		Grain Size (μm)	
			Intended	Measured	Intended	Measured
HPZ-118	15735	12	90	94	55	30
HPZ-122	15777	12	90	92	16	11
HPZ-123	15791	12	90	92	26	16
HPZ-127	15826	12	90	94	10	6
HPZ-130	15839	12	80	87	6	6
HPZ-131	15854	12	80	91	23	14

^aOne pellet from each lot was held for 24 h at 900°C, one at 1150°C, and one at 1350°C after storage at ambient temperature for ~18 months.

^bTwo pellets from each lot were held for ~27 months at 900°C, two at 1150°C, and two at 1350°C. One each of these was then heated to 1625°C in ~5 min after equilibration at test temperature.

TABLE II

PELLET FABRICATION PARAMETERS

Pellet Lot	Granule Seasoning ^a	Pressing	Pellet Sintering
HPZ-118	3 h at 1000°C	5000 psi, ^b 20 min, 1530°C	12 h at 1600°C
HPZ-122	3 h at 1150°C	5000 psi, ^b 20 min, 1530°C	6 h at 1350°C
HPZ-123	3 h at 1000°C	5000 psi, ^b 20 min, 1530°C	6 h at 1600°C
HPZ-127	3 h at 1000°C	5000 psi, ^b 30 min, 1490°C	18 h at 1000°C
HPZ-130	3 h at 1300°C	5000 psi, ^b 30 min, 1490°C	12 h at 1000°C
HPZ-131	6 h at 1300°C	5000 psi, ^b 20 min, 1530°C	6 h at 1527°C

^aAll feed consisted of 125- μ m granules. All granule seasoning and pellet sintering in Ar-H₂-¹⁸O.

^b5000 psi = 34.47 MPa.

polished and polished and etched pellet sections. Longitudinal pellet sections were prepared by pressure potting an entire pellet in epoxy, sectioning the mounted pellet with a slow-speed diamond saw, grinding with 280-4/0 grit SiC paper, and polishing on a Syntron vibratory polisher with Linde A (0.3- μ m Al₂O₃) on a nylon cloth. Water was used as a lubricant for all cutting, grinding, and polishing operations. The polished sections were chemically etched in a mixture of 27 cc HBr, 3 cc HCl, and 4-7 drops HF for times ranging from 2-50 minutes depending upon the grain boundary reactivity. The relative void volumes were measured from photographs of polished sections with the Imanco Quantimet Image Analyzer. Fabrication cracks were excluded in the void volume measurements.

RESULTS AND DISCUSSION

Ambient Temperature Storage Tests

One pellet from each of the six different pellet lots was heated to and held for 24 h at 900°C after the initial 18-months' storage at ambient temperature. The second and third pellets from each pellet lot were heated to and held for 24 h at 1150°C and

1350°C, respectively. These pellets and one from each lot in the as-stored condition were examined metallographically. The results are summarized in Table III.

No helium damage of the grain boundary bubble type was observed in the as-stored samples (Fig. 1a). No visible damage was detected in the pellets heat treated at 900°C (Fig. 1b), but the fact that these pellets etched more rapidly than those stored at ambient temperature (5-10 min compared to 20-25 min) suggests the presence of grain boundary strain energy.

Heat treatment for 24 h at 1150°C produced discernible damage. Fine helium bubbles were detected in the grain boundaries of some of the high-density areas of the test pellets, as shown in Fig. 1c. This damage, barely detectable in some pellets at 1000X, was the most severe in the 94% dense, 30- μ m grain size pellet lot. We believe, therefore, that 1150°C is the temperature at which microstructural damage first occurs in fractured 7.6-mm-diam by 7.6-mm-long ²³⁸PuO₂ pellets aged at ambient temperature for 18 months with a density range of 87-94% and a grain-size range of 6-30 μ m.

Heat treatment for 24 h at 1350°C produced more extensive helium bubble formation at the grain boundaries (Fig. 1d) for all pellet lots. The extent of

Fig. 1.

Effects of storage at ambient temperature for 18 months and subsequent heating in four samples from lot HPZ-118: (a) 15735-G, as-stored; (b) 15735-I, stored and heated to 900°C; (c) 15735-J, stored and heated to 1150°C; and (d) 15735-H, stored and heated to 1350°C. Etched section, 500X.

damage was greater, however, in the high-density, large-grain size lots. Small-grained material was more likely to contain grain boundary separations, whereas large-grained material was more likely to contain discrete grain boundary helium bubbles.

One objective of this study was to determine the temperature at which microstructural damage first occurs in aged fuels in order to recommend a thermal treatment that removes the helium inventory while causing a minimal amount of microstructural damage. Many factors can influence not only the temperature at which damage first occurs but also the type and extent of the damage. Examples include the helium inventory; the helium transport mechanism; the pellet density; the size and distribution of the porosity and the extent of its connection to a free surface; the grain size; the duration and temperature of the treatment (prior as well as current); the sinterability, which is influenced by the duration and temperature of the original sintering; the size and the shape of the sample (distance to a free surface); the presence of impurities; and, in our case, the distance to the nearest crack, which effectively forms a new free surface. It is therefore quite difficult to extrapolate these data to other fuel forms or to compare the results from these tests to those from other investigations.¹⁻⁵ McDonell and coworkers²⁻⁴ at Savannah River Laboratory, investigating 80-90% dense fuel forms aged for 3-30 months, have suggested a critical temperature of 1200°C, whereas Mueller and coworkers⁶⁻⁸ at Los Alamos Scientific Laboratory have observed grain boundary helium bubbles at temperatures as low as 1000°C in 97-98% dense ²³⁸PuO₂ fuel forms and as low as 800°C in PMC (molybdenum-coated ²³⁸PuO₂ particles) fuel forms and SSC (molybdenum-coated ²³⁸PuO₂-8 wt% ThO₂ particles) fuel forms. On the basis of his investigations, McDonell has suggested a "fix" for removal of the helium in stored fuels of heating every 5 months to 1440°C for an appropriate length of time. He suggests that heating at temperatures below the damage threshold for a period of time before heating to 1440°C does not reduce the microstructural damage appreciably compared to heating directly to 1440°C. In contrast to McDonell's results, the current work indicates that a more general "fix" for removing helium in aged fuels of differing fuel forms, particularly for fuels stored longer than 6 months, would be to heat rapidly to 1000°C, then heat at 30°C/h to 1450°C, and finally anneal at 1450°C. Such a treatment

reduces, at temperatures below the damage threshold, two factors to which microstructural damage appears to be sensitive—the total amount of helium and the rate at which helium is dumped into the grain boundaries. Also, when the damage is minimal, this proposed "fix" provides a maximum time for the annealing out of damage, which occurs at temperatures as low as 1200°C for some fuel forms.⁶ The final anneal at 1450°C allows the damage to be annealed out at a temperature where void mobility is reasonably high. The results of Mueller and coworkers indicate that the helium inventory would be near zero after the 1450°C anneal.

High-Temperature Storage Tests

The results from the 900, 1150, and 1350°C storage tests are tabulated in Table III and are shown in Figs. 2-5. Except for the four pellets from lots HPZ-118 and HPZ-123, damage resulting from storage at 900°C was limited to the formation of a few microcracks (Fig. 2), but the pellets were judged to be highly strained because they could be etched so readily. Mueller and coworkers, examining (by transmission electron microscopy) 97-98% dense fuel forms aged for 5-20 months, found defects quite numerous at 1000°C, diminishing at 1200°C, and almost gone at 1400°C. Ramping the pellets stored at 900°C to 1625°C (total heating time of ~10 min) led to extensive helium bubble formation and to a slight (~2 vol%) fuel reduction (Fig. 3). The extensive helium bubble formation indicates that a large fraction of the helium generated during storage was removed during ramping; that is, little or no helium was released during storage at 900°C. The four pellets from lots HPZ-118 and HPZ-123 shattered during the 900°C storage. The as-recovered material from one of the shattered HPZ-123 pellets (15791-A), shown in Fig. 6, can be compared to a relatively undamaged HPZ-127 pellet, also stored at 900°C, shown in Fig. 7. The pellets that shattered were from the higher density, larger grain-size lots. Both the as-stored and the as-ramped pellets from HPZ-131 show an increase in void volume, possibly because of pellet variation or sampling error resulting from choosing nonrepresentative areas of the pellet for analysis.

The pellets stored at 1150°C were damaged minimally by the release of helium (Fig. 4) except for the pellet from HPZ-123 (92% dense, 16-μm grain

Fig. 2.
Sample 15735-B-1 (lot HPZ-118) after 27 months at 900°C. Etched section, 500X.

Fig. 3.
Sample 15735-B-2 (lot HPZ-118) after 27 months at 900°C followed by heating to 1625°C. Etched section, 250X.

Fig. 4.
Sample 15735-C (lot HPZ-118) after 27 months at 1150°C. Etched section, 500X.

Fig. 5.
Sample 15735-F (lot HPZ-118) after 27 months at 1350°C. Etched section, 500X.

Fig. 6.
Sample 15791-A (lot HPZ-123) after 27 months
at 900°C. 2X.

Fig. 7.
Sample 15826-A (lot HPZ-127) after 27 months
at 900°C. 2X.

Fig. 8.
Sample 15791-E (lot HPZ-123) after 27 months
at 1150°C. Etched section, 500X.

Fig. 9.
Sample 15735-D (lot HPZ-118) after 27 months
at 1150°C followed by ramping to 1625°C.
Etched section, 500X.

size), which was damaged fairly extensively (Fig. 8). There was some helium bubble formation and some enhancement of the void volume at grain boundary triple points. Etching indicated some grain boundary strain. Ramping the pellets stored at 1150°C to 1625°C caused less extensive grain boundary helium bubble formation (Fig. 9) than in the 900°C samples; probably, some helium was released during storage at 1150°C.

The results from the 1350°C storage tests suggest that helium generated and released at 1350°C does not form grain boundary helium bubbles; instead it diffuses along the grain boundaries to the grain boundary triple points, where it is pinned and causes large triple-point voids (Fig. 5) that increased the void volume in these samples by about 20%. Figures 10 and 11 illustrate graphically the results of this void volume increase: the relatively tight fabrication cracks were essentially unchanged by ambient temperature storage, whereas the release of stored helium during aging at 1350°C not only increased the grain boundary triple-point porosity, but also widened the fabrication cracks. This large void-volume increase must be considered in the design of future fuel forms possibly by limiting the fuel density to 85-86% to promote the presence of intercon-

nected porosity. The absence of grain boundary helium bubble formation in the pellets stored at 1350°C appears to contradict the low-temperature storage tests, where pellets stored for 18 months at ambient temperature and then heated to 1350°C contained a continuous network of grain boundary helium bubbles. One explanation may be different helium release rates for the two cases. In the higher temperature aging there is no storage of helium in the lattice—it is released to the grain boundaries at the generation rate. At this release rate the helium diffuses along the grain boundaries without encountering a concentration sufficient for bubble nucleation until it reaches grain boundary triple points or other internal discontinuities. Mueller and coworkers⁹ have noted that increased heating times (5-300 min) at 1400°C of 97-98% dense fuels aged at ambient temperature for 5-20 months can vary the microstructure from fine grain boundary helium bubbles to coalescence at grain boundary triple points, a fact that suggests mobility not only of helium but also of voids at 1400°C. In the case of aging at ambient temperature followed by heating, the much higher effective release rate swamps the capacity of the grain boundaries and causes formation of numerous bubble nuclei, which grow to stable

Fig. 10.

Sample 15735-G (lot HPZ-118) after 18 months at ambient temperature. Polished section, 13X.

Fig. 11.

Sample 15735-F (HPZ-118) after 27 months at 1350°C. Polished section, 10X.

bubbles when additional helium arrives. This rate-dependent mechanism might also explain why helium bubbles are formed more readily in large-grained fuels than in small-grained fuels because the smaller the grain size, the larger the grain boundary volume and hence the lower the helium concentration at the grain boundaries.

CONCLUSIONS

The critical temperature for grain boundary helium bubble formation in 87-94% dense $^{238}\text{PuO}_2$ pellets (7.6 mm diam by 7.6 mm long) stored for 18 months was 1150°C. Both larger grain size and higher density tended to enhance grain boundary bubble formation.

The higher density pellets (92-94% dense) shattered during storage at 900°C. The rest of the pellets stored at 900°C were highly strained by the helium

accumulation. The pellets did not appear to release the helium generated during storage.

The pellets stored at 1150°C showed only minor amounts of microstructural damage but were somewhat strained. Ramping the pellets to 1625°C caused bubble damage; probably, not all of the helium generated during storage was released at the storage temperature.

All of the fuel pellets stored at 1350°C showed swelling and void agglomeration. The helium appeared to have been completely released and there was no evidence of strain.

These data suggest that an ideal fuel operating temperature, as far as helium damage is concerned, might be 1200°C. Below this temperature not all of the helium is released, leading to fuel strains that could adversely affect the fuel impact behavior from the standpoint of strength, ductility, and fines generation. Above this temperature void mobility is high enough to cause large void formation and swelling that could adversely affect the fuel strength and fines generation during impact.

TABLE III
MICROSTRUCTURAL DAMAGE IN $^{238}\text{PuO}_2$ PELLETS

Pellet Lot	Pellet Number	Heat Treatment	Grain Size (μm)	Pore Volume (%)	Observations
HPZ-118	15735-G	Stored at ambient for 586 day	30	7.7	No helium damage
HPZ-118	15735-I	Stored at ambient for 586 day + 24-h hold at 900°C	30	5.4	No helium damage
HPZ-118	15735-J	Stored at ambient for 594 day + 24-h hold at 1150°C	30	6.1	Barely discernible helium bubbles
HPZ-118	15735-H	Stored at ambient for 591 day + 24-h hold at 1350°C	25	6.4	Extensive helium bubble formation
HPZ-118	15735-B-1	Held at 900°C for 884 day	30	4.8	Pellet shattered during 900°C storage; no helium bubble formation
HPZ-118	15735-B-2	Held at 900°C for 884 day + 1625°C ramp	30	6.0	Helium bubble formation; <2% fuel reduction during ramping
HPZ-118	15735-C	Held at 1150°C for 878 day	30	7.8	Slight helium bubble formation; pellet highly strained

TABLE III (cont)

Pellet Lot	Pellet Number	Heat Treatment	Grain Size (μm)	Pore Volume (%)	Observations
HPZ-118	15735-D	Held at 1150°C for 878 day + 1625°C ramp	25	12.4	Helium bubble formation; pellet strained
HPZ-118	15735-F	Held at 1350°C for 883 day	30	20.2	Extensive helium damage, mostly in the form of coarse helium bubbles agglomerated at triple points
HPZ-118	15735-E	Held at 1350°C for 883 day 1625°C ramp	30	17.9	Very slight helium bubble formation; <2% fuel reduction
HPZ-122	15777-G	Stored at ambient for 566 day	10	6.6	No helium damage
HPZ-122	15777-I	Stored at ambient for 580 day + 24-h hold at 900°C	10	8.9	No helium damage
HPZ-122	15777-J	Stored at ambient for 581 day + 24-h hold at 1150°C	12	8.4	Helium bubbles barely discernible
HPZ-122	15777-K	Stored at ambient for 582 day + 24-h hold at 1350°C	13	10.2	Extensive grain boundary helium bubble damage
HPZ-122	15777-A	Held at 900°C for 884 day	12	8.3	No helium damage
HPZ-122	15777-B	Held at 900°C for 884 day + 1625°C ramp	10	7.6	Extensive helium bubble formation
HPZ-122	15777-C	Held at 1150°C for 878 day	10	8.9	No helium bubble formation
HPZ-122	15777-D	Held at 1150°C for 878 day + 1625°C ramp	10	13.1	Slight helium bubble formation; spallation indicative of strain
HPZ-122	15777-F	Held at 1350°C for 883 day	24	18.4	Extensive void agglomeration; <2% fuel reduction
HPZ-122	15777-E	Held at 1350°C for 883 day + 1625°C ramp	36	19.9	Slight helium bubble formation; extensive grain growth
HPZ-123	15791-G	Stored at ambient for 559 day	16	8.7	No helium damage
HPZ-123	15791-H	Stored at ambient for 581 day + 24-h hold at 900°C	16	7.6	No helium bubble formation; pellet strained
HPZ-123	15791-I	Stored at ambient for 586 day + 24-h hold at 1150°C	20	10.5	Fine helium bubbles
HPZ-123	15791-J	Stored at ambient for 587 day + 24-h hold at 1350°C	16	8.0	Extensive grain boundary helium bubble formation
HPZ-123	15791-B-1	Held at 900°C for 876 day	16	5.5	Pellet shattered during 900°C storage; no helium bubble formation
HPZ-123	15791-B-2	Held at 900°C for 876 day + 1625°C ramp	24	10.7	Extensive helium bubble formation; <2% fuel reduction
HPZ-123	15791-E	Held at 1150°C for 878 day	15	13.5	Extensive helium bubble formation and agglomeration at grain boundary triple points

TABLE III (cont)

Pellet Lot	Pellet Number	Heat Treatment	Grain Size (μm)	Pore Volume (%)	Observations
HPZ-123	15791-D	Held at 1150°C for 878 day + 1625°C ramp	16	16.8	Void enhancement
HPZ-123	15791-F	Held at 1350°C for 878 day	20	19.4	Extensive helium bubble formation and agglomeration at grain boundary triple points; no fine helium bubbles
HPZ-123	15791-C	Held at 1350°C for 878 day + 1625°C ramp	16	13.6	Slight helium bubble formation; <1% fuel reduction
HPZ-127	15826-F	Stored at ambient for 539 day	6	4.4	No helium damage
HPZ-127	15826-G	Stored at ambient for 572 day + 24-h hold at 900°C	6	5.6	No helium bubbles; pellet highly strained
HPZ-127	15826-H	Stored at ambient for 573 day + 24-h hold at 1150°C	6	6.0	Extremely fine helium bubbles in grain boundaries; a few intergranular microcracks
HPZ-127	15826-I	Stored at ambient for 574 day + 24-h hold at 1350°C	6	9.1	Extensive helium bubble microcracks
HPZ-127	15826-A	Held at 900°C for 847 day	6	5.0	Some microcracks
HPZ-127	15826-B	Held at 900°C for 847 day + 1625°C ramp	12	6.6	Helium bubble formation mostly in the form of intergranular microcracks
HPZ-127	15826-C	Held at 1150°C for 847 day	6	5.0	Helium damage in the form of intergranular microcracks
HPZ-127	15826-D	Held at 1150°C for 847 day + 1625°C ramp	8	7.7	Extensive grain boundary helium bubble formation
HPZ-127	15826-E	Held at 1350°C for 847 day + 1625°C ramp	16	22.8	Extensive void agglomeration; some grain boundary helium bubble formation
HPZ-130	15839-A	Held at 900°C for 835 day	6	14.3	Helium damage in the form of intergranular microcracks; pellet highly strained
HPZ-130	15839-B	Held at 900°C for 835 day + 1625°C ramp	16	12.0	Helium damage as discrete grain boundary helium bubbles and intergranular microcracks
HPZ-130	15839-C	Held at 1150°C for 834 day	10	16.8	No helium damage; pellet highly strained
HPZ-130	15839-D	Held at 1150°C for 834 day + 1625°C ramp	10	13.7	No helium damage
HPZ-130	15839-F	Held at 1350°C for 834 day	20	21.4	Porosity agglomeration
HPZ-130	15839-E	Held at 1350°C for 834 day + 1625°C ramp	18	17.3	No helium bubble formation; <2% fuel reduction

TABLE III (cont)

Pellet Lot	Pellet Number	Heat Treatment	Grain Size (μm)	Pore Volume (%)	Observations
HPZ-131	15854-G	Stored at ambient for 498 day	12	9.0	No helium damage
HPZ-131	15854-H	Stored at ambient for 517 day	14	9.3	No helium damage
		+ 24-h hold at 900°C			
HPZ-131	15854-I	Stored at ambient for 578 day	14	8.4	Extremely fine grain
		+ 24-h hold at 1150°C			boundary helium bubbles
HPZ-131	15854-J	Stored at ambient for 519 day	16	10.1	Extensive helium bubble
		+ 24-h hold at 1350°C			formation
HPZ-131	15854-A	Held at 900°C for 813 day	16	16.9	Some internal fracturing
HPZ-131	15854-B	Held at 900°C for 813 day	13	12.8	Helium bubble formation
		+ 1625°C ramp			in densest areas
HPZ-131	15854-C	Held at 1150°C for 817 day	14	16.6	Minimal helium damage
HPZ-131	15854-D	Held at 1150°C for 817 day	20	16.7	No helium damage
		+ 1625°C ramp			
HPZ-131	15854-F	Held at 1350°C for 817 day	18	20.5	Porosity agglomeration
HPZ-131	15854-E	Held at 1350°C for 817 day	14	15.7	No ramping effect
		+ 1625°C ramp			

ACKNOWLEDGMENTS

I wish to express my appreciation to B. A. Mueller who initiated the test plan and partially completed the tests, to Dick Kent and coworkers at LASL Group CMB-11 who processed the pellets, to D. Pavone who stored the high-temperature test pellets, to B. McLaughlin who heat treated the ambient temperature test pellets, and to S. E. Bronisz for his helpful discussions.

REFERENCES

1. P. Angelini, R. E. McHenry, J. L. Scott, W. S. Ernst, Jr., and J. W. Prados, "Helium Release from $^{238}\text{PuO}_2$ Microsphere," Oak Ridge National Laboratory report ORNL-4507 (March 1970).
2. " ^{238}Pu Fuel Form Processes," Savannah River Laboratory Monthly Reports (July 1976-January 1979).
3. W. R. McDonell and D. T. Rankin, "Microstructural Damage Produced by Helium Release from $^{238}\text{PuO}_2$ Pellets," Savannah River Laboratory report DP-MS-76-49 (1976).
4. W. R. McDonell, "Control of Microstructural Damage Produced by Helium in $^{238}\text{PuO}_2$ Pellets," Savannah River Laboratory report DP-MS-78-8X (1978).
5. R. N. R. Mulford and B. A. Mueller, "Measurements of Helium Release from Materials Containing $^{238}\text{PuO}_2$," Los Alamos Scientific Laboratory report LA-5215 (July 1973).
6. B. A. Mueller, D. D. Rohr, and R. N. R. Mulford, "Helium Release and Microstructural Changes in $^{238}\text{PuO}_2$," Los Alamos Scientific Laboratory report LA-5524 (April 1974).
7. B. A. Mueller, "Second Interim Report on Helium Release Behavior of Multi-hundred Watt Fuels," Los Alamos Scientific Laboratory, unpublished data, 1973.
8. B. A. Mueller, "Microstructural Damage in Stored MHW Fuel," Los Alamos Scientific Laboratory, unpublished data, 1975.