This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

E&TR

MASTER

Energy and Technology Review
Lawrence Livermore National Laboratory
March 1986

UCI --52000-86-3

DE86 012075

Preface	1
Dynamic High-Pressure Research with the Two-Stage Light-Gas Gun	2
Measuring Equations of State	8
Experiments to explore how the density of various materials changes in response to high shock pressures are yielding results of great interest in a wide variety of fields, from weapon-design calculations to the structure of the outer planets.	
Gas-Gun Experiments: Advanced Diagnostic Techniques	19
We have developed specialized diagnostic techniques that probe the molecular, electrical, and optical properties of matter at extremes of pressure and temperature.	
Novel Materials	28
A growing application of shock-compression techniques is the synthesis and study of novel materials.	
Studies of High Explosives	35
Supracompression of High-Explosive Detonation Products	36
Using the two-stage light-gas gun, we are investigating how supracompression by a planar shock wave affects the physics and chemistry of an explosive's detonation products.	
Modeling Explosive Behavior	41
The test of how completely we understand the physics and chemistry of explosive detonation is the extent to which our nonempirical calculations can reproduce the experimental data and predict the results of experiments that have not yet been done.	
Abstracts	48

UCRL-52000-86-3
Distribution Category UC-2
March 1986

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *EB*

About the Cover

The cover shows a cutaway view of a cryogenic fluid target at the moment of impact with a projectile fired by LLNL's two-stage light-gas gun. The projectile has just made contact with the aluminum base plate of the target. The hollow annular chambers around the periphery of the target assembly hold the liquid coolant. The central area just to the left of the impact surface holds the fluid sample and an array of shock-wave detector pins. This issue of *Energy and Technology Review* is devoted to our research with the two-stage light-gas gun, a facility that is unique both for the extreme conditions of pressure, density, and temperature it can create and for the range of experiments it makes possible.

Scientific Editors

Hriar S. Cabayan
Neil C. Holmes

General Editors

Wallace Clements
Richard B. Crawford
Lauren de Vore
Derek P. Hendry
Eleanor M. O'Neal

Graphics Designers

Lynn M. Costa
Paul M. Harding
Raymond Marazzi
John Schuster
Kimberly Smith

Compositor

Louisa Cardoza

Art Credit

Toney Sanchez (cover and p. 5)

Preface

This issue of *Energy and Technology Review* provides an overview of the research programs at our two-stage light-gas gun facility. Compared to other gas guns in this country, our facility is unique for the extreme conditions of pressure, density, and temperature it can create and for the range of experiments it makes possible—a range that has increased greatly in recent years and has attracted a growing number of users throughout the Laboratory and from various universities.

In this issue, we describe representative gas-gun experiments and discuss the impact of this research on other LLNL programs and on high-pressure physics in general. For example, work on the properties of nitrogen and hydrocarbons is cited throughout this issue, and the experimental, programmatic, and scientific implications of our results are highlighted.

The performance and interpretation of experiments at the two-stage gas gun are multidisciplinary tasks, involving the work of many individuals. Much of our success is

a result of the close collaboration between the experimenters and the theoretical physicists. The experiments themselves are complex and require an able technical staff to operate the gun safely and to fabricate the intricate and precise target assemblies.

Our gas-gun experiments have three main goals. We strive to provide the Laboratory's various programs with the best and most reliable data on the properties of materials at high shock pressures; these data can then be used in our weapon-design and simulation computer codes. At the same time, we strive to understand, at a fundamental level, the physics involved in the response of materials to extreme conditions of pressure, density, and temperature. Finally, we apply the results of our work to problems of more general scientific interest. For example, our work on the simple molecules produced in high-explosive detonations (water, ammonia, nitrogen, carbon dioxide and monoxide, etc.), carried out for the weapons program, is directly applicable to physics studies of the interiors of the giant planets (Jupiter, Saturn, Uranus, and Neptune). □

Dynamic High-Pressure Research with the Two-Stage Light-Gas Gun

For further information contact
Neil C. Holmes (415) 422-7213 or
William J. Nellis (415) 422-7200.

Nuclear and nonnuclear explosives subject matter of all kinds (metals, fluids, plastics, rocks, etc.) to extreme conditions of pressure (up to millions of atmospheres), density (several times the density of the solid state), and temperature (thousands to millions of degrees). The conditions are dynamic, being achieved and maintained for a millionth of a second or less. For many applications, we need to be able to predict how materials will respond at extreme conditions. Thus, we must have accurate physical descriptions (models) of the response of materials to extreme conditions. In some regions of density and temperature, it is possible to perform experiments to measure relevant properties. By using these data to validate theories, reliable physical models can be generated for materials over a wide range of thermodynamic variables. By implementing these physical models into computational data bases, reliable computer design calculations can be performed.

With the two-stage light-gas gun (see the box on p. 4), which we use to fire hypervelocity projectiles into highly instrumented targets, we can subject matter to high dynamic

pressures and temperatures in well-controlled and reproducible shock-wave experiments (see the box on p. 6) and can measure the responses with great accuracy. Although these experiments access only a portion of the wide range of temperatures and pressures of interest, the data thus obtained provide stringent tests of our theoretical models and improve our confidence in the design calculations.

For example, consider the problem of the response of a metallic part located next to a detonating high explosive. To be able to predict how the entire device behaves, we must first know the detonation properties of the explosive itself. When the explosive detonates, it produces a hot, dense mixture of reaction products at high pressure. To predict the behavior of this mixture, we must know the physics of each component over a wide range of pressure, density, and temperature, and we must know the way the components interact with each other in a mixture. Since the high pressure of the detonation products generates a shock wave in the adjacent metal part, the metal's response to the shock wave must also be known precisely. Thus, we must determine the properties of many

materials, both solids and fluids, over a wide range of dynamic conditions at high pressure, density, and temperature in less than a millionth of a second.

The relationship between pressure, density, and internal energy is called the equation of state (EOS). Experiments to determine the EOSs of various materials have formed the basis of our gas-gun program, and experiments on both solids (like the metal part above) and fluids (the detonation products) continue to be an important part of our research (see the article beginning on p. 8).

Because of their fundamental importance to the weapons program, the properties of high explosives are continually being studied in gas-gun experiments (see the article on p. 36). When explosives react, a multicomponent mixture of small molecules is formed. The theoretical treatment of postdetonation mixtures uses the EOS information from fluid experiments with the gas gun to treat detonation properties in a fundamental way (see the article on p. 41).

In recent years, our emphasis has shifted from EOS experiments to probes that provide more detailed information on the nature of matter at extreme conditions. We have begun to investigate other properties of shocked materials using such diagnostic methods as Raman and emission spectroscopy, and measuring such parameters as electrical conductivity and shock temperature. Data from these experiments provide more stringent tests of our theoretical models than do EOS data, enabling us to model such phenomena as molecular repulsion, rotation, vibration, and dissociation, electronic and molecular ionization, and chemical reactions and decomposition under a wide range of conditions. We discuss these new diagnostic techniques in the article beginning on p. 19.

Under shock conditions, it is also possible to induce novel metastable chemical reactions and crystalline

configurations that give materials new and remarkable properties. To put such discoveries to use, however, we must be able to recover the shocked specimens intact. We have adapted a method that we had originally developed for research into the changes induced in rock by extreme shocks (e.g., nuclear explosions). Some of the applications are described beginning on p. 28.

We are also using the shock compression of highly porous materials to explore the properties of expanded matter. If we start with microporous silica (about 5% the density of solid quartz) and shock compress it to one-sixth of its initial volume, raising its temperature to 20 000 K in the process, the sample will still have only one-third the density of solid quartz. These experiments are providing the first accurate experimental data in this range of density and temperature, and they will improve our confidence in crater calculations, for example, since silica-like materials constitute the earth's crust (see p. 31).

Other equally interesting uses of the gas gun and shock-wave experiments include research into the mechanisms by which a projectile penetrates armor. The results of such research can be used to design better armor and more penetrating projectiles. The response of explosive targets to the impact of steel rods, striking at 6 km/s, has been investigated for the Laboratory's Military Applications program.

Technology and methods developed with the two-stage gas gun have been transferred to many other programs at the Laboratory. For example, shock-wave detectors have been adapted to function in the environment close to an underground nuclear explosion and have been fielded at the Nevada Test Site to measure the EOSs of a variety of materials at terapascal pressures. In addition, techniques to measure the velocity of shock waves generated by high-intensity lasers, which we use for studies of porous materials, are now

used routinely in laser research to test the coupling of laser energy to sophisticated targets. Such information is essential to validate the physics models in computer simulation codes.

Our unique flash-x-ray source, developed for *in situ* diffraction studies of crystals at high shock pressures, has found application in laser research in the development of a plasma shutter for the Nova laser. A shutter is required to prevent laser light reflected by the target from propagating back down the laser amplifier chain and damaging the optical components. Absorption of x rays from our source was used to design an exploding plasma with sufficient areal mass density to absorb the reflected laser light from the target.

A substantial portion of our current research involves collaborations with faculty and students of the University of California (UC) through the Livermore branch of the UC Institute of Geophysics and Planetary Physics. For example, our work on emission spectroscopy is a result of a joint effort with chemists at UCLA. Geophysicists from UC Berkeley have used the gas gun to measure the electrical conductivity of iron oxide (FeO), an important component of the earth, at conditions similar to those that exist near the earth's core-mantle boundary. In collaboration with LLNL scientists, solid-state physicists at UC San Diego have measured, in their campus laboratories, the effects of superconductors shocked to 100-GPa (1-Mbar) pressures and recovered intact; a similar collaboration is being conducted with Stanford University. In addition, a number of graduate students from the California Institute of Technology and the UC Davis Department of Applied Science have performed research for their doctoral theses at our two-stage gas gun. ■

The Two-Stage Light-Gas Gun

The two-stage light-gas gun is illustrated in Figs. 1 and 2. It consists of a breech containing up to 3.5 kg of gunpowder, a pump tube filled with hydrogen, and an evacuated barrel for guiding a high-velocity projectile to the target. Hot gases from the burning gunpowder drive a heavy (4.5- to 6.8-kg) piston down the pump tube (90 mm i.d.). The piston compresses about 30 mol (60 g) of hydrogen gas, the second-stage driving medium, to about 140 MPa before the gas breaks the rupture valve. The motion of the heavy piston maintains a nearly constant mass flow rate of the hydrogen gas. In order to do this, the velocity of the hydrogen flow through the taper between the pump tube and

the barrel must increase. The hydrogen gas then accelerates a 10- to 25-g projectile down the barrel (28 mm i.d.) to a muzzle velocity of up to 8 km/s. (For comparison, the maximum velocities available with a single-stage gun and with planar high-explosive systems are 2 and 5 km/s, respectively.)

We usually use hydrogen for the second-stage driving gas because it produces the highest projectile velocities. The speed of sound in the driving gas determines the maximum rate at which it can transmit pressure to the projectile. For an ideal gas, which hydrogen closely approximates, the sound velocity is proportional to the square root of temperature divided

Fig. 1

Diagram of the two-stage light-gas gun. The hot burning gases from the gunpowder in the breech drive a heavy piston that compresses hydrogen gas in the pump tube (a). The high-pressure hydrogen gas breaks open the rupture valve and accelerates the projectile down the barrel. At the end of the barrel, the projectile has reached its highest velocity and impacts the target (b).

Key Words: equation of state; gun—two-stage light-gas; matter—expanded state, extreme condition; shock compression.

by molecular weight ($\sqrt{T/M}$). Light gases, in addition to their low molecular weights, are very compressible and thus can be driven to very high temperatures by the heavy piston. Thus, hydrogen has a high T/M ratio and produces the highest velocities.

We can obtain any desired projectile velocity in the range from 1 to 8 km/s by selecting the gun firing parameters: type and amount of gunpowder, driving gas (helium and nitrogen are used for velocities below 4 km/s), the pressure required to open the rupture valve, the diameter of the barrel, and the mass of the projectile.

When the projectile hits the target, the impact produces a high-pressure shock wave (see Fig. 3). The velocity of the shock wave, when combined with the initial conditions (projectile velocity, known densities and EOS of the projectile and target materials), yields a precise measure of the pressure, density, and energy attained. Other measurements performed in the brief interval while the shock wave is traversing the target yield information about a variety of other material properties. The shock pressure achieved by the impact increases approximately as the square of the impact velocity. Thus, the gas gun's maximum velocity of 8 km/s allows us to achieve significantly higher pressures than single-stage guns or planar explosive-driven systems.

Fig. 3

Artist's rendering of the target-impactor interaction. Here, a projectile fired by a flat tantalum disk is striking the aluminum base plate of a target assembly used to study cryogenic fluids. The hollow annular chambers around the periphery of the target contain liquid coolant. Just to the left of the base plate is the small cavity containing the liquid sample and the array of shock-wave detectors.

Fig. 2

Two views of the two-stage light-gas gun. In the top photograph, the gunpowder breach (the first driving stage) can be seen in the lower-left corner. The pump tube (the second driving stage) ends at the tapered section, where the man is standing. The photograph below shows the target chamber and the optical pyrometer (one of the diagnostics described in this issue). This gas gun was built by General Motors in the mid-1960s for ballistic missile studies; it has been operated at the Laboratory since 1972.

High-Pressure

When a hypervelocity projectile impacts a target, a strong shock is generated in the target material. The shock wave moves through the target in a fraction of a microsecond. The challenge in these experiments is to measure the properties of the shocked material during this extremely brief interval.

The shock wave suddenly changes the pressure in the target and travels in the target material with a supersonic velocity that is a function of the pressure. Figure 1 shows a shock wave at a position inside a target, moving at the shock velocity U_s . To the right of the shock front, the material is undisturbed and at its initial density ρ_0 . To the left of the shock front, the material has been compressed to a higher density and pressure. The shock front has negligible thickness and can be viewed as a discontinuous change in pressure, density, and energy. The

velocity of the shock front is a sensitive indicator of the compressibility of the material under the extremes of pressure and density imposed by the shock wave.

Even though the shock front is a discontinuity in pressure, density, and velocity, the fundamental quantities (mass, momentum, and energy) must still be conserved across it. This constraint is expressed in the Rankine-Hugoniot equations:

$$P - P_0 = \rho_0(U_s - U_0)(U_p - U_0), \quad (1)$$

$$V = V_0[1 - (U_p - U_0)/(U_s - U_0)], \quad (2)$$

$$E - E_0 = 1/2(P + P_0)(V_0 - V), \quad (3)$$

where:

P is the shock pressure.

V is the specific volume.

E is the shock energy.

U_s is the shock-wave velocity.

U_p is the mass velocity or particle velocity behind the shock front.

U_0 is the initial mass velocity, normally zero.

ρ_0 is the initial density of the unshocked specimen ($1/V_0$).

P_0 , V_0 , and E_0 are initial values of P , V , and E (P_0 and E_0 are usually negligible compared to P and E).

If we do a series of shock-wave experiments, each time compressing matter from a fixed initial volume and energy to a different pressure, each shock will induce a different change in volume. A plot of pressure-volume pairs of the final states achieved in such an experimental series is called a Hugoniot curve. As indicated by the arrow in Fig. 2, when the material is shocked to a given pressure, the change is discontinuous and no states of lower pressure are sampled along the way.

We use the Rankine-Hugoniot equations to design experiments to measure equation-of-state data (i.e., pressure, volume, and energy). The experiments measure the projectile velocity U_p , the shock velocity U_s , and the initial densities. Equation-of-state theory generally derives pressure as a function of density and temperature. For transparent materials, shock temperatures can be measured using optical pyrometry (see p. 25).

Since we can measure ρ_0 , P_0 , V_0 , E_0 , U_p , and U_s , we need only determine U_p , the mass velocity behind the shock front, to be able to calculate P , V , and E in the shocked state. We know that if impactor and target are of the same material, the mass velocity is exactly one-half the impactor velocity ($U_p = 1/2 U_i$), regardless of the EOS of the material. This precise relation enables us to determine very accurately the EOSs of a few materials and then use them as standards against which we can compare the shock response of other

Fig. 1

An ideal shock wave produced in a target with initial density ρ_0 . Ahead of the shock front (jump in pressure, density, and energy), the target is undisturbed. Behind the shock front (traveling at velocity U_s), the material is at a higher density ρ ; this region is uniform, as indicated by the flat top of the advancing shock-wave region.

Fig. 2

Plot of the change in pressure and volume of a shocked material. Each shock-wave experiment starts at a negligibly low pressure and an initial volume V_0 . When shocked, the material discontinuously goes to a new state (pressure P , volume V), indicated by the arrow (blue). A series of experiments with different shock pressures will trace out the principal Hugoniot (black curve).

Shock Waves

materials. The development of standards is described in the article on p. 8.

When the impactor and target are of different materials, determination of the mass velocity in the target depends on the EOS of the impactor. Using the standard materials, we can apply the principle of shock-impedance matching to determine the state of the new material. Impedance matching exploits the fact that the pressure and mass velocity are continuous across the impactor-target interface. This fact, together with the Rankine-Hugoniot equations, enables us to determine the state of the target material.

So far, we have been considering only a single shock produced by an impact on the front of a target. If this shock encounters an interface with another material (called an anvil), both the shock pressure and the shock velocity must change to accommodate the change in shock impedance ($\rho_0 U_s$). This change is again governed by the Rankine-Hugoniot equations. A shock wave, which may be larger or smaller in amplitude than the original shock (depending on the relative stiffness of the anvil) propagates forward into the anvil, and a second shock (if the pressure is larger than before) or a rarefaction wave (if the pressure is reduced at the anvil) moves back through the already shocked material of the target. In a double-shock experiment, the final state of the first shock is used as the initial state of the second shock in the Rankine-Hugoniot equations (Eqs. 1-3). Hence, by measuring the shock velocity in the anvil, we can determine the state of the original material under these new conditions of pressure and density.

The energy equation (Eq. 3) describes how shock waves differ from simple compression, in that

higher temperatures are achieved through higher internal energies imparted to the shocked material. Figure 3 shows that the Hugoniot lies above the isentropic and zero-Kelvin isothermal compression curves. The reason for this is that shock compression heats the material more and produces a higher thermal component of the pressure. The area under the isentrope (unshaded portion of the triangle) represents the reversible internal energy for a compression to a given volume. Equation 3 shows that the total energy in shock compression to the same volume can be represented as the area of the triangle.

The shaded area in Fig. 3 represents the amount of irreversible internal energy that is available for heating the target. Thus, shock waves produce both high pressures and high temperatures. It is this important fact that makes shock-wave studies so very useful. The temperatures reached can be as high as 20 000 K. These temperatures allow the study of a wide range of physical phenomena, such as chemical and solid-state reactions. The conditions reached in shocked specimens are directly applicable to studies of high-explosive detonation products and to investigations of the interiors of the giant planets.

Fig. 3

Plot of the irreversible internal energy or heating (shaded region) in an aluminum specimen shocked to 150 GPa. The Hugoniot is the best fit to the data; the 0-K isotherm and the isentrope were calculated.

Measuring Equations of State

We determine the equations of state of various materials to improve our understanding of the properties of matter under extreme conditions, information that is applicable to a wide range of disciplines.

For further information contact
William J. Nellis (415) 422-7200
or Neil C. Holmes (415) 422-7213.

Information about how a material responds to pressure is contained in the material's equation of state (EOS). We can investigate the EOSs of various materials, both solids and fluids, by measuring their response to the intense shocks generated by our two-stage light-gas gun. For more than a decade, we have been investigating and accumulating EOS data on many materials, including such solids as aluminum, copper, tantalum, and carbon (graphite), and such liquefied gases as nitrogen, oxygen, water, carbon monoxide, hydrogen, deuterium, helium, argon, xenon, ammonia, and methane.

For application of these data, consider, for example, the design of a weapon, nuclear or nonnuclear. We must know the detonation properties of the high explosive as well as the response of the metal parts adjacent to the explosive. When the explosive detonates, it produces a mixture of hot, dense reaction products at high pressure, and we must know the physics of each chemical component, over a wide range of pressure, temperature, and density, to be able to predict the behavior of the mixture. (These same considerations are also very important in investigations of the composition and character of the giant planets.) The high pressure of the

detonation products generates shock waves in the adjacent metal parts, and thus we must also know the behavior of various metals under conditions of extreme pressure, temperature, and density. In some applications, it is also useful to know if, under extremes of pressure and density, materials undergo phase transitions such as melting. In addition, predictions of the blast effects of an explosive or a weapon require knowledge of the equations of state and the mechanical constitutive properties not only of metals and explosives but also of other materials such as the rocks surrounding an underground nuclear test or the concrete structure of a potential target.

The EOSs of Solids

The operation of the gas gun is described in the box on p. 4, and a discussion of the shock process and the Rankine-Hugoniot equations that describe the shock process is given in the box on p. 6. In all EOS experiments, the initial densities of the impactor and the specimen are measured before the experiment, and the impactor velocity and the shock velocity are measured during the experiment. Then, using these data and the Rankine-Hugoniot equations, we derive the shock pressure, density,

and internal energy—that is, the state of the target material.

In EOS work, accuracy is extremely important because uncertainties in the measured quantities propagate into uncertainties in the determined state parameters. Using precision machining techniques, we fabricate impactors and targets of precisely known density, dimension, and flatness; for example, the faces of the impactor and target, typically millimetres thick, are lapped to a flatness of about $3\text{ }\mu\text{m}$. This great precision is required to achieve 1% uncertainties in pressure, density, and energy. This accuracy, in turn, is necessary for us to be able to test the theories that describe the behavior of materials at these extreme conditions.

Measurements

When the gas gun is fired, it accelerates the impactor to a very high velocity, sometimes as much as 8 km/s . When the projectile hits the target, the impact produces the high-pressure shock wave. This shock wave traverses the target specimen in a fraction of a millionth of a second, and during this very brief interval we must make a number of measurements from which we determine the exact conditions of pressure, temperature, and density and the material's properties under these extreme conditions.

In all our experiments, one of the most important experimental parameters is the impactor velocity. To measure this velocity precisely, we use pulsed x rays and take radiographs (flash-x-ray pictures) of the moving impactor at two positions in the target chamber at a precisely determined time interval. The x-ray pulses are very short (20 ns) to eliminate blur due to motion of the impactor. The distance the impactor has moved, divided by the time interval between the x-ray pulses, gives us the impactor velocity directly (1% accuracy).¹

To measure the shock-wave velocity, the other most crucial parameter, we set up an array of detectors on two planes in the target (Fig. 1). Each detector consists of an

Fig. 1

Shock-arrival-time detectors are arrayed on two planes in the target. (a) Each detector consists of an aluminum wire, 25 mm long and 0.75 mm in diameter, with a rounded insulated tip, that is spring-loaded against the target surface. A strong shock wave causes the insulating anodized layer to conduct electrically, which results in a fast voltage-discharge pulse when a shock wave arrives at the detector. Single-shock (b) and double-shock (c) experiments are similar, with the addition of the anvil in the double-shock targets.

aluminum wire, 25 mm long and 0.75 mm in diameter, with a rounded tip, that is spring-loaded against the target surface (Fig. 1a). The rounded tip of each detector is anodized to produce an insulating layer of aluminum oxide 1 to 2 μm thick. Each detector is connected to a coaxial cable whose outer conductor and the specimen are connected to a common electrical ground. A potential difference of 150 to 200 V is applied between the detector wire and the specimen across the anodized layer. Passage of a shock wave greater than 20 GPa drives the anodized layer into a conducting state, and the voltage discharges rapidly. High-speed electronics are used to time the resulting current pulse from each of the detectors to within 0.3 ns. The difference between arrival times at the two planes (about 200 ns for a 2-mm separation) yields the shock-wave velocity.

For measurements of high accuracy, the shock wave should have minimal tilt and be uniform across the face of the target. To ensure this kind of impact, we lap the faces of the impactor and target very flat and carefully align the target. However, it is impossible to guarantee that the impactor will fly absolutely flat, and the extreme forces of acceleration in the gun tend to distort the impactor somewhat. With the array of shock detectors, we record the arrival of the shock wave at each point; using a computer program to compare the shock arrival times, we can then determine the shock velocity, taking into account the amount of impactor distortion and tilt.

Standards

All our efforts to determine the EOSs of various materials hinge on the principal of shock-impedance matching, which states that shock pressure and mass velocity are continuous across an interface between two materials, and on the elegantly simple relation of $U_p = 1/2U_i$ for an impactor and target of the same material; that is, the mass

velocity behind the shock front U_p is exactly half the impactor velocity U_i , regardless of the EOS of the specific material. Pressure, volume, and specific internal energy are then calculated directly from the experimental data via the Rankine-Hugoniot equations (see the box on p. 6).

Therefore, using impactors and targets made of the same material, we have accurately determined the EOSs of a few "standard" materials—aluminum, copper, and tantalum.² By conducting many experiments in which we varied the impactor velocity and thus the conditions of pressure, temperature, and density created, we have accumulated the data from which to construct the Hugoniot equation of state for each standard.

We can use various combinations of standards for impactors and targets to access the widest possible range of pressures for each standard. If we use an impactor that is denser or stiffer than the target material, we can create much higher pressures in the target than are possible with an impactor of the same target material. The reverse is also true; if we use an impactor that is less stiff than the target, we can access pressures lower than those reached with impactor and target of the same material. For example, when we impact an aluminum target with an aluminum impactor, maximum pressures of 100 GPa are reached. However, when we impact an aluminum target with a tantalum impactor (tantalum is stiffer than aluminum), pressures reach 200 GPa.

For the case in which the impactor and specimen are of different materials, the mass velocity in the specimen depends on the EOS of both materials, and only if we know the EOS of one can we determine the EOS of the other. Thus, to determine the EOSs of "nonstandard" materials, we use a standard to impact the unknown material. Knowing the standard EOS and again applying the principal of shock-impedance matching, we can acquire EOS data on the new material.

We can also place buffer plates of various materials between the target and impactor to modify or "buffer" the shock conditions created in target. (We must, of course, know the EOSs of the different impactor and buffer-plate materials.) These types of variation in experimental setup enable us to systematically vary the shock conditions created in the target and to investigate the behavior of the target material under a very wide range of pressures, temperatures, and densities.

EOS data for these standard materials are also essential for testing the theories that describe material behavior at extreme conditions. That is, by using these data to validate theory, reliable physical models can be generated throughout the range of validity of the theory.

Double-Shock Experiments

Double-shock experiments are performed to create higher pressures and densities than can be obtained by a single shock and to probe states off the principal Hugoniot. In general, the pressure and temperature reached in a double-shock experiment to a given density are less than for a single shock to the same density. In the double-shock configuration, illustrated in Fig. 1c for a tantalum impactor shocking an aluminum specimen, the first shock traverses the aluminum target, and a shock of larger amplitude reflects off the aluminum-tantalum interface. The tantalum layer is called an anvil. A shock of higher pressure is reflected because tantalum has a higher shock impedance (is stiffer) than aluminum. If the tantalum anvil were replaced by a material of lower shock impedance than aluminum, a shock of lower pressure would be transmitted and a rarefaction wave would move back into the aluminum. In either case, both the pressure and mass velocity are continuous across the specimen-anvil interface.

In double-shock experiments, the Hugoniot of the impactor, target, and anvil must be known. The measured impactor velocity determines the first-shock state in the target. The second-

shock state is determined by the measured shock velocity in the anvil. A shock-compression diagram for aluminum is shown in Fig. 2; included is a data point for double-shocked aluminum. The solid point is the first-shock state at 160 GPa and the open point is the second-shock state at 300 GPa. Note that the double-shock pressure is much closer to the room-temperature (300-K) isotherm for aluminum (calculated by McMahon³) than to the principal Hugoniot (dashed curve) extrapolated to the same relative volume, showing that the material is indeed colder in a double-shock experiment.

We have also used a platinum anvil and a tantalum impactor with an impacting velocity of 8 km/s to achieve a 440-GPa pressure in double-shocked aluminum. This is quite close to the low end of the pressure range achieved in experiments located near underground nuclear explosions, in which 500-GPa first shocks and 900-GPa double shocks have been measured (aluminum target, copper anvil).

Ultrahigh Pressures

To further extend the pressure range of our EOS experiments, we have adapted gas-gun techniques so that we can use nuclear explosives to generate terapascals of pressure (1 TPa = 1000 GPa = 10 million atmospheres). The detector concept in Fig. 1a was scaled up to make it

Fig. 2

Shock-compression curves and room-temperature isotherm for aluminum, showing the principal Hugoniot starting from crystal volume and the reflected shock-wave Hugoniot obtained with double-shock experiments. The solid point is the first-shock state (160 GPa) and the open point is the second-shock state (300 GPa). Note that the material is cooler in a double-shock experiment than it would be on the principal Hugoniot at the same relative volume.

rugged enough for fielding in events hundreds of metres underground and to protect it against any neutron and gamma-ray preheat that may reach the detector ahead of shock wave.

In these ultrahigh-pressure experiments, performed in proximity to underground nuclear explosions, accurate EOS standards are essential. For these experiments, we have used the aluminum EOS as the standard to interpret the data for the other specimen materials. Because of the very high pressures involved (up to 2500 GPa), for which we do not have aluminum data, the EOS must be derived theoretically; it is checked against two-stage gas-gun data for aluminum obtained at the gas gun's highest pressure, 440 GPa.

To check the EOS of aluminum up to 2500 GPa, copper (another standard) is used as one of the specimens. This enables us to compare the results of copper derived from its own theoretical EOS with those based on the theoretical aluminum EOS. Good agreement between the two sets of copper results validates the EOSs of both materials at this ultrahigh pressure. This also gives us confidence that our interpretations of the data for the other materials, on the basis of the aluminum EOS, are accurate.

Hugoniot data for copper are summarized in Fig. 3, as shock velocity vs mass velocity. These data span the pressure range from 300 to 6000 GPa and were obtained by us, by investigators at Los Alamos,⁴ and by Soviet scientists.⁵ The smooth nature of the data is striking considering the variety of techniques, including gas gun, chemical explosives, and underground nuclear explosions, used over 25 years to collect the data.

New Diagnostics for Solids

For our future work on the EOSs of solids, we are developing a time-resolved optical velocimeter to measure the time history of the velocity of an interface between a specimen and a transparent window or of a free surface. This instrument will be used to measure the time-resolved response of materials to fast impulsive loading as encountered in weapon-effects studies, to study materials with time-dependent shocks like porous materials or explosives, and to study volume changes and kinetics in phase transitions in condensed matter. The latter information will be useful for synthesizing novel materials by high dynamic pressure and temperature, as discussed on p. 28.

Another diagnostic technique is flash-x-ray diffraction, which was developed for measuring the shift in the angular position of a strong x-ray diffraction line. This technique will permit us to observe shock compression on an atomic scale. We have shown that lithium fluoride (LiF) remains crystalline up to 100 GPa shock pressure by observing the pressure-induced shift in a diffraction line that persists to pressures greater than 100 GPa. This technique could be developed further to observe several diffraction lines in order to determine the crystal structures of phases formed at dynamic high pressures, temperatures, and densities. (The x-ray source for this experiment was also used to design a plasma shutter for the Nova laser, as mentioned earlier.)

Fig. 3

Shock-compression data for copper plotted in terms of shock velocity vs mass velocity. The data come from Los Alamos and Soviet scientists as well as our own work, and have been accumulated over the past 25 years. The agreement is remarkable in view of the wide variety of experimental systems and techniques. The dashed line is the extrapolation of the linear fit to the lower-pressure data; deviation from this line indicates a continuous change in electronic structure.

The EOSs of Fluids

Because of their higher compressibility, dense fluids reach much higher temperatures than do solids subjected to a shock wave of the same intensity. (Shocked gas specimens would reach even higher temperatures but much lower pressures and densities than shocked fluids.) The combination of high density and high temperature leads to a rich variety of observed phenomena. Information on the properties of fluids at extreme conditions enables us to predict the performance of high explosives and to model the interiors of the giant planets (e.g., Uranus and Neptune).

The postdetonation products of solid high explosives include nitrogen, water, carbon dioxide, carbon monoxide, hydrogen, ammonia, methane, and solid carbon. To understand the forces exerted by a detonating explosive well enough to model them, we must know how the pressure of each of these constituents responds to changes in density and temperature. Recently, we have obtained enough shock-compression data from gas-gun experiments with individual liquified gases to derive EOSs for detonation products by applying quantum-statistical mechanics and a mixture theory based on the minimization of free energy with respect to concentrations of the species present (see article on p. 41).

According to the best current knowledge, each of the giant outer planets in our solar system consists of a rocky core covered with a thick layer of "ice" (metallic hydrogen and helium for Jupiter and Saturn, and ammonia, methane, and water for Uranus and Neptune) and surrounded by a deep atmosphere of molecular hydrogen and helium.⁶ Because these planets are so massive, their interiors are very hot even though their "surface" temperatures (at the cloud tops) are very cold (about 80 K). The calculated temperatures and pressures at the bottom of Jupiter's atmosphere, for example, are as much as 10 000 K and 200 to 500 GPa. Therefore, our

gas-gun experiments, which attain quite similar temperatures and pressures, should be very useful for calibrating theories about the fluids thought to exist in these planets (see Fig. 4).

In fluids, the dominant effect at high densities and temperatures is intermolecular repulsion, the force that keeps the molecules of a fluid apart even when they are pushed close together. To model the interactions of molecules theoretically, we require a good description of how the intermolecular repulsion varies with the distance between the molecules. This description is called a pair potential, since interactions between pairs of molecules are dominant. (The pair potential is described in the box on p. 15.)

To conduct a shock-wave experiment on a liquid, we must first confine the liquid in a suitable target container that separates the liquid from the vacuum of the target chamber and presents a flat face to the impactor (Fig. 5). The front and back walls of the container must be strong enough to stay flat despite the difference in pressure across them.

Fig. 4

Shock compression data for hydrogen. The principal Hugoniot is the locus of the pressure-temperature points that can be reached by single-shock experiments from standard conditions (100 kPa pressure in the liquid state). It crosses the calculated isentropes of Jupiter and Saturn near 20 GPa and 4000 K. The solid black curve near the bottom of the figure is the solid/liquid melt line.

The walls must also be made of a material for which we have an accurate EOS (e.g., aluminum), since the liquid is shocked not directly but by a shock wave transmitted through the front wall, and we determine the second-shock state in the fluid by measuring the shock velocity in the back wall. Finally, most of the gases

we study stay liquid at atmospheric pressure only at very low temperatures, and for these we must provide cryogenic cooling. Since the target does not survive the passage of the shock wave, we must build a new target assembly for each experiment.

The fluids that we have studied include helium, hydrogen, deuterium, nitrogen, oxygen, air, argon, xenon, carbon monoxide, methane, ammonia, and water.

Noble Gases

The simplest materials to study are the noble gases (helium, argon, xenon, etc.) because they exhibit no phenomena other than intermolecular repulsion, provided they are kept cold enough to avoid electronic excitation.

Helium is the simplest monatomic fluid (only two electrons per atom) we can study experimentally. Hence, it is well suited for theoretical calculations. Helium is also a major constituent of Jupiter and Saturn.⁶ Thus, the properties of helium at extreme conditions are of great scientific interest, and shock compression is the only way to obtain EOS data for this gas at these conditions.

With helium, even though shock temperatures may run as high as 20 000 K, there is no chance of electronic excitation because still higher temperatures are required to excite the tightly bound helium electrons. Figure 6 compares the EOS calculated with a theoretical pair potential with the shock data.⁷ The agreement between experiment and theory is excellent.

For argon, the upper limit of the "cold" range is a single-shock pressure of 36 GPa, a compression to more than twice the initial density of the liquid, and a calculated temperature of 12 000 K. The pair potential derived from argon shock-wave data is in excellent agreement with pair potentials derived from molecular-beam scattering experiments (which, by their very nature, measure only two-body interactions), indicating that two-body interactions still dominate even in the dense fluid.

Fig. 5

A liquid-target setup for a single-shock experiment. The impactor strikes the base plate, which transmits the resulting shock to the contained liquid. The annular coolant chambers are filled with an appropriate cryogenic fluid such as liquid nitrogen. Rather than pouring in the sample liquid, we supply it as a gas and let it condense in the target cavity; this technique provides us with a sample of maximum purity and enables us to study different liquids with one coolant. The evacuated target chamber surrounding the whole target is not shown. (The front cover of this issue depicts such a target at the moment of projectile impact.)

Fig. 6

Comparison of experimental data on the shock compression of helium and the theoretical model. The agreement between experiment and theory is excellent.

Figure 7 displays the pressure-volume data for argon.⁸ The upper curve, calculated for interatomic repulsion only, agrees with the data below 36 GPa but then diverges. The colored curve, calculated with both interatomic repulsion and electronic excitation effects, fits all the data well. The difference in the two curves is caused by internal energy absorbed to excite electrons, leaving less energy available for heating and thermal pressure. We have obtained similar results with xenon.⁹

Hydrogen and Deuterium

Hydrogen, being the simplest diatomic molecule, has been of continuing interest, especially with respect to its insulator-to-metal transition. Shock compression is the primary way to obtain the EOS data for hydrogen and deuterium at the extreme conditions needed to test the molecular-phase EOS used to predict the transition from diatomic insulator to monatomic metal. Also, hydrogen is abundant in nature (e.g., hydrogen

is the major constituent of the outer planets). Thus, the properties of hydrogen at high pressure continue to be of considerable interest.

For hydrogen and deuterium, the theory becomes more complex because we are dealing with diatomic molecules instead of single atoms.

Fig. 7

A comparison of experimental data on the shock compression of argon (points with error bars) and two theoretical models. The black curve traces the model in which we assume that the only force acting is interatomic repulsion, whereas for the blue curve the calculation includes the effect of electronic excitation. Both curves fit the dots up to about 30 GPa, where electronic excitation begins to become important.

Pair Potentials

Shock-wave experiments on simple fluids can achieve final densities that are several times the initial density at temperatures of thousands of degrees. Under these conditions, the properties of the fluid are dominated by short-range repulsive forces. In our theoretical models, we must express these repulsive forces (and the attractive forces as well) in mathematical terms. It is both convenient and valid to express these forces in terms of how the potential energy between two particles in the fluid varies as a function of the distance between them (the separation distance r). This mathematical function is known as a pair potential. The realistic potential $\phi(r)$ we generally use is:

$$\phi(r) = \epsilon \left[\left(\frac{6}{\alpha - 6} \right) \exp \left[\alpha \left(1 - \frac{r}{r^*} \right) \right] - \left(\frac{\alpha}{\alpha - 6} \right) \left(\frac{r^*}{r} \right)^6 \right].$$

Here, α , ϵ , and r^* are scaling parameters (r^* is the location of the potential minimum, ϵ is the depth of the potential well).

This function is plotted at right using values derived from shock-wave experiments on argon, conducted with our two-stage light-gas gun. In this example, $\alpha = 13.0$,

$\epsilon/k = 122$ K (k is Boltzmann's constant), and $r^* = 0.385$ nm. Positive values of ϕ at small separations describe the repulsive part of the potential; when the potential is negative, the forces are attractive. Simply by changing the parameters on the basis of straightforward scaling relations, this description of the pair potential can be used for a variety of fluids.

Hence, in addition to intermolecular repulsions and attractions, we must take into account molecular vibrations and rotations. We have derived an effective pair potential for molecular hydrogen and deuterium that agrees well with an extensive body of shock-wave and static-compression data.

Because of the high shock temperatures, the theory treats both hydrogen and deuterium molecules as free rotors, making it possible to use a spherical approximation for the effective pair potential. We take the vibrational frequency as a constant because the change in the vibrational frequency up to 60 GPa in solid hydrogen at 300 K, measured in static-compression experiments, is not enough to influence the calculated thermodynamic parameters.

Calculated temperatures reached in our deuterium experiments were 4800 K at 20 GPa for the first shock and, depending on whether or not we include the effect of dissociation, 6500 or 7100 K at 75 GPa for the double shock. Calculations show that dissociation is negligible at the pressures and temperatures of our experiments.

The theory is also in excellent agreement with data on the compressibility of frozen hydrogen (5 K) to 37 GPa. Figure 8 compares the

present and previous shock data¹⁰⁻¹² with theory for deuterium.¹³ The theoretical two-body potential for hydrogen is considerably stiffer than the effective potential derived from these experiments, indicating that many-body attractions contribute significantly.

Nitrogen and Carbon Monoxide

Nitrogen is a simple diatomic molecule and is relatively abundant in nature (in Uranus and Neptune, for example). Thus, the properties of nitrogen at high pressure, like hydrogen, are of great interest. Nitrogen is also a major product molecule in detonated explosives, and recent theoretical work indicates that agreement between theory and experiment for the EOS of explosives can be improved if nitrogen is treated as insoluble in the mixture (see the article on p. 41). Because of its programmatic and scientific importance, we have undertaken a systematic study to understand the properties of pure nitrogen at high pressures and temperatures.

Figure 9 is a pressure-volume plot showing results from our experiments with nitrogen and carbon monoxide.¹⁴ Nitrogen and carbon monoxide are isoelectronic (they both have the same number of electrons per molecule), they have the same molecular weight and virtually identical critical points, and, in these experiments, they had the same initial density, 0.81 g/cm³. Thus, they might be expected to have the same compressibility, which they do up to about 15 GPa. The black curve, calculated using a pair potential scaled from our argon data, represents the expected behavior for both based on the assumption that neither dissociates.

From the agreement between the theoretical curve and the data, we can see that nitrogen retains its molecular structure up to about 30 GPa, where it probably undergoes a dissociative phase transition. At the densities achieved at 30 GPa shock pressure, virtually all the space is occupied by

Fig. 8

Comparison of experimental data on the shock compression of liquid deuterium (heavy hydrogen) with theory. The experimental data includes results from the work of researchers at Los Alamos and our own.

nitrogen molecules. In order to accommodate even higher densities, nitrogen molecules dissociate into atoms, which occupy less space.

Carbon monoxide, however, begins to decompose at 15 GPa and probably forms a large number of different product molecules. Above 70 GPa, the two curves (blue) merge again and differences related to the differing chemical nature of these two fluids diminish.

Double-shock EOS data for nitrogen (not shown) above 30 GPa have indicated that temperature should decrease as pressure increases above the Hugoniot.¹⁴ Later in this issue, shock temperature and electrical conductivity measurements are discussed (p. 19) that have revealed novel and unexpected properties for nitrogen in the region of this dissociative phase transition.

Butene and Polybutene

A fundamental problem of the EOS of explosives is the question of carbon condensation (see p. 35). One way to study the condensation of carbon, isolated from the many detonation products of a real explosive, is to study hydrocarbons (compounds containing only carbon and hydrogen). In order to test theory, it is desirable to obtain data for a hydrocarbon over a wide range of conditions.

Pressure, density, and temperature change continuously along shock-compression curves, and there is no way to independently vary the temperature of a substance in most of these experiments without changing the pressure at the same time. If, however, we can find two different forms of the same material that have different initial densities, then compression to the same volume will heat the denser one less than the other. This special case enables us to study a wide range of pressures and temperatures.

One example of such a pair of hydrocarbons is butene (C_4H_8) and polybutene ($n-C_4H_8$), compounds that are essentially the same chemically

(the hydrogen/carbon proportion of both is 2:1) but have substantially different liquid densities of 0.6 and 0.9 g/cm^3 , respectively. The shock-compression curves for the two (Fig. 10) are offset because of the higher temperatures achieved in the butene. They run parallel, however, indicating that the polymeric bonds that make polybutene initially so dense break at relatively low temperatures and leave the shocked fluid with no "memory" of its initial chemical state but only of its initial density.

The curves in Fig. 10 were calculated with the CHEQ code. This theory is in excellent agreement with the experimental data and indicates that at 50 GPa, the shock temperatures of polybutene and butene are 2500

Fig. 9

Comparison of experimental data on the shock compression of liquids (nitrogen and carbon monoxide) and a theoretical model that neglects the possibility of dissociation (black curve). Carbon monoxide begins to dissociate around 15 GPa and probably forms a variety of product molecules. Nitrogen molecules remain stable up to 30 GPa, at which pressure dissociation begins. At the highest pressures, the two experimental curves (blue) tend to merge, indicating that chemical differences are no longer important.

Fig. 10

Shock-compression data for butene (C_4H_8) and polybutene ($n-C_4H_8$). Although these two compounds have the same chemical composition, initially butene has only two-thirds the density of polybutene. Hence, if both are shock compressed to the same volume, the butene will be much hotter than the polybutene. This rather special case enables us to investigate a wider range of pressures and temperatures for a given material. The curves are calculated using the CHEQ code.

and 5000 K, respectively. The CHEQ code assumes that these molecules decompose into molecular hydrogen and a diamond-like carbon phase.

Summary

We have developed the experimental techniques for measuring EOS data for solids and fluids up to shock pressures of about 500 GPa. These data are of importance both programmatically and scientifically. The data for metals has been used to validate EOSs used in weapon-design calculations and to establish EOS standards for shock-compression experiments with other materials. Representative fluids have been studied to understand the basic phenomena that occur at high pressures and temperatures, including intermolecular repulsion, molecular vibration, rotation, dissociation, and decomposition, and electronic excitation. The data for butene and polybutene illustrate how a few experimental data points enable us to validate a theory over a wide range of pressures and temperatures. Shock-compression data for fluids are essential for validating the EOSs of individual molecular species included in mixture theories of high-explosive EOSs and for gaining an insight into

the compositions of the outer planets of our solar system. ■

Key Words: computer code—CHEQ; equation of state (EOS)—fluid, solid; shock compression; standard—aluminum, copper, tantalum; two-stage light-gas gun.

Notes and References

1. A. C. Mitchell and W. J. Nellis, *Rev. Sci. Instrum.* **52**, 347 (1981).
2. A. C. Mitchell and W. J. Nellis, *J. Appl. Phys.* **52**, 3363 (1981).
3. A. K. M. Mahan, *Bull. Amer. Phys. Soc.* **21**, 1303 (1976).
4. C. E. Ragan, *Phys. Rev. A* **29**, 1391 (1984).
5. L. V. Alshuler, A. A. Bakanova, and R. F. Trunin, *Soviet Phys. JETP* **15**, 65 (1962); R. F. Trunin et al., *Soviet Phys. JETP* **29**, 630 (1969); R. F. Trunin et al., *Soviet Phys. JETP* **35**, 550 (1972).
6. D. J. Stevenson, *Ann. Rev. Earth Planet. Sci.* **10**, 257 (1982).
7. W. J. Nellis et al., *Phys. Rev. Lett.* **53**, 1248 (1984).
8. M. Ross, W. Nellis, and A. Mitchell, *Chem. Phys. Lett.* **68**, 532 (1979).
9. W. J. Nellis, M. Van Thiel, and A. C. Mitchell, *Phys. Rev. Lett.* **48**, 816 (1982).
10. M. Van Thiel et al., *Phys. Rev. Lett.* **31**, 979 (1973).
11. R. D. Dick and G. I. Kerley, *J. Chem. Phys.* **73**, 5264 (1980).
12. W. J. Nellis et al., *J. Chem. Phys.* **79**, 1480 (1983).
13. M. Ross, F. H. Ree, and D. A. Young, *J. Chem. Phys.* **79**, 1487 (1983).
14. W. J. Nellis et al., *Phys. Rev. Lett.* **53**, 1661 (1984).

Gas-Gun Experiments: Advanced Diagnostic Techniques

To obtain ever more stringent tests of our theoretical models, we have developed specialized diagnostic techniques that probe the molecular, electrical, and optical properties of matter at extremes of pressure and temperature.

For many purposes, we must know more about a shocked material than just its equation of state (EOS). For example, two or more theoretical models may describe the same EOS data adequately and yet disagree strongly about the basic physical model of the material. In this case, one or the other of the theories might not be reliable if used for states different from the experimental Hugoniot data. We need additional information to decide which model is better. Our ultimate goal is to learn enough about the many physical processes that occur so that theoretical models can be used with confidence over wide ranges of pressure, density, and temperature.

To make the measurements required, we have developed a number of new experimental techniques. These include Raman and emission spectroscopy, measurements of electrical conductivity, and optical pyrometry. Spectroscopy enables us to identify substances that appear only briefly under high-pressure shock conditions. Conductivity measurements yield clues to the

electronic structure of matter. Optical pyrometry enables us to measure temperatures directly instead of inferring them from thermodynamic principles.

Spectroscopy
Spectroscopic methods are vital to studies of the behavior of particular molecules in a shocked material and for identifying new compounds formed by the shock process. For example, the detonation of an explosive is a rapid chemical reaction that produces various end products. We know the initial composition of the explosive and the final end products, but we know little about the reactions that convert the one into the other. How fast are they? Do they form intermediate products? For example, a key question is the formation of condensed carbon in the postdetonation mixture. The importance of this phenomenon is discussed in the article beginning on p. 35.

Even more basic is our need to know how much pressure the explosive can apply to the objects

For further information contact
Neil C. Holmes (415) 422-7213,
Douglas C. Hamilton (415) 422-7258,
or Harry B. Radousky (415) 422-4478.

around it. High explosives are complex chemical systems; after detonation, however, the products are generally relatively simple molecules such as water, nitrogen, carbon dioxide, and hydrocarbons. Our first goal is to understand the molecular behavior of these simple molecules under shock conditions; unraveling the complex chemistry of the detonation process will come later.

To identify these molecules and determine what is happening to them, we require a remote measurement technique that will not interfere with the shock wave, is fast enough to function in submicrosecond intervals, and is sensitive enough to observe extremely delicate effects. Spectroscopy, since it deals with the measurement of light, is well suited to these requirements. We have recently developed methods to use Raman and emission spectroscopy techniques in shocked fluids.

Raman Spectroscopy

Raman spectroscopy allows us to determine the chemical species

present in the shock state in a transparent molecular material by analysis of molecular vibrational frequencies. We used Raman spectroscopy to study shocked water (H_2O) in the liquid state up to 26 GPa and 1700 K.¹ Water is an important detonation product and is believed to be one of the most abundant constituents of the Uranus ice layer.² Prior to this work, no molecular data existed on liquid water at conditions relevant to these important issues. Our goals were to determine the structure of fluid water and to identify possible molecular dissociation species in the shocked state.

All molecules vibrate as the bonds between atoms stretch or bend, and the frequencies of these vibrations are characteristic not only of the particular molecule being studied but also of the interatomic bonds that form the molecule. For example, a carbon-oxygen bond will have a different set of characteristic frequencies than a hydrogen-oxygen bond. The vibrational frequencies of each kind of molecule are clues that enable us to deduce its structure.

Furthermore, when we apply high pressure and squeeze molecules closer together, we change the forces acting on each atom, thereby changing the characteristic frequencies. The kind and amount of these changes provide sensitive tests of our understanding of the molecular bonding forces.

To measure these molecular vibrations, we irradiate the sample material with a brief intense pulse of monochromatic ultraviolet light from a krypton-fluoride excimer laser (Fig. 1). To investigate conditions behind the shock wave, we focus the spectrometer optics on a point well into the sample and time the laser pulse to arrive there after the shock wave has passed. Most of this light simply passes through the specimen, but about one photon in 100 million imparts some of its energy to a molecule and the molecule vibrates at its characteristic frequencies. The photon, having lost energy, leaves the encounter with a different frequency.

Fig. 1

Diagram of the Raman spectroscopy technique as applied to shock-compression experiments. The impact on the aluminum base plate produces a shock wave in the water. The signal from the detector pin triggers the krypton-fluoride laser, which sends a 0.2-J, 10-ns pulse of highly monochromatic ultraviolet light (248-nm wavelength) into the shocked water. Photons that lose energy by exciting vibrations in the water molecules leave the sample with altered wavelengths. The spectrograph sorts this scattered light according to wavelength and measures the resulting distribution of intensities.

Simply by measuring the frequency of this very faint scattered light, we can determine the frequencies at which the molecule is vibrating.

In Raman spectroscopy at normal temperatures and pressures, we can use long time exposures (up to hours) to record the spectrum. However, because our gas-gun experiments are over so quickly, we have devised a system that records the entire spectrum of scattered light during the 10-ns laser pulse.

In this system, shown schematically in Fig. 1, we use a spectrograph with a gated microchannel-plate image intensifier in front of a 1024-element linear array of light-sensitive diodes. The front surface of the image intensifier is placed at the output focal plane of the spectrograph. The intensifier multiplies the intensity of the light falling on it several thousand times, helping to provide the high sensitivity required in a shock-wave experiment. The diode array records the output of the intensifier; each diode records the intensity of the scattered light at a slightly different frequency. The resulting 1024-point spectrum is stored in a desk-top computer for later analysis.

At the same time, the image intensifier acts as a shutter. It can be turned on for very brief intervals, as short as 20 ns. This lets us record only during the laser pulse and exclude the unwanted thermal light emitted by the shocked specimen, which lasts for a much longer time.

Figure 2a shows a pair of Raman spectra of water samples. The black curve shows the distribution of vibrational frequencies of the O-H stretching motion in liquid water under normal conditions. The blue curve is the spectrum obtained for water shocked to 7.5 GPa and a temperature of 640 K. The differences in the two spectra indicate the extent of the changes in the O-H bonds.

Previous spectroscopic studies of liquid water went only to about 0.4 GPa, but we have been able to extend these measurements up to 26 GPa. Our data can be explained by

the breakup of water molecule clusters (up to five H_2O molecules joined together by weak hydrogen bonds, see Fig. 2b), which are known from other work to exist in water at moderate pressures.¹ At 7.5 GPa (and 640 K), the clusters are still there but their range of vibrational frequencies is broader. Above 12 GPa (and 1000 K), the clusters begin to come apart. By 26 GPa (and 1700 K), they are almost all gone.²

Such information has a direct effect on our EOS calculations because

Fig. 2

Shocking a water specimen to 7.5 GPa and 370 K affects the part of its Raman spectrum that comes from vibrations that stretch the oxygen-hydrogen (O-H) bond in water molecules. (a) The spectrum of shocked water (blue) is broadened and shifted toward somewhat lower frequencies. (b) The structure of the water-molecule clusters whose vibrations we observe.

energy used to break intermolecular bonds is no longer available to heat the material. In addition, water is an important product of high-explosive detonations. Similar techniques can be applied to a variety of detonation products.

Emission Spectroscopy

Emission spectra from materials at high shock pressures and temperatures are used to measure the temperature at the shock front by observing the thermal grey-body emission and to identify chemical species by the nonequilibrium line or band emission they may emit, which is superimposed on the thermal spectrum. Here we concentrate on these nonequilibrium features (optical pyrometry deals with the grey-body emission and is described later).

In EOS experiments, we may observe the effects of chemical reactions indirectly, as changes in the slope of the Hugoniot curve or by matching theory to experiment. However, these techniques do not tell us what reactions are actually taking

place. Indeed, the abrupt changes in a material under shock conditions have led some workers to suggest that the chemistry induced by strong shock waves might be different from that expected on the basis of the pressure, density, and temperature achieved. Recovery experiments on shocked hydrocarbons have revealed that chemical decomposition does occur, but in these experiments the chemistry was not monitored as the pressure and temperature varied in the sample. To address this issue directly, we have developed the capability to record emission spectra while the shock wave is traveling through a sample.

At high shock pressures and temperatures, the shock front in initially transparent materials becomes opaque. If the material within an optical depth of the shock front is in thermal equilibrium, a grey-body continuum spectrum is observed in emission. If a molecule dissociates in such a way that the product molecules or atoms are formed in excited states, emission from those states may allow us to determine the molecules or atoms present in the postshock mixture.

In our first use of this new technique, we studied a simple hydrocarbon, benzene (C_6H_6), whose chemistry at high temperatures is well known from low-pressure shock tube work and whose Hugoniot is also well determined. We use the two-stage gas gun to produce precisely characterized states in benzene that last for up to 1 μs . These experiments are aimed at resolving the question of carbon condensation at extreme conditions (refer also to the article beginning on p. 35).

The target for these studies is similar to those used for other liquids, except that the back plate is a transparent window (Fig. 3). This window enables us to observe the light emitted from the shocked benzene during the initial compression and during the second compression by the reflected shock wave (reflected from the window). We provide two

Fig. 3

Diagram illustrates how we analyze and measure the light emitted by shocked specimens. The mirror directs the light outside the target chamber through a transparent window to the spectrographs and photodiodes. Filters restrict the input to each diode to a relatively narrow band of frequencies. Using more than one spectrograph widens the range of frequencies we can monitor.

spectrometers to observe either two adjacent spectral bands at the same time or the same portion of the spectrum at two different times; filtered photodiodes are used to monitor the behavior of selected narrow spectral regions as a function of time.

Figure 4 is an emission spectrum from benzene, double-shocked to 83 GPa and 3600 K (since this is a double-shock experiment, we are observing light from the region between the window and the reflected shock wave as it travels away from the window). The peaks at wavelengths of 470 and 515 nm are from diatomic carbon (C_2), and the peak at about 435 nm comes from an unstable carbon hydride (CH) fragment and C_2 . This is the first detection of product molecules in the condensed phase behind a shock front. This experiment demonstrates the feasibility of observing postshock reaction products at or near the shock front, and relates directly to the question of carbon condensation in the postdetonation mixture of high explosives.

From a series of such experiments at various pressures, we have determined that the reactions in shocked liquid benzene above 1300 K are about the same as those observed in low-pressure shock tubes. This suggests that temperature is the most important variable in determining which reactions occur. Furthermore, the presence of peaks of radiation intensity show that some of the material behind the shock front is not in equilibrium. However, at this time, we cannot estimate the extent of this nonequilibrium region.

Electrical Conductivity Measurements

Electrical conductivities are important for studying the possible onset of metallization, for detecting the presence of charged species, and for estimating their concentrations. This information supplements EOS data for validating physical models and provides data needed for

estimates of the optical depths of radiating shock fronts (i.e., the thickness of the region at the shock front from which light is emitted).

When insulating fluids such as water, nitrogen, and hydrocarbons are subjected to high shock pressures, they begin to conduct electricity. The effect may arise from ionic conduction, liberation of free electrons, or the formation of conductive materials such as graphite. At very high pressures, the conductivity can resemble that of a metal. Such insulator-to-metal transitions usually involve a rearrangement of the molecules or atoms into a more compact packing arrangement. All of these processes require energy (to break bonds, for example) that would otherwise be available to heat the material. Thus, they all have an influence on the EOS of the material.

Conductivity measurements provide an estimate of how many charge carriers are formed. This is a far more stringent test of our

Fig. 4

Spectrum of light emitted from behind the shock front in benzene (a double-shock experiment). The continuous background underneath the peaks is thermal radiation. The peaks at 470 and 515 nm come from diatomic carbon (C_2), and the peak at 435 nm comes from carbon hydride (CH) fragments and C_2 . The bands at about 390 nm are as yet unidentified. The presence of peaks in the spectrum is evidence that the material is not in equilibrium even though the shock wave has passed.

Fig. 5

Diagrams of the equipment used to measure the conductivity of shocked materials. (a) Typical target geometry. In place of the array of detector pins, we have two detector pins to trigger the data-recording system, two thermocouples for measuring the initial temperature just before the impact, and a pair of foil electrodes 1 mm wide spaced 1 mm apart. (b) Constant-current circuit for low-resistance measurements. S_1 is an electronic switch that is triggered about 10 μ s before the shock wave reaches the specimen between the foil electrodes (represented schematically as switch S_2 in series with specimen resistance R_s) to establish a steady current through resistor R_{CL} . The shock wave abruptly changes the conductivity of the material between the foil electrodes (equivalent to closing switch S_2), changing the voltage read by the oscilloscope.

(b) Constant-current circuit

theoretical models than EOS measurements alone.

The data we obtain are also important to models of the giant planets. The recent Voyager 2 flyby of the planet Uranus revealed an unexpectedly large magnetic field, which may be related to the conductivity of molecular materials inside the planet. Our shock experiments can generate conditions similar to those existing in the planet's interior. Hence, we have hope that a comprehensive set of conductivity experiments on possible planetary constituents may lead to an explanation of Uranus's magnetic field.

Nitrogen undergoes a dissociative phase transition above 30 GPa shock

pressure (see p. 13). To investigate possible changes of electronic structure or even metallization associated with this transition, we measured conductivities of liquid nitrogen from 20 to 60 GPa. We built a series of cryogenic targets fitted with thermocouples and foil electrodes (Fig. 5a) in place of most of the shock-detector pins used in our EOS targets. The constant-current circuit for measuring resistances (Fig. 5b) consists of a capacitor charged by a differential power supply through large ballast resistors (R_{BV}), large current-limiting resistors (R_{CL}), an electronic switch (S_1) that starts the current flowing 10 μ s before the shock wave reaches the foil electrodes (to eliminate start-up transients), and a voltage-divider arrangement (R_s and R_i) sized for maximum sensitivity to the expected sample resistance.

When the shock wave reaches the foil electrodes, the resistance of the material between the electrodes drops as the shock wave traverses their length. This is like closing a switch (S_2), which places the specimen resistance (R_s) in parallel with resistance R_i for 100 to 200 ns (while the shock wave is traversing the foil electrodes). A fast oscilloscope records the resulting change in voltage, from which we can deduce the unknown resistance R_s of the specimen.

The measured resistance depends not only on the resistivity of the shocked material but also on the area and spacing of the foil electrodes. We determine this geometrical factor separately, beforehand, by placing the foil electrodes in an electrolyte of known resistivity. We also monitor the temperature with a pair of thermocouples up to the time of the impact to determine the sample's initial state (density), so that we can determine its final state from the measured impactor velocity and the known EOS of liquid nitrogen.

According to our measurements (Fig. 6), the conductivity of liquid nitrogen increases by a factor of about 50 000 over the range of shock pressures from 20 to 60 GPa. The

curve plotted in Fig. 6 is a theoretical calculation by M. Ross of the fractional concentration of dissociated molecules in which he treated the dissociation energy as dependent on volume. (This dependence on volume is required to match the EOS data.) Figure 6 shows that the electrical conductivity is proportional to the concentration of dissociated nitrogen molecules (i.e., to the concentration of nitrogen atoms). This suggests that the conductivity is determined by electrons ionized from nitrogen atoms and that the electron mobility is slowly varying over the range of the data. These results demonstrate that a change in electronic structure is associated with the phase transition in nitrogen.

We will soon perform similar experiments to measure the conductivity of fluid mixtures approximating the composition of the interior of Uranus in an attempt to obtain insight into the possible origins of the magnetic field observed by Voyager 2.

Optical Pyrometry

The purpose of optical pyrometry experiments is to measure the shock temperature of initially transparent materials. The Rankine-Hugoniot equations, which express conservation of mass, energy, and momentum across the shock front, completely determine the shock pressure, volume, and total energy in a sample, if we know its initial density and have measured the shock velocity. What we don't have using these equations is a direct measurement of temperature. When a shock wave passes through a sample, some of the shock energy goes into heating the sample and some may go into "energy sinks," such as melting or another phase transition. Hence, direct measurements of temperature can give us yet another way to check our theoretical EOS models by providing a measure of the relative energy balance between external (thermal energy) and internal degrees of freedom.

However, such a temperature measurement must be remote and fast acting and must function without affecting either the shock wave or the sample. None of the usual temperature probes (e.g., thermocouples) are suitable. Since experiments happen so fast and the sample gets so hot (3000 to 20 000 K), we measure the emitted light and infer the temperature from that. Optical pyrometry, therefore, is the branch of emission spectroscopy that deals with the thermal radiation of the sample.

As a shock wave propagates through a sample, it suddenly compresses and heats the material. Everything behind the shock front is hot but everything in front is still in its original state. This means that if a window to the sample and the sample itself are both transparent, we can set up our pyrometer to look through them at the advancing shock front and, after the first shock reflects off the window, at a reflected shock front. This arrangement is basically the same as the setup used for emission spectroscopy of benzene (Fig. 3) except that, instead of two photodiodes, we use six photomultipliers, each one set to observe a narrow wavelength band.

The pyrometer itself consists of six photomultipliers (each set at a different wavelength) to record the time variation of the intensity of light at that wavelength. A combination gated microchannel plate/photodiode array records the middle 50 ns of the

Fig. 6

Data on the conductivity of nitrogen as a function of shock pressure (left-hand scale) compared with a theoretical curve of the percentage of dissociated nitrogen molecules as a function of pressure (right-hand scale). The close correspondence between the data and the curve suggests that the charge carriers are electrons ionized from nitrogen atoms.

light pulse over a broad spectral range. The photomultiplier signals provide evidence of the shock-front steadiness during the time it transits the specimen. The signals from the photodiode array go first to a dedicated microprocessor and then to a desk-top computer for further analysis. The array yields a complete spectral record of the emitted light over the range of 200 to 800 nm during a selected time interval.

We have been especially interested in shock-temperature studies of cesium iodide, both in relation to its insulator-to-metal transition (since it is isoelectronic to xenon) and in relation to melting under high pressure (since it is a simple ionic system). (Xenon's closed-shell electronic structure simplifies calculation of its EOS properties, but doing the same experiments with xenon is difficult. Hence, we work with its isoelectronic

analogue, cesium iodide.) Temperature measurements of shock waves in cesium iodide can tell us how much energy is going into electronic excitation, which allows us to observe the shift toward a metallic electronic structure with increasing density and temperature. At lower pressures, we can observe melting as the temperature stays almost constant with increasing pressure during the transition.

Figure 7 compares shock-temperature measurements of cesium iodide⁴ with theory. Between 20 and 40 GPa, the data follow the empirical melting curve (gray) based on the observation that many fluids freeze when the packing fraction exceeds 0.45. The three data points at higher pressures diverge from the melting line and approach the curve (blue-gray) based on semiconductor behavior. This kink indicates the completion of melting; it does not show up at all in the ordinary shock-compression data but is easy to see in the temperature data.

Above 5000 K, electronic excitation plays a major role and must be included in the calculation. The insulator (blue) curve, calculated on the assumption that there is no excitation, is clearly incorrect. The model used to calculate the semiconductor (blue-gray) curve yields an estimate of about 100 GPa for the metallization pressure of cesium iodide, an estimate that has since been verified by static high-pressure studies.

We have measured shock temperatures of liquid nitrogen to provide insight into the nature of the dissociative phase transition observed above 30 GPa.⁵ These shock-temperature measurements with liquid-nitrogen targets have turned up a completely unexpected phenomenon, shock-induced cooling. In every other material we have studied, the higher the shock pressure, the higher the temperature. In double-shock experiments, the temperature reached is not as high as it would be for a single shock to the same final

Fig. 7

Shock-temperature measurements of cesium iodide (CsI). Up to about 40 GPa, the temperature follows a theoretically calculated melting curve (gray). The two curves above 40 GPa represent different possibilities: that CsI would remain an insulator (blue) or that it would behave as a semiconductor (blue-gray).

volume but is still higher than it would be for the first shock. However, for certain pressures in nitrogen, we find that the temperature of the second shock is as much as 1300 K lower than the first shock! We have also verified our prediction⁵ that temperature decreases as pressure increases above the pressure-volume shock-compression curve for volumes in the phase transition region.

In our single-shock experiments (Fig. 8a), we begin to see evidence of dissociation at 30 GPa, the same pressure as for our EOS data (see p. 13). Above this pressure, the measured temperatures are much lower than expected from calculations that do not include dissociation. In contrast, static-pressure experiments at room temperature fail to show dissociation up to 130 GPa. The difference between static and shock experiments is that the latter involve high temperatures, indicating that dissociation is sensitive to both pressure and temperature.

Figure 8b shows how the difference in temperature between the first and second shock varies as we increase the first-shock pressure. (For all other materials we have studied, this curve slopes up rather than down.) The negative slope in Fig. 8b is caused by the internal energy absorbed in dissociating molecules; this energy thus is not available to heat the material. Eventually, at still higher first-shock pressures, this curve must bottom out and turn back upward when the nitrogen is fully dissociated and this particular energy sink disappears.

Summary

The advanced diagnostic instrumentation we have developed for our gas-gun experiments enables us to monitor aspects of shock compression other than the equation of state of matter, once our principal concern. Raman spectroscopy enables us to identify chemical species behind the shock front. Emission spectroscopy provides data on the chemical species present

in materials with opaque shock fronts. This technique helped show that shock-induced chemical reactions in benzene are more like high-temperature reactions at low pressures than had been thought. Conductivity measurements show the onset of the insulator-to-metal transition in dense fluid nitrogen at high temperatures and will help us understand such recent discoveries as the magnetic field of Uranus. Optical pyrometry yields insight into the dissociation of nitrogen at extreme conditions and opens a window on new, unexpected phenomena such as shock cooling.

Key Words: conductivity; emission spectroscopy; optical pyrometry; nonequilibrium radiation; Raman spectroscopy; shock compression; shock cooling; transition—insulator-to-metal, phase.

Notes and References

1. N. C. Holmes *et al.*, *Phys. Rev. Lett.* 55, 2433 (1985).
2. D. J. Stevenson, *Ann. Rev. Earth Planet. Sci.* 10, 257 (1982).
3. G. E. Walrafen, *J. Chem. Phys.* 47, 114 (1967).
4. H. B. Radousky *et al.*, *Phys. Rev. B* 31, 1457 (1985).
5. W. J. Nellis *et al.*, *Phys. Rev. Lett.* 53, 1661 (1984).

Fig. 8

Temperature measurements in shocked liquid nitrogen. (a) Single-shock data. Up to about 40 GPa, the temperature follows a curve (dashed) calculated without dissociation, but beyond this pressure it diverges. Simply including the effect of dissociation was not enough to make the theoretical curve (solid) match the data; we had to include a volume-dependent dissociation energy. (b) Double-shock data plotted as the change in temperature between the double-shock temperature T_2 and the first-shock temperature T_1 vs the first-shock pressure. This plot shows the newly discovered shock-cooling effect. In all other materials tested, the change in temperature produced by the second shock increases with increasing first-shock pressure. In nitrogen, the reverse is true over a limited range, and it is even possible for the second shock to cool the specimen by as much as 1300 K.

Novel Materials

Shock-wave techniques can be used to synthesize new materials that cannot otherwise be created, and other novel materials can be subjected to shock compression for study of expanded states of matter that cannot otherwise be achieved.

For further information contact
William J. Nellis (415) 422-7200,
Harry B. Radousky (415) 422-4478,
or Neil C. Holmes (415) 422-7213.

Thus far, we have focused on the use of shock waves to study the properties of materials compressed to high pressures, densities, and temperatures. In all of these experiments, the starting material has been either a normal solid or a liquid, and no attempt has been made to recover the specimens intact. Here, we focus on two new types of experiment. In the first, development of a recovery fixture enables us to subject specimens to extreme conditions and thereby synthesize, quench, and recover novel, metastable materials that cannot be created under less extreme conditions. The second involves the use of a novel material, silica aerogel, together with shock-compression techniques to investigate expanded states of matter that cannot be reached using conventional solid or liquid specimens.

Shock Synthesis
In the shock process, the extremes of pressure and temperature generated by the shock wave last only millionths of a second, and the cooling or quenching rate is extremely rapid (a billion degrees per second). This dynamic process can induce chemical reactions, melting and resolidification, phase transitions

(retained because of the rapid quenching), changes in crystal structure, and other modifications of a material's structure.

There are many materials whose properties would be particularly attractive if they could be synthesized in a nonequilibrium, metastable phase (e.g., superconductors that remain in the superconducting state at higher temperatures or under stronger magnetic fields than observed thus far). In most synthesis procedures, the material cools slowly enough that the atoms can diffuse into an equilibrium structure. However, the rapid quenching obtained in the shock process should enable us to "lock" the material in a metastable state. By varying the important experimental parameters, such as pressure, temperature, and shock duration, we can investigate and determine the specific requirements for creating metastable structures in broad classes of materials.

Because of the rich potential for making new materials by shock synthesis, we are developing the necessary techniques to subject specimens to high dynamic pressure and to recover them intact for investigations of new crystal structures, microstructures, and physical properties. Although our current

efforts have focused on superconducting materials, shock-synthesis techniques have natural applications to magnetic materials, materials with tailored mechanical properties, geological materials, polymers, glasses, ceramics, and composites.

Our initial aim is to use the two-stage gas gun to define the conditions required to synthesize such new materials in research-size specimens. As with the shock experiments already described, the high pressure in the specimen is generated by projectile impact. The gas gun provides simple tunability of the magnitude and duration of the shock pulse in the specimen. The maximum pressure obtained is controlled by choice of impactor material and by choice of impact velocity, which is continuously tunable. Maximum temperature is controlled by the initial specimen temperature and porosity. The duration of the shock pulse is controlled by the thicknesses of the impactor and specimen.

One obvious requirement for shock synthesis is that the specimen survive the process and be recovered intact. Ordinarily, in shock experiments, the energy deposited by the impacting projectile in the specimen tends to blow it apart. Therefore, we designed a special steel and lead fixture to contain the specimen and to permit recovery (Fig. 1).

The diagnostics described previously are not suited for this shock synthesis application. They are designed for the short time interval ($\sim 0.2 \mu\text{s}$) in which the shock wave traverses the specimen, and once the shock diverges into the recovery fixture they either no longer function or their presence compromises the intact recovery of the specimen. Thus, calculations must be used to characterize the conditions in the specimen. For this purpose, we use DYNA2D, a two-dimensional hydrodynamic computer code developed and refined for the Laboratory's engineering-design effort. Together with an extensive data base

of equations of state and mechanical constitutive properties, these calculations yield a reliable characterization of specimen histories over the time period required (tens of microseconds).

Bulk Niobium Specimens

Superconductors are materials that lose all electrical resistance below a transition temperature, and for this reason they are in great demand for electromagnets. However, above a certain limit, the high magnetic field destroys the material's superconducting state, thus limiting the strength of the magnetic field that can be produced. But, as the material's transition temperature increases, so does the achievable magnetic field. Therefore, if a superconducting magnet is operated at a very low temperature (say, liquid helium temperature, 4 K), a larger magnetic field can be produced by using a superconductor with a higher transition temperature.

Niobium is the element with the highest superconducting transition temperature. Therefore, we are using niobium as a simple test material as we develop our techniques and investigate the effects of shock-induced defects on superconducting properties. Since niobium is predicted to have a maximum shock-induced hardness at 90 GPa, we have used

Fig. 1

The special recovery fixture is a composite of steel inside a jacket of lead. With this fixture, we have recovered intact specimens of niobium, some as thin as 20 μm , subjected to gigapascal shock pressures.

shock pressures ranging from 60 to 120 GPa. Figure 2 plots ideal, one-dimensional pressure and temperature pulses experienced by a niobium sample in our shock process. In this example, the pressure rises to 100 GPa and the temperature rises to 2000 K in a tiny fraction of a second (about 10^{-12} s). Under such conditions, niobium is compressed a factor of 1.4 in density.

In our experiments, maximum pressure is maintained for about $0.2 \mu\text{s}$ and then released to zero in a comparable length of time. Because of irreversible shock heating (see the box on p. 6), the temperature only decreases to 1300 K. To quench the metastable structural features, this residual thermal energy must be removed as quickly as possible. We do this by using thin specimens and by precooling the recovery fixture so that thermal transport into the fixture is sufficient to quickly remove the specimen's residual thermal energy. Precooling both the fixture and the specimen offers the additional advantage that, after passage of the shock wave, the specimen's residual temperature is much lower as well, often close to room temperature.

Fig. 2

ideal, one-dimensional pressure and temperature pulses experienced by a niobium sample in the shock process. Shock pressure rises instantly to 100 GPa and temperature to 2000 K (calculated); these values are maintained for about $0.2 \mu\text{s}$. Pressure then releases to zero, but because of the irreversible shock energy imparted to the sample, the temperature falls not to zero but to a residual temperature of 1300 K. The cooling rate from 2000 to 1300 K is 10^8 K/s ; cooling from 1300 to 300 K occurs by thermal diffusion and is much slower.

In typical experiments, niobium specimens, measuring initially 13 mm in diameter and 9 mm thick, are placed in the recovery fixture and impacted with 3-mm-thick steel disks in polycarbonate plastic jackets. The niobium specimens are recovered intact; final dimensions are typically 20 mm in diameter and 4 mm thick, indicating substantial plastic flow.

X-ray diffraction reveals that the recovered niobium specimens retain their original body-centered-cubic crystal structure. Photomicrographs however reveal substantial alteration of the niobium grain structure. The specimen before shock processing has an isotropic grain structure (Fig. 3a) with fairly large grains and no preferred orientation. However, the samples shocked to 100 and 120 GPa (Fig. 3b) show bands of long, thin grains aligned perpendicular to the shock-wave front. This type of grain structure can have a dramatic and often desirable effect on the magnetic and mechanical properties of the material. For example, we expect that shock-induced defects in these grains will result in superconductivity persisting to higher magnetic fields. In permanent magnetic materials, this type of microstructure is expected to increase the coercivity (that is, the "permanency") of the magnet.

Although the shock processing greatly alters the microstructure of the niobium, measurements made by M. B. Maple (University of California, San Diego) reveal that it does not significantly affect the transition temperature. In all cases, the change in transition temperature is extremely small, with the maximum decrease being only 0.035 K (out of 9.2 K).¹

Thin Niobium Films

We have also subjected 30- μm -thick niobium films, produced by vapor deposition (by T. H. Geballe, Stanford University), to 100-GPa shock pressures. Vapor deposition can be used to fabricate a wide range of starting specimens with controllable structure and stoichiometry, thereby greatly increasing the number of novel

materials that can be produced with shock synthesis. The major hurdle to this approach, however, has been the question as to whether or not thin-film specimens can survive the shock process and be recovered intact. In our recent experiments with niobium films, we recovered thin-film specimens intact from shock pressures of 74 and 98 GPa. Like the bulk niobium specimens, the films experience plastic flow; originally 30 μm thick, the recovered niobium films are about 20 μm thick. As with the bulk specimens, the change in transition temperature is small; the superconducting transition temperature of the shock-processed and unshocked niobium films is in the range of 9.4 to 9.5 K.

For both bulk and film specimens of niobium, the transition temperature appears to be only very weakly sensitive to shock-induced defects. This suggests, in turn, that shock-induced defects have only a weak effect on the superconducting transition of equilibrium phases, and that shock-synthesized nonequilibrium superconductors may indeed have transition temperatures close to their intrinsic values. Thus, shock processing may prove to be a very effective and versatile technique for fabricating nonequilibrium, metastable phases of novel materials unobtainable by any other means.

Expanded States of Matter

The behavior of hot and expanded states of matter is important to many Laboratory programs that subject materials to high energy densities. Hot, expanded states are also of great scientific interest; no accurate EOS data exist for states in the region of 1 g/cm³ and a few electron volts (1 eV = 11 600 K). This density-temperature regime is important for modeling such diverse phenomena as weapons effects, cratering on the earth and moon, and the performance of magneto-hydrodynamic generators. Furthermore, after a dense material has been shock-compressed and

irreversibly heated, it will expand to lower densities and remain hot. These states are important to characterize. Shock compression offers a way to address these issues. In most shock studies of material properties at high pressures and temperatures, the starting material is a normal solid or liquid. However, years earlier, we realized that if we started with a solid whose initial density was less than its normal density, we could achieve even higher temperatures upon shock compression (see Fig. 4).

Usually, expanded states of materials must be studied as the shocked specimen is actively expanding, and, as a result, there are

(a) Before shock processing

(b) After shock processing

Fig. 3

Photomicrographs of a niobium specimen before (a) and after (b) shock processing. Before shock processing, the specimen has an isotropic grain structure; the grains are fairly large and there is no preferred orientation. After shock processing at 100 GPa, the specimen shows bands of long, thin grains aligned perpendicular to the shock-wave front.

always density and temperature gradients in the sample. Shock compression of low-density materials produces uniform states with large sample sizes, and the shock state can be highly expanded relative to the ideal crystal density of the starting material. Almost all of the precise measurement techniques developed for shock-wave equation-of-state experiments can be applied to these specimens.

Pursuing this approach, numerous studies have been done elsewhere with powders with initial densities of about one-third to one-half their normal densities. These experiments on porous (low-density) samples have suffered in accuracy from the lack of evenly distributed and sized pores. Very small pore sizes are important because, upon passage of the shock wave, they permit the material to mix

uniformly on a time scale that is much shorter than the time scale of our measurements. This, in turn, allows us to make the assumption that equilibrium is achieved.

Silica Aerogel

Recently, we have been using a new material, silica aerogel, that offers great promise for precise measurements of expanded material states. This material has a high porosity (and hence low initial density) and is uniform and homogeneous to very small scale lengths. Silica aerogel is a porous form of silica or silicon dioxide (SiO_2), the same substance that forms crystalline quartz and fused silica. Beach sand and many rocks also are primarily composed of silica.

Aerogel has a number of interesting characteristics. Its most notable feature is its very low density. Silica aerogel is available in a range of initial densities from 0.05 to 0.25 g/cm^3 . We have been using samples with a density of 0.13 g/cm^3 , about one-twentieth the density of crystalline quartz. Since the shock temperature and pressure are very sensitive to the sample's initial density, aerogel, with its range of low densities, gives us a way to use shock-compression techniques to explore a very wide range of expanded states.

Aerogel's pores are extremely small, about 10 nm; since the pores are much smaller than the wavelength of visible light (350 to 1000 nm), the material is transparent. In addition, aerogel is an open-cell foam structure, like a sponge, and thus can be pumped to a high vacuum or filled with liquid.

Aerogel is rigid, and although it is quite fragile it can be machined with care to exacting tolerances. For accurate measurements, the surface of the aerogel specimen must be very smooth and flat. Using the Laboratory's precision diamond-turning machines, we can produce aerogel samples with surfaces that are flat to within about 3 μm , several times flatter than is possible using standard machining methods.

Fig. 4

Plot of the pressure-volume state for shock compression and expansion of a typical material. The solid black curve depicts the effect of shock compression of a sample of normal initial density; the dashed curve shows expansion of a sample of normal initial density. The blue curve depicts the effect of shock compression of a sample with a low initial density (a highly expanded initial state). This curve intersects the expansion curve at some high pressure and temperature but at a density lower than the specimen's normal density. Thus, shock compression starting from a highly expanded initial state reaches the same conditions as expansion from normal density.

Studies with Aerogel

Our first task in the study of aerogel, as with any new material, is to determine its equation of state. To do this, we make stepped targets similar in size to those we use for metal specimens. However, we could not use electrical shorting pins to measure shock arrival times because aerogel is so fragile that contact with the pins would fracture the surface. Instead, we use an optical technique, first applied to laser-driven shock experiments, and measure the shock velocity in the aerogel with a fast electro-optic, time- and position-resolved streak camera (see Fig. 5). This method makes use of the fact that when the aerogel is shocked, it becomes very hot and emits a bright light from the shock front. The stepped surface of the aerogel target is coated with a thin layer of gold to make it opaque to that shock-emitted light. When the shock front arrives at the gold layer, the metal is heated very rapidly and the light emitted from the gold is recorded by the streak camera.

A typical record from an aerogel experiment is shown in Fig. 6. The shock arrives first at the base of the step (lower left) and later at the top (upper right); time is increasing upward. For this experiment, the step was about 1 mm high, and the shock traveled this distance in just 85 ns, which corresponds to a pressure of 14.6 GPa (146 000 times atmospheric pressure). The density was 0.95 g/cm^3 , which is greater than seven times the material's initial density (even though this is still only one-third the density of crystalline quartz). The temperature of the aerogel was not measured in this experiment, but is calculated to be well over 10 000 K.

Since most of the shock energy in the shock compression of aerogel is in thermal energy, it is important to accurately determine the temperature of the shocked specimen. We use the optical pyrometer described earlier (see p. 25) for this measurement. We exploit the fact that aerogel is transparent. This feature makes our

Fig. 5

The optical technique for measuring shock velocity, as used for aerogel experiments. A stepped aerogel target is machined to exacting tolerances and then coated with a thin, opaque layer of gold. When the shock front reaches each step, the rapidly heated gold coating emits light which is recorded by the streak camera, thus providing a record of the arrival times of the shock wave at the target's stepped surfaces.

Fig. 6

A typical streak camera record from an aerogel experiment. The bright signal at the lower left is the arrival of the shock wave at the base of the step. Later, the shock wave arrives at the top of the step (upper right). Time is increasing upward in this record. The slight slope of the initial shock arrival indicates that the projectile was slightly tilted at impact with the target.

experiments with aerogel similar to those conducted with liquid samples. In one experiment² in which aerogel was shocked to 6.7 GPa, we measured a temperature of 10 800 K. Higher shock pressures and lower aerogel initial densities will yield even higher temperatures.

Further Uses of Aerogel

Once we determine the equation of state of aerogel itself, we can use the material for a number of other experimental applications. For example, we are investigating the use of aerogel as a very-low-density, shock-impedance "standard." When shock waves pass out of one material and into another with a much lower density, the pressure and density fall. Thus, we can use aerogel to study the states of shocked materials far from their principal Hugoniot. Aerogel can also be used to generate and study "cool," high-density plasmas, where temperatures are a few electron volts and densities are near 1 g/cm^3 . These temperatures are similar to those achieved in experiments with shocked gases, but the densities are much higher. In addition, experiments with aerogel can help us enlarge our understanding of important geological processes, such as cratering produced by the impact of high-velocity meteorites. We can create conditions relevant to cratering in two ways: we can study aerogel itself (since it is SiO_2 , like many rocks), and we can shock actual geological materials (that

is, rock specimens) and allow them to release into the aerogel.

Summary

In our continuing studies of the properties and behavior of matter at extreme conditions of temperature and pressure, shock-compression techniques and novel materials are linked, hand in hand. On the one hand, shock compression can be used to create unique materials, such as the nonequilibrium metastable phases of superconductors, that cannot be synthesized using more traditional, less extreme processes. On the other, unusual materials like silica aerogel can be used as a means to study the properties of expanded states of matter, states that cannot be created with normal solid, liquid, or gaseous starting specimens. The more precisely we can control and understand the shock process, the greater the opportunities for using shock synthesis to create new materials. Also, as more materials with unusual properties of density or porosity are developed, there will be a greater range of material states available for study. ■

Key Words: matter—expanded state; niobium—bulk, thin film; shock compression; shock synthesis; silica aerogel; superconductor.

Notes and References

1. W. J. Nellis *et al.*, *Physica* **135B**, 240 (1985).
2. N. C. Holmes *et al.*, *Appl. Phys. Lett.* **45**, 626 (1984).

Studies of High Explosives

Understanding the behavior of high explosives is a very important and complex problem. Many Laboratory programs rely on numerical models of high-explosive properties for design purposes. The complexity of the problem arises from our need to model the response of detonating explosives and their subsequent interactions with surrounding matter, and from the fact that high explosives are complicated chemical systems. There are several ways to address this problem, and the following two articles illustrate two approaches.

A logical starting point is to study the behavior of detonating explosives. In an actual detonation experiment, the maximum pressure at the detonation front has a well-determined value depending on the particular properties of the explosive. With the two-stage light-gas gun, a very wide range of pressures and densities in explosives can be achieved and measured. The data obtained can then be directly compared to and used to refine theoretical models of detonation behavior. Because the conclusions drawn from the data can be very sensitive to small changes, these experiments must be extremely accurate. In this way, we can work from the measured properties of detonations and explosive equations of state to develop a general understanding of the detonation

process. The work described in the article on p. 36 takes this approach.

When an explosive detonates, it produces a complex mixture of chemical product molecules at high temperature. As time progresses, the composition of the mixture changes as chemical reactions are completed or as shock waves produced by the explosion move through the mixture. Another fundamental approach is to start with the chemical composition of the unreacted explosive and use data obtained from gas-gun experiments on the individual detonation product molecules to predict the detonation properties. The goal is to start with a comprehensive data base of molecular physics and physical and chemical principles and to produce a predictive general theory of explosive detonation behavior and its response to changes in pressure and temperature. This approach is described in the article beginning on p. 41.

In our attempts to model and predict high-explosive properties, we have used both approaches, and we have identified several phenomena that may explain the lack of complete agreement between experiment and theory. A vigorous experimental program is clearly desirable to address these questions, and new diagnostic techniques (such as those described in the article on p. 19) are required to provide more stringent tests of the theoretical models. ■

Supracompression of High-Explosive Detonation Products

We are using the two-stage light-gas gun to investigate how the physics and chemistry of an explosive's detonation products are affected by being shocked to a supracompressive state.

For further information contact
LeRoy G. Green (415) 422-6890
or Edward L. Lee (415) 422-1316.

In a number of weapons applications, shock reflection or a convergent detonation wave drives the detonation products of a high explosive to compression states significantly higher than those they can reach in an unperturbed, self-sustaining planar detonation. Equations of state (EOSs) based on data gathered from self-sustaining planar detonations cannot readily be extrapolated to describe these supracompressed states. Yet, studies of these states in a converging geometry are unattractive because of experimental difficulties. The ideal is to produce supracompressive states in a simple planar geometry.

We have produced such states in the laboratory by using hypervelocity projectiles from our two-stage light-gas gun to shock-compress high-explosive targets, and have measured them using the high-precision techniques developed to measure shocks in inert materials, as described in the article on p. 8. We have also developed new diagnostic techniques that apply specifically to work with detonation products. One of our main objectives was to extend the equations

of state of explosives based on HMX (PBX-9404 and LX-07), TATB (LX-17), and a mixture of HMX and TATB (RX-26-AF) well into the supracompressive region.

In our shock-velocity measurements, we have used input pressures ranging from 30 to 110 GPa. We have also done double-shock studies with PBX-9404, using anvils of copper to produce higher supracompressive states and of magnesium to obtain rarefaction to lower pressures from supracompression. Our PBX-9404 work agrees with previous measurements,¹ if we allow for the larger experimental uncertainties of the former work.

In general, our results indicate that current equation-of-state descriptions^{2,3} are inadequate to describe what we see in detonation products at substantially higher pressures. It is not yet clear how best to resolve this discrepancy. Explosive detonation theory may have to be modified to fit all the data, or it may be necessary to reevaluate the customary methods of determining the point at which equilibrium

conditions have been attained in ordinary self-sustaining detonations.

Theory

A detonation propagates through the explosive as a wave, and involves a number of distinct stages. One way to visualize these stages accurately is to imagine ourselves riding the crest of the detonation wave.

If we focus on the moment when the detonation wave is midway through a block of explosive, we can see that ahead of the wave there is nothing but unreacted explosive and behind it there is a highly compressed but expanding mixture of detonation products (Fig. 1). In the wave itself, there is a thin layer of explosive that has been compressed to about 75% of its original volume by the detonation's shock wave but has not had time to react, and another thin layer where the explosive is in the process of reacting. The point at the back of the wave where the explosive reactions have reached equilibrium is known as the Chapman-Jouguet (C-J) state. By definition, the C-J state is the place in a self-sustaining planar detonation front where irreversible chemical reaction is complete, the products are in equilibrium, and the flow is sonic (i.e., the shock wave is moving at the speed that sound travels in that medium).

The EOS of an explosive's detonation products is the functional relationship that makes it possible to calculate the work an explosive can do on its surroundings. The EOS is most easily formalized as the relationship between the pressure in the explosion products and their consequent kinetic and internal energies. If this functional relationship accurately represents the behavior of an explosive, we can use it to predict how the explosive will behave when it detonates and how it will affect the materials around it.

The solid curve in Fig. 2 represents the EOS of a typical explosive's detonation products. This EOS is a composite of two curves that join at

Fig. 1

As a planar detonation wave moves through an explosive at a steady-state velocity, it first compresses the explosive to about 75% of its initial volume. The explosive reaction takes a short but finite time, forming a reaction zone behind the pressure spike. At some point in the wave, known as the Chapman-Jouguet (C-J) point, all reactions have reached equilibrium and the compressed gases have begun to expand and do work.

Fig. 2

A typical EOS curve describing the states that the products of a detonating explosive can reach. The C-J point corresponds to the maximum equilibrium pressure that can be attained in a self-sustaining, planar detonation wave. The curve below this point is the set of pressure-volume states the expanding gases can occupy. Only if the planar shock wave is reflected off a dense barrier, made to converge, or augmented by the energy supplied by a hypervelocity impact can supracompression states (blue) on the Hugoniot above the C-J point be reached.

the C-J point. The upper region (blue) is the Hugoniot (the set of supracompression states the gases can attain only in a converging shock wave or by receiving a single large overshock). The lower region (black) is the expansion adiabat, referenced to the C-J state (the set of pressure-volume states the reaction products can attain as they expand after the detonation). Every point on the Hugoniot has a corresponding expansion adiabat; an expansion adiabat is the actual path the expansion follows, not just the end points of the process.

Although the C-J pressure of an explosive is a fundamental parameter for calculating the explosive's performance, measuring it precisely is very difficult. The most commonly used method measures the explosion-induced shock in a reference material, from which the C-J pressure in the explosive of interest can be inferred. This method incurs errors of several percent from the approximations required to solve the EOS equations, and additional errors arise from differentiation of the time-position data and extrapolation of the results.

Experimental Methods

Previous experimenters exploring the supracompression region^{1,4} used explosively driven flyer plates (impactors) hitting a buffer plate to transmit a powerful shock into the high explosive. They monitored the results with streak cameras or shock-detector pins. Our two-stage gas gun gives us more powerful impacts and better control over the impact velocity, and our ultrafast shock-detector pins yield more precise measurements of shock velocities than was previously possible.

The assembly of the target explosive is a meticulous process. We first compact the high explosive for the target specimens in a high-pressure die. After measuring the density and machining the sample to the required dimensions, the front and back surfaces of the targets are hand-

lapped flat and parallel to within 1 μm . In some of our experiments, we used an aluminum buffer plate between the impactor and the explosive target, but we found that higher accuracy could be obtained using an explosive buffer plate with exactly the same shock impedance as the high-explosive sample. The sample geometry we now use is very similar to that used for our single-shock standards experiments (see the figure on p. 9), except that the stepped surfaces of the target are formed by precisely bonding two samples of high explosive together with a very thin layer of adhesive. We use the same electrical shorting-pin shock-arrival detectors as shown on p. 9 and measure the thickness of the sample at the pin locations to within 2 μm . With these precision high-explosive assemblies, we can take full advantage of the diagnostics available with the gas gun.

Experimental Results

Figures 3 and 4 plot the experimental data from our supracompression experiments on two explosives, LX-17 and PBX-9404. The curves of shock velocity vs particle (mass) velocity are extrapolated from measurements of self-sustaining planar detonation waves (at or below the C-J pressure). Note that the data points for both explosives are consistently above the extrapolated curves. (This has also been the case for experiments with other explosives.) In addition, the data do not appear to be leveling off at the accepted C-J points, although this does not mean that C-J conditions cannot be met in supracompression experiments. The data close to the C-J point are too sparse and the uncertainty associated with the data points, while small, is too large to permit resolution of this question at this time. Even more precise measurements at closely spaced intervals of mass velocity are required to resolve this puzzle.

Figure 4 (for PBX-9404) includes an EOS (dashed curve) that fits our experimental data closely. However,

this EOS implies a C-J pressure of 34 GPa, whereas the EOS derived from the wealth of data from self-sustaining planar PBX-9404 detonations (solid curve) corresponds to a C-J pressure of 37 GPa. Although alternative explanations exist, it may well be that our supracompression experiments produce conditions different enough from the usual detonation to require a different C-J point in the calculational models.

Discussion
The value of the C-J pressure for ordinary detonations of PBX-9404 is well established (at 37 GPa) by countless experiments. One cannot simply substitute a new value of 34 GPa to fit the supracompression data; calculations of the initial motion of a metal plate being accelerated by a head-on detonation of PBX-9404, on the basis of this value, would yield a velocity much lower than we measure experimentally. Hence, it appears that while the state measured in planar detonation experiments may have many attributes of a C-J state and for many purposes may serve as a useful description, it may, in the final analysis, fail to qualify as the actual C-J state.

If the C-J pressure for PBX-9404 really is about 10% lower than that inferred from earlier experiments, as our supracompression experiments imply, one possible explanation might be that, in addition to the fast reactions in the explosive, there may be others that are slower. In a self-sustaining planar detonation, any changes produced by the slower reactions during the expansion of products would be very difficult to detect and measure, and the measurements of the assumed state would be of a nonequilibrium state. (Remember though, that by definition the C-J state must be an equilibrium state.) In supracompression experiments, the explosive is held at a higher temperature and a higher pressure for a relatively long time (the time for the shock to traverse the

whole specimen instead of the relatively thin reaction zone of a self-sustaining planar detonation). These conditions tend to speed up all the reactions in the explosive and to give them more time to come to equilibrium. More important, flow in the supracompressed region is subsonic (i.e., the shock front is traveling slower than the speed of sound in the medium), which means that changes within it can catch up with the shock front. (It is the trajectory of the shock front that is measured in the supracompressive experiments.)

A possible "slow" reaction we have considered to account for this 10% difference in C-J pressure for PBX-9404 is the condensation of carbon into the solid state, either graphite or diamond. One way to test this hypothesis experimentally is to compare the results of supracompression experiments with explosives that differ greatly in the amount of carbon they produce. For example, LX-17 produces a much

Fig. 3

Shock velocity vs particle velocity for supracompression experiments with LX-17 explosive. The EOS curve predicts where the data points should lie on the basis of data taken from expansion measurements and a measured C-J pressure of 30 GPa. Experiments in which we used an explosive buffer are designated with blue dots; black dots are for aluminum buffers.

Fig. 4

Shock velocity vs particle velocity for supracompression experiments with PBX-9404 explosive. The solid EOS curve predicts where the data points should lie on the basis of data taken from expansion measurements from self-sustaining planar detonations and a measured C-J pressure of 37 GPa. The dashed EOS curve, which fits the experimental points well, corresponds to an assumed C-J pressure of 34 GPa. Experiments in which we used an explosive buffer are designated with blue dots; black dots are for aluminum buffers.

higher proportion of carbon than does PBX-9404, and PETN produces very little. In supracompression experiments with LX-17 (Fig. 3), the measured shock velocity vs particle velocity data points are even farther from the "normal" EOS (calculated from nonsupracompressive experiments) than are the points for PBX-9404 (Fig. 4).

The existing experimental data on supracompressive states of PETN⁵ (Fig. 5) were gathered in the 1960s with equipment of lower precision than ours; we are planning additional supracompressive experiments on PETN to improve the accuracy of the experimental data base. However, even these old measurements come quite close to the "normal" EOS, in line with our hypothesis about carbon condensation.

A general description of both expansion and supracompressive states of an explosive's detonation products with a single EOS may not be possible if the C-J pressure as normally measured is, in fact, not an equilibrium state. A lack of equilibrium would imply chemical differences between the C-J states defined by the usual methods and those inferred from supracompressive experiments.

Summary
We have measured the high-compression behavior of detonation products to considerably

higher precision than has been achieved previously. We have incorporated this information into our hydrodynamic EOS models, albeit with reservations about the C-J model. In this regard, we now have strong evidence of a conflict between data generated with impactor-driven shock waves and that from self-sustaining detonation shock waves. Almost certainly, we will need to develop more general models for the detonation state. We are currently conducting further experimental and theoretical investigations of the behavior of shock waves and rarefactions in the supracompression region. □

Key Words: carbon condensation; Chapman-Jouguet (C-J) pressure; detonation product; equation of state (EOS); high explosive—HMX, LX-07, LX-17, PBX-9404, PETN, RX-26-AF, TATB; overdriven detonation; supracompression.

Notes and References

1. J. H. Kineke and C. E. West, presented at Fifth Symp. (Intl.) on Detonation, U. S. Naval Ordnance Laboratory, Pasadena, California, Repts. ACR-184 and ONR 0851-0057 (1970).
2. E. L. Lee, H. C. Hornig, and J. W. Kury, *Adiabatic Expansion of High-Explosive Detonation Products*, Lawrence Livermore National Laboratory, Rept. UCRL-50422 (1981).
3. H. C. Hornig *et al.*, presented at Fifth Symp. (Intl.) on Detonation, U. S. Naval Ordnance Laboratory, Pasadena, California, Repts. ACR-184 and ONR 0851-0057 (1970).
4. I. C. Skidmore and S. Hart, "The Equation of State of Detonation Products Behind Overdriven Detonation Waves in Composition B," presented at Fourth Symp. (Intl.) on Detonation, U. S. Naval Ordnance Laboratory, White Oak, Maryland, October 12-15, 1965.
5. J. H. Kineke, Lawrence Livermore National Laboratory, unpublished work (1984).

Fig. 5

A comparison between results from earlier supracompressed detonation experiments on PETN⁵ and a calculated EOS curve. The black data bars indicate uncertainties of one standard deviation above and below the measured data points. In contrast to the situation with respect to PBX-9404, the measured C-J state, the expansion states, and the supracompressed states for PETN are reasonably consistent with the calculated curve as normalized to the density of the PETN used in the experiments.

Modeling Explosive Behavior

We are developing mathematical models, based on the established principles of physics and chemistry, to correlate the vast store of accumulated experimental data on explosive behavior and to suggest fruitful directions for future research.

The goal of our research into the physics and chemistry of high-explosive detonations is to understand their behavior well enough to predict how much energy and momentum they can deliver for practical uses. In these studies, we need both theory and experiment; neither can proceed far without the other. Each experiment tells us facts about a particular set of conditions. Theory tentatively sketches in the gaps between the experimental points, often revealing new physical phenomena and thereby suggesting which experiments to try next.

We started our modeling efforts with simple explosives (nitric oxide, HNB, RX-23-AB) because the concentrations of their detonation products are largely unaffected by changes in temperature and pressure.¹ This simplified the calculations, enabling us to achieve substantial agreement with experimental data and to test specific parts of the model. This success with simple explosives encouraged us to extend our work to more complex explosives such as LX-14, PETN, TNT, and especially PBX-9404, for which there already is a large body of experimental data.

One of the effects that make these complex explosives more difficult to

model is that many of them produce relatively large amounts of nitrogen, water, or solid carbon. At low pressures, solid carbon exists in the forms of graphite; higher pressures transform it into diamond. Polar and nonpolar materials, like water and nitrogen, tend to separate into two phases. However, we can turn this complication into an advantage by comparing results for explosives that produce different amounts of carbon and nitrogen as a means of investigating the phenomena related to carbon condensation and phase changes.

Figure 1 illustrates the differences in composition of the detonation products of four explosives, PETN, HMX, TNT, and TATB. (HMX is the main component of both LX-14 and PBX-9404, the major weapons explosive, and TATB is important to weapons safety because it is relatively insensitive to heat and shock.) TNT and TATB produce large amounts of solid carbon, making them good candidates for investigations into the condensation of carbon during detonation. PETN and HMX produce relatively little condensed carbon, so we can use them to study the equilibrium properties of gaseous² mixtures without much complication

For further information contact
Francis H. Ree (415) 422-7234 or
Mathias Van Thiel (415) 422-7216.

from the effects of carbon condensation. Since HMX has more nitrogen than PETN, these two provide a good vehicle for studying the effects of nitrogen phase separation.

Theory

Gas-gun and detonation experiments using these explosives span thermodynamic states ranging in pressure from 1 to 100 GPa and in temperature from 1000 to 5000 K. Static experiments on mixtures have so far been confined to pressures below 5 GPa and temperatures below 1000 K. Hence, the availability of shock-wave and detonation data provide us with a unique opportunity to study the properties of mixtures under extreme conditions of pressure and temperature using the basic principles of physics and chemistry.

To do this, we must determine the intermolecular potentials, which determine the forces of attraction

and repulsion acting between the molecules (see the box on p. 15), the dynamics of the many possible chemical reactions, and such unusual phenomena as fluid-fluid phase separation. Some of the calculational tools for these tasks are already developed.²

Determining the intermolecular potential is relatively simple in a pure stable gas such as nitrogen or carbon dioxide. Where all the molecules are alike, we can use a single potential to describe how the forces between molecules vary as the molecules are pressed closer together. Potentials for nonpolar molecules (such as nitrogen and carbon dioxide) may be derived from critical constants, and those for polar molecules (such as water) are obtained by matching the experimental data. In these cases, we are able to reach relatively good agreement between calculated Hugoniot for pure, liquefied gases and the experimental data within the temperature range relevant to explosives (≤ 4000 K); see Fig. 2.^{3,4} In a gaseous mixture, the problem becomes more complex because the forces between two identical molecules will be different from the forces between different molecules. We can still manage, however, by finding an "effective" intermolecular potential and then treating the mixture as if it contained only one gas.

In modeling the products of a detonation, the problem becomes formidable because here we have a mixture whose composition varies with time. We have developed and tested a sophisticated computer code, called CHEQ, that solves the equilibrium aspect of this problem by continually checking the composition of a detonating mixture, picking the most stable mixture, and readjusting the effective intermolecular potential accordingly.

The equation of state (EOS) of solid carbon is relatively insensitive to pressure and temperature, in comparison with the EOSs of the gaseous detonation products. Hence, we can use a simple empirical EOS

Fig. 1

Each explosive has its own distinctive detonation-product composition. TNT and TATB produce relatively large amounts of condensed carbon. PETN produces little condensed carbon and much carbon dioxide and water. HMX (the main ingredient of PBX-8404 and other weapons explosives) yields much nitrogen and water and relatively little carbon and carbon dioxide.

(the Murnaghan form) that reliably describes the experimental data, including the phase change from graphite to diamond.

Computer Modeling

Using theoretical tools (the known interatomic potentials for the various gaseous constituents of the explosion products, solid EOSs for graphite and diamond, and the CHEQ code to follow and adjust for the changes in composition with pressure and temperature), we are in a position to compute detonation properties. If we allow properly for all the phenomena taking place, the calculation should match the experimental data closely. Where the calculation fails to match the data, we can run one calculation after another, each with a slightly different set of assumptions, to look for effects that may be causing the discrepancy.

When we tried this process with PETN, using the simplest assumptions (that we are dealing with only two phases, one a gas mixture and the other a solid form of carbon), our calculated C-J point (solid circle, Fig. 3a) was in nearly perfect

Fig. 2

Shock compression experiments with pure liquefied gases provide the basic parameters for our calculations of detonation performance for different explosives. The curves are nonempirical calculations of specific volume as a function of shock pressure (Hugoniot) for nitrogen, water, and carbon dioxide. The data points are drawn from various sources,^{3,4} including experiments with our two-stage light-gas gun. The data point to the left of the nitrogen curve is not in error; rather, it indicates the onset of the dissociative phase transition in nitrogen.

Fig. 3

Shock velocity versus pressure for PETN (a) and PBX-9404 (b) calculated with the CHEQ code compared with experimental results^{5,6} drawn from LLNL work and elsewhere. (BKW and JC23 are two other models.) In (b), the CHEQ result for PETN below 50 GPa is the state of the detonation products consisting of a single gas phase plus solid carbon. Fairly good agreement exists between calculation and data for PETN (a); however, the agreement for PBX-9404 (b) is disappointing.

agreement with existing experimental data on detonation velocity.^{5,6} When we used the same procedure with PBX-9404, even including the effect of carbon condensation, the lack of agreement was striking (Fig. 3b). For example, at the C-J point (the bottom of the curve in Fig. 3b), the theoretical detonation velocity is 9.25 km/s whereas the experimental detonation velocity is 8.78 to 8.80 km/s.

Fluid-Phase Separation

If we compare the experimental data for PETN and PBX-9404, we find that at their respective C-J points, PBX-9404 is cooler than PETN by 560 K but has a higher pressure by 5.4 GPa. This combination of high pressure and low temperature suggested a phenomenon that had not been previously investigated—phase separation of gases. Like oil and water, dense gas mixtures tend to separate even when heated above the critical temperatures of their constituents.

Nitrogen, carbon dioxide, and water make up 95% or more of the gaseous detonation products of PBX-9404 and PETN at their C-J points. Therefore, we decided to investigate the phase behavior of mixtures of these gases.

Calculation predicts that water and nitrogen mixtures can separate into two fluid phases, one rich in nitrogen and the other rich in water. Moreover, such a phase separation is predicted to occur at temperatures and densities relevant to explosive detonation.

Figure 4 is a solubility diagram for a ternary system consisting of nitrogen, water, and carbon dioxide at a pressure and temperature near the theoretical C-J point of PBX-9404 (its composition is indicated by the solid circle). Carbon dioxide tends to make nitrogen more soluble in water, in much the same way that soap makes oil and water more miscible. The area above the curves is the composition range for total solubility. The blue-gray area, which does not include the C-J point, represents the fluid-phase-separation region, if we assume the repulsive cores for the water-nitrogen and water-carbon dioxide mixtures are one-half the sums of the repulsive cores of the individual molecular species of interest.

However, the uncertainties in these values are about 5%. Therefore, extremely small changes in the magnitude of the effective potential of the mixture can have large effects on the solubility boundary. For example, we can expand the fluid-phase-separation region far beyond the C-J point simply by changing the repulsive-core parameter for water-nitrogen mixtures by +3% and that for water-carbon dioxide mixtures by -3.5% (gray). Hence, it is impossible to rule out water-nitrogen phase separation simply because changes well within the uncertainties of the individual interactions can place the C-J point within the phase-separation region.

The next step is to see if this effect can account for the discrepancy between experiment and calculations of PBX-9404 performance. We recalculated the PBX-9404 Hugoniot taking the possibility of phase separation into account. We achieved reasonable agreement with experiment (Fig. 5). This agreement is not absolute proof that fluid-phase separation is the effect responsible for the anomalous results seen in gas-gun experiments with PBX-9404, but it does lend support to that idea, subject to further confirmation.

Our theoretical model can be further tested with double-shock

Fig. 4

Phase diagram for a ternary system consisting of nitrogen, water, and carbon dioxide at 4082 K and 36 GPa that lies close to the theoretical C-J point of PBX-9404 (solid circle).

experiments in which we impact a disk of explosive on one side and place a metal plate or anvil on the other side. If the anvil material is stiffer than the explosive, the first shock is reflected and becomes a higher shock pressure propagating back into the explosive. If the anvil material is softer than the explosive, the first shock is returned as a pressure release wave from the interface. Figure 6 shows the satisfactory agreement between our CHEQ calculations and double-shock experimental data for PBX-9404 obtained with our two-stage light-gas gun.

Condensed Carbon

Explosives such as LX-07, LX-17, and TNT yield relatively large amounts of condensed carbon in their detonation products (Fig. 1). Since the solidification of carbon during detonation can be a slow process, we are currently studying the detonation behavior of several explosives to learn more about the condensed carbon particles formed during detonation.

Diamond is very incompressible whereas graphite is relatively compressible. Hence, it is important to know which form of carbon is present at different temperatures and pressures so we can use the appropriate compressibility in calculating the EOS of the detonation products. (In room-temperature, static-pressure experiments, graphite should transform into diamond at a pressure of about 1.3 GPa.)

One way to study the condensation of carbon by itself, in isolation from the many detonation-product molecules of a real explosive, is by observing the shock dissociation of a hydrocarbon. Shock experiments with the gas gun reach pressures and temperatures similar to those encountered in explosive detonations and, for hydrocarbons like benzene and butene, yield mostly gaseous hydrogen and condensed carbon. Because benzene and butene also form equilibrium product mixtures, we can consider them as prototype

explosives, even though the energy to "explode" the target is supplied externally by the impactor rather than internally by chemical reaction.

Figure 7 compares experimental data for benzene,⁷ both from the literature and from work with our

Fig. 5

Shock velocity vs pressure for PBX-9404, calculated with the CHEQ code and allowing the possibility of a second gas phase plus solid carbon, compared with experimental results^{5,6} drawn from LLNL work and that of others. The agreement between calculation and data is much improved over that shown in Fig. 3b.

Fig. 6

Shock pressure vs particle velocity for PBX-9404, illustrating the results of double-shock experiments. A copper anvil produces a reflected shock wave at a higher pressure (data points above the single-shock curve), a magnesium anvil produces a rarefaction wave (data points below the single-shock curve). The good agreement with the experimental points is a further test of our detonation model.

Fig. 7

Shock compression of benzene is one way to study carbon condensation. Under strong shock, benzene decomposes into hydrogen gas and solid carbon. The curve on the right, calculated assuming no decomposition, fits the data below about 19 GPa. The curve on the left, calculated with decomposition allowed, fits the data at higher pressures.

Fig. 8

Experimental results showing the effect on detonation velocity in three different explosives as a function of initial density (varied by using explosives with different degrees of porosity). The curves were calculated with CHEQ; breaks (indicated by arrows) signify the onset of some kind of phase change. The upper curve illustrates the onset of diamond formation in PETN. (The PETN curve is shifted upward by 1.5 km/s to prevent it from obscuring the RDX curve below.) The middle curve, for the mildly carbon-producing explosive RDX, has two slight breaks, one for the formation of graphite and the other for a nitrogen phase change. The lower pair of curves show two different calculations for TNT, which produces large amounts of condensed carbon. The bottom curve assumes equilibrium conditions, which is unrealistic because the carbon particles are so small. In a preliminary calculation (blue), we simulated the enhanced stability of graphite that nonequilibrium conditions would cause by artificially raising the heat of formation of diamond. We should be able to fit the data even more closely with an appropriate choice of EOS for graphite and formation energy for diamond.

two-stage light-gas gun, with theoretical curves of shock pressure vs relative volume. The curve on the left is the CHEQ result assuming that benzene decomposes into diamond and molecular hydrogen (in equilibrium); the curve on the right was calculated neglecting decomposition. Each curve fits the corresponding portion of the data. The good agreement between theory and experiment above 20 GPa indicates that the shocked hydrocarbon may indeed be dissociated and in equilibrium states.

Another way to investigate the effect of condensed carbon is with experiments in which we relate the detonation velocity in a porous explosive to the explosive's initial density. In Fig. 8, we compare the experimental detonation velocities of three explosives with our calculations. For PETN, which has the smallest amount of carbon, we note a sharp decrease in the slope near the highest density (see arrow). This is the effect of diamond formation from the gas. The middle curve for RDX shows two breaks (arrows). Since there is more carbon in RDX than in PETN, carbon condensation occurs at a lower density and therefore a lower pressure. At low pressure the condensed carbon forms in the graphite phase, whereas at high pressure it forms in the diamond phase. The change in slope near RDX's maximum density is due to the separation of the nitrogen phase from the product gases. Both PETN and RDX show reasonable agreement with experiment.

Only TNT (bottom curves) has enough carbon to produce solid carbon over the entire experimental range of initial densities. If the solid carbon is formed in its equilibrium form, the experimental data should follow the lower curve, which shows a change of slope at low density due to the graphite-to-diamond transformation. Contrary to the equilibrium assumption, however, the change in slope in the experimental data occurs close to the maximum

derivity. This suggests that diamond formation is a nonequilibrium process.

Real detonations occur very rapidly; there is scant time to reach equilibrium. It is quite difficult to calculate nonequilibrium processes, but we can simulate such a situation in an equilibrium calculation by artificially increasing the formation energy for equilibrium diamond to that for imperfect diamond. This raises diamond formation to a higher temperature and pressure. Our preliminary attempt in this direction is shown by the blue TNT curve in Fig. 8, and we should be able to fit the data even more closely by a suitable choice of EOS for graphite and formation energy for diamond.

The data in Fig. 8 can also be plotted as detonation velocity vs density at the peak pressure of the detonation wave. This shows a similar reduction in slope and allows comparison to higher-pressure shock data.^{5,6} Such data indicate that this reduction in density dependence of shock-wave velocity continues to higher pressures. This phenomenon may be associated with diamond formation as well as with the nitrogen phase separation mentioned earlier. At even higher pressures, the variation of shock-wave velocity increases again. Two-stage gas-gun measurements of shock velocity should help elucidate this behavior.

Summary

From our study, we can draw some tentative conclusions and suggestions. First, for explosives (such as PETN) that consist mainly of carbon, hydrogen, nitrogen, and oxygen (CHNO) and are especially rich in oxygen, the approach described here can reliably predict detonation performance. Second, fluid-phase separation of nitrogen and water fractions is, at least, a possible explanation of the discrepancy between calculated and experimental values of the C-J detonation velocity for various explosives, including PBX-9404. We need solubility experiments to explore this possibility.

Third, slow reactions that may be present in detonation-wave experiments with CHNO explosives may influence the C-J pressure more than they do the C-J detonation velocity. Experiments to elucidate this phenomenon should start by investigating the mechanism involved in the condensation of carbon under shock conditions. In this connection, the detonation properties of carbon-rich explosives like TNT and TATB depart sharply from low-carbon explosives such as PBX-9404, LX-14, and PETN. We have just begun to investigate the detonation behavior of high-carbon explosives to determine the role of carbon solidification in shaping their performance. ■

Key Words: benzene; carbon condensation; Chapman-Jouguet (C-J); computer code—CHEQ; explosive composition—carbon, nitrogen; gas-phase separation; high explosive—HMX, LX-14, LX-17, PBX-9404, PETN, RDX, TATB, TNT.

Notes and References

1. "Understanding the Physics of Explosion Products," *Energy and Technology Review* (UCRL-52000-81-9), September 1981, p. 12; see also F. H. Ree, "Postdetonation Behavior of Condensed High Explosives by Modern Methods of Statistical Mechanics," in *Proc. 7th Symp. on Detonation*, J. M. Short, Ed. (Naval Surface Weapons Center, White Oak, Maryland, 1981), Rept. NSWC MP 82-334, p. 646.
2. F. H. Ree, *J. Chem. Phys.* **81**, 1251 (1984).
3. W. J. Nellis and A. C. Mitchell, *J. Chem. Phys.* **73**, 6173 (1980); W. J. Nellis et al., *Phys. Rev. Lett.* **53**, 1661 (1984); S. P. Marsh, *LANL Shock Hugoniot Data* (University of California, Berkeley, 1980), p. 113.
4. V. N. Zubarev and G. S. Telegin, *Sov. Phys. Doklady* **7**, 43 (1964).
5. J. H. Kineke, Jr., and C. E. West, in *Proc. 5th Symp. on Detonation* (Office of Naval Research, Department of the Navy, 1970), Rept. ACR-184, p. 533; J. H. Kineke, Jr., *Shocked States of Seven Overdriven Explosives*, Ballistic Research Laboratories, Rept. DEA-G-106/MTG (1970);
6. L. Green et al., "Supra-Compression of LX-07, PBX-9404, and RX-26-AF and the Equation of State of Detonation Products," in *Proc. 8th Symp. on Detonation*, J. M. Short, Ed. (in press).
7. R. D. Dick, *J. Chem. Phys.* **52**, 6021 (1970); W. J. Nellis et al., *J. Chem. Phys.* **80**, 2784 (1984).

Measuring Equations of State

We have developed the equipment and techniques for measuring shock compressions in both solids and fluids up to pressures of about 500 GPa. The equations of state thus determined improve our understanding of the properties of matter under extreme conditions, information that is applicable to a wide range of disciplines. The resulting equations of state for metals are required to validate theories used in weapon-design calculations. Metals whose equations of state are well known serve as standards in shock-compression experiments with other solid and liquid specimens. Because liquids are much more compressible than metals, they reach much higher temperatures under equivalent shocks and hence exhibit a greater variety of phenomena. Theories that describe their behavior must take into account electronic excitation and molecular vibration, rotation, and dissociation. Shock-compression data on liquids is useful in predicting the performance of explosives and in understanding the composition and dynamics of the giant outer planets of the solar system.

Contact: William J. Nellis (415) 422-7200 or Neil C. Holmes (415) 422-7213.

Gas-Gun Experiments: Advanced Diagnostic Techniques

To obtain ever more stringent tests of our theoretical models, we have developed specialized diagnostic techniques that probe the molecular, electrical, and optical properties of matter at extremes of pressure and temperature. These advanced techniques enable us to monitor other aspects of shock compression besides the equation of state, once our principal concern. Raman spectroscopy enables us to identify chemical species behind the shock front. Emission spectroscopy provides data on the chemical species present in reacting opaque materials. Emission spectroscopy has helped reveal that shock-induced chemical reactions in benzene are more like high-temperature reactions at low pressures than had been thought. Conductivity measurements provide estimates of the insulator-to-metal transition pressures of various substances, which, in turn, may help us understand such recent discoveries as the magnetic field of Uranus. Optical pyrometry yields insight into metallization and dissociation and opens a window on phenomena such as shock cooling that were not previously expected.

Contact: Neil C. Holmes (415) 422-7213, Douglas C. Hamilton (415) 422-7258, or Harry B. Radousky (415) 422-4478.

Novel Materials

Shock-compression techniques are being applied both to continuing studies of the properties and behavior of matter at extreme conditions of temperature and pressure and to the synthesis of novel materials. Shock compression is being used to create unique materials, such as nonequilibrium metastable phases of superconductors, that cannot be made by more traditional, less extreme processes. In addition, unusual materials like silica aerogel are being used to study the properties of expanded states of matter, states that cannot be reached with normal solid, liquid, or gaseous starting specimens.

Contact: William J. Nellis (415) 422-7200, Harry B. Radousky (415) 422-4478, or Neil C. Holmes (415) 422-7213.

Supracompression of High-Explosive Detonation Products

We are using our two-stage light-gas gun to investigate how supracompression by a planar shock wave affects the physics and chemistry of an explosive's detonation products. We find that equations of state based on ordinary detonation experiments consistently underestimate the shock velocity measured in supracompression experiments in certain explosives, especially those whose detonation products include large amounts of carbon, either graphite or diamond. There appears to be a possibility that carbon condensation or some other relatively slow reaction may account for some of the discrepancies between extrapolations of data obtained in self-sustaining planar detonations and our work with supracompressive states.

Contact: LeRoy G. Green (415) 422-6890 or Edward L. Lee (415) 422-1316.

Modeling Explosive Behavior

We have developed mathematical models, based on the established principles of physics and chemistry, that correlate the vast store of accumulated experimental data on explosive behavior and suggest fruitful directions for future research. For carbon-hydrogen-nitrogen-oxygen (CHNO) explosives that are especially rich in oxygen (such as PETN), these models can reliably predict detonation performance. A possible explanation of the discrepancy between calculated and experimental values of the C-J pressure for various explosives, including BX-9404, is fluid-phase separation of nitrogen and water fractions. Experiments are planned to investigate this and other slow reactions, such as carbon condensation, that may influence the detonation properties of carbon-rich explosives like TNT and TATB.

Contact: Francis H. Ree (415) 422-7234 or Mathias Van Thiel (415) 422-7216.

Recent Titles

Articles published in recent issues of *Energy and Technology Review* are grouped below according to their chief sponsors, the Assistant Secretaries of the U.S. Department of Energy. Research funded by other federal agencies is listed under Work for Others.

DEFENSE PROGRAMS

Office of Inertial Fusion

A New Era in Laser Technology (November 1985)
X-Ray Lasing: The Diagnostics (November 1985)
X-Ray Lasing: The Experiments (November 1985)
X-Ray Lasing: Future Directions (November 1985)
X-Ray Lasing: The Novette Laser (November 1985)
X-Ray Lasing: The Targets (November 1985)
X-Ray Lasing: Theory (November 1985)
Optical Coatings by the Sol-Gel Process (October 1985)

Office of Military Application

Dynamic High-Pressure Research with the Two-Stage Light-Gas Gun (March 1986)
Gas-Gun Experiments: Advanced Diagnostic Techniques (March 1986)
Measuring Equations of State (March 1986)
Modeling Explosive Behavior (March 1986)
Novel Materials (March 1986)
Studies of High Explosives (March 1986)
Supracompression of High-Explosive Detonation Products (March 1986)
The Bunker 801 Project (February 1986)
New Laser Amplifier Improves Laser Doppler Interferometry (February 1986)
Integrating Computer-Aided Engineering at LLNL (January 1986)

LABORATORY REVIEWS

Neutron Spectrometry for Dosimetry (February 1986)

SCIENCE REVIEWS

M-2000 Computers, Ancient Skies (October 1985)

WORK FOR OTHERS

Department of Defense

Precision Engineering at LLNL (January 1986)
Generating Radar Images of the Earth with the S-1 Computer (December 1985)
Laser Pantography (December 1985)
Wafer-Scale Integration (December 1985)
Combustion Instabilities in Liquid Propellants (October 1985)

National Institute of Environmental Health Science

Mutagens in Cooked Food (January 1986)