Long-Term Research in Japan: Amorphous Metals, Metal Oxide Varistors, High-Power Semiconductors and Superconducting Generators

April 1985

**Prepared for the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830**

**Pacific Northwest Laboratory
Operated for the U.S. Department of Energy
by Battelle Memorial Institute**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PACIFIC NORTHWEST LABORATORY
operated by
BATTELLE
for the
UNITED STATES DEPARTMENT OF ENERGY
under Contract DE-AC06-76RLO 1830

Printed in the United States of America
Available from
National Technical Information Service
United States Department of Commerce
5285 Port Royal Road
Springfield, Virginia 22161

NTIS Price Codes
Microfiche A01

Printed Copy

Pages	Price Codes
001-025	A02
026-050	A03
051-075	A04
076-100	A05
101-125	A06
126-150	A07
151-175	A08
176-200	A09
201-225	A010
226-250	A011
251-275	A012
276-300	A013

LONG-TERM RESEARCH IN JAPAN: AMORPHOUS
METALS, METAL OXIDE VARISTORS, HIGH-POWER
SEMICONDUCTORS AND SUPERCONDUCTING
GENERATORS

G. J. Hane
M. Yorozu (a)
T. Sogabe (a)
S. Suzuki (a)

April 1985

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

(a) Mitsubishi Research Institute
Tokyo, Japan

SUMMARY AND CONCLUSIONS

In this study, Pacific Northwest Laboratory (PNL) reviewed fundamental research activities of four selected technologies in Japan: amorphous metals, metal oxide varistors, high-power semiconductors, and superconducting generators. These technologies are all very important to the future of electric energy systems.

The review revealed that significant activity is under way in the research of amorphous metals, but that little fundamental work is being pursued on metal oxide varistors and high-power semiconductors. Also, the investigation of long-term research program plans for superconducting generators reveals that activity is at a low level, pending the recommendations of a study currently being conducted through Japan's Central Electric Power Council.

The history of amorphous metals development in Japan has been marked by an emphasis on applied problems. The emphasis on applied problems was led by Professor Tsuyoshi Masumoto, the most prominent figure in amorphous alloy development in Japan. For example, in 1981, a five-year \$7.5 million program was funded by the Research and Development Corporation of Japan to develop production techniques for amorphous metal transformer cores. However, in 1980, the Japanese government had begun an amorphous metals program that emphasized developing insight into the more fundamental properties of amorphous materials. A three-year effort (1980-1982) to explore the basic physics of the material was sponsored by the Ministry of Education. Research from this effort resulted in 735 published papers. These papers address many critical areas of the magnetic behavior of amorphous metals, including the investigation of magnetic saturation, anisotropy, domain wall motion, and the stability of magnetic properties.

Research in Japan is addressing the effects of both the geometrical and chemical structures of amorphous metals on their properties. This work is particularly notable because it accelerated the fundamental work in Japan to international caliber, with several researchers at the international forefront. These researchers include K. Suzuki of Tohoku University for his studies of chemical structure and its effect on stability; K. Fukamichi of

Tohoku University for his study of Invar amorphous alloys; U. Mizutani of Nagoya University for his analyses of the electronic energy spectrum of amorphous alloys; Y. Sakurai for his work in amorphous thin films; M. Takahashi of Nagoya University for his study of anisotropy and the disaccommodation-structural relaxation relationships of amorphous magnetic materials; and F. Fujita of Osaka University for his Mossbauer studies of magnetic properties. Significant work from the Ministry of Education program was well-represented at the 1984 International Conference of Rapidly Quenched Metals, which was held in Europe.

In an effort to coordinate and integrate basic research with applied research, Japan's Ministry of Education and the Science and Technology Agency are jointly sponsoring a series of workshops to identify high-priority problems and approaches to solving those problems. Although the composition of the participants is uncertain, an estimated 35 companies and 20 universities are involved. The first three seminars have been completed and the following topics discussed:

- structural control of amorphous metals (October 1983)
- thermodynamics and dynamics of metal supercooling to the amorphous state (December 1983)
- chemical short-range order and the magnetic thermal stability of amorphous materials (February 1984).

Access to the proceedings of these workshops and the resulting research is limited to those who are participating in the workshops. The only public announcements may be in the form of advanced commercial technologies several years from now.

In contrast to amorphous metals, there is a minimal level of long-term, fundamental research activity in both metal oxide varistor materials and high-power semiconductors. The non-ohmic behavior of metal oxide materials was first noted in a 1971 paper by Michio Matsuoka of Matsushita. Since then, this technology has been developed primarily in the private sector. Consequently, most papers submitted by Japanese researchers tend to reflect a focus on developmental efforts such as compositional studies. Although Japanese researchers

submit a large number of patents in this area, perhaps 40% of worldwide patents in the last 5 years, these patents are compositional variations or alternative varistor or arrestor designs. Although Japan is active in this area, many U.S. researchers feel that Japanese technology is behind U.S. development. No significant analyses of the basic physics of metal oxide properties were uncovered.

High-power semiconductors also have been developed primarily in the private sector in Japan. However, unlike varistors, U.S. researchers noted the significant superiority of technology from Japan. The Electric Power Research Institute (EPRI) is currently testing thyristors and reports that the performance of several of Japan's devices have an order of magnitude better than that of U.S. devices. Because the private sector has been quite successful in developing this technology, the government has not pursued any direct research funding. No significant fundamental research into the basic physics of high-power semiconductors was identified.

Finally, this study investigated Japan's long-term research plans for superconducting generators. Fundamental research related to this technology is being sponsored by Japan's Ministry of Education. In a 7-year effort, which began in 1980, various aspects of the generator are being researched. These research projects include basic testing, analysis of electrical characteristics, finite element modeling, evaluations of shielding systems, and evaluation of a brushless generator with a magnetic flux pump.

Currently, most participants in the development of this technology are awaiting the results of a study being conducted by the Central Electric Power Council. The purpose of that study is to recommend a scheme for phasing this technology into the electric utility system. Hitachi has participated in a preliminary evaluation for the Power Council. Although the results are confidential, it is probably significant that both Hitachi and Toshiba have now initiated plans to build a generator larger than 100 MVA.

In summary, Japanese development and plans for development in the areas of amorphous metals, metal oxide varistors, high-power semiconductors and superconducting generators have shown various blends of government and private sector involvement. In metal oxide varistors and high-power semiconductors,

the private sector has taken the lead in development, with little direct government participation. In amorphous metals and superconducting generators, the government has actively funded and coordinated work with the private sector. It is recommended that the U.S. continue to keep abreast of these developments and consider the benefits of engaging in cooperative research to share in these international advances.

ACKNOWLEDGMENTS

The research staff would like to thank Dr. Paul Lewis and Dr. W. Bradford Ashton for their conceptual guidance and managerial support of this effort. We also thank Dr. Takeshi Egami of the University of Pennsylvania and Dr. Ryuske Hasegawa of Allied Corporation for their technical perspectives of significant research activities in Japan. Finally, we extend our appreciation to our sponsors, John Brogan, Terry Levinson, and Ken Klein of the Office of Energy Systems Research, U.S. Department of Energy, for their support throughout the project.

CONTENTS

SUMMARY AND CONCLUSIONS	iii
ACKNOWLEDGMENTS	vii
1.0 INTRODUCTION	1.1
1.1 BACKGROUND	1.1
1.2 SCOPE AND APPROACH	1.2
1.3 REPORT CONTENTS	1.3
2.0 AMORPHOUS METALS	2.1
2.1 RESEARCH PLAN AND STRUCTURE	2.3
2.1.1 Long-Term Research Program Plan	2.3
2.1.2 Primary Research Centers and Researchers	2.4
2.1.3 Major Sources of Financial Support	2.4
2.2 RESEARCH PROJECT SUMMARIES	2.5
2.2.1 The Special Project for Research on Amorphous Materials - Physics and Technology	2.5
2.2.2 Amorphous Material Committee No. 147 of the Japan Society for the Promotion of Science	2.11
2.2.3 Development of Production Technology of Non- crystalline Metals for Use in Power Transformer Iron Cores	2.12
2.2.4 Development of Guiding and Basic Energy- Conservation Technologies and Energy- Conserving Magnetic Materials	2.13
2.3 KEY TECHNICAL ISSUES	2.13
2.3.1 Magnetism and Structure	2.14
2.3.2 Structure	2.17
2.3.3 Electronic Structure	2.21
2.3.4 Applied Efforts: Magnetic Materials	2.22

3.0	METAL OXIDE VARIABLE RESISTANCE MATERIALS	3.1
3.1	THE RESEARCH PLAN AND STRUCTURE	3.2
3.1.1	The Long-Term Research Program Plans	3.2
3.1.2	Major Research Centers and Researchers	3.3
3.1.3	Major Sources of Financial Support	3.4
3.2	RESEARCH PROJECT SUMMARIES	3.4
3.2.1	UHV Electric Energy Transmission Special Committee, Phase I - CRIEPI	3.4
3.2.2	Development at Mitsubishi Electric	3.5
3.3	KEY TECHNICAL ISSUES	3.6
4.0	HIGH-POWER SEMICONDUCTORS	4.1
4.1	RESEARCH PLAN AND STRUCTURE	4.2
4.1.1	Long-Term Research Program Plan	4.2
4.1.2	Major Research Centers and Primary Researchers	4.2
4.2	RESEARCH PROJECT SUMMARIES	4.3
4.3	KEY TECHNICAL ISSUES	4.3
5.0	SUPERCONDUCTING GENERATORS	5.1
5.1	RESEARCH PLAN AND STRUCTURE	5.1
5.1.1	Long-Term Research Program Plan	5.2
5.1.2	Major Research Centers and Primary Researchers	5.2
5.2	RESEARCH PROJECT SUMMARIES	5.3
5.2.1	The Special Project for Research on Energy	5.3
5.2.2	Feasibility Study for Introduction of Superconducting Generators into Electric Power Systems	5.4
5.3	KEY TECHNICAL ISSUES	5.5
	APPENDIX - LIST OF RESEARCHERS INTERVIEWED	A.1
	REFERENCES	R.1

FIGURES

3.1	Application Development of Zinc Oxide Varistors	3.7
3.2	Technological Progress in Development of Zinc Oxide Varistors	3.8
3.3	Number of New Installations of Zinc Oxide Arresters and Conventional Arresters Since 1975	3.9
4.1	Improvements in GTO Power-Handling Capabilities	4.4
5.1	Current State of Global Superconducting Generator Development	5.6

TABLES

2.1	Examples of Potential Applications of Amorphous Metals	2.2
2.2	Organization of Project Research	2.6
2.3	Publishing Details of Treatises	2.8
5.1	Activities in the Program "Basic Research into the Dynamic Characteristics of Superconducting Synchronous Generators"	5.7

1.0 INTRODUCTION

The development of advanced technologies to support future high-technology industries has been receiving significant attention in Japan. Several technology areas that are expected to contribute to this advancement are those that are related to electrical energy systems. The purpose of this study is to investigate the long-term development of four such technologies in Japan: amorphous metals, metal oxide varistors, high-power semiconductors, and superconducting generators. Specifically, the U.S. Department of Energy (DOE) commissioned Pacific Northwest Laboratory (PNL) to investigate particular aspects of the development of these technologies:

- The evaluation of amorphous metals, metal oxide varistors, and superconducting generators was to focus on research into the basic physics of the behavior of the materials.
- The evaluation of superconducting generators was to focus on the long-term research plans of the Japanese government for this technology.

1.1 BACKGROUND

Electric energy system technologies are a major industry in the U.S., Japan and several European nations. Export sales alone of heavy electrical equipment (turbines, generators, transformers, etc.) were in the billions of dollars in each of the major producing countries (dhr 1982). Exports of these systems to developing countries are anticipated to significantly increase. One major U.S. manufacturer estimates that exports to developing countries will account for 40% of the world market between 1981 and 1995 (General Accounting Office 1983). To maintain a competitive position in that market and in related markets, countries are increasingly pressed to advance the efficiency and reliability of these technologies.

As technology developments in the area of electric energy systems around the world continue to advance, any technological leads that the U.S. once may have had are becoming eroded. As other countries advance technologies and develop advanced research skills, U.S. researchers can increasingly learn from

international research in the same way that the international community has often learned from research in this country. However, while the benefits of such technical information transfer to the U.S. are increasing, the system for monitoring research activities overseas is incomplete and inadequate. This is particularly true in the case of Japan, where the U.S. is handicapped with only sporadic views of Japanese research efforts. By contrast, the Japanese have established an extensive information monitoring system in the U.S. This study was initiated because of this information deficiency.

1.2 SCOPE AND APPROACH

In conducting this investigation, the scope of the effort was carefully limited to address issues most relevant to concerns of the Office of Energy Systems Research in the U.S. Department of Energy. As stated earlier, the focus in the investigation of amorphous metals, metal oxide varistors and high-power semiconductors was on long-term research activities that addressed the basic physics of the materials' behavior. Although notable applied and development activities for these technologies also may be under way, these issues were not considered. Also, the investigations relied only on publicly available information. This was not considered a major constraint because most long-term fundamental research is generally available to the public. In the case of superconducting generators, the primary interest was in the long-term development plans of the Japanese government for this technology. Again, only publicly available information was sought.

To conduct this review of research activities and research plans, a series of interviews was conducted in Japan by researchers at the Mitsubishi Research Institute (MIRI). Researchers who are recognized for their work in each of these areas were identified and interviewed, along with project and program managers. The analysis of fundamental research activities in amorphous metals was aided by the guidance of Dr. Kenji Suzuki of the Tohoku Research Institute for Iron, Steel and Other Metals.

In the U.S., researchers who were familiar with research in Japan were also interviewed for their perceptions of the strength of Japanese efforts. Valuable indepth comments were provided by two U.S. researchers who are exceptionally familiar with activities in Japan: Takeshi Egami of the University of Pennsylvania and Ryuske Hasegawa of Allied Corporation. These interviews were supplemented with a review of English language literature published by researchers from Japan.

1.3 REPORT CONTENTS

This report consists of five chapters and an appendix. Chapters 2.0 through 5.0 include the research plan and structure, research project summaries, and key technical issues of each technology. Chapter 2.0 discusses amorphous metals, Chapter 3.0 metal oxide variable resistance materials, Chapter 4.0 high-power semiconductors, and Chapter 5.0 superconducting generators. The appendix lists the researchers interviewed for this study and their respective institutions.

2.0 AMORPHOUS METALS

The research of "new materials" has become an area of significant activity in Japan since the late 1970s. Both the industry and the government have made significant investments in developing new materials. One of the primary areas is amorphous metals. Unlike conventional materials with crystalline structures, in which the regularity of the atomic arrangement determines the lattice of the structure, amorphous metals are noncrystalline. This noncrystalline structure provides amorphous metals with several striking characteristics. Amorphous metals have a significant resistance to corrosion, are among the strongest metals known, and can be made without a preferred direction of magnetization. This latter characteristic is a key advantage of amorphous metals used as power transformer cores. Such improved isotropic properties can reduce energy losses in transformer cores by more than 60% when compared with the conventional silicon-iron designs.

The amorphous arrangement is created by quenching the molten metal at a very rapid rate - on the order of one million degrees Celsius per second. As a result of this rapid quenching, the atoms do not have time to arrange themselves into an orderly crystalline form, thus creating the amorphous structure.

The industry and government in Japan have recognized the potential advantages of amorphous metals and have been aggressively pursuing development for several applications. Professor Tsuyoshi Masumoto, a key figure in amorphous metals development in Japan, noted in a paper presented at the Fourth International Conference on Rapidly Quenched Metals that a wide spectrum of uses is being explored. Example prospective applications cited by Professor Masumoto are summarized in Table 2.1, along with the unique properties of the amorphous metal being exploited.

The development of amorphous ribbons for transformer cores is a research and development issue that has many barriers to overcome. As mentioned above, during the manufacture of amorphous metals, the metal must be rapidly quenched to achieve the amorphous structure. This rapid quenching induces stresses, which increase unwanted anisotropy. The annealing process to reduce the anisotropy also increases the brittleness of the material, and any mechanical

TABLE 2.1. Examples of Potential Applications of Amorphous Metals (Masumoto 1981)

<u>Amorphous Metal Property</u>	<u>Prospective Application</u>
High magnetostriction	Magnetostrictive transducer Load cell Frost sensor
High magnetostriction and low acoustic loss	Delay line Length measuring device
Soft magnetic properties and low core loss	Power transformer Electric motor Flyback transformer Shock coil Current leakage detector
Soft magnetic properties and rectangular B-H loop	Magnetic amplifier Magnetic phase shifter Magnetic modulator
Soft magnetic properties and high corrosion resistance	Magnetic separator
High permeability	Magnetic recording head (Audio, Digital, Video) Magnetic shielding dc-CT magnetometer Analogue to digital convertor
Temperature dependence of permeability	Thermosensor

deformation also increases anisotropy. Additionally, a significant amount of energy loss occurs from the motion of magnetic domains, and the stability of the soft magnetic properties is not well understood.

Compounding the development problems with amorphous metals is the marked deficiency in the scientific understanding of the structure and atomic behavior of the material. A panel of researchers was convened by the Council on Materials Science of the U.S. DOE in 1980 to discuss major research concerns regarding fundamental amorphous materials research. Research directed toward understanding the atomic and electronic structure was noted to be a critical area of study. In electromagnetic devices, key problem areas in potential applications included research of the following:

- magnetic saturation
- magnetic anisotropy
- magnetic domain wall motion
- magnetic and structural stability.

As research in Japan continues to press the frontiers of the development of this technology, an increasing need evolves to pursue original and innovative ideas. This report examines long-term research addressing the fundamentals of the materials' behavior in such areas.

In this chapter, the research plan and structure for amorphous metal research programs in Japan is discussed, four research projects are summarized, and key technical issues are discussed.

2.1 RESEARCH PLAN AND STRUCTURE

In this section, the long-term research program plans and primary research centers and researchers are listed and the major sources of financial support are briefly discussed.

2.1.1 Long-Term Research Program Plan

The following four long-term research programs to investigate and develop amorphous metals have been undertaken in Japan:

1. The Special Project for Research on Amorphous Materials--Physics and Technology--funded by Ministry of Education scientific research grants
2. Committee No. 147 of the Japan Society for the Promotion of Science (an external organ of the Ministry of Education)
3. Development of Amorphous Metal Production Technology for Use in Power Transformer Iron Cores--a research and development project consigned by the Research Development Corporation of Japan (an external body of the Science and Technology Agency) to Nippon Steel Corporation
4. Development of Guiding and Fundamental Energy-Conservation Technologies and Energy-Conserving Magnetic Materials--part of the Moonlight

Project being advanced by the Ministry of International Trade and Industry's (MITI's) Agency of Industrial Science and Technology.

2.1.2 Primary Research Centers and Researchers

Japan's major researchers in the amorphous metal field are listed below, together with their respective institutions.

Dr. Yoshifumi Sakurai	Professor of Osaka University Department of Engineering
Dr. Tsuyoshi Masumoto Dr. Hiroyasu Fujimori Dr. Kenji Suzuki	Professors of Tohoku University The Research Institute for Iron, Steel and Other Metals
Dr. Kazuaki Fukamichi	Assistant Professor of Tohoku University The Research Institute for Iron, Steel and Other Metals
Dr. Uichiro Mizutani	Assistant Professor of Nagoya University Department of Engineering
Dr. Kenji Narita	Professor of Kyushu University Department of Engineering
Dr. Takahito Kaneyoshi	Assistant of Nagoya University Department of Physics
Dr. Toshikazu Katayama	Researcher of Electrotechnical Laboratory - MITI

2.1.3 Major Sources of Financial Support

Funding for the four research and development programs comes from both government and private sources. The Special Project for Research on Amorphous Materials and MITI's energy conservation project were funded by government grants. Financial assistance for Committee No. 147 comes primarily from the companies belonging to the Japan Society for the Promotion of Science. In the Development of Amorphous Metal Production Technology, the Research and Development Corporation of Japan received a national assistance grant, which was allocated to the Nippon Steel Corporation. Nippon Steel is also channeling funds of its own into the project.

2.2 RESEARCH PROJECT SUMMARIES

Each of the four program plans listed in 2.1.1 is summarized below.

2.2.1 The Special Project for Research on Amorphous Materials - Physics and Technology - Funded by Ministry of Education Scientific Research Grants

This research program was initiated through the active promotion of Japanese universities and research institutes affiliated with the Ministry of Education. The program's cost totaled 611.6 million yen (\$2.72 million). Almost all the chief researchers in amorphous physics in Japanese universities and Ministry of Education research institutes were involved in this effort. The program was under the leadership of Professor Yoshifumi Sakurai of Osaka University and was organized into four working groups: I) Fundamental Physics, II) Amorphous Metals, III) Amorphous Magnetic Materials, and IV) Amorphous Semiconductors. The researchers who were involved in this program are listed in Table 2.2. Table 2.3 lists the number of scientific treatises published (or scheduled to be published) as a result of the research conducted in this program.

A report on the results of the Special Project for Research on Amorphous Materials was published in November 1983. Summaries of the research conducted by the first three research groups, which had the most relevance to this study, are summarized below.

Group I - Fundamental Physics

The research goal of Group I, Fundamental Physics of Amorphous Materials, was to establish a scientific basis for developing amorphous material technologies through experimental and theoretical studies of the atomic structure of amorphous solids.

The research program of Group I was classified into three categories. The first category was high resolution observations of the geometrical and chemical short-range structure of amorphous alloys and semiconductors. To make these observations, experimental techniques such as pulsed neutron scattering,

TABLE 2.2. Organization of Project Research

Administration Board

Project Leaders:	Yoshifumi Sakurai	Osaka University
Members:	Jinichi Takamura	Kyoto University
	Kenji Narita	Kyushu University
	Kenji Suzuki	Tohoku University
	Yoshihiro Hamakawa	Osaka University
	Eiichi Fujita	Osaka University
	Tsuyoshi Masumoto	Tohoku University
	Shinji Ogawa	Electrotechnical Laboratory
	Yoshihiko Mizushima	Nippon Telegraph and Telephone Public Corporation

Group I Fundamental Physics

Group Leader:	Kenji Suzuki	Tohoku University
Members:	Mitsuo Shimoji	Hokkaido University
	Setsuo Kiyono	Tohoku University
	Minoru Takahashi	Tohoku University
	Yukio Onodera	Tohoku University
	Yasuo Yamaguchi	Tohoku University
	Toshihiro Arai	University of Tsukuba
	Masao Doyama	University of Tokyo
	Toshiyuki Ninomiya	University of Tokyo
	Fuminori Fujimoto	University of Tokyo
	Shin Takeuchi	University of Tokyo
	Atsuko Ito	Ochanomizu University
	Uichiro Mizutani	Nagoya University
	Takeo Matsubara	Kyoto University
	Fumiko Yonezawa	Kyoto University (Keio University)
	Kazuo Murase	Osaka University
	Akifumi Onodera	Osaka University
	Hamimu Kawamura	Kwansei-Gakuin University
	Ryosuke Yokota	Technological University of Nagaoka
	Yoichi Ishida	University of Tokyo
	Terutaro Nakamura	University of Tokyo
	Kazuhide Tanaka	Nagoya Institute of Technology
	Hikaru Terauchi	Kwansei-Gakuin University
	Takashi Takahashi	Tohoku University

TABLE 2.2 (contd)

<u>Group II</u>	Amorphous Metals	
Group Leader:	Tsuyoshi Masumoto	Tohoku University
Members:	Hiroshi Kojima	Tohoku University
	Hiroyasu Fujimori	Tohoku University
	Koji Hashimoto	Tohoku University
	Noboru Tsuya	Tohoku University
	Hiroshi Komiyama	University of Tokyo
	Hiromitsu Ino	University of Tokyo
	Hideo Shingu	Kyoto University
	Eiichi Fujita	Osaka University
	Itsuo Ohnaka	Osaka University
	Yoshimi Tanabe	Tokyo Metropolitan University
	Tooru Imura	Nagoya University
	Toshio Hirai	Tohoku University
	Yoji Nakamura	Kyoto University
	Kozo Osamura	Kyoto University
	Jinichi Takamura	Kyoto University
<u>Group III</u>	Amorphous Magnetic Materials	
Group Leader:	Yoshifumi Sakurai	Osaka University
Members:	Shun'ichi Yamanaka	Tokyo Institute of Technology
	Yasuo Gondo	Yokohama National University
	Tadashi Sasaki	Gifu University
	Susumu Uchiyama	Nagoya University
	Morio Masuda	Mie University
	Kimisuke Shirae	Osaka University
	Tetsuzo Kusuda	Hiroshima University
	Kenji Narita	Kyushu University
	Kenji Kawanishi	Nihon University
	Tadashi Mizoguchi	Gakushuin University
	Mitsuo Sugimoto	Saitama University
	Koichi Murakami	Tohoku University
	Koosuke Harada	Kyushu University
	Hiroshi Kobayashi	Waseda University
<u>Group IV</u>	Amorphous Semiconductors	
Group Leader:	Yoshihiro Hamakawa	Osaka University
Members:	Yasuo Nannichi	University of Tsukuba
	Kazuo Morigaki	University of Tokyo
	Shigeru Minomura	University of Tokyo
	Seiji Furukawa	Tokyo Institute of Technology
	Isamu Shimizu	Tokyo Institute of Technology
	Hiroshi Kukimoto	Tokyo Institute of Technology

TABLE 2.2. (contd)

Tatsuo Shimizu	Kanazawa University
Shoji Nitta	Gifu University
Akira Kawabata	Kyoto University
Yoshio Inuishi	Osaka University
Shogo Nakamura	Osaka University
Yukio Osaka	Hiroshima University
Hideomi Ohnishi	Ehime University
Yoshinobu Aoyagi	The Institute of Physical and Chemical Research
Akio Hiraki	Osaka University
Kazunobu Tanaka	Electrotechnical Laboratory
Hiroyuki Matsunami	Kyoto University
Kunio Tada	University of Tokyo

TABLE 2.3. Publishing Details of Treatises

<u>Publications/Periodicals</u>	<u>No. of Treatises</u>
Collection of treatises submitted to international meetings	211
Japanese Journal of Applied Physics	105
Journal of Applied Physics	45
Journal of the Magnetism Society of Japan	35
IEEE Transactions	24
Solid State Communications	23
Journal of Non-Crystalline Solids	17
Science Reports of the Research Institute Tohoku University	15
Solid State Physics	14
Journal of Physics	18
Journal of Materials Science	12
Journal of the Japan Institute of Metals	8
Applied Physics Letters	19
Philosophical Magazine	8
Journal of the Magnetism Society of Japan	8
Physical Review	10
Scripta Metallurgica	10
Nuclear Instruments and Methods	7
Transactions of the Japan Institute of Metals	10
Journal de Physique	4
University Bulletins	8
Journal of Magnetism and Magnetic Materials	11
Oyo Buturi	9
Others	<u>104</u>
Total	745

extended x-ray absorption fine structure, electron microscopy, Raman scattering, infrared absorption and Mössbauer spectroscopy were used. In the second category, computer simulations of the atomic structure of amorphous alloys were developed, with the results closely approaching the realistic behavior of the alloys. In particular, the elementary processes of atomic transport involved in plastic deformation and irradiation effects were examined. Correlations between the atomic arrangement and the electronic state were also simulated in a computer using theoretical models. The third category was the characterization of material properties related directly to the atomic scale structures such as structure relaxation, crystallization, atomic diffusion, electronic transport, electronic state, etc. The behavior of amorphous ceramics under high temperature and high pressure was also investigated.

Based on these experimental and theoretical investigations, it has been concluded that the geometrical and chemical structure of the atomic polyhedral structural units existing in amorphous alloys and semiconductors are totally prescribed by the chemical nature of valence electrons of constituent atoms. However, the mutual connectivity between the atomic polyhedral structural units can be widely controlled in the amorphous structure, even with the current state of processing amorphous materials. This implies that an important key for amorphous material design is the precise characterization and control of the intermediate-range structure as well as the short-range structure in amorphous materials.

Group II - Amorphous Metals

The wide diversity of potential production techniques for amorphous metal alloys can notably affect the characteristics and uses of the material. To examine different approaches to the production of amorphous metal alloys, Group II implemented several experiments on techniques other than the rapid liquid quenching through rotation roll. New experiments were also conducted on the catalytic and anti-corrosion characteristics of amorphous metals. The results have not produced significant new insight to the structure of the material, although they did reveal that the dense random packing theory is insufficient for actual materials.

Group III - Amorphous Magnetic Materials

Recently, two types of amorphous magnetic materials have received much attention. One is the rapidly quenched iron-based alloy amorphous tape and the other is the rare-earth transition metal alloy film. The former has superior mechanical properties and high magnetic permeability, making it very suitable as a soft magnetic material. The latter is a perpendicularly magnetized film with a low compensation (or Curie) temperature, making it useful for magnetic bubble and magneto-optical memory. Both types of amorphous magnetic materials were advanced as a result of this group's research.

In 1960 Duwez showed that rapidly quenched AuSi alloy has an amorphous structure. Gubanov also predicted in 1960 the existence of amorphous magnetic materials, and AuCo was obtained as the earliest amorphous magnetic material. Subsequently, many researchers have pursued the study of amorphous magnetic materials. In 1967 the strongly ferromagnetic amorphous $\text{Fe}_{83}\text{P}_{10}\text{C}$ alloy was developed. In 1969 amorphous alloys were continually cast into filaments. In 1973, CdCo amorphous films were prepared by an r-f sputtering method and studied as a bubble memory material.^(a)

The first result of Group III's research concerned the production of amorphous magnetic powders and the thin band. Because the characteristics of the thin band varied greatly with the production conditions, the relationship between the static and active characteristics and the production conditions for thin bands was investigated. The results of the research into the powder and production of amorphous ferrite were also reported.

The second result of Group III's research primarily concerned experimentation into rare earth and iron alloy amorphous films intended as materials for optical and thermal magnetic memories. Production conditions, composition and other factors having an influence on the magnetic characteristics of the film were tested. Research was conducted into methods for producing uniform wide surface area films and the causes of vertical magnetic anisotropy. Research

(a) Mitsubishi Research Institute. 1984 (Draft). Technical Characteristics of Long-Term Research: Selective Energy Areas in Japan. Mitsubishi Research Institute, Tokyo, Japan.

was also conducted into the structure and magnetism of rare earth and iron alloys, the production of amorphous film by ion injection, and (Co,Fe) (Ta,W,Zr) alloy films.

2.2.2 Amorphous Material Committee No. 147 of the Japan Society for the Promotion of Science

The Japan Society for the Promotion of Science is an external organ of the Ministry of Education. Its function is to inform industry of the results of scientific research. Committee No. 147 was established as a five-year program, beginning in fiscal 1983. Its purpose is to inform industrial circles about the results of the Special Project Research on Amorphous Material, completed in fiscal 1982. Professor Yoshifumi Sakurai of Osaka University was named Chairman of the committee. All of the committee's expenses are covered by the membership dues paid by companies belonging to the Japan Society, and there are no subsidies for the research costs, with travel costs paid for university personnel only. Membership in the committee is reported to total 35 universities and 20 companies. Companies participating in this society must have a proven record of achievements that would allow them to make a substantive contribution to the research of the committee. The results of this research are only available to members of this committee.

The committee meetings have been held since the inception of this program. The themes of the committee meetings are presented below.

First Committee Meeting (October 1983)

- structural control of amorphous metals
- recent advances in amorphous silicon and its application technology

Second Committee Meeting (December 1983)

- the thermodynamics and dynamics of metal supercooling to the amorphous state
- production and application of amorphous soft magnetic thin films
- rare iron alloy amorphous films

Third Committee Meeting (February 1984)

- amorphous silicon film production technology and film quality stability
- chemical short-range order and magnetic thermal stability of amorphous materials.

The first three committee meetings served as an introduction to amorphous materials for the participating companies. Full-scale research activities will be initiated from the fourth meeting.

2.2.3 Development of Production Technology of Noncrystalline Metals for Use in Power Transformer Iron Cores - A Research and Development Project Consigned by the Research Development Corporation of Japan to Nippon Steel Corporation

This project targets the production of a 30 KVA transformer through the use of thin bands 150 mm in width. The project is planned for five years, from 1981 through 1985, with 1.688 billion yen (\$7.5 million) consigned to Nippon Steel from the Research Development Corporation of Japan (RDCJ). Nippon Steel is also investing approximately the same amount of internal funds in this project.

Although this project primarily consists of consigned development from RDCJ to Nippon Steel, Professor T. Masumoto of Tohoku University has been placed in charge of the overall project. As project manager, his responsibilities involve checking and reviewing the research and development process at Nippon Steel. Professor Masumoto will also team up with Professor H. Fujimori, also of Tohoku University, to deliver lectures, guidance and other assistance to Nippon Steel.

The Research Institute for Iron, Steel and Other Metals of Tohoku University, to which Professors Masumoto and Fujimori are attached, is not participating as a member of this research project. Nippon Steel is also working independently in establishing close contact with transformer experts in the university community.

The breakdown of ownership rights of the project's results is as follows: Japan 25%; RDCJ 25%; and Nippon Steel Corporation 50%. However, if the

consigned development does not proceed and/or end successfully, Nippon Steel Corporation is obligated to return the equipment and other items to RDCJ. The patents of Professors Masumoto and Fujimori of Tohoku University are being used to promote this project. Because these two professors are civil servants, their patents are the property of Japan. Therefore, Japan has the right to use these patents as references in pursuing research and development in this field.

To date, no public announcement of the budget, schedule, basic data or other details of this consigned development has been made.

2.2.4 Development of Guiding and Basic Energy-Conservation Technologies and Energy-Conserving Magnetic Materials - Ministry of International Trade and Industry's Agency of Industrial Science and Technology, Moonlight Project

This project is the only long-term project being conducted by the Ministry of International Trade and Industry (MITI) in the amorphous metal field. Initiated in fiscal 1980, the project is scheduled for completion in fiscal 1985, with an annual budget of approximately \$22,200 (5 million yen). Under this project, thermal stability and structural relaxation of amorphous metals are being investigated. The project leader is Dr. Toshikazu Katayama of MITI's Electrotechnical Laboratory's Materials Department, Magnetic Materials Research Section.

2.3 KEY TECHNICAL ISSUES

As mentioned in the previous section, activity in fundamental studies of amorphous materials accelerated after 1980 through the efforts of the Ministry of Education. The research conducted in this program provided useful insight into the fundamental behavior of amorphous alloys and resulted in the development of a significant capability for the fundamental study of magnetism, structure, and electronic structure. This capability is being used in the current efforts of the Japan Society for the Promotion of Science. Some of the more significant fundamental research efforts are described below.

Research that is considered fundamental in the U.S. typically comprises investigations into the microscopic aspects of amorphous alloys. The tools

used by researchers in Japan span the full complement of research tools, including x-ray, neutron, and electron diffraction; small angle x-ray scattering (SAXS); nuclear magnetic resonance (NMR); scanning electron microscopy (SEM); transmission electron microscopy (TEM); Mössbauer spectroscopy; field ion microscopy (FIM); Auger electron spectroscopy (AES); electron spin resonance (ESR); extended x-ray absorption fine structure (EXAFS); soft x-ray emission spectroscopy (SXS); positron annihilation; and gamma-ray Compton scattering. There also are innovative applications of these techniques in laboratory-developed equipment, such as the electron holograph developed at Hitachi. Examples of microscopic investigations of the magnetic properties, atomic scale structure, and electronic properties of amorphous alloys are provided below. Because of the strength of the applied research effort in Japan, significant researchers working in that effort also will be discussed briefly.

2.3.1 Magnetism and Structure

- Spin wave excitation experiments on amorphous ferromagnetic alloys have been performed by researchers in the Departments of Physics and Applied Physics at Tohoku University and the Sendai Radio Technical College. This work is being conducted to explain the difference between the spin wave stiffness constants determined by neutron scattering and Brillouin scattering and the values deduced from magnetization measurement. Neutron scattering is used to study spin dynamics. The triple axis spectrometer at Tohoku University was used in conjunction with a computer-controlled vibrating sample magnetometer. The researchers are currently examining short-range atomic configurations of these alloys to determine the differences that exist between invar and noninvar amorphous alloys. A key researcher in this field has been Y. Ishikawa in the Department of Physics at Tohoku University.
- Researchers in the Departments of Physics at Tohoku University, Morioka College, and the Process Technology Research and Development Laboratory at Nippon Steel have collaborated to investigate the

instability and magnetic relaxation in amorphous ferromagnetic materials. Permeability measurements were made using an automatic disaccommodation measuring device constructed at Nippon Steel. Anisotropy was determined through a high-sensitivity torque magnetometer, and the magnetostriction and saturation magnetization were measured with a three capacitance dialometer.

A key researcher in the study of magnetic after-effect and anisotropy is M. Takahashi in the Applied Physics Department at Tohoku University. Dr. Takahashi is a well-known figure in magnetism and magnetic materials. He has been correlating properties of materials in liquid, amorphous and crystalline solid states. His extensive work shows that amorphous metals are frozen liquids. Recently, he has been involved in disaccommodation-structural relaxation relationship studies of amorphous magnetic metals. Professor Takahashi initiates his research from the perspective of very fundamental physics, and his work is expected to contribute a great deal to understanding the relationship between atomic structure and magnetism in amorphous metals.

Professor T. Mizoguchi at the Gakushuin University is also performing significant work in magnetic after-effect. The most advanced work in the world, however, is being conducted by P. Allia of Torino, Italy; H. Kronmüller of the Max Planck Institute in Stuttgart, Germany; and T. Egami at the University of Pennsylvania.

- Mössbauer spectroscopy is being widely used to examine the structure of amorphous alloys. At Osaka University and the Research Institute of Iron, Steel and Other Metals, researchers have used Mössbauer spectroscopy in combination with x-ray diffractometry to examine the structure and thermal stability of metal-metal alloys. Researchers at the Institute of Industrial Science of the University of Tokyo, the Department of Physics at Ochanomizu University, the Central Research Laboratory of Hitachi, Ltd., and the Electrotechnical

Laboratory at Sakura are investigating characteristics such as the magnetization axis and structural relaxation to determine the short-range order of the alloy.

Key researchers in this area are F. E. Fujita of the Engineering Science Department of Osaka University and A. Ito in the Physics Department at Ochanomizu University. Dr. Fujita has been using Mössbauer techniques in conjunction with electron microscopy and x-ray diffraction. He probes bulk and surface properties using transmission and conversion electron Mössbauer techniques. This probing is very useful in understanding the overall magnetic properties of a material. His work in the area of crystallization behavior of amorphous Fe-B alloys at high pressure is instructive. He claims that he can use Mössbauer techniques to probe local properties related to structural relaxation. In principle, this is possible, but practically very difficult.

Dr. Ito is trying to correlate data of Mössbauer, thermomagnetization, x-ray and electron microscopy measurements in an attempt to clarify relationships between atomic short-range order and magnetism. This is a promising approach, but the impact thus far has been limited.

- Mössbauer spectroscopy is also being used to study the crystallization process in amorphous alloys. Researchers in the Department of Electrical Engineering at Hokkaido University, the Department of Physics at Ochanomizu University, and the Central Research Laboratory of Hitachi, Ltd. are using Mössbauer spectroscopy in conjunction with x-ray diffraction, auger spectroscopy and field ion spectroscopy to observe the crystallization process. Back-scattering Mössbauer is used for surface analysis and transmission. Mössbauer is used for analysis of the interior.

Although the Mössbauer spectroscopy work in Japan is considered significant, the most advanced work is considered to be that performed by C. L. Chien of Johns Hopkins University.

- In-situ observations of magnetic domain behavior in bulk materials have been performed by researchers at the Fundamental Research Laboratory of Nippon Steel and JEOL, Ltd. using a method developed in their laboratories. Noting that Lorentz electron microscopy is limited to thin samples, researchers used a back-scattering mode of a high-voltage electron microscope.
- High-voltage Lorentz electron microscopy is being used at several universities to study the structure of magnetic domain walls. Research laboratories using this microscopy include those at Hiroshima University and at the Department of Applied Physics at Tohoku University.
- Theoretical bases for the magnetic behavior of amorphous materials are being pursued by T. Kaneyoshi of the Physics Department at Nagoya University. Dr. Kaneyoshi uses a molecular field type of approach in his theoretical work and has recently published a book entitled Amorphous Magnetism (1983). Molecular field approximation is crude but appears to be able to describe certain aspects of magnetic behavior of amorphous magnetic metals. As long as one can predict some magnetic properties in a given system, this approximation is useful. In this sense, Dr. Kaneyoshi's work is important.

2.3.2 Structure

- High-resolution observations of chemical and geometrical short-range structure in amorphous alloys by neutron scattering experiments have been carried out by researchers at the Research Institute of Iron, Steel and Other Metals (RIISOM) and the National Laboratory for High Energy Physics at Tsukuba. To perform these experiments, a spallation pulsed neutron source constructed on the 500 MeV proton synchrotron was used. The hydrogen atom environment and motion in hydrogenated amorphous alloys also were identified by neutron total scattering and neutron inelastic scattering.

A key researcher in this area has been K. Suzuki of the RIISOM, Tohoku University. Dr. Suzuki has been conducting chemical short-range order studies by pulsed neutron scattering techniques. This study is related to those of stability of amorphous metals and therefore, is very important from both basic and applied perspectives. Dr. Suzuki combines x-ray, electron and neutron diffraction data to obtain particle atom-atom pair correlation functions for metal-metalloid base and metal-metal base amorphous metals, including hydrogenated alloys. Especially noted in the latter materials is the finding that hydrogen atoms selectively occupy the tetrahedral holes surrounded predominantly by Ti atoms in amorphous Ni-Ti systems.

In related research, Y. Waseda of the Research Institute for Mineral Pressing and Metallurgy, Tohoku University, has been using anomalous x-ray scattering to obtain partial radial distribution functions. Taking advantage of synchrotron radiation, one can tune to the absorption edges of the atomic species of interest. Waseda did this type of work using Cornell's CHESS facility and is currently constructing a similar instrument at his laboratory. Both Professors Suzuki and Waseda are two leading experimentalists in the structural studies of amorphous metals in Japan and are expected to contribute significantly to the understanding of amorphous metal structure.

Currently, two accelerators in Japan can provide pulsed neutrons for scattering experiments with amorphous alloys. One is the 300 MeV electron LINAC at Tohoku University, which was installed in the early 1970s, and the other is a 500 MeV proton booster synchrotron at the National Laboratory for High Energy Physics at Tsukuba, which began operation in 1980.

- High-resolution electron microscopes are being used at several laboratories to investigate the structure of amorphous alloys. At the Department of Material Physics at Osaka University, TEM is used to more specifically characterize crystallization. Researchers at the National Institute for Metals in Tokyo, the Institute for Industrial Science at the University of Tokyo, and the Research Institute for

Scientific Measurement at Tohoku University are also looking at changes in the structure during crystallization and aging.

Y. Ishida of the Institute of Industrial Science, Tokyo University, uses high-resolution electron microscopy techniques to obtain lattice imaging leading to three-dimensional information for the structure. This is in contrast to the one-dimensional information obtained through conventional RDF studies using diffraction techniques. It is expected that structural relaxation, local inhomogeneities and effects of annealing can be monitored by the present method. However, this is not expected to be a significant challenge. T. Imura and M. Doi, both from Nagoya University, are planning similar studies.

- Field ion microscopy, in-situ high-voltage electron microscopy, high-resolution transmission microscopy, and analytical electron microscopy (STEM x-ray microanalysis) are used in combination with x-ray and electron diffraction to observe the structure and thermal stability of amorphous alloys by researchers in the Department of Metallurgy at Nagoya University.
- Field ion microscopy is also being used in the Department of Metallurgy and Material Science at the University of Tokyo to investigate the arrangement of individual atoms and changes in the structure and properties when annealing is performed at different temperatures.
- Muon spin relaxation is being used by researchers in the Departments of Metallurgy and Material Science, and Physics at the University of Tokyo and at the RIISOM to investigate the atomic structure of the alloys. Positive muon is a radioactive magnetic probe whose diffusional motion, like that of positrons, is very sensitive to the existence of trapping sites and lattice strains. From the observed precession frequency and the relaxation function of muon spin, one can obtain useful information about lattice defects, the diffusion of light-weight interstitial atoms and internal magnetic fields.

- Positron annihilation is also being used by researchers in the Departments of Metallurgy and Material Science, and Physics at the University of Tokyo to study the annealing behavior of amorphous alloys.

M. Doyama of Tokyo University has been conducting structural studies by using computer simulation, positron annihilation and field ion microscopy. In the simulation studies, he has been introducing quenching, deformation and radiation damage effects. He also has obtained phonon dispersion curves for amorphous solids. These types of studies become meaningful only after quantitative agreement is achieved between experiment and simulation. Additional research is needed to achieve this agreement.

- Small angle x-ray scattering (SAXS) is being used by the Department of Metallurgy at the University of Kyoto to investigate the long-range structure of various amorphous alloys. Initial experiments involved the observation of changes during isothermal aging. Researchers note that the other techniques typically used to investigate long-range order, transmission electron microscopy, and field ion microscopy are not quantitative enough to clarify the structure.
- X-ray photoelectron spectroscopy is being used at the RIISOM to measure changes in the passive layer. These experiments are being conducted with particular attention to effects upon corrosion.
- Extended x-ray absorption fine structure (EXAFS) is used by several research groups in the Department of Physics at Kwansei-Gakuin University, the Institute of Solid State Physics at the University of Tokyo and the RIISOM at Tohoku University to investigate the characteristic variations in the chemical short-range structure of iron-based metal-metalloid and metal-metal amorphous alloys due to the structure relaxation and different preparation processes.
- Researchers in Japan have also developed a number of theories and models concerning the behavior and structure of amorphous alloys. Much of this work has occurred at the University of Tokyo where

models have been developed of three-dimensional deformation, atomistic deformation, dislocation, polyhedron analysis, cavity analysis, and random packing.

- Computer simulations have been intensively performed to study the static and dynamic microscopic structure in amorphous metals, including the formation of realistic structure models, irradiation damage, elastic and plastic deformation, supercooled liquid-to-glass transition, atomic vibration energy spectrum and electronic energy density of states. Central activities of these computer simulation studies have been conducted in the Department of Metallurgy and Materials Science and Institute for Solid State at the University of Tokyo and in the Department of Physics at Keio University.

2.3.3 Electronic Structure

- Electronic transport properties, low-temperature specific heat, and electronic energy spectrum for metal-metalloid and metal-metal amorphous alloys, as well as for hydrogenated amorphous alloys, consisting of simple metals, transition metals and rare earth metals are being measured by researchers in the Department of Applied Physics at Nagoya University, the Department of Metallurgical Engineering at Nagoya Institute of Technology, and the Institute of Materials Science at the University of Tsukuba. Key researchers include U. Mizutani, K. Tanaka, and T. Fujiwara.

U. Mizutani of the Applied Physics Department at Nagoya University uses specific heat to study electronic structure and phonon properties of amorphous metals. The results of this study are very useful in interpreting magnetic properties of these materials. Professor Mizutani was trained by Ted Massalski of Carnegie Mellon University. Because he covers a wide area of amorphous materials, he is expected to contribute significantly to this field.

K. Tanaka of the Nagoya Institute of Technology is one of the few researchers who uses soft x-ray spectroscopy in any material. He has been studying selected amorphous metals using this technique and is

quite successful. From this study, one can get some information of partial density of states which suggests bonding characteristics between transition metal and metalloid in such systems as Fe-B and Fe-P. The results are also supplemental to those taken through XPS and UPS.

Some of the most significant work in this area is being conducted by T. Fujiwara of the University of Tokyo, Department of Applied Physics. He has been applying the linear-muffin-tin-orbital method in the atomic sphere approximation to selected amorphous metals such as Fe-B and Fe-P. The results agree quite well with the experimental data taken through XPS and UPS.

2.3.4 Applied Efforts: Magnetic Materials

Although significant activity is seen to be under way in the fundamental investigation of amorphous materials in Japan, the strength of Japanese research is in the applied research. Composition studies and production techniques have been of particular note. Various laboratories are experimenting with different compositions of metals and metalloids to obtain alloys with differing characteristics. For example, researchers are experimenting with various compositions of Co, Fe, Si, B, Mn, Cr, Zr, and other metals and metalloids to develop stable amorphous alloys with good soft magnetic properties. A few of the significant actors are described below.

H. Fujimori of the RIISOM, Tohoku University, has been involved in developing various amorphous magnetic alloys. He has generated a number of useful data of compositional dependence of magnetization, Curie temperature, magnetic anisotropy, etc., and also some technological properties such as B-H behavior. He has recently initiated study of sputtered amorphous metals such as Co-M (M=Y, Zr, Hf, Ti, Nb, Mo, W, Si, B, etc.). Based on his past record, Professor Fujimori is expected to generate useful data describing the properties of these materials. K. Fukamichi and N. Kazama in this group are active in the area of characterization of amorphous metals.

T. Masumoto of the RIISOM, Tohoku University, has been active in producing a number of amorphous metals that have been distributed to many researchers in

different disciplines, including those in magnetism and magnetic materials. He is considered to be one of the premier figures in amorphous metals research in Japan and is often credited with spurring the development of this technology in Japan. K. Narita of the Faculty of Engineering, Kyushu University, has been producing amorphous metal powder by spark erosion techniques. The powder size is less than about 30 μm and its shape is spherical.

I. Ohnaka of the Department of Metallurgical Engineering, Osaka University, is investigating methods of producing amorphous metal wires by ejecting the melt into water and liquid sodium. Ohnaka's and Narita's efforts to produce amorphous metals in forms other than ribbons are important technological developments.

In the area of amorphous metal thin films, several researchers are involved in film preparation by electro-deposition and sputtering. These films have potential for use in memory and display devices. Several noted investigators in this area include Y. Sakurai (Engineering Science Department, Osaka University), S. Uchiyama (Electrical Engineering Department, Nagoya University), T. Kusuda (Hiroshima University-Department Electronics), S. Yamanaka (Faculty of Engineering, Tokyo Institute of Technology) and T. Watanabe (Tokyo Metropolitan University), who has been studying electroplated Ni-B and Co-B films and is trying to extend the method to produce bulk materials.

From the limited number of examples above, it is evident that there is a strong interest in both the short-term and long-term development of amorphous alloys in Japan. The center of activity clearly appears to be the Research Institute of Iron, Steel, and Other Metals (RIISOM) at Tohoku University. This is the residence of Japan's most well-known amorphous metal researchers, Drs. T. Masumoto, K. Suzuki, and Y. Fujimori. However, the breadth of the effort also appears substantial with active fundamental research under way at the Universities of Tokyo, Osaka, Kyushu, Nagoya, Hiroshima, and Hokkaido. While industrial organizations such as Nippon Steel and Hitachi are most active in the development of amorphous products, fundamental research is also under way.

Although the interaction between university and industrial research has often been criticized as being very poor in Japan, activity observed in the amorphous metal's field indicates that such interaction is occurring and is

being encouraged by the government. Japanese research in this field is seen to be pressing at the frontiers of the technology. When combined with the trend toward better university-industry collaboration, the development and commercialization of this technology is only likely to become more effective in the future.

3.0 METAL OXIDE VARIABLE RESISTANCE MATERIALS

Varistors are variable resistance devices that are used in electrical systems for the control of voltage surges. These devices are electrically insulating up to a certain field strength, above which they become conducting. In a perfect varistor, once the field reaches this threshold value, the current would vary infinitely with small increases in the applied field. This non-ohmic behavior of varistors makes them well suited as means of overvoltage control in applications ranging from consumer electronics to surge arresters on high-power transmission lines. One category of material having particularly good non-ohmic properties is metal oxides.

The landmark paper in metal oxide varistor development was composed by Michio Matsuoka of Matsushita in 1971. In that paper he described the non-ohmic properties of zinc oxides. Matsuoka noted that the cause of this striking non-ohmic behavior is the resistance due to segregation layers which formed at the grain boundaries of the metal oxide material (Matsuoka 1971).

Although a significant amount of work has occurred in the development of metal oxide varistors since Matsuoka's paper, the work has focused primarily on compositional studies, processing techniques, and alternative varistor designs. Significant questions concerning fundamental aspects of varistor behavior still remain. For example, the physical processes that result in the non-ohmic behavior of metal oxides are still a mystery. Also, the role of small amounts of additives, which can significantly enhance varistor properties, is not understood.

Interviews with researchers in the U.S. have revealed the perception that most of the work conducted in Japan involves near-term projects such as compositional studies and arrester design. The researchers contacted include H. Phillip and L. Levinson of General Electric, G. Pike of Sandia National Laboratory, R. Lauf and E. Sonders of Oak Ridge National Laboratory, V. Tahiliani of the Electric Power Research Institute, and R. Perkins of Brown, Boveri and CIE. It was noted that little has been published by Japanese researchers, which indicates that efforts to pursue the fundamental characteristics of varistor behavior are lacking. Researchers also noted that it

is believed that U.S. development in this technology is more advanced than the efforts in Japan. This latter issue is explored in the following evaluation of selected metal oxide varistor research activities in Japan.

This chapter includes a discussion of the research plan and structure for metal oxide variable resistance materials, summaries of three research projects, and a discussion of key technical issues.

3.1 THE RESEARCH PLAN AND STRUCTURE

In this section the long-term research program plans, major research centers, and major sources of financial support for metal oxide research are briefly discussed.

3.1.1 The Long-Term Research Program Plans

Metal oxide variable resistance materials for electric energy systems consist of arresters that are now widely used under various names. These names include ZNR (zinc oxide nonlinear resistor--Matsushita Electric Industrial Co., Ltd.), MOA (metal oxide arresters--Mitsubishi Electric Corporation), and ZLA (zinc oxide lightning arresters).

Generally, research in this field in Japan can be divided into two categories: 1) research that is continued by manufacturers after commercialization to pursue more compact size, enhanced reliability and improved performance; and 2) research that addresses the feasibility of arresters for use in UHV transmission as well as other efforts aimed at expanding spheres of application. The following research projects that address metal oxide varistors will be reviewed in the next section:

1. UHV Electric Energy Transmission Special Committee, Phase I, Phase II--the Central Research Institute of Electric Power Industry (CRIEPI).
2. Research Directed Toward a 125 kV Arrester--Mitsubishi Electric and The Kansai Electric Power Co., Inc.
3. 500 kV-Class AC/DC Conversion Station Using a Dead Tank Type Arrester--Mitsubishi Electric.

Although significantly more activity is under way in the private sector, the information is not yet publicly available.

In addition to the research projects listed above, a Zinc Oxide Arrester Expert Committee has been established within the Institute of Electrical Engineers' Switching Protection Device Technology Committee. However, this expert committee is currently just an informal gathering of fellow researchers.

The Japanese Electrotechnical Committee contains an Arrester Standards Committee, which prepares new arrester standards in response to the anticipated wide proliferation of zinc oxide arresters. A preliminary proposal from Japan for arrester standards was submitted to the International Electrotechnical Committee, but adjustments have yet to be completed due to the lack of development in this field by the United States and Europe.

3.1.2 Major Research Centers and Researchers

In addition to the areas just mentioned, Meidensha Electric and other makers maintain their own independent research institutes, working on projects that range from materials development to trial production experiments. Another facility making a substantial contribution to this field is the Takeyama Testing and Research Center of CRIEPI.

Leading Japanese researchers in this field are as follows:

Dr. Michio Matsuoka	Matsushita Electronic Components Co., Ltd.
Dr. Tohei Nitta	Mitsubishi Electric Co., Itami Works Switching
Jun Ozawa	Hitachi, Ltd., Hitachi Research Laboratory
Dr. Yoshihiro Kawaguchi	Toshiba, Hama Kawasaki Factory
Dr. Misao Kobayashi	Meidensha Electric Manufacturing Co., Ltd.
Y. Ichida	The Tokyo Electric Power Co., Inc.
T. Tanabe	The Kansai Electric Power Co., Inc.
Dr. Yuzo Ozaki	Takeyama Testing and Research Center of CRIEPI

3.1.3 Major Sources of Financial Support

Of the long-term research programs listed in Section 3.1, only the UHV Electric Energy Transmission Special Committee is funded through the CRIEPI budget. The Ministry of International Trade and Industry is providing a subsidy of \$800,000 (180 million yen) to larger-scale research projects that incorporate the theme reflected in the other two projects.

3.2 RESEARCH PROJECT SUMMARIES

Each of the three projects listed in Section 3.1 is briefly summarized below.

3.2.1 UHV Electric Energy Transmission Special Committee, Phase I - CRIEPI.

This project targeted studies of the technological feasibility of using AC 100 KVA capacity arresters in the future "UHV transmission age." The following areas were included in the studies:

- transformer characteristics
- materials development
- resistor stability.

This was a three-year project conducted between April 1980 and March 1982. No funding was contributed by either the government or the electric utilities. Costs were borne independently by electric and heavy electric machinery makers participating in the special committee.

The committee members included Mitsubishi Electric, Meidensha Electric, Hitachi, Ltd. and Toshiba Corporation. Dr. N. Yamada, formerly professor at the University of Tokyo and currently professor at Tokyo Electrical Engineering College and visiting researcher at CRIEPI, served as the committee chairman. The ownership rights to the results are to be divided among the participating electric power companies and CRIEPI.

Because UHV transmission is not a development that can be put to practical use immediately, studies on AC 1.1-million KVA arresters focused more closely on technological feasibility than on cost. The cost of arresters represents only a small portion of an overall UHV transmission system. For example, even if superb arresters were developed, they would only have a minimal effect on

lowering total system cost. From the perspective of the user (the electric power companies), it is more desirable that all makers attain equal technical levels to maintain system stability and reliability.

With 500,000-KVA transmission having reached the application stage in Japan, manufacturers are now hoping that the research into the 1.1-million KVA arrester will exert a positive technological impact upon the 500,000-KVA arresters.

Following this effort, the "Phase II" plan was initiated in October 1982, targeting the use of DC transmission arresters. Phase II is scheduled to run through March 1985. This project is concerned primarily with laboratory-level material research and paper studies, and does not target actual commercialization. Results of both phases of the study will be published in March 1985.

3.2.2 Development at Mitsubishi Electric

Mitsubishi Electric is involved in two programs, which are described below.

Joint Research with the Kansai Electric Power Company

Mitsubishi Electric has been involved in joint DC arrester research with the Kansai Electric Power Company since 1980. The project goals are the manufacture of a prototype and enhanced understanding of the characteristics of DC arresters.

Development of 500,000 KVA AC/DC Conversion Station Arresters

This project is scheduled to last three years, from April 1982 through March 1985. In April 1984 a full-scale model was manufactured for prototype testing. This study represents one phase of a larger project, and thus, the budget for arrester development alone is unclear. The Ministry of International Trade and Industry has supplied an \$800,000 (180 million yen) grant to help fund the overall project.

According to the project plan and goals, Mitsubishi Electric will receive substantial ownership rights. All returns from the patents and the technologies developed will belong to Mitsubishi Electric. However, if the resulting

technology leads to products that are commercialized and marketed, after five years Mitsubishi Electric must return government funds, using a predetermined rate.

The material research phase of this project has been completed, and the only potential barrier is whether manufacturers will be able to maintain a favorable production yield.

3.3 KEY TECHNICAL ISSUES

In 1968 Matsushita Electric added tiny amounts of Bi_2O_3 , CoO , MnO , and Sb_2O_3 to ZnO , well known for some time as a semiconductor particle, and announced an improved nonlinear resistor element. This element not only possessed good non-ohmic V-I characteristics, it also used the particle field phenomenon particular to ceramics to achieve different levels of varistor control by varying the particle thickness and type of additive. This element was originally used primarily as a linear deflection circuit transistor protector and as other components in 100-400 V color televisions. However, in 1972 Matsushita developed a special zinc oxide surge absorber with improved surge characteristics. This marked the long-awaited debut of zinc oxide arresters for electric power use. Figures 3.1 and 3.2 show the progress of the development and technical changes of zinc oxide arresters.

Matsushita Electric has exclusive rights to the basic patent on the zinc oxide element, licensing out its use to 11 companies in Japan and overseas. These companies and the date they licensed use of the patent are as follows:

- General Electric (U.S., January 1971)
- Meidensha Electric (Japan, December 1972)
- Westinghouse (U.S., July 1976)
- Mitsubishi Electric (Japan, December 1976)
- Asea AB (Sweden, July 1977)
- Ohio Brass Co. (U.S., August 1977)
- Hitachi, Ltd. (Japan, February 1978)
- Toshiba Corporation (Japan, January 1979)
- Ishizuka Electronics Co., Ltd. (Japan, August 1979)

FIGURE 3.1. Application Development of Zinc Oxide Varistors

- Brown, Boveri, & Co., Ltd. (Switzerland, March 1980)
- Siemens (West Germany, August 1980).

Since the initial development of zinc oxide varistors, these varistors have been put to a broad range of uses, varying in scale from 3.3 to 500 KV.

Figure 3.3 shows the state of new installations of zinc oxide arresters and the conventional arrester. The use of zinc oxide arresters has expanded to account for 80% of all new installations in fiscal 1981. Currently, almost all newly installed arresters are of the zinc oxide variety, and the conventional arresters are being replaced with the zinc oxide types.

In recent years, with improvements in the characteristics and performance of zinc oxide elements, prospects are promising for developing 1000 KV UHV zinc oxide arresters, which would provide greatly enhanced protection performance. This higher-power technology is primarily being developed in the private sector.

FIGURE 3.2. Technological Progress in Development of Zinc Oxide Varistors

Research directed towards expanding the life span and improving the energy endurance of zinc oxide elements is being advanced through a) improving zinc oxide element production technology and b) searching for optimal materials composition. The former approach has produced particularly promising results, with the formation of stable particle fields including partial BiO_3 , in which the cooling speed is controlled. This is reported to make a significant contribution to extending service life span. Unification of boundary layers has also been achieved, increasing prospects of improving energy endurance.

Efforts are also under way to attain high levels of performance in zinc oxide arresters by reducing the nominal discharge current.

FIGURE 3.3. Number of New Installations of Zinc Oxide Arresters and Conventional Arresters Since 1975

Figure 2.2. Number of New Installations of Zinc Oxide Arresters and Conventional Arresters Since 1975

4.0 HIGH-POWER SEMICONDUCTORS (EMPHASIS ON GATE TURN-OFF)

High-power semiconductors have experienced rapid development over the past decade and are being used increasingly as switching devices in power conditioning equipment. The most widely used technology for high-power switching (greater than 50 kW) is the silicon controlled rectifier (SCR), which belongs to a family of devices known as thyristors. Although widely used, the SCR is difficult to turn off and is slow in switching between its on and off states. Consequently, in DC circuitry, the use of SCRs is complicated by the need for additional commutating components (either capacitors or inductors). The need for turn-off control resulted in the development of a device known as the "gate-turn-off thyristor" (GTO). This device turns off with a negative pulse.

Although GTOs are available from U.S. and European manufacturers, their power-handling capability has only been a little better than that of conventional transistors. However, recent announcements by Japanese manufacturers have indicated that they have developed technologies with power-handling capabilities that are an order of magnitude greater than any devices made in the U.S. In the U.S., the Electric Power Research Institute is currently testing several of these thyristors to verify the manufacturers' claims.

Researchers in the high-power semiconductor field have strongly indicated that Japanese commercial technology is clearly ahead of U.S. competition. These researchers include M. Schlecht at MIT, Fred Lee at the Virginia Polytechnic Institute, Richard Hoft at the University of Missouri, Atsuo Kawamura of the University of Missouri, and Hans Becke at the Bell Laboratories. M. Schlecht noted that at the 1984 IEEE Power Electronics Conference, 40% of the papers were from researchers in Japan. This group of U.S. researchers also noted that most of the development in this technology in Japan has been performed in the private sector, with little direct government activity.

Because electric trains are extensively used for mass transit in Japan, high-power semiconductors have major DC applications. In this chapter, the apparent level of activity in the fundamental research of high-power

semiconductors is evaluated. Information on research plans and structure, research project summaries and key technical issues for the high-power semiconductors is included.

4.1 RESEARCH PLAN AND STRUCTURE

This section discusses the long-term research plans and major research centers and researchers in the field of high-power semiconductors.

4.1.1 Long-Term Research Program Plan

High-power semiconductors are a sector in which Japan's heavy electric machinery makers have a significant technological lead over their overseas counterparts. Similar to metal oxide variable resistance materials, there is little if any margin for active participation in this field by university or national research institutes. The heavy electric manufacturers have a commanding grip on the entire range of research in this area, from materials development through commercialization. Currently, there is no GTO research program plan being conducted by the government or any consortium of heavy electric machinery makers or electric power companies. The only comparable effort consists of the Rectifier Expert Committee established within the Institute of Electrical Engineers in Japan in 1980. This committee seeks to examine the rapid trend toward improved characteristics and larger capacity in GTO and other self arc-suppressing elements. It is a three-year research study of the application of bipolar power transistors, power metal oxide semiconductor field effects transistors (MOSFETs), GTOs, gate auxiliary turn-off thyristors and electrostatic inductions.

Research program plans by manufacturers include the research into "The Move Toward Photo-Triggers in Super High Voltage Thyristors," a joint project being advanced by Toshiba and Hitachi. However, no outline of this project is available.

4.1.2 Major Research Centers and Primary Researchers

The primary research centers in this field are those attached to Japan's heavy electric machinery manufacturers. Primary researchers in the field are also attached to these manufacturers and include the following:

Hiromichi Ohashi	Toshiba Corporation Toshiba Research and Development Center
Tatsuo Miyajima	Mitsubishi Electric Corporation Kita-Itami Works
Osamu Hashimoto	Fuji Electric Company Semiconductor Research Institute
Satoshi Ishibashi	Meidensha Electric Manufacturing Company Research and Development Department

4.2 RESEARCH PROJECT SUMMARIES

No government funded research projects were identified.

4.3 KEY TECHNICAL ISSUES

Because GTOs do not require communication circuits, they can significantly contribute to reduced size, weight, and noise and to increased efficiency. GTOs have become extensively used for applications such as uninterruptible power supply and electronic power equipment for rolling stock. However, to more fully exploit the merits of these electric power convertors, GTOs with higher power ratings were needed.

Figure 4.1 shows the progress that has been made in increasing the electric capacity of GTO elements and their typical applications. The rating, which was set at 600 V/200 A originally, has been increased to 4500 V/2500 A today (Figure 4.1). Typical applications of GTOs are found in a variety of areas, including controllers for general industrial use, uninterruptible power supplies, and controllers for rolling stock. The operating power capacity that was around 50-60 KVA when first commercialized has been increased to over 1000 KVA today. Along with these improvements, researchers have been successful in improving the turn-off performance and the effect of the snubber circuits.

As noted above, progress in this field has been almost exclusively the territory of the manufacturers. Consequently, future research themes, approaches being used to reach solutions, or specific technological barriers

FIGURE 4.1. Improvements in GTO Power-Handling Capabilities

could not be directly obtained. However, some general information on current and future GTO research themes and new application fields is available:

GTO Research Issues

- production technology, focus on improved yield
- development of materials that are lightweight and offer excellent heat dispersion
- easy gate driving
- low power loss
- high-frequency operation
- safe operating area improvement

Future Application Areas Targeted for Research

- power converters for new energy sources (solar batteries, fuel batteries, MHD)
- self-commutated rectifier with low reactive control
- solid-state circuit breaker.

Japanese researchers dominated the GTO section of the International Power Electrical Conference held in 1983. It has also been learned from Japanese manufacturers that European companies are actively surveying Japanese activities in the GTO field. Moreover, many requests have been received from European and U.S. companies for GTO devices from Japanese manufacturers.

5.0 SUPERCONDUCTING GENERATORS

Superconducting generators are being developed in the U.S., Japan, Germany, France, Italy, and the Soviet Union for their potential to improve the efficiency and cost of electric power generation. Superconducting generators are estimated to be up to 40% smaller and 1% more efficient than other machines of similar power. As a result, it has also been estimated that installing and operating a 1000 MW superconducting generator is likely to cost 30% to 50% less than its conventional counterparts (Kirtley 1983). Cost and performance have improved because of the supercooled condition under which these generators operate. The dissipation of electricity is reduced because of the conductor's lack of resistivity.

Japanese interest in superconducting generators accelerated in the mid-1970s when the Ministry of International Trade and Industry (MITI) funded the Mitsubishi Electric Corporation and Fuji Electric to jointly develop a 6 MVA generator. This was followed by the subsequent development of a 30 MVA generator with private funds. Hitachi followed suit and began developing a 50 MVA generator with its internal funds, and Toshiba followed with experiments on a 1 MW generator.

Although the Japanese government has not invested a large amount of direct funding toward developing this technology, Japanese development is considered to be at the forefront of the technology. A recent interview with a well-known U.S. researcher in this field, who visited Japanese firms in late 1983, revealed the perception that their technology development is more advanced than that of the U.S.

This chapter explores the status of long-term plans for the development of this technology and includes information on the research plan and structure, research project summaries, and key technical issues for superconducting generators.

5.1 RESEARCH PLAN AND STRUCTURE

This section discusses the long-term plan and structure and major research centers and researchers in this field.

5.1.1 Long-Term Research Program Plan

Superconducting generators resemble amorphous metals in that manufacturers are aggressively advancing research and development, aided by some government participation. Hitachi, Ltd., for example, has already completed independent development of a 50 MVA rotor and stator and is currently advancing research into superconducting generators over 100 MVA in capacity. Toshiba Corporation, meanwhile, has reactivated its superconducting generator development with a single-pole version that was produced earlier but put on hold. Presently, Toshiba appears to be working on a design that is larger than 100 MVA.

Although initial efforts in this technology were undertaken with the support of MITI, subsequent development indicates that all electric manufacturers are traveling independent routes of research and development.

Japanese research projects in this field include the following:

- The Special Project for Research on Energy -- funded through the Ministry of Education, Culture and Science Grants to Scientific Research
- Feasibility Study for Introduction of Superconducting Generators into Electric Power Systems -- funded by Central Research Institute of the Electric Power Industry (CRIEPI).

5.1.2 Major Research Centers and Primary Researchers

The following is a list of the primary researchers in this field in Japan. With the exception of those affiliated with universities, the research centers to which these men are attached may be regarded as the major research centers in this field in Japan.

Kiyotaka Ueda	CRIEPI
Naoto Yamamoto	Engineering R&D Center The Tokyo Electric Power Co., Inc.
Dr. Takashi Yasukouchi	Faculty of Science and Engineering Nihon University

Dr. Takao Okada	Faculty of Science and Engineering Kyoto University
Dr. Isuya Muta	Faculty of Science and Engineering Saga University
Dr. Masatani Iwamoto	Central Research Laboratory Mitsubishi Electric Company
Naoki Maki	Hitachi Research Laboratory Hitachi, Ltd.
Dr. Haruyuki Fujimori	Research and Development Ltd. Fuji Electric Corporate
Dr. Yoshimichi Aiyama	Electrotechnical Laboratory Agency of Industrial Science and Technology

5.2 RESEARCH PROJECT SUMMARIES

The two research projects listed in Section 5.1 are briefly summarized below.

5.2.1 The Special Project for Research on Energy - Under Grant in Aid of Scientific Research of the Ministry of Education

This seven-year project was initiated in fiscal 1980 and is part of a larger program titled "Research on Effective Utilization and Densification of Electric Energy." Research related to superconducting generators is being conducted under the subtheme "Basic Research into the Dynamic Characteristics of Superconducting Synchronous Generators" within the larger theme "Application of Extremely Low Temperature and Superconducting Technology to Electric Power Machinery."

A comprehensive evaluation of the results of the initial three years was performed during the fourth year (fiscal 1983) of the program. This evaluation was intended to determine the course of research for the final three years. The total budget for the three years of this subtheme was approximately \$156,000 (35 million yen). In November 1983 an English-language report of the research results was published, entitled Research on Effective Utilization and Densification of Electric Energy (Ministry of Education 1983).

5.2.2 Feasibility Study for Introduction of Superconducting Generators into Electric Power Systems - CRIEPI

This research project was consigned from the Central Electric Power Council, an organization comprising the top managers of Japan's electric power companies. The CRIEPI is the chief organizer of the project. The study targets top managers of the electric power companies to determine whether there is value in actively pursuing research and development on the premise of introducing superconducting generators into electric power systems. If there is promise in pursuing this technology, the study will outline what specific systems and time schedules should be adopted to reach the goals specified. No public announcement of the results will be made.

The schedule for this research is as follows:

October 1986	Begin preliminary studies
December 1, 1987	Establish work groups, begin studies
December 1988	First-stage report of results to Central Electric Power Council
April-May 1989	Second-stage report of results to Central Electric Power Council
September 1989	Submit final report.

Participation in this research project is limited to those Japanese electric power companies that have significant research achievements in this field and are thus capable of making a meaningful contribution as members of the working groups. However, after the results are submitted to the Central Electric Power Council, they will be supplied to all electric power companies. The CRIEPI is funding this entire project, without assistance from the Central Electric Power Council. Manufacturers are cooperating by supplying various data to the project, with working groups conducting re-evaluations of these data in drafting their own options.

The results of this research will have a major impact on the future direction of research and development of superconducting generators in Japan. Dr. Yoshimichi Aiyama of the MITI Agency of Industrial Science and Technology

commented: "Although this may not advance as far as the Sunshine or Moonlight Projects, we personally hope that we will attain the type of direction needed to make it a national project."

5.3 KEY TECHNICAL ISSUES

Figure 5.1 displays the current capacities of various superconducting generators developed around the world. This figure shows that Japanese research and development have resulted in technology developments that are at the forefront of the field. The long-term research projects being supported by the Ministry of Education to further advance this technology are summarized in Table 5.1.

The most recent information from the CRIEPI assessment has revealed the following technological issues of superconducting generators:

1. stable load operation of superconducting materials
2. rotor reliability in maintaining vacuum under extremely low temperatures
3. theoretical elucidation of the gaseous phase and thermodynamic behavior of helium
4. development of high-tensile materials for use as structural elements capable of withstanding extremely low temperatures.

Unfortunately, specific information on the approaches being used, the technological barriers and the likelihood of their solution is not available.

FIGURE 5.1. Current State of Global Superconducting Generator Development

TABLE 5.1. Activities in the Program "Basic Research into the Dynamic Characteristics of Superconducting Synchronous Generators"

<u>Research (Fiscal Year)</u>	<u>Research Body</u>	<u>Researchers</u>	<u>Research Theme</u>
1980-82	Kyoto University	T. Okada T. Nitta	The Basic Test on the 20 KVA Superconducting Synchronous Generator
	"	"	Analysis on Electrical Characteristics of Superconducting Generators
	Saga University	I. Muta	Calculation of Steady-State Performance of 20 KVA Superconducting Synchronous Generator Using Finite-Element Analysis
	Seikei University	T. Ishigoka N. Mizukami	A Few Considerations of a Shielding System of Superconducting Generators
	Saga University	I. Muta	Preliminary Experiment for Feasibility of a Brushless Superconducting Synchronous Generator with Magnetic Fluxpump
1983	The University of Tokyo	E. Masada	Compensation of Industrial Load Variation with Superconducting Magnet Energy Storage
	Kyoto University	T. Okada N. Nitta	Research on the Dynamic Characteristics of Superconducting Synchronous Generators
	Nagoya University Toyohashi University of Technology	K. Horii M. Ozaki	Superconducting Cable Bushing and Cooling System Design
	Kyoto University Osaka University National Laboratory for High Energy Physics	M. Hayaski Y. Murakami M. Masuda	Energy Storage Superconducting Magnet Characteristics and System Applications
1984-86	Pending	Pending	Pending (at the time of this report)

APPENDIX

THE LIST OF RESEARCHERS INTERVIEWED

APPENDIX

THE LIST OF RESEARCHERS INTERVIEWED

General

Dr. Masutami Iwamoto	Mitsubishi Electric Company Central Research Laboratory
Mr. Toshikazu Shito	Tokyo Electric Power Co., Inc. Engineering R&D Center
Mr. Kiyoshi Yamagami	Electrotechnical Laboratory Energy Division
Dr. Hajime Takatsuki	Kanazawa Institute of Technology

Amorphous Metals

Dr. Tsuyoshi Masumoto	Tohoku University, The Research Institute for Iron, Steel, and Other Metal
Dr. Kenji Suzuki	Tohoku University, The Research Institute for Iron, Steel, and Other Metal
Dr. Kazuaki Fukamichi	Tohoku University, The Research Institute for Iron, Steel, and Other Metal
Dr. Setsuyo Kiyono	Tohoku University, The Research Institute for Iron, Steel, and Other Metal
Dr. Fuminori Fujimori	University of Tokyo
Dr. Takahito Kaneyoshi	Nagoya University
Dr. Uichiro Mizutani	Nagoya University
Dr. Yoshifumi Sakurai	Osaka University
Dr. Kenji Narita	Kyushu University
Dr. Hikaru Terauchi	Kwansei-Gakuin University

Dr. Toshikazu Katayama

Electrotechnical Laboratory
Material Department

Mr. Noboru Fujikawa

The Research Development
Corporation of Japan

Miss Kitazawa

The Japan Society for the
Promotion of Science

Metal Oxide Variable Resistance Materials

Dr. Tohei Nitta

Mitsubishi Electric
Corporation

Mr. Masaru Uchita

Mitsubishi Electric
Corporation

Dr. Michio Matsuoka

Matsushita Electric
Component Co., Ltd.

Mr. Jun Ozawa

Hitachi, Ltd.
Hitachi Research Laboratory

Dr. Tatsuo Kawamura

University of Tokyo

Dr. Misao Kobayashi

Meidensha Electric
Manufacturing Co., Ltd.

High-Power Semiconductor Devices

Mr. Hiromichi Ohashi

Toshiba Corporation

Mr. Tatsuo Miyajima

Mitsubishi Electric
Corporation

Superconducting Generators

Mr. Kiyotaka Ueda

Central Research Institute of
Electric Power Industry

Dr. Masamichi Aiyama

Electrotechnical Laboratory

Dr. Kenichi Koyama

Electrotechnical Laboratory

Dr. Takao Okada

Kyoto University

Dr. Itsuya Muta

Saga University

Mr. Naoki Maki

Hitachi, Ltd.

REFERENCES

- dhrr, Incorporated. 1982. Effects of Foreign Government Subsidies on the Competitiveness of U.S. Manufacturers of Heavy Electrical Equipment. dhrr, Inc., McLean, Virginia.
- General Accounting Office. 1983. International Restraints to Competitiveness of the U.S. Heavy Electrical Equipment Industry. House of Representatives, Washington, D.C.
- Kaneyoshi, T. 1983. Amorphous Magnetism. CRC Press, Boca Raton, Florida.
- Kirtley, J. L. April 1983. "Supercool Generation." IEEE Spectrum.
- Kurata, M. et al. 1982. "Gate Turn-Off Thyristors." Semiconductor Devices for Power Conditioning. Plenum Publishing Corporation, New York, New York.
- Masher, D. P. and J. S. Smith. 1981. Impact of Advanced Power Semiconductor Systems on Utilities and Industry. EM-2112, SRI International, Menlo Park, California.
- Masumoto, T. 1981. "Present Status and Prospects of Rapidly Quenched Metals." Presented at the 4th International Conference on Rapidly Quenched Metals, Sendai, Japan.
- Matsuoka, M. June 1971. "Nonohmic Properties of Zinc Oxide Ceramics." Japanese Journal of Applied Physics. (10):6.
- Ministry of Education. 1983. Research on Effective Utilization and Densification of Electric Energy. Ministry of Education, Tokyo, Japan.
- Sakurai, Y., ed. 1983. Amorphous Material: Physics and Technology. Editorial Committee of the Special Project Research on Amorphous Material, Osaka University, Osaka, Japan.
- U.S. Department of Energy. 1980. Panel Report on Amorphous Materials. Division of Materials Sciences, U.S. Department of Energy, Washington, D.C.
- Yasukochi, K. 1983. "Superconducting Magnet Development in Japan." IEEE Transaction on Magnetics. Vol. MAG-19, No. 3.

DISTRIBUTION

No. of
Copies

No. of
Copies

OFFSITE

1D K. Klein
CE-143
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

5 T. Levinson
CE-142
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

M. E. Gunn
CE-142
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

J. J. Eberhardt
CE-142
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

J. J. Brogan
CE-14
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

A. J. Streb
CE-12
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

K. M. Friedman
CE-132
U.S. Department of Energy
1000 Independence Avenue
Washington, D.C. 20585

30 DOE Technical Information
Center

D. Kroeger
Oak Ridge National Laboratory
P. O. Box X
Oak Ridge, TN 37830

C. Koch
Mechanical Engineering
Department
North Carolina State University
Raleigh, NC 27650

J. Carpenter
Oak Ridge National Laboratory
P. O. Box X
Oak Ridge, TN 37830

R. Hasegawa
P. O. Box 1021R
Morristown, NJ 07960

T. Egami
Department of Materials Science
and Engineering
University of Pennsylvania
3231 Walnut St.
Philadelphia, PA 19104

F. Luborsky
General Electric Research and
Development
P. O. Box 8
Schenectady, NY 12301

B. Rubinger
Global Competitiveness Council
15th Floor
50 Milk Street
Boston, MA 02109

5 G. J. Hane
70 Richdale Avenue
Cambridge, MA 02140

No of
Copies

ONSITE

DOE Richland Operations Office

H. E. Ransom

38 Pacific Northwest Laboratory

W. B. Ashton

E. L. Courtright

J. L. Eisenhower (20)

R. M. Fleischman

R. A. Hutchinson (5)

P. M. Lewis

Economics Library (2)

Publishing Coordination MH (2)

Technical Information Files (5)