MASTER

NOTICE

PORTIONS OF THIS REPORT ARE ILLEGIBLE. It has been reproduced from the best available copy to permit the broadest possible availability.

730-56

PROGRESS REPORT NO. 31

FOR A PROGRAM OF

THERMOELECTRIC GENERATOR TESTING

RECEIVED BY TIC JUL 27 1979
AND

RTG DEGRADATION MECHANISMS EVALUATION

Submitted to

The US Department Of Energy
Division of Advanced Nuclear Systems and Projects
Washington D.C.

Prepared by

G. Stapfer
L. Garvey

Project Engineers

Approved by

Jack F. Mondt

J.F. Mondt, Supervisor
Nuclear Thermal-to-Electric Power Group

by

The Jet Propulsion Laboratory
California Institute of Technology
Pasadena, California

July 1979

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

REPORT DISTRIBUTION LIST FOR JPL
INTERAGENCY AGREEMENT NO. E(04-3)-959

Carl Alexander (BMI) (1 copy)
D. Buden (LASL) (1 copy)
California Patent Group (DOE, SAN) (1 copy)
DOE Technical Information Center (Oak Ridge) (1 copy)
Norbert Elsner (GA) (1 copy)
E. F. Hampl, Jr. (3M Company) (3 copies)
W. Hudson (NASA-OAST) (1 copy)
C. E. Kelly, Jr. (GE) (1 copy)
H. Kling (Fairchild) (1 copy)
John McKiernan (Sandia) (1 copy)
J. Lombardo (DOE-NRA) (1 copy)
J. McNeff (USAF) (1 copy)
J. P. Mullin (NASA-OAST) (1 copy)
P. O'Riordan (DOE-NRA) (6 copies)
W. Osmeyer (Teledyne Isotopes) (4 copies)
Valvo Raag (Synca1) (1 copy)
Hilary Rauch (DOE, SAN) (1 copy)
A. C. Schaffhauser (Oak Ridge) (1 copy)
G. Silverman (GE) (1 copy)
W. Von Flue (DOE, SAN) (1 copy)
William W. Ward (Lincoln Lab) (1 copy)

INTERNAL DISTRIBUTION

F. Bell	277-102
G. Bodt	277-102
A. Bridgeforth	198-220
R. Campbell	277-102
J. Casani	169-427
A. Cherniack	198-112D
K. Dawson	198-102
R. Draper	233-307
L. Garvey	277-102
R. Goldstein	122-123
R. Heacock	264-443
T. Hsieh	277-102
R. Ivanoff	277-102
H. Johnson	198-220
A. Lockwood	277-102
J. Longoria	180-503G
J. Mondt	277-102
L. Noon	277-102
W. Phillips	198-220
R. Riebling	180-701
J. Savino	198-112D
J. Schwartz	233-307
W. Shipley	169-427
R. Spehalski	169-427
G. Stapfer	277-102
A. Uchiyama	198-220
P. Wiener	198-220
A. Wolfe	169-427
A. Zoltan	277-102
D. Zoltan	277-102

FOREWORD

This report is submitted to the Department of Energy covering work conducted under Interagency Agreement No. E(04-3)-959 by the Jet Propulsion Laboratory and documents all activities covering the period of April, May, and June 1979 performed under the technical direction of Mr. Patrick O'Riordan Power Systems Section, Space and Terrestrial Systems Branch of the DOE Division of Advanced Nuclear Systems and Projects.

CONTENTS

- I. SUMMARY
- II. SELENIDE TECHNOLOGY EVALUATION
 - A. Thermal Conductivity Tests
 - B. In-Gradient Tests
 - C. Thermophysical Properties and Compatibility Tests
 - D. Accelerated Resistance "Module" Tests
 - E. Degradation Modeling - SiGe
- III. THERMOELECTRIC GENERATOR TEST AND EVALUATION
 - A. High Performance Generator, HPG SN-2
 - B. Ring Converter
 - C. MHW Generator Q1-A
 - D. RCA Reference Generator
- IV. MHW FLIGHT GENERATOR PERFORMANCE
 - A. Power Performance Comparisons for LES 8 and 9 Flight RTGs
 - B. Power Performance of Voyager 1 and 2 Flight RTGs

I. SUMMARY

Thermal conductivity measurements of the p-type and n-type selenide alloys after 19,800 hours and 6,500 hours, respectively, continue to show good agreement with the 3M Co. published data.

Ingradient testing of n-legs after 8,900 hours show comparable performance to the reported 3M data. Ingradient testing of p-legs at accelerated test conditions has completed 5,432 hours and performance shows reasonable correlation with accelerated temperature and current gradients. This test has been discontinued to accomodate ingradient performance testing of the new design p-type legs with the Astroquartz/slurry wrap. Weight loss testing of the new design p-type TPM217 (no partition) with the Astroquartz/slurry wrap has been continued at both ingradient and isothermal test conditions. A check of one sample after 1,000 hours at $T_H 900^{\circ}\text{C}$ and $T_C 150^{\circ}\text{C}$ shows a very low weight loss rate, comparable to that reported by the 3M Co. and these tests are continuing.

A post-mortem examination of the RCA Reference Generator, which operated for 62,339 hours prior to failure, has been initiated and the metalligraphic analysis was completed during this report period.

The remaining MHW generator, Q1-A, on test has accumulated 14,191 hours and performance remains stable.

An evaluation of the performance of the Voyager 1 and 2 RTGs after 14,661 hours and 15,160 hours of operation, respectively, versus the DEGRA prediction code, continues to show good agreement.

II. SELENIDE TECHNOLOGY EVALAUTION

A. Thermal Conductivity Tests

The long term experiment of the p-type, singly partitioned legs, operated over a temperature gradient of $T_H = 800^\circ\text{C}$, $T_C = 400^\circ\text{C}$, has accrued approximately 19,800 hours of operation. The thermal conductivity values for the four legs continued on test were calculated and are shown in Figure 1 and normalized to the original value ($K_0 = 100$ hours) in Figure 2 as a function of operating time. The thermal conductivity of the samples, except for No. 5 shows reasonably good agreement with the 3M Co's published values. The thermal conductivity after the first 4000 hours has shown good stability, including sample No. 5. The testing of samples 1, 3, 5 and 6 will be continued.

The long-term testing of the n-type legs has been continued, utilizing the same type of calorimeter set-up as used for the p-type legs with the exception that all of the calorimeters have the molybdenum bellows cylinders. The legs operated over a temperature gradient of $T_H = 800^\circ\text{C}$ and a maximum $T_C = 250^\circ\text{C}$ have accrued approximately 6500 hours of operation. This limitation of the cold end junction temperature is required because lead foil is attached to the silver sputtered end of the leg as the cold end contact (silver-lead eutectic- 304°C). The thermal conductivity values for the four legs are shown in Figure 3 and normalized to the original value ($K_0 = 20$ hours) in Figure 4, as a function of operating time. The themal conductivity values for the four legs has remained stable and shows good agreement with the 3M Co's published value. These tests are continuing.

Figure 1. TPM-217 (P-LEG) Thermal Conductivity Calorimeter 1 to 6 T_H 800°C T_C 400°C

Figure 2. TPM-217 (P-LEG) Thermal Conductivity $T_H - 800^\circ\text{C}$ $T_C - 400^\circ\text{C}$

Figure 3. Thermal Conductivity Test N-Type Calorimeter 1 to 6 T_H 800°C T_C 240°C

Figure 4. Thermal Conductivity Test N-Type $T_H 800^\circ\text{C}$ $T_C 240^\circ\text{C}$

B. Ingradient Testing

Testing of the group of p-legs with rounded copper cold shoes (an earlier design) was discontinued during this reporting period. These p-legs were partitioned at approximately the same location as the GDS design p-legs. A total of 5,432 hours of operation was accumulated on these samples. Based on the acceleration factor of 5x calculated for this test, samples No. 1, 4 and 5 have an equivalent test time of 27,160 hours. Two p-legs were operated at "reference" conditions, $T_H = 800^\circ\text{C}$, $T_C = 150^\circ\text{C}$ and a current of 4.8 amps; these test conditions were used for previous ingradient tests of all p-legs. This current translates into a current gradient of 1.4 amps/cm for the upper (hot) segment and 7 amps/cm for the lower segment, which were nominal GDS design operating conditions. In an attempt to evaluate the effort of accelerated current gradients and temperatures at ingradient conditions the following test conditions were selected for the remaining three p-legs:

Sample No.	Temperature	Current	Total Acceleration
	T_H/T_C	Acceleration Amps	Acceleration
2,3	$800^\circ\text{C}/150^\circ\text{C}$	Reference 4.8	nominal
5	$800^\circ\text{C}/150^\circ\text{C}$	Reference 8.16*	5X
1	$830^\circ\text{C}/160^\circ\text{C}$	2X 6.72	5X
4	$870^\circ\text{C}/150^\circ\text{C}$	5X 4.8	5X

The performance of the p-legs over this testing period is given in Figures 5 through 8. Sample No. 5 appeared to have shorted at 4,276 hours, but examination of the test set-up upon opening the test station revealed that the voltage monitoring lead had broken off and the low load voltage reading was due to a 'pickup' in the measuring instrumentation. The current during this time

* Actual 7.5 amps due to limitation of power supply.

Figure 5. Open Circuit Voltage (EOC) VS TIME

"P" TYPE TPM 217

SAMPLE 1 $T_H = 830^{\circ}\text{C}$, $T_C = 150^{\circ}\text{C}$, $I = 6.72 \text{ AMP}$
 2 $T_H = 800^{\circ}\text{C}$, " " " " $I = 4.8 \text{ AMPS}$
 3 " " " " " " " "
 4 $T_H = 870^{\circ}\text{C}$, " " " " " " " "
 5 $T_H = 800^{\circ}\text{C}$, " " " " $I = 8.16 \text{ AMPS}$

Figure 5. Open Circuit Voltage (EOC) VS Time "P" Type TPM 217

730-56

Figure 6. Seebeck Voltage VS Time "P" Type TPM 217

"P" TYPE TPM 217

SAMPLE	1	$T_H = 830^\circ\text{C}$	$T_C = 150^\circ\text{C}$	$I = 6.12 \text{ A}$
"	2	$T_H = 800^\circ\text{C}$	"	$I = 4.8$
"	3	"	"	"
"	4	$T_H = 870^\circ\text{C}$	"	"
"	5	$T_H = 800^\circ\text{C}$	"	$I = 8.16$

Figure 7. Resistivity VS Time "P" Type TPM 217

"P" TYPE TPM 217

VACUUM BAKED

SAMPLE 1 $T_H=830^{\circ}\text{C}$; $T_C=150^{\circ}\text{C}$, $I=6.72$ AMPS
 " 2 $T_H=800^{\circ}\text{C}$; " " , $I=4.8$ AMPS
 " 3 $T_H=800^{\circ}\text{C}$; " " , $I=$ " "
 " 4 $T_H=870^{\circ}\text{C}$; " " , $I=$ " "
 " 5 $T_H=800^{\circ}\text{C}$; " " , $I=8.16$ AMPS

Figure 8. Power VS Time "P" Type TPM 217

period had remained constant and therefore it can be assumed that the actual performance of Sample No. 5 was reasonably stable throughout the latter part of the test period. It also had the lowest output power as evidenced by the lower open current voltage (E_{oc}) which is most likely due to a variation in the actual temperatures versus the measured temperatures. Sample No. 4 with the largest ΔT ($T_H 870^\circ\text{C} - T_c 150^\circ\text{C}$) correspondingly produced the highest output power. Performance of Samples 1, 2, and 3 shows reasonable agreement with previous p-type legs tested. (Progress Report No. 26.)

Upon opening the test station and removing the samples, it was noticed that all samples had 'mushroomed' at the hot end and the material on the upper partition had sublimed. The hot end foil and the partition foil were in direct contact and had skewed off to one side between 30° to 70° depending on the sample. All samples had extensive copper extrusion at the cold end, with the samples at the accelerated test conditions, particularly samples 4 and 5, being the most severe. These tests again confirm that the partitioned p-type elements, baffled with Fiber Frax 970 AH paper, would experience severe sublimation and deterioration in 5 years operation at GDS design conditions. It is planned to replace these p-legs with the new design unpartitioned p-legs with the slurry/Astroquartz wrapped samples received from the 3M Co. during this reporting period.

Ingradient testing of the n-type GdSe legs has been continued utilizing the same set-up designed for the p-type samples. The only difference being that a disc of gadolinium foil had been inserted between the molybdenum heater block and the hot end of the n-type sample. The n-legs are operated at a constant hot side of 800°C and a cold side temperature of 150°C in a hard vacuum environment. A total current of 3.7 amps, nominal GDS design operating conditions, was applied to the n-legs which are surrounded by Fiber-Frax paper 970 AH insulation.

N-legs, Nos. 1,3, and 4 have accumulated 8907 hours of operation and the performance has reasonably stabilized. N-leg No. 2 was removed after 7443 hours to make room for ingradient testing of p-type samples with the Astroquartz/slurry wrap from the 3M Co.. The open circuit voltage Seebeck coefficient, resistivity, open circuit voltage and power as a function of operation time, are shown in Figures 9 through 12, respectively, and show reasonable agreement with the published data. Sample Nos. 1, 3, and 4 are being continued on test.

Figure 9

Figure 10

SEEBECK VOLTAGE VS. TIME

N TYPE, GD-SE, TH=800C, TC=150C, I=3.7A, VAC. BAFFLED 78-1.

SAMPLE NO. 1=□ 2=○ 3=△ 4=◇ 5=★

Figure 11

RESISTIVITY VS. TIME

N TYPE, GD-SE, TH=800C, TC=150C, I=3.7A, VAC. BAFFLED 78-1.

SAMPLE NO.

1= $\square$

2= $\circ$

3= $\triangle$

4= $\diamond$

5= $\star$

Figure 12

LOAD POWER VS TIME

N TYPE, GD-SE, TH=800C, TC=150C, I=3.7A, VAC. BAFFLED 78-1.

SAMPLE NO.

1=□

2=○

3=△

4=◇

5=★

C. Thermophysical Properties and Compatibility Tests

The testing of n-type samples, unbaffled (zero current) in a vacuum environment was discontinued during this reporting period to accomodate a special test of n-type elements in a CO environment. The samples were tested at 800°C, 900°C and 1000°C and had accumulated 7666 hours of operation. The weight loss rate versus temperature of the n-type material is given in Figure 13. The last data point shows a slight increase in weight loss rate, however, the overall pattern shows a weight loss rate approximately three decades lower than the p-type material. When test station space is available, resumption of testing of these n-type elements will be considered.

Testing of p-type material in a partial pressure of oxygen, 2×10^{-5} tone, was discontinued during this reporting period to accomodate a special test of n-type elements in an oxygen environment. The samples were tested at 600°C, 700°C, 800°C and 900°C and had accumulated 7589 hours of operation, see Figure 14. The weight loss rate in the partial pressure of oxygen shows little difference compared to the rates measured in a vacuum environment.

Testing of the p-type-TPM217 thermoelectric elements with the Astro-quartz fiber wrap with the Mink-TE1800 slurry coating, received from the 3M Co., has been continued. These p-type elements have a 0.030-inch thick copper foil bonded to the cold end and a 0.020-inch thick tungsten/rhenium alloy cap bonded to the hot end. There is no partitioning foil. Two of these samples were placed on ingradient testing during the last reporting period at the same test conditions as used by the 3M Co. The samples were baffled with a $\frac{1}{2}$ " thick LO-CON Fiber Frax LO-CON blanket as were those tested by the 3M Co.

Figure 13 WEIGHT LOSS RATE OF
N-MATERIAL IN VACUUM - UNBAFF

Figure 14. Weight Loss Rate of P-Type TPM217 Material
in Partial Pressure of Oxygen, 2×10^{-5} Torr
(Fiberfrax Baffled - Zero Current)

Hot Junction Temperature - T_H - 900°C
Cold Junction Temperature - T_C - 150°C
Current Gradient - i_l/A - 11.0
Test Time - 1000 hours

One of these samples was removed after 1000 hours, see Figures 15 and 16. The weight loss was measured and compared to that obtained by the 3M Co., both exhibit very low weight loss rates.

3M Co. - $5.2 \times 10^{-6} \text{ gms/cm}^2 - \text{hr.}$

JPL - $8.7 \times 10^{-6} \text{ gms/cm}^2 - \text{hr.}$

Both the copper foil and tungsten/rhenium cap separated from the p-element upon removal of the Astroquartz/slurry wrap. The p-element was in excellent condition otherwise, and it was decided to allow the second sample to continue on ingradient test out to 2000 hours; this sample has accumulated 1680 hours to date. The performance of these two samples was monitored, see Figures 17 through 20, and shows reasonable agreement with 3M Co. data.

Six of the 3M Co's Astroquartz/slurry wrapped p-type samples (no partition) were subjected to isothermal test conditions at 800°C , 850°C and 900°C and a current gradient of $i_l/A = 11.0$ (5 amps). The test results are presented in Table I and compared to previous tests results obtained by the 3M Co. and of samples prepared and tested by JPL. This new technique of wrapping the p-type element developed by the 3M Co. shows a very low weight loss as compared to just bulk insulation (MinTE - 1800) or earlier wrap combinations.

WEIGHT LOSS MEASUREMENT

INGRADIENT TEST

P-TYPE (3M-WRAPPED)

$T_H = 900^{\circ} \text{C}$

$T_C = 150^{\circ} \text{C}$

$I = 5\text{AMP}$

RUN TIME 1000 HRS.

Figure 15

WEIGHT LOSS MEASUREMENT

INGRADIENT TEST

P-TYPE (3M-WRAPPED)

$T_H = 900^{\circ} \text{ C}$

$T_C = 150^{\circ} \text{ C}$

$I = 5 \text{ AMP}$

RUN TIME 1000 HRS.

Figure 16

Figure 17

OPEN CIRCUIT VOLTAGE VS. TIME
P TYPE, TPM-217, TH=900C, TC=150C, I=5.0A, VAC. BAFFLED 79-1

Figure 18

SEEBECK VOLTAGE VS. TIME

P TYPE, TPM-217, TH=900C, TC=150C, I=5.0A, VAC. BAFFLED 79-1

SAMPLE NO. 1=□ 2=○

RESISTIVITY VS. TIME

P TYPE, TPM-217, TH=900C, TC=150C, I=5.0A, VAC. BAFFLED 79-1

SAMPLE NO. 1=□ 2=○

Figure 20

LOAD POWER VS TIME

P TYPE, TPM-217, TH=900C, TC=150C, I=5.0A, VAC. BAFFLED 79-1

SAMPLE NO. 1=□ 2=○

TABLE I

WEIGHT LOSS RATE OF

ASTROQUARTZ/SLURRY WRAPPED P-TYPE ELEMENT

AT ISOTHERMAL TEST CONDITIONS

SAMPLE WRAP	3M Co.			JPL (JPL Prepared Samples) ①			JPL (3M Prepared Samples)		
	Temp.	iI/A	Wt. Loss Rate	Temp.	iI/A	Wt. Loss Rate	Temp.	iI/A	Wt. Loss Rate
	°C	(A/cm)	mg/cm ² -hr	°C	(A/cm)	mg/cm ² -hr	°C	(A/cm)	mg/cm ² -hr
Astroquartz/Cab-O-Sil	940	8.9	0.102	--	---	----	--	---	----
	940	11.0	--	900	11.0	.112	--	---	----
	940	17.8	0.44	--	---	----	--	---	----
Astroquartz/Mink-TE 1800	--	---	----	900	110	.100	--	---	----
3M Co. Astroquartz Wrap per Spec. MSI-2008-8.1.4	--	---	----	--	---	----	800 ②	11.0	.00124 - .00522
	--	---	----	--	---	----	850 ②	11.0	.0068 - .0112
	--	---	----	--	---	----	900 ③	11.0	.0167 - .047

NOTES: ① 180 hour Test Period - Both Samples

② 1000 hour Test Period - Samples 1 and 2

③ 160 hours and 500 hours - Sample 1 and 2, respectively

Ten (10) additional p-type samples were received from the 3M Co. during this reporting period and isothermal testing of some of these samples have been initiated as per the following test conditions:

<u>SAMPLE NO.</u>	<u>TEMPERATURE °C</u>	<u>iI/A</u>	<u>AMPS</u>
1	800	11	5
2	800	8	3.6
3	850	11	5
4	850	8	3.6
5	900	11	5
6	900	8	3.6

The samples will be weighed periodically with the wrap to note gross changes; upon detecting a significant shift in weight loss, the samples will be unwrapped and the weight loss rate calculated based on the 3M measured pre-wrap weight.

D. ACCELERATED RESISTANCE "MODULE" TEST

The accelerated resistance test, in a stainless steel test fixture, continued during this reporting period.

The object of this test is to determine whether the electrical resistance of the ceramic insulator in the 'cold current strap' decreases as a result of material sublimation or will be shorted by copper whisker growth due to dispersion of copper at the cold junction.

The module contains a TPM 217 "p" type pellet which is operated at a T_H of 850°C . The cold junction temperature is maintained at $150^{\circ}\text{C} \pm 5^{\circ}\text{C}$, by a back heater situated between the sample and the water-cooled baseplate. Approximately two-thirds of the length of the TPM 217 pellet is surrounded by Min-k TE 1800. The remainder is covered by layers of 'Fiber Frax' material, see Figure 21.

As to date, the test has accumulated 5200 hours. Using an acceleration factor of approximately 6x this is the equivalent of more than 31000 hours of operating time under GDS system design conditions. For more detailed information and calculations of the acceleration factor see Report No. 26, May 1978.

During this reporting period the insulator resistance has remained stable at 10^9 ohms, see Figure 22.

The open circuit voltage however, has diminished from approximately 0.178 V at beginning of test, to 0.167 V at present. The test is continuing.

Figure 21. Accelerated resistance module test of "Cold Current Strap Assembly"

Figure 22. Insulator Resistance

E. DEGRADATION MODELING - SiGe

Specialized exponential curve fits were developed for modeling loss rates for the n and p SiGe legs and for SiMo hot shoe sublimation losses. The curve fits were of the form

$$\text{Weight loss rate} = b10^{mx} \text{ g/cm}^2 \text{ - hr.}$$

$$\text{where } x = 10^4/T \text{ (}^{\circ}\text{K)}.$$

This particular mathematical representation can be linearized on a semilogarithmic plot and is well behaved in operational regions of interest for RTGs.

The curve fits have been developed and verified external to DEGRA2 using the same type of logic necessary to incorporate into the main code. Incorporation of these features will enable estimation of performance changes caused by changes in shunt resistance and insulation thermal conductivity due to sublimation losses.

The particular loss rate data for the uncoated hot shoe and SiGe n and p legs are derived from data given in Reference 1, while data for the SiMo* coated case were taken from Reference 2. The results from the computer fits are plotted in Figure 23.

In order to use the functional dependence of weight loss per unit couple versus temperature, one must know how much of the entire n and p legs are contributing and how much of the hot shoe is contributing to the total weight loss mechanism. Reference 2 indicates an area of 0.4 cm^2 of hot shoe was contributing to weight loss** and approximately the same area was contribution from the legs. Since sublimation is a surface area effect,

* SiGe coated case was assumed to be one decade lower than the uncoated SiGe.

** weight loss throughout this discussion refers to the amount of Silicon which is lost and reacts with SiO_2 to yield SiO(g) .

FIGURE 23 Loss rates for Coated & Uncoated Si-Mo hot shoe and Si-Ge legs.

$$\text{Perimeter of leg} = (.256 + .108) \times 2 \times 2.54$$

$$\text{or } P = 1.84912 \text{ cm.}$$

$$\text{A total surface area of } 0.1 \text{ cm}^2 \quad \text{or} \quad x = .02704 \text{ cm.}$$

$$t = .27 \text{ mm.}$$

Reference 2 also indicated an average temperature gradient of 35°C/mm length which corresponds to

$$(35^\circ\text{C/mm} \times 0.27 \text{ mm})$$

$\sim 9.5^\circ\text{C}$ drop for 0.1 cm^2 of leg surface area. This number is in close agreement with 10°C for 0.1 cm^2 of leg surface area quoted in Reference 2.

If one now assumes a 10°C drop, 0.1 cm^2 of surface area with a total contributing leg area of 0.6 cm^2 , an artificial temperature profile can be constructed in the leg which acts as the driving profile for sublimation from the leg. If this effect is summed with the 0.4 cm^2 contribution from the hot shoe, one can estimate the total sublimation giving rise to shunt resistance build up in the generator and thermal conductivity changes in the insulation (i.e. SiO). As will be shown later, the results from this calculation agree reasonably well with hand calculated results in Reference 2.

-
- (1) Caputo, R.; deWinter, F.; Raag, V. and Stapfer, G.; "Silicon Germanium Technology Programs - Report No. 2", JPL Report No. EM 342-228. pp. 90-99, 1973.
 - (2) Stapfer, G. and Truscello, V., "The Long Term Performance Degradation of a Radioisotope Thermoelectric Generator Using Silicon Germanium", 11th IECEC Proceedings, pp. 1533 - 1538, 1976.

The software developed was used with a temperature varying from 946°C to 1156°C ($10^4/T$ (°K) from 8.2 to 7.0). The slopes and intercepts of the weight loss rate equations are selected based upon coated or uncoated mode, the surface area is taken into account and the results combined for an effective hot shoe temperature and seven temperature segments down the leg.

The final results of this calculation for both uncoated and coated cases using the new fitting functions are plotted in Figure 24. They are compared with the results in Reference 1 and found to be reasonably close, certainly within a factor of 2 for worst case comparison and approximately 19% difference for best case. The reasons for the different results are thought to arise from several sources. The most important reason for the differences arises from different loss rate formalisms used in each set of calculations. The calculation developed here is based on the following assumptions:

- (1) Si_3N_4 Coated SiMo uses Reference 2, Figure 2;
- (2) Uncoated SiMo uses data from Figure 3-3, p. 91, Reference 1;
- (3) Uncoated SiGe uses data from Figure 3-8, p. 99, Reference 1, ("average" p and n data.);
- (4) Si_3N_4 coated SiGe uses an order of magnitude less than uncoated SiGe. The curves are therefore parallel on semilog paper but differ by a factor of ten.

A considerably weaker but appropriate reason for the observed differences may be that this calculation uses computer segmentation of seven segments while the calculation in Reference 1 was done by hand. The hand calculation used as many segments as necessary to drop one order of magnitude in loss rates while with the computer a fixed seven segments were always taken. According to the computer results for both the coated and uncoated cases, the number of segments required to reduce loss rates by an order of magnitude is approximately the same as used in

FIGURE 24. Si Loss / Unicouple vs T-hot junction

the computer formulation. The only difference then would be calculational accuracy and significant figures.

The final reason for differences in the computer and the results in Reference 1 would account for approximately a 50% systematic difference. The area of the leg assumed to contribute to the sublimation in the computer calculation was assumed to be 0.6 cm^2 while in the hand calculation the area was 0.4 cm^2 . The latest results would be therefore higher by 50% because of this difference.

Considering the many sources of differences in the calculational procedure, the results from the two calculations seem to be in reasonable agreement. When this newer calculation is factored into DEGRA2, the temperatures used will be an average sublimation temperature over the segment and considerably more segments will be used. It is therefore felt the newer calculation will yield better results and also allow flexibility for using separate loss rates for the n and p legs should that become available.

One final item is of interest in applying this software to DEGRA2. The sublimation from the leg is a strong function of temperature and therefore of evaluation position in the leg. The computer results obtained, as plotted in Figures 25 and 26 illustrate how quickly the first few layers (segments of surface area) of the leg account for most of the sublimation occurring in each leg. In fact, in both figures one can see that approximately 90% of the sublimation occurs in the first five segments regardless if the hot junction is at $T = 7.0$ (1135°C) or $T = 8.0$ (977°C). This observation will be taken into account when encoding these equations into the overall logic of DEGRA2.

FIGURE 25. LEG SUBLIMATION PERCENTAGE VS. SEPARATION DISTANCE FEET
HOT SUN. (UNCOATED CASE.)

FIGURE 26. LEG SUBLIMATION PERCENTAGE VS. SEPARATION DISTANCE FROM HOT SHOE. (COATED CASE.)

III. THERMOELECTRIC GENERATOR TEST AND EVALUATION

Thermoelectric generators, representing recent and advanced technology, assembled with lead telluride, TAG-85 and silicon-germanium materials are being tested at JPL. These generators are: The HPG (PbTe), and the Ring Converter (P-side PbSnMnTe/BiSbTe, N-side 2N-PbTe). Also, generator Q1-A (SiGe), representative of the MHW type generators, was on test during this reporting period.

A. HIGH PERFORMANCE GENERATOR HPG S/N-2

This generator has operated for a total time of 42,787 hours. After 41,300 hours of operation, the testing of the generator was temporarily interrupted, because of a scheduled preventive maintenance operations in the building. As the generator was cooled down, the generator and the environmental chamber were purged with a gas mixture of Argon (25.5%0 and Helium (74.5%).

During the last 1,513 hours of operation, the generator out power has decreased by 3.16%. Presently the generator out power is 127.05 watts. The generator open circuit voltage has also decreased slightly to its present value of 24.82 volts ± 0.05 volts, the internal resistance remained the same at 1.15 ohms. The generator hot and cold junction temperatures have changed due to the generator environmental change. Presently the AVG $\bar{T}_H = 538^\circ\text{C} \pm 3^\circ\text{C}$ and the AVG $\bar{T}_C = 181^\circ\text{C} \pm 2^\circ\text{C}$.

The generator degradation rate for the last 5,000 hours of operation was 1.03% (1,000 hours). The generator history is illustrated in Figure 27.

Figure 27

B.

RING CONVERTER

This generator has operated for a total accrued time of 38,420 hours. During the last 1,410 hours of operation the generator output power was slightly decreased by 0.36 watts, to its present value of 12.04 watts. In the same period the generator open circuit voltage and internal resistance has increased. ($E_{oc} = 4.128$ volts $R_{int} = 344$ milli ohms). The generator hot and cold junction temperatures were $AVG \bar{T}_H = 441^{\circ}C$ and $AVG \bar{T}_C = 168^{\circ}C$.

The generator degradation rate for the last 5,000 hours of operation was 0.58%/1,000 hours. The generator performance history is illustrated in Figure 28.

C.

MHW GENERATOR Q1-A

This generator has operated for a total time of 14,191 hours. During the last 1,294 hours of operation the generator out power has decreased by 1.10 watts. Presently the generator out power is 135.7 watts. The generator open circuit voltage and internal resistance has slightly increased in that time ($E_{oc} = 57.01$ volts and $R_{int} = 5.97$ ohms). The generator heat source temperature has slightly decreased, but the case temperatures have remained the same, $AVG \bar{T}_H = 1.33^{\circ}C$, $AVG \bar{T}_C = 262^{\circ}C$.

The generator degradation rate for the last 5,000 hours of operation was 0.61%/1,000 hours. The generator life history is illustrated in Figures 29 and 30.

Figure 28

Figure 29

Figure 30

D.

RCA REFERENCE GENERATOR

This generator has operated for a total accrued time of 62,339 hours; at which time the generator was removed from test and a thorough examination and analysis was initiated. The generator history is given in Progress Report No. 27, August 1978. Metallographic analysis has been completed on a number of thermocouples, which represent a cross section of the generator. SEM and EDAX examinations are now being performed and a separate report will then be prepared delineating the analysis conducted.

IV. MHW FLIGHT PERFORMANCE

A. POWER PERFORMANCE COMPARISONS FOR LES 8 AND 9 RTGs.

This information is furnished by Lincoln Laboratories on a quarterly basis. The power output of the four LES 8 and 9 RTGs has been compared with the calculated output of DEGRA2 up to a mission time of 26.574 hours, for a total of three (3) years of operation. The comparison is shown in Figures 21 and 22. For details of the DEGRA calculations, the reader is referred to Progress Report No. 23, September 1977. Based on the initial performance of these RTGs, the BOM age of RTG-1 on LES-8 and RTGs-1 and 2 on Les-9 was 1500 hours and the BOM age of RTG-2 on LES-8 was 500 hours. The degradation rate of RTG-1 on LES-8 and RTG-2 on LES-9, see Figure 31, show excellent agreement with the DEGRA calculation using a silicon nitride coating lifetime of 100,000 hours. RTG-1 on LES-9 has a slightly higher degradation rate, but still shows reasonably good agreement with the 100,000 hours coating lifetime curve. RTG-2 on LES-8, see Figure 32, shows excellent agreement with the DEGRA calculation using a silicon nitride coating of 100,000 hours.

FIGURE 31.

Comparison of LES 8/9 RTG Power with DEGRA

Figure 32

Comparison of LES 8 RTG Power with DEGRA

B. POWER PERFORMANCE OF VOYAGER 1 AND 2 FLIGHT RTGs

This information is provided by the Voyager Flight Project at JPL. The six thermoelectric generators which provide the power for the Voyager spacecraft are of the same type and design as are used on the LES-8 and LES-9 spacecraft. A comparison of the Voyager RTGs power output versus that predicted by DEGRA has been made. For details of the DEGRA calculations the reader is referred to Progress Report No. 23, September 1977. Based on the initial performance of the RTGs on both Voyager 1 and 2, the BOM age of all the RTGs was determined to be 1500 hours. The ratio of the output power to the original power at launch (P/P_o) of the RTGs on Voyager 1 and Voyager 2 is compared to the DEGRA data normalized to a Beginning Of Mission (BOM) "age" of 1500 hours, in Figure 33 and 34. The degradation rate of the RTGs 2 and 3 on Voyager 1 shows excellent agreement with the DEGRA calculations using a silicon nitride coating lifetime of 100,000 hours, see Figure 33. The degradation rate of RTG 1 showed a change at approximately 14,000 hours and has fallen below the coating lifetime curve of 100,000 hours, see Figure 33. The degradation rate of the two RTGs on Voyager 2 also show excellent agreement with the DEGRA calculations using a silicon nitride coating lifetime of 100,000 hours, see Figure 34. For information the plots of the "raw" data versus time, as previously reported, for Voyager 1 and Voyager 2 are shown in Figures 35 and 36. The accrued time and power output of the RTGs is listed on the following page:

VOYAGER - 1

Total operation time = 14,662 hours

Last period of operation = 1,272 hours

RTG-1	F-8	147.31 watts
-------	-----	--------------

RTG-2	F-6	148.13 watts
-------	-----	--------------

RTG-3	F-9	149.92 watts
-------	-----	--------------

RTGs Total	=	445.34 watts
------------	---	--------------

VOYAGER - 2

Total operation time = 15,160 hours

Last period of operation = 1,200 hours

RTG-1	F-10	150.97 watts
-------	------	--------------

RTG-2	F-12	149.88 watts
-------	------	--------------

RTG-3	F-11	Telemetry - Not Operating
-------	------	---------------------------

Figure 33

COMPARISON OF VOYAGER-1 RTG POWER WITH DEGRA

Figure 34

COMPARISON OF VOYAGER-2 RTG POWER WITH DEGRA

Figure 35

VOYAGER-1, RTG's, P_0 /TIME

Δ F-8, RTG-1
 $\circ$ F-6, RTG-2
 $\square$ F-9, RTG-3

Figure 36

VOYAGER-2, RTG's P_0 /TIME

Δ F-10, RTG-1

$\circ$ F-12, RTG-2

$\square$ F-11, RTG-3