DOE/ER/13484-3

QUANTITATIVE NON-DESTRUCTIVE EVALUATION OF HIGH-TEMPERATURE
SUPERCONDUCTING MATERIALS

DE FG02-86ER13484

DOE/ER/13484--3

DE92 011007

Technical Progress Report

September 1, 1989 - August 30, 1990

prepared by

J. D. Achenbach

Center for Quality Engineering and Failure Prevention
Northwestern University
Evanston, IL 60208-3020

Telephone (709) 491-5527

September 15, 1990

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	Page
1. Summary of Current Project.....	1
2. Summary of Results since Sept. 1, 1989.....	1
3. Work in Progress.....	3
4. Personnel.....	6
5. Oral Presentations of Project Work Since Sept. 1, 1989....	6
6. Publications for 1989 and 1990.....	6

1. Summary of Current Project

Even though the currently intensive research efforts on high-temperature superconducting materials have not yet converged on a well specified material, the strong indications are that such a material will be brittle, anisotropic, and may contain many flaws such as microcracks and voids at grain boundaries. Consequently, practical applications of high temperature superconducting materials will require a very careful strength analysis based on fracture mechanics considerations. Because of the high sensitivity of the strength of such materials to the presence of defects, methods of quantitative non-destructive evaluation may be expected to play an important role in strength determinations.

This proposal is concerned with the use of ultrasonic methods to detect and characterize isolated cracks, clusters of microcracks and microcracks distributed throughout the material. Particular attention will be devoted to relating ultrasonic results directly to deterministic and statistical linear elastic fracture mechanics considerations.

2. Summary of Results since September 1, 1989

Considerable progress has been achieved in the general area of ultrasonic waves in cracked solids (Section 2.1.1.C of the Proposal for the period Sept. 1, 1989 - August 31, 1992). The results, which are concerned with ultrasound in solids that are permeated by cracks, are for surface waves and for body waves. The purpose of these studies is to relate the density of cracks and their geometrical parameters to wave speed and attenuation, in order that measured data of the latter quantities can be used to estimate the extent of crack permeation.

2.1 Dispersion and attenuation of surface waves due to distributed surface-breaking cracks.

Dispersion and attenuation of surface waves propagating over the free surface of a half-space containing distributed surface-breaking cracks have been investigated. The 3-D problem of scattering of surface waves by a single surface-breaking crack is first formulated and the characteristic amplitude factor of the scattered surface wave is expressed in terms of the crack opening displacements. A relation between this amplitude factor and the scattered power flow is then derived. The scattering cross section is introduced as a measure of energy removal from the incident surface wave. By using energy considerations, the coefficient of attenuation is subsequently expressed in terms of the scattering cross section. Use of the Kramers-Krönig relation then yields an expression for the phase velocity. Numerical results are given for both the coefficient of attenuation and the phase velocity, as functions of the crack density, a characteristic length dimension of the crack and the frequency. The theoretical framework provided in this paper may lead to a novel application of surface waves for the detection and characterization of fatigue damage of metals under cyclic loading, as well as on the characterization of the state of microcracking in high-temperature superconducting materials. Numerical results are presented for several frequencies, crack densities and crack depths.

2. Effective wave velocity and attenuation in a material with distributed penny-shaped cracks.

Wave propagation in a material containing distributed penny shaped cracks has been investigated. An improved approach is developed for calculating the phase velocity and the attenuation of ultrasonic waves. In this approach, the effects of neighboring cracks on a reference crack are

approximated by the effects of triads of double forces of strengths proportional to the crack opening volumes and located at the geometrical centers of the cracks. The averaged crack opening displacements and crack opening volumes of the reference crack are split into two terms. The first term corresponds to the quantities induced by the interaction of the single reference crack with an incident wave, while the second term represents the interaction between this reference crack and neighboring cracks. The averaged crack opening displacements are used in calculating the forward scattering amplitude, from which the phase velocity and the coefficient of attenuation are subsequently computed. The present analysis is limited to parallel cracks and to low-frequencies, but the principle can be used for more general cases. Since crack interactions have been taken into account, the analysis provides a better approximation than the standard approach proposed by Foldy, especially for intermediate and large crack densities.

3. Work in Progress

Distributions of microcracks in materials can be generated by a number of physical phenomena and loading conditions. A typical example is fatigue damage in a polycrystalline solid or a composite material. For example, a powder metallurgied material consisting of an aluminum alloy matrix with SiC whiskers, will display microcracks at the interfaces of the whiskers and the matrix, when the material is subjected to fatigue loading. Another example is a brittle material such as a ceramic, which is subjected to rapid non-uniform temperature changes. When cooled such a material will develop distributions of microcracks. This kind of microcracking has been observed in high-temperature superconducting materials.

Clearly, extensive microcracking is undesirable from a strength point of view. It will be important to detect and characterize microcracks when

they are still microcracks, because the remaining lifetime once such cracks have coalesced to form macrocracks, is generally relatively small. Unfortunately it is very difficult indeed to detect and characterize individual microcracks with the conventional techniques of quantitative non-destructive evaluation. It is, however, possible to measure the overall effect of distributed microcracks, since microcracks affect both the wave speed and the attenuation of ultrasonic signals. Conversely, measurements of the latter will, in the light of an appropriate mathematical model, allow the deduction of such gross quantities as the number of cracks per unit volume and the average characteristic dimension of cracks.

The development of microcracks is often most pronounced near a free surface of a body, because the constraints to crack development are smaller than in the interior. It is also evident that surface-breaking microcracks have a greater tendency towards crack propagation, for the simple reasons that the stress intensity factor of a surface-breaking crack is higher than for a same-size crack in the interior. For these two reasons, it is of particular importance to develop a method for characterization of distributions of surface-breaking microcracks. Work in progress will present the theoretical framework based on the use of surface waves.

The sensitivity of Rayleigh surface waves to the presence of small surface breaking cracks is a consequence of the penetration of surface waves to approximately one wavelength. As a surface wave propagates along a cracked surface, every crack removes part of the incident wave energy by scattering processes. Consequently there is attenuation of the wave amplitude, and there are related changes of the phase velocity. In work that is in progress expressions will be derived for the coefficient of attenuation and for the phase velocity, in terms of the number of cracks per

unit surface area, a characteristic length dimension of the crack and the frequency.

Specifically, current work is extending previous results in that arbitrary orientations of the surface-breaking cracks are considered.

Another current effort is concerned with microcracks at grain boundaries or other material interfaces. In this work the reflection and transmission of Rayleigh surface waves by an interphase between identical or different materials, is being investigated. The interphase is normal to the free surface and contains a discrete disbond. The mechanical behavior of the interphase is represented by a thin layer which is modeled by extensional and shear springs. The mathematical statement of the problem is reduced to a system of singular integral equations for the displacements on the free surface and the tractions and the displacements across the interphase. Numerical solutions of this system are being computed, by the use of the boundary element method. Expressions for the reflection and transmission coefficients will be obtained by the use of half-plane Green's functions in conjunction with an elastodynamic representation integral. Both surface-breaking and near-surface disbands are being considered. Results will be presented for selected values of the elastic constants of the joined bodies, the stiffness parameters of the interphase, the length parameter(s) of the disbond and the wavelength of the incident surface wave.

In a third component of current research, experimental work is carried out both with a new self-calibrating device to measure surface wave data and with an acoustic microscope. The new device, which was developed in our laboratory, operates in the range of 1 to 10 MHz, and allows the measurement of phase velocity and attenuation of surface waves with greater accuracy than has been achieved by other investigators. Results have been obtained

for a material composed of SiC whiskers embedded in an Al matrix. For this material, data have been obtained for specimens that have been subjected to an increasing number of fatigue cycles.

Other measurements have been carried out with an acoustic microscope that is in operation in our laboratory. The microscope operates at 225 MHz. Small surface breaking cracks have been detected and work on characterization is in progress.

4. Personnel

Principal Investigator: J. D. Achenbach

The following Post-Doctoral Associates have participated or are participating in this work:

Y. C. Angel

J. Kim

Z.-L. Li

M. Kitahara

Ch. Zhang

5. Oral Presentations of Project Work since Sept. 1, 1989.

Invited Lectures

1. Gordon Conference on Composites, Jan. 2-6, 1990, "Quantitative Non-Destructive Evaluation of Composites," Ventura, CA.
2. Eighth Symposium on Energy Engineering Sciences, May 9-11, 1990. "Effects of Distributed Microcracking on Effective Wave Speed and Attenuation of Ultrasound," Argonne National Laboratory.

6. Publications for 1989 and 1990

1. (with Ch. Zhang) "Effect of an Adjacent Cavity on the Interaction of Elastic Waves with a Crack," Int. J. Engng. Sci. 27, pp. 711-722, 1989.

2. (with D. A. Sotiropoulos and Ch. Zhang), "Effects of Near-Tip Inhomogeneities on Scattering of Ultrasonic Waves by Cracks," Metallurgical Transactions 20A, pp. 619-626, 1989.
3. "Strength Evaluation by Ultrasonic Methods," Proc. ICF7, Advances in Fracture Research, K. Salama et al, eds., Pergamon Press, 1989.
4. J. Qu, "Elastic Wave Scattering by Macro-Micro Crack Configurations," Review of Progress in QNDE, 8A, Plenum Press, p. 79, 1989.
5. (with Y. Mikata), "Scattering by a Periodic Array of Collinear Cracks," Review of Progress in QNDE, 8A, Plenum Press, p. 87, 1989.
6. (with M. Kitahara and K. Nakagawa), "Backscatter from a Spherical Inclusion with Compliant Interphase Characteristics," Review of Progress in QNDE, 8A, Plenum Press, p. 47, 1989.
7. (with Ch. Zhang) "Effective Wave Velocity and Attenuation in a Material with Distributed Penny-Shaped Cracks," Int. J. Solids and Structures, accepted for publication.
8. (with Ch. Zhang) "Dispersion and Attenuation of Surface Waves due to Distributed Surface-Breaking Cracks," J. Acoust. Soc. Am., accepted for publication.
9. "Effects of Distributed Microcracking on Effective Wave Speed and Attenuation of Ultrasound," Proc. Eighth Symposium on Energy Engineering Sciences, to appear.

END

**DATE
FILMED
5107192**