9:
012263

1 OF 1

Here $f_{30}(D)$ is the least squares curve fit for the data of the ten channels below $D = 3.5 \mu m$ measured using the $30 \mu m$ orifice; $f_{100}(D)$ is the fit for the ten channels above $3.5 \mu m$ measured using the $100 \mu m$ orifice. The order of the polynomial fit is n , and a_i and b_i are constant coefficients.

**DOE/PC/79903-T12
(DE92012263)**

**SIZE DISTRIBUTIONS OF FLY ASH USING COULTER MULTISIZER: USE OF
MULTIPLE ORIFICES AND FITTING TO TRUNCATED LOG-NORMAL
DISTRIBUTIONS**

Topical Report

**By
S. Ghosal
J. L. Ebert
S. A. Self**

November 1991

Work Performed Under Contract No. AC22-87PC79903

**For
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

**By
Stanford University
Stanford, California**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

DOE/PC/79903---T12

DE92 012263

**SIZE DISTRIBUTIONS OF FLY ASH USING COULTER MULTISIZER:
USE OF MULTIPLE ORIFICES AND FITTING TO TRUNCATED
LOG-NORMAL DISTRIBUTIONS**

**By
S. Ghosal
J. L. Ebert
S. A. Self**

November 1991

Work Performed Under Contract No. DE-FG22-87PC79903

**For
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

**By
Stanford University
Stanford, California**

Contents

Preface	1
Abstract	2
Introduction	3
The Fly Ash Samples	4
The Coulter Multisizer	4
Lower Limit of Size Measurement	7
The Wet Siever	8
Combining Data Obtained Using Multiple Orifices	9
The Log-normal Distribution	10
Fitting Cumulative Data to Truncated Log-normal Distribution	12
Size Parameters of Fly Ashes	16
Conclusions	17
References	18
Appendix	19
Figures	20

Preface

This topical report summarizes some of the results of size distribution measurements made on six fly ashes performed as a part of Task 1 of the project 'Optical Properties of Coal Fly Ash' which was supported by DOE grant number DE-AC22-87PC 79903 administered through PETC. It is the manuscript of the paper of the same title that has been submitted for publication in *Aerosol Science and Technology*. The figures are shown in order at the end of the report.

Abstract

Fly ash particles, which are predominantly spherical and glassy, are produced by melting of the mineral inclusions in the coal during combustion. Particle diameters can range from sub-micrometer (micron or μm) to greater than 100 μm . The size distribution of fly ash is needed to determine its role in the radiation transfer process in pulverized coal combustors. The Coulter Multisizer is an useful instrument for sizing powders with a broad size distribution. A single Multisizer orifice can size particles only within a specific size range limited at the lower end to a few percent of orifice diameter by sensitivity and at the upper end by increasing non-linearity of the signal-volume relation. A scheme for combining data obtained using orifices of different diameters is described. The manufacturers state that the smallest particle which can be sized accurately is nominally 2% of the diameter of the orifice. However, it was found that the data for particles less than 4% of the orifice diameter were not reliable. In order to use the smaller orifices, the larger particles have to be removed from the sample. A wet-sieving apparatus, designed for accurate separation of the particles by size, is described. A log-normal distribution function, truncated outside the measurement limits, fits the size distribution data well. Size parameters for fly ashes of six representative U.S. coals are presented.

1 Introduction

In connection with a program to provide data for calculating the effects of suspended fly ash on radiant heat transfer in pulverized coal fired utility boilers, ash samples from six representative coals have been characterized with respect to their size distribution using the Coulter Multisizer. Fly ash is produced by melting of the mineral inclusions in the coal during char burnout, and consists predominantly of (closely) spherical particles of impure alumino-silicate glass.

The size distribution of fly ash is typically very broad and skewed toward small particles. For that reason, it is commonly fitted to a log-normal distribution (White (1950)). For instance, the median diameter by volume lies typically in the range 10–20 μm , whereas the median diameter by number count is typically $< 1 \mu m$. There is evidence (Flagan and Friedlander (1978)) that below 1 μm the distribution is bimodal due to a separate component of very fine particles resulting from condensation of mineral vapors. However, for radiation transfer, the submicron component makes a negligible contribution to scattering and absorption, so that the size range of interest in this work extends from approximately 1–100 μm .

For reasons discussed below, the Coulter Multisizer was chosen as the most appropriate device for sizing fly ash in this range. The basic output of this instrument is the differential distribution by volume, from which various other representations may be computed using suitable software. However, it was found that because of limitations on the dynamic range, it was necessary to use more than one orifice size. A procedure for combining data obtained using multiple orifices was developed. A wet sieve was constructed to classify the ashes to prevent large particles from blocking the small orifices.

For comparison with a log-normal distribution, there are well-known advantages in displaying the data as a cumulative distribution (by number, area, volume, etc.) on a log-probability plot. However, this requires a knowledge of the total (integrated) distribution, since the log-normal distribution is normalized on this quantity. For data

in the form of a differential distribution between some measurement limits $D = (a, b)$ say, one can only form the integral over this range and, if the cumulative distribution is normalized on the integral over this finite range, it is artificially forced to go to zero and unity at the limits (a, b) respectively. To overcome this problem, without making assumptions regarding the size distribution outside the measurement range, it was found convenient to fit the data to a truncated log-normal distribution.

Data are reported for the parameters of the best-fit log-normal distribution (i.e., the various median diameters and the geometric standard deviation) for all six ashes studied. This information, together with data on the complex refractive index of fly ashes as a function of wavelength, temperature and composition, reported in Ebert and Self (1989), should allow reliable computations of the contribution of fly ash to radiation heat transfer using Mie scattering and radiation transfer codes.

2 The Fly Ash Samples

The six fly ashes studied are representative of coals burnt at U.S. power plants. These coals are Illinois #6, Kentucky #9, Upper Freeport, PA, (all three bituminous), Beulah, ND and San Miguel, TX (both lignites) and Eagle Butte, WY (sub-bituminous). The first four samples came from Foster-Wheeler's pilot-scale combustor fitted with a cyclone followed by a baghouse. The San Miguel ash was obtained from a full-scale power plant's electrostatic precipitator. The particles in this sample are unusually large and scanning electron microscope examination of sections of particles embedded in epoxy show that the most of the particles contain bubbles (i.e., they are cenospheric). The Eagle Butte ash was collected by the fabric filter of a full-scale power plant.

3 The Coulter Multisizer

Figure 1 illustrates the working principle of the Coulter Multisizer. In essence, the instrument consists of two electrodes immersed in an electrolyte through which a small

current (0.2–0.8 mA) flows. The powder is deagglomerated by dispersing about 2–3 mg of it in a few milliliters of distilled water or electrolyte with a few drops of surfactant, and ultrasonically agitating the mixture. Several drops of the mixture are then added to the electrolyte of the Coulter Multisizer. The electrolyte is drawn by low vacuum through the orifice separating the two electrodes. The orifice diameters used range from 30 μm to 280 μm . When an insulating particle passes through the orifice, the resistance of the aperture is momentarily increased which generates a voltage pulse whose amplitude is proportional to the particle volume, within size limits expressed as fractions of the orifice diameter. The analog pulses are digitized and assigned to appropriate size bins. In this manner, tens of thousands of pulses are detected and processed, and the size distribution of the powder obtained in a minute or so. The diameter reported is actually the diameter of a sphere with the same volume as that of the particle. A detailed description of the principle and operation of the Coulter Multisizer can be found in Allen (1981).

The electronic unit of the Multisizer displays the size distribution on a video screen on the basis of number, volume or area. The data are presented either in differential or cumulative form, and for the cumulative option, the display may be as fraction oversize or undersize. The width of the size channel may be chosen such that the diameters corresponding to two adjacent channels bear either a constant difference or a constant ratio to each other. The latter option was chosen for all the results reported here. When the maximum of 256 channels are used, the constant ratio of one channel diameter to the adjacent smaller one is 1.013. The electronic unit outputs, via a serial port, the size data as the number count of particles in each size channel. PC based software was developed for reading and analyzing the data and performing calculations for size distributions based on number, area or volume. The distributions can be displayed on the computer screen and also plotted on paper using linear, log, or log-probability scales, on the basis of any of the options available to the Multisizer electronic unit described above.

The size resolution is specified as ± 1 channel in the 256 channel mode, and the aperture current is stated to be accurate to within $\pm 0.4\%$ of the setting. The instrument

was calibrated for the electrolyte (Isoton II) and for each orifice using monodisperse latex microspheres supplied by Coulter. The precision was estimated by comparing the diameter corresponding to 50% undersize by volume ($D_{50\%,v}$) for repeated measurements of the same ash sample, and was found to be within 0.7% for all the orifices.

This instrument has several advantages relative to alternative techniques for sizing powders similar to fly ash for the following reasons.

- (1) Samples of insulating powders are usually available only in a highly agglomerated form whereas individual particles have to be separated for accurate sizing. Effective deagglomeration is not possible in a gaseous dispersion (as required by competing optical or aerodynamic techniques) but a convenient and effective method for dispersion is to agitate a liquid suspension in an ultrasonic bath. A few drops of the deagglomerated suspension is then added to the Multisizer electrolyte.
- (2) A hundred thousand particles can be sized in a matter of minutes, ensuring good statistics.
- (3) The Multisizer has a wide dynamic range of 15:1 on the basis of diameter (i.e., a dynamic range of 15^3 :1 in terms of volume) for each orifice. Using the technique described here, this range can be increased to include the entire spectrum of size ranges that can be measured by the orifices supplied by Coulter.
- (4) The multi-channel analyzing feature of the instrument allows the measurement range of each orifice to be divided into a maximum of 256 size bins. Used with a large sample ($> 100,000$ particles), this high resolution permits accurate size distribution measurement.
- (5) Unlike sizing by sieving or impaction, no tedious weighing of particles is involved. Moreover, powders in which the density varies from particle to particle can be sized accurately.
- (6) Lastly, since the fly ash particles are remarkably spherical, the diameter measured by the Multisizer is the actual geometrical diameter.

4 Lower Limit of Size Measurement

It is suggested in the literature that the lower limit of size measurement using the Multisizer is set by the signal-to-noise ratio while the upper limit is set by the departure from linearity between the voltage signal and the particle volume (Allen (1981), Coulter (1987)). The nominal limits as stated by the manufacturer are 2% and 60% of the diameter of the orifice.

To test the specified lower limit, a sample of Illinois #6 baghouse ash was sized using four orifices of diameters 30, 50, 70 and 100 μm . The ash was initially sieved using the wet-siever described below with mesh size of 16 μm to prevent blockage of the smaller orifices by larger particles. The four differential size distribution functions, which are measures of the number of particles per differential size range dD at diameter D , were determined using the Multisizer. Since the four orifices measure the same ash dispersion, the measured distributions should, in principle, differ by only a constant multiple. Hence, the data were normalized by equating the number of particles of a certain size (in this case 4 μm), where an adequate number of particles were present for all four data sets.

Figure 2 shows the size distributions on a differential basis. The total sample size for each orifice was approximately 150,000. Quite correctly, the curves fall to zero near $D = 16 \mu\text{m}$. Within the limits of instrumental accuracy, and statistical uncertainty associated with sample size, the plots show that each orifice gives reliable results down to $D_{\text{particle}} \approx (0.04)D_{\text{orifice}}$. At $D_{\text{particle}} \approx (0.03)D_{\text{orifice}}$, each curve shows a maximum count, and then decreases for smaller D_{particle} , i.e., the mode of the distribution shifts to smaller diameters with decreasing orifice diameters. This seems to indicate that the Multisizer sensitivity decreases for $(D_{\text{particle}}/D_{\text{orifice}}) < 0.04$, i.e., it does not record all the signals. It is apparently not a question of signal/noise because if noise pulses were being recorded the count rate would increase. Therefore, we conclude that the manufacturer's recommended minimum size measurement limit (2% of D_{orifice}) is understated and that the smallest particle which can be accurately measured is closer to 4% of D_{orifice} . The minimum particle diameter measured by our smallest orifice of diameter 30 μm was 1.2 μm —

sufficiently small for our purpose.

Size data for a sample of 174,731 Illinois #6 fly ash particles, measured with a $100\text{ }\mu\text{m}$ orifice, are shown in Figure 3. The differential distribution by count is shown on log-log scales, normalized on the total count. The linearity of the data suggests an exponential relationship between the number distribution and the particle diameter. At the large diameter end, there are as few as one or two particles per channel compared to one to two thousand particles per channel at the small diameter end and, consequently, there is noticeable scatter in the data beyond $25\text{ }\mu\text{m}$ diameter. Appropriate functions for fitting the data will be discussed in later sections.

5 The Wet Siever

A wet sieving apparatus was designed and constructed to remove the larger particles which would otherwise cause blockage of the orifice. A schematic of the siever is shown in Figure 4. The mesh sizes of the stack of sieves decrease from top to bottom. A dilute suspension of the fly ash, ultrasonically deagglomerated in distilled water with added surfactant, flows from the top to the bottom of the stack. The important feature of this design, which distinguishes it from most commercially available ones, is the peristaltic pumping arrangement with adjustable backflow. The pump pulses the flow of the suspension through the sieves fifty times a minute. The constriction in the pump outlet causes a backflow which dislodges ash particles resting on the sieve screens until the next stroke of the pump when the action is repeated. This process induces particles smaller than the mesh size to pass through the sieve. The backflow, which controls the upward force on the particles can be adjusted using the clamp on the plastic tube. A small rubber wheel is mounted eccentrically on the shaft of a small motor running at 1200 r.p.m. to produce small amplitude vibration of the cylinder and sieve stack to agitate the particles on the sieve.

Compared to dry sieving, where agglomerates tend to persist on the screens, in

wet sieving, one is able to detach most of the small particles by ultrasonic agitation in the liquid. It is important that the ash suspension be dilute enough to prevent re-agglomeration of the particles on the screens.

For the San Miguel ash that had many large particles, a sieve of mesh size $53\ \mu m$ was used for the size separation. The smaller fraction was sized using the Multisizer with a $100\ \mu m$ diameter orifice. Next, another sample of the whole fly ash was separated with a sieve of mesh size $16\ \mu m$, and the smaller ash fraction sized using a $30\ \mu m$ orifice. Finally, the size distribution of the whole ash was determined with a $280\ \mu m$ orifice. The data obtained using the three orifice were combined in a manner described in the next section. The other ashes had very few particles of diameter larger than $50\ \mu m$. They were size separated using the $16\ \mu m$ mesh sieve and data from the $30\ \mu m$ and $100\ \mu m$ orifices were combined.

6 Combining Data Obtained Using Multiple Orifices

The process of combining data from different orifices is illustrated with the specific example of Illinois #6 baghouse ash. Initially, the $100\ \mu m$ orifice was used for sizing the ash in the diameter range $3.5\ \mu m < D < 60\ \mu m$. The ash was then wet sieved using a mesh size of $16\ \mu m$ and the smaller fraction sized using the $30\ \mu m$ orifice to obtain the size distribution in the range $1.5\ \mu m < D < 3.5\ \mu m$.

To match the two differential distribution functions at $3.5\ \mu m$, ten data points on each side of the matching point were curve fitted using least squares polynomial fits of the form

$$f_{30}(D) = \sum_{i=0}^n a_i D^i$$

$$f_{100}(D) = \sum_{i=0}^n b_i D^i$$

Here $f_{30}(D)$ is the least squares curve fit for the data of the ten channels below $D = 3.5 \mu m$ measured using the $30 \mu m$ orifice; $f_{100}(D)$ is the fit for the ten channels above $3.5 \mu m$ measured using the $100 \mu m$ orifice. The order of the polynomial fit is n , and a_i and b_i are constant coefficients.

Since the two orifices measure the same ash dispersion in the size range spanning the twenty points around $3.5 \mu m$, the two differential distributions should bear a constant ratio to each other. The match is made by multiplying the $30 \mu m$ data by the constant $C_{3.5}$, where

$$C_{3.5} = \frac{f_{100}(D = 3.5 \mu m)}{f_{30}(D = 3.5 \mu m)}$$

For the Illinois #6 ash the fit was made using linear ($n = 1$), quadratic ($n = 2$) and cubic ($n = 3$) polynomials and the values of $C_{3.5}$ were 8.46, 8.99, 8.89 respectively. The cubic and the quadratic fits gave the best results—differing only by about 1%; consequently the cubic fit ($n = 3$) was used. On Figure 5, the twenty data points are plotted along with $f_{30}(D)$ and $f_{100}(D)$, shown as solid lines. Figure 6 shows the two individual distributions as well as the combined one, on a cumulative basis.

This procedure can be extended to data sets corresponding to more than two orifices. However, the size ranges over which the polynomial fits are performed should contain sufficiently large samples (>5000 particles).

7 The Log-normal Distribution

The two parameter log-normal distribution function is often used to represent the size distribution of broad particulate polydispersions. Many naturally occurring and man-made particle dispersions are found to fit the log-normal distribution rather well. A detailed description of its properties and applications can be found in Aitchison and Brown (1957) and Crow and Shimizu (1988). Specific applications in particle science are discussed in Herdan (1960), Allen (1981) and Flagan and Seinfeld (1988). In the field of particle control technology, it is conventional to fit fly ash size data to a log-normal

distribution (White (1963)).

The log-normal distribution is one in which the logarithm of the variate obeys the normal law of probability.

$$\frac{dF(D)}{d(\ln D)} = \frac{1}{\sqrt{2\pi} \ln \sigma_g} \exp \left[-\frac{1}{2} \left(\frac{\ln D/D_n}{\ln \sigma_g} \right)^2 \right] \quad (1)$$

The variate, D , in this case is the particle diameter, and $F(D)$ is the cumulative undersize distribution over all sizes up to diameter D . Hence $\frac{dF(D)}{d(\ln D)}$ is the fraction of particles with diameter within $d(\ln D)$. Half the particles have diameters smaller than the median diameter, D_n , i.e., $D_n = D_{50\%}$. The geometric standard deviation, σ_g , is a measure of the breadth of the distribution. Approximately 68% of the particles have diameters between $\sigma_g D_n$ and D_n/σ_g . A value of $\sigma_g > 2$ implies that the powder has a very broad distribution while a closely monodisperse powder has $\sigma_g \rightarrow 1$.

The cumulative undersize (or oversize) form of the log-normal distribution is widely used because, whether plotted by number count, area, volume, etc., it plots as a straight line on a log-probability graph. This gives a simple method of presenting experimental data from which one can quickly determine the two parameters D_n and σ_g . While $D_n = D_{50\%}$, σ_g can be obtained from any of the following relations

$$\sigma_g = \frac{D_{84.13\%}}{D_{50\%}} = \frac{D_{50\%}}{D_{15.87\%}} = \sqrt{\frac{D_{84.13\%}}{D_{15.87\%}}}$$

As σ_g increases, the slope of the size distribution decreases. The cumulative count undersize is given by:

$$F(D) = \int_{-\infty}^{\ln D} \frac{1}{\sqrt{2\pi} \ln \sigma_g} \exp \left[-\frac{1}{2} \left(\frac{\ln x/D_n}{\ln \sigma_g} \right)^2 \right] d(\ln x) \quad (2)$$

At this point, it is useful to define the moments of the log-normal distribution because there appear to be differences in the use of the terms area and volume distributions in particle statistics and mathematical statistics (Crow and Shimuzu (1988)). Equations 1 and 2 represent the distributions by number, also referred to as the count distribution or the size-frequency distribution, in which D_n is the median diameter (sometimes referred to as the geometric mean diameter) and σ_g is the geometric standard deviation. The

size distributions by surface area and volume, as defined in particle statistics, are the distributions of the second and third moments, about the diameter, of the number distribution. The j^{th} moment distribution for a log-normal function, on a cumulative undersize basis, is given by

$$F_j(D) = \int_{-\infty}^{\ln D} x^j \frac{1}{\sqrt{2\pi} \ln \sigma_g} \exp \left[-\frac{1}{2} \left(\frac{\ln x / D_n}{\ln \sigma_g} \right)^2 \right] d(\ln x)$$

It can be shown that this distribution is also log-normal with parameters $\bar{D}_j = D_n \exp(j \ln^2 \sigma_g)$ and σ_g . Thus, $F_2(D, D_a, \sigma_g)$ and $F_3(D, D_v, \sigma_g)$ represent the area and volume distributions, respectively, where

$$D_a = \bar{D}_2 = D_n \exp(2 \ln^2 \sigma_g)$$

$$D_v = \bar{D}_3 = D_n \exp(3 \ln^2 \sigma_g)$$

On log-probability axes, the moment distributions plot as parallel straight lines with the same slope. Another useful size is the Sauter mean diameter, D_{32} . It is the ratio of the third moment of the distribution to the second moment, each integrated over the entire diameter range, and is given by

$$D_{32} = D_n \exp\left(\frac{5}{2} \ln^2 \sigma_g\right)$$

8 Fitting Cumulative Data to Truncated Log-normal Distribution

The cumulative log-normal distribution is defined for the infinite range, $D = (0, \infty)$, and is normalized on the integral of the differential distribution over this infinite range, so that $F(\infty) = 1$. Hence, in plotting experimental data one should normalize the measurements on the integral of the quantity (i.e., total number, area or volume) over the infinite range. For some particle sizing techniques, e.g., those based on sieving, settling or impaction, the integral over the infinite range is either directly measured or

simply derived from the data. However, in other techniques, e.g., optical and Coulter Multisizer, there are bounds $D = (a, b)$, say, to the measurement range and one has no information on the distribution for $D < a$ and $D > b$.

If one attempts to fit the cumulative data to a log-normal distribution (e.g., by plotting $F(D)$ on log-probability axes) by normalizing on the total count in the range (a, b) , then even if the distribution is truly log-normal over the whole range, the plotted data will not fall on the true straight line because the part of the distribution outside the measurement range is not included in the normalization (see Figure 7).

Of course, one can always plot the data directly in differential form over the range (a, b) and fit it to some assumed model distribution by a suitable computational algorithm. Besides varying the model parameters (e.g., D_n and σ_g for a log-normal distribution), one will also have an arbitrary amplitude to vary in order to fit the data. Clearly, fitting the data to any model defined for the infinite range involves some assumption about the size distribution outside the measurement range.

In these circumstances, a more logical procedure is to fit a truncated log-normal cumulative distribution to the experimental (truncated) cumulative distribution, since this avoids any assumptions about the form of the distribution outside the measurement range. This fit can be made using any of a number of suitable curve-fitting algorithms without introducing arbitrary assumptions.

The form of the log-normal distribution function, truncated outside the measurement limits a and b chosen to represent the measured fly ash size distributions is shown below:

$$\frac{dF^{a,b}(D)}{d(\ln D)} = \frac{\frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln D/D_n}{\ln \sigma_g} \right)^2 \right]}{\int_{\ln a}^{\ln b} \frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln x/D_n}{\ln \sigma_g} \right)^2 \right] d(\ln x)} ; \quad a \leq D \leq b \quad (3)$$

In the limit $a \rightarrow 0$ and $b \rightarrow \infty$, the denominator $\rightarrow 1$ and distribution (3) approaches distribution (1).

The cumulative undersize distribution function $F^{a,b}(D)$, obtained by integrating Equation 3, can be expressed in terms of the error function as

$$F^{(a,b)}(D) = \frac{\operatorname{erf}\left(\frac{\ln D/D_n}{\sqrt{2 \ln \sigma_g}}\right) - \operatorname{erf}\left(\frac{\ln a/D_n}{\sqrt{2 \ln \sigma_g}}\right)}{\operatorname{erf}\left(\frac{\ln b/D_n}{\sqrt{2 \ln \sigma_g}}\right) - \operatorname{erf}\left(\frac{\ln a/D_n}{\sqrt{2 \ln \sigma_g}}\right)} ; \quad a \leq D \leq b \quad (4)$$

As shown in the Appendix, the moment distributions of the truncated log-normal distributions bear the same relationships to the number distribution as in the untruncated case described in the previous section.

The best-fit truncated log-normal function yields value of $\bar{D}_j$ and σ_g (which are the parameter values of the j^{th} moment of the untruncated distribution). This $\bar{D}_j$ is not the same as $D_{50\%}$ of the data. The relative difference (or 'error'), $\eta = (D_{50\%} - \bar{D}_j)/\bar{D}_j$, depends on the degree of truncation, as measured by $(\frac{\bar{D}_j}{a\sigma_g})$ and $(\frac{b}{\bar{D}_j\sigma_g})$. As shown in Figure 8, when the latter parameters are large (slight truncation) the 'error' η is small. The circled data point represents the truncation conditions ($\eta = 2\%$) in fitting the cumulative volume distribution data for the Kentucky #9 baghouse ash using orifices of diameter 30 μm and 100 μm . At the other extreme, Figure 8 indicates that η is large if either $(\frac{\bar{D}_j}{a\sigma_g})$ or $(\frac{b}{\bar{D}_j\sigma_g})$ are small ($\ll 1$). This extreme implies that the size limits a and b are too large or too small respectively for the given size distribution, i.e., the orifice size(s) are inappropriate for the particular ash.

The function $F_3^{(a,b)}(D, D_v, \sigma_g)$ was fitted to the data obtained from the Multisizer measurement for all the ash samples. The parameters D_v and σ_g are computed by minimizing the r.m.s. error between $F_3^{(a,b)}(D, D_v, \sigma_g)$ and the data, using Nelder and Mead's multidimensional downhill simplex method for function minimization described in Press et al (1986). It is an iterative procedure which converges, in this case, in less than two minutes on an IBM PC AT. Trial values for D_v and σ_g , needed to initiate the computation, and obtained from the volume distribution data, are $D_{50\%,v}$ and $\sqrt{\frac{D_{84.13\%,v}}{D_{15.87\%,v}}}$, respectively.

In Figure 9, the best-fit truncated log-normal function is shown for the volume distribution data of Illinois #6 baghouse ash. The values of D_v and σ_g are 9.70 μm and 3.02, respectively. D_n , D_a and D_{32} are calculated to be 0.25 μm , 2.85 μm and 5.25 μm .

Because the number of particles corresponding to diameters over $20\ \mu\text{m}$ decreases very quickly (as shown in Figure 3), there is considerable scatter in the volume distribution in Figure 9 in this range. This statistical scatter can only be reduced either by increasing the sample size or by sizing with fewer channels (e.g. 64). However, the resolution will then decrease and the size distribution will be less accurate over the full range of diameters. The scatter at the large diameter end is acceptable as long as the sample size is large ($> 100,000$) and the best-fit log-normal function represents the data well in the $1\text{-}10\ \mu\text{m}$ range, which contains $\geq 99\%$ of the detected particles (by number) for most ashes. The 'shoulder' in the distribution between $2\ \mu\text{m}$ and $4\ \mu\text{m}$ is probably a residual error arising from the data combining process.

The cumulative distribution for the same ash is presented on log-probability axes in Figure 10, with every tenth data point plotted. The scatter seen in the differential distribution is smoothed out on the cumulative plot. Figure 11 illustrates the effect of truncation as discussed earlier by extending the best-fit log-normal function down to $0.1\ \mu\text{m}$ on the assumption that the size distribution of ash particles smaller than $1.2\ \mu\text{m}$ is given by the same log-normal function. The graph is now a straight line at the small size end.

Measurements of ash size distribution in the submicron region in other studies suggest that fly ash is commonly bimodal (Flagan and Friedlander (1978)). However, the contribution of the submicron particles to the higher moment distributions is very small. Moreover, submicron ash particles play a negligible role in radiation transfer in coal combustors because of their low extinction efficiencies at relevant wavelengths.

Cumulative size distributions based on diameter, surface area and volume plotted on the same axes are shown in Figure 12 for San Miguel fly ash. Because the distributions have the same σ_g , they plot as parallel straight lines on log-probability axes, except close to the measurement limits. The sample sizes for orifices of diameters $30\ \mu\text{m}$, $100\ \mu\text{m}$, and $280\ \mu\text{m}$ are 132,088, 151,495 and 194,270, respectively. The $100\ \mu\text{m}$ and $280\ \mu\text{m}$ data are matched at $10.5\ \mu\text{m}$, and the parameters of the best-fit log-normal function are

$D_v = 32.23 \mu m$ and $\sigma_g = 2.89$.

9 Size Parameters for Fly Ashes

Table 1 presents the parameters D_n , D_a , D_v , D_{32} , and σ_g , (corresponding to the best-fit truncated log-normal distributions) for the six fly ashes studied.

The values of D_v and σ_g tend to fall in the ranges of 9–15 μm and 2.0–3.0, respectively with two exceptions. The Eagle Butte ash ($\sigma_g=3.45$) has an unusually broad size distribution, with particles of diameter between 4 μm and 47 μm accounting for only 68% of the total volume. The Texas lignite ash, which is almost entirely cenospheric, contains many large particles. Although only 50% of the Kentucky # 9 baghouse ash particles have diameters greater than 1.46 μm , this fraction contributes more than 99.5% and 97.5% of the total volume and area, respectively. For many of the ashes, the values of D_n are below the lower limit of measurement. In these cases (as shown in Figure 3), the number of particles detected in each size channel continue to increase with decreasing diameter.

For comparison, the differential area distribution for all the fly ashes are presented in Figure 13. The solid symbols show whole ashes and the open symbols show ashes separated by cyclone. Almost all the total particle area is due to ash particles with diameter less than 50 μm . This particular cyclone does not exhibit a sharp cut-off point. However, as expected, D_a , is larger for the cyclone ash (Table 1), since the cyclone traps many of the larger particles before the ash is carried into the baghouse. The latter traps particles of a wider size range and, as a result, the baghouse ashes have larger geometric standard deviations (and, hence, broader distributions as seen in Figure 13). All of the three sets of baghouse and cyclone ashes show both trends.

Table 1: Size Distribution Parameters for Fly Ashes Studied

Fly ash	Coal Type	Collection	D_n	D_a	D_v	D_{32}	σ_g
Kentucky #9	Bituminous	Baghouse	1.46	5.49	10.64	7.64	2.26
Kentucky #9	Bituminous	Cyclone	3.58	9.58	15.67	12.26	2.02
Illinois #6	Bituminous	Baghouse	0.25	2.85	9.70	5.25	3.02
Illinois #6	Bituminous	Cyclone	2.58	8.24	14.72	11.01	2.14
Beulah, ND	Lignite	Baghouse	0.38	3.96	12.80	7.12	2.95
Beulah, ND	Lignite	Cyclone	1.34	5.65	11.63	8.11	2.34
Upper Freeport, PA	Bituminous	Baghouse	0.39	3.21	9.25	5.45	2.80
San Miguel, TX	Lignite	ESP	1.10	10.47	32.23	18.37	2.89
Eagle Butte, WY	Sub-bituminous	Fabric Filter	0.14	2.95	13.68	6.35	3.45

10 Conclusions

The size distributions of six coal fly ashes were measured using the Coulter Multisizer. A technique for measuring particle sizes over a broad range (from about a micron to hundreds of microns) using several orifice sizes is described. The method involves an accurate size separation of the ash by wet-sieving. A best-fit log-normal function, truncated outside the measurement limits, is fitted to the volume distribution data. Size distribution parameters for six fly ashes are presented and their significance discussed.

Acknowledgements: This work was supported by DOE grant number DE-AC22-87PC 79903. The authors would like to thank Rod Leach for his help in the design and construction of the wet-siever.

References

- [1] Aitchison, J. and Brown, J. A. C. (1957) *The Lognormal Distribution*. Cambridge University Press, Cambridge, U.K.
- [2] Allen, T. (1981) *Particle Size Measurement*. Chapman and Hall, London, p. 392.
- [3] Coulter Electronics Limited. (1986) *Fine Particle Application Notes for Coulter Counters*. Luton, U.K.
- [4] Crow, E. L. and Shimizu, K. (1988) *Lognormal Distributions*. Marcel Dekker Inc., New York.
- [5] Ebert, J.L. and Self, S.A. (1989) *The Optical Properties of Molten Coal Slag*. In *Heat Transfer Phenomena in Radiation, Combustion, and Fires* (R. K. Shah, ed.). American Society of Mechanical Engineers, New York, HTD-Vol. 106, Book No. H00498-1989, p. 123.
- [6] Flagan, R.C. and Friedlander, S.K. (1978) *Particle Formation in Pulverized Coal Combustion—a Review*. In *Recent Developments in Aerosol Science*. (D .T. Shaw, ed.). Wiley, New York, p. 25.
- [7] Flagan, R. C. and Seinfeld, J. H. (1988) *Fundamentals of Air Pollution Engineering*. Prentice Hall, Englewood Cliffs, New Jersey, p. 325.
- [8] Herdan, G. (1960) *Small Particle Statistics*. Butterworth, London, p. 81.
- [9] Press, W. H. et al (1986) *Numerical Recipes: The Art of Scientific Computing*. Cambridge University Press, Cambridge, U.K., p. 305.
- [10] White, H. J. (1963) *Industrial Electrostatic Precipitation*. Addison-Wesley, Reading, Massachusetts, p. 60.

Appendix

Consider F_j , the integral of the j^{th} moment of the log-normal distribution, about the diameter, over all possible diameters:

$$F_j = \int_{-\infty}^{\infty} x^j \frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln x/D_n}{\ln \sigma_g} \right)^2 \right] d(\ln x) \quad (\text{A1})$$

By successively substituting the variables $u = \frac{\ln x/D_n}{\sqrt{2 \ln \sigma_g}}$ and $z = u - \frac{j \ln \sigma_g}{\sqrt{2}}$, (A1) can be integrated to obtain

$$F_j = \exp \left(j \ln D_n + \frac{1}{2} j^2 \ln^2 \sigma_g \right) \quad (\text{A2})$$

The cumulative j^{th} moment of the truncated log-normal distribution is written as

$$F_j^{(a,b)}(D) = \frac{\int_{\ln a}^{\ln D} x^j \frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln x/D_n}{\ln \sigma_g} \right)^2 \right] d(\ln x)}{\int_{\ln a}^{\ln b} x^j \frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln x/D_n}{\ln \sigma_g} \right)^2 \right] d(\ln x)} ; \quad a \leq D \leq b \quad (\text{A3})$$

By dividing the integrand in both the numerator and the denominator (A3) by F_j (from (A2)) and replacing x^j by $\exp(j \ln x)$, (A3) may be put in the form:

$$F_j^{(a,b)}(D) = \frac{\int_{\ln a}^{\ln D} \frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln x/\bar{D}_j}{\ln \sigma_g} \right)^2 \right] d(\ln x)}{\int_{\ln a}^{\ln b} \frac{1}{\sqrt{2\pi \ln \sigma_g}} \exp \left[-\frac{1}{2} \left(\frac{\ln x/\bar{D}_j}{\ln \sigma_g} \right)^2 \right] d(\ln x)} ; \quad a \leq D \leq b$$

where

$$\bar{D}_j = D_n \exp \left(j \ln^2 \sigma_g \right)$$

This, too, is a truncated log-normal distribution with the same geometric standard deviation, σ_g , and a median diameter, $\bar{D}_j$. The Sauter mean diameter, D_{32} , is found to be: $D_{32} = F_3/F_2 = D_n \exp \left(\frac{5}{2} \ln^2 \sigma_g \right)$.

Figure 1: The Coulter Multisizer Principle

Figure 2: Size Distributions using Different Orifices

Figure 3: Size Distribution by Count with 100 μm Orifice

Figure 4: The Wet-Siever

Figure 5: Matching Data from 30 μm and 100 μm orifices at 3.5 μm

Figure 6: Combining Size Data from Two Orifices for Illinois #6 Ash

Figure 7: The Log-normal Distribution with Size Parameters Corresponding to those of Kentucky #9 Baghouse Ash

Figure 8: Effect of Truncation on Relation between D_n and $D_{50\%}$

Figure 9: Truncated Log-normal Function Fitted to Differential Size Data

Figure 10: Truncated Log-normal Function Fitted to Cumulative Size Data

Figure 11: Cumulative Data with a Truncated Log-normal Function Extended at the Lower End

Figure 12: Size Distributions of San Miguel Ash based on Volume, Area and Number

Figure 13: Area Distributions of Fly Ashes

END

**DATE
FILMED**

6 10 8 192