010785

1 OF 1

dissociates to form an extract molecule, as in the direct mechanism. It is the direct process of equation 1 that takes place in the direct absorption of light by the coal particles at the beginning and after the solvent refreshment. It is the indirect process described by equations 2 - 4 that occurs after extract

DOE/PC/91299--T1

U.S. DOE Patent Clearance is not required prior to the publication of this document.

TECHNICAL PROGRESS REPORT

for Period 10/01/91 to 12/31/91
on DOE/PETC Grant No. DE-FG22-91-PC91299

DOE/PC/91299--T1

DE92 010785

"Magnetic Relaxation - Coal Swelling, Extraction, Pore Size"

David C. Doetschman, Principal Investigator
Department of Chemistry, State University of NY, Binghamton, NY 13902-6000

MAR 8 1992

The grant activities during this period fall into four categories: (a) Completion of preparatory work, (2) Procedure refinement and actual preparation of whole coal, coal residue, coal extract and swelled coal samples for NMR studies, (3) Related studies of coal photolysis that employ materials from preliminary extractions and that examine the u.v.-visible and mass spectra of the extracts and (4) Continued investigations of the pulsed EPR characteristics of the whole coal samples that were prepared in the first quarter of the grant.

I. Preparatory Work

Completion of preparations included the integration of the new Micronow EPR magnetic field controller and data acquisition unit with the National Instruments IEEE bus controller in our IBM PS2 model 30 computer. A BASIC program has been completed with which subsequent 4 KByte EPR spectra will be run, acquired, averaged and stored on disk. A program has also been written for plotting these spectra via IEEE bus on our Soltec plotter. Sample cells, windows and presses, etc. have been organized for obtaining the IR spectra of the extracts. The research assistant working on the project, Mr. Mehlenbacher, has completed his training on the Bruker 360 MHz NMR spectrometer and has begun designing the pulse program or programs for potential use in the T_1 measurements of the samples.

II. Sample Preparation Procedure

Preliminary testing and refinement of the ultrasonic extraction, centrifugation, filtration and sample drying steps in the absence of air have been done. The actual extractions required for the NMR studies are well under way and some of the whole coal samples for the NMR studies planned for the first year of the project have been prepared.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

FEB 03 1992

III. Related Studies

Some of the coals selected for study in this project were extracted with tetrahydrofuran for reasons beyond the scope of this project. This has given us preliminary experience with the extraction process, the type of yields to be expected from different coals, the u.v.-visible absorption and mass spectra of the extracts and residues. Some resources of the grant have gone toward these studies and we report on them here in the form of a publication in draft form, entitled "Photochemical Extraction from Tetrahydrofuran Slurries of Representative Coals," attached to this report in the Appendix.

IV. Pulsed EPR

Work has continued on the pulsed EPR of the eight premium U.S. coal samples prepared by the Argonne National Laboratory that we began in advance of the extraction and swelling work. The analytical characterization of these samples, the oxygen-free preparation of the samples in EPR tubes and the pulsed EPR equipment were described in the 09/01/91 to 09/30/91 quarterly report. In that previous report work had been focused on the determination of the spin-spin relaxation times, T_2 , of the samples. In this quarter work has been focused on the determination of lineshapes at room temperature by pulsed EPR under conditions in which attempts were made to avoid instrumental broadening or the effects of instantaneous diffusion. Although it proved to be impossible to avoid both, the results reveal some interesting, previously unrecognized characteristics of the EPR lines in the coal samples.

The pulsed EPR spectra of the macerals with broad lines were obtained under several different conditions for different purposes. All of the methods essentially eliminated the contribution from the FID (free induction decay), mainly from the narrow EPR line of the inertinite macerals. All of the spectra obtained were the field dependencies of the echo intensities detected at the time of the echo 2τ or $2\tau + T$, where τ is the (initial) microwave pulse interval and T is the second interval in a three-pulse sequence, when employed. While in principal phase cycling methods can be devised to eliminate the FID that is also detected at 2τ , in practice we sometimes found the required phase and intensity adjustments difficult to achieve and maintain. In such cases we chose instead to subtract a trace in which the initial probe pulse was omitted under otherwise identical conditions.

One set of conditions employed in obtaining field-swept echo spectra was a $t_p/2-\tau-t_p$ sequence of pulses in which the pulse length parameter, $t_p = 128$ ns and the power level was such that $H_1 = 0.29$ G. The conditions were chosen by successive reductions of the power level until no further reduction in the linewidth was achieved. (Theoretically from the width of the magnetization probed by such a pulse, power broadening should be approximately 0.9 G.) However, signal intensity prevent us from

using a probe pulse much longer than 64 ns, which gives a theoretical uncertainty broadening of 5.6 G. Under these conditions the spectra were often weak and required $10^2 - 10^3$ scans for accurate determination of EPR linewidths as a function of τ . In all of the cases examined the results gave single, broad EPR lines, sometime with minor asymmetry. We examined the Upper Freeport, Wyadak, Illinois #6 and Lewiston-Stockton coals in this way. It is clear from the power levels at which these experiments were run in comparison with the studies of T_2 in the previous quarter that the effects of instantaneous diffusion were being successfully avoided. Only in the Upper Freeport coal did the observed linewidth change with pulse interval τ , increasing by about 2 Gauss to the long τ limit. The average (long τ -limiting) values of the observed linewidths at half-height are 7.1 ± 0.1 G (Upper Freeport), 9.5 ± 0.8 G (Wyodak), 10.2 ± 0.5 G (Illinois #6), 8.9 ± 0.3 G (Lewiston-Stockton). As expected, these results are generally 2 - 4 Gauss wider than the CW EPR values.

Another set of conditions employed was the field sweep of the echo intensity from a soft π - τ -hard $\pi/2$ pulse sequence with a 384 ns soft probe pulse and a 32 ns hard pulse. However, the π -probe pulse theoretically would lead to less than 0.3 Gauss power broadening and 0.9 Gauss uncertainty broadening. Both a two-pulse cycle to remove the FID from the hard pulse only and a full four-phase cycle to remove all FID were employed. An example of the unusual spectra that were recorded with the two-phase cycle is the $\tau = 600$ ns spectrum of the Illinois #6 coal shown in Figure 1. The 25 Gauss width of this unusually shaped spectrum is, to our knowledge, unprecedented!

Since we do not observe a spectrum with the multiple humps shown in Figure 1 when instantaneous diffusion processes are carefully eliminated, it is plausible that these processes may be responsible for the unusual shape. Instantaneous diffusion could lead to a faster decay at the center of the EPR spectra where it may represent species at a higher spin concentration than elsewhere. This would give a spectrum in which the central part of the spectrum is missing due to its decay prior to $2\tau = 1200$ ns. In Figure 2 is shown a 2D (two-dimensional) profile of echo intensity versus magnetic field and pulse interval τ for the Pittsburgh #3 coal, using the full, four-phase cycling. This profile is very typical of the results obtained from all of the coal samples. We could not obtain results at $\tau < 200$ ns and are therefore not observing much of the decay due to instantaneous diffusion. The profile, however, does appear to display a faster decay time between the double humps than is observed on the high-field side of the high-field hump and on the low-field side of the low-field hump, in agreement with the instantaneous diffusion explanation.

Whatever may be the explanation of the double hump, from the coal scientist's viewpoint it is the unprecedentedly larger EPR linewidths observed on these spectra that are most relevant. These results show that there exists in the distribution of free radical species in all of the coals, a small but readily detectable number of free radicals with linewidths of 25 Gauss or more, in addition to the narrower ordinarily observed spectrum discussed above. This raises the interesting possibility that there exists some stable aliphatic radicals with alpha protons ($a_H \sim 7 - 15$ G) and/or beta methyl groups ($a_{CH_3} \sim 20 -$

25 G). The existence of such species in coals has been dismissed on grounds of chemical instability. Alternatively, these observations provide explicit evidence for the widely held belief that there exist relatively small aromatic or heteroaromatic, odd-alternate free radicals with as few as two or three rings. We also note that the g values of the less concentrated species with the broad spectrum tend to be higher than the g values of the prevalent species with the fast decay (hole in the spectrum). This would suggest that the less concentrated, broad-spectrum species may contain more heteroatoms than the prevalent, narrow-spectrum species ordinarily observed in the EPR spectrum. This g value aspect, estimates of the numbers of broad-line species and correlations with the particular types of coal and their maceral compositions, should be examined in future work.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Figures

1. Pulsed X-band EPR spectrum of the Illinois #6 coal obtained from a field sweep of the two-pulse echo with pulse interval $\tau = 600$ ns. Conditions keep spectrum broadening to less than 1.2 G but do not preclude instantaneous diffusion effects. For details see text.
2. 2D profile of the pulsed X-band EPR spectrum of the Pittsburgh #8 coal as a function of the pulse interval τ . Conditions keep spectrum broadening to less than 1.2 G but do not preclude instantaneous diffusion effects. For details see text.

Figure 1.

Figure 2.

**DRAFT COPY
NOT IN FINAL FORM**

Photochemical Extraction from Tetrahydrofuran Slurries of Representative Coals

David C. Doetschman, Eiko Ito* and Osamu Ito[†]

Department of Chemistry
State University of New York at Binghamton
Binghamton, NY 13902-6000
U.S.A.

and

Dr. Hiroshi Kameyama
Senshu University
Tahlnomaki, Minami-Saki
Ishinomaki-986
Japan

Abstract

When representative coals were suspended in tetrahydrofuran (THF), ultraviolet (UV) light irradiation of the slurries yielded an increased rate of extraction for most coals. Some subbituminous coals were insensitive to photochemical extraction. Removal of the extract and refreshment of the solvent increased the photochemical extraction yield in comparison with continuous irradiation while the extract accumulated in the solvent. The photochemical extraction yield from a bituminous coal irradiated with all wavelengths of a high pressure Hg-Xe arc lamp greater than 230 nm was approximately twice the yield with output at wavelengths greater than 310 nm. The time profiles of the extraction yields, monitored for convenience with the extract UV spectra and mass spectrometry, have been employed to characterize the photochemical extraction process in the range of coals studied.

*Permanent address: Mayaki Medical School, Saiwai Cho, Miyagino-ku, Sendai-983, Japan.

[†]Permanent address: Institute for Chemical Reaction Science, Tohoku University, Katahira 2 Chome, Aoba-ku, Sendai 980, Japan.

Introduction

Under sunlight, coal weathering affects a variety of coal properties. For example, oxidation appears to affect the ability of coals to agglomerate (1). These effects may be either a direct result of the irradiation of the surfaces of the coal particles with sunlight or the acceleration of thermal processes. Both effects are believed to be involved in the oxidative weathering of coal but have not been evaluated separately. The direct oxidative process is probably caused by bond cleavage via photoexcitation and the indirect process simply by accumulation of thermal energy in coal piles.

The photolysis of coal suspensions in a solvent was first investigated by Hayatsu *et al.* (2-5). They found that photooxidation occurred when acidic aqueous suspensions of coals in a quartz flask (continuously bubbled with air) were irradiated with a high pressure mercury arc lamp. The eight-day irradiation of a lignite and a bituminous coal yielded 25 - 30 wt% of extracts that were soluble in water, methanol and chloroform. Photolysis of the residue with the same procedure further oxidized 22 - 24 wt% of the residue into soluble materials. Total extraction yields were 38 - 48 wt%. By mass spectroscopic characterization of the soluble materials, they evaluated the organic constituents of the coals.

Yürüm and Yiginus reported the effect of UV light on the sulfuric acid catalyzed depolymerization of a lignite in the presence of phenol (6). The larger amounts of soluble material that were formed as a result of the UV irradiation were attributed to an increased degree of phenol incorporation. Absorption of UV light by the phenol may have been initiating photochemistry involving the phenol. Yanagawa and Anazawa attempted to extract three coals photochemically in a tetralin slurry in a Pyrex vessel under a nitrogen atmosphere (7). They found that the benzene soluble extracts were increased by irradiation of a lignite and a subbituminous coal, but not by irradiation of a bituminous coal. These experiments show that light wavelengths longer than 310 nm may be used to cleave the macromolecules of the coals photochemically and tetralin acts as the hydrogen donor.

Hydrogen and CO₂ were generated photocatalytically by irradiation of Pt on TiO₂ in contact with fossil fuels (8,9).

In the present study, we employ solvents that are transparent in the UV region in order to

photoexcite particles of representative coals in suspension in solvents under a nitrogen atmosphere. Because of evidence that the extraction process itself renders the solvent no longer transparent, we also investigated the effect of periodically replacing the solvent and extract with fresh solvent during the irradiation in order to maintain the solvent transparency better. The results suggest the possible future study of a successive or continuous extraction technique in conjunction with the photolysis of coal suspensions in order to achieve improved maintenance of solvent transparency.

Experimental

A wide representation of coals was selected for this study, ranging from a brown coal to a semi-anthracite (10,11). The C, H and O elemental analyses of the coals are included in Table 1. Most of the coals were ground to 60-mesh (U.S.A.) powders, as received.

The procedure for the extraction that was carried out before the photolysis of the coals (pre-extraction), the photochemical extraction (photo-extraction) and the thermal extraction control experiment performed in the absence of light after pre-extraction are shown schematically in Figure 1. In the pre-extraction, the original coals were extracted with a Soxhlet extraction or by refluxing with the same solvent that was used in the photochemical extraction and control experiments. Tetrahydrofuran (THF) was the main solvent used in this study because it is transparent in the UV region >230 nm and has a high coal extract solubility in comparison with paraffinic solvents such as the hexanes. The THF was distilled before use to remove the stabilizer. The pre-extraction residue yields are given in Table 1. The percentage ash contents of the pre-extraction residue were calculated from the pre-extraction yields under the assumption that the "ash contents" of the original coals remain with the residue. The calculated percentage ash contents of the pre-extraction residues are also given in Table 1.

The residues from the pre-extractions, usually about 0.1 g, were maintained in suspension in 10 ml of solvent in a 13-mm i.d. quartz tube with a magnetic stirrer. The slurries were first purged by bubbling with nitrogen gas and sealed before beginning the irradiation with a 1 kW high pressure Hg-Xe lamp (Oriental Optical Corp.). About 130 milliwatts of light between 230 and 390 nm is reaching the

sample. The setup employed in the irradiation of the coal is shown schematically in Figure 2. In spite of the use of the 10 cm H₂O heat filter and the CS7-54 Corning 210 - 390 nm bandpass filter, considerable heating of the sample and solution occurred. Therefore, a constant temperature was maintained at a value below 60° C, depending on the particular suspension, by cooling with forced air. In the control experiments, thermal extractions were performed in a water bath maintained at the same temperature as the photochemical extraction.

The photochemical extraction and the thermal control extraction processes were monitored by removing aliquots periodically and examining their UV-visible absorption spectrum (Hewlett-Packard 8451A). Dilution of the aliquots was usually necessary in order to obtain a suitable extract concentration because of the very high initial absorbance of the aliquots. The extracts from the completed photochemical and control extraction experiments were dried in a vacuum desiccator (<10 µm Hg) at about 100° C for 12 hours and then weighed. Weight based effective absorption coefficients were calculated on the basis of the extract weights and the absorbance of solutions of the extracts.

In order to examine the photo-extraction of a coal with a more efficient pre-extraction solvent, the Upper-Freeport coal was pre-extracted with the mixed solvent, *N*-methyl-2-pyrrolidinone-CS₂ (MP-CS₂). The experimental procedure is summarized in the scheme shown in Figure 3, in which both the residue and extract of the MP-CS₂ pre-extraction were also subjected to THF pre-extraction before photolysis. The photo-extraction solvent was THF.

Field desorption mass spectra were obtained from the pre-extraction residues of the coals on JEOL JMD-DX302 with an accelerating potential of 3.0 kV.

Photo-extraction experiments in hexane were also performed on the samples in a similar manner. Appreciable increases in the UV absorbance were observed for some of the bituminous coals but the weights of the extracts were too small to perform meaningful experiments.

Results and Discussion

1. The Pre-Extraction Yields

The variation of the THF pre-extraction yields from the original coal samples with coal rank are shown in Table 1. The yields appear to decrease with increasing coal rank, with the exception of the Beulah-Zap coal. This trend suggests that it is the polar organic compounds in the original coals that are soluble in the relatively polar THF solvent. The low solubility of the Beulah-Zap coal may indicate that it contains a more highly cross-linked macromolecular network that is stable to THF. The exceptionally low pre-extraction yield from the Lower Kittanning, semi-anthracite coal may be due to its highly aromatized molecules for which THF is not an effective solvent. In comparison with the pyridine extraction yields that show a maximum for bituminous coals with 86% C (12), the THF extraction yields show a maximum at coals with significantly lower rank.

2. The Effect of Slurry Concentration

Figure 4 shows plots of the cumulative absorbance at 300 nm of the THF extracts versus time of irradiation of slurries of the pre-extract residue from Yubari coal at two concentrations of the residue slurry in THF. Results for the corresponding control, thermal extraction experiments are shown for comparison. Note that in this concentration range a proportionately greater yield of photochemical product was achieved with 10 g/l of extract in THF than with 5 g/l, assuming that absorbance is proportional to extract yield (i.e., that extract chemical compositions from the same coal remain the same). On the other hand, the thermal extraction yield was almost proportional to the slurry concentration.

For experiments at the much higher concentration of 100 g/l, which are not shown in Figure 4, the photochemical extraction yields were not increased greatly over the yields at 10 g/l. Moreover, the thermal control extraction at 100 g/l would suggest that only a small fraction of the yield in the photolysis experiment was actually due to photochemical reactions.

In both the photochemical and thermal control experiments it is clear in the results shown in Figure 4 that the removal of the extract from the THF solvent temporarily increases the rate of

extraction. This suggests that the leveling off of extraction with time is from the approach to an equilibrium between the extraction of molecules from the solid particles and their redeposition in the solid particles. It should be noted, however, that the effect is greater in the photochemical extraction experiment than in the thermal extraction experiment. Thus, there is also an additional influence of the accumulation of extract in the THF solvent upon the photochemical reactions occurring in the system. This will be discussed at greater length in the next section.

Although the yields of the thermal control experiments appear to be approximately proportional to slurry concentration, there are clearly other factors that are determining the yields from the photochemical extraction process. These factors need to be identified, controlled and understood in order eventually to optimize the photochemical yield. One of the factors appears simply to be the amount of light that may be absorbed by the coal particles under a given set of conditions. Clearly, in the limit of low slurry concentration in extract-free THF, the small fraction of light that is impinging on and being absorbed by the coal particles will be proportional to the slurry concentration. On the other hand, in the limit of high slurry concentration, when the coal particles absorb essentially all of the light impinging on the cell, the amount of light absorbed by the coal in the extract-free THF will approach a constant value that is independent of the slurry concentration. One might expect that in this limit the thermal extraction taking place simultaneously in the photochemical reactor, which is proportional to slurry concentration, could overtake and even exceed the amount of actual photochemical extraction. This appears to have happened in the experiments at 100 g/l. These conditions are clearly not the best ones under which to focus on the photochemistry.

In view of the considerations above, a slurry concentration of 10 g/l was chosen for all subsequent experiments on the set of coals chosen for study. The results from the photochemical and thermal extraction of the set of coals are given in Table 2 in terms of the cumulative extract absorbance at 300 nm at the end of the extractions. The extract and solvent were replaced with fresh THF at 10 h intervals during the 30-hour extractions for reasons to be discussed in the next section.

3. The Extract Inner-Filter Effect

For every coal examined in the 10 g/l slurries, it was found that, after 10 h of irradiation, the absorbance of the aliquots taken from the reactor had values of 9 or more (in 1 cm UV cells). This value would correspond to an average 300-nm photon penetration of less than about 1 mm into the 13-mm diameter sample tube (in the absence of coal particles) due to the absorption by the extract. The penetration depth would be less at shorter wavelengths and greater than 1 mm at longer wavelengths depending on the extract spectra to be discussed in detail in the next section.

It is clear from the results shown in Figure 4, curve a, that greater photochemical reaction rates are observed immediately at the beginning and after each solvent refreshment. This increase is much more than can be accounted for by the thermal extraction contribution, curve b, at the beginning but only slightly more than the thermal contributions at the subsequent solvent refreshments. However, what is most surprising to us about curve a is that even after the thermal extraction has leveled off (see curve b) and well after optical absorbances have exceeded 20 or 30, the rate of extraction by photochemical reaction continues practically unabated.

Thus, there are two types of photochemistry occurring that are indicated schematically in equations 1 - 4. In equation 1 the coal macromolecular-molecular complex is excited directly by the

absorption of light by the coal particle. The excited complex then dissociates the molecular fragment from the macromolecular network and forms another extract molecule. In equations 2 - 4 an indirect

process takes place in which the extract absorbs the light initially. The excited extract molecule then transfers its energy to the macromolecular-molecular complex of the coal particle, which then

dissociates to form an extract molecule, as in the direct mechanism. It is the direct process of equation 1 that takes place in the direct absorption of light by the coal particles at the beginning and after the solvent refreshment. It is the indirect process described by equations 2 - 4 that occurs after extract builds up and begins to absorb most of the light, extinguishing the direct process. The fact that the direct process 1 becomes less efficient in subsequent solvent refreshments than it was at the beginning suggests that the surface of the coal, while continuing to absorb light, becomes inert to further photochemistry. Perhaps the surface becomes depleted of the molecular parts of the complex, leaving behind only the "empty" macromolecular shell. Apparently the excited extract molecules continue to be in communication with the molecular parts of the interior of the coal particles.

We noted a coincident phenomenon that occurs in this same initial period of time that could be related either to the depletion at the coal particle surface or to some other effect. The phenomenon is that at the beginning of the photochemical extraction a strong blue luminescence was observed near the irradiated surface of the reactor which disappeared after about five hours of irradiation and did not return after subsequent solvent refreshments.

4. Optical Absorption Spectra of the Extracts

In Figure 5a are shown the absorption spectra of the Chinese Zao Zhung coal. The absorption spectrum of the photochemical extract is markedly broader than that of the thermal extract. The spectrum of the thermal extract is similar to the spectrum of the pre-extract. The broad absorption extending into the visible region appears to indicate the presence of highly condensed aromatic hydrocarbons and heteroaromatics in the photochemical extracts. Similar spectra were observed for the photochemical and thermal extracts from most of the coals, with the exceptions of the Pittsburgh #8, Yubari and Illinois #6 coals. For these coals the spectra of the photochemical and thermal extracts were much more similar, as is shown for the Pittsburgh #8 coal in Figure 5b.

An experiment was done to determine what contribution, if any, the irradiation of the thermal extract that had accumulated in the reactor was making to the results observed. Toward this end, the thermal extract from the Zao Zhung coal was irradiated under identical conditions in the absence of any coal particles. Figure 5a shows the result of this experiment, in which little change has occurred.

This result cannot begin to account for the change observed in the presence of coal particles. Thus, substantial photochemistry of the thermally extracted material alone appears not to be occurring in these experiments.

During the photochemical and thermal extractions, the absorption spectra of the extracts did not change appreciably with time. This afforded us the opportunity to monitor the progress of the extractions quantitatively by making measurements of the spectra of aliquots of the extract. Thus, the cumulative values of the absorbance at a given wavelength were proportional to the yield at various times. The absorptivities at 300 nm on a weight basis, given in Table 2 for each type of extract, are based on the final cumulative absorbance at 300 nm and the actual yield of extract by weight. The absorptivities at 300 nm of the various extracts lie between 5.0 and 9.3, except for the Bacchus Marsh coal. The small absorptivity of the Bacchus Marsh coal extracts result from spectra that are similar in shape to the Zao Ehung coal in Figure 5a. Although there are some exceptions, the absorptivities increase with coal rank. Also, the absorptivities of the photochemical extracts are slightly larger than those of the thermal extracts.

5. Effects of Wavelength and Continuity of the Irradiation Process

A comparison of the extraction yields from the irradiation of the Yubari coal pre-extraction residue with different parts of the spectrum and a comparison of continuous photolysis with photolysis and periodic solvent refreshment are shown in Figure 6. The latter comparison of extraction yields, here based on a percentage by weight basis, was discussed qualitatively in section 2 on the basis of the absorbance of the extracts.

Continuous 30-h irradiation experiments on 10 g/l slurries in THF with and without a 310-nm low-pass filter were performed. Curves a and b in Figure 6 show that the light from the Hg-Xe lamp between 230 and 310 nm is much more effective than the light at wavelengths longer than 310 nm alone. This is not surprising in view of the high UV output of the lamp in this region. Moreover, to the extent that the absorption of light by the extract molecules is directly involved in the photochemistry (see equations 2- 4) or to the degree that the extract spectra are similar to the spectra of the coal particles, Figure 5 shows that it is also in the 230 - 310-nm region that the stronger absorbance

occur.

The studies of the photolysis of coal slurries reported to date in the literature have been made by continuously irradiating samples for times as long as a few days. However, studies of the extraction yield as a function of time have not been reported. Curves a and d of Figure 6 compare the extraction yield during a continuous irradiation of a slurry of the Yubari coal pre-extraction residue with the yield when the solvent is refreshed every 10 h. During the initial 20 h of photolysis, the difference in yield was not appreciable. However, after the refreshment after 20 h of irradiation, the presence of extract in the continuously irradiated sample is clearly inhibiting photochemical conversion. We also note that after prolonged continuous irradiation there is a tendency for particles of residue or possibly precipitates from the extract to adhere to the inner surface of the reactor in spite of vigorous stirring, an effect that may also contribute to the leveling off of the yield in the continuously irradiated sample.

6. Effect of Coal Rank

In Figure 7 (bottom) are shown the time profiles of the (a) photochemical and the (b) control, thermal, extraction percentage yields from the Upper Freeport coal on a pre-extract residue basis. Curve c of Figure 7 (top) shows the difference between the photochemical and thermal extraction yields on the same basis. Although the photo-extraction yield appears to increase appreciably after the first THF solvent refreshment, the increase upon the second solvent refreshment at 20 h is not appreciable. In the case of the Yubari coal shown in Figure 4, the effect of solvent refreshment did not diminish until at least 30 h of irradiation. Thus, the effect of solvent refreshment appears to depend on the type of coal.

The percentage yields from the Zao-Zhung (top) and Kittanning (bottom) based on the original whole coals are plotted in Figure 8. Substantial amounts of thermally extractable material are present in the pre-extraction residue of the former coal. Photo-extraction seems to involve increasing the rate of thermal extraction, as well as producing soluble materials by photochemical reactions. The ratios of the 30-h photo-extraction yields to the 30-h thermal extraction yields are listed in Table 2. The ratios range between 2 and 5 for the semi-anthracite and bituminous coals but, on the other hand, the ratios

are less than 2 for the subbituminous and brown coals. Thus, the photo-extraction in THF is more effective for the higher rank coals studied. The low photo-extraction yield from the lower rank coals may be a consequence of their high pre-extraction yields, possibly indicating that the macromolecular compounds remaining after pre-extraction are highly cross-linked and photochemically inert.

In Figure 9 the net photo-extraction yields are plotted against the percent C in the original coal. These yields, which are based on the differences between the photo-extraction and thermal extraction yields, exhibit a maximum at the bituminous coals. This dependence is different than the dependences of the thermal and pre-extraction yields on percent C.

It is interesting to compare these findings with certain results reported on photo-extraction with the use of tetralin. The photo-extraction of benzene-soluble material at 60° C in a Pyrex tube from brown coals was more effective than from bituminous coals (7). This may be caused by a different mechanism of reaction involving the tetralin. In the presence of tetralin in the coal slurry, free radicals produced by the photolysis of the coal particles are stabilized by hydrogen transfer from the tetralin. On the other hand, in the THF coal slurries, where the free radicals cannot be stabilized by the THF, hydrogen from the hydroaromatics in the coal molecules themselves may serve to stabilize the radicals according to equation 5.

7. Effect of Pre-extraction Efficiency

In order to examine the photo-extraction of a coal with a more thorough pre-extraction, the Upper-Freeport coal was pre-extracted with the mixed solvent, *N*-methyl-2-pyrrolidinone-CS₂ (MP-CS₂). The experimental procedure was summarized in the scheme shown in Figure 3. Previous measurements have shown the MP-CS₂ extraction yields of this coal to be 40.7% at room temperature (13,14). In order to make comparison with the previous experiments, both the residue and extract of the MP-CS₂ pre-extraction were further pre-extracted with the THF by refluxing. The final residues were photo-extracted in THF. The yields from the various extractions involved in this procedure are given in Table 3.

The photo-extraction yield from the MP-CS₂- and THF-insoluble material from the Upper Freeport coal is not negligible. In fact, it is as high as the yield given in Table 2 from the THF-insoluble material from such high rank coals as the Pocahontas and Lower Kittanning coals. The photo-extraction yield of the THF-insoluble materials from the original Upper Freeport coal, abbreviated EY₀(photo) in Table 2, is close to the sum of the photo-extraction yields of the residues of the THF-soluble and THF-insoluble materials from the MP-CS₂ extraction residue of the coal. This suggests that photo-extraction of both the macromolecular and relatively small molecular components of the coal is occurring.

8. Mass Spectra of the Extracts

Field desorption mass spectra were obtained of the thermal and photochemical THF extracts from the pre-extraction residue of the coal samples. For example, in Figure 10 are shown the spectra of the Upper Freeport thermal (top) and photochemical (bottom) extract. There is a clear maximum in the molecular weight distribution of the thermal extract at about 450 a.m.u. The distribution of the photochemical extract is much wider than that of the thermal extract, with significant yields at around 200 a.m.u. and continuing to about 825 a.m.u. Previous results have indicated that the photo-extract contains the thermal extract as a largely unchanged subset. Thus, the results here show that the photochemistry is releasing molecular species at both higher and lower molecular weights than would be released by the thermal extraction alone.

Of uncertain significance is the abrupt cutoff of the photo-extract molecular weight distribution at about 825 a.m.u., while the thermal extract distribution continues to tail off beyond 825 a.m.u. This may be evidence that the photochemical cleavage of the large macromolecular units in the coal particles also takes place in solution on molecules with molecular weights above 825 a.m.u.

Also of interest is the pronounced cluster of fragments between 209 and 225 a.m.u. If these are assumed to be aromatic or hydroaromatic units, the data would indicate a prevalence of four-ring units. Whatever its significance, this cluster is not prevalent in the thermal extract and is clearly a result of the photochemistry.

Conclusions

In this study we have shown that 30-h irradiations of 10 g/l THF slurries of pre-extracted coals with the light between 230 and 310 nm from a 1000-watt, high pressure Hg-Xe lamp (~130 milliwatts) is capable of extracting as much as 9.7% of the material from the coal on a net weight basis, depending on the particular coal. The photochemical yields are up to five times what could be achieved by thermal extraction alone under the same conditions. Photo-extraction yields appear to be most effective for coal ranks around 87% C.

It is evident under the conditions employed in these experiments that the accumulation of extract in the solvent rapidly leads to almost complete absorption of the UV radiation by the extracted material. The kinetics of the production of extract with refreshment of the solvent at 10-h intervals shows that both direct irradiation of the coal particles and excitation of the extracted material lead to further extraction from the coal particles. The latter mechanism probably involves electronic energy transfer from excited extract molecules to molecules of the coal particle which are subsequently extracted in a mechanism similar to that following direct excitation.

Both the thermal and photochemical extracts reflect the increasing aromaticity of the coals with coal rank in that the absorptivities increase and extend further into the visible region with increasing coal rank. However, except for this general trend, thermal and photochemical extracts have markedly different compositions. The greater breadth and increased absorptivity of the UV-visible spectrum of the photo-extracts indicate the presence of much more highly condensed aromatic material than in the thermal extracts. The broader distribution toward higher molecular weights in the mass spectrum of the photo-extract than the thermal extract supports this hypothesis. The photo-extract mass spectrum also exhibits a broader extension to lower molecular weights than the narrower mass distribution of the thermal extract centered around 450 a.m.u.

These comparisons of the thermal and photochemical extracts suggest that a broader distribution of molecular species is being released by photochemical action than by solvent action. A possible reason is that the photochemistry is breaking up the macromolecular network of the coal particles. There exists a particular distribution of molecular species that can be released by solvent action that is

determined by the nature of the macromolecular network, the coal porosity and the molecular species present in the coal. However, when photochemistry breaks up the macromolecular network itself, the large fragments of the broken macromolecules and previously trapped small molecules are all released in addition to the molecules already capable of being released by the solvent.

Further work needs to be done to clarify what has been revealed in this exploratory study of coal photochemistry. Additional analytical measurements of the photochemical extract by elemental analysis, infrared spectroscopy, gas-chromatographic mass spectrometry and nuclear magnetic resonance spectrometry should be done to refine the chemical structural characterization of the extract molecules. It may also be useful to isolate the two photochemical mechanisms operating in this study. A continuous flow of fresh solvent into the photochemical reactor would make exclusive irradiation of the coal particles possible. Studies of the efficacy of specific electronic energy transfer agents should also be made. Since the reaction of free radicals formed in the cleavage of the covalent bonds of the coal macromolecules requires a source of hydrogen and since various coals (and their extracts) differ in hydroaromatic content, further experiments with external sources of hydrogen should be explored. In order to clarify the specific free radical mechanism(s) operating in the photochemistry, time-resolved optical or EPR studies of free radical formation and reaction should be attempted.

Acknowledgments

We would like to express our thanks to Dr. D. Dwyer and Mr. R. Barham for helpful suggestions and to the Department of Energy, Pittsburgh Energy Technology Center for its support under grant number DE-FG22-91-PC91299. We also acknowledge the Penn State Coal Sample and Data Bank and the Argonne Premium Coal Program for their provision of some of the samples and analyses used in this study.

References

1. J. A. Solomon and G. J. Mains, *Fuel* **1977**, *56*, 302.
2. R. Hayatsu, R. G. Scott, L. P. Moore and M. H. Studier, *Nature* **1975**, *257*, 378.
3. R. Hayatsu, S. Matsuoka, R. G. Scott, M. H. Studier and E. Anders, *Geochim. Cosmochim. Acta* **1977**, *41*, 1325.
4. R. Hayatsu, R. E. Winans, R. G. Scott, L. P. Moore and H. Studier, *Fuel* **1978**, *57*, 541.
5. R. Hayatsu, R. E. Winans, R. G. Scott, L. P. Moore and M. H. Studier, in "Organic Chemistry of Coal," J. W. Larsen, Ed., *Am. Chem. Soc. Symp. Ser. 71*, p. 108, Am. Chem. Soc., Washington, DC, 1978.
6. Y. Yürüm and T. Yiginsu, *Fuel* **1982**, *62*, 302.
7. A. Yanagawa and I. Anazawa, *Fuel* **1989**, *68*, 668.
8. K. Hashimoto, T. Kawai and T. Sakata, *J. Phys. Chem.* **1984**, *88*, 4083.
9. S. Sato and J. M. White, *Ind. Eng. Chem. Prod. Res. Dev.* **1980**, *19*, 542.
10. K. S. Vorres, *Users Handbook for Argonne Premium Coal Sample Program*, Argonne National Laboratory, 1989.
11. The Penn State Coal Sample Bank and Data Base, Coal Research Section, The Pennsylvania State University, 1982 and 1990.
12. H. N. M. Dormans and D. W. van Krevelen, *Fuel* **1960**, *39*, 273.
13. R. Takanohashi and M. Iino, *Energy & Fuels* **1990**, *4*, 452.
14. H. Seki, O. Ito and M. Iino, *Fuel* **1990**, *69*, 317.

Table 1. Elemental analyses and tetrahydrofuran (THF) pre-extraction yields of the coals used in this study. Coal abbreviations are given in parentheses.

Coal	Elemental Analysis (percent by weight, daf)			Pre-Extraction Yield (wt.%, daf)	Ash Content of Pre-Extraction Residue (wt%) ^a
	C	H	O		
Pocahantas #3 (PH) ^b	91.8	4.5	1.7	4.8	5.3
Lower Kittanning (LK) ^c	89.6	4.8	2.6	2.2	10.6
Upper Freeport (UP) ^b	88.1	4.8	4.7	6.3	13.6
Zao Zhung (ZZ) ^d	86.9	5.1	4.9	8.1	8.0
Yubari (YU) ^e	86.7	6.2	4.6	12.4	7.0
Pittsburgh #8 (PB) ^b	85.0	5.4	6.9	15.6	10.7
Blind Canyon (BC) ^b	81.3	5.8	10.9	15.8	6.0
Illinois #6 (IL) ^b	76.9	5.5	10.1	17.3	18.0
Beulah-Zap (BZ) ^b	74.1	4.9	19.1	2.3	10.2
Bacchus Marsh (BM) ^f	70.5	7.2	21.0	26.4	0.0

^a Calculated values; see text for explanation.

^b Argonne Premium Coal samples; see reference 10.

^c Pennsylvania State University Coal Data Bank coal PSOC-1197; see reference 11.

^d Chinese coal.

^e Japanese coal.

^f Acid washed Australian brown coal.

Table 2. Photochemical and thermal extraction yields from the pre-extraction residues of the coal samples and the cumulative absorbances at 300 nm from which they are determined. The pre-extraction residues were suspended in THF at 10 g/l and irradiated for 30 h with the THF extract solution being replaced with fresh solvent every 10 h.

Coal	Method	$A_{300\text{ nm}}^a$	$E_{300\text{ nm}}^b$	EY_r^c	EY_o^d	$(PEYd)_o^e$	R_o^f
PH	photo	40	8.2	5.3	5.0	2.7	2.2
	therm	17	7.4	2.4	2.3		
LK	photo	36	8.0	5.0	4.9	2.9	2.5
	therm	11	6.1	2.0	2.0		
UF	photo	70	8.0	10.4	9.8	6.3	2.8
	therm	22	7.6	3.6	3.5		
ZZ	photo	76	7.7	10.7	10.0	5.1	2.0
	therm	35	7.2	5.3	4.9		
YU	photo	115	9.0	13.8	12.1	9.7	5.0
	therm	20	8.0	2.7	2.4		
PB	photo	92	9.3	11.2	9.4	3.1	1.5
	therm	59	8.8	7.5	6.3		
BC	photo	64	6.1	11.5	9.4	5.0	2.0
	therm	17	5.0	5.4	4.8		
IL	photo	45	6.1	8.2	6.8	0.7	1.1
	therm	40	6.0	7.5	6.2		
BZ	photo	9	6.1	1.7	1.7	0.5	1.4
	therm	7	6.0	1.2	1.2		
BM	photo	34	3.3	10.0	7.4	3.4	1.9
	therm	11	2.0	5.4	4.0		

^a Absorbance after 30 h extraction at 300 nm for 1-cm cell.

^b Average absorption coefficient in units of 0.1 l/g cm.

^c Extraction yield based on residue weight.

^d Extraction yield based on weight of original coal.

^e Net photo-extraction yield [$EY_o(\text{photo}) - EY_o(\text{therm})$].

^f $EY_o(\text{photo})/EY_o(\text{therm})$.

Table 3. Photo-extraction yields from fractions of Upper Freeport coal. See Table 2 for definitions of symbols.

Sample	THF Pre-extract Yield	Method	A ₃₀₀	E ₃₀₀	EY _r	EY _o	(PEYd) _o
original coal	6.3	photo	70	8.0	10.4	9.8	6.3
		therm	22	7.6	3.6	3.5	
MP-CS ₂ extract (40.9 wt %)	15.2	photo	77	6.8	11.3	6.7	3.7
		therm	50	9.8	5.1	3.0	
MP-CS ₂ residue (59.1 wt %)	< 1	photo	31	8.2	5.5	2.2	1.6
		therm	8	7.7	1.5	0.6	

Figure Captions

1. Schematic representation of the extraction procedure employed using tetrahydrofuran (THF) solvent.
2. Apparatus employed in the photolysis of the coal slurries. LP: lamp; F1: water heat filter; F2: optical bandpass and cutoff filters; QR: 13-mm i.d. quartz reaction vessel; TM: thermometer; MS: magnetic stirrer; RF: reflector; FA: forced air cooling.
3. Schematic representation of the extraction procedure employed using *N*-methyl-2-pyrrolidinone- CS_2 (MP- CS_2) and tetrahydrofuran solvents.
4. Time profiles of the cumulative 300-nm absorbance of (a) the photo-extract and (b) the thermal extract from the Yubari coal pre-extraction residue slurry in THF (10 g/l) at 60° C under N_2 gas. Similar time profiles of (c) the photo-extract and (d) the thermal extract at a lower slurry concentration of 5 g/l. Arrows indicate the times at which the extracts were replaced with fresh THF.
5. UV-visible spectra of extracts in THF from (a) Zao Zhung coal pre-extraction residue (i) photo-extract, (ii) thermal extract, (iii) spectrum observed after 10-h additional irradiation of (ii) in the absence of coal particles and from (b) Pittsburgh #8 coal pre-extraction residue (i) photo-extract and (ii) thermal extract. The duration of the extractions was 30 hours.
6. Effects of the wavelength and continuity of the irradiation upon the time profiles of the extraction yield based on percent by weight of the initial pre-extraction residue at 10 g/l in THF. Continuous irradiation with (a) wavelengths 210 - 390 nm and (b) wavelengths 310 - 390 nm, (c) continuous thermal extraction and (d) photo-extraction with THF solvent refreshment (arrows) every 10 h.
7. Photo-extraction (a) and thermal extraction (b) yields (EY_t) based on percent by weight of the initial pre-extraction residue from the Upper Freeport coal and the net photo-extraction yield

[$(\text{PETd})_0$] based on percent by weight of the original coal. Extractions were from 10 g/l of slurry in THF at 60° C.

8. Time profiles of the yields of photo-extraction (a,c) and thermal extraction (b,d) based on weight percent of the original coal for the pre-extraction residues of the Zao Zhung (upper) and Lower Kittanning coals (lower). The pre-extraction yields are also exhibited.
9. Dependence of the net photochemical extraction yields on coal rank, based on weight percent of the original coal.
10. Relative abundances of the ion masses obtained from the field desorption mass spectra of the THF thermal extract (upper) and photo-extract (lower) from the THF pre-extraction residue from the Upper Freeport coal.

Figure 1.

Figure 2.

Figure 3.

Figure 4.

Figure 5.

Figure 6.

Figure 7.

Figure 8.

Figure 9.

Figure 10.

END

**DATE
FILMED
5107192**