Technical Progress Report for the Project

ELECTROCHEMISTRY OF Thiobacillus ferrooxidans
REACTIONS WITH PYRITE

Principal Investigator: Prof. B. Pesic
Co-principal Investigator: D.J. Oliver

Reporting Period: September 1991 - January, 1992

U.S. DOE Patent clearance is not required prior to publication of this document

DOE Project Grant No.: DE-FG22-88PC88920

DISCLAIMER

MASTER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

1. STATEMENT AND OBJECTIVES

The objective of this project is to provide the fundamental information on the mechanisms of bacterial leaching of pyrite. The knowledge of how bacterial leaching of pyrite functions is essential for design and development of a technology for coal cleaning with bacteria. The features of major electrochemical techniques will be examined to find out if any of them can provide a diagnostic information on the mechanisms of related reactions.

2. SCIENTIFIC AND TECHNICAL PROGRESS

2.1 GENERAL

This report discusses the research results obtain during the study of effect of environmental conditions on the chemical activity of *T. ferrooxidans*. More specifically, the environmental conditions mean the effect of heavy metals, particularly silver, on the activity of bacteria. The chemical activity of bacteria is expressed in terms of its oxidizing ability of ferrous ion. The method of measuring the activity of bacteria is based on the variation of solution redox potentials with time. Our technique is unique compared to the traditional chemostat techniques because it allows the measurement of the bacteria's activity due to its oxidizing property only, excluding the bacteria growth.

The redox potential measurement methods do follow already developed, traditional, kinetic models, and this kind of analysis will be reported in the next trimester. This is an encouraging news because the redox potential technique can be utilized to extract standard kinetic information plus it provides additional information which are not available in standard techniques.

This report represents a paper in preparation which will be submitted for review for publication after its completion.

EFFECT OF SILVER AND SOME OTHER HEAVY METALS
ON THE IRON OXIDIZING ABILITY OF
THIOBACILLUS FERROOXIDANS.

Gopal C. De and Batric M. Pesic

Department of Mining and Metallurgical Engineering
College of Mines and Earth Resources
University of Idaho
Moscow, Idaho 83843

Abstract

The effect of silver and some other heavy metal ions on the iron oxidizing ability of Thiobacillus ferrooxidans was studied using electrochemical and some other physico-chemical techniques. Electrochemical investigation was conducted using a method based on redox potential change. Experiments were performed by adding an aliquot of separately prepared concentrate of the bacteria into the solution of ferrous ion and monitoring the redox potential for at least one hour. Pyrite was used as the indicator electrode. Parameters examined were pH, microbial cell density, ferrous and ferric ion concentration, temperature, concentration of silver and some other cations and anions, pre-conditioning period of the bacteria with silver, etc.

Results obtained demonstrate that the reaction is pH dependent, the optimum pH range being 1.5-2.0. The first order rate constant of the reaction (standard value 0.06 min^{-1}) is largely influenced by the substrate to cell concentration ratio and temperature. The activation energy of this reaction has been observed to be 11.51 and 12.33 Kcal mole⁻¹ in the absence and in the presence of 10 mg/L silver, respectively. The presence of some heavy metal ions has been observed to affect the rate of reaction, while the anions studied (e.g. chloride and nitrate) have no effect on the reaction being investigated. Mercuric and silver ions have been observed to exert the most detrimental effects on the reaction rate. However, the bacteria are found to maintain their ferrous iron oxidizing ability in presence of a small concentration of silver depending on pH. Under standard condition of pH 1.7, the bacteria can maintain their iron oxidizing activity in a solution containing approximately 0.7 mg/L of silver, whereas at pH 1.4, this limit reduces to 0.25 mg/L of silver. Conditioning the bacteria with an appreciable concentration of silver (e.g. 1 mg/L or over) has been found to be adverse to the bacteria's iron oxidizing ability.

Introduction

Primarily because of a great technological potential, bioleaching involving Thiobacillus ferrooxidans and other autotrophic bacteria has received much attention (1, 2) over the past few decades. For example, microbial oxidation has been found to be useful for liberating precious metals from the refractory sulfide matrix, thereby rendering the cyanidation in heap leaching practice possible(3). Reportedly (3), biooxidation is also applicable for dump leaching of low grade refractory copper ores such as CuFeS_2 . Lately, active consideration is given to use bioleaching for the removal of pyritic sulfur from coal and help control environmental pollution (i.e. acid rain caused by SO_2 contained in the exhaust gases from coal power plants).

A literature review reveals that the role of T.ferrooxidans in bioleaching of metal sulfides is to catalyze the oxidation of iron sulfide(s) to Fe(III) sulfate. However, previous work does not specify which component of the microbial cell plays the key role during bioleaching. Earlier reports (4, 5) have mentioned that a c type cytochrome may be responsible for the transport of electrons from Fe(II) to oxygen, whereas a more recent communication (6) has cited that a 92K glycoprotein may be the most important component of the iron oxidizing system of the T. ferrooxidans. While there is a lack of agreement regarding the identity of the cell active sites responsible for Fe(II) (or sulfur) oxidation, two alternative mechanisms have generally been suggested for the microbial leaching of metal sulfides. According to direct mechanism, a physical contact between the bacteria and the sulfide mineral is required (7). In the indirect mechanism, the bacteria generated Fe(III) acts as a lixiviant for the solubilization of metals from the minerals (3). In actual fact, however, both of the mechanisms may operate simultaneously in a complementary manner.

An important side effect of bioleaching is codissolution of other

heavy metals, which if accumulated to a certain level can influence the activity of T. ferrooxidans cells. In a more drastic case, the heavy metals can even directly kill the bacteria, or at least inhibit their activity. The deactivation process may involve blocking or damaging of a significant fraction of the cell active sites by heavy metal ions. In another possible deactivation process, the presence of a particular heavy metal may enhance the formation of toxic species from dissolved oxygen, such as superoxide $O_2^{\cdot -}$. Oxygen toxicity through the superoxide formed in the biological systems is already known in the literature (8).

A reverse case may also be possible in which the bacteria's metal leaching activity may be enhanced in the presence of a heavy metal. This is likely to happen if a conducive metallic species are initially added into the leach system or released in-situ from a mineral by the indirect leaching mechanism.

Tuovinen and Kelly (9) have studied the effect of UO_2^+ on the iron oxidation of by T. ferrooxidans. It was found that the presence of uranium species partially inhibited the oxidizing activity of bacteria by blocking the cell active sites. Addition of a complexing agent like EDTA, or a non-toxic cation (e.g. Mg^{2+}), reduces the inhibitory action due to uranyl cation. Mercuric and mercurous ions are even more toxic than uranium, or any other heavy metal ions studied (Pb, As, Zn, Mo, Cu, Cd), as found by Imai et al. (4). The observed variation in toxicity of heavy metals might have resulted from differences in the modes of interactions between the cell active sites and various heavy metals ions. On the basis of the above information, it is likely that UO^{2+} may be physically sorbed onto the cell and still be available for removal by exchange with a divalent cation Mg^{2+} ions. On the other hand, Hg(II) may directly interact with the T. ferrooxidans by forming a chemical bond with iron oxidase.

Silver as another heavy metal is often cited as very toxic to T.

ferrooxidans (4, 10-13). For example, previous workers (11, 12) have reported that in an aqueous FeSO_4 solution of low pH, growth of the T. ferrooxidans is decreased and their ferrous iron oxidizing ability lost to a significant extent by the presence of approximately 0.10 mg/l Ag^+ . However, if a metal sulfide such as CuFeS_2 is used in the solid form as the sole nutrient source, then the presence of a significant quantity of silver may not cause any harm to the bacteria's leaching activity (14-16). On contrary, the bioleaching of CuFeS_2 was enhanced even in the presence of 30 mg/l Ag^+ (16). The positive effect of silver has been explained (14, 16) in terms of the fact that Ag^+ forms Ag_2S to generate the galvanic couple, $\text{Ag}_2\text{S}/\text{CuFeS}_2$, in which Ag_2S acts as a cathode facilitating anodic dissolution of CuFeS_2 .

In the light of the literature reports mentioned above, it is conceivable that the apparent dual role of silver in the ferrous iron oxidizing ability of T. ferrooxidans is due to differing experimental conditions. Consequently, it was decided to examine the effect of silver and a number of other heavy metals on the iron oxidizing activity of the T. ferrooxidans by extending the experimental parameters beyond those considered in the earlier investigations.

Experimental

Materials and Equipment

The equipment and the method of Thiobacillus ferrooxidans (strain ATCC 13598) growth are explained in reference 17. Only reagent grade chemicals were used.

Procedure

(a) Experiments without heavy metals

Experimental solution, 250 ml, consisted 0.001M Fe^{2+} and 0.0001M Fe^{3+} at desired pH. Ferric ion was present to obtain a stable initial potential. The biooxidation of ferrous ion was initiated by addition of 2mL of concentrated and washed bacteria cells. The chemical activity of bacteria was monitored by measuring the redox potential (vs SCE) of solution. Specially built pyrite electrode served as an indicator electrode.

(b) Experiments with heavy metals

The experimental procedure was similar to the preceding section except that a desired concentration of a heavy metal (e.g. silver) was present before the addition of bacteria to the solution.

To study the length effect of contact of bacteria with silver (conditioning) on their iron oxidizing activity, 2mL of concentrated bacteria was added to a solution containing 1-10mg/l Ag^+ . When the conditioning period, 5-120 minutes, was completed, requisite amounts, as above, of ferrous and ferric iron were added, and the redox potential monitoring initiated.

Standard experimental conditions are given in Table 1.

Table 1 Standard Experimental Conditions

pH	1.7
Temperature	25°C
Concentration of Fe(II)	0.001M
Concentration of Fe(III)	0.0001M
<u>T. ferrooxidans</u> cells	2mL

Results and Discussion

Experiments Without Heavy Metals

Effect of pH

The effect of pH on the redox potential change as a function of time is shown in Fig. 1. The potential versus time curves satisfy the Nernst equation with the standard potential equal to 0.4324V and the slope of 0.055V, equation (1). In accordance with

$$E = 0.4324 + 0.055 \log[\text{Fe(III)}]/[\text{Fe(II)}] \quad (1)$$

the Nernst's equation, an increase in the electrode potential results from an increase in the ferric ion concentration, which is caused by oxidation of ferrous ion with bacteria. The Nernst equation can be used to calculate the reaction rate constants(17), and the results are presented in Table 2. According to the results in Table 2, the ferrous iron oxidizing activity of T. ferrooxidans is significantly influenced by solution pH. T. ferrooxidans is the most active in the pH 1.4-2.1 range.

Table 1

Effect of pH on the observed rate constant
of the microbial oxidation of ferrous iron.

pH	Rate constant (min ⁻¹)
1.2	0.0270
1.4	0.0520
1.5	0.0570
1.7	0.0600
1.9	0.0610
2.0	0.0590
2.1	0.0500
2.5	0.0350
3.0	0.0150
3.5	0.0050

Effect of Cell Concentration

T. ferrooxidans absorb UV-VIS light at 590nm (7). This property was utilized in this study to establish a correlation between the cell concentration and the iron oxidation rate. At first, optical densities of the bacterial cells of various concentrations at 590 nm were measured. Subsequently, the corresponding concentrations of bacteria were used in ferrous iron oxidation experiments (standard conditions given in Table 1) to determine the rate constants from the measured change of redox potential with time (17). According to the results presented in Figure 2, the iron oxidation with T. ferrooxidans is first order with respect to the concentration of cells.

Effect of Fe(II) concentration

This parameter was studied in a series of experiments with different initial concentrations of Fe(II). The initial concentration of cells corresponded to $OD_{590} = 2.8$. The square symbols in Figure 3 represent the obtained results. It is observable from Fig. 3 that for Fe(II) concentration of 0.001M, the rate of microbial oxidation of Fe(II) is maximum under standard conditions. The observed rate constant has a value of 0.06 min^{-1} . However, at Fe(II) concentrations below or above 0.001M, the rate constant is observed to decrease. For instance, Fig. 3 indicates that at Fe(II) concentration of 0.00038M, the rate constant approaches 0.047 min^{-1} , which is approximately 26% lower than that for a Fe(II) concentration of 0.001M. To find an explanation for this observation, another experiment was performed with a Fe(II) concentration of 0.00038M and bacteria of lower cell density (indicated by $OD_{590}=1.2$). The rate constant was found to be a little over 0.06 min^{-1} . This finding suggests that the left hand side of the maximum in Fig. 3 corresponds to a decline in rate constant due to substrate limitation. Consequently, the observed

decrease in rate constant with an increase in Fe(II) concentration beyond 0.001M (right hand side of maximum point in Fig. 3) may be attributed to cell limitation. This was confirmed by an experiment performed by increasing the concentration of Fe(II) from 0.001M to 0.002M and adding 4mL T. ferrooxidans cells instead of 2mL, usually used for a reactor volume of 250mL. This experiment resulted in an observed rate constant of approximately 0.06 min^{-1} . Thus, our results suggest that for maximum ferrous iron oxidizing activity of the bacteria, the ratio of concentrations of the microbial cell and ferrous ions must be optimized. According to our findings, if 2mL of T. ferrooxidans cells of OD590=2.8 are used in a reactor volume of 250mL, then the optimum Fe(II) concentration will be 0.001M.

Effect of temperature

Variation of the 1st order rate constant of microbial oxidation of Fe(II) with temperature is shown by the data contained in Table 2. It is observed from Table 2 that the 1st order rate constant of the oxidation of Fe(II) in presence of T. ferrooxidans increases as the temperature is increased from 5.5 to 25°C, beyond which it decreases

Table 2

Effect of temperature on the rate constant
of the bacterial oxidation of ferrous iron.

Temperature (°C)	Rate constant (min^{-1})	
	No silver	10 ppm silver
5.5	0.0120	0.0060
10	0.0220	0.0100
15	0.0450	0.0140
21	0.0500	0.0180
25	0.0600	0.0285
30	0.0510	0.0100
35	0.0500	0.0090

to some extent. This observation suggests that 25°C is the optimum temperature for the reaction being studied.

Arrhenius plots were generated using the data points from Table 2 and shown in Fig. 4. From the plot, activation energy of microbial oxidation of Fe(II) in absence of any heavy metal is observed to be 11.51 Kcal mole⁻¹. It may be noted that this value of activation energy is slightly lower than that reported earlier (17).

Effect of anions

Experiments were performed with 10 ppm Cl⁻ and NO₃⁻ to examine the effects of these anions in our system. In each case, the observed rate constant was 0.06 min⁻¹, which is our standard value, and indicated that these two anions, practically, have no effect on the Fe(II) oxidizing activity of the T. ferrooxidans.

Results of experiments involving heavy metal ions

Effect of heavy metal ions

The effect of a number of heavy metal ions on the rate of Fe(II) oxidation in presence of T. ferrooxidans is shown in Table 3. The data contained in Table 3 indicate that mercuric ion is the most inhibitory to the reaction being investigated. This finding is in agreement with a previous report which has mentioned that mercury is extremely toxic to this bacteria (4). In addition, our results suggest that the bacteria's normal Fe(II) oxidizing activity is unaffected by presence of 10 ppm Co(II), Cu(II) and Zn(II). While the rate of bacterial oxidation of Fe(II) seems to be enhanced a little due to the presence of 10 ppm Mn(II), As(III) and Sn(II), the Fe(II) oxidizing ability of the bacteria is slightly lowered by

the presence of 10 ppm Pb(II) and Cd(II) in the system. Ag(I) is observed to be more inhibitory than any other heavy metal studied except Hg(II). The effect of silver on the Fe(II) oxidizing activity of the T. ferrooxidans has been studied in details and results will be discussed in the following sections.

Table 3

Effect of heavy metal ions on the rate of Fe(II) oxidation by T. ferrooxidans.

Heavy metal ion	Rate constant (min ⁻¹)
Ag(I)	0.0285
Co(II)	0.0610
Cu(II)	0.0610
Mn(II)	0.0650
Hg(II)	0.0020
Pb(II)	0.0500
As(III)	0.0660
Sn(II)	0.0660
Cd(II)	0.0560
Zn(II)	0.0600

The observed variation in the ferrous iron oxidizing ability of T. ferrooxidans in presence of different heavy metal ions may be attributed to the variation in the mode of interaction of various heavy metal ions with the microbial cell active sites. However, proper caution must be exercised before suggesting that the presence of Mn(II), As(III) and Sn(II) in the system is conducive to Fe(II) oxidation in presence of T. ferrooxidans. It should be noted that our results are based on redox potential measurements. An increase in measured potential might have occurred due to oxidation of these cations to their higher valency states. As a result, these ions may have partial contributions in the redox potential measured as a function of time during our experiments involving these cations and consequently, on the observed rate constants. This view was confirmed by the results of additional experiments mentioned below.

Separate experiments were performed without bacteria but using the standard set of other conditions and 10 mg/L of Mn(II), As(III) and Sn(II). In each of the experiments, redox potential of the solution was monitored as before using pyrite indicator electrode for over 60 minutes. It was observed that the potential of the indicator electrode remained constant around 375 and 377 mV in experiments with 10 mg/L Mn(II) and As(III), respectively. This suggests that during bacterial oxidation of Fe(II), the observed increase in redox potential in presence of Mn(II) and As(III), relative to those observed in their absence, may be due to the oxidation of these two heavy metal ions. Oxidation of Mn(II) and As(III) may occur directly by the bacteria or indirectly by the bacteria generated Fe(III). The indirect mechanism is known (18) to be effective in arsenopyrite bio-leaching. Consequently, observed increase in the rate of Fe(II) oxidation in presence of Mn(II) and As(III) in our experiments should be attributed to their own oxidation.

On the other hand, the redox potential of the pyrite indicator electrode was observed to increase from an initial value of 155 mV to a final value of 337 mV, when 10 mg/L Sn(II) was present in the system. This may be because of oxidation of Sn(II) to Sn(IV) by Fe(III). Thus, oxidation of Sn(II) is likely to have a significant contribution in the redox potential measured during experiments using the bacteria and Sn(II) together. Consequently, the observed increase in rate constant in experiments involving the bacteria and Sn(II), may not be due to enhancement of microbial oxidation of Fe(II) in presence of Sn(II). Rather, it is likely to be due to oxidation of Sn(II).

Effect of silver ion concentration

Effect of concentration of silver ion on the oxidation of Fe(II) at pH 1.7 has been demonstrated in Fig. 5. It is observed that the

electrode potential versus time plots representing various concentrations of silver (1 mg/L and above) are all below that corresponding to no silver (or <1 mg/L silver). This indicates that silver ions in the range 1-10 mg/L adversely affect the bacteria's iron oxidizing activity. The results also suggest that a silver concentration of around 0.5 ppm is not adverse to the bacteria's Fe(II) oxidizing activity at pH 1.7. This may indicate that the bacteria are able to tolerate certain concentration of silver. This view is supported by the results of additional experiments conducted at pH=1.4 and 3.0 described below.

Computation of the rate constant and subsequent plot against silver ion concentration (Fig. 6) shows more clearly that the rate of Fe(II) oxidation catalyzed by T. ferrooxidans is maintainable up to a threshold value of silver concentration, beyond which the rate decays. According to Fig. 6, the threshold value of silver concentration is pH dependent. For instance, at pH 1.7, the maximum concentration of silver that causes no harm to the microbial Fe(II) oxidation is approximately 0.7 ppm. On the other hand, at pH 1.4 and 3.0, the maximum value of silver concentration tolerable in the bacterial oxidation of Fe(II) approaches towards 0.25 and 0.8 ppm respectively. However, at pH 3.0, the effect of silver is not so pronounced, probably because, at this pH the bacteria's activity is very low even without silver. Thus, our results suggests that the effect of silver on the microbial oxidation of Fe(II) is concentration dependent. While a small concentration silver in the system may be tolerable, an appreciable concentration of silver (0.25 ppm or above depending on pH) is detrimental to the bacterial oxidation of ferrous iron in solution.

Oxidation of Fe(II) with bacteria conditioned with silver

Effect of time

These experiments were performed to examine the effect of conditioning the bacteria with silver for different amount of time. The effect of conditioning period of the T. ferrooxidans with 10 mg/L silver on the observed electrode potential is shown in Fig. 8. It is noticeable that the curves corresponding to different periods of initial contact of the T. ferrooxidans with silver are well below that representing no conditioning. This observation suggests that a preliminary contact with soluble silver remarkably reduces the bacteria's iron oxidizing activity. This effect becomes more pronounced as the duration of conditioning is increased from 0 to 2 hours (Fig. 8). This may be due to the fact that the longer the period of pre-contact of the bacteria with silver ions, the greater will be the proportion of the cell active sites which have been deactivated by silver.

The effect of conditioning period of the bacteria with silver on the rate constant of Fe(II) oxidation is represented by Fig. 9, which shows that the rate constant decreases as the duration of conditioning the bacteria with 10 mg/L silver is increased. The effect of conditioning time also depends on the concentration of silver. For example, after 30 minutes' conditioning with 1, 2.5 and 10 mg/L silver, the activity of the bacteria expressed as the rate constant of Fe(II) oxidation was 0.0485, 0.0415 and 0.017 min⁻¹, respectively (Fig. 9).

Effect of pH

Fig. 10 compares the effect of pH on the rate constant of the microbial oxidation of ferrous iron in the absence and in the presence of silver. The top curve of this figure represents the

ferrous iron oxidizing activity of the bacteria in the test solutions of differing pH in the absence of silver. The middle curve corresponds to the iron oxidizing activity of the bacteria in presence of 10 ppm silver in the solutions of various pH, while the bottom one demonstrates the activity of the bacteria conditioned for 1 hour with 10 mg/L silver in solutions of different pH. A comparison of the top curve with the other two curves suggests that the presence of a significant concentration of silver in the system and conditioning the bacteria for a prolonged time with an appreciable concentration of silver are detrimental to the microbial oxidation of Fe(II). For example, at pH 1.7 and in absence of silver, the rate constant of bacterial oxidation of ferrous iron is 0.06 min^{-1} . In presence of 10 mg/L silver (without conditioning), this value is reduced to 0.0285 min^{-1} . When the bacteria are conditioned with 10 mg/L silver for a period of 1 hour, the rate of bacterial oxidation of Fe(II) is further lowered to 0.012 min^{-1} .

Fig. 10 also shows that change of pH beyond 1.5-2.0 has a negative effect on the bacteria the absence of silver. However, because of severe loss in microbial activity, due to the presence of silver, and conditioning with silver, the pH effect becomes less pronounced in experiments with silver. Consequently, the portion of the rate constant versus pH curve at the vicinity of peak (refers to the top curve in Fig. 10) spreads over a wider pH range with an attendant decrease in activity of the bacteria, if 10 mg/L silver is present in the system. It becomes even wider and shows further loss of bacterial activity when the bacteria are conditioned with 10 mg/L silver for 1 hour. Thus, according to Fig. 10, factors adversely affecting the activity of the T. ferrooxidans may be arranged in the following sequence:

Conditioning with Ag^+ > presence of Ag^+ > pH changes.

Effect of temperature in the presence of silver

If the T. ferrooxidans cells are concurrently exposed to 10 mg/L silver and deviations from optimum reaction temperature (i.e. 25°C), then the rate of microbial oxidation of ferrous iron may decrease remarkably. This is depicted by the data shown in Table 2. For instance, at 25°C and in the presence of 10 mg/L silver in the biotic system, the observed rate constant of reaction reduces from the standard value of 0.06 to 0.0285 min⁻¹. In presence of 10 ppm silver, if the reaction temperature is varied from 25 to 5.5 and 35°C, the rate constant is observed to be lowered to 0.006 and 0.009 min⁻¹, respectively.

Arrhenius plots (Fig. 4) obtained on the basis of the data from Table 2 yields activation energy values of 11.51 and 12.33 Kcal mole⁻¹ for experiments without silver and in presence of 10 ppm silver respectively. Higher value of the activation energy when 10 ppm silver is present suggests that the presence a significant amount of silver in solution is detrimental to the iron oxidizing activity of the T. ferrooxidans.

Effect of Fe(II) concentration in the presence of silver

It is observable in Fig. 3 that the curve representing microbial Fe(II) oxidation in the presence of silver is below that obtained in experiments without silver, when the substrate concentration is around 0.0004M or above. However, below 0.0004M Fe(II) concentration, the curve representing experiments with 10 mg/L silver is observed to intersect the curve representing no silver and shows a peak corresponding to 0.00025M Fe(II). An increase in Fe(II) concentration beyond 0.00025M, in presence of 10 mg/L silver, had a negative effect on the activity of the bacteria in a similar fashion as in the absence of silver. This observation may be explainable in terms of the fact that in the presence of 10 mg/L

silver, a significant proportion of the microbial cells may be deactivated. This would result in a decrease in the proportion of the microbial cells effective for Fe(II) oxidation. A decrease in the proportion of the effective cells would require a lower Fe(II) concentration to optimize substrate to microbial cell ratio for maximum reaction rate. Hence, the reaction rate in the presence of 10 mg/L silver may be limited by the concentration of T. ferrooxidans cells when Fe(II) concentration is greater than 0.00025M. For Fe(II) concentrations lower than 0.00025M, in the presence of 10 mg/L silver, the reaction rate increases with increasing Fe(II) concentration. As a result this portion of the curve would correspond to substrate limitations.

Effect of added ferric ion

In our experiments, 0.0001M Fe(III) has always been added to obtain a stable, positive initial redox potential. However, an increase in the initially added Fe(III) concentration beyond 0.0001M results in a decrease in the reaction rate (Fig. 10). For example, at 0.0001M Fe(III), the rate constant of microbial oxidation of Fe(II) is 0.06 min⁻¹. If initial Fe(III) concentrations of 0.0003 and 0.0005M are used, then the rate constant is lowered to 0.03 and 0.022 min⁻¹, respectively. The observed inhibitory effect of Fe(III) in the present research is consistent with a previous study in which the researchers observed for a chemostat culture of T. ferrooxidans that Fe(III) may inhibit both growth and Fe(II) oxidation (19). Reportedly (19), inhibition by Fe(III) may take place either in a competitive or non-competitive manner.

Fate of silver

In order to examine whether silver ion is chemically reduced to metallic silver or sorbed on to the bacterial cell (either

physically or chemically), a number of experiments were performed to monitor the concentration of silver in solution with time. Typical experimental conditions included 1 or 2.5 mg/L silver, 0.001M Fe(II) and 0.0001M Fe(III) in 250mL deionized water of pH 1.7 at 25°C. In such an experiment, 3mL samples were withdrawn at the beginning and at the end of 30, 60 and 90 minutes after the start. The samples were filtered through 0.2 micron membrane filter and the filtrate analyzed for silver using flame AA. The constancy of the observed absorbance values indicate that silver ions were not reduced to silver metal, nor they are sorbed physically or chemically onto the T. ferrooxidans cells. If silver ions were reduced to metallic silver or bound to the microbial cells, then the bulk concentration of silver would have decreased. In deed, this was not observed.

This observation contradicts to the previous reports that silver accumulates in T. ferrooxidans cells (20), may bind to the DNA (21) or interact with the iron oxidase (4), even though our results generally agree with the previous reports that soluble Ag^+ is toxic to the bacteria (4, 10-13). However, one may not rule out the possibility that Ag^+ may interact with the cell active sites in an indirect manner. Silver may catalyze the formation of toxic $\text{O}_2^{\cdot -}$ species from dissolved oxygen. These toxic species may, in turn, modify the cellular activity (8), causing a decrease in the reaction rate. Further studies using electrochemical and spectroscopic techniques are in progress to generate information towards understanding the mechanism of inhibition of microbial oxidation of Fe(II) by silver and results will be reported in due course.

Conclusions

Microbial oxidation of ferrous iron by T. ferrooxidans was studied using a variety of experimental conditions, e. g. various solution

pH and temperature, different concentrations of bacteria, ferrous and ferric iron and heavy metal ions and period of conditioning the bacteria with heavy metal ions such silver. The results obtained lead to the following conclusions:

1) The bacterial oxidation of Fe(II) is pH dependent. The optimum pH range is observed to be 1.5-2.0.

2) At optimum pH and temperature, ferrous iron oxidizing ability of the T. ferrooxidans is strongly influenced by substrate to cell concentration ratio. If substrate to cell concentration ratio is varied from the optimum value, then the rate of reaction is likely to decline (Fig. 3). Under the conditions of our experiments, for a concentration T. ferrooxidans cells defined by OD590 = 2.8, the optimum Fe(II) concentration is 0.001M at 25°C and pH 1.7 in absence of a heavy metal.

3) The presence of some heavy metal ions in the biotic system has been observed to modulate the Fe(II) oxidizing activity of the T. ferrooxidans (Table 3). In our experiments, Hg(II), Ag(I), Pb(II) and Cd(II) are observed to inhibit the microbial oxidation of Fe(II), while Zn(II), Cu(II), Co(II) have no noticeable effect. However, the role of Mn(II), As(III) and Sn(II) on the microbial oxidation of Fe(II) is not clear from the results obtained so far.

4) The bacteria can maintain their Fe(II) oxidizing activity in the presence of a small amount of silver (generally <1 mg/L, dependent on pH). However, an appreciable concentration of silver (1 mg/L and over) is observed to be inhibitory to the Fe(II) oxidizing ability of the bacteria.

5) Conditioning of the bacteria with a significant concentration (1 mg/L or over) of silver is found to be more detrimental to the Fe(II) oxidizing activity of the T. ferrooxidans.

6) Use of conditioned bacteria (with silver) in experiments with solutions of pH beyond 1.5-2.0, the optimum pH range, results in a drastic reduction in the rate of the microbial Fe(II) oxidation (Fig. 9).

7) The T. ferrooxidans mediated oxidation of Fe(II) is remarkably sensitive to temperature changes. The optimum temperature for this reaction is 25°C. Any variation of temperature from this value is observed to reduce the reaction rate. Change of temperature above or below 25°C in the case of experiments involving 10 ppm silver is observed to cause further reduction of the rate of bacterial oxidation of Fe(II). Activation energy of the microbial oxidation of Fe(II), in the absence of silver is observed to be 11.51 Kcal mole⁻¹. In presence of 10 ppm silver this value increases to 12.33 Kcal mole⁻¹.

(8) The presence of 10 ppm Cl⁻ and NO₃⁻, practically, have no effect on Fe(II) oxidation catalyzed by T. ferrooxidans.

Acknowledgements

We thank the U.S. Department of Energy (University Coal Research Program) for financial support for this work under the grant number: DE-FG22-88PC88920. One of us (G. C. De) also thanks Jahangirnagar University, Bangladesh, for permission to undertake doctoral studies at the University of Idaho.

References

1. P. R. Norris and D. P. Kelly ed., (1988), Biohydrometallurgy: Proc. Int. Symp. (Warwick, 1987, Science and Technology Letters), p. 177-325.
2. B. J. Scheiner, F. M. Doyle and S. K. Kawatra ed. (1989), Biotech. Miner. Met. Process., (Littleton, CO: Society of Mining Engineers Inc), p. 9-31.
3. R. W. Bartlett, (Feb., 1990), "Aeration Pretreatment of Low Grade Refractory Gold Ores", Miner. Met. Process., p. 22.
4. K. Imai, T. sugio, T. Tsuchida and T. Tano, (1975), "Effect of Heavy Metal Ions on the Growth and Iron-oxidizing Activity of Thiobacillus ferrooxidans", Agri. Biol. Chem., vol. 39(7), p. 1349.
5. P. R. Norris and D. P. Kelly ed. (1988), Biohydrometallurgy: Proc. Int. Symp., (Warwick, 1987, Science and Technology

Letters), p. 103.

6. *ibid*, p. 89.

7. T. K. Datta, N. Ghosh, R. Sen and A. K. Dasgupta, (1990), "Pretreatment of Chalcopyrite Ore with Alkali: A Simple Technique to Improve the Leaching Mediated by Thiobacillus ferrooxidans", Miner. Eng., vol. 3(6), p. 641 and references cited therein.

8. T. G. Spiro ed., (1980), Metal Ion Activation of Dioxygen, (J. Wiley and Sons), p. 209.

9. O. H. Tuovinen and D. P. Kelly, (1974), "Studies on the Growth of Thiobacillus ferrooxidans II", Archiv. Microbiol., vol 95, p. 153.

10. B. J. Scheiner, F. M. Doyle and S. K. Kawatra ed., (1989), Biotech. Miner. Met. Process., (Littleton CO: Society of Mining Engineers Inc.), p. 95.

11. P. Roy and A. K. Mishra, (1981), "Iron Oxidation not Coupled to Growth in Thiobacillus ferrooxidans in Presence of Toxic Metals", J. Appl. Bact., vol. 51, p. 387.

12. O. H. Tuovinen, J. Puhakka, P. Hiltunen and K. M. Dolan, (1985), "Silver Toxicity to Ferrous Iron and Pyrite Oxidation and its Alleviation by Yeast Extracts in Cultures of Thiobacillus ferrooxidans", Biotech. Lett., vol. 7(6), p. 389.

13. B. Volesky ed., (1990), Biosorptions of Heavy Metals, CRC Press, Boston, p.104.

14. P. R. Norris and D. P. Kelly ed., (1988), Biohydrometallurgy: Proc. Int. Symp., (Warwick, 1987, Science and Technology Letters, p. 287.

15. A. Bruynesteyn, R. H. Hackl, R. W. Lawrence and A. I. Vizsolyi, (Feb. 1986), United States Patent 4,571,387, p. 59.

16. L. Ahonen and O. H. Tuovinen, (1990), "Catalytic Effects of Silver in the Microbiological Leaching of Finely Ground Chalcopyrite-containing Ore Materials in Shake Flasks", Hydromet., vol. 24, p. 219.

17. B. Pesic, D. J. Oliver and P. Wichlacz, (1989), "An Electrochemical Method of Measuring the Oxidation Rate of Ferrous Iron with Oxygen in the Presence of Thiobacillus ferrooxidans", Biotech. Bioeng., vol 33(4), p. 424.

18. B. Volesky ed., (1990), Biosorption of heavy metals, CRC press, Boston, p. 106 and reference(s) cited therein.

19. C. A. Jones and D. P. Kelly, (1983), "Growth of T. ferrooxidans on ferrous iron in chemostat culture: influence of product and substrate inhibition", J. Chem. Tech. Biotech., vol. 33B, p. 241.
20. F. D. Pooly, (Apr., 1982), "Bacteria Accumulate Silver During Leaching of Sulphide Ore Minerals", Nature, vol. 296, p. 642.
21. J. T. Trevors, (1987), "Silver Resistance and Accumulation in Bacteria", Enzyme Microb. Technol., vol. 9, p. 331.

Fig.1 Plot of potential of the pyrite indicator electrode as a function of time corresponding to different pH (without silver).

Fig. 2 Rate constant of the microbial oxidation of Fe(II) as a function of cell density (in terms of OD590) under standard conditions.

Fig. 3 Rate constant of the microbial oxidation of ferrous iron as a function of ferrous iron concentration (pH 1.7, OD590 2.8 and temperature 25C).

Fig. 4 Arrhenius plot of the oxidation of ferrous iron with *T. ferro-oxidans* in the absence and the presence of silver (OD590 2.8, pH 1.7 and concentration of silver 10 mg/lit).

Fig. 5 Potential of the pyrite indicator electrode versus time as a function silver concentration. There was no conditioning of the bacteria with silver.

Fig. 6. Variation of the rate constant of microbial oxidation of Fe(II) with concentration of silver at three different pH values. There was no conditioning of the bacteria with silver.

Fig. 7 Effect of initial ferric ion concentration on the rate of microbial oxidation of ferrous iron under standard conditions.

Fig. 8 Potential of pyrite indicator electrode versus time during oxidation of ferrous iron with bacteria, conditioned in solutions containing silver (10 mg/lit).

Fig. 9 Rate constant of the microbial oxidation of Fe(II) as a function of conditioning time of the bacteria with silver (other parameters unchanged).

Fig. 10 Plot of rate constant of the bacterial oxidation of Fe(II) as a function of pH (with and without silver).

END

**DATE
FILMED
4 129192**