DOE/PC/90056-T1

University of Kentucky
**CENTER FOR
APPLIED ENERGY
RESEARCH**

3572 Iron Works Pike
Lexington, KY 40511-8433
FAX: 606-257-0220

TECHNICAL PROGRESS REPORT FOR QUARTERLY PERIOD ENDING SEPTEMBER 30, 1991

TECHNOLOGY DEVELOPMENT FOR IRON FISCHER-TROPSCH CATALYSTS

#DE-AC22-91PC90056

P.I.: B. H. Davis

Begin Date: 12/18/90

End Date: 12/17/93

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

**An Equal Opportunity/
Affirmative Action University**

MAR 02 1992

QUARTERLY TECHNICAL PROGRESS REPORT

**Technology Development for Iron Fischer-Tropsch Catalysis - Period ending
September 30, 1991**

Contract No.:	DE-AC22-91PC90056	DOE/PC/90056--T1
Contractor:	University of Kentucky Research Foundation Kinkead Hall Lexington, KY 40506-0057	DE92 013028
Starting Date:	December 18, 1990	
Ending Date:	December 17, 1993	

A STUDY OF THE OXIDATION OF FERROUS HYDROXIDE IN SLIGHTLY BASIC SOLUTION

INTRODUCTION

It is established that aerial oxidation of $\text{Fe}(\text{OH})_2$ in aqueous solution can produce Fe_3O_4 , $\alpha\text{-FeOOH}$ or $\gamma\text{-FeOOH}$, depending on the reaction temperature, oxidation rate, initial reactant concentration and pH of the solution. Recently, it was reported that the initial molar ratio, $[\text{Fe}^{2+}]/[\text{OH}^-] = R$, significantly affected the structure of the product from air oxidation of $\text{Fe}(\text{OH})_2$ (1). For example, $\gamma\text{-FeOOH}$ will be major product when $R = 0.5833$ (7/12) and but it is not formed when $R < 0.5$.

On the other hand, it was reported that aerial oxidation of a neutral or slightly alkaline solution containing $\text{Fe}(\text{OH})_2$ yielded an intermediate green complex and solid Green Rust I or II, which depended on the anion coexisting in the solution: Green Rust I occurred when FeCl_2 was used as the starting material while Green Rust II was formed when FeSO_4 was used. The formation of the intermediate Green Rust has been considered to be necessary to effect the formation of $\gamma\text{-FeOOH}$ (2-5). This intermediate contains both $\text{Fe}(\text{II})$ and $\text{Fe}(\text{III})$ although its chemical composition has not been exactly defined. It can be further oxidized by air or oxygen to form either Fe_3O_4 or $\gamma\text{-FeOOH}$, or a mixture of the two, depending on the oxidation rate: fast oxidation produced $\gamma\text{-FeOOH}$ while slow oxidation resulted in the formation of Fe_3O_4 . Therefore, the formation of $\gamma\text{-FeOOH}$ in aqueous solution was restricted to the instances where the rapid aerial oxidation of ferrous ion was effected in a neutral solution or of $\text{Fe}(\text{OH})_2$ in a slightly basic solution. However, $\gamma\text{-FeOOH}$ was not formed from a ferric solution that did not contain ferrous ion when base was added to effect precipitation.

Although the oxidation process of $\text{Fe}(\text{OH})_2$ and the mechanism of formation of $\gamma\text{-FeOOH}$ have been studied by several groups, many questions still need to be answered. In addition, the procedure for the synthesis of pure $\gamma\text{-FeOOH}$ has not been well defined. This study is to an attempt to define better the chemistry associated with oxidizing Fe^{2+} to $\gamma\text{-FeOOH}$, and to provide a rationale for scaling this method up to produce kg/hr amounts of $\gamma\text{-FeOOH}$.

EXPERIMENTAL

Materials: Melanterite ($\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$), NaOH and $\text{Fe}_2(\text{SO}_4)_3$ were purchased from Aldrich. The chemicals were ACS reagent grade and were stored in a desiccator to prevent deterioration.

Apparatus: A four-neck round-bottom flask (1L) was fitted with a gas disperser (fritted-glass disc), pH electrode, motor-driven stirrer and gas inlet/outlet tubes. Inlet gas flow rate was monitored by a rotameter and the outlet gas by a wet-test flowmeter. The reaction vessel was placed in a constant-temperature water bath.

Preparation and Methods

After adding 500 mL deionized water to a 1L reaction flask, nitrogen gas was bubbled through the water (stirred at 1000 r.p.m.) for 40 min to remove dissolved carbon dioxide and oxygen, and then 41.7 g of $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ was added. After 10 minutes, a 2M NaOH solution (CO_2 and O_2 free) was added to give a molar ratio of $[\text{Fe}^{2+}] / [\text{OH}^-]$ of 0.5833 (7/12). The total volume was adjusted to 750 mL. The suspension was stirred for 15 minutes under nitrogen at room temperature until the suspension pH became constant. Oxygen was then passed into the solution at a constant rate of 20 cm^3/min . Reaction time was measured from the start of oxygen flow. During the

reaction, the pH value was recorded every minute. The extent of the oxidation reaction was easily recognized from a comparison of the outlet and inlet flow rate of oxygen, the pH of the suspension and the color. After 1 hr the oxidation had essentially stopped. The product was then collected by filtration; it was washed with deionized water several times until SO_4^{2-} was not detected in the filtrate, using BaCl_2 to test for the presence of SO_4^{2-} . The filter cake was then washed with acetone to remove most of the water. The precipitate was dried in vacuum at room temperature for 24 hr.

X-ray diffraction patterns of the product was measured using Cu K_α (1.5418 Å) radiation (40 KV and 20 mA) with a Philips X-ray diffractometer. The identification of the product was accomplished by matching the diffraction peak position and intensity with standards contained in the ASTM data (1,6).

To determine the phase and chemical composition of the intermediate products, samples were transferred to a Schlenk filter tube by a syringe at increasing time intervals; this was accomplished without exposure to air. The solid was collected and then washed successively with deoxygenated water and acetone, dried in vacuum at room temperature and stored at 4°C under a nitrogen atmosphere. For analysis by X-ray diffraction, the material was placed in a sample holder in a glove box immediately before recording the diffraction pattern.

RESULTS

A white precipitate was formed when FeSO_4 and NaOH were mixed in a ratio so that the pH of the suspension was 8.2. When oxygen was passed through the resulting iron hydroxide suspension, the white precipitate was oxidized and the color of the mixture turned first to green, then blue, and finally orange-yellow. The oxygen

reacted completely when its flow rate was 18.5 mL/min (Fig.1); oxygen usage can be easily estimated from the oxygen flow data. Approximately one hour was needed to complete the conversion of 6/7th of the Fe(II) to Fe(III).

The change in pH with time is presented in Fig. 1. At least two stages can be observed. During the first stage, the pH of the suspension was reduced only from 8.2 to 8.0. The viscosity of the mixture increased as oxidation progressed during this first stage. The first stage took about 16 min and approximately 28 mol% of the total iron(II) was oxidized during this stage. At the end of this stage, the pH abruptly decreased to 6.5 during 4-5 min with continuous oxygen flow. During this time, however, the pH did not continue to decrease if the oxygen flow was stopped. Thus, the sharp drop in pH is due to oxidation of Fe(II) by oxygen, and the hydrolysis reactions caused by the oxidation species.

During the second stage the pH remained at 6.5. When oxygen flow was stopped at any time during this second stage, the pH of the suspension increased slightly to about 7.0. However, the pH quickly decreased to 6.5 when oxygen flow was resumed. As with the first stage, there was finally an abrupt decrease in pH to less than 4. Following the second abrupt decrease in pH, oxygen consumption became very low and the pH remained nearly constant. The second step occurred when about 90 mole % of the total Fe (II) had been oxidized to Fe(III).

It should be possible to mimic the oxidation process by stopping the oxygen flow and adding Fe(III). This experiment is illustrated in Figure 2. Oxygen was flowed during the period corresponding to the portion of the curve between A and B. At B, the pH had just started to decrease corresponding to completion of the first stage. At

this point the oxygen flow was stopped and a slight increase in the pH occurred (BC). At point C, a solution of Fe(III) sulfate was added at a rate to correspond to a rate of Fe(III) being formed had oxygen flow been continued. The Fe(III) solution was added between points C and D; the Fe(III) caused the pH to decrease just as oxidation to Fe(III) does; this means that the hydrolysis of the Fe(III) ion is responsible for the generation of H^+ . The addition of Fe(III) does not appear to influence the time required to complete the second stage of the oxidation. In Figure 1 it is noted that the time required to complete the first stage is about half that required for the second stage; this is expected if the green rust has a stoichiometry corresponding to $\{Fe(III)_2 Fe(II)_4 (FeSO_4)\}$. In Figure 2, it appears that the times required for each of the stages is similar to that of Figure 1 if the time when oxygen is not flowing is taken into account.

The results in Figure 3 demonstrate the impact of stopping oxygen flow for a period and for adding H_2SO_4 at the same rate as the conversion of oxygen would produce H^+ . In the experiment represented in Figure 3, oxygen flow was continued until the pH began to decline (portion AB). At point B the oxygen flow was terminated and there was a gradual, but slight, increase in pH (BC). The slow increase in pH implies that the rate of production of H^+ is more rapid than the reaction(s) which consume H^+ . One possibility is that the dissolution of $Fe(OH)_2$ is the proton consuming reaction:

Between C and D sulfuric acid was added at a rate corresponding to that of oxidation; the pH changed just as it did in Figure 1 for oxidation with O_2 . The addition of sulfuric

acid during the second stage (during EF and GH) caused a decrease in the pH. However, in the absence of a flow of oxygen the pH, following sulfuric acid addition at EF, gradually returned to about the same pH as before addition of the acid. This is again consistent with the reaction that consumes H^+ being a slow reaction. The addition of H_2SO_4 during either stage one or stage two had only a transitory impact upon the pH/time curve.

The addition of base during the second stage caused an immediate increase in pH (Figure 4). Continuing the oxygen flow following base addition caused a rapid decrease in pH. This again implies that H^+ generation during oxygen addition is rapid, and that H^+ reaction with OH^- is rapid compared to the gradual reaction with the H^+ generated or added under conditions shown in Figure 3.

The oxidation of $FeSO_4$ has also been carried out in a dilute solution. A $FeSO_4$ solution (0.029M, 750 ml) was carefully titrated with NaOH (0.1N) until the pH of the solution was 7.8; precipitation did not occur during this operation. Oxygen was then passed through this solution. The pH vs. time curve (Fig.7) shows that there is no plateau for the first stage, instead, the pH smoothly decreases with time. However, there does appear to be a slight plateau that could be due to a second stage reaction.

It has been reported (7) that K_{sp} for ferrous hydroxide is about 10^{-14} . Using this K_{sp} , one can calculate that the curve shown in Figure 5 should be expected. Thus,

$$K_{sp} = 10^{-14} = [Fe^{2+}][OH^-]^2 = [0.03][OH^-]^2 \quad [2]$$

and

$$[OH^-] = \sim 5.8 \times 10^{-7} \text{ M/L} \quad [3]$$

The OH^- concentration due to dissociation of pure water is about 10^{-7} . Thus, the addition of 0.03M $\text{Fe}(\text{OH})_2$ will only marginally increase the OH^- concentration over that of pure water. If the solubility is due to the equation

the contribution of the iron compound to the concentration of OH^- will be even less. It is therefore reasonable that there should be little deviation from the curve expected for the addition of sulfuric acid to pure water.

The X-ray diffraction patterns of the green solid collected at the end of the first oxidation stage, but while the pH was still 8.0, is shown displayed in Figure 6. The pattern contains strong peaks at $2\theta = 8, 16$ and 24 degrees, which corresponds to the $[00Z]$ reflection of Green Rust (II) (6). The green intermediate in the solid state appears to be less readily oxidized than it is in an aqueous suspension since the change in color and XRD pattern was not observed until the solid was exposed to air for 90 minutes.

The only crystalline phase detected in the product collected following the completion of oxidation corresponding the end of the second stage was $\gamma\text{-FeOOH}$. The XRD pattern in Figure 7, with the five most intense peaks at $2\theta \sim 14, 27,$ and 36 degrees, is that expected for $\gamma\text{-FeOOH}$.

DISCUSSION

In the present experiment, molar ratio of $[\text{Fe}^{2+}] : [\text{OH}^-]$ was 0.5833(7/12). Thus, the initial reaction can be described as follows:

Under this condition, essentially all of the initial OH^- ions added are consumed to form Fe(OH)_2 , and 1/7th of the Fe^{2+} is left in solution.

As oxygen is passed through the suspension, ferrous ions in the solution are oxidized to produce ferric ions which combine with ferrous ions to form a mixed-valence green complex. It has been reported (8) that the green complex consists of Fe(II)-O-Fe(III) , which exhibits a charge transfer absorption band at 337 nm due to the oxo-bridges. The soluble green complex has been proposed to have the empirical formula $[(\text{Fe}^{2+})_2(\text{Fe}^{3+})(\text{OH})_4(\text{O}^{2-})]^+$ (9). The green rust has been viewed to have limited solubility and precipitates during the first stage, incorporating sulfate ion for charge balance. This intermediate is oxidized further to produce $\gamma\text{-FeOOH}$ during the second stage. At the end of first stage, Fe(OH)_2 has been completely converted to Green Rust(II) at a pH 8.0. Thus, the molar fraction of Fe(III) in green rust(II) is estimated to be about 30 per cent. The suggested chemical formula, which was based upon Mössbauer data and chemical analysis is $4\text{Fe(OH)}_2 \bullet 2\text{FeOOH} \bullet \text{FeSO}_4 \bullet n\text{H}_2\text{O}$ (1,9). The percentage of Fe^{3+} calculated from the amount of oxygen consumed agrees with the amount expected for this formula.

For such a complex situation one could envision a large number of oxidation-reduction schemes. Standard reduction potentials of oxygen in acid ($\text{pH} = 0$) and alkaline ($\text{pH} = 14$) solutions are listed in Table 1 together with the reduction potentials for $\text{pH} = 8.2$ and 6.5 , the pH for the first and second stage reactions respectively (10). The reduction potential can be calculated from

$$E/\text{volt} = E^{\circ} + 0.05916 \log H^{+}(\text{mol/l})PO_2(\text{atm})^{1/2} \quad [6]$$

The reduction potentials of the couples O_2/H_2O and H^{+}/H_2 as a function of pH are illustrated in Figure 8. In theory, the solvent should be oxidized to O_2 when the reduction potential is greater than the solid line in Figure 8. Actually, kinetic effects may require a greater potential than represented by the solid line. Thus, the broken line in Figure 8 represents this kinetic effect by estimating that the overpotential to account for kinetic effects is 0.5V. Thus, in practical cases oxygen (or hydrogen) formation is better represented by the broken line.

Peroxide is involved in several reactions listed in the acidic section of Table 1. This provides a complication since H_2O_2 can act as both an oxidizing and reducing agent. Thus, many materials are effective for the catalytic decomposition of peroxide. This decomposition can be viewed as an oxidation-reduction process and most homogeneous catalysts are oxidation-reduction couples of which the oxidizing agent can oxidize (be reduced by) H_2O_2 and the reducing agent can reduce (be oxidized by) H_2O_2 . The data in Table 1 indicate that any complex with a reduction potential in acid between 0.695 and +1.776 should catalyze the reaction. For the couple Fe^{3+}/Fe^{2+} , E° is +0.771V; thus a mixture of Fe^{2+} and Fe^{3+} should catalyze the decomposition of peroxide, and it does. Thus:

$$2Fe^{3+} + H_2O_2 \xrightarrow{-2H^+} 2Fe^{2+} + O_2 \quad [7]$$
$$2Fe^{2+} + H_2O_2 \xrightarrow{+2H^+} 2Fe^{3+} + 2HO_2 \quad [8]$$
$$\text{NET: } 2\text{H}_2\text{O}_2 \rightarrow 2\text{H}_2\text{O} + \text{O}_2 \quad [9]$$

Considering the equations and the corresponding emf at a pH of about 8.2, where the green rust is formed during the first stage of the oxidation, it appears that the sequence of reactions listed below is most reasonable:

$$\begin{array}{l} \text{O}_2 \xrightarrow{+\text{e}^-} \text{O}_2^- \xrightarrow{+\text{H}_2\text{O}, \text{e}^-} \text{HO}_2^- + \text{OH}^- \\ \quad \quad \quad \quad \quad \quad \quad \downarrow +\text{H}_2\text{O}, 2\text{e}^- \\ \quad \quad \quad \quad \quad \quad \quad 3\text{OH}^- \end{array} \quad [10]$$

and the net reaction for reduction is

$$O_2 + 2H_2O + 4e^- \rightarrow 4OH^- \quad [11]$$

Fe(II) is oxidized, and then undergoes hydrolysis:

$$Fe(OH)_2 \rightarrow Fe(OH)_2^+ + e^- \quad [12]$$
$$FeOH_2^+ + H_2O \rightarrow Fe(OH)_3 + H^+ \quad [13]$$

For this consideration it does not matter whether we write the Fe(III) species as $\text{Fe}(\text{OH})_3$ or a decomposition product, FeOOH (+ H_2O). Thus, the net reaction for oxidation at $\text{pH} = 8.2$ is

During the first stage the $\text{Fe}(\text{OH})_3$ species does not remain but further reacts to dehydrate and/or then to produce green rust:

This Fe(III) species is probably not completely formed but rather reacts with Fe(II) species to form a complex that can formally be described as:

Combining two of the above species would provide a possible structure for green rust (1,10):

The above equations ([11] and [14]) cannot explain why there should be a rapid decrease in the pH at the completion of the first stage. However, the pH certainly does decrease, and it decreases in a similar manner when Fe(III) is added as when oxidation continues. It appears that the first step change in pH is a result of the relative kinetic of H^+ generation and consumption together with a change in the reaction pathway for oxygen. The following is taken as evidence to support the view

that in a slightly basic solution the reaction that generates H^+ is much more rapid than the reaction(s) that consume it:

1. When oxygen flow is temporarily stopped there is a gradual, and not the abrupt change as noted with pH decrease, increase in pH.
2. When an OH^- containing solution is added to the suspension there is nearly an instantaneous increase in the pH, unlike the slow increase noted when oxygen flow is stopped.
3. Following addition of OH^- and continued oxygen flow there is a rapid decrease in pH to attain the value that existed prior to OH^- addition.
4. The addition of Fe(III) causes a rapid decrease in pH.

Thus, at or near the completion of the formation of green rust, the situation resembles that shown in Figure 5.

One possible explanation is that the more rapid reaction (production of H^+ in contrast to the slower series reaction leading to OH^-) produces a sufficient excess of H^+ to cause a sufficient decrease in pH to effectively stop the formation of the final product, OH^- , and to effect a change in the reaction pathways for reduction of the oxygen. It is speculated that as the H^+ concentration increases the intermediate in the basic reduction, HO_2^- , is converted to H_2O_2 , and then to water, rather than to OH^- as was the case in the basic media.

Another possibility is that as long as there is an excess of solid (Fe(II)), the precipitation of Fe(III) and Fe(II) as green rust allows the two reaction couples to produce H^+ and OH^- in equal amounts. Upon depletion of most of the Fe(II) it is

possible that the Fe(III) species, following hydrolysis to formally produce $\text{Fe}(\text{OH})_3 + \text{H}^+$, undergoes dimerization, etc. that produces additional H^+ .

Another possibility is that the oxidation of the FeSO_4 , and 1/7th of the initial Fe(II) is present as FeSO_4 , begins with the depletion of the $\text{Fe}(\text{OH})_2$ through partial oxidation and combination of the Fe^{2+} and Fe^{3+} to form green rust. Thus, if this is the case, the hydrolysis of the resulting Fe^{3+} would produce a proton for each FeSO_4 that is oxidized. Only an insignificant amount of the FeSO_4 present in the 0.2 or (1.2M) Fe suspension would have to be oxidized to decrease the pH from about 8 to 6.5; at a pH = 6.5 the oxidation of green rust becomes responsible for the consumption of oxygen and the pH remains essentially constant during the second stage. Upon completion of oxidation of the Fe(II) present in green rust at the completion of the second stage, the oxidation of FeSO_4 again takes place with a resulting decrease in pH until such a low pH is attained that oxidation will essentially cease. Whether one of these, or some other reaction, is responsible for the sudden step change in pH, it is an experimental fact that the pH does decrease and that oxidation of the green rust intermediate occurs at approximately pH = 6.2

The oxidation processes for low concentrations of iron in neutral or slightly acidic media using oxygen has been studied extensively (for example, 11-18). Goto (12), for example, proposed that the following reactions are involved in this oxidation:

Globally, it has been shown that the stoichiometry describing the oxidation of Fe(II) to Fe(III) and its subsequent hydrolysis is described as (16-18):

While this net reaction may account for dilute Fe(II) salt solutions such as $FeSO_4$, and even for the dilute solutions as used for generating the data in Figure 5, it cannot account for the case of $Fe(OH)_2$ oxidation as represented in Figure 1. In this case we have

and the pH of the solution will remain constant.

Thus, based on the reactions proposed by Goto (12), one possible pathway is:

Oxidation

Reduction

Combining the oxidation and reduction equations provides one of the possible global equations for the oxidation process that occurs during the constant pH portion that constitutes the second stage.

In principle, the above oxidation of $Fe(OH)_2$ by the above reaction could be effected in the solid state; however, it appears that the indirect reaction is not only faster but is able to selectively form the uniform green rust species wherein the arrangements of the $Fe(III)$ and $Fe(II)$ ions in the same in each unit.

The above reaction scheme cannot describe all oxidations of $Fe(II)$ by oxygen. The reactions are applicable, however, for the suspension has $[Fe]/[OH] \sim 0.58$ as was the case for this particular investigation.

REFERENCES

1. A. A. Olowe, B. Pauron, J. M. R. Genin, Corrosion Science, **32**, 985 (1991).
2. M. Kiyama, N. Jikuhara, T. Takada, Bull. Chem. Soc. Japan, **46**, 323 (1973).
3. M. Kiyama and T. Takada, Bull. Chem. Soc. Japan, **45**, 1923 (1972).

4. M. Kiyama, T. Akita, S. Shimizu, Y. Okuda and T. Takada, Bull. Chem. Soc., **45**, 3422 (1972).
5. M. Kiyama, Bull. Chem. Soc. Japan, **47**, 1646 (1974).
6. J. D. Bernal, E. R. Dusyputa, and A. L. Marckay, Clay. Min. Bull., **4**, 15 (1959).
7. N. N. Greenwood and A. Ernschaw, "Chemistry of the Elements", Pergamon Press, Oxford, 1984, pg 1269.
8. T. Misawa, K. Hashimoto, W. Suetaka, and S. Shimodaira, J. Inorg. Nucl. Chem., **35**, 4159 (1974).
9. T. F. Barton, T. Price, and J. G. Dillars, J. Coll. & Interface Sci., **141**, 553 (1991).
10. N. N. Greenwood and A. Ernschaw, "Chemistry of the Elements", Pergamon Press, Oxford, 1984, pg 736.
11. H. Tamara, K. Goto, and M. Nagayama, J. Inorg. Nucl. Chem., **38**, 113 (1976).
12. K. Goto, H. Tamara, and M. Nagayama, J. Inorg. Chem., **9**, 963 (1970).
13. J. Weiss, Naturwissenschaften, **23**, 64 (1935).
14. F. Haber and J. Weiss, Proc. Roy. Soc. (London), **A147**, 332 (1934).
15. G. W. Burb, J. H. Baxendale, P. Geoge, and K. r. Hargrave, Trans. Faraday Soc., **47**, 462 (1957).
16. G. Z. Just, J. Phys. Chem., **63**, 385 (1908).
17. J. Halide, M. Eberhardt, Vom Wasser, **79**, 24 (1957).
18. W. Stumm and G. F. Lee, Ind. Eng. Chem., **53**, 143 (1961).

Table 1

Standard Reduction Potentials for Oxygen in Acid and
Basic Solution and Reduction Potentials at pH 6.5 and 8.2

Acidic

	<u>E°</u>	<u>pH</u>	
		<u>6.5</u>	<u>8.2</u>
$O_2 + 4H^+ + 4e^- \rightleftharpoons 2H_2O$	1.229	0.8445	0.7439
$O_2 + 2H^+ + 2e^- \rightleftharpoons H_2O_2$	0.695	0.311	0.210
$O_2 + H^+ + e^- \rightleftharpoons HO_2$	-0.105	-0.490	-0.590
$H_2O_2 + H^+ + e^- \rightleftharpoons H_2O$	1.495	1.111	0.626
$H_2O_2 + 2H^+ + 2e^- \rightleftharpoons 2HO_2$	1.776	1.39	1.29
$H_2O_2 + H^+ + e^- \rightleftharpoons OH + H_2O$	0.71	0.326	0.225
$OH + H^+ + e^- \rightleftharpoons H_2O$	2.85	2.47	2.37

Basic

$O_2 + 2H_2O + 4e^- \rightleftharpoons 4OH^-$	0.401	0.845	0.7441
$O_2 + H_2O + 2e^- \rightleftharpoons HO_2^- + OH^-$	-0.076	0.309	0.409
$O_2 + e^- \rightleftharpoons O_2^-$	-0.563	-0.119	-0.220
$O_2^- + H_2O + e^- \rightleftharpoons HO_2^- + OH^-$	0.413	0.857	0.756
$HO_2^- + H_2O + 2e^- \rightleftharpoons 3OH^-$	0.878	1.32	1.22
$HO_2^- + H_2O + e^- \rightleftharpoons OH + 2OH^-$	-0.245	0.199	0.098
$OH + e^- \rightleftharpoons OH^-$	2.02	2.46	2.36

Figure 1. Recorded variation of pH and oxygen flow rate with oxidation time, oxygen flow rate: 18.5 mL/min.

Figure 2. Recorded variation of the pH with respect to oxidation and the addition of Fe(III) (oxygen flow during the period represented by AB and DE; oxygen flow stopped during BC; Fe(III) added during CD).

Figure 3. Recorded variation of the pH with respect to time of oxidation and for sulfuric acid addition (oxygen flow during the curve between AB, DE and HI; oxygen flow stopped during the period represented by BC and FG; sulfuric acid added during CD, EF and GH).

Figure 4. Recorded variation of pH with oxidation time (oxygen flow during periods AB, CD, EF and GH; NaOH was added during BC, DE and FG).

Figure 5. Recorded variation of pH with oxidation time ($[\text{Fe(II)}] = 0.029\text{M}$) (see text).

Figure 6. X-ray diffraction patterns of the Green rust sample taken out at the end of the first stage with pH 8.0 during the course of the oxidation of ferrous hydroxide.

Figure 7. X-ray diffraction patterns of the end product of oxidation.

Figure 8. Variation of the reduction potentials of the couples O_2/H_2O and H^+/H_2 as a function of pH (full lines). The broken lines are 0.5V above or below the solid lines and give the approximate limits of oxidants or reductants in aqueous solution beyond which the solvent itself is oxidized to O_2 (gas) or reduced to H_2 (gas).

END

DATE
FILMED

6/12/92