12/28/85 JFS (3) Cost 34
3

I-20/98

DR-0904-0

ORNL-6128

ornl

**OAK RIDGE
NATIONAL
LABORATORY**

MARTIN MARIETTA

SOLID STATE DIVISION

PROGRESS REPORT

Period Ending September 30, 1984

MASTER

OPERATED BY
MARTIN MARIETTA ENERGY SYSTEMS, INC.
FOR THE UNITED STATES
DEPARTMENT OF ENERGY

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ORNL--6128

DE85 008766

Contract No. DE-AC05-84OR21400

SOLID STATE DIVISION
PROGRESS REPORT
for Period Ending September 30, 1984

M. K. Wilkinson, Director
F. W. Young, Jr., Associate Director
B. R. Appleton, Section Head
J. F. Cooke, Section Head
L. H. Jenkins, Section Head
R. M. Nicklow, Section Head

Edited by:
P. H. Green
D. M. Watson

Date Published - March 1985

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831
operated by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
DEPARTMENT OF ENERGY

Reports previously issued in this series are as follows:

ORNL-1095	Period Ending April 30, 1951
ORNL-1128	Period Ending July 31, 1951
ORNL-1214	Period Ending October 31, 1951
ORNL-1261	Period Ending January 31, 1952
ORNL-1301	Period Ending May 10, 1952
ORNL-1359	Period Ending August 10, 1952
ORNL-1429	Period Ending November 10, 1952
ORNL-1506	Period Ending February 10, 1953
ORNL-1606	Period Ending August 30, 1953
ORNL-1677	Period Ending February 28, 1954
ORNL-1762	Period Ending August 31, 1954
ORNL-1951	Period Ending February 28, 1955
ORNL-1852	Period Ending February 28, 1955
ORNL-1944	Period Ending August 31, 1955
ORNL-1945	Period Ending August 31, 1955
ORNL-2051	Period Ending February 29, 1956
ORNL-2052	Period Ending February 29, 1956
ORNL-2188	Period Ending August 31, 1956
ORNL-2189	Period Ending August 31, 1956
ORNL-2413	Period Ending August 31, 1957
ORNL-2414	Period Ending August 31, 1957
ORNL-2614	Period Ending August 31, 1958
ORNL-2829	Period Ending August 31, 1959
ORNL-3017	Period Ending August 31, 1960
ORNL-3213	Period Ending August 31, 1961
ORNL-3364	Period Ending August 31, 1962
ORNL-3480	Period Ending May 31, 1963
ORNL-3676	Period Ending May 31, 1964
ORNL-3841	Period Ending May 31, 1965
ORNL-3935	Period Ending December 31, 1965
ORNL-4098	Period Ending December 31, 1966
ORNL-4250	Period Ending December 31, 1967
ORNL-4408	Period Ending December 31, 1968
ORNL-4526	Period Ending December 31, 1969
ORNL-4769	Period Ending December 31, 1970
ORNL-4779	Period Ending December 31, 1971
ORNL-4861	Period Ending December 31, 1972
ORNL-4952	Period Ending December 31, 1973
ORNL-5078	Period Ending December 31, 1974
ORNL-5135	Period Ending December 31, 1975
ORNL-5328	Period Ending April 30, 1977
ORNL-5486	Period Ending September 30, 1978
ORNL-5640	Period Ending February 29, 1980
ORNL-5850	Period Ending September 30, 1981
ORNL-5975	Period Ending March 31, 1983

Contents

ACRONYMS, ABBREVIATIONS, AND INITIALISMS	xiii
INTRODUCTION	xv

1. THEORETICAL SOLID STATE PHYSICS

SURFACES

Rippled Relaxation in the (110) Surface of the Ordered Metallic Alloy NiAl—H. L. Davis and J. P. Noonan	2
Layer Relaxation of the Clean W(112) Surface and Its Variation with Adsorbed Oxygen—H. L. Davis and G.-C. Wang	5
Angular Symmetry of the Ion Scattering Surface Yield for Large Outer Layer Relaxations—R. J. Culbertson, J. H. Barrett, and S. P. Withrow	7
Approximation for the Surface Backscattering Yield from an Atomic Row with Correlated Thermal Vibrations—D. P. Jackson and J. H. Barrett	8
Spin Waves at Surfaces and Interfaces in Cubic Heisenberg Systems—Gu Xing Xu, Mark Mostoller, and A. K. Rajagopal	8
Oscillatory Oxidation of CO over Pt, Pd, and Ir Catalysts: Theory—B. C. Sales, J. E. Turner, and M. B. Maple	9

ELECTRONIC, VIBRATIONAL, AND MAGNETIC PROPERTIES

Elastic Vibrations in Fractal Systems—S. H. Liu	10
New Interpretation of Spin-Wave Behavior in Nickel—J. F. Cooke, J. A. Blackman, and T. Morgan	11
Paramagnetic Form Factors from Itinerant Electron Theory—J. F. Cooke, S. H. Liu, and A. J. Liu	13
Band Structure Effects in the Electronic Properties of Solids Assessable by Neutron Scattering Studies—J. F. Cooke, J. A. Blackman, and T. Morgan	15
Critical Behavior of a Dilute Interacting Bose Fluid—M. Rasolt, M. J. Stephen, M. F. Fisher, and P. B. Weichman	17
Phase Transitions in a Third-Rank Tensor Hamiltonian: Application to Systems with Tetrahedral Symmetry—M. Rasolt and A. D. J. Haymet	18
Structure Factor of a Correlated Nonuniform Fermion Gas at Small Wavelength—M. Rasolt	19
Structure Factors for a Binary Mixture of Quantum and Classical Fermion Liquids—Mark Rasolt	20
Long-Range Part of the Interaction between Two Hydrogen Impurities in Jellium—F. Perrot and M. Rasolt	20
Traveling Cluster Approximation for Uncorrelated Amorphous Systems—Theodore Kaplan, L. J. Gray, A. K. Sen, and R. Mills	21

Lattice Vibrations in K_2Rb_{1-x} Alloys—Theodore Kaplan, Mark Mostoller, and L. J. Gray	22
Ionic Potential Models in Insulators Having the Rutile Structure—Mark Mostoller and J. C. Wang	23

PARTICLE-SOLID INTERACTIONS

The Role of Nonlocal Inelastic Energy Losses in Sputtering—M. T. Robinson	25
Ion Backscattering from Layered Targets—O. S. Oen and M. T. Robinson	26
Ion Damage in Crystalline Silicon—O. S. Oen	27
Ion Channeling in Elastically Strained Superlattices—J. H. Barrett	28
Structure Study of a GaSb/AlSb Strained Layer Superlattice—C. K. Pan, D. C. Zheng, T. G. Finstad, W. K. Chu, V. S. Speriosu, M.-A. Nicolet, and J. H. Barrett	29

LASER-SOLID INTERACTIONS AND RAPID SOLIDIFICATION

Multilayer Interfacial Model of Crystal Growth and Nonequilibrium Dopant Segregation—R. F. Wood, J. F. Cooke, T. Kaplan, and M. Mostoller	30
Bulk Nucleation and Amorphous Phase Formation in Highly Undercooled Molten Silicon—R. F. Wood, D. H. Lowndes, and J. Narayan	31
Modeling of Solidification Processes in Highly Undercooled Silicon and Germanium—R. F. Wood, A. Geist, A. Solomon, and G. E. Giles	32
Lifetime of an Electron-Hole Plasma of Silicon in the Picosecond Range—M. Rasolt and H. Kurz	33
Electron-Hole Plasma Formation in Semiconductors Due to the Absorption of Pulsed CO_2 Laser Light—R. B. James	35
Optically Induced Intervalence-Band Transitions in Germanium by the Absorption of 1.06- μm Picosecond Pulses—R. B. James	35
Interaction of a Tunable Probe Beam with a High-Intensity Pulsed CO_2 Laser Beam in p-Type Germanium—R. B. James and D. L. Smith	36

2. SURFACE AND NEAR-SURFACE PROPERTIES OF SOLIDS

SURFACE SCIENCE

The Effect of Surface Steps on W(001) Reconstruction Domains—J. F. Wendelken and G.-C. Wang	40
Finite Size Effects on the Critical Behavior of the W(001) Low-Temperature Phase Transition—J. F. Wendelken and G.-C. Wang	42
A Physical Realization of Two-Dimensional Ising Critical Phenomena: Oxygen Chemisorbed on the W(112) Surface—G.-C. Wang and T.-M. Lu	43
Distribution of Domain Sizes during Overlayer Growth—J. M. Pimbley, T.-M. Lu, and G.-C. Wang	45
More Than One Monolayer Adsorption of Oxygen on the W(112) Surface—G.-C. Wang, J. M. Pimbley, and T.-M. Lu	46
Oxygen Ordering on Cu(110)—G. R. Gruzalski, D. M. Zehner, J. F. Wendelken, and R. S. Hathcock	46
An XPS Study of Molecular and Atomic Oxygen on Cu(110)—G. R. Gruzalski, D. M. Zehner, and J. F. Wendelken	48
An Angle-Resolved UPS Study of the Oxygen-Induced Reconstruction of Cu(110)—R. A. DiDin, D. M. Zehner, and E. W. Plummer	49

Ion Scattering Study of Reconstruction in the Au(110)-(1×2) Surface—S. P. Withrow, J. H. Barrett, and R. J. Culbertson	50
Truncation-Induced Relaxations for a High-Index Surface—R. Noonan, H. L. Davis, and W. Erley	52

PLASMA-MATERIALS INTERACTIONS

Time-Resolved Impurity Fluxes in the TEXTOR Plasma Edge—R. A. Zuhr and W. R. Wampler	54
Deuterium Fluxes in the TEXTOR Plasma Edge Using Deposition Probe Techniques—R. A. Zuhr	56
The Influence of Impurities on the High-Temperature Sputtering Yield of Graphite—J. Roth, J. Bohdanský, and J. B. Roberto	57
Use of Isotopically Enriched Carbon Probes for Erosion/Deposition Measurements in the ASDEX Divertor—J. B. Roberto, J. Roth, E. Taglauer, and O. W. Holland	57
Ion-Enhanced Erosion of Graphite at High Temperature—J. Roth, J. B. Roberto, and K. L. Wilson	58
Beryllium Limiter Studies in ISX-B—R. A. Zuhr and J. B. Roberto	59
Synergistic Effects in Plasma Surface Interactions—J. B. Roberto and R. Behrisch	59
Time-Resolved Erosion Measurements at a Reference Limiter in ISX-B Using Laser-Induced Fluorescence—T. B. Cook, P. W. King, J. B. Roberto, K. A. Stewart, and K. E. Yokoyama	60
Measurement of the Ionization Length for Neutral Iron Near the Wall in the ISX-B Tokamak Using Laser-Induced Fluorescence—T. B. Cook, P. W. King, and J. B. Roberto	61

ION IMPLANTATION AND ION-BEAM PROCESSING

Morphological Instabilities and Ion Beam Mixing in Ge—B. R. Appleton, O. W. Holland, D. B. Poker, J. Narayan, and D. Fathy	62
Linear Dose Dependence of Ion Beam Mixing of Metals on Si—D. B. Poker and B. R. Appleton	63
Ion Mixing Studies of Self-Isotopes in Graphite—D. B. Poker, J. B. Roberto, J. Roth, and W. Möller	65
Effect of Boundary Conditions in Ion Mixing of Multilayered Ni-Si Samples—C. A. Hewett, S. S. Lau, I. Suni, and D. B. Poker	65
Comparison between Thermal Annealing and Ion Mixing of Alloyed and Multilayer Ni-W Films on Si— C. S. Pai, S. S. Lau, and D. B. Poker	66
Ion Beam Mixing in Ni-Al and Pd-Al Alloy Systems—M. Nastasi, J. M. Williams, L. S. Hung, H. H. Johnson, and J. W. Mayer	66
Enhanced Depth of Amorphization of Semiconductors by Molecular Implantation Due to Residual Gas Scattering—D. A. Hansen, D. B. Poker, and B. R. Appleton	67
Influence of Substrate Temperature on the Formation of Buried Oxide and Surface Crystallinity during High-Dose Oxygen Implantation into Silicon—O. W. Holland, T. P. Sjoreen, D. Fathy, and J. Narayan	68
A Search for Solute Drag—M. J. Aziz, D. H. Lowndes, G. E. Jellison, Jr., C. W. White, J. Y. Tsao, M. O. Thompson, P. S. Peercy, and W. H. Christie	70
Pressure Dependence of the Diffusivity of Arsenic in Crystalline Si—E. Nygren, M. J. Aziz, D. Turnbull, J. M. Poate, D. C. Jacobson, and R. Hull	70
Ion Implantation Effects in Silicon Carbide—J. M. Williams, B. R. Appleton, C. J. McHargue, G. M. Reagin, H. J. Kim, and R. F. Davis	71
Ion-Induced Decomposition and Mixing Effects in LiNbO_3 —B. R. Appleton, G. M. Beardsley, W. H. Christie, R. Eby, P. Ash'ev, and C. Bahr	72

Formation of Amorphous Layers in Al_2O_3 by Ion Implantation—C. W. White, G. C. Farlow, C. J. McHargue, P. S. Sklad, M. P. Angelini, and B. R. Appleton	73
Thermal Annealing of Fe-Implanted Al_2O_3 in Oxidizing and Reducing Environments—G. C. Farlow, C. W. White, C. J. McHargue, P. S. Sklad, and B. R. Appleton	74
Behavior of Implanted $\alpha-Al_2O_3$ in an Oxidizing Annealing Environment—G. C. Farlow, C. W. White, C. J. McHargue, and B. R. Appleton	75
Ion Implantation of Surgical Ti-6Al-4V Alloy—J. M. Williams, G. M. Beardsley, R. A. Buchanan, R. K. Bacon, and E. D. Rigney	77
Potential and Stopping Power Information from Ion Channeling in Ge—R. J. Culbertson, S. P. Withrow, and J. H. Barrett	78
Subsurface Strain in Semiconductor Surfaces: Comparison of Ge and Si—R. J. Culbertson, Y. Kuk, and L. C. Feldman	79

PULSED-LASER AND THERMAL PROCESSING

Review of Pulsed-Laser Annealing Effects in Silicon—B. C. Larson	81
X-ray Measurement of Overheating and Undercooling in Si during Pulsed-Laser Irradiation—B. C. Larson, J. Z. Tischler, and D. M. Mills	81
Germanium Laser Annealing—J. Z. Tischler, B. C. Larson, and D. M. Mills	82
Competition between Glass Formation and Nonequilibrium Crystallization during Ultrarapid Solidification of Cu-Ti Alloys—D. H. Lowndes, C. G. Woychik, and T. B. Massalski	84
UV Laser Incorporation of Dopants in Silicon: Comparison of Two Processes—E. P. Fogarassy, D. H. Lowndes, J. Narayan, and C. W. White	86
UV Laser-Induced Oxidation of Heavily Doped Silicon—E. P. Fogarassy, D. H. Lowndes, and C. W. White	86
Formation of Partially Coherent Antimony Precipitates in Ion-Implanted Thermally Annealed Silicon—S. J. Pennycook, J. Narayan, and O. W. Holland	87
Point Defect Supersaturation and Enhanced Diffusion in Supersaturated Silicon Alloys—S. J. Pennycook, J. Narayan, O. W. Holland	88
A Mechanism for Transient-Enhanced Diffusion in Ion-Implanted Silicon—S. J. Pennycook, J. Narayan, and O. W. Holland	89
Prediction of Transient-Enhanced Diffusion during Rapid Thermal Annealing of Ion-Implanted Silicon—S. J. Pennycook, J. Narayan, and O. W. Holland	91

3. DEFECTS IN SOLIDS

RADIATION EFFECTS

Depth Distribution of Self-Ion Damage and Comparison of Ion Damage Rates to Neutron Damage Rates for Aluminum—T. S. Noggle, B. R. Appleton, J. M. Williams, C. S. Oen, T. Iwata, and G. W. Vogl	94
The Magnetoresistivity of Copper Irradiated at 4.4 K by Spallation Neutrons—C. E. Klabunde and R. R. Coltman, Jr.	94
Organic Materials for Fusion Reactor Applications—G. F. Hurley and R. R. Coltman, Jr.	96
The National Low-Temperature Neutron Irradiation Facility: A Status Report—R. R. Coltman, Jr., C. E. Klabunde, and F. W. Young, Jr.	96

FRACTURE

Dislocation Shielding Model of Fracture Toughness—S. M. Ohr and S.-J. Chang	97
Inclined Dislocation Emission at a Shielded Crack Tip—S.-J. Chang and S. M. Ohr	98
Inclined Pileup of Screw Dislocations at the Crack Tip without a Dislocation-Free Zone—S.-J. Chang and S. M. Ohr	99
Elastic Interaction of a Wedge Crack with a Screw Dislocation—S. M. Ohr, S.-J. Chang, and R. Thomson	100
Dislocation Interactions in the Presence of Cracks—R. Thomson, I.-L. Lin, S. M. Ohr, and S.-J. Chang	101
Dislocation Arrangement in the Plastic Zone for Propagating Cracks in Nickel—S. Kobayashi and S. M. Ohr	101
Coexistence of Ductile and Brittle Fracture in Metals—S. M. Ohr, C. G. Park, S.-J. Chang, and R. Thomson	102
TEM Studies of Low-Temperature Fracture in Molybdenum—C. G. Park, T. E. Estes, and S. M. Ohr	103
Crack Tip Slip Systems in BCC Metals—C. G. Park, T. C. Estes, and S. M. Ohr	104

IMPURITIES AND DEFECTS

Atom Location by Electron Channeling Analysis—S. J. Pennycook	105
Atom Location by Axial Electron Channeling Analysis—S. J. Pennycook and J. Narayan	107
Direct Imaging of Dopant Distributions in Silicon by Scanning Transmission Electron Microscopy—S. J. Pennycook and J. Narayan	108
Ordering of Carbon Vacancies in Nonstoichiometric Transition-Metal Carbides—J. Hauck, B. C. Larson, G. R. Gruzalski, L. S. Darken, and J. F. Barhorst	109
Phase Determination of X-ray Structure Factor by Observations of Multiple Beam Effects—Qun Shen, J. Z. Tischler, and R. Colella	110
Anomalous Perturbed Magnesium Vacancy in Nickel-Doped MgO—J. L. Boldú, E. Muñoz Piconer, Y. Chen, and M. M. Abraham	111
Time Dependence of the Current Injection Phenomena in Nickel-Doped MgO Crystals at High Temperatures—K. L. Tsang, H. T. Tohver, and Y. Chen	112
Physical Parameters Associated with the Dielectric Breakdown of MgO Crystals at High Temperatures—K. L. Tsang, Y. Chen, and H. T. Tohver	113
EPR Powder Pattern Analysis for Cubic Sites of Fe^{3+} in MgO—J. L. Boldú, E. Muñoz P., Y. Chen, and M. M. Abraham	115
Degradation of Commercial Varistors by Reducing Ambients—E. Sonder	116

SEMICONDUCTOR PHYSICS AND PHOTOVOLTAGIC CONVERSION

Optical Properties of Ion-Implanted Silicon—G. E. Jellison, Jr., F. A. Modine, and C. W. White	116
Reflectivity of Silicon Implanted with PF_5 and BF_3 Complexes—G. E. Jellison, Jr., R. B. Wheeler, F. A. Modine, R. D. Westbrook, and R. F. Wood	117
Temperature-Dependent Reflectivity and Transmission Measurements of Semiconductors—G. E. Jellison, Jr., L. K. Craven, and H. Burke	117
Time-Resolved Reflectivity Measurements of Silicon during Pulsed Excimer Laser Irradiation—G. E. Jellison, Jr., D. H. Lowndes, and R. F. Wood	118

Stress Effects of Raman Line Position during Pulsed-Laser Annealing—G. E. Jellison, Jr., and R. F. Wood	119
A Time-Resolved Ellipsometer—G. E. Jellison, Jr.	120
Simulation of Antireflection Coatings for Solar Cells—G. E. Jellison, Jr.	121
Radial Concentration Gradients in HPGe Crystals—T. W. Raudorf and G. E. Jellison, Jr.	121
Application of Pulsed-Laser Processing in the Fabrication of Ge Nuclear Radiation Detectors—D. H. Lowndes and T. W. Raudorf	122
Effects of Pulsed Excimer and CO ₂ Laser Irradiation on the Wide Band Gap Semiconductors ZnO and SiC—D. H. Lowndes, F. A. Modine, E. Sonder, Y. Chen, W. J. Choyke, and J. M. Williams	123
Time-Resolved Studies of Ultrarapid Solidification of Highly Undercooled Molten Silicon Formed by Pulsed-Laser Irradiation—D. H. Lowndes, G. E. Jellison, Jr., R. F. Wood, and R. Carpenter	125
Improved Glow Discharge Implantation Equipment—R. D. Westbrook, R. T. Young, and R. F. Wood	126
Compatibility of Surface Texturization and Beam Processing of Solar Cells—R. T. Young, R. D. Westbrook, and R. F. Wood	127
Surface Texturization of Silicon Wafers—R. D. Westbrook and R. F. Wood	128

4. TRANSPORT PROPERTIES OF SOLIDS

FAST ION CONDUCTORS

Ionic Conduction and Water Diffusion in Li β -Alumina—J. C. Wang, J. B. Bates, and N. J. Dudney	130
Hydration Thermodynamics of Na β - and Na β' -Alumina—N. J. Dudney, J. B. Bates, W. E. Brundage, and J. C. Wang	131
Reaction of Polycrystalline Na β' -Alumina with CO ₂ and H ₂ O and the Formation of Hydroxyl Groups—J. B. Bates, D. Dohy, and R. L. Anderson	133
Hydrogen Diffusion in Pb β' -Alumina—J. B. Bates, N. J. Dudney, and J. C. Wang	135
Shell Model Calculations for Stoichiometric Na β -Alumina—J. C. Wang	136

INTERFACES

Impedance of Metal-Solid Electrolyte Interfaces—J. B. Bates, J. C. Wang, and R. L. Anderson	137
Model for the Frequency-Dependent Impedance of a Solid Electrolyte/Electrode Interface— J. C. Wang and J. B. Bates	138
Model for the Enhanced Conductivity of An Ionic Conductor Containing Submicron Insulator Particles—J. C. Wang, N. J. Dudney, and J. B. Bates	139
Enhanced Ionic Conductivity in Composite Materials Due to Interfacial Space Charge Layers— N. J. Dudney	140
Optical Investigations on AgCl—Y. T. Chu and J. B. Bates	141
Dispersion of Surface Polaritons in Uniaxial Al ₂ O ₃ —Y. T. Chu and J. B. Bates	142

SUPERCONDUCTIVITY

Flux-Line Pinning by the Grain Boundary in Niobium Bicrystals—H. R. Kerchner, D. K. Christen, A. Das Gupta, S. T. Sekula, B. C. Cai, and Y. T. Chou	144
Interpretation of the FLL Morphology in Superconducting V_3Si —D. K. Christen, H. R. Kerchner, and S. T. Sekula	145
Absolute Determination of the Temperature-Dependent Penetration Depth in Superconducting V_3Si —D. K. Christen, H. R. Kerchner, S. T. Sekula, and Y. K. Chang	147
Formation, Ion Modification, and Annealing of Superconductive VN Films—J. R. Thompson, D. K. Christen, S. T. Sekula, E. M. Beardsley, and D. H. Lowndes	148
Formation of Superconductive Al(GeSi) Alloys by Low-Temperature Laser-Quenching Methods—J. R. Thompson, S. T. Sekula, D. H. Lowndes, and H. R. Khan	150
Superconducting Properties of a Sputtered W Film—J. T. Ellis, J. R. Thompson, L. D. Hulet, and S. T. Sekula	150
Ferromagnetism in Ni_3Al -Based Alloys Containing Fe—S. T. Sekula, H. R. Kerchner, and J. R. Thompson	150
Magnetic Investigation of $CePO_4$ —J. T. Ellis, J. R. Thompson, S. T. Sekula, and L. A. Boatner	152
Apparatus For Galvanomagnetic Studies of Metals—J. T. Ellis, J. R. Thompson, D. K. Christen, and S. T. Sekula	152
High-Temperature Vibrating-Sample Magnetometer (HTVSM)—S. T. Sekula, H. R. Kerchner, D. K. Christen, and J. R. Thompson	153
Errors Due to Field Nonuniformity in Vibrating-Sample Magnetometry—H. R. Kerchner, S. T. Sekula, and J. R. Thompson	153

MASS AND CHARGE TRANSPORT IN MATERIALS

Approximate Formulas for the Amplitude and Phase of the Infrared Reflectance of a Conductor—F. A. Modine and D. Y. Smith	154
Optical Properties of TiC and ZrC from the Infrared to the Near Ultraviolet— F. A. Modine and C. Y. Allison	155
Electrical Properties of Titanium Carbide and Zirconium Carbide—F. A. Modine and T. W. Haywood	156
Preparation and Characterization of the (100) Surface of Tantalum Carbide—G. R. Gruzalski, D. M. Zehner, and G. W. Ownby	157
Electron Spectroscopic Studies of Tantalum Carbide—G. R. Gruzalski, D. M. Zehner, and G. W. Ownby	159
Small-Grain ZnO Varistors Produced by the Urea Process—E. Sonder, T. C. Quinby, and D. L. Kinser	160
Laser Fabrication of Electrodes on Zinc Oxide Varistors—F. A. Modine, D. H. Lowndes, J. R. Martinelli, and E. Sonder	161
Cation Transport in MgO—J. Martinelli, E. Sonder, R. A. Weeks, and R. A. Zuhr	162
Diffusion of Oxygen in MgO—J. Martinelli, E. Sonder, R. A. Weeks, and R. A. Zuhr	163

5. NEUTRON SCATTERING

SMALL-ANGLE SCATTERING

The National Center for Small-Angle Scattering Research (NCSASR)—G. J. Bunick, H. R. Child, W. C. Koehler, J. S. Lin, I. Maddox, R. Roseberry, S. Spooner, and G. D. Wignall	166
Radii of Gyration and Screening Lengths of Polystyrene Molecules Dissolved in a Good Solvent as a Function of Concentration—J. S. King, W. Boyer, R. Ullman, and G. D. Wignall	168
Molecular Dimensions in Polyethylene Terephthalate by SANS—K. P. McAlea, J. M. Schultz, K. H. Gardner, and G. D. Wignall	169
Morphology and Phase Dimensions of Interpenetrating Polymer Networks Based on Polybutadiene and Polystyrene by Small-Angle Neutron Scattering and Electron Microscopy—A. Fernandez, G. D. Wignall, and L. H. Sperling	171
Shear Alignment Studies of Anisotropy in Colloids and Gels—J. B. Hayter, J. Penfold, and B. J. Ackerson	172
Small-Angle Neutron Scattering of $(\text{Er}_{0.8}\text{Ho}_{0.2})\text{Rh}_4\text{B}_4$ —O. A. Pringle, H. A. Mook, and M. B. Maple	174
Modification of Cation-Exchange Properties of Activated Carbon by Treatment with Nitric Acid—J. S. Johnson, Jr., C. G. Westmoreland, F. H. Sweeton, K. A. Kraus, E. W. Hagaman, M. P. Eatherly, and H. R. Child	175
The Detection of Cytochalasin-D Induced Dimers of Mg^{2+} -Actin—D. Goddette, C. Frieden, E. Uberbacher, and G. J. Bunick	175
The Unfolding of Halophilic Malate Dehydrogenase from <i>Halobacterium Maris Mortui</i> —G. Zaccat, H. Eisenberg, G. J. Bunick, G. D. Wignall, and W. C. Koehler	177
Analysis of Beam Guide Effects on the NCSASR 30-m SANS Instrument—D. K. Christen, W. C. Koehler, and G. D. Wignall	178
SAX Study of Decomposition in Al-2.6 wt % Li Alloys—S. Spooner	179
Dynamic Scaling of the Decomposition Structure of Chromindur during Aging at 525°C—S. Spooner	180
Determination of Dispersoid Size Distribution in an Oxide-Strengthened Nickel-Chromium Alloy by Small-Angle X-Ray Scattering—J. J. Stephens and S. Spooner	181
Deformation of Microphase Structures in Polyurethanes—C. R. Desper, N. S. Schneider, J. P. Jasinski, and J. S. Lin	182
Dynamic SAXS Crystallization of Polymers—J. H. Magill, J. M. Schulcz, and J. S. Lin	182

LATTICE DYNAMICS

Inelastic Neutron Scattering from a Martensitically Transforming Indium-Thallium Alloy—T. R. Finlayson, Mark Mostoller, W. Reichardt, and H. G. Smith	184
The Lattice Dynamics of Layered Structure Compounds: PdTe_2 —T. R. Finlayson, W. Reichardt, and H. G. Smith	185
Intercalant Ordering and Lattice Dynamics in Potassium Mercurographitides—W. A. Kamitakahara, L. E. DeLong, P. C. Eklund, and R. M. Nicklow	187
Kohn Anomaly in Metastable FCC Lanthanum—J. Zarestky, C. Stassis, and G. S. Smith	188
Phonon Dispersion Curves of BCC Ba—J. Mizuki, C. Stassis, and J. Zarestky	188

MAGNETIC PROPERTIES

Direct Observation of Spin Waves Above T_c for Ni—H. A. Mook and J. W. Lynn	189
Magnetic Excitations in CuMn Spin-Glass Alloys—Y. Tsungja, M. Kunitomi, and J. W. Cable	190
Nuclear Spin Ordering Observed by Neutron Diffraction—S. Kawarazaki, M. Kunitomi, H. Suzuki, T. Ohtsuka, Y. Morii, R. M. Moon, and R. M. Nicklow	192
Magnetic Behavior of VBr_2 at Very Low Temperatures—J. R. Arthur, S. Kawarazaki, and K. Hirakawa	194
Observation of a Disordered Spin-Flop Phase in $Fe_{0.725}Co_{0.275}Cl_2$ —Po-zen Wong and J. W. Cable	195
Neutron Diffraction Studies of Some Gd-Y Alloys—W. C. Koehler, S. Legvold, and B. J. Beaudry	197
The Magnetic Structure of Nickel Diglycine Dihydrate—O. A. Pringle, R. Calvo, and R. E. Parra	198
On the Spin and Orbital Magnetic Densities in Ferromagnetic Nickel—G. P. Felcher, G. Maglic, J. W. Cable, and J. F. Cooke	199

STRUCTURE AND INSTRUMENTATION

High-Pressure Cells for Neutron Scattering—A. Onodera, H. G. Smith, and O. A. Pringle	200
Wide-Angle Neutron Diffractometer: A Flat-Cone Diffractometer Utilizing a Curved One- Dimensional Position-Sensitive Detector with Time-Resolved Data Acquisition System— M. Iizumi, R. M. Moon, S. Funahashi, R. M. Nicklow, S. Katano, H. R. Child, and M. P. Kopp	202
Real-Time Neutron Diffraction Measurements of the Kinetics of First-Order Phase Transitions— M. Iizumi, S. Katano, and H. R. Child	203

6. PREPARATION AND CHARACTERIZATION OF RESEARCH MATERIALS

GROWTH AND CHARACTERIZATION METHODS

Crystal Growth and Characterization Program—M. M. Abraham, L. A. Boatner, W. E. Brundage, Y. K. Chang, L. S. Darken, H. E. Harmon, J. O. Ramey, and B. C. Sales	205
Characterization of As-Grown Cu_3Au Single Crystals—Y. K. Chang, A. Fattah, W. Uelhoff, and G. Hanke.	206
Preparation of Transition-Metal Alloys, Y. K. Chang.	206
Crystal Growth of Superconducting Al_5 Compounds—Y. K. Chang and H. E. Harmon.	208
Lead-Iron Phosphate Glass: A Stable Storage Medium for High-Level Nuclear Waste—B. C. Sales and L. A. Boatner	210
Structural Properties of Lead-Iron Phosphate Glasses—B. C. Sales, M. M. Abraham, J. B. Bates, and L. A. Boatner.	212
Surface Layer Formation on Corroded Nuclear Waste Glasses—B. C. Sales, C. W. White, G. M. Begun, and L. A. Boatner.	213
EPR Observations of the Trivalent State of Hafnium and Zirconium in $LuPO_4$, YPO_4 , and $ScPO_4$ Single Crystals—M. M. Abraham, L. A. Boatner, M. Rappaz, and J. O. Ramey	215
Crystal-Field Analysis of Tm^{3+} and Yb^{3+} in YPO_4 AND $LuPO_4$ —P. Becker, T. Hayhurst, G. Shalimoff, J. G. Conway, N. Edelstein, L. A. Boatner, and M. M. Abraham.	215
Ninefold Coordination in $LaPO_4$: Pentagonal Interpenetrating Tetrahedral Polyhedron— D. F. Mullica, W. O. Milligan, D. A. Grossie, G. W. Beall, and L. A. Boatner.	216

SPECIAL MATERIALS

EPR Studies of Some f^n and d^n Electronic Impurities in KTaO_3 Single Crystals— M. M. Abraham, L. A. Boatner, D. M. Olson, and U. T. Hochli	216
Critical Quasielastic Light Scattering in $\text{KTa}_{0.968}\text{Nb}_{0.032}\text{O}_3$ —L. Lee, L. L. Chase, and L. A. Boatner	218
Thermoluminescence of Alkaline Earth Oxides X Irradiated at Low Temperatures— V. M. Orera, V. D. Rodriguez, R. Alcala, and Y. Chen.	218
Optical Properties and Infrared-Stimulated Luminescence from Oxygen Vacancies in CaO Crystals Containing Hydrogen—R. Gonzalez, G. P. Summers, Y. Chen, and K. Chakrabarti.	219
Luminescence from Oxygen Vacancies in MgO Crystals Thermochemically Reduced at High Temperatures—G. P. Summers, T. M. Wilson, B. T. Jeffries, H. T. Tohver, Y. Chen, and M. M. Abraham.	219
The Effect of Ionizing Radiation on Nickel-Doped MgO —J. L. Boldu O., E. Munoz P., K. L. Tsang, M. M. Abraham, and Y. Chen	219
PUBLICATIONS AND PAPERS	221
SEMINARS	252
AWARDS	260
SCIENTIFIC PROFESSIONAL ACTIVITIES	261
PERSONNEL CHANGES	267
ORGANIZATION CHART	270

ACRONYMS, ABBREVIATIONS, AND INITIALISMS

ABR—anti-Beevers-Ross	LG—large-grained
AES—Auger electron spectroscopy	LPE—liquid-phase-epitaxial
AR—antireflection	LRO—long-range-ordered
ARUPS—angle-resolved ultraviolet photoemission spectroscopy	LTVM—low-temperature vibrating-sample magnetometer
ASRO—atomic short-range order	MF—mean field
ATR—attenuated total reflection	MIR—multiple internal reflection
bcc—body-centered cubic	MO—mid-oxygen
BCS—Bilby-Cottrell-Swinden	MSAP—monocapped square antiprism
BE—binding energy	MSRO—magnetic short-range order
BR—Beevers-Ross	NCSASR—National Center for Small-Angle Scattering Research
BSR—Bulk Shielding Reactor	NiTG—nickel diglycine dihydrate
CD—cytochalasin D	MLTNIF—National Low-Temperature Neutron Irradiation Facility
CLS—characteristic loss spectroscopy	NKA—nuclear reaction analysis
CMA—cylindrical mirror analyzer	OC—octahedral
COO—crack opening displacement	OP—order parameters
CP—central peaks	PB/PS—polybutadiene/polystyrene
CPA—coherent-potential approximation	PET—polyethylene terephthalate
DFZ—dislocation-free zone	PITP—pentagonal interpenetrating tetrahedral/polyhedron
DLTS—deep-level transient spectroscopy	PLP—pulsed-laser processing
DOS—density of states	RBS—Rutherford backscattering
DVB—divinyl benzene	RE—rare earth
EBA—equivalent beam averaging	RG—renormalization group
EELS—electron energy loss spectroscopy	RRR—residual resistance ratio
EMA—effective medium approximation	RTA—rapid thermal annealing
ENDOR—electron nuclear double resonance	SANS—small-angle neutron scattering
EPR—electron paramagnetic resonance	SAXS—small-angle x-ray scattering
ERD—elastic recoil detection	SERS—surface-enhanced Raman scattering
EXAFS—extended x-ray absorption fine structure	SF—spin-flop
fcc—face-centered cubic	SIMS—secondary ion mass spectrometry
FED—Fusion Engineering Device	SOI—silicon-on-insulator
FG—fine-grained	SPE—solid phase epitaxial
FL—flux line	SRW—Savannah River wastes
FLL—flux-line lattice	STEM—scanning transmission electron microscopy
FWHM—full-width-at-half-maximum	TCA—traveling cluster approximation
GPC—gel permeation chromatography	TEM—transmission electron microscopy
HBD—helium beam diffraction	TFA—trifluoroacetic acid
HEIS—high-energy ion scattering	TL—thermoluminescence
HPGe—high-purity germanium	TM—transverse magnetic
HRP—high reflectivity phase	TMDC—transition-metal dichalcogenide
HTVSM—high-temperature vibrating-sample magnetometer	TP—trigonal prismatic
HW—half width	TTP—tricapped trigonal prism
HWHM—half-width-at-half-maximum	UHMWPE—ultrahigh-molecular-weight polyethylene
IBA—ion beam annealing	UPS—ultraviolet photoelectron spectroscopy
IBZ—irreducible Brillouin zone	VSM—vibrating sample magnetometer
ICRH—ion cyclotron resonance heating	WAND—wide-angle neutron diffractometer
ILL—Institut Laue-Langevin	WAXS—wide-angle x-ray scattering
IPN—interpenetrating polymer network	XPS—x-ray photoelectron spectroscopy
LCAO—linear combination of atomic orbitals	
LEED—low-energy electron diffraction	
LEIS—low-energy ion scattering	

INTRODUCTION

The reporting period covered by this progress report of the Solid State Division includes the eighteen months from April 1, 1983, through September 30, 1984. During this period relatively minor changes have occurred in the research areas of interest to the Division, and emphasis has continued along most directions that were reported in the last progress report. Nearly all research of the Division can be classified broadly as mission-oriented basic research because of its relationship to the materials problems that exist in advanced energy technologies.

Continued emphasis has been placed on the development and expansions of users' programs, whereby scientists outside ORNL can utilize unique equipment located at the Laboratory. There have always been informal arrangements for collaborative research, but these formalized programs have been established to ensure that our facilities are used for the best possible research. The Solid State Division now has responsibility for (1) the National Center for Small-Angle Scattering Research (NCSASR), (2) the Neutron Scattering Users' Program at HFIR, (3) the Surface Modification and Characterization (SMAC) Collaborative Research Center, and (4) the National Low-Temperature Neutron Irradiation Facility (NLTNIF). The NCSASR, which was established in 1978 through a joint interagency agreement between the Department of Energy and the National Science Foundation, operates exclusively in the users' mode to provide state-of-the-art instrumentation for small-angle neutron and x-ray scattering investigations. During the extended HFIR shutdown at the end of 1983 to replace the beryllium reflector, extensive modifications were made on the SANS facility, which have increased the neutron intensity by an order of magnitude for many experiments. The other neutron scattering facilities at the HFIR and the accelerators and lasers of the SMAC facility are available to users at times that do not interfere with the programmatic requirements of DOE. An extensive expansion is under way at the SMAC facility, and when this expansion is completed in about two years, at least twice as many users can be accommodated. The NLTNIF is under construction at the Bulk Shielding Reactor and should be available for users toward the end of 1985; it will be the main facility within the United States for basic research to study the effects of neutron irradiation on solids.

In addition to the formalized users' programs, there are other established programs for cooperative research that involve members of the Solid State Division. Special arrangements for collaborations in neutron scattering have been made with Ames Laboratory and with the government of Japan. The Ames Laboratory neutron scattering program was moved to

ORNL several years ago when the Ames Laboratory Research Reactor was shut down; Ames Laboratory equipment that has been installed at the ORR and ORNL equipment at the ORR and HFIR are available to scientists of both organizations. The cooperative program with Japanese scientists was negotiated by DOE under the umbrella of the U.S.-Japan Science and Technology Agreement. It involves the acquisition of new neutron scattering equipment at the HFIR with funds provided by the Japanese government and modest use of the HFIR neutron scattering facilities by Japanese scientists. During the past reporting period, a dilution refrigerator, which provides sample temperatures to about 10 mK in a vertical magnetic field up to 5 T, and a unique wide-angle neutron diffractometer (WAND) for time-slicing experiments have been made available through Japanese funds. Members of the Solid State Division are also involved in two participating research teams (PRT) at the National Synchrotron Light Source at Brookhaven National Laboratory. One PRT with the University of Pennsylvania will operate a facility on the VUV ring to investigate the properties of surfaces. The other PRT, which consists of scientists from ORNL and several universities, will operate a very flexible diffractometer on the x-ray ring.

The various collaborations and users' activities involve a large number of Solid State Division scientific and technical staff members. Some idea of the extent of these interactions can be gained from the large number of publications (listed in the back of this progress report) that are coauthored with members of other organizations. Such collaborations are a very important part of the Solid State Division activities, and they provide stimulating interactions with many scientists outside ORNL.

Several programs of the Division received special external recognition during this reporting period. The 1983 Division of Materials Sciences Solid State Physics Award for Significant Implication for Energy Technology was given to R. T. Young, R. D. Westbrook, R. F. Wood, and G. A. van der Leeden for their research on "High Efficiency Solar Cells by Beam Processing." B. C. Sales and L. A. Boatner won the same award in 1984 for their work on "Lead-Iron Phosphate Glass: A New Stable Storage Medium for High-Level Nuclear Waste." Members of the Solid State Division have now won five of these special DOE Materials Sciences Awards during the past four years. This is particularly gratifying because judges for the awards are program managers at other DOE laboratories, and these laboratories obviously have programs that compete for the same awards. Also during this reporting period, Division members won two IR-100 awards. R. Appleton, O. W. Holland, and J. Narayan won an IR-100 Award in 1983 for the "Development of Supersaturated Semiconductor Alloys," and H. A. Mook with G. K. Schulze of the Instrumentation and Controls Division won an IR-100 Award in 1984 for "Development of an Ultrasonically Pulsed Neutron Spectrometer." These awards, of course, indicate the close relationship of certain research programs to technological applications.

The arrangement of this progress report has been chosen to emphasize the major areas of solid state science in which the Solid State Division conducted research during the reporting period. These areas are Theoretical Solid State Physics, Surface and Near-Surface Properties of Solids, Defects in Solids, Transport Properties of Solids, Neutron Scattering, and Preparation and Characterization of Research Materials. There is a chapter of the report for each of these major research areas, and the chapters are divided into sections to emphasize specific topics. A short introduction to each of the chapters indicates the scope and goals of the research and gives a few highlights of recent investigations. It is also the intent of these introductions to show how the individual programs are inter-related and to indicate how research activities of the Solid State Division contribute to various programs of ORNL and DOE.

Because of the close interactions that exist among scientists of the Division, a number of research summaries do not fit uniquely into only one section of the progress report. The neutron scattering research on superconducting flux-line lattices is a good illustration of such a situation. Summaries for this research have been placed in the section on superconductivity, but they would have fit equally well in the section on small-angle neutron scattering. Of course, many experimental programs are closely coupled with theoretical research and with materials preparation and characterization; this overlap also results in research summaries that could be placed in more than one section. In most cases research summaries with overlapping interests have been placed into one of the appropriate sections on a somewhat arbitrary basis. It is hoped that readers of the report will not have any difficulty in finding those summaries of interest.

1. THEORETICAL SOLID STATE PHYSICS

The theoretical research effort within the Solid State Division contributes to the overall program in two important ways. It provides significant backup and support for existing experimental programs, and it initiates new directions for future work. The work presented in this chapter not only reflects the theoretical research accomplishments in the period covered by this progress report but also is particularly representative of these two aspects of our program. The research itself involves, of course, the extension of existing theories or the development of new ones. Because of the complexity of modern theories of condensed matter, numerical techniques, often requiring elaborate computer programs, must also be developed so that accurate results can be generated for realistic systems. Since our research program covers such a broad spectrum of problems, this chapter has been divided into four sections: Surfaces; Electronic, Vibrational, and Magnetic Properties; Particle-Solid Interactions; and Laser-Solid Interactions and Rapid Solidification.

Research on surfaces has expanded into a number of new and potentially significant areas. In addition to being able to analyze LEED data in terms of an expansion or contraction of layers perpendicular to the surface, the theory and numerical techniques have been generalized to include displacements parallel to the surface as well as the more exotic case of rippled relaxation. By using these new techniques, it has been clearly demonstrated that both parallel and perpendicular relaxations occur when oxygen is adsorbed on the W(112) surface and that a large atomic rippling exists in the NiAl(110) surface. These discoveries will definitely stimulate future work on both monatomic and ordered alloy surfaces. An analysis of the angular dependence of the surface yield obtained from ion scattering experiments has revealed that such angular scans can also provide important information about surface relaxation, but with a sensitivity which varies with the magnitude of the relaxation. In addition to the work on surface crystallography, an explanation for the oscillation with time of the oxidation of CO over Pt, Pd, and Ir catalysts has been proposed. This explanation is based on the concept that the oxidation of the surface layer must be coupled to the catalyzed production of CO₂ on the metal surface.

The study of the electronic, vibrational, and magnetic properties has continued on some long-standing problems, but new areas are also emerging. An investigation of a fundamental connection between the properties of fractal and disordered systems has been initiated. The fractal nature of the vibrational spectrum of an elastic fractal system has been shown

to provide a basis for an explanation of the anomalous temperature dependence of the spin-lattice relaxation rate of protein molecules. Work on interface problems is under way. Recent calculations based on itinerant electron theory have led to a new interpretation of spin-wave behavior in transition metal magnets, one in which spin waves exist throughout most of the Brillouin zone. The calculations of total form factors for bcc and fcc transition metal systems have been completed and, except for a few cases, yield results which are in reasonable agreement with experiment. Feasibility studies of experiments proposed for spallation neutron sources have continued. Results to date indicate that some information about electronic excitations in solids can, in principle, be obtained, but the experiments are going to be difficult to carry out. Some fundamentally important results concerning the critical behavior associated with the Bose-Einstein condensation in a dilute, weakly interacting Bose fluid have been derived. Results obtained thus far are in excellent agreement with experiments for ^4He films adsorbed on Vycor glass and have provided motivation for future experiments on spin-polarized hydrogen. Lattice vibrations in disordered binary alkali metal alloys and in insulators having the rutile structure have been studied using a variety of theoretical approaches. An examination of the interrelationship of phonon spectra, cohesive energy, and lattice constants has revealed rather serious problems with previous approaches for rutile systems.

Research on particle-solid interactions is based on the study of atomic collisions in solids. This includes the broad areas of ion damage in metals and channeling. Sputtering yields calculated for polycrystalline α -uranium were found to differ by a factor of 2, depending on the assumptions made about the energy lost by fast atomic recoils in exciting electrons. A partial explanation for this unexpected difference lies in unphysically large inelastic losses in the surface region generated by assuming these losses to depend only on the mean electron density. A different study involving the reflection of light ions from layered structures has important implications for many problems, including the study of the recycling of hydrogen isotopes between the plasma and confinement vessel in a fusion reactor. Calculations of the reflection coefficient and fraction of energy reflected for low incident energy hydrogen atoms on layered targets have provided some insight into the relative importance of various layers in the backscattering process. A new program has been initiated to provide support for the division's ion implantation effort. Some illustrative damage production calculations in crystalline silicon by various incident ions has revealed a number of interesting results, including the fact that the channeling of incident ions greatly reduced the overall damage. Ion channeling in elastically strained superlattices has continued with new emphasis placed on the role played by the mismatch of lattice constants on dechanneling phenomena.

The laser annealing theory program, which in the past was closely associated with the photovoltaic effort, has quite naturally evolved into

a much broader study of laser-solid interactions, rapid solidification, and associated nonequilibrium phenomena. As an initial step in this process, an elementary model for nonequilibrium crystal growth based on a multilayer treatment of the liquid-solid interface has been investigated. Results from calculations based on this model are consistent with the experimentally observed rapid increase in the interfacial segregation coefficient with increasing interface velocity for groups III and IV dopants in silicon. Models have also been developed to describe the solidification processes in highly undercooled silicon and germanium. Numerical results obtained from these models predict a remarkable variety of solidification behavior, such as the existence of molten material and "slush" layers in the interior of the sample after the surface has already solidified. A number of studies have been carried out to determine the behavior and response of electrons in semiconductors to laser pulses. In one such study, an explanation is proposed for the experimentally observed loss of the electron-hole plasma signature in silicon 15 ps after a laser pulse. It is based on the appearance of a new recombination channel which opens up when electron-hole recombination can be assisted by a plasmon and a phonon. Even though significant progress has been made in the study of laser-solid interactions and rapid solidification, further development and refinement of the theory are continuing in order to achieve a better understanding of these complicated nonequilibrium phenomena at a fundamental level.

SURFACES

RIPPLED RELAXATION IN THE (110) SURFACE OF THE ORDERED METALLIC ALLOY NiAl¹

H. L. Davis J. R. Noonan

LEED techniques, developed previously for determining the atomic positions in monatomic surfaces with a precision of better than 0.02 Å,²⁻⁵ have been extended recently to investigate alloy surfaces. An interesting example of the type of results which might be expected from such a study has been provided by a just-completed LEED analysis for the (110) surface of the ordered metallic alloy NiAl. Since NiAl has the CsCl structure, its hypothetical truncated bulk surface would consist of composite layers, parallel to the surface, with each layer containing half Ni and half Al sites which are exactly coplanar (Fig. 1.1). Now the intriguing result, which is briefly documented below, is that the actual NiAl(110) surface has a relatively large rippling where the Al sites of the top composite layer are displaced above the Ni sites by approximately 0.22 Å (Fig. 1.2). To our knowledge, the present result provides the first demonstration that such different, and relatively large, relaxations exist in the surface of an ordered alloy.

The procedures used to prepare the NiAl(110) surface prior to data collection were quite

detailed and will not be described here; however, a very good clean surface with large and well-ordered domains was obtained. The surface produced a sharp (1×1) LEED spot diffraction pattern, and a semiquantitative Auger analysis indicated that it nominally contained half Ni and half Al sites. A total of 14 intensity vs voltage (I-V) profiles were collected for all the individual members in the symmetrically equivalent {01}, {10}, {11}, {12}, and {20} sets. Equivalent beam averaging (EBA)⁶ then was applied to obtain the five EBA experimental profiles plotted in Fig. 1.3.

Detailed crystallographic information was extracted from the EBA experimental profiles by comparing them with calculated I-V profiles, which were obtained by performing numerous sets of dynamical LEED calculations. The comparison was made first with profiles calculated for the truncated bulk structure of NiAl(110) and resulted in a value of 0.131 for the total five-profile Zanazzi-Jona⁷ R factor. The single-profile R factors for this comparison are displayed by the respective calculated profiles in Fig. 1.3. A series of calculations were then performed, where the Ni and Al sites were constrained to be coplanar, but d_{12} , the spacing between the first and second composite Ni-Al layers, had relative changes of -15% to +10% of the bulk value. The overall minimum of the total R factor that resulted in this series was 0.129 for $\Delta d_{12} = -2.2\%$. Thus, variation of d_{12} produced only a very slight

Fig. 1.1. Truncated bulk surface 'or NiAl(110).

Fig. 1.2. Atomic rippling of the first composite layer of NiAl(110).

reduction in the total R factor. Also, no consistency was found in changes of the single-profile R's; in fact, three of the five increased (Fig. 1.3).

Since a total R factor of 0.13 could be considered a respectable value⁷ for the final result

Fig. 1.3. I-V profiles for NiAl(110). The profiles denoted TB were calculated for the truncated bulk; CP profiles were calculated for the best model, where the Ni and Al sites of the first composite layer were constrained to be coplanar; R profiles were calculated for the best model, where the Ni and Al sites were allowed to ripple; and E profiles are the EBA experimental profiles. The numbers associated with the calculated profiles are single-profile R factors.

of a LEED analysis, it could be concluded incorrectly from the above results that the structure of NiAl(110) closely resembles the truncated bulk with, at most, a slight contraction in d_{12} . However, there is no a priori reason why the Ni and Al sites should be coplanar in the outermost composite layers. Therefore, a series of LEED calculations were performed, where the positions of the Ni and Al sites in the first composite layer independently were varied perpendicularly to the surface. In these calculations $\Delta d_{12}(\text{Ni})$, the change in perpendicular position of Ni sites relative to the spacing between bulk composite layers (2.04 Å), was varied from -14% to +2%, and $\Delta d_{12}(\text{Al})$ was varied from -2% to +14%. The overall minimum for the total R factor for this series was 0.053, which occurred for $\Delta d_{12}(\text{Ni}) = -6.0\%$ and $\Delta d_{12}(\text{Al}) = +4.6\%$. These Δd_{12} 's correspond to a rippled first composite layer, where the plane of the Al sites is separated from the plane of the Ni sites by 0.22 Å (Fig. 1.2). Since the total R factor has been reduced by a factor of 2.4 from the best value obtained for models where the Ni

and A1 sites were constrained to be coplanar, the evidence for the existence of such a large rippling must be considered as quite strong. Also, all five of the analyzed I-V profiles have had their single-profile R's greatly reduced by consideration of rippling (Fig. 1.3). This consistency, profile to profile, is further evidence that a large rippled relaxation is a valid characterization of the NiAl(110) surface and not just an artifact of the LEED analysis.

All the single-profile R's associated with the I-V profiles calculated for the rippled surface (Fig. 1.3) are consistently small. In fact, their values would be considered⁷ quite small even for the LEED analysis of a monatomic metallic surface, which should serve to add further credibility to the results of the present analysis. However, it is surprising that such small R values were obtained. After all, there are features which could exist in surfaces of ordered alloys (e.g., surface segregation and disordering of atomic components) which could degrade the agreement achievable between calculated and experimental I-V profiles from that attainable for surfaces of monatomic metals. Our present opinion is, however, that the small R values obtained for NiAl(110) indicate a high degree of perfection of the sample in its surface region and that the actual surface is truly rippled.

It is anticipated that our demonstration of a large atomic rippling in NiAl(110) will lead to future work, both experimental and theoretical, on this and other surfaces. It is desirable that the present theories⁸⁻¹⁰ of surface relaxation in monatomic surfaces be extended to ordered alloys, with such extensions furnishing plausibility arguments for the large atomic rippling found in NiAl(110). In this regard, the Finis and Heine¹¹ idea of smoothing a surface's electronic density is easily extended to provide a plausibility argument for qualitative rippling in alloy surfaces whose atomic species have different core charges. Finally, since the first of the future theories for alloy surfaces probably will be quantitatively applicable to only s-p bonded alloys, obtaining structural information for such surfaces is of prime importance.

1. Summary of paper to be published.
2. J. R. Noonan, H. L. Davis, and W. Erley, *Surf. Sci.* (in press).
3. J. R. Noonan and H. L. Davis, *Phys. Rev. B* 29, 4349 (1984).
4. H. L. Davis and J. R. Noonan, *Surf. Sci.* 126, 245 (1983).
5. H. L. Davis and J. R. Noonan, *J. Vac. Sci. Technol.* 20, 842 (1982).
6. H. L. Davis and J. R. Noonan, *Physica Scripta* T4, 141 (1983).
7. E. Zanazzi and F. Jona, *Surf. Sci.* 62, 61 (1977).
8. U. Landman, R. N. Hill, and M. Mostoller, *Phys. Rev. B* 21, 448 (1980).
9. R. N. Barnett, U. Landman, and C. L. Cleveland, *Phys. Rev. B* 28, 1685 (1983).
10. R. N. Barnett, U. Landman, and C. L. Cleveland, *Phys. Rev. Lett.* 51, 1359 (1983).
11. M. W. Finnis and V. Heine, *J. Phys. F* 4, L37 (1974).

LAYER RELAXATION OF THE CLEAN W(112) SURFACE AND ITS VARIATION WITH ADSORBED OXYGEN

H. L. Davis G.-C. Wang¹

LEED, I-V profile, analyses have been performed for the clean W(112) surface, the W(112)p(2x1)O (0.5 monolayers of oxygen) system, and the W(112)p(1x2)O (1.5 monolayers of oxygen) system. Our interest in these crystallographic studies of the high-index, low-symmetry W(112) surface was motivated by insights which were acquired from some previous LEED analyses for clean (110) surfaces of fcc metals (e.g., see Refs. 2-4). To understand these insights, consider Figs. 1.4 and 1.5, which illustrate, respectively, the hypothetical truncated bulk fcc(110) and bcc(112) surfaces (bulk tungsten has the bcc structure). Although these truncated surfaces are similar and both have an open character, note the lower symmetry of bcc(112) because the atoms in its second layer are not centered in the rectangles formed by the atoms of the first layer. Since all actual surfaces differ, more or less, from the atomic structures of their corresponding truncated bulk surfaces, by comparing Figs. 1.4 and 1.5 prior to our LEED analysis for W(112), it was inferred that the crystallography of the actual W(112) surface probably would differ in two major aspects from that illustrated by Fig. 1.5. First, due to its open character and since a contraction has been found for every fcc(110) surface that has been analyzed by LEED, the first interlayer spacing d_{12} for the W(112) surface would be expected to be contracted from the value for the truncated bulk. That is, the entire first atomic layer would be expected to have a rigid relaxation in a direction perpendicular to the surface. Also, because of the low symmetry of the truncated bulk bcc(112) surface, a change in layer registry could

Fig. 1.4. Hypothetical truncated bulk fcc(110) surface.

Fig. 1.5. Hypothetical truncated bulk bcc(112) surface.

be expected for the W(112) surface, i.e., a relaxation of the entire first atomic layer parallel to the surface in a direction such that the atoms of the second layer would be nearer the centers of the rectangles of the first layer (Fig. 1.5). Thus, we were motivated to perform a LEED analysis for W(112) in order to determine whether such perpendicular and parallel relaxations actually existed in this surface. Of special interest was the possible parallel relaxation, since at the initiation of the analysis we were unaware of any demonstration of the existence of this type of layer relaxation.

The detailed experimental and theoretical procedures necessary for the LEED analysis of the clean W(112) surface have been performed, and the results definitely demonstrate that both perpendicular and parallel relaxations exist in this surface. The first interlayer spacing d_{12} is contracted by 0.16 Å, which is 12% of the bulk value. Also, there is a first-to-second layer registry shift of 0.09 Å, which is 20% of the shift required to place the atoms of the second layer in the centers of the rectangles of the first layer. During and subsequent to our analysis for W(112), two related papers appeared in the literature. Sokolov et al.⁵ have performed a LEED analysis for Fe(112), and their results demonstrate the existence of perpendicular and parallel relaxations for this surface. Also, Barnett et al.,⁶ extending earlier theoretical work for high-symmetry surfaces, have performed model-type calculations for low-symmetry surfaces, which provide qualitative theoretical justification for the existence of parallel layer relaxation in such surfaces.

The available theoretical research on perpendicular and parallel relaxations indicates that they are directly related to differences between the surface-region and bulk electronic structures.

Thus, if the surface-region electronic structure were changed, the amounts of the layer relaxations would be expected to change. One possible way to change a surface's electronic structure is by atomic adsorption. Therefore, to investigate whether a change in its layer relaxation actually could be shown to coincide with a change in W(112)'s electronic structure, we decided to conduct LEED analyses for the W(112)p(2x1)O (0.5 monolayers of oxygen) and W(112)p(1x2)O (1.5 monolayers of oxygen) systems. To date, the necessary I-V profile data have been collected for both systems; however, only partial theoretical analyses of these data have been completed. That is, the theoretical analyses have been done only for the integral order I-V profiles by assuming that oxygen ($Z=8$) has only a minor influence on the electron scattering as compared with that from tungsten ($Z=74$). However, this assumption is adequate for the present purpose, since it does enable the position of the tungsten layers to be determined with significant precision to investigate changes in layer relaxation.

For the W(112)p(2x1)O system the results of our partial LEED analysis indicate that d_{12} is contracted 0.09 Å with respect to the truncated bulk surface, which means this spacing is expanded by 0.07 Å from that for the clean W(112) surface. Also, for the same system, there is a first-to-second layer registry shift of 0.06 Å with respect to the truncated bulk. This figure represents a shift, toward lower symmetry, of 0.03 Å when compared with clean W(112). However, for the W(112)p(1x2)O system, d_{12} is contracted by 0.04 Å with respect to truncated bulk, but this is a 0.12 Å expansion from the value for clean W(112). For this system with 1.5 monolayers of oxygen, there is a first-to-second layer registry shift of 0.16 Å with respect to truncated bulk. This represents a shift of 0.07 Å, toward higher symmetry, with respect to clean W(112). Thus, the results of our analysis do demonstrate changes in layer relaxation as W(112)'s electronic structure is changed. It is expected that these results will stimulate further experimental and theoretical work on layer relaxation; for example, it would be of interest to study W(112) under the influence of an adsorbed electropositive element (e.g., lithium) and to compare the results with those obtained in the present work for electronegative oxygen.

1. Present address: Rensselaer Polytechnic Institute, Troy, N.Y.

2. H. L. Davis, J. R. Noonan, and L. H. Jenkins, *Surf. Sci.* **83**, 559 (1979).

3. H. L. Davis and J. R. Noonan, *Surf. Sci.* **126**, 245 (1983).

4. J. R. Noonan and H. L. Davis, *Phys. Rev. B* **29**, 4349 (1984).

5. J. Sokolov et al., *J. Phys. C* **17**, 371 (1984).

6. R. N. Barnett, U. Landman, and C. L. Cleveland, *Phys. Rev. Lett.* **51**, 1359 (1983).

ANGULAR SYMMETRY OF THE ION SCATTERING SURFACE YIELD FOR LARGE OUTER LAYER RELAXATIONS¹

R. J. Culbertson J. H. Barrett
S. P. Withrow

Using high-energy ion scattering measurements of the surface yield is one of several techniques to study surface structure. The surface yield is the area under the yield peak at the surface in an axially channelled spectrum, and it is usually expressed as an effective number of atoms per row. Asymmetry observed in the angular dependence of the surface yield for an ion beam incident near an off-normal low index crystal direction is indicative of a relaxation of the surface layer. The present work shows that this is true for relaxations (expansions or contractions) of up to 0.1-0.2 Å for the [101] axis of Au (110) but that for larger relaxations the situation is less straightforward.

The present work was stimulated by an ion scattering study of the structure of the Au(110)-(1×2) surface.² One result from that study is shown as curve (a) in Fig. 1.6. Zero angle in the figure represents incidence along the [101] direction; negative (positive) angles are for incidence closer to (further from) the surface normal than the [101] axis. One other experimental fact to be mentioned is that recent studies of this surface generally agree that there are alternating missing rows in the first layer of atoms, although they disagree on other particulars.

Curve (a) in Fig. 1.6 has its minimum near +0.5°. For the present angular convention, a minimum at a positive angle would be expected for small contractions in the top layer spacing. This is illustrated in Fig. 1.6 by curve (b). For simplicity, except for the top layer contraction,

a bulk-like model was assumed with no surface enhancement or correlations in the atomic vibrations. While the shape of curve (b) approaches that of the experimental data, the yield is about 0.7 of an atom per row lower. Curve (c) in Fig. 1.6 shows the results from a simulation with a large expansion in the top layer. The asymmetry is, perhaps surprisingly, close to that of curve (b), and now the yield is about 0.2 atoms per row below the experimental values. A shape such as curve (b) in Fig. 1.6 for a small surface relaxation is well known in ion scattering, and its interpretation has been the principal basis for using ion scattering to measure surface relaxations. However, the shape for a large relaxation such as (c) in Fig. 1.6 has not been studied previously and is a new feature in the present work.

In addition to the results shown in Fig. 1.6, calculations were made for other relaxations between -1.0 and +1.0 Å at 0.1-Å intervals in order to have a systematic survey of the effects of relaxations on the surface yield. Results were obtained for both a non-missing row model, in which all atoms in the surface layer were present and behaved in the same way, and a missing row model. For each model the angle at which the minimum surface yield occurs has a systematic trend with relaxation, as shown in Fig. 1.7. For each model there is a reversal of the direction of the angle of the minimum for large expansions of either sign when compared with small expansions of the same sign.

Two effects of surface relaxations on high-energy ion scattering are known from previous work. One is that small relaxations affect the symmetry of angular scans, allowing determination of their magnitude and sense. The other is that large relaxations increase the surface yield by one atom per row for each row beginning in the surface layer. The present work reveals a new effect in that large relaxations also affect the symmetry of an angular scan. As a result, the angular scan can be used in this case also to distinguish between expansions and contractions

Fig. 1.6. Surface yield for 300-keV He⁺ as a function of angle with the [101] axis of Au(110): (a) experimental data, (b) simulation for 0.1-Å contraction of first layer spacing, (c) simulation for 0.6-Å expansion of first layer spacing. Both simulations are for a missing row model.

Fig. 1.7. Dependence of the angle at which the minimum surface yield occurs on the expansion of the surface layer.

although there is varying sensitivity to the magnitude of the relaxation.

1. Summary of paper to be published.
2. S. P. Withrow, J. H. Barrett, and R. J. Culbertson, "Ion Scattering Study of Reconstruction in the Gold (110)-(1x2) Surface," this report.

APPROXIMATION FOR THE SURFACE BACKSCATTERING YIELD FROM AN ATOMIC ROW WITH CORRELATED THERMAL VIBRATIONS¹

D. P. Jackson² J. H. Barrett

The widespread use of Rutherford backscattering for investigating the structure of solid surfaces has prompted the development of methods for calculating the yields of ions backscattered from atomic rows. Although computer simulations are always used for making quantitative inferences from experiments, simple formulas are useful for purposes of estimation. Previously available formulas³ have included the effects of many factors but have not included the effect of correlations of the thermal vibrations. However, several ways have been suggested⁴ in which a reduction factor for the thermal vibration amplitude would be calculated to seek a result equivalent to the effect of correlations. We have looked at these suggested reduction factors and how they might be incorporated into a previously available formula. One of the reduction factors gives much better results than the others and can be incorporated in a satisfactory way into the previous formula. If the correlation coefficients are anisotropic, an average of the components transverse to the row should be used.

1. Summary of paper: *Nucl. Instrum. Methods in Phys. Res.* **B2**, 318 (1984).
2. Atomic Energy of Canada, Ltd., Chalk River, Ontario, Canada.
3. D. P. Jackson et al., *Nucl. Instrum. Methods* **194**, 143 (1982).
4. J. H. Barrett and D. P. Jackson, *Nucl. Instrum. Methods* **170**, 115 (1980).

SPIN WAVES AT SURFACES AND INTERFACES IN CUBIC HEISENBERG SYSTEMS¹

Bu Xing Xu² Mark Mostoller
A. K. Rajagopal³

For systems described by tight-binding-like Hamiltonians of finite range, the elementary excitations at surfaces and interfaces can be found by Green's function treatments that correspond to mappings onto linear chains.^{4,5} This is a logical consequence of the two-dimensional periodicity retained in three-dimensional crystals when a cleavage or internal boundary plane is introduced and may be applied to the following: electrons described by an orthogonal tight-binding Hamiltonian, phonons represented by a Born-von Kármán model, or magnons in the Heisenberg model.

The simple cubic (sc) lattice, with a single band and first neighbor interactions only (sometimes referred to as cubium), has been studied in a number of papers for a variety of purposes. Because it is the simplest possible example, it is usually sc(001) that is considered. There has also been some work on single electronic or spin-wave bands at other cubic crystal surfaces, but there have been few studies of the effects of crystal geometry and surface normal on surface and interface states in these simple systems. It is well known that the bulk densities of states for single bands in sc, fcc, and bcc crystals are quite different, and this might be expected to have some effect on the behavior at surfaces and interfaces. In this work, we present illustrative results for spin waves at those surfaces and interfaces in cubic Heisenberg ferromagnets that can be described by the very simplest linear chain mappings.

The seven systems treated are sc(001), (110), and (111); fcc(001) and (111); and bcc(001) and (110). The interfaces we consider consist of two semi-infinite lattices cut in the same way and in crystallographic registry with each other, which are brought together. Only first neighbor exchange is included. Interactions different from bulk values are allowed within the first plane and between the first and second planes on either side of the interface, as well as between the first planes on opposite sides. For surface calculations, the exchange interactions between the two half crystals are turned off.

The Green's functions in the surface and interface regions can be found by solving a set of scalar recursion equations as outlined by Mostoller and Kaplan.⁶ The results are expressed in terms of the exchange interactions in these regions and what we call the terminated bulk Green's functions; these are the Green's functions for the first layers of two half crystals in which all elements of the Hamiltonian retain their bulk values. The terminated bulk corresponds to perhaps the simplest model possible for electronic states at surfaces, but it does not constitute an acceptable model for spin waves (or phonons) at cleaved surfaces, because the Goldstone rule is not obeyed.

Consider the case of spin waves in a cleaved crystal with no changes in the nearest neighbor exchange interactions in the surface region. Let L denote the layer and i the site within a layer and assume that the interactions couple spins in plane L only with those in planes L and $L \pm 1$; this is true for the seven systems treated here. In the bulk, the Goldstone rule requires that the site-diagonal elements of the Hamiltonian be $H(L,i;L,i) = ZJ$, where Z is the number of neighbors and J is the exchange. In the terminated bulk crystal, the site-diagonal elements of the Hamiltonian retain this bulk value ZJ in every plane, including plane 1. In the cleaved crystal, a spin in plane 1 has fewer neighbors than in the bulk, $Z_1 < Z$, and the Goldstone rule for plane 1 requires that $H(1,i;1,i) = Z_1J < ZJ$.

Cleavage and the Goldstone rule by themselves have several interesting effects. First, they produce no true surface states for spin waves at the sc(001) surface, but do give rise to surface spin wave states at the other six surfaces studied. The surface states are weakest for sc and bcc(001),

stronger for sc and fcc(111), and strongest for fcc and bcc(110).

Figures 1.8 and 1.9 show bulk, terminated bulk, and cleaved surface layer densities of states for the fcc and bcc(001) surfaces, assuming that $J = 1$. The effects of the Goldstone rule appear as dramatic differences between the cleaved crystal and the terminated bulk results. The impact of the underlying crystal structure on excitations at surfaces is illustrated by the quite different results obtained for fcc and bcc(001). For a given crystal structure, variation from one surface to another can produce differences just as striking.

Fig. 1.8. Bulk, terminated bulk, and cleaved crystal densities of states for magnons at the fcc(001) surface, for $J = 1$. The dashed line in the bottom panel gives the band state contributions for plane 1.

Interfaces tend to represent weaker perturbations than surfaces, because interactions are altered rather than severed. However, interface states occurred in nearly every case we studied, split off above the band states for stronger interactions at the interface or below for weaker interactions. As for surfaces, there are pronounced

Fig. 1.9. Bulk, terminated bulk, and cleaved crystal densities of states for magnons at the bcc(001) surface, for $J = 1$.

differences in the results due to the underlying crystal structure and the interface normal.

1. Summary of paper to be published.
2. Louisiana State University, Baton Rouge, La.
3. Consultant from Louisiana State University, Baton Rouge, La.
4. M. Mostoller and T. Kaplan, *Phys. Rev. B* 19, 552 (1978).
5. M. Mostoller and A. K. Rajagopal, *Phys. Rev. B* 25, 6168 (1982).

OSCILLATORY OXIDATION OF CO OVER Pt, Pd, AND Ir CATALYSTS: THEORY¹

B. C. Sales J. E. Turner²
M. B. Maple²

Over the past several years, oscillations in the rate of CO_2 production have been reported over Pt, Pd, and Ir catalysts. The characteristics of the oscillations observed over these

metals are sufficiently similar to suggest a common origin for the oscillatory behavior.

A variety of explanations have been proposed in the literature to explain oscillatory rates of CO_2 production over Pt catalysts. These include (1) adsorption activation energies which are strong functions of surface coverage, (2) slow adsorption and desorption of an inert species, (3) clustering of CO molecules on the surface, (4) surface temperature as a driving mechanism, and (5) the alternate oxidation and reduction by CO of a Pt surface layer.

The oscillations reported by us and others had periods as long as an hour. In this interval, many thousands of monolayers of CO and O react on the catalyst surface. A simple comparison of time scales shows that reaction kinetics alone cannot be responsible for the oscillations. It seems more probable that the driving mechanism for the oscillations is associated with a slow and reversible modification of the catalyst surface. Furthermore, this surface modification must be general enough to account for the oscillations observed over Pt, Pd, and Ir surfaces.

In our opinion, the most reasonable driving mechanism is the alternate oxidation and CO reduction of the metal surface. All three metals have oxides which are thermodynamically stable for temperatures (373–673 K) and pressures (atmospheric) over which oscillations have been observed. In addition, all these oxides can be reduced, at least partially, by exposure to CO. While the chemisorption of oxygen to the metal surface is an essential step in the catalysis of CO oxidation, it is also the first step in metallic oxidation. Conversely, the chemisorption of CO is the first step in CO reduction of the metal oxide. The presence of these chemisorbed species during the reaction strongly suggests that the oxidation and reduction processes may be occurring on the catalyst surface.

These general arguments have been supported by direct measurements of the oxidation and CO reduction kinetics of Pt. In this oxidation study, the total uptake of oxygen by the metal was less than one oxygen atom per Pt surface atom. Hence, in the present context oxidation refers to the initial incorporation of oxygen into the metal which must occur before a stoichiometric oxide can form. This dissolved oxygen is referred to as subsurface oxygen. For a temperature of 550 K and pressures near atmospheric, this study indicated that the duration of the oxidation and reduction processes was the order of minutes. At 550 K, typical periods observed in the oscillatory oxidation of CO over a Pt catalyst were also the order of minutes.

The fact that a metal can be oxidized and reduced does not alone lead to oscillatory behavior. The oxidation or reduction of the surface layer must be coupled to the catalyzed production of CO_2 on the metal surface. One can construct a simple physical model which describes the oscillatory rates of CO_2 production over a Pt, Pd, or Ir surface by utilizing such a coupling scheme. Although only a Langmuir-Hinshelwood reaction mechanism is used in the model, the steady state solution of the kinetic equations yields two stable reaction branches for a given set of experimental conditions. The slow oxidation and reduc-

tion of the metal surface induces transitions between these two reaction branches. Using realistic values for the kinetic rate constants, the model quantitatively reproduces (Fig. 1.10) almost all of the oscillatory characteristics observed experimentally.

1. Summary of paper: *Surf. Sci.* **111**, 381 (1982).
2. University of California at San Diego, La Jolla, Calif.

Fig. 1.10. (a) Experimentally obtained oscillations in the rate of CO_2 production over Pt for various temperatures between 522 and 550 K, with $P_{\text{CO}}/P_{\text{O}_2} = 0.01$. (b) Calculated oscillations in the rate of CO_2 production.

ELECTRONIC, VIBRATIONAL, AND MAGNETIC PROPERTIES

ELASTIC VIBRATIONS IN FRACTAL SYSTEMS

S. H. Liu

Fractals and a variety of disordered solids share the intriguing geometrical property that they are self-similar under scale transformation. Consequently, it is of interest to analyze the physical properties of model fractal systems because the results may shed light on the corresponding properties of disordered solids. It has been argued that the vibrational frequency spectrum of an elastic fractal system is itself a fractal and that the fractal dimension of the spectrum called the spectral dimension $\bar{d}$ is related to the dimension of the fractal $\bar{D}$. Rammal and Toulouse carried out an analysis of a model fractal system called the Sierpinski gasket ($\bar{D} = \ln 3 / \ln 2$) and showed that $\bar{d} = 2 \ln 3 / \ln 5$. These authors used an isotropic force model in which the elastic constants for compression and shear are equal. Real solids do not have this property.

A more realistic elastic model is to connect the atoms with springs. We have analyzed the elastic vibrations of a Sierpinski gasket, in which a mass is attached to every vertex and nearest neighbor vertices are connected by springs. This model is known as the central force model in the literature. The basic building block of an elastic Sierpinski gasket is an equilateral triangle of three equal masses connected by three identical springs. One can write down a dynamical matrix for this system so that the natural modes are given by the zeros of the matrix. Then one uses the self-similar property to derive an iteration relation to generate the dynamical matrices and the frequency spectra of larger units. When carried to the infinite system, we find that the spectral dimension of this model is $\bar{d} = 2 \ln 3 / \ln 6$, which is different from the result for the isotropic model. This difference supports the speculation that the two force models belong to two distinct universality classes.

The simple elastic fractal model based on the Sierpinski gasket has been found useful in interpreting the spin-lattice relaxation data for protein molecules. These molecules have complicated irregular structures consisting of thousands of atoms, but their basic structure is a few long chains which curl up and form cross links. It has been proposed that the backbone of each chain resembles the shape of the path of a self-avoiding random walk. Consequently, for many purposes one may ignore the detailed structure of such molecules and instead regard them as fractals. The fractal dimension $\bar{d}$ of protein molecules varies from 1.2 to 1.8, and this range brackets the value 1.67 for the self-avoiding random walk.

Further evidence of fractal nature has been provided by the anomalous temperature dependence of the spin-lattice relaxation rate of protein molecules. At temperatures above 4 K the spin-lattice relaxation of insulating crystals is dominated by the phonon Raman effect, and the relaxation rate $1/T_1$ depends on the temperature according to the T^α law, where $\alpha = \frac{1}{2} + 2d$, and d is the dimension of the crystal. For protein molecules the experimental exponent α varies around 6, which cannot be understood on the basis of crystalline solids of integral dimensions. However, the exponential temperature dependence with $\alpha = 3 + 2\bar{d}$ seems to be well obeyed by a large number of proteins.

A previous theoretical argument gave the exponent $\alpha = 3 + 2\bar{d}$ in the asymptotic region (i.e., very low temperatures at which only long-wavelength, low-frequency modes are excited). Comparison between theory and experiment has led to the conclusion that $\bar{d} = \bar{d}$ for proteins. This conclusion contradicts the inequality $\bar{d} < \bar{d}$ for every model system analyzed so far.

We have studied rigorously for the first time the spin-lattice relaxation of an elastic fractal system over the entire temperature range. We use as the model the elastic Sierpinski gasket whose vibrational modes can be solved exactly. At low temperatures when only low-frequency modes are excited, the matrix element of the local strain operator, which is the coupling mechanism between the spin and the vibrational modes, is sensitive to the location of the spin. Consequently no simple power law of $1/T_1$ versus T can be found.

The previous theory ignored the matrix element effect and led to the wrong conclusion as a result. In the temperature range of the actual measurements, vibrations of rather high frequencies are excited, and these modes cannot be described by an asymptotic theory. An approximate power law can be extracted from the calculated $1/T_1$ versus T curve, and the exponent is found to be rather close to $3 + 2\bar{d}$. Thus, the empirical law is justified, and a controversy in the existing literature is resolved.

NEW INTERPRETATION OF SPIN-WAVE BEHAVIOR IN NICKEL¹

J. F. Cooke J. A. Blackman²
T. Morgan²

Past inelastic neutron scattering experiments have provided considerable information about the unusual properties of spin waves in the 3d-transition metal ferromagnets nickel and iron.³ Such information is useful to test theoretical models of ferromagnetism for metallic systems. Results from these experiments have supported the itinerant electron theory but have not provided a complete description of spin waves in these materials. Neutron scattering cross sections with energy transfer above 150 meV are very difficult, if not impossible, to measure using conventional steady-state reactors. Because of this difficulty and the need to reduce computer time to a minimum, early theoretical calculations of the inelastic neutron scattering cross section, magnetic susceptibility, and spin-wave behavior were restricted to energies below 200 meV.³ These calculations, based on "realistic" energy bands, were found to be in excellent agreement with experiments for energies below 100 meV. Above 100 meV, these calculations predicted the existence of an "optical" spin-wave mode at about 130-140 meV along the [100] direction in nickel and a spin-wave branch which continued above the 200-meV cutoff. Neither of these effects was found in the early experiments. Subsequent experiments⁵ using the hot source at the Institut Laue-Langevin (ILL) reactor confirmed the existence of the "optic" mode at the predicted energy but did not provide information about the higher energy part of the dispersion curve. Because of the recent improvement of the hot source at the ILL and the development of neutron spallation sources, which should be useful for energies up to 800 meV, we decided to map out the complete theoretical spin-wave spectra for nickel.

The total magnetic inelastic cross section consists of a transverse part, which contains information about spin-flip scattering, and a longitudinal part corresponding to nonspin-flip scattering. These cross sections are completely determined from the band structure (i.e., there are no adjustable parameters). We have evaluated them using the same band structure and numerical techniques used in previous calculations for energy transfer below 200 meV.⁴ The calculations were carried out for fixed wave vector q as a function of neutron energy transfer ω for energies up to 1 eV. The spin waves show up as peaks in the cross section. The positions of the peaks

determine the spin-wave energy, and the peak widths reflect inverse lifetimes.

A summary of results from an extensive series of calculations for nickel is given in Figs. 1.11 and 1.12. The two main features of the [100] branch (Fig. 1.11) are the apparent crossing of the acoustic and "optic" modes and the continuation of the upper branch to about 325 meV. The spin-wave peak is very sharp for energies below 100 meV.

Fig. 1.11. Calculated spin wave dispersion curve along [100] for nickel.

Fig. 1.12. Calculated spin wave dispersion curve along [111] for nickel.

The peak width broadens somewhat, and the peak height drops by about an order of magnitude in the region where the lower branch bends over. Relatively small peaks associated with this lower branch persist out to the zone boundary. The peak width of the upper branch increases rather slowly at first but broadens significantly as the zone boundary is approached. The results in Fig. 1.12 are for q along [111], where no "optic" branch is found. The spin-wave peaks broaden considerably, and the intensity drops significantly as the zone boundary is approached. At the zone boundary, they are somewhat sharper than corresponding (very broad) peaks associated with the upper branch along [100].

These numerical calculations provide a more coherent theoretical picture of spin-wave behavior in nickel. Early theoretical work had established that spin waves might run into a continuum of single-particle spin-flip excitations (Stoner excitations) and disappear at some wave vector inside the first Brillouin zone. Early experimental work on nickel found that spin-wave intensities did drop dramatically to undetectable limits at about one-quarter of the way to the zone boundary.³ The energy of the spin wave at this point was about 100 meV and was taken as direct evidence that the spin waves disappeared into the Stoner continuum. The problem with this interpretation was that the energy characteristic of Stoner excitations at such relatively small wave vectors should be near the spin-splitting energy, which at that time was estimated to be in the 600-800 meV range.

The results given in Figs. 1.11 and 1.12 provide a straightforward resolution of this conflict. The "disappearance" of the spin waves along [100] in the early experiments was associated with crossing of the "optic" and acoustic branches, a phenomena which was totally unexpected at the time. Our calculations indicate, however, that small remnants of spin-wave peaks exist out to the zone boundary in both the [100] and [111] directions. We interpret the substantial broadening of the spin-wave peaks in the upper branch along [100] near the zone boundary to be associated with the relatively large density of Stoner excitations, which is known to occur around the "average" spin-splitting energy (~400 meV for our band structure). It should be noted that because of s-p-d hybridization effects, Stoner excitations occur at essentially all energies, a fact which is reflected in the finite widths of the spin-wave peaks for all nonzero energies.

Results from recent neutron scattering experiments carried out at the ILL by Mook and Paul⁶ subsequent to our work appear to be in general agreement with the theoretical predictions. This is true for both the dispersion curves and the peak widths. There is, however, a problem with the lower energy branch along [100]. According to our results, the peak associated with the lower branch is longer and sharper than the one for the upper branch. This situation persists out to the zone boundary. The neutron measurements of Mook and Paul⁶ detected the upper branch near the zone boundary but not the lower one. This inconsistency might be attributed to neglecting all but the pure d-symmetry terms in the evaluation of the cross section. We do not expect

that inclusion of the s, p, and cross-symmetry terms will affect significantly the position of the peaks, but it could alter the peak widths, especially at lower energies. Work is currently under way to generalize our computer programs to include these terms.

In summary, our calculations indicate that for nickel the spin-wave peaks persist out to the zone boundary in the [100] and [111] directions with intensities that decrease significantly as the zone boundary is approached. We associate the very broad peaks found in the theoretical calculations and in the neutron experiments near the [100] zone boundary with the spin waves running into the large density of Stoner excitations near the "average" spin-splitting energy Δ . If true, this means that Δ is in the 300- to 400-meV range, a result which is consistent with angular-resolved photoemission results and a factor of 2 less than that predicted by local density theory.

1. Summary of paper to be published.
2. University of Reading, Reading, England.
3. H. A. Mook et al., *J. Appl. Phys.* **40**, 1450 (1969); H. A. Mook, J. W. Lynn, and R. M. Nicklow, *Phys. Rev. Lett.* **30**, 556 (1973); p. 781 in *Proceedings of the Nineteenth Conference on Magnetism and Magnetic Materials*, Boston, 1973, ed. by C. D. Graham, Jr., and J. J. Rhyne, AIP Conf. Proc. No. 18, AIP, New York, 1974.
4. J. F. Cooke and H. L. Davis, p. 1218 in *Proceedings of the Eighteenth Conference on Magnetism and Magnetic Materials*, Denver, 1972, ed. by C. D. Graham, Jr., and J. J. Rhyne, AIP Conf. Proc. No. 10, AIP, New York, 1975; J. F. Cooke, *Phys. Rev. B* **7**, 1108 (1973); J. F. Cooke, J. W. Lynn, and H. L. Davis, *Phys. Rev. B* **21**, 4118 (1980).
5. H. A. Mook and D. Tocchetti, *Phys. Rev. Lett.* **43**, 2027 (1979).
6. H. A. Mook and D. McK. Paul (to be published).

PARAMAGNETIC FORM FACTORS FROM ITINERANT ELECTRON THEORY¹

J. F. Cooke S. H. Liu
A. J. Liu²

A uniform magnetic field induces in a non-magnetic metal a magnetization density which has the periodicity of the lattice. The bulk susceptibility is proportional to the average of the moment density, and the magnetic form factor as measured by the polarized neutron scattering technique gives the Fourier transform of the moment distribution. In the past two decades the induced moment form factor has been measured for a large number of transition metals, and these data provide detailed information on the response of the metals to an external magnetic field. In principle, one should be able to relate the moment distribution to the energy levels and wave functions of the metallic electrons. In practice, however, the orbital part of the magnetic response of the itinerant electrons presents a major obstacle. The difficulty is well known. In short, the magnetic field B enters the Hamiltonian of

the electron system via the vector potential. In an infinite crystal the vector potential diverges so that a perturbative treatment of the field effect fails. An exact treatment is possible only in the free electron limit, which is not applicable to transition metals.

Oh et al.³ circumvented the divergence problem and derived an exact expression for the generalized susceptibility, which is proportional to the orbital contribution of the magnetic form factor. This expression depends on the electronic bands and relevant material elements and is difficult to evaluate. Oh et al.³ suggested an approximation scheme and applied it to Cr. Their scheme involved the neglect of certain surface integrals over the unit cell boundary, and they argued that it was justifiable for Cr but not for other transition metals.

An alternative to this approach is to formulate the magnetic response problem in real space, as was done by Benkowitz and Winter.⁴ The orbital part of the bulk susceptibility of Al, V, Nb, and Mo has been calculated by these authors, but no form factor calculation was attempted. In close analogy with Ref. 3, the authors of Ref. 4 also separated the total susceptibility into Van Vleck, Landau, and diamagnetic contributions. It was shown in Ref. 3 that such a procedure inevitably generates a number of unit cell surface integrals which are small for Cr and Mo but not small for V and Nb. It appears that these surface integrals were ignored in the algebraic manipulations in Ref. 4. Consequently the expression for χ_L in Ref. 4 is incomplete, and this is the reason for their unphysical result of large "paramagnetic" Landau susceptibility in V and Nb.

We have developed a different method to evaluate approximately the orbital part. The method is based on two observations: (1) that the largest contribution to the sum comes from states near the Fermi level, and in transition metals these are largely d states; and (2) that the dipole matrix elements between states in the d bands are very small. Consequently, we may neglect all terms which contain the dipole matrix element as a factor. Unlike the method of Ref. 3, we do not need to evaluate any surface integrals on the unit cell boundary. As a result, the new scheme is applicable to all transition metals. Neither method is applicable to simple metals, however, because they both neglect the Landau diamagnetism.

We have used this new approach to calculate the total magnetic form factor

$$F(\mathbf{G}) = \alpha_s F_s(\mathbf{G}) + F_o(\mathbf{G}) + F_c(\mathbf{G}), \quad (1)$$

based on local density theory. $F_s(\mathbf{G})$ is the unenhanced spin susceptibility,³ α_s is the corresponding spin enhancement factor, $F_o(\mathbf{G})$ is the orbital susceptibility, and $F_c(\mathbf{G})$ is the diamagnetic susceptibility for the core electrons (i.e., electrons not included in the calculation of F_o). All of the quantities in Eq. (1) are completely determined from the band structure (i.e., there are no adjustable parameters). To date, numerical results for Nb, Mo, Cr, V, Pd, and Rh have been obtained on an absolute scale using potentials

and spin enhancement factors determined by Moruzzi, Janak, and Williams.⁵ Comparisons of our results for Cr and Nb with experiment are shown in Figs. 1.13 and 1.14, respectively. These represent the best and worst cases found so far. The results for Cr are in excellent agreement with those of Oh et al.,³ which provide an important cross-check on our calculations.

Fig. 1.13. Comparison of calculated form factor for chromium with experimental data from Stassis et al.⁶

Fig. 1.14. Comparison of calculated form factor for niobium with experimental data from Moon et al.⁷

The results for Cr are dominated by the orbital contributions and are obviously in excellent agreement with experiment. Niobium is a case where the spin and orbital contributions are comparable at $G = 0$. However, the orbital term dominates for $G \neq 0$ because of the rapid decrease of the spin term with increasing $|G|$. The poor agreement with experiment indicates a problem with the wave functions generated by the local density approximation. A word of caution must be stated about comparisons of the type given in Figs. 1.13 and 1.14. Experimental form factor results are usually given on a relative scale with $F(0) = 1$. Since $F(0)$ cannot be determined from neutron measurements, some sort of extrapolated value must be used to normalize the data. It would be preferable if the form factor data were given on an absolute basis [disregarding $F(0)$] since this would allow a more detailed test of theoretical predictions.

Calculated results for the bulk susceptibility, $F(0)$, are given in Table 1.1. Our results for Nb and V are quite different from those of Benkowsch and Winter⁴ while results for Mo are in close agreement. In all cases the difference is almost exactly equal to their value for χ_L . This reinforces our point of view that their final expression for χ_L is incorrect. (We expect χ_L to be quite small and negative.) The reason the Mo results agree is because, unlike Nb and V, the Mo wave functions are approximately zero at the Wigner-Seitz sphere radius and the neglected surface integrals are likewise small. Unfortunately, not enough space is available here to give a detailed comparison with experiment. Experimental data for the bulk susceptibility for most paramagnetic materials vary over a wide range of values. Within these limits, it appears that, except for Pd, our results are reasonable.

In summary, our first principle calculations appear to be in reasonable agreement with experimental results. There are, however, certain discrepancies which appear to be outside combined numerical and experimental uncertainties. In order to help clarify the current situation it is important that we have more accurate form factor data (in absolute not relative units), as well as

Table 1.1. Calculated values of the spin ($\alpha_S F_S$), orbit (F_O), and core (F_C) contributions to the bulk susceptibility (χ). All values are in 10^{-6} emu/mol.

	$\alpha_S F_S$	F_O	F_C	χ
Cr	30	138	-7	161
V	126	113	-8	231
Nb	82	94	-14	162
Mo	25	98	-13	110
Pd	352	28	-10	370
Rh	82	51	-10	123

reliable bulk susceptibility data, on a wide range of pure materials at low temperatures.

1. Summary of paper: Proceedings 30th Annual Conference on Magnetism and Magnetic Materials (in press).
2. Cornell University, Ithaca, N.Y.
3. K. H. Oh et al., Phys. Rev. B **14**, 1283 (1976).
4. J. Benkowitsch and H. Winter, J. Phys. F **13**, 991 (1983).
5. V. L. Moruzzi, J. F. Janak, and A. R. Williams, Calculated Electronic Properties of Metals, Pergamon Press, Inc., New York, 1978.
6. C. Stassis, G. R. Kline, and S. K. Sinha, Phys. Rev. B **1**, 1171 (1975).
7. R. M. Moon, W. C. Koehler, and J. W. Cable, p. 577 in Proceedings of the Conference on Neutron Scattering, Vol. II, ed. by R. M. Moon, ERDA Report CONF-7670601-P2, ORNL, Oak Ridge, Tenn., 1976.

BAND STRUCTURE EFFECTS IN THE ELECTRONIC PROPERTIES OF SOLIDS ASSESSIBLE BY NEUTRON SCATTERING STUDIES¹

J. F. Cooke J. A. Blackman²
T. Morgan²

Inelastic neutron scattering experiments using thermal neutrons have traditionally been limited to neutron energy transfers of ~100 meV or less. This, of course, is ideal for the study of a wide variety of the elementary excitation spectra in solids. However, most electronic excitations which can occur in solids lie well outside this range of energy. The development of high-flux, high-energy spallation neutron sources could, in principle, raise this limit significantly, perhaps into the few-eV range. This type of source, therefore, has the potential of becoming an important tool for determining band structural information as well as dispersion curves for high-energy elementary excitations.

Because of the potential importance of this neutron source we have initiated a study of inelastic magnetic neutron scattering for metallic and semiconductor systems. There are two important categories of questions that must be addressed. One is associated with the type of information which might be obtained. What does the structure in the cross section look like? Can it be related directly or indirectly to features of the band structure and/or crystal field levels? What type of elementary excitations and electronic transitions occur at high energies and what sort of structure do they contribute to the cross section?

The other type of question concerns the order of magnitude of the scattering. Are the cross-section intensities for the structure of interest large enough to be measured? This is a nontrivial matter for experiments carried out for large neutron energy transfer. In general, neutron experiments are carried out for as small a wave-vector transfer Q as possible because of the dramatic decrease in intensity due to form factors or matrix elements decreasing with increasing Q .

On the other hand, Q must be large enough to satisfy the energy and momentum conservation conditions for these higher energy transfer experiments. The hope is that there will be a region of compromise where the intensities can be successfully measured.

We present here some results from two different studies of the theory of inelastic neutron scattering for energy transfers of a few electron volts or less. The purpose of this work is to aid in assessing the feasibility of determining new information about electronic transitions (band structure effects) and elementary excitations at higher energy transfers. The first study is concerned with the possibility of determining band structural information for semiconductors. This work represents an extension of previous calculations³ for silicon and germanium to Q 's which are more relevant to realistic experimental conditions. The second and more ambitious study is to investigate the scattering from ferromagnetic transition metals, which results from electronic transitions as well as elementary excitations (spin waves).

We have carried out an extensive series of calculations of the total cross section for Q along the [100], [111], and [110] directions for silicon and germanium. These results are based on the use of four valence and four conduction bands, which should ensure reasonable accuracy for neutron energy transfers of a few eV or less. The band structure was obtained using the empirical pseudopotential method outlined in Ref. 3. Representative examples of the type of results obtained from this study are given in Fig. 1.15. These results provide a comparison of the total scattering cross section to the orbital contribution for germanium and silicon. The difference is, of course, the spin contribution. Notice that the intensity scale is in millibarns/(sr-eV). A number of general features of the calculations for both silicon and germanium are illustrated in these two figures. The intensity profiles clearly have considerable energy-dependent structure, which also varies with Q . There are no special features which can be related to the band gap (~1 eV). However, if the structure in these intensity profiles could be measured, a "best" set of the pseudopotential parameters could be determined from some type of least-squares fitting procedure. Another important feature of these results is that the total scattering cross section also decreases significantly with increasing Q . From arguments given in Ref. 4, it appears unlikely that measurements can be made for Q 's inside the first Brillouin zone, because of the large neutron energy transfer. Therefore, the scale of intensities given in Fig. 1.15 is probably a reasonable upper bound for the scattering intensities to be expected in realistic experiments. That is, the experiments must be able to detect intensities in the range of tens of millibarns/(sr-eV).

We have also carried out calculations of neutron momentum transfer, the spin part of the zero temperature scattering cross sections, for fixed Q along [100] and neutron transfer energies ranging from zero to approximately 3 eV. The general approach that we have used to calculate the cross section is based on an extension of previous work^{5,6} which provides the details of the theory.

Fig. 1.15. Results for total scattering and orbital contribution for germanium (top) and silicon (bottom).

Representative results for the longitudinal, transverse, and total spin part of the scattering are given in Fig. 1.16. For each Q , there are two spin-wave peaks at low energy and some structure from electronic transitions at higher energy.

Based on the rather limited results obtained thus far it appears that important information about ferromagnetic nickel can be determined from neutron scattering experiments performed using a spallation source. Experiments at higher neutron energy transfer could map out the complete spin-wave spectra and provide information about electronic transitions above 1 eV. Unfortunately, it appears that the enhancement factors suppress any structure in the scattering cross section below 1 eV, which is generated by electronic transitions. In particular, there appears to be little hope that information about the spin-splitting energy for nickel could be determined directly from such experiments.

1. Summary of paper: in Proceedings NATO Advanced Research Workshop on Condensed Matter Research Using Neutrons, Today and Tomorrow, ed. by S. W. Lovesey, Abingdon, Oxfordshire, England, 1984.

2. Guest scientist from University of Reading, Reading, England.

3. J. F. Cooke and J. A. Blackman, Phys. Rev. B 26, 4410 (1982).

4. D. R. Allen, E. W. J. Mitchell, and R. N. Sinclair, J. Phys. E 13, 639 (1980).

5. J. F. Cooke and H. L. Davis, p. 1218 in Proceedings of the Eighteenth Conference on Magnetism and Magnetic Materials, ed. by C. D. Graham, Jr. and J. J. Rhyne, AIP Conf. Proc. No. 10, AIP, New York, 1975.

6. J. F. Cooke, Phys. Rev. B 7, 1108 (1973).

Fig. 1.16. Results for total spin (transverse and longitudinal) scattering intensity for nickel for $Q = (0.25, 0, 0)$ (top) and $Q = (0.625, 0, 0)$ (bottom).

CRITICAL BEHAVIOR OF A DILUTE INTERACTING BOSE FLUID¹

M. Rasolt¹ M. J. Stephen²
M. E. Fisher³ P. B. Weichman³

We have studied Bose-Einstein condensation in a dilute, weakly interacting Bose fluid and showed that the crossover from critical behavior to ideal function. Possible realizations of such a system are provided by superfluid ⁴He films adsorbed on porous Vycor glass⁴ and by spin-polarized hydrogen.⁵ Here we address ⁴He in Vycor, which is a highly connected, spongelike glass with a pore size of 50–80 Å in the experiments of Crooker et al.⁴ These authors studied the superfluid density in Vycor over a wide range of density ρ , with the resulting superfluid transition temperatures varying from 2 K down to 4.4 mK at the lowest density studied. For all critical temperatures $T_c(\rho)$ the experiments are consistent with the superfluid density varying as $\rho_s \sim (T_c - T)^\zeta$ with $\zeta = 2/3$ as $T \rightarrow T_c$. Thus, for all ρ the superfluid transition in Vycor appears similar to that occurring in bulk ⁴He, with the exponent ζ being sensibly constant. This effect suggests that the disorder introduced by the irregular Vycor structure is irrelevant to the critical behavior and is consistent with the general theory of the effects of disorder⁶ and the fact that the specific heat exponent of bulk ⁴He is negative ($\alpha = -0.02$). The thermal wavelength of the ⁴He atoms is comparable with the pore size at the lower temperatures, which should reduce the effects of disorder. Vycor is a highly connected structure,⁷ and although the ⁴He atoms are confined to the surface by the strong van der Waals potential, they would be expected to behave as a three-dimensional fluid.⁸ At the lower densities the superfluid interparticle spacing is from 5 to 12 times the atomic hardcore diameter, and thus the fluid is very dilute.

The observed size of the critical region described by $\zeta = 2/3$ shrinks as ρ decreases, and a crossover to ideal Bose-gas or mean-field-like behavior, $\rho_s \sim T_c - T$, is seen as $T_c(\rho) \rightarrow 0$. The scaling theory of critical phenomena indicates that this behavior should be described by a scaling function, the existence of which should be independent of any detailed model of ⁴He in Vycor. Our theory shows that the form of the scaling function for the superfluid density at low temperatures and densities in d dimensions is

$$\rho_s = \rho_s(0)(T/T_c)^{d/2} t Y[(a/\Lambda_T)^{d-2}/t^\phi] \quad (1)$$

Here $\rho_s(0)$ is the superfluid density at $T = 0$, $t = (T_c/T)^{d/2} - 1$, a is the scattering length characterizing the interaction of He atoms, $\Lambda_T = (h^2/2m^*k_B T)^{1/2}$ is the thermal wavelength of ⁴He atoms of effective mass m^* , and ϕ is a universal crossover exponent. Ideal Bose-gas behavior follows when $T \rightarrow 0$ if $Y(0) = 1$, and a crossover to bulk behavior, $\rho_s \sim t^\zeta$, follows as $t \rightarrow 0$ at $T_c > 0$ if $Y(y) \sim y^{(1-\zeta)/\phi}$ as $y \rightarrow \infty$. The critical region thus shrinks like $t \sim T(d-2)/2\phi$ as $T_c \rightarrow 0$.

Figure 1.17 illustrates that the data of Crooker et al.⁴ satisfy Eq. (1) rather well when

Fig. 1.17. A scaling plot of the experimental data (Ref. 4), including eleven values of $T_c(\rho)$ from 6 to 12 mK (open circles), 15 to 35 mK (triangles), and 37 to 77 mK (filled circles): To plot the data, we chose, purely for convenience, to set $(a^2 m^*/m_{He})^{1/2} = 5$ Å and $B = 0.025$. The solid line is the theoretical result, the single adjustable parameter being fixed by choosing $(a^2 m^*/m_{He})^{1/2} = 200$ Å to match the $y^{1-\nu}$ singularity at the origin, $u \rightarrow \infty$ (Ref. 9).

$\phi = 1$. To calculate the theoretical solid curves in Fig. 1.17 we modeled ⁴He in Vycor as a mobile, low-density, spinless Bose gas in a d -dimensionally connected medium whose properties entered only through an effective mass m^* and an effective two-body potential with Fourier transform v_k . The Hamiltonian is

$$\mathcal{H}_B = \sum_k \epsilon_k a_k^\dagger a_k + \frac{1}{2V} \sum_{kk'k''} v_k a_k^\dagger a_{k'}^\dagger a_{k''} a_{k+k'+k''} \quad (2)$$

where $\epsilon_k = \hbar^2 k^2 / 2m^*$ and $a_k^\dagger, a_k$ are Bose creation and annihilation operators. At low densities we can replace v_k by an effective s -wave scattering potential v_0 , which for $d = 3$ is $v_0 \sim (\hbar^2 / 2m^*) a^{d-2}$ and a is the scattering length.⁹ Both m^* and a should be only weakly temperature dependent.

In order to study the superfluid transition and utilize current knowledge of critical phenomena, we mapped Eq. (2) onto a classical spin model. We first noted that the critical properties of an ideal Bose gas coincide with those of the spherical model of a ferromagnet.¹⁰ Secondly, for $T_c \neq 0$, critical behavior does not depend on the noncommutative aspects of quantum mechanics.¹¹ We thus compare Eq. (2) with

$$\mathcal{H}_S = -\frac{1}{2} \sum_k J_k |S_k|^2 + \frac{1}{V} \sum_{kk'k''} u_k S_{-k} \cdot S_{k+k'} \quad (3)$$

where the exchange coupling of finite range R_0 is $J_k = J_0(1 - R_0^2 k^2 + \dots)$, while the S_k are classical n -component vectors with $\langle S_k^\mu \rangle = 0$. Corresponding to the implied constant-density constraint for Eq. (3), we impose the spherical constraint

$$\frac{1}{nV} \sum_k |S_k|^2 = \rho = \frac{1}{V} \sum_k \langle a_k^\dagger a_k \rangle. \quad (4)$$

Equations (3) and (4) can be studied using the ϵ expansion and solved exactly to lowest order in $\epsilon \equiv 4-d$. This gives the crossover from critical to ideal Bose fluid behavior as presented by the solid curve of Fig. 1.17. Clearly the results are in very good agreement with the experimental measurements, and the scaling functions can be shown to obey the form of Eq. (1). This observation supports the description of this system as a dilute, weakly interacting, three-dimensional Bose fluid.

1. Summary of paper: Phys. Rev. Lett. **53**, 798 (1984).
2. Serin Physics Laboratory, Rutgers University, Piscataway, N.J.
3. Baker Laboratory, Cornell University, Ithaca, N.Y.
4. B. C. Crooker et al., Phys. Rev. Lett. **51**, 666 (1983).
5. For a recent review see I. F. Silvera, Physica (Utrecht) **109B+C**, 1499 (1982).
6. A. B. Harris, J. Phys. C **7**, 1671 (1974).
7. The preparation of Vycor involves a leaching process beginning at the surface. This process ensures the presence of an infinite cluster of open pores which, in the experiments, is well above the percolation threshold. The presence of such clusters is shown by porosity measurements which give values of about 40% [R. H. Tait and J. D. Reppy, Phys. Rev. B **20**, 997 (1979)]. It is unlikely that Vycor should be viewed as a fractal structure, but if it is, the effect on the transition in an ideal Bose gas should be to give a condensate fraction $\rho_s \sim 1 - (T/T_c)d/2$, where d is the fractal dimension that determines the density of states (assumed extended) at low energies [S. Alexander and R. Orbach, J. Phys. Lett. (Paris) **42**, L625 (1982)].
8. This model is also consistent with heat-capacity studies, etc. (see Ref. 1). Some sound-attenuation experiments have been interpreted in terms of reduced dimensionality [B. Lambert, R. Persynski, and D. Salin, J. Phys. Lett. (Paris) **41**, L19 (1980)].
9. K. Huang and C. N. Yang, Phys. Rev. **105**, 767 (1957).
10. H. Berlin and M. Kac, Phys. Rev. **86**, 821 (1952); J. D. Gunton and M. J. Buckingham, Phys. Rev. **166**, 152 (1968).
11. R. Abe and S. Hikami, Phys. Lett. **47A**, 341 (1974).

PHASE TRANSITIONS IN A THIRD-RANK TENSOR HAMILTONIAN: APPLICATION TO SYSTEMS WITH TETRAHEDRAL SYMMETRY¹

M. Rasolt A. D. J. Haymet²

Orientational phase transitions for molecules of tetrahedral symmetry (e.g., solid methane) have occupied considerable interest and effort.³⁻⁷ All such studies, however, are based exclusively on either mean field (MF) calculations³ or numerical simulations,⁶ and therefore, definite predictions about the nature of the phase transitions are scarce. Here we describe the first renormalization group (RG) study of a continuum model Hamiltonian for tetrahedral symmetry and then make definite predictions regarding its critical behavior to order $\epsilon \equiv 4-d$, which is, therefore, in the range of small quartic coupling.

The spherical harmonic functions Y_L^M for the tetrahedral group start with the irreducible representation of $L = 3$ (or $n = 2L + 1$ vector components) and lead to an octapole-octapole interaction between them.³ These Y_L^M for $L = 3$ can be mapped to an equivalent representation⁸ of symmetric traceless third-rank tensors $Q_{\alpha\beta\gamma}$ (i.e., α, β , and γ run from 1 to p with $p = 3$, $Q_{\alpha\beta\gamma} = Q_{\gamma\alpha\beta} \dots$, and $\sum_{\alpha} Q_{\alpha\beta\alpha} = 0$). The appropriate Hamiltonian invariant under rotation of both coordinates and order parameters (OP) is then, in momentum space,

$$\begin{aligned} H = & \frac{1}{12} [(r + q^2) \delta_{\alpha_1\lambda_1} + h q_{\alpha_1} q_{\lambda_1}] \\ & \times Q_{\alpha_1\beta_1\gamma_1} Q_{\lambda_1\beta_1\gamma_1} + u (Q_{\alpha_1\beta_1\gamma_1} Q_{\alpha_1\beta_1\gamma_1})^2 \\ & + v Q_{\alpha_1\beta_1\gamma_1} Q_{\beta_1\gamma_1\alpha_2} Q_{\alpha_2\beta_2\gamma_2} Q_{\beta_2\gamma_2\alpha_1} \\ & + w Q_{\alpha_1\beta_1\gamma_1} Q_{\alpha_1\beta_2\gamma_2} Q_{\beta_1\beta_2\gamma_3} Q_{\gamma_1\gamma_2\gamma_3}. \end{aligned} \quad (1)$$

The three quartic terms are the only invariants possible. Unlike the work of Priest and Lubensky⁹ on second-rank tensors, H cannot contain third-order invariants and is therefore more appropriate for RG analysis. With h, u, v , and w all set = 0, the propagator of H in Eq. (1) is

$$\begin{aligned} \langle Q_{\alpha_1\beta_1\gamma_1} Q_{\alpha_2\beta_2\gamma_2} \rangle = & \frac{1}{r+q^2} [(1-\delta_{\alpha_1\beta_1})(1-\delta_{\alpha_1\gamma_1}) \\ & \times (1-\delta_{\beta_1\gamma_1}) \delta_{\alpha_1\alpha_2} \delta_{\beta_1\beta_2} \delta_{\gamma_1\gamma_2} + 2\{\delta_{\beta_1\beta_2} \\ & - \frac{1}{p+2}\} \delta_{\alpha_1\alpha_2} \delta_{\beta_1\gamma_1} \delta_{\beta_2\gamma_2} (1-\delta_{\alpha_1\beta_1})(1-\delta_{\alpha_1\beta_2}) \\ & + 6[1 - \frac{3}{p+2}] \delta_{\alpha_1\beta_1} \delta_{\alpha_1\gamma_1} \delta_{\alpha_1\alpha_2} \delta_{\alpha_1\beta_2} \delta_{\alpha_1\gamma_2} \\ & - [\frac{6}{(p+2)}] \delta_{\alpha_1\beta_1} \delta_{\alpha_1\gamma_1} \delta_{\alpha_1\alpha_2} \delta_{\beta_2\gamma_2} (1-\delta_{\alpha_1\beta_2})]]. \end{aligned} \quad (2)$$

The Hamiltonian of Eq. (1) has been renormalized via the ϵ expansion, and the fixed points u^* , v^* , w^* , and corresponding exponents ν and λ_i are listed in Table 1.2. These results predict a first-order-driven phase transition in a liquid crystal of tetrahedral symmetry.

For a cubic solid of tetrahedrally bonded molecules³⁻⁷ the phase transition still remains first order provided the crystal fields are weak. This is so since the RG flow lines of H (in Eq. 1) are not expected to make a discontinuous change in direction. The presence of fluctuations is therefore likely to modify strongly the $M\bar{r}$ conclusions even in methane.³ In fact, numerical simulations of such a Hamiltonian⁶ show a first-order phase transition (driven by fluctuations) going directly from the disordered to the uniformly ordered state,⁶ which is consistent with our RG results.

For a cubic system the largest irreducible representation for the OP has at most three independent components, and the quartic interactions will split into additional quartic invariants. Thus, we are continuing the RG study to such systems in order to make direct contact with strong cubic couplings.

1. Summary of paper: Phys. Rev. B (Rapid Communication) 30, 1619 (1984).

2. University of California, Berkeley, Calif.

3. H. M. James and T. A. Keenan, J. Chem. Phys. 31, 12 (1959).

4. W. Press, J. Chem. Phys. 56, 2597 (1972).

5. K. Maki, Y. Kataoka, and T. Yamamoto, J. Chem. Phys. 70, 655 (1979).

6. S. Nose et al., J. Chem. Phys. 75, 985 (1981).

7. M. L. Klein, I. R. McDonald, and Y. Ozaki, J. Chem. Phys. 79, 5579 (1983).

8. D. R. Nelson and J. Toner, Phys. Rev. B 24, 363 (1981).

9. R. G. Priest and T. C. Lubensky, Phys. Rev. B 13, 4159 (1976).

STRUCTURE FACTOR OF A CORRELATED NONUNIFORM FERMION GAS AT SMALL WAVELENGTH¹

M. Rasolt

Hubbard² and Nozières and Pines³ were some of the first to recognize the utility of studying the detailed dependence of the structure factor, for a uniform correlated electron gas, on the individual wave vectors q . Following these ideas there were several recent extensions⁴⁻⁹ of such calculations to nonuniform systems, with some surprising results⁹. It was shown that any non-uniformity, superimposed on a uniform Fermion system, fundamentally changes the nature of the structure factor $S_\lambda(r, r')$ in the thermodynamic limit. The $S_\lambda(r, r')$ or equivalently the exchange-Coulomb hole^{8,9} is given by

$$S_\lambda(r, r') = \langle \phi_\lambda | [\rho(r) - \rho(r)][\rho(r') - \rho(r')] | \phi_\lambda \rangle, \quad (1)$$

Table 1.2. Fixed points [results listed should be multiplied by $\epsilon/(12^2 K_0)$, where K_0 is the phase factor in dimension four] and associated exponents of the Hamiltonian in Eq. (1) for $p = 3$ (or $n = 7$).^a

Fixed point & associated exponents	u^*	v^*	w^*	ν^{-1}	λ_1	λ_2	λ_3
Gauss	0.	0.	0.	2.	ϵ	ϵ	ϵ
Heisenberg	1/15	0.	0.	$2.-3/5\epsilon$	$-\epsilon$	$\epsilon/5$	$\epsilon/5$
Real+	0.093	-0.0522	-0.0522	$2.-3/5\epsilon$	$-\epsilon$	$-\epsilon/5$	$\epsilon/5$
Real-	0.130	-0.261	-0.261	2.	$-\epsilon$	ϵ	ϵ
Comp ₁ +	0.108+0.103i	-(0.0654+0.271i)	0.0156+0.0646i				
Comp ₁ -	0.108-0.103i	-(0.0654-0.271i)	0.0156-0.0646i				
Comp ₂ +	0.0868+0.0142i	-(0.0225+0.0932i)	0.0585+0.242i				
Comp ₂ -	0.0864-0.0142i	-(0.0225-0.0932i)	0.0585-0.242i				

^aThe exponent ν and the crossover exponents λ_i are as defined, e.g., in Ref. 7. At $p = 3$, four of the eight fixed points are complex and are given by comp₁ $\pm$ (the $\pm$ correspond to the sign of the discriminant; see text). Since for each set of λ_i , at least one is positive, none of the fixed points is stable. The Gauss fixed point is most unstable followed by Real-, Heisenberg, and Real+.

where ϕ_λ is the full ground state for the non-uniform interacting Fermion system with interparticle interaction $\lambda v(q)$ and electron density $\rho(r)$. We have extended our results for $S(r, r')$ to small separations between r and r' and showed that the local density approximation to $S(r, r')$ is not rigorous. The famous local approximation to the exchange and correlation potential is closely tied to $S(r, r')$. Therefore, previous assumptions that such potentials are rigorous locally (i.e., as $r \rightarrow r'$) have been challenged.

1. Summary of paper: Phys. Rev. B **29**, 3703 (1984).
2. J. Hubbard, Proc. R. Soc. London, Ser. A **240**, 539 (1957).
3. P. Nozières and D. Pines, Phys. Rev. **111**, 443 (1958).
4. V. Peuckert, J. Phys. C **9**, 4173 (1976).
5. D. C. Langreth and J. P. Perdew, Phys. Rev. B **15**, 2884 (1977).
6. M. Rasolt, G. Malmström, and D. J. W. Geldart, Phys. Rev. B **20**, 3012 (1979).
7. M. Rasolt and D. J. W. Geldart, Phys. Rev. B **21**, 3158 (1980).
8. D. C. Langreth and J. P. Perdew, Phys. Rev. B **21**, 5469 (1980).
9. M. Rasolt and D. J. W. Geldart, Phys. Rev. B **25**, 5133 (1982).

STRUCTURE FACTORS FOR A BINARY MIXTURE OF QUANTUM AND CLASSICAL FERMION LIQUIDS¹

Mark Rasolt

The structure factor $S(q)$ of a liquid metal shows significant differences when measured by neutrons or X rays. Such differences are not apparent in liquids where all the electrons are tightly bound to the nuclei (e.g., Ar). Of particular interest is the presence of a linear dependence² in $S(q)$ on the momentum transfer q in the range $0.08 \text{ \AA}^{-1} \leq |q| \leq 0.3 \text{ \AA}^{-1}$. The above results have been postulated to originate in the two fluid nature of a liquid metal^{3,4} (electrons and nuclei). However, microscopic calculations of the electron structure factor⁵ have not provided an adequate explanation of this behavior. We have now shown that the interaction of the underlying classical liquid of nuclei with the electron fluid, does provide such a linear behavior at small q and also gives additional variation in $S(n)$ at large q .

1. Summary of paper: Physical Review B, Brief Reports (in press).
2. Y. Watabe, Z. Naturforsch (to be published).
3. P. A. Egelstaff, M. H. March, and N. C. McGill, Can. J. Phys. **52**, 1651 (1974).
4. C. C. Matthoi and N. H. March, Phys. Chem. Liq. **11**, 207 (1982).
5. J. Chihara, p. 137 in The Properties of Liquid Metals, ed. by S. Takeuchi, Taylor and Francis, London, 1973.

LONG-RANGE PART OF THE INTERACTION BETWEEN TWO HYDROGEN IMPURITIES IN JELLIUM¹

F. Perrot² M. Rasolt

A large body of theoretical work exists concerning the interaction of dilute hydrogen impurities with metallic hosts.³ For a proton in a simple metal, reliable numerical results for the heat of solution (including both electronic and lattice relaxations) have been obtained within various refinements of the jellium model.⁴ More recent efforts are directed toward study of the electronic structure of H in noble and transition metals,⁵ where the local effects of the d electrons introduce additional complications.

For higher concentrations of impurities, the properties of the H-H interaction in the metal become important. The standard method for calculating pairwise interactions in simple metals is based on pseudopotential theory.⁶ Unfortunately, it is completely inapplicable to the H-H interaction, since the proton is a very strong scatterer and any kind of linear screening fails. Even if the host potential (for instance, a lattice of weak pseudopotentials) is ignored, the full nonlinear screening of a pair of protons in jellium is a formidable two-center problem.

We have derived the first such pair interactions between two protons in which the important nonlinear screening of the proton with the host electrons has been included. The results for three different host electron density parameters (i.e., $r_s = 2.07, 2.65$, and 3.93) are presented in Fig. 1.18. We plan to apply such pair interactions to the β phase of metal hydrides to predict the phonon spectrum of the H sublattice and thus to motivate some neutron experiments for these systems.

1. Summary of paper: Phys. Rev. B **27**, 3273 (1983).
2. Commissariat à l'Energie Atomique, Centre d'Etudes de Limeil, Villeneuve-Saint-Georges, France.
3. D. S. Larsen and J. K. Morskov, J. Phys. F **9**, 1975 (1979), and references therein.
4. F. Perrot and M. Rasolt, Phys. Rev. B **23**, 6534 (1981).
5. P. Jena, F. Y. Fradin, and D. E. Ellis, Phys. Rev. B **20**, 3543 (1979); A. C. Switendick, p. 57 in Proceedings JIMIS-2, Transactions of the Japan Institute of Metals, Supplement to Vol. 21 of Hydrogen in Metals, Japan Institute of Metals, Sendai, Japan, 1980, and references therein.
6. W. A. Harrison, Pseudopotentials in the Theory of Metals, Benjamin, New York, 1966. For more recent calculations, see M. Rasolt and R. Taylor, Phys. Rev. B **11**, 2717 (1975); L. Dagens, M. Rasolt, and R. Taylor, Phys. Rev. B **11**, 2726 (1975).

Fig. 1.18. H-H interaction in jellium, as a function of internuclear distance R . The values of the density parameter $r_s = 2.07, 2.65$, and 3.93 correspond to the densities found in Al, Mg, and Na, respectively.

TRAVELING CLUSTER APPROXIMATION FOR UNCORRELATED AMORPHOUS SYSTEMS¹

Theodore Kaplan L. J. Gray²
A. K. Sen³ R. Mills³

The properties of electronic states in spatially disordered systems, after many years of study, are still not well understood. On the one hand, there have been exact, or nearly exact, numerical studies, in which the actual states are counted for finite, randomly chosen, one-dimensional samples to obtain the integrated density of states. These results, which can be described as "computer experiments," can be used to demonstrate the success or failure of theories developed to understand the physics of such systems. On the other hand, there are analytical methods which start from the one-electron Hamiltonian and make some approximations to obtain the configuration-averaged Green's function. Our presentation falls in the category of analytical approximation methods. There are two important aspects of the problem to be considered. The first is the effect of local clusters of scatterers (regardless of correlations), and the second is the effect of correlations (or short-range order). In each case, it is particularly important to preserve the Herglotz property of

the averaged Green's function, which is the set of analytical properties that are necessary to ensure causality and a non-negative, single-valued density of states.

The coherent potential approximation (CPA)⁴ is a single-site approximation (that is, it does not include scattering from clusters) that was developed for substitutional alloys and preserves Herglotzity. The application of the CPA logic to liquids due to Klauder⁵ is also Herglotz, but like the substitutional CPA does not take into account short-range order. The effective medium approximation (EMA) of Roth⁶ is also a single-site approximation which deals with short-range order by means of an approximate expression for the n -scattered correlation function in terms of the pair correlation function. Like almost all other ways of including short-range order, the EMA fails to preserve the Herglotz property, but nevertheless gives quite reasonable results in many instances.

Of the efforts to include cluster scattering in random substitutional alloys, there are two extensions of the CPA that preserve Herglotzity and translational symmetry, the traveling cluster approximation (TCA) of Mills and Ratanavararaksa⁷ and the generalization of the TCA to off-diagonal and environmental disorder by Kaplan, Leath, Gray, and Dienl (KLGD).⁸ The TCA retains translational symmetry and achieves Herglotzity by the inclusion of large classes of cumulant average graphs. KLGD similarly achieves proper translational symmetry and Herglotzity while extending the cluster approximation to general Hamiltonians by paralleling the TCA development in the augmented space formalism.⁸⁻¹⁰ The major shortcoming of these approximations is that short-range order cannot be treated fully self consistently but rather only in a perturbation expansion of the uncorrelated solution.¹¹

In this paper, we apply the TCA concepts to spatially disordered, uncorrelated systems (e.g., fluids or amorphous metals without short-range order). This is the first approximation scheme for amorphous systems that takes cluster effects into account while preserving the Herglotz property for any amount of disorder. We have performed some computer calculations for the pair TCA, for the model case of δ -function potentials on a one-dimensional random chain. These results are compared with "exact calculations" (which, in principle, take into account all cluster effects) and with the CPA, which is the single-site TCA. The density of states for the pair TCA clearly shows some improvement over the CPA, and yet, apparently, the pair approximation distorts some of the features of the exact results. We conclude that the effects of large clusters are much more important in an uncorrelated liquid metal than in a substitutional alloy. As a result, the pair TCA, which does quite a nice job for alloys, is not adequate for the liquid. Larger clusters must be treated exactly, and therefore an n -TCA with $n > 2$ must be used.

1. Summary of paper: Physical Review B (in press).

2. Engineering Physics Division, ORNL.
3. Ohio State University, Columbus, Ohio.
4. P. Soven, *Phys. Rev.* **156**, 809 (1967);
D. M. Taylor, *Phys. Rev.* **156**, 1017 (1967).
5. J. R. Klauder, *Ann. Phys.* **14**, 43 (1961).
6. L. M. Roth, *Phys. Rev. B* **9**, 2476 (1974).
7. R. Mills and P. Ratanavararaksa, *Phys. Rev. B* **18**, 5291 (1978).
8. T. Kaplan et al., *Phys. Rev. B* **21**, 4230 (1980).
9. T. Kaplan and L. J. Gray, *Phys. Rev. B* **14**, 3462 (1976).
10. A. Mookerjee, *J. Phys. C* **6**, L205 (1973);
A. Mookerjee, *J. Phys. C* **6**, 1340 (1973).
11. L. J. Gray and T. Kaplan, *Phys. Rev. B* **24**, 1872 (1981).

LATTICE VIBRATIONS IN $K_{1-c}Rb_c$ ALLOYS

Theodore Kaplan Mark Mostoller
L. J. Gray¹

Lattice vibrations in the disordered binary alkali metal alloy system $Rb_{1-c}K_c$ have been studied experimentally at low temperatures (T~5K) by Kamitakahara and Copley.² Coherent inelastic neutron scattering measurements were performed for longitudinal modes propagating along the [110] direction and for transverse modes along the [001] direction, the former at potassium concentrations of $c = 0.06, 0.18$, and 0.29 and the latter at the two higher concentrations. A local mode band associated with the motion of the lighter potassium atoms was observed to grow in intensity as the potassium concentration increased. In addition, modest shifts occurred in the in-band peak positions relative to the corresponding phonon frequencies in pure Rb.

We have already studied this system theoretically³ using the mass defect coherent potential approximation (CPA)⁴ and the CPA-F.⁵ The mass defect CPA is a single site approximation which allows only the disorder in the masses to be included; it gave results that were generally in poor agreement with experiment.

The CPA-F is a single site theory which can incorporate force constant changes when the force constants are assumed to superimpose linearly, namely, when the A-B force constants are the arithmetic average of the A-A and B-B force constants. We included only the changes in the radial nearest neighbor force constants and determined them by fitting the CPA-F neutron scattering cross section to the experimental results. While we obtained significant improvement over the mass defect CPA results, there still existed sizable discrepancies with experiment, particularly near the zone boundary.

The deficiencies in the mass defect CPA and CPA-F theories have led us to apply a more sophisticated approximation which was developed by Kaplan, Leath, Gray and Diehl (KLGD).⁶ This approximation is a generalization of the CPA which is not restricted to single site averaging, but can include cluster scattering. More important, it can incorporate force constant changes without any restrictions. As a first application of KLGD, we have included nearest neighbor radial and tangential force constant changes with single

site averaging. As in the previous cases, all longer range forces are included in a virtual crystal approximation. In this study we have not tried to fit the force constants. Instead we have used a pseudopotential approximation by Grünewald and Scharnberg⁷ to determine the force constants in K-Rb alloys.

In general the KLGD results show significant improvement over the mass defect CPA and CPA-F results. In Fig. 1.19 the neutron scattering cross sections of $K_{0.29}Rb_{0.71}$ for the two most difficult scattering vectors to reproduce theoretically, $Q = (2\pi/a)(2.5, 2.5, 0)$ and $(2\pi/a)(2, 2, 1)$, are plotted. While these figures show an overall improvement by the KLGD theory over the mass defect CPA and CPA-F theories, the match with experiment still can be improved. One way to proceed would be to include force constant changes beyond first neighbors and averaging over clusters. However, it is most likely that the results can be most significantly improved by using a more accurate approximation to the force constants.

1. Engineering Physics Division, ORNL.

Fig. 1.19. KLGD theory (—), CPA-F (---), mass defect CPA (···) and experimental neutron scattering cross sections for $K_{0.29}Rb_{0.71}$ at zone boundary modes (a) $Q = (2\pi/a)(2.5, 2.5, 0)$ and (b) $Q = (2\pi/a)(2, 2, 1)$. Instrumental broadening is included in the calculated curves (FWHM=0.1 THz).

2. W. A. Kamitakahara and J. R. D. Copley, *Phys. Rev. B* **18**, 3372 (1978).
3. M. Mostoller and T. Kaplan, *Phys. Rev. B* **16**, 2350 (1977).
4. D. W. Taylor, *Phys. Rev.* **156**, 1017 (1967).
5. T. Kaplan and M. Mostoller, *Phys. Rev. B* **9**, 1783 (1974).
6. T. Kaplan et al., *Phys. Rev. B* **21**, 4230 (1980).
7. G. Grünewald and K. Scharnberg, p. 443 in *Proceedings of the International Conference on Lattice Dynamics*, ed. by M. Balkanski, Flammarion, Paris, 1978.

IONIC POTENTIAL MODELS IN INSULATORS HAVING THE RUTILE STRUCTURE¹

Mark Mostoller J. C. Wang

There have been extensive experimental and theoretical studies of the properties of defects in insulators, primarily for cubic systems like the alkali halides, the alkaline-earth oxides, and fluorite structure crystals. Recently, calculations of defect properties have been done for materials of lower symmetry such as α -alumina² and insulators that have the rutile structure.^{2,3} The potential model used in these calculations is the shell model, whose constituents are the charged ion cores and electronic shells, with the shells bound harmonically to their cores and with long-range Coulomb interactions between the charged constituents. The short-range interactions are taken to be a combination of Born-Mayer and van der Waals potentials acting between the shells. As in similar studies for cubic systems, the shell model parameters for the host crystal were fitted to the measured elastic and dielectric constants.

The shell model may also be used to describe the lattice dynamics of insulators; indeed, such applications were routine before shell model studies of defects in insulators were begun. The alkali halides and the alkaline-earth oxides, which crystallize in the rock-salt structure, have been studied quite extensively. Materials of lower symmetry are more difficult to treat, both experimentally and computationally, but nonetheless, there have been shell model fits to neutron scattering data for the lattice dynamics of such materials as TiO_2 , MnF_2 , and MgF_2 .⁴⁻⁶ To calculate the vibrational spectra of a perfect crystal, however, it is not necessary to know the full short-range pair potentials, but only their first and second derivatives at the equilibrium separations. These first and second derivatives are the Hooke's law spring constants for the vibrational problem, and they, rather than any more general pair potential parameters, are usually fitted to the data in lattice dynamical calculations.

In crystals of lower symmetry, it can be difficult to reconcile the defect (pair potential) and lattice dynamical (force constant) approaches. In the TiO_2 and Al_2O_3 structures, for example, the negative ions are located at sites where there is a nonzero static electric field, and to stabilize the lattice, these negative ions carry permanent dipole moments. The equilibrium positions of

the negative ion shells are therefore not known a priori. In most shell model calculations of lattice vibrations in rutile-structure materials, this feature is ignored, and it is assumed that the equilibrium positions of the negative ion cores and shells are equal. Cran and Sangster⁵ have included a static F-ion core-shell separation in their work on MnF_2 , but they treat this as an adjustable parameter rather than calculating it from some potential model.

In the recent shell model treatments of defects in TiO_2 , values were provided for the various model parameters, but no values were given for the lattice parameters to which they (actually) correspond, and no calculations of the phonon spectra were done. When such values are given, physical shortcomings of the models become apparent. Figure 1.20 shows dispersion curves calculated from the shell model of Catlow et al.² Imaginary frequencies are plotted as negative in the figure. The calculations were performed at the minimum-energy lattice constants, which were determined subject to two conditions. First, only first and second neighbor (1nn-2nn) Ti-O and first through fourth neighbor (1nn-4nn) O-O short-range interactions were included. Second, it was assumed that the crystal structure was that of rutile, which as we shall see, is not a defensible premise. The lattice constants predicted by the model of Catlow et al. are given in Table 1.3.

Negative eigenvalues occur in Fig. 1.20 along each of the three major symmetry directions in the Brillouin zone. These values are an indication that the crystal is unstable. This instability was confirmed by static calculations showing that the total potential decreased when the ions and shells were moved in the patterns predicted by the dynamical calculations at zero wave vector. The instabilities persist if no cutoffs are imposed on the short-range forces, if different cutoffs are used, or if we do not relax the crystal to equilibrium to minimize the potential energy, but assume instead that the

Fig. 1.20. Dispersion curves for TiO_2 calculated from the potential model of Catlow et al. Imaginary frequencies are plotted as negative in the figure.

Table 1.3. Observed and calculated lattice constants a , c , u_{core} , and cohesive energy E for TiO_2 . Units are a , c - Å; u_{core} - dimensionless; E - eV.

	a	c	u_{core}	E
Experiment	4.59373	2.95812	0.3053	126.
Catlow et al.	4.24633	3.42928	0.3085	111.4
This work	4.47889	3.07644	0.3053	93.4

lattice constants have the measured values given in Table 1.3 and that $u_s = u_c$. In short, the potential model of Catlow et al. does not give the correct equilibrium crystal structure.

Sawatari et al.³ have also investigated the formation energies of various point defects in rutile. Their potential model also generates lattice instabilities, which are if anything more severe. It is clearly necessary to assess a model's viability in terms of its predictions concerning lattice structure and dynamics before applying it to defects.

We have done extensive calculations for TiO_2 , but have not as yet found a potential model that gives good agreement with the measured phonon spectra and that simultaneously fits the cohesive energy well and the lattice constants exactly. However, we have found that it is possible to obtain fairly good agreement with the phonon data if the cohesive energy is ignored and the lattice constants are only required to be near the observed values (Fig. 1.21). The calculated curves fit the data of Traylor et al.⁴ as well as their own phenomenological shell model; the latter assumed that the equilibrium oxygen core and shell positions were the same, and it varied force constants rather than pair potential parameters. As shown in Table 1.3, the lattice constants a and c predicted by our potential model are fairly close

to experiment (97.5 and 104.0%, respectively), and the cohesive energy is about 25% too low. For comparison, the values for a , c , and E obtained with the model of Catlow et al. (ignoring instabilities therein) are 92.4, 115.9, and 88.4% respectively, of the observed values.

MnF_2 is considered to be a more fully ionic material than TiO_2 , so it is perhaps not surprising that we have found it easier to find satisfactory potential models for this material. A reasonably good fit to the neutron scattering data for MnF_2 can be obtained with models that also fit the measured cohesive energy very well and the lattice constants exactly. The results are still not as satisfactory, however, as those for cubic crystals. In the alkali halides, for example, very good agreement with the measured phonon spectra, cohesive energies, and lattice constants can be obtained with a shell model that includes only first neighbor Born-Mayer short-range interactions.

It is clearly more difficult to construct satisfactory potential models for materials with the rutile structure than for cubic crystals like the alkali halides. As might have been expected, the problems are more severe for TiO_2 than for MnF_2 , since TiO_2 is considered to be less ionic, has larger permanent dipole moments on the negative ions, and exhibits more anisotropy in its elastic and dielectric constants. The potential models employed in recent defect studies in TiO_2 generate lattice instabilities and therefore appear to be of questionable value.

There are several ways in which the simple shell model might be changed or extended to provide a better description of the static and dynamical properties of rutile-structure insulators. Short-range pair potential forms different from the Morse plus van der Waals potentials should perhaps be explored, as has been done for some cubic crystals and also for MnF_2 . For TiO_2 , we have done some exploratory calculations in which harmonic, three-body O-Ti-O forces were added after the manner of Keating⁷ and found modest to substantial improvements in the fit to the phonon spectra, depending on how far away from good agreement we started. Finally, in the rutile structure, with the negative ions occupying sites of such low symmetry that they carry static dipole moments, it is likely that the electronic distributions around the negative ions are both distorted and deformable. Distortion of the distributions might be modeled by adding quadrupole moments or by locating two shells at different positions. The most straightforward extension of the simple shell model would be to include electronic deformation effects by going to a breathing shell model, with anisotropic deformations allowed for the negative ions.

Fig. 1.21. Calculated dispersion curves for TiO_2 vs experiment.

1. Summary of paper to be published.
2. C. R. A. Catlow et al., *Phys. Rev. B* 25, 1006 (1982).
3. H. Sawatari, E. Iguchi, and R. D. Tilley, *J. Phys. Chem. Solids* 43, 1147 (1982).
4. J. G. Traylor et al., *Phys. Rev. B* 3, 3457 (1971).
5. G. C. Cran and M. J. L. Sangster, *J. Phys. C* 7, 1937 (1974).

6. R. Almairac and C. Benoit, *J. Phys. C* 7, 2614 (1974).

7. P. N. Keating, *Phys. Rev.* 145, 637 (1966).

PARTICLE-SOLID INTERACTIONS

THE ROLE OF NONLOCAL INELASTIC ENERGY LOSSES IN SPUTTERING

M. T. Robinson

Calculations of the self-sputtering yield of polycrystalline α -uranium were reported earlier.¹ The results, obtained with the MARLOWE program, are sensitive to assumptions about the inelastic (electron excitation) energy losses of fast atomic recoils. Similar results were found by Eckstein and Biersack with the structureless medium code TRIM SP.² The extreme cases are a so-called *Local* model in which the inelastic loss is correlated with the apsis in each atomic collision and a *nonlocal* model in which the loss depends only on the particle kinetic energy and the distance along each flight segment. The two models differ mainly in that the former shows much smaller inelastic losses at low energies than does the latter. Sputtering yields calculated with the local model were twice those with the nonlocal model, independent of the incident energy, at energies above about 1 keV. The result was unexpected in that it was not realized that inelastic losses involving the very low energy recoils (some 5 to 15 eV) which dominate the sputtering process could be so significant.

An explanation of a portion of this effect can be given. The final inelastic loss in the local model occurs at the apsis of the last collision which a recoil makes before leaving the target. In the nonlocal model, a loss also occurs in the "final flight" of each recoil. Such flights involve motions mainly in the "fringing field" in front of the solid surface (Fig. 1.22). It is at least debatable if electron excitations by low-energy recoils moving in this region should be included in the calculation. To see the effect of their inclusion, we write the stopping rate of a projectile as

$$-dE/dx = kE^{1/2},$$

where k is a constant, E is the kinetic energy of a recoil, and the distance x is measured along the particle track. Integration gives

$$E_f = E_0 - kxE_0^{1/2} + k^2x^2/4, \quad (1)$$

where E_0 is the energy with which a recoil emerges from its last collision, and E_f is the energy with which it must surmount the binding energy of the solid. Only the component of the recoil motion along the target surface normal is available to overcome the binding. That is, the condition for the escape of a recoil is

$$E_f \cos^2 \theta > U_s, \quad (2)$$

where U_s is the cohesive energy of the solid. Noting from Fig. 1.22 that $x = z/\cos \theta$ and combining Eqs. (1) and (2), we obtain

$$E_0 \cos^2 \theta > U_{eff}, \quad (3)$$

where the "effective" binding energy is

$$U_{eff} = U_s + kzU_s^{1/2} + k^2z^2/4. \quad (4)$$

Note that U_{eff} is independent of the energies in the calculation. Equation (4) shows the nonlocal inelastic energy loss in the surface region of the target to play somewhat the role of an increased binding energy. The amount of the increase depends on the average distance that a particle travels from its last collision before it escapes. In the MARLOWE model, this distance is roughly the first neighbor distance in the crystal. Thus, if inelastic energy losses deeper within the target could be ignored, U_{eff}/U_0 would measure the ratio between the sputtering yields calculated with the local and the (original) nonlocal MARLOWE models. Table 1.4 shows the predictions obtained in this way for the sputtering of Ni and α -U.

To test the explanation outlined above, MARLOWE was modified so that it no longer includes nonlocal inelastic energy losses for particle flight segments near the surface of a target unless they terminate in a collision. Many of the earlier

Fig. 1.22. A schematic representation of some typical particle trajectories near a target surface.

Table 1.4. Effective binding energies for sputtering calculations in a nonlocal inelastic energy loss model.

	Nickel	α -Uranium
k (eV ^{1/2} /nm)	2.506	2.627
U_s (eV)	4.26	5.37
Mean first neighbor distance (nm)	0.2492	0.3136
U_{eff}/U_s	1.325	1.387

calculations were repeated with this modified non-local model. For the sputtering of polycrystalline Ni by 1-keV Ne^+ ions, the yield was originally calculated to be 1.095 ± 0.029 . In the modified model, this increases to 1.451 ± 0.035 . The ratio 1.325 ± 0.047 is in excellent agreement with Table 1.4. For the self-sputtering of $\alpha\text{-U}$ at 1 keV, the yield increases from 1.591 ± 0.025 to 2.157 ± 0.029 . The ratio 1.355 ± 0.029 is again in good agreement with Table 1.4. From other calculations, it appears that the ratio decreases somewhat as the incident particle energy increases.

Thus, the large difference between the original MARLOWE nonlocal model and the local model can be divided into two parts: one portion is associated with inelastic losses in the surface region and is likely to be unphysical; the other is associated with inelastic losses deeper within the target.

1. M. T. Robinson, *J. Appl. Phys.* **54**, 2650 (1983).

2. W. Eckstein and J. Biersack, *Nucl. Instrum. Methods B* **2**, 550 (1984).

ION BACKSCATTERING FROM LAYERED TARGETS¹

O. S. Den M. T. Robinson

A continuing problem of interest to the magnetically confined fusion energy program is the recycling of the hydrogen isotopes between the plasma and the walls of the confinement vessel. An important aspect of this problem is the kinetic reflection of these light, low-energy (<1 keV) particles from the walls back into the plasma. The main problem in experiments designed to measure reflection coefficients involves detection of the reflected particles, most of which are electrically neutral. For this reason little experimental work has been done at ion energies below ~ 1 keV. In this important energy region, the approach has been to refine the computational models to fit experimental data at higher energies and to rely on the calculations at the lower energies. An additional motivation for reflection studies is the recent development of a model treating the formation of H^- and D^- by particle backscattering from alkali-metal surfaces by Hiskes and Schneider². Important features of their model are the reflected fraction, energy, and angular distribution. Of special interest is reflection from layered targets, for instance, targets with an alkali-metal covering another metal substrate. To date, there have been very few studies on reflection of light particles from layered structures, which is the topic of this investigation.

The present work investigated the reflection of hydrogen atoms, whose incident energy ranged from 0.01 to 1 keV, from layered targets. The calculations used the binary collision computer program MARLOWE³ (Version 11.9), modified to treat layered target structures. Briefly, the projectile ion strikes the surface normally and is followed collision-by-collision until it leaves the surface again or until its energy falls below

a preset value (1 eV). Each collision consists of an elastic and an inelastic part. The elastic part is treated by classical scattering mechanics using the Molière⁴ approximation to the Thomas-Fermi interatomic potential with the screening lengths proposed by Firsov.^{5,6} The inelastic part is described by the (nonlocal) electronic stopping theory of Lindhard et al.⁵ The calculations were made using MARLOWE to simulate amorphous solids, and a typical run consisted of following the motions of 1000–2000 incident particles.

The targets studied were chosen to have large differences between the atomic numbers of the overlayer and the substrate in order to emphasize possible reflection differences from that of monatomic targets. For very low incident energies, the back reflection is found to be characteristic of the surface overlayer; at higher energies it becomes characteristic of the underlying substrate. The energy at which the reflection becomes characteristic of the substrate increases with increasing overlayer thickness. The reason is simply that the maximum penetration depth reached before a particle is reflected increases with increasing energy. This leads to the result that for low-Z overlayers on high-Z substrates, the reflection coefficient may actually increase with an increase in energy, at least over a limited range.

Figure 1.23 shows the effects of an overlayer of a low-Z element (Li) on a high-Z substrate (W) on the fraction R_N of H reflected. High-Z targets such as W have much larger reflection coefficients than do low-Z targets like Li at all incident energies. For the thinnest Li overlayer, the particle reflection coefficient R_N is depressed at the lowest energies, but rapidly increases to that of pure W targets as the incident energy rises. The reason is that with increasing energy it is more probable for a larger fraction of the hydrogen to be reflected from the substrate. That is, it becomes energetically feasible for an incident particle to transverse the Li overlayer, be backscattered in the substrate, and still have sufficient energy to pass again through the Li overlayer and emerge as a reflected particle. As the thickness of the Li overlayer is increased, the particle reflection coefficient remains similar to that of pure Li over a wider energy region. With increasing energy, R_N exhibits more and more of the characteristics of the reflection from pure W, indicating that the substrate is playing the dominant role in the reflection. The results of Fig. 1.23 are qualitatively similar to those of Jackson and Eckstein,⁷ who calculated the reflection of H and He from a W target with an overlayer of WO_3 .

The results for the fraction of energy R_E reflected for the case of Fig. 1.23 are quite similar to those for R_N . One difference is that for a target with a Li overlayer, R_E never reaches values as large as those of pure W targets. This may be explained by noting the additional energy lost by the reflected particles in traversing the overlayer.

The angular distributions of the reflected particles integrated over all reflected energies were found to be approximately cosine. However, the particles reflected in the highest energy groups have an under-cosine angular distribution

ORNL-DWG 83-18422

Fig. 1.23. Fraction of hydrogen R_H reflected from tungsten, lithium, and tungsten with lithium overlayers of various thicknesses as a function of the incident H ion energy. The error bars represent the standard deviation of the values plotted based on the Monte Carlo calculations.

that is more nearly isotropic than cosine. The results are similar to our previous amorphous and polycrystalline simulations of reflection from monatomic targets.⁸

1. Summary of paper: p. 171 in Proceedings of the Third International Symposium on Production and Neutralization of Negative Ions and Beams, ed. by Krsto Prelec, American Institute of Physics, New York, 1984.

2. J. R. Hiskes and P. J. Schneider, J. Nucl. Mater. 93/94, 536 (1980).

3. M. T. Robinson, Phys. Rev. B 27, 5347 (1983).

4. G. Molière, Z. Naturforsch. 22, 133 (1947).

5. O. B. Firsov, Sov. Phys. JETP 6, 534 (1958).

6. J. Lindhard, M. Scharff and H. E. Schiøtt, Mat.-Fys. Medd. 33, No. 14 (1963).

7. D. P. Jackson and W. Eckstein, Nucl. Instrum. Methods 194, 671 (1982).

8. O. S. Oen and M. T. Robinson, J. Nucl. Mater. 111/112, 789 (1982).

ION DAMAGE IN CRYSTALLINE SILICON

O. S. Oen

The use of ion implantation for the controlled introduction of dopants into semiconductors has stimulated much interest in the lattice damage introduced by the implanted ions. A detailed understanding of the nature of this damage and its spatial extent is needed in order to help develop techniques to remove it efficiently. To date, virtually all calculations on the damage or energy loss profiles have assumed the slowing down of an ion in a random or amorphous solid. An exception is the computer program MARLOWE,¹ which treats crystalline material.

In the present work MARLOWE² has been used to make some illustrative damage production calculations in crystalline silicon by various incident ions. In these calculations the Molière³ approximation to the Thomas-Fermi interatomic potential with a Firsov⁴ screening distance is used to describe the binary elastic collisions. The electronic slowing down theory of Lindhard et al.⁵ is used to account for the inelastic energy losses. In the simulation program the incident ion is followed collision-by-collision in the crystalline silicon target until it slows down to rest. In addition, any Si target atom that is set into motion when it receives an energy greater than the displacement threshold energy E_d (15 eV) is followed until its energy drops below E_d . A lattice binding energy of 0.1 eV is assumed so that the struck Si atom leaves its lattice site with nearly the full transferred energy, provided it is above E_d . The spatial position of each and every recoil target atom together with its energy is recorded when its energy drops below the displacement energy; from this information, together with the total number of vacancies produced, the number of displaced atoms as a function of depth is deduced. The net effect of incorporating this atom transport is to produce a damage profile at deeper target depths than that deduced from the energy loss profile of the incident ion alone. In calculating ion irradiation damage in crystalline media, it is important to realize that ion channeling may affect the results. In channeling the motion of the ion is constrained to move in the more open avenues of the crystal, thus greatly reducing the probability of violent collisions that produce cascade damage. Effects of channeling on damage production have been known for a long time since they were first predicted⁶ and experimentally confirmed.⁷

Figure 1.24 shows the elastically deposited energy as a function of penetration depth for a 100-keV Bi ion incident at a tilt angle of 7° (about [110] axis) from the normal of a (110) silicon surface. The dashed curve gives the profile of the total elastic energy transferred directly to the Si lattice atoms by the incident Bi ion. The solid curve gives the elastic deposited energy, taking the transport effect of the knocked-on Si atoms into account. Because these Si atoms lose energy inelastically, the area under the solid curve is less than that under the dashed curve. As can be seen from the figure the

Fig. 1.24. The elastically deposited energy as a function of penetration depth for a 100-keV Bi ion into Si.

atom transport of energy is twofold: first, there is a large reduction in the energy deposited in the surface region; second, there is an enhancement of the trailing edge of the energy deposition profile. Although the tilt angle of 7° in Fig. 1.24 was chosen to minimize possible channeling effects (a critical axial channeling angle of 4.5° was estimated from Lindard's channeling theory⁸), some channeling effects are seen by the presence of the long tail in the energy deposition.

Figure 1.25 shows how the number of displaced Si atoms depends on the incident Bi beam direction in a (110) single crystal. Curve 1 is the same as the case discussed above. In each of the three curves the azimuthal angle ϕ (measured from [110]) was chosen to minimize channeling from any major planes. In curve 2, $\theta = 3^\circ$ and $\phi = 15^\circ$; and in curve 3, $\theta = 0^\circ$ and $\phi = 0^\circ$. A beam divergence of 0.25° was used in curve 2, and one of 0.50° in curve 3. It is seen that channeling of the incident ions greatly reduces the overall damage. The

Fig. 1.25. The number of displaced atoms vs penetration depth in Si produced by a 100-keV Bi ion.

effects are twofold on the damage profile: first, there is a large reduction of the central damage peak; second, there is a component of the damage profile that extends more deeply into the target. There are several reasons why damage is produced even when the beam is incident within the critical channeling angle. First, some ions never become channeled since they undergo large deflection angles in collisions with surface atoms. Second, dechanneling mechanisms, such as thermal vibrations, cause some channeled ions to dechannel before they slow down to rest. Third, for systems of large projectile-target mass ratios it is possible for the projectile to produce displacements and still remain channeled. For instance, a 10-keV Bi ion undergoes a laboratory deflection of less than one degree in transferring an energy of 15 eV to a Si atom. Both the second and third reasons enable the creation of damage at much greater target depths than in a random target assemblage because of the greater range of channeled ions.

1. M. T. Robinson, *Phys. Rev. B* 27, 5347 (1983).
2. M. T. Robinson, "User's Guide to MARLOWE" (Version 12), 1984 (unpublished). This guide describes a version of the program which is available from the National Energy Software Center, Argonne National Laboratory, Argonne, Illinois 60439, and from the Radiation Shielding Information Center, Oak Ridge National Laboratory, P. O. Box X, Oak Ridge, Tennessee 37831.
3. G. Molière, *Z. Naturforsch.* 2a, 133 (1947).
4. O. B. Firsov, *Zh. Eksperim. Teor. Fiz.* 33, 696 (1957) [*Sov. Phys. JETP* 6, 534 (1958)].
5. J. Lindhard, M. Scharff, and H. E. Schiøtt, *K. Dan. Vidensk. Selsk., Mat.-Fys. Medd.* 33, No. 14 (1963).
6. O. S. Oen and M. T. Robinson, *Appl. Phys. Lett.* 2, 83 (1963).
7. T. S. Noggle and O. S. Oen, *Phys. Rev. Lett.* 16, 395 (1966).
8. J. Lindhard, *K. Dan. Vidensk. Selsk., Mat.-Fys. Medd.* 35, No. 14 (1965).

ION CHANNELING IN ELASTICALLY STRAINED SUPERLATTICES¹

J. H. Barrett

In the last few years ion channeling and back-scattering have been used in a number of studies of semiconductor superlattices. These studies, as well as many others by other methods, resulted from the general interest in these superlattice materials because of their potential use in optical and electronic devices. Elastic strains within the layers have been shown to be the source of the unusual ion dechanneling observed in several semiconductor superlattice materials. These strains occur because of the slight mismatch between the lattice constants of the two materials and cause the rows and planes of atoms in the crystal that are inclined to the surface normal to have small directional misalignments at the

interfaces between the layers. The effects of these misalignments have been studied by computer simulations of ion trajectories in the crystal and have been shown to account in a reasonable manner for the observed dechanneling behavior. Several ways have been tried or suggested for using ion channeling and backscattering to measure the amount of misalignment and are as follows.

(1) Measured rates of dechanneling could be compared with rates calculated by computer simulation.² Values obtained in this way are about 15% too large, which probably indicates the accuracy of this method.

(2) A detailed comparison might be made between measured and calculated angular and depth dependences of the backscattering yield in the near-surface region. This has recently been done for axial channeling,³ and the accuracy is again about 15%. Planar channeling used in this way has been studied by computer simulation and might yield better results.

(3) For superlattices with layers very thin compared with the wavelengths of the ions in the layers, the direction for best channeling several layers deep in the crystal would be the average of the channeling directions in the two types of layers. Although attempts have been made to use this technique,⁴ it is uncertain that the layers were sufficiently thin.

(4) As the ion energy is varied, the wavelength of ions in a planar channel can be varied. In experiments of this kind, it was observed that the dechanneling effect was a maximum when the half-wavelength of the ions was matched to the path-length through a layer.⁵ This effect can be used to estimate the misalignment, but approximations in the estimation procedure leave the accuracy of this method uncertain.

(5) The expected amount of misalignment in the absence of dislocations can be calculated readily from elasticity theory. The existence of this expected amount of misalignment could be assessed by using channeling to look for the presence or absence of misfit dislocations, which might relieve part of the misfit strain. In this case one would want to compare channeling along the axis parallel to the growth direction in the superlattice to the channeling along the same axis in a single crystal of one of the layer materials. This method could only set an upper limit on the dislocation density and so give only a lower limit on the amount of misalignment.

Each of these procedures has promise, but each needs further work to establish its accuracy and range of applicability. Most of these methods will tend to be most sensitive to the strains in the first few layers at the surface, in contrast to x-ray methods, which sense the average strain throughout the entire superlattice.

1. Summary of paper: p. 465 in *Thin Films and Interfaces II*, ed. by J. E. E. Baglin, D. R. Campbell, and W. K. Chu, North-Holland, New York, 1984.

2. John H. Barrett, *Phys. Rev. B* **28**, 2328 (1983).

3. C. K. Pan et al., "Structure Study of a GaSb/AlSb Strained Layer Superlattice," this report.

4. S. T. Picraux et al., *Appl. Phys. Lett.* **43**, 1020 (1983).

5. W. K. Chu et al., *Phys. Rev. Lett.* **52**, 125 (1984).

STRUCTURE STUDY OF A GaSb/AlSb STRAINED LAYER SUPERLATTICE¹

C. K. Pan² D. C. Zheng²
T. G. Finstad² W. K. Chu²
V. S. Speriosu³ M.-A. Nicolet³
J. H. Barrett

Due to the lattice mismatch, a superlattice consisting of alternating layers of GaSb and AlSb will be strained. The specimen used in the present study was grown by molecular beam epitaxy on a GaSb [100] substrate and had ten 30-nm thick layers of each material. For layers of this thickness, the strain is expected to be purely elastic with no misfit dislocations. Because of the substrate's thickness, it and the GaSb layers are unstrained, and the strain in the AlSb layers is easily calculable from elasticity theory. The differing strains will cause crystallographic axes inclined to the growth direction to have slightly different directions in the two types of layers. For [110] this difference or "kink angle" is calculated to be 0.374°. Measurements to determine this angle were performed by ion channeling and backscattering and by X rays.

The ion scattering measurements for the first four layers are shown in Fig. 1.26 along with results calculated using a previously described⁴ computer simulation program incorporating special features to describe the superlattice properties.

Fig. 1.26. Angular scan profiles from backscattering of 1.76-MeV He ions from a GaSb/AlSb superlattice (a) for the experimental measurements and (b) for computer simulations with a kink angle of 0.37°. The yields have been normalized to those from a random direction. The tilt angle is measured from the [110] direction, and the scan is in a plane that makes an angle of 14° with the (001) plane. The vertical dashed line in (a) is the limiting center position for layers much deeper in the specimen.

For each of the four curves in each part of Fig. 1.26 we found an angular position termed the direction or angle for "best channeling" for a given depth. It was defined as the mid-position between the intercept of half heights of the left- and right-hand portions of the angular yield curve, respectively. This parameter serves to quantify the observed effect. The direction for "best channeling" shifts back and forth from layer to layer, which we attribute to the periodic changes of the [110] direction in the superlattice structure. The shoulders of the simulated scan profiles in Fig. 1.26(b) reproduce in great detail the shoulders of the experimental ones in Fig. 1.26(a), giving strong support to use of the simulations to make quantitative inferences from the measurements. The most important difference between the experimental and calculated curves in Fig. 1.26 is that the difference between the angles for "best channeling" in the first and second layers is less for the experimental curves than for the calculated ones. From the results in Fig. 1.26 together with similar simulation results for kink angles of 0.17° and 0.24° , we concluded that the kink angle corresponding to the scan in Fig. 1.26(a) was $0.28^\circ \pm 0.04^\circ$.

X-ray measurements were performed on the specimen used in the ion scattering measurements. The experimental procedure and data analysis were by standard methods.⁵ Data were collected on the spot where the ion scattering measurements were made and also on an unirradiated spot. The kink angle determined for the unirradiated spot was $0.365^\circ \pm 0.004^\circ$, and that for the irradiated spot was $\sim 0.17^\circ$.

The x-ray value for the kink angle on the unirradiated spot is in excellent agreement with the value from elasticity theory. The lower x-ray value on the irradiated spot is a clear indication that radiation damage relieved about half of the strain, presumably by agglomeration of defects into misfit dislocations. The beam dose required for alignment of the specimen using the ion beam was much larger than the dose during the angular scan so that the strain should not have changed appreciably during the scan. The specimen was later used in other ion scattering measurements, which gave it a further large dose before x-ray measurements were made. So it is quite reasonable that the strain during the angular scan shown in Fig. 1.26(a) would be intermediate between the unirradiated value and the final irradiated value.

Radiation damage is clearly an important factor in using ion beams to make measurements on semiconductor superlattices. This also means that it may be possible to use ion beams to modify the strains in these materials. X rays provide very accurate measurements of the strains, while ion scattering provides measurements of less accuracy. The accuracy of the ion scattering measurements can possibly be improved if care is taken to avoid radiation damage. Also, ion scattering will measure the strain in the first few layers, while X rays will measure an average strain over the whole superlattice structure.

1. Summary of paper: Physical Review B (in press).

2. University of North Carolina, Chapel Hill, N.C.

3. California Institute of Technology, Pasadena, Calif.

4. John H. Barrett, Phys. Rev. B **28**, 2328 (1983).

5. V. S. Speriosu and C. H. Wilts, J. Appl. Phys. **54**, 3325 (1983).

LASER-SOLID INTERACTIONS AND RAPID SOLIDIFICATION

MULTILAYER INTERFACIAL MODEL OF CRYSTAL GROWTH AND NONEQUILIBRIUM DOPANT SEGREGATION

R. F. Wood J. F. Cooke
T. Kaplan M. Mostoller

The elementary phenomenological theory of crystal growth ignores the structure of the liquid-solid interface, and therefore all of the interface-related quantities appearing in the theory must be considered as having been averaged in some sense over the configurations through which the interface passes. There have been several developments extending the kinetic rate approach on which the classical theory is based to multilayer interfacial regions. However, until the advent of pulsed-laser annealing and the well-controlled, one-dimensional melting and resolidification obtained with it, there has been little impetus to develop and test multilayer models. We are in the process of developing a model for nonequilibrium crystal growth based on a multilayer treatment of the interface similar to one proposed by Fletcher.¹

Fletcher employed a model in which the liquid is viewed essentially as a solid with a large concentration of defects. This concept could be viewed as a weakness of the model (as Fletcher recognized), but in fact there is no entirely satisfactory theory of the liquid state. Moreover, the exact description of the liquid is not crucial to the conceptual foundation of the model; for example, the concentration of imperfect bonds, a disorder parameter, etc., could be introduced instead of the "concentration of defects." In any case, Fletcher wrote an expression for the free energy of the bulk material in terms of the concentration of defects C , the defect formation energy ϵ , and the temperature. Because of the large concentration of defects present in the liquid, ϵ is itself a function of C [i.e., $\epsilon = \epsilon(C)$]. For particular sets of values of the quantities appearing in the expression for the free energy, Fletcher showed that the solid and liquid could coexist at some "melting" temperature T_m . The defect concentration in the solid was $\sim 10^{-11}$, and in the liquid it was ~ 0.5 .

Next, an expression for the free energy of material containing a planar, layered, interfacial region was minimized to obtain the variation of the defect concentration across the equilibrium (stationary) interface. The extent to which the defect formation energy in a given layer depended on C determined whether the interface was diffuse or sharp.

With the defect structure of the equilibrium interface fixed, Fletcher allowed the interface to sweep through the solid at a given velocity and solved the set of simultaneous differential equations for the defect concentration in the various layers. For example, for the N th layer the time dependence of the concentration is given by

$$\begin{aligned} \frac{\partial C_N}{\partial t} = & -K_N(C_N C_N - C_i C_i) - C_N[v(N, N-1) \\ & + v(N, N+1)] + C_{N-1}v(N-1, N) \\ & + C_{N+1}v(N+1, N). \end{aligned} \quad (1)$$

The term quadratic in the C 's is an intralayer defect annihilation term, and K is the kinetic rate coefficient for this process. The other terms account for diffusive jumps between the N th layer and its adjacent neighbors, $N-1$ and $N+1$, with rates determined by the v 's. When the set of differential equations is solved for times long enough for steady state to be established, it is found that the concentration of defects in the solid depends on the velocity of the interface as expected.

This type of approach can be extended to the impurity segregation problem by writing an equation similar to Eq. (1) for the two component system. For dilute concentrations of the impurity and for solidification velocities which are not great enough to produce significant defect concentrations in the solid, the set of equations can be effectively decoupled. An equation of the form

$$\begin{aligned} \frac{\partial C_{d,N}}{\partial t} = & -C_{d,N}[v_d(N, N-1) + v_d(N, N+1)] \\ & + C_{d,N-1}v_d(N-1, N) + C_{d,N+1}v_d(N+1, N) \end{aligned} \quad (2)$$

can then be written for $C_{d,N}$, the dopant concentration in the N th layer. This equation is, of course, very similar to Eq. (1) except that there is no "dopant annihilation" term. The rate constant $v_d(N, N-1)$ can be expressed in activated form as

$$v_d(N, N-1) = A(N, N-1) \exp[-U_d(N, N-1)/kT], \quad (3)$$

in which $U_d(N, N-1)$ is the activation energy for the jump of a dopant atom from the N to the $N-1$ layer. This activation energy will depend strongly on where the N and $N-1$ layers are, relative to the interface region. If both these layers are in the liquid, $U_d(N, N-1)$ should be closely related to the activation energy for diffusion in the liquid, and if they are in the solid, $U_d(N, N-1)$ should be related to the activation energy for diffusion in the solid. In the interface region the activation energies vary in some manner between these two limits.

Calculations based on the above approach demonstrate that the observed rapid increase in

the interfacial segregation coefficient k_i with interface velocity v for groups III and V dopants in silicon can be readily explained. We intend first to refine the calculations in a number of ways and then to relate the v dependence of k_i to the structure of the interfacial region. We hope also to demonstrate how a multilayer treatment of the interface can give rise to an effective v -dependent activation energy² in a simpler, phenomenological treatment in which the explicit structure of the interface is neglected.

1. M. H. Fletcher, *J. Cryst. Growth* **35**, 39 (1976).
2. R. F. Wood, *Appl. Phys. Lett.* **37**, 302 (1980); *Phys. Rev. B* **25**, 2786 (1982).

BULK NUCLEATION AND AMORPHOUS PHASE FORMATION IN HIGHLY UNDERCOOLED MOLTEN SILICON¹

R. F. Wood D. H. Lowndes
J. Narayan

Rapid solidification of molten materials has been a topic of long-standing interest in materials science and metallurgy. Recent work on the pulsed laser annealing of semiconductors has refocused attention on the subject. For example, the laser-induced conversion of crystalline Si (c-Si) to amorphous Si (a-Si) by way of ultrarapid melting and solidification has been widely studied. The conventional thermodynamic interpretation of this phenomenon apparently requires undercoolings of 200–400 deg in liquid Si (l-Si) for the $l \rightarrow a$ phase transition to occur. However, recent work^{2–4} in which highly undercooled l -Si was formed by pulsed laser melting of a-Si layers on c-Si substrates bears on this interpretation because it indicates that bulk nucleation occurs in the undercooled liquid at temperatures above that of the $l \rightarrow a$ transition. In this paper we demonstrate by model calculations that the release of latent heat by nucleation and growth during melting is essential in determining the observed melt-front penetration.

We first summarize the transmission electron microscopy (TEM) results^{2–4} for laser-irradiated a-Si layers 0.1–0.5- μ m thick formed in c-Si by self-ion implantation. For pulse energy densities E_L slightly less than 0.2 J/cm², the surface melts (as indicated by a jump in reflectivity). A typical TEM micrograph for $E_L = 0.2$ J/cm² shows a region of fine-grained (FG) polycrystalline Si (p-Si) at the surface, followed successively by a-Si, the a-c interface, and the c-Si substrate. As E_L is increased, a layer of large-grained (LG) polycrystalline Si (p-Si) is found at the surface, followed in order by the FG p-Si, a-Si, and c-Si. Further increases in E_L result in the growth of the LG p-Si region, displacement of the FG region toward the a-c interface, and reduction in the thickness of the a-Si layer. At increasingly higher values of E_L , both the a-Si and FG regions disappear, and finally even the LG p-Si region no longer appears when epitaxial regrowth is realized. The grains of the FG p-Si are randomly oriented and equiaxed, indicating that there is no preferred direction of crystal growth during

the formula . . . this region. This behavior is strongly . . . of bulk nucleation; insight into its origins can be gained from the calculations described next.

Finite-difference calculations were modified to simulate nucleation effects under pulsed laser irradiation conditions, as described in Ref. 2. In the calculations, the melting temperatures of a- and c-Si are denoted by T_a and T_c , respectively, the corresponding latent heats by L_a and L_c , and the thermal conductivities of c-, a-, and ϵ -Si by K_c , K_a , and K_ϵ , respectively; the nucleation temperature is denoted by T_n . Typical results of the calculations are illustrated in Figs. 1.27 and 1.28 for a 0.10- μ m a-layer. Figure 1.27 shows temperature profiles at the times when the melt front reaches its maximum penetrations. T_n was varied to obtain approximate agreement with the TEM results for the widths of the FG, LG, and a-Si regions; Fig. 1.27 shows $T_n = 1210^\circ\text{C}$, but

Fig. 1.27. Temperature vs depth at maximum melt-front penetration.

Fig. 1.28. Melt-front profiles for different E_L . The cross-hatching indicates the absence of a well-defined melt front.

this value depends on the assumed value of T_a . Figure 1.27 indicates that the temperature of the ϵ -Si for 0.2 J/cm² does not rise above T_n , so that only FG p-Si is expected at the surface (in agreement with TEM), followed by the remainder of the a-Si. For 0.3 J/cm², in the region nearest the surface, $T > T_n$ and a thin region of LG material is expected to grow from the underlying, bulk-nucleated FG material. As E_L increases, the LG region grows in size while the FG region shrinks until at ~ 0.6 J/cm² only ~ 200 Å of FG p-Si remains; for $E_L > 0.8$ J/cm² the melt front penetrates completely through the a-Si. The kink in each of the curves at ~ 0.10 μ m occurs because $T_a < T_c$ and $L_a < L_c$; the melt front pauses until enough energy is absorbed for it to penetrate the a-c interface. For $0.6 \leq E_L \leq 0.8$ J/cm², the front contacts the interface but does not penetrate it. For $E_L \leq 0.6$ J/cm², the temperature of part or all of the ϵ -Si is $< T_n$, and nucleation occurs in an extended region for which no well-defined melt front exists, as indicated schematically by the cross-hatching on Fig. 1.28.

Initial calculations for 0.40- μ m a-Si layers gave melt-front penetrations much less than the measured combined thickness of the FG and LG regions. This seemed to imply that bulk nucleation and grain growth occurred before the melt front reached its maximum penetration. We might expect (and the calculations confirmed) this to be an important effect for thick layers but not for 0.10- μ m layers. Bulk nucleation during melting was simulated by allowing an increment ΔE_n of latent heat to be released during melt-front penetration. ΔE_n was estimated from the relationship $\Delta E_n = F \rho L_c X_m$, where X_m is the measured maximum penetration at a given E_L , ρ is the density, and F is a factor interpreted as the fraction of ϵ -Si that solidifies before the melt front reaches X_m . To be physically meaningful, F must be < 1 , and we found $F = 0.5$ – 0.6 for most E_L . Moreover, the temperature profiles produced when X_m was reached again indicated that the widths of the LG and FG p-Si regions extracted from the calculations were in good agreement with the TEM values if $T_n = 1210^\circ\text{C}$. The model calculations clearly indicate that molten material can exist in the interior of the sample after the surface has resolidified.

1. Summary of papers: *Appl. Phys. Lett.* 44, 770 (1984); *Mat. Res. Soc. Symp. Proc.* 23, 141 (1984).
2. D. H. Lowndes, R. F. Wood, and J. Narayan, *Phys. Rev. Lett.* 52, 561 (1984).
3. D. H. Lowndes et al., *Mat. Res. Soc. Symp. Proc.* 23, 99 (1984).
4. J. Narayan and C. W. White, *Appl. Phys. Lett.* 44, 35 (1984).

MODELING OF SOLIDIFICATION PROCESSES IN HIGHLY UNDERCOOLED SILICON AND GERMANIUM

R. F. Wood A. Geistl
A. Solomon¹ G. E. Giles²

It is now reasonably well established that T_a , the melting temperature of amorphous (a) silicon,

is approximately 200 ± 100 deg less than T_c , the melting temperature of crystalline (c) silicon. Therefore, when a-Si is melted by pulsed laser irradiation, highly undercooled liquid silicon can be formed. Also, after the pulsed laser melting of c-Si under some conditions, the kinetic rate processes at the liquid-solid interface may become so sluggish compared with the heat-flow rate that the liquid undercools by hundreds of degrees before solidification occurs. Processes in which large undercoolings of the liquid (or superheating of the solid) occur before the phase change takes place are difficult to treat by the mathematical modeling techniques developed for heat conduction problems in which undercooling does not play a significant role. In order to treat such processes more adequately, a computer program based on an enthalpy formulation of the heat flow problem has been developed and tested.

The computer program is based on the heat conduction equation written in finite-difference form as

$$\rho \Delta \tau^{-1} (h_i^{n+1} - h_i^n) = \frac{1}{2\Delta x^2} [(K_{i+1} + K_i)(T_{i+1}^n - T_i^n) + (K_i + K_{i-1})(T_{i-1}^n - T_i^n)] + S_i^n.$$

Here, h_i^n is the enthalpy of the i th cell at the n th time interval after initiation of the laser pulse. The density of the material ρ is assumed to be independent of temperature and phase. K_i is the thermal conductivity in the i th cell; it can depend on the temperature T_i and the phase of the material. S_i^n is the energy from the laser pulse deposited in the i th cell of width Δx during the n th time interval of duration $\Delta \tau$. Behavior of the material in each finite-difference cell is determined by the above equation, the boundary conditions assumed for the problem, and a state array.

The state array specifies the conditions under which the material in a given cell can make a transition to another phase or to another form. For example, the possible phases are liquid, crystalline, and amorphous, but the crystalline phase is subdivided into single-crystal, large-grained polycrystalline, and fine-grained polycrystalline forms. Moreover, cells can contain mixtures of the various phases called "slush" or "mush." A transition of material from one phase or form to another in a given cell depends on such parameters as enthalpy content of the cell, time that the temperature of the cell has been at or below a specified temperature (this feature can be used to simulate bulk nucleation), the phases and forms of the materials in each adjacent cell, and the thermal and optical properties of the various phases. In addition to being able to treat the various phases and forms of any given material, the program can handle up to ten different materials in a one-dimensional, layered configuration. Thus far, the new program has been used most extensively to investigate the solidification dynamics of a-Si melted by excimer and ruby laser pulses.

Recently available experimental data² and computer simulations⁴ using modified versions of the

HEATING5 program indicate that the solidification of undercooled molten silicon prepared by pulsed laser melting of a-Si is a complex process. Time-resolved reflectivity and electrical conductivity measurements and the calculations provide information about surface melting and suggest the presence of buried molten layers. Transmission electron micrographs show the formation of both fine- and large-grained polycrystalline regions if the melt front does not penetrate through the a-Si layer. The results of calculations with the new program, which has been given the name LASER-8, show all of the general features seen in the experimental results. In fact, the calculations reveal a remarkable variety of solidification behavior. For low-energy pulses, a molten layer continues to penetrate into the sample after the surface has solidified. For more energetic pulses, a solidification front recedes to the surface while phase fronts bounding undercooled liquid and "slush" layers several hundred angstroms thick continue to penetrate into the solid.

1. Engineering Physics and Mathematics Division, ORNL.
2. Computing and Telecommunications Division, Martin Marietta Energy Systems, Inc.
3. D. H. Lowndes, R. F. Wood, and J. Narayan, *Phys. Rev. Lett.* **52**, 561 (1984).
4. R. F. Wood, D. H. Lowndes, and J. Narayan, *Appl. Phys. Lett.* **44**, 770 (1984).

LIFETIME OF AN ELECTRON-HOLE PLASMA OF SILICON IN THE PICOSECOND RANGE¹

M. Rasolt H. Kurz²

The temporal and spatial evolution of the e-h plasma in Si, during and after excitation with intense picosecond laser pulses, is central to understanding the pulsed-laser annealing mechanism and, in particular, to the energy transfer from the e-h plasma to the lattice. Reflectivity and transmission measurements in the ps and fs range, which contain the signature of the e-h plasma, have aroused intense interest in several recent studies.³ Here we present such measurements in the ps range, which clearly show loss of the e-h plasmon signature, at roughly 15 ps after the pump laser pulse, for densities (equivalently plasma frequencies ω_p) comparable to or greater than the indirect gap energy $E_g(T)$. We attribute this plasmon loss to a new recombination channel with a lifetime $\tau = 100$ fs.

Plasma resonances are easily observed in silicon excited with 20-ps 0.532- μ m pulses at a probing frequency of $\omega_0 = 0.4$ eV ($\lambda = 2.8$ μ m). As shown in Fig. 1.29, for a time delay $t = 15$ ps between pump and probe pulse, the reflectivity of bulk silicon drops from the quiescent solid state value to a minimum with increasing fluence $F(2\omega)$. Above $F(2\omega) = 30$ mJ/cm² the reflectivity starts to rise up to 60%, which indicates the buildup of the plasmon density sufficient to support plasma oscillations in resonance with the probing frequency. At higher fluence levels one might expect an observable plasma resonance at higher frequencies. Experimentally, however, the

Fig. 1.29. Bulk reflectivity of silicon, at laser pulses $t = 15$ ps and different wavelengths, vs fluence of the excitation pulse at $0.532 \mu\text{m}$.

reflectivity never increases over its initial value at the probing frequency of 1.17 eV , which corresponds to a $1.06\text{-}\mu\text{m}$ wavelength. Apparently, it is impossible to raise the carrier density and the plasma frequency to this level, which is also comparable to the band gap.

To interpret the results of Fig. 1.29, we solved Eqs. (1) and (2) below for the correct density $n(x,t)$ and temperature $T(x,t)$:

$$\frac{\partial T(x,t)}{\partial t} = \frac{\partial}{\partial x} \left[D_{th}(T) \frac{\partial T}{\partial x} \right] + S(x,T,t), \quad (1)$$

$$\frac{\partial j_m(x,t)}{\partial x} + \frac{\partial n(x,t)}{\partial t} = G(x,T,t) - \gamma(n)n^3, \quad (2a)$$

where

$$j_m(x,t) = -D_a \left[\frac{\partial n}{\partial x} + \frac{n}{2k_B T} \frac{\partial E_i}{\partial x} + \frac{n(p+1)}{T} \frac{\partial T}{\partial x} \right], \quad (2b)$$

D_{th} is the thermal diffusivity, S the heating source, G the generation rate of e-h, $\gamma(n)$ the Auger recombination, j_m the e-h pair current, D_a the ambipolar diffusion current density, and E_i the indirect band gap.

We next constructed a Drude-like approximation for the transverse dielectric response $\kappa_T(n(x,t), T(x,t), \omega_0)$ for a probe frequency ω_0 :

$$\begin{aligned} \kappa_T &= \epsilon_0(n(x,t), T(x,t), \omega_0) \\ &= \frac{4\pi n(x,t)e^2(1/m_{oe} + 1/m_{oh})}{\omega_0(\omega_0 + i/\tau_{PL})} + \epsilon'_0(\omega_0) \\ &= \epsilon_0 \left[1 - \frac{\omega_p^2(x,t)}{\omega_0(\omega_0 + i/\tau_{PL})} \right] + \epsilon'_0(\omega_0), \quad (3) \end{aligned}$$

where $\epsilon_0(\omega_0)$ is the virgin Si dielectric response, the second term is the e-h plasma contribution

with the lifetime τ_{PL} of the carriers,⁵ $\epsilon'_0(\omega_0)$ is the additional intervalley correction from the e-h carriers, and m_{oe} and m_{oh} are the electron and hole effective optical masses.

Equation (3) provides three possible interpretations of Fig. 1.29:

1. The density $n(x,t)$ never reaches the value $\omega_p[n(x,t)] = 1 \text{ eV}$ at $t = 15$ ps?
2. $\epsilon'_0(\omega)$ adds a major modification to the Drude form at $\omega_0 \geq 1 \text{ eV}$?
3. m_{oe} and m_{oh} change significantly at densities $\omega_p[n(x,t)] \geq 1 \text{ eV}$?

Concerning (1), the Auger recombination $\gamma(n)$ [in Eq. (2a)] plays a crucial role in controlling the magnitude of $n(x,t)$. If we take the most favorable⁶ value of $\gamma(n) = 3.8 \times 10^{-31} \text{ cm}^6/\text{s}$, we get for the Auger recombination lifetime at densities of $10^{21}/\text{cm}^3$ (which corresponds to $\omega_p = 1 \text{ eV}$ in Si) that $\tau = 1/[\gamma(n)n^2]$ or $\tau = 3 \times 10^{-12} \text{ s}$. With reasonable values for D_a and D_{th} we cannot account for the full gamut of probe frequencies ω_0 presented in Fig. 1.29. More precisely, Eqs. (1) and (2) give an excellent description of Fig. 1.29 at $\lambda = 2.8 \mu\text{m}$, but for probing wavelengths $\lambda < 1.9 \mu\text{m}$, Eqs. (1)-(3) develop obvious inconsistencies.

Electron-hole recombinations in Si can conserve energy and momentum only via three (or more) particle interactions assisted by a phonon.⁷ When the density, however, reaches $\omega_p[n(x)] \geq E_i$, a new recombination channel opens up where e-h recombination assisted by a plasmon and a phonon is possible.⁸

We evaluated this new channel, whose recombination self energies (or equivalently lifetimes), are shown in the insert of Fig. 1.30, to get lifetimes of the order of 100 fs. When such a lifetime is inserted in Eq. (2), we find a compelling

Fig. 1.30. The inserts represent the self energy of an electron due to scattering to a hole assisted by a phonon (wavy line) and a plasmon (dashed line). The plots give the inverse of the lifetime of an electron in the conduction band from the bottom of the conduction band $p = 0$ to the Fermi momentum $p = p_{F,e}$, for three electron densities n_e . The plasmon frequencies corresponding to these densities are $\omega_p = 0.95, 1.1$, and 1.5 eV .

interpretation of Fig. 1.29: $\hbar\omega_{up} < 0.92$ eV sensible choices for $\gamma(n)$, D_a , etc., yield a satisfactory description for our experimental observations. For $\omega_p > 0.92$ eV an additional term $n/\tau(n)(\tau = 10^{-13}$ s) must be added, which does not allow $n(x,t)$ to reach its expected values; therefore, when $t = 15$ ps, the plasma signature disappears for $\lambda < 1.06$ μ m (in agreement with the experimental observations of Fig. 1.29).

1. Summary of paper: Physical Review Letters (in press).
2. Harvard University, Cambridge, Mass.
3. J. M. Liu, H. Kurz, and H. Bloembergen, Appl. Phys. Lett. 41, 643 (1982); D. von der Linde and M. Fabricius, Appl. Phys. Lett. 41, 991 (1982); L. A. Lompré et al., Appl. Phys. Lett. 43, 168 (1983); C. V. Shank, R. Yen, and C. Hirshman, Phys. Rev. Lett. 50, 454 (1983).
4. H. Kurz, L. A. Lompré, and J. M. Liu, J. de Physique 44, C5-23 (1983).
5. τ_{pl} includes e-h scattering and intraband e-h phonon scattering. Note that unlike a single component plasma, the current of the e-h plasma does not commute with H . This gives a finite e-h scattering lifetime (roughly 10^{-15} – 10^{-16} s).
6. This value of $\gamma(n)$ is interpreted at low carrier densities. For our n it is expected to be screened significantly and $\tau(n)$ significantly longer.
7. W. Lochmann and A. Haug, Solid State Commun. 35, 553 (1980).
8. Plasmon-assisted recombination, without a phonon, has been considered by P. A. Wolff, Phys. Rev. Lett. 24, 266 (1970).

ELECTRON-HOLE PLASMA FORMATION IN SEMICONDUCTORS DUE TO THE ABSORPTION OF PULSED CO₂ LASER LIGHT¹

R. B. James²

In many semiconductors the absorption of light with a frequency less than the band gap but greater than the lattice absorption region is dominated by free-carrier transitions. At high light intensities, the absorption associated with the free carriers becomes a function of the light intensity due to a modification in the carrier distribution. This research was initiated to calculate the nonequilibrium carrier distribution of several semiconductors due to the presence of high-intensity optical excitation in the 9–11- μ m region.

In the calculation, the carrier-carrier collisions are considered to be sufficiently frequent for the distribution to be described by a carrier temperature. The carrier temperature is calculated by balancing the rate at which the carriers receive energy from the laser light and the rate at which the carriers lose energy to the lattice by scattering events. For low light intensities, the carrier temperature is approximately equal to the lattice temperature, but for sufficiently high intensities, the carrier temperature can greatly exceed the lattice temperature. The average energy of the carriers will continue to increase with intensity up to an avalanche break-

down of the sample. These "hot electron effects" have been observed in several experiments.

The absorption of high-intensity pulsed CO₂ laser light in several semiconductors is divided into two categories, the absorption by free electrons and the absorption by free holes. The first half of this work presents calculated results for n-type semiconductors, where the absorption is dominated by free electrons, and the second half presents results for p-type semiconductors, where the absorption is dominated by free holes.

In the n-type semiconductors considered, the absorption is dominated by intraconduction-band transitions. The transitions are indirect and require the cooperation of a third particle (such as a phonon or impurity) to conserve crystal momentum.

A simplified calculation of the intensity dependence of the electron distribution in n-type materials is presented here. It is assumed that the concentration of carriers exceeds some critical concentration for which the intercarrier collisions can maintain a Maxwell-Boltzmann distribution, thus allowing the hot electron distribution to be described by a carrier temperature T_e . The impact ionization thresholds found here differ by only a factor of 2 or less from the intensity threshold values obtained in previous treatments. This is important in that the calculational approach presented in this paper is considerably simpler than solving the set of rate equations constructed in an earlier paper.³

Calculated results for the carrier temperature have also been obtained for several p-type semiconductors. For most p-type semiconductors, the main contribution to the free-hole absorption at low light intensities is from intervalence-band transitions, where a free-hole in the heavy- or light-hole band makes a direct transition to another band in the valence-band structure. In addition, there exist some indirect intravalence-band transitions, but for hole temperatures (T_h) less than 300 K, it is generally much smaller than the direct intervalence-band transitions. For T_h much greater than room temperature, the indirect intravalence-band cross section can be comparable to or larger than the direct intervalence-band cross section. Values for the impact ionization intensity threshold by highly energetic hole carriers are found to be comparable to or larger than the thresholds for impact ionization by hot electrons.

1. Summary of paper to be published.
2. Present address: Sandia National Laboratories, Livermore, Calif.
3. R. B. James and D. L. Smith, IEEE J. Quantum Electron. QE-18, 1841 (1982).

OPTICALLY INDUCED INTERVALENCE-BAND TRANSITIONS IN GERMANIUM BY THE ABSORPTION OF 1.06- μ m PICOSECOND PULSES¹

R. B. James²

The optical properties of high-density electron-hole plasmas in germanium have been extensively investigated both experimentally and theoretically

in the recent past. Results of studies of the time-resolved transmission of picosecond optical pulses through germanium by the excite-and-probe technique have been reported by several groups. Such measurements give information about the ultrafast dynamics of the high-density electron-hole plasma formed by the absorption of the excitation pulse.

Several interesting effects associated with the presence of the nonequilibrium electron-hole plasma have been observed in the transmission experiments. For example, the transmission of a probe pulse (delayed 62 ps after the 7-ps excite pulse) has been measured as a function of the energy density of the excite pulse, and three distinct regions have been observed.³ For excite pulse-energy densities less than about 0.9 mJ/cm², the transmission of the probe pulse is independent of the excite pulse. For excite pulse-energy densities in the range 0.9–10 mJ/cm², there exists an increase in the transmission of the probe as a function of the incident energy density of the excite beam, which has been attributed to the partial filling of the resonantly coupled interband states. This partial filling of the resonant valence and conduction band states is believed to be a band-filling effect caused by the large number of optically generated electron-hole pairs. At excite pulse-energy densities greater than about 10 mJ/cm², the transmission of the probe beam no longer increases with increasing excitation intensity, and above 30 mJ/cm², the transmission of the probe pulse begins to decrease with increasing energy density of the pump. This behavior strongly suggests the possibility of a new absorption mechanism at these high excitation levels. The turnover in the probe transmission is consistent with the expected onset of direct intervalence-band absorption, as previously noted in Ref. 2.

A model which has been successful in reproducing several of the basic features of the pulse transmission experiments up to an excite energy density of about 30 mJ/cm² has been proposed.⁴ For greater energy densities, the model predicts that the pulse transmission continues to increase with increasing excitation, which is in conflict with experiment. Some of the limitations of the model were subsequently removed, but the agreement with experiment was still not satisfactory. In this work, the intervalence-band absorption coefficient was calculated in a way which realistically accounts for the nonparabolic and anisotropic nature of the valence bands in germanium. The calculated results for the absorption cross section differ considerably from results of the earlier theoretical treatments. The largest differences occur for hole temperatures less than about 500 K and hole densities less than about 10^{20} cm⁻³. For example, at a hole temperature of 300 K and hole density of 6×10^{19} cm⁻³, the theory presented here finds the intervalence-band absorption coefficient to be about 4×10^3 cm⁻¹, while a value of about 50 cm⁻¹ is predicted by Leung and Scully.⁵ At higher hole temperatures (>1000 K), the effect of anisotropy of the bands on the direct free-hole transitions is not as important, and the two calculations differ by a factor of 5 or less.

In addition, the absorption due to the free-hole intervalence-band transitions is saturable by a state-filling effect, whereby the excitation pulse depletes the distribution of free holes in the resonant region. This saturation behavior is found to depend strongly on the light intensity, hole density, and lattice temperature. The light intensities for which the saturation effects are expected to become relevant are easily attainable by using picosecond pulses. Absorption saturation of the intervalence-band transitions due to band filling is negligible for light with a wavelength of 1.06 μ m.

1. Summary of paper to be published.
2. Present address: Sandia National Laboratories, Livermore, Calif.
3. A. Miller, G. J. Perryman, and A. L. Smirl, *Opt. Commun.* **38**, 289 (1981).
4. A. Elci et al., *Phys. Rev. B* **16**, 191 (1977).
5. C. Y. Leung and F. O. Scully, *Phys. Rev. B* **23**, 6797 (1981).

INTERACTION OF A TUNABLE PROBE BEAM WITH A HIGH-INTENSITY PULSED CO₂ LASER BEAM IN p-TYPE GERMANIUM¹

R. B. James² D. L. Smith³

In many p-type semiconductors, the absorption of light with photon energies less than the band gap is dominated by direct free-hole transitions. For light in the CO₂ laser spectrum ($\lambda \sim 10 \mu$ m), these intervalence-band transitions in p-Ge occur between the heavy- and light-hole bands, whereby a free hole in the heavy-hole band absorbs a photon and makes a direct transition to a state in the light-hole band. The absorption due to the intervalence-band transitions in p-Ge has been experimentally shown to saturate at high CO₂ light intensities in a manner closely approximated by an inhomogeneously broadened two-level model. Theoretical calculations suggested that this nonlinear behavior of the absorption coefficient results from a population effect, in which the hole occupation probabilities for states in the resonant region of the heavy- and light-hole bands begin to approach one another at high light intensities.

Experimental attempts have been made to understand the response of the free-hole distribution to a high-intensity pump of fixed wavelength by measuring the transmission of a weak tunable probe also resonant between the heavy- and light-hole bands. By measuring the transmission of the probe beam as a function of detuning of the pump and probe, one can investigate modification of the free-hole distribution by the high-intensity pump for states nearly resonant with the pump laser. The specific features of the spectral linewidths of the probe absorption also yield valuable information on the relaxation times.

In this report, we present calculations of the absorption line shape of the probe beam as a function of the intensity of the pump beam. The absorption coefficient of the probe beam is found

to consist of two separate contributions. One part is due to the decrease in the distribution of free holes in the resonant region of the heavy-hole band induced by the saturating beam. This hole-burning effect can be described using a theory in which rate equations are constructed to determine the distribution of hole states in k space as a function of the intensity of the saturating beam. The second part results from the nonlinear response of the hole distribution to a forcing oscillation at the beat frequency Δ ($\Delta = \omega_+ - \omega_-$) for a pump laser with frequency ω_+ and a probe laser with frequency ω_- . This forcing oscillation induces pulsations of the difference in occupation probabilities between states in the resonant region of the heavy- and light-hole bands. These population pulsations act as a temporal and spatial laser-induced grating which can scatter pump photons into the direction of the probe beam with the frequency shifted to that of the probe beam, and vice versa. This coherent scattering can have a significant influence on the light transmission as measured in the probe

direction. Calculated results show that the light as measured along the probe direction cannot be directly related to the response of the semiconductor due to the presence of the pump beam alone. The contribution from coherent coupling of the two beams can be decreased by using beams with orthogonal polarizations.

In addition to the coherent contribution to the probe beam absorption, the population pulsations can also generate a third optical wave at a frequency ($2\omega_+ - \omega_-$) with a wave vector ($2\mathbf{k}_+ - \mathbf{k}_-$). Here $\mathbf{k}_+$ and $\mathbf{k}_-$ are the wave vectors of the pump and probe beams, respectively. If phase matching conditions are satisfied, this generated wave can reach an intensity comparable to that of the probe beam.

-
1. Summary of paper to be published.
 2. Present address: Sandia National Laboratories, Livermore, Calif.
 3. California Institute of Technology, Pasadena, Calif.

2. SURFACE AND NEAR-SURFACE PROPERTIES OF SOLIDS

Ion beam and laser processing continue to provide a major focus for investigating fundamental materials interactions and for near-surface modifications. These nonequilibrium processing techniques are ideal for fundamental materials research because they place extreme boundary conditions on materials interactions which are not achievable with conventional materials processing methods. The fundamental studies reported here range from investigations of the processing phenomena themselves (i.e., ion implantation damage effects, cascade quenching phenomena, laser-solid interactions, etc.) to studies of conventional and new materials interactions which utilize these processing methods (i.e., ultrarapid crystal growth, metastable phase formation, overheating and undercooling, etc.). The practical aspects of near-surface modifications achieved by these processing techniques are also increasing in importance. These range from the use of ion implantation and laser processing for semiconductor device fabrication to the modification of surgical alloys and to the fabrication of optical waveguides. Collaborative research involving scientists from industries, universities, and other ORNL divisions has increased substantially with the formalization of the Surface Modification and Characterization Collaborative Research Center. The multiplicity of coauthors listed on a majority of papers in this chapter reflects the extent of these collaborations and the multidisciplinary nature of the research. Surface studies which cover structural properties and kinetics of clean and adsorbate-covered surfaces are not only intrinsically interesting from a fundamental viewpoint, but also provide an invaluable complement to the near-surface modification work. In particular, insights from the surface studies are increasingly important for understanding interface interactions, which are often the first step in ion- or laser-induced materials interactions.

During the past year, structural properties of both clean and adsorbate-covered surfaces have been investigated with a variety of surface sensitive techniques. Clean surfaces exhibiting multilayer relaxation or surface reconstruction have been examined, and geometric structures proposed. The effects of ordered arrays of steps and adsorbed hydrogen on surface reconstruction have also been studied. Ordered surface structures formed subsequent to the adsorption of oxygen at various crystal temperatures have been determined, as well as the domain size distribution during overlayer growth. In addition, the adsorption kinetics for oxygen adsorption at different crystal temperatures have been determined. Surfaces provide an ideal way of investigating two-dimensional phase transitions, and they have been used to

study using critical phenomena for an oxygen overlayer and for the effect of surface steps on the critical behavior of a 2D-XY phase transition. Using synchrotron radiation, the band structure of ordered oxygen overlayers has been determined, and these results permit discrimination between various proposed model geometries. Additional investigations dealing with clean surface multilayer relaxations and electronic properties of refractory metal carbides are reported elsewhere.

The Plasma-Materials Interaction Program in the Solid State Division conducts research in support of the ORNL and national magnetic fusion energy programs. This program is very interactive with the international fusion community through scientific personnel exchanges and actual experiments on tokamaks such as ISX-B at ORNL and TEXTOR in Jülich, Federal Republic of Germany. Over the past year, research in this program has utilized time-resolved laser fluorescence spectroscopy and plasma edge deposition probes analyzed by ion scattering techniques to study (1) impurity and deuterium fluxes in the plasma edge region of TEXTOR and ISX-B, (2) limiter problems arising from plasma edge erosion and deposition in ISX-B and ASDEX, and (3) synergistic effects in tokamaks. In addition, laboratory experiments such as ion-enhanced erosion of carbon at high temperatures were performed to support the in situ studies. Over the next few years the in situ portion of this program will be shifted into the ORNL Fusion Energy Division.

Work reported in the Ion Implantation and Ion Beam Processing Section encompasses a variety of materials and materials properties and ranges from fundamental studies to practical applications. Several examples of new materials properties or interactions induced by ion beam or laser processing are reported. Among these is the unique morphological instability initiated in the amorphous phase of Ge by ion bombardment. A variety of techniques were employed to elucidate the mechanisms governing ion beam mixing (i.e., the materials interactions between two systems induced by ion bombardment). These include studies of the materials properties induced by heavy ion bombardment of a variety of materials combinations (semiconductor/metal, metal/metal, metal/ceramic) at both high and low temperatures, comparisons of materials interactions governed by equilibrium (thermal annealing) and nonequilibrium (ion beam mixing) reaction methods, and the use of self-isotope methods. Several papers deal with effects that are very important for the use of ion implantation doping in semiconductor device fabrication. An understanding of high dose-rate damage effects in Si is essential to the future use of focused ion beams for direct writing on Si chips. Damage and annealing effects associated with oxygen implantation relate to the formation of buried insulating layers (SiO_2) in a single-crystal matrix for three-dimensional device structures. Continued studies of the structural alterations and chemical (electrical) changes which occur in Al_2O_3 and SiC following ion implantation doping and thermal annealing have led to a detailed understanding of the origins of beneficial surface modifications induced by these treatments. Artificial hip joints

made of the alloy Ti-6Al-4V and implanted with N have shown a phenomenal reduction of ~1000 in corrosive wear tests designed to simulate the use of the artificial joint in the human body. This result is not only of fundamental interest but also has resulted in the commercialization of the N surface modification process for use on the hip joints supplied by a major manufacturer.

The research in the section on Pulsed-Laser and Thermal Processing reflects several trends. First, pulsed-laser annealing has become a powerful tool for fundamental materials research because of the controlled, rapid processing it provides. It has been used for basic studies of melting and rapid solidification, for the determination of nonequilibrium solubility limits and solute trapping mechanisms, for the identification of morphological instabilities and surface structure quenching, and for the controlled study of precipitate formation and defect interactions. Second, the technique of rapid thermal annealing, which is becoming increasingly important in semiconductor processing, has spurred research into the defect annealing, diffusion, and precipitate formation mechanisms. Third, these basic studies have initiated the use of new analysis methods and calculations. Nanosecond resolution time-resolved x-ray diffraction measurements have been used to determine the strain profiles, temperature gradients, and undercooling of Si and Ge during pulsed-laser processing. Time-resolved optical measurements and the accurate determination of temperature-dependent optical properties have led to a better understanding of the laser melting process and to improved melting model calculations.

SURFACE SCIENCE

THE EFFECT OF SURFACE STEPS ON W(001) RECONSTRUCTION DOMAINS¹

J. F. Wendelken G.-C. Wang²

Low-energy electron diffraction (LEED) patterns show that the W(001) surface reconstructs at temperatures below room temperature when clean^{3,4} and at room temperature when exposed to hydrogen.^{5,6} Although the LEED patterns appear the same in each case (i.e., $(\sqrt{2} \times \sqrt{2})R45^\circ$), the actual reconstruction is different. The clean, low-temperature reconstruction has a p2mg symmetry and is generally thought to result from lateral surface atom shifts in [1,1] directions to form "zigzag" rows.⁴ With hydrogen-induced reconstruction, lateral motion in [1,0] directions occurs to form dimers and to give a c2mm symmetry.⁶⁻⁸ In both cases, the reconstruction may occur in two rotationally equivalent domains. It has been shown that steps on a surface may limit the growth of these domains and may also influence the selection of domain orientations.^{9,10} It is the purpose of this study to explore in more detail the effect of steps on domain growth and selection.

Reconstruction domain sizes, shapes, and orientations have been studied for both planar

and stepped surfaces through analysis of LEED intensities and beam shapes. The planar surface was cut and polished to within 0.1° of the (001) plane, while two stepped surfaces were prepared with alignments $3.25^\circ \pm 0.25^\circ$ off the (001) plane with step edges perpendicular to the [110] in one case and to the [100] in the other case. These steps, herein referred to as [110] and [100] steps, have an average separation of ~ 30 Å as may be determined from the beam splitting shown in Fig. 2.1. All measurements on these surfaces were performed in a single UHV system in which the base pressure indicated by an ion gauge was 2.5×10^{-11} Torr. Sample cleanliness and freedom from hydrogen, in particular for the clean surface measurements, were monitored with an electron energy loss (EEL) spectrometer, which was also used for the LEED beam shape measurements reported. From beam shapes, determined with a series of angular scans, the reconstruction domain geometries could be determined using the formula¹¹ $M = 0.888 \lambda / \Delta \theta \cos \theta$. Here M is the domain dimension in the direction of the angular scan made with an electron beam energy corresponding to wavelength λ at diffraction angle θ where the physical broadening $\Delta \theta$ is determined after corrections for the instrument response function.

When the clean, flat W(001) surface was observed at temperatures below 150 K, the $\{1/2, 1/2\}$ LEED beams at 42 eV were uniformly

GRNL-DWG 84-16323

LOW TEMPERATURE RECONSTRUCTION DOMAINS ON HIGH STEP DENSITY W(001) SURFACES

Fig. 2.1. (a) Schematics of LEED patterns associated with low-temperature reconstruction of W(001) surfaces having $[1\bar{1}0]$ and $[100]$ steps, respectively. (b) Associated reconstruction domain geometries determined from angular profiles of $\{1/2, 1/2\}$ LEED beams.

broadened by about 0.8° . Data obtained for different beams at several energies indicate that the domains are generally rounded with an average domain size of 129 ± 20 Å. All four of the $\{1/2, 1/2\}$ beams were observed with nearly equal intensity, indicating an equal mixture of both of the rotationally equivalent $p2mg$ symmetry reconstruction domains.

The effect of surface steps on these reconstruction domains is indicated in Fig. 2.1. The integral order beam splitting which appears in the LEED schematics is perpendicular to the step edges and indicates a terrace width of ~ 30 Å in each case. A limitation of reconstruction domain growth by the steps is indicated by the fact that the $\{1/2, 1/2\}$ beams do not split at any energy. Preference for a single rotational domain is shown on the $[1\bar{1}0]$ stepped surface by a 30:1 intensity ratio between $\{1/2, 1/2\}$ LEED beams. The more intense beams are associated with the domain having displacements perpendicular to the step edges.⁹ For the $[100]$ stepped surface, where the atomic displacements of either domain are 45° to the step edge, no domain selection is expected or observed. Measurement of the angular width perpendicular to the steps in each shows that the domain growth perpendicular to the steps is almost equal to the terrace width. However, as shown in Fig. 2.1 the domain growth parallel to the

steps is influenced by the step orientation. In the case of the $[1\bar{1}0]$ stepped surface, where a single domain orientation is preferred, the growth parallel to the steps is equal to the flat surface domain size. However, on the $[100]$ stepped surface the domain size is limited to less than half of the flat surface dimension. The difference in the two cases is probably due to the difference in number of competing domain orientations.

Hydrogen absorption on W(001) proceeds with two distinct reconstruction phases at room temperature.^{5,6} The commensurate phase LEED pattern from a flat surface is identical to the low-temperature clean surface LEED pattern and shows full development at 0.12 monolayer coverage.¹ Broadening of the $\{1/2, 1/2\}$ beams also indicates round domains with an average diameter of 123 ± 20 Å. Additional hydrogen coverage results in the development of an incommensurate phase characterized by a fourfold splitting of each of the $\{1/2, 1/2\}$ beams. These splittings can be understood in terms of anti-phase boundaries⁷ which develop within the commensurate phase domains. The maximum splitting observed indicates a minimum boundary separation of 15 Å before the surface returns to a (1×1) structure.

Step effects on the commensurate-phase hydrogen-induced reconstruction are similar to the effect on the low-temperature reconstruction and are illustrated in Fig. 2.2. The domains are limited by the terrace widths; however, the different symmetry of the hydrogen-induced reconstruction means that domain selection does not occur with the $[1\bar{1}0]$ steps but does with the $[100]$ steps. The domain size parallel to the $[1\bar{1}0]$ steps is limited to less than half the flat surface dimension, as might be expected when compared to the low-temperature reconstruction with $[100]$ steps. However, the parallel dimension with the $[100]$ steps is similarly limited for reasons which are not clear. Incommensurate phase development proceeds as on the flat surface, the only difference being the smaller commensurate phase domains from which it develops.

The study of step effects on reconstructed tungsten surfaces has provided increased understanding of the interaction of defects with surface reconstruction, as well as demonstrating a useful method for further studies as described in the following article.

1. Summary of papers: J. Vac. Sci. Technol. A 2, 888 (1984); (to be published).
2. Present address: Rensselaer Polytechnic Institute, Troy, N.Y.
3. T. A. Felter, R. A. Barker, and P. J. Estrup, Phys. Rev. Lett. 38, 1138 (1977).
4. M. K. Debe and D. A. King, Phys. Rev. Lett. 39, 708, (1977); Surf. Sci. 81, 193 (1979).
5. R. A. Barker and P. J. Estrup, Phys. Rev. Lett. 41, 1307 (1978).
6. D. A. King and G. Thomas, Surf. Sci. 92, 201 (1980).
7. R. A. Barker and P. J. Estrup, J. Chem. Phys. 74, 1442 (1981).
8. K. Griffiths, D. A. King, and G. Thomas, Vacuum 31, 671 (1981).

ORNL-DWG 84-15750

**HYDROGEN-INDUCED RECONSTRUCTION DOMAINS ON
HIGH STEP DENSITY W(001) SURFACES**

Fig. 2.2. (a) Schematics of LEED patterns associated with hydrogen-induced reconstruction of W(001) surfaces having [110] and [100] steps, respectively. (b) Associated reconstruction domain geometries determined from angular profiles of $\{1/2, 1/2\}$ LEED beams.

9. G.-C. Wang and T.-M. Lu, *Surf. Sci.* 122, 1635 (1982).
10. J. F. Wendelken and G.-C. Wang, *Surf. Sci.* 140, 425 (1984).
11. D. P. Woodruff, G.-C. Wang, and T.-M. Lu, p. 259 in *The Chemical Physics of Solid Surfaces and Heterogeneous Catalysis*, Vol. II, ed. by D. A. King and D. P. Woodruff, Elsevier Publishing Company, Amsterdam, 1983.

**FINITE SIZE EFFECTS ON THE CRITICAL
BEHAVIOR OF THE W(001) LOW-TEMPERATURE
PHASE TRANSITION¹**

J. F. Wendelken G.-C. Wang²

The clean W(001) surface undergoes a phase transition upon cooling below 250 K in which lateral displacements of surface layer tungsten atoms result in a "zigzag" structure as discussed

in the preceding article.³ With LEED, the transition is indicated by the appearance of half-order beams which indicate a change in structure from (1×1) to $(\sqrt{2} \times \sqrt{2}) R45$. This phase transition has been predicted to be a realization of the 2d-XY model with cubic anisotropy⁴ in which the critical behavior is expected to be nonuniversal (i.e., dependent on the actual physical interactions). Theoretical studies of this and other phase transition models predict that the singularities present in the thermodynamic limit (infinite system) are both rounded and shifted in a finite system.⁵

To study the predicted finite size effects on the phase transition critical behavior, we have observed the intensity and angular width dependence on temperature of the half-order electron diffraction beams associated with flat and stepped W(001) surfaces. As discussed in the previous article,³ steps on the surface may be used to control the size of reconstruction domains.⁶ For this study, the surface with [100] oriented step edges and ~ 30 Å terrace width was used. This surface had the smallest domain size (~ 30 Å $\times$ 60 Å vs 129 Å $\times$ 129 Å for the flat surface), which should result in the largest finite size effect.

The temperature dependence of the $(1/2, 1/2)$ beam intensity $I(T)$ was observed while the crystal was cooling either after high-temperature flashing (~ 2000 K) to remove oxygen or mild heating (~ 450 K) to remove hydrogen and at several fixed temperatures. The data obtained are independent of cooling rate and reversible with temperature. After Debye-Waller factor correction, the normalized $I_N(T)$ curves from the two surfaces are shown in Fig. 2.3(a). These $I_N(T)$ curves stay near 1 for a small temperature range and then rapidly drop in the vicinity of a critical temperature T_C . In contrast, the integral order beam intensities increase slightly near T_C , reflecting a redistribution of intensity in the entire reciprocal space, after which typical Debye-Waller temperature-dependent decay is observed. For $T < T_C$, $I_N(T)$ obtained from small, step-limited domains is lower than the $I_N(T)$ obtained from large domains, and the reverse is true when $T > T_C$ [i.e., $I_N(T)$ has a higher intensity tail for a smaller domain size]. This rounding of $I_N(T)$, which is proportional⁵ to the square of the order parameter, is in qualitative agreement with theoretical results. A note of caution is that the theoretical results assume round domains while the domains on our stepped surface are elongated. Possible shape effects are assumed to be small, and our experimental results indicate that $I_N(T)$ depends strongly on total ordered area.

The temperature dependence of the FWHM of the $(1/2, 1/2)$ beams have also been measured and are shown in Fig. 2.3(b). The broadening of these beams is coincident with the rapid decay in peak intensity and implies that the large reconstruction domains break into much smaller ones near T_C . The domains still have a detectable width of ~ 12 Å even at temperatures much higher than the transition temperature, indicating the existence of short-range order even after loss of long-range order in agreement with Monte-Carlo and renormalization group studies on the

Fig. 2.3. (a) Normalized (1/2,1/2) LEED beam intensity vs temperature for flat and [110] stepped W(001) surfaces. (b) (1/2,1/2) LEED beam broadening vs temperature.

W(001) surface,⁷ and consistent with the experimental results of photoemission⁸ and high-energy ion scattering.⁹

The rounding of $I_N(T)$ near the transition temperature and the shifting of the transition temperature due to finite size domains can be quantified by following the procedures used by Lyuksyutov and Fedorus¹⁰ to extract the critical exponent β and critical temperature T_c from the critical region. For an infinite system the phase transition should be described by a power law of the form $I = I_0[(T_c - T)/T_c]^{2\beta}$. However, to account for finite size effects, the intensity in the critical region is fitted with the aid of a formula used by Horn et al.¹¹

$$I = I_0 / (2\pi)^{1/2} \int_{T-T_c}^{T_c-T+t} \left(\frac{T_c - T}{T_c + t} \right)^{2\beta} \exp\left[-\frac{1}{2} \left(\frac{t}{\Delta t} \right)^2\right] dt,$$

where Δt describes the transition temperature "smearing" width and I_0 is a constant. The "best fit" values for T_c and β for the flat surface are 211 K and 0.14 ± 0.04 , while for the stepped surface the resulting values are 217 K and 0.05 ± 0.01 , respectively. The calculated $I_N(T)$ using these optimum values follows closely the measured $I_N(T)$ for $T < T_c$. Results indicate that the critical exponent β decreases and the critical temperature T_c increases as the finite domain size decreases.

In conclusion, two W(001) surfaces with different step densities were prepared and provided two distinct size distributions of reconstruction domains. This allowed the study of finite size effects on the critical behavior of the 2d-XY model with cubic anisotropy phase transition. The critical exponent β and the critical temperature were found to have different values for different domain sizes, and the anticipated rounding of $I(T)$ for smaller domains was observed.

1. Summary of paper to be published.
2. Present address: Rensselaer Polytechnic Institute, Troy, N.Y.
3. J. F. Wendelken and G.-C. Wang, "The Effect of Surface Steps on W(001) Reconstruction Domains," this report.
4. P. Bak, *Solid State Commun.* 32, 581 (1979).
5. D. P. Landau, *Phys. Rev. B* 13, 2997 (1976); A. N. Berker and S. Ostlund, *J. Phys. C* 12, 4961 (1979); M. E. Fisher and M. N. Barber, *Phys. Rev. Lett.* 28, 1516 (1972).
6. J. F. Wendelken and G.-C. Wang, *J. Vac. Sci. Technol. A* 2, 888 (1984).
7. L. D. Roelofs, G. Y. Hu, and S. C. Ying, *Phys. Rev. B* 28, 6369 (1983).
8. M. I. Holmes and T. Gustafsson, *Phys. Rev. Lett.* 47, 1649 (1980).
9. I. Stensgaard, L. C. Feldman, and P. J. Silverman, *Phys. Rev. Lett.* 42, 247 (1979).
10. I. F. Lyuksyutov and A. G. Fedorus, *Sov. Phys. JETP* 53, 1317 (1981).
11. P. M. Horn et al., *Phys. Rev. Lett.* 41, 961 (1978).

A PHYSICAL REALIZATION OF TWO-DIMENSIONAL ISING CRITICAL PHENOMENA: OXYGEN CHEMISORBED ON THE W(112) SURFACE¹

G.-C. Wang² T.-M. Lu³

Recently it has been shown that continuous order-disorder phase transitions for localized adsorption on surfaces may exhibit different universality class behavior.⁴ Among them, the 2-D Ising universality class is of particular interest. This system is perhaps the most significant nontrivial statistical problem which has been solved exactly with mathematical rigor.⁵ In this report, we present an experimental study of the 2-D Ising phase transition in a lattice gas system using LEED.

Oxygen chemisorbed on a W(112) surface forms a $p(2 \times 1)$ superstructure over a wide range of

submonolayer coverage at room temperature. The structures of both the clean W(112) surface and a half-monolayer oxygen-covered $p(2 \times 1)\text{-O}$ surface have been determined by recent LEED analyses, whose results indicate a nonreconstructed surface (or 1×1 reconstruction) and a simple overlayer, respectively.⁶

The temperature dependence of the peak intensities $I(T)$ of the $(1/2, 0)$ beams follows the Debye-Waller behavior at temperatures lower than 700 K. For temperatures higher than 700 K, the intensity starts to deviate from the Debye-Waller slope and falls off much more rapidly. Figure 2.4 shows the normalized temperature-dependent peak intensity for both heating and cooling. Within experimental uncertainty, the process is reversible. Also shown in the same figure is the measured temperature-dependent full-width-at-half-maximum (FWHM) of the angular intensity distribution of the $(1/2, 0)$ beam, obtained by scanning the Faraday cup across the diffracted beam. Broadening of the FWHM away from the constant width indicates disappearance of the long-range order and appearance of short-range order above a transition temperature. This broadening is an indication of a continuous phase transition. We have also measured the temperature dependence of the peak intensities and FWHM of the integral order beams from both clean and oxygen-covered surfaces. In contrast to the results obtained from the $(1/2, 0)$ beams, the $I(T)$ always follows the Debye-Waller slope up to 1000 K, and the FWHM do not broaden. These observations indicate that the substrate tungsten provides the 2-D absorption lattice sites for the oxygen overlayer. The abrupt change in intensities and FWHM of the $(1/2, 0)$ beams is attributed to the order-disorder phase transition in the overlayer.

We have further measured the amount of oxygen adsorbed on the surface over a wide range of temperatures using Auger electron spectroscopy (AES), including the temperature region where the rapid change of $(1/2, 0)$ beam intensity

Fig. 2.4. Normalized peak intensity and FWHM vs temperature of a superlattice beam. Open squares: measured peak intensity corrected by Debye-Waller factor; filled circles: measured FWHM.

occurs. The AES results show that the O/W signal ratio stays constant over the entire temperature range. Oxygen can only be desorbed at $T > 2200$ K. We therefore have a 2-D "closed system."

The LEED pattern shows that the disordered phase of the oxygen overlayer is (1×1) , which has a $P2_{mm}$ space group symmetry. The order parameter ϕ_k of the ordered $p(2 \times 1)$ phase has only one component. One can obtain the Landau-Ginzburg-Wilson (LGW) Hamiltonian by constructing all possible invariants of the ϕ_k under all elements of $P2_{mm}$, and the final form is identical to that of the 2-D Ising Hamiltonian. The order-disorder phase transition of oxygen on the W(112) surface at a half-monolayer coverage thus belongs to the 2-D Ising universality class.

Next, we present the critical exponents extracted from the critical region. The theory of critical phenomena predicts that in the vicinity of T_c (the critical region), the function $F(T)$ varies according to a power law $F(T) = F_\lambda(T - T_c)^\lambda$. For $T < T_c$, $F(T) = I_L(T)$ and $\lambda = 2\beta$; for $T > T_c$, $F(T) = I_S(T)$ and $\lambda = -\gamma$, $F(T) = W_S(T)$ and $\lambda = \nu$, where F_λ is a constant, β is the critical exponent associated with the long-range order, and γ and ν are exponents associated with susceptibility and correlation length, respectively. I_L and I_S are the peak intensities due to long-range order and short-range order, respectively, and W_S is the FWHM of the short-range scattering. The final values of the critical exponents are listed in Table 2.1. The uncertainties associated with β , γ , and ν are the results of allowing a ± 5 K change in T_c (899 K). For comparison, theoretical predictions of Ising, 3- and 4-state Potts models are also listed in Table 2.1.

1. Summary of paper to be published.
2. Present address: Rensselaer Polytechnic Institute, Troy, N.Y.
3. Rensselaer Polytechnic Institute, Troy, N.Y.
4. E. Domany et al., *Phys. Rev. B* 18, 2209 (1978).
5. L. Onsager, *Phys. Rev.* 65, 117 (1944).
6. H. L. Davis and G.-C. Wang (to be published).

Table 2.1. The values of the experimental critical exponents are consistent with predictions of the theoretical Ising model. The large error (~10%) introduced in the determination of the values of the exponents comes mainly from the finite size effect and the finite instrumental resolution.

Experimental	Theory		
	2-D Ising	3-state Potts	4-state Potts
$\beta = 0.13 \pm 0.01$	1/8	1/9	1/12
$\gamma = 1.79 \pm 0.14$	7/4	13/9	7/6
$\nu = 1.09 \pm 0.11$	1	5/6	2/3

DISTRIBUTION OF DOMAIN SIZES DURING OVERLAYER GROWTH¹

J. M. Pimbley² T.-M. Lu³
G.-C. Wang³

Recently, the kinetics of domain growth in two-dimensional systems has attracted much theoretical⁵ and experimental⁶ attention. The time evolution of a nonconserved, order-disorder transition has been described by Lifshitz and by Allen and Cahn (LAC).⁷ This theory assumes that after the system is quenched from a disordered to an ordered state, domains separated by antiphase boundaries are formed. The degree of ordering of the individual domains is close to the equilibrium value. These domains will grow to reduce the curvature of the boundaries. The theory predicts that the domain size growth is proportional to the square root of time. In this report, we construct a microscopic model to describe the distribution of domain or island sizes during the growth of an overlayer. This model is used to describe results from a LEED experiment, the growth of the $p(2 \times 1)$ oxygen antiphase domains on a $W(112)$ surface. For the case where the order-parameter is not conserved, our basic assumption is that, after a quench, antiphase boundaries are generated at random positions and obey Markovian disorder. This assumption implies physically that we neglect the possibility of boundary-boundary interactions. The boundaries may possess different phases, and annihilation of boundaries occurs during the coarsening process. The density of boundaries is then reduced, and the average domain size grows.

In order to describe the above statements quantitatively, let us consider a cut along the doubly spaced direction in the oxygen $p(2 \times 1)$ structure on $W(112)$. Let γ be the probability of stepping down from an overlayer atom to a substrate atom in going from one lattice site to the adjacent one. Therefore, the probability of an overlayer atom going to an adjacent overlayer atom is $1 - \gamma$. Since the coverage is $1/2$, the probability of stepping up from a substrate atom to an overlayer atom in going from one lattice site to the adjacent one is also γ . The γ for each site is independent and thus defines a Markovian disorder. One can show that the $p(2 \times 1)$ domain size distribution $P_D(N)$ of such "Markov chains" obeys a geometric distribution function: $P_D(N) = \gamma^2(N-1)(1-\gamma^2)$, where N is the number of overlayer atoms in a domain in the direction of a . N is therefore a measure of the diameter of the two-dimensional domains. The sum of $P_D(N)$ is normalized to unity [i.e., $\sum P_D(N) = 1$], and the average domain size is given by

$$\bar{N} = \sum_{N=1}^{\infty} N P_D(N) = \frac{1}{1-\gamma^2}.$$

Therefore, $\gamma = 1$ implies a perfect $p(2 \times 1)$ structure with an infinite domain size, and $\gamma = 1/2$ implies a disordered random lattice gas having an average domain size of $4/3$ atoms. Many types of antiphase boundaries with different widths

na, where $n = 1, 3, 4, 5, \dots$ and a is the repeat distance, are possible. They occur with the probability of $P_B(n) = 1 - \gamma$, $n = 1$; $P_B(n) = \gamma^2(1-\gamma)n^{-2}$, $n = 3, 4, 5, \dots$.

The diffraction problem of the above distribution of domain sizes and boundaries can be solved exactly (kinematic scattering), and the LEED angular profile can be written in closed form $I(S) = (1-\rho^2)/[1+\rho^2-2\rho\cos(S_1a)]$, where S and S_1 are the momentum transfer and the momentum transfer parallel to the surface, respectively, and $\rho = (1-2\gamma)$. The above equation predicts a smooth broadening of the half-order beams. As the average domain size increases, the profile becomes sharper. The width of the profiles is determined by γ only. Qualitatively, this is consistent with our observation of the diffraction angular profiles during the growth of oxygen antiphase domains on a $W(112)$ surface.

In order to test the model more quantitatively, a large number of $(1/2, 0)$ beam angular profiles were measured at different up-quenching temperatures ranging from 266 to 333 K at the final stages of growth. All profiles were obtained at approximately 300 s after quenching. At this time, the growth came to a halt, representing a quenched-in, metastable state. The γ values extracted from the best fit between the calculated angular profile and the measured profile are $\gamma = 0.952$ (for 294 K) and 0.974 (for 291 K), which correspond to the average domain sizes of $\bar{N} = 10.6$ and 19.1 in units of $2a$. The domain size distributions can be obtained from $P_D(N)$ and are shown in Fig. 2.5. For any fixed value of γ , there are more domains smaller than N than there are those larger than N in this geometric distribution of domain sizes.

1. Summary of paper to be published.
2. General Electric and Rensselaer Polytechnic Institute, Troy, N.Y.
3. Rensselaer Polytechnic Institute, Troy, N.Y.

Fig. 2.5. The oxygen $p(2 \times 1)$ domain size distribution extracted from the LEED angular profiles.

4. Present address: Rensselaer Polytechnic Institute, Troy, N.Y.

5. P. S. Sahni, G. S. Crest, and S. A. Safran, *Phys. Rev. Lett.* **50**, 60 (1983).

6. G.-C. Wang and T.-M. Lu, *Phys. Rev. Lett.* **50**, 2014 (1983).

7. I. M. Lifshitz, *Sov. Phys. JETP* **15**, 939 (1962); S. M. Allen and J. W. Cahn, *Acta Metall.* **27**, 1085 (1979).

MORE THAN ONE MONOLAYER ADSORPTION OF OXYGEN ON THE W(112) SURFACE¹

G.-C. Wang² J. K. Pimbley³
T.-M. Lu⁴

Previous investigations⁵ have shown that for a half monolayer coverage ($\theta = 0.5$ ML) of oxygen, adsorbed at room temperature, a very well ordered $p(2 \times 1)$ structure can be formed after annealing to >600 K. With additional exposure, the intensities of the superlattice beams of the $p(2 \times 1)$ LEED pattern are gradually diminished due to the continuous adsorption of oxygen, and eventually a (1×1) pattern is observed [Fig. 2.6(a)], corresponding to a coverage of one monolayer of oxygen, $\theta = 1$ ML [Fig. 2.6(b)]. The sticking coefficient does not reduce to zero after a full monolayer of oxygen coverage is established, a rather unusual result for the adsorption of a reactive gas on a solid surface. A diffuse $p(1 \times 2)$ pattern appears after further adsorption of oxygen, and the sticking coefficient is reduced to almost zero

only after the $p(1 \times 2)$ structure has been fully developed [Fig. 2.6(c)].

We have used a 2-keV primary electron beam to measure the oxygen KVV (507 eV) and the W (350 eV) peak-to-peak Auger signal intensities as a function of oxygen exposure. The ratio of oxygen to tungsten peak-to-peak heights was plotted as a function of exposure. The ratio of a fully developed $p(1 \times 2)$ pattern to a $p(2 \times 1)$ pattern is found to be ~ 3 . This result confirms that the $p(1 \times 2)$ structure results from the adsorption of more than one monolayer of oxygen on the surface (i.e., 1.5 ML).

We believe that the ability to chemisorb more than one monolayer of oxygen is due to the openness of the W(112) surface. A portion of the surface is still "exposed" to the impinging oxygen gas even for a coverage of 1.0 ML. This is easily visualized using a hard sphere model as shown in Fig. 2.6(d). Oxygen atoms, represented by hatched circles, are believed to sit in the "troughs" in the $[111]$ direction [i.e., column A of the W(112) surface]. Because of the openness of the surface, after all the "troughs" are filled by oxygen atoms ($\theta = 1.0$ ML), the topmost W atoms (column B) are still exposed to, and therefore can still react with, the impinging oxygen gas. A second layer of adsorbed oxygen is therefore possible. The second layer of oxygen atoms is assumed to sit in the bridge sites of the topmost layer of W atoms (column B). This is shown schematically in Fig. 2.6(d) as dashed circles.

We have measured LEED I-V profiles for the first and second integral-order and half-order beams from the $p(1 \times 2)$ structure and found a mirror plane perpendicular to the $[110]$ direction. This result is consistent with the model shown in Fig. 2.6(d). However, a dynamical LEED calculation has yet to be performed.⁶

Fig. 2.6. (a) Schematic of $W(112)p(1 \times 1)-O$ LEED pattern. (b) Schematic of one monolayer of oxygen adsorption on a $W(112)$ surface. Open circles: W atoms; hatched circles: O atoms. (c) A schematic of $W(112)p(1 \times 2)-O$ LEED pattern. (d) A schematic of the model of 1.5 monolayer of oxygen adsorption on a $W(112)$ surface. Second layer of oxygen: dashed circles.

1. Summary of paper to be published.
2. Present address: Rensselaer Polytechnic Institute, Troy, N.Y.
3. General Electric and Rensselaer Polytechnic Institute, Troy, N.Y.
4. Rensselaer Polytechnic Institute, Troy, N.Y.
5. G.-C. Wang and T.-M. Lu, *Phys. Rev. B* **28**, 6795 (1983).
6. H. L. Davis and G.-C. Wang (to be published).

OXYGEN ORDERING ON Cu(110)¹

G. R. Gruzalski D. M. Zehner
J. F. Wendelken R. S. Hathcock²

The LEED patterns exhibited by the (110) surface of copper exposed to room-temperature molecular oxygen at surface temperatures T_s near or slightly above 300 K are well established. With increasing oxygen exposure the patterns observed are (1×1) , (2×1) , a superposition of (2×1) and $c(6 \times 2)$ [denoted as $c(6 \times 2) \times (2 \times 1)$], and, after an exposure of 5×10^4 Langmuir (L), $c(6 \times 2)$. These same patterns also have been observed by following a quite different procedure: exposing them at relatively low T_s to relatively small amounts

of room-temperature molecular oxygen and then annealing. To understand these observations better, we have begun studies designed to establish (1) the relationship between Cu(110)-O surfaces reflecting the same symmetry but prepared by these two procedures, (2) the structure of the different surfaces involved, (3) the chemical state (atomic or molecular) of the oxygen adsorbate following exposures at lower surface temperatures, and (4) the role played by the oxygen coverage θ in determining which structure is present upon adsorption and after a given heat treatment. (Here θ is the number of adsorbed oxygen atoms per substrate atom; $\theta = 1$ corresponds to 1.08×10^{15} atoms/cm².) As an initial step toward accomplishing these goals, LEED observations and x-ray photoelectron spectroscopy (XPS) measurements have been made after exposures at either $T_s = 83 \pm 1$ K (denoted as T_L) or $300 \leq T_s \leq 320$ K (denoted as T_H) of up to 10^5 L oxygen, and again after isochronal anneals at temperatures T_a up to 880 K. Prior to these exposures, the surfaces were either clean or preexposed to oxygen and then annealed to effect adsorbate ordering. These studies have allowed us to ascertain the role of θ in determining which LEED pattern is seen upon adsorption and after a given anneal and to conclude, for example, that the adatom surface densities of the $c(6 \times 2)$ structures resulting from the two procedures mentioned above are different (see below). In addition, they have provided information on the adsorption kinetics and have yielded results consistent with the interpretation that the adsorbate formed at T_L is largely molecular.^{3,4} In this article some of the results directly related to the LEED observations are summarized; information herein regarding θ derives from the XPS study,⁵ which is summarized in the following article.⁶

The LEED patterns observed after exposures at T_L are summarized in Fig. 2.7. (Those observed after exposures at T_H will not be discussed.) Basically, prefix A signifies a pattern that contains additional reflections, and prefix M signifies one that is modulated as the primary-beam voltage is varied. No change was seen in the LEED patterns as a function of time: if the electron beam was affecting the surface, it did so on a time scale either very long or very short with respect to the observation time (minutes).

The oxygen coverages for the as-exposed surfaces in regions I, II, and III (defined in Fig. 2.7) were determined to be $0.14 \leq \theta \leq 0.50$, $0.50 \leq \theta \leq 0.67$, and $0.67 \leq \theta \leq 0.74$, respectively. Within experimental uncertainty, θ was not changed by the 5-min anneals at up to about 480 K. For surfaces initially having $\theta > 0.50$ (region-II and III surfaces), annealing to higher temperatures reduced the coverage until $\theta = 0.50$; the resulting surfaces exhibited (2×1) LEED patterns. This loss of surface oxygen is explicable in terms of oxygen diffusing into the bulk. Surfaces exhibiting the $c(6 \times 2) + (2 \times 1)$ pattern had coverages in the range $0.50 \leq \theta \leq 0.67$; the two similarly shaped curves in Fig. 2.7 intersecting the right ordinate axis at about 860 and 610 K are curves of constant coverage: the upper one corresponds to $\theta = 0.50$, the lower one to $\theta = 0.67$. (Following these curves to the left, they begin

Fig. 2.7. Summary of LEED patterns exhibited by Cu(110) exposed at T_L to room-temperature molecular oxygen and then heat treated. The heat treatments consisted of a series of 5-min anneals starting at 130 K and going as high as 880 K in 50-degree increments.

almost parallel to the abscissa axis, become coincident with the region-II boundaries, and in the sense of constant coverage, may be visualized as extending down the region-II boundaries to 83 K.) For surfaces having $\theta \leq 0.50$ (region-I surfaces), the annealing produced no measurable change in coverage.

If the adsorbate formed at T_L is largely molecular, it appears that it remains so during the anneals⁶ to 130 and 180 K and, hence, that the (3×1) LEED pattern, which is not formed during an exposure at T_H , may be due to a molecular configuration (assuming that the electron beam had no effect on the ordering).

The adatom surface density (Fig. 2.8) of $c(6 \times 2)_{LT}$, the $c(6 \times 2)$ structure resulting from an exposure at T_L and a subsequent anneal, appears to be about 20% less than that of $c(6 \times 2)_{HT}$, the $c(6 \times 2)$ structure formed during an exposure at T_H . These surface densities were determined to be $2/3$ and $5/6$ adatom per substrate atom, respectively. This result is interpreted as suggesting that the phases $c(6 \times 2)_{HT}$ and $c(6 \times 2)_{LT}$ are different or, if the same, that $c(6 \times 2)_{LT}$ has an adatom vacancy concentration of about 20%. Structural models are presented in Fig. 2.8 as candidates for these phases; the models merely display the surface density and symmetry of the unit mesh, and implications concerning adatom

Fig. 2.8. Suggested structures of c(6x2)HT and c(6x2)LT. Large and small circles denote atoms of copper and oxygen, respectively; cross-hatched circles represent copper atoms in the second layer. Another possibility is that both surfaces consist of the same phase [e.g., the one illustrated in (a)], with c(6x2)LT having an adatom vacancy concentration of about 20%.

location, surface relaxation, or surface reconstruction are not intended.

1. Summary of papers: *Surface Science Letters* (in press); *Surface Science* (in press).

2. Summer research intern from Rollins College, Winter Park, Fla.

3. D. Schmeisser and K. Jacobi, *Surf. Sci.* **108**, 421 (1981).

4. A. Spitzer and H. Lüth, *Surf. Sci.* **118**, 121 (1982).

5. G. R. Gruzalski, D. M. Zehner, and J. F. Wendelken (to be published).

6. G. R. Gruzalski et al., "An XPS Study of Molecular and Atomic Oxygen on Cu(110)," this report.

AN XPS STUDY OF MOLECULAR AND ATOMIC OXYGEN ON Cu(110)¹

G. R. Gruzalski D. M. Zehner
J. F. Wendelken

An investigation using XPS has been performed to study oxygen adsorption on clean and modified Cu(110) and to follow changes in the coverage θ and chemical status (atomic or molecular) of the adsorbate owing to isochronal anneals at temperatures T_a of up to 880 K. The motivation and purpose of this work are given in the preceding article.² The XPS data were taken with an unmonochromatic x-ray source (aluminum anode) operated at 10 kV and 55 mA and with a double-pass cylindrical mirror analyzer (CMA) operated in the retarding mode (25-eV pass energy). The energy scale of the spectrometer was calibrated by setting the Au 4f_{7/2} binding energy (BE) equal to 84.1 eV with respect to the Fermi level.³ From the measured FWHM of the Au 4f_{7/2} peak (1.24 eV), the total instrumental resolution was approximated as being about 1.2 eV.

Following exposures of room-temperature molecular oxygen at surface temperatures $T_s = 83 \pm 1$ K (denoted as T_L) and $300 \leq T_s \leq 320$ K (denoted as T_H), the XPS spectra exhibited peaks at 530.15 ± 0.2 eV BE having FWHM's of about 1.9 and 1.6 eV, respectively. These peaks are attributed to photoemission from 1s levels of chemisorbed oxygen. The narrowest peaks are ascribed to strongly bonded atomic oxygen. The broadest ones may be considered as consisting of two of the narrowest peaks separated by about 0.3 eV. This last point is consistent with distinguishable oxygen environments and, hence, with molecular oxygen having been present.^{4,5} Furthermore, the broadest peaks remained broad even after surfaces were annealed at 130 and 180 K and did not begin to sharpen until during the 230 K anneal; changes in ultraviolet photoelectron spectroscopy (UPS) spectra accompanying similar anneals⁵ are interpretable as owing to dissociation. We tentatively conclude, therefore, that the broadest peaks may be due to chemisorbed molecular oxygen. If this assignment is correct, several conclusions follow. (1) The spectra obtained in this study differ from all other reported spectra of which we are aware in that, to within experimental uncertainty, the positions of the 1s peaks for an atomic and molecular adsorbate are equal. (2) The molecular state remains basically unchanged during anneals to 130 and 180 K. (3) At least some molecules dissociate during the 230 K anneal, but the dissociation process is very sluggish in that it continues during anneals at up to 280 or 330 K and/or the dissociation products differ from strongly bonded atomic oxygen.

Anneals at up to 480 K produced no measurable change in coverage, which was determined from areas under the O(1s) peaks near 530.15 eV BE. For higher temperature anneals up to 880 K, the

coverage reduced until $\theta = 0.50$ if $\theta > 0.50$ initially; if $\theta < 0.50$ initially, no change was observed. As mentioned in the preceding article,² the loss of surface oxygen accompanying the anneals is explicable in terms of oxygen diffusing into the bulk.

Oxygen coverage-vs-exposure curves and corresponding relative sticking probabilities S/S_0 are shown in Figs. 2.9(a) and 2.9(b), respectively. Here S is the probability that an incident molecule will chemisorb and $S_0 = S(\theta = 0)$. As seen, S/S_0 at T_h is relatively constant with θ up to some critical coverage, and then it sharply decreases. To a lesser extent, the same is true at T_h . The data for T_h and T_h were fitted to

approximate expressions appropriate for dissociative and nondissociative adsorption, respectively; the expressions were derived by assuming a mobile precursor state kinetics strongly influenced by adsorbate ordering. The fits, which are displayed as dashed curves in Fig. 2.9(b), are nearly indistinguishable from the data for most values of θ . The initial sticking probabilities at T_h and T_h were determined to be about 0.23 and 0.77, respectively.

Ordered adlayers of atomic oxygen may be prepared by either of the two procedures mentioned in the preceding article.² If any of these adlayers completely covered the surface (as determined from the oxygen density and θ), then the increase in chemisorbed oxygen, atomic or molecular, owing to a subsequent exposure at T_h was found to be negligible. On the other hand, these adlayers appeared to have no effect upon subsequent oxygen uptake at T_h .

Fig. 2.9. (a) Oxygen coverage θ vs exposure at T_h and T_h . (b) Conversion of data in (a) to relative sticking probabilities S/S_0 (solid curves). $S_0(T_h) = 0.77$ and $S_0(T_h) = 0.23$ were extracted from the fits (dashed curves) described in ref. 1.

1. Summary of paper to be published.
2. G. R. Gruzalski et al., "Oxygen Ordering on Cu(110)," this report.
3. C. J. Powell, M. E. Erickson, and T. Jach, *J. Vac. Sci. Technol.* 20, 625 (1982).
4. D. Schmeisser and K. Jacobi, *Surf. Sci.* 108, 421 (1981).
5. A. Spitzer and H. Lüth, *Surf. Sci.* 118, 121 (1982).

AN ANGLE-RESOLVED UPS STUDY OF THE OXYGEN-INDUCED RECONSTRUCTION OF Cu(110)¹

R. A. DiDio² D. M. Zehner
E. W. Plummer²

The nature of the oxygen-covered Cu(110) surface is currently a subject of controversy. In particular, the $p(2 \times 1)0$ structure causes the Cu(110) surface to reconstruct, and two models explaining the resulting surface geometry have been advanced. Both low-energy ion scattering (LEIS)³ and He beam diffraction (HBD)⁴ studies argue that the reconstruction is a result of alternating missing rows of Cu atoms in the $\langle 001 \rangle$ direction, while LEED⁵ and high-energy ion scattering (HEIS)⁶ experiments favor a slight outward displacement of alternating $\langle 001 \rangle$ rows (the buckled-row model). It should be noted that all of the above experiments predict that the O atoms reside in the long-bridge site along the $\langle 001 \rangle$ Cu rows. In the buckled-row model, it is the $\langle 001 \rangle$ rows containing the O atoms that are displaced outward from their unreconstructed positions.⁵

In an attempt to differentiate between these two reconstruction models, angle-resolved ultraviolet photoemission spectroscopy (ARUPS) has been used to study the electronic structure of clean Cu(110) and the $p(2 \times 1)0/\text{Cu}(110)$ chemisorption system. The experiments were conducted at the Tantalus I storage ring of the University of Wisconsin using the University of Pennsylvania toroidal grating monochromator. The experimental procedures used to measure the two-dimensional band dispersions of ordered adsorbates have been described in detail in a recent review article.⁷

The Cu(110) crystal was cleaned by sputtering with He ions at room temperature and annealing at 700 K for ~30 min, while the p(2x1)O overlayer was prepared by exposing the clean Cu(110) to 20 L of O₂ at 300 K, followed by a 10-min anneal at 425 K.

The full two-dimensional band dispersions of the O 2p-derived levels measured in these studies are shown in Fig. 2.10. It should be noted, in particular, that an anomalously large (1.85 eV) dispersion is measured for the O 2p_y-derived level along $\bar{\Gamma}\bar{Y}$ and $\bar{X}'\bar{S}'$. These directions are parallel to the O-containing rows of <001> Cu atoms. This dispersion is much too large to be explained by O-O overlap (a tight-binding approach) and is much larger than those seen for simple overlayers of O with comparable nearest-neighbor distances on other metal surfaces. It must then be substrate induced and a direct indication of the strength of the O-Cu bond on the Cu(110) surface.

The LEIS³, HBD⁴ and LEED⁵ results place the O atoms in the long-bridge site along the <001> Cu rows, with O-Cu distances in the range of the stable Cu oxides. This location yields a model of linear O-Cu-O chains separated by twice the <001> row spacing of the Cu(110). One result of this strongly directional bonding should be the splitting of the 2p_x and 2p_y levels at $\bar{\Gamma}$ and is dictated by the C_{2v} symmetry of the long-bridge site. Figure 2.10 shows this splitting to be ~0.3 eV at $\bar{\Gamma}$. A splitting this large has not been seen for the chalcogens in any other C_{2v} configuration on a metal surface. On these surfaces, the adsorbed atoms sit in the fourfold rather than the long-bridge site and presumably do not bond exclusively in one direction.

The O-Cu bond is strongly localized to the O(2p_y)-Cu(3d) interaction. There are two arguments for this. There are large d-band changes at $\bar{Y}$ which are most likely due to the O-Cu bonding and not to buckling at the surface, since little d-band change was seen perpendicular to the buckled rows at $\bar{X}'$. Secondly, the steeply dispersing O-derived band along $\bar{\Gamma}\bar{X}$ and $\bar{X}'\bar{S}'$ tracks with the bottom of the Cu d bands along these directions. This Cu d band is indicated by the dashed line in Fig. 2.10, and it was experimentally measured by looking for extremal

Brillouin zone. The generating wave functions for this band are the Cu 3d_{x²-y²}.

In summary, ARUPS data indicate that the missing row model of the p(2x1)O-induced reconstruction of the Cu(110) surface is not tenable. Thus, the buckled-row model is favored. The amount of the buckling is open to question, however. The O-Cu bond is highly directional along the <001> rows of Cu atoms and is primarily carried through the O(2p_y)-Cu(3d_{x²-y²}) interaction.

1. Summary of paper: *J. Vac. Sci. Technol. A* 2, 852 (1984).
2. University of Pennsylvania, Philadelphia, Pa.
3. R. P. N. Bronckers and A. G. J. DeWit, *Surf. Sci.* 112, 133 (1981).
4. J. Lapujoulade et al., *Surf. Sci.* 118, i03 (1982).
5. H. L. Davis and J. R. Noonan, p. 83 in *Proc. 41st Physical Electronics Conference*, Bozeman, Mont., 1981.
6. R. Feidenhans'l and I. Stensgaard, *Surf. Sci.* 133, 453 (1983).
7. E. W. Plummer and W. Eberhardt, *Adv. Chem. Phys.* 49, 133 (1982).

ION SCATTERING STUDY OF RECONSTRUCTION IN THE Au(110)-(1x2) SURFACE¹

S. P. Withrow J. H. Barrett
R. J. Culbertson

The clean (110) surface of Au exhibits an atomic reconstruction with respect to the bulk lattice termination, which is characterized by a doubling of the lattice periodicity in the [001] direction. It is generally believed that the most probable surface structure involves the absence of every other [110] atomic row in the surface layer, the "missing row" model. However, the actual location of the atoms in the surface is unknown. Earlier investigations at ORNL ruled out the simple missing row model^{2,3} in which the surface layer atoms are at bulk lattice sites, suggesting that the reconstruction includes vertical and/or lateral displacements. On the basis of low-energy electron diffraction (LEED),⁴ x-ray diffraction,⁵ ion scattering^{6,7} He diffraction,⁸ and electron microscopy⁹ experiments, several missing row models have been suggested. In the work reported here these models are evaluated by comparisons made between experimental high-energy ion scattering data and theoretical predictions obtained by calculating ion scattering surface yields for the specific models. Additionally, modifications to these models have been investigated.

Ion scattering surface yields, expressed as an effective number of atoms per row, were measured on a clean, well-ordered Au(110)-(1x2) surface from single alignment Rutherford backscattering spectra. All experiments were made at room temperature. The dependence of the surface yield both on incident He ion energy for normal and nonnormal incidences and on incident

Fig. 2.10 Oxygen 2p-derived band dispersions for p(2x1)O/Cu(110).

angle for small angles near the nonnormal [100] and [101] axes was measured. The experimental results are compared to theoretical predictions obtained using Monte Carlo calculations.¹⁰ The calculations incorporate correlated atomic vibrations.¹¹

The energy dependence of the surface yield for normal incidence was measured for incident energies between 0.2 and 1.0 MeV. The surface yield over this range is between 0.2 (at 0.2 MeV) and 0.4 (1.0 MeV) atoms per row higher than a calculation prediction based on a model with all surface atoms in bulk termination lattice sites and using a vibrational amplitude of 0.089 Å. For normal incidence this bulk termination model and a simple missing row model are equivalent. The addition of enhanced surface vibrations and/or lateral translations to the surface model would increase the calculated values and improve the agreement with the experiment. However, the relative contributions of these two effects cannot be determined.

An energy scan for incidence along the non-normal [101] axis has also been obtained. The experimental surface yield is approximately a half atom per row higher than that obtained for the [110] normal incidence energy scan. Surface yield measurements along the nonnormal incidence direction are sensitive to relaxations perpendicular to the surface. The half monolayer increase can be attributed to vertical relaxation since it was not detected along the normal direction.

The angular dependence of the surface yield for measurements near off-normal low index crystal directions can be used to investigate these surface layer relaxations. Surface yield angular scans around the [101] axial direction at 60° from the surface normal and around the [100] axial direction at 45° from the surface normal are given in the left and right panels, respectively, of Fig. 2.11. The data were obtained at an incident energy of 0.3 MeV.

The [101] axis experimental scan, shown in Fig. 2.11, is asymmetric, with a minimum at ~0.4°. Calculated results obtained for four missing row models proposed for this surface are also shown,

Fig. 2.11. Angular scans in the (111) plane through the [101] axis (left panel) and in the (100) plane through the [100] axis (right panel). Negative (positive) angles represent incidence at angles closer to (farther from) the surface normal than the low index axes. Circles are the experimental data, and solid lines are computer simulations on (a) Robinson model, (b) Moritz-Wolf model, (c) Hemme model, and (d) Marks model.

and parameters used for the calculations are listed in Table 2.2. Experimental data and calculations for the same four models for an angular scan around the [100] axis are given in the right panel of Fig. 2.11. The experimental scan is asymmetric, with a minimum at approximately -0.3°.

In Fig. 2.11 the poor agreement between experimental data and calculations based on the Marks model for the [101] axis and the Moritz-Wolf model for the [100] axis rule out these models for further consideration. The Robinson model predicts the surface yield reasonably well. The Hemme model calculations come close to matching the position and shape of the minimum for both axis scans although the surface yields are several tenths of atoms per row too low. Small modifications in the crystallographic and vibrational

Table 2.2. Parameters used in the model calculations presented in Figs. 2.11 and 2.12. Values in parentheses are not given in reference and have been assumed. Δd_{12} and Δd_{23} represent the change in layer spacing between the first-to-second and second-to-third layers, respectively. All models assume a second layer pairing of [101] rows. Δy_2 represents lateral translations of the second layer rows from bulk lattice sites. $\langle x^2 \rangle^{1/2}$ is the bulk mean square thermal vibration, and SVF is the multiplication factor for $\langle x^2 \rangle^{1/2}$ to account for increased thermal vibrations for atoms in the top two layers.

Model	Δd_{12}	Δd_{23}	Δy_2 (Å)	$\langle x^2 \rangle^{1/2}$	SVF	Reference
Moritz-Wolf	-0.22 ± 0.04	0.0 ± 0.05	0	0.087	(1.5)	4
Robinson	0.62 ± 0.40	0	0.12 ± 0.12	0.084	1.55 ± 0.36	5
Marks	0.29 ± 0.07	0	0	(0.087)	(1.5)	9
Hemme	-0.25	0.10	0.08	(0.087)	(1.5)	12
Hemme-modified	-0.25	0.10	0.12	0.089	1.55 ^a	

^aWith enhancement of 1.25 in the third layer.

parameters are sufficient to increase the yields to those of the experiments.

Calculations for the Robinson model and the modified Hemme model are given in Fig. 2.12. The results for both models reasonably match both the intensity of the experimental data and the asymmetry. However, none of the calculated results predicts the experimental width. Finally, while several proposed structures have been ruled out the present results show that missing row models of the surface incorporating either a large expansion or small contraction in the outer layer appear capable of explaining the yield and asymmetry of the angular scans.

1. Summary of paper to be published.
2. B. R. Appleton et al., *Solid State Div. Prog. Rep.*, September 30, 1978, ORNL-5486, p. 38.
3. J. R. Noonan et al., *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 42.
4. W. Moritz and D. Wolf, *Surf. Sci.* **88**, 629 (1979).
5. I. Robinson, *Phys. Rev. Lett.* **50**, 1145 (1983).
6. Y. Kuk, L. C. Feldman, and I. K. Robinson, *Surf. Sci.* **138**, L168 (1984).
7. S. H. Overbury et al., *Surf. Sci.* **109**, 239 (1981).
8. M. Manninen, J. K. Norskov, and Cyrus Umrigar, *Surf. Sci.* **119**, L393 (1982).
9. L. D. Marks, *Phys. Rev. Lett.* **51**, 1000 (1983).
10. J. H. Barrett, *Phys. Rev. B* **3**, 1527 (1971).
11. H. R. Schober, M. Mostoller, and P. H. Dederichs, *Phys. Status Solidi* **64**, 173 (1974); M. Mostoller (private communication).
12. H. Hemme and W. Heiland, *Nuclear Instruments and Methods* (in press).

Fig. 2.12. Comparison of experimental angular scans with computer simulations based on (a) the Robinson model and (b) a modified Hemme model. [101] axis scans are given in left panel and [100] scans in right panel. Hemme model calculation for the [100] axis has been normalized by a factor of 1.03.

TRUNCATION-INDUCED RELAXATIONS FOR A HIGH-INDEX SURFACE¹

J. R. Noonan H. L. Davis
W. Erley²

The electronic properties of interfaces, grain boundaries, and defects in solids are areas of increasing research interest. However, quantitative information concerning such properties is not readily available because of problems in obtaining direct experimental information about the interface or defect region. Recent advances in experimental and theoretical studies of the vacuum-solid interface (i.e., the surface) may provide information which will be useful in analyzing other interfaces such as grain boundaries. For example, it was not until theoretical bulk electronic band structure predictions agreed with a physically measurable quantity, the Fermi surface in this case, that significant advances could be made in the band theory of metals. Once the theoretical formalism could be successfully tested against a measurable quantity, the theory then could be used to obtain properties which were not measured as easily. In a similar way, the measured crystallographic and electronic properties of a surface provide a test for theoretical formalisms of interfaces.

Recently developed theories of metal surfaces have predicted that, due to electrostatic forces on the atoms at the surface, several of the outermost layers of atoms relax away from the truncated bulk lattice positions³⁻⁵ (i.e., multilayer relaxation of the surface). Concurrently, due to advances in LEED analysis of surfaces, multilayer relaxations of surfaces have been identified for many metals.^{6,7} Importantly, results for analysis of the Al(110) surface illustrate that the agreement between different experimental results is noteworthy^{6,7} and that the agreement between theoretical predictions and experimental results is very good.³⁻⁷

In view of the remarkable success for the structure determination of the Al(110) surface, extending the study to other aluminum surfaces should prove informative. The Al(311) surface provides an interesting surface on which to perform a LEED analysis. Due to asymmetric placement of the adjacent planes of atoms, the Al(311) has an oblique unit cell, a small interplanar spacing, and a single mirror plane. The surface could be displaced laterally as well as vertically such as found for bcc (211) surfaces.^{8,9}

An ordered Al(311) could be obtained easily by Ar⁺ ion sputter cleaning and annealing to ~500°C. The sputter cleaning easily removed adsorbed contaminants at the surface. However, due to a large segregation coefficient, a small amount of Si (<0.05% as measured by the derivative AES peak heights using a CMA) was present at the surface. Several tests were performed to demonstrate that the Si appeared to have no significant effect on the experimental LEED I-V spectra.

The theoretical I-V spectra were calculated using computer codes developed at ORNL. Due to the relatively small interplanar spacing (~1.22 Å), reverse scattering perturbation formalism¹⁰

was employed because it converges more rapidly and is more stable than other perturbation techniques for small interplanar spacings. To ensure that the determined structure was not an artifact of the perturbation technique, tests were performed using the full dynamical calculations of the LEED spectra for selected structures. Although the analysis of the Al(311) did not include as extensive a study of nonstructural parameters as other studies, it has been determined that the nonstructural parameters do not significantly affect the determined surface structure when the study is near the optimum values. The best agreement between calculated and measured spectra, so far, was found using $\theta_p = 550$ K, $V_{01} = -4.75$ eV, $V_{pr} = 10.9$ eV, and the Moruzzi-Janak-Williams band structure potential.¹¹ In addition, two reliability factors were tested to ensure that no systematic differences resulted from the sensitivity of the analysis to the R-factor algorithm.

The quality of agreement is illustrated by the R factors calculated for relaxations of the first and second atomic planes. As shown in Fig. 2.13, the R factors are plotted as functions of the relative changes of the first interplanar spacing Δd_{12} and the second Δd_{23} . The R_2 relates the mean square difference between calculated and measured spectra,¹² and R_{ZJ} refers to the Zanazzi-Jona reliability factor formalism.¹³ Several features of the analysis are illustrated in this figure. First, the quality of the agreement (as determined by the value of the R factor) is very sensitive to Δd_{12} and Δd_{23} . Second, the R value at no relaxation ($\Delta d_{12} = \Delta d_{23} = 0$) is significantly larger than the value of the best agreement (the minimum of the topograph), which strongly suggests that the surface layers are relaxed away from the truncated bulk position. Additionally, it is clear that the relaxations of both layers need to be considered. For example, if only Δd_{12} was considered ($\Delta d_{23} = 0$), the predicted relaxation from the analysis of R_2 is -16%, whereas the single layer relaxation predicted using R_{ZJ} is -10%. However, when Δd_{23} is allowed to relax, not only are both R values reduced significantly but also the predicted

Fig. 2.13. R_2 and R_{ZJ} topographs for 34 LEED beams as a function of relative changes in the first, Δd_{12} , and second, Δd_{23} , interplanar spacings. The (0,0) point corresponds to no relaxation of the surface.

values from R_2 ($\Delta d_{12} = -13.3\%$, $\Delta d_{23} = +8.8\%$) and R_{ZJ} (-12.3% , $+9.2\%$) are in good agreement since a 1% difference is only ~ 0.012 Å.

The relaxations of the first two interplanar spacings can also be demonstrated visually. Figure 2.14 compares the measured I-V spectra (curve c) with the calculated spectra for the truncated bulk structure (curve d: $\Delta d_{12} = 0$, $\Delta d_{23} = 0$); the structure in which only the first layer was allowed to relax to the best agreement (curve a: $\Delta d_{12} = -10\%$, $\Delta d_{23} = 0$); and for the case where both d_{12} and d_{23} were optimized self-consistently (curve b: $\Delta d_{12} = -13.3\%$, $\Delta d_{23} = +8.8\%$) for the (20), (02), (21), and (12) LEED beams. Each calculated spectrum is compared to the measured spectrum using the single beam R_{ZJ} . As is apparent, the quality of the agreement between the measured spectra and the calculated spectra for $(-13.3\%, +8.8\%)$ is good. The improvement in agreement between the best model and the one for no relaxations is especially notable.

As noted earlier, LEED analyses of some high-index surfaces have identified lateral as well as vertical displacements of the surface plane.^{8,9} Therefore, the effects of lateral displacements of the first layer with respect to the second were also examined. Importantly, the analysis did not identify any lateral displacement of the surface layer.

In conclusion, although the Al(311) surface is reasonably complex, since it has an oblique unit cell with the second layer not centered

Fig. 2.14. I-V spectra for the (20), (02), (21), and (12) beams. Curve a: calculated for $(\Delta d_{12} = -10\%, \Delta d_{23} = 0\%)$; curve b: calculated for $(-13.3\%, +8.8\%)$; curve c: experimental; curve d: calculated for (0,0). The (10) beam is along the [233] direction. The single-beam R_{ZJ} factor which resulted when the respective calculated profile was compared with the experimental spectrum profile is given with each calculated spectrum.

PLASMA-MATERIALS INTERACTIONS

TIME-RESOLVED IMPURITY FLUXES
IN THE TEXTOR PLASMA EDGE¹R. A. Zuhre W. R. Wampler²

with respect to the first and a small interlayer spacing, the structure of the Al(311) surface was determined to a reasonable accuracy using LEED I-V analysis. The model which provides the best quality of agreement with the measured LEED spectra had $d_{12} = -13.3 \pm 1.1\%$ and $d_{23} = +8.8 \pm 1.5\%$ or $d_{12} = 1.068 \text{ \AA}$, $d_{23} = 1.335 \text{ \AA}$ ($d_{\text{bulk}} = 1.227 \text{ \AA}$). The agreement yielded an R_{ZJ} of 0.07. Further analysis of the structure is in progress in which the effects of deeper relaxations and second layer lateral displacements are being assessed.

Now that the surface structures of the Al(110) and Al(311) have been determined, these results can be used to test the predictive quality of some of the current theories of surface relaxations. It is hoped that this will be done in the near future.

1. Summary of paper: Surface Science (in press).
2. Guest scientist from Kernforschungsanlage Jülich, Federal Republic of Germany.
3. U. Landman, R. N. Hill, and M. Mostoller, Phys. Rev. B **21**, 448 (1980).
4. R. N. Barnett, U. Landman, and C. L. Cleveland, Phys. Rev. B **28**, 1685 (1983).
5. K. M. Ho, S. Auluck, and K. P. Bohnen, Proceedings of the International Conference on the Structure of Surfaces, Berkeley, Calif., August 13-16, 1984.
6. J. N. Andersen et al., J. Phys. C: **17**, 173 (1984), and references within.
7. J. R. Noonan and H. L. Davis, Phys. Rev. B **29**, 4349 (1984), and references within.
8. H. L. Davis and G.-C. Wang (to be published).
9. J. Sokolov, F. Jona, and P. M. Marcus, Solid State Comm. **49**, 307 (1984).
10. R. S. Zimmer and B. W. Holland, J. Phys C **8**, 2395 (1975).
11. V. L. Moruzi, J. F. Janak, and A. R. Williams, p. 55 in Calculated Electronic Properties of Metals, Pergamon Press, New York, 1978.
12. M. A. Van Hove, S. Y. Tong, and M. H. Elconin, Surf. Sci. **64**, 85 (1977).
13. E. Zanazzi and F. Jona, Surf. Sci. **62**, 61 (1977).

The internal configuration of the TEXTOR tokamak at Kernforschungsanlage (KFA) Jülich, FRG, has been modified recently to include antennas for ion cyclotron resonance heating (ICRH) of the plasma. Passive deposition probe measurements of edge impurity fluxes were made for typical ohmic discharges with this new liner configuration. The time-resolved behavior of impurities in the edge was determined as a function of radius and limiter position using rotating probe techniques. All exposures were made for standard ohmic hydrogen discharges having the following parameters: toroidal field = 2 T, plasma current = 340 kA, line average electron density = $2-3 \times 10^{13} \text{ cm}^{-3}$, central electron temperature 1-1.5 keV, and discharge length = 2.5 s. After exposure the samples were removed and transferred in air to an MeV accelerator facility where Rutherford backscattering (RBS) was used to determine quantitatively the amounts of impurities retained on the samples. Present results are compared with previous measurements of edge fluxes made prior to modifications to the plasma-side liner of TEXTOR.

The amounts of impurity elements detected in the scrapeoff layer of TEXTOR at 2 and 5 cm behind the limiter radius are given in Table 2.3. The numerical values are the average fluxes retained in the electron drift direction for exposures that are time integrated over nondisruptive ohmic discharges. The most common element in the edge is seen to be oxygen, with maximum time-average fluxes on the order of $5 \times 10^{15} \text{ cm}^{-2} \text{ s}^{-1}$. The most abundant metallic elements are the components of stainless steel, iron, chromium, and nickel. Lesser amounts of molybdenum, which is a component in one of the inconel alloys used in TEXTOR, and traces of tungsten or tantalum are also observed. Titanium, the material from which the probe slits were made, is not present on the samples. The ratio of iron-to-chromium-to-nickel found on the probes is approximately 8:2:1. Nickel, the major constituent of inconel, is present in smaller amounts than either iron or chromium. Such a result indicates that the metallic impurities originate from stainless

Table 2.3. Time-average-retained impurity fluxes in the electron drift direction for ohmic hydrogen discharges in TEXTOR ($\text{cm}^{-2} \text{ s}^{-1}$).

r_p	$r_p - r_l$	O	Fe	Cr	Ni	Mo
47 cm	2 cm	5.8×10^{15}	2.8×10^{15}	7.8×10^{14}	3.4×10^{14}	2.4×10^{13}
50 cm	5 cm	4.9×10^{15}	1.0×10^{15}	2.7×10^{14}	1.2×10^{14}	1.1×10^{13}

steel components, such as the limiters, rather than from the inconel liner.

The radial dependence of the impurity deposition was measured as a function of time during ohmic discharges. The time dependence of radial distributions in the electron drift direction for stainless steel (Fe, Cr, and Ni), oxygen, and molybdenum is shown in Fig. 2.15. Here the retained flux is plotted as a function of the tokamak minor radius at six different times during the 2.5-s discharges. Time resolution for these data is ± 370 ms. On this time scale it is clear that the radial distribution of impurities is a smoothly varying function of time. The magnitude of the distribution rises from a flat background to a maximum during the central portion of the discharge and then slowly decays. There is no indication of accumulation of impurities in the edge as the discharge progresses. This is an important result and confirms data obtained in earlier TEXTOR discharges.³ All the metallic impurities share a similar radial profile, decreasing monotonically with radius and showing a slight flattening near the limiters. Although the curves are not well represented by an exponential decay, an approximate e-folding length of 2.5 cm for the metals can be determined. The relative increase in the slope of the profiles at about 49 cm is believed to be due to the fixed inner limiter at 49 cm and the limiting action of the newly installed rf antennas which are located just inside this radius. In contrast to the metals, the flux of retained oxygen is far more uniform over the region of interest, showing only a ~30% decrease between radii of 47 and 52 cm. The amount of oxygen retained also peaks later in the discharge than that of the metals. These results suggest that the source and mechanism for introduction of oxygen into the plasma are different from those of the metals.

are different from those of the metals.

In comparison with measurements made prior to modification of the liner, several changes are observed. The radial dependence of the impurities now shows a clear decrease with distance behind the limiter that may have been smeared by plasma instability in earlier exposures. The previous increase in metallic fluxes near the liner is no longer observed, perhaps because of decreased contact between the plasma and the liner due to the limiting effect of the antenna installation. The deposited fluxes of oxygen are approximately the same, indicating a similar level of wall conditioning, but the flux of transition metals has increased by a factor of 2-3. The relative amounts of iron, chromium, and nickel have also changed. The relative amount of iron has increased, while that of nickel has decreased, indicating relatively less interaction between the plasma and the inconel liner. In combination these changes point toward a more stable plasma that is better confined by the limiters and interacts less strongly with the first wall.

1. Summary of paper: *Journal of Vacuum Science and Technology* (in press).
2. Sandia National Laboratories, Albuquerque, N.M.
3. R. A. Zuhr, *J. Nucl. Mater.* 122-123, 1193 (1984).

ORNL-DWG 84 15671R

Fig. 2.15 Time evolution of the radial dependence of impurity fluxes for stainless steel, molybdenum, and oxygen. Data are for ohmic hydrogen discharges in the electron drift direction at -0.5 s (▲), -0.2 s (△), 0 s (■), 1.6 s (□), 2.3 s (●), and 3.0 s (○).

DEUTERIUM FLUXES IN THE TEXTOR PLASMA EDGE USING DEPOSITION PROBE TECHNIQUES¹

R. A. Zuhr

Deposition probe techniques have proven to be effective methods of studying the plasma edge region of magnetic confinement fusion devices.² In the present work, the application of these techniques to measure the deuterium fluxes in the scrapeoff layer of the TEXTOR tokamak at KFA Jülich, FRG, is described.

Deposition probe exposures using carbon (Papyex) collectors were made along a major radius in the horizontal midplane of TEXTOR $\sim 19^\circ$ in the ion drift direction from the main outside limiter. Insertion and positioning of the probe were microprocessor controlled with complete electrical isolation, using optical couplers, between the tokamak and the diagnostic area.³ Exposures were made as functions of radius and direction. Time-resolved measurements were made by electrically rotating a cylindrical sample behind a fixed slot. All exposures were made with the probe at floating potential. After exposure the samples were transferred in air to an accelerator facility, where elastic recoil detection (ERD) with 1.75-MeV ^4He at 30° and nuclear reaction analysis (NRA) with the $\text{D}(^3\text{He},p)^4\text{He}$ reaction were used for analyses of the retained hydrogen isotopes. Typical operating parameters during the present investigations were toroidal field, ($B_t=2$ Tesla), toroidal current ($I_p=300$ kA), and average electron density ($\bar{n}_e=2 \times 10^{13}/\text{cm}^3$).

Time-resolved deuterium (D) deposition rates were measured with a time resolution of ± 150 ms using the rotating system previously described. The results are plotted in Fig. 2.16 along with independent measurements of the loop voltage V , plasma current I_p , and average electron density $\bar{n}_e$, for exposures to two different sets of D discharges. The upper D curve presents the flux deposited on a carbon probe exposed in the ion direction to three discharges that are typified by the voltage, current, and density traces above it. The discharges last 2.5 s and show minimal disruptive activity as demonstrated by the constant loop voltage. After the initial peak, which has been observed during start-up in the scrapeoff layer of many machines,² the retained flux is low and steady, indicating a stable, centered plasma that is not interacting strongly with the limiters. These discharges also show the lowest levels of metallic impurities in the plasma edge.

The lower half of Fig. 2.16 shows the deuterium retained on samples exposed to five discharges in the electron direction, two of them as just described and three as typified by the lower set of voltage and current curves. Here the discharges become disruptive, as evidenced by spikes in the loop voltage, and terminate in less than 1 s. The disruptive behavior results in increased D flux to the probe from 0.5 to 1 s. Substantially higher metallic impurity levels are also observed for this type of discharge.

A number of exposures were made to determine the trapping or saturation behavior of hydrogen and deuterium in the probe material. Such data can be used to estimate the flux and energy of

Fig. 2.16. Time-resolved D retention rate is compared with loop voltage V , plasma current I_p , and average density $\bar{n}_e$, for two different discharge types in TEXTOR.

the incident particles.² At 3 to 7 cm outside the limiter radius the incident deuterium fluence was estimated to be $1\text{--}1.5 \times 10^{16}/\text{cm}^2\text{-discharge}$ with a Maxwellian energy distribution and $kT = 100$ eV.

Measurements of the in situ erosion rate of a 2.5-nm gold film deposited on a polished silicon substrate were also made. The film thickness was measured before and after exposure to the plasma edge using RBS. Erosion rates in TEXTOR for samples perpendicular to the magnetic field in the ion drift direction were close to the limits of detection in both hydrogen and deuterium plasmas, making accurate measurements difficult. However, the average erosion rate for radii between 3 and 7 cm behind the limiter was found to be $\sim 5 \times 10^{13}$ atoms/ $\text{cm}^2\text{-s}$, and an upper limit on erosion of $10^{14}/\text{cm}^2\text{-s}$ during normal discharges can be assigned.

1. Summary of paper: *J. Vac. Sci. Technol. A* 2, 686 (1984).

2. R. A. Zuhr, J. B. Roberto, and B. R. Appleton, *Nucl. Sci. Appl.* 1, 617 (1984).
 3. R. A. Zuhr and J. B. Roberto, *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 51.

THE INFLUENCE OF IMPURITIES ON THE HIGH-TEMPERATURE SPUTTERING YIELD OF GRAPHITE¹

J. Roth² J. Bohdanský²
 J. B. Roberto

The influence of surface and bulk impurities on the chemically enhanced sputtering of graphite near 600°C and the radiation-enhanced sublimation of graphite above 1000°C has been investigated. Such investigations yield additional information on the mechanisms of high-temperature erosion processes in graphite and may lead to procedures for minimizing the erosion rates. In particular, an understanding of the effect of simultaneous impurity fluxes on the enhanced erosion could be important in determining the usefulness of graphite as a high-temperature plasma-side material in fusion reactors.

The chemical sputtering yield for 500-eV H ion bombardment of graphite at 600°C was investigated at the Max-Planck-Institut high-current ion source for graphite samples with deposited layers of Au, Fe, Ni, Ti, and Mo. For the Au, Fe, and Ni films, clustering of the deposited films allowed high chemical sputtering (methane) yields despite average surface coverages of many monolayers. For the nonclustering Ti and Mo films, suppression of the chemical sputtering yield was approximately a factor of 2 with one monolayer coverage. Addition of bulk impurities (4 at. % Si) was most effective in suppressing the chemical sputtering of graphite.

The radiation-enhanced sublimation of graphite bombarded at 1520°C by 50-KeV Ar ions was investigated during simultaneous Ti evaporation onto the surface at the ion implantation facility in the Solid State Division. The Ti concentration in the near surface has a strong influence on the ion-enhanced sublimation yield as shown in Fig. 2.17. Low concentrations of Ti initially increase the carbon erosion yield, while concentrations above 10 at. % lead to a nearly complete suppression of the enhanced yield. The increase in carbon erosion at low Ti concentrations is attributed to the occupation of vacancies by Ti atoms, allowing additional carbon interstitials to diffuse to the surface and evaporate.

Overall, the results indicate that suppression of high-temperature erosion processes in graphite can occur for sufficiently high surface coverages and bulk concentrations of impurities. Furthermore, the effectiveness of bulk impurity concentrations in reducing erosion rates indicates that the chemical and radiation-enhanced erosion processes originate at depths beyond the surface layer.

1. Summary of paper: *Journal of Nuclear Materials* (in press).

2. Max-Planck-Institut für Plasmaphysik, Garching bei München, Federal Republic of Germany.

Fig. 2.17. Sputtering yield as a function of Ti near-surface concentration for a graphite sample at 1520°C simultaneously bombarded by 50-keV Ar ions and an evaporated Ti flux.

USE OF ISOTOPICALLY ENRICHED CARBON PROBES FOR EROSION/DEPOSITION MEASUREMENTS IN THE ASDEX DIVERTOR¹

J. B. Roberto J. Roth²
 E. Taglauer² O. W. Holland

An isotopic marker technique has been developed and used to measure near-surface erosion and carbon and impurity deposition on carbon samples exposed in the ASDEX divertor chamber. Papyex graphite samples were enriched to ~20% ¹³C over the first 1000 Å by ion implantation. The implanted ¹³C can be clearly distinguished from ¹²C of the host by RBS using 2.7-MeV ⁴He. Carbon erosion and deposition can be determined from changes in the depth distribution of the ¹³C while impurity accumulation is simultaneously monitored in the backscattering spectrum. Laboratory experiments have demonstrated the stability of the ¹³C distribution under severe thermal conditions, including low-energy hydrogen bombardment at temperatures above 1800 K. Other experiments have demonstrated the usefulness of the probes in sputtering, ion mixing,³ and self-diffusion studies.

In ASDEX, the ¹³C-enriched probes intercepted a cross section of the diverted flux in front of the upper divertor plate. Both integrated and time-resolved exposures were made for plasmas with neutral injection or lower hybrid auxiliary heating. Profiles of ¹³C remained sharp in spite of high heat fluxes to the samples (sufficient to melt stainless steel) and showed clear evidence of simultaneous erosion and deposition of carbon and impurities.

Time-resolved results for diverted discharges with 3.1-MW neutral injection are shown in Fig. 2.18. These data are for a carbon sample that was rotated behind a slit facing the diverted flux centered in front of the upper divertor

Fig. 2.18. Time-resolved erosion/deposition for a ^{13}C probe centered in front of the upper divertor plate for ten ASDEX discharges with 3.1 MW of neutron injection at 1.1–1.3 s.

plate. Carbon erosion increases rapidly in the beginning of the discharge to exceed 250 Å/s (erosion of the entire ^{13}C layer) at 0.6 s. This large erosion rate is observed in spite of the accumulation of ~60 Å of Fe and Ti (from the walls) on the probe, indicating mixing of the impurities in the near surface. During neutral injection, erosion remains high, but impurity accumulation ceases at the center of the divertor plate. This high erosion may correspond to the low confinement phase at the beginning of neutral injection, which results in significant increases in power flux to the divertor. Following injection, net deposition of C is observed along with a slight accumulation of Fe and Ti. The shift from carbon erosion to deposition corresponds to a reduction in plasma density which could result in lower heat fluxes in the divertor throat.

Extrapolated to steady state, the erosion rates observed in the divertor would correspond to ~50 cm/y or 35 cm/y for the grazing incidence surface of a limiter or divertor plate. The observed erosion is consistent with a sputtering yield of ~0.1 for estimated ion fluxes to the probe, which corresponds to the erosion yield for 100-eV hydrogen ions on graphite at 1500°C. Erosion would be substantially reduced for probe temperatures below 400°C. These results are for the highest flux region in the ASDEX divertor (~ 10^{19} D/cm²-s) and suggest that erosion is much

larger than impurity deposition under high-power conditions at the divertor plate. The results also demonstrate the applicability of the 130 technique for erosion/deposition experiments at high heat-flux surfaces in the plasma edge.

1. Summary of paper: *Journal of Nuclear Materials* (in press).

2. Max-Planck-Institut für Plasmaphysik, Garching bei München, Federal Republic of Germany.

3. D. B. Pcker et al., "Ion Mixing Studies of Self Isotopes in Graphite," this report.

4. J. Roth, J. B. Roberto, and K. L. Wilson, "Ion-Enhanced Erosion of Graphite at High Temperature," this report.

ION-ENHANCED EROSION OF GRAPHITE AT HIGH TEMPERATURE¹

J. Roth² J. B. Roberto
K. L. Wilson³

Previously reported^{4,5} measurements of the enhanced physical erosion of graphite under energetic ion bombardment above 1000 K have been extended to include determination of the activation energy and threshold ion energy for the effect. The enhanced erosion is characterized by the near thermal release of carbon atoms⁶ and is not associated with the release of volatile compounds observed during the chemical sputtering of graphite by hydrogen ions at 700–1000 K. The process results in effective sputtering yields at 2000 K of 10–20 times the room temperature value and seriously limits the usefulness of graphite as a high-temperature plasma-side material in fusion reactors.

The erosion measurements were performed using 35- to 150-keV H, C, O, and Ar ions from the Solid State Division's ion implantation accelerator and 0.13- to 8-keV H ions from the high-current ion source at Max-Planck-Institut, Garching. Papyex graphite samples were heated resistively to temperatures up to 1800 K in the implant chamber, with C erosion yields determined from the analysis of catcher probes and by weight change. Temperature-dependent erosion yields are consistent with activation energies for the enhanced erosion process, which vary from 0.5 eV for heavy ions to 1.1 eV for low-energy light ions. Such activation energies would lead to significant thermal evaporation at temperatures well below 1000 K, assuming normal pre-exponential factors. The ion-enhanced erosion is not observed below 1000 K, suggesting that additional steps beyond evaporation are involved in the erosion process. For comparison, the activation energy for ordinary thermal sublimation of graphite is ~8 eV.

The threshold behavior of the erosion yield at 1800 K is indicated for incident H ions in Fig. 2.19. The solid and dashed curves in the figure are TRIM calculations of the nuclear deposited energy at the surface for the incident conditions, assuming a 5- and 30-eV displacement threshold, respectively. Also shown in Fig. 2.19 are similar data and calculations for Ar, C, and D ions on graphite. All of the energy-dependent

Fig. 2.19. Energy dependence of the erosion yield and the calculated nuclear deposited energy for H, D, C, and Ar on graphite at 1800 K.

data scale approximately with the deposited energy. The low-energy H measurements suggest an effective displacement threshold of ~5 eV for the enhanced erosion process.

There is a considerable body of evidence which suggests that the enhanced erosion of graphite under ion bombardment above 1000 K is a radiation-enhanced sublimation process.⁴⁻⁶ The present results further clarify the importance of radiation damage in the process, since the enhanced yields are proportional to nuclear deposited energy at the surface for a wide spectrum of incident ion energies and masses. These results, along with the activation and threshold energy data, have led to the development⁷ of a model for the effect which assumes the creation of interstitial-vacancy pairs in the bulk graphite due to the ion bombardment and the subsequent diffusion of interstitials to the surface where they evaporate. This model can explain the observed temperature and energy dependence of the erosion yield using activation energies for interstitial and vacancy diffusion taken from radiation damage theory.

1. Summary of paper: *Journal of Nuclear Materials* (in press).

2. Guest scientist from Max-Planck-Institut für Plasmaphysik, Garching bei München, Federal Republic of Germany.

3. Sandia National Laboratories, Livermore, Calif.

4. J. Roth, J. Bohdansky, and K. L. Wilson, *J. Nucl. Mater.* 111/112, 775 (1982).

5. J. Roth, J. B. Roberto, and K. L. Wilson, *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 51.

6. V. Philipps, K. Flaskamp, and E. Vietzke, *J. Nucl. Mater.* 111/112, 781 (1982).
7. J. Roth and W. Möller (to be published).

BERYLLIUM LIMITER STUDIES IN ISX-B

R. A. Zuhr J. B. Roberto

Beryllium has been suggested as a promising material for plasma-side components in tokamaks and is being considered for use in the Joint European Torus. Its advantages of low Z, good thermal conductivity, and low self-sputtering coefficient may be compromised by its low melting point and handling complications arising from its toxicity. For these reasons metallic beryllium limiters were tested in a plasma environment in the ISX-B tokamak.

A number of different studies of conditions in the plasma edge were made during the beryllium limiter operation. The limiter tiles were weighed with milligram precision before and after operation so that gross erosion and redeposition could be determined. One of the tiles was implanted with 320-keV silicon ions as a depth marker so that changes in the thickness of the surface layer could be monitored. The amounts of impurities and deuterium retained in different sites on the limiter surface will also be measured using accelerator-based analysis techniques. In addition to these measurements on the limiter itself, two collection probe experiments were made to look at both beryllium transport and scrapeoff layer parameters. In one of these, long-term silicon collection samples were placed at the wall position in a variety of locations to measure the redistribution of beryllium around the tokamak. In the other probe experiment, a rotating silicon collector was exposed during an ohmic discharge in order to measure time-resolved beryllium, impurity, and deuterium fluxes. Analysis of all of these samples, as well as the beryllium limiter tiles themselves, is currently under way. Initial results indicate substantial erosion from the central portion of the limiter (<40 mg/cm²) with redeposition dominant at the edges of the limiter.

SYNERGISTIC EFFECTS IN PLASMA SURFACE INTERACTIONS¹

J. B. Roberto R. Behrisch²

An improved understanding of the interaction between the plasma and exposed surfaces in fusion devices is central to the resolution of many technological issues in fusion research. Plasma surface interactions are critical factors in impurity control, fuel management, and materials performance in fusion reactors. Although considerable progress has been made toward understanding the fundamental processes involved in plasma surface interactions, the correlation between the basic phenomena and actual in situ observations requires careful consideration of possible interactive or synergistic effects among the many processes which occur simultaneously at plasma-side surfaces.

In this paper, possible synergistic effects which can contribute to plasma surface interaction phenomena in fusion devices are reviewed. These effects include the influence of reactive ions, surface modification, temperature, radiation damage, external forces and fields on erosion yields, hydrogen retention and release, and other surface processes. The important synergistic effects are described in terms of surface and edge conditions encountered in present fusion devices and expected in future reactors. Priority data needs include the chemical erosion of graphite at high particle fluxes, melt-layer stability under disruption-induced eddy current forces, the influence of bulk neutron damage on hydrogen retention, and in situ measurements of synergistic effects in operating fusion devices.

1. Summary of paper: Journal of Nuclear Materials (in press).

2. Max-Planck-Institut für Plasmaphysik, Garching bei München, Federal Republic of Germany.

TIME-RESOLVED EROSION MEASUREMENTS AT A REFERENCE LIMITER IN ISX-B USING LASER-INDUCED FLUORESCENCE¹

T. B. Cook P. W. King²
J. B. Roberto K. A. Stewart²
K. E. Yokoyama³

We report time-resolved laser-induced fluorescence measurements for erosion of a probe limiter in which particles are removed primarily by bombardment due to the circulating ion flux in the edge. The released neutral particles are then followed toroidally in the edge plasma until they become ionized. For the case of a particular ohmically heated discharge in a titanium-gettered vessel, we have also determined the ionization length of the released atoms, compared the erosion rate for D₂ and H₂ discharges, and correlated the results with Langmuir probe data. Finally, the implications of these results for limiters in a reactor-scale device are briefly considered.

For these measurements the excitation laser beam was apertured to be 2 mm wide by 3 mm high and passed immediately in front of the reference limiter surface as shown in Fig. 2.20, which also gives the view from the fluorescence collection window on top of the vacuum vessel. The interrogated volume, which is 2.5 cm outside the radius of the main outer limiter, is defined by the intersection of the laser beam with the collection cone of the detection optics and is indicated by the shaded region in the figure. During most measurements the erosion surface faced toward the plasma current. Density calibration was performed by measuring the fluorescence signal from titanium atoms present during gettering cycles. The gettering source strength was determined by deposition measurements near the time of the fluorescence determination. In these experiments, for a type-304 stainless steel surface, a calibration factor for FeI detection was calculated relative to the absolute TiI sensitivity.

Fig. 2.20. View of the erosion probe and laser beam as seen from above by the detection optics. The center of the tokamak is toward the top.

The ionization length for iron released from the probe limiter during ohmically heated discharges was determined by measuring the atomic density at several distances from the probe face. Including corrections for the finite probe dimensions and a velocity dependence typical of sputtering, an ionization length of 0.8–0.9 cm was calculated. This value compares well with the expected ionization length based on Langmuir probe measurements taken during this sequence, which yielded an estimated ionization length of 0.74 cm, assuming atomic velocities typical of release by sputtering.

Ionization length measurements have also been performed to detect titanium from a TiC-on-graphite probe during neutral-beam-heated discharges. For this case, an ionization length of 0.1–0.3 cm was estimated, which is qualitatively consistent with the more complete data for ohmically heated discharges, given the increased edge densities encountered in beam-heated discharges.

Determining erosion rates is somewhat more difficult than measuring ionization lengths, due in part to the need for absolute calibration of the system (40% uncertainty) and in part to the need to determine the position of the eroded surface with respect to the laser beam (10% density uncertainty). The solid curve in Fig. 2.21 shows the erosion rate, obtained by extrapolation to the probe face, for an ohmically heated deuterium discharge as a function of discharge time. The first peak in the data near $t = 0$ is associated with the discharge initiation. The second and largest peak seems to be associated with a period of poor confinement at low density

Fig. 2.21. Measured erosion during the discharge. Closed circles are for a deuterium plasma. The solid line is included to lead the eye. The dashed line corresponds to a hydrogen-fueled plasma.

immediately before the strong gas puff was applied. From 150 through 250 ms the plasma was stable, and erosion rates were relatively low at a level of 8×10^{14} atom $\text{cm}^{-2} \text{s}^{-1}$. The final peak is associated with a disruptionless termination of the discharge. During the time from 250 to 280 ms the plasma current was ramped steeply to zero. This was accompanied by a sharp outward movement of the plasma as it left the inner rail limiter, on which it leans during most ISX-B shots, and shifted to the outer mushroom limiter. The erosion peak is due to the combination of the shift several centimeters outward toward the probe limiter and the poor confinement during this phase of the discharge.

The measured erosion may be compared with the expected rate based on particle loading. The reference limiter was not instrumented to measure the ion saturation current directly, but an estimate is available from the Langmuir probe data, giving 3.5×10^{18} ion $\text{cm}^{-2} \text{s}^{-1}$. This value is in good agreement with biased probe⁴ and deposition probe⁵ measurements at the same minor radius in ISX-B. With a sputtering yield of 1×10^{-3} for monoenergetic 60-eV D^+ , an estimated ion flux of 3.5×10^{15} atom $\text{cm}^{-2} \text{s}^{-1}$ leaving the probe face is calculated, in good agreement with the measured flux of 8×10^{14} . Integrating the measured erosion over the shot gives a total loss of 3.5×10^{15} atom/discharge. This compares well with a value of 5×10^{14} obtained by gold erosion measurements at the same location in ISX-B.⁶

Also shown in Fig. 2.21 is the comparable erosion rate for a hydrogen-fueled plasma with the same nominal parameters. Although the ratio of erosion rates varies somewhat during the course of the discharge, the results are largely consistent with the factor of ~ 3 expected for particle release by near-threshold physical sputtering.

Extrapolation of the reference limiter results to the location of the outer mushroom limiter in ISX-B is also of interest. The e-folding lengths for the ion saturation current have been measured⁴ by biased probe methods to be 2 cm. The ion flux density to the mushroom limiter is then 3.5 times higher than that measured in this experiment or 1×10^{19} ion $\text{cm}^{-2} \text{s}^{-1}$. For the same sputtering yield, this results in an erosion of 1×10^{16} atom $\text{cm}^{-2} \text{s}^{-1}$, corresponding to ~ 3 cm per plasma-year.

Finally, we note that if the ion flux to the mushroom limiter in ISX-B were reduced by a factor of 3, it would then equal the assumed peak flux in the Fusion Engineering Device (FED)/International Tokamak Reactor design. Since the combined sputtering rate for deuterium and tritium (D-T) ions on graphite at the FED edge energies is ~ 30 times higher than that for deuterium ions on stainless steel at ISX-B energies, we would estimate erosion of 30 cm per year in the FED due to physical D-T sputtering. This is equal to the value obtained for this case by modeling the plasma edge.⁷

1. Summary of paper: Journal of Nuclear Materials (in press).
2. Fusion Energy Division, ORNL.
3. The University of Tennessee, Knoxville, Tenn.
4. P. K. Mioduszewski, P. H. Edmonds, and J. Sheffield, J. Vac. Sci. Technol. **20**, 1284 (1982).
5. R. A. Zuhr, J. B. Roberto, and S. P. Withrow, J. Vac. Sci. Technol. **20**, 1244 (1982).
6. J. B. Roberto, R. A. Zuhr, and S. P. Withrow, J. Nucl. Mater. **93/94**, 146 (1980).
7. H. C. Howe, Fusion Engineering Device Design Description, ORNL/TM-7948 (1981), p. 2.

MEASUREMENT OF THE IONIZATION LENGTH FOR NEUTRAL IRON NEAR THE WALL IN THE ISX-B TOKAMAK USING LASER-INDUCED FLUORESCENCE¹

T. B. Cook P. W. King²
J. B. Roberto

An important source of high-Z impurities in fusion devices is the first wall, which is subject to high power and particle loadings that can result in significant release of metal atoms into the plasma. In this work we report the first direct measurements of metal atom transport in the edge plasma of a tokamak by monitoring the decrease in neutral metal density due to electron impact ionization as a function of distance from the first wall. Such measurements are sensitive to both impurity introduction mechanisms and edge plasma parameters. The results were obtained using the laser-induced fluorescence³ technique and are consistent with previous reports,⁴⁻⁶ which suggest heavy impurity introduction in ISX-B by wall sputtering.

The major metallic impurities in ISX-B are iron from the stainless steel vacuum vessel and titanium from Ti-sublimation gettering that has been performed in the vessel at various times.

Both of these impurities are measurable by laser-induced fluorescence.

The ultraviolet laser beam entered at the mid-plane of the torus along a major radius and exited at a razor-blade beam dump mounted on the inner wall of the vessel. The laser-excited volume was viewed from above by detection optics. Stacks of interference and absorption filters spectrally filtered the light reaching the phototubes. Subtraction of the plasma light background was performed, but the plasma light levels are often very high, leading to large statistical fluctuations, which are the major source of uncertainty in the relative measurements. Detection sensitivity depends on background light levels, but is typically $\sim 10^6 \text{ cm}^{-3}$ for iron during tokamak discharges.

Measurements of the metal atom density at two different radial locations in the edge plasma permit a scrapeoff length for that species to be determined. Results for a moderate density discharge ($n_e \sim 2.8 \times 10^{13}$) with 0.9 MW of neutral-beam heating indicate a scrapeoff length (l_e) which is typically 4–5 cm for neutral iron close to the wall in ISX-B. Based on the measured scrapeoff length, an estimated ionization length of 4 cm for neutral iron at a distance of 2 cm from the wall can be deduced⁷ considering the appropriate extended source geometry. This result is consistent with edge electron density and temperature of $\sim 8 \times 10^{11}/\text{cm}^3$ and 1G eV, respectively, and is in approximate agreement with recent Langmuir probe measurements⁸ in the edge region of ISX-B. The present results are indicative of wall sputtering since the observed ionization length is an order of magnitude higher than expected for thermal Fe particles for the same edge conditions. This measurement is consistent with previous results from deposition probe⁶ and plasma shift^{4,5} experiments.

1. Summary of paper: *J. Vac. Sci. Technol.* A 2, 707 (1984).
2. Fusion Energy Division, ORNL.
3. E. Hintz, *Phys. Scripta* T2/2, 454 (1982).
4. R. C. Isler et al., *Phys. Rev. Lett.* 47, 330 (1981).
5. C. H. Muller and K. H. Burrell, *Phys. Rev. Lett.* 47, 330 (1981).
6. R. A. Zuhr et al., *J. Vac. Sci. Technol.* 20, 1244, (1982).
7. M. T. Robinson (private communication).
8. K. E. Yokoyama (private communication).

ION IMPLANTATION AND ION BEAM PROCESSING

MORPHOLOGICAL INSTABILITIES AND ION BEAM MIXING IN Ge¹

B. R. Appleton O. W. Holland²
D. B. Poker J. Narayan³
D. Fathy⁴

Recent experiments^{1,5,6} have shown that heavy ion irradiation of Ge induces a morphological

instability in the amorphous phase which erupts to form surface craters ~ 20 – 40 nm in diameter and $\sim 200 \text{ nm}$ deep. Crater formation has been observed for room temperature implantations into Ge(111) and Ge(100) of the heavy ions Ge, As, Kr, In, Sn, Sb, Xe, W, Tl, Pb, and Bi. However, craters are not formed by light ion implantation (i.e., He, F, and Si). This is interpreted to mean that a critical defect production rate or collision cascade density is necessary to initiate crater formation. Implantation at liquid nitrogen temperature completely suppresses crater formation, resulting in only a simple amorphous surface layer. Implantation at temperatures above room temperature accelerates crater formation until the amorphous-to-crystalline phase transition temperature is reached ($\sim 325^\circ\text{C}$). Above this temperature the amorphous phase never forms, and craters are not initiated. This highlights two important observations; namely, that craters are initiated only in the amorphous phase of Ge and that the effect has the characteristics of a defect-driven phenomenon.^{1,5,6} Prior to discovery of the crater phenomenon, the ion beam mixing behavior of several metal/semiconductor eutectic systems was investigated.^{7,8} The purpose of the papers summarized here was to reevaluate the Au/Ge and Al/Ge systems under a variety of ion beam mixing conditions in order to determine the effect of crater formation on the ion-induced materials interactions and vice versa. The reader is also directed to another paper in this report which relates to this same problem.⁹

Correlated ion scattering/channeling and cross-section electron microscopy were utilized to study the mixing and structural alterations of the Au/Ge and Al/Ge systems under a variety of mixing conditions. Thin films of Al and Au were deposited on Ge(100) and Ge(111) single crystals and on crystals which were demorphized by Ge⁺ bombardment at liquid nitrogen temperature prior to deposition. In addition, Au, Al, and Ge films were prepared in layered structures on Al_2O_3 substrates. These composite samples were then mixed by ion bombardment with Ge⁺ or Xe⁺ at substrate temperatures from 4 to 350 K.

The Au/Ge system mixed very efficiently under ion irradiation, even to temperatures as low as 4 K, to a well-defined composition and on annealing to near room temperature, this amorphous mixture formed a metastable crystalline phase. This behavior is analogous to many silicide-forming systems, where phase formation provides the driving force for mixing during ion irradiation. The Au/Ge system also showed a rate of mixing that was linear with dose, indicating that the rate limiting step in the mixing process is the interaction at the interface to form the metastable phase and not the transport of the atoms across the mixed layer. This also appears to be the case in several other metal/semiconductor systems mentioned elsewhere in this report, although the question of the linear rate observed by us versus the square root dependence of mixing observed by other researchers is not yet resolved. The level of mixing was also different on single-crystalline versus amorphous substrates, a fact that may be supporting evidence that interface interactions are the controlling process, but this is not yet resolved either.

Microstructural and phase analysis by TEM of the Au/Ge surfaces mixed at room temperature confirmed a mixed crystalline metastable Au-Ge phase at the surface and showed no evidence of crater formation in either the mixed phase or underlying amorphous Ge substrate.

In contrast, even though Au/Ge and Al/Ge are simple eutectic systems with similar phase diagrams and, arguably, similar defect properties, the Al/Ge systems showed virtually no mixing and no metastable phase formation under ion irradiation. It appears that the chemical or metallurgical preference of this system during ion irradiation is for phase separation. In this case, net defect fluxes may be important, but the preferential coupling of the Al and/or Ge atoms to these fluxes and the preference for single-phase formation over alloying are the factors that inhibit mixing. Cross-section TEM analysis of an Al film on amorphous Ge on single-crystalline Ge after ion beam mixing with 230 keV, 2×10^{16} Ge⁺/cm², is shown in Fig. 2.22. The dark band at the top of the figure -80-nm wide corresponds to the Al film, which is essentially as-deposited. Underneath is a band of craters which extends into the amorphous layer -240 nm.

The dark band underneath the craters is the remnant of the originally demorphized surface layer. The observation that Ge⁺ bombardment initiates crater formation in the amorphous Ge phase underneath the Al surface film shows that the crater formation process is not necessarily a free surface effect and is not a sputtering or sputter-initiated effect. Crater formation in the Au/Ge system is probably suppressed by the mixing and metastable phase formation. Further

experiments are in progress to identify the origins of the anomalous crater formation, the rate dependence of mixing in the metal/semiconductor systems, and the controlling mechanisms for mixing in these systems.

1. Summary of two papers: B. R. Appleton, p. 195 in *Ion Implantation and Ion Beam Processing of Materials*, ed. by G. K. Hubler, et al., North-Holland, New York, 1984; and B. R. Appleton, *Nucl. Instrum. Methods* (in press).
2. Present address: Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
4. Guest scientist from Microelectronics Center of North Carolina, Research Triangle Park, N.C.
5. B. R. Appleton et al., *Appl. Phys. Lett.* 41, 711 (1982).
6. O. W. Holland et al., *J. Appl. Phys.* 54, 2295 (1983).
7. S. S. Lau et al., *Nucl. Instrum. Methods* 182/183, 97 (1981).
8. B. R. Appleton, p. 189 in *Ion Implantation and Beam Processing*, ed. by J. S. Williams and J. M. Poate, Academic Press, New York, 1984.
9. D. B. Poker and B. R. Appleton, "Linear Dose Dependence of Ion Beam Mixing of Metals in Si," this report.

LINEAR DOSE DEPENDENCE OF ION BEAM MIXING OF METALS ON Si¹

D. B. Poker B. R. Appleton

200nm

Fig. 2.22. Cross-section TEM of Al on amorphous Ge after bombardment with 230 keV, 2×10^{16} Ge⁺/cm².

Ion beam mixing of a thin surface film on a substrate material shows great promise as a technique for tailoring the surface properties of a material while leaving the bulk properties essentially unchanged. The concomitant increase in adhesion of the surface layer is especially valuable for purposes of improving the surface bonding of coatings. While there has been much interest in the uses of ion beam mixing, the mechanisms involved have not been well understood. Theoretical treatments of thin marker layers have had some success in treating the effects of ion beam mixing. The variance of the marker distribution is predicted to increase linearly with dose, and this dependence has generally been confirmed. This analogy with diffusion kinetics has led to the belief that mixing can be treated as a diffusion problem with time replaced by the mixing dose. In the case of bilayered samples, this would result in the depth of the mixed layer increasing as the square root of dose, as has been observed for many materials. Some linear dose dependences have been measured, but are considered the exception. Both linear and square root dependences have been reported for Nb/Si and Au/Si bilayers. Linear dependences have also been observed² for Au/Ge.

These experiments were conducted to determine the dose dependences of ion beam mixing of various metal-silicon couples. V/Si and Cr/Si were included because these couples were previously

suspected of exhibiting a linear dose dependence. Pd/Si was chosen because it had been reported as exhibiting only the square root dependence. Samples were cut from wafers of <100> n-type Si. The samples were cleaned in organic solvents, etched in hydrofluoric acid, and rinsed with methanol before mounting in an oil-free vacuum system for thin-film deposition. Films of Au, V, Cr, or Pd were evaporated onto the Si samples with a nominal deposition rate of 10 Å/s. The thicknesses were large compared with those usually used to measure ion beam mixing and were used to ensure that conditions of unlimited supply were met. Samples were mixed with Si ions ranging in energy from 300 to 375 keV, chosen to produce ion ranges that significantly exceeded the metal film depth. Si was used as the mixing ion to prevent impurity doping of the Si substrate and to exclude a background signal from the Rutherford backscattering (RBS) spectra. Samples were mixed at room temperature, with the exception of the Au/Si samples, which were mixed at liquid nitrogen temperature. The samples were alternately mixed and analyzed in situ without exposure to atmosphere between mixing doses. The compositional distributions after mixing were measured using RBS of 2.5-MeV ^4He atoms.

The mixing doses and the corresponding mixed depths were normalized to the maximum mixing doses and mixed depths, respectively. Except for Cr/Si, these data represent the results from several samples of each type. The plots of depth as a function of dose exhibit a marked linearity, as shown in Fig. 2.23. A nonlinear least-squares fit to a power law has been made for each of the curves and is shown in Table 2.4. Each of the curves exhibits a power law dependence that is within a few percent of linearity.

These results of mixing Au/Si, V/Si, Cr/Si, and Pd/Si show only linear mixing rates. Mixing rates of Au/Si, V/Si, and Cr/Si have previously been reported as exhibiting both linear and square root dependences, while Pd/Si has been reported as only square root. There may be possible causes of these conflicting results:

(1) Xe is used frequently as the mixing ion due to its high mass and correspondingly dense cascades. However, the range of Xe in most materials is only a few hundred angstroms at 300 keV, a typical mixing energy. This places the metal-silicon interface for thin films on a steeply decreasing portion of the damage density curve. As the mixed layer grows, the deeper interface sees even less damage energy. The use of a lighter mixing ion allows greater depths to be used, with more uniform damage densities at the interface.

(2) The definition of mixed depth from the backscattering spectra in the case of stoichiometric mixing can be done using the half-height method of Lever and Chu.³ This definition is inappropriate for nonstoichiometric mixing, and a method similar to that of Averback et al.⁴ can be used. Also, the use of thin films that are comparable in depth to the detector resolution requires that the measured mixed depths be corrected for the detector resolution.

(3) Sample preparation may be responsible for variations in the trapping defect density of the films. The justification for use of the square root dose dependence derives from an assumed

Fig. 2.23. Mixed depth vs mixing dose for four metal-silicide couples. The mixed depth and mixing dose have been normalized to their respective maximum values for each material. The solid lines represent linear mixing.

Table 2.4. Power law dependence of mixed depth vs dose.

Metal	Film thickness (Å)	Power
Au	900	1.01
V	510	0.92
Cr	675	0.94
Pd	1500	1.06

similarity to thermal diffusion. If the diffusion of the mixing atoms across the mixed layer is not the limiting process, then the dose dependence should reflect the dose dependence of the limiting mechanism.

1. Summary of paper: *Journal of Applied Physics* (in press).

2. D. B. Poker, O. W. Holland, and B. R. Appleton, *Mat. Res. Soc. Symp. Proc.* 27, 73 (1984).

3. R. F. Lever and W. K. Chu, p. 149 in *Ion Beam Surface Layer Analysis I*, Plenum Press, New York, 1976.

4. R. S. Averback et al., *J. Appl. Phys.* 53, 1342 (1982).

ION MIXING STUDIES OF SELF-ISOTOPES IN GRAPHITE

D. B. Poker J. B. Roberto
J. Roth¹ W. Möller¹

The process of ion beam mixing has been shown to depend critically upon parameters such as the chemical potential of the mixing species, radiation-enhanced diffusion, and cascade and ballistic collision processes. Efforts to compare the results of ion mixing with calculations are hindered by the difficulty of including the effects of chemical potentials in purely collisional models. Therefore, it would be desirable to be able to study ion beam mixing in a system in which there are no effects of chemical potentials. The use of thin surface layers enriched in an uncommon isotope of the substrate element provides such a system. For this study, ¹³C on graphite was chosen.

Samples were prepared by low-energy ion implantation of ¹³C into the near-surface region of pyrolytic graphite. Rutherford backscattering spectroscopy of 3.75-MeV ⁴He atoms provided sufficient resolution to differentiate the surface layer from the substrate. Preliminary results indicate that the effective diffusion coefficient of the mixing is two or three orders of magnitude greater than can be expected from purely collisional mixing theory. These theories, however, do not consider the effects of radiation-enhanced diffusion and are being modified in an attempt to account for such effects. Additional measurements at lower temperatures, where radiation-induced defects are not mobile, are planned.

¹ Max-Planck-Institut für Plasmaphysik,
Garching bei München, Federal Republic of
Germany.

EFFECT OF BOUNDARY CONDITIONS IN ION MIXING OF MULTILAYERED Ni-Si SAMPLES¹

C. A. Hewett² S. S. Lau³
I. Suni⁴ D. B. Poker

In metal/semiconductor systems, ion mixing of bilayer samples initially leads to the formation of equilibrium phases. However, in multilayer samples, where the average composition is fixed, ion irradiation at high doses can lead to metastable (or amorphous) phase formation. The metastable phase appears to form at a critical ion dose, without the formation of any compounds at subcritical doses. The purpose of this study was to investigate the effect of layer thickness on the reaction product.

Five types of samples were prepared for ion irradiation. A sample of Ni on Si was used to measure the bilayer condition. Multilayer samples of two, three, or five layers of Ni interposed with an equal number of Si layers on SiO₂ were used for the multilayer case. The average composition was fixed at Ni_{1.65}Si. The fifth sample type was obtained by annealing one of the five-layer samples at 300°C for 30 min in vacuum to promote the nucleation of Ni₂Si and Ni₃Si₂. The

samples were ion irradiated at room temperature with 175 keV ²⁸Si to varying doses, and the mixing was determined from Rutherford backscattering and x-ray diffraction.

The bilayer samples produced only crystalline Ni and Ni₂Si due to irradiation, while the multilayer samples showed various combinations of Ni, Ni₂Si, and amorphous phases. The multilayer samples that were preannealed to nucleate Ni₂Si and Ni₃Si₂ showed only crystalline phases, indicating the resistance of these crystalline phases to amorphization by irradiation.

Amorphous phase formation in multilayered samples by ion irradiation may be explained by the bifurcation concept. The bifurcation model⁵ is used to explain the enhanced amorphous formation under quenching from a melt in alloys with a composition near a deep eutectic. It is postulated that just above the eutectic temperature the structure of the liquid may be considered to consist of two distinct types of clusters. These clusters are microscopically bifurcated into regions rich in element A with the short-range order of element A and regions rich in element B with the short-range order of element B, both regions having dimensions on the order of a few lattice spacings. Rapid quenching of the bifurcated liquid then results in an amorphous mixture consisting of small clusters rich in A and clusters rich in B. This concept then suggests that compositions in a two-phase region near a deep eutectic trough are much more likely to bifurcate than compositions near a congruently melting compound.

In this case, the composition of the samples is Ni_{1.65}Si, which is located near a deep eutectoid trough. In principle, all multilayer samples should amorphize upon ion irradiation. However, the initial boundary condition for multilayer samples is similar to bilayer samples; a crystalline Ni₂Si phase is always initially formed by ion mixing. Crystalline Ni₂Si is, however, resistant to amorphization, as shown by the results on preannealed samples. Therefore, the formation of Ni₂Si dominates in bilayer samples and in multilayer samples with relatively thick layers. As the layer thickness decreases, ion-induced bifurcation between Ni₂Si and Ni₃Si₂ competes more favorably with the formation of Ni₂Si alone, enhancing the ease of amorphization in samples with thinner layers.

1. Summary of paper: Nuclear Instruments and Methods (in press).

2. Guest scientist from University of California at San Diego, La Jolla, Calif.

3. University of California at San Diego, La Jolla, Calif.

4. Technical Research Centre Semiconductor Laboratory, Espoo, Finland.

5. W. L. Johnson, p. 183 in Metastable Materials Formation by Ion Implantation, ed. by S. T. Picraux and W. J. Choyke, Elsevier Science Publishing Company, Inc., New York, 1982.

COMPARISON BETWEEN THERMAL ANNEALING AND ION MIXING OF ALLOYED AND MULTILAYER Ni-W FILMS ON Si

C. S. Pail S. S. Lau
U. B. Poker

Ion beam mixing is considered to be a transient process, while furnace thermal annealing is a steady state process. However, the initial silicide phases induced by these two processes on samples consisting of a single metal layer on Si substrates (M/Si) have been observed to be similar. In this study, a comparison between ion beam mixing and furnace thermal annealing of both Ni-W cosputtered samples ($\text{Ni}_{38}\text{W}_{62}/\text{Si}$ and $\text{Ni}_{87}\text{W}_{13}/\text{Si}$) and Ni-W multilayer samples ($\text{Ni}/\text{W}/\text{Si}$ and $\text{W}/\text{Ni}/\text{Si}$) has been carried out.

The effects of ion beam mixing or thermal annealing on the reaction products, component redistribution, and surface morphology were analyzed by four-point probe, Read camera x-ray diffraction, backscattering spectrometry, and optical microscopy. Thermally annealed samples show phase separation in the case of cosputtered samples, while one configuration of the multilayer samples ($\text{Ni}/\text{W}/\text{Si}$) shows phase reversal. In contrast, ion beam mixing leads to the formation of a ternary phase: crystalline in the case of a cosputtered W-rich film ($\text{Ni}_{38}\text{W}_{62}/\text{Si}$), amorphous in the case of a multilayer ($\text{W}/\text{Ni}/\text{Si}$) film. For cosputtered Ni-rich films ($\text{Ni}_{87}\text{W}_{13}/\text{Si}$) and multilayer ($\text{W}/\text{Ni}/\text{Si}$) films, no difference between thermal annealing and ion mixing was observed. These experimental results can be attributed to the different moving species during reactions in these two processes. Ni is the mobile species during thermal annealing, while Si is the mobile species during ion beam mixing. The relationship between moving species, phase separation, phase reversal, and ternary compound formation is being investigated.

1. University of California at San Diego, La Jolla, Calif.

ION BEAM MIXING IN Ni-Al AND Pd-Al ALLOY SYSTEMS

M. Nastasi¹ J. M. Williams
L. S. Hung¹ H. H. Johnson¹
J. W. Mayer¹

Ion beam mixing shows promise of becoming an important materials processing technique, but the principles that govern the process are still poorly understood. The present experiments were primarily intended to yield fundamental information on the possible role of cascade energy density, as opposed to total amount of energy deposited, in determining the products that appear after an ion beam mixing process. To create a broad enough range of situations in which to examine this main point, a large matrix of data, revealing other interesting points, has been developed. Data acquisition, particularly for the Pd-Al system, is continuing. Results below are for the Ni-Al system.

Film composites (Fig. 2.24) consisting of alternating, interlaced, tapered layers of Al and Ni were produced by a vapor deposition technique that will not be described here. The films were of nearly pure Al on one end, nearly pure Ni on the other, and all possible ratios of Ni to Al in between. The composite strips were cut into individual samples ~3 mm in length. Thermal reaction of such films by annealing at 350°C produces by interdiffusion all phases and intermetallic compounds to be expected at given concentrations on the basis of the equilibrium phase diagram. Analysis for phases present was by electron diffraction throughout the experiments (Fig. 2.24). Both reacted and as-deposited samples from the whole composition range were ion bombarded at three temperatures, -190, 30, and 100°C (approximately). The effects of bombarding with 300-keV Xe ions at fluences of $2 \times 10^{15}/\text{cm}^2$ and with 60-keV Ne ions at fluences of 1.3×10^{16} were compared for compositions across the range, all implant temperatures, and both preconditions (as deposited and thermally reacted). The fluence-energy combinations for the respective ions were chosen on the basis of calculation^{2,3} so that the total damage energy deposited, the damage energy per unit volume, and the ion ranges would be as near the same as possible for the two

Fig. 2.24. Schematic representation of composite type of film sample together with equilibrium phase diagram for the Ni-Al system and electron diffraction patterns for selected compositions.

ions. Fluxes were such that the rates of energy deposition were the same. Any differences in product should be due to the fact that energy densities within individual cascades should be greater for the heavier Xe ions than for the Ne ions.

The differences in phases that appeared for the two ions were interesting but not drastic and are best understood in the context of the broad points of behavior that are common to both ions. Systematic trends were observed, which will not be described here in detail. The equilibrium structures characteristic of the compounds NiAl_3 , Ni_2Al_3 , and α' are not stable or are hardly stable against bombardment. They transform and/or decompose to other phases. For example, near 40 at. % Ni the ordered trigonal structure of Ni_2Al_3 (if preexisting) transforms entirely to the ordered CsCl structure, characteristic of the β' phase, upon bombardment. This applies for both ions at all implantation temperatures. At the same concentration, ion-mixed layered films exhibited $\beta' + \alpha$. Thus, depending on concentration, the products that appear after bombardment are somewhat, but not entirely, independent of the degree of equilibration that existed before bombardment. NiAl_3 remained only after high-temperature bombardments and was more stable at a given temperature for Ne than for Xe. Otherwise, the only structures that ever appeared were the terminal phases, Al and α , the β' (CsCl) structure, and amorphous structures. Amorphous structures appeared in the composition range 10–35% Ni, depending on conditions, and were always present together with one of the other phases. Amorphous structures were favored for lower implantation temperatures and for compositions in the range 10–35 at. % Ni. Xenon bombardment produced amorphous structures for higher temperatures and a broader composition range than Ne.

These systematic behavior patterns appear amenable to explanation^{4,5}; analysis is continuing.

1. Cornell University, Ithaca, N.Y.
2. I. Manning and G. P. Mueller, *Comput. Phys. Commun.* 7, 85 (1974).
3. J. P. Biersack and L. G. Hagmark, *Nucl. Instrum. Methods* 174, 257 (1980).
4. M. Nastasi et al., *Journal of Applied Physics* (to be published).
5. W. L. Johnson et al., *Nuclear Instruments and Methods* (to be published).

ENHANCED DEPTH OF AMORPHIZATION OF SEMICONDUCTORS BY MOLECULAR IMPLANTATION DUE TO RESIDUAL GAS SCATTERING¹

D. A. Hansen² D. B. Poker
B. R. Appleton

The range of implanted atomic and molecular ions in semiconductors is of interest to the semiconductor industry due to the use of ion implantation in the doping of semiconductor devices. Since the depth of the doped region is a critical parameter in device fabrication, the precise prediction of ion ranges is important. Measurements of the depth of amorphization resulting from

implantation of atomic and molecular species had indicated that the range of the molecular species varies from 1.2 to 2.5 times the range of the corresponding atomic species. The purpose of this study was to determine the cause of this difference.

Single crystals of Si cut from $\langle 111 \rangle$ wafers, Ge single crystals cut from $\langle 100 \rangle$ wafers, and GaAs single crystals cut from $\langle 111 \rangle$ wafers were used for these measurements. Implantations were made using the Varian/Extrion model 200–1000 ion implanter. All implantations were performed at liquid nitrogen temperature to eliminate effects due to crater formation, as has been observed in Ge. The samples were preamorphized with self ions to a depth of 1000 Å to eliminate channeling effects. SiF_3 at 180 keV was used in all molecular implants; the energy per unit mass (59 keV for Si and 40 keV for F) and the total number of implanted atoms were identical for the corresponding monatomic implants. In this way, most physical variables (such as ion range, cascade volume, or fractional energy deposited in nuclear collisions) were identical for the two cases. The amorphized depth was determined by channeling 2.5 MeV helium ions.

The amorphized depth as a function of dose for implantation of molecular and atomic SiF_3 on Si is shown in Fig. 2.25. The depth for the atomic implant saturates at about 0.2 μm , at doses greater than 2×10^{15} molecules/cm², which is the depth predicted by the Monte Carlo TRIM computer code. The molecular implants are predicted to saturate at the same depth, since the energies and doses are adjusted to give equal velocities for all particles at the surface. However, the molecular implants saturated with an amorphized depth as much as 2.5 times deeper than predicted. Secondary ion mass spectroscopy measurements indicated that the fluorine was distributed over the entire amorphous region. Similar effects were seen using atomic and diatomic arsenic.

Fig. 2.25. Depth of amorphization vs implanted dose for molecular and atomic implants of SiF_3 on Si. The energy and dose of the components of the atomic implants were equal to the corresponding molecular values.

It was postulated that this effect might be caused by breakup of the molecular species due to collisions with gas molecules within the accelerator after energy analysis and before final acceleration. The final energy of a molecule that did not undergo a collision would be distributed among the constituent atoms. Each atom would enter the implanted solid with the same velocity; and since the stopping power varies directly with velocity, the range of each atom is approximately the same. However, each of the fragments of a molecule that has undergone a collision would receive an energy corresponding to the full acceleration potential and would have a correspondingly greater range. This postulate was tested by placing an adjustable air leak valve after the energy analyzing magnet and before the final acceleration tube. The resulting amorphized depth as a function of the pressure at the leak valve for molecular implants is shown in Fig. 2.26. At high pressure ($>10^{-2}$ Torr), the amorphized depth saturates at $0.5 \mu\text{m}$. At lower pressures, the amorphized depth approaches that for the atomic species, $0.2 \mu\text{m}$. It was concluded that the deeper depth of amorphization of the molecular species was a result of collisions with air molecules within the accelerator. Because of their much smaller collision cross sections, atomic ions were affected by these collisions to a smaller degree. The presence of air molecules in the vacuum system was determined to be the result of deteriorating vacuum seals. After the seals were replaced, however, the molecular species still showed a 20% enhancement in amorphized depth compared with atomic species, indicating the necessity for vacuum pumping in addition to that originally supplied with the accelerator.

1. Summary of paper to be published.
2. Summer research intern from the University of California, Berkeley, Calif.

Fig. 2.26. Depth of amorphization vs pressure in the implant accelerator for molecular implants at 2×10^{16} molecules/cm² at 180 keV.

INFLUENCE OF SUBSTRATE TEMPERATURE ON THE FORMATION OF BURIED OXIDE AND SURFACE CRYSTALLINITY DURING HIGH-DOSE OXYGEN IMPLANTATION INTO SILICON¹

O. W. Holland²
D. Fathy³

T. P. Sjoreen
J. Narayan⁴

The formation of a buried oxide layer in Si by high-dose implantation of oxygen has been widely studied because of its technological importance. The isolation provided by an insulating layer makes silicon-on-insulator (SOI) an excellent material for high-speed, high-density integrated circuits.⁵ The buried layer has been shown to be stoichiometric SiO₂ with atomically sharp interfaces.⁶⁻⁸ However, the suitability of the material for device fabrication depends on preservation of the crystallinity of the near surface. Since the amorphous SiO₂ phase isolates the superficial Si layer from the single-crystal substrate, it is imperative that the crystallinity of this layer not be lost during implantation. Once lost, it cannot be recovered in single-crystal form. Maintaining the crystallinity can be accomplished by holding the sample at high temperature during irradiation. The most frequent technique for heating the sample described in the literature is to use a high current density ion beam. Extremely high temperatures are possible by direct beam heating if the sample is not heat sunk. However, there have been reports that sample heating from a source independent of the ion beam, such as a resistive heater, results in a better quality crystalline surface.^{8,9}

We have studied the influence of substrate heating on the crystal quality of the surface layer. Optimum implant conditions were found which produce a uniform SiO₂ layer with sharp interfaces and an excellent crystal surface layer. The quality of the surface layer is superior to any that has been reported, even after host implantation annealing. Not only does in situ annealing avoid postimplantation treatment, but it also results in a more suitable surface to accommodate epitaxial growth of a Si overlayer by chemical vapor phase deposition. Such epitaxial layers should have fewer grown-in dislocations since the seed for growth is more perfect.

The influence of substrate heating during implantation can be seen in Fig. 2.27, which compares aligned and random backscattering spectra from a Si(100) single crystal which was implanted with ¹⁶O(180 keV, 2×10^{18} cm⁻², 37 $\mu\text{A}/\text{cm}^2$). The substrate or heater temperature was maintained at 475°C during the implantation. The scattering yield from Si atoms is shown in the figure, while the low-energy portion of the spectra containing the yield from the implanted O has been excluded. Two distinct regions can be identified in the spectra of Fig. 2.27. The decreased scattering yield in the random spectrum between 330–750 nm indicates that a buried oxide has formed. Since silicon forms a noncrystalline oxide, no differences are observed in the aligned and random yield in this region. The stoichiometry of this oxide was determined to be SiO₂ from a comparison of the scattering height in this region to that from elemental Si. The top 300 nm however has remained a single crystal as

Fig. 2.27. Aligned and random spectra from a Si(100) crystal implanted at 475°C with ^{16}O (180 keV, $2 \times 10^{18} \text{ cm}^{-2}$, 37 $\mu\text{amps/cm}^2$).

indicated by the aligned yield which falls below random over the entire region. While the rapid increase in the aligned yield clearly indicates extensive damage in this region, the near surface has remained remarkably defect free. The minimum yield (the ratio of aligned to random yield) just behind the surface peak is 3.3% compared with 2.4% from a virgin (undamaged) crystal. These spectra clearly demonstrate that implantation not only results in the formation of a thick (>400-nm) uniform oxide but also preserves the crystalline quality of the surface. Thus, the crystal quality maintained by in situ annealing is far superior to that achieved by postimplantation annealing. While there is some variation in the literature, the value of the minimum yield in samples implanted with an energy and dose of O^+ comparable to the present case but without substrate heating, have been substantially greater than that reported here. The best reported results were achieved by postimplantation annealing of such samples (1150°C for 3 h in an argon ambient), which decreased the minimum yield from its as-implanted value of 33% to 12%.¹⁰

The effect of substrate heating during implantation was found to be critical in determining the crystalline quality of the superficial crystalline layer. Figure 2.28 compares the aligned spectra from samples irradiated at different temperatures. It is clear from the spectra that the crystalline quality, as determined by the aligned scattering yield, is substantially better for the 475°C implant than for implantation at temperatures above this optimum temperature. The minimum yield increased to 12.3% when the substrate heating was decreased to 450°C, a clear indication that considerable implantation damage remains at this temperature. This observation correlates well with previous studies of radiation-induced damage in Si, which have shown that defect clustering is inhibited for temperatures in excess of 450°C.¹¹⁻¹³ Therefore, clustering at lower temperatures can lead to the nucleation of dislocation loops or other stable damage structures. Analysis by transmission electron microscopy showed that the near-surface region of the 450°C

Fig. 2.28. Aligned spectra from Si(100) crystals implanted at different temperatures with ^{16}O (180 keV, $2 \times 10^{18} \text{ cm}^{-2}$, 37 $\mu\text{amps/cm}^2$).

implanted sample had a high density of such dislocation loops and tangles consistent with radiation-induced damage. Extensive networking of dislocations was a characteristic of all lower temperature irradiations. Thermocouple measurements of the sample surface during implantation showed that beam heating raised the sample temperature in excess of 800°C. However, it is felt that dislocation loops can nucleate initially during irradiation before the sample attains its equilibrium temperature. Once nucleated, these loops are relatively stable and will provide trapping sites for subsequently generated point defects, even at higher temperatures. Therefore, the substrate or heater temperature, which sets a lower limit on the sample temperature, is critical in determining the microstructural evolution of the sample during implantation.

Further increases in the heater temperature did not result in additional improvement in the quality of the crystalline overlayer. In fact as shown in Fig. 2.28, the minimum yield increased to 7.5% in the sample implanted at 550°C. The degradation of the minimum yield is thought to result from an enhanced diffusivity of oxygen in the implanted region at the sample temperature. The increased motion of O leads to the formation of an extensive network of oxide precipitates in this region, which can explain the increased damage at this temperature. Therefore, for the implant conditions that were used, a narrow temperature range near 475°C yielded the best crystalline surface.

In conclusion, we have shown that a superior crystalline overlayer on SOI material can be produced by high-temperature implantation of oxygen in Si. The substrate temperature is a sensitive parameter in determining the microstructure of the material. To a large extent, the damage morphology which develops initially during irradiation (before the sample attains its steady state temperature) determines the structural evolution during the entire implant. An interesting aspect of the microstructure is a rippled network

of oxygen precipitates. Dislocations produced by the irradiation provide sites for nucleation of these precipitates and apparently give rise to the ripple morphology. The narrow range of substrate temperature over which a good quality crystalline surface can be maintained during implantation results from a competition between annealing and increased oxygen diffusion which leads to precipitation and growth of the oxide phase.

1. Summary of paper: Applied Physics Letters (in press).
2. Present address: Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. Guest scientist from North Carolina State University, Raleigh, N.C.
4. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
5. K. Izumi, M. Doken, and H. Ariyoshi, Electron. Lett. 14, 593 (1978).
6. Takayoshi Hayashi, Hamao Okamoto, and Hoslikazu Homma, Jpn. J. Appl. Phys. 19, 1005 (1980).
7. R. F. Pinizzotto, R. L. Vaandrager, and H. W. Lam, Mat. Res. Soc. Symp. Proc. 7, 401 (1982).
8. S. R. Wilson and D. Fathy, J. Elec. Mater. 13, 127 (1984).
9. P. L. F. Hemment et al., Nucl. Instrum. Methods, 209/210, 157 (1983).
10. A. H. Hamdi et al., Appl. Phys. Lett. 41, 1143 (1982).
11. R. L. Minear, D. G. Nelson, and J. F. Gibbons, J. Appl. Phys. 43, 3468 (1972).
12. M. D. Matthews and S. J. Ashby, Philos. Mag. 27, 1313 (1973).
13. D. Fathy et al., Inst. Phys. Conf. Ser. No. 67: Section 10, 493 (1983).

A SEARCH FOR SOLUTE DRAG

M. J. Aziz ¹	D. H. Lowndes
G. E. Jellison, Jr.	C. W. White
J. Y. Tsao ²	M. O. Thompson ³
P. S. Peercy ²	W. H. Christie ⁴

Galvin et al.⁵ have shown that during resolidification subsequent to pulsed-laser melting, the solid-liquid interface slows down when it encounters a doped region. This was predicted by Aziz⁶ on the basis of theoretical considerations of free energy dissipation. Several possible sources of this velocity reduction have been identified: a decrease in the intrinsic interface mobility with increasing concentration, a reduced driving force for alloy solidification due, in part, to a melting point depression, and a "solute drag" effect due to the drag force exerted on the advancing interface by segregating solute. In order to distinguish between these effects and to make a quantitative comparison between theory and experiment, a system whose thermodynamic and thermophysical parameters are well known must be used; at present, Si-Ge is the only such semiconductor system. We are investigating this phenomenon by the ion implantation of Ge into Si and of Si into Ge. The interface

velocity v has been measured by the transient conductance technique. The velocity has been observed to decrease as the interface leaves a region of pure Si and encounters a Si-Ge alloy region, and a subsequent velocity increase has been observed upon its return to a region purer in Si. Likewise, the velocity in germanium has been observed to increase as the interface leaves a region of pure Ge and encounters a region doped with Si. Solute depth profiles are being measured by Rutherford backscattering and secondary ion mass spectroscopy. Interfacial segregation coefficients $k(v)$ are being deduced for measured velocities. Analysis with an accurate thermodynamic model for the Si-Ge system and with numerical models for heat flow and liquid-phase diffusion will allow the separation of the various sources of velocity changes that have been observed.

1. Eugene P. Wigner Fellow.
2. Sandia National Laboratories, Albuquerque, N.M.
3. Cornell University, Ithaca, N.Y.
4. Analytical Chemistry Division, ORNL.
5. G. J. Galvin, J. W. Mayer, and P. S. Peercy, p. 111 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, Elsevier, New York (1984).
6. M. J. Aziz, Appl. Phys. Lett. 43, 552 (1983).

PRESSURE DEPENDENCE OF THE DIFFUSIVITY OF ARSENIC IN CRYSTALLINE SI

E. Nygren ¹	M. J. Aziz ²
D. Turnbull ¹	J. M. Foote ³
D. C. Jacobson ³	R. Hull ²

Because solid phase diffusion is the main process by which electronic devices have been made, an understanding of the mechanisms by which it occurs is of primary importance for semiconductor technology. In addition, as devices have become smaller and the diffusion requirements for their fabrication more exacting, more complete knowledge of the processes becomes necessary. Progress in elucidating the mechanisms of impurity diffusion in Si has been slow, as most of the experimental evidence is indirect, due to the extremely low concentration of point defects.

Measurements of the pressure dependence of the diffusivity of arsenic in Si are being made. The results are expected to have a direct bearing on whether the primary point defects involved in this process are vacancies or interstitials.

Wafers of (100) Si have been implanted with 5×10^{15} As/cm² at 100 keV and are first annealed by standard rapid thermal annealing techniques to 1100°C to restore crystallinity by solid phase epitaxy. Subsequent anneals were done either under pressure in a Royd-England-type piston-cylinder press or in evacuated ampules in a furnace. The arsenic depth distribution before and

after treatment has been examined by RBS techniques. To date we have investigated the arsenic diffusivity over the temperature range 850–950°C at pressures of 0, 20, and 30 kilobars. Preliminary analyses of the results indicate the following:

(1) The diffusivity of arsenic in silicon increases with pressure. At 30 kb, the enhancement is about a factor of 6 over vacuum furnace anneals. The behavior can be described with an activation volume of approximately $-6 \text{ cm}^3/\text{mole}$.

(2) The activation energy appears to remain constant at about 90 kcal/mol.

(3) The diffusivity shows a concentration sensitivity as reported by other investigators, tending to increase with As concentration.

The volume of the system should be decreased by interstitial formation but increased by vacancy addition. Thus the application of pressure should increase the equilibrium concentration of the former defect and decrease that of the latter. Given this tendency, an interstitial diffusion mechanism would appear to be consistent with observation (1) above, while a vacancy mechanism would not. Since the activation enthalpy is a sum of defect formation and mobility terms and because the effect of pressure on the mobility has not been independently determined, we cannot conclusively rule out a vacancy mechanism. However, theoretical and experimental evidence for very high ambient-pressure mobilities for both types of defects indicates that the application of pressure is unlikely to enhance significantly the mobility term. Thus an interstitial mechanism appears more likely than a vacancy mechanism for diffusion of As in Si.

1. Harvard University, Cambridge, Mass.
2. Eugene P. Wigner Fellow.
3. AT&T Bell Laboratories, Murray Hill, N.J.

ION IMPLANTATION EFFECTS IN SILICON CARBIDE

J. M. Williams	B. R. Appleton
C. J. McHargue ¹	G. M. Reagin ²
H. J. Kim ³	R. F. Davis ³

Studies⁴ on production and annealing of lattice disorder by ion implantation of SiC were continued. Results may be classified into three areas of interest: production of disorder at room temperature, annealing of disorder after ion implantation at room temperature, and production of disorder by ion implantation at elevated temperatures.

Single-crystal samples of α -SiC, grown by the Carborundum Company, were polished to present {0001} planar surfaces for study. Single crystals of α -SiC were grown with {100} orientations by chemical vapor deposition onto Si substrates. Samples were implanted with either B, N, Al, or Cr ions at the respective energies, 46, 62, 130, and 260 keV. Ion energies were chosen so that the projected ranges and calculated damage-energy profiles^{5,6} (in normalized form) would be about

the same regardless of ion mass. Lattice damage was detected by RBS/He-ion channeling techniques and by Raman spectroscopy. Production of disorder at room temperature was studied over fluence ranges of nearly four orders of magnitude (e.g., 10^{13} to $10^{17}/\text{cm}^2$) for each ion, with the actual relevant fluence range being relatively lower for ions of higher mass. Annealing was done after selected fluences at room temperature. Implantations at elevated temperatures were done for selected fluences. Development of lattice disorder with dose at room temperature is similar in some ways to that for Si. In a channeling analysis the yield of backscattered ions from the implant-affected depth increases with fluence until it reaches the level characteristic of random or amorphous material. For B and N ions the entire development of the disorder with dose correlates well with the damage energy calculations.^{5,6} Ion energies were chosen so that the damage energy profiles would be peaked within the samples rather than decrease monotonically from the surface. At fluences below the level required for amorphization, the damage profiles as determined from ion channeling experiments bore reasonable resemblance to the calculated profiles. No systematic deviations from linearity of total damage with fluence could be detected at our resolution level. The samples first went amorphous at the depth of the calculated peak in the damage energy profile. If the corresponding damage energy is taken as the minimum value necessary to produce amorphization, thereafter the amorphous region expands with minimum energy criterion. The damage energy necessary to produce amorphization is approximately $2 \times 10^{24} \text{ eV}/\text{cm}^3$.

The correlations described above did not hold for the case of Al and Cr. For a damage energy profile of given form, actual lattice disorder effects were much more broadly distributed than would have been expected using the correlations that applied for B and N ions. For example, for the same total damage energy and the same ion range, amorphization depths for Cr ions were 50% greater than for N ions. This difference between the lighter and the heavier ions is attributed to the fact that the calculations used thus far do not take account of secondary knock-on transport of damage energy. Incident ions which are heavier than target atoms can transfer sufficient energy to the target atoms so that the range of the knocked-on atom exceeds the range of the incident ion considerably. This effect broadens the distribution of damage energy in comparison with the types of calculations generally in use at present. Calculations using a more advanced version of TRIM⁷ are under way to confirm this idea.

Annealing through the rather low-temperature range 300–750°C produced a surprising amount of recovery (90%), provided that the material had not been fully amorphized. For fluences where the disorder level was so high that the backscattered He-ion yield in channeling analyses was the same as that from amorphous or randomly oriented samples, almost no recovery occurred up to 1100°C. What recovery did occur was epitaxial in appearance rather than being distributed over the whole damage profile.

Implantation at moderately elevated temperatures (750°C) produced detectable disorder, but amorphization, as determined by both ion channeling analysis and Raman spectroscopy, did not occur, even for damage energies 100 times the minimum necessary to produce amorphization at room temperature.

1. Metals and Ceramics Division, ORNL.
2. Chemistry Division, ORNL.
3. North Carolina State University, Raleigh, N.C.
4. J. M. Williams, C. J. McHargue, and B. R. Appleton, *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 61.
5. I. Manning and G. P. Mueller, *Comput. Phys. Commun.* 7, 85 (1974).
6. J. P. Biersack and L. G. Haggmark, *Nucl. Instrum. Methods* 174, 257 (1980).
7. J. P. Biersack, private communication.

ION-INDUCED DECOMPOSITION AND MIXING EFFECTS IN LiNbO_3

B. R. Appleton	G. M. Beardsley ¹
W. H. Christie ²	R. Eby ²
P. Ashley ³	C. Bahr ³

One of the most promising materials for the fabrication of integrated optical elements is LiNbO_3 because of its large electro-optic and acoustic-optic coefficients and low optical loss. Waveguides, waveguide couplers, modulators, switches, and other more complex elements have been made by the in-diffusion of elements such as Ti, V, and Ni; the out-diffusion of Li; the use of ion exchange techniques; and the use of ion-induced damage to form buried layers of reduced index of refraction.⁴ All these fabrication techniques have inherent limitations. The original intent of the present work was to investigate the use of ion implantation doping or ion beam mixing, followed by selective annealing if necessary, to introduce Ti into LiNbO_3 for fabrication of waveguides. However, our initial ion implantation studies revealed an ion-induced decomposition of the near surface of LiNbO_3 which had not been observed in previous ion bombardment studies. In this paper, we characterize this effect and report initial results of ion beam mixing. We have utilized ion scattering/channeling, secondary ion mass spectrometry (SIMS), and optical microscopy to characterize the implanted and ion-mixed LiNbO_3 .

Both x- and z-cut LiNbO_3 single crystals were implanted with Ti^+ or N^+ at a variety of doses (10^{14} – 5×10^{16} ions/cm²), energies (35–300 keV), and substrate temperatures (room temperature and liquid nitrogen temperatures). The ion-induced decomposition phenomena can be illustrated by results from z-cut crystals implanted with three different energies (36, 100, and 224 keV) of Ti^+ at doses controlled to give a uniform distribution of Ti from the surface to a depth of ~2000 Å. The crystals were implanted at room temperature to a total dose of 5×10^{16} Ti^+ /cm². Immediately after implantation the near surface of the originally

clear crystals acquired a brown appearance as a consequence of implantation, but the surface remained smooth and shiny. The coloration of ion bombarded LiNbO_3 has been attributed by others to O vacancies.

When the implanted crystals were removed from vacuum and exposed to the atmosphere for times >1 h, the shiny surface became cloudy in appearance. Examination under an optical microscope showed the formation of surface precipitates. These precipitates had a buttery consistency and could be easily removed by wiping or dissolving in H_2O or methanol. Once removed the underlying surface was smooth and shiny. Analysis of the stoichiometry of these samples by SIMS showed an excess of Li at the surface for samples covered with surface precipitates and a graded depletion of Li in the near-surface region to depths equal to the implanted Ti for crystals which were washed in H_2O to remove the precipitates prior to analysis. A controlled assay of the amount of Li washed from the surface of the sample discussed above showed a minimum of 1.4 $\mu\text{g}/\text{cm}^2$ of Li. (The assay was made by spiking the wash with a known concentration of ^6Li and analyzing the residue by SIMS, comparing ^6Li and ^7Li .)

Other pertinent observations include surface depletion and precipitate formation which occurred for the following:

1. Implantation of N^+ or Ti^+ at energies from 35–300 keV,
2. Ti^+ doses from 10^{14} – 5×10^{16} Ti/cm^2 , increasing in concentration with increasing dose,
3. Both x- and z-cut crystals,
4. Room temperature and liquid nitrogen implants after warming to room temperature.

The visible surface precipitates appeared white and were very hydroscopic, forming only when exposed to moist air and forming more rapidly the greater the moisture content. This and the chemistry of Li suggest that the surface precipitates may be LiOH .

A consistent picture for this process is that ion implantation of Ti^+ or N^+ drives lithium from the near surface to the surface. The depletion of Li and the range of the damage distribution of the implanted Ti^+ correlate very well. The surface segregation may be either a charge-driven or radiation-enhanced diffusion process. Upon exposure to wet air the surface lithium reacts with water to form the visible precipitates. Both the amount of segregated lithium detected in the wash and the depletion of lithium in the near surface observed by SIMS correspond to about 30–50% of the lithium originally present over the range of the Ti^+ . Experiments are in progress to differentiate some of these mechanisms. As with other insulators, sample charging was observed during ion beam analysis of LiNbO_3 . The charging problems were negligible for LiNbO_3 crystals which had been implanted or had evaporated Ti surface films, but virgin crystals often cracked under 2.5-MeV He^+ irradiation even at very low doses.

Preliminary analysis by ion scattering and SIMS of thin (500-Å) Ti films on LiNbO_3 mixed by Ti^+ bombardment showed definite interfacial mixing, suggesting that the dominant mechanism was probably ballistic mixing. However, the Li

was mixed to greater depths than Nb. No segregation of Li to the surface was observed. Ion beam mixing appears to be a promising and viable alternative to implantation for introducing the desired dopants without the detrimental surface decomposition. Future studies will investigate this process further for fabricating waveguides and will look at mixing of other species like V and Ni. The versatility of the ion mixing and implantation processes seems certain to offer solutions to some of the materials problems which limit the use of LiNbO_3 for waveguides.

1. Oak Ridge Associated Universities faculty research participant from Millsaps College, Jackson, Miss.
2. Analytical Chemistry Division, ORNL.
3. U.S. Army Missile Laboratory, Redstone Arsenal, Ala.
4. G. L. Destefanis et al., *J. Appl. Phys.* 50, 7898 (1979); and references therein.

FORMATION OF AMORPHOUS LAYERS IN Al_2O_3 BY ION IMPLANTATION¹

C. W. White G. C. Farlow²
C. J. McHargue³ P. S. Sklad³
M. P. Angelini³ B. R. Appleton

Previous work has established that it is difficult to turn the near-surface region of $\alpha\text{-Al}_2\text{O}_3$ amorphous by ion implantation at room temperature.^{4,5} In this work we have established the conditions that are necessary to form an amorphous region in Al_2O_3 by ion implantation.

In general, we find that high doses at room temperature or moderate doses at LN_2 temperatures are required to turn the near surfaces amorphous. These studies have been carried out using Rutherford backscattering (RBS)-ion channeling measurements to characterize the structural property changes resulting from ion implantation. Selected crystals have also been examined by transmission electron microscopy (TEM).

Figure 2.29 shows RBS-ion channeling spectra measured in $\langle 0001 \rangle$ -oriented Al_2O_3 following the implantation of Cr (150 keV, $4 \times 10^{16}/\text{cm}^2$) at substrate temperatures of 77, 300, and 640 K. At room temperature or above, implantation causes the introduction of extensive damage to the lattice, but the implanted region remains crystalline as demonstrated by the fact that the aligned spectrum does not reach the random value. By contrast, at 77 K an amorphous region $\sim 1500\text{-\AA}$ thick is formed. Results similar to those presented in Fig. 2.29 have been obtained over a wide range of implantation current densities. These results demonstrate that the retention of damage introduced into the Al_2O_3 lattice is strongly dependent on temperature. At LN_2 an amorphous region can be formed, but at room temperature (or above) dynamic annealing during implantation prevents the formation of the amorphous phase unless very high doses are used. (For Cr, a dose in excess of $10^{17}/\text{cm}^2$ is required to form the amorphous phase during implantation at room temperature.)

Fig. 2.29. 2.0-MeV He backscattering spectra from $\langle 0001 \rangle$ -oriented $\alpha\text{-Al}_2\text{O}_3$ implanted at (a) 77, (b) 300, and (c) 640 K.

At LN_2 temperature, only moderate doses are required to produce an amorphous layer. This is shown by the channeling results in Fig. 2.30 for crystals implanted by Cr (150 keV) at LN_2 temperature to doses in the range $1\text{--}3 \times 10^{15}/\text{cm}^2$.

Fig. 2.30. RBS-ion channeling spectra from Al and O sublattices following implantation by Cr (150 keV) to different doses at 77 K. Scattering yield is plotted as a function of depth in each sublattice.

(In Fig. 2.30 channeling results are presented as a function of depth for the Al and O sublattices separately. Results for the O sublattice were obtained by subtracting the Al background from the random and aligned spectra.) As shown in Fig. 2.30, the crystal is damaged but not turned amorphous for doses up to $1 \times 10^{15}/\text{cm}^2$. If the dose is increased to $2 \times 10^{15}/\text{cm}^2$, a buried amorphous layer ~ 400 Å thick is formed. At $3 \times 10^{15}/\text{cm}^2$ the amorphous layer has increased in thickness to 1100 Å, and it extends to the surface. Thus, at LN₂ temperature, Cr doses of $\sim 2 \times 10^{15}/\text{cm}^2$ are sufficient to form the amorphous phase, whereas at room temperature a dose at least two orders of magnitude greater is required.

1. Summary of paper to be published.
2. ORAU Postdoctoral Fellow.
3. Metals and Ceramics Division, ORNL.
4. H. Naranoto et al., *J. Appl. Phys.* **54**, 683 (1983).
5. H. Naranoto et al., *Nucl. Instrum. Methods* **209/210**, 1159 (1983).

THERMAL ANNEALING OF Fe-IMPLANTED Al_2O_3 IN OXIDIZING AND REDUCING ENVIRONMENTS¹

G. C. Farlow² C. W. White
C. J. McHargue³ P. S. Sklad³
B. R. Appleton

The effects of ion implantation of Al_2O_3 followed by thermal annealing in a reducing environment have been studied and compared with the results obtained by annealing in an oxidizing environment for the case of implanted Fe. Single crystals of Al_2O_3 were implanted with Fe at 160 keV to a dose of $4 \times 10^{16}/\text{cm}^2$. The samples were subsequently annealed in either flowing oxygen or a flowing mixture of argon and hydrogen. The annealing was done in the temperature range 800–1500°C. The samples were examined using Rutherford backscattering and ion channeling techniques and transmission electron microscopy (TEM) measurements to determine the response of the implanted material to annealing in the different ambients.

For the samples annealed in hydrogen the lattice damage in both the Al and oxygen sublattices relaxes smoothly with annealing temperature to give X_{min} values representative of the virgin material after annealing at 1500°C [$X(\text{Al}) \sim 2\%$ and $X(\text{O}) \sim 8\%$]. (X_{min} is defined in the usual way as the ratio of the aligned to random backscattering yields.) This behavior is in contrast to the situation that occurs when an Fe-implanted sample is annealed in oxygen and the annealing curves show two very definite stages of annealing, one below 800°C and one above 1200°C. Thus, the final crystal quality as measured by X_{min} is comparable after annealing to 1500°C, but the behavior at lower temperatures is dependent on the environment. How the annealing environment is affecting the defect structures which mediate the annealing has not been determined.

Figure 2.31 shows backscattering curves on semilog plots from samples with an $\langle 0001 \rangle$ surface normal implanted with Fe. Results are presented

Fig. 2.31. 2-MeV He^+ backscattering and channeling spectra from ^{56}Fe -implanted (160 keV, $4 \times 10^{16}/\text{cm}^2$) $\alpha\text{-Al}_2\text{O}_3$: (a) as-implanted, (b) annealed 1 h at 1500°C in oxygen, and (c) annealed 1 h at 1500°C in hydrogen.

for the as-implanted state [Fig. 2.31(a)] and following annealing at 1500°C in either oxygen [Fig. 2.31(b)] or hydrogen [Fig. 2.31(c)]. The results of Fig. 2.31(a) do not show any evidence that the Fe occupies a preferred site in the lattice in the as-implanted state since the random and aligned yields from the implanted Fe are virtually indistinguishable. In the temperature range 900–1500°C in either annealing environment the Fe moves into positions which are shadowed along the $\langle 0001 \rangle$ axis. After annealing at 1500°C in an oxidizing environment [Fig. 2.31(b)] the Fe is almost completely shadowed along the $\langle 0001 \rangle$ axis [$X(\text{Fe}) \sim 10\%$]. By contrast, shadowing along the c axis is much less after annealing at 1500°C in a reducing environment [$X(\text{Fe}) \sim 40\%$ from Fig. 2.31(c)].

Detailed angular scan data for the $\langle 0001 \rangle$, $\langle 1210 \rangle$, and $\langle 1010 \rangle$ axes on the samples annealed at 1500°C have been acquired. The axial scan curves for the Fe-implanted sample annealed in hydrogen give no evidence that the Fe is in substitutional sites on either the Al or oxygen sublattices. The scan curves for Fe are wider than those for either the Al or oxygen sublattices for each of the three axes, and there is a substantial channeling dip for Fe along each axis. Given that the Fe half angles are wide and that the Al and O half angles are comparable with those of the unimplanted material along two of the axes, the most reasonable interpretation is to assign the scan curves of the Fe impurity to precipitates. (See Ref. 4 for scan curves of unimplanted Al_2O_3 .) These precipitates would have to be crystalline with some preferred orientation to account for the amount of channeling observed along the various axes. In addition, the angular scans show evidence of strain along the $\langle 1210 \rangle$ direction following annealing at 1500°C in hydrogen. Confirmation of the existence and determination of the composition and structure of the proposed precipitates are presently under way using TEM measurements.

The scan across the $\langle 0001 \rangle$ axis of the sample annealed at 1500°C in oxygen shows a remarkable congruence between the scan curves for the Al

sublattice and the Fe impurity, suggesting that the Fe might be substitutional in the lattice. However, the scans across the $\langle 1210 \rangle$ and $\langle 1010 \rangle$ axes, where the curves for the Fe impurity are clearly different from those for the Al sublattice and where the channeling is much less pronounced, demonstrate that this is not true. A micrograph from a cross-sectional TEM specimen taken from the sample annealed in oxygen at 1500°C is shown in Fig. 2.32(a). The areas of dark contrast are Fe-rich precipitates ranging in size from 15–50 nm in diameter and lying at a mean depth of 96 nm, which is consistent with the backscattering data [Fig. 2.31(b)]. Convergent beam diffraction patterns [Fig. 2.32(b)] taken from the precipitates show them to be crystalline. Additionally, the channeling data along the $\langle 0001 \rangle$ axis require that one of the major channeling axes be nearly aligned with the Al_2O_3 $\langle 0001 \rangle$ axis.

Preliminary analyses of the diffraction patterns from precipitates give values for the lattice parameters consistent with the composition and structure of Fe_3O_4 . Compositions of the form $\text{Fe}(\text{Fe}_x\text{Al}_{1-x})_2\text{O}_4$ or FeO cannot be ruled out; however, the phase diagram for the Fe-Al-O system suggests that the Fe_3O_4 or the mixed spinel is more likely than FeO given the temperature and oxygen partial pressure of the annealing conditions. The diffraction pattern of the precipitate shown in Fig. 2.32(b) has an $\langle 011 \rangle$ zone axis of a cubic structure. The diffraction pattern from the Al_2O_3 matrix adjacent to the precipitate shows the $\langle 0001 \rangle$ axis to be 3 deg off the $\langle 011 \rangle$ observed for the precipitate. This misalignment is greater than that suggested by the scan curves

along the $\langle 0001 \rangle$ direction, and this discrepancy is as yet unresolved. Determination of the exact orientational relationship of the precipitates will require further channeling and correlated TEM measurements.

1. Summary of paper: Nuclear Instruments and Methods (in press).
2. ORAU Postdoctoral Fellow.
3. Metals and Ceramics Division, ORNL.
4. H. Haramoto et al., J. Appl. Phys. 54, 683 (1983).

BEHAVIOR OF IMPLANTED $\alpha\text{-Al}_2\text{O}_3$ IN AN OXIDIZING ANNEALING ENVIRONMENT¹

G. C. Farlow² C. W. White
C. J. McHargue³ B. R. Appleton¹

A series of first-row transition-metal ions, Fe, Mn, Ni, Cu, and also Ga, were implanted into single-crystal Al_2O_3 with a mean range of 50 to 100 nm and to a dose of $4 \times 10^{16}/\text{cm}^2$. These samples were subsequently annealed in flowing oxygen at temperatures in the range $600\text{--}1600^\circ\text{C}$. Helium Rutherford backscattering and channeling techniques and Knoop microhardness measurements have been used to characterize the response of these samples to annealing. Results from Ti- and Cr-implanted Al_2O_3 samples which were annealed in oxygen⁴ are included in this discussion.

Lattice damage recovery during annealing is similar in all cases. Annealing of the lattice damage begins during implantation. Since we

ORNL-Photo 7617-84

Fig. 2.32. Electron microscopy of ^{56}Fe -implanted (160 keV , $4 \times 10^{16}/\text{cm}^2$) $\alpha\text{-Al}_2\text{O}_3$ annealed in oxygen: (a) bright field TEM image of a cross-sectional specimen showing variation with depth of Fe-rich precipitates (dark contrast features) and cavities (light contrast features) and (b) convergent beam diffraction pattern showing $[011]$ zone axis of the Fe-rich precipitates.

know that at low temperatures the lattice is amorphized over the entire implantation range,⁵ it is clear that the implantation beam induces annealing in the as-implanted specimen if implantation is done at room temperature or above. Presumably this annealing is produced by kinetic interactions of the beam with the existing lattice damage and/or conversion of the beam energy to thermal energy as the ions come to rest.

In all cases the Al sublattice recovers at lower temperatures than the oxygen sublattice. This is shown most clearly in Fig. 2.33, which consists of plots of $X_{\min}$ (the ratio of the aligned to random yield) vs temperature for the Cu-implanted specimens. The $X_{\min}$ for Al is significantly lower than the value for oxygen, except perhaps after annealing at 1500°C. One will note too that the oxygen sublattice is still nearly amorphous in the as-implanted state, indicating that it is relatively less affected by the ion-beam-induced annealing. This effect is present irrespective of the implanted species. Thus, we infer that the Al interstitial becomes mobile at much lower temperatures than the oxygen interstitial.

Fig. 2.33. Lattice recovery and impurity incorporation into the lattice following thermal annealing in O_2 of Al_2O_3 implanted with ^{63}Cu (130 keV, $4 \times 10^{16}/cm^2$).

Transport of impurities in Al_2O_3 during thermal annealing is limited. If the impurity exhibits any redistribution during annealing, there is a definite preference to move toward the surface rather than toward the bulk. This effect suggests that the presence of oxygen in the atmosphere during annealing induces a chemical gradient affecting diffusion.

Channeling and transport behavior of the impurity following annealing at 1500°C can be divided into three groups. The first consists of Ga and Cr, both of which are better than 95% substitutional in the lattice after annealing at 1500°C. The backscattering spectra show the Ga to have redistributed after annealing at this temperature, and the Cr is known to diffuse after annealing at 1600°C. Cr is known to have valence 3+ after annealing at 1600°C, and Ga is rarely found in an oxidation state other than 3+. Additionally, both Cr_2O_3 and Ga_2O_3 have the same crystal structure as Al_2O_3 . The second group consists of Cu and Mn, which show neither any evidence of channeling nor any redistribution in depth. The oxides of these elements are expected to be divalent, MnO having a cubic symmetry and CuO having a tetragonal symmetry. The third group consists of Ti, Ni, and Fe, all of which show some amount of channeling and redistribution but which are definitely not substitutional. The Ti- and Fe-implanted samples are known to form precipitates after annealing at 1500°C. It is in fact the orientation of the precipitates which is believed to be responsible for the channeling observed along the $\langle 0001 \rangle$ Al_2O_3 direction for the Fe-implanted case.⁶ It is not known whether the Ni has formed precipitates. All three of these ions can take a 3+ oxidation state; however, it is the preferred state for Fe only, and the valence of these ions in the implanted and annealed material is not known.

Knoop microhardness measurements have been made on Cu- and Fe-implanted specimens. These are more or less typical of two patterns of behavior of the microhardness observed following annealing. Both show an increase in the hardness relative to the unimplanted material of 20 to 30% in the as-implanted state. The Cu hardness quickly diminishes after annealing at 1200°C and above. The lattice damage has also diminished to nearly that of the unimplanted state. The hardness of the Fe-implanted samples shows only marginal decrease following annealing. We suspect that the fine precipitate structure in the Fe-implanted samples is producing precipitation hardening of the material following annealing at the higher temperatures and perhaps is also stabilizing any residual lattice damage.

1. Summary of paper: p. 385 in *Ion Implantation and Ion Beam Processing of Materials*, ed. by G. K. Hubler et al., Elsevier, New York, 1984.
2. ORAU Postdoctoral Fellow.
3. Metals and Ceramics Division, ORNL.
4. H. Naramoto et al., *J. Appl. Phys.* 54, 683 (1983); H. Naramoto et al., *Nucl. Instrum. Methods* 201/202, 1159 (1983).
5. C. W. White et al., "Formation of Amorphous Layers in Al_2O_3 by Ion Implantation," this report.

6. G. C. Farlow et al., "Thermal Annealing of Fe-Implanted Al_2O_3 in Oxidizing and Reducing Environments," this report.

ION IMPLANTATION OF SURGICAL Ti-6Al-4V ALLOY¹

J. M. Williams G. M. Beardsley²
R. A. Buchanan³ R. K. Bacon³
E. D. Rigney³

The alloy Ti-6Al-4V is nearly ideal as a surgical implant material owing to a host of desirable properties including good corrosion resistance and biocompatibility, good ductility and fabricability, high tensile strength, good fatigue life, low density, and perhaps most importantly, its low modulus of elasticity. Thus, this alloy is widely used for construction of the femoral component in total artificial hip joint systems, and its use is increasing. During walking, the alloy head of the femoral component works in the acetabular cup constructed of ultra-high-molecular-weight polyethylene (UHMWPE). Unfortunately, in such service the poor wear resistance of the alloy threatens to compromise both the biocompatibility and the lifetimes of these prostheses to an unacceptable degree. The present work strongly suggests that ion implantation of N is an ideal solution to this wear problem. In addition, we believe that the solution is practical, cost effective, and will receive swift application.

The test apparatus was designed to simulate approximately pertinent factors of the hip-joint application and also provide an in situ measurement of wear rate.¹ Cylindrical alloy samples were rotated between loaded, conforming UHMWPE pads (at a relative speed similar to that which occurs in the hip joint during walking) with these working components immersed in saline electrolyte. Electrochemical corrosion currents at anodic potential (-100 mV vs SCE) measured during this mechanical action were interpreted as a measure of corrosive-wear rate. With no mechanical action, no corrosion current is measured because the sample is quickly passivated. Rubbing by the pads and abrasive action by oxide particles in the sliding interface remove the oxide, and as the sample repassivates itself, a corrosion current is measured. Thus the corrosion current reflects the rate of this continuing process of oxide removal and repassivation. Removal of alloy substrate before it has been oxidized, possibly by abrasive action, is not detected as corrosion current. Therefore, both profilometry measurements and a Zr marker technique were used in addition to the electrochemical measurements. The marker technique involved depth measurements of ion-implanted Zr markers by use of He-ion backscattering techniques. Ion backscattering studies of samples and wear product were done to generate analyses which might help explain the test results. Our principal ion implantation treatment was designed to produce a concentration of about 20% of implanted N to a depth of about 100 nm.¹

Implantation of the 20% N reduced the corrosion currents by average factors that ranged from 500 at the start of the tests to 10⁴ at the end

of 10-h tests. This variation means that most of the material removal for implanted samples occurred in the early part of the test. By use of Faraday's law the integrated corrosion currents for 10-h tests convert to 0.7 μ m of material removed for unimplanted samples and to 0.3 nm for implanted ones, on the average. Unimplanted samples became heavily blackened and scored, whereas implanted samples remained as polished (Fig. 2.34). Circumferential wear striations on the unimplanted sample are easily detected by touching. Profilometry measurements indicate that two to three times as much material is removed from unimplanted samples as is calculated from the electrochemical measurements. Furthermore, the wear is highly localized in the striations. Profilometer traces of implanted tested samples were indistinguishable from those of new samples. To a resolution level of 7 nm, no material removal for implanted samples was detected by the Zr marker technique in tests extending to 14 h.

Ion backscattering analyses of the black deposit (Fig. 2.34) were done with 2.0-MeV He ions and with 1.79-MeV H ions. The latter energy is near the resonance energy for elastic backscattering of H from C by the reaction, $^{12}C(p,p)^{12}C$. Thus, the detectability of C is enhanced in comparison with that which obtains under pure Rutherford scattering. The black deposit apparently consists largely of TiO_2 embedded in polyethylene wiped from the pads. Some evidence for unoxidized metallic debris from the substrate was also found. The deposit is about 2 μ m thick. Thus, all evidence points to the conclusion that wear of the unimplanted material is at the micron level or greater. The absence of C on the implanted samples (and other evidence not discussed here) means that implantation of the alloy also improves wear performance of the UHMWPE wear partner. This finding is also of practical importance.

ORNL-Photo 5050-84

Fig. 2.34. Photograph showing unimplanted (left) and 20% N-implanted (right) Ti-6Al-4V samples after 10-h corrosive-wear tests in saline electrolyte.

Ion implantation of N reduces the corrosive-wear rates of Ti-6Al-4V alloy from very high levels, detectable by crude means to nearly zero, hardly measurable levels. Thus, impressive, but not very precise, improvement factors can be quoted. Such large effects suggest that some type of threshold effect might explain the improvement. Considerable support can be found for the idea that implantation hardens the alloy surface so that it is just harder than the TiO_2 wear debris. Under such a condition any protective oxide that forms is better supported against puncturing by existing wear debris than that for unimplanted samples. Also, direct abrasion of the substrate might be nearly impossible.

1. Summary of papers: *Mat. Res. Soc. Symp. Proc.* 27, 735 (1984); *Materials Science Engineering* (to be published).

2. Oak Ridge Associated Universities faculty research participant from Millsaps College, Jackson, Miss.

3. The University of Alabama-Birmingham, Birmingham, Ala.

POTENTIAL AND STOPPING POWER INFORMATION FROM ION CHANNELING IN Ge¹

R. J. Culbertson S. P. Withrow
J. H. Barrett

Planar channelled ions can be steered by the ion-atom interaction potential into oscillating trajectories that periodically approach the walls of the planes. At depths where the approaches occur, the ions have an enhanced nuclear encounter probability and increased backscattering yield. Because of energy loss as the ions penetrate the solid, the periodically increased yield appears as peaks in the backscattering energy spectrum. The separation in energy of adjacent peaks a and b , ΔE_{ab} , can be related to the half wavelength of the oscillations $\lambda/2$ and the stopping power of the ions in the solid by the equation

$$\Delta E = \frac{\lambda}{2} S_r(k^2 E_0) \frac{\cos \theta_{in}}{\cos \theta_{out}} + \frac{\lambda}{2} k^2 \gamma_0 S_r(E_0), \quad (1)$$

where θ_{in} , θ_{out} are the incoming and outgoing angles relative to the surface normal, k^2 is the kinematic scattering factor, $S_r(E)$ is the stopping power for a random direction in the solid at energy E , and γ_0 is the ratio of the stopping power S_c for channelled ions at energy E_0 oscillating with large amplitude in the channel to the random stopping power at the same energy. It is possible to obtain γ_0 and $\lambda/2$ experimentally by measuring ΔE_{ab} as a function of $\cos \theta_{in}/\cos \theta_{out}$ and using Eq. (1). This method is referred to as the "cosine method."

Barrett² has proposed an alternative method for obtaining $\lambda/2$ and γ_0 , referred to here as the "q method." This latter approach involves measuring the angle of inclination of the incident beam from the plane ψ_M that produces the maximum yield of backscattered ions. Barrett has shown by computer simulations that ψ_M is an

indication of the strength of the interaction potential.

Results for planar channeling of 1.0 and 2.0 MeV He^+ in three low-index planes of Ge were obtained, and comparisons were made between the two methods. Computer simulations were used to study the interaction potential in Ge.

Using the cosine method, spectra were obtained at a fixed scattering angle for different values of the angle θ_{in} . The energy separation of adjacent peaks in the backscattering spectra was plotted as a function of $\cos \theta_{in}/\cos \theta_{out}$. The energy separation between the first two peaks ΔE_{12} is shown in Fig. 2.35 over a range of cosine ratios for spectra obtained by channeling in a $\{110\}$ plane at 1.0 and 2.0 MeV. The half wavelength $\lambda/2$ and stopping power ratio γ_0 were determined from the slope and intercept of a fitted line using Eq. (1). Values for ΔE_{23} were slightly larger than for ΔE_{12} . The values for the ratio of channeling to random stopping power γ_0 were derived from the intercept, slope, k^2 , $S_r(E_0)$, and $S_r k^2(E_0)$. The values of γ_0 and $\lambda/2$ were 0.97 ± 0.16 and 35.3 ± 2.2 nm, respectively, for 1 MeV, and the values at 2 MeV were 1.15 ± 0.13 and 43.7 ± 2.4 nm, respectively.

Fig. 2.35. ΔE_{12} vs $\cos \theta_{in}/\cos \theta_{out}$ for He^+ incident [in a $\{110\}$ plane] of Ge. The incident energy is 2.0 MeV for the closed circles and 1.0 MeV for the open circles.

Using the q method the angles θ_{in} and θ_{out} were fixed, and an angular scan across a plane was made by varying the angle between the beam direction and the plane. The height of the highest yield oscillation in each of these near-planar channeling spectra was plotted as a function of the angle ψ from the plane, and the angle ψ_M where the graph is a maximum was determined.

Figure 2.36 shows the results of a ψ scan for 2 MeV He^+ near a $\{110\}$ plane of Ge. The θ_{in} and the laboratory scattering angle were fixed at 28.29° and 84.00° , respectively. The height of the highest yield oscillation in each spectrum is plotted as a function of the angle ψ . Normalization to the yield for a random direction was used.

For each ion energy and set of target planes, a plot of backscattering yield as a function of distance into the crystal for exact alignment of the ion beam with the planar channel was made. From these plots values were obtained for the first and second half wavelengths, $(\lambda/2)_1$ and $(\lambda/2)_2$. Values of ψ_M were obtained by the curve-of-maxima method,² one example of which is shown in Fig. 2.36. The q method gives a value of

44.1 ± 1.7 nm for $\lambda/2$, which is in good agreement with the cosine method.

The agreement between calculated and experimental values of $\lambda/2$ and ψ_M is better when a Molière potential is used with Firsov screening rather than screening for the target atom only. Thus, the true potential is slightly weaker than the potential with target atom screening. The modification of the potential due to the difference between the two screening lengths used in our calculations produces large enough changes in the calculated surface yield to be of possible significance when ion scattering is being used to study surface structure.

The two methods appear to have comparable accuracy in determining Y_0 , although the cosine method is probably more convenient for this purpose. However, the q method may be preferred to obtain information about the interaction potential since the strength of the potential is more directly indicated by the value of ψ_M than $\lambda/2$.

1. Summary of paper: Nucl. Instrum. Methods 230, 19 (1984).
2. J. H. Barrett, Phys. Rev. B 20, 3535 (1979).

Fig. 2.36. Height of the highest yield oscillation as a function of angle between the incident beam direction and a $\{110\}$ plane in Ge for 2.0-MeV He^+ . The open and closed circles are experimental points from opposite sides of the plane. The squares are calculated using the Firsov screening function.

SUBSURFACE STRAIN IN SEMICONDUCTOR SURFACES: COMPARISON OF Ge AND Si¹

R. J. Culbertson Y. Kuk²
L. C. Feldman²

Ion scattering was used to characterize the subsurface strain in the (001) and (111) crystallographic surfaces of Ge. The results were compared with previous work on Si(001)³ and Si(111),⁴ and a strong correlation in the nature of the displacements was found for these two elemental semiconductors: large, in-plane displacements for Ge(001)-(4×2) extending to 3 monolayers deep and large displacements perpendicular to the surface for Ge(111)-(2×8) surface. Also, measurements were made for the deuterium uptake on these two Ge surfaces, and direct comparison of the rate of deuterium adsorption for these surfaces and for Si(111)-(7×7) from a previous study⁵ was made.

The clean (001) face of germanium exhibited a (2×1) reconstruction at room temperature, but evidence of streaks at the position of the quarter order spots was observed. Below room temperature the quarter order streaks became sharper and were well-defined spots at 100 K. The energy dependence of the ion scattering surface peak along the normal [001] and non-normal [101] directions was measured. The results were compared with calculations for several models: vacancy model,⁶ conjugated chain model,⁷ symmetric dimer model,⁸ and buckled dimer model.^{9,10} The experimental points were generally higher than the calculated values for all models, although the dimer models showed better agreement than the other models.

These results are qualitatively very similar to those of previous work on Si(001).³ By plotting the surface peak as a function of a parameter such as the ratio of the two-dimensional vibration amplitude a to the radius of the ion shadow

cone at one atom distance away,¹¹ the temperature and energy dependence for both surfaces were compared, as shown in Fig. 2.37. The solid line is from the "universal curve,"¹¹ and it represents the value of the surface peak for an ideal bulk-like structure. Values above this line indicate deviations from an idealized structure due to static and dynamic atom displacements. The data for both Ge and Si clearly indicate the existence of substantial displacements.

The clean (111) face of germanium exhibits a (2×8) low-energy electron diffraction (LEED) pattern. The measurements of the surface peak energy dependence of Ge(111)-(2×8) for [111] and [100] incidences at 300 and 130 K are shown in Fig. 2.37. As in the case of the (001) surfaces, the comparison of Ge and Si was made for the (111) case. Although the normal incidence data for both surfaces exceed the values for an idealized surface, the data for [001] incidence are much higher. This indicates in Ge and Si that atoms are displaced both parallel and perpendicular to the surface, but the perpendicular displacements are much more significant.

The results of hydrogen uptake measurements as a function of exposure for Ge(001) and Ge(111) were fitted to a simple exponential and compared to previous results on Si(111)⁵ which were done in the same geometry. The sticking coefficient for Ge(001) was 2.3 times lower than that of Si(111). The saturation coverage for Ge(001)

was 1.5 monolayers. Previous work on Si(101) yielded a value of 1.6 monolayers for saturation.³ The hydrogen sticking coefficient on Ge(111) was essentially the same as on Si(111). However, the saturation coverage was approximately 1.0 monolayers compared with 1.25 monolayers for Si(111). The higher saturation on Si(111) may be due to additional bonding sites at steps or adatoms, while the Ge(111) surface apparently lacks these sites.

The Ge(001)-c(4×2) structure changes to a (2×1) structure after a fraction of a monolayer of hydrogen is chemisorbed. When hydrogen was chemisorbed up to 1.5 monolayer, the surface peak was approximately 0.1 to 0.2 atoms/row lower than that of the clean surface. This effect implies that chemisorbed hydrogen in part relieves the strain of the reconstruction surface. Although a sharp dihydride (1×1) pattern has been observed on Si(001) at saturation coverage,¹² the (2×1) pattern persisted in Ge(001) all the way to saturation. This difference in behavior of the hydrogen chemisorbed surfaces may be indicative of the relative strengths of the Si and Ge surface dimers.

The Ge(111) surface reveals similar adsorption behavior to that of the Si(111) surface: as hydrogen is chemisorbed, some higher order spots in the LEED pattern disappear while the background intensity increases.

In the case of the Ge(001) surface, models with large in-plane first-layer displacements, second-layer displacement mainly along the in-plane direction, and the third-layer displacement along the out-of-plane direction show the best agreement with the data. This is in qualitative agreement with the clean Si(001) surface.

Similar to the case of Si, the saturation coverage of hydrogen on Ge(001) was approximately 1.5 monolayers, although it is significant that, unlike Si, the Ge structure did not convert to a (1×1) at saturation.

The (111) surfaces of Ge and Si also have many similarities. Both surfaces have atom displacements parallel to the surface and much larger displacements perpendicular to the surface, although other types of models such as stacking faults¹³ can also explain the data. The rates of hydrogen uptake on both Ge(111) and Si(111) are nearly identical. The gradual increase in the background and the persistence of the fractional order spots in the LEED pattern are also similar.

Fig. 2.37. Ion scattering surface peak as a function of p/R_M the (001) and (111) surfaces of Ge and Si. The Si(001) data are from reference 3 and the Si(111) data are from references 4 and 14. The solid line is from the "universal curve" in reference 11.

1. Work sponsored in part by AT&T Bell Laboratories, Murray Hill, N.J.
2. AT&T Bell Laboratories, Murray Hill, N.J.
3. I. Stensgaard, L. C. Feldman, and P. J. Silverman, *Surf. Sci.* 102, 1 (1981).
4. R. J. Culbertson, L. C. Feldman, and P. J. Silverman, *Phys. Rev. Lett.* 45, 2043 (1980).
5. R. J. Culbertson et al., *J. Vac. Sci. Technol.* 20, 868 (1982).
6. W. A. Harrison, *Surf. Sci.* 55, 1 (1976).
7. T. D. Poppendieck, T. C. Ngoc, and M. B. Webb, *Surf. Sci.* 75, 287 (1978).
8. J. A. Applebaum and D. R. Hamann, *Surf. Sci.* 74, 21 (1978).

9. D. J. Chadi, *Phys. Rev. Lett.* **43**, 43 (1979).
10. M. T. Yin and M. L. Cohen, *Phys. Rev. B* **24**, 2303 (1981).
11. I. Stensgaard, L. C. Feldman, and P. J. Silverman, *Surf. Sci.* **77**, 513 (1978).
12. T. Sakurai and H. D. Hagstrum, *Phys. Rev. B* **14**, 1593 (1976).
13. P. A. Bennett et al., *Phys. Rev. B* **28**, 3656 (1983).
14. R. J. Culbertson, L. C. Feldman, and P. J. Silverman (unpublished data).

PULSED-LASER AND THERMAL PROCESSING

REVIEW OF PULSED-LASER ANNEALING EFFECTS IN SILICON¹

B. C. Larson

A short review of the lattice heating, dopant redistribution, and rapid crystal growth effects associated with pulsed-laser annealing in silicon is given. The mechanism of pulsed-laser annealing in silicon has been discussed in terms of the "thermal melting" and "plasma fluid" models. Although a heated controversy arose as to the appropriate model, evidence establishing thermal melting as the mechanism of defect removal and dopant redistribution is now overwhelming. Time-resolved x-ray diffraction, transient electrical conductivity, and thermal particle emission played central roles in distinguishing between the two models.

The rapid melting and regrowth associated with pulsed-laser annealing have provided an opportunity for performing fundamental crystal growth investigations under highly nonequilibrium conditions in a controlled and reproducible manner. As a result, measurements and calculations have been appearing in these areas in increasing numbers. This is especially true with respect to investigations involving solute redistribution and solute trapping during the regrowth phase of the annealing process. Large changes have been found in the segregation coefficients for solutes as a function of regrowth velocity and growth direction, and new considerations for undercooling and morphological instabilities have manifested themselves. As careful measurements are performed in these areas and detailed correlations are made with evolving theoretical models for these phenomena, a significant amount of new information regarding the use of nonequilibrium conditions to produce metastable materials and materials modifications of technological importance can be expected.

X-RAY MEASUREMENT OF OVERHEATING AND UNDER-COOLING IN SI DURING PULSED-LASER IRRADIATION

B. C. Larson J. Z. Tischler
D. M. Mills¹

Many of the fundamental aspects of crystal growth involving rapid melting and recrystallization encountered in pulsed-laser processing of semiconductors are not well understood. Detailed microscopic models do not exist for solute trapping during rapid crystal growth, nor is there agreement on the mechanism of amorphization in silicon that occurs at growth velocities >15 m/s. In this study we have used time-resolved x-ray measurements to investigate lattice overheating and undercooling as the driving forces for rapid melting and crystal growth in laser-irradiated Si.

The velocity v of the liquid-solid interface defines the rate of melting or growth of a solid during heating or cooling, and it can be written in kinetic terms as:

$$v = v_0(1 - e^{-\Delta G/kT}) \quad (1)$$

where ΔG is the free energy associated with the thermodynamic driving force, k is Boltzmann's constant, T is the lattice temperature, and v_0 is the maximum possible regrowth velocity. Although much of the physics is contained in v_0 , relatively little quantitative information is available for this parameter because of its dependence on microscopic variables, such as the crystal surface geometry, atomic or diffusional jump frequencies, and the interface temperature in the liquid. Therefore, Eq. (1) is difficult to relate to experimental measurements. However, for materials with large melting enthalpies, such as silicon and germanium, the interface velocity is governed primarily by the transport of latent heat at the interface; therefore, the velocity can be written in terms of macroscopic heat flow as

$$v = K\bar{\nabla}T/\Delta H_m \quad (2)$$

where K is the thermal conductivity, $\bar{\nabla}T$ is the thermal gradient at the interface, ΔH_m is the melting enthalpy, and ρ is the density. Combining Eqs. (1) and (2) and writing $\Delta G = \Delta H_m \Delta T/T_m$, where T_m is the melting temperature, we obtain the form

$$\frac{K\bar{\nabla}T}{\Delta H_m} = v_0 [1 - e^{-(\Delta H_m \Delta T/kT_m)}] \quad (3)$$

This indicates that experimental measurements of the thermal gradient $\bar{\nabla}T$ and the overheating or undercooling ΔT provide information on v_0 and hence on the microscopic aspects of the crystal growth process.

Time-resolved x-ray measurements with nanosecond resolution have been made on the temperature profiles in Si during pulsed-laser irradiation using the time structure of the Cornell High Energy Synchrotron Source. The measurements were made on <111>- and <100>-oriented Si irradiated

1. Summary of review paper to be published.

by 1.2 J/cm^2 laser pulses with a FWHM of 25 ns and a wavelength of 249 nm. Lattice temperatures were determined by analyzing² the time-resolved x-ray Bragg profile measurements in terms of thermal expansion induced strain. Figure 2.38 shows $\langle 111 \rangle$ Bragg profile measurements made both during the laser pulses (15 ns) when rapid melting was occurring and after the laser pulses (45 ns) during the recrystallization; the scattering at negative $\Delta\theta$ indicates the presence of thermal strains from the transient laser heat pulse. The solid lines represent least-squares fits of the measured x-ray intensities to scattering calculations for a thermally strained lattice, where the lattice temperatures as a function of depth served as the fitting parameters. The temperature profiles corresponding to these data are shown in Fig. 2.39; the depth scale is referenced to the liquid-solid interface as the liquid layer produces no Bragg scattering. In addition to the high temperatures at the interface and the large

Fig. 2.38. Time-resolved x-ray scattering profiles measured on the $\langle 111 \rangle$ reflection during pulsed-laser irradiation. The times are referenced to the beginning of the laser pulses, and the solid lines are fits to the data.

Fig. 2.39. Lattice temperature profiles corresponding to the measured data in Fig. 2.38.

temperature gradients, Fig. 2.39 shows that the interface temperature measured during the laser pulses was $\sim 120 (\pm 30) \text{ K}$ higher than that measured during the regrowth process. This indicates the magnitude of overheating (and undercooling) required to drive the rapid melting (and regrowth) on the $\langle 111 \rangle$ surface of Si.

The lattice temperature gradient for the 45-ns measurements in Fig. 2.39 corresponds to a crystal regrowth velocity of $\sim 7 \text{ m/s}$ [using Eq. (2)], a value consistent with detailed numerical heat flow calculations³ which give $\sim 10 \text{ m/s}$ melt-in velocities and $\sim 6 \text{ m/s}$ regrowth velocities for the above laser conditions. Similar x-ray measurements made on the $\langle 400 \rangle$ reflection during pulsed-laser irradiation yielded only a $45 (\pm 20) \text{ K}$ temperature difference at the interface for $\langle 100 \rangle$ -oriented Si. Since the thermal conductivity is isotropic, the melting and regrowth velocities do not change with orientation. Therefore, these measurements have shown that a smaller driving force is required for growth on $\langle 100 \rangle$ Si than on $\langle 111 \rangle$ Si.

Uncertainties in the temperature dependence of the thermal expansion coefficients and the elastic constants preclude an accurate separation of the lattice overheating from the undercooling. However, under the assumption that v_0 behaves similarly for overheating and undercooling, "effective" v_0 values of ~ 35 and $\sim 195 \text{ m/s}$ can be obtained for the $\langle 111 \rangle$ and $\langle 100 \rangle$ orientations, respectively, using Eq. (3).

1. Cornell High Energy Synchrotron Source, Cornell University, Ithaca, N.Y.
2. B. C. Larson et al., *Appl. Phys. Lett.* **42**, 282 (1983).
3. M. Aziz (private communication).

GERMANIUM LASER ANNEALING

J. Z. Tischler B. C. Larson
D. M. Mills¹

This experiment used time-resolved x-ray diffraction to measure thermal strain in germanium crystals during pulsed-laser irradiation. As described elsewhere in this report,² lattice temperatures were obtained from Bragg profiles measured during and immediately after the laser pulse, thus observing both melt-in and regrowth. Temperature profiles in the crystal were computed from the measured Bragg profiles. These temperature profiles provide information on the thermodynamic properties of germanium associated with heat flow and crystal growth. We found that the temperature gradients near the liquid-solid interface were two or three times larger than those expected from heat-flow calculations using published thermal conductivity data. These results are surprising in view of the results from the silicon investigations,² in which the calculated and measured temperature profiles were in good agreement.

This experiment was performed at the Cornell High Energy Synchrotron Source (CHESS) and used the pulsed nature of the x-ray beam. The Bragg profile data were taken at fixed times after 0.6-J/cm^2 25-ns KrF excimer laser pulses. The

delay time was reckoned from the start of the laser pulse until the arrival of the synchrotron x-ray pulse and was measured to within ± 2 ns.

The Bragg profiles were taken at delay times of 15 and 45 ns, which correspond to the times of the maximum melt-in and regrowth velocities. Germanium (111) profiles obtained in a step scan mode (with 9 laser pulses at each point) are shown in Fig. 2.40, where the tails of the Bragg profile extending to negative angles directly indicate the presence of hot (expanded) crystalline material near the interface. A recursive procedure was used to obtain temperature profiles from these data by a fitting routine that adjusted the temperature profile until the scattering calculated from the thermal strain distribution matched the measured scattering. The solid lines in Fig. 2.40 represent the calculated scattering from the fitted temperature profiles.

The fitted and calculated temperature profiles for 15 and 45 ns are shown in Fig. 2.41. The cal-

Fig. 2.40. Measured and fitted Bragg profiles for the Ge (111) reflection at delay times of 15 and 45 ns. The solid line represents scattering calculations fitted to the measured data points. Note that the 15-ns data extend to slightly larger angle. Thus, the liquid-solid interface temperature is higher during melt-in than during regrowth.

Fig. 2.41. Measured temperature profiles (solid lines). Temperature profiles calculated using equilibrium thermal conductivity (dashed lines) and modified thermal conductivity (dotted lines): (a) at 15-ns delay; (b) at 45-ns delay.

culated temperature profiles were produced using a numerical heat-flow program from M. U. Thompson and the thermal parameters for germanium.³ The most important differences between the measured and calculated temperature profiles are the higher temperature gradients near the interface in the measured profiles and the generally higher temperatures in the calculated profiles. This lack of heat flow into the lattice suggests that thermal conductivity near the interface is lower than the equilibrium value.

The magnitude of thermal conductivity change needed to explain such an effect was modeled by repeating the heat-flow calculation with reduced thermal conductivity at the higher temperatures. The dotted profiles in Fig. 2.41 were obtained with the conductivity set to a power law in T between the equilibrium value at 900 K and 0.05 W/cmK at the melting point; the equilibrium value at the melting point is 0.175 W/cmK. Note how much better this new profile fits the measured one.

Although the physical origin of such a large change in the thermal conductivity has not been established, two processes present themselves as possible causes. The conductivity may have decreased due to oxygen diffusing into the crystal from a stable oxide layer that formed after a few laser shots. Also, the large strain gradients may enhance the lattice thermal resistance by increasing the scattering of long wavelength phonons.

We note that the interface temperature of the 15-ns data is 100 K higher than that of the 45-ns data. This difference is believed to be related to overheating and undercooling of the interface during melting and regrowth. However, since the apparent regrowth temperature is above the 1210 K equilibrium melting point, effects such as uncertainty in the thermal expansion coefficient and nonthermal electron-carrier induced expansion (which might affect both the melting and regrowth temperatures) must be investigated before the overheating and undercooling can be determined.

The thermal conduction effects observed here are under further investigation as are similar effects observed during pulsed-laser irradiation of arsenic-implanted silicon. Thermal conductivity under nonequilibrium conditions with high temperatures and strain gradients has not been previously investigated and may reveal new physical phenomena.

1. Cornell High Energy Synchrotron Source, Cornell University, Ithaca, N.Y.
2. B. C. Larson, "Pulsed-Laser Annealing Effects in Silicon," this report.
3. Thermophysical Properties of Matter, Vol. 2, IFI/Plenum, New York, 1970. Thermal conductivity of the liquid came from the Wiedeman-Franz law.

COMPETITION BETWEEN GLASS FORMATION AND NONEQUILIBRIUM CRYSTALLIZATION DURING ULTRARAPID SOLIDIFICATION OF Cu-Ti ALLOYS¹

D. H. Lowndes C. G. Woychik²
T. R. Massalski²

The possibility of forming a solid metallic glass by rapid quenching from the molten phase

depends upon the composition of the liquid alloy and upon the quenching rate. Conventional ribbon-spinning techniques (producing cooling rates $>10^5$ K/s) were recently shown to result in glass formation over the central one-third of the Cu-Ti phase diagram.³ However, samples quenched by this technique were found not to be completely amorphous, but to contain crystalline structures that apparently compete with glass formation during rapid cooling. Nanosecond duration laser pulses are capable of producing cooling rates some five orders of magnitude more rapid ($\sim 10^{10}$ K/s); thus, it is of interest to study the competition between glass formation and crystallization under these much more rapid quenching conditions in order to determine (1) whether the compositional range for glass formation can be extended and (2) whether the same crystalline phases, or new nonequilibrium crystalline phases, compete with glass formation under highly non-equilibrium conditions.

Molten alloys of five different compositions (corresponding to Cu:Ti ratios of 20:80, 43:57, 50:50, 75:25, and 85:15) were subjected to rapid cooling both by spinning thin (40–50 μm) ribbons directly from the melt and by pulsed ruby laser melting and solidification. The maximum ribbon-spinning speed corresponded to a calculated maximum average cooling rate of about 5×10^5 K/s. Pulsed ruby laser (694-nm wavelength, 18-ns FWHM pulse duration) irradiation resulted in measured melt depths of 0.1 to 0.5 μm and in a quenching rate calculated to be slightly greater than 10^{10} K/s. X-ray microanalysis was carried out after rapid solidification using scanning transmission electron microscopy to determine the morphology and composition of crystalline and amorphous regions.

Table 2.5 summarizes the phases detected for the various alloy compositions and quenching conditions. Even at the maximum quenching rates obtainable using the ribbon-spinning technique, glass formation was found to be limited to the center of the Cu-Ti compositional range, with CuTi_2 crystals being formed instead of metallic glass from Cu-poor alloys and with the fcc phase (which appears to be an extension of the equilibrium fcc phase on the Cu-rich side of the phase diagram) and other equilibrium crystalline phases forming instead of glass from Cu-rich alloys.

Table 2.5. Phases present following rapid quenching of Cu-Ti alloys

Rapid cooling conditions	$\text{Cu}_{20}\text{Ti}_{80}$	$\text{Cu}_{43}\text{Ti}_{57}$	$\text{Cu}_{50}\text{Ti}_{50}$	$\text{Cu}_{75}\text{Ti}_{25}$	$\text{Cu}_{85}\text{Ti}_{15}$
Low-speed ribbon-spinning (cooling rate $\sim 10^5$ K/s)		$\text{CuTi}_2 + \text{CuTi}$	CuTi		
High-speed ribbon-spinning (cooling rate $\sim 5 \cdot 10^5$ K/s)	CuTi_2	$\text{CuTi}_2 + \text{glass}$	$\text{CuTi}_2 + \text{glass}$	$\text{Cu}_3\text{Ti}_2 + \text{Cu}_6\text{Ti} + \text{Cu}_3\text{Ti} + \text{fcc}$	fcc
Pulsed-laser quenching (cooling rate $\sim 10^{11}$ K/s)		fcc + glass	fcc + glass		fcc + glass

In contrast to the variety of structures obtained by melt spinning, laser quenching was found to result in the formation of only metallic glass or of crystallites of the fcc phase (Table 2.5). For the $\text{Cu}_{43}\text{Ti}_{57}$ and $\text{Cu}_{50}\text{Ti}_{50}$ compositions, a profusion of very fine fcc microcrystallites was observed, with an average grain size of about 100 Å. Selected area microdiffraction measurements showed that these fine fcc crystallites were always mixed together with amorphous material and that some peripheral regions of completely amorphous material were also present. For the $\text{Cu}_{85}\text{Ti}_{15}$ alloy, laser quenching resulted only in small regions of the amorphous phase and in much larger regions consisting of several large fcc crystals alternating with regions of very fine fcc crystallites.

A substantial difference was found in the measured lattice parameters for the large- and fine-grained fcc phase for the $\text{Cu}_{85}\text{Ti}_{15}$ composition; this result made it of immediate interest to determine the composition dependence of the lattice parameter (or average interatomic spacing) in the metastable fcc phase throughout the Cu-Ti system. Figure 2.42 shows the Seitz radii r_0 that were calculated for the laser-induced fcc structures, where $r_0 = (3/4\pi\rho)^{1/3}$ and ρ is the volume of the unit cell. The upper straight line in Fig. 2.42 joins r_0 for HCP Ti and fcc Cu (assuming that r_0 for Ti may be calculated in this way); deviations from this line then represent deviations from an assumed Vegard's law for Seitz radii. The lower straight line in Fig. 2.42 is an extrapolation of the trend of the equilibrium α -Cu phase lattice parameters;⁴ the measured lattice parameters for the large fcc crystals obtained by laser quenching of $\text{Cu}_{85}\text{Ti}_{15}$ do lie on this extrapolated line. In contrast, Seitz radii for the fine-grained fcc crystals exhibit large positive deviations of 10–15% from the assumed Vegard's law behavior. Thus, the large

fcc crystals appear to have been formed at a cooling rate much slower than that associated with formation of the very fine fcc crystallites. One intriguing possibility is that the positive deviations from the assumed Vegard's law behavior shown in Fig. 2.42 represent a real quenched-in free volume contribution resulting from rapid solidification from the liquid phase. Volume differences between liquid and crystalline forms resulting from equilibrium solidification rarely exceed 4% for pure metals. Theoretical estimates suggest that from 5 to 11% of the total volume of Au-Ge-Si, Pd-Cu-Si, and Pd-Ni-P metallic glasses may be due to quenched-in free volume,⁵ while volume differences of 10–25% have been observed for polymer glasses.⁵ In contrast, our measurements of Seitz radii correspond to a quenched-in free volume of about 40%, relative to Vegard's law behavior. This seems too large to be credible, but probably only indicates the inapplicability of Vegard's law to Fig. 2.42.

The observed very small grain size of the fcc crystallites, together with their distribution over a substantial part of the resolidified laser-irradiated region, implies that their growth may not have occurred epitaxially at a rapidly advancing melt-solid interface but instead may have occurred nearly simultaneously by a "volume" or "bulk" nucleation and growth process.⁶ The small size of the fcc microcrystals in this case would be the result of the very short time available for their growth, before further growth was interrupted by glass formation in the surrounding regions. Some evidence in support of this model comes from transmission electron microscopy selected-area diffraction patterns of the region containing extensive fine-grained fcc microcrystals. These diffraction patterns show a faint diffuse halo, in addition to the rings from fine-grained fcc microcrystals, suggesting that glass at least coexists with, and perhaps surrounds, the fine-grained fcc microcrystals.

One of the conclusions drawn from this work is that only one crystalline phase competes with glass formation but that the structure of the competing phase differs, depending upon the cooling rate. For the lowest cooling rates obtained by ribbon-spinning, only near-equilibrium crystal structures are produced, presumably at temperatures much above the glass formation temperature T_g . However, as the cooling rate increases ($\sim 10^6$ K/s), a single-phase metastable structure (CuTi_2) competes with glass formation in Ti-rich alloys, even for eutectic compositions. At the high cooling rates ($\sim 10^{10}$ K/s) produced by pulsed-laser quenching, it is a composition-invariant microcrystalline fcc phase that competes with glass formation for all compositions tested. The reason for the occurrence of this fcc structure, in preference to other possible structures, may be that it is close packed and thus most nearly resembles the random close packing of the liquid phase. However, measured lattice parameters (Seitz radii) for the fine-grained fcc crystallites that are formed at the highest quenching rates are larger than is expected; this is tentatively ascribed to quenched-in free volume. Estimated epitaxial regrowth velocities following pulsed-laser melting are 10–30 m/s; however, both

Fig. 2.42. Seitz radii and compositions of fcc crystallites found within the laser-melted regions of Cu-Ti alloys having nominal initial compositions $\text{Cu}_{43}\text{Ti}_{57}$, $\text{Cu}_{50}\text{Ti}_{50}$, and $\text{Cu}_{85}\text{Ti}_{15}$.

bulk nucleation and epitaxial nucleation and growth of crystallites may have occurred.

1. Summary of paper to be published.
2. Carnegie-Mellon University, Pittsburgh, Pa.
3. T. B. Massalski, C. G. Woychik, and J. L. Murray, p. 241 in *Alloy Phase Diagrams*, ed. by L. H. Bennett, T. B. Massalski, and B. C. Giessen, North-Holland, New York, 1983.
4. W. Trzebiatowski, J. Berak, and T. Romotowski, *Rozc. Chem.* 27, 426 (1953).
5. P. Ramachandrarao, B. Cantor, and R. W. Cahn, *J. Mater. Sci.* 12, 2488 (1977).
6. D. H. Lowdes, R. F. Wood, and J. Narayan, *Phys. Rev. Lett.* 52, 561 (1984); R. F. Wood, D. H. Lowdes, and J. Narayan, *Appl. Phys. Lett.* 44, 770 (1984).

UV LASER INCORPORATION OF DOPANTS IN SILICON: COMPARISON OF TWO PROCESSES

E. P. Fogarassy¹ D. H. Lowdes
J. Narayan² C. W. White

The rapid deposition of pulsed-laser energy into the near-surface region of silicon leads to melting of crystal, followed by liquid phase epitaxial regrowth from the underlying substrate at a growth velocity of several meters per second. During rapid solidification, implanted or deposited group III and V impurities can be incorporated into substitutional sites in the silicon lattice with concentrations far in excess of their equilibrium solubility limit. We have investigated and compared the incorporation of implanted or deposited antimony into the silicon lattice during laser annealing with a pulsed KrF UV laser ($\lambda = 0.249 \mu\text{m}$, $Z = 35 \text{ ns}$). The surface melting dynamics resulting from laser irradiation have been studied by time-resolved reflectivity. In the two cases, the sharp transition to the high reflectivity phase ($R = 72\%$, at $\lambda = 0.633 \mu\text{m}$ of the HeNe laser probe) is characteristic of molten silicon. Surface melt durations measured on implanted Sb (150 KeV, $5 \times 10^{16} \text{ cm}^{-2}$) and deposited Sb (80 Å thick on crystalline silicon) are significantly larger than those for virgin silicon. The distribution profiles of the dopant, deduced from Rutherford backscattering experiments, show in both cases (Figs. 2.43 and 2.44) a maximum substitutional concentration of about $2 \times 10^{21} \text{ cm}^{-3}$. This value, which corresponds to the solubility limit of Sb for interface velocities close to 6 m/s (as deduced from heat flow calculations), is limited by interface instabilities that develop during regrowth and lead to the formation of a cell structure in the near surface as confirmed by transmission electron microscopy. However, we observe two kinds of cellular structure for implanted and deposited layers. For the implanted case, the cell structure is that which arises from constitutional supercooling during regrowth. In the deposited case, there is a much larger cell structure in addition to that resulting from constitutional supercooling. The larger cell structure is

Fig. 2.43. Comparison of total and substitutional concentrations in ^{121}Sb -implanted (150 keV , $4 \times 10^{16} \text{ cm}^{-2}$) and excimer laser-annealed $\langle 100 \rangle$ Si.

Fig. 2.44. Comparison of total and substitutional concentrations for a thin film of Sb (80 Å) deposited on $\langle 100 \rangle$ Si after excimer laser-induced diffusion.

believed to result from convective instabilities during regrowth.

1. Guest scientist from the Centre National de la Recherche Scientifique, Strasbourg, France.
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.

UV LASER-INDUCED OXIDATION OF HEAVILY DOPED SILICON

E. P. Fogarassy¹ D. H. Lowdes
C. W. White

Rapid oxidation in silicon induced by UV laser pulses has been reported.^{2,3} A significant amount of oxygen was observed to be incorporated in the

regrown silicon layer when irradiation took place in air or in oxygen ambient.

In this work we have investigated the incorporation of oxygen into heavily doped silicon by laser treatment. Different dopants from groups III and V (such as As, Sb, and In) were implanted into <100> silicon to doses in the range $1-5 \times 10^{16} \text{ cm}^{-2}$. Laser annealing was carried out in air using repetitive UV pulses ($\sim 1 \text{ Hz}$) provided by excimer lasers, XeCl ($\lambda = 0.308 \mu\text{m}$), or KrF ($\lambda = 0.243 \mu\text{m}$). The pulse durations were about 35 ns, and the energy density per pulse was in the range $1-1.3 \text{ J/cm}^2$, sufficient to melt the silicon surface layer to a depth of several thousand angstroms, for a time period not exceeding approximately 150 ns. We observe in all cases, after one laser shot, incorporation of a small amount of oxygen localized in the surface as a thin silicon dioxide layer 50-60 Å thick, as deduced from ellipsometry measurements (native oxide $\sim 30 \text{ Å}$). Below the oxide layer, ion-implanted Si is recrystallized, and the different dopants (As, Sb, and In) are incorporated in substitutional sites into silicon lattice; at very high concentration levels (Fig. 2.45) when compared with their solubility limit at thermal equilibrium. By repetitive laser irradiation (50 to 500 shots) at the same energy density, we observe that the amount of oxygen incorporated depends markedly on the dopant, as shown in Fig. 2.45. (In this figure, the amount of oxygen in the near surface is plotted in counts as deduced from RBS spectra.) For As and Sb doping, after approximately 10 shots the amount of oxygen atoms incorporated into Si saturates at a level corresponding to an oxide layer which does not exceed 100 Å, as confirmed by ellipsometry measurements. By contrast, we measure a continuous increase of the amount of oxygen incorporated into indium-implanted silicon as a function of the number of laser shots. In addition, oxygen

incorporation seems to be associated with a degradation of optical properties of the surface. (A dull surface develops, which is believed to be induced by an increase of the surface roughness.) We have also measured solubility limits of different dopants in silicon as a function of the number of laser shots. As shown in Fig. 2.45 substitutional solubilities for As and Sb do not depend on the number of laser shots. For In, the solubility limit decreases dramatically with increasing numbers of laser shots (less than $5 \times 10^{19} \text{ cm}^{-3}$ above 100 shots). We have also observed that multiple-pulse laser irradiation can lead to dopant distribution profiles with deep diffusion tails when the amount of incorporated oxygen is high. Further experiments are in progress to determine the effect of multiple-pulse irradiations on ion-implanted silicon.

1. Guest scientist from the Centre National de la Recherche Scientifique, Strasbourg, France.

2. Y. S. Liu, S. W. Chiang, and F. Bacon, *Appl. Phys. Lett.* 38, 1005 (1981).

3. T. E. Orłowski and H. Richter *Appl. Phys. Lett.* 45, 241 (1984).

FORMATION OF PARTIALLY COHERENT ANTIMONY PRECIPITATES IN ION-IMPLANTED THERMALLY ANNEALED SILICON¹

S. J. Pennycook J. Narayan²
J. W. Holland³

Supersaturated silicon alloys can be produced by ion implantation followed by thermal processing techniques which trap the dopant in substitutional sites but do not allow time for its precipitation. Such systems are metastable, however, and additional thermal processing may cause the precipitation of the dopant in excess of the solubility limit. Here we present a detailed characterization of Sb precipitates in Si with respect to structure, shape, orientation, and coherency with the matrix. {100} and {111} Si were implanted with $^{121}\text{Sb}^+$ (200 keV, $4.4 \times 10^{15} \text{ cm}^{-2}$) and recrystallized by solid-phase epitaxial growth at 550°C for 20 min and then heated at 900°C for 40 min. The process of precipitation was found to start with homogeneous nucleation within the SPE-grown layer (which was free of extended defects), which produced precipitates 5-10 nm in diam, centered at the depth corresponding to the mean projected range of the implanted Sb ions. Then dislocation loops formed near the precipitates, which grew and coalesced to produce a planar dislocation network. Precipitates associated with these dislocations coarsened. Thus, two distinct size ranges of precipitates were present in the high-temperature-annealed specimen, which can be seen clearly in the micrograph of Fig. 2.46, which shows a typical region of a (100) Si specimen. Since the temperature of annealing (900°C) is above the melting point of Sb (630°C), the precipitates are liquid during these coarsening processes.

The shape of the precipitates is such as to minimize the surface energy of the Si/liquid Sb

Fig. 2.45. Excimer laser annealing of heavily doped silicon: influence of the number of laser shots on oxygen incorporation and on dopant solubility.

SSDN-2986

Fig. 2.46. Transmission electron micrograph of (100) Si + $^{121}\text{Sb}^+$ ($4.4 \times 10^{15} \text{ cm}^{-2}$, 200 keV) after thermal annealing (550°C for 20 min and 900°C for 40 min) imaged under multibeam conditions so that all dislocations are visible.

interface at the annealing temperature. Although no well-defined shape is seen from the [100] orientation, along [111] Si almost all the precipitates appear hexagonal with sides parallel to $\langle 110 \rangle$ Si. This observation suggests that they are icositetrahedral in shape, having 24 faces bounded by {112} Si surfaces, six of which are parallel to the [111] beam direction. The points of the hexagons are rounded, showing that the edges between adjacent faces have been smoothed off. In a [100] projection, no {112} faces are parallel to the beam direction, and the icositetrahedron would look octagonal with sides parallel to $\langle 102 \rangle$ Si formed by the projection of the edges between faces (shown schematically in Fig. 2.4b). Since these edges are smoothed off, the precipitates look much more rounded in the [100] projection than in [111]. Normally in covalent materials, the {111} planes have the lowest free energy, but here we find {112} surfaces. Apparently, contact with the liquid Sb has lowered the surface energy of the {112} Si planes relative to the {111} planes, perhaps by saturating some of the dangling bonds of the Si surface.

As the sample cools after annealing, the Sb crystallizes within the existing icositetrahedral cavities in the Si in an orientation which maximizes the coherency between the two lattices. Selected area diffraction patterns show many spots arising from the precipitates and, therefore, cannot be used to determine the crystal orientation. Using microdiffraction techniques, diffraction patterns can be taken from the larger individual precipitates with a minimum contribution from the surrounding Si matrix. By thinning the samples slightly from the implanted side, the precipitates can be studied in a thin area of Si, and by careful tilting, a large number of Sb poles can be found. These poles positively identify the

precipitates as Sb, since they all can be indexed on the basis of the trigonal $R\bar{3}m$ structure of Sb (the arsenic structure).

The orientation of the precipitates was found to be $\{10\bar{1}2\}\text{Sb} // \{111\}\text{Si}$ with $\langle 2\bar{2}01 \rangle \text{Sb} // \langle 101 \rangle \text{Si}$, although with the trigonal structure of Sb it is not possible to satisfy exactly these two relationships; actual particle orientations varied by up to 4° from this alignment. Six of the {112} Si faces are parallel to the [111] Si axis and contain both the {111} Si planes ($d = 0.3135 \text{ nm}$) and the $\{10\bar{1}2\}$ Sb planes ($d = 0.3109 \text{ nm}$), which are coherent across the interfaces. By aligning $\langle 2\bar{2}01 \rangle \text{Sb} // \langle 10\bar{1} \rangle \text{Si}$ four of the remaining precipitate faces are close to low-order planes, although they do not form coherent interfaces. This orientation relationship therefore provides ten low-order Sb faces for the precipitates, six of them forming coherent interfaces, although not all these planes can be exactly aligned simultaneously. Hence, small angular variations are seen between particles showing the same microdiffraction patterns, depending on which particular surface nucleated the crystallization of the precipitate. From the coherency relationship determined above, we calculate the expected strain of Si lattice around the precipitate to be 0.25%.⁴ From measurements of the width of the black-white contrast around a number of larger particles imaged at the exact (202) Si reflecting orientation and using the calculations of Ashby and Brown,⁵ we measure a strain of $0.22 \pm 0.07\%$ in agreement with that expected. The sign of the strain was determined from dark-field micrographs and indicated the Sb spacing to be smaller than the Si spacing, as expected.

1. Summary of paper: *J. Appl. Phys.* 54, 687 (1983).
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. Present address: Microelectronics Center of North Carolina, Research Triangle Park, N.C.
4. H. F. Ashby and L. M. Brown, *Philos. Mag.* 8, 1083 (1963).

POINT DEFECT SUPERSATURATION AND ENHANCED DIFFUSION IN SUPERSATURATED SILICON ALLOYS¹

S. J. Pennycook¹ J. Narayan²
O. W. Holland³

Supersaturated Si alloys have recently been produced using ion implantation followed by new thermal processing techniques, such as controlled furnace or pulsed-laser annealing.^{4,5} These techniques remove the implantation damage and leave the dopant trapped on substitutional sites to achieve electrically active dopant concentrations greatly exceeding the solubility limit. Here we demonstrate that the alloys produced by solid-phase-epitaxial (SPE) growth contain a high concentration of trapped interstitials which give rise to transient, greatly enhanced dopant diffusion during subsequent annealing. These results are compared to the behavior of alloys produced by liquid-phase-epitaxial (LPE) growth.

We have studied (100) Si implanted with $^{121}\text{Sb}^+$ (200 keV, $4.4 \times 10^{15} \text{ cm}^{-2}$) and recrystallized, either by SPE growth (furnace annealing under flowing dry He gas at 550°C for 20 min) or by LPE growth (pulsed ruby laser annealing, 1.4 J cm^{-2} and 15-ns pulse duration). The dopant profile obtained in the SPE case was approximately 80-nm broad at a depth of 70 nm, with a peak concentration of 1 at. %, but in the LPE case an approximately uniform concentration of 0.5 at. % was obtained down to a depth of 140 nm. The retrograde maximum solubility is 0.16 at. %.

Figure 2.47 shows the results of 20-min anneals of the SPE sample at various temperatures. At the lowest temperature the nucleation rate is very low, but a few precipitates are visible [Fig. 2.47(a)]. The nucleation rate and the mean precipitate size increase with higher temperature anneals [Figs. 2.47(b) and 2.47(c)]. After the 750° anneal, loops are visible [Fig. 2.47(d)], which grow with further annealing, and additional loops nucleate [Fig. 2.47(e)]. The loops were found to be faulted, lying on {111} planes, having Burgers vectors of $a/3\langle 111 \rangle$, and to be interstitial in nature. With the LPE sample, higher temperatures were required to induce the precipitation, and no loops were observed. The diffusion coefficients obtained from the precipitate size distribution were found to be enhanced over the tracer values by about five orders of magnitude and showed an activation energy for diffusion of $1.8 \pm 0.2 \text{ eV}$ during the initial transient. During the higher temperature anneals, loops were formed by condensation of the trapped interstitials. With the LPE sample, diffusion coefficients were obtained much closer to the tracer values. The small enhancement may indicate some point defect trapping in this case, even though no loops were observed in this alloy.

These observations provide a clear demonstration of an interstitialcy mechanism of diffusion. Furthermore, the activation energy of the transient-enhanced diffusion must, therefore, correspond to the migration enthalpy of Sb by the interstitialcy mechanism. The original concentra-

tion of trapped interstitials was estimated to be $3 \times 10^{18} \text{ cm}^{-3}$ from an isothermal annealing study at 680°C, in which the size and number density of loops eventually became constant. From the experimental diffusion coefficients, therefore, the Sb diffusivity by this mechanism can be estimated as $D_I = 0.04 \exp(-1.8/kT) \text{ cm}^2 \text{ s}^{-1}$. The concentration of trapped interstitials is less than 0.4% of the concentration of implanted Sb.

1. Summary of paper: *J. Appl. Phys.* 55, 837 (1984).
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. Present address: Microelectronics Center of North Carolina, Research Triangle Park, N.C.
4. J. Narayan, O. W. Holland, and B. R. Appleton, *J. Vac. Sci. Technol.* B 1, 871 (1983).
5. C. W. White et al., *J. Appl. Phys.* 51, 378 (1980).

A MECHANISM FOR TRANSIENT-ENHANCED DIFFUSION IN 10M-IMPLANTED SILICON¹

S. J. Pennycook¹ J. Narayan²
O. W. Holland³

High-dose ion implantation followed by solid-phase-epitaxial (SPE) growth is now a well-established technique for the production of supersaturated silicon alloys. However, these alloys also contain a high supersaturation of silicon interstitials, which give rise to transient, greatly enhanced dopant diffusion with subsequent heating. In this contribution, we present a study of a series of Si-Sb alloys of various concentrations which were made by Sb implantation under various conditions to deduce the origin of the observed transient diffusion.

A multiple implant scheme was employed to produce samples with an approximately uniform dopant concentration from 40 to 150 nm in depth, but with the amorphous layer extending to a depth of 380 nm. By scaling the implant doses, alloys with different concentrations in the uniform region were produced, allowing an accurate measure of diffusion coefficients as a function of concentration. This band of high dopant concentration is well removed from the damage layer remaining after SPE growth, marking the original amorphous/crystalline interface. In this region, radiation-enhanced diffusion may result from the annealing of the damage in the underlying crystal. However, this mechanism cannot occur within the band of high dopant concentration since the material has been amorphized by the implantation. We show that a new mechanism is responsible for the transient effects observed.

Diffusion coefficients during the transient enhanced diffusion were measured by precipitation⁴ and are shown on an Arrhenius plot in Fig. 2.48(a). Several Si-Sb and one Si-Bi alloys are shown for various implantation conditions. All points are several orders of magnitude enhanced over the tracer values. The Sb points show an activation energy of $1.8 \pm 0.2 \text{ eV}$, and the Bi points, $2.0 \pm 0.2 \text{ eV}$. The diffusion coefficients are higher for higher Sb concentrations and for room

SSDN-3030

Fig. 2.47. Results of 20-min anneals of SPE sample at (a) 650°C; (b) 700°C; (c) 750°C observed in a nondiffracting orientation; (d) area of (c) observed in diffraction contrast showing onset of loop formation; and (e) as (d) but with additional 780°C anneal.

Fig. 2.48. (a) Arrhenius plot of Sb and Bi transient diffusion coefficients for various concentrations implanted in Si at room temperature or liquid nitrogen temperature and recrystallized by SPE growth. IBA denotes ion beam annealing. Tracer diffusion coefficients are shown for comparison. (b) Plot of Sb and Bi transient diffusion coefficients D^* , measured or extrapolated to 680°C, as a function of dopant concentration, C_0 .

temperature compared with liquid nitrogen temperature implants. The transient nature of the enhancement is very obvious; continued annealing at these low temperatures caused loops to form, after which precipitation practically ceased, even though only a small fraction of the dopant had been precipitated. The loops were determined to be interstitial in nature, clearly demonstrating that the transient-enhanced Sb diffusion is due to the motion of interstitials released from some trapping site by the anneal. When they condense

into loops, the transient ends. This is a very clear demonstration of the interstitialcy mechanism of diffusion, whereby substitutional Sb atoms are displaced from site to site by passing interstitial silicon atoms.

The trapping of interstitials either may be an intrinsic part of recrystallization by SPE growth, which we call regrowth trapping, or it may occur by some kind of bond between the Sb and the interstitial Si atoms, which we call electronic trapping. For regrowth trapping, the concentration of trapped interstitials C_i would be independent of the Sb concentration C_0 , but for electronic trapping, $C_i = kC_0$, where k is a constant dependent on the implantation conditions. This will affect the enhanced diffusion coefficient D since $D = C_i D_i$, where D_i is the Sb diffusivity by the interstitialcy mechanism. Therefore, for electronic trapping, D will be proportional to C_0 . Figure 2.48(b) shows that this is indeed the case, the constant being lower for the low-temperature implant. For room temperature implants we find $k = 0.02$, and for liquid nitrogen temperature implants we find $k = 0.01$. Higher values are obtained with ion beam annealing (IBA) [Figs. 2.48(a) and 2.48(b)]. The fraction of dopant which traps an interstitial is dependent on the implantation conditions but independent of SPE growth velocity. The trapping must take place during implantation, and subsequent thermal processing can only cause the release of the trapped interstitials. We propose that under the heavy flux of interstitials present during Sb implantation, a small fraction of the Sb acquires five Si neighbors to become fully saturated. At low temperatures the mobility of point defects is reduced, and less Sb can become fully saturated. These saturated Sb atoms retain their extra neighbor in the amorphous state following implantation and during recrystallization by SPE growth to create interstitial Si atoms trapped at Sb sites. Subsequent heating causes the complex to split up, and the mobile interstitials cause a transient, greatly enhanced diffusion of the Sb dopant before finally condensing into interstitial loops.

The trapping of interstitials during ion implantation may be a fundamental limitation to the incorporation of high concentrations of group V dopants in Si. We have also shown that there is no analogous effect with group III ions. $^{11}\text{B}^+$ implanted into Si (pre-amorphized to exclude the radiation enhanced diffusion) shows only tracer diffusion coefficients. This observation is not surprising since rejecting the fifth neighbor from a group V atom during SPE growth would require a bond to be broken, a process needing considerable energy. To change a group III atom from threefold to fourfold coordination requires much less energy and can easily be achieved during SPE growth.

1. Summary of papers to be published.
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. Present address: Microelectronics Center of North Carolina, Research Triangle Park, N.C.
4. S. J. Pennycook, J. Narayan, and O. W. Holland, *J. Appl. Phys.* 55, 837 (1984).

5. T. Y. Tan, U. Goesele, and F. F. Morehead, *Appl. Phys.* A31, 97 (1983).

PREDICTION OF TRANSIENT-ENHANCED DIFFUSION DURING RAPID THERMAL ANNEALING OF ION-IMPLANTED SILICON¹

S. J. Pennycook¹ J. Narayan²
O. W. Holland³

There have been several reports of transient-enhanced diffusion during furnace⁴ or rapid thermal⁵⁻⁸ annealing of ion-implanted silicon and some reports of no enhancement.⁹ In this contribution, we show that many of the observed effects can be accounted for by an interstitial trapping mechanism, in which large numbers of Si atoms are trapped by group V dopant atoms in the amorphous material during implantation. These trapped atoms are retained during solid-phase-epitaxial (SPE) growth, but can be released later during thermal processing to give the transient-enhanced diffusion. We present a model which can predict the transient effects (or lack of them) for any concentration of Sb, Bi, or As dopants sufficient to amorphize the silicon and any thermal processing technology which relies on SPE growth (furnace, cw laser, or rapid thermal annealing).

All of our results from furnace annealing of Si-Sb alloys can be expressed as a single concentration dependent, transient diffusion coefficient D^* , given by

$$D^* = 0.0083 \alpha C_0 e^{-1.8/kT} \text{ cm}^2 \text{ s}^{-1} \quad (1)$$

where $\alpha = 0.01$ for implants at liquid nitrogen temperature, $\alpha = 0.02$ for implants at room temperature, and C_0 = atomic fraction of dopant.

This very high transient diffusivity lasts only until the supply of interstitials is exhausted. We observe experimentally that for room temperature implantations, the end of the transient diffusion occurs roughly at $D^*t^* = 4 \times 10^{12} \text{ cm}^2$ independent of dopant concentration, where t^* is the length of the transient in seconds, and at half this value for low-temperature implantations.

From Eq. (1) we, therefore, predict

$$t^* = \frac{2.5 \times 10^{-8}}{C_0} e^{1.9/kT} \quad (2)$$

For process times $t < t^*$, we will see enhanced diffusion given by D^* [Eq. (1)]. For process times $t > t^*$, we will observe the full transient effect D^*t^* and concomitant effects of precipitation and loop formation; in addition, we may see the effects of normal diffusion for the remaining time, characterized by $D(t-t^*)$. Whether this normal diffusion is significant depends primarily on the temperature. At low temperatures, D^* is many orders of magnitude greater than the normal diffusion coefficient D , and therefore it would need to exceed t^* by the same factor for the effects of normal diffusion to be observable. However, the situation changes at high temperatures, since the tracer diffusion has a much larger activation energy. In fact, at a suf-

ficiently high temperature T^* , D will exceed the transient diffusivity D^* , even for times less than t^* . The extrapolation of the tracer and transient diffusion coefficients cross at

$$T^* = 2.5 \times 10^{-2} [\ln(675/\alpha C_0)]^{-1} \quad (3)$$

Here, the diffusion caused by thermally generated point defects equals the diffusion caused by the release of the fixed number of trapped interstitials, and the transient effects will not be significant. In Fig. 2.49(a), we summarize these

Fig. 2.49. (a) Predicted duration of the transient-enhanced diffusion as a function of dopant concentration and temperature. (b) Predicted enhanced diffusion coefficient as a function of dopant concentration and temperature.

predictions, plotting t^* against $1/kT$ for various dopant concentrations. The bold dotted line marks the temperature T^* above which normal diffusion exceeds the transient diffusion for all times. Figure 2.49(b) shows D^* as a function of $1/kT$ and C_0 , the bold line again marking the division between normal and enhanced diffusion.

To test the prediction of these transient effects, we have taken Sb-implanted Si ($C_0 = 9.31 \times 10^{20} \text{ cm}^{-3}$, implanted at liquid nitrogen temperature) and compared the effects of furnace and rapid thermal annealing (RTA). At the typical temperatures of RTA, the SPE growth process is completed in a few milliseconds so that the annealing time can be taken as equal to the processing time. The sample for furnace annealing was first regrown at 575°C for 40 min and then annealed at 700°C for 90 min, at which temperature $t^* = 50$ min. The sample for RTA was annealed at 1050°C for a nominal time of 15 s, where $t^* = 10$ s. Both treatments should therefore take the material to the end of the transient, and both samples indeed showed identical precipitate size distributions and loop number densities, reflecting the fact that the same numbers of interstitials have condensed with the two thermal processing treatments.

Transient effects with As-implanted samples have also been shown to have a 1.8-eV activation energy.^c If we assume the same trapping efficiency α for As as for Sb and Bi, the transient effects should again be predictable from Eqs. (1) and (2). Kalish et al.⁶ report enhancement by 170 times for 1010/10 s RTA and 50 times for 1118/10 s RTA. These times are both less than t^* , and we predict enhancements of 63 and 15 times, roughly three times lower than their results. Considering the probable errors in t^* and the experimental values for annealing time and tem-

perature, the model predicts the observed effects very well. The general underestimate of the effect may in fact be due to radiation-enhanced diffusion or pipe diffusion contributing to the observed transient diffusion, since for their results the original amorphous/crystalline interface was at a depth of only ~1400 Å.

No enhanced diffusion was reported by Hodgson et al.⁹ during the RTA of As-implanted ($8 \times 10^{19} \text{ cm}^{-3}$, Si at 1200°C/1 s. This is also predicted by the model, since from Fig. 2.49 we see that these experimental conditions lie very close to the point at which normal diffusion becomes dominant. We predict only a 20% enhancement, whereas they report a factor of 2. In general, our model seems able to predict transient effects even in As-implanted Si to within a factor of 2 or 3 and explains why some experimental conditions result in no observed enhancement.

1. Summary of paper to be published.
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. Present address: Microelectronics Center of North Carolina, Research Triangle Park, N.C.
4. S. J. Pennycook, J. Narayan, and O. W. Holland, *J. Appl. Phys.* **55**, 837 (1984).
5. J. Narayan et al., *Appl. Phys. Lett.* **43**, 957 (1983).
6. R. Kalish et al., *Appl. Phys. Lett.* **44**, 107 (1984).
7. J. B. Lasky, *J. Appl. Phys.* **54**, 6009 (1983).
8. T. E. Seidel, *IEEE Electron Device Lett.* **EDL-4**, 353 (1983).
9. K. T. Hodgson et al., p. 253 in *Energy Beam-Solid Interactions and Transient Thermal Processing*, Elsevier, New York, 1984.

3. DEFECTS IN SOLIDS

The subject matter in this chapter does not reflect accurately the pervasive interest within the division in the defect solid state. In every chapter of this report contributions will be found which are concerned with defects. Here it is attempted to report research which focuses primarily on the properties of defects per se, rather than how they may affect other properties of interest. Many interesting contributions of the latter type can be found in sections dealing with, for example, particle-solid interactions, mass and charge transport, and neutron scattering, as well as in other portions of this report. Research activities on the physics of defects will be intensified in the near future by the addition of a major new experimental capability. Construction of the National Low-Temperature Neutron Irradiation Facility at the ORNL Bulk Shielding Reactor is proceeding on schedule. This user facility will provide a fast neutron flux of about 2×10^{17} n/m²s at controlled temperatures of 3.5 to 500 K; in addition to various experimental facilities within the irradiation cryostat, provision will be made for removal and storage of irradiated samples at 4 K. The facility is expected to be ready for operation and experimentation by users in late 1985.

Microscopic mechanisms of metal fracture have continued to be investigated by making direct observations of crack propagation in an electron microscope and also by performing theoretical analyses of observed behavior of dislocations at a crack tip. It has been shown that dislocations shield a crack tip from the applied stress and contribute greatly to increasing the fracture toughness. This increase has been calculated by considering the elastic interaction between the crack and the dislocations, and the effect of crack blunting on the crack tip stress field has been analyzed successfully for the first time. A mechanism for the coexistence of brittle and ductile fracture, observed in many structural materials, is proposed from the criteria for brittle crack extension and crack tip deformation. In situ electron microscope studies of crack propagation have been extended to the phenomenon of brittle fracture observed in bcc metals at low temperatures. In addition, the material parameters responsible for activating slip systems at the crack tip have been determined.

During the reporting period a novel means of determining the location of impurity atoms in solids has been examined. Approximations have been derived which, by comparing x-ray yields from matrix and impurity atoms, employ electron channeling analysis to determine locations of impurity

atoms in a Si matrix. This technique has been used to determine substitutional fractions of dopants and, when combined with transmission electron microscopy measurements, the process of impurity precipitation. Studies of vacancy ordering in binary systems have continued, as have examinations of vacancies and impurities in alkaline-earth oxides and investigations of dielectric breakdown in MgO at elevated temperatures.

Defects in semiconductors have been studied for many years, but it appears that much remains unknown about these materials of high technological importance. Recent studies have focused primarily on a better understanding of the pulsed-laser annealing (PLA) process and on further improvements of crystalline silicon solar cells. Time-resolved optical studies of amorphous Si during PLA have been used to study thermal properties of the amorphous phase, as well as the kinetics of ultrarapid solidification from a highly undercooled melt. Very accurate time-resolved reflectivity measurements during pulsed excimer laser annealing have been used to estimate temperatures optically before and after the molten phase and to detect inhomogeneous melting at laser energy densities just above the melting threshold. The studies of PLA with nanosecond resolution have also been extended to include high-purity Ge (used for radiation detectors) and the wide band gap semiconductors ZnO and SiC. A nanosecond-resolution ellipsometer, which should prove useful for a variety of time-resolved optical studies, has been developed. The work on single crystal Si solar cells during this reporting period has concentrated on refinements of the fabrication process to provide additional increases in efficiency; these refinements have included improvements and optical characterization of the glow discharge implantation technique, production and evaluation of texturized surfaces for solar cells, and a computer investigation of antireflection coatings.

RADIATION EFFECTS

DEPTH DISTRIBUTION OF SELF-ION DAMAGE AND COMPARISON OF ION DAMAGE RATES TO NEUTRON DAMAGE RATES FOR ALUMINUM¹

T. S. Noggle	B. R. Appleton
J. M. Williams	O. S. Oen
T. Iwata ²	G. W. Vogl ³

Resistivity damage rates as a function of ion penetration depth were measured for 2.7 to 5.4 MeV Al ions in aluminum. These damage rates accurately scale with damage energy calculations for a large fraction of the range of the ions, but are ~14% low in the region of the maxima in the damage curves. This difference in the peak region was related to changes in the damage efficiency expected from differences in the recoil spectra in the peak region compared to the incident beam. Deviation from the Lindhard-Scharff-Schiøtt velocity proportional electronic stopping was indicated by these experiments, and an improved agreement between experiment and calculation

was obtained by adjustment of the parameters in the Brice formula for the electronic stopping cross section. The fission spectrum neutron damage production rate in aluminum was measured and compared with the ion damage rates. The damage efficiency of neutron damage is in agreement with the ion damage efficiencies to within ~8%.

1. Summary of paper. *J. Nucl. Mater.* 125, 330 (1984).

2. Japan Atomic Energy Research Institute, Tokai-mura, Japan.

3. Hahn Meitner Institut, Berlin, Federal Republic of Germany.

THE MAGNETORESISTIVITY OF COPPER IRRADIATED AT 4.4 K BY SPALLATION NEUTRONS¹

C. E. Klabunde R. R. Coltman, Jr.

The stabilizer (normal metal) of a composite superconductor safely carries the current during

a localized momentary normalization of the superconducting matrix. The amount of normal metal needed for safe operation increases with increasing resistivity of the metal. As a result, the design of large composite superconducting magnets for fusion reactors will depend sensitively upon increases in the resistivity of the stabilizer produced by irradiation during its lifetime. To minimize these increases and hence the cost of magnets and their radiation shielding, consideration is given to periodic warming of the magnets to remove annealable portions of the radiation-produced resistivity. For large power reactors such warming cycles are costly, and the frequency of these operations becomes an economic "trade-off" parameter with various capital-cost parameters such as shield thickness and amount of normal metal. It is essential to the magnet design to be able to predict the resistivity of the stabilizer throughout its life.

In response to these needs, studies were made on eight differently prepared copper stabilizer specimens (Table 3.1) irradiated in the ANL/IPNS-I Radiation Effects Facility.² Magnetoresistivity measurements were made on each sample at zero and nine transverse magnetic field strength values up to 6.5 T at each step over three irradiation (4.4 K) and annealing (300 K) cycles. The total neutron fluence was $4.8 \times 10^{21} \text{ n/m}^2$ ($E > 0.1 \text{ MeV}$). The results show a strong dependence upon sample purity and state of cold work.

Table 3.1. Preirradiation characteristics of the samples.

Designation	Treatment	Resistivity ^a (4.2 K $10^{-11} \Omega \text{ m}$)
OFHC-Unox. 0-cw	Recrystallized	4.36
OFHC-Unox. 1-cw	7.5% cold worked	10.00
OFHC-Unox. 2-cw	14.3% cold worked	15.28
OFHC-Ox. 0-cw	Recrystallized	2.43
OFHC-Ox. 1-cw	7.5% cold worked	8.01
OFHC-Ox. 2-cw	14.3% cold worked	13.56
ASARCO-Ox. 0-cw	Recrystallized	0.627
ASARCO-Ox. 2-cw	14.3% cold worked	9.92

^aCorrected for size effect.

Figure 3.1 shows all of the resistivity values determined throughout the experiment for 0, 6.5, and 10 T as a function of cycle number. The most striking feature of the data is the strong dependence of the resistivity upon the magnetic field strength and upon the initial condition (purity, annealing treatment, and state of cold work) of the samples. With regard to annealing treatment it can be seen that, overall, the resistivities of the oxidized material are less than those of the unoxidized OFHC material. With the present results there are now data for three neutron energy spectra^{3,4} that encompass those to be expected in fusion magnets, but there is some shortfall in meeting the desired range of dose and field strength.

Fig. 3.1. The resistivity at 0, 6.5, and 10 T of variously prepared stabilizer specimens determined at each step over three consecutive irradiation (4.4 K) and annealing (30 min at 300 K) cycles. Resistivities for each irradiation cycle were determined for a neutron fluence of $1.7 \times 10^{21} \text{ n/m}^2$ ($E > 0.1 \text{ MeV}$). The data for 10 T were obtained by extrapolation. The upper and lower curves for each case trace, respectively, the as-irradiated and the after-anneal resistivities.

Recent developments suggest that the data base on the magnetoresistivity of stabilizers should be extended to considerably higher neutron fluences. The "cable-in-conduit" concept⁵ for cooling composite superconductors and the use of superfluid He near 1.8 K are two methods by which Joule heat in the stabilizer can be removed at higher rates than with previous methods. These cooling methods provide cryostable operation with higher resistivity stabilizers than before. As a result the designers' range of cost optimization is extended. These methods can provide cost reductions by the use of less stabilizer material or by a tolerance for higher resistivity increases from the higher neutron flux that results from thinner, less costly radiation shields. To make such economic trade-off studies, however, it is necessary to extend the magnetoresistivity data base to higher neutron fluence than we now have. A new National Low-Temperature Neutron Irradiation Facility now under construction at ORNL⁶ will provide the needed irradiation temperatures, neutron fluence, and magnetic-field strengths which will enable U.S. experimenters to meet these projected needs.

1. Summary of paper: Sixth Annual Progress Report on Special Purpose Materials for Magnetically Confined Fusion Reactors, DOE/ER-0113/3 (May 1984).

2. R. C. Birtcher et al., J. Nucl. Mater. 108/109, 3 (1982).

3. M. W. Guinan and R. A. Van Konyenburg, J. Nucl. Mater. 122/123, 1365 (1984).

4. R. R. Coltman, Jr., J. Nucl. Mater. 106/109, 559 (1982).
5. L. Dresner, Cryogenics 20, 558 (1980); L. Dresner, Cryogenics (to be published).
6. R. R. Coltman, Jr., C. E. Klabunde, and F. W. Young, Jr., J. Nucl. Mater. 122/123, 1357 (1984); "The National Low-Temperature Neutron Irradiation Facility: A Status Report," this report.

ORGANIC MATERIALS FOR FUSION REACTOR APPLICATIONS¹

G. F. Hurley² R. R. Coltman, Jr.

Organic insulation is specified for superconducting coils in fusion reactors because of its lower material and fabrication costs compared with alternate forms of insulation.

The major part of the insulation system in a superconducting magnet will comprise a high-strength glass-reinforced polymer composite material, of which the National Electrical Manufacturers Association G-10CR is typical. Such materials differ in two important respects from most other metallic and nonmetallic reactor components. The most important difference is that the properties of organic materials and glasses are degraded by both the neutrons and gamma rays present in fusion magnets. As a result, the radiation response of organic insulation will depend upon the mix of neutron and gamma-ray intensities, which differ for various reactor designs.³⁻⁶ In contrast, the remaining important components of a superconducting magnet, the superconductor and the copper or aluminum stabilizer, are sensitive only to neutron radiation. The serious damage is to the electrical properties; irradiation of superconductors results in decreased critical current density and critical temperature, while in the stabilizer materials lifetime is limited by an increase in resistivity. A second difference is that structural degradation of the organics occurs at lower irradiation doses than those for the other classes of magnet materials.⁷ The available data for degradation of these components in calculated magnet irradiation environments show that the radiation response for either the stabilizer or the epoxy-based, or both, is the critical^{8,9} factor for magnet lifetimes.

A detailed understanding of the stress, temperature, and radiation conditions imposed on superconducting magnet insulators and of the response of candidate materials to these conditions is the key to the successful engineering of these large magnet systems.

1. Summary of paper: J. Nucl. Mater. 122/123, 1327 (1984).
2. Los Alamos National Laboratory, Los Alamos, N.M.
3. D. C. Phillips, The Effects of Radiation on Electrical Insulators in Fusion Reactors, AERE-R8923 (1978).
4. Neutronics Analysis of the Mirror Coil, University of Wisconsin, WIS-MARS-82-022 (1982).

5. Y. Gohar, p. 6.1 in Proceedings of the Meeting on Electrical Insulators Fusion Magnets, CONF-801237, Germantown, Md., 1981.
6. B. A. Engholm, p. 5.1 in Proceedings of the Meeting on Electrical Insulators Fusion Magnets, CONF-801237, Germantown, Md., 1981.
7. D. T. Grubb, J. Mater. Sci. 9, 1715 (1974).
8. R. R. Coltman, Jr., and C. E. Klabunde, Special Purpose Materials Annual Progress Report for 1981, DOE/ER-0113/1 (1982), p. 101.
9. R. A. Van Konynenburg and M. W. Guinan, Special Purpose Materials Annual Progress Report for 1981, DOE/ER-0113/1 (1982), p. 83.

THE NATIONAL LOW-TEMPERATURE NEUTRON IRRADIATION FACILITY: A STATUS REPORT¹

R. R. Coltman, Jr. C. E. Klabunde
F. W. Young, Jr.

In accordance with the recommendations of the Working Group on Low-Temperature Neutron Irradiation² and after considering its programmatic needs, the DOE Division of Materials Sciences authorized in May 1983 the establishment of a National Low-Temperature Neutron Irradiation Facility (NLTNIF) at ORNL's Bulk Shielding Reactor (BSR). The NLTNIF, which will be available for qualified experiments at no cost to users, will provide high radiation intensities and special environmental and testing conditions that have not been previously available in the U.S.

Figure 3.2 shows a sketch of the NLTNIF irradiation cryostat and its relationship to the core of the BSR, which is movable within a large open pool. In the primary cryostat, irradiation temperatures from 3.5 to 500 K can be obtained; irradiation at temperatures up to 800 K can be realized in an auxiliary facility. The primary irradiation zone will be 40 mm diam x 250 mm long. Located 1.5 m above the irradiation zone will be a 200 mm diam x 300 mm long test chamber into which specimens can be moved without warm-up. Provisions will be made for the transfer of specimens at 4.2 K into test devices or into vessels for shipment to other laboratories. On-line data acquisition and computer capability will be provided.

Two features of the BSR will aid NLTNIF experimenters. First, the core fuel loading provides sufficient excess reactivity to permit restarting after any operating history—xenon poisoning is not an operational limitation. This is an asset for experiments that require frequent on-off reactor operations. Second, the open pool provides the opportunity to construct almost unlimited ambient and cryogenic storage facilities for radioactive experiment assemblies and specimens. Such facilities will be located close to the irradiation cryostat, and they make use of pool water for biological shielding.

Based on recent neutronics measurements and computer calculations, the fast neutron flux at full reactor power (2 MW) is expected to be between 2.0 and 2.5 x 10¹⁷ n/m²s (E>0.1 MeV) at the center of the sample chamber. The accompanying thermal neutron flux is expected to be

Fig. 3.2. A sketch of the NLTNIF cryostat and its relationship to the BSR pool and reactor core.

$1.5 \times 10^{17} \text{ n/m}^2\text{s}$. Any lower intensity can be obtained. Interchangeable gamma-ray shields will be used between the BSR fuel elements and the vacuum jacket of the irradiation cryostat. Initially, the shield will be made of zircaloy, for which a central nuclear heating value in Al has been determined to be 0.32 W/g at 2 MW. Later an alternate shield will be made of lead, for which a corresponding value of 0.16 W/g has been found. Fast neutron fluences up to $2 \times 10^{23} \text{ n/m}^2$ ($E > 0.1 \text{ MeV}$) and energy deposition values (in Al) up to $3 \times 10^{10} \text{ rads}$ will be possible routinely. Twice these values are possible with special arrangements.

Construction and installation of a new personnel platform adjacent to the access port of the irradiation cryostat is complete, while construction of the cryostat is scheduled for com-

pletion in 1994. Ambient temperature in-pool storage tubes for radioactive experiment assemblies have been installed, and two special 100-L liquid He vessels for in-pool storage at 4.2 K have been ordered. A 12-T superconducting magnet will be fitted to the test chamber of the cryostat, and a data acquisition system has been purchased.

An improved liquid He refrigeration system with five times the cooling power of the old ORNL system will be installed. After final performance testing, the facility is expected to be ready for operation by users in late 1985.

1. Summary update of paper: *J. Nucl. Mater.* 122/123, 1357 (1984).

2. Report of the Working Group on Low-Temperature Irradiation, U.S. Department of Energy, DOE/ER-0138 (July 1982).

FRACTURE

DISLOCATION SHIELDING MODEL OF FRACTURE TOUGHNESS¹

S. M. Ohr S.-J. Chang²

A recently developed dislocation model of fracture has shown that fracture toughness of a material depends directly on the number of dislocations in the plastic zone. The model is based on TEM observations that there is a dislocation-free zone (DFZ) between the crack tip and the plastic zone and that the crack tip is shielded from the applied stress by the dislocations in the plastic zone. Elasticity is restored in the region immediately ahead of the crack tip, and hence it is possible to define a crack tip stress intensity factor k . Figure 3.3 shows three crack

ORNL DWG 84C-13554

(a) ELASTIC CRACK:

$N = 0$
 $k = K$
NO DISLOCATION SHIELDING

(b) PLASTIC CRACK (BCS):

$N = N_{max}$
 $k = 0$
COMPLETE SHIELDING

(c) ELASTIC-PLASTIC CRACK:

$0 < N < N_{max}$
 $0 < k < K$
PARTIAL SHIELDING

Fig. 3.3. Classification of cracks based on the distribution of dislocations and the extent of dislocation shielding.

tip geometries that can be classified based on the dislocation model of fracture. The elastic crack with no dislocations in the plastic zone ($N=0$) may be considered as a special case of an elastic-plastic crack in which the DFZ is infinitely long. In the absence of crack tip deformation the local k is equal to the applied stress intensity factor K . The plastic crack is characterized by the plastic zone, which reaches all the way to the crack tip. The number of dislocations in the plastic zone in this case is written as N_{max} . There is no DFZ, and the local K is zero. This may be regarded as the case of complete dislocation shielding of the crack tip from the applied K . The elastic-plastic crack is expected when the number of dislocations in the plastic zone (N) is greater than zero but is less than N_{max} . That is, there is an insufficient number of dislocations in the plastic zone to shield completely the crack tip. A DFZ is present between the crack tip and the plastic zone, and the local k is less than the applied K . This may be called the case of partial shielding of the crack tip by the dislocations.

From the DFZ model of fracture, it is possible to derive an expression for the fracture toughness of a material in terms of the parameters describing the crack tip geometry. It is shown that under mode III loading conditions the applied stress intensity factor K is related to the local stress intensity factor k by

$$K = \frac{k(e^2 - c^2)^{1/2} \Pi(S, p)}{(a^2 - c^2)^{1/2} F(p)}, \quad (1)$$

where c , e , and a are the lengths of the crack, DFZ, and the plastic zone, respectively; F and Π are the complete elliptic integrals of the first and third kinds; $S^2 = (a^2 - e^2)/(a^2 - c^2)$; and $p^2 = S^2 c^2 / e^2$. If the onset of brittle crack extension is defined by the local k reaching k_c for brittle fracture, the fracture toughness of the material is obtained from Eq. (1) by substituting k_c for k . In Fig. 3.4, we have plotted k/K as a function of N/N_{max} . It can be seen that there is a unique relationship between k/K and N/N_{max} , independent of the crack tip geometry. That is, the local k is a function only of the number of dislocations in the plastic zone.

1. Summary of paper to be published.
2. Engineering Technology Division, ORNL.

INCLINED DISLOCATION EMISSION AT A SHIELDED CRACK TIP¹

S.-J. Chang² S. M. Ohr

Dislocation pileup along an inclined direction from a crack tip has been observed in metals during tensile deformation in an electron microscope. Dislocations emitted from the crack tip move through a dislocation-free zone (DFZ) and pile up in the plastic zone. In order to investigate the effect of dislocation pileup on subsequent emission of dislocations at the crack tip, the case

ORNL-DWG 84C-13556

Fig. 3.4. The ratio of local to applied stress intensity factor vs the fractional content of dislocations in the plastic zone.

for an inclined pileup with a DFZ has been solved. The result is used to discuss crack tip blunting due to dislocation emission vs brittle crack extension. It also shows that the resistance constant K_e of dislocation emission for a given material can be determined by measuring the size of the DFZ.

As calculated in a previous paper,³ the stress field at a distance $z (=x+iy)$ from a semi-infinite crack due to screw dislocations located at z_k ($k=1,2,\dots$) is

$$\sigma = \sigma_y + a\sigma_x = \frac{K_3}{\sqrt{2\pi z}} - \frac{ub}{4p} \left[\frac{1}{2z} + \frac{1}{z+|z|} \right] + \sum_k \frac{ubk}{4\pi\sqrt{z}} \left[\frac{1}{\sqrt{z}-\sqrt{z_k}} - \frac{1}{\sqrt{z}+\sqrt{z_k}} \right], \quad (1)$$

where the summation excludes the self-image term due to the dislocation at z and K_3 is the applied stress intensity factor for mode III deformation. With the dislocation interaction force obtained from Eq. (1), the pileup integral equation can be derived as

$$\frac{K_3}{\sqrt{2\pi r}} \cos\left(\frac{\psi}{2}\right) - \sigma_f = \frac{ub}{4\pi\sqrt{r}} \int_e^l f(r') \times \left[\frac{1}{\sqrt{r'}-\sqrt{r}} + R_e \frac{1}{\sqrt{r'}+\sqrt{r}} e^{i\psi} \right] dr', \quad (2)$$

where $f(\cdot)$ is the distribution function along the inclined direction ψ , e denotes the length of DFZ, and l is the pileup length.

The distribution function $f(r)$ is obtained from the integral equation by applying the Wiener-Hopf technique. The relationship between the pileup length l and the applied stress intensity factor K_3 is obtained in a simple form,

$$2\sigma_f(2\pi l)^{1/2}/(K_3\pi) = \sqrt{F_{lg}} \sin(a\pi) \times (1+a)^{(1+a)/2}(1-a)^{(1-a)/2}/(a\pi), \quad (3)$$

where $a = \psi/\pi$ and F_{lg} is a function of e/l , which becomes unity when the DFZ is not present. The numerical value of F_{lg} is plotted in Fig. 3.5. The true stress intensity factor at the crack tip is defined as the difference between the applied stress intensity K_3 and the factor K_0 due to the presence of the shielding dislocations. The numerical values of K/K_3 are also plotted in Fig. 3.5 for a series of values of a . As a is increased, the dislocations located at the same distance from the crack tip contribute less to the shielding of the crack tip. Thus, more dislocations are needed to reach the same value of K/K_3 .

The emission of a screw dislocation along an inclined angle ψ is possible if the radial force on the dislocation due to the true stress intensity factor K is greater than the self image force of the emitted dislocation. The total radial force F_r is given by

$$F_r = \frac{Kb}{\sqrt{2\pi r}} \cos\left(\frac{\psi}{2}\right) - \frac{ub^2}{4\pi r}. \quad (4)$$

The critical stress intensity factor K_e for spontaneous emission of dislocations can be defined by substituting $r = r_c$ in Eq. (4):

$$K_e = \frac{ub}{2\sqrt{2\pi r_c}} \frac{1}{\cos(\frac{\psi}{2})}.$$

An equilibrium configuration of the dislocation pileup will be reached if the true stress intensity factor K is equal to the critical K_e of the material. The value of K/K_3 can be determined from the experimentally measured value of e/l using Fig. 3.5. This measured value of K can then be compared with the theoretical value of the material, K_e . This will serve as a test for the validity of the theory of dislocation emission proposed recently.^{4,5}

1. Summary of paper to be published.
2. Engineering Technology Division, ORNL.
3. S.-J. Chang and S. M. Ohr, J. Appl. Phys. 55, 3505 (1984).
4. S.-J. Chang and S. M. Ohr, J. Appl. Phys. 52, 7174 (1981).
5. S. M. Ohr and S.-J. Chang, J. Appl. Phys. 53, 5645 (1982).

INCLINED PILEUP OF SCREW DISLOCATIONS AT THE CRACK TIP WITHOUT A DISLOCATION-FREE ZONE¹

S.-J. Chang² S. M. Ohr

Fig. 3.5. Stress intensity factor K/K_3 and reduction factors F_{gn} and F_{lg} plotted against the length of the DFZ e/l . The angle of inclination ψ is proportional to a .

Recent electron microscope studies of dislocation behavior at a crack tip in various metals have shown that a number of slip geometries are possible depending on the state of stress and the orientation of the specimen. The effect of a pileup of screw dislocations on coplanar planes on the stress field at the crack tip has been discussed previously. In the present work, a linear array of screw dislocations in front of a mode III crack that lie on a plane inclined to the crack is studied. The problem is formulated in terms of an integral equation describing the equilibrium condition between the dislocations and the crack under an externally applied shear stress. The expression for the condition of finite stress at the end of the plastic zone, the Bilby, Cottrell, and Swinden (BCS) condition, and the crack opening displacement (COD) are obtained in simple analytical forms as functions of the inclination angle. The distribution function for the dislocations is derived from the solution of the integral equation by applying the Wiener-Hopf technique. Numerical results show that, for a given applied stress, the distribution function, the length of the plastic zone, and the COD decrease only slightly as the angle of inclination increases from 0 to $\pi/2$. The quantity $\sigma_f \cdot \text{COD}$, where σ_f is the friction stress, is shown to be equal to the radial component of the complex

J integral and, hence, is the total force on the dislocations along the direction of the pileup.

1. Summary of paper: *J. Appl. Phys.* 55, 3505 (1984).
2. Engineering Technology Division, ORNL.

ELASTIC INTERACTION OF A WEDGE CRACK WITH A SCREW DISLOCATION¹

S. M. Ohr S.-J. Chang²
R. Thomson³

Plastic deformation occurring at a crack tip can alter the stress field in the vicinity of the crack tip when edge dislocations are generated on inclined planes, thus creating a wedge-shaped blunted crack. The propagation of blunted cracks has been observed by Vehoff and Neumann⁴ during in situ SEM observations of fracture cracks in copper and silicon and also during in situ TEM tensile deformation of niobium.⁵ In spite of the significant role that crack blunting can play in the fracture mechanics of elastic-plastic crack propagation, very little work has been reported on the elastic properties of the blunted cracks.

In the present work, the stress field near the tip of a semi-infinite wedge crack under mode III loading conditions has been obtained by the method of conformal mapping. It is found that the stress components at $z = r \exp(i\theta)$ in front of a wedge crack of angle α , shown in Fig. 3.6, are given by

$$\begin{aligned}\sigma_{yz} &= \frac{\lambda \cos(s\theta)}{(2\pi r)^s}, \\ \sigma_{xz} &= \frac{\lambda \sin(s\theta)}{(2\pi r)^s},\end{aligned}\quad (1)$$

where λ is the wedge stress intensity factor, $s = (\pi - \alpha)/(2\pi - \alpha)$. It is noted that, except for

Fig. 3.6. A semi-infinite wedge crack of wedge angle α .

$\alpha = 0$, the wedge stress intensity factor λ has a physical dimension that is different from the stress intensity factor K defined for a sharp crack. In general, it can be shown that λ and K are related by a connection formula

$$\lambda = K(2\pi d)^{s-1/2}, \quad (2)$$

where d is a characteristic distance from the crack tip where the wedge crack stress field approaches that of a sharp crack. From the elastic field thus obtained, it is found that the crack extension force for the wedge crack is zero.

We have also considered the elastic interaction between a wedge crack and a screw dislocation. Again, applying the method of conformal mapping, it is found that the stress field at z in the presence of a screw dislocation located at $\zeta = \rho \exp(i\phi)$ is given by

$$\sigma_D^0(z) = \frac{\mu b q}{2\pi z^s} \left(\frac{1}{z^q - \zeta^q} - \frac{1}{z^q + \zeta^q} \right), \quad (3)$$

where b is the Burgers vector and $q = 1 - s$. The contribution of a screw dislocation to the wedge stress intensity factor λ_D may be found from this equation and is given by

$$\lambda_D = - \frac{2bq \cos(q\phi)}{(2\pi\rho)^q}. \quad (4)$$

The condition for the emission of a dislocation from a crack tip may be defined in terms of the positive stress on the dislocation at the distance equal to the core size, r_c , of the dislocation from the crack tip. The stress on the emerging dislocation, in mode III geometry, consists of the crack stress and the image stress:

$$\sigma_{\phi z} = \frac{\lambda \cos(q\phi)}{(2\pi r_c)^s} - \frac{\mu b}{4\pi r_c}. \quad (5)$$

Thus, the emission condition can be written as

$$\lambda > \lambda_e = \frac{\mu b \sec(q\phi)}{2(2\pi r_c)^q}. \quad (6)$$

Figure 3.7 shows a plot of λ_e vs the emission angle ϕ for a series of wedge angles α . It can be seen that λ_e is minimum at $\phi = 0$ for all α (i.e., the dislocation emission is favored in the direction parallel to the crack plane). At first, λ_e increases very slowly as ϕ increases, and then it increases rapidly as the plane of the emission approaches the crack flank. At $\phi = 0$, λ_e is lowest when $\alpha = 180^\circ$, and it is highest for a sharp crack. By combining the emission condition [Eq. (6)] with the connection formula [Eq. (2)] between λ and K , it is found that the applied stress intensity factor K_p required for dislocation

Fig. 3.7. Critical wedge stress intensity factor for dislocation emission λ_c vs the emission angle ϕ for a series of wedge angles α .

emission for the wedge crack is greater than that for a sharp crack.

1. Summary of paper to be published.
2. Engineering Technology Division, ORNL.
3. National Bureau of Standards, Washington, D.C.
4. H. Vehoff and P. Neumann, *Acta Metall.* 27, 915 (1979).
5. S. M. Ohr, p. 438 in *The Structure and Properties of Crystal Defects*, ed. by V. Paidar and L. Lejcek, Elsevier, New York, 1984.

DISLOCATION INTERACTIONS IN THE PRESENCE OF CRACKS¹

R. Thomson² I.-L. Lin³
S. M. Ohr S.-J. Chang⁴

The elastic interaction between dislocations is affected by the presence of surfaces, cracks, etc., which introduce a variety of image-like effects. In deriving analytic expressions for the forces on dislocations in two-dimensional elastic mediums, it is convenient to introduce the Goursat potentials. In terms of these potentials, forces on the dislocations can be expressed relatively simply in terms of the residues of the complex potential functions. The potentials must then

be found by any of the standard techniques of analysis.

For a screw dislocation, the complex stress field can be represented by a potential $\eta(z)$ as

$$\sigma(z) = \sigma_{32} - i\sigma_{12} = 2\eta'(z), \quad (1)$$

where $z = x + iy$. For an edge dislocation under the plane strain condition, the complex stress field near the tip of a semi-infinite crack is given by

$$\sigma_{22} - i\sigma_{12} = \rho' + \bar{w}' + (z - \bar{z})\bar{\rho}' \quad (2)$$

The potentials $\eta(z)$, $\rho(z)$, and $w(z)$ have been obtained for the cases of semi-infinite crack and wedge cracks. Forces on an edge dislocation and on a screw dislocation near a crack have been calculated by the residue theorem.

In another approach, the Green's functions for the potential functions for dislocations can be derived in a relatively simple way, giving rise to analytic results for the forces on the dislocations without finding the stress directly. For wedge cracks, it is necessary to use mapping theory to map known solutions for simple boundaries to more complex shapes such as wedges.

1. Summary of paper to be published.
2. National Bureau of Standards, Washington, D.C.
3. National Bureau of Standards, Boulder, Col.
4. Engineering Technology Division, ORNL.

DISLOCATION ARRANGEMENT IN THE PLASTIC ZONE FOR PROPAGATING CRACKS IN NICKEL¹

S. Kobayashi² S. M. Ohr

Since nickel is a metal of high stacking fault energy, it is of interest to study the arrangement of dislocations in the plastic zone for propagating cracks and to compare the results with those found in metals of low stacking fault energy. It has been found that two distinct distributions of dislocations in the plastic zone are associated with cracks in nickel. In one of these, the plastic zone appeared as a thin ribbon and consisted of a number of partial dislocations with stacking fault fringes. From contrast analysis and stereoscopic observations, the crack was found to be approximately mode III type, and the plane of the plastic zone was identified as (111). The crack geometry was very similar to that observed in metals of low stacking fault energy, namely, stainless steel and copper. The second type of plastic zone observed was not in the form of a thin ribbon; that is, the dislocations in the plastic zone were not split into partial dislocations. Since the dislocations were not split, they cross-slipped readily from the original slip plane and formed a broad plastic zone.

It is surprising that the dislocations observed in the plastic zone of nickel are sometimes split into partials. This observation, however, is in agreement with internal friction results³ obtained

in nickel, which indicate that dislocations are not split during stage I of deformation but rather are split into partials at the onset of stage III. In order to understand the possible causes of the dislocation splitting, the effect of purity on the dislocation configuration was studied. It was found that the specimen purity is not an important parameter because the splitting of dislocations was observed in the plastic zone of zone-refined high-purity single crystals of nickel. It was also noted that splitting of the dislocations in the plastic zone is dependent on the orientation of the tensile axis. For tensile axis orientations near [111], the dislocations in the plastic zone are extended to partials, whereas the structure of the plastic zone changed to a broad array of perfect dislocations for orientations near [001]. This type of dislocation behavior is consistent with the mechanism of dislocation splitting suggested by Copley and Kear.⁴ They pointed out that when a dislocation is split, the resolved shear stresses acting on the leading and trailing Shockley partials are different. This difference in the forces on the partials, combined with the repulsive force between the partials and the stacking fault energy, determines whether a pair of partials will remain split or will be brought back together to form a perfect dislocation. For a tensile axis near [111], the resolved shear stress on the leading partial is greater than the trailing partial. Thus, it is expected that the leading partial should be generated preferentially at the crack tip. On the other hand, for a tensile axis near [001] the situation is reversed so that when the leading partial is nucleated it is even easier to nucleate the trailing partial. Once nucleated, the width of the stacking fault is lowered even further because the force on the trailing partial is greater than that on the leading partial. It is concluded that the stress-induced nucleation and separation of the partials are responsible for the orientation dependence of the dislocation configuration observed in the plastic zone of nickel.

1. Summary of paper: *J. Mater. Sci.* 19, 2273 (1984).
2. Present address: Toyota Central Research and Development Laboratories, Nagoya, Japan.
3. D. N. Beshers and R. J. Gottschall, p. 134 in *Proc. 5th Int. Conf. Internal Friction and Ultrasonic Attenuation in Solids*, Vol. II, ed. by D. Lenz and K. Lucke, Springer-Verlag, Berlin, 1975.
4. S. M. Copley and B. H. Kear, *Acta Metall.* 16, 227 (1968).

COEXISTENCE OF DUCTILE AND BRITTLE FRACTURE IN METALS¹

S. M. Ohr C. G. Park
S.-J. Chang² R. Thomson³

It is well known that semibrittle body-centered cubic (bcc) metals fail at low temperatures by cleavage that is preceded by crack tip deformation.

Sinclair and Finnis⁴ proposed a mechanism by which crack tip deformation may be combined with brittle crack extension. In this model, edge dislocations are emitted from a crack tip on an inclined plane under pure mode I loading conditions. These dislocations shield the crack tip from the stress designated by the applied mode I stress intensity factor K_I . Furthermore, these dislocations will induce a local mode II stress intensity factor k_{II0} . As K_I is raised, more dislocations are emitted from the crack tip, thus increasing k_{II0} . Although k_{II0} is negative, it will contribute positively to the energy release rate J , because J is proportional to the square of k_{II0} . Eventually, J can reach J_c , the critical value for cleavage, by a combination of k_I^2 and k_{II}^2 , in which the latter is contributed by the dislocations generated by crack tip deformation.

Although the model of Sinclair and Finnis is very useful in understanding the mechanism of the coexistence of ductile and brittle fracture, there are some difficulties associated with this model which require further clarification. One of these is the assumption that the emission of edge dislocations from the crack tip occurs on only one inclined plane under mode I loading. Experimental evidence we have accumulated so far indicates that under mode I loading conditions the dislocations are emitted along at least two inclined slip planes that are symmetric with respect to the crack plane. As pointed out by Sinclair and Finnis, if dislocation emission occurs on two symmetrically inclined planes, $k_{II} = 0$ because k_{II0} 's contributed by the dislocations located on the opposite side of the crack plane cancel one another. Moreover, if we have a mixed mode loading condition (e.g., K_I and K_{II}), K_{II} and k_{II0} have opposite signs so that the resultant mode II local stress intensity factor is expected to be much smaller than k_{II0} . Thus, the contribution of k_{II} to J may be very small. Another difficulty associated with this model is that for semibrittle bcc metals, in which brittle fracture coexists with crack tip deformation, the critical stress intensity factor for dislocation emission for mode I, k_{Ie} , is greater than that for brittle fracture, k_{Ic} , so that a material loaded in pure mode I is likely to fail by cleavage before crack tip deformation can occur.

We propose a new mechanism of brittle fracture of semibrittle metals preceded by crack tip deformation by extending the model of Sinclair and Finnis and by incorporating experimental evidence on mixed mode crack propagation observed by transmission electron microscopy (TEM). We have shown experimentally that, even when the orientation of the dislocations in the plastic zone indicated pure mode III crack tip deformation, the crack opening displacement determined from the relative displacement of the crack flanks showed the presence of an additional mode I component. We have also shown that zigzag crack propagation observed in many metals can occur only if mode I cleavage is superimposed to mode II crack tip deformation.

We will consider a semibrittle metal which is loaded equally in modes I and II. This type of mixed loading condition is always found in our TEM observations. We have found that for all of the bcc metals,

$$k_{IIe} < k_{IIc} = k_{Ic}$$

$$k_{IIIe} < k_{IIIc} < k_{Ic}$$

so that crack tip deformation in mode II (or mode III) is expected before brittle crack extension can occur in any of the modes as the applied load is increased. In pure mode II crack tip deformation, edge dislocations are emitted along the slip plane that is coplanar with the crack. The edge dislocations emitted along the coplanar slip plane reduce k_{II} , but they do not affect k_I because $k_{II} = 0$. Also, the screw dislocations emitted under mode III do not influence k_I whether they are emitted along the coplanar slip plane or not. Therefore, as the applied load is increased, the crack tip deformation continues in mode II (or mode III), and the value of k_{II} stays at k_{IIe} . In the meantime, k_I continues to increase with the applied load because the dislocations emitted do not affect the magnitude of k_I . Finally, k_I reaches k_{Ic} , which is less than k_{IIe} for these metals, and brittle fracture occurs in mode I.

1. Summary of paper to be published.
2. Engineering Technology Division, ORNL.
3. National Bureau of Standards, Washington, D.C.
4. J. E. Sinclair and M. W. Finnis, p. 1047 in *Atomics of Fracture*, ed. by R. M. Latanision and J. R. Pickens, Plenum, New York, 1983.

TEM STUDIES OF LOW-TEMPERATURE FRACTURE IN MOLYBDENUM

C. G. Park T. C. Estes
S. M. Ohr

Crack initiation and propagation have been studied at low temperatures by electron microscopy in bcc molybdenum in order to examine the temperature dependence of crack tip deformation and its relationship to the ductile-brittle transition of fracture. A low-temperature deformation stage was built to carry out this experiment at temperatures as low as 100 K. As the test tem-

perature was lowered, the extent of crack tip deformation decreased, and the emission of long screw dislocations from grain boundary irregularities, such as ledges and junctions, increased.

In the first series of experiments, the specimens were stressed at room temperature to allow a crack to nucleate at the edge of the electro-polishing hole. The specimens were subsequently cooled to 120–150 K, and the stress was applied again. Three distinct fracture-related activities were observed during the low-temperature tensile tests. First, the nucleation and propagation of new cracks occurred along a new direction from the old cracks that were introduced at room temperature (Fig. 3.8). The crack, which propagated originally along the x_1 direction, changed its direction and propagated along a new direction (x_2) by emitting edge dislocations on different slip planes. This observation indicated that the slip systems activated depended on test temperature.

Another type of crack propagation observed during low-temperature deformation was an abrupt extension of a crack that was introduced at room temperature. The crack extended along the slip plane on which crack tip deformation occurred at room temperature but without plastic deformation. In these instances, small irregular ligaments were often observed along the crack flanks. The third feature observed was the nucleation and propagation of a new crack from the edge of the polishing hole. The crack propagated in a zigzag manner accompanied by some localized crack tip deformation. The average direction of the crack propagation was along the (001) cleavage plane. It was also found that the ligaments, or the widths of sawtooth, were very short and irregular and that the extent of crack tip deformation was reduced markedly.

The nucleation and propagation of cracks were also studied in specimens that were not precracked at room temperature. From a series of bulk tensile tests, the ductile-brittle transition temperature was established as 160–170 K. During in situ TEM fracture experiments at low temperatures, crack tip deformation was observed at temperatures greater than 160 K, in agreement with the bulk tensile tests. In most cases, the activated slip systems had the highest crack tip Schmid factors. At temperatures below 140 K, a

Fig. 3.8. Electron micrographs showing the arrangement of dislocations ahead of a mode II crack observed in molybdenum during in situ tensile tests performed at 150 K.

rapid transgranular brittle crack extension with very little plastic deformation was observed. Again the mode of fracture observed during low-temperature in situ TEM fracture experiments using thin foil specimens agreed well with that of bulk tensile tests.

CRACK TIP SLIP SYSTEMS IN BCC METALS¹

C. G. Park T. C. Estes
S. M. Ohr

When plastic deformation occurs ahead of a crack tip under an applied stress, it is necessary to examine the material parameters that are responsible for determining the slip systems that are activated. In this study, the choice of slip systems at the tips of propagating cracks has been studied in bcc molybdenum during in situ TEM tensile deformation. The slip systems are identified experimentally from the Burgers vectors of the dislocations and the observed slip planes. These slip systems are analyzed in terms of the resolved shear stress, which is modified by the presence of the crack.

Figure 3.9 shows the geometry of crack tip deformation and crack coordinate system in a TEM foil specimen. Uniaxial tensile stress σ_a is applied along the direction which makes an angle of β with the x axis. The resolved shear stress on the slip plane, inclined by an angle θ to the crack, along the slip direction may be expressed in terms of the stress intensity factor K_j ($j = I, II, \text{ and } III$) for each mode of loading.² The crack tip Schmid factor S_j for each of the three modes is defined as the ratio of the resolved

shear stress at $r = c/2$, where $2c$ is the crack length, to the applied stress σ_a .

Figure 3.10 shows electron micrographs taken from tensile specimens of molybdenum deformed in the electron microscope. Figure 3.10(a) shows the distribution of dislocations ahead of a mode III crack that was nucleated at the edge of a small polishing hole. The plastic zone is made up of dislocations emitted from the crack tip on four different slip planes. All of the dislocations are identified as screw dislocations with the identical Burgers vector. Figure 3.10(b) shows crack tip slip systems activated under mode II loading conditions. The dislocations observed are identified as edge dislocations. As was found in many other cracks studied, a dislocation-free zone is present between the crack tip and the plastic zone. From the direction of the tensile axis, the relative magnitudes of the stress intensity factor for all three modes are determined. From these, the crack tip Schmid factors (S_j), as well as the bulk Schmid factor (B), are calculated for all possible slip systems. Table 3.2 lists the results of the calculation for the crack shown in Fig. 3.10(b). It can be seen that the activated slip systems have the highest crack tip Schmid factors.

In all of the cracks analyzed, it was noted that the applied stress had components of at least two modes of crack tip deformation [i.e., no case of a pure single mode of loading was found (cf., K_j 's in Table 3.2)]. Among the three modes of deformation, mode III was favored over mode II, and in turn, mode II was favored over mode I. When all three modes were stressed equally, mode III crack tip deformation, involving the generation and motion of screw dislocations on a slanted slip plane, was observed. In most cases, the slip planes were identified as $\{110\}$, $\{112\}$, and $\{123\}$ crystallographic planes, and the activated slip systems had the highest crack tip Schmid factors. Many slip systems which had higher bulk Schmid factors were not activated because of the modification of the stress field in the presence of the crack.

SSOM-3327

Fig. 3.9. Geometry of crack tip deformation and crack coordinate system.

1. Summary of paper to be published.
2. P. C. Paris and G. C. Shih, p. 30 in Fracture Toughness Testing and Its Applications, ASTM STP No. 381, Philadelphia, 1965.

Table 3.2. Crack tip Schmid factors (S_j) and bulk Schmid factors (B) calculated for several possible slip systems for the crack tip geometry shown in Fig. 3.10(b).

K_j	Slip systems	S_{III}	B
$K_I = 0.206$	$(211)/[111]$	0.362	0.331
$K_{II} = 0.405$	$(312)/[111]$	0.362	0.391
$K_{III} = 0.004$	$(321)/[111]$	0.351	0.260
	$(213)/[111]$	0.276	0.480
	$(213)/[111]$	0.055	0.470

Fig. 3.10. (a) Distribution of screw dislocations emitted from a mode III crack in molybdenum. (b) Arrays of edge dislocations observed in front of a mode II crack.

IMPURITIES AND DEFECTS

ATOM LOCATION BY ELECTRON CHANNELING ANALYSIS¹

S. J. Pennycook

For many years the orientation dependence of the characteristic x-ray emission close to a Bragg reflection has been regarded as a hindrance to accurate microanalysis, and a random incident beam direction has always been recommended for accurate composition analysis. However, this orientation dependence can be put to use to extract information on the lattice location of foreign atoms within the crystalline matrix. Close to a Bragg reflection, a standing wave pattern is set up by the electron wavefront, which results in channeling of the electron current along or between the Bragg reflecting planes. When a standard "two-beam" condition is set up with the incident beam just outside the Bragg reflecting planes, the electron current is channeled predominantly between these planes depending on the exact incident beam orientation.² This effect can be used as the basis for atom location studies by comparing the variations seen in the x-ray yield from the matrix and impurity atoms, when the beam is tilted between these two channeling conditions.

The technique is referred to as electron channeling analysis, by analogy with the closely related and widely used technique of ion chan-

neling analysis,³ and was developed for lattice location studies of dopants in semiconductors at high spatial resolution.⁴ No mass difference is required with electron channeling which, therefore, allows neighboring elements to be analyzed. Only two spectra are required for each channeling analysis, one in each of the channeling conditions described above. If the matrix and dopant x-ray yields vary identically between the two orientations, the dopant necessarily lies within the reflecting matrix planes. If the dopant x-ray yield does not vary, the dopant atoms are randomly located with respect to the matrix planes. Examples of the electron channeling analysis of these two situations are shown in Figs. 3.11(a) and 3.11(b), respectively. The exact matrix yield variations depend on the exact orientations chosen, the sample thickness, and the beam convergence and are slightly different in Figs. 3.11(a) and 3.11(b). However, by using a ratio technique the need for detailed dynamical theory calculations of the electron intensity profiles is avoided.

It should be possible to determine the substitutional fraction F_s of the dopant in the region analyzed directly from the two spectra obtained in the two channeling orientations by defining

$$F_s = \frac{\Delta X_{sb} - 1}{\Delta X_{si} - 1} \quad (1)$$

Fig. 3.11. X-ray spectra from electron channeling analysis of Si-Sb alloys with the Sb 99% and 5% substitutional. Insert indicates schematically beam tilt conditions showing incident and diffracted beams with respect to Kikuchi lines.

where ΔX is the ratio of the x-ray yields. Experimentally, however, it was found that the Sb variation systematically exceeded the Si variation, giving F_s values greater than unity. This is due to the different spatial localization of the Sb and Si inner shell excitations. A fast electron of velocity v may excite the shell from a considerable distance away, referred to as the impact parameter b . An average impact parameter b_{RMS} for x-ray generation is obtained by integrating over all scattering angles, weighted by the inelastic cross section,⁵ to give

$$b_{RMS} = \frac{\pi v}{\Delta E} \left[\ln \left(\frac{4E}{\Delta E} \right) \right]^{-1/2}, \quad (2)$$

where E is the incident beam energy and ΔE is the inner shell binding energy. For 100-keV electrons, we find $b_{Sb}^{RMS} = 0.0120 \text{ nm} > b_{Si}^{RMS} = 0.0249 \text{ nm}$. While both are small compared with the {220} interplanar spacing of $d = 0.192 \text{ nm}$, so that both x-ray intensities show good channeling effects, the greater localization of the Sb excitation leads to a yield variation slightly greater than that for Si. To take account of this differing localization of impurity and matrix excitations, we define

$$F_s = \frac{1}{C} \frac{(\Delta X_{Sb}-1)}{(\Delta X_{Si}-1)}, \quad (3)$$

where C is the delocalization correction factor, found to be 1.10 ± 0.04 for {220} planar channeling analysis of Sb in Si.⁵ Delocalization effects will be more apparent with lower energy excitations; for example, boron will be mostly delocalized, although neighboring elements, such

as P in Si, will be delocalized to similar extents and should need no correction.

The process of precipitation of the Sb has also been studied by a combination of electron channeling analysis and transmission electron microscopy (TEM). The fraction of Sb in precipitate form was measured from the size distribution observed in the TEM image and compared to the nonsubstitutional fraction of dopant determined from the same region by electron channeling. Results are shown in Fig. 3.12 from the sample of Fig. 3.11(a) subjected to a sequential anneal between 680 and 950°C to precipitate out increasing amounts of dopant. At the end of the sequence, where the precipitates are randomly oriented, as in Fig. 3.11(b), the two measurements agree closely. However, in the early stages of precipitation, there appears to be over twice as much nonsubstitutional dopant than can be accounted for in precipitates. Both electron and ion channeling agree closely on the apparent nonsubstitutional fraction. TEM images taken under dynamical diffraction conditions show matrix strains around these precipitates. If they were coherent with the silicon lattice but with their planes in an interstitial location between the Si planes, then the Sb in the precipitates would show a reverse channeling effect to the Si, rather than no x-ray yield variation. The total Sb yield variation would be reduced by twice as much as for randomly located Sb, as is seen experimentally. The error in the ion channeling analysis is due to flux peaking effects. If the coherent precipitates were aligned with the Si planes, the Sb in them would appear substitutional, and the points in Fig. 3.12 would lie on the other side of the diagonal line. By combining electron channeling and TEM, information concerning the interface between the matrix and precipitates can be deduced. It

Fig. 3.12. Open circles show results of sequential anneal referred to in the text. Solid symbols are results of single anneals analyzed by electron channeling (circles) and bulk ion channeling (triangles) showing quantitative agreement.

should be possible to study other interfaces by such techniques.

1. Summary of paper to be published.
2. P. B. Hirsch et al., *Electron Microscopy of Thin Crystals*, Butterworth, London, 1965.
3. L. C. Feldman, J. W. Mayer, and S. T. Picraux, *Materials Analysis by Ion Channeling*, Academic Press, New York, 1982.
4. S. J. Pennycook, J. Narayan, and O. W. Holland, *Appl. Phys. Lett.* 44, 747 (1984).
5. S. J. Pennycook, *Contemp. Phys.* 23, 371 (1982).

ATOM LOCATION BY AXIAL ELECTRON CHANNELING ANALYSIS¹

S. J. Pennycook¹ J. Narayan²

Axial electron channeling analysis is a new technique for determining the lattice location of dopant or impurity atoms from small regions of a crystal examined by a transmission electron microscope. The analysis uses the strong variation in characteristic x-ray intensity seen for small changes in crystal orientation close to a zone axis. It is a quantitative technique which is simple to use and can be applied to any crystal structure. All previous techniques have used a planar channeling geometry, when the variation of x-ray yield with crystal orientation is rather small.³ In axial geometry the effects are much larger, allowing higher sensitivity and much

more convenient lattice location analysis. A similar advantage of axial geometry is seen in the closely related technique of ion channeling analysis.⁴

With a planar channeling geometry (referred to as a "two-beam" condition in electron microscopy), a single set of reflecting planes is used to set up a standing wave pattern of electron intensity normal to the planes.³ Small changes in the incident beam direction allow the intensity maxima to be located either on or between the reflecting planes to give a variation in characteristic x-ray yields, which forms the basis of the lattice location techniques. In axial geometry, two or more sets of planes can be used, simultaneously setting up standing waves in several directions and channeling the electron current into columns. These may be located on the atomic rows of the crystal or in various positions in between, forming a powerful new technique for lattice location analysis.

Figure 3.13 shows the computed electron intensity at the exit surface of a (001) Si crystal of various thicknesses, for two beam orientations; the bright areas correspond to high intensity. For each orientation the intensity

Fig. 3.13. Electron current distributions for $\langle 100 \rangle$ axial channeling analysis in Si at various thicknesses (t) of crystal with the two incident beam orientations shown schematically.

scale is normalized to the peak intensity encountered, and the projected potential is shown to mark the atom sites. The calculation was performed by a multislice program using 41 diffracted beams.⁵ Figure 3.13(a) shows the case with the electron beam incident exactly along [001], when the current is well channeled down the columns of Si atoms. The peak intensity is approximately six times the mean intensity and shows a spatial periodicity along the channel of approximately 25 nm. In Fig. 3.13(b), the incident beam is tilted just outside the exact Bragg orientation of (220) and (220) planes, when the current is channeled between the columns of Si atoms. The peak intensities are only three times the mean intensity, and well-formed peaks occur approximately every 12.5 nm in depth, although the position of these peaks varies somewhat along the direction of beam tilt. A similar situation occurs in a (111) orientation.

The strong channeling of the electron current along atomic rows results in substantially enhanced x-ray yields with the beam incident along a zone axis. The $\langle 111 \rangle$ axis gives greater enhancement than the $\langle 100 \rangle$ axis, consistent with computed peak intensities. A comparison of the typical x-ray yield variations ΔX is given in Table 3.3 for {220} and {400} planar³ and $\langle 100 \rangle$ and $\langle 111 \rangle$ axial channeling conditions. It can be seen that a rough estimate of the axial yield variation is given by the product of the yield variations for the lowest order planes contained in the zone axis; thus, $\Delta X \langle 100 \rangle = [\Delta X \{220\}]^2$, and $\Delta X \langle 111 \rangle = [\Delta X \{220\}]^3$, although the exact yield variations seen, in practice, depend on the exact incident beam directions and convergence and the local sample thickness.

Table 3.3. Typical Si x-ray yield variations seen for various channeling conditions and the corresponding delocalization correction factors C for Sb atom location.

	ΔX_{Si}	C
{220} planar	1.4	1.10 ± 0.04
{400} planar	1.2	1.17 ± 0.07
$\langle 100 \rangle$ axial	2.2	1.04 ± 0.03
$\langle 111 \rangle$ axial	3.1	1.05 ± 0.02

The quantitative determination of substitutional fraction F_s is also aided by the axial geometry. Delocalization correction factors are needed when the characteristic x-ray emissions from dopant and matrix occur at substantially different energies. Table 3.3 shows that these are reduced in axial geometry, presumably because the peak in the electron current is moved a larger distance from the atom site in axial geometry compared with planar geometry, 0.71d for $\langle 100 \rangle$ axial channeling and 0.5d for {220} planar channeling. This simulates a larger interplanar spacing when delocalization effects are reduced. The greater sensitivity of axial chan-

neling allows the electron channeling analysis to be extended to situations in which lower x-ray intensities are generated, thus opening up exciting areas related to impurity precipitation and segregation at dislocations, twins, and stacking faults, which are the fundamental processes governing gettering and alloying phenomena in materials, particularly semiconductors.

1. Summary of paper to be published.
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. S. J. Pennycook, J. Narayan, and O. W. Holland, *Appl. Phys. Lett.* **44**, 547 (1984).
4. *Materials Analysis by Ion Channeling*, ed. by L. C. Feldman, J. W. Mayer, and S. T. Picraux, Academic Press, New York, 1982.
5. Computer programs supplied by the Facility for High Resolution Electron Microscopy, Arizona State University, Tempe, Ariz.

DIRECT IMAGING OF DOPANT DISTRIBUTIONS IN SILICON BY SCANNING TRANSMISSION ELECTRON MICROSCOPY¹

S. J. Pennycook J. Narayan²

Conventional transmission electron microscopy (TEM) relies on diffraction or phase contrast mechanisms to form the image and can, therefore, only image the dopant in semiconductors when it forms a separate distinct phase, such as a precipitate. With scanning transmission electron microscopy (STEM), incoherent imaging modes, which allow the formation of images showing strong atomic number (Z) contrast, are available. The image intensity simply reflects the number of atoms under the beam, and it is not critical whether the atoms are isolated or in precipitate form. We have directly imaged Bi concentrations of 0.2–1 at. % and Sb concentrations of 0.6–6 at. % in ion-implanted silicon using cross-section samples. These results represent the first direct images of dopant distributions in semiconductors by electron microscopy.

The Z-contrast image is obtained in STEM with an annular detector placed around the transmitted beam, collecting electrons scattered at high angles, where the dominant scattering mechanism is Rutherford scattering. The resulting image can reveal the distributions of heavy dopants while still in solution, with minimum contrast from crystal defects. It is entirely complementary to conventional images in which the contrast is due primarily to crystal defects. The different information from the two types of images is clearly demonstrated in Fig. 3.14, which shows cross-section images of $^{121}\text{Sb}^+$ -implanted (80 keV, $1.35 \times 10^{16} \text{ cm}^{-2}$) Si, which was recrystallized by solid-phase-epitaxial (SPE) growth at 550°C for 40 min. The conventional TEM image of the sample [Fig. 3.14(a)] shows a band of dislocation loops underlying the SPE-grown region and the layer of twinned and polycrystalline Si near the surface. The image is dominated by diffraction contrast. Figure 3.14(b) shows an annular dark field STEM micrograph of the same region, using the same

SSDN 3194

Fig. 3.14. Cross-section micrographs of $^{121}\text{Sb}^+$ -implanted (80 keV , $1.35 \times 10^{16}\text{ cm}^{-2}$) Si (100) following recrystallization by SPE growth at 550°C for 40 min: (a) TEM, (b) STEM image using diffraction contrast, and (c) STEM image from Rutherford scattered electrons showing Sb distribution. Markers indicate original sample surface.

diffraction conditions, but at a lower image resolution.

Figure 3.14(c) shows the image obtained using Rutherford scattered electrons, which clearly delineates the implantation profile of Sb and shows that no Sb precipitates have formed. The narrow line visible in the image probably indicates segregation of Sb at the boundary of the single-crystal and polycrystalline regions. A line scan of the image contrast is shown in Fig. 3.15(a) and agrees quantitatively with the Sb concentration profile measured directly by x-ray microanalysis [Fig. 3.15(b)]. The microscopically determined Sb profile is also in agreement with the bulk RBS analysis [Fig. 3.15(c)].³ It is clear that the image contrast quantitatively reflects the dopant profile. In fact, the high-angle image has much greater sensitivity for detecting segregation phenomena, and it should be possible to use such an image for elemental mapping at high spatial resolution in thin specimens. The characteristic x-ray emission cannot be used for this purpose since the intensity emitted by the dopant is too low when using a small probe. These images will be of great value in studying dopant segregation effects at twins and dislocations, particularly when the dopants cluster or form precipitates that are below the resolution limit of the diffraction contrast imaging mode.

1. Summary of paper: *Appl. Phys. Lett.* **45**, 385 (1984).
2. On leave to Microelectronics Center of North Carolina, Research Triangle Park, N.C.
3. J. Narayan, O. W. Holland, and B. R. Appleton, *J. Vac. Sci. Technol.* **B 1**, 871 (1983).

Fig. 3.15. (a) Line scan showing high-angle detector contrast. (b) Sb profile determined by x-ray microanalysis. (c) RBS analysis of Sb.

ORDERING OF CARBON VACANCIES IN NONSTOICHIOMETRIC TRANSITION-METAL CARBIDES¹

J. Hauck² B. C. Larson
G. R. Gruzalski L. S. Darken³
J. F. Barhorst⁴

The ordering of carbon vacancies in nonstoichiometric VC_x and ZrC_x single crystals has been

measured using x-ray superlattice reflections. The ordering structure was determined from the reciprocal-space superlattice pattern, and the degree of ordering and the magnitude of lattice distortions were determined using the superlattice intensities. While $VC_{0.88}$ was found to order in the V_8C_7 structure as expected, $VC_{0.84}$ exhibited a superlattice pattern corresponding to a one dimensionally disordered V_6C_5 structure rather than the expected long-range-ordered V_6C_5 structure. This $VC_{0.84}$ result was interpreted in terms of a lack of long-range order in the stacking sequence along the $\langle 111 \rangle$ directions such as that introduced by high densities of stacking faults. $ZrC_{0.65}$ samples were found to be only partially ordered in the as-grown state but were fully ordered in the Ti_2C structure after 100-h anneals at 800°C. The zirconium atoms in octahedral coordination were found to be attracted ~ 0.03 Å toward the three carbon atoms in facial configuration and away from carbon vacancies. The affinity of Zr for oxygen yielded oxygen-rich surface layers after the prolonged (~ 100 h) high-temperature anneals; these oxygen-rich layers were found to be ordered in the Ti_8C_5 structure and were presumably an oxycarbide.

A model has been proposed for understanding the ordered structures of these carbides based on an "equal distribution" rule analogous to that proposed⁵ for the ordering of vacancies and interstitials in interstitial alloys and interstitial oxides. The model postulates that (1) each metal atom in the NaCl structure has the same number of vacant nearest neighbor (carbon) sites and that (2) each vacant carbon site has the same number of neighboring vacant (carbon) sites out to third-nearest neighbors. These postulates are based on the assumption of strong metal-carbon bonding and strong (repulsive) interactions between vacant carbon sites. The first postulate is fulfilled for MC_x for $x = n/6$, where n is the number of neighboring atoms at octahedral sites of the NaCl lattice. The V_6C_5 and Ti_2C structures satisfy both the postulates while the V_8C_7 and Ti_8C_5 structures fulfill only the second postulate. It is suggested that V_8C_6 would prefer to decompose into $V_6C_5 + VC$ if VC were thermodynamically stable, a conjecture that is reinforced by the fact that the V_8C_7 structure does not exist in niobium and tantalum carbides, where compositions near stoichiometric NbC and TaC exist. The Ti_8C_5 structure found in the oxygen-rich surface layers may have been stabilized by presence of the oxygen since it was present only in the thin oxygen-rich layer.

PHASE DETERMINATION OF X-RAY STRUCTURE FACTOR BY OBSERVATIONS OF MULTIPLE BEAM EFFECTS

Qun Shen¹ J. Z. Tischler
R. Colella¹

All common x-ray methods for determining electronic charge distributions in crystalline materials make use of only the absolute value of the complex x-ray structure factors, $F(H)$. Since only the complex structure factors can be directly Fourier transformed to give the charge distribution, the best one can do with the absolute value of the structure factor $|F(H)|$ is to get the auto-correlation function of the charge distribution. This is sufficient for determining the basic structure of most inorganic crystals. However, to determine accurately the charge distribution in many crystals (e.g., silicon and germanium), the phase of $F(H)$ is also needed.

One method for determining phases that has received much discussion in recent years uses the interference of multiple x-ray beams.^{2,3} Multiple reflections occur when more than one reciprocal lattice point lies on the Ewald sphere. By rotating the crystal through an angle ϕ about the main reciprocal lattice vector H , extra reciprocal lattice points pass through the Ewald sphere and cause additional diffraction. With many coherent beams simultaneously interfering, the phases of structure factors significantly affect the integrated intensity. In this experiment, we have demonstrated the utility of using such multiple beam effects for direct phase determination.

The (442) reflection in diamond structure materials (specifically silicon) is forbidden for an ideal spherical atom. However, the non-spherical bonds give rise to a small structure factor $F(442)$. From the symmetry of the silicon crystal, the phase of $F(442)$ must be either 0 or π , but there is no basis for choosing one phase over the other.

Earlier experimental measurements of $|F(442)|$ versus temperature showed that $F(442)$ increases monotonically from a value of -0.035 at 300 K to a value of $+0.035$ at 700 K.⁴ This earlier work obtained the phase from a comparison of the temperature dependence of $F(442)$ to the known temperature dependence of anharmonic vibration. Since the $F(442)$ exactly reverses sign for these two temperatures, only the effect of phase upon multiple scattering was observed. The present experiment consisted of measuring the (442) integrated intensity for various ϕ orientations at both 300 K and 700 K. To simplify matters, all data were taken in the vicinity of one multiple reflection, the (111).

Figure 3.16 shows theoretical calculations of the silicon (442) integrated intensity at 1.542 Å. The large peak in ϕ occurred as the (111) reciprocal lattice point passed through the Ewald sphere. The solid curve in Fig. 3.16(a) was calculated assuming $F(442) = -0.035$, and in Fig. 3.16(b) assuming $F(442) = +0.035$. Note the distinct difference in shape resulting from the change in sign. Comparing the calculated integrated intensities to the measured intensities

1. Summary of paper: Journal of Applied Crystallography (in press).

2. Guest scientist from Kernforschungsanlage Jülich, Federal Republic of Germany.

3. Present address: Tennelec, Inc., Oak Ridge, Tenn.

4. Present address: Emerson Electric Co., St. Charles, Mo.

5. J. Hauck, Acta Cryst. A36, 228 (1980).

JRSI-DRL 8--17643

Fig. 3.16. Plot of integrated intensity versus ϕ [measured about an axis normal to the (442) planes]. In both parts the curves are from eight-beam dynamical calculations, and the points are measured data. The measurements were multiplied by a scale factor since the incident intensity was not accurately known. Part (a) shows the data at 300 K, and part (b) the data at 700 K.

clearly indicates the proper phase for $F(442)$ to be π at 300 K and 0 at 700 K. Similar multiple reflection measurements were performed on germanium, and again visually comparing the measured integrated intensity versus ϕ to calculations indicated a phase that agreed with previous measurements.⁴

This clear agreement between the shape of experimental and theoretical curves demonstrates the possibility of directly determining phase information from diffraction measurements using multiple reflections.

1. Purdue University, Lafayette, Ind.
2. D. Chapman, D. Yoder, and R. Colella, *Phys. Rev. Lett.* **46**, 1578 (1981).
3. H. Jruetschke, *Phys. Rev. Lett.* **48**, 1487 (1982).
4. J. Z. Tischler and B. W. Batterman, *Phys. Rev. B* **30** (in press).

ANOMALOUS PERTURBED MAGNESIUM VACANCY IN NICKEL-DOPED MgO ¹

J. L. Boldú²
Y. Chen

E. Muñoz Picone²
M. M. Abraham

Two species of radiation-induced paramagnetic defects exist in MgO crystals which possess identical electronic g values: $g_1 = 2.0386(2)$ and $g_2 = 2.0033(2)$. The first species is the intrinsic, isolated V^- center, whose linear configuration can be described as $\text{O}^{2-}-[\text{V}_{\text{Mg}}]-\text{O}^-$, where the O^- represents an oxygen with a trapped hole. (This defect will be referred to as the unperturbed V^- defect.) The second defect is a V^- perturbed (or charge compensated) by an Al^{3+} ion at the next nearest neighbor. The linear configuration of this defect is $\text{Al}^{3+}-\text{O}^{2-}-[\text{V}_{\text{Mg}}]-\text{O}^-$. (This defect is referred to as either the perturbed V^- or the V_{Al} center.) While investigating the effects of γ irradiation on paramagnetic defects in nickel-doped MgO crystals, a new defect was discovered that has the same g values as the unperturbed V^- and the perturbed V^- centers. This defect, however, cannot be classified as being either of these centers. The new defect has the following characteristics. First, no electron nuclear double resonance (ENDOR) of aluminum or any other nuclei with nonzero nuclear spin ($I \neq 0$) was detected at 4.2 K. This observation indicates that any charge compensators in a near-neighbor site must have $I = 0$; or if $I \neq 0$, they must occupy positions beyond the first two neighbors. Second, motional averaging of the hole was not observed. The implication is that a charge compensator exists nearby (even if it is not at the first two nearest neighbors), which removes the electronic isotropy of the defect at room temperature. Third, this defect was observed after a dose of only 1×10^6 R. This observation suggests that the vacancy was already present prior to irradiation and that it became paramagnetic due to the trapping of a hole. Fourth, the defect is very stable, with a room temperature half-life of more than a year. Furthermore, analyses of the thermoluminescence associated with the hole release indicate that the thermal activation energy is 1.5 eV. This indicates that any charge compensator must be located beyond the next nearest neighbor.

On the basis of these results, it appears that a third species exists, involving a charge compensator which is not far beyond the next nearest neighbor. We have been unable to identify the charge compensator by electron paramagnetic resonance (EPR) or ENDOR. In addition, the signal-to-noise ratio was not large enough to obtain the ^{25}Mg superhyperfine interaction by ENDOR. This latter information can be used, in principle, to provide the location of the compensator.

1. Summary of paper: *Phys. Rev. B* **29**, 6365 (1984).
2. Universidad Nacional Autónoma de México, Distrito Federal, México.

TIME DEPENDENCE OF THE CURRENT INJECTION
PHENOMENA IN NICKEL-DOPED MgO CRYSTALS
AT HIGH TEMPERATURES¹

K. L. Tsang² H. T. Tohver³
Y. Chen

The electrical conduction mechanisms in MgO:Ni with Pt electrodes at 1473 K have been studied over electric-field ranges up to ~10 kV/cm. The current transients induced by pulsed changes of the applied voltage, as well as transient short-circuit currents, have been measured and analyzed to yield two electron-hole recombination lifetimes of 10 and 250 s. The main features of the results are consistent with the double-injection model of the electrical breakdown of MgO at high temperatures.

The electrical current in nonmetallic solids can be conducted by carriers present at thermal equilibrium and also by excess electrons or holes (or both) injected by external contacts into the solid.^{4,5} The current resulting from single-carrier injection is space-charge limited; that from double injection is limited by the recombination rate of the injected electrons and holes. Yet both injection processes can lead to the same current-voltage relationship,⁴ namely $I \propto V^2$, making it difficult to distinguish between the two injection mechanisms. However, the transient response of the current to changes in the applied potential provides a simple, clearcut distinction between ohmic, single-injection, and double-injection conduction.⁵

For ohmic currents, the linear I-V relationship holds for time-dependent voltages as well. The current response for single-carrier injection into an insulator is an initial overshoot of the current of the steady-state value followed by a small undershoot and a final asymptotic decay toward a steady-state value. For double injection into a semiconductor (where local charge neutrality can be assumed), the transient current is given by

$$I(t) = I_f [1 - \exp(-t/\tau)(V_f - V_i)/V_f] \quad (1)$$

$$I(0+) = I_i (V_f/V_i) \quad (2)$$

where V_f is the final voltage, V_i the initial voltage, I_f the final steady state current, I_i the initial current, $I(0+)$ the initial current after voltage change, and τ the electron-hole recombination lifetime. Equation (2) represents an ohmic current step, while Eq. (1) predicts an exponential approach of the transient current to the steady-state value with no overshoot.

These transient responses are used in this work to check the predictions of a model proposed by Tsang, Chen, and O'Dwyer⁶ for the high-temperature dielectric breakdown of MgO under a constant electric field (1500 V/cm). This model assumes that the small initial current is carried by thermal-equilibrium carriers—principally electrons, with the holes being trapped. With time, hole injection at the anode is augmented by the

accumulation of negative charges through some form of ion or vacancy migration. The resultant increase in hole concentration demands an equal increase in electron concentration from the cathode. Thus, a monotonically increasing current, which unchecked would lead to sample destruction, is the result of double injection.

The initial I-V curve was measured after varying the electric field from 200 to 8000 V/cm. Each point was measured every minute by applying the electric field for one second. Subsequent curves were taken after a constant current of (1) 1 mA for 15 h, (2) 1 mA for 15 h followed by 10 mA for 16 h, and (3) 10 mA for 90 h following treatments (1) and (2). All these characteristics are displayed in Fig. 3.17. The transition from linear to quadratic voltage dependence of the current is evident in curves 1 through 3, indicating a shift from current carried by equilibrium charge carriers to an injected current. In the linear region, where the conductivity is proportional to the equilibrium carrier concentration, there is a difference in the conductivity of curve 3 and of the "initial" curve of a factor of ~10². This raises the possibility that subjecting MgO to electric fields at high temperatures can increase the equilibrium carrier concentration by orders of

Fig. 3.17. I-V characteristics of a MgO:Ni crystal at 1473 K. The I-V measurements were performed at the beginning of the experiment and after several constant-voltage treatments.

magnitude. A measurement of the temperature dependence of the initial current at 200 V/cm over the range of 1400 to 1690 K yielded an activation energy of 2.7 ± 0.1 eV.

The transient current following a voltage pulse lasting 10 min was measured in three different regions of the I-V curve: the linear, transition, and quadratic regions. The sample had been treated for 16 h at 10 mA. The current transients are shown in Fig. 3.18. The transient shown in the bottom curve resulted from a voltage pulse of amplitude plus 1 volt applied on top of a quiescent voltage of 2 volts. This increased the applied electric field from 34 to 52 V/cm during the pulse duration—values well within the linear region of the I-V curve (Fig. 3.17). As expected for currents carried by thermal carriers, the current and voltage pulse are related by a constant multiplier (i.e., ohm's law holds). The middle transient resulted from a field increase to 340 from 170 V/cm. This pulse takes the current from the linear to the quadratic region. The transient-current response is in qualitative agreement with that expected from single-carrier injection. The top transient in Fig. 3.18 resulted from a field increase from 1380 to 1550 V/cm, both fields being within the quadratic region. The transient current could be fitted to Eqs. (1) and (2) after the asymptotic Eq. (1)

had been modified for the presence of two instead of just one decay constant.

The transition from linear to quadratic I-V characteristics after long-term application of electric field represents the onset of the predicted double injection at high fields. The time dependence of the transient current following a voltage pulse is in good agreement with the theory for double injection.

1. Summary of paper: p. 207 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, Elsevier Science Publishers, Inc., New York, 1984.

2. Graduate laboratory participant from the University of Alabama-Birmingham, Birmingham, Ala.

3. University of Alabama-Birmingham, Birmingham, Ala.

4. M. A. Lampert and P. Mark, Current Injection in Solids, Academic Press, New York, 1970.

5. P. Mark and M. Allen, Ann. Rev. Mater. Sci. 3, 111 (1973).

6. K. L. Tsang, Y. Chen, and J. J. O'Dwyer, Phys. Rev. B 26, 6909 (1982).

PHYSICAL PARAMETERS ASSOCIATED WITH THE DIELECTRIC BREAKDOWN OF MgO CRYSTALS AT HIGH TEMPERATURES¹

K. L. Tsang² Y. Chen
H. T. Tohver³

Dielectric breakdown is a serious problem in the application of insulating materials at high temperatures in electric fields. The mechanisms involved depend on the material and conditions such as temperature, geometry, electric field, ambient atmosphere, electrode material, and impurity content. Electrical breakdown, therefore, is a complicated phenomenon. In this work, we studied the prebreakdown electrical characteristics induced by these parameters individually. The results are found to be compatible with the double injection model.

Time dependence and field reversals. In general, the time-dependent currents when the electric field is reversed can be described accurately as the sum of two exponential terms

$$I(t) = I_{01}e^{-t/\tau_1} + I_{02}e^{t/\tau_2} \text{ for } t > 0 \quad (1)$$

where I_{01} , I_{02} , τ_1 , and τ_2 are positive constants, and $I_{01} > I_{02}$, $\tau_1 < \tau_2$. The equation shows a minimum in $I(t)$ at a time denoted by t_m . At $t < t_m$, the first term, $I_{01}e^{-t/\tau_1}$, is predominant. At $t > t_m$, the second term dominates.

Potential profile. The potential profile along the crystal thickness varies with time and changes from nonlinear to nearlinear as the current increases. Initially the electric field strength is much higher in the regions near electrodes than in the central part of the crystal. This condition indicates that local electrical

Fig. 3.18. Transient-current response due to step voltage change. The voltage changes were taken after the sample had been treated for 16 h at 10 mA and were performed in three regions: linear I-V region (bottom), quadratic I-V region (middle), and a transient region in between (top).

neutrality prevails as current increases. A rapid building of the field strength near the electrodes when the field is reversed indicates that there is a high electron injection as soon as field is applied. Polarization effects⁴ are not a factor. Furthermore, the initial field strength near the electrode decreases as the current increases, indicating that the whole sample approaches a plasma condition.⁵

Thickness dependence. The breakdown characteristics are nearly independent of sample thickness.

Temperature and field strength effect. The effects of temperature and field strength on τ_2 were determined individually. The relationship can be expressed as

$$\tau_2 = \tau_{02} \exp\{(Q_2/KT) - \beta E\}, \quad (2)$$

where the activation energy Q_2 is 2.3 eV, β is a positive constant, and $\beta E > 0$.

Ambient atmosphere effect. The dielectric breakdown of MgO:Ni crystals at 1473 K was also examined using an electric field of 1500 V/cm in flowing oxygen and nitrogen atmospheres. The results are shown in Fig. 3.19. The current behavior was essentially similar in both oxygen and nitrogen atmospheres, and the time constant was the same. At high current levels, the rate of current increase was less in air than in either oxygen or nitrogen. The characteristic times for breakdown of MgO crystals at 1473 K in pure oxygen, pure nitrogen, and air were 7.5, 7, and 16 h, respectively. Since air is a composite of these two gases, it is not immediately obvious why the breakdown time in air is twice that in the others.

Electrode effect. The observed breakdown characteristics depend strongly on the electrode

material. Four kinds of electrode materials were used: platinum, rhodium, iridium, and graphite. All the measurements were performed in a flowing dry-nitrogen atmosphere. Both the cathode and the anode were of the same material. The current behavior is illustrated in Fig. 3.20. During the first 30 min the current behaved differently. Subsequently, current in samples with Pt, Rh, and graphite electrodes increased with nearly the same time constant. The time constant associated with Ir was about four times smaller. The characteristic times for breakdown were 2, 4, 5, and 7 h for Ir, graphite, Rh, and Pt electrodes, respectively. Using different combinations of electrode materials, it was shown that the current behavior is determined primarily by the cathode material.

Impurity effects. An undoped MgO crystal typically required 22 h for the current to reach imminent breakdown. Crystals doped with V, Cr, Fe, or Ni had lower characteristic times for breakdown.⁶ Doping crystals with H, Co, or Cu increases the time required for dielectric breakdown. Clearly, impurities play an important role in determining the lifetime of MgO crystals used as electrical insulators at high temperatures.

The nonequilibrium conduction mechanism can be described satisfactorily by a double injection model involving drift of ionic species or vacancies. The current increase results from an increase of hole injection, which is enhanced by the migration of negatively charged ionic species or vacancies toward the anode, as well as the development of local electrical neutrality.⁷ The τ_2 appears to be related to the short-range migration of the negatively charged ionic species or vacancies toward the anode. Impurities are expected to affect the current behavior and the breakdown characteristics, because impurities can either create charge trapping sites which affect the development of the local electrical

Fig. 3.19. The effect of atmospheric conditions on the current behavior of MgO:Ni crystals. The log of current is plotted against time. Three different atmospheres were used: pure oxygen, pure nitrogen, and air.

Fig. 3.20. The effect of electrode material on the current behavior of MgO:Ni crystals. Samples were treated at 1473 K with the use of an electric field of 1500 V/cm in flowing dry N_2 . Four different electrodes were investigated: Ir, graphite, Rh, and Pt.

neutrality or create vacancies (or ionic species) which determine the rate of hole injection.

1. Summary of paper: Physical Review B (in press).
2. Graduate laboratory participant from the University of Alabama-Birmingham, Birmingham, Ala.
3. University of Alabama-Birmingham, Birmingham, Ala.
4. A. J. Moulson, W. R. Phillips, and P. Popper, p. 199 in Special Ceramics, ed. by P. Popper, Academic Press, New York, 1965.
5. M. A. Lampert and P. Marks, Current Injection in Solids, Academic Press, New York, 1970.
6. K. L. Tsang and Y. Chen, J. Appl. Phys. 54, 4531 (1983).
7. K. L. Tsang, Y. Chen, and J. J. O'Dwyer, Phys. Rev. B 26, 6909 (1982).

EPR POWDER PATTERN ANALYSIS FOR CUBIC SITES OF Fe^{3+} in MgO ¹

J. L. Boldú² E. Muñoz P.²
Y. Chen M. M. Abraham

A powder EPR spectrum is composed of a superposition of spectra from the randomly oriented single crystals. The contributions are not uniformly distributed, and a line in the powder pattern is observed only when the magnetic field position of the transition $[H(\theta, \phi)]$ reaches a stationary value. Those stationary states have been derived by calculating the singularities of the integrand of the powder absorption curve.³

It is known that for a $3d^5$ system in a cubic crystal field for $M \neq 1/2$, the stationary values of $H(\theta, \phi)$ are found at $(\theta=0^\circ)$, $(\theta=54.74^\circ, \phi=\pi/4)$, $(\theta=\pi/2, \phi=\pi/4)$, $(\theta=\pi/4, \phi=\pi/2)$, and $(\theta=\pi/4, \phi=0^\circ)$. The first value represents equivalent $\langle 100 \rangle$ directions, the second represents $\langle 111 \rangle$ directions, and the last three represent equivalent $\langle 110 \rangle$ directions. The $\langle 100 \rangle$ and $\langle 111 \rangle$ directions will be observed in the powder pattern as shoulders while the $\langle 110 \rangle$ will produce divergences.

The angular variation in the $\langle 110 \rangle$ plane for Fe^{3+} in an MgO single crystal was studied by verifying the local cubic symmetry. It was observed that the only stationary values for the magnetic field positions of the transitions with $M \neq 1/2$ occur at the $\langle 100 \rangle$, $\langle 110 \rangle$, and $\langle 111 \rangle$ crystallographic directions. In Fig. 3.21, the EPR spectra obtained with the field parallel to the $\langle 100 \rangle$, $\langle 111 \rangle$, and $\langle 110 \rangle$ directions are shown. At the bottom of Fig. 3.21, the EPR powder spectrum obtained after grinding the single crystal is also presented. The measured magnetic field positions of both single-crystal and powder-pattern transitions were fitted to the equations of Ref. 4, and there is a one-to-one correspondence between the peak positions in the single-crystal and powdered samples. If the powder particle size is sufficiently small, the occurrence of axial- or lower-symmetry sites is inevitable due to the proximity of the surface, and the EPR powder pattern would show departures from cubic symmetry. In the present case, the

Fig. 3.21. EPR absorption spectrum for Fe^{3+} in single-crystal and powdered samples of MgO .

process of mechanically grinding the single crystal to a powder (particle size $\sim 1-10 \mu$) does not remove the cubic symmetry or introduce an appreciable concentration of new noncubic sites which might be induced by lattice distortion of the crystallites due to strain. All the shoulders and divergences observed in the EPR powder pattern can be identified and explained in terms of the single-crystal EPR spectral transitions.

1. Summary of paper: J. Chem. Phys. 80, 574 (1934).

2. Universidad Nacional Autónoma de México, Distrito Federal, Mexico.

3. R. W. Reynolds et al., *J. Chem. Phys.* 56, 5607 (1972).

4. J. Rubio O. et al., *J. Chem. Phys.* 70, 633 (1979).

DEGRADATION OF COMMERCIAL VARISTORS BY REDUCING AMBIENTS

E. Sonder

Previous work¹ has shown that the electrical performance of ZnO varistors degrades rapidly when the varistors are exposed to reducing atmospheres at elevated temperatures (250–300°C). This degradation is in part a surface effect but also involves short-circuiting current pathways through the bulk. The high rate and/or low temperature of occurrence of this phenomenon rules out normal bulk or grain boundary diffusion of ions; the variability of the degradation rate in different samples suggests the presence of flaws (such as interconnected pores or cracks). It has not been possible to identify these flaws, but we report here two experiments that yield additional information on these flaws in commercial varistors.

A degraded varistor was cut into 1-mm squares for measurement² of the electrical properties. The results show that the electrical properties are not uniform—that some pieces exhibit short circuiting while others retain their nonlinear characteristics. It is possible to conclude from this result that the flaws in question are few in number and are distributed in such a fashion that some areas (1 mm²) do not contain flaws.

In another series of measurements, commercial varistors of different ratings were treated identically at 300°C in CO/CO₂ gas for 1 h and then tested to determine whether there was any correlation between the processing variables necessary to produce the different varistor materials and their degradation behavior. Table 3.4 shows the measured leakage resistances. The results

Table 3.4. Leakage resistance of commercial varistors before and after 1-h anneals at 300°C in reducing ambients.

Commercial varistor specification	Voltage rating (volts)	Leakage resistance	
		Before treatment	After treatment
V 130 LA 10 A	130	1 × 10 ¹⁰	5 × 10 ⁹
		1 × 10 ¹⁰	3 × 10 ⁵
V 130 LA 20 A	130	3 × 10 ¹⁰	3 × 10 ¹⁰
		1 × 10 ¹¹	3 × 10 ¹⁰
V 510 PA 80 A	510	3 × 10 ⁹	1 × 10 ⁴
V 550 PA 80 A	550	3 × 10 ¹⁰	1 × 10 ⁵
V 1000 LA 10 A	1000	3 × 10 ⁹	3 × 10 ⁹
		3 × 10 ¹⁰	1 × 10 ⁹
		1 × 10 ¹⁰	1 × 10 ⁶
		3 × 10 ⁹	1 × 10 ⁹

indicate that some samples have not been greatly affected by the reduction treatment, whereas others exhibit decreases in the leakage resistance greater than five orders of magnitude. The changes in leakage resistance are not correlated with the varistor ratings, but appear to occur randomly.

1. E. Sonder, M. M. Austin, and D. L. Kinser, *J. Appl. Phys.* 54, 3566, (1983).

2. These measurements were performed by L. M. Levinson and H. R. Philipp, General Electric Research Laboratories, Schenectady, N.Y.

SEMICONDUCTOR PHYSICS AND PHOTOVOLTAIC CONVERSION

OPTICAL PROPERTIES OF ION-IMPLANTED SILICON

G. E. Jellison, Jr. F. A. Modine
C. W. White

The optical properties of amorphous silicon formed by ion implantation are of great interest for pulsed-laser annealing applications. However, the study of the optical properties of ion-implanted amorphous materials is complicated by the fact that those properties are often a function of sample preparation variables, including (1) the ion used, (2) the dose, (3) the sample substrate temperature, and (4) post-implantation annealing that may have occurred.

The study of the optical properties of ion-implanted materials is further complicated by the fact that, in general, the optical properties may vary significantly with the depth from the surface of the sample. That is, the surface is often only lightly damaged and may therefore have optical properties different from those near the damage peak, which in turn may be quite different from those of the substrate. The minimum number of layers that must be considered to obtain accurate values of the optical functions from ellipsometry in such a case is six: namely, air, native oxide, a lightly damaged layer, a heavily damaged layer, another lightly damaged layer, and finally the semi-infinite substrate.

One possible way of reducing the number of layers that must be considered is to implant the surface using several different ion energies, resulting in an evenly damaged front surface region. In this case, the surface can be modeled with only three media: air, oxide, and amorphous silicon. Figure 3.22 shows the real and imaginary parts of the dielectric function of amorphous silicon prepared by ion implanting Si⁺ into Si at several implantation energies, resulting in a uniformly damaged layer ~230 nm thick. Also shown in Fig. 3.22 are the dielectric functions of crystalline silicon and silicon implanted with 10¹⁶ B/cm². As can be seen, the B implantation results in only a slight alteration of the optical spectra, while the optical spectra are completely changed when the implantation atom is silicon. The dielectric function of a-Si:Si is very similar to that of amorphous silicon formed

Fig. 3.22. The complex dielectric functions plotted vs photon energy of crystalline silicon (c-Si); ion-implanted amorphous silicon, implanted with 10^{16} Si $^{+}$ /cm 2 (a-Si:Si $^{+}$); and silicon implanted with 10^{16} B $^{+}$ /cm 2 (c-Si:B $^{+}$).

by chemical vapor deposition,¹ where the peak in ϵ_2 occurs at 3.3 eV with a value of 24.

1. D. E. Aspnes, *J. Vac. Sci. Technol.* 18, 389 (1981).

REFLECTIVITY OF SILICON IMPLANTED WITH PF $_5$ AND BF $_3$ COMPLEXES

G. E. Jellison, Jr. R. B. Wheeler
F. A. Modine R. D. Westbrook
R. F. Wood

Recent studies have shown that solar cells of high efficiency can be fabricated using a low-energy ion implantation process followed by pulsed excimer laser annealing.^{1,2} In the low-energy ion implantation process, BF $_3$ or PF $_5$ is ionized into various excited complexes (such as BF $_3^+$, BF $_2^+$, and B $^{3+}$) and accelerated with a voltage $\sim$ 2 kV.

In order to assist in the characterization of the differences in the laser annealing of silicon implanted with BF $_3$ and PF $_5$, reflectivity spectra of two implanted wafers were taken and are shown in Fig. 3.23, with the reflectivity of c-Si for comparison. As can be seen, the reflectivity from the material implanted with PF $_5$ is

Fig. 3.23. The reflectivity of crystalline silicon (c-Si) and silicon implanted with complex ions formed from PF $_5$ (PF $_5$) and from BF $_3$ (BF $_3$).

nearly the same as c-Si, particularly at photon energies below $\sim$ 3 eV. On the other hand, the reflectivity of the BF $_3$ -implanted sample is considerably different from that of both crystalline and PF $_5$ -implanted Si; the reflectivity at low energies is higher than that for c-Si and the PF $_5$ -implanted sample, and the two peaks are much lower in reflectivity and are moved to lower energies. Apparently, the BF $_3$ -implanted sample is more heavily damaged than the PF $_5$ -implanted sample, a surprising result in that mass-analyzed P implantation will amorphize the front surface region, while B implantation will not.

These results are of particular interest in connection with excimer laser annealing (XeCl; $\lambda = 308$ nm $\approx$ 4.03 eV) and explain the observation that the energy density to anneal BF $_3$ -implanted samples is substantially ($\sim$ 20%) less than that required to anneal PF $_5$ -implanted samples. Certainly one contribution to this difference is the difference in the reflectivity (57% for PF $_5$ vs 51% for BF $_3$), resulting in $\sim$ 17% more energy being absorbed in the BF $_3$ -implanted samples than in the PF $_5$ -implanted samples. Other contributions could possibly come from the differences in the thermal properties which probably exist between samples implanted with the two different species.

1. D. H. Lowndes et al., *Appl. Phys. Lett.* 41, 938 (1982).

2. R. T. Young et al., *Appl. Phys. Lett.* 43, 666 (1983).

TEMPERATURE-DEPENDENT REFLECTIVITY AND TRANSMISSION MEASUREMENTS OF SEMICONDUCTORS

G. E. Jellison, Jr. L. K. Craven¹
H. Burke²

To understand fundamental aspects of pulsed-laser annealing, accurate knowledge of the

optical properties of semiconductors at elevated temperatures is required. It is of particular interest to know these quantities accurately at wavelengths corresponding to common laser lines. Unfortunately, the data that have been available have either not been sufficiently accurate or have not been extended to high enough temperatures.

In response to the need for these data, we have constructed a system for accurate measurements of the reflectivity (R), the transmission (T), and the incident light intensity (i) simultaneously for temperatures up to 1000°C. The incident light sources are common cw lasers (Ar⁺ ion: 458, 488, and 514 nm; HeNe: 633 and 1152 nm). Because part of the incident beam is split off and measured continuously, an accurate normalization of R and T is obtained. The entire experiment is computer controlled, and R and T can be measured to an accuracy of 0.1% relative to the room temperature value.

In Fig. 3.24, we show the reflectivity of silicon as a function of temperature using the HeNe laser (633 nm). As can be seen, the data can be well represented by a linear expression,

$$R(T) = R_0 + aT, \quad (1)$$

where $R_0 = 0.347$ and $a = 4.6 \times 10^{-5} \pm 0.2 \times 10^{-5}$. This value corresponds well to values determined

Fig. 3.24. The reflectivity for Ge and Si as a function of temperature at $\lambda = 632.8$ nm.

previously by other authors for measurements at lower temperatures. We also show the reflectivity at 633 nm for germanium in Fig. 3.24. As can be seen, the simple linear expression is no longer valid. This is because the direct band gap of germanium is 2.2 eV at room temperature and moves to lower energies with increasing temperature. On the other hand, the lowest direct gap in silicon is 3.4 eV at room temperature, well above the HeNe laser line.

1. Oak Ridge Associated Universities research trainee from The University of Tennessee, Knoxville, Tenn.

2. Great Lakes Associated Colleges student from Earlham College, Richmond, Ind.

TIME-RESOLVED REFLECTIVITY MEASUREMENTS OF SILICON DURING PULSED EXCIMER LASER IRRADIATION

G. E. Jellison, Jr. D. H. Lowndes
R. F. Wood

Time-resolved measurements have been used recently by several groups to study the physical mechanisms of pulsed-laser annealing of semiconductors and to monitor the time evolution of transient carrier densities, temperature profiles, and temperature gradients on the ns to fs time scales. Common difficulties with all measurements of this type are the limitations on accuracy caused by spatial inhomogeneities in the laser pulses, by large pulse-to-pulse variations in the pulse energy density, and by noise inherent in the detection systems.

Several improvements have recently been made in our measurement system to allow accurate measurements of the reflectivity (on the nanosecond time scale) and the pulse energy density. These improvements include (1) the use of an ultra-violet excimer laser with excellent pulse-to-pulse reproducibility and spatial homogeneity of the energy density; (2) digital data acquisition, including recording of the energy density of individual laser pulses; and (3) use of energy-discriminated signal averaging, which results in enhanced signal-to-noise ratio without significant deterioration of rise and fall time.

The reflectivity of silicon versus time during and after pulsed irradiation with an excimer (KrF) laser is shown in Fig. 3.25 for energy densities below and just above the melting threshold. Also shown in Fig. 3.25 for comparison is the time profile of the laser pulse. For all energy densities shown, the reflectivity begins to rise when the laser pulse turns on and continues to rise monotonically to ~42% before it goes into the high-reflectivity phase (this value corresponds to crystalline silicon at the melting point).¹ The lowest energy density shown does not produce a high-reflectivity phase, while the three intermediate energy densities produce reflectivity jumps less than that of the highest energy density shown, indicating incomplete melting (over the first 200 Å for these energy densities).

It is also possible to determine the final crystallization front velocity from the falling

Fig. 3.25. The time-resolved reflectivity of silicon during pulsed irradiation with an excimer (KrF, 248 nm) laser. The dotted line indicates the time profile of the laser pulse in arbitrary intensity units. The numbers in the upper right corner indicate the energy density of the various laser pulses in J/cm^2 .

edge of the reflectivity signal, since the probe laser light will begin to detect the moving liquid-solid interface when this interface is within $\sim 200 \text{ \AA}$ of the surface. Calculations of the reflectivity versus liquid film thickness for thicknesses up to about two skin depths indicate an approximately linear relationship. Such measurements of this crystallization front velocity indicate that it is $3.5 \pm 0.5 \text{ m/s}$ for energy densities greater than $\sim 1 \text{ J}/\text{cm}^2$; these results are in agreement with melting model calculations² and are consistent with the time-resolved conductivity measurements taken using ruby laser irradiation by Galvin et al.³

1. G. E. Jellison, Jr., L. K. Craven, and H. H. Burke, "Temperature-Dependent Reflectivity and Transmission Measurements of Semiconductors," this report.

2. R. F. Wood and G. E. Giles, *Phys. Rev. B* 23, 2923 (1981).

3. G. J. Galvin et al., *Phys. Rev. B* 27, 1079 (1983).

STRESS EFFECTS OF RAMAN LINE POSITION DURING PULSED-LASER ANNEALING¹

G. E. Jellison, Jr. R. F. Wood

It has been accepted for some time that the results of pulsed-laser irradiation of silicon in the ns regime can be explained primarily in terms of a classical, but complex, heat-flow problem, and that annealing takes place by a melting and rapid epitaxial regrowth mechanism.² Compaan et al.,³ however, measured a phonon frequency shift of -13 cm^{-1} from Raman scattering

measurements, which corresponds to $\sim 470^\circ\text{C}$, if only temperature effects on the phonon frequency are included.

In a recent series of time-resolved x-ray experiments, Larson et al.⁴ found that the front surface region was severely strained for $\sim 1 \mu\text{s}$ after the beginning of the laser pulse. This strain was assumed to be uniaxial and a direct result of lattice heating but different from conventional tensile strain in that it results from a balancing of the stresses in the plane of the sample surface caused by thermal expansion and the clamping of the hot material due to the unheated sample outside the area of the laser beam. This stress will shift the phonon frequency.⁵ Hook's law gives $\epsilon = ST$, where ϵ is the strain tensor (2nd rank), S is the compliance tensor (4th rank), and T is the stress tensor (2nd rank). For cubic materials, it can be shown that only three of the elements of S are independent; they are often referred to as S_{11} , S_{12} , and S_{44} , which are dependent on temperature and pressure.

If it is assumed that the axis of symmetry for an uniaxially stressed material is the z direction, then the stresses along the x and y directions are the same, and no shear stresses exist. Furthermore, the elements of the compliance tensor determined for stresses along a $\langle 100 \rangle$ direction can easily be transformed for stresses along any other direction, such as a $\langle 111 \rangle$ direction.⁶ If the stress is a tensile stress (the material is either pulled or compressed in one direction only), then $T_{zz} = \tau$ and all other elements of T are 0. If the uniaxial stress is that found in pulsed-laser annealing⁴ or evaporated films,⁶ then $T_{xx} = T_{yy} = \tau$ and all other elements of T are 0.

It has been found that when a uniaxial tensile stress is applied to silicon, the optical phonon shifts its frequency and splits into a singlet and a doublet.⁵ Both the shift and the splitting are found to be proportional to the applied stress. We have performed a calculation similar to that found in Ref. 5 to determine the phonon frequency shift and splitting for the case of pulsed-laser-annealed silicon.

The results are shown for $\langle 100 \rangle$ silicon in Table 3.5(a) and for $\langle 111 \rangle$ silicon in Table 3.5(b). As can be seen from Table 3.5, the average frequency shift due to the stresses in the material is positive and can be as large as 15 cm^{-1} at 1400°C . Therefore, any attempt to relate the phonon frequency to the lattice temperature during pulsed-laser annealing will result in biasing the measurement to lower temperatures. The phonon frequency shifts of -13 cm^{-1} observed by Compaan et al. correspond to a lattice temperature of $\sim 800^\circ\text{C}$, not 470°C as they concluded.³ (Stress and other effects on the phonon frequency were mentioned as possibilities in Ref. 3, but not developed in detail.) Considering that the lattice temperature decreases very rapidly after the melt front has reached the surface, this temperature is consistent with melting-model calculations.

1. Summary of paper: p. 153 in *Energy Beam-Solid Interactions and Transient Thermal Processing*, ed. by J. C. C. Fan and N. M. Johnson North-Holland, New York, 1984.

2. R. F. Wood and G. E. Giles, Phys. Rev. B **23**, 2923 (1981).
3. A. Compaan et al., p. 23 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
4. B. C. Larson et al., Appl. Phys. Lett. **42**, 282 (1983).
5. E. Anastassakis et al., Solid State Commun. **8**, 133 (1970).
6. R. W. Vook and F. Witt, J. Appl. Phys. **36**, 2169 (1965).

Table 3.5. Phonon frequencies for pulsed-laser-annealed silicon, showing the effects of stress. The value of the stress shown in the table for each temperature is the resultant stress in the x-y plane from the laser heating. The quantity $\omega_0(T)$ indicates the phonon energy when only temperature effects are considered, while the columns under "singlet" and "doublet" also contain the stress contribution to the phonon frequency.

Temperature (°C)	Stress (GPa)	Phonon energies (1/cm)		
		$\omega_0(T)$	Singlet	Doublet
<u>(a) <100></u>				
0	0.0	522.3	522.3	522.3
200	-0.100	518.3	519.9	519.3
400	-0.222	513.4	517.2	515.7
600	-0.352	507.8	514.2	511.7
800	-0.484	501.6	510.7	507.2
1000	-0.613	494.7	506.8	502.2
1200	-0.736	487.1	502.4	496.8
1400	-0.850	478.9	497.6	490.7
<u>(b) <111></u>				
0	0.0	522.3	522.3	522.3
200	-0.104	518.3	518.9	519.9
400	-0.233	513.4	515.0	517.1
600	-0.369	507.8	510.5	513.9
800	-0.508	501.6	505.5	510.4
1000	-0.645	494.7	499.9	506.4
1200	-0.776	487.1	493.9	502.0
1400	-0.899	478.9	487.3	497.1

A TIME-RESOLVED ELLIPSO-METER

G. E. Jellison, Jr.

With the advent of lasers with nanosecond to femtosecond pulse widths, it is now possible to probe the interaction of light with condensed matter on these time scales. An important class of experiments to examine phenomena on time scales less than ~100 ns involves the interaction of the solid with two laser beams: (1) an intense "pump" beam and (2) a weaker "probe" beam. Usually, only the reflectivity and/or the transmission is

determined. One possible extension of these experiments is to include a compensator and/or polarizers to get additional information about the reflected light.

In an ellipsometric experiment, one is interested in measuring the quantities ψ and Δ , where

$$r_p/r_s = \tan\psi e^{i\Delta}; \quad (1)$$

the quantities r_p and r_s represent the Fresnel reflection coefficients for light polarized parallel and perpendicular to the plane of incidence, respectively. Often, the related ellipsometric parameters N , S , and C are measured, where

$$N = \cos 2\psi \quad (2a)$$

$$S = \sin 2\psi \sin \Delta \quad (2b)$$

$$C = \sin 2\psi \cos \Delta \quad (2c)$$

Here, an ellipsometer which is capable of measuring one of the related ellipsometric parameters N , S , or C as a function of time is described. The ellipsometer is of the standard polarizer-compensator-sample-analyzer type, where the analyzer is a Wollaston prism and the light source is a cw laser. Since the Wollaston prism spatially separates light polarized in one direction from light polarized perpendicular to it, it is possible to detect the intensities of both polarizations I_1 and I_2 simultaneously. Therefore, if the ellipsometer is properly aligned, the function

$$F = (I_1 - I_2)/(I_1 + I_2) \quad (3)$$

is equal to either N , S , or C , depending upon the alignment of the various optical elements.

Because there are no moving parts to the ellipsometer, the time resolution of the device is limited only by the rise time of the photodetector and the digitization rate of the recorder. With fast p-i-n diodes and the fastest waveform digitizers available, a time resolution of 1 ns is possible. With a streak camera acting as both detector and digitizer, time resolutions of ~2 ps are possible. This ellipsometer scheme has three added advantages: (1) in calculating the function F , all fluctuations in the probe beam intensity are normalized; (2) it is possible to monitor continuously any of the functions N , S , or C without relying on pump-and-probe techniques; and (3) the system is achromatic, with the exception of the compensator; a Babinet-Soliel compensator is used to facilitate changing to other wavelengths.

A detailed analysis of the errors introduced into F by misalignment of the optical components has been performed, and a scheme for accurately setting the alignment of the optical components has been determined. Also, the possible errors introduced by sample roughness and/or depolarization effects are considered. This technique is now being used to perform time-resolved ellipsometric measurements on excimer laser-irradiated silicon.

SIMULATION OF ANTIREFLECTION COATINGS FOR SOLAR CELLS

G. E. Jellison, Jr.

A computer code has been written to calculate the effect of antireflection (AR) coatings on solar cell performance. In this calculation, the internal quantum efficiency for a p-n junction solar cell is determined, using the emitter surface recombination velocity (S_e) and the base diffusion length (L_b) to simulate different quality cells. Two different solar cells are used: cell 1 has good integrated quantum efficiency with $S_e = 5 \times 10^4$ cm/s and $L_b = 600$ μ m, while cell 2 has a poor IR and UV response, simulated by reducing L_b to 50 μ m and by increasing S_e to 1×10^7 cm/s.

The total current density collected from a solar cell with an AR coating is given by

$$I_{\text{tot}} = q \int_0^\infty F(\lambda) \cos \theta \eta(\lambda) [1 - R(\lambda, \theta)] d\lambda, \quad (1)$$

where $F(\lambda)$ is the solar spectrum (given in units of photons/cm²-s per unit wavelength), q is the charge of the electron, $\eta(\lambda)$ is the internal quantum efficiency of the solar cell, $R(\lambda, \theta)$ is the reflectivity of the cell with the AR coating, and θ is the angle of incidence of the sunlight onto the solar cell.

If there are N layers to the AR coating, then the reflectivity

$$R = f[\theta, \lambda, d_1, \dots, d_N, n_1(\lambda), \dots, n_N(\lambda), k_1(\lambda), \dots, k_N(\lambda), n_{\text{Si}}(\lambda), k_{\text{Si}}(\lambda)], \quad (2)$$

where d_i is the thickness of the i th layer, n is the index of refraction, and k is the extinction coefficient (usually 0 for AR coatings). Because of dispersion, n and k of all layers and the silicon itself will be functions of the wavelength of light, which must be included to give an accurate value of the reflectivity of the solar cell.

We have incorporated into our calculations the dispersion relations (wavelength dependence of the index of refraction) of 12 different materials found in the literature: SiO_2 , MgF_2 , Ta_2O_5 (2 sets of values), TiO_2 (4 sets of values), Al_2O_3 (2 sets of values), Si_3N_4 , and ZnS . Note that more than one dispersion relation was used to simulate films of Ta_2O_5 , TiO_2 , and Al_2O_3 . A 1.5-nm SiO_2 film was assumed to exist between the AR coating and the Si surface. We have also performed the simulations for four different illumination spectra, corresponding to AMO and AM1.5 (the solar spectrum where the light has passed through 0 and 1.5 earth atmospheres, respectively), and to an ELH lamp early and late in its life. (The ELH lamp is a commonly used solar simulator with a more peaked spectrum than the sun.)

In discussing the quality of AR coatings, the percent gain is generally used as the quality factor; that is, the total current collected/current collected with no AR coating [$F(\text{no AR})$]. Although

this quantity is useful from an experimental view, it gives no indication of how much more improvement is possible. For this reason, the quantity total current/maximum current ($= F_{\text{max}}$) is used, knowing that a value of 1 is the highest obtainable.

From the calculations, the following conclusions can be drawn. (1) The optimum thickness of a single-layer coating is dependent on the type and quality of the film deposited, on the solar cell being irradiated, and on the illumination spectrum used. As an example, if a single-layer Si_3N_4 coating is used, the maximum current is obtained with a 73-nm film, resulting in $F_{\text{max}} = 0.901$ for cell 1 irradiated with AMO; on the other hand, if cell 2 is irradiated with an ELH lamp late in life, the optimum film thickness is 79 nm and $F_{\text{max}} = 0.960$. (2) Two-layer coatings allow the solar cell to collect 2-7% more usable light, where the optimum thicknesses of the two films and F_{max} are dependent on the internal quantum efficiency of the solar cell spectrum. In addition, the F_{max} from two-layer coatings is less sensitive to errors in film thicknesses than are single-layer coatings. Three-layer coatings were also simulated and were found to give only minor improvement to the collected current over two-layer coatings. (3) The dependence of the collected current on the actual film thickness is quite small for film thicknesses within ~ 5 nm of the optimum. For example, a 5-nm error in the optimum film thickness of an Si_3N_4 film on cell 1 illuminated with AMO results in decreasing F_{max} to 0.898, whereas the same error for cell 2 illuminated with the ELH lamp late in life yields $F_{\text{max}} = 0.954$, twice the decrease of the previous example [compare item (1)]. (4) The quality of the AR coating film in terms of its refractive index versus wavelength is clearly very important. For a single-layer TiO_2 film on cell 1 illuminated with AMO, the optimum thickness varies from 63.7 to 75.2 nm and F_{max} from 0.868 to 0.891, depending on the optical properties of the film.

RADIAL CONCENTRATION GRADIENTS IN HPGe CRYSTALS

T. W. Raudorf¹ G. E. Jellison, Jr.

Some high-purity germanium (HPGe) crystals grown for x-ray and gamma-ray detectors show substantial radial carrier concentration gradients, and devices made from such crystals invariably exhibit charge carrier trapping. The radial gradient appears to originate from deep rather than shallow levels; therefore, a deep-level transient spectroscopy (DLTS) study was performed to determine the origin of the radial concentration gradient and the trapping.

Two 57-mm diameter crystals (HP1185 and HP71T) have been examined in this study. Three DLTS samples were fabricated from the center (A), halfway between center and edge (B), and the edge (C) of a wafer 2 mm thick taken from each of the two crystals. The hole concentrations of each sample were determined from Hall-effect measurements at 77 K and are shown in Table 3.6. Also shown in Table 3.6 are the concentrations of individual defects (in arbitrary units) determined

Table 3.6. The concentration of holes (in units of $1/\text{cm}^3$) and various defects (in relative units) found in two high-purity germanium samples. Sample A is taken from the center of the crystal, and sample C is taken from the edge. Sample B (not shown) was taken between samples A and C and showed hole and defect concentrations similar to those of sample A.

Concentrations	HP1185		HP71T	
	A	C	A	C
Holes ($\times 10^9/\text{cm}^3$)	7.6	16.8	25	51
Defects (relative units)				
Cu ²⁻		0.389	0.059	0.421
Cu-H(i)		1.000	0.374	1.000
G	0.516	0.316	0.011	
V-H	0.453	0.263	0.034	
Cu-H(ii)		0.642	0.338	0.558
Cu ⁻		0.558	0.081	0.363

from DLTS measurements; the identity of each defect will be described below. Sample B is not shown in each case, because the hole concentration, as well as the concentration of individual defects, was nearly the same for sample B as for sample A. Sample HP1185A contains two defects commonly observed in p-type HPGe material: G, which has been previously described²⁻⁵ but is of unknown origin, and V-H, which has been attributed to the divacancy-hydrogen complex that occurs commonly in HPGe, particularly in dislocation-free material.⁵ Note that there are no defects associated with copper in this sample. By contrast, the DLTS spectrum of specimen HP1185C has a more complicated structure. Four defects are present, which originate from doubly ionized substitutional copper (Cu²⁻), two copper-hydrogen complexes [Cu-H(i) and Cu-H(ii)], and singly ionized substitutional copper (Cu).²⁻⁵ The G and H-V defects appearing in HP1185A are clearly present in HP1185C, but their concentrations are less than in HP1185A. The reduction in concentration of these two defects has been observed previously in HPGe when copper is introduced.² The reduced concentration of the V-H level is probably due to the rapid annihilation of vacancies by interstitial Cu atoms,³ while the G defect is probably linked to the occurrence of vacancies in the germanium crystal because of its reduced concentration when copper is present. We propose that it is this defect that makes dislocation-free material useless for detector fabrication, rather than the V-H level as previously reported.^{3,5} At normal detector operating temperatures (~80 K), the V-H defect has an emission time constant of only ~10 ns, which is too fast to cause significant hole trapping and consequent degradation of devices fabricated from dislocation-free material. On the other hand, the G level has a measured

activation energy of 142 meV and an emission time constant of ~0.35 ms at 80 K, and it is much more likely to cause trapping in nuclear radiation detectors than the V-H level. One or two observations should be made concerning the HP1185B sample. Its DLTS spectrum did indicate a weak presence of copper; in particular, the Cu-H(i) level appeared but with only half the concentration of the G level. However, the V-H level concentration decreased and appeared as a shoulder on the Cu-H(ii) line, as normally is observed even when only a little copper is present.

On the basis of the DLTS spectra of the three samples from HP1185 it is apparent that the radial gradient in carrier concentration was caused by the presence of copper. The actual carrier concentration due to copper in HP1185C at 77 K is $9.2 \times 10^9/\text{cm}^3$, and most of the copper exists near the outer surface of the crystal.

The results of DLTS measurements on crystal HP71T are also shown in Table 3.6. In sample HP71TA substitutional copper and copper-hydrogen complexes are present, but not large concentrations of G and V-H levels. The low concentration of interstitial copper is expected, since it rapidly annihilates the vacancy-hydrogen (V-H) complex, forming a copper-hydrogen complex.³ If the G level is also due to some sort of vacancy complex, then it too should be annihilated by interstitial copper. Possibly interstitial copper can transform the V-H and G level into the Cu-H(ii) and the Cu-H(i) levels. The sample of HP71TC has the same character as that of HP71TA, but all levels are more dense, indicating that much more copper in its substitutional and interstitial form was present in that sample. Again the difference in carrier concentrations of $2.6 \times 10^{10}/\text{cm}^3$ gives the carrier excess due to copper at the edge of the crystal. Specimen HP71TB had a DLTS spectrum very similar to that of HP71TA. This demonstrates that the radial gradient in carrier concentration of crystal HP71T is also due to copper, most of which is positioned near the outer edge of the crystal.

1. Guest scientist from EG&G Ortec, Oak Ridge, Tenn.
2. T. W. Raudorf, G. E. Jellison, Jr., and R. C. Trammel, *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 120.
3. A. O. Ewaraye, R. N. Hall, and T. J. Soltys, *IEEE Trans. Nucl. Sci.* NS-26, 271 (1979).
4. E. Simoen et al., *IEEE Trans. Nucl. Sci.* NS-29, 789 (1982).
5. E. E. Haller et al., *IEEE Trans. Nucl. Sci.* NS-26, 265 (1979).

APPLICATION OF PULSED-LASER PROCESSING IN THE FABRICATION OF Ge NUCLEAR RADIATION DETECTORS¹

D. H. Lowndes T. W. Raudorf²

It has been established that noninjecting thin (<1000 Å) p⁺ contacts can be produced on very high purity germanium (HPGe) for use in nuclear radiation detectors by either an evaporated metal

Schottky barrier or by B implantation. However, all the noninjecting n^+ contacts formed on HPGe have shortcomings related to their method of formation. Low-temperature ($\sim 300^\circ\text{C}$) Li diffusion produces a layer that is quite thick (normally a fraction of a millimeter), which precludes its use, in many cases, as either an entrance or an exit window for nuclear radiation. Thin n^+ contacts have also been fabricated on HPGe detectors by using thermally evaporated amorphous (a) Ge³ and by P ion implantation.⁴ However, a-Ge produces a contact with a large reverse leakage current, in comparison with Li-diffused contacts, while P implantation (unlike the B used for a p^+ contact) requires a relatively high-temperature ($>400^\circ\text{C}$) annealing step for electrical activation. Elevated temperature processing must normally be avoided in the fabrication of HPGe devices because of the risk of i -diffusion of Cu, a known hole trap with a large diffusion coefficient. The reverse leakage current obtained via P implantation, while better than for a-Ge, is still worse than for devices utilizing a Li-diffused n^+ contact.

We recently reported⁵ the first fabrication of a thin, non-injecting n^+ contact and a high-quality n^+ - p junction with very low reverse leakage current on a HPGe detector, using a pulsed-laser process that requires no subsequent heating of the bulk HPGe. The method used was in-diffusion of P from the liquid tributylphosphate⁶ (TBP, $\text{C}_{12}\text{H}_{27}\text{O}_4\text{P}$), in which the HPGe samples were immersed (after cleaning) during irradiation by a pulsed ruby laser (694-nm wavelength, 25-ns pulse duration). TBP, containing $>2 \times 10^{21}/\text{cm}^3$ P atoms in solution, acts as a rich surface source of P during the brief period of pulsed-laser melting of the near-surface region; TBP is almost completely transparent to ruby laser radiation so that the results obtained are nearly independent of the depth of the liquid layer.⁶ In our experiments, HPGe samples were irradiated with from 1-5 ruby laser pulses at energy densities $E_L = 0.5$ - 1.0 J/cm^2 .

In Figure 3.26 we compare the forward and reverse current characteristics obtained for diodes that were fabricated following two different sets of ruby laser irradiation conditions. As shown, three laser pulses at $E_L = 0.96 \text{ J/cm}^2$ resulted in an n^+ - p junction with very low reverse leakage current and no sign of breakdown of the n^+ contact up to 50 volts reverse bias; such an n^+ - p junction would be suitable to make a useful commercial radiation detector. Subsequent testing of this diode as an alpha-particle detector revealed a strong alpha particle signal even at zero bias, indicative of a good n^+ - p junction with the built-in voltage alone sufficient for charge collection. The fact that this diode functioned as an alpha detector also indicates that the n^+ region is thin, probably of order $0.25 \mu\text{m}$, in agreement with preliminary secondary ion mass spectroscopy measurements.

1. Summary of paper to be published.
2. Guest scientist from EG&G Ortec, Oak Ridge, Tenn.
3. W. L. Hansen and E. E. Haller, *IEEE Trans. Nuc. Sci.* NS-24, 61 (1977).

Fig. 3.26. Forward and reverse current characteristics at $T \sim 77 \text{ K}$ for two n^+ - p diodes fabricated on high-purity p -type Ge ($|N_D - N_A| = 9 \times 10^{19}/\text{cm}^3$), following three ruby laser pulses through tributylphosphate liquid dopant at 0.71 J/cm^2 or 0.96 J/cm^2 .

4. C. S. Hubbard, E. E. Haller, and W. L. Hansen, *IEEE Trans. Nuc. Sci.* NS-24, 161 (1977).
5. D. H. Lowndes and T. W. Raudorf, p. 125 in *Conference on Lasers and Electro-Optics Tech. Digest*, Optical Society of America, 1984.
6. R. Stuck et al., *Appl. Phys. Lett.* 38, 715 (1981).

EFFECTS OF PULSED EXCIMER AND CO_2 LASER IRRADIATION ON THE WIDE BAND GAP SEMICONDUCTORS ZnO AND SiC

D. H. Lowndes F. A. Modine
E. Sonder Y. Chen
W. J. Choyke¹ J. M. Williams

Both ZnO and SiC are wide band gap ($E_g > 3 \text{ eV}$) semiconductors having relatively high melting points (~ 2000 and 2700°C for ZnO and SiC , respectively). However, both are volatile and sublime at lower temperatures (~ 1700 and 2000°C for ZnO and SiC , respectively). In pure form, ZnO and SiC are transparent at visible wavelengths and thus are not candidates for pulsed-laser processing (PLP) using visible or near-infrared lasers.

However, both absorb strongly ($\alpha > 10^5 \text{ cm}^{-1}$) in the near ultraviolet (UV), and both have reststrahlen absorption bands near $10 \mu\text{m}$ ($\alpha \sim 10^2$ and 10^3 cm^{-1} for ZnO and SiC, respectively). Moreover, the coupling of laser radiation to these materials is fundamentally different for CO_2 and excimer lasers: UV radiation couples to the electronic system via transitions across the band gap, while CO_2 radiation couples directly into the crystal lattice.

We recently initiated a study of PLP of ZnO and SiC, in order to compare the effects of CO_2 and excimer lasers and to address several fundamental issues that are of concern in connection with PLP of wide band gap compound materials in general. The mechanism for pulsed-laser annealing of ion-implanted silicon (and other narrow-gap semiconductors) is known to be thermal melting followed by rapid liquid-phase epitaxial regrowth from the crystalline substrate beneath. It is important to know whether a similar epitaxial-regrowth process occurs in wide band gap semiconductors and whether repair of implantation lattice damage and activation of implanted or deposited dopant ions can be accomplished by PLP. Other concerns include whether PLP will cause preferential loss of one constituent (such as occurs for GaAs) and whether wide band gap materials have sufficient thermal stress resistance to avoid microfracture in the presence of large pulsed-laser-induced temperature gradients.

The lasers used in this study were a pulsed KrF excimer laser (248 nm, $\sim 35 \text{ ns}$ FWHM pulse duration) at energy densities E_L , ranging from 0.5 – 2.0 J/cm^2 , and a pulsed CO_2 laser ($10.6 \mu\text{m}$, $\sim 60 \text{ ns}$ FWHM) with $E_L = 0.3$ – 6.0 J/cm^2 . All the SiC specimens were of the 6H crystalline poly-type (including undoped, nitrogen-, and aluminum-doped specimens); both poly- and single-crystalline samples of ZnO were used.

In situ time-resolved measurements of the reflectivity of a low-power 633-nm HeNe probe laser beam from the surfaces of ZnO and SiC samples were used to determine whether pulsed-laser irradiation induces melting on the nanosecond time scale, by detection of the different reflectivity of the molten phase. Experiments using the KrF laser in air at 1 atm pressure revealed no large jump to a high-reflectivity phase (such as occurs for silicon) for either SiC or ZnO. Instead, a small ($\sim 10\%$) increase in reflectivity was observed for SiC at $E_L = 0.8 \text{ J/cm}^2$ (with the duration proportional to laser E_L at higher E_L), together with bright luminescence during the early part of the period of increased reflectivity. Similar measurements were carried out for SiC under 80 atm Ar pressure in the expectation that a high-pressure ambient would favor melting rather than sublimation or vaporization. In this case, the first laser shot on a virgin SiC specimen did induce a 50–75% reflectivity increase (for a period of $\sim 150 \text{ ns}$ at $E_L = 1.3 \text{ J/cm}^2$), still accompanied by bright luminescence during the first 50 ns. However, the final reflectivity of the SiC sample surface was higher than that initially, and time-resolved reflectivity measurements during subsequent laser shots on the same sample revealed no high-reflectivity phase, but only an increasingly bright luminescence signal

and the higher value of the final surface reflectivity.

No reflectivity increase was detectable for ZnO, for which intense luminescence completely dominated the time-resolved optical signal, even at low E_L . Postirradiation inspection showed that a single laser shot (either CO_2 or excimer) vaporized the ZnO near-surface region, resulting in the loss of most of the oxygen and producing an easily visible and highly conducting metallic film approximately $0.1 \mu\text{m}$ thick.

These experiments provide evidence (1) that melting does occur for SiC but not for ZnO (which is vaporized) and (2) that PLP is accompanied by irreversible changes in the near-surface region for both SiC and ZnO.

For ZnO, microfracture on the length scale of 10 – $20 \mu\text{m}$ was always observed following PLP by either excimer or CO_2 lasers. For SiC, similar microfracture was observed following pulsed CO_2 laser irradiation, but optically visible microfracture was not apparent following pulsed excimer laser irradiation. (This difference for SiC may be a consequence of the comparatively poor spatial homogeneity of the CO_2 laser beam on the $\sim 10\text{-}\mu\text{m}$ length scale.) However, ion backscattering measurements (Fig. 3.27) showed that KrF excimer laser irradiation of SiC produced a highly disordered near-surface layer, on a depth scale much shorter than optical wavelengths, and with the depth of the disordered layer increasing with laser E_L . As shown in Fig. 3.27, the extent of disorder does not reach that expected for a completely amorphous near-surface layer, but does correspond to very fine-grained polycrystalline SiC (perhaps with some amorphous material mixed in). Backscattering measurements also indicated that the Si/C ratio remains approximately constant in this disordered near-surface layer.

The differences in microfracture behavior for SiC and ZnO, when using the relatively homogeneous radiation provided by the KrF excimer laser, appear to result from their different

Fig. 3.27. Backscattering yield vs depth for 6H-SiC specimens following KrF excimer laser irradiation at several pulsed energy densities.

thermal conductivities and their resulting different resistances to thermally induced stress, as is illustrated in Table 3.7. (The thermal stress resistance R of a material is proportional to its thermal conductivity and inversely proportional to its linear coefficient of thermal expansion.) The low thermal diffusivity of ZnO also results in large temperature gradients in the near-surface region, during the time interval when pulsed-laser radiation is being absorbed (Table 3.7).

Table 3.7. Melting temperature (T_m), thermal conductivity (k), linear thermal expansion ($\Delta L/L$), relative thermal stress resistance (R), and absorption coefficient (α) for Si, SiC, and ZnO. The thermal parameter values are averages between room temperature and T_m .

	Si	SiC	ZnO
T_m (K)	1683	3100	2250
k (W/cm-K)	0.54	0.5	0.055
$\Delta L/L$ (%)	0.6	1.7	1.4
$R = [k/(\Delta L/L)]$	0.9	0.29	0.039
α (cm ⁻¹)			
UV	>10 ⁶	10 ⁵	10 ⁵
IR	-	10 ³	10 ²

Direct doping of SiC by laser-induced diffusion of electron beam evaporated boron and aluminum films was also attempted. However, postirradiation sheet electrical properties measurements revealed no electrical activation in the near-surface layer; this result is not surprising in view of the highly disordered nature of this region. Pulsed CO₂ laser annealing of Cr-ion-implanted SiC resulted in both Cr ion redistribution and some annealing of ion implantation lattice damage, but very substantial lattice damage remained. Thus, pulsed UV or infrared laser irradiation of SiC has not so far resulted in single-crystalline regrowth.

1. Westinghouse Research Laboratories and University of Pittsburgh, Pittsburgh, Pa.

TIME-RESOLVED STUDIES OF ULTRARAPID SOLIDIFICATION OF HIGHLY UNDERCOOLED MOLTEN SILICON FORMED BY PULSED-LASER IRRADIATION¹

D. H. Lowndes G. E. Jellison, Jr.
R. F. Wood R. Carpenter²

We recently reported new results of nano-second resolution time-resolved optical reflectivity measurements taken during pulsed excimer (KrF, 248 nm) laser irradiation of Si-implanted amorphous (a) silicon layers which, together with model calculations and postirradiation TEM measurements, have allowed us to study both the

transformation of a-Si to a highly undercooled liquid (ℓ) phase and the subsequent ultrarapid solidification process.

The melting temperature (T_m) of a-Si is apparently some 200–300 K below the melting temperature ($T_c = 1683$ K) of crystalline (c) Si;³ thus, molten ℓ -Si that is undercooled by hundreds of Kelvins can be prepared by pulsed-laser melting of a-Si layers using laser pulses of low-energy density (E_L). By melting only partially through an a-Si layer, the undercooled ℓ -Si remains isolated from the c-Si beneath because of the low thermal conductivity of the remaining a-Si. This makes it possible to study the subsequent process of re-solidification from a highly undercooled melt under relatively well-controlled experimental conditions.

A number of improvements were made in both experimental and calculational techniques for our current studies. Three different thicknesses (approximately 90, 190, and 440 nm) of a-Si layers were used. An excimer laser (~35-ns FWHM pulse duration) provided a highly homogeneous and reproducible pulsed light source while minimizing differences in the optical properties of the a-, ℓ -, and c-phases of Si (a significant simplification for model calculations). In situ E_L monitoring of every laser pulse reduced the uncertainty in individual E_L measurements to $\pm 2\%$. A Tektronix 7912AD transient digitizer (time constant ~1 ns) interfaced to a laboratory computer system was used to record and store both the time-resolved reflectivity (R) signals and sample laser pulses with 512-point resolution on the time axis.

As a result of these improvements, we can now accurately monitor the heating of a-Si during absorption of the initial part of a laser pulse while still in the solid phase. Together with measurements of the precise time t_m of the onset of melting during the laser pulse, measurements in the solid phase provide data which can be used to determine the thermal conductivity k_a of a-Si. For example, model calculations^{4,5} show that experimental data for t_m (E_L) imply a temperature-averaged $k_a \approx 0.02$ W/cm-K, compared with k_c (300 K) = 1 W/cm-K for c-Si.⁴

The importance of the thermal isolation provided by the unmelted a-Si remaining beneath any molten layer of ℓ -Si is illustrated in Fig. 3.28, where the surface melt duration τ_s [duration of the high reflectivity phase (HRP)] is plotted v. E_L for three different a-Si layer thicknesses. The τ_s varies by a factor of 3 or more between the thinnest and thickest layers at the higher E_L values. Furthermore, τ_s does not increase monotonically with increasing E_L : model calculations show that both the plateau in τ_s for the 100-nm a-Si layer and the actual decrease (between 0.5 and 0.65 J/cm²) in τ_s for the 190-nm a-Si layer are due primarily to the increased rate of heat loss from the ℓ -Si that occurs when the melt front approaches the a-c interface.

Typical transmission electron micrographs⁶ following low E_L laser irradiation of a 500-nm-thick a-Si layer on a c-Si substrate reveal a region of fine-grained (FG) polycrystalline Si (μ -Si) at the surface, followed at increasing depth by the remaining a-Si, the a-c interface, and the c-Si substrate. Individual grains in

Fig. 3.28. Surface melt duration vs KrF excimer laser energy density for a-Si layers.

the FG region are quite small (~10 nm) and are randomly oriented and equiaxed, indicating that there is no preferred direction of crystal growth and strongly suggesting that bulk nucleation has occurred.^{4,5}

Our new optical measurements also appear to provide in situ time-resolved evidence of the beginning of bulk nucleation and crystallite growth very near the highly undercooled molten surface, while penetration of the melt front into the a-Si layer is still in progress. Figure 3.29 shows a series of R signals observed from a ~440-nm-thick a-Si layer, as a function of E_L . R was monitored using a low-power, cw HeNe probe laser, for which the optical skin depth in ordinary liquid Si would be about 9.6 nm at the probe's 633-nm wavelength. At the lowest E_L values, the R signal (Fig. 3.29) never achieves the flat-topped shape that is characteristic of

Fig. 3.29. Decaying time-resolved reflectivity signals associated with bulk nucleation.

the HRP associated with pulsed-laser melting of c-Si (see inset), but instead decays to lower values almost immediately. This decay we attribute to the occurrence of bulk nucleation within a few nanoseconds after melting has occurred in the highly undercooled melt that exists near the surface at low E_L . During this time, the optical properties of the region being observed are those of a "slush," a mixture of undercooled liquid and growing crystallites. With increasing E_L , the fall in R occurs later in the HRP (Fig. 3.29) and is of smaller magnitude; model calculations associate this with a prolonged duration for the slush region near the surface, brought about by a competition between bulk nucleation and remelting due to the release of latent heat. Finally, at about 0.44 J/cm², a flat-topped HRP is observed throughout the duration of surface melting, indicating that the temperature of the melt remains above the nucleation temperature throughout the shallow region sampled by the 633-nm probe beam, until a recrystallizing front returns to the surface by epitaxial regrowth from the polycrystalline silicon formed below.

Calculations of laser melting of a-Si layers can be "calibrated" by comparison with time-resolved reflectivity measurements and used to determine temperature profiles in the undercooled a-Si. Comparing these profiles with the solidification structures observed by transmission electron microscopy, we were able in our original calculations to simulate that bulk nucleation in the liquid occurs at a temperature approximately 50°C higher than T_d .^{4,6} These model calculations were greatly improved recently by the development of a new computer program based on an enthalpy formulation of the heat-flow and phase-change problems. This new formulation is described elsewhere in this progress report.⁷

1. Summary of paper: D. H. Lowndes et al., in Proceedings of the 17th International Conference on the Physics of Semiconductors (in press).
2. Arizona State University, Tempe, Ariz.
3. See complete reference list in Ref. 4.
4. D. H. Lowndes, R. F. Wood, and J. Narayan, Phys. Rev. Lett. 52, 561 (1984).
5. R. F. Wood, D. H. Lowndes, and J. Narayan, Appl. Phys. Lett. 44, 770 (1984).
6. J. Narayan and C. W. White, Appl. Phys. Lett. 44, 35 (1984).
7. R. F. Wood et al., "Modeling of Solidification Processes in Highly Undercooled Silicon and Germanium," this report.

IMPROVED GLOW DISCHARGE IMPLANTATION EQUIPMENT

R. D. Westbrook R. T. Young¹
R. F. Wood

Gas discharge ion implantation using a simple dc glow discharge is an effective and inexpensive way to implant shallow layers of doping elements into a semiconductor surface.² In contrast to conventional high-energy, high-current ion implantation systems, glow-discharge equipment provides

a low-cost means to implant large areas of material with a high-current (up to milliamps), low-energy (<5 keV) ion beam in a short (<5 min) time. Also, as the implanted layer is very shallow, it is ideally suited for solid state devices requiring very thin, high sheet conductivity emitter regions. We describe here the latest version of the gas discharge equipment developed at ORNL and discuss its operating characteristics.

A drawing of the ORNL equipment is shown in Fig. 3.30. The vacuum system operates from a 6" oil diffusion pump with a liquid nitrogen trap. The discharge chamber is a 6" i.d. Pyrex or quartz cylinder about 8" long containing a ring to hold the silicon anode; the anode is electrically connected to the outside of the chamber through a heavy spring-loaded tungsten wire. Wafers up to 5" in diameter can be accommodated. Gases containing the dopant atoms enter through the top plate and pass through a number of perforations in the glass anode ring to equalize flow into the discharge region of the chamber. The cathode electrode, which supports the sample, is made of stainless steel or Al and is fitted with guard rings to improve the uniformity of the electric field and charge transfer near the edge of the wafer. Guard rings are particularly useful at the higher plasma impedances (higher voltages, lower discharge currents) that are encountered when deep implantations are desired. A large-area cathode avoids the problem of falloff in charge transfer toward the outer 2-3 mm of a wafer. The voltage-regulated power supply can provide several milliamperes of current at voltages up to 10,000 volts and is connected to the chamber through a series resistance of 1 to 10 $M\Omega$. The implantation chamber is mounted in a laminar flow hood for increased cleanliness.

The semiconductor wafer to be implanted is mounted on the cathode and held down with a Teflon ring or Teflon screws. The system, with the

sample in place, is pumped to the 10^{-5} – 10^{-6} Torr range. The dopant gas (e.g., PF_5 or BF_3 for silicon implantation) is introduced into the chamber through a micrometer metering valve, and the rate is adjusted to give the proper discharge current density, which is a function of the pressure. Typical current densities range between 0.05 and 0.2 mA cm^{-2} , and most implants have been made at 1-2 kV. Implantation times of 1-4 min are typical, with a total charge transfer ranging from 0.003 to 0.06 C cm^{-2} , depending on the application intended.

Because there is no provision for mass separation in a simple glow discharge system, ions (e.g., BF_3^+ with BF_3 and PF_5^+ with PF_5 sources) other than the primary dopant species impinge on the wafer. We have no indication that the fluorine associated with these ions causes any deleterious effects.

After implantation, the samples can be annealed either by conventional thermal annealing or by laser annealing. Values of the sheet resistance and carrier concentration obtained by van der Pauw measurements on samples cut across the diameter of 2" boron-implanted wafers show variations which are essentially within the experimental error of the van der Pauw equipment. With the new system, four 2" wafers implanted simultaneously show the same excellent uniformity of sheet resistance and carrier concentration for samples from all four wafers. Additional evidence of the high degree of uniformity achieved with glow discharge implantation is provided by the consistency of values of the open circuit voltage, short circuit current, fill factor, and efficiency obtained from completed solar cells.

1. Present address: Energy Conversion Devices, Inc., Troy, Mich.
2. R. T. Young et al., *Appl. Phys. Lett.* 43, 666 (1983).

Fig. 3.30. Diagram of improved glow discharge implantation system.

COMPATIBILITY OF SURFACE TEXTURIZATION AND BEAM PROCESSING OF SOLAR CELLS

R. T. Young¹ R. D. Westbrook
R. F. Wood

The use of beam processing, especially pulsed-laser annealing, for junction formation in silicon with texturized surfaces was thought by many to be impossible, because the rapid melting and solidification of the surface cause a rounding of the pyramids, uneven junction formation, and even "punch-through" of the junction in some areas. Early work by Spire Corporation with e-beam annealing seemed to indicate that extensive rounding of the pyramids was unavoidable when melting occurred. More recently, early attempts at excimer laser annealing of ion-implanted texturized surfaces gave disappointing results. Nevertheless, the recent success of Spire in obtaining 18% AM1 solar cells on texturized surfaces convinced us that we should make a more careful study of the compatibility of texturization and beam processing. We report here on the present status of this study.

After texturization, the wafers were glow-discharge implanted with boron, and the cells were fabricated as fairly standard (for beam processing) number of parameters were investigated experimentally; while conditions have not yet been optimized, preliminary results do indicate that texturization and laser annealing are not incompatible. Table 3.8 shows results

Table 3.8. Solar cell parameters for laser-processed cells on texturized surfaces.

Sample	V_{oc} (mV)	I_{sc} (mA/cm ²)	FF	n (no AR)	Energy density (J/cm ²)
1	578	30.0	73.4	12.6	0.8
2	578	31.0	75.9	13.8	0.7
3	583	30.6	75.3	13.6	0.7
4	563	31.0	75.4	13.4	0.6
5	533	30.6	71.0	11.8	0.5

obtained for annealing of 1 Ω -cm n-type material with a ruby laser, diffuser plate, and substrate heating at 500°C. It is evident from this table that solar cells can be made on texturized silicon by beam processing. Although both open circuit voltage and fill factor are low, the current shows about the expected improvement due to texturization. The fill factors for control cells which were not texturized were about the same as those in the table. It is evident from the table that the cell parameters are quite sensitive to the energy density used for annealing. In the next few months we anticipate optimizing the beam processing of texturized cells to approximately the same extent we have been able to optimize the processing of cells with smooth surfaces.

1. Present address: Energy Conversion Devices, Inc., Troy, Mich.

SURFACE TEXTURIZATION OF SILICON WAFERS

R. D. Westbrook R. F. Wood

One method of reducing reflection losses from the surface of a solar cell is the selective etching or texturization of the front surface

before formation of the p-n junction. The etching process results in a surface consisting of micron-sized polyhedra. On a (100) surface, the faces of the tetrahedra form angles of about 57 deg to the surface, and light reflected from them is intercepted by other pyramids. Thus, the reflection loss is uniformly reduced throughout the solar spectrum. Texturization, followed by a single-layer antireflection coating, will reduce reflection losses to approximately 2-3%. Moreover, it has been suggested that, in addition to the minimization of reflection losses, some improvement of the current may be realized because long-wavelength photons are expected to be absorbed somewhat nearer the p-n junction on a texturized surface than they are on a smooth surface.

Since texturization often seems to be a black art rather than a science and since other laboratories are reluctant to supply large quantities of texturized wafers, we decided to investigate carefully the texturization process and adapt it to our needs.

We have found two acceptable texture etches, the choice depending upon the desired size of the tetrahedra. A commercial product, Transene solar cell etch 100, is a hydrazine-based etch and works well for obtaining relatively large pyramids of approximately 25-30- μ m base length. Hydrazine is a potentially hazardous material and must be handled accordingly. The etching process takes place at or near boiling temperature (~115°C) in a reflux apparatus under a chemical hood. Etching time is 5-15 min. The other etch is based on KOH, and several formulations appear to be satisfactory. These etches produce pyramids of 5-10- μ m base lengths at 80-100°C, require 30-60 min, and though slower are less hazardous than the hydrazine etches. We have built and/or purchased suitable equipment for processing quantities of various sized samples.

With either etchant, proper sample preparation is essential if acceptable results are to be obtained. In our procedure, the wafers are first thoroughly cleaned of all organic material and the native oxide removed with HF. Then the HF is displaced with alcohol, and without exposure to air the wafers are placed in the etchant. One of the heavier alcohols, such as isopropyl, stays on the wafer long enough to make the transfer to the etchant possible without air exposure. It appears that any growth whatsoever of oxide on the surface makes the etching process unpredictable. When a wafer has been successfully etched, scanning electron micrographs show the surface to be of very good quality as far as the definition and uniformity of the texturization are concerned.

4. TRANSPORT PROPERTIES OF SOLIDS

The constant changes in research emphasis which occur within the division, as problems in one area are solved and challenges in another are identified, are reflected by topics in this chapter. Research on fast ion transport is being gradually de-emphasized and being replaced by studies of transport across solid-solid interfaces. Likewise, research on properties of oxide ceramic systems, other than in varistor materials, is decreasing while increasing emphasis is given to transition-metal carbide and nitride ceramics. Research which emphasizes studies relevant to transport processes in solids are featured here. However, because the multidisciplinary nature of the problems requires a great deal of cooperative effort among various research groups, information pertinent to transport properties will be found in other chapters of this volume. Reports of related phenomena will be found, most especially in the chapters dealing with theory, preparation and characterization of research materials, and defects in solids.

Water that is easily adsorbed from the ambient atmosphere into the conduction layers of the β - and β' -aluminas has been demonstrated to degrade the electrolytic properties of these materials. The mechanisms and thermodynamics of hydration processes have been established, and a related process contributing to degradation has been observed; ambient CO_2 reacts with the water to form either NaHCO_3 or hydrated Na_2CO_3 scales and crust on the ceramic surface, further degrading the desirable properties of the surface and near-surface regions of the material. Finally, shell model calculations have been employed to obtain better agreement with experimental data than that obtained by others employing different computer codes to study structure and transport in Na β -alumina.

The measured impedances of metal-solid electrolyte interfaces show that the systems frequently do not exhibit the behavior of an ideal capacitor. A model for the frequency-dependent impedance of an interface is being developed. Although more work is required, the model does provide a physical basis for use of some equivalent circuits reported in the literature. Studies of the effects of interfacial space charge layers on ionic conductivities of composite materials have been initiated; use of the techniques of surface-enhanced Raman scattering to examine the Ag/AgCl interface and attenuated total reflection spectroscopy to obtain surface polariton dispersion data on Al_2O_3 have been successful.

Superconductivity investigations have continued to focus on the static and dynamic properties of flux lines (FL) in Type II superconductors and on their interactions with well-characterized defects. Studies of the

critical current and flux flow resistivity in niobium bicrystals identify the pinning of FL to be due to electron scattering by the grain boundary and the FL anisotropy in the grains. Small-angle neutron scattering studies in these samples under identical conditions reveal FL bending during transport current flow and suggest a means to explore more closely the spatial distribution of current in these materials. A model to account for the observed correlations between the flux-line lattice (FL) and the crystal lattice in terms of a weakly anisotropic penetration depth in V_3Si is presented. Form factor measurements of the FLL in V_3Si also provide an absolute determination of the temperature dependent penetration depth, which is examined here in the light of current theories. Studies of the fabrication of VN thin films (a member of the important family of superconductors with the BI structure) are presented along with investigations of the effect of ion damage and thermal annealing on this material. Examinations of metastable superconductors produced by laser quenching and sputtering have continued. Also reported here is a description of a magnetometer which complements existing low-temperature apparatus.

Research on the transition-metal carbides has emphasized determination of the electronic structure and transport properties. Optical and electrical properties measurements of TiC and ZrC proved to be generally similar, and the following conclusions could be drawn: transport parameters obtained from the two types of measurements agree quite well; free electron conduction is due to a single carrier with an effective mass near unity; and interband transitions contribute strongly to the reflectance spectra at low energies. A variety of electron spectroscopic techniques in ultrahigh vacuum were employed to determine the electronic structure of TaC; the experimental results agree very well with theoretical densities of states. Reported also is some recent work related to an investigation that was initiated to obtain a better understanding of the basic physics of varistors.

FAST-ION CONDUCTORS

IONIC CONDUCTION AND WATER DIFFUSION IN Li β -ALUMINA¹

J. C. Wang J. B. Bates
N. J. Dudney

The properties of Li β -alumina such as the c-lattice parameter, the activation energy for conduction, and the diffusivity of H_2O are exceptions to the trends set by other alkali-metal β -aluminas. In this work we review and analyze these results. It is concluded that all these may be attributed to the small size of the Li^+ ion.

The Beevers-Ross (BR) site in the conduction plane of β -alumina is surrounded by six oxygen ions of the neighboring spinel blocks. The distance from the BR site to these oxygen ions is about 2.8 Å, but the sum of the ionic radii

of Li^+ (0.6 Å) and O^{2-} (1.4 Å) is only 2.0 Å. It is therefore natural that the Li^+ ion in this region deviates away from the conduction plane. The electric field produced by all ions except the Li^+ ion in question was calculated and is shown in Fig. 4.1(a). Note that because most of the ions in the crystal are polarized by the field produced by other ions, the field shown in Fig. 4.1(a) is not the total field. The total electric field experienced by the Li^+ ion includes the contribution from the induced dipoles and is shown in Fig. 4.1(b).

As can be seen from Fig. 4.1(b), the electric field near the BR site tends to push a cation away from the conduction plane. The magnitude of this displacement depends mainly on the core-repulsive potential between the cation and the O^{2-} ions. It can be expected that half of the Li^+ ions will deviate toward one side and the other half toward the other side. The mutual coulomb interaction between the two Li^+ sublayers formed this way tends to pin the Li^+ ions to the

Fig. 4.1. Electric field experienced by a Li^+ ion in the plane containing the BR and anti-BR sites and perpendicular to the conduction layer in the ideal structure of Li β -alumina. The field produced by the monopoles of other ions is shown in Fig. 4.1(a), and the field produced by the inclusion of their induced dipoles is shown in Fig. 4.1(b).

spinel blocks and to push the spinel blocks farther apart. This may explain why the c-lattice parameter of Li β -alumina lies between those of Na and K β -alumina, even though the Li^+ ion is the smallest among the three.

The activation energies for conduction determined from slopes of the Arrhenius plots are 0.24, 0.14, and 0.28 eV for Li, Na, and K β -alumina, respectively. They have the same trend as that of the c-lattice parameter. To understand this, we notice that the low activation energy for conduction in Na β -alumina is due to the correlated motion of the $\text{Na}^+\text{-Na}^+$ pairs formed by the excess Na^+ ions. During this interstitialcy conduction process, the single Na^+ ions surrounding the $\text{Na}^+\text{-Na}^+$ pair also adjust their positions accordingly when one of the paired Na^+ ions moves out of the shared potential well to form a new pair in a neighboring well.² If the surrounding single Na^+ ions are not allowed to

adjust their positions, the activation energy for conduction is increased. This has been demonstrated by the result that the calculated activation energy for Na β -alumina is 0.14 eV when four Na^+ ions next to the $\text{Na}^+\text{-Na}^+$ pair are allowed to move, but becomes 0.26 eV when they are fixed at their BR sites.² In Li β -alumina, the deviation of single Li^+ ions from the conduction plane tends to restrict their motion to the pocket sites formed by O^{2-} ions of the spinel blocks. This pinning of the single Li^+ ions to the spinel blocks, according to the above argument, explains why the activation energy of Li β -alumina is higher than that of Na β -alumina.

It has been demonstrated from an experiment using H_2^{18}O that during the diffusion of water in the conduction layers the oxygen of the water species exchanges frequently with the oxygen ions of the Li β -alumina crystal.³ A possible mechanism consistent with the experimental results involves the following steps³: (1) the protons and oxygen ion in a water molecule dissociate, (2) the oxygen ion pushes away and replaces a nearby oxygen ion in the conduction plane of the crystal, and (3) the protons join the displaced oxygen ion to form a new water molecule. The key step in the above mechanism is the dissociation of H_2O . There is no evidence for the dissociation of water in Na β -alumina. This might explain water's much lower rate of diffusion in Na β -alumina and suggests that the water dissociation in Li β -alumina may also be related to the small size of the Li^+ ion.

1. Summary of paper to be published.
2. J. C. Wang, M. Gaffari, and Sang-il Choi, *J. Chem. Phys.* 63, 772 (1975).
3. N. J. Dudney, J. B. Bates, and J. C. Wang, *Phys. Rev. B* 24, 6831 (1981).

HYDRATION THERMODYNAMICS OF Na β - AND Na β'' -ALUMINA¹

N. J. Dudney J. B. Bates
W. E. Brundage J. C. Wang

Water is often suspected of contributing to deterioration of the electrolytic properties of Na β - and β'' -alumina. Both materials have a layered crystal structure, and water is readily adsorbed from the atmosphere into the so-called conduction layers which contain the mobile sodium ions. This work was undertaken to determine the thermodynamic parameters of the hydration reactions.

The equilibrium concentration of absorbed water was determined from infrared absorption measurements for single-crystal samples treated under a wide range of elevated temperature and water vapor pressure conditions. These data are presented in Figs. 4.2 and 4.3. Most measurements were made using unpolarized light incident normal to the conduction layers (E_{ic}), but for very small water concentrations it was necessary to measure and then scale the much more intense absorbance for the E_{ic} polarization. The infrared absorbance due to the internal vibrational modes of the absorbed water molecules² is

Fig. 4.2. Concentration of water absorbed by Na β -alumina as a function of the treatment temperature and water vapor pressure. The open circles indicate infrared absorption measurements for the EIC polarization; the closed circles are for EIC measurements scaled by the observed ratio of the absorption coefficients, $\epsilon_1/\epsilon_2 = 0.05$. The infrared absorbance at 3190 cm^{-1} divided by the sample thickness is also shown.

Fig. 4.3. Concentration of water absorbed by Na β'' -alumina as a function of the treatment temperature and water vapor pressure. The infrared absorbance/sample thickness is for the 3413 cm^{-1} peak, which is one of two major water peaks.

proportional to the total water concentration. Absolute water concentrations were obtained from several measurements of the amount of water evolved from samples at high temperatures using a P_2O_5 electrolytic cell. The uncertainties in the magnitudes of absolute water concentrations are $\pm 40\%$ for Na β -alumina and $\pm 20\%$ for Na β'' -alumina.

The data in Figs. 4.2 and 4.3 were fit to the expression for the equilibrium constant $K = C/[P_{\text{H}_2\text{O}}(C_{\text{satd}} - C)] = \exp(\Delta S/k) \times \exp(-\Delta H/kT)$, where C is the absorbed water concentration and C_{satd} the saturation water concentration. This expression assumes that the water molecules are randomly distributed among the available sites within the conduction layers. Results of the least-squares fits are shown as curves in the figures and in Table 4.1.

Table 4.1. Enthalpy, entropy, and saturation concentration for hydration of Na β - and Na β'' -alumina.

	Na β -alumina	Na β'' -alumina
ΔH (kJ/mol)	-67 ± 1	-57 ± 2
ΔS (J/mol-K)	-144 ± 3	-144 ± 4
$C_{\text{satd}}(\text{H}_2\text{O}/\text{planar cell})$	3.90	0.30 ± 0.03

For our crystals the compositions per planar unit cell are $\text{Na}_{1.67}\text{Mg}_{0.67}\text{Al}_{10.33}\text{O}_{17}$ (β'') and $\text{Na}_{1.2}\text{Al}_{11}\text{O}_{17.1}$ (β). Because there is no indication of the approach to saturation for Na β -alumina in Fig. 4.2, C_{satd} has been fixed equal to the concentration of available water sites determined for Li β -alumina, which was prepared from the same Na β -alumina material.³ The value of C_{satd} determined from the fit for Na β'' -alumina is equal within the uncertainty to the concentration of vacant sodium sites in the conduction planes. The experimental hydration entropies are consistent with estimated values based on the calculated spectroscopic entropies and the number of equivalent orientations that H_2O is believed to occupy at each site. These values are -153 ± 12 and $-148 \pm 12 \text{ J/mol-K}$ for Na β - and Na β'' -alumina, respectively. The difference in the hydration enthalpies for Na β'' - and Na β -alumina is attributable to the difference in the estimated coulomb repulsion between the sodium ions, the repulsion being larger for Na β'' -alumina due to the larger concentration and therefore closer proximity of the sodium ions to the water molecules.

1. Summary of paper to be published.
2. J. B. Bates et al., *J. Chem. Phys.* 77, 4838 (1982); *Solid State Ionics* 9, 237 (1983).
3. N. J. Dudney, J. B. Bates, and J. C. Wang, *J. Chem. Phys.* 77, 4857 (1982).

REACTION OF POLYCRYSTALLINE Na β -ALUMINA
WITH CO₂ AND H₂O AND THE FORMATION
OF HYDROXYL GROUPS¹

J. B. Bates D. Dohy²
R. L. Anderson

The results of several previous studies suggest that β - and β' -alumina react with water vapor and CO₂, causing the formation of a carbonate on the surface of these materials. Recent infrared reflectance measurements have provided evidence that polycrystalline Na β -alumina reacts with CO₂ and water vapor, resulting in the formation of NaHCO₃ at high CO₂ pressures or hydrated Na₂CO₃ at low CO₂ pressures on the surfaces of ceramic specimens. The infrared measurements also show that Na⁺ ions removed from the conduction layers are replaced by H₃O⁺ ions which, on heating the ceramic specimens, dissociate to produce hydroxyl groups.

Most of the samples investigated were bar-shaped specimens of Li-stabilized Na β -alumina (Ceramtec, Inc.) with a reported composition by weight of 8.85% Na₂O, 9.75% Li₂O, and 90.4% Al₂O₃. Infrared reflectivity measurements were made on the as-received and treated specimens at 25°C and at elevated temperatures using a Fourier transform spectrometer. Multiple internal reflection (MIR) measurements were made on the bar-shaped specimens using KRS-5 trapezoids in which the internal incidence angles were 60° and 45°.

Multiple internal reflection spectra of a bar-shaped specimen after treatment in H₂O-saturated CO₂ and of a thin film of NaHCO₃ are shown in Fig. 4.4. It can be seen that the spectra of Na β -alumina obtained with the 60° and 45° trapezoids closely match the spectrum of NaHCO₃. There is no evidence in either spectrum for the presence of Na₂CO₃, as would be indicated by the appearance of a peak at 880 cm⁻¹.

External reflection spectra of as-received specimens in the region from 2000 to 400 cm⁻¹ (top curve in Fig. 4.5) displayed prominent peaks near 3450 and 3090 cm⁻¹, which are due to H₂O molecules located in the conduction layers of the Na β -alumina grains, and weaker features at 2128 and 2336 cm⁻¹. These latter peaks and new broad features at 2685 cm⁻¹ and at 3350 cm⁻¹, which appear after treatment in H₂O-saturated CO₂, are attributed to the stretching modes of H(H₂O)_n⁺ species in the conduction layers of the Na β -alumina grains.³ Since the peaks due to these species were not seen in spectra after treatment of samples in moist O₂ or in dry CO₂, it is concluded that H₃O⁺ replaces Na⁺ as a consequence of the reaction of Na β -alumina with CO₂ and H₂O. Since NaHCO₃ has also been identified as a product of this reaction, the following process is plausible:

The thermochemical properties of Na β - and H₃O β -alumina are not known, but using literature values for the heats of formation ΔG° of NaHCO₃, H₂O, and CO₂, and the known values of

Fig. 4.4. Multiple internal reflection spectra of polycrystalline Na β -alumina after treatment in H₂O-saturated CO₂ obtained using KRS-5 trapezoids with internal incidence angles of 60° (top curve) and 45° (middle curve). Lower curve is the MIR spectrum of an evaporated film of NaHCO₃ on KRS-5. Measurements were made at 25°C.

$P_{\text{H}_2\text{O}}$ and P_{CO_2} , ΔG (kJ/mol) for the reaction in Eq. (1) at 298°K can be expressed as

$$\Delta G_1 = 18 + \Delta G^\circ(\text{H}_3\text{O}\beta) - \Delta G^\circ(\text{Na}\beta). \quad (1b)$$

Since $\Delta G_1 < 0$, then $\Delta G^\circ(\text{H}_3\text{O}\beta) < \Delta G^\circ(\text{Na}\beta) - 18$. Thus, the formation of NaHCO₃ according to Eq. (1) requires ΔG° for hydronium β -alumina to be lower than ΔG° for β -alumina by at least 18 kJ/mol (-0.2 eV).

After exposure of Na β -alumina specimens to H₂O-saturated laboratory air at 25°C, the peaks at 2128 and 2336 cm⁻¹ were clearly defined in the external reflection spectra, but only two peaks at 1440 and 1380 cm⁻¹ could be identified in the MIR spectra. The relative intensities and wave numbers of these latter peaks are consistent with their assignment to split components of ν_3 of CO₃²⁻ in Na₂CO₃·7H₂O or Na₂CO₃·10H₂O. These results indicate that a hydrated sodium

Fig. 4.5. Reflection spectra of Na β'' -alumina after treatment in H₂O-saturated CO₂. The bottom curve was obtained after treatment in D₂O-saturated CO₂. The sample temperature during each measurement is indicated above each spectrum.

carbonate is formed when Na β'' -alumina is treated in H₂O-saturated air. The formation of Na₂CO₃·10H₂O can be written as

with

$$\Delta G \text{ (kJ/mol)} = 70.5 + 2[\Delta G^\circ(\text{H}_3\text{O}\beta'') - \Delta G^\circ(\text{Na}\beta'')] \quad (2b)$$

The occurrence of reaction (2a) requires the standard free energy of H₃O β'' -alumina to be lower than that of Na β'' -alumina by at least 35.2 kJ/mol (~0.4 eV). Most of this energy difference is likely due to hydrogen bonding, but part of the energy gained from hydrogen bond formation and from an increase in polarization energy will be offset by the energy required to expand the lattice along the c direction, which evidently occurs on replacement of Na⁺ by H₃O⁺.

The spectra observed in the 2000 to 4000 cm⁻¹ region of H₂O-CO₂ treated specimens at elevated temperatures are illustrated in Fig. 4.5. With increasing temperature, the intensities of the broad H₃O⁺ bands decreased, while the intensities of sharper peaks due to OH⁻ near 3640 and 3525 cm⁻¹ increased. Since the increase in intensities of the OH⁻ peaks with increasing temperature was accompanied by a decrease in the intensities of the H₃O⁺ bands, it is reasonable to conclude that OH⁻ is formed from the dissociation of H₃O⁺. A possible reaction is $\text{O}_{(s)}^{2-} + \text{H}_3\text{O}_{(s)}^+ = \text{OH}_{(s)}^- + \text{H}_2\text{O}_{(g)}$, where $\text{O}_{(s)}^{2-}$ represents an oxygen ion of the host lattice. Provided that the temperature did not exceed the arbitrarily chosen limit of 350°C, the samples behaved reversibly in that the same spectral features were observed at corresponding temperatures on heating or cooling. When the sample temperature was increased to 600°C, the OH⁻ peaks vanished rapidly, and they did not reappear when the sample was cooled to 25°C in the spectrometer. This suggests that OH⁻ is removed from the conduction layers, possibly by a process in which H₂O is formed and released to the vapor phase: $2\text{OH}_{(s)}^- = \text{H}_2\text{O}_{(g)} + \text{O}_{(s)}^{2-}$. Such a process could account for the reported "burst" of H₂O released from Na β'' -alumina at 500°C.

It is concluded from this study that sodium β'' -alumina reacts with CO₂ and H₂O to form NaHCO₃ at high CO₂ pressures or Na₂CO₃·xH₂O at low CO₂ pressures. The bicarbonate or carbonate produced in the reaction forms a 20–50- μ m-thick crust or scale on the Na β'' -alumina, which eventually retards further corrosion of the surface. The H₃O⁺ ions in the Na β'' -alumina grains dissociate by an endothermic process to produce OH⁻ species. At high temperatures, ~600°C, the OH⁻ is rapidly removed from Na β'' -alumina, probably by the formation and evolution of H₂O. The net result of reaction with CO₂ and H₂O, dissociation of H₃O⁺, and removal of OH⁻ according to the processes discussed above is to change irreversibly the composition of the grains in the degraded region near the surface.

1. Summary of paper to be published.

2. Guest scientist from Centre Scientifique et Polytechnique, Université Paris Nord, Villetaneuse, France.

3. No distinction is made among the possible species, H₃O⁺, H₃O⁺·H₂O, and H₅O₂⁺, in the discussion to follow.

4. T. K. Hunt, N. Weber, and T. Cole, p. 95 in *Fast Ion Transport in Solids*, ed. by P. Vashishta, J. N. Mundy, and G. K. Shenoy, North-Holland, Amsterdam, 1979.

HYDROGEN DIFFUSION IN Pb β -ALUMINA¹

J. B. Bates N. J. Dudney
J. C. Wang

The mobile Na⁺ ions in Na β -alumina can be completely exchanged with Pb²⁺ ions by treatment² in molten PbCl₂. When this exchange was carried out in the presence of air, protons in the form of OH⁻ were introduced into the conduction layers along with lead ions. Although the concentration of OH⁻ was low, on the order of 5×10^{-3} per formula unit of Pb_{0.84}Mg_{0.67}Al_{10.33}O₁₇, the distribution of OH⁻ after ion exchange indicated that the proton mobility in Pb β -alumina is high. The potential use of Pb β -alumina as a fast proton conductor that is stable at 400°C motivated further studies of hydrogen diffusion. In this report, the results of tracer diffusion measurements by isotope exchange will be presented.

Single crystals of Pb β -alumina containing hydrogen or deuterium were prepared by ion exchange of Na β -alumina crystals in molten PbCl₂ at ~510°C in the presence of H₂O-saturated N₂ or D₂O-saturated N₂. Crystals containing one kind of hydrogen isotope were heated in N₂ saturated with water vapor of the other isotope. Crystals were cooled rapidly to room temperature, and the absorbance profiles of OH⁻ and OD⁻ were measured by the infrared technique described previously.³ In these measurements, the sample was positioned behind a small aperture through which the incident radiation passed. Absorption measurements were made from the edge of each crystal through the center along the bisector of the (001) face. If x is the distance from the edge of the crystal to the center of the aperture, then it can be shown that the absorbance at x , $A(x)$, is given by

$$A(x) = -\log \left\{ \frac{2}{\pi r^2} \int_{x-r}^{x+r} ds [\sqrt{r^2 - (s-x)^2}] \right. \\ \left. \times \log(-\alpha C(s)d) \right\} \quad (1)$$

where r is the radius of the aperture, α is the absorption coefficient, d is the sample thickness, and $C(x)$ is the concentration at x . For diffusion in a rectangular slab (x, y plane), $C(x)$ along the bisector ($y=L_y$) is given by⁴

$$C(x, L_y) = C_b + (C_0 - C_b) \frac{16}{\pi^2} G(u)G(v), \quad (2)$$

where C_b is the boundary concentration and C_0 is the initial concentration in the crystal. In Eq. (2),

$$G(u) = \sum_n \frac{(-1)^n}{2n+1} \cos \left[\frac{(2n+1)\pi u}{2L_x} \right] \\ \times \exp \left[\frac{-(2n+1)^2 \pi^2 D t}{4L_x^2} \right], \quad (3)$$

in which $2L_x$ is the length of the crystal along the x axis, D is the diffusion coefficient, t is the time of diffusion, and $u = L_x - x$.⁵ For diffusion into the crystal, $C_0 = 0$.

After each diffusion anneal, absorbance profiles were determined for species diffusing into and out of the crystal. Using Eqs. (1) and (2), D and C_0 or C_b were fit to give the best agreement between the observed and calculated absorbance at each value of x . Least-squares fits of these parameters were also made using the observed absorbances at the center of the crystal ($x=L_x$, $y=L_y$) for different treatment times.

The fitted values of the tracer diffusion coefficients D_t are listed in Table 4.2, and values of $\ln D_t$ vs $1/T$ are shown in Fig. 4.6. Each data point represents the average of the values determined from the different measurements at the same temperature. The solid line is the result of a least-squares fit of the three data points to the expression $D_t = D_0 \exp(-E_a/kT)$, where $E_a = 0.54$ eV is the activation energy for diffusion and $D_0 = 2.7 \times 10^{-3}$ cm²/s. For comparison, values of D_0 for Pb²⁺ ions at comparable temperatures are also listed in Table 4.2 and plotted in Fig. 4.6. These were calculated using the conductivities determined from four-joint impedance measurements and the expression $D_0 = 4.95 \times 10^{-8} \sigma T$ cm²/s, with σT in units of Ω^{-1} cm⁻¹ K. (The number of mobile Pb²⁺ ions was taken to be 0.835 per formula unit.) For Pb²⁺ ions, $E_a = 0.23$ eV and $D_0 = 7.5 \times 10^{-4}$ cm²/s.

Table 4.2. Tracer diffusion coefficients D_t for hydrogen and D_0 for Pb²⁺ ions in Pb β -alumina.

$T(^{\circ}\text{C})$	$D_t \times 10^7$ (cm ² /s)	$D_0 \times 10^7$ (cm ² /s)
520		265
515	9.1 (± 1.7)	
455	5.3 (± 0.7)	201
352		114
350	1.1 (± 0.12)	

The diffusion mechanism of H⁺ in Pb β -alumina is presently not known. It was suggested previously³ that the homogeneous distribution of OH⁻ observed in large single crystals of Pb β -alumina after treatment of Na β -alumina in PbCl₂ indicated simultaneous diffusion of Pb²⁺

ORNL-DWG 84C-15894

Fig. 4.6. Diffusion coefficients for Pb^{2+} ions (D_{σ}) and H^{+} ions (D_{τ}) in $\text{Pb } \beta''\text{-alumina}$.

and H^{+} ions during ion exchange. However, as shown in Fig. 4.6, the diffusivity of Pb^{2+} ions is significantly larger than that of H^{+} ions within the temperature range of the experiments. There is no evidence from the diffusion measurements, therefore, to suggest that the mobility of the protons is associated with the high mobility of the lead ions. There is evidence which strongly indicates that most, if not all, of the hydrogen enters the conduction layer as H_2O molecules rather than H^{+} ions, which, because of the Pb^{2+} ions, dissociate to form OH^{-} species. It is unlikely that proton transport occurs by the movement of OH^{-} through the conduction layers. It is more likely that diffusion occurs through jumps of H^{+} from one O^{2-} ion to another in the conduction layers.

1. Summary of paper to be published.
2. G. C. Farrington and B. Dunn, *Solid State Ionics* 7, 267 (1982).
3. J. B. Bates et al., *Solid State Ionics* 9&10, 237 (1983).
4. H. S. Carslaw and J. C. Jaeger, *Conduction of Heat in Solids*, Chap. V, Oxford University Press, Oxford, England, 1947.
5. At a general position in the x,y plane, $C(x,y) = C_b + (C_o - C_b) \frac{16}{\pi^2} G(u)G(v)$ with $v = Ly$, where $2Ly$ is the length of the crystal along the y axis.

SHELL MODEL CALCULATIONS FOR STOICHIOMETRIC Na β -ALUMINA¹

J. C. Wang

Walker and Catlow^{2,3} recently reported the results of their shell model calculations for the structure and transport of Na β -alumina ($\text{Na}\beta$). For stoichiometric $\text{Na}\beta$ (s $\text{Na}\beta$), in which the number of Na^{+} ions is equal to the number of Beavers-Ross (BR) sites, they performed three lattice energy calculations; in each case all the Na^{+} ions were situated at one of the three sets of sites: BR sites, anti-BR (aBR) sites, or mid-oxygen (mO) sites. According to their results, while the BR configuration has the lowest lattice energy, the energies per Na^{+} ion for aBR and mO configurations are higher by only 0.15 and 0.39 eV, respectively. They concluded that their results suggest a "fluid" conduction plane structure.

For nonstoichiometric $\text{Na}\beta$, they calculated the structure for the case of one Na^{+} ion added to the s $\text{Na}\beta$ structure. From their results, they concluded that the aBR site is the stable configuration for the excess Na^{+} ion and that the activation energy for an interstitialcy mechanism is 0.58 eV. These latter results are quite different from those observed experimentally^{4,5} and from those reported by Wang et al.⁶ from calculations based on a polarizable point charge model. The results of Wang et al. suggest that the excess Na^{+} ion will displace a Na^{+} ion from its BR site and share with it the potential well centered at the BR site. As a result, the $\text{Na}^{+}\text{-Na}^{+}$ pair occupies two neighboring mO sites. Because of the correlated motion of the paired Na^{+} ions, the activation energy for one of them to move out of the potential well to form a new pair in a neighboring well was calculated to be only 0.14 eV. A comparison of the calculated results with experimental observations is shown in Table 4.3.

Table 4.3. Comparison of calculated and observed activation energies and site occupation factors in Na β -alumina.

	Activation energy (eV)	Na ⁺ ions per planar unit cell		
		BR	mO	aBR
Walker & Catlow ^a	0.58	1.0	0.0	0.29
Wang et al. ^b	0.14	0.71	0.58	0.0
Experiment	0.142 ^c	0.75 ^d	0.52 ^d	0.0

^aRef. 3, assuming the number of Na^{+} ions per BR site to be 1.29.

^bRef. 6.

^cRef. 4.

^dRef. 5.

The main computer programs used by Walker and Catlow for their calculations are PLUTO and HADES II. The latter, a recent version of HADES II written for cubic crystals, is believed to be applicable to defects in crystals of both cubic and hexagonal symmetry. PLUTO is usually used in calculating properties of perfect crystals before defects are introduced into the structure. Walker and Catlow claim that, in some respects, their models are superior to those of Wang et al. Yet, as can be seen from Table 4.3, their results are quite different from those observed experimentally. In this work these differences are investigated by using a computer program designed to calculate lattice energies for s Na⁺ using the same shell model parameters adopted by Walker and Catlow. The core and shell positions of all ions, as well as the lattice parameters, were fully relaxed. As can be seen from Table 4.4, the calculated energy difference between aBR and BR sites (0.33 eV) is about twice as large as that reported by Walker and Catlow. The present results also show that the relaxed oxygen ion positions next to the conduction plane in this case are displaced from their observed sites reported in Ref. 5. When the core-shell spring constant of the oxygen ion was adjusted to minimize these displacements, the above-mentioned energy difference increased to about 0.56 eV. (See Table 4.4 for a detailed comparison.) These results cast doubt on the "fluid" conduction plane structure suggested by Walker and Catlow and on the defect structure and activation energy obtained from their calculations.

Table 4.4. Calculated lattice energies (in eV per Na⁺ ion) for s Na β -alumina.

	Position of Na ⁺ Ions		
	BR	mO	aBR
Walker and Catlow ^a	0 ^b	0.39	0.15
This work ^c	0 ^b	0.38	0.33
This work with k(O ²⁻) changed ^d	0 ^b	0.47	0.56

^aReference 2.

^bThe lattice energy with Na⁺ ions occupying BR sites is set to 0.

^cUsing the same energy-parameter values as those used by Walker and Catlow. The short-range potentials were cut off at 20 Å.

^dSame as in b except that the core-shell spring constant of the oxygen ion was changed from 103.07 to 48.449 eV Å⁻².

It is appropriate here to provide some possible explanations for the various discrepancies mentioned above:

(1) Walker and Catlow listed "bulk lattice strains" in one of their papers.³ This description implies that they did not allow the ions and lattice parameters to relax fully, which may

have produced errors in their energy difference and activation energy calculations.

(2) The core-shell spring constant of the O²⁻ ion used by Walker and Catlow is too high. This is reflected by the fact that their calculated high-frequency dielectric constant is about 35% smaller than that observed experimentally.³ When the differences between calculated and observed O²⁻ ion positions are minimized in the present calculations by reducing the spring constant, the high-frequency dielectric constant should also increase. As can be seen from Table 4.4, this has a drastic effect on the energy of the aBR site.

(3) Walker and Catlow did not report the cutoff distance they used for their short-range interactions. Present calculations show that the energy difference between aBR and BR sites depends very much on this distance. (The value used here was 20 Å.) Small cutoff distances sometimes can introduce ambiguities concerning the inclusion or exclusion of some of the ions in the border region when calculating the potential energies.

1. Summary of paper to be published.
2. J. R. Walker and C. R. A. Catlow, *Nature* **286**, 473 (1980).
3. J. R. Walker and C. R. A. Catlow, *J. Phys. C* **15**, 6151 (1982).
4. K. K. Kim, J. N. Mundy, and W. K. Chen, *J. Phys. Chem. Solids* **40**, 743 (1979).
5. C. R. Peter et al., *Acta Crystallogr. B* **27**, 1826 (1971).
6. J. C. Wang, M. Gaffari, and Sang-il Choi, *J. Chem. Phys.* **63**, 772 (1975).

INTERFACES

IMPEDANCE OF METAL-SOLID ELECTROLYTE INTERFACES

J. B. Bates J. C. Wang
R. L. Anderson

Previous studies¹ have shown that the impedance of solid state cells such as Pt/Na β -alumina/Pt can be described by the function,

$$Z(\omega) = R + \frac{D}{\omega^n} \left[\cot\left(\frac{n\pi}{2}\right) - 1 \right], \quad (1)$$

where R is the bulk resistance of the electrolyte. The last two terms represent the ac response of the metal-electrolyte interface, where D and n are parameters, with 0 < n < 1. These terms are equivalent to the so-called universal capacitor² or constant phase angle element³ given by $C(n) = D(i\omega)^{-n}/\sin(n\pi/2)$. For an ideal capacitor, n = 1, the second term in Eq. (1) vanishes, and D = 1/C. Deviation from ideal behavior (n < 1) appears to be a general trend for metal-solid electrolyte interfaces, especially those cases in which the mobile ions of the electrolyte are blocked at the electrode

(no steady-state dc current can pass through the cell).

Examples of impedance data for Na β -alumina with sputtered platinum electrodes, presented as schematic graphs of $-\text{Im}(Z)$ vs $\text{Re}(Z)$, are shown in Fig. 4.7. The frequency range for these measurements is typically from 10 to 10^6 Hz. The effect of surface roughness is illustrated in Fig. 4.7(a). Curve 1 represents the impedance of a sample with platinum sputtered onto saw-cut faces while curve 2 represents the impedance of a sample with electrodes deposited on faces polished with 0.5- μm alumina. Scanning electron micrographs showed the saw-cut faces to be rough on a scale of $\sim 0.5 \mu\text{m}$. The value of the parameter n determines the angle between the impedance graph and the $\text{Re}(Z)$ axis: $\theta = n\pi/2$. For the sample with rough surfaces, $n = 0.83$, but for the sample with the smoother electrodes, $n = 0.98$. Similar data for other metal-solid electrolyte systems are sparse, but from the few published results⁴ it appears that in general $n \rightarrow 1$ as the interface becomes smoother.

Fig. 4.7. (a) Schematic impedance graphs of two Pt/Na β -alumina/Pt cells with metal contacts deposited on saw-cut (curve 1) and polished (curve 2) faces. (b) Schematic impedance graphs for the cell with contacts on saw-cut faces at various temperatures.

The impedances observed for the same Pt/Na β -alumina/Pt cell at several temperatures are represented by the graphs in Fig. 4.7(b). For the purpose of illustration, the graphs were shifted along the $\text{Re}(Z)$ axis to a common intercept. The trend displayed (i.e., n decreases as T increases) is characteristic of all of the cells measured regardless of the degree of roughness of the interface. The high-temperature limit of n is not known, but the graph of n plotted as a function of $1/T$ is nearly linear above 400 K and extrapolates to $n = 0.5$ above 1000 K.

The impedance of metal-solid electrolyte interfaces as described by the frequency dependent terms in Eq. (1) is not understood. A model to account for the dependence of Z on the degree of roughness of the interface is described elsewhere in this report.⁵ In this model, the interface is represented by a plane surface containing pores, and the impedance is calculated by connecting an ideal capacitor in parallel with a pore. In some cases, the resulting impedance has the form $Z(\omega) = A(i\omega)^{-n}$ over several decades of frequency with $0 < n < 1$. Le Mehaute and Crepy⁶ have proposed a theory to account for interfacial impedance which is based on the idea of transport in fractal media. In this theory, n is related to the fractal dimension of the interface. Although these models may be able to relate the impedance to interface structure, there is presently no model which can account for the temperature dependence of n . In the case of the Pt/Na β -alumina/Pt cell, the temperature dependence of n above $\sim 60^\circ\text{C}$ suggests the occurrence of more than one electrode process at elevated temperatures. The nature of these processes is, at present, unknown.

1. H. Engstrom, J. R. Bates, and J. C. Wang, *Solid State Commun.* 35, 543 (1980).
2. A. K. Jonscher, p. 91 in *Dielectric Relaxation in Solids*, Chelsea Dielectrics Press Ltd., London, 1983.
3. P. H. Bottelberghs and G. H. J. Broers, *J. Electroanal. Chem.* 67, 155 (1976).
4. R. D. Armstrong, T. Dickinson, and P. M. Willis, *J. Electroanal. Chem.* 53, 389 (1974).
5. J. C. Wang and J. B. Bates, "Model for the Frequency-Dependent Impedance of a Solid Electrolyte/Electrode Interface," this report.
6. A. Le Mehaute and G. Crepy, *Solid State Ionics* 9&10, 17 (1983).

MODEL FOR THE FREQUENCY-DEPENDENT IMPEDANCE OF A SOLID ELECTROLYTE/ELECTRODE INTERFACE

J. C. Wang J. B. Bates

Usually the conductivity of a solid electrolyte is determined by measuring the impedance of the system, blocking-electrode/electrolyte/blocking-electrode, as a function of frequency under small applied voltages. Reliable data analyses depend crucially on the equivalent circuit used for the electrolyte/electrode interface. The simplest equivalent circuit is a capacitor for a smooth

electrode. Its impedance graph, $-\text{Imag}(Z)$ vs $\text{Real}(Z)$, where Z is the frequency-dependent interfacial impedance, is a vertical line. Another possible equivalent circuit is the Warburg impedance which is used to simulate the diffusive motion of charges at a porous electrode. Its impedance graph is a straight line forming a 45° angle with the $\text{Real}(Z)$ axis. Experimental impedance graphs for interfaces, however, often lie between those of a capacitor and a Warburg impedance. In this work we construct a model to connect the frequency dependence of the interfacial impedance with the roughness of the electrode surface.

The roughness of an interface is represented by pores on the electrode. The electrical response of a pore in the form of a uniform long channel can be approximated by a Warburg impedance¹ (i.e., a transmission line with constant resistance r and capacitance c per unit length). Its impedance is given by

$$Z(\omega) = (r/c)^{1/2} (i\omega)^{-1/2}, \quad (1)$$

where ω is the angular frequency and i is equal to $\sqrt{-1}$. The penetration depth of an ac current into the pore can be shown to be

$$d_p(\omega) = (2/rc)^{1/2} \omega^{-1/2}, \quad (2)$$

suggesting that the frequency dependence of the Warburg impedance given by Eq. (1) is closely related to the penetration depth.

In general a pore may not be long and uniform. It is therefore natural to allow r and c to be dependent on position. For example, for a pore in the shape of a cone, the value of r becomes larger and that of c becomes smaller with increasing depth into the pore. This effect changes the current penetration depth and therefore the frequency dependence of the impedance. By solving a system of first-order differential equations numerically, the impedance of a pore can be calculated.

The interfacial impedance for an electrode with pores can be simulated by putting a capacitor (corresponding to the flat portion of the electrode) in parallel with the impedance associated with the pores. It is demonstrated that for some cases the resultant impedance is of the form

$$Z(\omega) = A(i\omega)^{-n}, \quad (3)$$

over several orders of frequencies. In the above equation, A is independent of ω and $1 > n > 1/2$. This gives an impedance graph of a straight line lying between that of a capacitor ($n=1$) and that of a Warburg impedance ($n=1/2$) as usually observed experimentally. Our present model provides some physical basis for using non-Debye capacitors² or constant phase elements³ in some equivalent circuits reported in the literature.

1. R. de Levie, *Electrochim. Acta* **8**, 751 (1963).

2. H. Engstrom, J. B. Bates, and J. C. Wang, *Solid State Commun.* **35**, 543 (1980).

3. P. H. Bottelberghs, p. 145 in *Solid Electrolytes*, ed. by P. Hagenmuller and W. van Gool, Academic Press, New York, 1978.

MODEL FOR THE ENHANCED CONDUCTIVITY OF AN IONIC CONDUCTOR CONTAINING SUBMICRON INSULATOR PARTICLES

J. C. Wang M. J. Dudney
J. B. Bates

The ionic conductivity of several silver and alkali halides such as LiI can be enhanced by several orders of magnitude by the addition of small particles of an insulator material such as Al_2O_3 .^{1,2} Several models¹ have been proposed to explain the phenomenon. In general it is assumed that the enhancement is caused by the existence of a high conductivity layer surrounding each particle. In this work we adopt this idea and calculate the composition dependence of the conductivity using a very simple model.

We assume that the insulator particles are in the form of cubes and are arranged on a simple-cubic lattice which is embedded in the conducting material. The size of each cube and the position-dependent conductivity in its vicinity are treated as parameters. The system is then approximated with a resistor network, and its conductivity is calculated. It is found that the model can describe several reported experimental results quite well.

The values of the parameters are determined by fitting some of the existing conductivity data $\sigma(c)$, where c stands for the volume fraction of the insulator particles. The results show that the conductivity in the vicinity of each insulator cube has a maximum at some distance away from its surface. The lower conductivity in the region between the surface and the maximum is demanded by the experimental result^{1,2} that $\sigma(c)$ usually drops rapidly with c at large values of c . The position dependence of the conductivity beyond the maximum (far away from the surface) is dictated by the rapid increase of $\sigma(c)$ with c at small values of c . The above result suggests that the detailed form of the high conductivity layer, surrounding each insulator particle is probably determined by a combination of the space charge distribution and the position-dependence of the charge mobility.

1. C. C. Liang, *J. Electrochem. Soc.* **120**, 1289 (1973).

2. J. P. Wagner, Jr., *Mater. Res. Bull.* **15**, 1691 (1980).

ENHANCED IONIC CONDUCTIVITY IN COMPOSITE MATERIALS DUE TO INTERFACIAL SPACE CHARGE LAYERS¹

N. J. Dudney

The ionic conductivity of a number of salts (e.g., β -AgI, LiI, CuCl, HgI₂, etc.) can be enhanced by one to three orders of magnitude with the addition of fine particles of an insoluble and nonconducting material such as Al₂O₃ or SiO₂. Typically the conductivity increases with addition of the inert particles and reaches a peak at 10–40 vol % of the particles. The mechanism responsible for the enhanced conductivity of the composite is not understood at this time. Some claim that this effect is due to an increased concentration of charge carriers in a diffuse space charge layer near the charged surface of the particle.² The goal of the present study is to test this proposed mechanism by calculating the maximum space charge layer effect and then using this result to estimate the conductivity of a composite with a random distribution of Al₂O₃ particles. Also, the conductivity of composite systems has been investigated assuming an ordered distribution of particles which are surrounded by a high conductivity layer.³

For a Frenkel defect material, such as a silver halide, an equilibrium space charge layer develops at a surface or interface as a consequence of the difference in the free energies for formation of silver vacancies F_V versus silver interstitials F_i . These individual reactions for formation of the Frenkel defects can be written as

where the notation indicates the effective charges and sites of the ion or defects (s being a surface or interface site). Following the continuum model developed by Kliewer,⁴ the site fractions for Ag_i^+ and V_{Ag}^- are given by

$$\frac{n_V}{N} = \exp \left[\frac{-(F_V + e\phi_x)}{kT} \right] ,$$

$$\frac{n_i}{N_i} = \exp \left[\frac{-(F_i - e\phi_x)}{kT} \right] ,$$

where ϕ_x is the electrical potential of the space charge layer defined to be zero at the boundary ($x=0$). An example of the calculated defect distribution near a boundary of AgCl containing 10-ppm divalent cation impurities is shown in Fig. 4.8. At 400 K the boundary is positive with respect to the bulk. From the integrated defect concentrations and the rel-

Fig. 4.8. Site fraction of point defects in space charge layer of AgCl at 400 K. Potential difference across the layer ($e\phi_m$) = 0.24 eV. Values used in this calculation are $F_i = 0.97$ eV - 1.7 kT and $F_V = 0.47$ eV - 7.7 kT (ref. 4). Thickness of AgCl layer = 2 μm , average $\text{M}_{\text{Ag}}^{2+}$ concentration = 10 ppm, binding energy ($\text{M}_{\text{Ag}}^+ - \text{V}_{\text{Ag}}^-$) = 0.4 eV.

tive mobilities of the interstitials and vacancies, the conductivity through a 1- μm layer next to the boundary is calculated to be 25% larger than the bulk conductivity infinitely far from the boundary ($\sigma/\sigma_m=1.25$). This is considerably smaller than the typical enhancements observed for the composite systems.

The relative values of F_i and F_V depend on the nature of the surface or interface and may be very different for the interfaces of a composite system than for free surfaces or grain boundaries. The space charge layers and conductivity have been calculated for two extreme cases: (1) $F_V = 0$, $F_i = F_f$ and (2) $F_i = 0$, $F_V = F_f$; where F_f is the Frenkel defect formation energy. For (1) the concentration gradients are similar, although steeper than those shown in Fig. 4.8. The value of σ/σ_m is 1000 at 200 K, but it decreases rapidly with increasing temperatures. Case (2) is more complex due to the strong segregation of the divalent impurities to the interface at low temperatures. For thin layers or small grains, this segregation leads to a depletion of the defect concentrations and conductivity at the center of the grain. Again the largest values for σ/σ_m are ~1000 at low temperatures.

The maximum expected conductivity of an AgCl/Al₂O₃ composite as a function of the composition has been estimated using an effective medium model.⁵ The composite is assumed to be a

dense random compact of approximately spherical Al_2O_3 and AgCl grains. Conduction along the interfaces and through the grains was represented by a parallel path network. From the calculations above, the conductivity near an $\text{AgCl}/\text{Al}_2\text{O}_3$ interface is assumed to be at most 1000 times larger than near an AgCl/AgCl grain boundary. The results for one set of parameters are shown in Fig. 4.9. The conductivity is enhanced ~50 times by the addition of Al_2O_3 particles.

Fig. 4.9. Ionic conductivity of an $\text{AgCl}/\text{Al}_2\text{O}_3$ composite. Values chosen for this calculation are grain size ratio $\text{AgCl}/\text{Al}_2\text{O}_3 = 10$, σ single-crystal $\text{AgCl} = 10^{-7}$ (ohm-cm^{-1}), σ polycrystalline $\text{AgCl} = 1.1 \times 10^{-7}$ (ohm-cm^{-1}), σ single-crystal $\text{Al}_2\text{O}_3 = 10^{-16}$ (ohm-cm^{-1}), relative conductivities near interfaces $= 10^3:1:10^{-3}$ for $(\text{AgCl}/\text{Al}_2\text{O}_3):(\text{AgCl}/\text{AgCl}):(\text{Al}_2\text{O}_3/\text{Al}_2\text{O}_3)$, respectively.

At this time only preliminary experimental data have been reported for AgCl composites.⁶ The largest reported enhancements have been for composites of Al_2O_3 with $\beta\text{-AgI}$ or LiI .² Because both the Frenkel energy of $\beta\text{-AgI}$ and the Schottky energy of LiI are smaller than the Frenkel energy of AgCl , the maximum enhanced conductivity for the space charge layer is also expected to be smaller than those calculated above. Although additional calculations are still in progress, it appears that the large (100 to 1000x) enhanced ionic conductivities reported for the AgI and LiI composite materials can be attributed only in part to the effect of enhanced carrier concentrations in the space charge layers near the interfaces.

1. Summary of paper to be published.
2. J. Bruce Wagner, Jr., *Mater. Res. Bull.* 15, 1691 (1980).
3. J. C. Wang, M. J. Dudney, and J. B. Bates, "Model for the Enhanced Conductivity of an Ionic Conductor Containing Submicron Insulator Particles," this report.
4. K. L. Kliewer, *J. Phys. Chem. Solids* 27, 705 (1966).
5. S. Kirkpatrick, *Rev. Mod. Phys.* 45, 574 (1973).
6. A. Khandkar and J. B. Wagner, Jr., *J. Electrochem. Soc.* 130, 133C (1983).

OPTICAL INVESTIGATIONS ON AgCl

Y. T. Chu J. B. Bates

Surface-enhanced Raman scattering (SERS)¹ and attenuated total reflection (ATR)² are powerful optical means of studying adsorbed molecules on metals and surface modes of crystals, because a large enhancement (10^4 – 10^6) of Raman intensity can be easily reached by the SERS method and the surface polariton dispersion curves can be accurately obtained by the ATR method.

The observation of SERS of molecules adsorbed on a metal surface generally requires that the metal surface be roughened. Since the electrodynamic characteristics of a rough surface may differ considerably from those of a smooth surface, it is reasonable to regard SERS as being primarily of electrodynamic origin. Provided that the damping is small, a strong local field near a rough surface can be generated by excitation of a surface plasmon on the metal particles. Usually noble metals (Cu , Ag , Au) are good candidates for SERS experiments because of their small damping in the visible region. Although the detailed enhancement mechanism involved in SERS is still unsolved, it is commonly recognized that the enhancement is due to an electric field effect ($\sim 10^4$) and a chemical effect ($\sim 10^2$).

Preliminary SERS experiments on AgCl films have been conducted. The metal substrate was prepared by microlithograph techniques to produce a rough surface. A silicon wafer with a 500-nm-thick thermally grown oxide layer was cut into a 1 x 1 cm square and coated with 50 Å of silver. The substrate was then placed into a resistively heated oven at about 750°C for about 30 s. This process resulted in the formation of many oblate spheroid silver particles on the substrate. These silver particles were used as a mask for reactive plasma etching of the SiO_2 in a CHF_3 low-pressure plasma. Finally, the substrate was seen to consist of many randomly shaped and sized SiO_2 posts. The substrate was coated with about 500 Å of silver, and then a thin AgCl overlayer was deposited onto the silver by thermal evaporation.

Nichols and Hexter³ predicted that the stretching vibration frequency of Ag-Cl on a silver surface depends on the surface coverage of the AgCl layer. At full coverage, the mode was predicted to occur at 240 cm^{-1} while it

shifts to lower wave numbers at partial coverage. This frequency dependence is due to the interaction between dipoles arising from the absorbed molecules and their induced image dipoles. We observed a strong Raman peak at 240 cm^{-1} in a scattering experiment using a 50-Å AgCl film. When the thickness of AgCl film was reduced to less than a single molecular layer, a weak and broad Raman peak at $220\text{--}240\text{ cm}^{-1}$ was observed. Although the exact thickness of the AgCl film was not known, we believe that the shift of the Raman peak to lower wave numbers was a result of only partial coverage because the Raman peak shifted back to 240 cm^{-1} after redeposition of AgCl onto this sample. Our experimental results support Nichols and Hexter's predictions, but more quantitative measurements are still in progress.

The transverse magnetic (TM) surface polaritons can be excited by the method of attenuated total reflection.² A surface polariton exists at the interface of two media whose dielectric constants have opposite signs. All of the characteristics of the excitation of TM surface polaritons by the ATR method can be derived from Maxwell's equations for a multilayer configuration.

A theoretical investigation has been made of the surface polaritons at the interface between air and a thick AgCl crystal. We consider here the interface between air and a semi-infinite AgCl crystal. The frequency-dependent dielectric constant (damping and spatial dispersion being neglected) for a AgCl crystal is given by

$$\epsilon(\omega) = \epsilon_{\infty} \frac{\omega^2 - \omega_{LO}^2}{\omega^2 - \omega_{TO}^2}, \quad (1)$$

where $\epsilon_{\infty} = 4.04$ is the high frequency dielectric constant and $\omega_{TO} = 103\text{ cm}^{-1}$ and $\omega_{LO} = 181\text{ cm}^{-1}$ are the wave numbers of the transverse and longitudinal optical phonons, respectively. It can be seen that the dielectric constant is negative in the reststrahlen band ($\omega_{TO} < \omega < \omega_{LO}$). The surface polariton dispersion relation at the air-AgCl interface is

$$k = \frac{\omega}{c} \left[\frac{\epsilon(\omega)}{\epsilon(\omega) + 1} \right]^{1/2}, \quad (2)$$

[with the condition $\epsilon(\omega) < -1$], where k is the component of wave vector along the interface. From the above equation we see that $k > \omega/c$; consequently, the dispersion curve (Fig. 4.10) is on the right hand side of the light line ($k = \omega/c$), and the use of conventional optical absorption measurements to observe surface polaritons is not possible. However, if a prism with an index of refraction $N_p > 1$ is separated from the AgCl crystal by a thin air gap, the wave vector k of an incident TM-polarized wave at the prism-air interface is

$$k = \frac{\omega}{c} N_p \sin \theta, \quad (3)$$

Fig. 4.10. Calculated surface polariton dispersion curve at interface between air and a thick AgCl crystal. A is the light line $k = \omega/c$, B is $k = (\omega/c)N_p \sin \theta$ ($\theta > \theta_c$), and C is $k = (\omega/c)N_p$ ($N_p = 3.4$ = refractive index of Si prism). The range between lines A and C is the accessible range for the experiment.

where θ is the angle of incidence in the prism. If the incident angle θ is greater than the critical angle θ_c , the wave undergoes total internal reflection and $N_p \sin \theta > 1$ (i.e., $k > \omega/c$). The evanescent tail of the reflected wave can penetrate the air gap and excite the surface polaritons. When this occurs, there is a dip in the reflectivity of the system as a function of ω corresponding to the excitation of surface polaritons. By varying the angle of incidence θ , it should be possible to trace out the dispersion curve.

1. D. L. Jeanmaire and R. P. Van Duyne, *J. Electroanal. Chem.* **84**, 1 (1977).
2. A. Otto, *Z. Physik* **216**, 398 (1968).
3. H. Nichols and R. Hexter, *J. Chem. Phys.* **74**, 2059 (1981).

DISPERSION OF SURFACE POLARITONS IN UNIAXIAL Al_2O_3

Y. T. Chu J. B. Bates

Nonradiative surface polaritons can be investigated experimentally by the technique known as attenuated total reflection (ATR). In this method, a prism is separated from a sample by a small air gap. The intensity of the internally totally reflected beam is measured as a function of frequency and angle of incidence; when the frequency and the wave vector parallel to the prism-air interface match those of a surface polariton of the sample, the reflected beam has a minimum intensity. This occurs because the

evanescent tail of the reflected field can couple to the field of the surface polariton in the sample. This method can be used to measure surface dispersion curves very accurately.

Since a uniaxial crystal is optically anisotropic, the dielectric constants $\epsilon_{\parallel}$ and $\epsilon_{\perp}$ have different values at a given frequency. According to the classical oscillator model,¹ $\epsilon_{\parallel}$ and $\epsilon_{\perp}$ can be calculated by:

$$\epsilon_{\kappa}(\omega) = \epsilon_{\infty\kappa} + \sum_j \frac{S_{j\kappa} \omega_{j\kappa}^2}{\omega_{j\kappa}^2 - \omega^2 - i\omega\gamma_{j\kappa}}, \quad (1)$$

where $\kappa = \parallel$ or $\perp$ indicates the direction of the electric field relative to the optic axis (c axis); $\epsilon_{\infty\kappa}$ is the limiting value of ϵ_{κ} at high frequency; and $S_{j\kappa}$, $\omega_{j\kappa}$, and $\gamma_{j\kappa}$ are the strength, frequency, and linewidth of the n th mode of a classical oscillator, respectively. The numerical values of the parameters involved in the above equation for Al_2O_3 crystal are given in Table 4.5.¹

Table 4.5. Classical oscillator parameters for Al_2O_3 .

E $\perp$ c axis ($\epsilon_{\infty\perp} = 3.2$)			
j	$\omega_{j\perp}$ (cm^{-1})	$S_{j\perp}$	$\gamma_{j\perp}/\omega_{j\perp}$
1	385	0.3	0.015
2	442	2.7	0.010
3	569	3.0	0.020
4	635	0.3	0.020

E $\parallel$ c axis ($\epsilon_{\infty\parallel} = 3.1$)			
j	$\omega_{j\parallel}$ (cm^{-1})	$S_{j\parallel}$	$\gamma_{j\parallel}/\omega_{j\parallel}$
1	400	6.8	0.020
2	583	1.7	0.035

The surface polariton dispersion relations² at the air-uniaxial crystal interface can be derived from Maxwell's equations and classified into the following cases:

A. Ordinary surface polaritons. These occur when the c axis is parallel to the air-crystal interface and perpendicular to the direction of propagation of the surface polariton. The dispersion relation is

$$\kappa = \frac{\omega}{c} \left[\frac{\omega_{\perp}(\omega)}{\omega_{\perp}(\omega) + 1} \right]^{1/2}, \quad (2)$$

with the condition $\epsilon_{\perp}(\omega) < -1$. This dispersion relation has the same form for surface polaritons at the interface of air and an optically isotropic medium.

B. Extraordinary surface polaritons. These can be excited using two geometries:

1. The c axis is perpendicular to the air-crystal interface and the direction of propagation of the surface polariton. The dispersion relation is

$$\kappa = \frac{\omega}{c} \left[\frac{\epsilon_{\parallel}(\omega)\epsilon_{\perp}(\omega) - \epsilon_{\perp}(\omega)}{\epsilon_{\perp}(\omega) - 1} \right]^{1/2}, \quad (3)$$

with the conditions $\epsilon_{\perp}(\omega) < 0$ and $\kappa > \omega/c$.

2. The c axis is parallel to the air-crystal interface and the direction of propagation of the surface polariton. The dispersion relation is

$$\kappa = \frac{\omega}{c} \left[\frac{\epsilon_{\parallel}(\omega)\epsilon_{\perp}(\omega) - \epsilon_{\parallel}(\omega)}{\epsilon_{\parallel}(\omega)\epsilon_{\perp}(\omega) - 1} \right]^{1/2}, \quad (4)$$

with the conditions $\epsilon_{\parallel}(\omega) < 0$ and $\kappa > \omega/c$.

The ATR spectra were measured using KRS-5 prisms. Mylar foils, 6.25 μm thick, were used as spacers for the air gap. The incident wave was polarized in the plane of incidence by a metal wire-grid polarizer on a KRS-5 substrate, and the wave vector along the prism-air interface was calculated from

$$\kappa = \frac{\omega}{c} n_p \sin \theta, \quad (5)$$

where $n_p = 2.4$ is the refractive index of the prism and θ is the internal angle of incidence. The reflected wave has intensity minima (absorption maxima) at frequencies which are obtained from the crossing points of the dispersion curves (2), (3), and (4) with the straight line (5). The theoretical and experimental results are given in Table 4.6.

It is interesting to note that the extraordinary surface polariton in the range 485–514 cm^{-1} (Case B2) is a virtual excitation. Its dispersion branch should terminate at some finite wave vector. The theoretical value of the termination point is $\kappa = 11,000 \text{ cm}^{-1}$. We have not been able to verify this because the wave vector higher than 11,000 cm^{-1} is not accessible by those prisms available in the market.

1. A. S. Barker, Jr., *Phys. Rev.* **132**, 1474 (1963).

2. A. Hartstein and E. Burstein, *Surf. Sci.* **34**, 81 (1973).

Table 4.6. Wave numbers (cm^{-1}) of surface polaritons.

Incident angle θ (degree)	Ordinary surface polaritons		Extraordinary surface polaritons			
	Case A		Case B1		Case B2	
	Calc	Exp	Calc	Exp	Calc	Exp
30	476	473	477	474	480	477
45	479	477	480	479	482	480
30					502	501
45					510	508
30	750	752	742	741	730	732
45	805	803	792	793	788	783

SUPERCONDUCTIVITY

FLUX-LINE PINNING BY THE GRAIN BOUNDARY IN NIOBIUM BICRYSTALS

H. R. Kerchner D. K. Christen
A. Das Gupta¹ S. T. Sekula
B. C. Cai² Y. T. Chou²

In recent years interest in flux-line pinning by grain boundaries has been rekindled for a variety of reasons. First, the grain-boundary/cell-wall structure is a major source of pinning in both Nb_3Sn and NbTi conductors, which presently dominate the superconducting-magnet market. Second, recent theoretical advances have inspired new hope that the observed pinning in polycrystals can be understood quantitatively. Third, the production of bicrystals of niobium by groups in the United States and the Soviet Union has made it possible to perform experiments on individual grain boundaries.

In an effort to obtain more information on flux-line pinning by grain boundaries, a collaborative investigation is currently under way involving members of the Solid State Division and the Metals and Ceramics Division at ORNL and a group at Lehigh University in Bethlehem, Pennsylvania. Niobium bicrystals grown at Lehigh³ have been investigated by measuring the lossless current flow on the grain boundary and the small-angle neutron scattering produced by flux-line lattices (FLL) in the superconducting mixed state.

Current-voltage relations were measured at 4.2 K in a conventional iron-core electromagnet. Although other procedures were sometimes used, typically a constant current larger than the critical value was applied at each field of interest, and the dc flux-flow voltage was measured at 0.1° intervals as the applied magnetic field was rotated. Elsewhere we also measured the inductive and resistive transitions at the critical temperature T_c of each sample in

zero field. Flux-line bending arising from the presence of a transport current was determined by studying the neutron rocking-curve width measured with the 30-m spectrometer at the National Center for Small-Angle Scattering Research (NCSASR).

The flux-flow voltages observed in the current-voltage measurements always dipped sharply when the angle τ between the grain boundary and the applied field was less than $1-2^\circ$. Outside this range the voltage was nearly independent of τ and almost proportional to the current, indicating a small bulk critical current. The voltage dips (critical-current peaks) showed fine structure that depended on the applied field and the magnitude and direction of the applied current. These observations indicate that the grain boundaries are not perfectly flat but instead consist of flat segments misoriented by small angles less than 1° . It was possible to match curved flux lines roughly to the segmented boundary as evidenced by the fact that a current level could be found (different for each sample and weakly field dependent) that produced a single, symmetric, and almost structure-free voltage dip.

The pinning force per unit area of grain boundary $F_b(\tau)$, deduced from the current-voltage measurements, for one of the samples investigated most extensively is shown in Fig. 4.11. Both the

Fig. 4.11. The peak value and the angle-integrated force per unit area of grain boundary vs the magnetic flux density B at 10 A total current. The flux density at the upper critical field B_{c2} is indicated on the abscissa. The inset shows the orientations of the two grains, the boundary, the applied field, and the positive current direction (corresponding to a positive pinning force).

peak pinning force $F_b(I_p)$ and the angle-integrated forces $F_b(I)dl$ are plotted as functions of the magnetic flux density. As indicated in the inset, when the applied field is parallel to the grain boundary, it is oriented in the $[100]$ direction of one grain and in the $[111]$ direction of the other. A large rectification effect is observed in this sample—the flux pinning is much stronger for flux-line motion from the $[100]$ grain into the $[111]$ grain than for movement in the opposite direction. This rectification drops to a very small level at the upper critical field, while the portion of the pinning force $F_p(I)$ that is nearly independent of flux-flow direction persists to higher fields. Although a small portion of this rectification arises from the grain boundary segmenting, the source of the major portion remains unclear at the present time. We believe that it must arise in some unknown way from the intrinsic anisotropy of the material.⁴

The observation of lossless currents on the grain boundary at fields above the bulk upper-critical field of niobium (slightly different for the two grains because of anisotropy) implies the existence of a localized superconducting state in this field range. No equivalent localized state could be observed in our simultaneous measurements of the inductive and resistive transitions in zero field. The extension of superconductivity on the grain boundary to fields above the upper critical field but not to temperatures above the bulk critical temperature strongly supports the notion that electron scattering by the grain boundary modifies the superconducting properties locally and contributes to the flux-line pinning. It would not, however, produce the rectification effect observed at lower fields.

In Fig. 4.12 the scattered-neutron intensity (for another sample) is plotted on the right as a function of rocking angle ϕ for two values of the total current. The form of the curves fitted to these data was calculated by assuming that the flux-line curvature arose from a uniform current, flowing axially through the cylindrical sample. Since a portion of the curvature arises from the current flowing nonuniformly on the grain boundary, the rocking curve widths plotted vs total current on the left lie between the calculated widths, based on the assumption that the flux-line curvature arises from a uniform current equal to the total current or that it arises from a uniform current equal to the total current less the portion flowing on the grain boundary. A more detailed investigation of the flux-line curvature awaits neutron measurements on samples having weaker bulk pinning so that the current actually flowing uniformly can be reduced. In addition, a full analysis of such data will require numerical calculations of the rocking-curve peaks based on a realistic model of the transport-current distribution. Of special interest is a neutron study of the discontinuity in the FLL symmetry expected at the grain boundary for the sample shown in Fig. 4.11.

To date we have investigated flux-line pinning by the grain boundary in two different niobium bicrystals using electrical techniques.

Fig. 4.12. Neutron rocking-curve peaks (shown on the right) due to scattering by the FLL in a Nb bicrystal. The rocking-curve width arises from the flux-line curvature associated with the presence of a transport current I . The I dependence of the rocking-curve width is shown on the left.

Two mechanisms for the pinning can be identified qualitatively: one is due to electron scattering by the grain boundary, and the other arises from anisotropy of the material. Preliminary measurements of the flux-line bending by neutron scattering suggest that such measurements can be used to test realistic models of the distribution of current flow in these samples.

1. Metals and Ceramics Division, ORNL.
2. Lehigh University, Bethlehem, Pa.
3. B. C. Cai, A. Das Gupta, and Y. T. Chou, *J. Less Common Metals* 86, 145 (1982).
4. H. R. Kerchner, D. K. Christen, and S. T. Sekula, *Phys. Rev. B* 21, 86 (1980).

INTERPRETATION OF THE FLL MORPHOLOGY IN SUPERCONDUCTING V_3Si

D. K. Christen H. R. Kerchner
S. T. Sekula

Measurements of the flux-line lattice (FLL) morphology in V_3Si using small-angle neutron diffraction have revealed correlations between the symmetries of the FLL and the real crystal, as well as a curious and somewhat complex dependence on the magnitude of the magnetic flux density.¹ At the same time, determinations of the FLL form factor indicate that the low-field ($B < 1T$) FL-FL interaction is quite simple, as

evidenced by a London-like behavior, with linear superposition of individual FL microscopic fields.^{2,3} In the London picture the FL core is assumed to be negligibly small, so that the FL-FL interaction depends only on the microscopic fields and supercurrents and is parametrized only by the magnetic field penetration depth λ . For V_3Si , this model should be a very good approximation for well-separated flux lines (i.e., at low flux density).

Conceptually, it is appealing to envision anisotropic FL interactions as arising from an anisotropic penetration depth $\lambda(\hat{r})$ in a generalized London model. Presently, we have analyzed the observed FLL morphology data using such a phenomenological approach and find the qualitative agreement presented below.

Since V_3Si has the A15 cubic structure, the procedure is to express the penetration depth, wherever it appears in the London interaction, as an expansion in ortho-normal cubic harmonic functions $H_n(\hat{r})$, $\lambda(\hat{r}) = \lambda[1 + \sum_{n=4,6,8} A_n H_n(\hat{r})]$. Then, the set of expansion coefficients A_n are found, which minimize the FLL free energy F for the observed FLL symmetry. This requires a sum over the FLL sites r_{mn} of the individual (anisotropic) FL-FL interaction energies $U[r_{mn}/\lambda(\hat{r}_{mn})]$, where

$$F = \frac{1}{2} \sum_{m,n} U[r_{mn}/\lambda(\hat{r}_{mn})],$$

and

$$U[r/\lambda(\hat{r})] = \phi_0^2 K_0[r/\lambda(\hat{r})]/8\pi^2 [\lambda(\hat{r})]^2.$$

Here, $\phi_0 = 2.07 \times 10^{-15} \text{ T-m}^2$ is the flux quantum, and K_0 is a modified Bessel function.

With this simple model, a set of three lowest order cubic harmonic coefficients can be found that describe the following experimental observations: (1) For the applied field H parallel to a $\langle 110 \rangle$ crystal axis, the FLL half unit cell is an isosceles triangle with its base aligned parallel to a $\langle 100 \rangle$ crystal axis. This configuration is shown in Fig. 4.13(a), along with a polar plot of the deduced anisotropy in the penetration depth in the (110) plane. (2) For $H \parallel \langle 001 \rangle$ crystal axis, the FLL is comprised of two types of FLL domains. For each domain, the half unit cell is an isosceles triangle with its base aligned along a crystal lattice $\langle 110 \rangle$ axis. This is shown in Fig. 4.13(b), along with the λ -anisotropy in the (001) plane. (3) For $H \parallel [110]$, the FLL symmetry changes with flux density B in such a way that the half unit cell is always isosceles, but the leg-to-base ratio crosses from $b/a > 1$ to $b/a < 1$ at $B = 0.1 \text{ T}$. This is shown in Fig. 4.14, where it is seen that the general features of the observations are described, but the agreement is only semiquantitative.

It should be pointed out that this general agreement requires $A_4 < 0$, $A_6 > 0$, and $A_8 < 0$, with details in the FLL symmetry depending sensitively on the particular values. The preliminary set of A_n used ($A_4 = -0.001$, $A_6 = 0.00045$, and $A_8 = -0.0005$) was found by trial and error and does not represent a global "best fit" to all the data. This latter procedure is quite

Fig. 4.13. The observed FLL morphology for (a) $H \parallel [110]$ and (b) $H \parallel [001]$. The anisotropy in λ that is found to stabilize these symmetries is shown on polar plots in each plane. The deduced magnitude of the anisotropy is $\Delta\lambda/\lambda = 0.005$.

involved and is probably not justified at present due to the crudeness of the model.

Work in progress entails finding a more realistic FL-FL potential derived from microscopic theory, with full inclusion of the fundamental anisotropies. In this way it may be possible to use the FLL morphology as a sensitive probe of the anisotropic material electronic-elastic properties.⁴

1. D. K. Christen et al., *IEEE Trans. Magn. MAG-19*, 884 (1983).
2. D. K. Christen et al., *Physica* 107d, 301 (1982).
3. D. K. Christen et al., *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 143.
4. The small λ -anisotropy responsible for the FLL symmetry should be manifested also in variations of the FLL form factor with different FLL reflections. However, these small differences cannot be resolved in the form factor data. See D. K. Christen et al., "Absolute Determination of the Temperature-Dependent Penetration Depth in Superconducting V_3Si ," this report.

Fig. 4.14. The observed FLL symmetry as a function of flux density B , for Hf [110], and $T = 4.85$ K. The points of the model interaction were determined numerically by minimizing the FLL free energy for a given λ -anisotropy in the interaction potential. The dashed line is a guide for the eye.

ABSOLUTE DETERMINATION OF THE TEMPERATURE-DEPENDENT PENETRATION DEPTH IN SUPERCONDUCTING V_3Si

D. K. Christen H. R. Kerchner
S. T. Sekula Y. K. Chang

The temperature-dependent penetration depth $\lambda(T)$ is the fundamental length that describes the spatial variation of a static magnetic field within a superconductor, including the field decay from the core of an isolated flux line (FL) in a type-II superconductor in the mixed state. The penetration depth has been the subject of extensive investigation in a number of superconducting pure materials and alloys.¹ Few experimental techniques enable an absolute determination of λ ; usually one may obtain only relative changes with temperature. We have shown that for an extreme (high- κ) type-II superconductor, such as V_3Si , it is possible to measure $\lambda(T)$ absolutely from the low-field flux-line lattice (FLL) form factor F_{hk} , which is extracted from the intensity of neutrons diffracted at small angles from the FLL.² At low field, $|F_{hk}| = (1 + \lambda^2 K_{hk}^2)^{-1/2}$. Here, K_{hk} is the FLL reciprocal space vector for the reflection hk . Since this technique provides an absolute determination, it enables a direct comparison to the predictions of microscopic theory. Here we compare the observed λ to the BCS theory and its modifications due to many-body effects.

In Fig. 4.15, the data are plotted in reduced form as a deviation function with respect to the temperature dependence of the two-fluid model of superconductivity. The solid curve is the BCS theory for a clean high- κ material and is seen to deviate from the data. It is known that both impurity scattering and the effects of strong electron-phonon coupling can result in such deviations. We have evaluated the impurity contribution using the measured resistivity, along with the best available data for the coherence length ξ_0 and the Fermi-surface area,^{3,4} to obtain the impurity parameter $\alpha = 0.882 \xi_0 / \lambda = 0.20$, where λ is the electron-transport mean-free path. Within the context of the BCS theory deviations cannot be explained by this impurity correction alone as indicated by the dashed curve. To include the effects of strong coupling, we have used the technique of scaling the temperature-dependent gap where it appears in the BCS expressions. This procedure is a good approximation if the strong-coupling correction factor $\eta_\Delta(T)$ for the gap parameter $\Delta(T)$ is only weakly temperature-dependent.⁴ The result of such a fit is shown in Fig. 4.15, where we have included the combined effects of strong coupling and impurity scattering. From this we obtain, $\eta_\Delta = \Delta(0)/\Delta(0)_{\text{BCS}} = 1.10 \pm 0.02$, or $2\Delta(0)/k_B T_C = 3.88 \pm 0.07$. This new value seems to agree with, but lie near the upper range of, previous determinations found by a variety of experimental techniques.

Fig. 4.15. The experimental results plotted as a reduced deviation function with respect to the two-fluid model. Solid curve: BCS London limit. Dashed curve: BCS theory corrected for the observed impurity scattering. Dash-dot curve: BCS theory corrected for strong coupling as well as impurity effects.

From the measured absolute penetration depth at low temperature, we obtain the London penetration depth $\lambda_L(0) = 91.6 \pm 2.5$ nm. The value $\lambda_L(0)_{\text{BCS}} = 57$ nm, found using unrenormalized properties calculated from band theory,⁵ would imply an anomalously large electron-phonon coupling constant $\lambda_{\text{ep}} = 1.6$. This observation is consistent with a previously recognized problem in vanadium-based compounds and may be reconciled by more subtle effects such as spin fluctuations, anisotropy, a sharply peaked density of states at the Fermi level,^{4,5} or by Fermi-liquid effects discussed below.

It has been recognized recently that quasi-particle interactions (in addition to the electron-phonon mediated interaction) may be necessary for an adequate description of many high-field superconductors, including vanadium-based compounds.⁶ The Fermi-liquid theory, as formulated for superconductors,⁷ predicts a manifestation of quasi-particle interactions in the penetration depth of high- κ , relatively clean materials. We generalize this relation as follows,

$$\left(\frac{\lambda(0)}{\lambda(T)}\right)^2 = \left(\frac{\lambda(0)}{\lambda(T)}\right)_{\text{BCS}}^2 \left\{ 1 + \frac{F_1}{3} \left[1 - \left(\frac{\lambda(0)}{\lambda(T)}\right)_{\text{BCS}}^2 \right] \right\}^{-1}. \quad (1)$$

Here, F_1 is the lowest order, spin-independent Landau parameter of the Fermi-liquid theory. The asterisks on the BCS expressions indicate that they have already been renormalized by strong-coupling and impurity effects. Unfortunately, it is not possible to deduce an unambiguous F_1 from a fit to the data since Fermi-liquid and strong-coupling interactions produce similar changes in the temperature dependence of λ , and a "best" value for η_Δ is not well-defined. However, using Eq. (1) we may plot a locus of η_Δ and F_1 combinations that depicts the best fit to the data. This result is shown in Fig. 4.16. [Any combination of η_Δ and F_1 corresponding to this curve results in a $\lambda(T)$ which is virtually indistinguishable from the dot-dash curve of Fig. 4.15.] The band of F_1 values shown corresponds to the indicated approximate range of η_Δ values reported for V_3Si in the literature. All these η_Δ , however, have been determined under the implicit neglect of any Fermi-liquid effects. Also, it should be noted that a negative F_1 is probably unphysical, since all likely attractive interactions presumably have been included in the strong-coupling corrections. Thus, our data indicate only that, if spin-independent Fermi-liquid effects are important, V_3Si remains a strong-coupling superconductor with $\eta_\Delta > 1.10$ [$2\Delta(0)/k_B T_C > 3.88$].

1. R. Meservey and B. B. Schwartz, p. 117 in *Superconductivity*, Vol. 1, ed. by R. D. Parks, Marcel Dekker, New York, 1969.

2. D. K. Christen et al., p. 1035 in *Proceedings of the Seventeenth International Conference on Low-Temperature Physics*, ed. by U. Eckern et al., North-Holland, Amsterdam, 1984.

3. Y. Muto et al., *J. Low Temp. Phys.* **34**, 617 (1979).

Fig. 4.16. The locus of values for the strong-coupling factor η_Δ and Fermi-liquid parameter F_1 that best fits the data. The symbols are selected combinations at which least-squares fits to the temperature-dependent data were performed, the curve is an interpolation. The error bar represents the typical statistical error in the fitting procedure.

4. T. P. Orlando et al., *Phys. Rev. B* **19**, 4545 (1979).

5. A summary of several experimental and theoretical values is given in B. Mitrović and J. P. Carbotte, *Phys. Rev. B* **26**, 1244 (1982).

6. T. P. Orlando and M. R. Beasley, *Phys. Rev. Lett.* **46**, 1598 (1981).

7. A. J. Leggett, *Phys. Rev.* **140**, 1869 (1965).

FORMATION, ION MODIFICATION, AND ANNEALING OF SUPERCONDUCTIVE VN FILMS

J. R. Thompson¹ D. K. Christen
S. T. Sekula G. M. Beardsley²
D. H. Lowndes

Recently there has been a growing interest in the superconductive compound vanadium nitride. Several factors contribute to this interest, including a recent theoretical calculation³ concluding that spin fluctuations severely suppress the onset of superconductivity in this material. Also, VN_x crystallizes in a NaCl, B1 phase for $x > 0.7$; when damaged by neutrons, these materials tend to have smaller reductions in the superconductive transition temperature T_C than other high- T_C materials, especially those from the A15 family. For these reasons and others, we have investigated the formation and subsequent modification of VN using the

techniques of ion implantation, ion damage, laser quenching, and thermal annealing. A variety of material properties were investigated including T_C , the electrical residual resistance ratio (RRR) and resistivity ρ , and in some cases, the upper critical magnetic field, $H_{C2}(T)$.

Most of the materials investigated began as vanadium thin films of approximately 1000 Å thickness, deposited by electron-beam evaporation onto single-crystal sapphire substrates. Formation of the B1 VN phase was achieved by heating the samples to 1100°C in an atmosphere of nitrogen gas for a period of 10 min.

A number of independent preparations yielded VN films having T_C values in the range 6.6–8.6 K, resistance ratios of 1.2–2.3, and low-temperature resistivities ρ_0 of 70–20 $\mu\Omega\cdot\text{cm}$, respectively. Variations within and between batch preparations occurred for reasons that are not understood, although oxygen contamination and variations in stoichiometry may be contributing factors.

One aspect investigated was the influence of lattice damage on the superconductive properties of VN. This information is mandatory before potential application of B1 phase materials in a radiation environment. In this study VN films were damaged at ambient temperature by N-ion irradiation at 45 and 350 keV in order to provide an approximately uniform damage-energy profile.

The results of this study are shown in Fig. 4.17, a plot of T_C and RRR as a function of N-ion fluence. Data for two separate samples are included and are found to overlap quite well. Both T_C and the resistance ratio have a region of rapid decrease followed by a saturation at higher fluence. In the saturation region, the resistivity is temperature independent at $\sim(124\text{--}140)\ \mu\Omega\cdot\text{cm}$. The degradation of T_C toward its equilibrium value with fluence can be described by a simple exponential decay function; the decay constant corresponds to a fluence of 0.7×10^{15} N-ions/cm². Using damage energy calculations obtained from the computer code

Fig. 4.17. The superconductive transition temperature T_C of VN plotted vs N-ion fluence. The solid line is an exponential function fitted to the data.

E-DEP-1 and assuming bulk atomic densities, this fluence is equivalent to an average damage energy of 11 eV per VN molecule.

Other researchers have shown previously⁴ that the superconductive transition temperature T_C in bulk VN_x increases rapidly with nitrogen content x . Thus, in a separate series of experiments, N ions were implanted into VN films (at 77 K) in order to increase x (calculated from T_C) to 1.00, 1.05, and 1.11. In addition, another film was ion damaged by irradiation with 2×10^{16} Ne-ions/cm² at 160 keV. We found that the damage due to irradiation dominated any change in T_C arising from alloying. For the nitrogen-implanted films, T_C decreased to the range 2.9–3.8 K, while the temperature-independent resistivities increased to 100–110 $\mu\Omega\cdot\text{cm}$. A theoretical calculation³ of T_C in several B1 phase nitrides concluded that in VN the T_C would be near 30 K in the absence of spin fluctuations, which depress T_C substantially. While one can speculate that disorder might suppress the spin fluctuations and thereby enhance T_C , the present results show that the aggregate effect is a reduction of the transition temperature due to accumulated radiation damage.

To remove deleterious lattice damage, two series of annealings were undertaken. In one series, short pulses of excimer laser light ($\lambda=248$ nm, $\tau=30$ ns) were used to heat a VN film affixed to the cold finger of an optical cryostat. With increasing laser-energy density, we observed first a small increase (0.4 K) in T_C and then a decrease in T_C and rise in film resistance due to laser-induced damage.

A second series of thermal annealings was carried out with samples both in vacuo and under one atmosphere of N₂ gas. Isochronal anneals of 10-min duration were made in steps of 100°C in the same furnace used for the nitriding process. At least three fairly distinct stages were observed. By 500°C, the materials, whether vacuum or atmosphere annealed, exhibited a partial recovery of T_C to 4.4–4.8 K while the RRR remained very nearly unity. At 700–800°C, the T_C 's recovered additionally to 7.2–7.8 K. This was accompanied by an increase in RRR to ~ 1.3 . For the vacuum-annealed VN films, annealing at still higher temperature $T_A \approx 1000^\circ\text{C}$ produced a rapid decrease in T_C and deterioration of the RRR, which can be attributed to decomposition of the film, based on the existing equilibrium temperature-composition-pressure data.⁵ For the material annealed in a nitrogen atmosphere, however, T_C continued to increase slowly with T_A up to 1300°C and then dropped rapidly following higher temperature anneals. There are several mechanisms which may account for this; however, the present information is insufficient to distinguish between them. In future work complementary x-ray diffraction studies will be performed to obtain positive identification of crystallographic phase, lattice constant, line width, etc. In addition, the effect of contaminants such as C and O will be explored.

1. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.

2. Oak Ridge Associated Universities faculty research participant from Millsaps College, Jackson, Miss.

3. H. Rietschel, H. Winter, and W. Reichardt, *Phys. Rev. B* **22**, 4284 (1980).

4. F. I. Ajami and R. K. MacCrone, *J. Phys. Chem. Solids* **36**, 7 (1975).

5. N. Kieda et al., *J. Less Common Metals* **99**, 131 (1984).

FORMATION OF SUPERCONDUCTIVE $\text{Al}(\text{GeSi})$ ALLOYS BY LOW-TEMPERATURE LASER-QUENCHING METHODS¹

J. R. Thompson² S. T. Sekula
D. H. Lowndes H. R. Khan³

Highly disordered, superconductive alloys of Al with the group-IV elements Ge and Si have been formed by rapid quenching to cryogenic temperatures. In this investigation, the starting materials were finely grained, multi-phase alloys with compositions $\text{Al}_{0.7}\text{Ge}_{0.3}$ and $\text{Al}_{0.7}\text{Ge}_{0.15}\text{Si}_{0.15}$. Metastable materials with enhanced superconductive transition temperatures T_c were produced by very rapid cooling of the surface layer, previously heated by a short burst of light from an excimer laser ($\lambda=248$ nm, $\tau=40$ ns). The experiments were performed in an optical cryostat permitting in situ four-terminal resistive determination of T_c as a function of incident laser-energy density E/A . Quenching the material to liquid-helium temperatures maximizes the quench rate and more importantly reduces the likelihood of any structural rearrangement.

Before irradiation, the ternary alloy had a residual resistance ratio of 1.6 with resistivity $\rho(300\text{ K})$ of approximately $170\text{ }\mu\Omega\text{-cm}$ and $T_c = 2.9\text{ K}$. The corresponding values in $\text{Al}_{0.7}\text{Ge}_{0.3}$ were 2.6, $30\text{ }\mu\Omega\text{-cm}$, and 1.9 K . Irradiation using low-energy pulses with $E/A < 0.2\text{ J/cm}^2$ had little effect on T_c . As the energy density was increased beyond the threshold value of $0.20\text{--}0.25\text{ J/cm}^2$, however, T_c increased rapidly. Its maximum values (T_c onset) were 8.0 K in the ternary alloy and 6.4 K in the binary. The superconductive behavior of $\text{Al}_{0.7}\text{Ge}_{0.3}$ alloys produced by other rapid quenching techniques reveals similar T_c values and suggests that slightly higher T_c values may be correlated with higher quench rates.

The alloy's surface temperature at the end of the laser pulse can be estimated. Assuming negligible reflection of the UV light, we find that 0.25 J/cm^2 is required to heat the Al-rich phase of $\text{Al}_{0.7}\text{Ge}_{0.3}$ to the melting point of the eutectic. Comparing this with the energy threshold discussed above leads us to conclude that the higher T_c surface layer is highly disordered material formed by rapid solidification and quenching from the liquid state.

1. Summary of paper: p. 1265 in *Proceedings of the 17th International Conference on Low-Temperature Physics*, ed. by U. Eckern et al., North-Holland, Amsterdam, 1984.

2. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.

3. Institut für Edelmetalle und Metallechemie, Schwäbisch Gmünd, Federal Republic of Germany.

SUPERCONDUCTING PROPERTIES OF A SPUTTERED W FILM

J. T. Ellis¹ J. R. Thompson²
L. D. Hulet³ S. T. Sekula

The use of W films as a moderator for generating monoenergetic positrons is currently under investigation in the ORNL Analytical Chemistry Division. In a collaborative effort, the superconducting properties of a W film prepared by sputtering in argon were studied in order to characterize the material since it is well known that the superconducting transition temperature T_c is extremely sensitive to details of sample preparation. T_c of pure bulk W is 0.015 K , while T_c in thin films has been reported to vary from 1 to 5 K .

A sputtered film $\sim 10^{-6}\text{ m}$ in thickness was investigated in apparatus described elsewhere.⁴ The superconducting transition temperature T_c defined as the midpoint of the resistive transition was found to be 3.68 K in agreement with earlier work.⁵ The breadth of the transition was large with $\Delta T_c = 0.33\text{ K}$ and, coupled with studies of the transition at lower temperatures in a magnetic field, suggests that the sample is inhomogeneous. The normal state resistivity of the material at 4.2 K was $\rho = 110\text{ }\mu\Omega\text{-cm}$ with a weak metallic temperature dependence. X-ray diffraction studies indicate a body-centered cubic structure.

Attempts to remove the suspected occlusions of argon in the sample by high-temperature annealing under UHV conditions with subsequent low-temperature studies are planned.

1. Graduate laboratory participant from The University of Tennessee, Knoxville, Tenn.

2. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.

3. Analytical Chemistry Division, ORNL.

4. J. T. Ellis et al., "Apparatus for Galvanomagnetic Studies of Metals," this report.

5. P. H. Schmidt, *J. Vac. Sci. Technol.* **10**, 611 (1973).

FERROMAGNETISM IN Ni_3Al -BASED ALLOYS CONTAINING Fe¹

S. T. Sekula H. R. Kerchner
J. R. Thompson²

A study has been undertaken on the magnetic properties of a series of alloys produced by substituting Fe in Ni_3Al . The alloys, which were fabricated by the Metals and Ceramics Division of ORNL, crystallize in the Cu_3Au -type L_{12} structure. The materials are of interest

for both technical and fundamental reasons. Technically, they constitute a set of superalloys which possess desirable high-temperature strength and corrosion properties.³ Since it is well known that magnetic energies can affect substantially the stability of equilibrium, crystalline phases, we have determined the Curie temperature and spontaneous magnetization of these alloys. Fundamentally, interest arises from the fact that the binary alloy $\text{Ni}_3\text{Al}_{(1-y)}$ is highly polarizable and forms an itinerant weakly ferromagnetic system⁴ for Ni contents greater than the critical concentration, 74.5 at. %. Substitution of Fe into the easily magnetized matrix produces a quite large collective moment (a "giant moment") and rapidly leads to a more conventional strongly ferromagnetic system.

The experimental investigations were carried out using two locally developed vibrating sample magnetometers (VSM's): a low-temperature model covering the range 4.2–100 K and a high-temperature unit⁵ covering 77–800 K. Physically the samples were either thin slabs or cylinders with masses of 100–500 mg. The Fe was introduced stoichiometrically (that is, 2n Fe atoms were accommodated by removing n Ni and n Al atoms) at concentrations of 0, 1, 3, 6, 10, 15, and 20 at. % Fe. To determine the Curie temperature, the disappearance of spontaneous magnetization was detected in most cases by sweeping the temperature in the presence of a weak magnetizing field and/or the use of Arrott plots.

The measured Curie temperatures are shown as a function of Fe concentration in Fig. 4.18. One notes that T_C initially increases very rapidly with the addition of Fe to the Ll_2 -structure material but that it becomes nearly independent of Fe content for concentrations >10 at. %. For the 10- and 15-at. %-Fe alloys, the ferromagnetic transition in the Ll_2 phase material was also detected by observing an anomaly in the thermal-expansion coefficient.⁶ These T_C values determined by x-ray techniques are also shown on

Fig. 4.18. The Curie temperature T_C of $\text{Ni}_3\text{Al}(\text{Fe})$ alloys vs Fe concentration in at. %.

Fig. 4.18 for comparison, where quite good agreement in the Curie temperature is obtained for the 10%-Fe alloy. For the 15% alloy, a significantly higher value for T_C is obtained magnetically. This difference is not well understood, but may be associated with the appearance in the sample of a second magnetic phase having another much higher Curie temperature (~700 K). It was subsequently learned that a second physical phase, enriched in Fe, had been detected using transmission electron microscopy. At 20 at. % Fe, the high- T_C second phase constituted a larger fraction of the magnetic signal, as one would expect once the Fe solubility limit is exceeded. Included in Fig. 4.18 are the T_C values for the second phase, whose identity is not yet established.

From the low-temperature data for the spontaneous magnetization, the average magnetic moment per Fe atom, μ_{Fe} , was obtained. In Fig. 4.19, the values of μ_{Fe} at 4.2 K (effectively $T = 0$, since $T \ll T_C$) are shown as a function of Fe concentration. A giant moment of 17 μ_B per Fe is observed for the alloy with 1 at. % Fe. With increasing concentration, μ_{Fe} decreases dramatically to 4.9 μ_B for the material with 10 at. % Fe; even here, the moment is substantially larger than that in pure bcc iron, 2.2 μ_B . This rapid decrease in magnitude of the giant moment is attributed primarily to two factors. First, one expects that as the Fe concentration is increased, the extended polarization clouds surrounding Fe moments will suffer increased overlap, which results in a lower average μ_{Fe} . Second, the composition of the matrix " Ni_3Al " increasingly deviates from its nearly stoichiometric value and may become less polarizable. Macroscopically, we find that the saturation moment per gram of alloy first increases rapidly with Fe content and then

Fig. 4.19. The giant moment per Fe atom μ_{Fe} , deduced from the low-temperature spontaneous magnetization of $\text{Ni}_3\text{Al}(\text{Fe})$ alloys vs Fe concentration in at. %.

varies almost linearly with concentration above 6 at. %. Interestingly, this behavior persists even for the 15- and 20-at. % alloys, which contain the second, higher T_C phase.

We conclude by noting that a recent self-consistent renormalization theory seems to describe well Fe-free, Ni_3Al -type, weak ferromagnetic systems. Its applicability appears, however, to be much more limited in regard to the systems investigated here. Although ill-suited for describing the higher concentration Fe alloys, testing of the theory on lower concentration alloys must await further experimental study.

1. Summary of paper to be published.
2. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.
3. C. T. Liu et al., Initial Development of Nickel and Nickel-Iron Aluminides for Structural Uses, ORNL-6067 (August 1984).
4. H. Sasakura, K. Suzuki, and Y. Masuda, J. Phys. Soc. Japan 53, 854 (1984).
5. S. T. Sekula et al., "High-Temperature Vibrating Sample Magnetometer (HTVSM)," this report.
6. T. Leventouri, O. B. Cavin and, J. S. Faulkner (to be published).

MAGNETIC INVESTIGATION OF $CePO_4$

J. T. Ellis¹ J. R. Thompson²
S. T. Sekula L. A. Boatner

The magnetic properties of rare-earth orthophosphates have been a subject of interest for some time. Wang and Feigelson^{3,4} have reported quite high Néel temperatures (225 to 505 K) for $GdPO_4$, $TbPO_4$, and $DyPO_4$, while a Néel temperature of 88 K has been reported⁵ for $CePO_4$. In view of the many interesting properties of Ce-based compounds and alloys and the technical importance of the rare-earth orthophosphates, we have investigated the bulk magnetic properties of $CePO_4$.

Two methods were utilized in preparing the material: a urea preparation which produced a fine, white powder, while larger black crystals (powdered prior to measurement) were flux grown. The magnetic susceptibility of $CePO_4$ was determined as a function of temperature from 1.5 to 90 K using a vibrating-sample magnetometer. In the range investigated, susceptibility of the material is described by a sum of a Curie term and a temperature-independent term: $\chi(T) = (C/T) + \chi_0$, with $C = 0.277 \text{ cm}^3 \text{ K/mole}$ and $\chi_0 = 2.19 \times 10^{-2} \text{ cm}^3 \text{ mole}^{-1}$. From the Curie constant, an effective moment, μ_{eff} , of 1.49 μ_B per Ce ion is obtained. This value is lower than that given by Hund's rule (2.54 μ_B) for Ce^{3+} . When analyzing the data in the Curie-Weiss model (that is, plotting χ^{-1} vs T) the resulting curve goes smoothly to zero as T goes to zero, indicating no antiferromagnetic behavior. Despite the strikingly different physical appearance, the materials with different preparation display very similar magnetic behavior.

Qualitatively, the observed results may arise from crystal-field splitting of the Ce^{3+} levels. The temperature dependence with a reduced effective moment is due to the lowest lying levels split by the crystal field. Levels split by energies $\gg kT$ would produce a temperature independent Van Vleck susceptibility, as observed. It appears that the erroneous report⁵ of an 88 K Néel temperature (actually a Curie-Weiss intercept) resulted from a neglect of this temperature independent susceptibility, since the experimental data are in reasonable agreement where they overlap.

1. Graduate laboratory participant from The University of Tennessee, Knoxville, Tenn.
2. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.
3. F. F. Y. Wang and R. S. Feigelson, p. 77 in Proceedings of the Fourth Conference on Rare-Earth Research, ed. by L. Eyring, Gordon and Breach, New York, 1964.
4. F. F. Y. Wang, Phys. Status Solidi 14, 193 (1966).
5. F. D. Strygley and L. K. Wilson, Bull. Am. Phys. Soc. 24, 104 (1979).

APPARATUS FOR GALVANOMAGNETIC STUDIES OF METALS

J. T. Ellis¹ J. R. Thompson²
D. K. Christen S. T. Sekula

Measurements of electrical transport phenomena in superconductors and other metallic systems in a magnetic field are of considerable interest. While the primary purpose of this newly constructed apparatus is to characterize the temperature dependence of the upper critical field, $H_{C2}(T)$, of superconducting foils and films, studies of localization effects in highly disordered metallic systems as well as heavy-fermion effects in mixed-valence materials³ are anticipated.

The system provides for measurements [e.g., $H_{C2}(T)$, Hall voltage, and magnetoresistance] in magnetic fields up to 8.0 T in a temperature range 1.5–300 K and utilizes a high-homogeneity superconducting solenoid. Temperature control above 4.2 K is achieved by controlling the flow rate of cold He gas across the sample in combination with an electrical heater mounted on the sample holder. An Allen-Bradley carbon sensor serves to vary the heater power in order to obtain good temperature regulation. For operation below 4.2 K, liquid He is admitted into the sample chamber, and the pressure above the bath is controlled. Thermometry from 1.5 to 40.0 K is provided by a field-insensitive carbon glass sensor and from 40 to 300 K by a Pt sensor, both mounted on the sample holder.

Figure 4.20 shows some experimental data of $H_{C2}(T)$ vs T for an "as prepared" VN film with a thickness of 132 nm. In this case the sample was oriented with its surface perpendicular to the variable magnetic field. Using a four-contact method the superconducting-to-normal resistive transition was investigated at various

Fig. 4.20. The upper critical field, H_{c2} , as a function of temperature, T , for a VN film. The solid curve is derived from the theory of Ref. 4 in the dirty limit.

temperatures. The transition temperature T_c was found to be 6.7 K. We also measured a low-temperature, normal-state resistivity of $52.6 \mu\Omega\text{-m}$ and a residual resistance ratio $R_{300K}/R_{6K}=1.22$. As seen in the figure, the data can be adequately fit to the theory of Werthamer et al., in the dirty limit,⁴ neglecting Pauli-paramagnetic limiting and spin-orbit scattering effects.

1. Graduate laboratory participant from The University of Tennessee, Knoxville, Tenn.

2. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.

3. S. H. Liu and K.-M. Ho, *Phys. Rev. B* 28, 4220 (1983).

4. N. R. Werthamer, E. Helfand, and P. C. Hohenberg, *Phys. Rev.* 147, 295 (1966).

HIGH-TEMPERATURE VIBRATING-SAMPLE MAGNETOMETER (HTVSM)

S. T. Sekula H. R. Kerchner
D. K. Christen J. R. Thompson¹

A vibrating-sample magnetometer has been designed and constructed to permit magnetization investigations of condensed matter in fields up to 6.0 T over a temperature interval from -80 to 800 K. The primary motivation for this construction was to provide an overlap capability with an existing low-temperature vibrating-sample magnetometer² (LTVSM) for investigations

of the normal-state magnetic properties of Al₅ superconductors well above the superconducting transition temperature. At these higher temperatures, the inherently larger heat capacities and the decrease in sensitivity of cryogenic thermometers result in diminished performance of the LTVSM.

The new apparatus employs a sixth-order superconducting solenoid mounted in a helium cryostat designed to provide a "high-temperature" access volume. Pickup coils are positioned in the region of uniform magnetic field. Magnetization samples mounted in a capsule on the lower end of a drive rod are mechanically vibrated between the pickup coils by means of a transducer at the head of the cryostat. The sample can be thermally isolated from the pickup coils and electrically heated to temperatures in excess of 700 K. A Pt film resistor serves as a thermometer and as a sensor for temperature regulation. The sensitivity of the instrument is calibrated using a pure Ni sphere. This apparatus has been successfully employed in a study of magnetic phase transitions in a series of Ni₃Al(Fe) compounds.³

1. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.

2. S. T. Sekula and J. R. Thompson, *Solid State Div. Prog. Rep.*, September 30, 1981, ORNL-5850, p. 183.

3. S. T. Sekula, H. R. Kerchner, and J. R. Thompson, "Ferromagnetism in Ni₃Al-Based Alloys Containing Fe," this report.

ERRORS DUE TO FIELD NONUNIFORMITY IN VIBRATING-SAMPLE MAGNETOMETRY¹

H. R. Kerchner S. T. Sekula
J. R. Thompson²

Vibrating-sample magnetometers are widely used for measuring the magnetic properties of materials. We have identified errors that can sometimes arise in such measurements due to the nonuniformity of the magnetizing field. The effect of concern is caused by the time variation of the magnetic field in the reference frame of a moving sample when the field is not perfectly uniform. This time-varying field induces eddy currents in highly conductive or superconducting samples. The magnetization connected with the eddy current produces a spurious signal that cannot be distinguished from the desired signal arising from the dc magnetization.

For most samples in any reasonably uniform field, the spurious signal is only a negligible fraction of the total. In certain special situations, such as the case of a moderately hysteretic, high-field superconductor near its upper critical field, the spurious signal can seriously affect the measurement. In this regime the dc magnetization of the sample is small, and the ac field seen by the sample can be comparable to the dc magnetization. The induced eddy currents can mimic a magnetization

similar in magnitude to the small dc magnetization of the sample. A small degree of flux pinning (and associated magnetic hysteresis) can enhance the eddy currents, exacerbating the situation.

Our experimental work began with an uncompensated solenoid. The error was identified in one case as a spurious 2.5-mT paramagnetic displacement of the measured magnetization near the upper critical field (1.45 T) of a NbZr alloy superconductor. Adding additional windings in order to compensate the solenoid to fourth order reduced the 2.5-mT error by about a factor of 40 to a negligible level for this relatively extreme example.

1. Summary of paper: *Rev. Sci. Instrum.* 55, 533 (1984).

2. Adjunct research and development participant from The University of Tennessee, Knoxville, Tenn.

MASS AND CHARGE TRANSPORT IN MATERIALS

APPROXIMATE FORMULAS FOR THE AMPLITUDE AND PHASE OF THE INFRARED REFLECTANCE OF A CONDUCTOR¹

F. A. Modine D. Y. Smith²

Several approximate formulas are known for the specular reflectance at normal incidence of infrared light from a conductor in the Drude free-electron model. Most of these formulas are well established, but often they are applied outside their range of validity, and some of them contain minor errors or approximations that are unnecessarily poor. Moreover, the approximations describe only the behavior of the reflectance amplitude. Little or no attention has been given to approximations for the phase change on reflection in the infrared, despite the fact that such phase information is required (along with reflectance amplitude) to determine optical constants. In this paper, approximations to both the amplitude and phase are derived in a unified manner by a straightforward method that clarifies the accuracy of the results. The more accurate approximations are valid to frequencies as high as half the screened plasma frequency, but simpler versions are shown to hold over more restricted ranges. Several significant improvements over the classical approximations to the reflectance amplitude are obtained.

The approximations to the amplitude r and phase θ of the infrared reflectance follow from a series expansion of the logarithm of the reflectance expressed in terms of the complex refractive index $N = n + ik$:

$$\begin{aligned} \ln(r) + i\theta &= \ln[(N-1)/(N+1)] \\ &= -2 \sum_{j=0}^{\infty} 1/[(2j+1)N^{2j+1}] \quad (1) \end{aligned}$$

If N is large, the first term of the series is a good approximation to the sum, and the errors are approximately given by the neglected third-order term. Thus, if $|N|$ is as large as 4, $|\delta r| = |\delta\theta| < 0.01$, while if $|N|$ is as large as 9, $|\delta r| = |\delta\theta| = 0.001$.

The Drude complex dielectric function ϵ may be substituted for the refractive index:

$$N^2 = \epsilon = \epsilon_0 - (\omega_p^2/\omega)/(\omega + i\gamma) \quad (2)$$

where ω_p is the plasma frequency, γ is the relaxation frequency, and ϵ_0 is a "background" dielectric function, constant in the infrared, which arises from transitions at higher energies. If only the lowest order terms in ω_p^{-2} are retained, the following formulas are obtained:

$$\begin{aligned} \ln[r(\omega)] &= \tau(\omega/2\pi\sigma)^{1/2} [(1+\omega^2/\gamma^2)^{1/2} + \omega/\gamma]^{1/2} \\ \theta(\omega) &= \tau(1+(1-\delta/\epsilon_0)(\omega^2/\omega_s^2)[2 \pm (1+\gamma^2/\omega^2)^{1/2}])^{1/2} \quad (3) \end{aligned}$$

where $\sigma = \omega_p^2/(4\pi\gamma)$ is the conductivity, $\omega_s = \omega_p/\sqrt{\epsilon_0}$ denotes the screened plasma frequency, and the parameter $\delta = 2/3$ when the contribution of the third-order term of Eq. (1) is included. Equation (3) is nearly equivalent to a formula obtained by Bennett and Bennett,³ except that δ has been properly identified as 2/3 rather than 1, and the expression for $\theta(\omega)$ is obtained also.

Simpler expressions applicable to more restricted frequency ranges are easily obtained from Eq. (3). At very low frequencies where $\omega \ll \gamma < \omega_s$, an improved version of the well-known Hagen Rubens⁴ approximation is obtained along with its companion expression for the phase shift:

$$\begin{aligned} \ln[r(\omega)] &= \tau(\omega/2\pi\sigma)^{1/2} \quad (4) \\ \theta(\omega) & \end{aligned}$$

When $\omega \ll \omega_s/2$, Eq. (3) reduces to

$$\begin{aligned} \ln[r(\omega)] &= \tau(\omega/2\pi\sigma)^{1/2} \\ \theta(\omega) &= \tau[(1+\omega^2/\gamma^2)^{1/2} + \omega/\gamma]^{1/2} \quad (5) \end{aligned}$$

and at higher frequencies where $\gamma < \omega \ll \omega_s/2$,

$$\ln[r(\omega)] = -\omega_p/4\pi\sigma \quad (6)$$

$$\theta(\omega) = 2\omega/\omega_p \quad (7)$$

Equation (5) corresponds to the approximation of Kronig,⁵ and Eq. (6) is an improved version of the Dingle⁶ approximation. In general, the approximations here to $\ln[r(\omega)]$ are more accurate than the original expressions. Figure 4.21 compares several approximate formulas for the reflectance amplitude and phase with exact Drude-theory results in two illustrative cases.

1. Summary of paper: *Journal of the Optical Society of America* (in press).
2. Argonne National Laboratory, Argonne, Ill.
3. H. E. Bennett and J. M. Bennett, "Validity of the Drude Theory for Silver, Gold and Aluminum in the Infrared," p. 175 in *Optical Properties and Electronic Structure of Metals and Alloys*, ed. by F. Abeles, North-Holland, Amsterdam, 1966.

Fig. 4.21. A comparison of approximate formulas for the reflectance amplitude and phase with Drude theory results. The solid curves are computed from Drude theory; the more accurate approximations derived in this work are represented by alternating dots and dashes (M-S); the long dashes represent the approximation of Bennett and Bennett (B-B); the short dashes represent the approximation of Kronig (K) and a corresponding approximation to the phase; the dotted curves represent the Hagen-Rubens approximation (H-R) and its phase counterpart; and the approximation of Dingle is equivalent to that of Kronig when $\omega \gg \gamma$.

4. M. Born and E. Wolf, *Principals of Optics*, Pergamon Press, New York, 1975.

5. R. de L. Kronig, *Proc. Roy. Soc. (London)* A 133, 255 (1931).

6. R. B. Dingle, *Physica* 19, 311 (1953).

OPTICAL PROPERTIES OF TiC AND ZrC FROM THE INFRARED TO THE NEAR ULTRAVIOLET¹

F. A. Modine C. Y. Allison²

The transition-metal carbides are extremely hard, stable at high temperatures, and in some cases superconducting. These properties have prompted interest in both the electronic transport and electronic structure of the materials. In this work the optical properties of TiC and ZrC were investigated. Optical properties have been previously studied by others. However, sizable inconsistencies are found in the earlier optical data for TiC; the only available optical data for ZrC are reflectance measurements made on polycrystalline material, from which no optical functions were computed. The optical results of this study span the spectral region from the far infrared to the near ultraviolet. Information about electronic transport is contained in the far infrared spectra, where optical properties are contributed by free carriers. At shorter wavelengths, the optical properties are contributed by interband transitions that yield information about electronic structure. The results here are based upon both reflectance and ellipsometry measurements. The combination allows optical functions to be computed reliably from the limited spectra, and it provides a consistency check on the results.

The crystals were grown by the rf float-zone technique. Thin triangular platelets having dimensions of 5–10 mm on a side and no preferential crystallographic orientation were cut from crystalline rods. The platelets were mechanically polished with diamond grits and then electropolished. Optical reflectance was measured with a Cary Model 17D between 0.5 and 6.5 eV and with a Perkin Elmer Model 580 spectrophotometer between 0.03 and 0.5 μ . Ellipsometric measurements were made between 1.2 and 4.6 eV with a scanning photometric instrument.

The reflectance spectra of TiC and ZrC are similar. The reflectance of ZrC is shown in Fig. 4.22. At lowest energies the reflectance of the materials drops precipitously rather than exhibiting the plateau characteristic of a classical metal. This behavior reveals strong interband transitions at relatively low energies. Above about 2 eV the reflectance drops more slowly, and broad structure associated with interband transitions is seen.

Both the reflectance and its phase are required to compute the optical constants and dielectric functions. The reflectance phase for ZrC is shown as the inset of Fig. 4.22. The phase was computed from the reflectance amplitude; agreement with the phase found from the ellipsometry is achieved by adding a correction proportional to energy to the phase calculated

Fig. 4.22. Reflectance and reflectance phase for ZrC. The inset shows the phase obtained by correcting a Kramers-Kronig inversion of the reflectance amplitude as a dashed line and the phase computed from ellipsometric data as a solid line. The dashed reflectance curve is from measurements on polycrystalline ZrC by Alward et al.³ and the solid line is the reflectance of ZrC_{0.89} measured in this work.

by Kramers-Kronig inversion of the reflectance data. Dielectric functions were computed from the reflectance amplitude and phase, and results for ZrC are shown in Fig. 4.23.

In spite of the low-energy interband contributions to the optical spectra, it is possible to obtain transport parameters from the data that agree exceptionally well with the results of electrical measurements.³ The parameters fitted to the optical conductivity are compared with those obtained from electrical measurements

Fig. 4.23. The real and imaginary parts of the dielectric function of ZrC.

in Table 4.7. The excellent agreement increases confidence both in the results and in the conclusions drawn from them. The free-electron conduction is adequately described as due to a single carrier with an effective mass near unity. The parameters of Table 4.7 can be used to separate the intraband and interband contributions to the optical data. In the case of ZrC, such a separation reveals more electronic states at low energies than are found in empirical pseudopotential calculations.³

1. Summary of paper to be published.
2. Oak Ridge Associated Universities faculty research participant from Oklahoma State University, Stillwater, Okla.
3. F. A. Modine and T. W. Haywood, "Electrical Properties of Titanium Carbide and Zirconium Carbide," this report.
4. J. F. Alward et al., *Phys. Rev. B* 12, 1105 (1975).

Table 4.7. Electron transport parameters for TiC and ZrC as found from optical and electrical measurements. The dc electrical conductivity, relaxation rate, and plasma frequency are denoted by σ , γ , and ω_p , respectively. Parameters are computed from the electrical conductivity and Hall coefficient by assuming an effective mass of unity.

Parameter (eV)	Optical		Electrical	
	TiC	ZrC	TiC	ZrC
$\pi\sigma$	3.4	2.9	3.3	2.9
$\pi\gamma$	0.24	0.14	0.22	0.28
$\pi\omega_p$	3.2	2.2	3.1	3.2

ELECTRICAL PROPERTIES OF TITANIUM CARBIDE AND ZIRCONIUM CARBIDE¹

F. A. Modine T. W. Haywood²

The electrical properties of the transition-metal carbides are so sensitive to crystal structure, crystal perfection, defect content, and impurities that they are neither generally known nor well understood. In this work, a study of the electrical properties of specimens of TiC and ZrC was undertaken in conjunction with an investigation³ of the optical properties of the materials. The electrical results are of interest per se, and they are an aid to interpreting the free-carrier contributions to optical measurements in the infrared.

The specimens were triangular platelets cut from crystals grown by the rf float zone technique that had dimensions of 5–10 mm on a side and thicknesses of about 1 mm. A large number of carbon vacancies in the crystals was revealed

by sizable deviations from stoichiometry; the composition of the specimens was found to be $\text{TiC}_{0.92}$ and $\text{ZrC}_{0.89}$.

The electrical measurements were made by the van der Pauw technique with a fully automated apparatus having a temperature range 4.2–300 K. The results for TiC are shown in Fig. 4.24, and the ZrC results are quite similar. Precise resistivity values were easily measured; however, Hall measurements on such small, unfavorably shaped specimens were very difficult because spurious thermal voltages were as large or larger than the Hall voltages. Consequently, statistical methods were employed to obtain meaningful results from several hundred measurements taken over a period of several hours. The distribution of the Hall measurements for TiC is shown in the inset of Fig. 4.24.

Fig. 4.24. The electrical properties of titanium carbide. The inset shows the distribution of values measured for the Hall coefficients.

The temperature dependence of the resistivity data can be fitted to the empirical equation

$$\rho = \rho_0 + AT + B \exp[-C/T] \quad (1)$$

and the fit to the TiC data is shown in Fig. 4.24. The equation has been given a theoretical interpretation based upon a strong temperature dependence of the Fermi energy.⁴ Equation (1) more generally describes the resistivities of the transition-metal carbides than does the parallel resistance formula that alternatively has been used to describe the saturation of the resistivity at high temperatures. Parameter values fitted to the data by the least-squares method are given in Table 4.8. The distributions of the Hall measurements have been fitted to Gaussian curves such as shown in the inset of Fig. 4.24. It is presumed that such curve fitting gives better results than does a simple

Table 4.8. Parameters fit to the electrical data for TiC and ZrC. The resistivity at 300 K is included to permit a quick reference to the room temperature values. R_H and its uncertainty are computed from the mean and variance of the Hall data, whereas $\langle R_H \rangle_G$ and its uncertainty are computed from a Gaussian curve fitted to these data.

Parameter	TiC _{0.92}	ZrC _{0.89}
ρ_0 ($\mu\Omega\cdot\text{cm}$)	169.5 $\pm$ 0.1	191.5 $\pm$ 0.3
A ($\mu\Omega\cdot\text{cm}$)	0.009 $\pm$ 0.003	0.025 $\pm$ 0.006
B ($\mu\Omega\cdot\text{cm}/\text{K}$)	36.2 $\pm$ 4	26.5 $\pm$ 9
C (K)	504 $\pm$ 53	495 $\pm$ 140
ρ_{300} ($\mu\Omega\cdot\text{cm}$)	178.9	204.2
R_H (mm^3/C)	-0.906 $\pm$ 0.004	-0.91 $\pm$ 0.03
$\langle R_H \rangle_G$ (mm^3/C)	-0.923 $\pm$ 0.004	-0.83 $\pm$ 0.02

calculation of the mean and variance of the data. However, the results of both calculations are included in Table 4.8.

1. Summary of paper to be published.
2. University of North Carolina-Wilmington, Wilmington, North Carolina.
3. F. A. Modine and C. Y. Allison, "Optical Properties of Titanium Carbide and Zirconium Carbide," this report.
4. R. W. Cohen, G. D. Cody, and J. J. Halloran, *Phys. Rev. Lett.* 19, 840 (1967).

PREPARATION AND CHARACTERIZATION OF THE (100) SURFACE OF TANTALUM CARBIDE

G. R. Gruzalski D. M. Zehner
G. W. Ownby

There exists a rather long history of research involving transition-metal carbides.¹ The earliest work in this area was directed predominantly toward understanding their extreme hardness, but over the years detailed studies of electrical, superconducting, thermal, and other properties have been made, and there is now a considerable body of experimental and theoretical literature devoted to these materials. Relatively little work, however, has been directed toward studying the near-surface region of these materials, even though there is much interest in understanding their catalytic properties. Moreover, of the work that has been done in this area, little has involved single-crystal surfaces, and in particular, single-crystal surfaces of tantalum carbide have been virtually unexplored.

We have been making low-energy electron diffraction (LEED) observations and Auger electron spectroscopy (AES), characteristic loss spectroscopy (CLS), and x-ray photoelectron spectroscopy (XPS) measurements on a (100) single-crystal surface of tantalum carbide prepared by argon-ion bombardment at various energies and/or

by annealing to various temperatures and on this same surface simply exposed to air. One objective of these studies has been to characterize the surfaces and, hence, to obtain feedback about preparation techniques. In this regard, AES and XPS provide information on carbon-to-tantalum ratios (denoted herein as x) and on the presence of unwanted impurities, and LEED provides information on geometric ordering. A second objective of these studies has been to obtain information on electronic structure: KVV AES provides information on the valence band, CLS on the conduction band, and XPS on the valence band as well as on core-level energies. In this article, results regarding surface preparation and characterization are presented; in the following article² we summarize what has been learned about the electronic structure of tantalum carbide.

The relative peak-to-peak amplitude of the carbon KVV AES signal near 268 eV with respect to the tantalum signal near 163 eV, I_C/I_{Ta} , was used as one measure of x . These data were taken with a double-pass cylindrical-mirror analyzer (CMA) containing a coaxial electron gun; the 3-keV primary beam was normally incident to the surface. Of the surfaces studied, those prepared by argon ion bombardment yielded the lowest value of I_C/I_{Ta} , and this value was independent of ion energy for energies between 100 and 1000 eV; it was also independent of sputtering time for times of 10 min and longer. Using atomic sensitivity factors in Ref. 3 and areas under XPS spectra for carbon 1s and tantalum 4f, we obtained $x = 0.70$ for the as-sputtered surface; note, however, that this is a semiquantitative result, accurate only to about 10% or so. Note too that this value reflects the relative number of atoms averaged over the volume of detection; the outermost layer may be considerably more carbon-deficient than the inner layers. (For the bulk, $x = 0.99$.) Other information regarding the as-sputtered surfaces includes that they did not exhibit well-resolved LEED patterns, that oxygen was detected immediately after sputtering, and that the amount of oxygen present increased with time: as much as 0.1 monolayer may have been present within 50 h after sputtering.

Figure 4.25 shows I_C/I_{Ta} vs annealing temperature for surfaces prepared by argon ion bombardment (1000 V, 10 μ A, 10 min). As seen, I_C/I_{Ta} increased with annealing temperatures up to about 1200°C. Also, I_C/I_{Ta} increased with annealing time for anneals near 800°C. These results are consistent with the interpretation that, during the anneals carbon diffuses from the bulk to the surface, which was initially deficient in carbon, presumably because carbon is preferentially sputtered. We have also made measurements following short anneals (seconds) to 2600°C of surfaces previously sputtered and annealed to 2000°C and have found that I_C/I_{Ta} decreased by about 10% (i.e., from about 2.55 to about 2.3); this result is consistent with previous data¹ showing that the vapor pressure of carbon over tantalum carbide at 2600°C is greater than that of tantalum over tantalum carbide at 2600°C. Similar values of I_C/I_{Ta} (i.e., near 2.3) were also found after short anneals to 2600°C of as-sputtered surfaces. Using atomic

Fig. 4.25. Auger-electron intensity ratio I_C/I_{Ta} vs annealing temperature for surfaces prepared by argon ion bombardment (1000 V, 10 μ A, 10 min); the anneals were 10 min.

sensitivity factors and areas under XPS spectra, we have obtained $x = 1.07$ for surfaces having the largest carbon-to-tantalum ratios (i.e., those sputtered and then annealed at 2000°C); again, this value of x should be good to about 10% or so. It is highly unlikely, however, that $x > 1.0$, and therefore it seems reasonable to conclude that these surfaces are probably either stoichiometric or deficient in carbon by no more than a few atomic percent. The values of I_C/I_{Ta} shown in Fig. 4.25 vary by a factor of almost 2; the corresponding ratios of areas under XPS spectra vary by a factor of about 1.5. These data would be consistent if some or all of the prepared surfaces had a concentration gradient. (The Auger data are more surface sensitive, because the escape depths of the Auger electrons used in this study are less than half those of the photoelectrons.)

Unlike the as-sputtered surfaces, those that were sputtered and then annealed at 2000°C exhibited a very sharp (1x1) LEED pattern and remained free of oxygen for days. Moreover, after being exposed to 1 atm of air for 24 h, these surfaces still exhibited a (1x1) LEED pattern (though not a sharp one) and contained no more than one monolayer or so of oxygen. In addition, the magnitudes of the core-level binding energies for atoms associated with these surfaces were determined to be slightly greater (further from the Fermi level) than those associated with the as-sputtered surfaces; it is as if the Fermi level of the as-sputtered surfaces was lower (i.e., closer to that of tantalum).

1. F. K. Storms, *The Refractory Carbides*, Academic Press, New York, 1967; L. E. Toth, *Transition Metal Carbides and Nitrides*, Academic Press, New York, 1971.

2. G. R. Gruzalski, D. M. Zehner, and G. W. Ownby, "Electron Spectroscopic Studies of Tantalum Carbide," this report.

3. C. D. Wagner et al., p. 188 in *Handbook of X-ray Photoelectron Spectroscopy*, ed. by G. E. Muilenberg, Perkin-Elmer Corporation, Eden Prairie, Minn., 1979.

ELECTRON SPECTROSCOPIC STUDIES OF TANTALUM CARBIDE

G. R. Gruzalski D. M. Zehner
G. W. Ownby

AES, CLS, and XPS measurements are being made on (100) surfaces of tantalum carbide prepared by the various procedures discussed in the preceding article.¹ One objective of this work is to obtain information on the electronic structure of these surfaces. In this article, results are presented for surfaces prepared by argon ion bombardment (1000 V, 10 μ A, 10 min) followed by 10-min anneals at 2000°C; surfaces thus prepared may be slightly carbon deficient, but probably by no more than a few atomic percent.¹

Measurements were made in an ion-pumped UHV chamber having a base pressure of less than 10^{-8} Pa and equipped with a double-pass CMA containing a coaxial electron gun and an aluminum x-ray anode. The XPS data were taken with the CMA in the retarding mode (15-eV pass energy); the CLS and AES data were taken with the CMA in the nonretarding, first-derivative mode (1-V peak-to-peak modulation). LCAO (Slater-Koster) parameters for tantalum carbide were used to compute eigenvalues and eigenvectors on a mesh of about 600 points in the fcc IBZ, and the results were then integrated using the tetrahedron method² to obtain the total density of states (DOS); the computation included 1536 tetrahedra in the IBZ. The Slater-Koster parameters were determined by Klein et al.,³ who employed a least-squares fitting procedure using eigenvalues from their self-consistent APW calculation; the fit included a basis set of 13 orbitals. In Fig. 4.26, XPS, carbon-K CLS, and carbon-KVV AES spectra (solid curves) are compared with data generated from the computed total DOS; in each figure the point of zero energy was chosen to correspond with the Fermi level.

The valence-band XPS spectrum and $N(E)$ are shown in Fig. 4.26(a), where $N(E)$ is the total valence-band DOS (computed) broadened with an instrument resolution function (a Gaussian with 1.2 eV FWHM). Two peaks are prominent in the spectra: the one near -12 eV is due to carbon 2s states, and the one near -5 eV is due to carbon 2p and tantalum 5d states. As seen, the overall agreement between the two curves is quite good. Nonetheless, two comments should be made regarding the agreement. First, $N(E)$ is not a theoretical spectrum in that matrix-element effects have not been included; this simplification, however, should not significantly affect peak locations. Second, the relatively large intensities of the experimental spectrum at energies corresponding to the bottom of the valence band are due to inelastically scattered

Fig. 4.26. Comparison of (a) valence-band XPS, (b) carbon-K CLS, and (c) carbon-KVV AES spectra (solid curves) with data generated as described in the text.

electrons and, moreover, to a_3 and a_4 satellite excitations of tantalum 4f_{7/2} electrons.

In Fig. 4.26(b) is shown the carbon-K CLS spectrum, which has been background-corrected, integrated, and loss-deconvoluted (i.e., features owing to inelastically scattered electrons have been removed). The primary beam energy E_p was 1100 eV for the CLS spectrum and 820 eV for the electron-loss spectrum used in the loss-deconvolution process⁴; the energy at the adsorption edge was about 283 eV. The curve labeled $N(E)$ is the total conduction-band DOS

broadened with Gaussian distributions having FWHM's equal to 0.6% of the kinetic energy of the detected electrons. Agreement between the two curves is again quite good. The peak near 3 eV is primarily due to tantalum 5d states. The one near 9 eV [barely discernible in the $N(E)$ curve] is due to carbon 2p and tantalum d-Eg states; these states hybridize to form tantalum-carbon covalent bonds and are therefore somewhat localized about carbon atoms, which may account for the peak near 9 eV being more pronounced in the CLS spectrum. (Because this spectrum involves carbon 1s electrons, one expects that it should reflect the conduction-band DOS weighted somewhat by states localized about carbon atoms.) A similar statement may be applicable to the peak near 30 eV. Another reason to expect discrepancies at these higher energies, however, is that the LCAO fit included only 13 orbitals; therefore, only 13 bands could be produced. Hence, although this LCAO representation should be good near and below the Fermi level, it simply cannot properly describe the electronic structure at higher energies where other bands exist.

Figure 4.26(c) shows the carbon-KVV spectrum, which has been background-corrected, integrated, and loss-deconvoluted. E_p was 3 keV for the Auger spectrum and 272 eV for the electron-loss spectrum used in the loss-deconvolution process. The KVV spectrum is compared with $N(E) \cdot N(E)$, the total valence-band DOS self-convoluted and broadened with Gaussian distributions having FWHM's equal to 0.6% of the kinetic energy of the detected electrons. Discrepancies between these two curves may be due, in part, to energy-dependent transition rates and many-body effects, especially those connected with two-hole states in the valence band. In addition, because the initial core-hole state is strongly localized about the carbon atom, the Auger line shape should preferentially reflect the corresponding local DOS. Overall, however, the agreement appears to be sufficiently good to identify the sources of the most prominent peaks; this may be done simply by inspection of $N(E)$ in Fig. 4.26(a).

1. G. R. Gruzalski, D. M. Zehner, and G. W. Ownby, "Preparation and Characterization of the (100) Surface of Tantalum Carbide," this report.
2. O. Jepsen and O. K. Andersen, *Solid State Commun.* 9, 1763 (1971).
3. B. M. Klein, D. A. Papaconstantopoulos, and L. L. Boyer, *Phys. Rev. B* 22, 1946 (1980).
4. H. H. Madden and J. E. Houston, *J. Appl. Phys.* 47, 3071 (1976).

SMALL-GRAIN ZnO VARISTORS PRODUCED BY THE UREA PROCESS

E. Sonder T. C. Quinby¹
D. L. Kinser²

A varistor is a nonlinear resistor that becomes highly conducting for voltages greater than a given "breakover" voltage. Commercially available varistors are produced by ball milling mixtures of oxide powders, followed by sintering. These techniques make it difficult to produce

(1) very fine grained varistor ceramics, desirable for high voltage use, and (2) varistors with uniform composition and grain size, desirable for sharp breakover characteristics. Moreover, the ball milling may introduce inadvertent impurities.

We have developed a procedure that does not rely on physical milling to mix and grind the component powders; homogeneity is ensured since all chemical components are dissolved in nitric acid. Oxide powder then is produced by diluting the nitric acid solution in molten urea and by a series of thermal treatments, removing the contained water and nitrates, solidifying the mixture as melamine, and burning off the organics to leave uniformly mixed, small-grain-sized oxide powders. The resulting oxides are then densified by hot pressing or sintering to produce the desired shape and electrical properties.

The electrical properties, in particular the electric field for the breakover region, are a strong function of the hot pressing or sintering temperature. Figure 4.27 shows the field/current density characteristics of varistors prepared by the method described above and hot pressing at three different temperatures. The samples were hot pressed in a graphite die at 10.4 Kpsi (7.2×10^7 Pa) and reoxidized in air for times between 1 and 3 h at 775°C. Samples sintered at 1100°C or higher exhibit progressively lower breakover fields. The breakover field of the sample hot pressed at 750°C is the highest ever reported, approximately 6×10^4 V/cm. The average grain size as determined by scanning electron microscopy of a similarly prepared sample is 1.3 μ .

The powder preparation technique reported here is applicable to a large range of constituents and compositions desirable for varistors. We have produced a number of powder compositions. To make comparison with other

Fig. 4.27. Nonlinear electrical properties of varistors prepared by the urea process and hot pressing. The numbers for each curve are the hot pressing temperatures.

experimental varistors easier, the varistors (Fig. 4.27) were of a well-known composition (ZnO , 9%; Sb_2O_3 , 1%; and 0.5% each for Bi_2O_3 , CoO , MnO , and Cr_2O_3) which is used by many investigators and patented by T. Masuyama, M. Matsuoka, and T. Nishi (U.S. Patent Nos. 3663458 and 3903226).

1. Operations Division, ORNL.
2. Vanderbilt University, Nashville, Tenn.

LASER FABRICATION OF ELECTRODES ON ZINC OXIDE VARISTORS¹

F. A. Modine D. H. Lowndes
J. R. Martinelli E. Sonder

Zinc oxide varistors are electronic ceramics comprised of a sintered aggregate of ZnO grains and impurity phases. Varistors are used primarily in voltage clamping and surge arrester applications. Electrodes are an integral part of a varistor and of its manufacture. The electrodes have little influence on the electrical characteristics of a varistor, but they may influence varistor stability or initiate failures of the electrical breakdown type.

A novel method of fabricating electrodes on ZnO varistors by the use of lasers has been developed. A submicrosecond, high-energy laser pulse is used to heat the surface of a varistor to above the ZnO sublimation temperature of 1700°C . Because oxygen is lost more readily from the heated surface than is zinc or the dopant metals, a highly conducting electrode forms on the varistor surface. Both a KrF excimer laser and a CO_2 laser have been used. Better results were obtained with the excimer laser, apparently because the excimer laser beam is better coupled to the ZnO and is spatially more uniform than the CO_2 laser beam. The band gap of ZnO is about 3.2 eV, and the absorption coefficient for photons with energies above the gap is about 10^5 cm^{-1} . Thus, the 248- μm light (5-eV photons) of a KrF laser couples efficiently to the electronic system of ZnO . In contrast, the 10.6- μm light of the CO_2 laser couples to the infrared reststrahlen absorption of ZnO , but the coupling is less efficient because the absorption coefficient is only about 10^2 cm^{-1} . Energies of a few tenths of a J/cm^2 per pulse from the excimer laser will form an electrode, whereas a few J/cm^2 per pulse are required from the CO_2 laser.

The dc electrical characteristics of a varistor with electrodes fabricated using an excimer laser are compared in Fig. 4.28 to those of a varistor with electrodes made of a silver paint; the electrical characteristics reveal typical varistor nonlinearities and are virtually identical. Photographs of the two varistors are inset on Fig. 4.28.

The thickness and composition of the electrodes were investigated using Rutherford backscattering. Figure 4.29 shows backscattering measurements made before and after a ZnO varistor was irradiated with an excimer laser.

Fig. 4.28. A comparison of the electrical characteristics of varistors having electrodes fabricated using a KrF excimer laser and made with silver paint. The inset shows photographs of the varistors; the varistor with laser-fabricated electrodes is on the left.

Fig. 4.29. Rutherford backscattering measurements made before and after a varistor was irradiated with an excimer laser. The results were obtained for 2-MeV alpha particles backscattered at an angle of 150° .

It is clear that the near-surface concentrations of Bi, Sb, Zn, and Co are enhanced by the laser heating. From the widths of the Bi and Sb peaks, it was calculated that the thickness of the electrode is only about $0.1 \mu\text{m}$.

Optical measurements also reveal that the electrode is not a thick metallic coating. The infrared reflectance of a metal is nearly unity, whereas that of a semiconductor can be quite low. In ZnO there is a reflectance minimum near $15 \mu\text{m}$ that is used routinely to gauge the

resistivity and carrier concentration of ZnO varistors. Pulsed-laser heating of the varistor surface increases the reflectance at this minimum by as much as two orders of magnitude and thereby reveals a substantial increase in the conductivity of the surface. Nevertheless, the IR reflectance does not approach that of a good metal such as zinc.

The van der Pauw technique was used to measure the electrical properties of laser-fabricated electrodes. Because the varistor itself only conducts significantly at relatively high voltages, the electrode properties can be measured independent of the underlying ceramic. The sheet resistivity of the electrodes was measured as about 10^3 ohm; from Hall voltage measurements a sheet carrier concentration of approximately $2 \times 10^{15}/\text{cm}^2$ was found. If the thickness calculated from the backscattering data is used, a bulk resistivity of 10^{-2} ohm-cm and an electron concentration of about $2 \times 10^{20}/\text{cm}^3$ are computed. These values can be compared with the grain resistivity and electron concentration of 0.3 ohm-cm and $3 \times 10^{17}/\text{cm}^3$, respectively, that are deduced from the infrared reflectance spectrum of the varistor before laser irradiation. Because the conductivity does not increase in proportion to the carrier concentration, the carriers must have a much shorter mean-free path in the electrode than in the ZnO.

Because the electrodes are thin and are not excellent conductors, their current-carrying capability is limited. Thus, the electrodes may fail before the varistor ceramic if the electrical contacts to the electrodes are too small. In tests employing high-current pulses (e.g., $10\text{A}/\text{cm}^2$ for 1 ms), the electrodes failed when the contact area was reduced to about 10^{-2} cm^2 . Both these tests and rough calculations indicate that the maximum electrode current density is about $10^4\text{ A}/\text{cm}^2$ for millisecond pulses. The lateral currents in the electrodes exceed this value when the electrodes are too small, even though the current density in the ceramic is typically limited by stability considerations to about $10\text{A}/\text{cm}^2$ in a 1-ms pulse.

1. Summary of paper to be published.

CATION TRANSPORT IN MgO

J. Martinelli¹ E. Sonder
R. A. Weeks² R. A. Zuhr

The nuclear reaction $^{18}\text{O}(p,\alpha)^{15}\text{N}$ can be used to measure the thickness of a layer of Mg^{18}O produced by Mg motion to the cathode face of an MgO sample and reaction with ^{18}O ambient at that face. By use of this method, parameters such as cation vacancy diffusion coefficients, transference numbers, and magnesium diffusion coefficients can be obtained.

We have measured the buildup of Mg^{18}O films as a function of time, electric field, and temperature for the range 800–1000°C. Ionic transference numbers and values for the vacancy mobility are given in Table 4.9. Magnesium-ion

Table 4.9. Ionic transference number and mobility for cation vacancies in MgO.

Temperature (°C)	Transference number	Vacancy mobility ($\text{cm}^2/\text{s V}$)
1118		8.8×10^{-11}
1168	0.45	1.3×10^{-9}
1204	0.48	2.2×10^{-9}
1246	0.37	4.8×10^{-9}

self-diffusion coefficients are plotted vs inverse temperature in Fig. 4.30. That figure also depicts magnesium diffusion data published by others.³⁻⁵ Our results are consistent with an extrapolation of the results of sectioning experiments performed by Wuensch et al.³ It thus appears that the measured activation energy for vacancy motion, 2.2 eV, does not vary much over a wide range of temperatures.

1. Graduate laboratory participant from Vanderbilt University, Nashville, Tenn.

Fig. 4.30. Comparison of measured magnesium diffusion coefficients. The various sets of data are labeled with the authors and dates of publication.³⁻⁵

2. Present address: Vanderbilt University, Nashville, Tenn.

3. B. J. Wuensch, W. C. Steele, and T. Vasilos, *J. Chem. Phys.* **58**, 5258 (1973).

4. B. C. Harding, D. M. Price, and A. J. Mortlock, *Philos. Mag.* **23**, 399 (1971).

5. R. Lindner and G. D. Parfitt, *J. Chem. Phys.* **26**, 182 (1957).

DIFFUSION OF OXYGEN IN MgO

J. Martinelli¹ E. Sonder
R. A. Weeks² R. A. Zuhr

The reaction $^{18}\text{O}(p,\alpha)^{15}\text{N}$ can be used to detect the presence of ^{18}O as a function of depth below the surface of a solid sample. Therefore, its use permits measurement of diffusion profiles produced by annealing a solid sample in $^{18}\text{O}_2$ gas.

We have used this technique to obtain data on oxygen diffusion rates in MgO for the temperature range 800–1000°C. Figure 4.31 depicts our results and those of previous investigators.^{3–5} The close agreement between our data and results obtained by a different method³ gives confidence that the measured diffusion coefficients are reliable.

The activation energy calculated from our data, 1.7 eV, as well as that given by Rovner,³ 1.3 eV, is very low, even for extrinsic oxygen diffusion. It is possible that interstitialcy diffusion is dominant. Another possibility is that diffusion short circuiting along small-angle grain boundaries occurs at these low temperatures.

1. Graduate laboratory participant from Vanderbilt University, Nashville, Tenn.

Fig. 4.31. Comparison of oxygen diffusion data in MgO single crystals. Oishi and Kingery, Ref. 3; Reddy, Ref. 4; and Rovner, Ref. 2.

2. Present address: Vanderbilt University, Nashville, Tenn.

3. L. H. Rovner, Ph.D. Thesis, Cornell University, 1966.

4. Y. Oishi and W. D. Kingery, *J. Chem. Phys.* **33**, 905 (1960).

5. K. P. R. Reddy, Ph.D. Thesis, Case Western Reserve University, 1979.

5. NEUTRON SCATTERING

The research carried out in the Neutron Scattering Program encompasses a broad range of problems on the fundamental microscopic behavior of condensed matter. The facilities at the High Flux Isotope Reactor (HFIR) and the Oak Ridge Research Reactor are designed to exploit fully the unique properties of neutrons (energy, wavelength, and magnetic moment) in order to investigate the structure and dynamics of solids and liquids under a variety of environmental conditions including ultralow temperatures, high temperatures, high magnetic fields, and high pressures. The information obtained in these investigations is invaluable for the understanding of materials properties, and it is unique since much of it cannot be obtained through other experimental techniques. Consequently, neutron scattering research contributes significantly toward increasing our knowledge of the solid state and toward providing insight to the solution of our energy-related materials problems.

The involvement with outside users of the ORNL neutron scattering facilities has continued to grow. The National Center for Small-Angle Scattering Research is routinely operating at full capacity with an average of about 100 user experiments per year. The use of the remainder of our neutron facilities by outside scientists has grown substantially during this report period. In spite of the six-month shutdown of our instruments, which was necessary in the replacement of the HFIR beryllium reflector, approximately 60 experiments proposed by users were performed compared with about 40 for the previous period. A highlight of this report period was the Workshop on Instrumentation for an Advanced High-Flux Reactor and the User Meeting held May 30-31, 1984. At the User Meeting a formal User Group with a charter and elected executive committee was formed. At present, approximately 100 U.S. scientists have joined the User Group. A second highlight of this report period was the installation at HB-4A of the HFIR of the new wide-angle neutron diffractometer (WAND), constructed through the financial assistance of the Japanese Government as part of the United States-Japan Cooperative Program on Neutron Scattering. A description of the diffractometer and the results of initial experiments can be found at the end of this chapter. Our close and productive collaboration with the Ames Laboratory staff has continued to be of significant benefit to both laboratories.

The small-angle scattering program in this division has now matured to become one of the strongest in the U.S. During this report period it has featured a wide range of studies including polymers and polymer solutions, shear alignment of gels, magnetic superconductors, macromolecules

of biological importance, and alloys. Several improvements of the 30-m small-angle neutron scattering instrument were made during the HFIR shutdown. These included replacement of several graphite monochromators with material of higher quality and the installation of fixed-neutron beam guides between the two monochromator banks and movable guides between the monochromator and the sample. With the movable guides in place, these improvements produce an overall intensity gain of more than a factor of 10 over that obtained with the old system.

In the area of lattice dynamics, studies have been initiated to investigate the relationship between phonon energies and lifetimes and the fcc-fct martensitic phase transition of $\text{In}_{1-x}\text{Tl}_x$ alloys. Studies on two superconducting materials with layered structures were carried out. For PdTe_2 the phonon dispersion curves show somewhat unusual behavior, which cannot be reproduced by standard models for the interatomic forces. For graphite intercalated with K and Hg (KHgC_8 and KHgC_4), studies of both structural and dynamical properties were aimed at understanding the relationship between the stage dependence of the superconducting transition temperature and long-range ordering of the KHg layers and lattice vibration frequencies. The phonon dispersion curves of La and Ba were also measured.

In studies on magnetism, high-resolution polarized-beam measurements of the magnetic inelastic scattering of Ni have shown that spin-wave-like excitations exist at temperatures above T_c for wave vectors $q > (0.1, 0.1, 0.1)2\pi/a$ in agreement with earlier work at ANL. Work on Cu-Mn spin glasses has continued with measurements of the excitation spectrum for wave vectors corresponding to the locations in reciprocal space of the intense diffuse scattering that arises from the magnetic short-range order. Studies of electronic magnetic ordering were carried out on the random field system $\text{Fe}_{1-x}\text{Co}_x\text{Cl}_2$ ($x=0.275$), Gd-Y alloys, and nickel diglycine dihydrate, a metal derivative of the amino acid glycine.

Several neutron scattering investigations were carried out as part of the U.S.-Japan Cooperative Program. The dilution refrigerator was utilized extensively in studies of the nuclear spin ordering of HoVO_4 , PrCu_2 , and VBr_2 in the millikelvin temperature range. Tests of the high-pressure cells (30 kbar) for neutron scattering were initiated through studies of the B1-B2 phase transformation of KCl at 20 kbar, the pressure dependence of T_N in 2.77 at. % $\gamma\text{-Fe}$ in Cu, and the pressure dependence of phonon energies in SnTe . The new WAND has been utilized for time-resolved studies of the kinetics of first-order phase transitions of RbNO_3 and Sn.

SMALL-ANGLE SCATTERING

THE NATIONAL CENTER FOR SMALL-ANGLE SCATTERING RESEARCH (NCSASR)¹

G. J. Bunick H. R. Child
W. C. Koehler J. S. Lin
L. Maddox² R. Roseberry³
S. Spooner G. D. Wignall

The activities of the NCSASR for the period April 1, 1983–September 30, 1984, are summarized. Included are descriptions of the reinstallation of the 30-m SANS facility, the upgrade of the Oak Ridge Research Reactor (ORR) SANS instrument, and the use of the Center's facilities.

30-M SANS facility. The High Flux Isotope Reactor was shut down in mid-September 1983, in order to replace the beryllium reflector. This is an event that occurs every nine years, and the present change-out is the second in the history of the reactor. As part of this process all the instrumentation in the beam room, the level beneath the 30-m SANS instrument, had to be removed. The instrumentation of the facility was affected in that the lower bank of monochromators, the upper bank of monochromators, and

the vacuum flight path between them were removed. In addition, the shielding maze around the upper crystal mount had to be dismantled to provide access to the main shutter for HB-4.

The work on the reactor went very well indeed, with the start-up taking place as scheduled, on December 28, 1983. Reinstallation of the instruments in the beam room started in January 1984, beginning with the spectrometers at HB-1 and working around, sequentially, to the instruments at HB-4. For a number of reasons, the installation of the SANS instrumentation at HB-4 took somewhat longer than anticipated. Among these was the implementation of a number of improvements to the system, including replacement of three pairs of the graphite monochromators with higher quality materials and the installation of vertical neutron beam guide sections in the vacuum flight path between the monochromator banks. Neutron beam guides have also been installed in the horizontal presample flight path (Fig. 5.1). There are three 2-m sections of guide, having the approximate dimensions of the projected area of the upper crystals. These sections can be positioned accurately in the presample flight path, and they act to transport the initial divergence 2, 4, or 6 m toward the sample. With three guide sections in place, the

30-m SMALL ANGLE NEUTRON SCATTERING FACILITY

Fig. 5.1. Schematic layout of the 30-m SANS facility after the installation of vertical and horizontal guide sections.

overall gain relative to the system as it was before the shutdown is more than a factor of 10. Significant gain has also been achieved in the high-resolution mode with the horizontal guide sections out of the beam.

The construction projects that were under way at the end of the last report period, October 1, 1981–September 30, 1982, have been completed. These included the computer enclosure, the bio-laboratory, and the automatic sample changer for cells containing liquid specimens.

To make the use of this sample changer more convenient, overhead cable trays have been relocated in order to install a beam and chain fall above the sample chamber. This rearrangement will also serve to facilitate the placement of magnets, cryostats, and other heavy equipment in the beam line, and it will improve the appearance of the system. The shield maze around the upper monochromator bank has been rebuilt with additional shielding in an effort to reduce back-ground at the detector, and it has been sheathed in plywood and painted for a more attractive and permanent appearance. The return to full time user operation took place on June 14, 1984.

10-M SANS facility. In order to provide interim service to the user community during the time the 30-m SANS facility was down, we have reactivated and upgraded what was formerly called the 5-m SANS facility at the ORR. This instrument was operational on November 1, 1983, and it has seen active use since the first experiments were carried out in mid-November 1983. It is planned to keep this facility in operation as a long wavelength facility for both DOE research and part-time use by the users of the NCSASR. The effective Q range attainable in the standard configuration (2-cm-diam source slit, 1-cm-diam sample slit) is $7.4 \times 10^{-3} \text{ \AA}^{-1} < Q < 125 \times 10^{-3} \text{ \AA}^{-1}$, and the flux on the sample in this configuration is approximately $1.0 \times 10^{14} \text{ n/cm}^2/\text{s}$.

10-M SAXS camera. The principal item to report for the x-ray laboratory is that the generator continues to deteriorate, and we are experiencing more and longer downtimes. Funding, supplied in part by DOE and in part by NSF, has been obtained to purchase a new 12-kW rotating

anode Rigaku generator. Delivery of this apparatus is expected in January 1985.

Use of the facilities. The 30-m SANS instrument went into full user-mode operation on October 1, 1980. At the end of this present report period, the NCSASR will have seen four full years of operation with both neutron and x-ray scattering facilities available. Table 5.1 presents a summary of the number of users, number of visits, and number of user-days for the neutron and x-ray facilities in the five categories indicated. Table 5.2 lists these data, again for the five categories, according to discipline.

1. The NCSASR is operated under an agreement between the Department of Energy and the National Science Foundation (Interagency Agreement DOE No. 40-637-77, NSF No. DMR-7724458).

2. Computing and Telecommunications Division, Martin Marietta Energy Systems, Inc.

3. Instrumentation and Controls Division, ORNL.

Table 5.1. User report October 1, 1980–September 30, 1984.

	Users		Visits		User-days	
	N ^a	x ^b	N ^a	x ^b	N ^a	x ^b
Industrial	21	13	65	16	236	48
University	59	69	198	173	804	857
ORNL	16	12	96	54	454	259
Other government						
laboratories	6	7	8	25	29	110
Foreign	15	5	36	18	108	82

^aNeutron scattering facilities.

^bX-ray scattering facilities.

Table 5.2. Use of scattering facilities by discipline October 1, 1980–September 30, 1984.^a

	Discipline (days)									
	I		U		ORNL		OGL		F	
	N	X	N	X	N	X	N	X	N	X
Polymer science	9	40	456	158	36	8	11	97	30	31
Chemistry	48	5	203	6	63	9	7	6	54	12
Materials and metallurgy	19	3	128	65	140	170	11	7	16	39
Biology			17	28	215				8	

^aThe abbreviations I, U, ORNL, OGL, and F stand for the categories listed in Table 5.1; N refers to use of neutron; and X to use of x-ray scattering facilities.

RADI OF GYRATION AND SCREENING LENGTHS OF POLYSTYRENE MOLECULES DISSOLVED IN A GOOD SOLVENT AS A FUNCTION OF CONCENTRATION¹

J. S. King² W. Boyer²
R. Ullman³ G. D. Wignall

The swelling of macromolecules in a good solvent arises from excluded volume interactions between pairs of monomer units on a single polymer chain. As the polymer concentration increases, the excluded volume effect is screened and diminished, and in the limit of the bulk polymer, the conformation of a single chain can be described as an unperturbed random coil as originally predicted by Flory⁴ and verified by numerous SANS measurements. Since the early 1970s, developments in polymer solution theory involving the application of scaling methods have led to an upsurge of interest in this area, although only one systematic experimental study of chain dimensions as a function of concentration, c , has been hitherto attempted.⁵ That study showed that for polystyrene in CS₂ the radius of gyration R_g varied as $c^{-0.25}$ in apparent agreement with the then current prediction of

scaling laws.⁵ Since that time, there have been reports of many violations of scaling laws which should be valid in principle only in the asymptotic limit of infinite molecular weight.

Why the scaling exponent (-0.25) was observed with only modest molecular weights has been a long-standing puzzle, and therefore further measurements on polystyrene in a different solvent have been made. Considerable effort was expended to improve the statistical accuracy of the experiment by careful attention to machine reproducibility, by cross checking the consistency of the data by means of redundant data sets, and by the use of high-concentration deuterium labeling methods developed by G. Summerfield and Z. Akcasu^{6,7} (University of Michigan). The measurements gave conclusive evidence that high-concentration labeling methods give highly reproducible results and produced data with the best internal consistency of any polymer data taken previously at ORNL. Several complementary methods of analysis were employed, and each led to the conclusion that the concentration exponent (-0.163) for the molecular weight range measured (~100,000) fell substantially below that predicted by scaling theory (Fig. 5.2).

ORNL-DWG 84-9810R

Fig. 5.2. Variation of R_g with c for polystyrene in toluene.

An alternative parameter, the screening length ζ , which measures the range over which a molecule is swollen by excluded volume effects, was introduced by S. F. Edwards (Cambridge University, England) and may also be extracted from the SANS data. This length varies from the order of the R_g of the entire polymer chain (~ 100 Å) in dilute solutions to the size of a monomer repeat unit (~ 2 Å) in the bulk polymer. The data show that ζ varies as c^{-n} , where $n = 0.70 \pm 0.02$ (Fig. 5.3) in reasonable agreement with an exponent of $n = 0.75$ predicted from renormalization group analysis or mean field theory.

MOLECULAR DIMENSIONS IN POLYETHYLENE TEREPHTHALATE BY SANS¹

K. P. McAlea²
K. K. Gardner³

J. M. Schultz²
G. D. Wignall

The dimensions of chain molecules in amorphous polymers have been investigated by small-angle neutron scattering in a wide range of systems in the past decade, and in general they have been shown to be close to the unperturbed dimensions of chains in ideal θ solvents.⁴ However, despite the importance of polyethylene terephthalate from both scientific and technological viewpoints, no measurements of chain dimensions have been reported in either the amorphous or crystalline states. This is partly due to the difficulties encountered in preparing samples in which the background scattering arising from the polymer matrix and heterogeneities (voids, catalyst/solvent residues, etc.) is sufficiently low that it does not mask the scattering due to the contrast between the labeled (deuterated) and unlabeled (hydrogenous) molecules. Moreover, many of the earlier experiments were performed with low relative concentrations of labeled molecules, which intensified the problem of background subtraction. In this communication we report measurements of molecular dimensions in polyethylene terephthalate

1. Summary of paper to be published.
2. University of Michigan, Ann Arbor, Mich.
3. Ford Motor Company, Dearborn, Mich.
4. P. J. Flory, *J. Chem. Phys.* 17, 303 (1949).
5. M. Daoud et al., *Macromolecules* 8, 804 (1975).
6. A. Z. Akcasu et al., *J. Polym. Sci., Polym. Phys. Ed.* 18, 853 (1980).
7. S. N. Jahshan and G. C. Summerfield, *J. Polym. Sci., Polym. Phys. Ed.* 18, 1859 (1980).

ORNL-DWG 84-9809R

Fig. 5.3. Plot of screening length ζ vs concentration for polystyrene in toluene.

(PET) from samples where the background scattering has been reduced to an acceptably small fraction of the scattering due to the labeled molecules. This has been accomplished by improvements in the sample preparation technique to reduce the concentration of heterogeneities that give rise to background scattering and also by use of high concentrations of labeled polymers. It has been shown earlier that both the radius of gyration and molecular weight can be obtained from a single concentration measurement, provided the molecular weights of the labeled and unlabeled molecules are matched.⁵

Fully deuterated PET was supplied by Allied Chemical Company. This material was solid state polymerized under vacuum at 240°C for 50 h (series A) and 40 h (series B). The hydrogenous material was commercial PET (Goodyear Cleartuff, lot 1002A).

Protonated blanks, deuterated blanks, 20-wt-% (volume fraction = 0.193) PET-D, and 40-wt-% (volume fraction = 0.390) PET-D samples were prepared. Sample material was first dissolved in trifluoroacetic acid (TFA) and then reprecipitated by slowly pouring the solution into a blender containing ice water. The polymer was then filtered, washed with water and acetone, and dried under vacuum at 100°C for 24 h. A small amount (0.5 gm) of the dried polymer flakes was then redissolved in TFA in a petri dish, and the solution was slowly evaporated at low temperature on a hot plate. When the solution reached the consistency of a gel, the dish was quickly immersed in water, yielding a cloudy polymer film. The films were dried under vacuum for 48 h and then pressed at 10,000 psi at 100°C for 15 min. The pressing step considerably reduces the coherent scattering in the protonated and deuterated blanks presumably by eliminating voids in the samples. The as-prepared films are semicrystalline, and density measurements show them to be 30% crystalline on the average. The neutron measurements were performed on the 30-m SANS facility at the High Flux Isotope Reactor and also on the 10-m SANS instrument located at the Oak Ridge Research Reactor. Measurements on the two different instruments sampled three different ranges of the scattering vector $Q = 4\pi\lambda^{-1} \sin\theta$, giving an overall range of $0.004 < Q < 0.125 \text{ \AA}^{-1}$, where $\lambda = 4.75 \text{ \AA}$ is the incident wavelength and 2θ is the angle of scatter. In all three Q ranges the scattering patterns were corrected on a cell-by-cell basis for instrumental backgrounds and detector efficiency variations, divided by the sample transmission and thickness, and normalized to a constant incident flux. Blank samples of pure PET-D and PET-H were also measured in all three Q ranges to check for the presence of scattering from voids or other heterogeneities and to provide a basis for subtraction of the angular independent incoherent scattering arising principally from H^1 nuclei.

All the corrected scattering patterns exhibited cylindrical symmetry about the incident beam, and the measured intensities were therefore radially averaged and converted to an absolute differential scattering cross section $d\Sigma(Q)/d\Omega$ per unit solid angle, per unit volume of material (in units of cm^{-1}), by comparison with the scattering or precalibrated secondary

standards. The overall agreement between all calibration standards was better than $\pm 5\%$ after scaling for the different sample-detector distances used in each Q range.

Figure 5.4 shows a Zimm plot of the data for high molecular weight PET-D. The weight-averaged SANS molecular weight ($M_w = 128 \times 10^3 \text{ gm}$) agrees with the value ($M_w = 103.6 \times 10^3$) determined by gel permeation chromatography (GPC). Fig. 5.5 shows the R_g and M_w derived from fitting a Debye function to the data of Fig. 5.4. This expression has been shown to give a reasonable description of the SANS patterns for several amorphous polymers.⁴ The SANS molecular weight (115×10^3) from the Debye fit is closer to the GPC value (103.6×10^3) than that derived from the Zimm

Fig. 5.4. $(d\Sigma/d\Omega)^{-1}(Q)$ vs Q^2 for 40-wt-% PET-D in PET-H.

Fig. 5.5. $(d\Sigma/d\Omega)(Q)$ vs Q for 40-wt-% PET-D in PET-H.

fit (128×10^3), and both values are again within the overall uncertainty of the two determinations.

In calculating values of the ratio of R_g to $M_w^{1/2}$, the SANS and GPC molecular weights were averaged for two series of samples (A and B), and the measured z-averaged R_g^2 was converted to a weight-averaged R_g^w via the known polydispersity. The values of $R_g^w/M_w^{1/2}$ are 0.391 and 0.380 for series A and B, respectively, compared to the unperturbed dimensions of 0.394 (theoretical⁶) or 0.398–0.420 (experimental⁷). Thus the measured molecular dimensions in PET are again close to those measured in ideal θ solvents, as has been found for a range of amorphous polymers. That we obtain essentially unperturbed dimensions in samples with some crystallinity is not surprising, in view of the SANS work on crystallizable polymers. In these studies⁸ it has been shown that R_g is generally very similar in the amorphous and crystalline states.

1. Summary of paper to be published.
2. University of Delaware, Newark, Del.
3. E. I. du Pont de Nemours and Company, Wilmington, Del.
4. G. D. Wignall, *Trans. Am. Crystallogr. Assoc.* 19, 17 (1983).
5. G. D. Wignall et al., *Polymer* 22, 886 (1981).
6. K. Altgelt and G. V. Schultz, *Makromol. Chem.* 36, 209 (1960).
7. P. J. Flory, p. 191 in *Statistical Mechanics of Chain Molecules*, Wiley Interscience, New York, 1969.
8. G. D. Wignall et al., *J. Polym. Sci.* 20, 245 (1982).

MORPHOLOGY AND PHASE DIMENSIONS OF INTERPENETRATING POLYMER NETWORKS BASED ON POLYBUTADIENE AND POLYSTYRENE BY SMALL-ANGLE NEUTRON SCATTERING AND ELECTRON MICROSCOPY¹

A. M. Fernandez² G. D. Wignall
L. H. Sperling²

An interpenetrating polymer network (IPN) may be defined as a combination of two polymers in network form, at least one of which was polymerized in the immediate presence of the other. Sequential IPN formation involves the synthesis of network I, a subsequent swelling in a second monomer together with initiator and cross-linking agent, and polymerization of monomer II in situ. In the semi-I-IPN materials, the first polymer synthesized is cross-linked, while the polymer II is linear.³

Polybutadiene/polystyrene (PB/PS), IPNs, and semi-I-IPNs were prepared where the second polymer synthesized, polystyrene, was fully deuterated to enhance the contrast for small-angle neutron scattering (SANS) and to permit the determinations of domain dimensions. Several SANS studies of polymer blends^{4–6} have indicated that the scattering from these systems may often be represented by the well-known Debye-Bueche relation. The inhomogeneities present in a

random two-phase system may be characterized by the Debye correlation function

$$\gamma(r) = (-r/a), \quad (1)$$

where a is the correlation distance defining the size of the heterogeneities which are distance r apart.^{7,8} If this correlation function is applicable, a plot of the reciprocal of the square root of the scattered differential cross section, $[d\sigma(Q)/d\Omega]^{-1/2}$ vs Q^2 , where $Q = 4\pi/\lambda \sin\theta$, should yield a straight line having a slope/intercept ratio proportional to a^2 . The specific surface area S_{sp} is related to the correlation distance by

$$S_{sp} = \frac{4\phi_1\phi_2}{a}, \quad (2)$$

where ϕ_1 and ϕ_2 are the volume fractions of the PS and PB phases, respectively.

For dilute dispersions, a may be taken as a measure of the size of the dispersed component. However, for more concentrated systems, the domain dimensions may be described by the mean chord intercept lengths L_1 and L_2 :

$$L_1 = \frac{a}{(1-\phi_1)}; L_2 = \frac{a}{(1-\phi_2)} \quad (3)$$

For spherical domains the equivalent diameters are given by

$$D = \frac{3}{2} \left(\frac{a}{1-\phi} \right), \quad (4)$$

where the appropriate subscripts 1 or 2 are attached. The IPNs and semi-I-IPNs were synthesized by thermal polymerization techniques. The elastomeric phase was prepared by dissolving the PB in tetrahydrofuran, adding the appropriate amount of cross-linking agent dicumyl peroxide (Dicup), and evaporating the solvent. The PB matrix was partially cured in a compression mold operating at a temperature of 120°C.

To form the plastic phase of the materials, styrene monomer solutions containing 0.4 % w/v benzoyl peroxide and the required amount of divinyl benzene (DVB) were prepared. The cross-linked PB networks were immersed in the styrene mixture at room temperature. Swollen polymer then was placed in a saturated styrene atmosphere so that a uniform distribution of monomer could be achieved throughout the sample. The styrene was polymerized thermally at 70°C, and the materials were subject to a vacuum drying operation to remove unreacted monomer. For the semi-I-IPNs, the DVB component was omitted, yielding linear polystyrene. Transmission electron microscopy (TEM) was used to elucidate the IPN morphology using osmium tetroxide (OsO_4) staining techniques to prepare specimens for the microscope. The materials were sectioned to a thickness ~700 Å and directly observed in a Philips 300 TEM, where photomicrographs were obtained. The neutron experiments were performed on the 30-m SANS facility at the National Center for Small-Angle Scattering Research in the range $0.003 < Q < 0.030 \text{ Å}^{-1}$. The SANS data indicate that the Debye approximation is reasonable for these systems, and a typical plot of $[d\sigma(Q)/d\Omega]^{-1/2}$ vs Q^2 is shown in Fig. 5.6. The correlation lengths evaluated from such plots

Fig. 5.6. $[d\Gamma(Q)/d\Omega]^{-1/2}$ vs Q^2 for two PB/PS semi-IPN materials with different amounts of cross-linker (Dicup).

are relatively small, ranging from 106 to 37.5 Å, while for the PS phase, mean chord intercepts range from 550 to 150 Å. The values of L_1 , L_2 , and S_{sp} are shown in Table 5.3 along with estimates of the disperse phase diameters by TEM and SANS, which indicate reasonable agreement between the two techniques. The large interfacial areas indicated by S_{sp} are sites for grafting and interphase bonding. These values are in the range exhibited by colloids. The results indicated that low cross-linked IPNs and semi-I-IPNs present a geometry characterized by dual-phase continuity. The TEM micrographs show that an increase in the cross-linking level of both polymers produces a finer morphology with rather greater regularity. When both polymers are cross-linked, indications are that two continuous phases are formed with the domains decreasing in size with increasing cross-linking density. Consequently, the characterization and measurement of the domains become difficult by TEM. The Debye treatment of phase domain dimensions does not impose geometrical requirements, but rather assumes a random interdispersion of the phases. The SANS technique can resolve both large and small domains and thus gives overall average dimensions slightly smaller than TEM (Table 5.3),

which does not properly resolve the smaller dimension. Therefore, the SANS technique has advantages when applied to dual-phase continuous IPN materials.

1. Summary of paper to be published.
2. Lehigh University, Bethlehem, Pa.
3. L. H. Sperling, p. 3 in *Interpenetrating Polymer Networks and Related Materials*, Plenum, New York, 1976.
4. D. J. Blundell, G. W. Longman, and G. D. Wignall, *Polymer* 15, 33 (1974).
5. J. T. Koberstein, *J. Polym. Sci. Phys. Ed.* 20, 593 (1982).
6. G. D. Wignall, H. R. Child, and R. J. Samuels, *Polymer* 23, 957 (1982).
7. P. Debye and A. M. Bueche, *J. Appl. Phys.* 20, 518 (1949).
8. P. Debye, H. R. Anderson, and H. Brumberger, *J. Appl. Phys.*, 28, 679 (1957).

SHEAR ALIGNMENT STUDIES OF ANISOTROPY IN COLLOIDS AND GELS

J. B. Hayter J. Penfold¹
B. J. Ackerson²

Structural studies of colloidal dispersions of anisotropic particles or of gels formed from anisotropic supramolecular assemblies are severely hampered by the loss of information due to angular averaging when scattering from phases which exhibit bulk isotropy. Further, in the many interesting systems in which the particles interact with each other (e.g., via an electrostatic or magnetic dipolar potential), the theoretical interpretation of the data is rendered intractable because the correlations between relative particle orientations and positions are generally not calculable. However, in the special case when all the particles have the same orientation, the scattered intensity factors into a single-particle scattering function $P(Q)$ and a structure factor describing positional correlations between the parallel particles $S_{\parallel}(Q)$:

$$I(Q) = P(Q) S_{\parallel}(Q).$$

Table 5.3. PB/PS (DB) IPNs and semi-I-IPN dimensions by SANS and TEM techniques.

Volume fractions		Correlation	Intercepts (Å)		S_{sp} m ² /gm	Diameters (Å) (PS)	
ϕ_1 (PB)	ϕ_2 (PB)	lengths a (Å)	L_1 (PS)	L_2 (PB)		D_a	D_b range
0.807	0.193	106	549	131	58.8	824	700-1500
0.730	0.270	53	194	73	149	291	350-600
0.770	0.230	58	252	75	122	378	500-1100
0.76	0.24	37.5	154	49	196	231	400-800

$$a \text{ From } D = \frac{3}{2} \frac{a}{(1-\phi_1)}.$$

b From TEM measurements.

In the absence of interactions, $S_w(Q) = 1$, and the scattering exhibits the particle symmetry through $P(Q)$.

In the case of nonmagnetic particles, alignment may be achieved through application of a suitable viscous shear field. An approximate theoretical approach³ shows that the scattering function may be characterized by a parameter $r = G/D_r$, where G is the applied shear gradient and D_r is the rotational diffusion coefficient for

the particle; full alignment is achieved when $r \gg 1$.

Figure 5.7 shows the development of alignment in a viscous gel formed of supramolecular assemblies having cylindrical form with diameter 50 Å and length 3200 Å. Once aligned, the particles may be studied in detail using standard SANS techniques such as contrast variation. The technique is applicable to a wide range of problems. It has the added novel feature that information

Fig. 5.7. Measured SANS intensity maps for scattering from a micellar gel, showing shear-induced anisotropy. Black corresponds to maximum; white corresponds to zero scattered intensity. The fluid velocity u_x is parallel to x , and the gradient $G = \partial u_x / \partial y$ is parallel to y (into the page). (a) $G = 1000 \text{ s}^{-1}$; (b) $G = 3800 \text{ s}^{-1}$. Data were collected on the 10-m ORR SANS spectrometer. In the absence of shear, the scattering pattern is isotropic.

may be obtained about particles whose length lies outside the normal range of observation (determined by the minimum momentum transfer of the spectrometer), since the length couples to the variation of scattering with shear-rate via D_T .

1. Rutherford Appleton Laboratory, Oxon, England.
2. Oklahoma State University, Stillwater, Okla.
3. J. B. Hayter and J. Penfold, *J. Phys. Chem.* 88, 4589 (1984).

SMALL-ANGLE NEUTRON SCATTERING OF (Er_{0.8}Ho_{0.2})Rh₄B₄¹

O. A. Pringle H. A. Mook
M. B. Maple²

The pseudoternary rare-earth (RE) rhodium boride compounds RERh₄B₄ are useful for studying the interaction between superconductivity and long-range magnetic order, as well as for exploring the effects of competing magnetic moment anisotropies and magnetic order. One example of a pseudoternary system is the (Er_{1-x}Ho_x)Rh₄B₄ system, whose low-temperature phase diagram³ is shown in Fig. 5.8. This phase diagram displays regions in which the Er³⁺ and Ho³⁺ moments order independently and ferromagnetically within the basal plane and along the tetragonal c axis, respectively, separated by a region where the magnetic phases are mixed. There is also a tem-

Fig. 5.8. Low-temperature phase diagram for the (Er_{1-x}Ho_x)Rh₄B₄ system. The dashed line extending beyond $x = 0.3$ shows where the magnetic ordering changes from along the tetragonal c axis to a mixture of c axis and basal plane ordering, and the lower solid line represents the $T_{C2}(x)$ phase boundary.

perature region above T_{C2} in which the sinusoidally modulated phase in ErRh₄B₄ coexists with normal ferromagnetic domains. This inhomogeneous phase presumably persists within the shaded area in Fig. 5.8 as previously conjectured³ from ac magnetic susceptibility and neutron diffraction measurements.

The $T_{C2}(x)$ phase boundary has a minimum near $x = 0.3$. It has been suggested that near $x = 0.3$ there could be a Lifshitz point.⁴ In order to verify the existence of the modulated phase away from $x = 0$ and to examine the possibility of a Lifshitz point near $x = 0.3$, we made small-angle neutron scattering (SANS) measurements on a polycrystalline (Er_{0.8}Ho_{0.2})Rh₄B₄ sample at temperatures between 1.36 and 0.49 K.

The (Er_{0.8}Ho_{0.2})Rh₄B₄ sample was synthesized by arc melting the RE tetraborides with Rh under high-purity argon followed by annealing in a manner previously described.⁵ Boron enriched in ¹¹B was used to reduce neutron absorption. The sample was mounted in a ³He refrigerator having a low-temperature capability of about 0.4 K. The SANS data were taken on the 30-m SANS instrument at the National Center for Small-Angle Scattering Research at ORNL using a sample-to-detector distance of 3.71 m, which gave a useful Q range from about 0.015 to 0.14 Å⁻¹. The neutron wavelength was 4.75 Å. All the SANS spectra were isotropic and were radially averaged prior to data analysis. All data were taken with the sample having been cooled from the superconducting phase.

We measured SANS spectra at a number of temperatures between 1.36 and 0.49 K. For temperatures between about 1.0 and 0.5 K, we observed peaks in the SANS patterns at Q values near 0.065 Å⁻¹, corresponding to a sinusoidal modulation of the magnetic moment with a wavelength close to 100 Å. No peak was observed at 1.36 K. We corrected for instrumental background by subtracting the radially averaged 1.36 K data from the data for the other temperatures. The background corrected data were then fit to Gaussians plus additional sloping backgrounds. The corrected data and fits for five of the temperatures are shown in Fig. 5.9. A very weak peak showed up in an additional scan taken at 0.49 K, but the data are not plotted in this figure to avoid confusion with the rest of the data. The sloping background in Fig. 5.9, which becomes stronger as the temperature is lowered, is attributed to scattering from the ferromagnetic phase.

These results show that the modulated moment phase persists to x values close to the minimum in the $T_{C2}(x)$ phase boundary and verify the existence of the shaded region of the low-temperature phase diagram in Fig. 5.8. The fitted peak positions show that there is little change in the wave vector of the modulation over the entire temperature range where the modulated moment phase exists, except for possibly a slight decrease at lower temperatures. Furthermore, the wavelength of the modulation has not changed appreciably from the $x = 0$ case (about 100 Å).^{6,7} For a Lifshitz point to exist near $x = 0.3$, the magnitude of the wave vector of the modulation must approach zero continuously as x approaches 0.3. The fact that the wave vector remains the same at $x = 0.2$ as at $x = 0$ virtually rules out the existence of a Lifshitz point near $x = 0.3$.

1. Summary of paper: Journal of Applied Physics (in press).
2. University of California at San Diego, La Jolla, Calif.
3. M. B. Maple, p. 479 in Proceedings of the International Conference on Magnetism, ed. by K. Adachi, North-Holland, Amsterdam, 1983.
4. B. Schuh and M. Grene, Z. Physik B 46, 149 (1982).
5. H. A. Mook et al., Phys. Rev. B 25, 372 (1982).
6. S. K. Sinha et al., Phys. Rev. Lett. 48, 950 (1982).
7. D. E. Moncton et al., Phys. Rev. Lett. 45, 2060 (1980).

ORNL-DWG 84-14546

Fig. 5.9. SANS peak from $(\text{Er}_{0.8}\text{Ho}_{0.2}\text{Rh}_4\text{B}_4)$ at various temperatures.

MODIFICATION OF CATION-EXCHANGE PROPERTIES OF ACTIVATED CARBON BY TREATMENT WITH NITRIC ACID¹

J. S. Johnson, Jr.² C. G. Westmoreland²
 F. H. Sweeton² K. A. Kraus²
 E. W. Hagaman² W. P. Eatherly³
 H. R. Child

The uptake of inorganic cations by high-surface-area activated carbon can be increased by an order of magnitude by controlled exposure to high concentrations of nitric acid at elevated temperatures. Distribution coefficients of cations are also increased. Oxidation treat-

ment causes some loss in particle strength. Acid strength of the functional groups from the nitric acid treatment is greater than those of the starting material. Surface area measurements from small-angle neutron scattering indicate that the increase in effective ion-exchange capacity is not accompanied by gross change in the structure of the material. ¹³C-NMR on solid samples suggests that the concentration of carboxyl and phenolic functional groups in the carbon is increased by the treatment.

1. Summary of paper to be published.
2. Chemistry Division, ORNL.
3. Metals and Ceramics Division, ORNL.

THE DETECTION OF CYTOCHALASIN-D INDUCED DIMERS OF Mg^{2+} -ACTIN

D. Goddette¹ C. Frieden¹
 E. Uberbacher² G. J. Berick

Actin is a protein which has been implicated in a wide number of cellular functions. In non-muscle cells, it is constantly being reorganized in response to functional demands such as endocytosis, filopodial projections, and many other forms of motility. As isolated, actin is a monomer protein of 42 Kd (G actin), but can be induced to polymerize into a filamentous form, F actin.

While the polymerization process is fairly well understood in vitro, the mechanisms by which the cell rapidly redistributes polymerized actin is just now being elucidated. Under physiological conditions, pure actin would be completely polymerized, yet it is found to be mostly depolymerized in vitro. It is clear that a variety of actin-binding proteins which can sever and cap actin filaments are involved in keeping the actin depolymerized and in the redistribution processes.

Cytochalasin D (CD) is a 500 dalton fungal metabolite which inhibits cellular motile functions presumably through its interactions with actin. In vitro it mimics the effects of actin-binding proteins on the kinetics of actin polymerization. Fluorescence studies show that CD binds to G actin, with its stoichiometry dependent on the divalent cation: 1:1 in the presence of Ca^{2+} and 1:2 (CD:actin) in the presence of Mg^{2+} . However, other studies such as analytical ultracentrifugation have been unsuccessful in determining the existence of the CD-induced actin dimer. The present SANS study was undertaken to determine the state of actin in the presence of Mg^{2+} and thereby determine if the fluorescence measurements are a correlate of actin dimerization.

Actin was purified by the method of Spudich and Watt³ and lyophilized for storage. Samples were prepared for scattering measurements by reconstitution in the appropriate D_2O buffer followed by extensive dialysis involving several changes of the buffer. Prior to use, all samples were centrifuged at $100,000 \times g$ for one hour and stored on ice. The scattering geometry selected made use of one beam guide, slit sizes of 3.5, 1.79, and 1.6 cm, sample-to-detector distance of

0.002 m, beam stop of 8-cm diam, and neutron wavelength of 4.75 Å. The samples were contained in cylindrical quartz cells 5-mm thick, having a capacity of approximately 1.5 mL. The concentration of actin was determined spectrophotometrically for each sample. Multiple measurements were made on each sample in one-hour exposures, and appropriate data sets were subsequently combined. Data analysis consisted of determining the forward scatter $I(0)$ and the radius of gyration (R_g) for each sample from Guinier plots $[\ln(I) \text{ vs } k^2]$. The shape of the Guinier plots for some of the samples revealed polydispersity. In these cases, the curves were deconvoluted by adjusting the quantities of monomer, dimer, and higher oligomers of actin to obtain the best fit between the calculated scattering curve and the observed data.

The behavior of monomeric actin is kinetically different depending on the divalent cation associated with it. To study this effect and the effect of cytochalasin D, actin at high and low concentrations (4.2 and 1.2 mg/mL) was measured in Ca^{2+} and Mg^{2+} buffers with and without CD. These measurements also served as a concentration series. The Guinier plots from the actin samples in Ca^{2+} buffer without CD showed the presence of monomer actin, but also revealed very large aggregates in some of the samples. These aggregates probably resulted from improper recovery technique in the centrifugation step during sample preparation. The R_g of monomer actin was determined to be 19.9 Å, which is in excellent agreement with calculated values derived from x-ray crystallographic and electron microscopy data. The behavior of actin at low concentration in Ca^{2+} buffer with CD was similar to the experiments without CD. However, at the high-actin concentration, the effect of CD in the Ca^{2+} buffer was not as expected. The Guinier plot was nonlinear, and the $I(0)$ indicated that considerable polymerization had occurred. Deconvolution of the data showed the presence of dimer and higher oligomers in addition to monomer actin.

Actin at low concentration (0.9 mg/mL) in Mg^{2+} buffer showed a linear Guinier plot. The measured $I(0)$ was higher than expected for monomer, and the R_g was also higher than the value expected for monomer. If the difference between the observed $I(0)$ and that expected for pure monomer is considered to be due to dimer, then the approximate composition of the sample works out to 86% monomer, 14% dimer. The Guinier plot for actin (0.8 mg/mL) in Mg^{2+} buffer with 80 μM CD is also linear. The measured R_g is 27.5 Å, which is too large for monomer and too small for dimer thus suggesting a mixture of the two. The approximate composition was determined to be 69% dimer and 31% monomer.

The first attempt to collect data from actin at 5 mg/mL in Mg^{2+} buffer failed when the sample polymerized unexpectedly. It was decided to follow the time course of polymerization with a fresh sample. Twelve one-hour runs were collected. The first Guinier plot was linear, but all subsequent plots were decidedly nonlinear. The data were deconvoluted, and the $I(0)$ quantities for monomer and dimer were plotted as a function of time (Fig. 5.10).

Fig. 5.10. Plot of $I(0)$ vs time (hours) for monomer actin (—●—) and dimer actin (—■—), showing decrease in actin monomer and increase in actin dimer as the time course of polymerization proceeds. Equilibrium is essentially reached after about four hours.

Several important conclusions resulted from this study. The radii of gyration for the monomer and dimer actin were determined. The values were 19.9 and 29.0 Å, respectively. The center-to-center distance between monomer subunits in the dimer was calculated from the R_g data to be 42.2 Å. This number suggests that actin monomers overlap considerably when forming dimers. The formation of dimers through end-to-end contacts would result in a longer center-to-center distance. The behavior of the Ca^{2+} -actin system followed predictions from the fluorescence and ultracentrifugation experiments except at the high concentration with CD present. The Mg^{2+} -buffer experiments were very significant because they showed the presence of increased amounts of dimer when CD was added to the Mg^{2+} buffer actin system. Thus, the general prediction of actin behavior in Mg^{2+} buffer was corroborated by the neutron scattering experiments: in Mg^{2+} buffer, CD induces the dimerization of actin. The neutron scattering experiments also provided the first direct evidence of actin dimers under these conditions. The kinetic study of actin polymerization in Mg^{2+} buffer provided new data to be compared with fluorescence data and demonstrated the capacity for Mg^{2+} alone to induce actin dimer formation under appropriate conditions.

1. Washington University, St. Louis, Mo.
2. The University of Tennessee—Oak Ridge Graduate School of Biomedical Sciences and Biology Division, ORNL.
3. J. A. Spudis and S. Watt, *J. Biol. Chem.* 246, 1466 (1971).

THE UNFOLDING OF HALOPHILIC MALATE DEHYDROGENASE FROM HALOBACTERIUM MARIS MORTUI

G. Zaccari¹ H. Eisenberg²
G. J. Bunick G. D. Wignall
W. C. Koehler

Saturated salt solutions have markedly different thermodynamic properties than the weakly saline solutions that are the usual life-supporting systems. In high salt concentrations the contributions of ionic interactions to the free energy are essentially zero. However, obligate halophilic organisms that survive only in highly concentrated salt solutions do exist. Their existence raises fundamental questions about the influence of environment on biological processes.

One such organism is the enzyme malate dehydrogenase. It is a halophilic enzyme that can be purified from *Halobacterium Maris Mortui*, and it loses its activity quite markedly in salt concentrations below 2 M NaCl. Something is known of its structure from analytical centrifuge data and x-ray and neutron scattering experiments.

Above 2 M NaCl, the enzyme behaves as a particle of invariant volume and composition. It is made up of a protein dimer in a 5.5 M NaCl microenvironment. The associated water and salt make up as much mass in the particle as the protein moiety alone. In the present experiment, carried out at the newly upgraded 30-m SANS facility, a study of the enzyme in dilute, 1 M NaCl, solution was made.

The intensity of scattering at zero wave vector $I(0)$ and R_g , the radius of gyration, can be measured in absolute units in a SANS experiment. These quantities are directly related to the molecular weight, composition, and spatial structure of a particle in solution. These parameters were followed for the enzyme in 1 M NaCl as a function of time in order to correlate its loss of activity with structural changes and also to explore its interactions with salt in different environments. The automatic sample changer for liquids was used in a cyclic mode. A one-hour exposure for the enzyme (5.4 g/L of protein) was followed by exposures of the buffer alone, empty cell, and cadmium. Each cycle took between one and five hours in all.

As a control, the active enzyme (6.7 g/L) in a 4 M NaCl buffer was measured, and the results are shown in Fig. 5.11. It is often convenient to give a thermodynamic interpretation to the scattering,³ according to which

$$I(0) = \frac{c_2 M_2}{N_A} \left(\frac{\partial \rho_N}{\partial c_2} \right)^2,$$

where c_2 and M_2 are the concentration and molecular weight of protein, N_A is Avogadro's number, and $\partial \rho_N / \partial c_2$ is the neutron scattering length density increment (cm/g). The measured $I(0)$, Fig. 5.11, agrees perfectly with the calculated value for the enzyme in the given experimental conditions ($M_2 = 87,000$, $\partial \rho_N / \partial c_2 = 18 \times 10^9$ cm/g). The measured R_g is 32.3 Å.

Fig. 5.12 shows the values of $I(0)$ and R_g , measured as a function of time for the enzyme in

Fig. 5.11. Guinier plot of active halophilic malate dehydrogenase (6.7 g/L; in 4 M NaCl). The $k = 0$ intercept corresponds, in absolute value, to 0.308 cm^{-1} , which can be related to the molecular weight and $\partial \rho_N / \partial c$. The slope of the curve is a measure of the radius of gyration.

Fig. 5.12. $I(0)$ and R_g , in the absolute units, as a function of time for the enzyme in 1 M NaCl.

1 M NaCl (25°C). The solid line through the points has an exponential decay of about 0.5 h^{-1} ; the extrapolation to $t = 0$ is the expected $I(0)$ for the inactive particle in 1 M NaCl ($M_2 = 87,000$, $\partial \rho_N / \partial c_2 = 23 \times 10^9$ cm/g). The plateau in $I(0)$ corresponds to $M_2 = 43,500$ $\partial \rho_N / \partial c_2 = 18 \times$

10^9 cm/g. These significantly lower values show that the enzyme has lost its salt and water binding properties in these low salt conditions. In fact, the value of $\partial\rho/\partial c_2$ found in a 1 M NaCl buffer is a reasonable value for a nonhalophilic protein.

If there had been no compositional change with time ($\partial\rho/\partial c_2$ constant at 23×10^9 cm/g), the $I(0)$ would have followed the dotted line in the figure. After about 6 h the experimental points lie below the plateau value because of degradation of the protein, probably by hydrolysis. The R_g value is essentially the same in the time course of the experiment and shows that the enzyme monomers unfold out of the globular conformation they had in the dimer particle.

In summary, the enzyme progressively dissociates into monomers which unfold and which do not have exceptional water- and salt-binding properties. The unfolded protein is susceptible to hydrolysis, whereas the high salt particle is extremely stable. The 5.5 M salt microenvironment appears to be essential, therefore, in maintaining the enzyme structure and activity. Apparently, this microenvironment cannot be sustained below about 2 M NaCl in the solution.

1. Guest scientist from Centre National de la Recherche Scientifique, Grenoble, France.
2. Weizmann Institute, Rehovot, Israel.
3. H. Eisenberg, *Q. Rev. Biophysics* 14, 219 (1981).

ANALYSIS OF BEAM GUIDE EFFECTS ON THE NCSASR 30-M SANS INSTRUMENT

D. K. Christen W. C. Koehler
G. D. Wignall

The (horizontal) neutron beam of the 30-m small-angle neutron scattering facility is extracted from the High Flux Isotope Reactor source through two banks of graphite monochromator crystals. Each bank is comprised of six mosaic crystals, and the two banks are offset vertically by about 5 m (one floor in the reactor building). This configuration enables a low experimental background but also results in a long pre-sample flight path, with an attendant intensity loss unless neutron-reflecting beam guides are employed. Recently the 30-m machine has been upgraded by the installation of parallel guide plates in the vertical flight path between the two monochromator banks and by a series of 2-m long rectangular guide surfaces in the horizontal, presample flight path. Because of the unique and complex geometry of this crystal-monochromated system relative to the common guided and chopped beam configuration, calculations were performed to assess the anticipated intensity gains. Here we briefly describe these calculated projections and compare them with the observed results.

A thorough analysis requires tracing the beam-ray angle-wavelength correlations through the monochromator reflections. For this we used the simple model of a monochromator crystal comprised of small, nonattenuating mosaic blocks. This model provided a transfer function for incident-

to-reflected rays, which was then approximated by a Gaussian distribution of the same parameter arguments. We used Gaussian distributions in order to obtain analytic results and to represent geometrical truncations of the beam by the finite source size and monochromator dimensions. The nickel-plated guides were assumed to be perfectly reflecting for neutrons impinging on the surface at less than the critical angle $\theta_g = 0.47^\circ$ and perfectly absorbing otherwise. We made the calculations for only one of the six crystal pairs, assuming that the other pairs respond identically, but at slightly different mean wavelengths. No attempt was made to account for the wavelength dependence of θ_g , due to the small wavelength spread ($\Delta\lambda/\lambda = 0.013$) for a given monochromator.

First, the effect of the vertical guides alone is expressed as the ratio of intensity at the sample position with and without the guides.

$$\frac{I_w}{I_{w/o}} = \alpha [1 + (\Delta\theta_m/\Delta\theta_c)^2]^{1/2} \text{erf}(\theta_g/\alpha\Delta\theta_m) \quad (1)$$

where

$$\alpha = \left[\frac{1 + (\Delta\theta_m/\Delta\theta_s)^2}{1 + 2(\Delta\theta_m/\Delta\theta_s)^2} \right]^{1/2}$$

$\Delta\theta_m = 1.2(\sin\theta_g)\Delta\theta_{FMM}$; $\Delta\theta_{FMM}$ is a monochromator rocking curve FWHM, and θ_g is the "mean beam" Bragg angle,

$\Delta\theta_s$ = gaussian width of the source flux geometrical truncation as viewed from the lower monochromator bank,

$$\Delta\theta_c^* = \Delta\theta_c \left[\frac{1 + (\Delta\theta_m/\Delta\theta_s)^2}{1 + (\Delta\theta_m/\Delta\theta_s)^2 + (\Delta\theta_c/\Delta\theta_s)^2} \right]$$

$\Delta\theta_c$ = the gaussian width of the vertical beam collimation due to the monochromator dimensions.

Second, with the vertical guide installed, the effect of the horizontal guide segments is calculated by comparing the intensity $I(G)$ at the sample position for a given total guide length G to that intensity $I(0)$ with no horizontal guides.

$$\frac{I(G)}{I(0)} = \frac{\text{erf}[B_v(G)]\text{erf}[B_h(G)]}{\text{erf}[B_v(0)]\text{erf}[B_h(0)]} \quad (2)$$

where

$$B_v(G) = Y_g/[2\Delta\theta_v(L-G)]$$

$$B_h(G) = X_g/[2\Delta\theta_h(L-G)]$$

X_g and Y_g = the horizontal and vertical dimensions of the horizontal guide rectangular bore—32 and 36 mm, respectively.

$\Delta\theta_h$ and $\Delta\theta_v$ = gaussian widths of the horizontal source-beam intensity distribution from the upper monochromator. (These widths include the cumulative effects of collimation, vertical guides, and monochromator reflections.)

L = the (fixed) sample-to-source slit distance
7.5 m.

The results calculated from Eqs. (1) and (2) are compared with the empirically observed gains in Table 5.4. Generally, the calculated values exceed those observed, with the worst agreement occurring for the final 2-m length of horizontal guide. Both the calculated and observed gains fall below those expected for a uniform distribution in the source intensity. Physically, this is because the guides are active only for divergent beam components that are well below the peak in the source intensity distribution (i.e., $\Delta\theta_H$ and $\Delta\theta_V$ are not large compared with θ_g). Thus, the disagreement between calculated and observed gains for the 6-m guide may result from a calculated intensity distribution that is slightly too broad.

SAXS STUDY OF DECOMPOSITION IN Al-2.6 WT % Li ALLOYS

S. Spooner

The aging process in Al-Li alloys proceeds rapidly to the coarsening stage. Precipitate/matrix interfacial energy is low, and lattice strain between the precipitate and matrix is very small. These barriers to nucleation being low and lithium mobility being high point to a very rapid passage through the nucleation and growth stage of decomposition. One consequence is that the study of coarsening kinetics should be convenient, and the fact that the precipitates are spherical makes scattering studies very appropriate. However, the precipitate density is high (approaching 50% depending on aging temperature), and problems of interprecipitate interference in the scattering arise.

In current studies, aging at low temperatures is under investigation with the object of examining very early stages of decomposition. Readily observable decomposition effects can be

seen for aging at 100°C after only a few hours. The principal method of monitoring decomposition kinetics is to examine changes in the apparent Guinier radius. However, interparticle interference effects are important, as indicated in the observation of a scattering intensity maximum away from zero scattering angle. The kinetic response can also be followed by assuming that there is a master scattering curve which can be scaled in time on the intensity and scattering vector axes. By either method of monitoring kinetics the results are not very satisfying. There appears to be a high degree of variability in results obtained from sets of samples which stems from preaging treatment. Nevertheless, scaling to a master curve is possible and suggests that a scaled particle size distribution is a kinetic invariant which is an essential feature of particle size coarsening.

An accurately determined master scattering curve should be interpretable in terms of the invariant size distribution function. In this study, the method of Schmidt-Brill for inversion of the scattering function in terms of a size distribution function of spheres would normally be appropriate. Attempts to extract the size distribution function have not yielded physically reasonable results. The reason is clearly due to interparticle interference as shown in Fig. 5.13. There is a secondary maximum, as well as a suggestion of a tertiary maximum, in these data. Interparticle interference effects have been observed in samples receiving a variety of heat treatments at several temperatures. The problem now calls for the separation of size distribution and interparticle distribution effects. Methods used in the analysis of micelle structures appear to be promising. Until such methods can be worked out, tests of coarsening theory through the determination of size distribution cannot be made convincingly.

In the meantime, prequenching effects are under investigation, where differences in aged structure are found to depend on whether the alloy is quenched directly to aging temperature

Table 5.4. A comparison of the calculated and observed intensity gains due to installation of neutron beam guides in both the vertical and horizontal flight paths of the 30-m SANS machine. The intensity was measured behind a 1-cm² slit at the sample position. The quantity $[L/(L-G)]^2$ is the expected gain for a uniform, monochromatic source intensity.

<u>Effect of vertical beam guides only</u>			
	<u>Calculated</u>	<u>Observed</u>	
$I_w/I_{w/o}$	1.37	1.28	
<u>Effect of horizontal beam guides (vertical guides in place)</u>			
<u>G(m)</u>	<u>Calculated $I(G)/I(0)$</u>	<u>Observed $I(G)/I(0)$</u>	<u>$[L/(L-G)]^2$</u>
2	1.76	1.78	1.86
4	4.12	4.09	4.59
6	9.20	5.60	25

Fig. 5.13. The function $k^4 I(k)$ is used to obtain particle size distribution in the Schmidt-Brill method. Note the subsidiary maxima in the plot, which indicate strong interparticle interference.

or quenched to room temperature and upquenched to the aging temperature. The aging temperature chosen for current studies is 100°C. It has been found that the scale of microstructure is larger for a given aging time when an initial quench to room temperature is eliminated. However, the general trend in differing kinetics does not become clear cut until after 16 h. Apparent inconsistencies at early times may reflect differences in speed of quench, time at room temperature, and possible loss of lithium solute from the sample foils.

DYNAMIC SCALING OF THE DECOMPOSITION STRUCTURE OF CHROMINDUR DURING AGING AT 525°C

S. Spooner

Iron-chromium and iron-chromium-cobalt alloys have been studied rather intensively in the last few years because of interest in understanding the decomposition process by aging within the miscibility gap. Iron-rich and chromium-rich regions evolve through a uniformly distributed phase separation, which was thought to begin by composition fluctuations of small amplitude rather than by the generation of distinct precipitates. Use of these alloys in the study of phase separation has the advantage that lattice strain effects and other sources of crystalline anisotropy are minimal. Neutron small-angle scattering is particularly appropriate since

both nuclear and magnetic scattering contrasts arising from chemical composition differences are large and make scattering measurements rather easy.

The distinction between the spinodal evolution of structure and the nucleation and growth of distinct precipitates is not clear. In the original Cahn-Hilliard treatment of spinodal decomposition, one expects to observe the development of a scattering maximum indicative of a kinetically favored decomposition-fluctuation wavelength. The size or scale of this wavelength was expected to be fixed in time with only a growth of scattered intensity as the fluctuation grew in amplitude. At long aging times a dynamic scaling having a $t^{1/3}$ dependence is expected for the structure whether the structure evolved by spinodal decomposition or by nucleation and growth. Consequently, in the decomposition process, dynamic scaling laws could be expected to have time exponents from zero to 1/3.

In recent studies of Fe-Cr by small-angle neutron scattering, dynamic scaling laws show time exponents in the range 0.1–0.3.¹ The results do not support a time exponent of zero as expected from the zeroth order spinodal decomposition theory. Furthermore, there are indications that several kinetic regimes are encountered in the process of decomposition.

In the current study of Chromindur (Fe-28 wt % Cr-10.5 wt % Co), a series of coupons were solution heat treated at 925°C for 2 h, quenched into icy brine, and aged at 525°C for times up to almost 500 h. The peak position in the small-angle scattering pattern was followed as a function of time and is plotted in Fig. 5.14. It was found that a time exponent of 0.16 appears to apply to the decomposition for up to 20 h. A time exponent of 0.25 then applies from approximately 20 h to almost 500 h. No $t^{1/3}$ dependence was seen for the times examined.

Fig. 5.14. The scattering vector value at the intensity peak is shown as a function of time for a series of chromindur samples aged at 525°C. Dynamic crossover is observed at approximately 20 h.

This result would not be so interesting if it were not for the fact that a similar transition in dynamic scaling has been seen in an entirely different system, viz., Al-Zn. In that system the decomposition proceeds by homogeneous nucleation of a zinc-rich precipitate, and in making a transition from one dynamic scaling regime to another, a change in precipitate morphology was seen. By analogy, it is suspected that a morphology change is occurring in Chromindur wherein the topological connectedness of the chromium-rich region may change. Ultimately, a final evolution to entirely separated precipitates of chromium-rich regions can be expected with a $t^{1/3}$ dynamic scaling.

The time variation of the integrated intensity, interestingly enough, does not appear to exhibit any remarkable change at the dynamic crossover at 20 h. Instead, a gradual increase in integrated intensity following a $t^{0.06}$ dependence is seen. The implication in this observation is that final compositions for each iron- or chromium-rich region are reached quickly but very slow changes in composition profile are still occurring. In a true "precipitate and matrix structure" the integrated intensity should be independent of time. The slow change may be attributable to the slow migration kinetics of chromium in this alloy.

1. S. Katano and M. Iizumi, *Phys. Rev. B* 52, 835 (1984).

DETERMINATION OF DISPERSOID SIZE DISTRIBUTION IN AN OXIDE-STRENGTHENED NICKEL-CHROMIUM ALLOY BY SMALL-ANGLE X-RAY SCATTERING¹

J. J. Stephens² S. Spooner

High creep strength at elevated temperatures is achieved in mechanically alloyed oxide dispersions in nickel-based alloys and is based on the inhibition of dislocation motion by un-shearable oxide particles. The strengthening effect can arise from the Orowan dislocation bowing stress or from the stress required to unpin edge dislocations from the interface between the oxide and the matrix. In either case the relevant structural feature is the separation L between oxide particles evaluated on a slip plane in the matrix. The dispersion-strengthening component of the creep strength can then be calculated from the value of L . The object of this study is to evaluate the oxide dispersoid size distribution on an absolute scale, which then can be used to determine L .

Transmission electron microscopy (TEM) has been used in past investigations of oxide strengthening but is limited in statistical precision because the sampling volume is small and may encompass only a few thousand oxide particles. Small-angle scattering has an advantage in employing a much larger sampling volume, and when the oxides exhibit good electron density contrast with the alloy matrix, the scattering effects are easily measured. Interpretation of the scattering data is most straightforward when the shape of the scattering oxide is spherical and when an

analytic expression for the size distribution can be used—the most often assumed function is that of the log-normal distribution. If the oxide can be assumed to be spherical, then the Schmidt-Brill method of scattering analysis can be used to determine the size distribution without having to assume a particular functional form for the distribution.

In this study three methods for characterizing the size distribution of essentially Y_2O_3 dispersoids in a nickel-chromium matrix were undertaken. First, the distribution of oxide dispersoids was fit to a log-normal distribution based on approximately 2000 particles. Second, the shapes of the x-ray small-angle scattering curves were fit to a log-normal distribution using the known relationship between the mean and variance parameters, the forward intensity, and the Porod asymptote obtained in a plot of $k^4 I(k)$ vs k , where k is $4\pi/\lambda$ and $I(k)$ is the scattering intensity. Finally, the Schmidt-Brill analysis of scattering was applied to the scattering data. In the analysis of oxide dispersoids, the absolute determination of the number of particles per volume is as important as the size distribution for the evaluation of L . With TEM the foil thickness in the sampled region must be determined accurately. In x-ray scattering an absolute scattering standardization is required. In this study, a sample of irradiated aluminum having a distribution of voids which have been well characterized in neutron scattering experiments was used for calibration.

Results of the investigation are shown in Fig. 5.15, which is a plot of the cumulative percent of dispersoids versus dispersoid diameter for a

Fig. 5.15. Cumulative percentage distribution of particles is shown on a probability plot. The methods used to calculate these results are direct determinations from TEM micrographs and two methods of indirect analysis employing small-angle x-ray scattering.

particular alloy (MA 754). It can be seen that the Schmidt-Brill analysis indicates a larger fraction of dispersoids for small sizes in comparison with the TEM results. The log-normal fitting results obtained from the x-ray scattering data appear to run between the two sets of results. This points to a subtle but important difference between the actual distribution and the assumed normal distribution function.

These analyses of oxide dispersion were then used for the calculation of L for two alloys subjected to creep testing. A minimum creep strain rate for one alloy was found to be 25% greater than that for a second alloy at the same temperature. The only difference between the alloys was the oxide dispersion parameters. With the results of the size distributions from the Schmidt-Brill analysis, a 26% difference in creep resistance was calculated for these two alloys on the basis of the dispersoid separation L . It is concluded that the analysis of small-angle scattering, using only the assumption of spherical oxide particles, was capable of producing a surprisingly quantitative result in this study.

1. Summary of paper to be published.
2. Stanford University, Stanford, Calif.

DEFORMATION OF MICROPHASE STRUCTURES IN POLYURETHANES

C. R. Desper¹ N. S. Schneider¹
J. P. Jasinski² J. S. Lin

The elastomeric properties of segmented polyurethanes have long been associated with microphase separation. The microphase which is rich in soft segment units confers elastomeric behavior, while the microphase which is rich in hard segments provides physical cross-linking. Stretching such a structure results in the orientation of the periodic microphase structure and of the hard- and soft-segmented molecular units within the microphases.

In polyurethane elastomers, a high level of long-term residual deformation is commonly observed after removal of stress.³ The hysteresis behavior in such mechanical properties must be understood for practical applications. For diol-cured elastomers, residual hard-segment orientation was observed upon removal of applied tensile stress. This orientation hysteresis effect was particularly pronounced in elastomers totally lacking N-H groups, which participate in hydrogen bonding. In the opposite extreme, amine-cured polyurethanes possess two N-H groups per hard-segment unit, and they have shown a greater propensity toward microphase segregation than their diol-cured counterparts, presumably because of the large number of possible hydrogen bonds between the hard-segment chemical groups.

In this first quantitative study of polyurethane microstructure deformation by small-angle x-ray scattering (SAXS), we investigated the response of microphase structure to deformation in three types of polyurethanes. These three distinct classes of polymers are amine-cured, triol-cured, and diol-cured polyurethanes.

All polymers were synthesized by a two-step process and are transparent, indicating no evidence of crystallinity or of monomer-phase separation; this was also confirmed by wide-angle x-ray scattering (WAXS).

Experimentally, SAXS patterns were obtained in the unstretched state at 50, 100, and 200% elongation and in the recovered state five minutes after removal of the applied stress. The residual deformations in the recovered states were found to be 10, 10, and 41% for amine-, triol-, and diol-cured polymers, respectively.

As shown in Figs. 5.16(a)–5.16(c), the iso-intensity contour SAXS patterns for the three types of polyurethanes deformed to 200% clearly demonstrate that there are three different modes of deformation of the polyurethane microstructure. A shear mode, a tensile mode, and a rotation of independent particles are, respectively, proposed for amine-cured, diol-cured, and triol-cured polyurethanes. The detailed arguments about the deformation response and hysteresis behavior in these three modes are presented elsewhere.⁴ Chemical composition and morphology may well influence the mode of deformation response, and thus further studies, involving a wider variety of practically important polyurethanes, are required.

1. Army Materials and Mechanics Research Center, Watertown, Mass.
2. Keene State College, Keene, N.H.
3. C. Hepburn, p. 51 and p. 249 in *Polyurethane Elastomers*, Applied Science Publishers, New York, 1982.
4. C. R. Desper et al., *Polymer* (in press).

DYNAMIC SAXS CRYSTALLIZATION OF POLYMERS¹

J. L. Magill² J. M. Schultz³
J. S. Lin

Many techniques^{4,5} have been employed to measure the kinetics of phase transformations in polymers. The most common methods involve optical microscopy, dilatometry, and differential scanning calorimetry. Indeed, any procedure that provides a sensitive and realistic measure of the liquid $\leftrightarrow$ solid phase change is a useful tool for monitoring the transformation. In other words, the technique employed must be capable of following the nucleation and growth rates of the macromolecules. Most conventional measurements made on supercooled polymer melts normally lack the capability of investigating in situ the intricacies of morphology associated with nuclei formation, their development or growth into spherulites, and changes in lamellar dimensions with time during isothermal transformation and secondary crystallization. Frequently, these measurements are made independently on specimens after the crystallization is completed. There are obvious disadvantages associated with studies carried out in this manner, since analyses require that certain concepts are valid, for example, as in Avrami analysis^{4,6} of the crystallization kinetics of polymeric materials.

Fig. 5.16. Isointensity SAXS contour patterns after 200% elongation for (a) amine-cured, (b) diol-cured, and (c) triol-cured polyurethanes.

With the availability of high-intensity x-ray sources and computerized data acquisition systems, considerable versatility is now at hand for the experimenter who wishes to study and analyze the more intricate and mechanistic aspects of crystallization. Although there are resolution and time restrictions associated with the microscopic and/or molecular details of the morphology and kinetics, the small-angle x-ray scattering (SAXS) technique allows one to follow the development of scattered intensity and measurement of crystallite dimension in real time as the crystallization proceeds through its primary and secondary stages. The ORNL 10-m SAXS camera with its two-dimensional position-sensitive detector⁷ and relatively high speed data acquisition system enables one to record morphological changes, as SAXS curves, during the isothermal or nonisothermal crystallization from the polymer melt. Data of these kind relate directly to the microstructure or textures formed during crystallization. Ancillary facilities^{8,9} are needed to change and control the specimen temperature during fusion and crystallization. Sample degradation must be minimized during runs of long duration.

Schematics of the experimental apparatus have appeared in the literature,⁸ and further accessories will be mentioned in this presentation. At present, more than one person is required to run the experiment, but with refinements and improvements in design and automation, the ease of manipulation and control will undoubtedly become more facile.

Although the ORNL 10-m SAXS facility does not possess the high intensity of a synchrotron source, a proper match of experiment and equipment can be made for many phase transformation studies, melt + solid, solid + solid, and solid + melt transitions, where important unanswered problems exist in materials systems.

Several diverse experiments have been carried out to investigate the following:

1. the effect of undercooling upon rate of crystallization,
2. the effect of crystallization temperature on the long period measured at the crystallization temperature and at room temperature,
3. the effect of crystallization time on the long period,
4. the effect on scattered intensity of time, temperature, and molecular weight,
5. the effect of cooling rate upon crystallization behavior,
6. the influence of sample molecular weight on the long period,
7. the morphological changes associated with solid + solid transition, etc.

There is plenty of scope for novel investigations and/or comparisons among other experimental procedures which depict both primary and secondary crystallization behavior. Investigations are in progress to test theories or models of crystallization over a large crystallization range.

1. Summary of paper: *Polymer Preprints* 24, 221 (1983).

2. University of Pittsburgh, Pittsburgh, Pa.
3. University of Delaware, Newark, Del.
4. J. H. Magill, p. 247 in *Treatise on Materials Science and Technology*, Vol. 10, ed. by J. M. Schultz, Academic Press, New York, 1977.
5. B. Wunderlich, p. 115, in *Macromolecular Physics*, Vol. 2, Chapter VI, Academic Press, New York, 1976.
6. M. Avrami, *J. Chem. Phys.* 7, 1103, (1939); 8, 212 (1940); 9, 177 (1941).
7. R. W. Hendricks, *J. Applied Crystallogr.* 11, 15 (1978).
8. J. M. Schultz, J. S. Lin, and R. W. Hendricks, *J. Appl. Crystallogr.* 11, 551 (1978).
9. J. H. Magill, J. M. Schultz, and J. S. Lin, *Bull. Amer. Phys. Soc.* 28, 310 (1983).

LATTICE DYNAMICS

INELASTIC NEUTRON SCATTERING FROM A MARTENSITICALLY TRANSFORMING INDIUM-THALLIUM ALLOY¹

T. R. Finlayson² Mark Mostoller
W. Reichardt³ H. G. Smith⁴

There is currently considerable interest in materials which exhibit structural distortions driven by phonon softening with variation in temperature. In InTl alloys, in the composition range 15.5–31 at. % Tl, the distortion is from face-centered cubic to face-centered tetragonal on cooling below a transformation temperature T_m . The experimental evidence for phonon softening has been the temperature dependence of the elastic stiffness modulus, $c' = (c_{11} - c_{12})/2$,⁵ while a theoretical calculation by Gunton and Saunders⁶ predicted an appreciable softening for $[c\bar{c}0]$ phonons with $[c\bar{c}0]$ polarization and having $0 < q < 0.2$ ($2\pi/a$). However, severe damping of certain ultrasonic waves in these materials often prevents the direct measurement of c' , which is consequently calculated from the stiffness constants for other modes. Therefore, we have attempted to observe phonon softening in InTl directly using neutron scattering measurements.

On account of the large ratio of the absorption to coherent scattering cross sections for indium (190 b/2.2 b), the preferred specimen geometry was a large flat crystal, such that measurements could be made predominantly in reflection. Two such single-crystal plates, of composition In 24 at. % Tl and approximately $40 \times 20 \times 3$ mm³, were spark machined from a 25-mm-diameter cylindrical crystal grown by the Bridgman technique from starting materials of 5N purity. Each plate had an $[001]$ direction parallel to its length, and the two had $[100]$ and $[110]$ directions normal to their largest area faces, respectively. The neutron scattering measurements were performed on the HB-2 triple-axis spectrometer at the High Flux Isotope Reactor. Pyrolytic graphite (002) planes were used as both monochromator and analyzer, generally with collimation of 40 min before and 20 min after the specimen.

The dispersion curves measured at room temperature for In 24 at. % Tl are plotted in Fig. 5.17. Measured values for FWHM were 0.1 THz at low q and increased to as much as 0.9 THz as q increased. For constant- E scans, δq at half the maximum intensity was typically 0.1 ($2\pi/a$) at low q and increased as q increased. Some examples of phonon scans are given in Fig. 5.18, from which the significant broadening of the phonon groups for q increasing is apparent. With the aid of a computer program developed previously⁷ for mass-defect CPA calculations, it has been shown that to some extent the observed broadenings are qualitatively consistent with the effect of the heavy mass defect (thallium) on intensity distributions for the "perfect indium crystal."

A satisfactory fit to the data has been obtained using a general Born-von Kármán force-constant model extended to fourth-nearest neighbors (12 parameters), which is the maximum number of neighbors that can be included in fitting only high symmetry data with a general model. The phonon frequencies calculated from this model are indicated by the full curves in Fig. 5.17 and are in good agreement with the experimental data.

The dashed-dot lines in Fig. 5.17 represent a phenomenological, local pseudopotential fit to the data. The curves shown were calculated using an Ashcroft (empty core) pseudopotential,⁸ with an effective charge $Z = 0.9463$ and a core radius $r_M = 1.1166$ Å. The electronic screening function used was a very accurate interpolation

Fig. 5.17. The dispersion curves at room temperature for In 24 at. % Tl. The solid curves show calculated frequencies for the general force-constant model, and dashed-dot curves show frequencies calculated using the pseudopotential discussed in the text. The thin lines show initial slopes expected from the elastic constants. The inset shows low- q data along the T_1 branch with a "guide-to-the-eye" line drawn through the experimental points.

Fig. 5.18. Measured data from (a) constant-E scans along the $[111]_L$ branch and (b) constant-Q scans along the $[111]_T$ branch.

formula⁹ for the Geldart-Taylor response function,¹⁰ which incorporates exchange and correlation corrections to the RPA. The pseudopotential fit to the data is inferior to that of the four-neighbor Born-von Kármán model but is nonetheless remarkably good in view of the simplicity of the pseudopotential model, which has only two adjustable parameters, or three if the well depth is allowed to vary away from the Ashcroft value of zero. It would appear that the lattice vibrations in the In-Tl system, and perhaps the phase

diagram as well, can be discussed in terms of models appropriate for simple metals. In this regard, Gunton and Saunders⁶ have performed non-local pseudopotential calculations for In-Tl alloys. Their results for In 25 at. % Tl compare reasonably well with our data, except for the $[111]_L$ $[111]_T$ branch. Their calculated values for this, the soft mode for the phase transition, lie considerably above the measured points except at low wave vectors (where the softness is operative).

The relatively high transformation temperature for the In 24 at. % Tl precluded any worthwhile search for a temperature dependence of T_1 phonons in this crystal. For this purpose we used instead a crystal with a composition, 27 at. % Tl ($T_1=150$ K). Constant-Q scans at $q = 0.15$ ($\sqrt{2}(2\pi/a)$) and 0.25 ($\sqrt{2}(2\pi/a)$) were performed at a number of temperatures. In addition, the whole branch was measured at 293 and 180 K. No phonon softening was observed with decreasing temperature. Clearly, any phonon softening associated with the structural transformation must be occurring for q values closer to the zone center than it has been possible to study during the present experiment, and we are attempting to prepare crystals having sharper rocking curves, with a view to investigating this point.

1. Summary of paper: Solid State Communications (in press).
2. Guest scientist from Monash University, Clayton, Victoria, Australia.
3. Guest scientist from Kernforschungszentrum Karlsruhe, Federal Republic of Germany.
4. On assignment with the Division of Materials Sciences, U.S. Department of Energy, Washington, D.C.
5. D. B. Novotny and J. F. Smith, Acta Metall. 13, 881 (1965).
6. D. J. Gunton and G. A. Saunders, Solid State Commun. 12, 569 (1973).
7. T. Kaplan and M. Mostoller, Phys. Rev. B 9, 353 (1974).
8. N. W. Ashcroft, Phys. Lett. 23, 48 (1966).
9. Mark Mostoller, unpublished.
10. D. J. W. Geldart and R. Taylor, Can. J. Phys. 48, 167 (1970); *ibid* 48, 155 (1970).

THE LATTICE DYNAMICS OF LAYERED STRUCTURE COMPOUNDS: PdTe_2 ¹

T. R. Finlayson² W. Reichardt³
H. G. Smith⁴

PdTe_2 , with the CdI_2 structure (space group D_{3d}), is a superconducting transition-metal dichalcogenide (TMD). The superconducting transition temperature T_c for PdTe_2 is only 1.7 K, but this compares favorably with the transition temperatures for other TMDs.⁵ These compounds of general formula MX_2 consist of a group IV to VIII metal M and a chalcogen atom X (S, Se, or Te), and they crystallize in various polytypes composed of X-M-X sandwiches. In general for the superconducting members the M-X coordination is trigonal prismatic (TP). PdTe_2 is the notable exception to this generalization, since for it

the M-X coordination is octahedral (0). Most of the other C coordination TMDCs show semiconducting or semimetallic properties.

Discussion of the superconductivity of the TMDCs has emphasized the highly anisotropic, partly two-dimensional character of these compounds,⁶ an aspect which is further exemplified by the occurrence of superconductivity among some intercalated TMDCs.⁵

Existing data for the phonon dispersion of most of the TMDCs suffer from the disadvantage that crystals have invariably been small, and thus there is no complete data set for these compounds. PdTe₂, on the other hand, crystallizes very readily, and the availability of a large, roughly cylindrical sample, ~60 mm long and ~12 mm in diameter, provided the initial stimulus for measuring the dispersion curves by neutron scattering techniques in the hope of gaining some understanding of the superconductivity in this material.

The experiments were carried out primarily on the HB-3 spectrometer at the High Flux Isotope Reactor. The data obtained at room temperature for each of the symmetry directions $[\zeta 0 0]$, $[\zeta \zeta 0]$,

and $[00 \zeta]$ are reproduced in Fig. 5.19. The assignments made on the figure have been accomplished with the aid of structure factor calculations using a model for the lattice dynamics of PdTe₂. The branches in Fig. 5.19 have been labeled according to the irreducible representations.

Features of the results which are of particular interest are the pronounced dips in some low-energy optic branches (Δ_2 , Σ_1 , T_2) in the vicinity of Γ_2^+ . The structures observed in these branches are not caused by hybridization with other branches. This observation is quite obvious for the $[\zeta \zeta 0]$ direction because the T_2 branch and the T_1 branch around 4 THz belong to different irreducible representations. In the $[\zeta 0 0]$ directions the corresponding branches have the same symmetry, but their mutual interaction is small. However, there is a strong interaction between the upper Σ_1 branch and the longitudinal acoustic Σ_1 branch, which results in anticrossing behavior near $q = 0.35$ ($4\pi/a\sqrt{3}$). The measured dispersion curves for PdTe₂ cannot be reproduced by a simple force-constant model with short-range interactions only. This is especially true for dips in the low-frequency optic

Fig. 5.19. Phonon dispersion curves measured at room temperature for PdTe₂. The lines are calculated from the force-constant model described in the text.

branches in the vicinity of the Γ point. Therefore, we included in our model shell interactions, which are similar to those introduced by Weber,⁷ to account for dips in some acoustic branches of the superconducting refractory carbides. Thus, the model consisted of conventional axially symmetric Born-von Kármán interactions between the ion cores plus negative short-range interactions between the charge- and mass-less shells which were coupled weakly to the ion cores. The dynamical matrix is given by the expression

$$D(q) = D_0(q) + K[K + R(q)]^{-1} R(q), \quad (1)$$

where $D_0(q)$, $R(q)$, and K represent the Born-von Kármán, the shell-shell, and the shell-core interactions, respectively.

The lowest, doubly degenerate, optic, Γ -point frequency, Γ_2^+ , is associated with modes where the two tellurium planes of the sandwich move with opposite phase in either the x or y direction and the palladium atoms are at rest. The frequency of the corresponding vibration of tellurium atoms, perpendicular to the planes, Γ_2^+ at about 4 THz is higher by a factor of almost 2. From this large ratio it is apparent that an essentially transverse interaction between nearest neighbor tellurium atoms must be responsible for the low Γ_2^+ frequency. This effect has been incorporated in the model by including a transverse inter-shell force constant for the interactions between Te-Te nearest neighbors. This force constant had to be negative in order to produce a dip in the dispersion curves.

The dispersion curves obtained with this model are shown compared directly with the data in Fig. 5.19. We used 14 Born-von Kármán force constants for interactions out to the seventh nearest neighbor and two additional parameters for the shell interaction. The quality of the fit to the data is reasonably good considering the simplicity of the model.

The use of axially symmetric forces must be considered only an approximation. Furthermore, the shell interactions introduced in order to simulate electronic screening effects are represented by only one force constant. This produces too sharp a drop in the lowest optic branch of the $[00c]$ direction, whereas for directions within the basal plane, the structures in the calculated branches are less pronounced than those found experimentally. Likewise, the optic branch around 4 THz is much flatter than indicated by the model. We conclude that the phonon frequencies near Γ_2^+ are renormalized to some extent by the same mechanism which produces dips in the lowest optic branches near Γ_2^+ . We have attempted to describe this behavior, with little success, by a second model in which we included longitudinal shell-shell interactions. Further experimental and theoretical work is needed in order to understand the relationship between the unusual shapes of these dispersion curves and superconductivity in PdTe_2 .

3. Guest scientist from Kernforschungszentrum Karlsruhe, Federal Republic of Germany.

4. On assignment with the Division of Materials Sciences, U.S. Department of Energy, Washington, D.C.

5. B. W. Roberts, *J. Phys. Chem. Ref. Data* 5, 581 (1976) and NBS Tech. Note No. 983 (1978).

6. T. F. Smith, R. M. Shelton, and R. E. Schwall, *J. Phys. F* 5, 1713 (1975).

7. W. Weber, *Phys. Rev.* 38, 5082 (1973).

INTERCALANT ORDERING AND LATTICE DYNAMICS IN POTASSIUM MERCURIOGRAPHITIDES¹

W. A. Kamitakahara²
P. C. Eklund³

L. E. Delong³
R. M. Nicklow

The interplay of dimensionality with physical properties such as normal state conductivity, superconductivity, phase transitions, and phonon spectra is a central theme of research on graphite compounds. A degree of freedom unique to these systems lies in the ability to vary the degree of anisotropy through changes in stage number. Elastic and inelastic scattering experiments have been carried out on samples of KHgC_8 and KHgC_8 , revealing their intercalant ordering and low-frequency vibrational spectra. These materials exhibit unusual superconducting properties, including very anisotropic critical fields, moderate T_c 's (1.5 K for stage-one KHgC_8 and 1.9 K for stage-two KHgC_8), and a dramatic sharpening of the transition and a slight increase in T_c for KHgC_8 under pressure. The higher T_c for stage two is interesting in that greater anisotropy of the electronic structure and lower Hg content ought to decrease rather than increase T_c . Synthesis of a pure stage-three sample and proper characterization of its superconducting behavior would be of further interest, since its electronic structure should be nearly two-dimensional.

Our elastic scattering data on the stage-one compound reveal two distinct phases of KHgC_8 ; within the same sample, a 93% majority phase with a c-c interplanar distance $I_c = 10.24$ Å and a 7% minority phase with $I_c = 10.83$ Å. The KHg intercalant ordering exhibits long-range order in the basal plane (i.e., almost perfect 2-D order) and strong correlations along the c axis (i.e., tendencies toward 3-D order) for both phases. In contrast, for stage-two KHgC_8 , we find only a single phase with perfect (2×2) in-plane registry but no intercalant interlayer correlations. Structural models that fit the data for the (2×2) phases of KHgC_8 and KHgC_8 have been constructed. The presence of two phases for stage one provides a clue to its peculiar behavior under pressure, the sharpening and rise in T_c presumably being due to favoring of one phase over the other or to rearrangement of the intercalant within one phase. Also relevant to the superconductivity of KHgC_8 are precise measurements we have made of the C-C bond distance, which is a measure of the charge transfer from KHg to C layers. The charge transfer to each C atom is much less than in KC_8 or RbC_8 (the only other known type of superconducting graphite intercalation compound, with

1. Summary of paper to be published.

2. Guest scientist from Monash University, Clayton, Victoria, Australia.

$T_C \sim 0.1$ K), indicating that the intercalant layers are much more metallic in KHgC_8 .

The lattice vibrational spectra for KHgC_8 and K_2HgC_8 are rather similar, apart from expected stage-related differences. One unusual feature is that out-of-plane Hg motions have much lower energies (~ 3 meV) than in-plane motions (10 meV). However, KHgC_8 and K_2HgC_8 do not differ in this respect. Since the density of states at the Fermi level is known from heat capacity data to be smaller for KHgC_8 and since KHgC_8 is three dimensionally ordered while K_2HgC_8 is not, it is difficult to understand on the basis of present data why the latter has a higher T_C .

1. Summary of papers: *Phys. Rev. B* 29, 460 (1984); p. 861 in *Proceedings of the 17th International Conference on Low-Temperature Physics (LT-17)*, North-Holland, Amsterdam, 1984.
2. Ames Laboratory and Iowa State University, Ames, Ia.
3. University of Kentucky, Lexington, Ky.

KOHN ANOMALY IN METASTABLE FCC LANTHANUM

J. Zarestky¹ C. Stassis¹
G. S. Smith¹

At atmospheric pressure, metallic lanthanum exists in three different crystallographic forms. The bcc γ phase exists between 1191 K (the melting point) and approximately 1138 K. The fcc β phase is stable between 1138 and 609 K, whereas the double hcp α phase is considered to be the stable phase of lanthanum below 609 K. The free-energy difference between the α and β phase is so small, however, that the fcc β phase can exist below 609 K in a metastable form.

The fcc phase of lanthanum has many rather intriguing properties. Its superconducting transition temperature at atmospheric pressure is approximately 1 K higher than that of the stable hcp phase, increases with increasing pressure, and saturates to a value of nearly 13 K at approximately 200 kbar. The thermal expansion coefficient of this phase becomes negative at approximately 40 K and reaches its largest negative value in the vicinity of 18 K.

A fundamental understanding of the rather unusual properties of fcc lanthanum has been hindered by a lack of information regarding the elastic and lattice dynamical properties of the metastable phase of this metal. Recently, we were able to grow a single crystal of the metastable fcc phase of sufficient size to study the lattice dynamics by inelastic scattering of neutrons. In this note, we present some of the results obtained in this study.

The measured dispersion curves along the $[\xi\xi\xi]$ symmetry direction at room temperature and at 10 K are plotted in Fig. 5.20. At room temperature, the $T[\xi\xi\xi]$ branch has rather unusual dispersion for $\xi > 0.25$, a behavior similar to that exhibited by this branch in the high-temperature stable fcc phase. At 10 K, on the other hand, this branch develops a pronounced dip at a reduced wave vector of approximately 0.42. The phonon frequencies in the vicinity of $\xi = 0.42$ decrease

Fig. 5.20. Experimental dispersion curves along the $[\xi\xi\xi]$ direction of the metastable fcc phase of lanthanum at 295 and 10 K.

gradually with decreasing temperature, and they reach their lowest values below approximately 40 K.

To ascertain the origin of this anomaly, we performed self-consistent calculations with the use of a first-principles pseudopotential method in which the 4f states were excluded. We find that the Fermi surface exhibits a pronounced nesting feature along the $[\xi\xi\xi]$ direction with $\xi = 0.425$. As a result of this nesting, the generalized susceptibility along the $[\xi\xi\xi]$ direction exhibits a distinct peak at $\xi = 0.425$. Thus, the calculations strongly suggest that the phonon anomaly observed at low temperatures is a Kohn anomaly arising from a particular nesting feature of the Fermi surface of fcc lanthanum.

1. Guest scientist from Ames Laboratory and Iowa State University, Ames, Ia.

PHONON DISPERSION CURVES OF BCC Ba

J. Mizuki¹ C. Stassis¹
J. Zarestky¹

Ba, as well as Sr and Ca, is a divalent alkaline earth metal. At room temperature and ambient

pressure, the structure of Ba is bcc, whereas that of Sr and Ca is fcc. Under pressure, the bcc phase of Ba transforms to an hcp structure at 55 kbar. Also, at 37 kbar Ba becomes a superconductor with $T_c = 0.06$ K. These properties are highly dependent on the position of the d bands relative to the Fermi level.

Experimental investigation of the elastic and lattice dynamical properties of these metals has been hindered by difficulties in growing single crystals. However, recently we were able to grow several single crystals of bcc Ba of sufficient volume for inelastic neutron scattering experiments. The crystals were grown using the following procedure. Several grams of polycrystalline Ba were encapsulated in a Ta crucible in a helium atmosphere. A single crystal was then grown from the melt in a furnace in situ on a double-axis neutron spectrometer located at the Oak Ridge Research Reactor.

The phonon dispersion curves along the $[\xi 00]$, $[\xi \xi 0]$, and $[\xi \xi \xi]$ symmetry directions were measured at room temperature using a triple-axis spectrometer at the High Flux Isotope Reactor. Also, the curves along the $[\xi 00]$ direction were measured at 600°C. The general features of the dispersion curves are similar to those of simple bcc metals (like Na and K). The most interesting feature, however, is that the transverse branch appears to lie higher in frequency than the longitudinal branch in the $[\xi 00]$ direction. The existence of this feature was established by making high-resolution measurements on several single crystals at room temperature and at 600°C. Generalized pseudopotential calculations which include the d-band effect cannot reproduce this kind of anomaly. To clarify this point, frozen phonon calculations are presently in progress in the solid state theory group at the Ames Laboratory.

1. Guest scientist from Ames Laboratory and Iowa State University, Ames, Ia.

MAGNETIC PROPERTIES

DIRECT OBSERVATION OF SPIN WAVES ABOVE T_c FOR NI

H. A. Monk J. W. Lynn¹

Measurements made about 10 years ago demonstrated the unexpected result that spin waves measured in constant energy scans changed little in Ni as the temperature was increased above the Curie point T_c .^{2,3} Because of the steepness in the dispersion relation of the magnetic excitations, a large energy broadening could still produce a sharp peak in constant energy scans; however, it was estimated that the half width in energy of the excitations was smaller than the excitation energy for energies above about 40 meV. This seems reasonable on general physical grounds: T_c corresponds to an energy of about 54 meV, and as the excitation energy approaches and exceeds this value, it is expected that the thermal fluctuations will not completely destroy the spin-wave-like excitations.

However, recent work at Brookhaven National Laboratory⁴⁻⁶ using polarized neutron beams showed that for temperatures above T_c the excitations produced neutron scattering with a maximum intensity at $E = 0$ and thus could be described by a diffusive-like behavior. The earlier ORNL work clearly suggested diffusive behavior for small momentum transfers, but the Brookhaven work attempted to demonstrate that diffusive behavior existed over much of the Brillouin zone.

Now high-resolution polarized-beam measurements have been made at ORNL using the HB-1 spectrometer at the High Flux Isotope Reactor, which clearly demonstrates the spin-wave nature of the magnetic excitations above T_c for momentum values of $[0.1 \ 0.1 \ 0.1]$ and larger in zone-boundary units. High resolution was obtained by using ^{57}Fe as polarizing and analyzing crystals and by using a large (400-gram) sample of ^{60}Ni . Figure 5.21 shows constant momentum transfer scans for

Fig. 5.21. Magnetic excitations for the $[111]$ direction in nickel for $T = 1.1 T_c$. Solid lines are Lorentzian fits to the data.

nickel at $1.1 T_c$. Only the magnetic spin-flip scattering is shown. Clearly the scattering peaks at $E = 0$ for these scans, so a diffusive picture is appropriate. Figure 5.22 shows scans at higher momentum transfers. The scattering shown does not peak at $k = 0$ but at finite higher energy values that increase as the momentum transfer increases. A diffusive picture is not appropriate for these excitations, and the solid lines are given by a fit to the data with a damped harmonic oscillator. This result shows that the spin-wave-like excitations exist above T_c as originally suggested in our earlier work and that the Brookhaven picture of the excitations for nickel above T_c is incorrect. Additional measurements are planned to characterize further the nature of the magnetic excitations above T_c in both Ni and Fe.

1. On leave from the University of Maryland, College Park, Md.
2. H. A. Mook, J. W. Lynn, and R. M. Nicklow, *Phys. Rev. Lett.* **30**, 556 (1973).
3. J. W. Lynn, *Phys. Rev. B* **11**, 2624 (1975).
4. O. Steinsvoll et al., *Phys. Rev. Lett.* **51**, 300 (1983).
5. Y. J. Uemura et al., *Phys. Rev. Lett.* **51**, 2322 (1983).

Fig. 5.22. Magnetic excitations for the $[111]$ direction in nickel for $T = 1.1 T_c$ at higher momentum transfers than those in Fig. 5.21. The data show that the excitations no longer peak at zero energy and that a spin wave type of excitation exists. Solid lines are damped harmonic oscillator fits to the data.

6. G. Shirane et al., *J. Appl. Phys.* **55**, 1887 (1984).

MAGNETIC EXCITATIONS IN CuMn SPIN-GLASS ALLOYS^{1,2}

Y. Tsunoda³ N. Kunitomi³
J. W. Cable

Recent neutron scattering measurements have helped to clarify two important features of CuMn spin glasses. Murani and co-workers⁴ have studied the dynamical behavior of spin-glass systems and have observed characteristic ferromagnetic spin correlations with a broad distribution of relaxation times and a dynamical freezing process. By means of the polarization analysis technique, Cable and co-workers⁵ have observed the coexistence of two types of magnetic short-range order (MSRO): one is a modulated-spin structure, and the other is a ferromagnetic cluster associated with the atomic short-range order (ASRO). These ordered regions produce diffraction maxima which are found at the $(1/2, 1/2, 0)$ and the $(1, 1, 0)$ reciprocal lattice points, respectively. Both of these observations seem to be essential for understanding the CuMn spin-glass system. However, the physical relationship of these properties is not yet understood.

We have studied the inelastic scattering of neutrons around the magnetic diffuse peak positions of a $\text{Cu}_{78.7}\text{Mn}_{21.3}$ single crystal. The spin-glass freezing temperature of a CuMn alloy with this Mn concentration is estimated to be $T_f \sim 90$ K. Most of the data were taken by scanning along the $[010]$ direction from the (100) to the (110) reciprocal lattice points.

Experimental data at 20 K are shown in Fig. 5.23. The strong peaks observed at $\Delta E = 0$ meV are due to the superposition of the broad ASRO peak centered at $(1/2, 1/2, 0)$ and the MSRO peaks. The magnetic contribution to the diffuse scattering, which is derived by subtracting the data at 290 K from those at 20 K, is shown by the open circles. The magnetic-diffuse scattering at $\Delta E = 0$ meV is also composed of two parts, comparatively narrow satellite diffuse peaks at $(1/2, 1/2, 0)$ and a broad peak at $(1, 1, 0)$; this result is consistent with the previous data.⁵ Weak inelastic peaks are observed around both of the magnetic-diffuse peak positions even though the temperature is far below the freezing temperature ($T \sim 0.22 T_f$). Figure 5.24 indicates the data obtained at 150 K ($1.6 T_f$). Elastic magnetic diffuse scattering still exists with an intensity of about one third that at 20 K. On the other hand, the inelastic-scattering intensities are markedly increased. At room temperature ($3.2 T_f$), the elastic component of the diffuse peak is mostly due to the ASRO, while the inelastic-scattering intensities have increased even more. Longitudinal scans along the $[100]$ direction passing through the $(1/2, 1/2, 0)$ diffuse peak position have also been performed at 150 and 290 K. A single peak centered at $(1/2, 1/2, 0)$ has been observed for each scan. All of the data show that the magnetic-excitation peaks are always located around the position

ORNL-DWG 84-16928

Fig. 5.23. Experimental data for $\text{Cu}_{78.7}\text{Mn}_{21.3}$ at 20 K. Solid lines show the calculated line profiles by using the fitting parameters given in Table 5.5. Broken lines indicate the background counts estimated from the line shape fitting calculation. Open circles show the magnetic contribution to the elastic diffuse scattering.

where the MSRO peaks are observed at low temperatures, which indicate that a strong spatial correlation exists over the temperature range of the measurements.

We attempted to fit the line shapes of the inelastic-scattering peaks with a superposition of three Lorentzian-type scattering cross sections; i.e.,

$$\frac{d^2\sigma}{d\Omega d\omega} = \frac{h\omega}{e^8 h\omega - 1} \frac{k'}{k} f^2 \sum_{i=1}^3 \frac{A_i}{(q - Q_i)^2 + \kappa_i^2} \frac{\Gamma_i}{(h\omega)^2 + \Gamma_i^2},$$

ORNL-DWG 84-16929

Fig. 5.24. Experimental data at 150 K and the best fitting curves.

where $Q_1 = (1 \ 1/2 \ 0)$, $Q_2 = (1 \ 1/2 \ 0)$, and $Q_3 = (1 \ 1/2 \ 0)$, κ_i is the Ornstein Zernike type inverse correlation length, and $\kappa_1 = \kappa_3$ is assumed. A_i is proportional to the volume fraction associated with each peak. For simplicity the inverse relaxation time Γ_i is assumed to be the same for all three Lorentzians. The solid lines in Figs. 5.23 and 5.24 show the calculated best-fitting curves including the experimental resolution and using the parameters indicated in Table 5.5. There are two points to be noticed as characteristic features of these spin glasses. (1) The inverse correlation length κ_i is almost independent of temperature. This leads us to a model in which the spins always behave as clusters and the size of the fluctuating clusters does not

Table 5.5. Lorentzian fitting parameters for $\text{Cu}_{78.7}\text{Mn}_{21.3}$.

	δ ($\text{\AA}^{-1}$)	A_2/A_1	A_3/A_1	$\kappa_1 = \kappa_3$ ($\text{\AA}^{-1}$)	κ_2 ($\text{\AA}^{-1}$)	Γ (meV)	N^a $\times 10^{-3}$
20 K		9 ± 2		0.12 ± 0.02		3.5 ± 0.7	1.10
150 K	0.35 (fixed)	13 ± 1	1.30 (fixed)	0.11 ± 0.01	0.38 ± 0.04	3.5 ± 0.5	0.90
290 K		11 ± 1		0.12 ± 0.01			

^aNormalization constant between the calculated intensities and the observed values.

depend much on temperature. (2) The frequency dependence of the inelastic peaks can be well described by a constant value of Γ rather than $\Gamma = \gamma q^2$ as given by the spin diffusion model. Calculations based on the spin diffusion model have also been performed but could not reproduce well the experimental line shape. This suggests the absence of a kinematical slowing down in the spin-glass system.

Murani et al.¹ have regarded the time correlation of spins as the essential ingredient of spin-glass systems. Cable et al.² have pointed out the significance of the MSRO. Present results indicate the importance of space and time correlations of the spins and provide us the following picture of the CuMn spin glasses. At T well above T_f ($T \sim 3 T_f$), since strong inelastic scattering is observed around the MSRO peak positions, a rather large portion of the spins already couple locally and build various sizes of spin clusters. The orientations of the spins of these clusters are rotating as a whole. In the case of CuMn, there are mainly two types of clusters, one with the modulated-spin structure and the other with the ferromagnetic structure associated with the ASRO. As the temperature is lowered toward T_f , the interactions among the clusters gradually evolve, and some portion of the clusters begins to freeze according to each local environmental condition. In the course of this process, the distribution of relaxation times becomes broader and broader, and the elastic component of diffuse scattering increases. Below T_f , the interacting clusters may be connected into a macroscopic size. However, since each cluster freezes with random orientation, elastic scattering of neutrons still shows broad diffuse peaks even though certain clusters may grow in size in the freezing process. Even at the lowest temperature, inelastic scattering is observed around the MSRO position, indicating the existence of fluctuating clusters or the persistence of nonpercolated clusters.

1. Research carried out at the Oak Ridge National Laboratory under the U.S.-Japan Cooperative Program on Neutron Scattering.

2. Summary of paper: Journal of Applied Physics (in press).

3. Osaka University, Osaka, Japan.

4. A. P. Murani, J. Magn. Magn. Mater. 22, 271 (1981).

5. J. W. Cable et al., Phys. Rev. B 29, 1268 (1984).

NUCLEAR SPIN ORDERING OBSERVED BY NEUTRON DIFFRACTION^{1,2}

S. Kawarazaki³ N. Kunitomi⁴
H. Suzuki⁵ T. Ohtsuka⁶
Y. Morii⁷ R. M. Morii
R. M. Nicklow

Neutron scattering experiments have been carried out in the milli-Kelvin temperature range to study nuclear-spin ordering in the singlet-ground-state compounds PrSn_3 , PrCu_2 , and HoVO_4 . The magnetic behavior of systems with singlet electronic ground states has been of interest for many years, and neutron scattering studies have provided considerable information about the static and dynamic properties of these systems. It is now well established, theoretically and experimentally, that no magnetic ordering of the electronic system alone occurs spontaneously above 0 K unless the magnitude of the exchange interaction exceeds a certain threshold value. Specifically, if the magnitude of the parameter $\eta = 4K_0\alpha^2/\Delta$ exceeds unity (where $2K_0$ is the ion-ion exchange interaction, Δ is the energy separation between the ground state $|G\rangle$ and the first excited state $|E\rangle$, and $\alpha = \langle E|J_z|G\rangle$), the electronic system undergoes a self-induced spontaneous polarization at a finite temperature, and if $|\eta| < 1$, it does not.

When $|\eta| < 1$, the role of the nuclear spins is very important. Although the direct magnetic interaction between nuclei is extremely small, leading to cooperative nuclear-spin ordering only in the relatively inaccessible micro-Kelvin temperature range, in these singlet-ground-state systems an indirect coupling between nuclei via the hyperfine and exchange (or dipole) interaction is relatively large and leads to a rich assortment of nuclear and electronic magnetic phenomena in the much higher 1-100 milli-Kelvin temperature range. That is, under certain conditions even though the nuclear and electronic

systems individually show no magnetic phase transition, the coupled system does.

The measurements were carried out on a neutron spectrometer located at the High Flux Isotope Reactor. The samples were cooled to the milli-Kelvin temperature range with a ^3He - ^4He dilution refrigerator manufactured by Oxford Instruments, Ltd. The PrCu_2 and PrSn_3 samples were thermally anchored to the refrigerator mixing chamber and they reached a minimum temperature of 10 mK. For these samples the temperature was measured with carbon or germanium resistance thermometers, which were soldered on the sample and which we had previously calibrated by using a ^{60}Co nuclear orientation thermometer. The HoVO_4 sample was attached to the mixing chamber by a bundle of 300 thin copper wires. This attachment allowed simultaneous measurement of the neutron diffraction and the rf magnetic susceptibility which was used to determine the sample temperature. The HoVO_4 crystal was first cooled in zero magnetic field to below 30 mK, then a field of 3T was applied, and the crystal was self-cooled by adiabatic demagnetization to 2.7 mK.

It is convenient to categorize the magnetic ordering of coupled nuclear-electronic spin systems into three regimes depending on the magnitude of n : pure nuclear, mixed electronic-nuclear, and pure electronic. The materials we have studied exhibit properties which are representative of these regimes.

(1) Nuclear regime: HoVO_4 . In the nuclear regime, $n \ll 1$, and therefore the electronic system is very far from possessing the properties required for the development of a spontaneous self-induced electronic moment. However, the hyperfine interaction admixes some electronic moment into the $2I \pm 1$ nuclear substates of the singlet electronic ground state. Although the induced moment might be small, it is much larger than the "bare" nuclear moment. The induced moment is usually referred to as the "enhanced" nuclear moment. Then exchange or dipole interactions between the induced moments on different atoms can lead to a spontaneous polarization of the nuclear spin states below a transition temperature which is typically in the range 1–10 milli-Kelvin. Of course, the induced electronic moments order also, but the most important feature is the total polarization of the nuclear spin system.

HoVO_4 is an example of such a system which has been studied previously in some detail. Magnetic susceptibility measurements⁸ revealed that HoVO_4 developed antiferromagnetic order at about 4.5 mK and that a spin-flop transition took place in an applied field of about 60 Oe.

Below the Néel temperature we observed diffraction peaks due to an antiferromagnetic spin structure that was predicted by Bleaney.⁹ The measured temperature dependence of the intensity of the (100) antiferromagnetic peak, shown in Fig. 5.25, as well as the observation of rather large intensity at the (009) and (11,0,0) reflections, where the electronic form factor is small, indicates that we have observed the scattering due to the nuclear magnetic order.

In order to observe the spin-flop transition, the magnetic field effects on the neutron diffraction spectra intensities were measured. In

Fig. 5.25. Temperature dependence of the peak intensity of the (100) diffraction peak from HoVO_4 measured from the background. The insert shows the square root of the peak intensity.

Fig. 5.26, the peak intensities of both the (100) and (001) reflections are shown as a function of magnetic field, which was applied in the (010) direction. The intensity of the (100) peak decreases rapidly at about 80 Oe as expected for this spin-flop transition.

(2) Mixed regime. PrCu_2 . In the mixed regime $n < 1$, and the exchange interaction is just below the threshold necessary for the formation of an electronic self-induced spin polarization. In this case both the nuclear and electronic systems, coupled via the hyperfine interaction, can develop large spontaneous spin polarization at the same temperature. The order parameter of

Fig. 5.26. Magnetic field dependence of the peak intensities of the (100) diffraction peak (closed circles) and the (001) diffraction peak (open circles) from HoVO_4 . The magnetic field was applied along the (010) direction. The temperature during the measurement was approximately 3.5 ± 0.2 mK.

the transition presumably contains both of the polarizations, and neutron scattering is the only experimental technique that can determine how each polarization develops as a function of temperature.

PrCu_2 is believed to be a system with this type of mixed phase transition. At present only preliminary neutron scattering results are available because the individual electronic and nuclear spin polarizations have not yet been measured. However, our results show that a magnetic phase transition occurs in PrCu_2 at 58 mK. The temperature dependence of one of the observed magnetic diffraction peaks is shown in Fig. 5.27. At this stage of our study the most interesting result obtained is that the positions in reciprocal space of the diffraction peaks indicate that the magnetic structure (electronic + nuclear) is incommensurate with the chemical lattice. The wave vector of the magnetic structure is given by $\tau = 0.24 \text{ a}^* \pm 0.68 \text{ c}^*$.

Fig. 5.27. Temperature dependence of the peak intensity of the (0.24, 0, 0.68) diffraction peak from PrCu_2 . The open circles and solid circles are the data measured when the sample was cooling and heating, respectively. The insert shows the square root of the peak intensity measured from the background.

(3) Electronic regime: PrSn_3 . In the electronic regime $n > 1$, and the magnetism is dominated by the behavior of the electronic system, which undergoes a self-induced spontaneous spin polarization below a relatively high temperature. Work on PrSn_3 was reported previously.¹⁰

1. Research carried out at the Oak Ridge National Laboratory under the U.S.-Japan Cooperative Program on Neutron Scattering.

2. Summary of papers: S. Kawarazaki et al., *Solid State Commun.* 49, 1147 (1984); S. Kawarazaki et al., *Solid State Commun.* 49, 1153 (1984); H. Suzuki et al., *Solid State Commun.* 49, 1157 (1984).

3. Guest scientists: from Osaka University, Osaka, Japan.

4. Osaka University, Osaka, Japan.

5. Guest scientist from Tohoku University, Sendai, Japan.

6. Tohoku University, Sendai, Japan.

7. Guest scientist from the Japan Atomic Energy Research Institute, Tokai-mura, Japan.

8. H. Suzuki et al., *J. Phys. (Paris)* C6, 801 (1978).

9. B. Bleaney, *Proc. R. Soc. London* A370, 313 (1980).

10. S. Kawarazaki et al., *Solid State Div. Prog. Rep.*, March 31, 1983, ORNL-5975, p. 192.

MAGNETIC BEHAVIOR OF VBr_2 AT VERY LOW TEMPERATURES¹

J. R. Arthur S. Kawarazaki²
K. Hirakawa³

Vanadium dibromide, along with VCl_2 and VI_2 , has a hexagonal crystal structure (CdI_2 structure) in which the magnetic coupling of vanadium ions within the c planes is much stronger than the interplane coupling. These systems are of interest as possible examples of highly frustrated two-dimensional triangular lattice antiferromagnets. This interest is encouraged by high-temperature magnetic susceptibility measurements, which yield Weiss constants of several hundred degrees Kelvin. In fact, magnetic transitions do not occur in these substances until temperatures of less than 50 K are reached, indicating that the antiferromagnetic interactions are frustrated. A neutron scattering experiment using VBr_2 powder⁴ has shown the onset of magnetic order at 29 K, though no sharp anomaly in the magnetic susceptibility has been observed at this temperature. The magnetic structure of the ordered state has not been determined precisely, but the symmetry is antiferromagnetic both within the c planes and between the layers.^{4,5} Several structures have been proposed, some of which involve partial ordering, or ordering that is somewhat fluid on time scales that are long compared with the passage time of a diffracting neutron.⁶

A search for possible new transitions at very low temperatures was conducted with a VBr_2 single-crystal sample mounted in the dilution refrigerator neutron diffraction facility at HFIK. The crystal was not of very good quality, but three distinct magnetic reflections were observed at 4.2 K and below. Figure 5.28 shows the intensities of these reflections as a function of temperature. For each reflection, the intensity decreases smoothly as the temperature is lowered below about 0.6 K. This intensity decrease is much more gradual than would be expected if the magnetic structure were undergoing a phase transition to a structure of different symmetry. It is more likely caused by spin-dependent nuclear scattering, as the vanadium nuclei become polarized in the internal magnetic field of the sample. Such nuclear polarization can be enhanced by the effective field due to hyperfine interactions between the nuclei and electrons and can be significant at these temperatures.⁷

Because little is known about the hyperfine fields in VBr_2 , the observed behavior cannot be

Fig. 5.20. Temperature dependence of intensities of antiferromagnetic reflections in VBr₂.

explained positively as a nuclear polarization effect. In the near future, further experiments are planned, using a larger crystal of better quality, so that many more magnetic reflections can be observed. This will help to distinguish nuclear from electronic polarization effects, since the nuclear and electronic form factors are quite different. The fact that the temperature dependences (fraction of intensity lost vs T) of the reflections that have been observed are not identical is indicative of competing nuclear and electronic scattering effects, but more data are needed. A similar experiment is also planned using a crystal of VCl₂.

Though this study is not complete, some general conclusions can be made. Most significant is that no transition to a new magnetic ordering has been observed at temperatures down to 30 mK. It is surprising that the unusual, possibly semi-fluid state observed below 29 K persists to such low temperatures. A better characterization of this state is clearly needed. The nuclear ordering effect that has been observed could help to sort out the nature of the electronic state by providing information about the hyperfine field at the vanadium nuclei.

1. Research carried out at the Oak Ridge National Laboratory under the U.S.-Japan Cooperative Program on Neutron Scattering.

2. Guest scientist from Osaka University, Osaka, Japan.
3. University of Tokyo, Tokyo, Japan.
4. K. Hirakawa, H. Kadowaki, and K. Ubukoshi, *J. Phys. Soc. Japan* 52, 1814 (1983).
5. M. Nishi et al., *J. Phys. Soc. Japan* 53, 1214 (1984).
6. Though VBr₂ is a spin 3/2 system, it exhibits some similarities to the spin 1/2 system discussed by P. W. Anderson, *Mater. Res. Bull.* 8, 153 (1973).
7. S. Kawarazaki et al., *Solid State Commun.* 49, 1147 (1984).

OBSERVATION OF A DISORDERED SPIN-FLOP PHASE IN Fe_{0.725}Co_{0.275}Cl₂¹

Po-zen Wong² J. W. Cable

Multicritical phenomena in uniaxial antiferromagnets have been the subject of wide interest during the last decade. Experimental studies of their phase diagrams in longitudinal magnetic fields, in particular, have produced beautiful results, which confirmed many novel theoretical predictions obtained by renormalization group calculations. Generally speaking, in weak-anisotropy systems, one finds bicritical-point phase diagrams with spin-flop (SF) transitions (in which the ordering direction of the spins changes from parallel to perpendicular to the easy axis) at high fields. In strong-anisotropy systems, however, one finds tricritical-point phase diagrams with spin-flip transitions (in which the spins on the two sublattices flip from antiparallel to parallel) at high fields. In more recent years, there has been considerable effort to extend these studies to random antiferromagnets. Although the phase diagram obtained in these studies appears to be of the same kind as the pure system, there are drastic differences in details which are not understood. The difficulties are most likely to be related to random field effects.

It is by now well recognized that the longitudinal applied field generates site-random staggered fields in these systems, and their effects are not well understood. In particular, there is a controversy on whether a true long-range-ordered (LRO) phase can exist in these systems in low fields. Without that knowledge, it is very difficult to make precise interpretations on the very delicate phase diagram and multicritical behavior.

To understand these problems better, it is essential to study carefully the nature of the ordered states in both high and low fields by neutron scattering. Although much work has been done in recent years to study the low-field phase, because of its correspondence to the random-field Ising model, there has been little effort to study the ordering in the high-field phases. Here we report a neutron scattering study of the high-field phase in the random antiferromagnetic system Fe_{0.725}Co_{0.275}Cl₂.

Our motivation for studying Fe_{1-x}Co_xCl₂ is twofold. First, pure FeCl₂ is one of the best studied tricritical systems. Random substitution of Fe ions by Co ions is known to decrease

the average anisotropy of the system. Galam and Aharony⁴ have shown by both mean-field and renormalization-group calculations that the reduction of anisotropy has the same general effects in random systems as it has in pure systems (i.e., SF phase should appear at low temperature and high field, and the phase diagram should become bicritical). A neutron scattering experiment which probes directly the spin orientation will provide the first test of the Galam-Aharony idea. Second, in the earlier study of $\text{Fe}_{1-x}\text{Co}_x\text{Cl}_2$ in zero field by Wong and co-workers,³ it was argued that there should be random off-diagonal exchange interactions between the different spin-components due to the lack of local symmetry. With such interactions, a magnetization in the c direction will produce random molecular fields in the ab plane. Since the spin component in the plane ($S_{\parallel}$) has negligible anisotropy if a SF phase occurs, it should be described by the 3-D XY model in random fields, which is generally believed to be disordered at all temperatures but has never been observed in magnetic systems.

In zero field, the spin components parallel to the c axis ($S_{\parallel}$) in this sample are known to order antiferromagnetically with 3-D Ising characteristics.³ In finite fields, it corresponds to the random-field Ising model.⁵ In our previous study,⁵ we found that for $H < 4$ kOe, the ordered state was unchanged (within our instrumental resolution) regardless of how the sample was cooled. Above 4 kOe, however, the system is disordered when cooled in a field but ordered when the field is applied after cooling in zero field. Time dependence tests suggest that the zero-field-cooled state is the equilibrium state. We shall refer to this phase as the antiferromagnetic phase. In Fig. 5.29, we show the T-H phase diagram that extends to higher fields. We find that there is a region at low temperature and high field in which $S_{\parallel}$ develops large local staggered

magnetization, but without LRO. In other words, there is a disordered SF phase.

Evidence for this disorder is illustrated in Fig. 5.30, which shows a typical scan at (1,0,1) transverse to the reciprocal lattice vector. At this reflection in zero field, we have determined that a resolution-limited Bragg peak can be fitted by a Gaussian plus a Lorentzian (G+L) with a Gaussian width $\Gamma_G = 0.0045(1) \text{ \AA}^{-1}$ (HWHM). The central part of such a peak is depicted by the dashed line in Fig. 5.30. The measured peak is clearly not resolution limited. If the scan in Fig. 5.30 is fitted to the same G+L form, we find $\Gamma_G = 0.0055 \text{ \AA}^{-1}$, 20% wider than the resolution limit.

Fig. 5.30. A transverse scan of the (1,0,1) peak in the SF phase. The dashed curve corresponds to the instrumental resolution.

Fig. 5.29. Temperature-applied field phase diagram of $\text{Fe}_{0.725}\text{Co}_{0.275}\text{Cl}_2$ for fields parallel to the c axis.

These results are consistent with the theoretical expectation that a SF phase should occur with the reduction of anisotropy. The quantitative predictions by Galam and Aharony⁴ clearly cannot apply since the SF phase is disordered. The most likely explanation for this unusual SF phase is perhaps the one given above in terms of the random off-diagonal exchange and the random-field XY model.

Finally, we note that in the SF phase of two other weak anisotropy systems, $\text{Gd}_{1-x}\text{La}_x\text{AlO}_3$ and $\text{Mn}_{1-x}\text{Zn}_x\text{F}_2$, there was no indication of disorder. The reasons, we believe, are (1) in $\text{Gd}_{1-x}\text{La}_x\text{AlO}_3$, the S^2 phase has uniaxial anisotropy; and (2) both Gd^{3+} and Mn^{2+} are S-state ions, the off-diagonal terms coming mainly from dipolar interactions, which are very small. In a competing-anisotropy system such as $\text{Fe}_{1-x}\text{Co}_x\text{Cl}_2$, the off-diagonal terms can be larger because of orbital contributions, and the effects are more noticeable.

1. Summary of paper: *Phys. Rev. B: Rapid Commun.* 30, 485 (1984).

2. Schlumberger-Doll Research, Ridgefield, Conn.

3. P. Wong et al., *Phys. Rev. B* 27, 428 (1983).
4. S. Galam and A. Aharony, *J. Phys. C* 13, 1065 (1980).
5. P. Wong and J. W. Cable, *Solid State Commun.* 51, 545 (1984).

NEUTRON DIFFRACTION STUDIES OF SOME Gd-Y ALLOYS

W. C. Koehler S. Legvold¹
B. J. Beaudry¹

It has long been known that the addition of Y to the heavy rare-earth metals Gd, Tb, and Dy tends to stabilize the helical configuration relative to the ferromagnetic one.² In pure Gd, the initial ordering (decreasing temperatures) is to a c-axis ferromagnet ($T_C=293$ K). At about $T_F = 235$ K (T_F = spin reorientation temperature) the easy axis moves away from the c axis and lies on a cone of semiapex angle θ which varies somewhat with temperature.³ Early magnetization measurements⁴ showed that Gd-Y alloys with more than about 40% Y exhibited an upper ordering transition to a helical state, while those with less than about 32% Y were ferromagnetic, and early powder diffraction data demonstrated that the interlayer turn angle in the helical structure attained relatively small values.⁵ With sufficiently high concentrations of Y, the alloy retains a helical structure to the very lowest temperatures.

Interest in the system has recently been reawakened by some precise measurements of magnetization⁶ and resistivity⁶ on single-crystal specimens of compositions in the critical range near 32% Y. The very interesting and complex effects found have led Legvold et al.⁷ to postulate "double" ferromagnetism in $Gd_{70}Y_{30}$ single crystals and Legvold et al.⁸ to search for Lifshitz points (at special compositions) in various rare-earth alloys.

The present series of measurements were undertaken on crystals containing 30, 32, and 32.3% Y in Gd in an attempt to explore, by neutron scattering methods, the two phenomena just mentioned. The specimens, pillars of dimension $2 \times 2 \times 10$ mm³, were cut from crystalline buttons grown by the strain-anneal method, and they are the same ones studied in the magnetization experiments. The long dimension was parallel to a crystallographic a axis. Rocking curves around the (002) position and 10z scans around the (100) position were made on the HB-3 spectrometer at the High Flux Isotope Reactor at temperatures ranging from room temperature to 10 K. To reduce the effect of absorption in the Gd, the measurements were made at a neutron wavelength of 0.467 Å; and to maximize the intensity on the sample, the usual presample collimation was removed, as was the sapphire filter. Scans typically made at 10 or 20 s/point gave reasonable statistical accuracy, but the resolution was relatively poor. We plan to repeat some of the measurements with tighter collimation.

The $Gd_{70}Y_{30}$ crystals, according to the magnetization measurements, are ferromagnetic with two Curie points. The upper one, at 218.8 K, was supposed by Legvold to correspond to ordering of

the c-axis component with random planar components, and the lower temperature, 205.5 K, to ordering of the planar components to produce simple ferromagnetism.

Neutron diffraction data taken in this temperature range are shown in Fig. 5.31. They imply that the lower temperature is a reorientation temperature at which moments initially parallel to the c axis turn abruptly into or nearly into the basal plane.

For the compositions $Gd_{68}Y_{32}$ and $Gd_{67.7}Y_{32.3}$, there is a wide range in temperature over which the helical configuration is stable. This is illustrated in Fig. 5.32, where the interlayer turn angles measured from the positions of the magnetic satellite reflections are plotted. Data for $Gd_{68}Y_{32}$ are less complete because the crystal studied exhibited a double peaked structure. In each case, however, the minimum turn angle is relatively small, but the point at which θ tends to zero is at a boundary between the helical and ferromagnetic configurations. The initial value of the turn angle is relatively large. It thus appears that the prediction of the existence of a Lifshitz point in the composition near to $Gd_{67.7}Y_{32.3}$ has not been substantiated.

Fig. 5.31. Integrated intensity of (100) and (002) reflections for $Gd_{70}Y_{30}$ single crystals. At $T_C = 218$ K there is a magnetic contribution to the (100) reflection and no corresponding contribution to the (002), implying a c-axis moment. At $T_C' = 205.5$ K a strong basal plane contribution puts intensity in the (002), and there is a sharp drop, at first, in the contribution to the (100).

Fig. 5.32. Turn angle as a function of temperature for two crystals $\text{Gd}_{68}\text{Y}_{32}$ and $\text{Gd}_{67.7}\text{Y}_{32.3}$. The transition temperatures are obtained from the neutron diffraction data.

During the course of these experiments we have learned of rather more extensive measurements under way at the Institut Laue-Langevin, Grenoble, by Palmer et al. Where our experiments overlap theirs, they are, in general, in agreement.

1. Ames Laboratory and Iowa State University, Ames, Ia.

2. See for example, W. C. Koehler, p. 81 in *Magnetic Properties of Rare-Earth Metals*, ed. by R. J. Elliott, Plenum Press, New York, 1972.

3. J. W. Cable and W. C. Koehler, *J. Appl. Phys.* 53, 1904 (1982).

4. W. C. Thoburn, S. Legvold, and F. H. Spedding, *Phys. Rev.* 110, 1298 (1958).

5. H. R. Child and J. W. Cable, *J. Appl. Phys.* 40, 1003 (1969).

6. Much of this work is still in progress by Legvold and Beaudry and by Sousa et al. and will be published in due course.

7. S. Legvold, T. Ito, and B. J. Beaudry, *Phys. Rev. Lett.* 45, 1275 (1980); T. Ito, S. Legvold, and B. J. Beaudry, *Phys. Rev. B* 23, 3409, (1981).

8. S. Legvold, P. Burgart, and B. J. Beaudry, *Phys. Rev. B* 22, 2573 (1980).

THE MAGNETIC STRUCTURE OF NICKEL DIGLYCINE DIHYDRATE¹

O. A. Pringle¹ R. Calvo²
R. E. Parra²

Nickel diglycine dihydrate (NiDD) [$\text{Ni}(\text{CH}_2\text{CO}_2\text{NH}_2)_2 \cdot 2\text{H}_2\text{O}$] is a metal derivative of the amino acid glycine. NiDD is interesting in that it is a possible metamagnet with a large single-ion anisotropy compared with the magnetic interaction between nickel ions. The compound is also a good model system for metal ions in proteins, and from it one may learn something about electronic paths for superexchange in these macromolecules.

Magnetic susceptibility³ and specific heat⁴ measurements have previously been reported for NiDD . These measurements were used to construct a model for describing the magnetic properties of NiDD .³ The Ni^{2+} ions have an effective spin S , with $S = 1$. The single-ion Hamiltonian in a low-symmetry environment and with an applied magnetic field H can be written

$$H = D[S_z^2 - S(S+1)/3] + E(S_x^2 - S_y^2) + g\mu_B H \cdot S, \quad (1)$$

where D and E give the magnitude of the interaction of the Ni^{2+} ions with the crystal field; g is the gyromagnetic factor, which is assumed to be isotropic; and μ_B is the Bohr magneton.

From the specific heat data, the values $D = -14.5$ K, $|E| = 1.13$ K, and the phase transition temperature $T_N = 0.88$ K were determined.⁴ The specific heat data did not allow determination of the anisotropy axes to which the Hamiltonian of Eq. (1) is referred. The magnetic susceptibility data for NiDD were compared with a simple two-sublattice molecular field model, but the predictions of this model did not give satisfactory agreement with the data.³ The poor agreement was attributed to the fact that the model did not consider the different orientations of the anisotropy axes for the two Ni^{2+} ions in the crystalline unit cell.

In order to understand the magnetic properties of NiDD , we made neutron diffraction measurements on single-crystal samples. NiDD crystallizes in the monoclinic $P2_1/c$ space group, with two NiDD molecules per unit cell.⁵⁻⁷ The two Ni^{2+} ions are located at the $(0,0,0)$ and $(0,1/2,1/2)$ positions in the unit cell. We call these two positions the A and B sites, respectively. The NiDD molecule at the B site is obtained from the NiDD molecule at the A site by a rotation of 180° around the b axis. Thus, if μ_A and μ_B are the atomic magnetic spin vectors at A and B, we expect μ_B to be either a rotation by 180° of μ_A around the b axis or a rotation of 180° followed by an inversion. The latter case is called an antirotaion. We also note that in this structure the Ni^{2+} ions can be viewed as arranged in layers parallel to the bc plane.

We carried out our neutron diffraction measurements using a ^3He refrigerator with a low-temperature capability of about 0.4 K. For temperatures below 0.88 K we observed a number of magnetic reflections which obeyed the selection

rule $hkl: h = 2n + 1$, where the index h corresponds to a unit cell doubled along the a axis. The existence of magnetic reflections with k or l even ruled out a doubling of the unit cell along the b or c axes, while all observed extinctions were consistent with a unit cell doubled along a . We concluded that the NiDD magnetic unit cell is obtained from the crystallographic unit cell doubled along the a axis only.

We calculated μ_A and μ_B from the intensities of the magnetic reflections. We used a coordinate system xyz , where $\hat{x} = \hat{b} \times \hat{c}$, $\hat{y} = \hat{b}$, and $\hat{z} = \hat{c}$. In this coordinate system the Ni^{2+} ions are arranged in layers parallel to the yz plane, and the x axis is normal to the layers. We obtained $\mu_A = -0.80 \hat{x} + 0.32 \hat{y} + 0.51 \hat{z}$ and $\mu_B = -0.80 \hat{x} - 0.32 \hat{y} + 0.51 \hat{z}$, with the moment magnitude $\mu = (2.33 \pm 0.14) \mu_B$. These results were obtained with the antirotation model. No fit using the rotation model was capable of giving a reasonable set of calculated magnetic structure factors. Figure 5.33 shows a molecule of NiDD, with the arrows indicating the moment directions. We show the two possible moment directions referred to a single NiDD molecule because we have no way to identify each of the two molecules in the crystallographic unit cell with each of the two moment directions obtained here.

Fig. 5.33. A molecule of nickel diglycine dihydrate. Arrows represent the Ni^{2+} moment directions as determined by neutron diffraction.

Our neutron diffraction measurements show that the NiDD-ordered phase consists of Ni^{2+} layers coupled antiferromagnetically, with a canted ferromagnetic ordering within layers. The layers lie in planes parallel to the bc plane. The directions of the Ni^{2+} moments in the ordered phase correspond neither to the molecular nor to the crystalline axes of NiDD. The values $D = -14.5$ K and $E = 1.13$ K obtained from the specific heat data indicate a well-defined axial direction for the anisotropy energy, so that the moment direction in the ordered phase must be the result of the interplay between the large anisotropy energy

(given by D and E) and the exchange interactions between the canted spins. This interplay also determines the magnitude of the magnetic moment in the ordered phase. The value $\mu = (2.33 \pm 0.14) \mu_B$ obtained here for the magnetic moment should be compared with the value $\mu_{eff} = 3.19 \mu_B$ obtained from the magnetic susceptibility data in the paramagnetic phase,³ which represents the free ion value. The observed reduction of μ is consistent with large departures of the spin directions from those deduced from the single-ion anisotropy energy. An analysis of the magnetic properties of NiDD using a four sublattice molecular field model is now being carried out in order to evaluate the exchange interactions in NiDD and to calculate the temperature dependence of the magnetic order parameter and the magnetic susceptibility.

1. Summary of paper: Physical Review B (in press).
2. Instituto Venezolano de Investigaciones Científicas, Caracas, Venezuela.
3. R. Calvo et al., J. Appl. Phys. 53, 2674 (1982).
4. R. Calvo et al., J. Appl. Phys. 53, 2671 (1982).
5. A. J. Stosick, J. Am. Chem. Soc. 67, 365 (1945).
6. H. C. Freeman and J. M. Guss, Acta Crystallogr. Sect. B 24, 1133 (1968).
7. E. E. Castellano, O. R. Nascimento, and R. Calvo, Acta Crystallogr. Sect. B 38, 1303 (1982).

ON THE SPIN AND ORBITAL MAGNETIC DENSITIES IN FERROMAGNETIC NICKEL¹

G. P. Felcher² G. Maglic²
J. W. Cable J. F. Cooke

The technique of polarized neutron diffraction has been used for many years to determine with high accuracy the distribution of magnetism in crystalline ferromagnetic metals, offering a benchmark against which to test the validity of band calculations. The earliest experiments were done on the elemental ferromagnets of the 3-d series; for these, the experimental form factors were found to be in good agreement with those calculated (by the Hartree-Fock method) for the single atoms in some ionized state. However, later experiments on enhanced paramagnets showed a decisive difference with the atomic models, a difference that was explained by accurate band calculations. In the present paper we present new detailed information on the magnetic distribution of ferromagnetic nickel and show that even for this ferromagnetic metal, the atomic model breaks down.

In the framework first proposed by Freeman and Watson³ and then followed by Mook⁴ for analyzing his data on nickel, the magnetic form factor at the scattering vector k is given by

$$f(k) = (2/g) f_{\text{spin}}(k) + [(g-2)/g] f_{\text{orbit}}(k), \quad (1)$$

where g is the spectroscopic splitting factor. Suppose that g is isotropic as in a cubic system

$$f_{\text{spin}} = \langle j_0 \rangle + \left(\frac{3}{2} e_g - t_2 g \right) A_{hk1} \langle j_4 \rangle, \quad (2)$$

where the $\langle j_n \rangle$ are Bessel transforms of the radial spin density, the e_g and $t_2 g$ are occupation numbers of the orbitals with the respective symmetry, and A_{hk1} is the effect of asphericity of the magnetic cloud on the form factor of a Bragg reflection. In Mook's analysis of the nickel data, the orbital part of the form factor was taken as the spherical component. Intuitively, aspherical terms are expected, since the orbital form factor depends not only on the direction of scattering but also on the direction of magnetization around which the electron currents rotate with an aspherical path. By measuring the form factor of the same reflection for different orientations of the magnetization, it should be possible to separate experimentally the spin and orbital contributions of the form factor. Since in the atomic formulation the orbital contribution can be readily calculated, an experimental test can check the validity of the atom-like calculations.

Calculations of the free atom orbital form factor for Ni^{+2} show that when the magnetic field is rotated in the $hk0$ plane, the form factor varies proportionally to the function $\sin^2 \phi$, where ϕ is the angle with the 001 reflection. For reflections of lower symmetry, the dependence of magnetic amplitude p on the direction of the applied field becomes more complicated, but it is always possible to define a pair of directions, H_M and H_m , in which, respectively, p is maximum and minimum. Results indicate that the aspherical orbital effects are indeed quite small; however, with a determined experimental effort they are observable, and the most promising reflection is the (440).

The polarized neutron measurements on the (440) reflections were made at the CP-5 reactor at Argonne National Laboratory. The sample was kept at room temperature, in an applied magnetic field of 8 kOe, amply sufficient to saturate the sample. The magnetic field was applied in several directions in the (110) zone. The results are presented in Fig. 5.34. The magnetic response seems quite independent of the direction of the magnetic field, except for a sharp spike at $\phi = 0, 180$ due to simultaneous reflection.

Experimental results indicate that the magnetic amplitude of the (440) reflection changes less than ~1% with the direction of the magnetic field, while calculations based on the atomic model predict a 3% variation. It has to be concluded that even for nickel, the atomic model, brought to its extreme consequences, breaks down.

In the atomic model the orbital density is mathematically determined once the spin density and the gyromagnetic ratio are given. This constraint does not exist in form factor calculations based on the itinerant electron theory. Recently, calculations of the total (spin + orbit) ferromagnetic form factor for nickel and iron⁵ have been carried out based on itinerant electron theory. A study of the variation of the form factor as a function of spherical coordi-

Fig. 5.34. Magnetic amplitude of the (440) reflection of nickel at room temperature. A magnetic field of 8 kOe is applied in a direction of the [110] zone, at a ϕ angle with the (001) direction. Dotted line: expected result of the atom-like calculation (with an average value p given by Mook). Solid line: average of the present results.

nates (θ, ϕ) which fixes the magnetic moment direction with respect to the crystal axes was carried out for nickel. Changes of only a percent or less were detected over the range of possible (θ, ϕ) . Since this is within the error limits of the calculation, these results indicate that the (θ, ϕ) dependence is small to negligible. Therefore, the itinerant-electron calculation is consistent with the experimental results and confirms that the orbital density is much more spherical than predicted by atomic calculations.

1. Summary of paper: *Physical Review B* (in press).
2. Argonne National Laboratory, Argonne, Ill.
3. A. J. Freeman and R. E. Watson, *Acta Crystallogr.* 14, 231 (1961).
4. H. A. Mook, *Phys. Rev.* 148, 425 (1966).
5. J. F. Cooke and J. A. Blackman (to be published); *Bull. Am. Phys. Soc.* 28, 248 (1983).

STRUCTURE AND INSTRUMENTATION

HIGH-PRESSURE CELLS FOR NEUTRON SCATTERING¹

A. Onodera² H. G. Smith³
O. A. Pringle

Two high-pressure cells for neutron scattering have been developed, which are modeled after high-pressure cells developed by McWhan et al.⁴ and

by Bloch et al.⁵ They have been designed in particular to be useful for studies of magnetic structures and phonon dispersion relations at pressures greater than 20 kbar.

Figure 5.35 shows a cross section of the McWhan-type cell. We will concentrate on the McWhan-type cell in this report because it provides a continuous window for the neutron beam. The sample to be studied is placed inside an aluminum capsule along with a pressure-transmitting fluid such as Fluorinert. The capsule is held in the center of a barrel-shaped cylinder of hot-pressed Al_2O_3 . The Al_2O_3 cylinder is supported by two opposing wedge rings and is prestressed by pressure applied to the upper support ring and locked by the clamping ring. Pressure is applied to the sample via the upper piston and upper pressure pad and locked by the clamping bolt. The clamped cell can be mounted on a neutron spectrometer and can be cooled to liquid helium temperatures.

Fig. 5.35. High-pressure cell for neutron scattering (McWhan-type).

The Al_2O_3 cylinder has an inner diameter of 8 mm for the sample cavity. A hole in the lower piston allows removal of electrical leads so that pressure generated inside the cylinder can be monitored by measuring the change of electrical resistance of manganin wire. Alternatively, the pressure on the sample can be estimated from a previously determined calibration of the generated pressure as a function of the applied load.

Figure 5.36 shows an example of neutron diffraction data obtained with the McWhan-type cell. The sample was KCl, which undergoes a pressure-induced B1-B2 phase transformation around 20 kbar, as first observed by Bridgman.⁶ The (002) reflection from the B1 phase of KCl at several pressures is plotted in Fig. 5.36. The reflection disappeared at a pressure of 21 kbar on loading, indicating a transformation to the B2 phase. On

Fig. 5.36. KCl (002) Bragg reflection at several pressures (compression run). The reflection disappeared at a pressure of 21 kbar. On decompression the reflection reappeared, but with the intensity decreased by a factor of 20.

release of pressure the reflection reappeared at the same angle as observed before compression, but with the intensity, decreased by a factor of 20. Other preliminary neutron diffraction studies using the McWhan-type cell have included the effect of pressure on T_N in 2.77% γ Fe in Cu, in which the pressure cell was cooled to 9 K, and the effect of pressure on phonons in SnTe.

1. Research carried out at the Oak Ridge National Laboratory under the U.S.-Japan Cooperative Program on Neutron Scattering.
2. Guest scientist from Osaka University, Osaka, Japan.
3. On assignment with the Division of Materials Sciences, U.S. Department of Energy, Washington, D.C.
4. D. B. McWhan et al., *Phys. Rev. B* 20, 4612 (1979).
5. D. Bloch et al., *Rev. Sci. Instrum.* 47, 269 (1976).
6. P. W. Bridgman, *Proc. Am. Acad. Arts Sci.* 76, 1 (1945).

**WIDE-ANGLE NEUTRON DIFFRACTOMETER: A FLAT-
CONE DIFFRACTOMETER UTILIZING A CURVED ONE-
DIMENSIONAL POSITION-SENSITIVE DETECTOR WITH
TIME-RESOLVED DATA ACQUISITION SYSTEM¹**

M. Iizumi² R. M. Moon
S. Funahashi² R. M. Nicklow
S. Katano² H. R. Child
M. K. Kopp³

A new type of neutron diffractometer has been installed at the HFIR (Fig. 5.37). The instrument has several novel features: (1) it utilizes a newly developed position-sensitive detector of the curved one-dimensional type with wide-angle coverage, (2) the detector and single-crystal samples can be arranged in the so-called flat-cone diffraction geometry, (3) the curved detector is equipped with an oscillating radial collimator, and (4) the data acquisition system has capability of carrying out time-resolved measurements. Real-time diffraction measurements make it feasible to study structure changes of a system that is in a nonstationary state.

The detector is a curved one-dimensional position-sensitive proportional counter with an

effective radius of 75 cm, covering a 130° angular range. The position analysis is performed by a distributed LC delay-line cathode, which produces pulses at opposite ends of the line with shapes that depend on the position of the neutron capture event. The position is decoded as the time difference between the zero crossing for each differentiated pulse. Automatic time slicing for the time-resolved measurements can be done by adding a constant offset time to the digitized time difference for each successive slice.

One-dimensional position-sensitive detectors with a curved shape and with wide-angle coverage previously have been used mostly for powder measurements. The application of such detectors in single-crystal diffraction is certainly a promising field to be developed in the near future. The most favorable use of such a detector in single-crystal diffraction studies is to arrange it in such a way that the whole arc of the detector lies on a specific layer in reciprocal space of the single-crystal diffraction pattern. This arrangement is the so-called inclination geometry adopted in the Weissenberg camera often used in x-ray diffraction studies. The geometry

ORNL-Photo 7734-84

Fig. 5.37. Wide-angle neutron diffractometer installed at HB-4A in HFIR.

is realized in the curved detector cases by tilting it around the horizontal axis that intersects the incident beam perpendicularly at the sample position. This is the so-called flat-cone arrangement in which the incident beam is inclined at a certain angle to the rotation axis of a crystal sample, so that for each level the diffracted beam is normal to the axis and makes a "flat cone."

In the present instrument, the base plate, which holds the crystal goniometer and the shielding assembly containing an oscillating collimator and the detector, can be tilted as a whole by a motor drive around the horizontal axis defined above. An intrinsic disadvantage of the wide-angle detector is its weakness for background. Neutrons scattered by air on the beam line and by the wall of furnaces or cryostats can easily reach the detector because of the wide aperture of the detector. In order to reduce the background, a multiblade radial collimator with a fan shape is mounted in front of the detector inside the detector shielding. This collimator is oscillated back and forth with constant velocity during the measurements to smear out shadows of the blades.

The setting of the diffraction geometry, the collimator motion, and the time-slice data acquisition are controlled by a PDP 11/44 computer and CAMAC system. A three-dimensional scan of a prescribed region in reciprocal space is performed automatically by a computer-controlled selection of the crystal rotation and the diffractometer tilt angle.

The time-resolved measurements are performed synchronously with the change of an external condition applied to a sample. There are two types of time-resolved measurements: one-shot and periodic. The one-shot measurements are done for phenomena which cannot be repeated easily. The study of the ordering kinetics of alloys is an example. The feasibility of this kind of measurement is determined by the shortest time period in which diffraction data can be accumulated. In cases of powder diffraction, this time period is a few seconds. A large number of time slices are required to observe a prolonged variation of the diffraction pattern. The time intervals are changed by degrees in these cases, and the recorded data are successfully transferred to the disk storage of the computer. The periodic measurements are employed in cases where the change is reversible according to a periodic external condition. Forty-eight repetitive time slices with a minimum time interval of 10 ms are used to observe this sort of change. Also, a special furnace has been prepared in order to change the sample temperature very rapidly; the maximum heating and cooling rate is 20 C/s.

Installation of the instrument was completed at the end of March 1984. After performance tests and some modifications, the use of the instrument for time-resolved measurements of the kinetics of first-order phase transitions and single-crystal diffraction measurements has been started. Some early results are described in a separate report.

1. Research carried out at the Oak Ridge National Laboratory under the U.S.-Japan Cooperative Program on Neutron Scattering.

2. Guest scientist from the Japan Atomic Energy Research Institute, Tokai-mura, Japan.

3. Instrumentation and Controls Division, ORNL.

REAL-TIME NEUTRON DIFFRACTION MEASUREMENTS OF THE KINETICS OF FIRST-ORDER PHASE TRANSITIONS¹

M. Iizumi² S. Katano²
H. R. Child

The wide-angle neutron diffractometer recently installed at the HFIR has the capability of performing time-resolved or time-slicing measurements. Neutron diffraction patterns, which are usually measured only by a step-by-step scanning of diffractometer angles, can be obtained simultaneously by this instrument. Consequently, diffraction patterns can be acquired within a relatively short time period. In cases of measuring an irreversible process, the speed of time slicing is determined by the minimum time period within which a single-diffraction pattern can be collected with tolerable counting statistics. At present, this period is about one minute. With increased neutron beam intensity obtained by using an improved monochromator, we expect that the minimum time can be reduced by a factor of 10.

One of the interesting problem areas we have explored using this time-slicing function of the diffractometer is the kinetics of structural changes occurring after a temperature jump across a value at which a first-order phase transition occurs. Two measurements of this sort have been carried out: the phase III to II transition in RbNO_3 and the transition between the alpha and beta phases in Sn.

Rubidium nitrate (RbNO_3) shows a series of three-phase transitions among CsCl-like structures (IV and III) at low temperatures and NaCl-like structures (II and I) at high temperatures. We studied only the transition from phase III to phase II, which shows the largest hysteresis and the most conspicuous changes in diffraction patterns among the three transitions. After a rapid temperature change from a temperature below T_c (transition temperature $T_c = 500 \text{ K}$) to $T_c + \Delta T$, the diffraction patterns were recorded by using the time-slicing mode of the instrument. The fractions of phases III and II within the mixed diffraction patterns were deduced for each time slice by fitting Gaussian line shapes to typical diffraction peaks corresponding to each phase. Full courses of the fraction change were observed for several values of ΔT , ranging from 1–26°C. For large temperature jumps (i.e., a high degree of metastability), the change was very fast and finished within 10 min, while for a small jump (i.e., a low degree of metastability), the change was so slow that it took more than 60 min to

finish. The experimental possibility of measuring a rapid process was found to be limited in practice by how rapidly the temperature of the furnace can be changed and by how fast the temperature of each part of the powder sample follows the change.

A measurement of the structural-change kinetics, occurring after a temperature jump from the lowest phase to the highest phase in RbNO_3 , was tried for the purpose of observing how the intermediate phases appear and disappear in this process; it was not successful, because the temperature change of the furnace was not rapid enough. The kinetics of these sorts of structure changes have never been observed, and it will be interesting to carry out such studies in the near future.

The second measurement we carried out was on the alpha-to-beta phase transition in tin. Normal white tin (beta phase) transforms to gray tin (alpha phase) below 260 K. The transformation is fairly slow, taking from 1-12 h, depending on the temperature. The reverse transformation from alpha to beta occurs above 290 K, and the change becomes very rapid as the temperature increases above 290 K. Extensive measurements were carried out on both the alpha-to-beta and beta-to-alpha transformations. Typical changes of the diffraction patterns are illustrated in Fig. 5.38 which shows a very limited part of the

Fig. 5.38. Change of the diffraction pattern of tin during transformation from the beta-to-alpha phase. These patterns were measured by using the time-slicing function of the wide-angle neutron diffractometer.

diffraction patterns for a few selected time slices. The entire diffraction patterns were analyzed to determine the fractions of existing alpha and beta phases. Results show typical nucleation and growth kinetics with authentic incubation times depending on the temperature. Figure 5.39 shows the time required for half of

Fig. 5.39. Time required for half of the tin sample to transform from the alpha-to-beta or beta-to-alpha phases.

the sample to transform for the respective temperatures shown. The slowing down of kinetics in the vicinity of transition temperature is apparent. The real time can be scaled by this halftime to give a universal fraction-vs-time relation. Detailed analysis of the results is now in progress.

1. Research carried out at the Oak Ridge National Laboratory under the U.S.-Japan Cooperative Program on Neutron Scattering.
2. Guest scientist from the Japan Atomic Energy Research Institute, Tokai-mura, Japan.

6- PREPARATION AND CHARACTERIZATION OF RESEARCH MATERIALS

The Research Materials Program is defined by four major objectives. These are (1) contributing to the resolution of materials problems that relate to the principal research goals of DOE; (2) preparing and characterizing high-quality research specimens for use in efforts within the Solid State Division, as well as at other DOE laboratories, industrial research centers, and university laboratories; (3) collaborating with other research groups engaged in energy-related research; and (4) developing new techniques and methods for the preparation and characterization of relevant research materials.

This chapter is divided into two sections: the first section deals with growth and characterization methods, and the second is devoted to special materials. The scope of the research carried out in this program and its extensive cooperative aspects are evident from the first summary in this chapter. The following three entries describe work on single crystals of Cu_3Au , transition-metal alloys, and superconducting A15 compounds. The succeeding research summaries deal with one of the highlights of the program during this reporting period. A new material that is a promising primary waste form for the disposal of high-level commercial and defense nuclear wastes has been discovered. This new material, lead-iron phosphate glass, can be processed at temperatures significantly lower than those required for borosilicate glasses, and it exhibits a corrosion resistance that is 100 to 1000 times better. The following four entries in the first section of this chapter deal with investigations of the corrosion resistance of borosilicate nuclear waste glasses and with fundamental studies of the lanthanide orthophosphates. The second section of this chapter contains entries describing research on the mixed perovskite-structure tantalates. The final four summaries detail the results of investigations of optical and associated defect properties of the alkaline earth oxides.

GROWTH AND CHARACTERIZATION METHODS

CRYSTAL GROWTH AND CHARACTERIZATION PROGRAM

M. M. Abraham	L. A. Boatner
W. E. Brundage	Y. K. Chang
L. S. Darken	H. E. Harmon
J. O. Ramey	B. C. Sales

In order to increase the impact and effectiveness of the crystal growth and character-

ization program, a liberal policy of working with scientists in other ORNL divisions, other national laboratories, and university and industrial laboratories is deliberately pursued. Samples resulting from the efforts of this program are provided to others, on either a loan or collaborative basis, depending on the degree of involvement by staff members of the program. These samples are generally the subject of physical properties measurements that are either complementary or supplementary to ongoing research activities in the ORNL Solid State

Division. This activity is an effective means of enhancing the exchange of scientific information and of broadening the scope of in-house research efforts. Table 6.1 lists some representative examples that illustrate the nature and diversity of the research arising from this activity. Also shown are various laboratories that benefit from the current policy.

1. Present address: Tennelec, Oak Ridge, Tenn.

CHARACTERIZATION OF AS-GROWN Cu_3Au SINGLE CRYSTALS

Y. K. Chang A. Fattah¹
W. Uelhoff¹ G. Hanke¹

The perfection and morphology of as-grown Cu_3Au single crystals produced by pulling from an advanced Czochralski crystal growth system have been characterized nondestructively by means of gamma-ray diffractometry and optical microscopy. Due to the short wavelength of 0.03 Å, gamma rays easily penetrate large bulk crystals—unlike X rays which only scan the near-surface region. During the crystal growth process, a number of growth parameters, such as the melt temperature, crystal diameter, meniscus height, and crystal length were automatically monitored, and information regarding the growth and morphology has been obtained by correlating the experimental results with either measured or derived growth parameters.

A series of gamma-ray rocking curves [(220) reflection] taken with a $0.5 \times 5 \text{ mm}^2$ slit at 5-mm intervals along a Cu_3Au crystal, pulled with a [110] growth direction, is shown in Fig. 6.1. The region after the neck had a half-width (HW) of 70 s of arc. The HW widened, however, when the seed and crucible rotation rates were slowed from a counter-rotation of $\pm 30 \text{ rpm}$ to an isorotation of 15 and 5 rpm. This occurred in the region located between 48 and 49 mm, as measured from the initiation of single-crystal growth. When both rotations were stopped, the mosaic spread was found to broaden further, though some recovery has been observed after additional growth had taken place. Furthermore, the crystal quality was drastically lowered when the pulling speed was increased from 3 to 10 mm/h. This decrease in crystal quality was accompanied by the formation of surface roughness and columnar structure—an evidence of constitutional supercooling. In order to illustrate the progressive effect on crystal perfection after changing the rotation rates, a series of gamma-ray rocking curves taken at 1-mm intervals is shown in Fig. 6.2. Although there was no observable change in the crystal diameter and melt temperature, the crystal perfection (or the mosaic spread) has been strongly affected by altering the rotation rate. The width of the mosaic spread continued to grow for about 5 mm before stabilizing at a new width.

No significant difference in crystal perfection was found for crystals grown along different low symmetry directions. However, a {111} facet

formation occurred on crystals grown along [100] and [110] directions. For the observed {111} and {100} facets, the areas of {111} facets are always larger, implying that the {111} face has the lowest surface free energy. These facets have not been observed during the growth of pure copper or gold.

1. Kernforschungsanlage Jülich, Federal Republic of Germany.

PREPARATION OF TRANSITION-METAL ALLOYS

Y. K. Chang

Transition metals form continuous solutions with noble metals, and the transport properties of the resulting alloys are often rapidly altered as a function of the concentrations. Therefore, such systems are ideal subjects for exploring conduction electron behavior when two metals are mixed. The silver-palladium system is one of the attractive choices for such a study. Single crystals with wide concentration ranges are required for measurements of photoemission and positron annihilation in order to test the results of recent band structure calculations.¹ For this purpose, pure Ag and pure Pd single crystals have been prepared by Bridgman and float-zone techniques, respectively. Specimen rods of PdAg (50 at. % Ag) were initially zoned in an induction float-zone system using compressed argon gas to suppress evaporation associated with the low vapor pressure of the alloy. Maintaining a stable molten zone was very difficult in these systems because of low surface tension of the liquid alloy. A modified Bridgman approach in which the alloy was melted in an Al_2O_3 Bridgman crucible was subsequently used to avoid problems of this type. Void formation on the crystal surface was eliminated by baking out the crucible at high temperatures before loading with the AgPd alloy.

Niobium-titanium alloys have been used for decades as windings in superconducting magnets. Recent interest in investigating the flux-line-lattice interaction with defects in NbTi has led to a requirement for high-quality single crystals. Rods of niobium alloyed with 50 wt % titanium were float zoned at a speed of 5–7 mm/h under 3 atm of argon to suppress the evaporation of Ti. An example of the large single crystals that were obtained is shown in Fig. 6.3. The diameter of the zoned (crystal) region, which is larger than the starting rod, was formed by slowly feeding the polycrystalline rod into the molten zone during growth.

1. A. J. Pindor et al., *J. Phys. F* 10, 2617 (1980).

Table 6.1. Loan of research materials samples for investigations outside the Research Materials Program.

Material	Type of study	User	Organization
CaTiO ₃	Radiation effects	F. Clinard	LANL
LnPO ₄	Mineral analysis	R. Ewing	University of New Mexico
Basalt glasses	Nuclear waste form performance	R. Ewing	University of New Mexico
CaTiO ₃	Electron microscopy	L. Hobbs	MIT
Y ₂ O ₃	Thin film reactions	L. Greene	Bell Laboratories
LnPO ₄	Microprobe analysis	P. Roeder	Queens University, Kingston, Canada
YPO ₄	EPR	J. Boldú	UNAM, Mexico
K _{1-x} Li _x Ta _{1-y} Nb _y O ₃	Light scattering	L. Chase	Indiana Univeristy
EuPO ₄	Optical spectroscopy	N. Edelstein	LBL
TbPO ₄	Raman scattering	P. Becker	LBL
KTaO ₃	High-temperature conductivity	A. Nowick	Columbia University
CaTiO ₃	X-ray analysis	D. Mullica	Baylor University
Pb ₂ P ₂ O ₇	Structural refinement	D. Grossie	Baylor University
ZrO ₂	Electrical properties	J. Bates	ORNL
Borosilicate glass	Raman scattering	G. Begun	ORNL
KTa _{1-x} Nb _x O ₃	Photorefractive studies	J. Feinberg	University of Southern California
Pb-Fe phosphate glass	EXAFS	G. Greaves	Daresbury Laboratories, England
GdFeO ₃	EXAFS	G. Greaves	Daresbury Laboratories, England
MgO	TEM	L. Horton	ORNL
ZrC	Vacancy ordering	E. Storms	LANL
NbC	Ellipsometry	F. Modine	ORNL
LnPO ₄	TEM	P. Angelini	ORNL
Pb-Fe phosphate	Thermal conductivity	B. Williams	ORNL
KTaO ₃	Light scattering	W. Unruh	University of Kansas
KTa _{1-x} Nb _x O ₃	Optical studies	R. Bunch	Rose-Hulman Institute
LnPO ₄	SIMS	R. Jonasson	University of Western Ontario, Canada
MgO:Ni	Surface solute enrichment	R. McCune	Ford Motor Company
CaO:Sr	ODMR	J. Spaeth	University of Paderborn, FRG
MgO	Optical emission	G. Summers	University of Oklahoma
CaO	Ionic thermal conductivity	J. Crawford	University of North Carolina
MgO:Mg	Luminescence	A. Mooradian	MIT
MgO	Emission spectroscopy	J. Grant	University of Melbourne, Australia
CaO:Sr	EPR	H. Tohver	University of Alabama
MgO:Ni	TEM	R. Gonzalez	University of Madrid, Spain
LnPO ₄	EXAFS	R. Greigor	Boeing Company
LnPO ₄	EXAFS	F. Lytle	Boeing Company
Ni ₃ Al	Grain boundary fracture	C. Liu	ORNL
Ni ₃ Al	Ferromagnetism	S. Sekula	ORNL
V	Tritium doping	K. Farrell	ORNL
Ni	LEED	J. Noonan	ORNL
Ti ₃ Au	Neutron scattering	H. Smith	ORNL
Fe _{0.65} Ni _{0.20} Cr _{0.15}	Irradiation study	P. Jung	KFA Jülich, FRG
Ni	EELS	J. Wendelken	ORNL
V ₃ Si	Transformation	R. Colella	Purdue University
V ₃ Si	Thermal conductivity	T. Finlayson	Monash University, Australia
NbTi	Magnetization	D. Christen	ORNL
NbTi	Superconductivity	H. Kerchner	ORNL
NbTa	Superconductivity	H. Kerchner	ORNL

Table 6.1 (continued)

Material	Type of study	User	Organization
$\text{Fe}_{0.69}\text{Cr}_{0.21}\text{V}_{0.10}$	Neutron scattering	S. Spooner	ORNL
$\text{Fe}_{0.7}\text{Ni}_{0.15}\text{Cr}_{0.15}$	Radiation damage studies	K. Farrell	ORNL
$\text{Fe}_{0.7}\text{Ni}_{0.15}\text{Cr}_{0.15}$	Mechanical properties	M. Yoo	ORNL
InTi	Neutron scattering	T. Finlayson	Monash University, Australia
$\text{Cu}_{0.99}\text{Co}_{0.01}$	Neutron scattering	S. Spooner	ORNL
$\text{Na}\beta$ -alumina	Hydration studies	J. Bates	ORNL
^{57}Fe -3% Si	Neutron polarizing monochromator	H. Mook	ORNL
Cu_3Au	Neutron scattering	N. Wakabayashi	Keio University, Yokohama, Japan

Fig. 6.1. A series of gamma-ray rocking curves [(220) reflection] taken with a $0.5 \times 5 \text{ mm}^2$ slit at 5-mm intervals along a Cu_3Au crystal prepared by the Czochralski method.

CRYSTAL GROWTH OF SUPERCONDUCTING A15 COMPOUNDS

Y. K. Chang H. E. Harmon

The growth of single crystals of superconducting A15 compounds has been continued from earlier reporting periods. New emphasis has been placed on preparing nonstoichiometric V_3Si and V_3Ge , however, and on overcoming crusting problems that arise during the growth of $\text{Nb}_3\text{Ge}_{(1-x)}$.

Stoichiometric V_3Si is found to undergo a martensitic transformation (from cubic to

tetragonal structure) around 21 K. It is believed that this transformation disappears when the silicon concentration is reduced slightly. Rods of vanadium mixed with 24.5 at. % silicon, approximately 8 mm in diameter, were prepared by an induction-heated cold-boat technique. These rods were then float zoned in a multipurpose crystal growth system using a recently installed, 100-KW induction generator. Surface striations were usually observed on these crystals, and they were generally inferior to the crystals prepared from stoichiometric mixtures.

Fig. 6.2. A series of gamma-ray rocking curves [(200) reflection] taken with a $0.5 \times 5 \text{ mm}^2$ slit at 1-mm intervals from 46 to 56 mm on the same crystal shown in Fig. 6.1.

ORNL-Photo 5882-84

Fig. 6.3. Single crystal of NbTi alloy (50 wt % Ti) grown by the rf-induction float-zone technique.

Conflicting reports^{1,2} for the phase diagrams regarding the Al5 V₃Ge phase have prompted the preparation of slightly off-stoichiometric V₃Ge (V + 24 at. % Ge) in order to avoid the formation of a second phase (V₅Ge₃) near the stoichiometric composition and, thereby, improve the crystal quality. Our observation of a higher melting temperature is in better agreement with the more recently reported temperature (1920°C)² than with the earlier results reported by Savitsky et al. (1690°C).¹ Our results of better crystals from stoichiometric mixtures, however, seem to be in better agreement with the report by Savitsky et al. on the range of composition of the Al5 phase.

Since the equilibrium Al5 phase of niobium-germanium exists only with germanium compositions less than 19 at. %, we have made several attempts to grow crystals from rods of 18 at. % Ge and 17.5 at. % Ge by the induction float-zone method. As found from past experience with these systems, a layer of solid crust forms over the molten zone and complicates the growth process by interfering with induction coupling to the zoned rod. We have found that the solid crust was dissolved by increasing the rf power. Under these growth conditions, however, the molten zone becomes longer and the crystal diameter gradually grows larger until the molten zone finally becomes unstable. The crystals produced in this process are normally 10 to 15 mm long, have bright surfaces, and are of high quality.

1. E. M. Savitsky et al., *Russ. Metallurgy* (English Translation, Scient. Inf. Consultants, London), No. 3, p. 137 (1974).

2. J. F. Smith, *Bull. Alloy Phase Diagr.* 2, 205 (1981).

3. J. L. Jorda, R. Flukiger, and J. Muller, *J. Less-Common Metals* 62, 25 (1978).

4. R. Flukiger, private communication.

LEAD-IRON PHOSPHATE GLASS: A STABLE STORAGE MEDIUM FOR HIGH-LEVEL NUCLEAR WASTE¹

B. C. Sales L. A. Boatner

A new lead-iron phosphate glass nuclear waste form that appears to be unusually well suited to the safe immobilization and permanent disposal of various types of high-level radioactive waste has been developed. By melting lead-iron phosphate glass together with simulated nuclear waste, a homogeneous stable glass can be formed at a relatively low temperature (900°C) in which the radioactive nuclei are chemically incorporated in the glass structure.

The effects of iron oxide on the properties of pure lead phosphate glasses are quite remarkable. Pure lead phosphate glasses are relatively susceptible to aqueous corrosion and tend to devitrify (crystallize) at temperatures as low as 300°C. The addition of iron oxide to these glasses improves the corrosion resistance by a factor of more than 10,000 (Fig. 6.4) and results in the formation of glasses that do not exhibit any evidence of

Fig. 6.4. Leachate conductivity vs time data for a lead metaphosphate glass [Pb(PO₃)₂] doped with 0.0, 1.0, 3.0, 6.0, and 9.0 wt % iron oxide. The addition of 9.0 wt % iron oxide to lead metaphosphate glass reduces the corrosion rate by a factor of about 10,000 relative to the undoped glass.

devitrification after being heated in air at 575°C for 100 h. Perhaps most significantly, extremely stable lead-iron phosphate glasses can be prepared and poured easily at temperatures between 800 and 900°C. The amount of iron oxide which must be added to form the lead-iron phosphate waste glass depends on the iron concentration already present in the nuclear waste.

The results illustrated in Fig. 6.4 can be used in tailoring the composition of the lead-iron phosphate glass frit depending on the iron concentration of a given type of nuclear waste. The highly stable waste form is realized when the iron concentration is adjusted to correspond to a content of about 9.0 wt % Fe₂O₃ relative to pure lead phosphate. High-level defense waste typically contains about 50 wt % Fe₂O₃, and for this type of nuclear waste, no additional iron is added to the pure lead phosphate frit for the formation of a very stable nuclear waste glass. For most high-level commercial wastes of the type generated by light water nuclear power reactors, however, additional iron oxide must be added to the pure lead phosphate glass in order to form a sufficiently stable,

corrosion-resistant nuclear waste glass. Both the commercial and the defense-loaded lead-iron phosphate nuclear waste glasses were black, reflective, very homogeneous, and had a density of about 5 g/cm³. The maximum amount of simulated nuclear waste that could be completely dissolved in the lead-iron phosphate host glass was approximately 15–20 wt %. Due to the high density of the lead-iron phosphate waste form, this amount corresponds to the same waste per volume loading obtained in a typical borosilicate glass loaded with 30–40 wt % waste.

One of the most important characteristics of any potential nuclear waste glass is the ability of the glass to retain hazardous radioactive nuclei in the event that groundwater comes in contact with the waste form for prolonged or repetitive periods of time. Leaching of radioactive nuclei from the glass into groundwater is generally regarded as the most likely mechanism by which radioactive waste could be reintroduced into the biosphere. Standardized corrosion tests were used to make comparisons between the corrosion behavior of lead-iron phosphate nuclear waste glasses and identically loaded borosilicate nuclear waste glasses. Nuclear waste glasses loaded with either simulated U.S. defense waste or simulated reprocessed nuclear power reactor waste were investigated.

Each glass waste form was exposed to distilled water at 90°C for one month. The leachate solutions were then analyzed for all major elements present in a given glass type using standard quantitative analytical techniques (inductively coupled plasma emission analysis, atomic absorption, and fluorimetry). The results of these experiments show that, under the specified corrosion conditions, the net release of all elements from lead-iron phosphate nuclear waste glasses containing either defense or power reactor wastes was at least 100 to 1000 times smaller than the corresponding release from a comparable borosilicate nuclear waste glass. A comparison of the typical leaching data obtained for defense waste-loaded lead-iron phosphate glass with that of defense waste-loaded borosilicate nuclear waste glass is shown in Fig. 6.5. It should be noted that the concentrations of all elements present in the lead-iron phosphate leachates were below the detectability limits of the analytical chemical techniques employed. In particular, under these corrosion conditions, the lead-iron phosphate waste form successfully immobilizes Cs, Na, and Mo, elements which are notoriously difficult to retain in borosilicate waste glasses exposed to aqueous conditions.

The experimental results indicate that lead-iron phosphate nuclear waste glasses represent a new, very stable, and easily prepared medium for the disposal of some important classes of nuclear waste. Relative to borosilicate nuclear waste glass, the lead-iron phosphate nuclear waste glass has several distinct advantages, including the following: (1) a corrosion rate at 90°C that is generally about 1000 times lower than that of comparable borosilicate glass; (2) a formation temperature that is 100–250°C lower than the temperature of ~1150°C that is required for a comparable borosilicate glass; (3) a rela-

Fig. 6.5. The 30-day corrosion rates at 90°C in distilled water for lead-iron phosphate [Pb(PO₃)₂ + 15 wt % simulated high-level defense waste] and borosilicate (frit 131 + 29 wt % simulated high-level defense waste) nuclear waste glasses. The compositions of the borosilicate glass frit and the simulated high-level defense waste are given in Ref. 2. The composition of the simulated high-level defense waste (2) was used in preparing both the lead-iron phosphate and borosilicate glass nuclear waste forms. The concentrations of all elements present in the lead-iron phosphate leachate were below the detectability of standard analytical chemical techniques, and accordingly, the limiting values shown above for lead-iron phosphate represent the analytical detectability limits for each indicated element. Lead-iron phosphate and borosilicate nuclear waste glasses had the same waste-per-volume loading.

tively good capacity of the molten glass for dissolving the elements found in both defense and commercial power reactor wastes; (4) a melt viscosity and processing (i.e., pouring) temperature in the 800–1000°C temperature range that is significantly lower than the ~1150°C pouring temperature of borosilicate glass; and (5) lead-iron phosphate glass that can be used for both commercial and defense-related nuclear waste disposal. As a final point, whose practical significance is perhaps equally as important as the characteristics listed above, it

appears that the lead-iron phosphate glass waste form could be processed using a technology similar to that developed previously for processing borosilicate glass nuclear waste forms.

1. Summary of paper: Science 226, 45 (1984).

2. R. G. Baxter, Description of Defense Waste Processing Facility Reference Waste Form and Canister (Report DP-1606, Rev. 1), E. I. duPont de Nemours & Company, Wilmington, Del., 1982.

STRUCTURAL PROPERTIES OF LEAD-IRON PHOSPHATE GLASSES¹

B. C. Sales M. M. Abraham
J. B. Bates L. A. Boatner

Lead metaphosphate glass $[\text{Pb}(\text{PO}_3)_2]$ is one member of a very large class of materials which have the general formula $\text{M}(\text{PO}_3)_y$, where the metal M with valence y can be an alkali, alkaline earth, rare-earth, actinide, or transition metal. All of the metaphosphates can be prepared in the glassy or crystalline state, and all of the resulting materials have the same basic structure regardless of the metal cation M. From infrared and Raman measurements, x-ray diffraction analyses, and chromatographic data, it has been determined that both the glassy and the crystalline forms can be viewed as consisting of chains of PO_4 tetrahedra bonded to adjacent tetrahedra by bridging oxygen atoms. Neighboring polyphosphate chains are then linked together by cross bonding between the metal cation and the two nonbridging oxygen atoms of each PO_4 tetrahedron. The P-O-P bond between PO_4 tetrahedra in the same chain is generally much stronger than the cross bond between chains via the metal cation.

Although lead metaphosphate glass can be prepared and poured at relatively low temperatures ($\sim 800^\circ\text{C}$), the glass is susceptible to aqueous

corrosion and tends to crystallize at temperatures as low as 300°C . It has been recently discovered, however, that the addition of iron oxide to lead metaphosphate results in an unusually stable and chemically durable glass, which can still be prepared and poured at $\sim 800^\circ\text{C}$. In fact, some lead-iron phosphate glasses have aqueous corrosion rates which are approximately 10^4 times lower than pure lead metaphosphate glass. Additionally, these lead-iron phosphate glasses do not exhibit any evidence of devitrification after being heated in air at 550°C for 100 h.

The effects of iron concentration, fusion temperature, and soak time on the glass transition temperature T_g , softening point T_s , thermal expansion coefficient, and aqueous corrosion rate of several lead-iron phosphate glasses are summarized in Table 6.2. The corrosion rates shown in Table 6.2 are normalized with respect to the most corrosion resistant lead-iron phosphate glass ($x=0.216$) which lost less than 0.1 ppm of its original mass after exposure to distilled water at 90°C for 60 h. Concentrations of Fe_2O_3 substantially higher than $x = 0.216$ produced polycrystalline material rather than a glass.

From the data presented in the first four rows of Table 6.2, where the fusion temperature T_f varied between 700 and 1000°C , it appears that the thermal properties and corrosion resistance of pure lead metaphosphate glass are not significantly affected by altering the fusion temperature. The glass that was melted at 700°C has a slightly lower softening point, which is probably due to the presence of water in the glass structure. Infrared absorption measurements indicated that about five times as much water was present in the glass melted at 700°C , as compared with a lead metaphosphate glass melted at 900°C . The glass prepared at 1000°C for 24 h had a slightly higher softening point. This is probably caused by a small amount of dissolved Pt in the glass, which gave the glass a pale yellow tint. All of the other lead metaphosphate glasses were clear and had an optical absorption edge in the ultraviolet at about 4.6 eV.

Table 6.2. Thermal and chemical properties of lead-iron phosphate glasses $[(1-x)\text{Pb}(\text{PO}_3)_2 + x\text{Fe}_2\text{O}_3]$ as a function of fusion temperature T_f and soak time t.

x	$T_f(^{\circ}\text{C})$	t(h)	$T_g(^{\circ}\text{C})$	$T_s(^{\circ}\text{C})$	$\alpha(10^{-6}, ^{\circ}\text{C}^{-1})$	Normalized corrosion rate
0	700	1.5	314	340	14.3	7000
0	800	3	326	349	14.2	7000
0	900	3	326	349	14.3	7000
0	1000	24	336	357	13.7	7000
0.03	900	3	344	379	12.7	1500
0.06	900	3	359	395	12.3	500
0.085	900	3	364	406	12.5	500
0.152	900	3	421	468	11.7	250
0.216	900	3	478	518	10.5	1

From the data shown in the last five rows of Table 6.2, it can be seen that increasing the iron oxide concentration in these glasses increased both the glass transition and softening temperature, while decreasing the thermal expansion coefficient and aqueous corrosion rate. Also, infrared absorption measurements indicated that under identical preparation conditions the water content in these glasses decreased by about a factor of 3 as the iron concentration was increased.

The local environment and valence states of iron ions in lead-iron phosphate glasses were studied using transmission Mössbauer spectroscopy. A typical Mössbauer absorption spectrum is shown in Fig. 6.6. The absence of any appreciable absorption in the region near 2-3 mm/s

Fig. 6.6. Transmission Mössbauer absorption spectrum from a lead-iron phosphate glass. The spectrum was fit using two quadrupole split Fe^{3+} doublets corresponding to two types of iron sites in the glass structure.

indicates that for this lead-iron phosphate glass, which was melted at 900°C , at least 99% of the iron in the glass is Fe^{3+} . For a glass with a similar iron concentration but which was melted at 1000°C , however, approximately 10% of the iron is Fe^{2+} . A more detailed analysis of the spectrum shown in Fig. 6.6 strongly suggests that there are at least two major inequivalent Fe^{3+} sites in this glass. Furthermore, both of these sites have isomer shifts which correspond to octahedral or "modifying" sites in the glass structure between the phosphate chains. Given the general structural characteristics of lead metaphosphate glass and the local environment of iron in these glasses, it seems likely that the iron improves the chemical durability in lead-iron phosphate glasses by strengthening the cross bonding between the polyphosphate chains. With increasing iron concentrations, the average length of the polyphosphate chains is reduced, and the iron may also be effective in bonding the ends of the chains to the surrounding glass

structure. Finally, a secondary effect of iron in these glasses is its ability to increase the rate at which water is removed from the glass during the fusion process.

i. Summary of paper to be published.

SURFACE LAYER FORMATION ON CORRODED NUCLEAR WASTE GLASSES¹

B. C. Sales C. W. White
G. M. Begun² L. A. Boatner

The corrosion of a borosilicate nuclear waste glass is accompanied by the formation of an altered layer on the glass surface. This layer has a chemical composition that is radically different from that of the bulk glass and can be many microns thick. In this study, the combined techniques of Rutherford backscattering depth profile analysis, Raman scattering, quantitative solution analysis, and solution conductivity measurements have been used to investigate the elemental distribution, chemical stability, chemical composition, and protective ability of the altered surface layers formed on several simulated nuclear waste glasses that were corroded in aqueous media. The properties of altered glass surface layers formed by exposure to distilled H_2O , acidic, basic, and brine solutions were investigated (Fig. 6.7). Exposure to the different solutions resulted in significant variations in the characteristics of the corroded surface layer. In particular, the surface layers formed in one solution were frequently unstable when the glass was re-exposed to different corrosion conditions. Raman spectroscopy was employed in establishing that for glasses corroded in distilled H_2O , strontium is present in the altered surface layer in the form of SrCO_3 . The major findings of this study are enumerated below:

1. Glasses corroded in distilled water or a basic 0.01 N NaOH (pH=12) solution develop surface layers that are rich in relatively stable transition metal compounds [e.g., $\text{Fe}(\text{OH})_3$, $\text{Mn}(\text{OH})_2$, and $\text{Ti}(\text{OH})_4$].
2. Glasses corroded in an acidic 0.01 N HCl (pH=2) solution develop surface layers that are depleted in B and all metal elements (except perhaps Ti and Fe) but are rich in Si.
3. The transition-metal-rich layer, which forms on glasses corroded in distilled water or a basic solution, is rapidly removed when the glass is exposed to an acidic solution (pH=2).
4. The silicon-rich layer which forms on glasses corroded in an acidic solution (pH=2) is rapidly dissolved when the glass is placed in a basic solution (pH=12).
5. For simulated nuclear-waste-containing glasses corroded in distilled water, Sr and Cs are selectively leached from the glass while U is selectively retained in the surface layer as a precipitate of a relatively insoluble U compound.
6. For glasses corroded in a basic solution, Cs and U go into solution at about the same rate as the borosilicate matrix elements

Fig. 6.7. Energy spectra of 2.0-MeV $^4\text{He}^+$ ions backscattered from uncorroded (a) and corroded (b) simulated borosilicate nuclear waste glass (Frit 21 + 20 wt % SRW + 3 wt % UO_2). Each glass sample was corroded for 6 h at 90°C in either (a) distilled water, (b) 0.01 N HCl (pH=2), (c) 0.01 N NaOH (pH=12), or (d) brine. The arrows denote the onset energy for scattering from U, Fe, Mn, Ti, and Ca. A comparison of the backscattering results shown in (a) and (d) shows the qualitative similarities of the altered surface layer for glass samples leached for this time period in distilled water or brine. In both cases, enhanced concentrations of U, Fe, Mn, and Ti are present in the surface layer. The results shown in (b) for leaching in a pH = 2 solution clearly illustrate the selective removal (i.e., leaching in the traditional sense) of uranium from the nuclear waste glass.

(Si, B), but Sr will eventually precipitate on the glass surface (or in the container) as SrCO_3 .

7. The elements U, Sr, and Cs are all selectively leached from glasses corroded in a 0.01 N HCl solution (pH=2). For example, corroding a U-doped glass in a pH 2 solution for 6 h resulted in a surface layer in which no uranium was detectable within 1 μm of the surface (Fig. 6.8).

8. The uranium compound, which precipitates on a glass corroded in distilled water, does not form on a glass corroded in either an acidic or a basic solution. Hence, at least for short corrosion periods, uranium is only selectively retained by the glass when the glass is corroded by a solution with a pH in the neutral region.

9. The Raman spectra from simpler borosilicate glasses corroded in distilled water clearly show the presence of the CO_3^{2-} ion in

conjunction with the presence of Sr in the glass. These data confirm the presence of SrCO_3 in the surface layer as expected from solubility calculations.

10. The Raman spectrum of the corroded Frit 21A specimen in the spectral region below 800 cm^{-1} exhibits much sharper peaks than would be expected from a glass. These relatively sharp features are probably due to the initial formation of crystalline material in the surface layer.

11. Solution conductivity measurements on specimens of Frit 131 + 29 wt % SRW precorroded in distilled water indicate that the drop in the normalized corrosion rates with time of elements such as B is due to the presence of the transition-metal-rich surface layer. For other nuclear waste glasses with similar compositions, however (i.e., PNL 76-68 glass and Frit 21 + 20

Fig. 6.8. Uranium concentration vs depth profiles from a simulated nuclear waste glass corroded for 6 h at 90°C in distilled water (●) or a pH = 2 solution (■). For comparison, the U concentration vs depth profile from an uncorroded glass (○) is also shown. The exact depth to which the uranium has been removed cannot be determined due to the onset of scattering from Fe and Mn in the layer.

wt % SRW), the altered layer is not so effective in reducing the corrosion rate of the underlying glass.

1. Summary of paper to be published.
2. Chemistry Division, ORNL.

EPR OBSERVATIONS OF THE TRIVALENT STATE OF HAFNIUM AND ZIRCONIUM IN LuPO₄, YPO₄, AND ScPO₄ SINGLE CRYSTALS¹

M. M. Abraham L. A. Roatner
M. Rappaz² J. O. Ramey

The orthophosphates of lutetium, yttrium, and scandium crystallize with the tetragonal zircon structure where each heavy metal atom is coordinated with eight nearest-neighbor oxygen ions. Single crystals of these materials may be prepared by a flux technique in which a lead pyrophosphate (Pb₂P₂O₇) flux contained in a platinum crucible is slowly cooled from a temperature of 1360°C. The electron paramagnetic resonance (EPR) spectrum of what was eventually

identified as trivalent zirconium was first observed as a parasitic signal in undoped flux-grown single crystals of ScPO₄. This spectrum consisted of a strong central line and six less intense hyperfine lines and was axially symmetric. A careful measurement of intensities showed that the $I = 5/2$ isotope was approximately 11% abundant. This value is in agreement with the natural abundance of the isotope ⁹¹Zr. An unequivocal verification of the unusual trivalent state of zirconium was accomplished by growing single crystals of ScPO₄ that were intentionally doped with isotopically enriched ⁹¹Zr.

Subsequently, single crystals of LuPO₄ and YPO₄ doped with both naturally abundant Zr and isotopically enriched ⁹¹Zr were prepared. Investigations of these samples revealed that Zr³⁺ was also stable at room temperature in LuPO₄ but not in YPO₄. The EPR spectrum of Zr³⁺ could be observed for YPO₄, however, by irradiating the crystal at 77 K in a gamma source.

Orthophosphate crystals doped with hafnium were also grown. EPR signals due to hafnium were only observed, however, when the samples were gamma irradiated at 77 K and maintained at 77 K during the EPR observations. Since there are two odd isotopes of hafnium with different nuclear spins and different abundances, the verification of the spectrum of Hf³⁺ was straightforward. Further unequivocal identification was made by preparing crystals doped with isotopically enriched hafnium. The EPR spectrum obtained for naturally abundant Hf³⁺ in ScPO₄ is shown in Fig. 6.9. This spectrum was obtained at a frequency of 9.12 GHz at 77 K. The tetragonal spin-Hamiltonian parameters at 77 K were determined for both Zr³⁺ and Hf³⁺.

1. Summary of paper to be published.
2. Ecole Polytechnique Fédérale de Lausanne, Lausanne, Switzerland.

CRYSTAL-FIELD ANALYSIS OF Tm³⁺ AND Yb³⁺ IN YPO₄ AND LuPO₄¹

P. Becker² T. Hayhurst³
G. Shalimoff² J. G. Conway²
N. Edelstein² L. A. Roatner
M. M. Abraham

The optical and near-infrared absorption spectra of dilute Tm³⁺ and Yb³⁺ impurities in YPO₄ and LuPO₄ single crystals have been investigated at liquid helium and nitrogen temperatures. For Tm³⁺, the spectral region from 5000 to 38,000 cm⁻¹ was examined, and Zeeman spectra were obtained in the visible region. The observed transitions were assigned and fit to a semiempirical Hamiltonian with adjustable parameters via a least-squares procedure. These calculations were made using a full diagonalization of the Hamiltonian matrix in the (L, S, J, J_z) representation. Good agreement was obtained between the observed and calculated energies and g values.

Fig. 6.9. EPR spectrum of Hf³⁺ in a single crystal of ScPO₄. The sample had been gamma-irradiated at 77 K.

In the case of Yb³⁺ in YPO₄ and LuPO₄, scans were made at both pumped liquid He and N₂ temperatures from 9,000 to 11,000 cm⁻¹. Linear polarization of the spectra was obtained in the directions perpendicular and parallel to the crystal axis. The experimental g values for the ground state doublets were determined by means of EPR spectroscopy and have been reported previously.⁴ Zeeman splittings in the 10,000 cm⁻¹ region were photographed at liquid He temperatures with the crystallographic c axis both parallel and perpendicular to the magnetic field of 26.9 kG. The Zeeman pattern for Yb³⁺ in YPO₄ was analyzed in detail since the accidental degeneracy of two of the excited states results in a mixing of these states when an applied magnetic field is not parallel to the S₄ axis. Because there are more parameters than experimental levels for Yb³⁺, the empirical Hamiltonian parameters ζ , B_0^2 , B_0^4 , and B_4^0 were adjusted, while B_0^6 and B_4^6 were fixed at the values found for Tm³⁺. Energy levels and Zeeman splittings calculated using these parameters are in good agreement with the measured quantities.

1. Summary of Paper: Journal of Chemical Physics (in press).
2. Lawrence Berkeley Laboratory, Berkeley, Calif.
3. The Aerospace Corporation, Los Angeles, Calif.
4. M. M. Abraham et al., J. Chem. Phys. **78**, 3 (1983).

NINEFOLD COORDINATION IN LaPO₄: PENTAGONAL INTERPENETRATING TETRAHEDRAL POLYHEDRON¹

D. F. Mullica² W. O. Milligan²
 D. A. Grossie² G. W. Beall³
 L. A. Boatner

The crystal structure of LaPO₄ has been determined from three-dimensional single-crystal x-ray diffraction data. The respective residual indices R_1 and R_2 have been refined to 0.020 and 0.021, based on 625 unique reflections. Crystallization of LaPO₄ occurs in the monoclinic space group P2₁/n (No. 14) with $a = 6.825(4)$, $b = 7.057(2)$, $c = 6.482(2)$ Å, and $\beta = 103.21(4)$ and $Z = 4$. The lanthanum metal atom is nine-coordinated to oxygen atoms, and the nine-coordinated La atoms are linked together by distorted tetrahedral phosphate groups. In CePO₄, the polyhedron surrounding the cerium atom has been described as an irregular nine-coordinated system (i.e., a very distorted monocapped square antiprism). After a careful reexamination of the stereochemistry of the nine-coordinated CePO₄ system using a scale model and after investigating the geometric form of LaPO₄, determined structurally in this work, a pentagonal interpenetrating tetrahedral polyhedron is considered to be the proper structural description. A nine-coordinated polyhedron described as an intermediate between a monocapped square antiprism (MSAP) and a tricapped trigonal prism (TTP) has been presented in the literature. The pentagonal interpenetrating tetrahedral polyhedron illustrated in Fig. 6.10, however, does not resemble a hybrid or intermediate between MSAP and TTP. The crystallographic structural studies of LaPO₄ are relevant to lanthanide coordination chemistry and the characteristics of nuclear waste materials.

1. Summary of paper: Inorg. Chim. Acta **95**, 231 (1984).
2. Baylor University, Waco, Tx.
3. Weston Company, Rockville, Md.

SPECIAL MATERIALS

EPR STUDIES OF SOME fⁿ AND dⁿ ELECTRONIC IMPURITIES IN KTaO₃ SINGLE CRYSTALS¹

M. M. Abraham L. A. Boatner
 D. N. Olson² U. T. Höchli³

Recent investigations of hydrogen diffusion in potassium tantalate (KTaO₃) and the interactive role played by transition-metal impurities have led to renewed interest in the solid state properties of doped tantalate crystals. In the specific case of Fe³⁺ in single crystals of KTaO₃, recent results have shown that the conditions resulting in the formation of OH⁻ in KTaO₃ also produce a significant change in the relative intensities of the cubic- and axial-site Fe³⁺ EPR spectra. In order to investigate the relationships between the properties of

Fig. 6.10. (a) LaPO₄, structurally oriented, (b) LaPO₄, pentagonal interpenetrating tetrahedral polyhedron (PITP), (c) idealized PITP demonstrating the plane of symmetry C₅.

other transition-metal impurities and the diffusion of hydrogen, a series of investigations has been carried out that provides fundamental information regarding the local environments of *f*ⁿ and *d*ⁿ electronic impurities in KTaO₃. These results represent a basis for future studies of the effects of hydrogen in doped tantalate crystals.

Single crystals of the cubic perovskite host, KTaO₃, doped with iron group, lanthanide, and actinide impurities were investigated using the EPR technique, and the EPR spectra of Yb³⁺ and U⁵⁺ were observed for the first time in potassium tantalate by employing crystals codoped with both impurities. Multiple doping of the material during the crystal growth process avoided the production of semiconducting KTaO₃ and resulted in the incorporation of adequate concentrations of the trivalent lanthanide ion Yb³⁺. An Yb³⁺ EPR spectrum was observed at 4.2 K. This spectrum exhibited tetragonal symmetry about the three <100> crystallographic axes. With the applied magnetic field parallel to a [100] axis, one of the three equivalent centers has $\theta = 0^\circ$. The other two centers both have $\theta = 90^\circ$, and therefore, their EPR spectra coincide. The EPR spectrum with the applied field *H* perpendicular to the principal axis of the axial Yb³⁺ site is shown in Fig. 6.11. The intense line from the *I* = 0 isotopes and the lines exhibiting hyperfine structure from the ¹⁷¹Yb (*I* = 1/2, 14% natural abundance) and ¹⁷³Yb (*I* = 5/2, 16% natural abundance) isotopes are evident. The EPR results indicate that Yb³⁺ occupies a site in which the local symmetry is axial as a result of nearby charge compensation.

For uranium-doped KTaO₃ crystals, a line was observed at both 77 and 4.2 K with an isotropic *g* value of 0.616(2). The line had a full width at half maximum of 75 gauss at 4.2 K when the magnetic field was parallel to a [100] axis, and there was some indication of superhyperfine structure. The results show that U⁵⁺, an ion that is isovalent with Ta in KTaO₃, is located

Fig. 6.11. EPR spectrum of KTaO₃ doped with Yb³⁺ at an applied magnetic field angle of $\theta = 90^\circ$ relative to the [100] axis. The hyperfine structure is indicated by the bar diagram below the experimental trace. No superhyperfine structure is in evidence.

in a site of cubic symmetry. New EPR results were also obtained for Cu²⁺ in KTaO₃, and EPR spectroscopy was used in a reexamination of KTaO₃ doped with Co²⁺, Mn²⁺, and Ni³⁺.

1. Summary of paper: Journal of Chemical Physics (in press).

2. St. Olaf College, Northfield, Minn.

3. IBM Zurich Research Laboratory, Rüschlikon, Switzerland.

CRITICAL QUASIELASTIC LIGHT SCATTERING IN $\text{KTa}_{0.96}\text{Nb}_{0.04}\text{O}_3$ ¹

E. Lee² L. L. Chase²
L. A. Boatner

The dynamical behavior of crystalline solids near second-order phase transitions has been a subject of great interest for well over a decade. A striking experimental manifestation of this behavior is the occurrence of central peaks (CP) that reflect relaxational responses of the media, distinct from the coexisting, damped periodic responses inherent in the soft phonon or magnon modes. In the case of nominally displacive structural transitions, the coupling between the soft phonon mode and the CP fluctuations leads to a saturation of the soft mode frequency at a nonzero value near T_c , and the dynamical features of the transition become dominated by the fluctuation processes which produce the CP. Both intrinsic and impurity or defect-induced mechanisms involving coupling to the order parameter of the transition have been proposed in order to account for these quasielastic peaks. Mixed-crystal systems which undergo phase transitions provide an excellent opportunity to examine the influence of impurities on critical phenomena over a very wide range of concentrations. A particularly interesting material for experimental work in this area is the cubic perovskite KTaO_3 , which is an incipient ferroelectric. The substitutions of Nb for Ta (KTN) and of Na or Li for K lead to ferroelectric phase transitions.

Intense quasielastic light scattering has been observed in KTN at temperatures near the ferroelectric transition at $T_c \approx 40$ K. The CP has a non-Lorentzian shape and consists of a sharp component with a broad tail. Near T_c , the sharp component narrows to 1.5 GHz (FWHM), which is close to the limit of resolution achievable when using an I_2 filter to eliminate elastically scattered light. It is, therefore, possible that the CP has a much narrower distribution than that of the renormalized Fabry-Perot data. Spectra obtained over a range of frequency shifts, including the Raman scattering from the soft TO mode, have been fitted by a coupled-mode formalism in which it is assumed that the CP derives all of its intensity from the coupling to the TO phonon. This model accounts reasonably well for the relative intensities of the CP and phonon and the large renormalized frequency of the phonons near T_c . The integrated intensity of the CP has a temperature dependence which is singular at T_c , whereas that of the TO phonon is close to a step function increase at T_c . Although ordinary two-phonon difference scattering cannot be excluded as a possible origin of the observed quasielastic scattering, several properties of the quasielastic and Raman spectra, as well as other recent experimental results, suggest a mechanism involving fluctuations due to the disorder in the polarizabilities and force constants introduced by the Nb substitution.

The CP spectra observed for KTN provide the first evidence that at least a substantial part

of the fluctuation spectrum is distributed over a broad range of frequencies. This is difficult to reconcile with a model of a small number of isolated impurities or defects which are coupled strongly to the order parameter. It seems more likely that the disorder in the unit cell polarizabilities resulting from the random distribution of Nb ions causes polarization fluctuations having a range of relaxation times due to the varying sizes and configurations of the polarized regions. Qualitative ideas of this type have been proposed previously by several authors.

1. Summary of paper to be published.
2. Indiana University, Bloomington, Ind.

THERMOLUMINESCENCE OF ALKALINE EARTH OXIDES X IRRADIATED AT LOW TEMPERATURES¹

V. M. Orera² V. D. Rodriguez²
R. Alcalá² Y. Chen

Thermoluminescence measurements have been performed on both MgO and CaO single crystals, as well as on single crystals of each material doped with Li, all of which were X irradiated at 80 K. The results obtained are summarized below.

In pure MgO, four glow peaks, observed at 175, 220, 245, and 265 K, are associated with the release of holes from different traps. All these glow peaks show two emission bands at 375 and 700 nm (the latter due to Cr^{3+} ions), while a band at 245 nm is found only in the 175 K peak. In MgO:Li, five glow peaks appear at 120, 135, 150, 165, and 220 K, all of which are due to the recombination of holes with electron centers. The peak at 220 K is correlated with the thermal destruction of $[\text{Li}]^0$ centers. Two emission bands, observed at 430 and 700 nm, are detected in all of the glow peaks.

In pure CaO, five glow peaks at 105, 130, 175, 205, and 275 K are associated with the thermal release of holes from different traps. All these peaks show a main emission band at 610 nm, which coincides with the main band observed in the x-ray-induced emission spectra. A band at 260 nm is observed only in a glow peak at 190 K and is tentatively assigned to the release of electrons with subsequent recombination with V-type centers. In CaO:Li, besides the emission bands at 260 and 610 nm, a new band at 330 nm is observed. Two glow peaks at 130 and 200 K, which show emission bands at 330 and 610 nm, are associated with the release of holes. The peak at 220 K is due to the thermal annihilation of $[\text{Li}]^0$ centers.

Activation energies for thermal ionization of the traps related to the main glow peaks have been determined for all four systems.

1. Summary of papers: *Phys. Status Solidi A* **75**, 577 (1983); *Phys. Status Solidi A* **77**, 625 (1983).
2. Universidad de Zaragoza, Zaragoza, Spain.

OPTICAL PROPERTIES AND INFRARED-STIMULATED LUMINESCENCE FROM OXYGEN VACANCIES IN CaO CRYSTALS CONTAINING HYDROGEN¹

R. Gonzalez² G. P. Summers³
Y. Chen K. Chakrabarti³

Optical absorption measurements show that substitutional H⁺ ions, that is, protons with two electrons on anion sites, are thermally more stable than anion vacancies when thermochemically reduced CaO crystals are annealed in a reducing atmosphere. The H⁺ ions are identified by the infrared vibrational modes observed at 880 and 911 cm⁻¹. Electron irradiation decreases the concentration of H⁺ ions and increases the concentration of oxygen vacancies with a cross section much larger than for elastic collision damage. This effect is characteristic of the same radiation-induced diffusion process which involves the displacement of protons in the H⁺ configuration and their relocation elsewhere in the crystal. The room temperature lifetime of the 2.1-eV anion-vacancy luminescence decreases when the concentration ratio of the vacancies to H⁺ ions increases. The 2.1-eV luminescence has been produced using low-energy and low-intensity photons ($E < 2.4$ eV) (i.e., less than the energy of the main anion vacancy absorption). Thermoluminescence measurements indicate that electrons trapped at substitutional H²⁺ ions are involved in the energy transfer leading to the luminescence.

1. Summary of paper: *Phys. Rev. B* 29, 5878 (1984).
2. Universidad Complutense, Madrid, Spain.
3. Oklahoma State University, Stillwater, Okla.

LUMINESCENCE FROM OXYGEN VACANCIES IN MgO CRYSTALS THERMOCHEMICALLY REDUCED AT HIGH TEMPERATURES¹

G. P. Summers² T. M. Wilson²
B. T. Jeffries² H. T. Tohver³
Y. Chen M. M. Abraham

Experimental measurements and theoretical calculations, which may resolve some of the remaining difficulties associated with photoemission from anion vacancies in thermochemically reduced MgO crystals, have been performed. The intensities of the 2.3- and 3.2-eV luminescence bands are found to be strongly influenced by both the concentrations of H⁺ ions and anion vacancies present and also by the intensity of the ~5.0-eV exciting light. Theoretical calculations predict that for a ¹A_{1g} relaxation of the surrounding ions, the ¹T_{1u} and ³T_{1u} electronic states of the F center are almost degenerate and ~0.05 eV above the ³A_{1g} state. The ¹T_{1u} + ¹A_{1g} and the ³T_{1u} + ¹A_{1g} transition energies are predicted to be 2.2 and 2.9 eV.

1. Summary of paper: *Phys. Rev. B*, 27, 1283 (1983).

2. Oklahoma State University, Stillwater, Okla.

3. University of Alabama-Birmingham, Birmingham, Ala.

THE EFFECT OF IONIZING RADIATION ON NICKEL-DOPED MgO¹

J. L. Boldu O.² E. Munoz P.²
K. L. Tsang³ M. M. Abraham
Y. Chen

The recent demonstration⁴ that Ni-doped magnesium oxide (MgO:Ni) crystals can be used as a versatile and commercially viable laser material, which is tunable in the infrared region, has provided the impetus for characterizing these crystals. The purpose of the present study is to investigate point defects in the MgO:Ni system using electrons and holes generated by ionizing radiation as probes to explore paramagnetic species of ions and vacancies. The ionizing radiation was provided by ⁶⁰Co γ rays with a dose of 1.0×10^6 R, which is too low to produce displacements of ions. Therefore, only impurity valence changes and trapping of electrons or holes at existing vacancies can occur.

The MgO:Ni crystals were grown at Oak Ridge National Laboratory by an arc-fusion technique. The nickel content of the crystals used in this study was much lower than that of the crystals used earlier.⁴ Due to the low oscillator strength of Ni²⁺ ions, the crystals were clear with only a faint hint of green coloration. The inherent impurities in crystals grown from Kanto powders are typically Al (10 ppm), Ca (40 ppm), Fe (5 ppm), Si (15 ppm), and P (10 ppm). Mn, V, and Cr are almost always present but are generally <1 ppm.

Four techniques were used in the present investigation: (1) EPR was used to probe impurities or defects with unpaired electrons; (2) electron-nuclear double resonance probed the neighborhood of the paramagnetic defects for impurities with nonzero spins ($I \neq 0$); (3) optical absorption measurements permitted the determination of optical-transition energies with their associated oscillator strengths; and (4) thermoluminescence (TL) provided an estimate of the activation energy associated with carrier release from defects.

Prior to the irradiation, the most pronounced EPR signal was Ni²⁺, with a concentration of $\sim 10^{18}$ cm⁻³. No Ni³⁺ was detected. The Fe³⁺ concentration was $\sim 10^{16}$ cm⁻³. All other paramagnetic impurities had concentrations $< 10^{15}$ cm⁻³. After γ irradiation, Ni³⁺ emerged, but its concentration was only a small fraction of that of Ni²⁺. The Fe³⁺ concentration decreased slightly, presumably due to conversion to Fe²⁺. The change in concentration of Cr³⁺, Mn²⁺, and V²⁺ (all $\sim 10^{14}$ cm⁻³) was minimal. The effects of the γ irradiation can be eradicated by thermal annealing. Isochronal anneals of 10 min each were performed. The growth and decay of Ni²⁺, Ni³⁺, Fe³⁺, Cr³⁺, Mn²⁺, V²⁺, and V⁻ defects are shown in Fig. 6.12. All these impurities are in cubic symmetry sites. (Lower symmetry sites were not detected.) There were very little changes in

ORNL-DWG 84-15828

Fig. 6.12. Thermal annealing of defects and impurities in a γ -irradiated MgO:Ni crystal.

the concentrations of Ni^{2+} , Fe^{2+} , Cr^{2+} , Mn^{2+} , and V^{2+} during the annealing. The most obvious change was for Ni^{3+} and the V^- defect. The latter began to decay at temperatures slightly higher than 300 K. This indicates that the holes from the V^- were thermally released, leaving behind the diamagnetic V^{2-} linear configuration: $\text{O}^{2-}-[\text{Mg vacancy}]-\text{O}^{2-}$. By 400 K, the V^- was depleted. At 420 K, the Ni^{3+} concentration diminished rapidly and was attended by a rejuvenation of the V^- . This indicates that the holes from the Ni^{3+} were thermally released and were captured by the V^{2-} to form V^- defects:

Obviously, the release of holes from Ni^{3+} was so copious that the V^- could retain a sizable fraction of the holes, even while decaying. After annealing at $T \sim 500$ K, the concentration of the various species returned to that prior to the irradiation.

EPR results established that substitutional nickel impurities are normally present as Ni^{2+} ions with local cubic symmetry. With a short ionizing radiation, a small fraction of the Ni^{2+} was transformed into Ni^{3+} via hole capture. Three optical absorption peaks were observed at 2.6, 3.8, and 5.0 eV and are tentatively attributed to optical transitions of Ni^{3+} ions. Presumably, the electrons are captured by Fe^{3+} and/or Cr^{3+} to form their divalent species. Also present in the crystal before irradiation is a magnesium vacancy, which is probably charge compensated by an aliovalent ion at a site not far from but beyond the next nearest neighbor. After irradiation, this defect becomes paramagnetic by hole capture, forming an anomalous V^- center.⁵ A TL peak observed at 367 K has been assigned to the release of holes from the anomalous V^- defect, and another observed at 528 K has been assigned to the release of holes from the Ni^{3+} ion.

1. Summary of Paper: p. 141 in *Defect Properties and Processing of High-Technology Non-metallic Materials*, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, Elsevier Science Publishers, Inc., New York, 1984.

2. Universidad Nacional Autonoma de Mexico, Mexico, D.F.

3. Graduate laboratory participant from the University of Alabama-Birmingham, Birmingham, Ala.

4. P. F. Moulton et al., *Bull. Am. Ceram. Soc.* 59, 350 (1980).

5. J. L. Boldú et al., *Phys. Rev. B* 29, 6365 (1984).

PUBLICATIONS AND PAPERS

JOURNAL ARTICLES

- M. M. Abraham, L. A. Boatner, W. H. Christie, F. A. Modine, T. Negas, R. M. Bunch, and W. P. Unruh, "Electrolytic Coloration and Electrical Breakdown of MgO Single Crystals," J. Solid State Chem. **51**, 1 (1984).
- M. M. Abraham, L. A. Boatner, D. N. Olson, and U. T. Hochli, "EPR Studies of Some f^n and d^n Electronic Impurities in KTaO_3 Single Crystals," J. Chem. Phys. **81**, 2528 (1984).
- W. W. Adams, E. L. Thomas, and J. S. Lin, "SAXS Invariant Analysis of Solid State Extruded Polyethylene," Polymer Preprints **24**, 372 (1983).
- R. Al-Jishi, G. Dresselhaus, P. C. Eklund, V. Yeh, H. G. Smith, and R. M. Nicklow, "Inelastic Neutron Scattering from Low-Frequency $00q$ Longitudinal Lattice Modes in Graphite- SbCl_5 Intercalation Compounds," Phys. Rev. B **29**, 2138 (1984).
- B. R. Appleton, H. Naramoto, C. W. White, O. W. Holland, C. J. McHargue, G. Farlow, J. Narayan, and J. M. Williams, "Ion Implantation, Ion Beam Mixing, and Annealing Studies of Metals in Al_2O_3 , SiC , and Si_3N_4 ," Nucl. Instrum. Methods in Phys. Research B1, 167 (1984).
- B. R. Appleton, J. Narayan, C. W. White, J. S. Williams, and K. T. Short, "Coherent Precipitate Formation in Ti-Implanted Si," Nucl. Instrum. Methods **209/210**, 239 (1983).
- R. J. Arsenault, D. M. Esterling, R. M. Nicklow, and Mark Mostoller, "Lattice Dynamics of a Molybdenum-Ruthenium Alloy," J. Phys. F **14**, 1619 (1984).
- D. K. Atwood, M. A. Home, C. G. Shull, and J. Arthur, "Neutron Phase Shift in a Rotating Two-Crystal Interferometer," Phys. Rev. Lett. **52**, 1673 (1984); Errata, Phys. Rev. Lett. **53**, 1300 (1984).
- M. J. Aziz, "Dissipation-Theory Treatment of the Transition from Diffusion-Controlled to Diffusionless Solidification," Appl. Phys. Lett. **43**, 552 (1983).
- C. Ballesteros, J. Llopis, R. Gonzalez, and Y. Chen, "Impurities-Induced Cathodoluminescence in Undoped Spinel," Solid State Commun. **51**, 37 (1984).
- John H. Barrett, "Ion Dechanneling Due to Lattice Strains in Semiconductor Superlattices," Phys. Rev. B **28**, 2328 (1983).
- F. S. Bates, C. V. Berney, R. E. Cohen, and G. D. Wignall, "Single-Chain Scattering in Heterogeneous Block Copolymers," Polymer **24**, 519 (1983).
- J. B. Bates, J. C. Wang, and N. J. Dudney, "Local Field and Infrared Absorption Intensities of H_2O in Hydrated β -Alumina," J. Chem. Phys. **80**, 173 (1984).
- J. B. Bates, J. C. Wang, N. J. Dudney, and W. E. Brundage, "Hydration of β -Alumina," Solid State Ionics **9/10**, 237 (1983).
- D. Bendedouch, S.-H. Chen, and W. C. Koehler, "Determination of Interparticle Structure Factors in Ionic Micellar Solutions by Small-Angle Neutron Scattering," J. Phys. Chem. **87**, 2621 (1983).
- F. E. Bertrand, J. R. Beene, and T. P. Sjoreen, "Heavy Ion Excitation and Photon Decay of Giant Resonances," J. Phys. (Paris) **45**, C4-99 (1984).
- M. Blecher, K. Gotow, R. L. Burman, M. V. Hynes, M. J. Leitch, N. S. Chant, L. Rees, P. G. Roos, F. E. Bertrand, E. E. Gross, F. E. Obenshain, T. P. Sjoreen, G. S. Blanpied, B. M. Freedom, and R. G. Ritchie, "Isospin Effects in π^2 Elastic Scattering from ^{12}C , ^{13}C , and ^{14}C at 65 and 80 MeV," Phys. Rev. C **28**, 2033 (1983).

- L. A. Boatner, "Growing Single Crystals of Refractory Materials," ORNL Review 16, 120 (1983).
- L. A. Boatner, M. M. Abraham, and B. C. Sales, "Lanthanide Orthophosphate Ceramics for the Disposal of Actinide-Contaminated Nuclear Wastes," Inorg. Chim. Acta 94, 146 (1983).
- J. L. Boldú O., E. Muñoz P., Y. Chen, and M. M. Abraham, "An Anomalous Perturbed Magnesium Vacancy in Nickel-Doped MgO," Phys. Rev. B 29, 6365 (1984).
- J. L. Boldú, E. Muñoz P., Y. Chen, and M. M. Abraham, "EPR Powder Pattern Analysis for Cubic Sites of Fe^{3+} in MgO," J. Chem. Phys. 80, 574 (1984).
- J. W. Cable, J. R. Thompson, and S. T. Sekula, "Magnetic Moment Distribution in FeNiV and FeCoV Alloys," J. Magn. Magn. Mater. 40, 147 (1983).
- J. W. Cable, S. A. Werner, G. P. Felcher, and N. Wakabayashi, "Neutron Polarization Analysis Study of the Spin Structure of Cu-Mn Spin Glasses," Phys. Rev. B 29, 1268 (1984).
- S.-J. Chang and S. M. Ohr, "Inclined Pileup of Screw Dislocations at the Crack Tip Without a Dislocation-Free Zone," J. Appl. Phys. 55, 3505 (1984).
- Y. K. Chang, "The Float-Zone Growth of Ti_3Au and Ti_3Pt ," J. Cryst. Growth 62, 627 (1983).
- Y. Chen, R. Gonzalez, O. E. Schow, and G. P. Summers, "Charge and Mass Transfer Involving Hydrogen in MgO Reduced at High Temperatures," Phys. Rev. B 27, 1276 (1983).
- Y. Chen, R. Gonzalez, and K. L. Tsang, "Diffusion of Deuterium and Hydrogen in Rutile TiO_2 Crystals at Low Temperatures," Phys. Rev. Lett. 53, 1077 (1984).
- D. K. Christen, H. R. Kerchner, J. Narayan, Y. K. Chang, B. C. Larson, and S. T. Sekula, "Experimental Characterization of the Flux-Line Lattice in Superconducting V_3Si ," IEEE Trans. Magn. MAG-19, 884 (1983).
- Y. T. Chu, V. E. Anderson, H. H. Hubbell, Jr., and T. L. Ferrell, "Asymptotic Solution for the Diffraction of an Electromagnetic Plane Wave by a Cylinder-Tipped Half-Plane," J. Opt. Soc. Am. 73, 768 (1983).
- Y. T. Chu, R. J. Warmack, R. H. Ritchie, J. W. Little, R. S. Becker, and T. L. Ferrell, "Contribution of the Surface Plasmon to Energy Losses by Electrons in a Cylindrical Channel," Particle Accelerators 16, 13 (1984).
- G. J. Clark, A. D. Marwick, and D. B. Poker, "Ion-Beam Mixing in Silicon and Germanium at Low Temperatures," Nucl. Instrum. Methods 209/210, 107 (1983).
- R. R. Colman, Jr., C. E. Klabunde, and F. W. Young, Jr., "A National Low-Temperature Neutron Irradiation Facility," J. Nucl. Mater. 122/123, 1357 (1984).
- T. B. Cook, P. W. King, and J. B. Roberto, "Measurement of the Ionization Length for Neutral Iron near the Wall in the ISX-B Tokamak Using Laser-Induced Fluorescence," J. Vac. Sci. Technol. A 2, 707 (1984).
- Mario Corti, Vittorio Degiorgio, John B. Hayter, and Martin Zulauf, "Micelle Structure in Isotropic C_{12}E_8 Amphiphile Solutions," Chem. Phys. Lett. 109, 579 (1984).
- B. Crist, W. W. Graessley, and G. D. Wignall, "Response to 'Comments on Crist et al.'s Paper on Chain Dimensions of Crystallizable Polymer, An Alternative Interpretation of the Experimental Data,'" Polymer Commun. 25, 136 (1984).
- R. J. Culbertson, S. P. Withrow, and J. H. Barrett, "Potential and Stopping Power Information from Ion Channeling in Ge," Nucl. Instrum. Methods in Phys. Research 230 (B2), 19 (1984).
- L. S. Darken, "High Resolution Photothermal Ionization Spectroscopy of Lithium-Related Shallow Donors in Germanium," Phys. Rev. B 27, 6564 (1983).
- L. S. Darken, "Mechanism for the Graphoepitaxy of Electrodeposited Tin," J. Electrochem. Soc. 130, 1274 (1983).
- L. S. Darken and S. A. Hyder, "Photoconductive Response of Compensating Impurities in Photothermal Ionization Spectroscopy of High-Purity Silicon and Germanium," Appl. Phys. Lett. 42, 731 (1983).
- H. L. Davis and J. R. Noonan, "Equivalent Beam Averaging (EBA) of I-V Spectra for LEED Analysis," Physica Scripta T4, 141 (1983).

- H. L. Davis and J. R. Noonan, "Multilayer Relaxation in Metallic Surfaces as Demonstrated by LEED Analysis," Surf. Sci. **126**, 245 (1983).
- C. R. Desper, M. S. Schneider, and J. S. Lin, "Deformation of Microphase Structures in Polyurethanes," Polymer Preprints **24**, 396 (1983).
- R. A. DiDio, D. M. Zehner, and E. W. Plummer, "An Angle-Resolved UPS Study of the Oxygen-Induced Reconstruction of Cu(110)," J. Vac. Sci. Technol. A **2**, 852 (1984).
- G. S. Dixon and R. M. Nicklow, "Low-Frequency Lattice Vibrations of LaF_3 by Neutron Scattering," Solid State Commun. **47**, 877 (1983).
- Mark I. Donnelly, Fred C. Hartman, and V. Ramakrishnan, "The Shape of Ribulose Bisphosphate Carboxylase/Oxygenase in Solution as Inferred from Small-Angle Neutron Scattering," J. Biol. Chem. **259**, 406 (1984).
- N. J. Dudley, J. B. Bates, and W. E. Brundage, "Raman Measurements of the Mobile Cation Vibrations in Na, K, Ag, and Li β -Alumina," Solid State Ionics **9/10**, 207 (1983).
- S. Dutta, H. E. Jackson, J. T. Boyd, and C. W. White, "Rutherford Backscattering Evidence for Solid Phase Laser Annealing of Corning 759 Glass and ZnO Thin Films," J. Appl. Phys. **54**, 2125 (1983).
- J. E. Epperson, B. A. Loomis, G. H. Lander, S. R. Gerber, R. W. Hendricks, J. S. Lin, and M. B. Lewis, "A Small-Angle X-ray Scattering Study of Voids Formed in Oxygen-Doped Niobium Due to $^{58}\text{Ni}^{+}$ Bombardment," J. Nucl. Mater. **119**, 251 (1983).
- G. Farlow, A. Blose, Sister J. Feldott, R. Lounsberry, and L. M. Slifkin, "Studies of the Near-Surface Ionic Space Charge in Silver Halide Crystals," Radiat. Eff. **75**, 1 (1983).
- M. Fatemi, C. S. Pande, and H. R. Child, "Detection of Several ω Phase Morphologies in α -III Ti by Small-Angle Neutron Scattering and Transmission Electron Microscopy," Philos. Mag. A **48**, 479 (1983).
- D. Fathy, J. Narayan, O. W. Holland, B. R. Appleton, and R. F. Davis, "Microstructure Analysis of Ni-SiC Mixed Layers," Mater. Lett. **2**, 324 (1984).
- C.-L. Fu, K.-M. Ho, B. N. Harmon, and S. H. Liu, "Renormalization of the H-Point Phonon Anomaly in Molybdenum," Phys. Rev. B **28**, 2957 (1983).
- R. Gonzalez, M. M. Abraham, L. A. Boatner, and Y. Chen, "The Correlation of Hydrogen Diffusion with the Relative Intensities of Cubic and Axial Fe^{3+} Sites in KTaO_3 ," J. Chem. Phys. **78**, 660 (1983).
- R. Gonzalez, G. P. Summers, and Y. Chen, "Optical Properties of CaO Crystals Containing Hydrogen," Phys. Rev. B **30**, 2112 (1984).
- J. A. Gotaas, J. S. Kouvel, T. O. Brun, and J. W. Cable, "Quadrupolar Coupling and Structural Instability in $\text{PrAg}_{1-x}\text{Cu}_x$," J. Magn. Magn. Mater. **36**, 208 (1983).
- H. Hayashi, P. J. Flory, and G. D. Wignall, "Configuration of the Polyisobutylene Chain According to Neutron and X-ray Scattering," Polymer Preprints **24**, 234 (1983).
- J. B. Hayter, "Concentrated Colloidal Dispersions Viewed as One-Component Macrofluids," Faraday Disc. Chem. Soc. **76**, 7 (1983).
- J. B. Hayter and J. Penfold, "Determination of Micelle Structure and Charge by Neutron Small-Angle Scattering," Colloid Polymer Sci. **261**, 1022 (1983).
- J. B. Hayter and J. Penfold, "The Use of Viscous Shear Alignment to Study Anisotropic Micellar Structure by Small-Angle Neutron Scattering," J. Phys. Chem. **88**, 4589 (1984).
- J. S. Higgins, K. Ma, L. K. Nicholson, J. B. Hayter, K. Hodgson, and J. A. Semlyen, "Studies of Cyclic and Linear Poly(dimethylsiloxanes) 12: Observation of Diffusion Behavior by Quasielastic Neutron Scattering," Polymer **24**, 793 (1983).
- R. R. Highfield, R. P. Humes, R. K. Thomas, P. G. Cummins, D. P. Gregory, J. Mingins, J. B. Hayter, and O. Schärpf, "Critical Reflection of Neutrons from a Soap Film," J. Colloid Interface Sci. **97**, 367 (1984).
- R. R. Highfield, R. K. Thomas, P. G. Cummins, D. P. Gregory, J. Mingins, J. B. Hayter, and O. Schärpf, "Critical Reflection of Neutrons from Langmuir-Blodgett Films on Glass," Thin Solid Films **99**, 165 (1983).

- K.-M. Ho, C. L. Fu, S. H. Liu, D. M. Kolb, and G. Piazza, "Observation of Surface States at the Metal-Electrolyte Interface by Electreflectance Spectroscopy," J. Electroanal. Chem. **150**, 235 (1983).
- O. W. Holland, B. R. Appleton, and J. Narayan, "Ion Implantation Damage and Annealing in Germanium," J. Appl. Phys. **54**, 2295 (1983).
- O. W. Holland and J. Narayan, "Mechanism for Dynamic Annealing during High-Flux Ion Irradiation in Si," Appl. Phys. Lett. **44**, 758 (1984).
- D. J. Horen, F. E. Bertrand, E. E. Gross, T. P. Sjoreen, D. K. McDaniels, J. R. Tinsley, J. Lisantti, L. W. Swenson, J. F. McClelland, T. A. Carey, S. J. Seestrom-Morris, and K. Jones, "Excitation of E2 Transitions in ^{40}Ca by 334-MeV Protons," Phys. Rev. C **30**, 709 (1984).
- C.-K. Hu, H. B. Huntington, and G. R. Gruzalski, "Atom Motions of Copper Dissolved in Lead-Tin Alloys," Phys. Rev. B **28**, 579 (1983).
- G. F. Hurley and R. R. Coltman, Jr., "Organic Materials for Fusion Reactor Applications," J. Nucl. Mater. **122/123**, 1327 (1984).
- M. V. Hynes, J. L. C. Ford, Jr., T. P. Sjoreen, J. L. Blankenship, and F. E. Bertrand, "Design and Performance of a Vertical Drift Chamber for Heavy Ion Applications," Nucl. Instrum. Methods **224**, 89 (1984).
- D. P. Jackson and J. H. Barrett, "Approximation for the Surface Backscattering Yield from an Atomic Row with Correlated Thermal Vibrations," Nucl. Instrum. Methods in Phys. Research **230** (B2), 318 (1984).
- R. B. James, "Carrier Multiplication in Semiconductors Induced by High-Intensity Infrared Light," J. Appl. Phys. **54**, 3220 (1983).
- R. B. James and D. L. Smith, "Effect of Uniaxial Stress on the Saturation of Intervalence-Band Absorption in p-Type Ge," Phys. Rev. B **28**, 586 (1983).
- R. B. James and D. L. Smith, "Interaction of a Tunable Probe Beam with a High-Intensity Pulsed CO_2 Laser Beam in p-Type Germanium," Phys. Rev. B **29**, 2036 (1984).
- G. E. Jellison, Jr., D. H. Lowndes, and R. F. Wood, "Importance of Temperature-Dependent Optical Properties for Raman-Temperature Measurements for Silicon," Phys. Rev. B **28**, 3272 (1983).
- G. E. Jellison, Jr., and F. A. Modine, "Optical Functions of Silicon Between 1.7 and 4.7 eV at Elevated Temperatures," Phys. Rev. B **27**, 7466 (1983).
- L. M. Kahn, F. Perrot, and M. Rasolt, "Electric Field Gradient of Single Impurities in Aluminum," Phys. Rev. B **27**, 5110 (1983).
- W. A. Kamitakahara, L. E. DeLong, J. C. Eklund, and R. M. Nicklow, "Intercalant Ordering and Lattice Dynamics in Stage-1 KHgCl_2 ," Phys. Rev. B **29**, 460 (1984).
- Theodore Kaplan and L. J. Gray, "A Self-Consistent Approximation for Muffin-Tin Models of Random Substitutional Alloys with Environmental Disorder," Phys. Rev. B **29**, 3684 (1984).
- S. Kawarazaki, N. Kunitomi, R. M. Moon, R. M. Nicklow, and H. Suzuki, "Observation of the Magnetic Phase Transition in PrCu_2 below 58 mK by Neutron Diffraction," Solid State Commun. **49**, 1153 (1984).
- S. Kawarazaki, N. Kunitomi, Y. Morii, H. Suzuki, R. M. Moon, and R. M. Nicklow, "Neutron Diffraction Study on the Hyperfine-Induced Nuclear Spin Order in the Antiferromagnet PrSn_3 ," Solid State Commun. **49**, 1147 (1984).
- H. R. Kerchner, D. K. Christen, C. E. Klabunde, S. T. Sekula, and R. R. Coltman, Jr., "Low-Temperature-Irradiation Study of Flux-Line Pinning in Type-II Superconductors," Phys. Rev. B **27**, 5467 (1983).
- H. R. Kerchner, S. T. Sekula, and J. R. Thompson, "Errors Due to Field Nonuniformity in Vibrating Sample Magnetometry," Rev. Sci. Instrum. **55**, 533 (1984).
- John S. King, William Boyer, George D. Wignall, and Robert Ullman, "Measurement of Polymer Solutions by High Concentration Labeling," Polymer Preprints **24**, 218 (1983).
- C. E. Klabunde and R. R. Coltman, Jr., "Debonding of Epoxy from Glass in Irradiated Laminates," J. Nucl. Mater. **117**, 345 (1983).

- S. Kobayashi and S. M. Ohr, "Dislocation Arrangement in the Plastic Zone of Propagating Cracks in Nickel," J. Mater. Sci. **19**, 2273 (1984).
- W. C. Koehler, "Neutron Scattering in Magnetic Fields," Revue de Physique Appliquée **19**, 691 (1984).
- W. C. Koehler, "The Magnetic Structures of the Rare Earth Metals—An Historical Survey," J. Less-Common Metals **93**, 15 (1983).
- W. C. Koehler, "The Rare Earths in Modern Science and Technology," Cryst. Latt. Def. and Amorph. Mat. **10**, 123 (1983) (Book Review).
- B. C. Larson, C. W. White, T. S. Noggle, J. F. Barhorst, and D. M. Mills, "Time-Resolved X-ray Diffraction Measurement of the Temperature and Temperature Gradients in Silicon during Pulsed-Laser Annealing," Appl. Phys. Lett. **42**, 282 (1983).
- E. M. Lawson, K. T. Short, J. S. Williams, B. R. Appleton, O. W. Holland, and O. E. Schow III, "Anomalous Near-Surface Effects in Room Temperature Implanted Germanium," Nucl. Instrum. Methods **209/210**, 303 (1983).
- S. H. Liu, "Microscopically Inhomogeneous Nature of Stern Layer," J. Electroanal. Chem. **150**, 305 (1983).
- S. H. Liu and K.-M. Ho, "Effects of d-f Correlation on the Mixed-Valent Properties of Ce Systems," Phys. Rev. B **28**, 4220 (1983).
- S. H. Liu and K.-M. Ho, "Effects of d-f Correlation on the Mixed-Valent Properties of Cerium Systems: The f Band Problem," Phys. Rev. B **30**, 3039 (1984).
- C.-K. Loong, C. Stassis, J. Zarestky, O. D. McMasters, and R. M. Moon, "Temperature Dependence of the Field-Induced Magnetic Form Factor of the Intermetallic Compound PrSn_3 ," J. Appl. Phys. **55**, 1838 (1983).
- D. H. Lowndes, R. F. Wood, and J. Narayan, "Pulsed-Laser Melting of Amorphous Silicon: Time-Resolved Measurements and Model Calculations," Phys. Rev. Lett. **52**, 561 (1984).
- D. H. Lowndes, R. F. Wood, and R. D. Westbrook, "Pulsed Neodymium: Yttrium Aluminum Garnet Laser (532 nm) Melting of Crystalline Silicon: Experiment and Theory," Appl. Phys. Lett. **43**, 258 (1983).
- J. H. Magill, J. M. Schultz, and J. S. Lin, "Dynamic SAXS Crystallization Studies of Polymers," Polymer Preprints **24**, 231 (1983).
- R. Magruder, D. L. Kinser, and R. A. Weeks, "The Effect of Gamma Radiation on the DC Resistivity of GeO_2 ," J. Am. Ceram. Soc. **66**, C62 (1983).
- W. O. Milligan, D. F. Mullica, H. O. Perkins, G. W. Beall, and L. A. Boatner, "Crystal Data for Lanthanide Orthophosphates with the Zircon-Type Structure," Inorg. Chim. Acta **77**, 123 (1983).
- D. M. Mills, B. C. Larson, C. W. White, and T. S. Noggle, "Nanosecond Resolved X-ray Diffraction during Pulsed-Laser Annealing of Silicon," Nucl. Instrum. Methods **208**, 511 (1983).
- F. A. Modine, G. E. Jellison, Jr., and G. R. Gruzalski, "Errors in Ellipsometry Measurements Made with a Photoelastic Modulator," J. Opt. Soc. Am. **73**, 892 (1983).
- F. A. Modine, R. W. Major, T. M. Haywood, G. R. Gruzalski, and D. r. Smith, "Optical Properties of Tantalum Carbide from the Infrared to the Near Ultraviolet," Phys. Rev. B **29**, 836 (1984).
- H. A. Mook, "Density Dependence of the Momentum Distribution for ^4He ," Phys. Rev. Lett. **51**, 1454 (1983).
- H. A. Mook and J. W. Lynn, "Magnetic Excitations in Amorphous Isotropic Ferromagnets," Phys. Rev. B **29**, 4056 (1984).
- H. A. Mook, O. A. Pringle, S. Kawarazaki, S. K. Sinha, G. W. Crabtree, D. G. Hinks, M. B. Maple, Z. Fisk, D. C. Johnston, L. D. Woolf, and H. C. Hamaker, "Superconductivity and Magnetism in Ternary Rare-Earth Compounds," Physica **120B**, 197 (1983).
- R. M. Moon, S. H. Liu, and K. Werner, "Induced Magnetic Form Factor of the Mixed Valence Material $\text{Sm}_{0.76}\text{N}_{0.24}\text{S}$," J. Magn. Magn. Mater. **31-34**, 387 (1983).

- D. F. Mullica, W. O. Milligan, David A. Grossie, G. W. Beall, and L. A. Boatner, "Ninefold Coordination in LaPO_4 : Pentagonal Interpenetrating Tetrahedral Polyhedron," Inorg. Chim. Acta **95**, 231 (1984).
- H. Naramoto, C. J. McHargue, C. W. White, J. M. Williams, O. W. Holland, M. M. Abraham, and B. R. Appleton, "Near-Surface Modification of $\alpha\text{-Al}_2\text{O}_3$ by Ion Implantation Followed by Thermal Annealing," Nucl. Instrum. Methods **201/202**, 1159 (1983).
- J. Narayan, "Nature of Unseeded Crystallization in Semiconductors," Mater. Lett. **2**, 219 (1984).
- J. Narayan and Y. Chen, "Physical Properties of Oxides Containing Metal Precipitates—Part II," Philos. Mag. A **49**, 475 (1984).
- J. Narayan, Y. Chen, R. M. Moon, and R. W. Carpenter, "Characterization of Metal Precipitates in Magnesium Oxide—Part I," Philos. Mag. A **49**, 287 (1984).
- J. Narayan, D. Fathy, O. W. Holland, B. R. Appleton, R. F. Davis, and P. F. Becher, "Ion Beam and Laser Mixing of Nickel Overlayers on Silicon Carbide," J. Appl. Phys. **56**, 1577 (1984).
- J. Narayan, D. Fathy, O. S. Oen, and O. W. Holland, "High-Resolution Imaging of Ion Implantation Damage and Mechanism of Amorphization in Semiconductors," Mater. Lett. **2**, 211 (1984).
- J. Narayan and O. W. Holland, "Characteristics of Ion Implantation Damage and Annealing Phenomena in Semiconductors," J. Electrochem. Soc. **131**, 2651 (1984).
- J. Narayan, O. W. Holland, and B. R. Appleton, "Solid-Phase-Epitaxial Growth and Formation of Metastable Alloys in Ion-Implanted Silicon," J. Vac. Sci. Technol. B **7**, 871 (1983).
- J. Narayan, O. W. Holland, R. E. Eby, J. J. Wortman, V. Ozguz, and G. A. Rozgonyi, "Rapid Thermal Annealing of Arsenic- and Boron-Implanted Silicon," Appl. Phys. Lett. **43**, 957 (1983).
- J. Narayan, O. W. Holland, C. W. White, and R. T. Young, "Excimer Laser Annealing of Ion-Implanted Silicon," J. Appl. Phys. **55**, 1125 (1984).
- J. Narayan and C. W. White, "Pulsed-Laser Melting of Amorphous Silicon Layers," Appl. Phys. Lett. **44**, 35 (1984).
- J. Narayan, C. W. White, O. W. Holland, and M. J. Aziz, "Phase Transformation and Impurity Redistribution during Laser Irradiation of Amorphous Silicon Layers," J. Appl. Phys. **56**, 1821 (1984).
- T. S. Noggle, B. R. Appleton, J. M. Williams, O. S. Oen, T. Iwata, and G. W. Vogl, "Depth Distribution of Self-Ion Damage and Comparison of Ion Damage Rates to Neutron Damage Rates for Aluminum," J. Nucl. Mater. **125**, 330 (1984).
- J. R. Noonan and H. L. Davis, "Truncation-Induced Multilayer Relaxation of the $\text{Al}(110)$ Surface," Phys. Rev. B **29**, 4349 (1984).
- Ordean S. Oen, "Universal Shadow Cone Expressions for an Atom in an Ion Beam," Surf. Sci. **131**, L407 (1983).
- J. M. O'Reilly, S. M. Melpolder, L. W. Fisher, G. D. Wignall, and V. R. Ramakrishnan, "Small-Angle Neutron Scattering of Polymer Core-Shell Latex Particles," Polymer Preprints **24**, 407 (1983).
- J. M. O'Reilly, R. S. Stein, G. Hadzioannou, and G. D. Wignall, "Effect of Vitrification Pressure on Radius of Gyration, Specific Heat, and Density of Amorphous Polymers," Polymer **24**, 1255 (1983).
- V. M. Orera, V. D. Rodriguez, R. Alcala, and Y. Chen, "Thermoluminescence of Low-Temperature X-Irradiated CaO and $\text{CaO}:\text{Li}$ Single Crystals," Phys. Status Solidi A **77**, 625 (1983).
- R. Pareja, R. Gonzalez, and Y. Chen, "Transmission Electron Microscope Studies of Crystalline LiNbO_3 ," J. Appl. Phys. **56**, 660 (1984).
- S. J. Pennycook, A. Howie, M. D. Shannon, and R. Whyman, "Characterization of Supported Catalysts by High Resolution STEM," J. Mol. Catalysis **20**, 345 (1983).
- S. J. Pennycook and D. McMullan, "A New High-Angle Annular Detector for STEM," Ultramicroscopy **11**, 315 (1983).
- S. J. Pennycook and J. Narayan, "Direct Imaging of Dopant Distributions in Silicon by STEM," Appl. Phys. Lett. **45**, 385 (1984).

- S. J. Pennycook, J. Narayan, and O. W. Holland, "Formation of Partially Coherent Antimony Precipitates in Ion-Implanted Thermally Annealed Silicon," J. Appl. Phys. 54, 6875 (1983).
- S. J. Pennycook, J. Narayan, and O. W. Holland, "Point Defect Trapping in Solid Phase Epitaxially Grown Silicon-Antimony Alloys," J. Appl. Phys. 55, 837 (1984).
- S. J. Pennycook, J. Narayan, and O. W. Holland, "Spatially Resolved Measurement of Substitutional Dopant Concentrations in Semiconductors," Appl. Phys. Lett. 44, 547 (1984).
- F. E. Pinkerton, A. J. Sievers, M. B. Maple, and B. C. Sales, "Far Infrared Absorption Measurements in Mixed Valence Compounds," Phys. Rev. B 29, 609 (1984).
- L. Pintschovius, H. G. Smith, N. Wakabayashi, W. Reichardt, W. Weber, G. W. Webb, and Z. Fisk, "Lattice Dynamics of the $Al_5 Nb_3 Sb$," Phys. Rev. B 28, 4866 (1983).
- D. B. Poker, "Release of Ion-Implanted and Transmutation-Produced Helium from Nickel," Radiat. Eff. 78, 101 (1983).
- D. B. Poker, G. G. Setser, A. V. Iranato, and H. K. Birnbaum, "Low-Temperature Ultrasonic Study of Trapped Hydrogen in Niobium," Phys. Rev. B 29, 622 (1984).
- P. P. Pronko, R. S. Bhattacharya, O. W. Holland, and B. R. Appleton, "Comment on 'Lattice Location of Chromium in Semi-Insulating GaAs by Ion Channeling Techniques,'" Appl. Phys. Lett. 44, 150 (1984).
- R. Pynn and J. B. Hayter, "A Theory of Correlations in a Magnetically Aligned Ferrofluid," J. Magn. Magn. Mater. 31-34, 955 (1983).
- R. Pynn, J. B. Hayter, and S. W. Charles, "Determination of Ferrofluid Structure by Neutron Polarization Analysis," Phys. Rev. Lett. 51, 710 (1983).
- Mark Rasolt, "Asymmetry in the Raman Cross Section from Large Temperature Variation," Phys. Rev. B 27, 6066 (1983).
- M. Rasolt, "Exact Identities for Multicomponent Nonuniform Fermi Systems," Phys. Rev. B 27, 5653 (1983).
- Mark Rasolt, "Structure Factor of a Correlated Nonuniform Fermion Gas at Small Wavelength," Phys. Rev. B 29, 3703 (1984).
- Mark Rasolt and A. B. J. Haymet, "Phase Transitions in a Third-Rank-Tensor Hamiltonian: Application to Systems with Tetrahedral Symmetry," Phys. Rev. B 30, 1619 (1984).
- Mark Rasolt and F. Perrot, "Pair Potentials on Metal Surfaces," Phys. Rev. B 28, 6749 (1983).
- Mark Rasolt, Michael J. Stephen, Michael E. Fisher, and Peter B. Weichman, "Critical Behavior of a Dilute Interacting Bose Fluid," Phys. Rev. Lett. 53, 798 (1984).
- R. M. Richardson, A. J. Leadbetter, J. B. Hayter, W. G. Stirling, G. W. Gray, and A. Tajbakhsh, "Dynamics of the Modulated Crystal Smectic B Phase of 50.7 by Neutron Scattering Experiments," J. Phys. (Paris) 45, 1061 (1984).
- J. B. Roberto, R. E. Clausing, E. Dullni, L. C. Emerson, L. Heatherly, B. Schweer, S. P. Withrow, and R. A. Zuhr, "Plasma Edge Studies in ISX-B and EBT-S Using Surface Probes and Laser-Induced Fluorescence," J. Vac. Sci. Technol. A 1, 929 (1983).
- Mark T. Robinson, "Computer Simulation of Collision Cascades in Monazite," Phys. Rev. B 27, 5347 (1983).
- Mark T. Robinson, "Computer Simulation of the Self-Sputtering of Uranium," J. Appl. Phys. 54, 2650 (1983).
- V. D. Rodriguez, V. M. Orera, Y. Chen, and R. Alcala, "Thermoluminescence of Low-Temperature X-Irradiated MgO and MgO:Li Single Crystals," Phys. Status Solidi A 75, 577 (1983).
- J. Roth, J. B. Roberto, and K. L. Wilson, "Enhanced Sputtering of Graphite at High Temperature," J. Nucl. Mater. 122/123, 1447 (1984).
- B. C. Sales and L. A. Boatner, "Lead-Iron Phosphate Glass: A Stable Medium for High-Level Nuclear Waste," Science 226, 45 (1984).

- B. C. Sales and L. A. Boatner, "Lead Phosphate Glass as a Stable Medium for the Immobilization and Disposal of High-Level Nuclear Waste," Mater. Lett. 2, 301 (1984).
- B. C. Sales and M. B. Maple, "Low-Frequency Electrical Resistance of Iron, Cobalt, and Nickel in the Vicinity of Their Curie Temperatures," Appl. Phys. A 31, 115 (1983).
- B. C. Sales, J. E. Turner, and M. B. Maple, "Oscillatory Oxidation of CO over Pt, Pd, and Ir Catalysts: Theory," Surf. Sci. 14, 381 (1982).
- B. C. Sales, C. W. White, G. M. Begun, and L. A. Boatner, "Surface Layer Formation on Corroded Nuclear Waste Glasses," J. Non-Cryst. Solids 67, 245 (1984).
- B. C. Sales, C. W. White, and L. A. Boatner, "Application of Ion Implantation and Backscattering Techniques to the Analysis of Nuclear Waste Glass Corrosion," Mater. Lett. 2, 1 (1983).
- B. C. Sales, C. W. White, and L. A. Boatner, "A Comparison of the Corrosion Characteristics of Synthetic Monazite and Borosilicate Glass Containing Simulated Nuclear Defense Waste," Nucl. Chem. Waste Management 4, 281 (1984).
- Dale W. Schaefer and J. S. Lin, "Do Scaling Laws Apply in Moderately Concentrated Polymer Solutions?" Macromol. 16, 1615 (1983).
- S. T. Sekula, J. R. Thompson, G. M. Beardsley, and D. H. Lowndes, "Low-Temperature Laser Quenching Studies of Superconducting Mo-N and Mo-C Alloys," J. Appl. Phys. 54, 6517 (1983).
- S. A. Shaheen, J. S. Schilling, and S. H. Liu, "Simple Scaling Behavior in the Magnetic Susceptibility of CeSn_3 under High Pressure," Phys. Rev. B 27, 4325 (1983).
- S. K. Sinha, G. W. Crabtree, D. G. Hinks, H. A. Mook, and D. A. Pringle, "Neutron Scattering Studies of Magnetic Superconductors," J. Magn. Magn. Mater. 31-34, 489 (1983).
- T. P. Sjoreen, F. E. Bertrand, R. L. Auble, E. E. Gross, D. J. Horen, D. Shapira, and D. B. Wright, "Inelastic Excitation of Giant Resonances by 400-MeV ^{16}O ," Phys. Rev. C 29, 1370 (1984).
- T. P. Sjoreen, J. L. C. Ford, Jr., J. L. Blankenship, R. L. Auble, F. E. Bertrand, E. E. Gross, D. C. Hensley, D. Schull, and M. V. Hynes, "The Vertical Drift Chamber as a High Resolution Focal Plane Detector for Heavy Ions," Nucl. Instrum. Methods 224, 421 (1984).
- H. G. Smith and G. H. Lander, "Neutron Scattering Investigation of α -Uranium in the Charge-Density-Wave State," Phys. Rev. B 30, 5407 (1984).
- E. Sonder, M. M. Austin, and D. L. Kinser, "Effect of Oxidizing and Reducing Atmospheres at Elevated Temperatures on the Electrical Properties of Zinc Oxide Varistors," J. Appl. Phys. 54, 3566 (1983).
- S. Spooner and W. E. Brundage, "Isotropy of Spinodal Decomposition in Fe-30% Cr," Scripta Metall. 17, 573 (1983).
- Ferdinand C. Stehling and George D. Wignall, "Small-Angle Neutron Scattering Studies of the Compatibility of Blends of Polyethylenes in the Melt and Solid States," Polymer Preprints 24, 211 (1983).
- G. P. Summers, K. Chakrabarti, and Y. Chen, "Infrared-Stimulated Luminescence from Oxygen Vacancies in CaO ," Phys. Rev. B 29, 5878 (1984).
- H. Suzuki, T. Ohtsuka, S. Kawarazaki, N. Kunitomi, R. M. Moon, and R. M. Nicklow, "Neutron Diffraction Study on the Hyperfine-Enhanced Nuclear Spin Order of HoVO_4 ," Solid State Commun. 49, 1157 (1984).
- M.-Y. Tang, J. F. Fellers, and J. S. Lin, "Dynamic Small-Angle Scattering for Oriented Polystyrene," Polymer Preprints 24, 376 (1983).
- J. R. Tinsley, D. K. McDaniels, J. Lisannti, L. W. Swenson, R. Liljestrang, D. M. Drake, F. E. Bertrand, E. E. Gross, D. J. Horen, and T. P. Sjoreen, "Observation of 2 μm Hexadecapole Strength in Lead Nuclei from 200 MeV Inelastic Proton Scattering," Phys. Rev. C 28, 1417 (1983).
- J. Z. Tischler, "A Standard Format for Data Files," Nucl. Instrum. Methods in Phys. Research 222, 339 (1984).
- E. C. Trantham, H. F. Rorschach, J. S. Clegg, C. F. Hazlewood, R. M. Nicklow, and N. Wakabayashi, "Diffusive Properties of Water in Artemia Cysts as Determined from Quasi-Elastic Neutron Scattering Spectra," Biophys. J. 45, 927 (1984).

- R. Triolo and H. R. Child, "Small-Angle Neutron Scattering Study of Coal Extract Solutions in Pyridine," Fuel **63**, 273 (1984).
- R. Triolo, J. B. Hayter, L. J. Magid, and J. S. Johnson, Jr., "Small-Angle Neutron Scattering from H_2O/D_2O Solutions of a Sodium Alkylbenzenesulfonate Having a Branched Alkyl Chain," J. Chem. Phys. **79**, 1977 (1983).
- K. L. Tsang and Y. Chen, "Suppression of Dielectric Breakdown in MgO Crystals at High Temperatures by Impurity Doping," J. Appl. Phys. **54**, 4531 (1983).
- E. C. Uberbacher, V. Ramakrishnan, D. E. Olins, and G. J. Bunick, "Neutron Scattering Studies of Nucleosome Structure at Low Ionic Strength," Biochem. **22**, 4916 (1983).
- G.-C. Wang and T.-M. Lu, "Dynamics of Two-Dimensional Ordering: Oxygen Chemisorbed on the W(112) Surface," Phys. Rev. Lett. **50**, 2014 (1983).
- G.-C. Wang and T.-M. Lu, "Phase Diagram of a Chemisorbed Oxygen Overlayer on Tungsten (112) Surface," Phys. Rev. B **28**, 6795 (1983).
- G.-C. Wang and T.-M. Lu, "Summary Abstract: Kinetics of Antiphase Domains Coarsening in an Overlayer," J. Vac. Sci. Technol. A **2**, 1048 (1984).
- J. C. Wang, "Application of the Path Probability Method to Conduction Problems of β - and β' -Alumina," Phys. Rev. B **27**, 6088 (1983).
- R. J. Warmack, R. S. Becker, V. E. Anderson, R. H. Ritchie, Y. T. Chu, J. Little, and T. L. Ferrell, "Surface-Plasmon Excitation during Reflection Scattering of Low-Energy Electrons in Micropores in a Thin Metal Film," Phys. Rev. B **29**, 4375 (1984).
- R. A. Weeks, D. L. Kinser, G. Kordas, R. Magruder, and M. Wells, "The Influence of Melting Condition on the Radiation Sensitivity of GeO_2 Glass," J. Phys. (Paris) **43**, 149 (1982).
- J. F. Wendelken and G.-C. Wang, "Finite Size Effects on Reconstruction Domains of Tungsten (001) Surfaces," J. Vac. Sci. Technol. A **2**, 888 (1984).
- J. F. Wendelken and G.-C. Wang, "Hydrogen-Induced Reconstruction on a High-Step Density W(001) Surface," Surf. Sci. **140**, 425 (1984).
- P. A. Westbrook, J. F. Fellers, M. Cakmak, J. S. Lin, and R. W. Hendricks, "An Analysis of the Reflective Component of Small Angle X-ray Scattering Patterns from Crazed Polystyrene," J. Polym. Sci., Polym. Phys. Ed. **21**, 1913 (1983).
- P. A. Westbrook, J. F. Fellers, R. W. Hendricks, and J. S. Lin, "Small-Angle X-ray Scattering Studies of Crazed Glassy Polymers," J. Polym. Sci., Polym. Phys. Ed. **21**, 969 (1983).
- C. W. White, "Dopant Incorporation during Nonequilibrium Solidification," J. Phys. (Paris) **C5**, 145 (1983).
- C. W. White, "Laser Annealing of Semiconductors," Jpn. J. Appl. Phys. **22**, 191 (1983).
- C. W. White, G. Farlow, J. Narayan, G. J. Clark, and J. E. E. Baglin, "Ion Beam Mixing of Metal Films on SiO_2 ," Mater. Lett. **2**, 367 (1984).
- J. D. Wignall, "Small-Angle Neutron Scattering from Synthetic Polymers at Oak Ridge," ACA Transactions **19**, 17 (1983).
- J. D. Wignall and W. Wu, "A SANS Investigation into the Role of Melting and Recrystallization during Solid State Deformation of Polyethylene," Polymer Preprints **24**, 235 (1983).
- J. D. Wignall and W. Wu, "Small-Angle Neutron Scattering Studies of Plastic Deformation in Crystalline Polyethylene," Polymer Commun. **24**, 354 (1983).
- S. R. Wilson, W. M. Paulson, R. B. Gregory, G. Tam, C. W. White, B. R. Appleton, A. K. Rai, and P. P. Pronko, "Thermal Stability of Electrically Active Dopants in Laser-Annealed Silicon Films," J. Appl. Phys. **54**, 5004 (1983).
- S. P. Withrow, J. E. Weidley, and P. S. Herrell, "Simple UHV Transfer System for Surface Barrier Detectors," Rev. Sci. Instrum. **54**, 1059 (1983).

- Po-zen Wong and J. W. Cable, "Hysteretic Behaviors of the Diluted Random-Field Ising System $\text{Fe}_{0.70}\text{Mg}_{0.30}\text{Cl}_2$," Phys. Rev. B Rapid Commun. **28**, 5361 (1983).
- Po-zen Wong and J. W. Cable, "Neutron Diffraction Study of the Nondiluted Random-Field Ising System $\text{Fe}_{1-x}\text{Co}_x\text{Cl}_2$," Solid State Commun. **51**, 545 (1984).
- Po-zen Wong and J. W. Cable, "Observation of a Disordered Spin-Flop Phase in $\text{Fe}_{0.725}\text{Co}_{0.275}\text{Cl}_2$," Phys. Rev. B: Rapid Commun. **30**, 485 (1984).
- Po-zen Wong, J. W. Cable, and P. Dimon, "Experimental Studies of Random-Field Effects in Uniaxial Random Antiferromagnets," J. Appl. Phys. **55**, 2377 (1984).
- Richard F. Wood and Rosa T. Young, "Future Developments in the Laser Processing of Solar Cells," Solar Cells **12**, 245 (1984).
- R. F. Wood, D. H. Lowndes, and J. Narayan, "Bulk Nucleation and Amorphous Phase Formation in Highly Undercooled Molten Silicon," Appl. Phys. Lett. **44**, 770 (1984).
- Ping Young, Thein Kyu, J. S. Lin, and R. S. Stein, "Polymer Deformation by Small-Angle X-ray Scattering," Polymer Preprints **24**, 392 (1983).
- P. Young, T. Kyu, S. Suehiro, J. S. Lin, and R. S. Stein, "Dynamic Small-Angle X-ray Scattering from Crystalline Polymers," J. Polym. Sci., Polym. Phys. Ed. **21**, 881 (1983).
- R. T. Young, J. Narayan, W. H. Christie, G. A. van der Leeden, J. I. Levatter, and L. J. Cheng, "Semiconductor Processing with Excimer Lasers," Solid State Technol. **26**, 183 (1983).
- R. T. Young, G. A. van der Leeden, R. L. Sandstrom, R. F. Wood, and R. D. Westbrook, "High-Efficiency Si Solar Cells by Beam Processing," Appl. Phys. Lett. **43**, 666 (1983).
- J. Zarestky, C. Stassis, B. N. Harmon, J. A. Begum, R. M. Moon, S. H. Liu, and D. D. Koelling, "Induced Neutron Magnetic Form Factor of LaSn_3 ," J. Magn. Magn. Mater. **38**, 61 (1983).
- A. Zeilinger, C. G. Shull, J. Arthur, and M. A. Horne, "Bragg-Case Neutron Interferometry," Phys. Rev. A **28**, 487 (1983).
- R. A. Zuhr, "Characterization of the TEXTOR Plasma Edge Using Deposition Probe Techniques," J. Vac. Sci. Technol. A **2**, 686 (1984).
- R. A. Zuhr, "Impurity Measurements in the TEXTOR Plasma Edge Using Deposition Probe Techniques," J. Nucl. Mater. **122/123**, 1193 (1984).
- R. A. Zuhr, J. B. Roberto, and B. R. Appleton, "Ion Beam Surface Analysis in Plasma Edge Studies," Nucl. Sci. Appl. **1**, 617 (1984).

BOOKS AND PROCEEDINGS

- B. R. Appleton, "Ion Beam and Laser Mixing: Fundamentals and Applications," p. 189 in Ion Implantation and Ion Beam Processing, ed. by J. S. Williams and J. M. Poate, Academic Press, New York, 1984.
- B. R. Appleton, "Ion-Induced Morphological Instabilities in Ge," p. 195 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- B. R. Appleton, J. Narayan, O. W. Holland, and S. J. Pennycook, "Coherent Precipitate Formation in Pulsed-Laser and Thermally Annealed, Ion-Implanted Si," p. 281 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- M. J. Aziz, "Crystal Growth and Solute Trapping," p. 369 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.
- John H. Barrett, "Ion Channeling in Elastically Strained Superlattices," p. 465 in Thin Films and Interfaces II, ed. by J. E. E. Baglin, D. R. Campbell, and W. K. Chu, North-Holland, New York, 1984.

- J. B. Bates, N. J. Dudney, and J. C. Wang, "Hydration of β - and β' -Alumina," p. 562 in Proceedings of the Twelfth North American Thermal Analysis Society Conference, ed. by Jean C. Buck, North American Thermal Analysis Society, Wilmington, Delaware, 1984.
- J. B. Bates, J. C. Wang, N. J. Dudney, and W. E. Brundage, "Hydration of β' -Alumina," p. 237 in Solid State Ionics-83, Part I, ed. by M. Kleitz, B. Sapoval, and Y. Chabre, North-Holland, Amsterdam, 1983.
- J. L. Boldú, E. Muñoz P., K. L. Tsang, M. M. Abraham, and Y. Chen, "The Effect of Ionizing Radiation on Nickel-Doped MgO," p. 141 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, North-Holland, New York, 1984.
- J. G. Cabanas-Moreno, M. S. Yang, M. Roth, Z. Y. Zhang, G. D. Wignall, and W. C. Koehler, "Studies of Grain Boundary Cavitation by Small-Angle Neutron Scattering," p. 95 in Fatigue Mechanisms: Advances in Quantitative Measurement of Physical Damage, ASTM STP 811, ed. by J. Lankford, D. L. Davidson, W. L. Morris, and R. P. Wei, American Society for Testing and Materials, Philadelphia, Pennsylvania, 1983.
- D. K. Christen, H. R. Kerchner, S. T. Sekula, and Y. K. Chang, "Experimental Determination of the Temperature-Dependent Penetration Depth in V_3Si ," p. 1035 in Proceedings of the Seventeenth International Conference on Low-Temperature Physics, ed. by U. Eckern, A. Schmid, W. Weber, and H. Wühl, North-Holland, Amsterdam, 1984.
- G. J. Clark, J. E. E. Baglin, F. M. d'Heurle, C. W. White, G. Farlow, and J. Narayan, "Ion Beam Irradiation of Metal Films on SiO_2 ," p. 55 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- J. F. Cooke, J. A. Blackman, and T. Morgan, "Band Structure Effects in the Electronic Properties of Solids Assessable in Neutron Scattering Studies," in Condensed Matter Research Using Neutrons, NATO-ASI Series Vol. 112, ed. by S. W. Lovesey, Plenum Press, New York, 1984.
- R. J. Culbertson, S. P. Withrow, and J. H. Barrett, "Potential and Stopping Power Information from Ion Channeling in Ge," p. 19 in Proceedings of the Tenth International Conference on Atomic Collisions in Solids, ed. by H. E. Roosendaal, H. O. Lutz, W. Heiland, and H. J. Andra, North-Holland, Amsterdam, 1984.
- L. S. Darken, "The Characterization of Germanium and Silicon for Nuclear Radiation Detectors," p. 47 in Nuclear Radiation Detector Materials, ed. by E. E. Haller, H. W. Kraner, and W. A. Higginbotham, North-Holland, New York, 1983.
- J. B. Davidson and H. G. Smith, "TV-Based Neutron Detectors and Applications," p. 767 in Proceedings of the International Symposium on the Use and Development of Low and Medium Flux Research Reactors, Vol. 44, ed. by Otto K. Harling, Lincoln Clark, Jr., and Peter von der Hardt, Atomkernergie Kerntechnik, 1984.
- R. J. De Angelis, A. G. Dhere, J. D. Lewis, and H.-K. Kuo, "Application of X-ray Diffraction Techniques to Study the Sintering of Catalysis," p. 181 in Sintering and Heterogeneous Catalysis, ed. by G. C. Kuczyniski, A. E. Miller, and G. A. Sargent, Plenum Press, New York, 1984.
- N. J. Dudney, J. B. Bates, and W. E. Brundage, "Raman Measurements of the Mobile Cation Vibrations in Na, K, Ag and Li β' -Alumina," p. 207 in Solid State Ionics-83, Part I, ed. by M. Kleitz, B. Sapoval, and Y. Chabre, North-Holland, Amsterdam, 1983.
- G. C. Farlow, C. W. White, C. J. McHargue, and B. R. Appleton, "Behavior of Implanted α - Al_2O_3 in an Oxidizing Annealing Environment," p. 395 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- Sister J. Feldott, G. Farlow, A. Blose, B. Lounsberry, R. A. Hudson, and L. M. Slifkin, "Experiments on the Ionic Space Charge in Silver Halides," p. 167 in The Physics of Latent Image Formation in Silver Halides, ed. by A. Buldereschi and W. Ljaja, World Scientific Publishing Company, Singapore, 1984.
- J. A. Harvey, H. A. Mook, N. H. Hill, and O. Shahal, "Solid State Effects on Thermal Neutron Cross Sections and on Low-Energy Resonances," p. 961 in Proceedings of the International Conference on Nuclear Data for Science and Technology, ed. by K. H. Bockhoff, D. Reidel Publishing Company, Holland, 1983.
- John B. Hayter, "Instrumentation at the ILL—Development and Demand," p. 31 in Instrumentation for the Advanced High-Flux Reactor, CONF-8405192, ed. by R. M. Moon, ORNL, Oak Ridge, Tennessee, 1984.

- O. W. Holland, J. Narayan, C. W. White, and B. R. Appleton, "Pulsed-Laser Annealing of Ion-Implanted Ge," p. 297 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- L. D. Hulett, J. M. Dale, S. Pendyala, Y. K. Chang, and W. S. Lyon, "Positron Spectroscopy Applied to the Analysis of Surfaces," p. 1443 in Proceedings of the International Symposium on Applied Technology of Ionizing Radiations, Vol. 3, Malaz, Riyadh, Saudi Arabia, 1982.
- D. P. Jackson and J. H. Barrett, "Approximation for the Surface Backscattering Yield from an Atomic Row with Correlated Thermal Vibrations," p. 318 in Proceedings of the Tenth International Conference on Atomic Collisions in Solids, ed. by H. E. Roosendaal, H. O. Lutz, W. Heiland, and H. J. Andrä, North-Holland, Amsterdam, 1984.
- G. E. Jellison, Jr., D. H. Lowndes, and R. F. Wood, "A Detailed Examination of Time-Resolved Pulsed Raman Temperature Measurements of Laser-Annealed Silicon," p. 35 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- G. E. Jellison, Jr., and R. F. Wood, "Stress Effects of Raman Measurements of Pulsed-Laser-Annealed Silicon," p. 153 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.
- W. A. Kamitakahara, H. Zabel, and R. M. Nicklow, "Phonon Dispersion of Transverse Basal Plane Modes in Alkali-Graphite Compounds," p. 311 in Intercalated Graphite, ed. by M. S. Dresselhaus, G. Dresselhaus, J. E. Fischer, and M. J. Moran, North-Holland, New York, 1983.
- E. N. Kaufmann, R. G. Musket, C. A. Colmenares, and B. R. Appleton, "Enhancement of Uranium Oxidation Resistance by Molybdenum Implantation," p. 747 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- H. R. Kerchner, O. K. Christen, A. Das Gupta, S. T. Sekula, B. C. Cai, and Y. T. Chou, "Flux-Line Pinning by the Grain Boundary in Niobium Bicrystals," p. 463 in Proceedings of the Seventeenth International Conference on Low-Temperature Physics, ed. by U. Eckern, A. Schmid, W. Weber, and H. Wühl, North-Holland, Amsterdam, 1984.
- S. Kim, J. R. Weertman, S. Spooner, C. J. Glinka, V. Sikka, and W. B. Jones, "Microstructural Evaluation of a Ferritic Stainless Steel by Small-Angle Scattering," in Applications and Development of Nondestructive Evaluation for Use in Materials Processing, ed. by S. Wolf and O. Buck, American Society for Metals, Metals Park, Ohio, 1983.
- B. C. Larson, C. W. White, T. S. Noggle, J. F. Barhorst, and D. M. Mills, "Time-Resolved Study of Silicon during Pulsed-Laser Annealing," p. 43 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- S. H. Liu, "Frequency Spectrum of an Elastic Sierpinski Gasket," p. 169 in Kinetics of Aggregation and Gelation, ed. by Fereydoon Family and David P. Landau, North-Holland, Amsterdam, 1984.
- J. Llopis, C. Ballesteros, R. Gonzalez, and Y. Chen, "Cathodoluminescence Emission from Crystalline LiNbO_3 ," p. 129 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, North-Holland, New York, 1984.
- D. H. Lowndes, J. W. Cleland, W. H. Christie, R. E. Eby, G. E. Jellison, Jr., J. Narayan, R. D. Westbrook, R. F. Wood, J. A. Nilson, and S. C. Dass, "Pulsed Excimer Laser (308 nm) Annealing of Ion-Implanted Silicon and Solar Cell Fabrication," p. 407 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- D. H. Lowndes, F. A. Modine, E. Sonder, Y. Chen, and W. J. Choyke, "Pulsed Excimer and CO_2 Laser Processing for Fabrication of ZnO and SiC Devices," p. 220 in CLEO Technical Digest, Optical Society of America, Washington, D.C., 1984.
- D. H. Lowndes and T. W. Raudorf, "Application of Pulsed-Laser Processing in the Fabrication of Ge Nuclear Radiation Detectors," p. 170 in CLEO Technical Digest, Optical Society of America, Washington, D.C., 1984.
- D. H. Lowndes, R. F. Wood, C. W. White, and J. Narayan, "Pulsed-Laser Melting of Amorphous Silicon: Time-Resolved and Post-Irradiation Studies," p. 99 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.

- C. J. McHargue, M. B. Lewis, B. R. Appleton, H. Naramoto, C. W. White, and J. M. Williams, "Alteration of Surface Properties by Ion Implantation," p. 451 in Science of Hard Materials, ed. by R. K. Viswanadham, D. J. Rowcliffe, and J. Gurland, Plenum Press, New York, 1983.
- C. J. McHargue, H. Naramoto, C. W. White, J. M. Williams, B. R. Appleton, P. S. Sklad, and P. Angelini, "Structure of Ceramic Surfaces Modified by Ion Beam Techniques," p. 519 in Emergent Process Methods for High-Technology Ceramics, ed. by Robert F. Davis, Hayne Palmour III, and Richard L. Porter, Plenum Press, New York, 1984.
- C. J. McHargue, C. W. White, B. R. Appleton, G. C. Farlow, and J. M. Williams, "Ion Beam Modification of Ceramics," p. 385 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- R. M. Moon, "Experimental Facilities," p. 13 in Instrumentation for the Advanced High-Flux Reactor, CONF-8405192, ed. by R. M. Moon, ORNL, Oak Ridge, Tennessee, 1984.
- R. M. Moon, "Interaction between Users of Large and Small Research Reactors," p. 34 in Proceedings of the International Symposium on the Use and Development of Low and Medium Flux Research Reactors, Vol. 44, ed. by Otto K. Harling, Lincoln Clark, Jr., and Peter von der Hardt, Atomkernenergie Kerntechnik, 1984.
- R. M. Moon, "Summary of Workshop Recommendations," p. 79 in Instrumentation for the Advanced High-Flux Reactor, CONF-8405192, ed. by R. M. Moon, ORNL, Oak Ridge, Tennessee, 1984.
- J. Narayan, "Laser Annealing of Ion-Implanted Semiconductors," p. 491 in Defects in Semiconductors, ed. by J. W. Corbett and S. Mahajan, North-Holland, New York, 1983.
- J. Narayan, "Rapid Thermal Annealing of Ion-Implanted Silicon and Gallium Arsenide," p. 335 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.
- J. Narayan, Y. Chen, and R. M. Moon, "Metal Colloids in Oxides," p. 101 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, North-Holland, New York, 1984.
- J. Narayan and D. Fathy, "Atomic Structure of Ion Implantation Produced Amorphous Silicon and Amorphous-Crystalline Interface Structure and Kinetics," p. 122 in Proceedings of the 41st Annual Meeting of the Electron Microscopy Society of America, ed. by G. W. Bailey, San Francisco Press, Inc., San Francisco, California, 1983.
- J. Narayan, O. W. Holland, and G. L. Olson, "Solid-Phase-Epitaxial Growth of Ion-Implanted Silicon Using CW Laser and Electron Beam Annealing," p. 155 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- J. Narayan, C. W. White, and O. W. Holland, "Melting Phenomena and Impurity Redistribution during Pulsed-Laser Irradiation of Amorphous Silicon Layers," p. 188 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.
- J. R. Noonan and H. L. Davis, "Reliability of Contemporary Data Acquisition Techniques for LEED Analysis," p. 449 in Surface Structure by LEED, ed. by P. M. Marcus and F. Jona, Plenum Press, New York, 1984.
- Ordean S. Oen, "Ion Reversibility Studies in Amorphous Solids Using the Two-Atom Scattering Model," p. 39 in Recent Theoretical (Computational) Developments in Atomic Collisions in Solids, ed. by Y. H. Ohtsuki, World Scientific Publishing Company, Singapore, 1983.
- Ordean S. Oen and Mark T. Robinson, "Ion Backscattering from Layered Targets," p. 171 in Proceedings of the Third International Symposium on Production and Neutralization of Negative Ions and Beams, ed. by Krsto Prelec, American Institute of Physics, New York, 1984.
- S. M. Ohr, "Electron Microscope Observation of Crack Propagation and a Dislocation Model of Fracture," p. 438 in The Structure and Properties of Crystal Defects, ed. by V. Paidar and L. Lejcek, Elsevier Science Publishing Company, New York, 1984.
- S. M. Ohr, J. A. Horton, and S.-J. Chang, "Direct Observations of Crack Tip Dislocation Behavior during Tensile and Cyclic Deformation," p. 3 in Defects, Fracture and Fatigue, ed. by G. C. Sih and J. W. Provan, Martinus Nijhoff Publishers, The Hague, 1983.

- G. L. Olson, J. A. Roth, L. D. Hess, and J. Narayan, "Kinetics of Solid Phase Crystallization in Ion-Implanted and Deposited Amorphous Silicon Films," p. 17 in Advances in Solid State Technology, Reidel Publishing Company, New York, 1984.
- S. J. Pennycook, J. Narayan, and C. W. Holland, "Dopant Site Location by Electron Channeling in Ion-Implanted Silicon," p. 97 in Electron Microscopy of Materials, ed. by W. Krakow, D. A. Smith, and L. W. Hobbs, North-Holland, New York, 1984.
- S. J. Pennycook, J. Narayan, and O. W. Holland, "Point Defect Supersaturation and Enhanced Diffusion in SPE Grown Silicon," p. 293 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- S. J. Pennycook, J. Narayan, and O. W. Holland, "Redistribution and Precipitation of Dopant on Thermal Annealing of Bismuth-Implanted Silicon," p. 126 in Proceedings of the 41st Annual Meeting of the Electron Microscopy Society of America, ed. by G. W. Bailey, San Francisco Press, Inc., San Francisco, California, 1983.
- D. T. Pierce, R. J. Celotta, and G.-C. Wang, "What Can PLEED Contribute to Surface Structure Determination," p. 339 in Surface Structure by LEED, ed. by P. M. Marcus and F. Jona, Plenum Press, New York, 1984.
- D. B. Poker, O. W. Holland, and B. R. Appleton, "Dose Dependence of Ion Beam Mixing of Au on Amorphous and Single-Crystalline Si and Ge," p. 73 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- P. P. Pronko, A. W. McCormick, D. C. Ingram, A. K. Rai, J. A. Woollam, B. R. Appleton, and D. B. Poker, "Ion Irradiation Smoothing and Film Bonding for Laser Mirrors," p. 559 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- M. T. Robinson, "Theoretical Aspects of Monocrystal Sputtering," p. 99 in Raspyleniya Tverdykh Tel Ionnoi Bombardirovkoii, ed. by R. Berysha, Mir, Moskva, USSR, 1984.
- Mark T. Robinson, "The Physics of Ion Sputtering," p. 151 in Resonance Ionization Spectroscopy 1984, Institute of Physics Conference Series No. 71, London, 1984.
- B. C. Sales, M. Petek, and L. A. Boatner, "Electrical Conductivity Measurements of Leachates for the Rapid Assessment of Waste Form Corrosion Resistance," p. 251 in Scientific Basis for Nuclear Waste Management, Vol. 6, ed. by D. G. Bronkins, North-Holland, New York, 1983.
- E. Sonder and L. S. Darken, "The Influence of Cation Stoichiometry on the Electrical Conductivity and High-Temperature Stability of $\text{MgO:nAl}_2\text{O}_3$ Spinel," p. 215 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, North-Holland, New York, 1984.
- L. H. Sperling, A. M. Fernandez, and G. D. Wignall, "Correlation Network in Polymeric Materials Determined by Small-Angle Neutron Scattering," p. 71 in Characterization of Highly Cross-Linked Polymers, ed. by S. S. Labana and R. A. Dickie, ACS Symposium Series 243, Maple Press, York, Pennsylvania, 1983.
- J. R. Thompson, S. T. Sekula, D. H. Lowndes, and H. R. Khan, "Formation of Superconductive $\text{Al}(\text{GeSi})$ Alloys by Low-Temperature Laser Quenching Methods," p. 1265 in Proceedings of the Seventeenth International Conference on Low-Temperature Physics, ed. by U. Eckern, A. Schmid, W. Weber, and H. Wühl, North-Holland, Amsterdam, 1984.
- K. L. Tsang, H. T. Tohver, and Y. Chen, "Time Dependence of Current Injection Phenomenon in Nickel-Doped MgO Crystals at High Temperatures," p. 207 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Jr., Y. Chen, and W. A. Sibley, North-Holland, New York, 1984.
- C. W. White, "Nonequilibrium Crystal Growth during Laser Annealing of Silicon," p. 437 in Proceedings of the Flat-Plate Solar Array Project Research Forum on High-Speed Growth and Characterization of Crystals for Solar Cells, DOE/JPL-1012085, Department of Energy, Washington, D.C., 1984.
- C. W. White, G. C. Farlow, H. Naramoto, C. J. McHargue, and B. R. Appleton, "Modification of the Near-Surface Region of Al_2O_3 by Ion Implantation," p. 163 in Defect Properties and Processing of High-Technology Nonmetallic Materials, ed. by J. H. Crawford, Y. Chen, and W. A. Sibley, North-Holland, New York, 1984.

- C. W. White, D. M. Zehner, S. U. Campisano, and A. G. Cullis, "Segregation, Supersaturated Alloys, and Semiconductor Surfaces," p. 81 in Surface Modification and Alloying, ed. by J. M. Poate, G. Foti, and D. C. Jacobson, Plenum Press, New York, 1983.
- C. W. White, D. M. Zehner, J. Narayan, O. W. Holland, B. R. Appleton, and S. R. Wilson, "Dopant Incorporation during Rapid Solidification," p. 287 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- J. M. Williams, G. M. Beardsley, R. A. Buchanan, and R. K. Bacon, "Effect of N Implantation on the Corrosive-Wear Properties of Surgical Ti-6Al-4V Alloy," p. 735 in Ion Implantation and Ion Beam Processing of Materials, ed. by G. K. Hubler, O. W. Holland, C. R. Clayton, and C. W. White, North-Holland, New York, 1984.
- R. F. Wood, "Amorphous Phase Trapping as a Result of Pulsed-Laser Irradiation of Silicon," p. 83 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- R. F. Wood, D. H. Lowndes, and J. Narayan, "Solidification of Highly Undercooled Silicon: Bulk Nucleation and Amorphous Phase Formation," p. 141 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.
- D. P. Woodruff, G.-C. Wang, and T.-M. Lu, "Surface Structure and Order-Disorder Phenomena," p. 259 in Chemical Physics of Solid Surfaces and Heterogeneous Catalysis, Vol. II, ed. by D. A. King and D. P. Woodruff, Elsevier Science Publishing Company, New York, 1983.
- R. T. Young, "Semiconductor Processing with Excimer Lasers: An Overview," p. 217 in Energy Beam-Solid Interactions and Transient Thermal Processing, ed. by J. C. C. Fan and N. M. Johnson, North-Holland, New York, 1984.
- R. T. Young, J. Narayan, W. H. Christie, G. A. van der Leeden, D. E. Rothe, and L. J. Cheng, "Semiconductor Processing with Excimer Lasers," p. 266 in Excimer Lasers-1983, ed. by C. K. Rhodes, H. Egger, and H. Pummer, American Institute of Physics, New York, 1983.
- R. T. Young, J. Narayan, W. H. Christie, G. A. van der Leeden, D. E. Rothe, and R. L. Sandstrom, "Effect of Pulse Duration on the Annealing of Ion-Implanted Silicon with a XeCl Excimer Laser and Solar Cells," p. 401 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- D. M. Zehner and C. W. White, "Surface Studies of Laser-Annealed Semiconductors," p. 317 in Laser-Solid Interactions and Transient Thermal Processing of Materials, ed. by J. Narayan, W. L. Brown, and R. A. Lemons, North-Holland, New York, 1983.
- T. Zemb, J. Chevalier, M. Hayoun, and J. B. Hayter, "Mixed Micelle Structure: Charge and Alcohol Influence," p. 28 in Proceedings of CESIO-III World Surfactants Congress, ed. by Kuerle Druck, Verlag, Munich, Federal Republic of Germany, 1984.

REPORTS ISSUED

- D. E. Bartine, J. W. Cable, H. A. Mook, R. M. Moon, and R. M. Nicklow, ORNL Presentation to the Major Materials Facilities Committee of the National Research Council, Oak Ridge National Laboratory (February 1984).
- R. R. Coltman, Jr., and C. E. Klabunde, "The Strength of G-10CR and G-11CR Epoxies after Irradiation at 5 K by Gamma Rays," p. 91 in Fifth Annual Progress Report on Special Purpose Materials for Magnetically Confined Fusion Reactors, DOE/ER-0113/2 (October 1983).
- R. R. Coltman, Jr., and C. E. Klabunde, "The Use of a New National Low-Temperature Neutron Irradiation Facility (MLTNIF) for Fusion Magnet Materials Studies," p. 59 in Sixth Annual Progress Report on Special Purpose Materials for Magnetically Confined Fusion Reactors, DOE/ER-0113/3 (May 1984).
- S. A. David and L. A. Boatner, eds., Future Directions for Research on Composite Materials at Oak Ridge National Laboratory, ORNL/TM-9010 (January 1984).
- C. E. Klabunde and R. R. Coltman, Jr., "Debonding of Epoxy from Glass in Irradiated Laminates," p. 79 in Fifth Annual Progress Report on Special Purpose Materials for Magnetically Confined Fusion Reactors, DOE/ER-0113/2 (October 1983).

- C. E. Klabunde and R. R. Colman, Jr., "The Magnetoresistivity of Copper Irradiated at 4.4 K by Spallation Neutrons," p. 53 in Sixth Annual Progress Report on Special Purpose Materials for Magnetically Confined Fusion Reactors, DOE/ER-0113/3 (May 1984).
- F. A. Modine, Summary Report on Responses to a Questionnaire on DOE's Materials Research Facilities, ORNL/PPA-84/2 (June 1984).
- R. M. Moon, D. E. Bartine, F. J. Peretz, and J. A. Murray, Feasibility Study for High Flux Isotope Reactor-II, X-OE-247 (April 1984).
- J. O. Sease, P. Angelini, F. T. Binford, J. O. Blomeke, L. A. Boatner, E. S. Bomar, E. A. Bondietta, H. M. Butler, N. H. Cutshall, L. M. Ferris, F. E. Harrington, L. J. King, E. H. Krieg, T. W. Oakes, and S. K. Whatley, Long-Range Planning Basis for Radioactive Waste Management at ORNL, Parts I and II, ORNL/CF/82-278/P2 (April 1984).
- David Turnbull, L. A. Boatner, L. C. De Jonghe, R. C. Ewing, R. L. Fleischer, A. H. Heuer, W. G. Johnston, D. J. Lam, A. J. Machiels, R. D. Maurer, C. J. Northrup, Jr., and B. J. Wuensch, Scientific Needs of the Technology of Nuclear Waste Containment, University of Illinois (July 1983).
- R. T. Young, R. F. Wood, R. D. Westbrook, and G. A. van der Leeden, Applications of Laser Annealing and Laser-Induced Diffusion to Photovoltaic Conversion, Solar Energy Research Institute Annual Progress Report for the Period March 1, 1982, to April 30, 1985, ORNL/TM-8878 (October 1983).
- R. A. Zuhr, J. B. Roberto, and B. R. Appleton, Ion Beam Surface Analysis in Plasma Edge Studies, ORNL/TM 8815 (October 1983).

THESES

- Jose Roberto Martinelli, "Self Diffusion in MgO under the Influence of Moderate Electric Fields in the Temperature Range of 1100–1250 K," thesis submitted to the Faculty of the Graduate School of Vanderbilt University in partial fulfillment of the requirements for the Ph.D. degree, September 1984.

PATENTS GRANTED

- Y. Chen, R. Gonzalez, and G. P. Summers, High-Quantum Efficiency, Long-Lived Luminescing Refractory Oxides, U.S. Patent No. 4,427,570 (January 24, 1984).
- R. F. Wood and R. T. Young, Modified Laser Annealing Process for Improving the Quality of Electrical P-N Junctions and Devices, U.S. Patent No. 4,436,557 (March 13, 1984).

PAPERS PRESENTED AT TECHNICAL MEETINGS

Workshop on the Simulation of Electrified Interfaces, Paris, France, April 10–21, 1983:

S. H. Liu, "Electroreflectance of Ag Single-Crystal Surfaces"

Third Annual Symposium and Equipment Exhibit of the Tennessee Valley Chapter of the American Vacuum Society, Knoxville, Tennessee, May 8–11, 1983:

J. R. Noonan and H. L. Davis, "Truncation-Induced Multilayer Relaxations of Metal Surfaces"

G.-C. Wang, "Study of Two-Dimensional Phase Transitions by LEED"

One Hundred Sixty Third Meeting of the Electrochemical Society, San Francisco, California, May 8–13, 1983:

J. B. Bates, N. J. Dudney, and S. M. Casey, "Adaptation of a Network Analyzer for Four-Point AC Electrical Measurements of Ionic Conductors" [J. Electrochem. Soc. 130, 107C (1983)]

SERI Photovoltaic Fifth Annual Review and Development Meeting, Golden, Colorado, May 19-20, 1983:

R. T. Young, G. A. van der Leeden, P. L. Sandstrom, R. F. Wood, and R. D. Westbrook, "Beam Processing for High-Efficiency Si Solar Cells" (invited paper)

The Twelfth Polymer Consortium Meeting, Knoxville, Tennessee, May 23-24, 1983:

J. S. Lin, "The NCSASR and SAS Applications to Industrial Problems"

First European Materials Research Society Meeting, Strasbourg, France, May 25-27, 1983:

C. W. White, "Dopant Incorporation during Nonequilibrium Solidification" (invited paper)

Second International Conference on Radiation Effects in Insulators, Albuquerque, New Mexico, May 30-June 3, 1983:

B. R. Appleton, H. Naramoto, C. W. White, O. W. Holland, C. J. McHargue, G. Farlow, J. Narayan, and J. M. Williams, "Ion Implantation, Ion Beam Mixing and Annealing Studies of Metals in Al_2O_3 , SiC, and Si_3N_4 "

C. W. White, J. M. Williams, C. J. McHargue, O. W. Holland, B. R. Appleton, and H. Naramoto, "Ion Implantation and Thermal Annealing of $\alpha-Al_2O_3$ "

International Conference on Crack Tip Structure and Processes, Washington, D.C., June 6-8, 1983:

S. M. Ohr, "Direct Observations of Crack Tip Dislocations" (invited paper)

International Symposium on the Structure and Properties of Crystal Defects, Liblice, Czechoslovakia, June 13-17, 1983:

S. M. Ohr, "Direct Observation of Crack-Tip Dislocations and Dislocation Model of Fracture" (invited paper)

Forty Third Annual Conference on Physical Electronics, Santa Fe, New Mexico, June 20-22, 1983:

T.-M. Lu and G.-C. Wang, "Dynamics of Two-Dimensional Ordering: Oxygen Chemisorbed on the W(112) Surface"

J. R. Noonan, H. L. Davis, G.-C. Wang, and T.-M. Lu, "Has the Structure of the Reconstructed Au(110) Been Determined"

U.S.-Japan Seminar on Solid Phase Epitaxy and Interface Kinetics, Oiso, Japan, June 20-24, 1983:

G. L. Olson, J. A. Roth, L. D. Hess, and J. Narayan, "Kinetics of Solid Phase Crystallization in Ion-Implanted and Deposited Amorphous Silicon Films"

SERI Polycrystalline Silicon Subcontractors' Review Meeting, Golden, Colorado, June 27-28, 1983:

Russell D. Westbrook, Richard F. Wood, and Rosa T. Young, "Applications of Laser Annealing and Laser-Induced Diffusion to Photovoltaic Conversion"

Fourth International Conference on Solid State Ionics, Grenoble, France, July 4-8, 1983:

J. B. Bates, J. C. Wang, and N. J. Dudney, "Hydration of β -Alumina"

N. J. Dudney, J. B. Bates, and W. E. Brundage, "Raman Measurements of β -Alumina"

Gordon Conference on Point Defects, Line Defects and Interfaces, Plymouth, New Hampshire, July 11-15, 1983:

S. J. Pennycook, J. Narayan, and O. W. Holland, "Point Defect Supersaturation and Enhanced Diffusion in SPE Regrown Silicon"

Summer School on Physics of New Materials and Experimental Techniques for Characterization, Santander, Spain, July 11-15, 1983:

Y. Chen, "Defects in High-Temperature Oxides"

Y. Chen, "Refractory Oxides for Quantum Electronic Devices: Tunable Lasers and Infrared Conversion"

Eighth Latin American Symposium on Solid State Physics, Oaxtepec, Mexico, July 18-22, 1983:

J. L. Boldú O., E. Muñoz, M. M. Abraham, and L. A. Boatner, "EPR and Thermoluminescence Investigations of Mn^{2+} in Single Crystals and Powders of the Zircon-Structure Orthophosphates $LuPO_4$, YPO_4 , and $ScPO_4$ " [*Notas de Física* 6, 160 (1983)]

Tenth International Conference on Atomic Collisions in Solids, Bad Iburg, Federal Republic of Germany, July 18-22, 1983:

R. J. Culbertson, S. P. Withrow, and J. H. Barrett, "Potential and Stopping Power Information from Ion Channeling in Ge"

D. P. Jackson and J. H. Barrett, "Approximation for the Yield from an Atomic String with Correlated Thermal Vibrations"

Mark T. Robinson, "A Study of Recoil Trajectories in Crystalline Media"

DOE/FSA High-Speed Growth and Characterization of Crystals for Solar Cells Research Forum, Port St. Lucie, Florida, July 25-27, 1983:

C. W. White, "Nonequilibrium Crystal Growth during Laser Annealing of Silicon" (invited paper)

Informal Discussion Meeting on Magnetic Superconductors, Argonne, Illinois, August 1-2, 1983:

O. A. Pringle, H. A. Mook, S. K. Sinha, and D. G. Hinks, "Neutron Diffraction Study of Magnetic Properties of $ErRh_4B_4$ "

First Summer Institute in Theoretical Physics, Kingston, Ontario, Canada, August 9-11, 1983:

Mark Rasolt, "Exchange and Correlation in Nonuniform Fermi Systems" (invited paper)

Conference on Glass in Planetary and Geological Phenomena, Alfred, New York, August 14-18, 1983:

Magdi Nasrallah and R. A. Weeks, "Constraints on the Fusion Processes of Some Natural Glasses"

B. C. Sales, C. W. White, G. M. Begun, and L. A. Boatner, "Surface Layer Formation on Corroded Nuclear Waste Glasses: Evolution, Composition, Chemical Stability, and Protective Ability"

A. Van den Bosch, J. Vansummeren, and R. A. Weeks, "Temperature and Field Dependent Susceptibilities of Libyan Desert Glass"

Adrian C. Wright, J. A. Erwin, D. Kenneth Bailey, R. A. Weeks, and Roger N. Sinclair, "Neutron Diffraction Studies of Natural Glasses"

ACS National Meeting, Washington, D.C., August 28-September 2, 1983:

W. W. Adams, E. L. Thomas, and J. S. Lin, "SAXS Invariant Analysis of Solid State Extruded Polyethylene"

C. R. Desper, N. S. Schneider, and J. S. Lin, "Deformation of Microphase Structures in Polyurethanes"

H. Hayashi, P. J. Flory, and G. D. Wignall, "The Configuration of the Polyisobutylene Chain According to Neutron and X-ray Scattering" (invited paper)

John S. King, William Boyer, George D. Wignall, and Robert Ullman, "Measurement of Polymer Solutions by High Concentration Labeling"

J. H. Magill, J. M. Schultz, and J. S. Lin, "Dynamic SAXS Crystallization Studies of Polymers" (invited paper)

J. M. O'Reilly, S. M. Melpolder, L. W. Fisher, G. D. Wignall, and V. R. Ramakrishnan, "Small-Angle Neutron Scattering of Polymer Core-Shell Latex Particles"

Ferdinand C. Stehling and George D. Wignall, "Small-Angle Neutron Scattering Studies of the Compatibility of Blends of Polyethylenes in the Melt and Solid States"

M.-Y. Tang, J. F. Fellers, and J. S. Lin, "SAXS from Polystyrene Crazes and the Growth of Microcrack under Deformation"

G. D. Wignall and W. Wu, "A SANS Investigation into the Plastic Deformation Mechanisms of Polyethylene" (invited paper)

Ping Young, Thein Kyu, J. S. Lin, and R. S. Stein, "Polymer Deformation by Small-Angle X-ray Scattering"

First International Conference on the Chemistry and Technology of the Lanthanides and Actinides, Venice, Italy, September 5-10, 1983:

L. A. Boatner, M. M. Abraham, and B. C. Sales, "Lanthanide Orthophosphate Ceramics for the Disposal of Actinide-Contaminated Nuclear Wastes"

Third National Conference on Synchrotron Radiation Instrumentation, Upton, New York, September 12-18, 1983:

J. Z. Tischler, "A Standard Form for Data Files"

Faraday Discussion on Concentrated Colloidal Dispersions, Loughborough, England, September 14-16, 1983:

J. B. Hayter, "Concentrated Colloidal Dispersions Viewed as One-Component Macrofluids" (invited paper)

Third Topical Meeting on Fusion Reactor Materials, Albuquerque, New Mexico, September 19-22, 1983:

R. R. Coltman, Jr., C. E. Klabunde, and F. W. Young, Jr., "A National Low-Temperature Neutron Irradiation Facility" [*J. Nucl. Mater.* 122/123, 1357 (1984)]

G. F. Hurley and R. R. Coltman, Jr., "Organic Materials for Fusion Reactor Applications" [*J. Nucl. Mater.* 122/123, 1327 (1983)] (invited paper)

J. Roth, J. B. Roberto, and K. L. Wilson, "Sputtering of Graphite at High Temperatures"

R. A. Zuhr, "Impurity Measurements in the TEXTOR Plasma Edge Using Deposition Probe Techniques"

Ninth International Vacuum Congress and Fifth International Conference on Solid Surfaces, Madrid, Spain, September 26-October 1, 1983:

J. B. Roberto, J. Roth, and K. L. Wilson, "Enhanced Sputtering of Graphite at High Temperatures"

D. M. Zehner, J. R. Noonan, H. L. Davis, and C. W. White, "A LEED Analysis of Laser-Annealed Ge(111)-(1x1)"

U.S. Fall Meeting, Philadelphia, Pennsylvania, October 2-4, 1983:

Stephen Spooner, R. W. Gould, and M. M. Kersker, "Natural Aging in Al-Mg-Zn: Early Stage Decomposition Kinetics of G-P Zones"

Stephen Spooner and Hyung Jin Yoon, "Structure and Properties of Permendur Alloys in Isothermally Coarsened Fe-Cr-Co"

Fall Meeting of the Metallurgical Society of AIME, Philadelphia, Pennsylvania, October 2-5, 1983:

S. M. Ohr, "TEM Studies of Fracture by In Situ Deformation Technique" (invited paper)

Annual Meeting of Physical Society of Japan, Okayama, Japan, October 11-24, 1983:

H. Suzuki, T. Ohtsuka, S. Kawarazaki, M. Kunitomi, R. M. Moon, and R. M. Nicklow, "Neutron Diffraction Study on the Hyperfine Enhanced Nuclear Spin Order of HoVO_4 "

Society of Rheology Fifty-Fifth Annual Meeting, Knoxville, Tennessee, October 16-20, 1983:

J. S. Lee, J. F. Fellers, J. L. White, and J. S. Lin, "SAXS Studies of Kevlar/Epoxy Composites"

M.-Y. Tang, P. A. Westbrook, J. F. Fellers, and J. S. Lin, "Reflection Phenomena in the Study of Cracks by SAXS"

P. A. Westbrook, J. F. Fellers, and J. S. Lin, "The Stress and Time Dependence of Localized Straining in Polystyrene at the 100 Å Level via SAXS"

International Symposium on the Use and Development of Low- and Medium-Flux Research Reactors, Cambridge, Massachusetts, October 17-19, 1983:

R. M. Moon, "Interaction Between Users of Large and Small Research Reactors" (invited paper)

Fifth European Communities Photovoltaic Solar Energy Conference, Athens, Greece, October 17-22, 1983:

G. A. van der Leeden, R. T. Young, R. L. Sandstrom, R. F. Wood, and R. D. Westbrook, "Beam Processing for High-Efficiency Si Solar Cells"

NBS-DOE Workshop on Materials at Low Temperatures, Vail, Colorado, October 18-19, 1983:

R. R. Coltman, Jr., "Current and Future Possibilities for Cryogenic Nonmetallic Radiation Research" (invited paper)

Materials Science Symposium for 3M Inorganic Materials Technical Forum, Minneapolis, Minnesota, October 20-21, 1983:

C. W. White, "Ion Beam and Laser Techniques in Materials Research"

Workshop on Neutrons in Technologically Important Problems in Powders, Gels, and Colloids, Grenoble, France, October 27-28, 1983:

J. B. Hayter, "Static Small-Angle Neutron Scattering and Its Applications to Some Colloidal Systems"

J. B. Hayter, "Beyond Structure—An Introduction to Dynamic Studies"

American Vacuum Society Thirtieth National Symposium, Boston, Massachusetts, November 1-4, 1983:

T. B. Cook, P. W. King, and J. B. Roberto, "Measurement of the Radial Distribution of Neutral Iron in the Plasma Edge of the ISX-B Tokamak Using Laser-Induced Fluorescence"

H. L. Davis and G.-C. Wang, "Relaxation of Layer Registry in the W(112) Surface—A (1x1) Reconstruction"

J. F. Wendelken and G.-C. Wang, "Finite Size Effects on Reconstruction Domains of Tungsten (001) Surfaces"

D. M. Zehner, R. A. DiDio, and E. W. Plummer, "The Electronic Structure of Ordered Oxygen Overlayers on Cu(110)"

R. A. Zunr, "Characterization of the TEXTOR Plasma Edge Using Deposition Probe Techniques"

Southeastern Section Meeting, American Physical Society, Columbia, South Carolina, November 3-5, 1983:

R. R. Coltman, Jr., C. E. Klabunde, and F. W. Young, Jr., "Early Progress on a National Low-Temperature Neutron Irradiation Facility (MLTNIF)"

Twenty-Fifth Annual Meeting of the Division of Plasma Physics, American Physical Society, Los Angeles, California, November 7-11, 1983:

T. B. Cook, P. W. King, J. B. Roberto, and J. R. Reagan, "Measurements of the Radial Distribution of Neutral Metals in the Edge Plasma of ISX-B" [*Bull. Am. Phys. Soc.* 28, 1112 (1983)]

P. W. King, T. B. Cook, and J. B. Roberto, "Laser Fluorescence Parametric Studies of Sputtered Neutral Metals in the Limiter Shadow of the ISX-B Tokamak" [*Bull. Am. Phys. Soc.* 28, 1254 (1983)]

Twenty-Ninth Annual Conference on Magnetism and Magnetic Materials, Pittsburgh, Pennsylvania, November 8-11, 1983:

C.-K. Loong, C. Stassis, J. Zarestky, O. D. McMasters, and R. M. Moon, "Temperature Dependence of the Field-Induced Magnetic Form Factor of the Intermetallic Compound PrSn_3 "

Po-zen Wong, J. W. Cable, S. von Molnar, and P. Dimon, "Experimental Studies of Random-Field Effects in Random Antiferromagnets"

Thirty-Fifth Southeast Regional Meeting of the American Chemical Society, Charlotte, North Carolina, November 9-11, 1983:

J. S. Lee, J. F. Fellers, J. L. White, and J. S. Lin, "SAXS Studies of Kevlar/Epoxy Composites"

M.-Y. Tang, P. A. Westbrook, J. F. Fellers, and J. S. Lin, "Reflection Phenomena in the Study of Crazes by SAXS"

J. C. Wang, J. B. Bates, and N. J. Dudney, "Lithium β -Alumina" (invited paper)

P. A. Westbrook, J. F. Fellers, and J. S. Lin, "The Stress and Time Dependence of Localized Straining in Polystyrene at the 100 Å Lever via SAXS"

Materials Research Society Annual Meeting, Boston, Massachusetts, November 14-17, 1983:

B. R. Appleton, "Ion Damage and Mixing Effects in Ge" (invited paper)

M. J. Aziz, "Crystal Growth and Solute Trapping"

John H. Barrett, "Ion Dechanneling in Elastically Strained Superlattices" (invited paper)

J. L. Boldú, E. Muñoz P., K. L. Tsang, M. M. Abraham, and Y. Chen, "The Effect of Ionizing Radiation on Nickel-Doped MgO "

G. J. Clark, J. E. E. Baglin, F. M. d'Heurle, C. W. White, and G. Farlow, "Ion Beam Irradiation of Metal Films on SiO_2 "

G. Farlow, C. W. White, C. J. McHargue, and B. R. Appleton, "Behavior of Implanted $\alpha\text{-Al}_2\text{O}_3$ in an Oxidizing Annealing Environment"

O. W. Holland and J. Narayan, "High Current Density Implantation and Ion Beam Annealing in Si"

G. E. Jellison, Jr., and R. F. Wood, "Stress Effects of Raman Measurements of Pulsed-Laser-Annealed Silicon"

E. M. Kaufmann, R. G. Masket, C. A. Colmenares, and B. R. Appleton, "Enhancement of Uranium Oxidation Resistance by Molybdenum Implantation"

B. C. Larson, C. W. White, T. S. Noggle, J. F. Barhorst, and D. M. Mills, "Time-Resolved X-ray Diffraction Study of Ge during Pulsed-Laser Irradiation"

D. H. Lowndes, R. F. Wood, C. W. White, and J. Narayan, "Pulsed-Laser Melting of Amorphous Silicon: Time-Resolved and Post-Irradiation Studies"

J. Llopis, C. Ballesteros, R. Gonzalez, and Y. Chen, "Cathodoluminescence Emission from Crystalline LiNbO_3 "

C. J. McHargue, C. W. White, B. R. Appleton, G. C. Farlow, and J. M. Williams, "Ion Beam Modification of Ceramics" (invited paper)

P. J. McMarr, K. Vadam, and J. Narayan, "Characterization of Ion-Implanted Silicon by Spectroscopic Ellipsometry"

J. Narayan, "Defect Annealing and Diffusion Mechanisms during Rapid Thermal Annealing of Semiconductors" (invited paper)

J. Narayan, "Formation of Metal Colloids in Oxides" (invited paper)

J. Narayan, D. Fathy, and O. W. Holland, "Atomic Displacement Cascades and Amorphization in Ion-Implanted Silicon"

S. J. Pennycook, J. Narayan, and O. W. Holland, "Point Defect Supersaturation and Enhanced Diffusion in SPE Regrown Silicon"

S. J. Pennycook, J. Narayan, and O. W. Holland, "Dopant Site Location by Electron Channeling in Ion-Implanted Silicon"

D. B. Poker, O. W. Holland, and B. R. Appleton, "Dose Dependence of Ion-Beam Mixing of Au on Amorphous and Single-Crystalline Si and Ge"

D. B. Poker, O. W. Holland, and B. R. Appleton, "Ion Beam Mixing of Au on Amorphous and Single-Crystalline Si"

P. P. Pronko, A. W. McCormick, D. C. Ingram, A. K. Rai, J. A. Woollam, B. R. Appleton, and D. B. Poker, "Ion Irradiation Smoothing and Film Bonding for Laser Mirrors"

Edward Sonder, "Electrical Properties of Magnesium Aluminate Spinel"

K. L. Tsang, Y. Chen, and H. T. Tohver, "Time Dependence of Current Injection Phenomena in the Pt-MgO-Pt System at High Temperatures"

J. F. Wendelken, D. M. Zehner, P. A. Bruhwiler, R. S. Hathcock, and G. R. Gruzalski, "An XPS Investigation of NO Adsorption and Reaction on the (100) and (110) Cu Surfaces"

C. W. White, "Ion Implantation for Near-Surface Modification of Materials" (invited paper)

C. W. White, H. Naramoto, C. J. McHargue, G. Farlow, and B. R. Appleton, "Modification of the Near-Surface Region of Al_2O_3 by Ion Implantation" (invited paper)

J. M. Williams, G. M. Beardsley, R. A. Buchanan, and R. K. Bacon, "Effect of N-Implantation on the Corrosive-Wear Properties of Surgical Ti-6Al-4V Alloy"

R. F. Wood, D. H. Lowndes, and J. Narayan, "Solidification of Highly Undercooled Silicon: Bulk Nucleation and Amorphous Phase Formation"

R. T. Young, "Semiconductor Processing with Excimer Lasers: An Overview" (invited paper)

Third International Symposium on Production and Neutralization of Negative Ions and Beams, Upton, New York, November 14-18, 1983:

Ordean S. Nen and Mark T. Robinson, "Ion Backscattering from Layered Targets" (invited paper)

American Physical Society Fall Meeting, San Francisco, California, November 20-23, 1983:

S. J. Pennycook, "Electronic and Compositional Studies of Defects in Diamond" [Bull. Am. Phys. Soc. 28, 1318 (1983)] (invited paper)

Program Review Meeting, Insulators for Fusion Magnets, Philadelphia, Pennsylvania, December 6, 1983:

R. R. Colman, Jr., "Low-Temperature Irradiation Studies" (invited paper)

International Symposium on Vacuum Technology and Nuclear Application, Trombay, Bombay, India, December 6-9, 1983:

J. Marayan, "Laser Processing of Materials and Applications"

The Sixth International Conference on Lasers and Applications, San Francisco, California, December 12-16, 1983:

R. B. James, "Optically Induced Intervalence-Band Transitions in Germanium by the Absorption of 1.06- μ m Picosecond Pulses"

R. B. James, "Electron-Hole Plasma Formation in Semiconductors Due to Absorption of Pulsed CO₂ Laser Light"

R. F. Wood and R. T. Young, "Excimer Laser Processing of Semiconductors: Fabrication of High-Efficiency Solar Cells" (invited paper)

Biointeractions '84, London, England, January 4-6, 1984:

R. A. Buchanan and J. M. Williams, "Ion Implantation as a Means to Improve the Corrosive-Wear Properties of Surgical Alloys"

INDO-U.S. Workshop on Diffusion in Solids, Bombay, India, January 9-14, 1984:

J. B. Bates, "Ionic and Molecular Transport in Beta- and Beta'-Alumina" (invited paper)

Technology Transfer Workshop on New Zinc Oxide Varistor Materials, Knoxville, Tennessee, January 11, 1984:

F. A. Mdine, "Overview of ZnO Varistors" (invited paper)

High-Energy Excitations in Condensed Matter Workshop, Los Alamos, New Mexico, February 13-15, 1984:

J. F. Cooke, J. A. Blackman, and T. Morgan, "Theoretical Study of Neutron Scattering Cross Sections in Semiconductors" (invited paper)

H. A. Mook, "Introduction to Neutron Scattering by Magnetic Excitations"

Workshop on Sample Environment in Neutron and X-ray Experiments, Grenoble, France, February 13-15, 1984:

W. C. Koehler, "Magnetic Fields and Neutron Scattering" (invited paper)

Biophysical Society Meeting, San Antonio, Texas, February 19-23, 1984:

E. Uberbacher, G. J. Bunick, and V. Ramakrishnan, "Structural Analysis of HMG-17 Nucleosomes by Small-Angle Neutron Scattering"

Meeting of the Major Materials Facilities Committee of the National Research Council, Washington, D.C., February 26, 1984:

D. E. Bartine, J. W. Cable, H. A. Mook, R. M. Moon, and R. M. Nicklow, "ORNL Presentation to the Major Materials Facilities Committee of the National Research Council"

Annual Meeting of the Metallurgical Society of AIME, Los Angeles, California, February 26-March 1, 1984:

S.-J. Chang and S. M. Ohr, "Crack Tip Blunting versus Brittle Extension" [J. Met. 35, 11 (1983)]

S.-J. Chang and S. M. Ohr, "Inclined Pileup of Screw Dislocations at the Crack Tip with a Dislocation-Free Zone" [J. Met. 35, 11 (1983)]

D. K. Christen, H. R. Kerchner, A. Das Gupta, S. T. Sekula, and Y. T. Chou, "The Flux-Line Lattice in a Niobium Bicrystal" [J. Met. 35, 52 (1983)]

H. R. Kerchner, D. K. Christen, A. Das Gupta, S. T. Sekula, and Y. T. Chou "Flux-Line Pinning by the Grain Boundary in a Niobium Bicrystal" [J. Met. 35, 52 (1983)]

T.-M. Lu, J. M. Pimbley, and G.-C. Wang, "Antiphase Domain Size Distribution in an Overlayer during Growth" [J. Met. 35, 49 (1983)]

S. M. Ohr and S.-J. Chang, "Dislocation Shielding Model of Fracture Toughness" [J. Met. 35, 90 (1983)]

C. G. Park and S. M. Ohr, "Geometry of Crack Tip Deformation in BCC Metals" [J. Met. 35, 12 (1983)]

J. J. Stephens, J. B. Kortright, and S. Spooner, "Particle Size Distributions in Oxide Dispersion Strengthened Alloys Determined by SAXS" [J. Met. 35, 18 (1983)]

Collaborative Working Group on Radiation Effects in Crystalline Nuclear Waste Forms, Santa Fe, New Mexico, March 1-2, 1984:

L. A. Boatner, "Nuclear Waste Characterization Studies in the ORNL Solid State Division"

NATO Advanced Research Workshop on Condensed Matter Research Using Neutrons, Today and Tomorrow, Abingdon, Oxfordshire, United Kingdom, March 26-29, 1984:

J. F. Cooke, J. A. Blackman, and T. Morgan, "Band Structure Effects in the Electronic Properties of Solids Assessable in Neutron Scattering Studies"

American Physical Society Meeting, Detroit, Michigan, March 26-30, 1984:

D. K. Christen, H. R. Kerchner, S. T. Sekula, and Y. K. Chang, "Absolute Measurement of the Temperature-Dependent Penetration Depth in V_3Si " [Bull. Am. Phys. Soc. 29, 384 (1984)]

H. L. Davis and G.-C. Wang, "Registry Relaxation of the W(112) Surface—A (1x1) Reconstruction" [Bull. Am. Phys. Soc. 29, 221 (1984)]

G. R. Gruzalski, D. M. Zehner, and J. F. Wendelken, "The Adsorption and Evolution of Oxygen on Cu(110)" [Bull. Am. Phys. Soc. 29, 433 (1984)]

R. B. James and D. L. Smith, "Interaction of a Tunable Probe Beam with a High-Intensity Pulsed CO_2 Laser Beam in p-Type Germanium" [Bull. Am. Phys. Soc. 29, 477 (1984)]

M. L. Kasakevich, H. R. Brown, and G. D. Wignall, "Morphology of PVC by Small-Angle Neutron Scattering" [Bull. Am. Phys. Soc. 29, 450 (1984)]

E. Lee, L. L. Chase, and L. A. Boatner, "Quasielastic Light Scattering in $KTa_{1-x}Nb_xO_3$ " [Bull. Am. Phys. Soc. 29, 557 (1984)]

S. H. Liu and K.-M. Ho, "The f Band in Ce and Its Mixed-Valent Compounds" [Bull. Am. Phys. Soc. 29, 404 (1984)]

F. A. Modine, T. W. Haywood, and L. S. Darken, "Optical and Electrical Properties of Zirconium Carbide" [Bull. Am. Phys. Soc. 29, 431 (1984)]

J. Narayan, R. B. James, and O. W. Holland, "Pulsed CO_2 Laser Annealing of Ion-Implanted Silicon" [Bull. Am. Phys. Soc. 29, 389 (1984)]

S. M. Ohr, "Electron Microscope Studies of Crack Propagation in Metals" [Bull. Am. Phys. Soc. 29, 417 (1984)] (invited paper)

S. M. Ohr, S.-J. Chang, and R. Thomson, "Dislocation Emission From a Wedge Crack" [Bull. Am. Phys. Soc. 29, 489 (1984)]

S. J. Pennycook, J. Narayan, and O. W. Holland, "Electron Channeling Studies of Ion-Implanted Silicon"

O. A. Pringle, R. Calvo, and R. E. Parra, "Magnetic Structure of Nickel Diglycine Dihydrate" [Bull. Am. Phys. Soc. 29, 520 (1984)]

B. C. Sales, M. M. Abraham, J. B. Bates, and L. A. Boatner, "Spectroscopic Study of Iron in Crystalline and Glassy Lead Metaphosphate" [Bull. Am. Phys. Soc. 29, 297 (1984)]

S. T. Sekula, J. R. Thompson, D. K. Christen, and G. M. Beardsley, "Formation and Modification of Vanadium Nitride Films" [Bull. Am. Phys. Soc. 29, 483 (1984)]

A. K. Sen, R. Mills, T. Kaplan, and L. J. Gray, "Electronic Density of States of a Liquid/Amorphous Metal without Short-Range Order—Beyond the CPA" [Bull. Am. Phys. Soc. 29, 379 (1984)]

R. Thomson, S. M. Ohr, and S.-J. Chang, "Conformal Mapping Techniques for Crack-Dislocation Calculations" [Bull. Am. Phys. Soc. 29, 489 (1984)]

J. C. Wang, "Shell Model Calculations for Stoichiometric Na β -Alumina" [Bull. Am. Phys. Soc. 29, 231 (1984)]

X.-Y. Zhu, K.-M. Ho, and S. H. Liu, "Investigation of d-f Correlation in Mixed-Valent Ce Systems" [Bull. Am. Phys. Soc. 29, 403 (1984)]

Conference on Statistical Mechanics, University of California, Davis, California, March 29–31, 1984:

Mark Rasolt, "Exact Identities for Both Single- and Two-Component Nonuniform Fermi Systems" (invited paper)

Sixth European Conference on Surface Science (ECOSS6), York, England, April 1–5, 1984:

J. R. Noonan, H. L. Davis, and W. Erley, "Truncation-Induced Relaxations of a High-Index Surface: Al(311)"

International Topical Conference on Kinetics of Aggregation and Gelation, Athens, Georgia, April 2–4, 1984:

S. H. Liu, "Frequency Spectrum of an Elastic Sierpinski Gasket"

Stephen Spooner, "A Small-Angle Neutron Scattering Study of the Decomposition of Fe-28Cr-10.5Co"

The Werner Brandt Workshop on Penetration Phenomena: Inelastic Near-Surface Interactions, Oak Ridge, Tennessee, April 12–13, 1984:

S. J. Pennycook, "Comments on the Image Contrast from Inelastically Scattered Electrons," (invited paper)

J. F. Wendelken, "Electron Energy Loss Spectroscopy—Applications to Surface Studies" (invited paper)

Second International Symposium on Resonance Ionization Spectroscopy and Its Applications, Knoxville, Tennessee, April 16–20, 1984:

Mark T. Robinson, "The Physics of Ion Sputtering" (invited paper)

Workshop on High Heat Flux Materials for TFCX, Germantown, Maryland, April 17–18, 1984:

J. B. Roberto, "Critical Near-Term Materials R&D for TFCX" (invited paper)

American Physical Society Meeting, Washington, D.C., April 23-26, 1984:

B. R. Appleton, "Ion Beam and Laser Processing of Solids" [Bull. Am. Phys. Soc. 29, 746 (1984)] (invited paper)

Eighty-Sixth Annual Meeting of the American Ceramic Society, Pittsburgh, Pennsylvania, April 29-May 3, 1984:

N. J. Dudney, J. B. Bates, J. C. Wang, and W. E. Brundage, "Thermodynamics of the Hydration of Na β - and Na β' -Alumina" [Am. Ceram. Soc. Bull. 63, 424 (1984)]

G. C. Farlow, C. W. White, B. R. Appleton, M. P. Angelini, and C. J. McHargue, "Temperature Effects on Ion-Induced Damage in Al_2O_3 " [Am. Ceram. Soc. Bull. 63, 508 (1984)]

J. R. Martinelli, R. A. Weeks, E. Sonder, and R. A. Zuhr, "Oxygen Diffusion in Magnesium Oxide Subjected to Electric Fields" [Am. Ceram. Soc. Bull. 63, 458 (1984)]

E. Sonder and R. A. Weeks, "Degradation of Electrical Properties of Spinel and Other Insulating Oxides by Moderate Electric Fields at High Temperatures" [Am. Ceram. Soc. Bull. 63, 426 (1984)]

R. A. Weeks and M. Nasrallah, "Correlation of Electron Magnetic Resonance Spectra with La Concentration in $BaTiO_3$ and $SrTiO_3$ Powders" [Am. Ceram. Soc. Bull. 63, 482 (1984)]

Third NCSASR Users' Group Meeting and Workshop in Small-Angle Methods, Oak Ridge, Tennessee, April 3-May 2, 1984:

G. J. Bunick, "Modeling of the Nucleosome HMG-17 Complex by SANS Data"

American Society of Metals Meeting on Materials for Energy Systems, Washington, D.C., May 1-3, 1984:

B. R. Appleton and C. W. White, "Surface Modification of Solids" (invited paper)

Eleventh Annual Symposium of the North Central Chapter of the American Vacuum Society, Detroit, Michigan, May 3, 1984:

D. M. Zehner, "Characterization of Laser-Annealed Semiconductor Surfaces" (invited paper)

American Vacuum Society Meeting, Knoxville, Tennessee, May 3-5, 1984:

O. W. Holland, D. Fathy, J. Narayan, and B. R. Appleton, "Ion Beam Mixing" (invited paper)

J. M. Williams, G. M. Beardsley, R. A. Buchanan, and R. K. Bacon, "Wear Improvement of Ti-6Al-4V Hip Joint Alloy by Ion Implantation" (invited paper)

Sixth International Conference on Plasma-Surface Interactions in Controlled Fusion Devices, Nagoya, Japan, May 14-18 1984:

C. K. Chen, J. Bohdanský, W. Eckstein, and M. T. Robinson, "Energy Reflection Coefficient for H^+ Ions at Energies between 10 and 80 keV"

T. B. Cook, P. W. King, and J. B. Roberto, "Time-Resolved Erosion Measurements at a Reference Limiter in ISX-B Using Laser-Induced Fluorescence"

P. H. Edmonds, P. Mioduszewski, J. B. Roberto, R. D. Watson, M. F. Smith, and K. J. Dietz, "The IXS-JET Beryllium Limiter Experiment"

J. B. Roberto and R. Behrisch, "Synergistic Effects in Plasma Surface Interactions" (invited paper)

J. B. Roberto, J. Roth, E. Taglauer, and O. W. Holland, "The Use of Isotopically Enriched Carbon Probes for Erosion/Deposition Measurements in the ASDEX Divertor"

J. Roth, J. Bohdanský, and J. B. Roberto, "On the Influence of Impurities on the High-Temperature Sputtering Yield of Graphite"

First National Meeting of the American Crystallographic Association on Surface Crystallography, Lexington, Kentucky, May 21-25, 1984:

H. L. Davis and J. R. Noonan, "Multilayer Relaxation in Metallic Surfaces—An Outgrowth of Precision LEED Analysis" (invited paper)

J. R. Noonan and H. L. Davis, "LEED Structure Analysis of the Al(311) Surface"

S. Spooner and J. S. Lin, "Small-Angle Scattering as a Method of Catalyst Characterization"

J. F. Wendelken and G.-C. Wang, "Structure of Reconstruction Domains on Flat and High Step Density W(001) Surfaces"

S. P. Withrow, R. J. Culbertson, and J. H. Barrett, "Ion Scattering Investigation of Reconstruction in the Au(110)-(1×2) Surface"

Workshop on Instrumentation for the Advanced High Flux Reactor, Oak Ridge, Tennessee, May 30, 1984:

J. B. Hayter, "Instrumentation at the I.L.L.—Development and Demand" (invited paper)

R. M. Moon, "Experimental Facilities at HFIR-II" (invited paper)

American Association of Immunologists Meeting, St. Louis, Missouri, June 3-7, 1984:

G. J. Bunick, V. Ramakrishnan, and E. Uberbacher, "Structural Analysis of HMG-17 Nucleosomes by Small-Angle Neutron Scattering"

Second European Materials Research Society Meeting, Strasbourg, France, June 4-8, 1984:

B. R. Appleton, "Morphological Instabilities in Ion-Irradiated Amorphous Ge"

Twelfth DOE Surface Studies Conference, Oak Ridge, Tennessee, June 11-14, 1984:

J. R. Noonan and H. L. Davis, "Vacuum-Solid Interface Effects on Aluminum"

Forty Fourth Annual Conference on Physical Electronics, Princeton, New Jersey, June 18-20, 1984:

R. A. DiDio, D. M. Zehner, and E. W. Plummer, "O₂ on Cu(110): Molecular Precursor to Dissociative Adsorption"

J. M. Pimbley, T.-M. Lu, and G.-C. Wang, "Antiphase Domain Wall Distribution during Overlayer Growth"

J. F. Wendelken and G.-C. Wang, "Finite Size Effect on the Critical Behavior of the 2D-XY Phase Transition of W(001) Surfaces"

Conference on Lasers and Electro-Optics, CLEO '84, Anaheim, California, June 19-22, 1984:

R. B. James, J. Narayan, W. H. Christie, O. W. Holland, and R. F. Wood, "Pulsed CO₂ Laser Annealing of Silicon"

D. H. Lowndes, F. A. Modine, E. Sonder, Y. Chen, and W. J. Choyke, "Pulsed Excimer and CO₂ Laser Processing for Fabrication of ZnO and SiC Devices"

D. H. Lowndes and T. W. Raudorf, "Application of Pulsed-Laser Processing in the Fabrication of Ge Nuclear Radiation Detectors"

Symposium on the Application of Synchrotron Radiation and Neutron Scattering to Materials Science, East Hanover, New Jersey, June 25-26, 1984:

W. C. Koehler, "Small-Angle Neutron and X-ray Scattering in Materials Science" (invited paper)

Third Trieste IUPAP Semiconductor Symposium on High Excitation and Short Pulse Phenomena, Trieste, Italy, July 1-6, 1984:

D. H. Lowndes and R. F. Wood, "Studies of Pulsed-Laser Melting and Rapid Solidification Using Amorphous Silicon" (invited paper)

High-Efficiency Crystalline Silicon Solar Cell Research Forum, Phoenix, Arizona, July 9-11, 1984:

R. F. Wood and R. T. Young, "Excimer Laser Processing of Silicon Solar Cells" (invited paper)

Conference on the Effects of Modes of Formation on the Structure of Glasses, Nashville, Tennessee, July 9-12, 1984:

O. W. Holland, D. Fathy, J. Narayan, and S. R. Wilson, "Optimized Conditions for the Formation of Buried Insulating Layers in Si by High-Dose Implantation of Oxygen"

B. C. Sales, M. M. Abraham, J. B. Bates, and L. A. Boatner, "Fundamental Structural Properties of Lead-Iron Phosphate Glasses"

1984 Gordon Research Conference on Particle-Solid Interactions, Plymouth, New Hampshire, July 9-13, 1984:

B. R. Appleton, "Anomalous Damage Distributions in Molecular Ion-Implanted Semiconductors"

R. J. Culbertson, J. H. Barrett, and S. P. Withrow, "Angular Dependence of Ion Scattering Surface Yield for Large Outer Layer Relaxations"

Sixth American Conference on Crystal Growth/Sixth International Conference on Vapor Growth and Epitaxy, Atlantic City, New Jersey, July 15-20, 1984:

L. A. Boatner, F. A. Modine, M. Linvill, and B. C. Sales, "The Growth and Characterization of Single Crystals of Semiconducting $KTaO_3$ "

Y. K. Chang, W. Uelhoff, A. Fattah, and G. Hanke, "Growth and Characterization of Cu_3Au Single Crystals"

J. Narayan, "Interface Structure and Instability during Crystallization of Semiconductors" (invited paper)

S. J. Pennycook, J. Narayan, and O. W. Holland, "Enhanced Diffusion from Interstitial Trapping during SPE Growth of Si Alloys"

Fourth Analytical Electron Microscopy Workshop, Bethlehem, Pennsylvania, July 16-20, 1984:

S. J. Pennycook, "Atom Location by Electron Channeling Analysis" (invited paper)

Ion Beam Modification of Materials Conference, Ithaca, New York, July 16-20, 1984:

B. R. Appleton, G. C. Farlow, W. H. Christie, and P. Ashley, "Implantation and Ion Beam Mixing in $LiNbO_3$ "

B. R. Appleton, O. W. Holland, D. B. Poker, J. Narayan, and D. Fathy, "Morphological Instabilities and Ion Beam Mixing in Ge"

G. C. Farlow, C. W. White, C. J. McHargue, and B. R. Appleton, "Annealing of Implanted Al_2O_3 in a Reducing Environment"

D. Fathy, J. Narayan, O. W. Holland, B. R. Appleton, and R. F. Davis, "High Resolution and Microanalytical Investigations of Ni-SiC Mixed Layers"

C. A. Hewett, S. S. Lau, I. Suni, and D. B. Poker, "The Effect of Boundary Conditions in Ion Mixing of Multilayered Ni-Si Samples"

O. W. Holland and D. Fathy, "Ion Beam Processing of Si"

C. S. Pai, S. S. Lau, and D. B. Poker, "A Comparison Between Thermal Annealing and Ion Mixing of Alloyed and Multilayer Ni-W Films on Si"

D. B. Poker and B. R. Appleton, "Anomalous Ion Beam Mixing of Au on Amorphous and Single-Crystalline Si"

C. W. White, G. C. Farlow, C. J. McHargue, P. S. Sklad, M. P. Angelini, and B. R. Appleton, "Formation of Amorphous Layers in Al_2O_3 by Ion Implantation"

J. M. Williams, B. R. Appleton, C. J. McHargue, P. S. Sklad, G. M. Begun, P. Angelini, and R. C. Davis, "Ion Implantation Effects in SiC"

J. M. Williams, R. A. Buchanan, and G. M. Beardsley, "Ion Implantation of Surgical Ti-6Al-4V Alloy"

NATO Advanced Study Institute on the Physics of Plasma-Wall Interactions in Controlled Fusion, Val-Morin, Quebec, Canada, July 30-August 10, 1984:

R. A. Zuhr, "Deposition Probe Studies of the TEXTOR Plasma Edge"

DOE-DMS Workshop on Theory and Computer Simulation of Materials Structures and Imperfections, Houghton, Michigan, August 6-10, 1984:

R. F. Wood, "Introductory Overview Talk" (invited paper)

International Workshop on the Electromagnetic Response of Surfaces, Cholula, Puebla, Mexico, August 6-10, 1984:

K.-M. Ho and S. H. Liu, "Electroreflectance Spectroscopy as a Probe of the Electronic Structure at the Metal-Electronic Interface"

Seventeenth International Conference on the Physics of Semiconductors, San Francisco, California, August 6-10, 1984:

R. B. James, J. Narayan, W. H. Christie, O. W. Holland, and R. F. Wood, "Pulsed CO_2 Laser Annealing of Silicon"

D. H. Lowndes, G. E. Jellison, Jr., R. F. Wood, and R. Carpenter, "Time-Resolved Studies of Ultrarapid Solidification of Highly Undercooled Molten Silicon Formed by Pulsed-Laser Irradiation"

Thirteenth Congress and General Assembly of the International Union of Crystallography, Hamburg, Federal Republic of Germany, August 9-18, 1984:

H. L. Davis and J. R. Noonan, "Accuracy and Reliability of Surface Structure Determined by LEED" (invited paper)

B. C. Larson, J. Z. Tischler, C. W. White, T. S. Noggle, and D. M. Mills, "Nanosecond Resolution X-ray Study of Si and Ge during Pulsed-Laser Irradiation"

M.-Y. Tang and J. S. Lin, "A New Treatment of the Theory for Small-Angle X-ray Scattering with Applications to Polystyrene Crazes"

M.-Y. Tang, P. A. Westbrook, J. F. Fellers, and J. S. Lin, "An Interpretation of the Dynamic Morphological Character of Polystyrene Crazes Using Small-Angle X-ray Surface and Volume Scattering Theory"

G. D. Wignall, D. McAlea, J. M. Schultz, and K. H. Gardner, "Small-Angle Neutron Scattering from Poly(ethylene terephthalate)"

First International Conference on the Structure of Surfaces, Berkeley, California, August 13-16, 1984:

H. L. Davis and G.-C. Wang, "Layer Relaxation of the Clean W(112) Surface and Its Variation with Adsorbed Oxygen"

J. R. Noonan and H. L. Davis, "Several Faces of Aluminum" (invited paper)

Seventeenth International Conference on Low-Temperature Physics, Karlsruhe, Federal Republic of Germany, August 15-22, 1984:

D. K. Christen, H. R. Kerchner, S. T. Sekula, and Y. K. Chang, "Experimental Determination of the Temperature-Dependent Penetration Depth in V_3Si "

H. R. Kerchner, D. K. Christen, A. Das Gupta, S. T. Sekula, B. C. Cai, and Y. T. Chou, "Flux-Line Pinning by the Grain Boundary in Niobium Bicrystals"

J. R. Thompson, S. T. Sekula, D. H. Lowndes, and H. R. Khan, "Formation of Superconductive Al(GeSi) Alloys by Low-Temperature Laser Quenching Techniques"

Symposium on Small-Angle Scattering and Related Methods, Hamburg, Federal Republic of Germany, August 20-23, 1984:

J. S. Lin, "Dynamic Small-Angle X-ray Scattering of Polymers"

M. Y. Tang, J. F. Fellers, and J. S. Lin, "Small-Angle X-ray Scattering Studies of Crazes in Oriented Polystyrene"

G. D. Wignall, "Resolution Effects in SANS Studies of Synthetic Polymers on the Oak Ridge 30-m Instrument"

G. D. Wignall, V. R. Ramakrishnan, J. M. O'Reilly, S. M. Melpolder, and L. W. Fisher, "Small-Angle Neutron Scattering of Polymer Core-Shell Latex Particles" (invited paper)

International Conference on Defects in Insulating Crystals, Salt Lake City, Utah, August 20-24, 1984:

M. M. Abraham, L. A. Boatner, M. Rappaz, and J. O. Ramey, "EPR Observations of Zirconium and Hafnium in the Trivalent State in $LuPO_4$, YPO_4 , and $ScPO_4$ Single Crystals"

Y. Chen, "Electron Trapping Properties and Sensitivity to Ionizing Radiation of the Hydride Ion in Refractory Oxides" (invited paper)

R. Gonzalez, Y. Chen, and K. L. Tsang, "Diffusion of Deuterium and Hydrogen in Crystalline Oxides"

Wing-Kit Lee, A. S. Nowick, and L. A. Boatner, "Protonic Conduction in $KTaO_3$ Crystals Doped with Cu or Ni"

R. F. Wood and D. H. Lowndes, "Laser Processing of Wide Band Gap Semiconductors and Insulators"

American Chemical Society Annual Meeting, Philadelphia, Pennsylvania, August 26-31, 1984:

A. M. Fernandez, G. D. Wignall, and L. H. Sperling, "Morphology and Phase Dimensions of Interpenetrating Polymer Networks Based on Polybutadiene and Polystyrene by Small-Angle Neutron Scattering and Electron Microscopy"

K. P. McAlea, J. M. Schultz, G. D. Wignall, and K. H. Gardner, "Small-Angle Scattering from Polyethylene Terephthalate"

G. D. Wignall, "SANS Studies of Synthetic Polymers at the Oak Ridge 30-m Instrument" (invited paper)

Yamada Conference IX on Dislocations in Solids, Tokyo, Japan, August 27-31, 1984:

S.-J. Chang and S. M. Ohr, "Inclined Dislocation Emission at a Crack Tip versus Brittle Extension"

R. M. Thomson, I.-H. Lin, S. M. Ohr, and S.-J. Chang, "Dislocation Interactions in Presence of Cracks"

Joint U.S.-Japan Seminar on Materials Science of Fracture, Sendai, Japan, September 2-4, 1984:

S.-J. Chang, "Elastic Interaction of Dislocations with Wedge" (invited paper)

S. M. Ohr, "Electron Microscope Studies of Crack Tip Deformation" (invited paper)

Fall Meeting of the Metallurgical Society of AIME, Detroit, Michigan, September 16-20, 1984:

S.-J. Chang and S. M. Ohr, "Inclined Dislocation Emission versus Brittle Extension at Crack Tip"

S. M. Ohr, J. A. Horton, S.-J. Chang, and R. Thomson, "Mixed Mode Crack Propagation in Molybdenum"

C. G. Park and S. M. Ohr, "TEM Studies of Crack Tip Deformation in BCC Metals at Low Temperatures"

International Conference on Surface Modification of Metals by Ion Beams, Heidelberg, Federal Republic of Germany, September 17-21, 1984:

C. J. McHargue, G. C. Farlow, C. W. White, J. M. Williams, B. R. Appleton, and H. Naramoto, "The Amorphization of Ceramics by Ion Beams"

C. J. McHargue, M. B. Lewis, J. M. Williams, and B. R. Appleton, "The Reactivity of Ion-Implanted Silicon Carbide"

J. M. Williams and R. A. Buchanan, "Ion Implantation of Surgical Ti-6Al-4V Alloy" (invited paper)

SEMINARS

SOLID STATE DIVISION SEMINARS AT ORNL

During this period F. A. Modine served as Seminar Chairman June 1981–September 1983, and D. H. Lowndes, October 1983–continuing. The following seminars were held:

- "The Structure and Dynamics of Molten Salts Studied by Neutron and Light Scattering," E. W. J. Mitchell, Oxford University, Oxford, England
- "Defects in Silicon and Gallium Arsenide," P. S. Dobson, University of Birmingham, Birmingham, England
- "Phase Transitions on Nickel Single-Crystal Surfaces at the Curie Temperature," J. C. Hamilton, Sandia National Laboratories, Livermore, California
- "High-Temperature Resistivity and a New Thermal Defect,"¹ G. Grimvall, Royal Institute of Technology, Stockholm, Sweden
- "Applications of Synchrotron X-ray Topography to the Study of Deformation and Fracture of Materials,"² J. Bilello, State University of New York, Stony Brook, New York
- "Neutron Scattering Studies of Li Diffusion in LiAl: a Li-Ion and Electron Conductor," T. Brun, Argonne National Laboratory, Argonne, Illinois
- "Ion Implantation in Metals and Carbides and Industrial Applications," G. Dearnaley, Atomic Energy Research Establishment, Harwell, England
- "Modification of the Properties of Benzene-Derived Graphite Fibers by Intercalation and Ion Implantation," M. S. Dresselhaus, Massachusetts Institute of Technology, Cambridge, Massachusetts
- "The Significance of High-Pressure Studies of Magnetism from Valence Fluctuations to Liquid ³He," J. Schilling, Iowa State University, Ames, Iowa
- "Silicon Carbide—A Materials Challenge," J. W. Faust, Jr., University of South Carolina, Columbia, South Carolina
- "The Role of Spin Conservation in Spin Dynamics in Solids," F. Mezei, Institut Laue-Langevin, Grenoble, France
- "Influence of Impurity-Stabilized Defect Structures on the Superconducting Transition Temperature of Ion-Implanted Transition Metals," G. Linker, Kernforschungszentrum Karlsruhe, Federal Republic of Germany
- "Surface-Enhanced Raman Scattering by Molecules on Metal Island Films" C. Y. Chen, Universal Energy Systems, Dayton, Ohio
- "Optical Detection of Magnetic Resonance for Defects in Semiconductors," G. D. Watkins, Lehigh University, Bethlehem, Pennsylvania
- "Use of Infrared Techniques to Characterize Ion-Implanted Materials," C. N. Waddell, University of Southern California, Los Angeles, California
- "Ion-Beam-Induced Surface Modification of Alloys," H. Wiedersich, Argonne National Laboratory, Argonne, Illinois
- "Small-Angle Neutron Scattering and Polymer Physics," H. Benoit, Centre National de la Recherche Scientifique, Strashbourg, France
- "Order/Disorder Transition on the Growth Surfaces of Polymer Crystals," D. Sadler, University of Bristol, Bristol, England

- "Structural Properties of HNO_3 -Graphite Intercalation Compounds Using Photon Scattering and Neutron Diffraction," G. Shahal, Nuclear Research Center, Negev, Israel
- "Electron Spin Resonance of Induced Defects in Oxide Hosts: the Breit-Rabi Equation and Experiments," H. Kawazoi, Tokyo Metropolitan University, Tokyo, Japan
- "Neutron Diffraction Studies of Amorphous Solids," A. C. Wright, University of Reading, Reading, England
- "Electronic States of Actinides and Actinide Compounds,"¹ P. Weinberger, University of Vienna, Vienna, Austria
- "Recent Neutron Scattering Experiments on Polymers: Structure, Conformation, and Diffusion," M. Stamm, Kernforschungsanlage Jülich, Federal Republic of Germany
- "The In Situ High-Voltage Electron Microscopy and X-ray Topography for Materials Research and Development,"² T. Imura, Nagoya University, Nagoya, Japan
- "Interface Kinetics during Pulsed-Laser Melting of Semiconductors," M. O. Thompson, Cornell University, Ithaca, New York
- "Quasi-Particle and Non-Quasi-Particle Transport in Solids,"¹ P. B. Allen, State University of New York, Stony Brook, New York
- "Small-Angle Scattering from Polymers in a Shear Gradient," R. Oberthur, Institut Laue-Langevin, Grenoble, France
- "Nature of Magnetic Moments in Heusler Alloys, Magnanese, Iron, MnO , and NiO ,"¹ J. Kubler, University of Darmstadt, Darmstadt, Federal Republic of Germany
- "Ordering of Carbon Vacancies in Nonstoichiometric Transition-Metal Carbides," J. Hauck, Kernforschungsanlage Jülich, Federal Republic of Germany
- "Theory of Magnetic Phase Transitions in Metals,"¹ B. L. Gyorffy, University of Bristol, Bristol, England
- "Physics of Fracture," R. M. Thomson, National Bureau of Standards, Washington, D.C.
- "Recent Progress in the Development of Novel Inorganic Materials," D. G. H. Ballard, Imperial Chemical Industries, Runcorn, England
- "Chemical and Physical Behavior of Graphite under Thermal and Energetic Hydrogen Bombardment," V. Philipps, Kernforschungsanlage Jülich, Federal Republic of Germany
- "Exact Results in the Theory of X-ray Spectra of Metals,"⁴ G. D. Mahan, Indiana University, Bloomington, Indiana
- "Quantum Theory of Localized Defects,"¹ M. Schluter, Bell Laboratories, Murray Hill, New Jersey
- "Kinetics of Solid Phase Crystallization in Ion-Implanted and Ion-Deposited Amorphous Silicon Films," G. L. Olson, Hughes Research Laboratories, Malibu, California
- "Silicon Carbide—Looking Back and Looking Forward—A Personal View," W. J. Choyke, University of Pittsburgh and Westinghouse R&D Center, Pittsburgh, Pennsylvania
- "Random Field Effects in Two and Three Dimensions," V. Jaccarino, University of California, Santa Barbara, California
- "Cluster Study of the Interaction of an H_2O Molecule with the $\text{Al}(100)$ Surface,"¹ J. Muller, Kernforschungsanlage Jülich, Federal Republic of Germany
- "Multicolor Solar Cells and Their Fabrication Using MOCVD," L. Fraas, Chevron Research, Richmond, California
- "Composite Transducers," R. E. Newnham, Pennsylvania State University, University Park, Pennsylvania
- "Interdiffusion of Thin Films of Aluminum and Polysilicon," N. Herbots, Université Catholique de Louvain, Louvain, Belgium
- "Short-Range Order in Fe and Ni above T_c ," J. Brown, Institut Laue-Langevin, Grenoble, France

- "Dynamics of Ablative Photodecomposition of Polymer Films by Pulsed Far-Ultraviolet (193-nm) Laser Radiation," R. Srinivasan, IBM Thomas J. Watson Research Center, Yorktown Heights, New York
- "An Alternative Description of Molecular Electronic Spectra Using Electron Pair Functions,"¹ Y. Ohrn, University of Florida, Gainesville, Florida
- "Orbital Magnetism in Rare-Earth 3D Metallic Compounds," D. Givord, Laboratoire Louis Néel, Centre National de la Recherche Scientifique, Grenoble, France
- "Fatigue and Fracture of Metal Matrix Composites," R. A. Page, Southwest Research Institute, San Antonio, Texas
- "Neutron Irradiation of Superconducting Magnet Components for Fusion Reactors," H. W. Weber, Atom Institut der Österreichischen Universitäten, Vienna, Austria
- "High-Speed Melting and Solidification Phenomena," A. G. Cullis, Royal Signals and Radar Establishment, Malvern, England
- "Neutron eV Spectroscopy: a Revisit to Harmonic Systems and Neutron-Photon Studies," Stephen Lovesey, Rutherford Appleton Laboratory, Chilton, England
- "The Application of Neutron Scattering to Metallurgy," C. Windsor, Atomic Energy Research Establishment, Harwell, England
- "Modeling of Alloy Phase Equilibrium,"¹ J. M. Sanchez, Henry Krum School of Mines, Columbia University, New York, New York
- "The Quantized Hall Effect," R. B. Laughlin, Lawrence Livermore National Laboratory, Livermore, California
- "The Influence of Grain Boundary Segregation and Microstructure on the Electrical Properties of Zinc Oxide Varistors," J. P. Gambino, Massachusetts Institute of Technology, Cambridge, Massachusetts
- "Dynamic Impurities Involving Hydrogen in Very Pure Germanium," L. Falicov, University of California, Berkeley, California
- "Reflections on a Study Leave at Oak Ridge: the Lattice Dynamics of PdTe₂ and InTe,"³ T. Finlayson, Monash University, Clayton, Victoria, Australia
- "Oxygen Ion Conductors," A. Nowick, Columbia University, New York, New York
- "Electronic Metastabilities in Amorphous Silicon," P. C. Taylor, University of Utah, Salt Lake City, Utah
- "Continuum Mechanics of Dislocation Loops and Cracks," H. O. K. Kirchner, Institute for Solid State Physics, University of Vienna, Vienna, Austria
- "SANS Studies of Micellar and Microemulsion Systems," L. Magid, The University of Tennessee, Knoxville, Tennessee
- "Fractal Geometry of Disorderly Condensed Matter," F. Family, Emory University, Atlanta, Georgia
- "Critical Fluctuations in a Dilute Bose Gas: Application to Helium-4 and Vycor,"³ M. Rasolt, Solid State Division, ORNL
- "Low-Energy Absorption Spectra of Magnesium and Zinc in a Lithium Host," M. H. Bakshi, University of Illinois, Urbana-Champaign, Illinois
- "Fractals: Seeking Order in Disorder,"³ S. H. Liu, Solid State Division, ORNL
- "Fundamental Experiments with Neutron Waves," A. Zeilinger, Atom Institut, Vienna, Austria
- "Random Field Effects in Dilute Antiferromagnets," D. Belanger, Brookhaven National Laboratory, Upton, New York
- "Magnetism in Transition Metals," H. Capellmann, University of Aachen, Aachen, Federal Republic of Germany
- "Optical Constance of Solids from Inelastic Electron Scattering," T. J. Aton, University of Virginia, Charlottesville, Virginia

- "Surface-Enhanced Raman Scattering: Paradox or Panacea?" T. Furtak, Rensselaer Polytechnic Institute, Troy, New York
- "Spin Dynamics and Solitons in the One-Dimensional Antiferromagnet, CsCoBr_3 ," S. E. Nagler, IBM Thomas J. Watson Research Center, Yorktown Heights, New York
- "The Structural Stability of Metals and Compounds,"¹ D. G. Pettifor, Imperial College of Science and Technology, London, England
- "Symmetry Determination of DLTs: the Silicon A-Center," C. D. Lamp, University of Missouri, Columbia, Missouri
- "Electronic Structure, Order, and Stability of Transition-Metal Alloys and Compounds,"¹ F. Gautier, Université Louis Pasteur, Paris, France
- "Trace Diffusion at General Concentrations—A Correlated Random Walk on a Lattice" and "Vibrations in Amorphous Solids," R. J. Elliott, Oxford University, Oxford, England
- "Nonlinear Oscillations and Chaos in Semiconductors," R. M. Westervelt, Harvard University, Cambridge, Massachusetts
- "High-Resolution Electron Microscopy of Interfaces," J. M. Gibson, Bell Laboratories, Murray Hill, New Jersey
- "Magnetic Excitations in the Paramagnetic Phase," Per-Anker Lindgard, Risø National Laboratory, Roskilde, Denmark
- "Reconstruction and Chemisorption on Metal Surfaces," P. Estrup, Brown University, Providence, Rhode Island
- "Recent Developments in Spin-Polarized Electron Spectroscopy for Magnetic and Nonmagnetic Materials," J. Kirschner, Kernforschungsanlage Jülich, Federal Republic of Germany
- "The CO Oxidation and NO Reduction Reactions on Single-Crystal Rhodium Surfaces at Low and High Pressures," G. B. Fisher, General Motors Research Laboratories, Warren, Michigan
- "Picosecond Experiments on Nitromethane Photolysis and Laser-Induced Shock," L. S. Goldberg, Optical Sciences Division, Naval Research Laboratory, Washington, D.C.
- "X-ray Diffraction Studies of Grain Boundaries and of Hexatic Order in Liquid Crystals,"² J. Budai, Cornell University, Ithaca, New York, and Bell Laboratories, Murray Hill, New Jersey
- "Anomalous Spin-Relaxation Rates of Dangling Bonds in Amorphous Silicon" and "Fractal Dimensions of Proteins from Electron Spin Relaxation Data," H. J. Stapleton, Department of Physics and Materials Research Laboratory, University of Illinois, Urbana-Champaign, Illinois
- "Observations of the $\text{Cu}_3\text{Au}(001)$ Phase Transition Using a Novel Low-Energy Electron Diffraction System," E. G. McRae, Bell Laboratories, Murray Hill, New Jersey
- "Ultrafast Processes in Amorphous Semiconductors," J. Tauc, Brown University, Providence, Rhode Island
- "LEED Structure Analysis Using a Minicomputer," K. Heinz, Institut für Angewandte Physik, Universität-Erlangen-Nürnberg, Erlangen, Federal Republic of Germany
- "Picosecond Excitation of Silicon with One-Micron Light," S. C. Moss, North Texas State University, Denton, Texas
- "Ion Implantation in Anisotropic Materials," M. S. Dresselhaus, Massachusetts Institute of Technology, Cambridge, Massachusetts
- "High Densities and New Limitations on Spin-Polarized Hydrogen," I. Silvera, Harvard University, Cambridge, Massachusetts
- "Ordering in the Transition-Metal Carbides," J. Venables, Martin Marietta Laboratories, Baltimore, Maryland
- "Response and Lifetime of an Electron-Hole Plasma of Silicon in the Picosecond Range,"³ M. Rasolt, Solid State Division, ORNL
- "Order and Disorder in Amorphous Silicon," M. H. Brodsky, IBM Thomas J. Watson Research Center, Yorktown Heights, New York

- "The Sources of Defects in Indium-Phosphite/Indium-Gallium-Arsenic-Phosphite Emitters," S. Mahajan, Carnegie-Mellon University, Pittsburgh, Pennsylvania
- "Development of Displacement Cascades in Polyatomic Materials," D. Parkin, Los Alamos National Laboratory, Los Alamos, New Mexico
- "Valence of Cerium in Metals," D. Wohlleben, University of Cologne, Cologne, Federal Republic of Germany
- "Oxidation and Mechanical Behavior of Cr-Mo Steels,"² K. P. Singh, Indian Institute of Technology, Kanpur, India
- "Electronic Transport and Trapping Processes in Polymer Dielectrics," S. R. Kurtz, Electronic Properties of Materials, Sandia National Laboratories, Albuquerque, New Mexico
- "Correlation of Ions near an Electrode Surface," F. Forstmann, Free University, Berlin, Federal Republic of Germany
- "Scattering, Sputtering, and Light Emission in Low-Energy Ion-Surface Interactions,"⁵ W. Heiland, University of Osnabrück, Osnabrück, Federal Republic of Germany
- "Studies of Anti-Site Defects in III-V Semiconductors by Optically Detected Magnetic Resonance," J. M. Spaeth, University of Paderborn, Paderborn, Federal Republic of Germany
- "Permeation and Reemission of Deuterium Implanted in Nickel and Stainless Steel," P. Børgesen, Max-Planck-Institut für Plasmaphysik, Garching, Federal Republic of Germany
- "Solidification Dynamics in Pulsed-Laser-Melted Silicon," G. J. Galvin, Cornell University, Ithaca, New York
- "Recent Developments in Ion Transport in Solids—Potentials, Stopping Powers, Ranges, and Ion Beam Mixing," J. P. Biersack, Hahn-Meitner-Institut, Berlin, Federal Republic of Germany
- "Atomic Transport in Crystalline Solids," A. B. Lidiard, Atomic Energy Research Establishment, Harwell, England
- "Displacement Cascades and Cascade Collapse at Low Temperatures in Cu_3Au ," M. L. Jenkins, Oxford University, Oxford, England
- "Analytical Electron Microscopy Techniques Applied to Materials Problems," T. A. Stephenson, United Technology Research Center, East Hartford, Connecticut
- "Ion Implantation in Insulators,"² P. Townsend, University of Sussex, Sussex, England
- "Fractal Wave Functions in Disordered Systems?"¹ R. L. Mills, Ohio State University, Columbus, Ohio
- "Neutron Scattering Studies of Fast Ion Conductors," K. Funke, University of Hanover, Hanover, Federal Republic of Germany
- "Electronic Structure of $\text{Fe}_2\text{Ni}_{1-x}\text{C}$ Alloys: Implications for the Invar Effect,"¹ F. J. Pinski, University of Cincinnati, Cincinnati, Ohio
- "New Neutron Guide Laboratory at the FRJ-2 Reactor at Jülich," K. Werner, Kernforschungsanlage Jülich, Federal Republic of Germany
- "In Search of the Last Bit of Entropy: Nuclear Magnetism in Metals," P. Kumar, Low-Temperature Laboratory, Helsinki University of Technology, Helsinki, Finland
- "The Embedded Atom Method: Surfaces, Fracture, and the Effects of Hydrogen," M. S. Daw, Sandia National Laboratories, Livermore, California

¹Metals and Ceramics Division and Solid State Division Joint Theoretical Seminar.

²Sponsored jointly by Metals and Ceramics Division and Solid State Division.

³Solid State Division Research in Progress Seminar Series.

⁴ORNL/UT Distinguished Scientist Program Lecture Series.

⁵Sponsored jointly by Chemistry Division and Solid State Division.

LECTURES AND SEMINARS

- B. R. Appleton—Rutgers University, New Brunswick, New Jersey, "Ion Beam and Laser Techniques in Materials Research"; Atomic Energy Research Establishment, Harwell, England, "Morphological Instabilities in Ion-Irradiated Amorphous Ge"; Center for Nuclear Studies, Saclay, France, "Ion-Induced Damage Effects and Phase Changes in Metal/Semiconductor Systems"; Kernforschungsanlage Jülich, Federal Republic of Germany, "Ion-Induced Damage and Annealing Effects in Si and Ge"
- John H. Barrett—University of North Carolina, Chapel Hill, North Carolina, "Calculations of Channeling in Semiconductor Superlattices"
- J. B. Bates—Universite de Paris Nord, Paris, France, "Structure and Properties of Water in β -Alumina"; University of North Carolina, Chapel Hill, North Carolina, "Ionic and Molecular Transport in β - and γ -Alumina"
- L. A. Boatner—University of South Carolina, Columbia, South Carolina, "The Growth of Single Crystals and Their Applications in Solid State Physics"; Texas A&M University, College Station, Texas, "Monazite Nuclear Waste Forms"; Baylor University, Waco, Texas, "The Growth and Characterization of Lanthanide Orthophosphate Single Crystals,"; Kernforschungsanlage Jülich, Federal Republic of Germany, "The Growth and Characterization of Research Materials in the ORNL Solid State Division"
- J. W. Cable—Universite de Paris-Sud, Orsay, France, and Kernforschungsanlage Jülich, Federal Republic of Germany, "Correlations in Cu-Mn Alloys"; Atomic Energy Research Establishment, Harwell, England, and CENG, Grenoble France, "Random Field Effects in $(\text{Fe,Mg})\text{Cl}_2$ and $(\text{Fe,Co})\text{Cl}_2$ "
- J. Chen—Universidad Internacional Menéndez Pelayo, Santander, Spain, and Universidad Nacional Autónoma de México, México City, México, "Refractory Oxides for Quantum Electronic Devices: Tunable Lasers and Infrared Converters"; Universidad Nacional Autónoma de México, México City, México, "Radiation Damage in Refractory Oxides"; New Mexico State University, Las Cruces, New Mexico, "Refractory Oxides for Tunable Laser"; University of Alabama—Birmingham, Birmingham, Alabama, "Refractory Oxide Crystals for Quantum Electronic Devices"
- R. R. Colman, Jr.—Clemson University, Clemson, South Carolina, "The Use of a New National Low-Temperature Neutron Irradiation Facility at ORNL"
- R. J. Culbertson—University of Aarhus, Aarhus, Denmark, "The Structure of $\text{Ag}(110)$ and $\text{Ge}(111)$ Surfaces"; Atomic Energy Research Establishment, Harwell, England, "Surface Structure Studies Using MeV Ion Scattering"; FOM Institute for Atomic and Molecular Physics, Amsterdam, the Netherlands, "Single-Alignment Ion Scattering Studies of Crystal Surfaces"; Arizona State University, Tempe, Arizona, "High-Energy Ion Scattering Studies of Crystal Surface and Interface Structure"
- H. L. Davis—Rice University, Houston, Texas, "Multilayer Relaxation in Metallic Surfaces—An Outgrowth of Precision LEED Analysis"; Kernforschungsanlage Jülich, Federal Republic of Germany, "Multilayer Relaxation of Metallic Surfaces via Precision LEED"; FOM Institute for Atomic and Molecular Physics, Amsterdam, the Netherlands, "Precision LEED Demonstrations of Multilayer Relaxation in Metallic Surfaces"; Risø National Laboratory, Roskilde, Denmark, "Multilayer Relaxation of Clean Metallic Surfaces by Using LEED Analysis"
- J. Hayter—Enrico Fermi School of Physics, Varenna, Italy, "Determination of the Structure and Dynamics of Micellar Solutions by Neutron Scattering" (two lectures); Chemical Physics Seminar Series, ORNL, "Neutron Scattering Studies of Micelles, Colloids, and Gels"
- G. E. Jellison—University of Kansas, Lawrence, Kansas, University of Missouri, Columbia, Missouri, University of Missouri—Rolla, Rolla, Missouri, and University of Tulsa, Tulsa, Oklahoma, "Optical Properties of Silicon and Applications to Pulsed-Laser Annealing"; Oak Ridge Associated Universities, Oak Ridge, Tennessee, "Progress toward More Efficient Solar Cells Using Pulsed-Laser Processing"
- H. R. Kerchner—University of South Florida, Tampa, Florida, "Superconductivity—The Phenomenon and Its Applications"; Florida State University, Tallahassee, Florida, "Why Do Superconductors Carry Current Losslessly at High Fields?" and "The Critical State Model of Hysteresis in High-Field Superconductors"; University of Kentucky, Lexington, Kentucky, "Toward a Microscopic Understanding of the Critical State of High-Field Superconductors."
- W. C. Koehler—National Bureau of Standards, Gaithersburg, Maryland, "Small-Angle Neutron Scattering? Why?"; Laboratoire Leon Brillouin, C.E.N. Saclay, France, "Recent Neutron Scattering Activities at ORNL"; Exxon Research Laboratories, Clinton, New Jersey, "The National Center for Small-Angle Scattering Research"

- B. C. Larson—Kernforschungsanlage Jülich, Federal Republic of Germany, Kernforschungszentrum Karlsruhe, Federal Republic of Germany, and University of Munich, Munich, Federal Republic of Germany, "Nano-second Resolution, Time-Resolved X-ray Study of Si and Ge during Pulsed-Laser Irradiation"
- J. S. Lin—The University of Tennessee, Knoxville, Tennessee, "The NCSASR SAS Applications to Industrial Problems"
- S. H. Liu—University of Georgia, Athens, Georgia, and Florida State University, Tallahassee, Florida, "Surface Electronic States"; CNRS, Saclay, France, "Electroreflectance of Noble Metal Surfaces"; The University of Tennessee, Knoxville, Tennessee, and Chemical Physics Seminar, ORNL, "Fractals: Seeking Order in Disorder"
- D. H. Lowndes—The Microelectronics Center of North Carolina, Research Triangle Park, North Carolina, "Pulsed-Laser Processing of Semiconductors: 1. Fundamental Studies in Amorphous Silicon and 2. Applications to Semiconductor Materials and Devices"; Avionics Laboratory, Wright Patterson AFB Research Center, Dayton, Ohio, "Pulsed-Laser Processing of Semiconductors"; Oregon Graduate Center, Portland, Oregon, "Pulsed-Laser Processing of Semiconductors: Fundamental Studies and Potential Device Applications"
- H. A. Mook—Massachusetts Institute of Technology, Cambridge, Massachusetts, "Competition between Magnetism and Superconductivity in $(\text{ErHo})(\text{RhIr})_2\text{B}_4$ "; University of California, Santa Barbara, California, "Magnetism and Superconductivity in the Rare-Earth Rhodium Borides"; University of California at La Jolla, San Diego, California, "Why Neutrons Are Good for the Study of Condensed Matter Physics"; Institut Laue-Langevin, Grenoble, France, "Competition Between Magnetism and Superconductivity in the Rare-Earth Rhodium Borides"
- J. Narayan—Microelectronics Research Center of North Carolina, Research Triangle Park, North Carolina, "Ion Implantation and Transient Processing of Microelectronic Materials" (Distinguished Lecture Series)
- T. S. Noggle—Kernforschungsanlage Jülich, Federal Republic of Germany, "Time-Resolved X-ray Diffraction Studies of Si during Pulsed-Laser Annealing"; Hahn-Meitner Institut, Berlin, Federal Republic of Germany, "Damage Production Rates of Al Ions in Al and the Normalization to Fast Neutron Damage"
- J. R. Noonan—Chalmers University of Technology, Gothenburg, Sweden, and University of Munich, Munich, Federal Republic of Germany, "Characterization of the Vacuum-Surface Interface of Metals"
- S. M. Ohr—Princeton University, Princeton, New Jersey, and State University of New York, Stony Brook, New York, "Electron Microscope Observations of Crack Propagation"; Oxford University, Oxford, England, Atomic Energy Research Establishment, Harwell, England, Harvard University, Cambridge, Massachusetts, and Japan Atomic Energy Research Institute, Tokai, Japan, "Electron Microscope Studies of Fracture"; University of Seoul, Seoul, Korea, and Korea Advanced Institute of Science and Technology, Seoul, Korea, "Application of Electron Microscope Techniques to Fracture"; Korea Standards Research Institute, Dae Deog, Korea, "Recent Developments in Electron Microscopy"; Institut National Polytechnique de Lorraine, Nancy, France, "Dislocation-Free Zone Theory of Fracture"; Brookhaven National Laboratory, Upton, New York, and IBM Thomas J. Watson Research Center, Yorktown Heights, New York, "Electron Microscope Studies of Crack Tip Deformation"
- S. J. Pennycook—Cavendish Laboratory, University of Cambridge, United Kingdom, "Giant Diffusion Mechanisms and Site Location in Ion-Implanted Silicon"
- M. Rasolt—University of California, Berkeley, California, and Dalhousie University, Halifax, Nova Scotia, Canada, "Critical Fluctuations in an Interacting Dilute Bose Gas" and "Lifetime of an Electron Hole Plasma in the Picosecond Range"; Harvard University, Cambridge, Massachusetts, "Lifetime of an Electron Hole Plasma in the Picosecond Range"
- J. B. Roberto—James Madison University, Harrisonburg, Virginia, "Surface Physics and Fusion—Plasma Materials in Tokamaks"; Culham Laboratory, Abingdon, United Kingdom, Kernforschungsanlage Jülich, Federal Republic of Germany, and Max-Planck-Institut für Plasmaphysik, Garching, Federal Republic of Germany, "Beryllium for Plasma-Side Applications"; Technical University, Vienna, Austria, "Sputtering of Graphite at High Temperatures"; Max-Planck-Institut für Plasmaphysik, Garching, Federal Republic of Germany, "Surface Physics Contributions to Plasma Physics"
- M. T. Robinson—Atomic Energy Research Establishment, Harwell, England, "Recent Computer Simulations of Sputtering and Radiation Damage"; Max-Planck-Institut für Plasmaphysik, Garching, Federal Republic of Germany, "Local Order Effects on Reversal Ranges in Crystals"

- G.-C. Wang—IBM T. J. Watson Research Center, Yorktown Heights, New York, and Argonne National Laboratory, Argonne, Illinois, "Study of Two-Dimensional Ordering by Low-Energy Electron Diffraction"; Bell Laboratories, Murray Hill, New Jersey, "Two-Dimensional Ordering in Chemisorbed Overlayers"; Rensselaer Polytechnic Institute, Troy, New York, "Two-Dimensional Phase Transitions and Critical Phenomena: Oxygen Chemisorbed on W(112) Surface"
- C. W. White—IBM T. J. Watson Research Center, Yorktown Heights, New York, "Surface Modification of Al_2O_3 by Ion Implantation"
- G. D. Mignall—The University of Tennessee, Knoxville, Tennessee, "SANS from Synthetic Polymers at the NCSASR"; Lehigh University, Bethlehem, Pennsylvania, "Highlights of Small-Angle Neutron Scattering Studies on Synthetic Polymers at Oak Ridge"; The University of Michigan, Ann Arbor, Michigan, Northwestern University, Evanston, Illinois, Allied Chemical Corporation, Newark, New Jersey, and West Virginia University, Morgantown, West Virginia, "Small-Angle Neutron Scattering from Synthetic Polymers at Oak Ridge"; Leeds University, Leeds, England, "SANS Studies of Chain Deformation (Orientation) Processes in Crystalline Polymers"; Deutsches Elektronen-Synchrotron, Hamburg, Federal Republic of Germany, "SANS Studies of Chain Conformation and Transesterification Kinetics in Polyethylene Terephthalate (PET)"
- D. M. Zehner—FOM Institute for Atomic and Molecular Physics, Amsterdam, the Netherlands, "Studies of Oxygen Chemisorbed on the Cu(110) Surface"; IBM, Ruschlikon, Switzerland, "Laser Annealing of Semiconductor Surfaces"
- R. A. Zuhr—University of Osnabruck, Osnabruck, Federal Republic of Germany, "Deposition Probe Measurements in Magnetic Confinement Devices"; Kernforschungsanlage Jülich, Federal Republic of Germany, "Characterization of the TEXTOR Plasma Edge Using Deposition Probe Techniques"

AWARDS

B. R. Appleton	1983 IR-100 Award for the Development of Supersaturated Semiconductor Alloys
M. J. Aziz	Eugene P. Wigner Fellowship, 1983 Materials Research Society Graduate Student Award, 1983
J. B. Bates	American Physical Society Fellowship, 1984
L. A. Boatner	DOE's 1984 Materials Sciences Research Competition Award: Significant Implication for Energy Technology Category
Y. Chen	American Ceramic Society Fellowship, 1984
O. W. Holland	1983 IR-100 Award for the Development of Supersaturated Semiconductor Alloys
D. H. Lowndes	Institute of Electrical and Electronics Engineers Senior Member, 1983
H. A. Mook	1984 IR-100 Award for the Ultrasonically Pulsed Neutron Spectrometer
J. Narayan	1983 IR-100 Award for the Development of Supersaturated Semiconductor Alloys American Association for the Advancement of Science Fellowship, 1984
B. C. Sales	DOE's 1984 Materials Sciences Research Competition Award: Significant Implication for Energy Technology Category
R. D. Westbrook	DOE's 1983 Materials Sciences Research Competition Award: Significant Implication for Energy Technology Category
C. W. White	1983 IR-100 Award for the Development of Supersaturated Semiconductor Alloys
M. K. Wilkinson	American Association for the Advancement of Science Fellowship, 1983
R. F. Wood	DOE's 1983 Materials Sciences Research Competition Award: Significant Implication for Energy Technology Category American Association for the Advancement of Science Fellowship, 1984 Union Carbide Corporation Fellowship, 1984
R. T. Young	DOE's 1983 Materials Sciences Research Competition Award: Significant Implication for Energy Technology Category

SCIENTIFIC PROFESSIONAL ACTIVITIES

- M. M. Abraham Member, Editorial Board, KINAM Revista de Fisica
- B. R. Appleton Member, Solid State Sciences Committee of the National Research Council
 Vice President, Materials Research Society, 1983-1984
 Chapter Editor, DOE Panel Report on Coatings and Surface Modifications
 Organizing Committee, International Conference on Ion Beam Modification of
 Materials, Ithaca, New York, 1984
 Co-Chairman, Program Committee, Materials Research Society Meeting,
 Boston, Massachusetts, 1983
 Participant, Ad Hoc Working Group on Rapid Solidification Technology
 Committee on Materials, Washington, D.C., 1983
 Participant, DOE Panel Meeting on Surface Modifications, Berkeley,
 California, 1983
 Member, Editorial Board, Nuclear Science Applications
 Member, ASTM Subcommittee on Energetic Ion Analysis
 Member, Program Committee, Nominating Committee, Publications Committee,
 Education Committee, and Corporate Participation Committee, Materials
 Research Society
 Associate Editor, Materials Letters
 Director, ORNL/DOE Surface Modification and Characterization Collaborative
 Research Center
- J. B. Bates Associate Editor, Solid State Ionics
 Member, High-Temperature Materials Laboratory Committee, ORNL
 Member, Scientific Committee, Fifth International Conference on Solid
 State Ionics (to be held in 1985)
 Member, Working Group on Beta-Alumina
 Co-Chairman, Gordon Research Conference on Solid State Ionics (to be held
 in 1986)
- L. A. Boatner Member, Program Committee, Corporate Affiliates Committee (Chairman), and
 Finance Committee, Materials Research Society
 Member, High-Temperature Materials Program Committee, ORNL
 Member, Program Committee, Materials Research Society Symposium on the
 Scientific Basis for Nuclear Waste Management, Boston, Massachusetts,
 1983
 Member, Long-Range Nuclear Waste Planning Committee, ORNL
 Associate Editor, Materials Letters
 Lecturer, ORAU Traveling Lecture Program, 1983-1984
 Member, Working Group on Radiation Effects in Crystalline Nuclear Waste
 Forms, Santa Fe, New Mexico, 1983
 Co-Chairman, ORNL Committee on Future Directions for Research on Composite
 Materials, 1983
- G. J. Bunick Research Assistant Professor, The University of Tennessee Graduate School
 of Biomedical Sciences
- J. W. Cable Guest Scientist, Laboratoire Leon Brillouin, Saclay, France, April-October
 1983
- Y. K. Chang Guest Scientist, Kernforschungsanlage Jülich, Federal Republic of Germany,
 September-December, 1983
- Y. Chen Member, Graduate School Doctoral Committee, Department of Physics,
 University of Alabama, Birmingham, Alabama
 Co-Chairman, Materials Research Society Symposium on Defect Properties and
 Processing of High-Technology Nonmetallic Materials, Boston,
 Massachusetts, 1983

- Session Chairman, Materials Research Society Symposium, Boston, Massachusetts, 1983
Co-Chairman, Materials Research Society Symposium on High-Temperature Ceramics (to be held in 1985)
- D. K. Christen Participant, Third NCSASR User's Group Meeting and Workshop in Small-Angle Methods, Oak Ridge, Tennessee, 1984
- R. R. Coltman, Jr. Adjunct Professor, Department of Physics and Astronomy, Clemson University, Clemson, South Carolina
- J. F. Cooke Member, Session Organizing Committee, American Physical Society Meeting, 1983-1984
- R. J. Culbertson Lecturer, ORAU Traveling Lecture Program, 1983-1984
Member, Education Committee, Materials Research Society, 1983-1984
- H. L. Davis Member, Selection Committee, Morton M. Traub Surface Science Student Award, American Vacuum Society, 1983
Session Chairman, American Physical Society Meeting, Detroit, Michigan, 1984
Treasurer, Fourth Annual Symposium and Equipment Exhibit of the Tennessee Valley Chapter, American Vacuum Society, Knoxville, Tennessee, 1984
Session Chairman, American Crystallographic Association Meeting, Lexington, Kentucky, 1984
Treasurer, Tennessee Valley Chapter, American Vacuum Society, 1984-1985
- N. J. Dudney Member, ORNL Committee on Future Directions for Research on Composite Materials
- J. B. Hayter Organizer, International Study Group on Macromolecular and Colloidal Research with a European Synchrotron at the Proposed Maxwell Institute, Grenoble, France, 1983
Session Chairman, Enrico Fermi School on Physics of Amphiphiles, Varenna, Italy, 1983
Member, Scientific Program Subcommittee on Polymer and Colloid Research, Institut Laue-Langevin, Grenoble, France, 1983
Participant, Conference on the Effects of Modes of Formation on the Structure of Glass, Nashville, Tennessee, 1984
Co-Chairman and Organizer, Workshop on Neutrons in Technologically Important Problems in Powders, Gels, and Colloids, Grenoble, France, 1983
- G. E. Jellison, Jr. Member, ORNL Committee on Future Directions for Research on Composite Materials
- L. H. Jenkins Member, Wigner Fellowship Committee, ORNL
Member, Ph.D. Recruiting Steering Committee, ORNL
Chairman, Exploratory Studies Committee, ORNL 1984-1986
- H. R. Kerchner Lecturer, ORAU Traveling Lecture Program, 1983-1984
- W. C. Koehler Director, ORNL-NSF-DOE National Center for Small-Angle Scattering Research
Member, Editorial Advisory Board, Journal of Magnetism and Magnetic Materials
Participant, Third NCSASR Users' Group Meeting and Workshop in Small-Angle Methods, Oak Ridge, Tennessee, 1984
Guest Scientist, Institut Laue-Langevin, Grenoble, France, January-February, 1984
- S. C. Larson Member, Program Advisory Board, Cornell High Energy Synchrotron Source, Cornell University, Ithaca, New York
Lecturer, ORAU Traveling Lecture Program, 1984-1985
- J. S. Lin Adjunct Professor, Department of Chemical, Metallurgical, and Polymer Engineering, The University of Tennessee, Knoxville, Tennessee
Participant, Third NCSASR Users' Group Meeting and Workshop in Small-Angle Methods, Oak Ridge, Tennessee, 1984

- S. H. Liu Session Chairman, American Physical Society Meeting, Detroit, Michigan, 1984
Lecturer, ORAU Traveling Lecture Program, 1983-1984
- D. H. Lowndes Chairman, 1983, and Member, Users Advisory Committee, Francis Bitter National Magnet Laboratory, Massachusetts Institute of Technology, Cambridge, Massachusetts
- F. A. Modine Session Chairman, American Physical Society Meeting, Detroit, Michigan, 1984
- H. A. Mook Secretary, ORNL Neutron Scattering Users' Group
Member, Joint Program Committee for Argonne IPNS and Los Alamos WNR
Session Chairman, Workshop on High-Energy Excitations in Condensed Matter, Los Alamos, New Mexico, 1984
Session Chairman, Gordon Conference on Quantum Solids and Fluids, Wolfeboro, New Hampshire, 1983
- R. M. Moon Member, NRC Panel on the Current Status of Neutron Scattering Research and Facilities in the United States
Member, NAS-NRC Evaluation Panel for the Center for Materials Science, National Bureau of Standards
Editor, Instrumentation for the Advanced High-Flux Reactor, ORNL, Oak Ridge, Tennessee, 1984
- J. Narayan General Co-Chairman, Materials Research Society Annual Meeting, Boston, Massachusetts, 1984
Member, Scientific Advisory Committee, Materials Research Society Symposium on Defect Properties and Processing of High-Technology Nonmetallic Materials, Boston, Massachusetts, 1983
Member, Electronic Materials Committee, the Metallurgical Society of AIME
Member, Program Committees, American Conference on Crystal Growth (ACCG-6) and International Conference on Vapor Growth and Epitaxy (ICVGE-6), Atlantic City, New Jersey, 1984
Member, Technical Advisory Committee, ASM International Conference, 1984
Adjunct Professor, Physics Department, North Carolina State University, Raleigh, North Carolina
- R. M. Nicklow Member, Research Committee, U.S.-Japan Cooperative Program on Neutron Scattering
Session Chairman, American Physical Society Meeting, Detroit, Michigan, 1984
Session Chairman, Twenty-Ninth Annual Conference on Magnetism and Magnetic Materials, Pittsburgh, Pennsylvania, 1983
- T. S. Noggle Guest Scientist, Kernforschungsanlage Jülich, Federal Republic of Germany, September 1983-August 1984
- J. R. Noonan Chairman, Scholarship Committee, Tennessee Valley Chapter, American Vacuum Society
Member, Executive Board, Tennessee Valley Chapter, American Vacuum Society, 1983
Member, Publications Committee, American Vacuum Society
Members, Publication Policy Committee, American Institute of Physics, 1984
- S. M. Ohr Member, Chemistry and Physics of Metals Committee, the Metallurgical Society of AIME
Member, Nuclear Metallurgy Committee, the Metallurgical Society of AIME
Member, Nuclear Metallurgy Committee, Materials Science Division, American Society for Metals
Symposium Organizer, the Metallurgical Society of AIME Symposium on Modern Materials Characterization Techniques, Philadelphia, Pennsylvania, 1983
Session Chairman, Fall Meeting of the Metallurgical Society of AIME, Philadelphia, Pennsylvania, 1983
Session Chairman, Annual Meeting of the Metallurgical Society of AIME, Los Angeles, California, 1984
Chairman and Organizer, International Conference on Fundamentals of Fracture (to be held in 1985)
Participant, Joint U.S.-Japan Seminar on Materials Science of Fracture, Sendai, Japan, 1984

- D. A. Pringle Participant, Informal Discussion Meeting on Magnetic Superconductors, Argonne, Illinois, 1983
- M. Rasolt Guest Scientist, Harvard University, Boston, Massachusetts, October 1982–August 1983
Lecturer, ORAU Traveling Lecture Program, 1984–1985
- J. B. Roberto Guest Scientist, Max-Planck-Institut für Plasmaphysik, Garching, Federal Republic of Germany, July–November 1983
Coordinator, ORNL Plasma Materials Interactions Program
Member, Editorial Advisory Board, Journal of Nuclear Materials
Co-Chairman, Materials Research Society Symposium on Advanced Photon and Particle Techniques for the Characterization of Defects in Solids (to be held in 1984)
Member, Plasma Materials Interactions Task Group, DOE-OFE
Co-Chairman, DOE-OFE Workshop on High Heat Flux Materials for TFCX, Germantown, Maryland, 1983
Member, International Advanced Limiter (ALT-II) Review Panel, Mt. Fuji, Japan, 1984
Member, International Program Committee, Workshop on Synergistic Effects in Surface Phenomena Related to Plasma Surface Interactions, Nagoya, Japan, 1984
Coordinator, U.S. Plasma Wall Interactions Experiments in the TEXTOR (Federal Republic of Germany) Tokamak
R&D Coordinator, Energy/Particle Removal Systems in TFCX
Participant, DOE-OFE Workshop on International Cooperation in Plasma Materials Interactions and High Flux Component Development, Germantown, Maryland, 1984
Member, Technical Staff, Energy Resources Advisory Board Materials Panel, 1983
Guest Lecturer, The University of Tennessee, Knoxville, Tennessee, 1983
- M. T. Robinson Western Hemisphere Editor, Radiation Effects
Participant, DAFS Information/Planning Meeting, University of California, Santa Barbara, 1984
Member, Special NSERC Committee on Applied Physics at Canadian University Accelerators, Montreal, Canada
- B. C. Sales Member, Molecular Beam Epitaxy Study Group, ORNL
- S. T. Sekula Adjunct Professor, Department of Physics, The University of Tennessee, Knoxville, Tennessee
- H. G. Smith Member, Neutron Diffraction Commission of the International Union of Crystallography, 1984–1987
Member, International Program Committee, Conference on Developments in Neutron Scattering (to be held in 1987)
Guest Scientist, Division of Materials Sciences, Department of Energy, Washington, D.C., September 1983–June 1985
- E. Sonder Adjunct Professor, Vanderbilt University, Nashville, Tennessee
- S. Spooner Chairman, Structures Activity, American Society for Metals, 1984
Member, Small-Angle Scattering Special Interest Group, American Crystallographic Association, 1984
Chairman, Materials Science, Third NCSASR Users' Group Meeting and Workshop in Small-Angle Methods, Oak Ridge, Tennessee, 1984
Member, Ph.D. Recruiting Committee, ORNL
Lecturer, ORAU Traveling Lecture Program, 1984–1985
- G.-C. Wang Member, General Committee, Physical Electronics Conference (to be held in 1985)
- J. C. Wang Lecturer, ORAU Traveling Lecture Program, 1984–1985
- J. F. Wendelken Lecturer, ORAU Traveling Lecture Program, 1983–1984

- C. W. White
 President, Materials Research Society, 1984
 First Vice President, Materials Research Society, 1983
 Council Member, Materials Research Society, 1983-1984
 Co-Chairman, Materials Research Society Symposium on Ion Implantation and Ion Beam Processing of Materials, Boston, Massachusetts, 1983
 Co-Editor, Ion Implantation and Ion Beam Processing of Materials, North-Holland, New York, 1984
 Associate Editor, Materials Letters
 Associate Editor, Nuclear Instruments and Methods in Physics Research, Section B
 Co-Editor, Pulsed-Laser Processing of Semiconductors, Academic Press, New York (to be published)
- G. D. Wignall
 Lecturer, ORAU Traveling Lecture Program, 1983-1984
 Adjunct Professor, Department of Chemical, Metallurgical, and Polymer Engineering, The University of Tennessee, Knoxville, Tennessee
 Chairman and Organizer, ACS Polymer Science Engineering Lecture Series on Introduction to Small-Angle Scattering, Washington, D.C., 1983
 Chairman and Organizer, ACS Symposium on New Developments in Small-Angle Scattering from Polymers, Washington, D.C., 1983
 Organizer, Third NCSASR Users' Group Meeting and Workshop in Small-Angle Methods, Oak Ridge, Tennessee, 1984
 Member, Board of Directors, ACA Small-Angle Scattering Interest Group
- M. K. Wilkinson
 Member, Solid State Sciences Committee of the National Research Council
 Member, Program Advisory Committee, National Synchrotron Light Source, Brookhaven National Laboratory
 Executive Secretary, DOE Basic Energy Sciences Laboratory Program Panel
 Member, Organizing Committee, International Conference on Magnetism (to be held in 1985)
 Member, Advisory Committee, Department of Physics, University of South Carolina, Columbia, South Carolina
 Member, DOE Basic Energy Sciences Council on Materials Science
 Adjunct Professor, School of Physics, Georgia Institute of Technology, Atlanta, Georgia
 Member, NRC Panel on the Current Status of Neutron Scattering Research and Facilities in the United States
 Consultant to Steering Committee, U.S.-Japan Cooperative Program on Neutron Scattering
 Member, ORNL Emergency Review and Advisory Committee
 Member, ORNL HFIR-II Steering Committee
- J. M. Williams
 Lecturer, ORAU Traveling Lecturer Program, 1984-1985
- S. P. Withrow
 Member, ORNL Ph.D. Recruiting Committee
- R. F. Wood
 Editor, Solid State Physics, Computer Physics Communications, North-Holland, New York
 Participant, SERI Program Review Meetings on Si and GaAs Solar Cell Technology
 Co-Editor, Pulsed Laser Processing of Semiconductors, Academic Press, New York (to be published)
 Member, Advisory Committee, International Conference on Defects in Insulating Crystals, Salt Lake City, Utah, 1984
 Member, Professional Education Resources Committee, ORNL
 Member, ORNL/UT Distinguished Scientist Program Committee, 1984
- F. W. Young, Jr.
 Member, Executive Committee, American Association of Crystal Growth
 Member, Editorial Board, Topics in Crystal Growth
 Session Chairman, American Physical Society Meeting, Detroit, Michigan, 1984
 Organizer, Materials Physics Topical Group, American Physical Society
 Member, External Advisory Committee on Materials, University of Pittsburgh
 Session Chairman, American Association for Crystal Growth Meeting, Atlantic City, New Jersey, 1984

- D. M. Zehner Co-Chairman, Education Committee, American Vacuum Society, 1984
Member, Executive Committee, Surface Science Division, American Vacuum Society, 1983-1984
Member, Executive Board, Tennessee Valley Chapter, American Vacuum Society, 1983-1984
Co-Chairman, Education Committee, Materials Research Society, 1984
- R. A. Zuhr Guest Scientist, Kernforschungsanlage Jülich, Federal Republic of Germany, March-April, 1984

PERSONNEL CHANGES

New Staff Members

A. Scientific Staff

J. R. Arthur, Massachusetts Institute of Technology, Cambridge, Massachusetts
M. J. Aziz, Harvard University, Boston, Massachusetts
G. J. Bunick, The University of Tennessee—Oak Ridge Graduate School of Biomedical Sciences, Oak Ridge, Tennessee
Y. T. Chu, The University of Tennessee, Knoxville, Tennessee
C. B. Finch, transferred from ORNL Metals and Ceramics Division
J. B. Hayter, Institut Laue-Langevin, Grenoble, France
N. Herbots, Universite Catholique, Louvain, Belgium
J. D. Lewis, University of Kentucky, Lexington, Kentucky
C. G. Park, Northwestern University, Evanston, Illinois
T. P. Sjoreen, State University of New York, Stony Brook, New York

B. Administrative and Technical Staff

R. L. Anderson, Senior Laboratory Technician
L. Romo, Laboratory Technician
D. K. Thomas, Senior Laboratory Technician (transferred from Operations Division)
J. R. Weir III, Laboratory Technician
R. B. Wheeler, Senior Laboratory Technician

Staff Transfers and Terminations

A. Scientific Staff

J. F. Barhorst (voluntary resignation)
O. W. Holland (voluntary resignation)
R. B. James (voluntary resignation)
V. R. Ramakrishnan (voluntary resignation)
G.-C. Wang (voluntary resignation)
R. T. Young (voluntary resignation)

B. Administrative and Technical Staff

L. Romo, Laboratory Technician (voluntary resignation)

Guest Assignments

A. Scientific Staff

R. Arons, Kernforschungsanlage Jülich, Federal Republic of Germany
D. Dohy, University of Paris, Paris, France
R. J. Elliott, Oxford University, Oxford, England
W. Erley, Kernforschungsanlage Jülich, Federal Republic of Germany
D. Fathy, North Carolina State University, Raleigh, North Carolina
T. R. Finlayson, Monash University, Clayton, Victoria, Australia
E. Fogarassy, Centre National de la Recherche Scientifique, Paris, France
F. Forstman, Free University Berlin, Berlin, Federal Republic of Germany
D. Grider, Georgia Institute of Technology, Atlanta, Georgia
E. Gurewitz, Nuclear Research Center, Negev, Israel
J. Hauck, Kernforschungsanlage Jülich, Federal Republic of Germany
M. Iizumi, Japan Atomic Energy Research Institute, Tokai-mura, Japan
S. Katano, Japan Atomic Energy Research Institute, Tokai-mura, Japan
S. Kawanazaki, Osaka University, Osaka, Japan

J. W. Lynn, University of Maryland, College Park, Maryland
 G. D. Mahan,* The University of Tennessee, Knoxville, Tennessee
 J. Mizuki, Ames Laboratory/Iowa State University, Ames, Iowa
 Y. Morii, Japan Atomic Energy Research Institute, Tokai-mura, Japan
 H. Motohashi, Japan Atomic Energy Research Institute, Tokai-mura, Japan
 Y. Nakai, Osaka University, Osaka, Japan
 A. Onodera, Osaka University, Osaka, Japan
 W. Reichardt, Kernforschungszentrum Karlsruhe, Federal Republic of Germany
 J. Roth, Max-Planck-Institut für Plasmaphysik, Garching, Federal Republic of Germany
 R. Ruckteschler, Fraunhofer-Institut für Solare Energiesysteme, Freiburg, Federal Republic of Germany
 K. Shung, The University of Tennessee, Knoxville, Tennessee
 G. S. Smith, Ames Laboratory/Iowa State University, Ames, Iowa
 H. Suzuki, Tohoku University, Sendai, Japan
 R. Thomson, National Bureau of Standards, Washington, D.C.
 Y. Tsunoda, Osaka University, Osaka, Japan
 Y. Yamaguchi, Tohoku University, Sendai, Japan
 J. Zarestky, Ames Laboratory/Iowa State University, Ames Iowa

*ORNL/U.T. Distinguished Scientist

B. Graduate Students

J. T. Ellis, The University of Tennessee, Knoxville, Tennessee
 J. R. Martinelli, Vanderbilt University, Nashville, Tennessee
 K. L. Tsang, University of Alabama, Birmingham, Alabama

C. ORAU Postdoctoral Research Fellowship Program

G. C. Farlow, University of North Carolina, Chapel Hill, North Carolina

D. Great Lakes College Association Science Program

H. H. Burke, Earlham College, Richmond, Indiana

E. Southern Colleges and Universities Union Science Program

P. A. Bruhwiler, Southwestern at Memphis, Memphis, Tennessee

Summer Assignments (1983 and 1984)

A. Scientific Staff

R. C. Allen, Virginia Polytechnic Institute and State University, Blacksburg, Virginia
 J. A. Blackman, University of Reading, Reading, England
 J. T. Ellis, The University of Tennessee, Knoxville, Tennessee
 D. A. Hansen, University of California, Berkeley, California
 R. S. Hathcock, Rollins College, Winter Park, Florida
 C. A. Hewitt, University of California at San Diego, La Jolla, California
 A. Liu, University of California, Berkeley, California
 K. L. More, North Carolina State University, Raleigh, North Carolina
 T. Morgan, University of Reading, Reading, England
 D. N. Olson, St. Olaf College, Northfield, Minnesota
 R. Triolo, University of Palermo, Palermo, Italy
 K. L. Tsang, University of Alabama, Birmingham, Alabama
 N. Wakabayashi, Keio University, Yokohama, Japan (Two Summers)

B. Administrative and Technical Support Staff

M. A. Goodson, Knoxville Business College, Knoxville, Tennessee
 T. L. Miller, Liberty Baptist College, Lynchburg, Virginia
 V. Wilburn, Knoxville College, Knoxville, Tennessee
 C. S. Yoo, Harvard University, Boston, Massachusetts

C. ORAU—University Faculty

C. Y. Allison, Oklahoma State University, Stillwater, Oklahoma
 G. M. Beardsley, Millsaps College, Jackson, Mississippi (Two Summers)
 M. C. Lu, Walters State Community College, Morristown, Tennessee

D. ORAU—Undergraduate Research Trainees

M. Aronson, Pennsylvania State University, University Park, Pennsylvania
L. Craven, The University of Tennessee, Knoxville, Tennessee
A. Liu, University of California, Berkeley, California
J. S. Loyd, Clemson University, Clemson, South Carolina
J. L. Robertson, Clemson University, Clemson, South Carolina
A. J. Smith, University of California, Santa Cruz, California

SOLID STATE DIVISION

OCTOBER 1, 1980

¹MULTIPLE CAPACITY²FINANCE AND MATERIALS DIVISION³PLANT AND EQUIPMENT DIVISION⁴FORMERLY DISTINGUISHED SCIENTIST⁵GUEST SCIENTIST⁶ON DOMESTIC ASSIGNMENT⁷COMPUTING AND TELECOMMUNICATIONS DIVISION⁸PART TIME EMPLOYMENT⁹ON ASSIGNMENT FROM AMES LABORATORY¹⁰GRADUATE STUDENT¹¹ON FULBRIGHT FELLOWSHIP¹²ON FULBRIGHT FELLOWSHIP¹³ON ASSIGNMENT TO CMO¹⁴ON LEAVE OF ABSENCE¹⁵ON LEAVE OF ABSENCE¹⁶ON LEAVE OF ABSENCE¹⁷ON LEAVE OF ABSENCE¹⁸ON LEAVE OF ABSENCE¹⁹ON LEAVE OF ABSENCE²⁰ON LEAVE OF ABSENCE²¹ON LEAVE OF ABSENCE²²ON LEAVE OF ABSENCE²³ON LEAVE OF ABSENCE²⁴ON LEAVE OF ABSENCE²⁵ON LEAVE OF ABSENCE²⁶ON LEAVE OF ABSENCE²⁷ON LEAVE OF ABSENCE²⁸ON LEAVE OF ABSENCE²⁹ON LEAVE OF ABSENCE³⁰ON LEAVE OF ABSENCE

INTERNAL DISTRIBUTION

1. M. M. Abraham	68. L. W. Hinton
2. H. L. Adair	69. D. W. Jared
3. E. D. Aebischer	70. K. Jarmolow
4. T. D. Anderson	71. G. E. Jellison, Jr.
5-9. B. R. Appleton	72-76. L. H. Jenkins
10. R. R. Arons	77. S. I. Kaplan
11. J. R. Arthur	78. T. Kaplan
12. M. J. Aziz	79. P. R. Kasten
13. J. B. Ball	80. S. V. Kaye
14. J. H. Barrett	81. A. M. Keesee
15. J. B. Bates	82. H. R. Kerchner
16. S. S. Berr	83. S. P. King
17. E. E. Bloom	84. C. E. Klahunde
18. L. A. Boatner	85. W. C. Koehler
19. C. W. Boggs	86. C. H. Krause
20. W. E. Brundage	87. E. H. Krieg
21. K. C. Brunson	88. B. C. Larson
22. J. D. Budai	89. J. D. Lewis
23. G. J. Bunick	90. J. S. Lin
24. R. L. Burrell	91. S. H. Liu
25. W. H. Butler	92. D. H. Lowndes
26. J. W. Cable	93. J. T. Luck
27. R. S. Carlsmith	94. G. D. Mahan
28. H. P. Carter	95. F. C. Maieschein
29. S.-J. Chang	96. L. K. Mansur
30. Y. K. Chang	97. J. R. Martinelli
31. Y. Chen	98. J. R. McGuffey
32. H. R. Child	99. C. J. McHargue
33. D. K. Christen	100. L. E. McNeese
34. Y. T. Chu	101. T. K. Miller
35. G. W. Clark	102. J. Mizuki
36. T. L. Collins	103. F. A. Modine
37. R. R. Coltman, Jr.	104. H. A. Mook
38. T. B. Cook III	105. R. M. Moon
39-43. J. F. Cooke	106. J. L. Moore
44. B. J. Copeland	107. M. E. Mostoller
45. R. J. Culbertson	108. F. R. Mynatt
46. L. C. Cunningham	109-113. R. M. Nicklow
47. H. L. Davis	114. T. S. Noggle
48. N. J. Dudley	115. J. R. Noonan
49. T. C. Estes	116. O. S. Oen
50. S. L. Evans	117. S. M. Ohr
51. G. C. Farlow	118. G. E. Oliphant
52. C. B. Finch	119. G. W. Ownby
53. A. H. Fincher	120. C. G. Park
54. P. H. Fleming	121. D. C. Parzyck
55. W. Fulkerson	122. S. J. Pennycook
56. M. A. Gillespie	123. J. J. Pinajian
57-61. P. H. Green	124. D. B. Poker
62. G. R. Gruzalski	125. H. Postma
63. M. Hagen	126. M. L. Poutsma
64. W. E. Harmon	127. O. A. Pringle
65. J. B. Hayter	128. J. O. Ramey
66. V. G. Hendrix	129. M. Rasolt
67. N. Herbots	130. S. Richardson

131.	C. R. Richmond	157.	L. S. Tyler
132.	G. D. Robbins	158.	J. C. Wang
133.	J. B. Roberto	159.	D. M. Watson
134.	M. T. Robinson	160.	J. R. Weir III
135.	M. W. Rosenthal	161.	J. F. Wendelken
136.	T. H. Row	162.	R. D. Westbrook
137.	B. C. Sales	163.	R. O. Wheeler
138.	O. E. Schow III	164.	C. W. White
139.	S. T. Sekula	165.	F. W. Wiffen
140.	J. L. Sellers	166.	G. D. Wignall
141.	W. D. Shults	167-239.	M. K. Wilkinson
142.	K. Shung	240.	J. M. Williams
143.	T. P. Sjoreen	241.	R. S. Wiltshire
144.	D. L. Slagle	242.	S. P. Withrow
145.	G. S. Smith	243.	R. F. Wood
146.	H. G. Smith	244-248.	F. W. Young, Jr.
147.	E. J. Soderstrom	249.	J. L. Zarestky
148.	E. Sonder	250.	D. M. Zehner
149.	S. Spooner	251.	A. Zucker
150.	J. O. Stiegler	252.	R. A. Zuhr
151.	J. H. Swanks	253.	Biology Library
152.	D. K. Thomas	254-255.	Central Research Library
153.	J. R. Thompson	256.	ORNL-Y-12 Technical Library
154.	J. Z. Tischler	257.	Document Reference Section
155.	K. L. Tsang	258-259.	Laboratory Records Department
156.	D. B. Trauger	260.	Laboratory Records, ORNL - RC

EXTERNAL DISTRIBUTION

261. Dr. Philip H. Abelson, Editor, Science, 1515 Massachusetts Avenue N.W., Washington, DC 20005
262. Dr. S. Amelinckx, SCK/CEN, B 2400-Mol, Belgium
263. Dr. R. T. Arnold, Department of Physics, University of Mississippi, University, MS 38677
264. Prof. Frank Avignone, Chairman, Department of Physics, University of South Carolina, Columbia, SC 29208
265. Dr. K. J. Bachmann, Department of Chemistry, North Carolina State University, Box 5247, Raleigh, NC 27650
266. Dr. R. W. Balluffi, Department of Materials Science and Engineering, Massachusetts Institute of Technology, 77 Massachusetts Avenue, Cambridge, MA 02139
267. Mr. J. H. Barhorst, Emerson Electric, Electronics and Space Division, 8100 W. Florissant, St. Louis, MO 63136
268. Prof. Boris W. Batterman, Applied and Engineering Physics, 227 Clark Hall, Cornell University, Ithaca, NY 14853
269. Dr. George M. Beardsley, Department of Physics and Astronomy, Millsaps College, Jackson, MS 39202
270. Dr. Rainer Behrisch, Max-Planck-Institut für Plasmaphysik, D-8046 Garching bei München, Federal Republic of Germany
271. Bibliothèque, Institut Max von Laue-Paul Langevin, 156 X 38042 Grenoble, Cédex, France
272. Dr. N. Bloembergen, Gordon McKay Laboratory, 9 Oxford Street, Cambridge, MA 02138
273. Dr. M. Blume, Brookhaven National Laboratory, Upton, NY 11973
274. Dr. J. L. Boldu O., Instituto de Física, Universidad Nacional Autónoma de México, Apartado Postal 20-364, 01000 México, D.F.
275. Dr. A. I. Braginski, Westinghouse R&D Center, 401-3A15, 1310 Beulah Road, Pittsburgh, PA 15235
276. Dr. William F. Brinkman, Vice-President for Research, Sandia National Laboratories, P.O. Box 5800, Albuquerque, NM 87115
277. Dr. F. C. Brown, Department of Physics, University of Illinois, Urbana, IL 61801
278. Dr. Walter Brown, Room IE452, Bell Laboratories, 600 Mountain Avenue, Murray Hill, NJ 07974
279. Dr. R. Bullough, Atomic Energy Research Establishment, Harwell, Didcot, Oxon OX11 0RA, England
280. Dr. John Burnett, Division of Chemical Sciences, Office of Basic Energy Sciences, Office of Energy Research, Department of Energy, Washington, DC 20545
281. Dr. Les Butler, Inorganic Chemistry Department, Louisiana State University, Baton Rouge, LA 70803
282. Dr. W. J. L. Buyers, Atomic Energy of Canada Limited, Chalk River Nuclear Laboratories, Chalk River, Ontario K0J 1J0, Canada
283. Prof. Nicolas Cabrera, Departamento de Física Fundamental, Facultad de Ciencias, Universidad Autónoma de Madrid, Canto-Blanco, Madrid 34, Spain
284. Prof. Ray W. Carpenter, Center for Solid State Science, Arizona State University, Tempe, AZ 85287

285. Dr. R. L. Chaplin, Department of Physics, Clemson University, Clemson, SC 29631
286. Dr. Andre Chatelain, Lab. Phys. Exp., Federal Institute of Technology, PH Ecublens, 1015 Lausanne, Switzerland
287. Dr. M. J. Choyke, Westinghouse R&D Center, 1310 Beulah Road, Pittsburgh, PA 15235
288. Dr. Wei-Kan Chu, Department of Physics and Astronomy, University of North Carolina, Chapel Hill, NC 27514
289. Dr. Mui Fatt Chung, Physics Department, National University of Singapore, Singapore 0511
290. Dr. C. B. Clark, Department of Physics, University of North Carolina, Greensboro, NC 27412
291. Dr. G. J. Clark, T. J. Watson Research Center, International Business Machines Corporation, P.O. Box 218, Yorktown Heights, NY 10598
292. Prof. Marvin Cohen, Department of Physics, University of California, Berkeley, CA 94720
293. Dr. Morrel H. Cohen, Exxon Research and Engineering Company, Corporate Research Science Laboratories, P.O. Box 45, Linden, NJ 07036
294. Prof. James M. Corbett, Department of Physics, State University of New York at Albany, Albany, NY 12222
295. Dr. Juan C. Crespi, Comision Nacional de Energía Atómica, Gerencia Desarrollo-Dto. Materiales, Avenida del Libertador 8250, 1429 Buenos Aires, Argentina
296. Mr. Floyd L. Culler, Jr., Electric Power Research Institute, 3412 Hillview Avenue, Palo Alto, CA 94303
297. Dr. Gordon Czjzek, Kernforschungszentrum Karlsruhe, INFP, Postfach 3640, D-7500 Karlsruhe 1, Federal Republic of Germany
298. Dr. L. S. Darken, Tennelec, Inc., 601 Oak Ridge Turnpike, Oak Ridge, TN 37830
299. Dr. Lubomir David, Director, Centro de Física, Instituto Venezolano de Investigaciones Científicas (IVIC), Apartado 1827, Caracas 1010-A, Venezuela
300. Prof. Dr. P. H. Dederichs, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, 5170 Jülich 1, Federal Republic of Germany
301. Dr. J. Diehl, Max-Planck-Institut für Metallforschung, Institut für Werkstoffwissenschaften, Seestrasse 92/BRD, D-7000 Stuttgart 1, Federal Republic of Germany
302. Dr. R. A. DiDio, 127 Senix Avenue, Center Moriches, NY 11934
303. Dr. J. Dienes, Department of Physics 510B, Brookhaven National Laboratory, Upton, NY 11973
304. Prof. Dr. H.-D. Dietze, Institut für Theoretische Physik C, RWTH Aachen, 5100 Aachen, Federal Republic of Germany
305. Dr. G. Dolling, Atomic Energy of Canada Limited, Chalk River Nuclear Laboratories, Chalk River, Ontario K0J 1J0, Canada
306. Dr. D. G. Doran, Hanford Engineering Development Laboratory, P.O. Box 1970, Richland, WA 99352
307. Dr. Mildred Dresselhaus, Rm. 13-2090, Massachusetts Institute of Technology, Cambridge, MA 02139
308. Dr. C. B. Duke, Xerox Webster Research Center, Xerox Square 114, Rochester, NY 14644
309. Dr. Dean E. Eastman, T. J. Watson Research Center, International Business Machines Corporation, P.O. Box 218, Yorktown Heights, NY 10598
310. Dr. Norman Edelstein, MMRD/Bldg. 70A/Room 1115, Lawrence Berkeley Laboratory, Berkeley, CA 94720
311. Prof. Henry Ehrenreich, D.A.S. Pierce Hall 205A, Harvard University, Cambridge, MA 02138
312. Dr. Yic Emery, Department of Physics, Brookhaven National Laboratory, Upton, NY 11973
313. Harriet L. Fadem, Librarian, National Synchrotron Light Source, Brookhaven National Laboratory, Upton, Long Island, New York 11973
314. Dr. G. P. Felcher, Argonne National Laboratory, 9700 South Cass Avenue, Argonne, IL 60439
315. Dr. C. Peter Flynn, Director, Materials Research Laboratory, University of Illinois, 104 S. Goodwin, Urbana, IL 61801
316. Dr. F. Y. Fradin, Argonne National Laboratory, Science Building 212, 9700 South Cass Avenue, Argonne, IL 60439
317. Prof. Dr. Werner Frank, Max-Planck-Institut für Metallforschung, Institut für Physik, Heisenbergstrasse 1, D-7000, Stuttgart 80, Federal Republic of Germany
318. Dr. Roger Frech, Department of Chemistry, University of Oklahoma, Norman, OK 73019
319. Prof. Arthur Freeman, Physics Department, Northwestern University, Evanston, IL 60201
320. Dr. J. Friedel, Physique des Solides, Université Paris Sud, 91405 Orsay, France
321. Dr. A. T. Fromhold, Department of Physics, Auburn University, Auburn, AL 36849
322. Dr. Noboru Fukusaka, Department of Physics, College of General Education, Osaka University, Toyonaka, Osaka 560, Japan
323. Dr. W. B. Gauster, Physical Research Division 8347, Sandia National Laboratories, Livermore, CA 94550
324. Dr. H. A. Gersch, School of Physics, Georgia Institute of Technology, Atlanta, GA 30332
325. Dr. J. F. Gibbons, Stanford Electronics Laboratories, McCullough 220, Stanford University, Stanford, CA 94305
326. Dr. A. N. Goland, Associate Chairman for Energy Sciences, Department of Applied Sciences, Bldg. 179A, Brookhaven National Laboratory, Upton, NY 11973
327. Dr. M. Guinan, Lawrence Livermore National Laboratory, P.O. Box 808, Livermore, CA 94550
328. Dr. Eitan Gurewitz, Nuclear Research Centre-Negev, P.O. Box 9001 Beer-Sheva, Israel
329. Dr. Kichinosuke Harada, Head, Division of Physics, Japan Atomic Energy Research Institute, Tokai Research Establishment, Tokai-mura, Naka-gun, Ibaraki-ken 319-11, Japan
330. Dr. Juergen Hauck, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, D-5170 Jülich 1, Federal Republic of Germany

331. Prof. B. Henderson, Department of Pure and Applied Physics, Trinity College, Dublin 2, Ireland
332. Dr. T. J. Hicks, Department of Physics, Monash University, Clayton, Victoria, Australia 3168
333. Dr. J. K. Hiroven, Code 52150, Naval Research Laboratory, Washington, DC 20390
334. Dr. J. W. Hodby, University of Oxford, Clarendon Laboratory, Oxford OX1 3PU, England
335. Dr. P. C. Holloway, Department of Materials Sciences and Engineering, University of Florida, Gainesville, FL 32601
336. Dr. H. H. Hopkins, Jr., Rockwell International, Atomics International Division, Rockwell-Hanford Operations, P.O. Box 800, Richland, WA 99352
337. Dr. J. C. Houmann, Risø National Laboratory, DK-4000 Roskilde, Denmark
338. Dr. Marc Hou, Physique des Surfaces, Faculté des Sciences, Université Libre de Bruxelles, Campus de la Plaine (C.P. 234), Boulevard de Triomphe, B-1050 Bruxelles, Belgium
339. Dr. John J. Hren, Department of Materials Science & Engineering, University of Florida, Gainesville, FL 32611
340. Dr. A. E. Hughes, Materials Development Division 8552, Atomic Energy Research Establishment, Harwell, Didcot, Oxon OX11 0RA, England
341. Dr. Louis C. Ianniello, Director, Division of Materials Sciences, Office of Basic Energy Sciences, Office of Energy Research, ER-13, Department of Energy, Washington, DC 20545
342. Dr. Tadao Iwata, Division of Physics, Japan Atomic Energy Research Institute, Tokai-mura, Naka-gun, Ibaraki-ken 319-11, Japan
343. Dr. P. K. Iyengar, Director, Physics and Chemical Groups, Bhabha Atomic Research Centre, Bombay 400 085, India
344. Dr. Vincent Jaccarino, Department of Physics, University of California, Santa Barbara, CA 93106
345. Ms. Beth Jinkerson, University Programs Division, Oak Ridge Associated Universities, P.O. Box 117, Oak Ridge, TN 37830
346. Dr. A. Wayne Johnson, Division 5126, Sandia National Laboratories, Albuquerque, NM 87185
347. Dr. W. A. Kamitakahara, Ames Laboratory and Department of Physics, Iowa State University, Ames, IA 50011
348. Dr. D. W. Kamm, Department of Physics, Albion College, Albion, MI 49224
349. Dr. Takaji Kaneda, Research Laboratories, Ashigara, Fuji Photo Film Company, Ltd., Minami-Ashigara, Kanagawa, 250-01 Japan
350. Dr. Fred Keller, Department of Physics, Clemson University, Clemson, SC 29631
351. Dr. Q. H. Khan, N.P.D., PINSTECH, P. O. Nilore, Rawalpindi, Pakistan
352. Dr. D. L. Kinser, Department of Materials Science, Box 1689-B, Vanderbilt University, Nashville, TN 37235
353. Dr. J. S. Koehler, Physics Department, University of Illinois, Urbana, IL 61801
354. Prof. Eckhard Krätzig, Universität Osnabrück, Fachbereich Physik, Postfach 4469, 4500 Osnabrück, Federal Republic of Germany
355. Dr. R. H. Kropschot, Associate Director for Basic Energy Sciences, Office of Energy Research, ER-10, Department of Energy, Washington, DC 20545
356. Prof. J. Kühler, Theoretische Physik, Institut für Festkörperphysik, Technische Hochschule Darmstadt, Hochschulstrasse 2, 6100 Darmstadt, Federal Republic of Germany
357. Dr. Gerard H. Lander, PNS-372, Argonne National Laboratory, 9700 South Cass Avenue, Argonne, IL 60439
358. Dr. S. S. Lau, Department of EECS, C-014, University of California at San Diego, La Jolla, CA 92093
359. Library, Building 465, Atomic Energy Research Establishment, Harwell, Didcot, Oxon OX11 0RB, England
360. Library, Department of Physics, Quaid-I-Azam, University Islamabad, Pakistan
361. Dr. A. B. Lidiard, Theoretical Physics Division, Building 424.4, Atomic Energy Research Establishment, Harwell, Didcot, Oxon OX11 0RA, England
362. Dr. W. M. Lomer, Director, UKAEA Culham Laboratory, Abingdon, Oxon OX14 3DB, England
363. Dr. C.-K. Loong, Argonne National Laboratory, 9700 S. Cass Avenue, Argonne, IL 60439
364. Dr. Stephen W. Lovesey, Rutherford Appleton Laboratory, Chilton, Didcot, Oxon OX11 0QX, England
365. Dr. G. Lucovsky, Department of Physics, North Carolina State University, Raleigh, NC 27650
366. Dr. J. W. Lynn, Department of Physics, University of Maryland, College Park, MD 20742
367. Dr. R. W. Major, Department of Physics, University of Richmond, Richmond, VA 23173
368. Dr. W. C. Mallard, Department of Physics and Astronomy, Georgia State University, Atlanta, GA 30303
369. Dr. P. M. Marcus, T. J. Watson Research Center, International Business Machines Corporation, P.O. Box 218, Yorktown Heights, NY 10598
370. Dr. J. H. Mayer, Department of Materials Sciences, Cornell University, Ithaca, NY 14853
371. Dr. A. Merlini, Physics Division, C.C.R. EURATOM, 21020 Ispra (Varese), Italy
372. Dr. James L. Merz, Electrical and Computer Engineering Department, University of California, Santa Barbara, CA 93106
373. Dr. E. W. J. Mitchell, Department of Physics, Clarendon Laboratory, University of Oxford, Parks Road, Oxford, OX1 3PU, United Kingdom
374. Dr. I. V. Mitchell, Solid State Science Branch, Atomic Energy of Canada, Ltd., Chalk River Nuclear Laboratories, Chalk River, Ontario K0J 1J0, Canada
375. Dr. J. W. Mitchell, Department of Physics, University of Virginia, Charlottesville, VA 22901

376. Dr. Y. Morii, Japan Atomic Energy Research Institute, Tokai-mura, Naka-gun, Ibaraki-ken 319-11, Japan
377. Dr. R. B. Murray, Office of Graduate Studies, University of Delaware, Newark, DE 19711
378. Dr. Yutaka Nakai, Osaka University, Suita, Osaka, Japan 545
379. Dr. H. Naramoto, Japan Atomic Energy Research Institute, Uchisaiwai-cho, Chiyoda-ku, Tokyo, Japan
380. Dr. Jagdish Narayan, Microelectronics Center of North Carolina, P.O. Box 12889, Research Triangle Park, NC 27709
381. Dr. M.-A. Nicolet, Department of Electrical Engineering, 116-81, California Institute of Technology, Pasadena, CA 91125
382. Dr. Frank Nolfi, Division of Materials Sciences, Office of Basic Energy Sciences, Office of Energy Research, Department of Energy, Washington, DC 20545
383. Dr. L. H. Mosanow, Director, Division of Materials Research, National Science Foundation, Washington, DC 20550
384. Dr. A. S. Nowick, Columbia University, 1146 S. W. Mudd Building, New York, NY 10027
385. Oak Ridge Associated Universities, MERT Division Library, P.O. Box 117, Oak Ridge, TN 37830
386. Office of Assistant Manager for Energy Research and Development, Department of Energy, Oak Ridge Operations Office, Oak Ridge, TN 37830
- 387-466. Office of Information Services, Oak Ridge Associated Universities, P.O. Box 117, Oak Ridge, TN 37830
467. Dr. D. N. Olson, Department of Physics, St. Olaf College, Northfield, MN 55057
468. Dr. V. M. Orera, Departamento de Optica, Facultad de Ciencias, Universidad de Zaragoza, Zaragoza, Spain
469. Dr. A. W. Overhauser, Department of Physics, Purdue University, West Lafayette, IN 47907
470. Dr. Robert L. Park, Director, Center for Materials Research, University of Maryland, College Park, MD 20742
471. Dr. P. S. Peercy, Division 5112, Sandia National Laboratories, Albuquerque, NM 87115
472. Dr. Hans Peisl, Sektion Physik, Universität München, Geschwister-Scholl-Platz 1, 8000 München 22, Federal Republic of Germany
473. Physics/Optics/Astronomy Library, 374 Bausch and Lomb Building, University of Rochester, Rochester, NY 14627
474. Dr. Elliott Pierce, Director, Division of Chemical Sciences, Office of Basic Energy Sciences, Office of Energy Research, Department of Energy, Washington, DC 20545
475. Dr. Lothar A. R. Pintschovius, Kernforschungszentrum Karlsruhe GmbH, Postfach 3640, D-7500 Karlsruhe 1, Federal Republic of Germany
476. Dr. E. W. Plummer, Department of Physics, University of Pennsylvania, Philadelphia, PA 19104
477. Dr. J. M. Poate, Bell Laboratories, 600 Mountain Avenue, Murray Hill, NJ 07974
478. Dr. P. P. Pronko, Universal Energy Systems, 3195 Plainfield Road, Dayton, OH 45432
479. Dr. Y. Quéré, Centre d'Études Nucléaires de Fontenay-aux-Roses, B.P. No. 6, 92260 Fontenay-aux-Roses (Seine), France
480. Dr. V. R. Ramakrishnan, Biology Department, Brookhaven National Laboratory, Upton, NY 11953
481. Dr. W. Reichardt, Kernforschungszentrum Karlsruhe GmbH, Institut für Angewandte Kernphysik 1, Postfach 3640, D-7500 Karlsruhe, Federal Republic of Germany
482. Dr. R. W. Reynolds, General Research Corporation, 307 Winn Drive, Huntsville, AL 35807
483. Dr. James R. Rice, Division of Applied Sciences, Rm 224, Pierce Hall, Harvard University, 29 Oxford Street, Cambridge, MA 02138
484. Dr. E. Rimini, Istituto di Struttura della Materia, Dell Università, 57 Corso Italia, 195129 Catania, Italy
485. Dr. T. Risse, Institute for Energy Technology, P.O. Box 40, 2007 Kjeller, Norway
486. Dr. J. E. Rives, Department of Physics, University of Georgia, Athens, GA 30602
487. Dr. Joachim Roth, Max-Planck-Institut für Plasmaphysik, 8046 Garching bei München, FRG
488. Dr. Marvin L. Roush, Chemical and Nuclear Engineering, University of Maryland, College Park, MD 20742
489. Dr. J. M. Rowe, Reactor Radiation Division, National Bureau of Standards, Washington, DC 20234
490. Dr. J. J. Rush, Reactor Radiation Division, National Bureau of Standards, Washington, DC 20234
491. Dr. F. W. Saris, FOM-Institute for Atomic and Molecular Physics, P.O. Box 4.483, 1009 DB Amsterdam, The Netherlands
492. Dr. H. Sato, School of Materials Engineering, Purdue University, West Lafayette, IN 47907
493. Dr. William R. Savage, Department of Physics and Astronomy, University of Iowa, Iowa City, IA 52242
494. Dr. C. K. Saw, Argonne National Laboratory, 9700 S. Cass Avenue, Argonne, IL 60439
495. Dr. Kurt Scharnberg, Institut für Angewandte Physik, Universität Hamburg, Jungiusstrasse 11, D-2000 Hamburg 36, Federal Republic of Germany
496. Dr. W. Schilling, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, 5170 Jülich 1, Federal Republic of Germany
497. Prof. Dr. W. Schmatz, Kernforschungszentrum Karlsruhe GmbH, Institut für Angewandte Kernphysik 1, Postfach 3640, D-7500 Karlsruhe, Federal Republic of Germany
498. Dr. W. Schnepple, EG&G, Energy Measurements Group, Santa Barbara Operations, 130 Robin Hill Road, Goleta, CA 93017

499. Prof. R. Schuttler, I.N.S.A. Service Informatique, Avenue de Rangueil, F-31077 Toulouse, Cédex, France
500. Dr. H.-B. Schweer, Institut für Plasmaphysik der Kernforschungsanlage Jülich GmbH, Postfach 1913, 5170 Jülich 1, Federal Republic of Germany
501. Prof. Dr. A. Seeger, Max-Planck-Institut für Metallforschung, Institut für Physik, Heisenbergstrasse 1, Postfach 80 06 65, 7000 Stuttgart 80, Federal Republic of Germany
502. Dr. David N. Seidman, Department of Materials Science and Engineering, Bard Hall, Cornell University, NY 14850
503. Dr. G. Shirane, Department of Physics, Bldg. 5108, Brookhaven National Laboratory, Upton, NY 11973
504. Dr. C. G. Skull, Department of Physics, 13-2154, Massachusetts Institute of Technology, Cambridge, MA 02139
505. Dr. W. A. Sibley, Assistant Vice President for Research, 101 Whitehurst Hall, Oklahoma State University, Stillwater, OK 74074
506. Dr. R. H. Silsbee, Clark Hall, Physics Department, Cornell University, Ithaca, NY 14853
507. Prof. Dr. T. Springer, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, D-5170 Jülich 1, Federal Republic of Germany
508. Dr. C. Stassis, Physics Department, Iowa State University, Ames, IA 50011
509. Dr. D. K. Stevens, Deputy Associate Director for Basic Energy Sciences, Office of Energy Research, ER-11, Department of Energy, Washington, DC 20545
510. Dr. J. R. Stevenson, Executive Assistant to the President, Georgia of Technology, Atlanta, GA 30332
511. Prof. R. Street, Vice-Chancellor, The University of Western Australia, Nedlands, Western Australia 6069, Australia
512. Dr. B. W. Stritzker, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, 5170 Jülich 1, Federal Republic of Germany
513. Dr. Thomas Surek, Photovoltaic Program Office, Solar Energy Research Institute, 1617 Cole Boulevard, Golden, CO 80401
514. Dr. M. L. Swanson, Atomic Energy of Canada Limited, Chalk River Nuclear Laboratories, Chalk River, Ontario K0J 1J0, Canada
515. Dr. F. J. E. Tasset, Institut Max Von Laue-Paul Langevin, BP 156X, 38042 Grenoble Cédex, France
516. Dr. D. O. Thompson, Ames Laboratory, Iowa State University, Ames, IA 50010
517. Dr. M. W. Thompson, Vice-Chancellor, University of East Anglia, Norwich, Norfolk, NR4 7TJ, England
518. Dr. J. O. Thomson, Department of Physics, The University of Tennessee, Knoxville, TN 37996-1200
519. Dr. R. M. Thomson, National Bureau of Standards, Washington, DC 20234
520. Dr. H. T. Tohver, Department of Physics, University of Alabama, Birmingham, AL 35233
521. Dr. G. T. Trammell, Physics Department, Rice University, P. O. Box 1892, Houston, TX 77251
522. Dr. J. G. Traylor, Buena Vista College, Storm Lake, IA 50588
523. Dr. R. Y. Tsaur, MIT Lincoln Laboratory, Lexington, MA 02173
524. Dr. K. N. Tu, T. J. Watson Research Center, International Business Machines Corporation, P.O. Box 218, Yorktown Heights, NY 10598
525. Prof. David Turnbull, Division of Applied Sciences, Harvard University, Cambridge, MA 02138
526. Universidade Federal de Minas Gerais, ICEx-Cx.P. 702-Depto. de Física (Instituto de Ciências Exatas), Serviço de Documentação, 30.000-Belo Horizonte-MG-Brasil
527. Dr. W. P. Unruh, Department of Physics and Astronomy, University of Kansas, Lawrence, KS 66045
528. Dr. Gerard van der Leeden, EG&G ORTEC, 100 Midland Road, Oak Ridge, TN 37830
529. Dr. Priya D. Vashishta, Solid State Sciences Division, Argonne National Laboratory, Bldg. 223, 9700 South Cass Avenue, Argonne, IL 60439
530. Dr. W. E. Vehse, Department of Physics, University of West Virginia, Morgantown, WV 26506
531. Dr. H. Verbeek, Max-Planck-Institut für Plasmaphysik, 8046 Garching bei München, Federal Republic of Germany
532. Dr. Donald L. Vieth, Chief, Materials and Radiation Effects Branch, Division of Development and Technology, Office of Fusion Energy, Office of Energy Research, Department of Energy, Washington, DC 20545
533. Dr. P. R. Vijayaraghavan, Nuclear Physics Division, Bhabha Atomic Research Centre, Trombay, Bombay 400 085, India
534. Dr. F. L. Vook, Solid State Sciences, Org. 1100, Sandia National Laboratories, Albuquerque, NM 87185
535. Dr. N. Wakabayashi, Keio University, Yokohama, Japan
536. Prof. David Walsh, Department of Physics, Ernest Rutherford Physics Building, McGill University, 3600 University Street, Montreal PQ, H3A 2T8, Canada
537. Dr. G.-C. Wang, 4 Vandenburg Lane, Ithaca, NY 12110
538. Prof. George D. Watkins, Sherman Fairchild Laboratory 161, Department of Physics, Lehigh University, Bethlehem, PA 18015
539. Dr. Harlan L. Watson, Deputy Staff Director, Subcommittee on Energy Development & Applications, Committee on Science & Technology, U.S. House of Representatives, 8374 Rayburn House Office Building, Washington, DC 20515
540. Dr. R. A. Weeks, P.O. Box 1687, Vanderbilt University, Nashville, TN 37235
541. Dr. A. M. Weinberg, Director, Institute for Energy Analysis, Oak Ridge Associated Universities, Oak Ridge, TN 37830

- 542. Prof. Dr. H. F. Wenzl, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, 5170 Jülich 1, Federal Republic of Germany
- 543. Dr. K. Werner, Institut für Festkörperforschung der Kernforschungsanlage Jülich GmbH, Postfach 1913, 5170 Jülich 1, Federal Republic of Germany
- 544. Prof. S. Werner, Department of Physics, University of Missouri, Columbia, MO 65201
- 545. Dr. C. A. Wert, Head, Department of Metallurgy and Mining Engineering, University of Illinois, Urbana, IL 61801
- 546. Dr. A. R. Williams, T. J. Watson Research Center, International Business Machines Corporation, P.O. Box 218, Yorktown Heights, NY 10598
- 547. Dr. W. Williams, Materials Research Laboratory, University of Illinois, 104 S. Goodwin Avenue, Urbana, IL 61801
- 548. Dr. S. C. Wilson, Semiconductor Group, Motorola, Inc., Mail Drop B-132, 5006 East McDowell, Phoenix, AZ 85008
- 549. Dr. L. M. Wilson, Department of Physics, Oklahoma State University, Stillwater, OK 74078
- 550-556. Dr. William A. Hoffman, Jr., Director, Oak Ridge Science Semester, GLCA, Denison University, Main Street, Granville, OH 43023
- 557. Dr. Mark C. Wittels, Division of Materials Sciences, Office of Basic Energy Sciences, Office of Energy Research, ER-132, Department of Energy, Washington, DC 20545
- 558. Prof. Dr. H. Wollenberger, Hahn-Meitner-Institut für Kernforschung Berlin GmbH, Glienicke Strasse 100, D-1000 Berlin 39, Federal Republic of Germany
- 559. Dr. R. T. Young, Energy Conversion Devices, Inc., 1675 West Maple Road, Troy, MI 48064
- 560. Dr. Solomon Zwerdling, Northeast Solar Energy Center, 70 Memorial Drive, Cambridge, MA 02142
- 561-587. Technical Information Center, Department of Energy, Oak Ridge, TN 37830