CONF - 790862 - 2

MASTER

PHONON SCATTERING IN METALLIC GLASSES *

by

J. L. Black
Department of Physics
Brookhaven National Laboratory **
Upton, New York 11973

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States, nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights.

* Invited talk at the Third International Conference on Phonon Scattering at Providence, Rhode Island, August 1979.

** Work supported by Division of Basic Energy Sciences, U. S. Department of Energy, under Contract No. EY-76-C-02-0016.

The submitted manuscript has been authored under contract EY-76-C-02-0016 with the Division of Basic Energy Sciences, U.S. Department of Energy. Accordingly, the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U.S. Government purposes.

fy

PHONON SCATTERING IN METALLIC GLASSES

J. L. Black

Physics Department
Brookhaven National Laboratory
Upton, New York 11973

INTRODUCTION

The purpose of this article is to review some recent theoretical and experimental developments in the study of metallic glasses at temperatures near or below 1K. In this temperature regime, it appears that practically all glasses, whether metallic or insulating, behave in a similar fashion. The fact that such similarities occur, despite substantial structural differences between metallic and insulating glasses¹, constitutes a major theoretical challenge. This challenge, however, is not directly addressed in what follows. Instead, we shall concentrate upon the evidence for universal behavior and upon the theory which is necessary to understand this evidence. It turns out that most of this evidence involves a comparison of phonon scattering in metallic glasses with its counterpart in insulating glasses.

The theoretical framework for describing the low-temperature properties of amorphous solids is provided by the tunneling model of Anderson et al² and Phillips³. This model is a phenomenological prescription for calculating the effects of local rearrangements within the glassy structure. In the simplest version, these atomic rearrangements produce low-energy excitations which are quantum-mechanical two-level systems (TLS). These form a dilute (concentration of TLS active below 1K is less than 10^{-5}) collection of $S=\frac{1}{2}$ pseudospins which interact with the strain fields caused by long-wavelength phonons. It is an established fact that this model describes most low-temperature properties of insulating glasses in considerable detail⁴. From a fundamental point of view, this success supports the idea that the insulating-glass "ground state" actually consists of many states of roughly the

same energy and that some small fraction of these states are accessible to each other within experimental time scales. We are then led to wonder whether these principles apply to metallic glasses, and (if so) whether the conduction electrons affect the behavior of the TLS.

EVIDENCE AND PUZZLES

The natural way to look for TLS in metallic glasses involves those experiments which give convincing proof in insulating glasses. In this list of experiments⁴ we find the linear specific heat, the T^2 thermal conductivity, the $\ln T$ sound velocity, the saturation of the sound attenuation, the ability of one ultrasonic pulse to diminish the absorption of a second pulse, and generation of phonon echoes by coherently excited TLS. In metallic glasses, direct electronic contributions to the specific heat and thermal conductivity overwhelm the TLS effect unless special methods of eliminating the electrons can be devised. By using such methods, Matey and Anderson⁵ and Graebner et al⁶ have reported evidence for TLS in several bulk metallic glasses, while von Löhneysen and Steglich⁷ have done the same for amorphous metallic films. On the other hand, ultrasonic experiments are not masked by direct electronic contributions in competition with the TLS. Bellessa and coworkers⁸ have observed the distinctive logarithmic temperature dependence of the sound velocity in numerous metallic glasses. Most significantly Doussineau et al⁹ and Golding et al¹⁰ have seen convincing evidence of saturation of the ultrasonic attenuation in the bulk metallic glass PdSiCu. Taken together, these experiments are strong support for the existence of TLS in metallic glasses.

Upon closer examination, however, a number of puzzles appear. As shown in Figure 1, the phonon flux required to saturate the absorption is several orders of magnitude greater in a metallic glass than in its insulating counterpart at the same temperature and frequency. Secondly, consider the attenuation which remains after the resonant attenuation has been fully saturated. A comparison between metal^{10,11} and insulator¹² of the temperature dependence of this additional absorption, usually called relaxation- α ¹², is shown in Figure 2. In the metallic glass, this absorption rises at a lower temperature and obviously has a much weaker T dependence than the insulating glasses. A third point of difference is that various effects involving two or more ultrasonic pulses separated by very small time intervals are completely absent in metallic glasses¹⁰. In the insulating glasses, these effects include phonon echoes¹³ and the saturation of one pulse by another⁴. Finally, a number of discrepancies in the magnitude

Figure 1. Curves showing typical metallic vs insulating behavior in the saturation of ultrasonic attenuation at temperatures near 10mK and frequencies near 1GHZ. Absorption is normalized to its low-power value.

Figure 2. Illustration of the different temperature dependence in the relaxational attenuation in a metallic glass¹⁰ (PdSiCu) as compared with a typical insulating glass¹² (e.g. SiO₂).

and temperature/frequency dependence of the resonant absorption in metallic glasses have been pointed out by Matey and Anderson¹⁴ and by Araki et al¹⁵.

Table 1 presents a summary of the experimental situation in metallic glasses with an emphasis on the comparison with insulators. It is apparent that there are some very substantial differences, which raises the question of whether a TLS in a metal is intrinsically different than a TLS in an insulator. As we shall see below, making such an intrinsic distinction is not justified. Most of the apparent differences in Table 1 can be understood by taking into account effects of the conduction electrons upon the TLS.

THE ELECTRON/TLS INTERACTION

In insulating glasses, the TLS are described by

$$H_0 = \sum_i E_i S_i^z + \sum_i (2M_i S_i^x + D_i S_i^y) e_i + H_{\text{phonon}}, \quad (1)$$

where E_i is the energy splitting of the TLS at site i , whose state is described by the Pauli matrices $2S_i^a (a=x, y, z)$. The strain field e_i modifies the TLS environment, leading to the coupling tensors M_i and D_i . Similarly, it is expected that the TLS will be coupled to conduction electrons in a metallic glass¹⁶⁻¹⁸. Figure 3 shows a schematic representation of the atomic displacements, d_i , associated with a single TLS whose atomic cores are located at positions $X_\ell = R_\ell^0 \pm \frac{1}{2} d_i$. Associated with each of these cores is an atomic pseudopotential which causes the electrons to see a potential whose Fourier transform has the form

$$V_{L,R}(q) = \frac{1}{v} u(q) \rho_{L,R}(q) \quad (2)$$

where $u(q)$ is the pseudopotential, v is the atomic volume, and the TLS density operator is given by

$$\rho_{L,R}(q) = \sum_{\ell=1}^{N'} e^{iqX_\ell} \quad (3)$$

The N' atoms comprising the TLS may be in the "left" state (L) or "right" state (R). As shown in Figure 3, the existence of these two positions for each core gives rise to a difference potential $V_L - V_R$, which is the origin of the important coupling to the TLS. If we now express X_ℓ in terms of the pseudospin operators of Eq. (1), we obtain interaction terms of the form¹⁸:

Table 1. Classification of Metallic Glass Experiments
(With References in Parentheses)

INSULATOR-LIKE BEHAVIOR	UNUSUAL BEHAVIOR
Linear Specific Heat (6)	Size of Saturation Threshold (9,10)
T^2 Thermal Conductivity (5,6,7)	T-Dependence of Relaxational Absorption (10,11)
$\ln T$ Sound Velocity (8)	Absence of Two-Pulse Saturation (10)
Saturation of Resonant Absorption (9,10)	Absence of Phonon Echoes (10)
	Quantitative Discrepancies in Resonant Absorption (14,15)

Figure 3. Schematic drawing of the origin of the electron/TLS coupling. The displacement of the ions in a TLS from the "L" position to the "R" position leads to a difference potential, $V_R - V_L$, which is felt by the electrons.

$$H_1 = \frac{1}{N} \sum_{i,k,q} e^{iqr_i} [v_{||}^i(q) S_A^i + v_{\perp}^i(q) S_x^i] c_{k+q}^+ c_k, \quad (4)$$

where N is the total number of atoms, c_k is an electron operator, and r_i denotes the center of the TLS from which X_ℓ is measured. The coupling matrix elements are given by¹⁸

$$\begin{pmatrix} v_{||}^i(q) \\ v_{\perp}^i(q) \end{pmatrix} = \frac{2iu(q)}{v} \sum_{\ell} e^{iqX_{\ell}^0} \sin(qd_{\ell}/2) \begin{pmatrix} \Delta^i/E^i \\ \Delta_0^i/E^i \end{pmatrix}, \quad (5)$$

where Δ is the well asymmetry and Δ_0 is the tunneling energy for the TLS⁴.

Given the existence of this coupling, a number of interesting possibilities then present themselves. For example, what types of temperature-dependent contributions to the electrical resistivity arise from Eq. (4)? Can the TLS contribute (as phonons do) to the attractive electron-electron interactions which lead to superconductivity? Can the electrons produce RKKY-type "spin-spin" interactions among the TLS? Does a Korringa-type decay process significantly alter the dynamics of the TLS? For the present discussion of phonon scattering, it turns out that this last question is the most relevant.

PHONON SCATTERING REVISITED

The "spin lattice" relaxation rate T_1^{-1} controls the return to thermal equilibrium of a TLS which has been disturbed, for example, by an ultrasonic pulse. In insulating glasses, this rate is governed by exchange of energy with the thermal phonon bath⁴. In metals, electronic excitations provide an alternative, extremely efficient mechanism. This "Korringa process" follows from a Golden Rule calculation¹⁰ based upon Eq. (4):

$$T_1^{-1} = \frac{\pi}{4\hbar} (\rho V_A)^2 E \coth(\beta E/2) \quad (6)$$

where ρ is the electronic density of states per atom at E_F and E is the TLS energy splitting. A rough estimate from Eqs. (5) and (6), using $u/v = 2\text{eV}$, $k_F d = 0.1$, and $\rho = .5 \text{ eV}$ yields a T_1 in the nanosecond regime at $T = 10\text{mK}$ and $E/\hbar = 1\text{GHz}$. This value is to be compared with a T_1 in the millisecond regime for an insulating glass at the same temperature and energy splitting. It is this tremendous difference which explains many of the apparent puzzles listed in Table 1.

Consider, for example, the saturation curves shown in Figure 1. The point at which saturation occurs is determined by the

competition between the driving ultrasonic field e_i , which reduces S_z , and the relaxation rate T_1^{-1} which restores it toward $\langle S_z \rangle$. By demanding that these two processes balance at threshold, it follows^{4,10} that the critical ultrasonic intensity is proportional to T_1^{-2} . Quantitative agreement with the observed threshold in PdSiCu glass has been obtained from Eq. (6) using $\rho V \approx 0.2$, which is reasonable for the values of u/v , $k_F d$, and ρ mentioned above¹⁰. In fact, this value of the coupling also gives a straightforward explanation for the lack of multipulse saturation and coherent effects in metallic glasses. The TLS simply returns to thermal equilibrium long before the second pulse arrives.

Further evidence for this fast relaxation comes from the anomalous relaxational absorption illustrated in Figure 2. This type of absorption occurs¹² as the TLS responds to a harmonically varying modulation of its energy splitting resulting from the term proportional to D in Eq. (1). This response is governed by the relationship between the frequency ω of the modulating strain field and the response rate T_1^{-1} of the TLS, leading to an absorption proportional to $\langle A(A^2 + 1)^{-1} \rangle$, where $A = \omega T_1$. Generally this type of absorption remains small at low temperatures, where A is large, and first becomes significant when $A=1$. As illustrated in Figure 2, this condition is met at a significantly lower temperature in a metallic glass. Furthermore, the linear E dependence of T_1^{-1} in a metal (compared with E^3 for an insulator) leads to a more gradual temperature dependence in the metallic glass. All of these results are in reasonable quantitative agreement with the data^{10,11} for PdSiCu when the value $\rho V = 0.2$ is used¹⁰.

A conclusive test of these ideas would be to "remove" the conduction electrons by cooling the metallic glass below the superconducting transition at T_c . Recent calculations by Black and Fulde¹⁹ show that the electronic contribution to T_1^{-1} is exponentially activated for $T \ll T_c$ and increases with infinite slope for $T \lesssim T_c$. The predicted consequence for the relaxational absorption of Figure 2 is a dramatic crossover from the insulating to the metallic curve as T increases toward T_c or as a magnetic field is applied. Similar effects should be observable in the saturation threshold and in multipulse ultrasonic experiments.

CONCLUSIONS

We have reviewed the evidence that TLS exist in metallic glasses and have shown that most of the ultrasonic puzzles can be understood in terms of a fast decay process via the conduction electrons. Of the remaining puzzles, it is interesting to note that the experiments of Araki et al.¹⁵ almost certainly fall into a previously unexplored region ($T_1^{-1} \gg \omega$) of resonant attenuation in glasses, where new effects may be expected. Furthermore, it has become apparent that the ultrasonic evidence for a new inter-

action in the form of Eq. (4) gives new impetus to the search for effects of the TLS upon the electronic properties of metallic glasses^{16-18,20}. All of these new effects and possibilities are interesting in themselves, but they should not be allowed to obscure the significance of the fact that a model originally designed for insulating glasses^{2,3} can be supplemented without essential modification to explain low-temperature experiments in metallic glasses.

REFERENCES

1. D. Weaire, *Contemp. Phys.* 17, 173 (1976).
2. P.W. Anderson, B.I. Halperin, and C.M. Varma, *Phil. Mag.* 25, 1 (1972).
3. W.A. Phillips, *J. Low-Temp. Phys.* 7, 351 (1972).
4. S. Hunklinger and W. Arnold in *Physical Acoustics*, ed. by R.N. Thurston and W.P. Mason, (Academic Press, N.Y., 1976) 12, 155.
5. J.R. Matey and A.C. Anderson, *J. Non-Cryst. Sol.* 23, 129 (1977).
6. J.E. Graebner, B. Golding, R.J. Schutz, F.S.L. Hsu, and H.S. Chen, *Phys. Rev. Lett.* 39, 1480 (1977).
7. H. v.Löhneysen and F. Steglich, *Z. Phys. B* 29, 89 (1978).
8. G. Bellessa, *J. Phys. C* 10, L285 (1977).
9. P. Doussineau, P. Legros, A. Levelut and A. Robin, *J. Phys. (Paris) Lett.* 39, L265 (1978).
10. B. Golding, J.E. Graebner, A.B. Kane, and J.L. Black, *Phys. Rev. Lett.* 41, 1487 (1978).
11. B. Golding, J.E. Graebner, and W.H. Haemmerle in *Proc. of Int. Conf. on Lattice Dynamics*, ed. by M. Balkanski (Flammarion, Paris, 1977), p. 348; P. Doussineau, A. Levelut, G. Bellessa, and O. Bethoux, *J. Phys. (Paris) Lett.* 38, L483 (1977).
12. J. Jäckle, L. Piche, W. Arnold, and S. Hunklinger, *J. Non-Cryst. Sol.* 20, 365 (1976).
13. J.E. Graebner and B. Golding, *Phys. Rev. B* 19, 964 (1979).
14. J.R. Matey and A.C. Anderson, *Phys. Rev. B* 17, 5029 (1978).
15. H. Araki, G. Park, A. Hikata, and C. Elbaum, proceedings of this conference.
16. R. Cochrane, R. Harris, J. Ström-Olson, and M. Zuckerman, *Phys. Rev. Lett.* 35, 676 (1975).
17. J. Kondo, *Physica* 84B, 40, 207 (1976).
18. J.L. Black, B.L. Gyorffy and J. Jäckle, *Phil. Mag.* (in press, Aug. 1979).
19. J.L. Black and P. Fulde, *Phys. Rev. Lett.* 43, 453 (1979).
20. J.L. Black and B. Gyorffy, *Phys. Rev. Lett.* 41, 1595 (1978).

Acknowledgements - The author wishes to thank P. Fulde, B. Golding, J.E. Graebner, G. Gyorffy, and J. Jäckle for useful discussions. Work supported by the Division of Basic Energy Sciences, Department of Energy, Contract No. EY-76-C-02-0016.