140
2-28-92 85①

BNL 52304

A COMPARISON OF SOLIDIFICATION MEDIA FOR THE STABILIZATION OF LOW-LEVEL RADIOACTIVE WASTES

M.G. Cowgill

October 1991

**NUCLEAR WASTE AND MATERIALS TECHNOLOGY DIVISION
DEPARTMENT OF NUCLEAR ENERGY
BROOKHAVEN NATIONAL LABORATORY, ASSOCIATED UNIVERSITIES, INC.
UPTON, NEW YORK 11973**

**CONTRACT NO. DE-AC02-76CH00016
UNITED STATES DEPARTMENT OF ENERGY**

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

BNL--52304

DE92 007981

BNL 52304

UC-630

(Environmental Compliance and Risk
Assessment - DOE/OSTI-4500-R75)

A COMPARISON OF SOLIDIFICATION MEDIA FOR THE STABILIZATION OF LOW-LEVEL RADIOACTIVE WASTES

M.G. Cowgill

October 1991

**NUCLEAR WASTE AND MATERIALS TECHNOLOGY DIVISION
OFFICE OF ENVIRONMENTAL GUIDANCE
ENVIRONMENT, SAFETY AND HEALTH
UNITED STATES DEPARTMENT OF ENERGY**

**BROOKHAVEN NATIONAL LABORATORY
UPTON, LONG ISLAND, NEW YORK 11973**

MASTER

EP

ABSTRACT

When requirements exist to stabilize low-level radioactive waste (LLW) prior to disposal, efforts to achieve this stability often center on the mixing of the waste with a solidification medium. Although historically the medium of choice has been based on the use of portland cement as the binder material, several other options have been developed and subsequently implemented. These include thermoplastic polymers, thermosetting polymers and gypsum. No one medium has thus far been successful in providing stability to all forms of LLW. The characteristics and attributes of these different binder materials are reviewed and compared. The aspects examined include availability of information, limitations to use, sensitivity to process or waste chemistry changes, radionuclide retention ability, modeling of radionuclide release processes, ease and safety of use, and relative costs.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT.	iii
LIST OF TABLES.	vi
EXECUTIVE SUMMARY	vii
1. INTRODUCTION.	1
2. AVAILABILITY.	2
2.1 Cementation Processes.	2
2.2 Thermoplastic Polymers	3
2.3 Thermosetting Polymers	3
2.4 Gypsum	3
3. LIMITATIONS TO USE.	3
3.1 Cementation Processes.	4
3.2 Thermoplastic Polymers	4
3.3 Thermosetting Polymers	4
3.4 Gypsum	4
4. SENSITIVITY TO PROCESS OR WASTE CHEMISTRY CHANGES	5
4.1 Cementation Processes.	5
4.2 Thermoplastic Polymers	5
4.3 Thermosetting Polymers	5
4.4 Gypsum	5
5. RADIONUCLIDE RETENTION ABILITY.	6
5.1 Cementation Processes.	6
5.2 Thermoplastic Polymers	6
5.3 Thermosetting Polymers	6
5.4 Gypsum	7
6. MODELING OF RADIONUCLIDE RELEASE PROCESSES.	7
7. EASE AND SAFETY OF USE.	7
7.1 Cementation Processes.	7
7.2 Thermoplastic Polymers	8
7.3 Thermosetting Polymers	8
7.4 Gypsum	8
8. APPROXIMATE RELATIVE COSTS.	9
8.1 Cementation Processes.	10
8.2 Thermoplastic Polymers	10
8.3 Thermosetting Polymers	10
8.4 Gypsum	11

TABLE OF CONTENTS (cont.)

	<u>Page</u>
9. SUMMARY	11
10. REFERENCES	11

LIST OF TABLES

Table 1	Chemical Tolerance of Solidification Agents	15
Table 2	Diffusion Coefficients and Leachability Indices in Cement-Based Waste Forms	16
Table 3	Comparative Costs for Cementation and Bituminization Processing of Sludge	17
Table 4	Comparative Costs for Cementation and Bituminization Processing of Spent Resins	18
Table 5	Approximate Costs Associated with Various Solidification Media.	19
Table 6	Summary of Solidification Media Characteristics and Attributes.	20
Table 7	Comparison of the Properties of Immobilized Waste Forms	21

EXECUTIVE SUMMARY

Low-level radioactive waste (LLW) is being continuously produced as a result of a variety of operations and processes, including nuclear fuel fabrication, operation of nuclear power plants and in medical, educational and research facilities. Irrespective of the source of the waste, there exist requirements by the US Nuclear Regulatory Commission (NRC) that LLW with specific radioactivity characteristics (Classes B and C, and some Class A) be stabilized in some form prior to disposal. The stability thus imposed is intended to ensure that the waste does not degrade structurally and affect the overall stability of the disposal site, ultimately leading to water infiltration. Stabilization is also intended to limit exposure to an inadvertent intruder to the site. Among other benefits, handling, transportation and interim storage of the waste are facilitated if the waste is in a stabilized form, and the potential for migration of radioactive species into the biosphere is minimized greatly. In practice, the required stability is often achieved by solidification in an inert and durable medium.

During the early years of LLW disposal, stabilization by solidification was generally sought using cement or concrete as binder material, but other options were subsequently investigated and developed. Some, such as incorporation in bitumen, have enjoyed a degree of success, while others, including encapsulation in urea formaldehyde, have proved to have insurmountable problems. However, no one method appears to offer a panacea for all waste streams and situations. As was pointed out by Akins in 1983, *"to select one (solidification agent) as a universal system would be wrong ... each system must be evaluated on its merits in conjunction with all the specific parameters of its intended use."*

The present review summarizes the findings to date relative to the following solidification media options:

- * cementation (using portland cement, lime/flyash, etc.)
- * thermoplastic polymers (primarily bitumen)
- * thermosetting polymers (vinyl-ester styrene, etc.)
- * gypsum

Emphasis has been placed on those options which are available commercially and have been demonstrated to be viable to various degrees. At the same time, it is recognized that other media are being researched as possible future options. Included in these possibilities are polymer-impregnated cement, polyethylene, modified sulfur cement and vitrification. However, though some of these other methods have reached advanced stages of development and demonstration, their viability has yet to be demonstrated on a commercial scale and it is not possible to fully assess their suitability at this stage. It should also be pointed out that problems have been encountered with the solidification of some specific waste streams, and most waste generators frequently use high integrity containers (HICs) to provide the required stability for Class B and C wastes. These containers are generally very expensive but this disadvantage may be offset to some degree by simplified processing of the wastes. In particular, utilities prefer HICs for many reasons, including ease of use, lack of on-site solidification capability, etc. However, it has been pointed out that, when account is taken of transportation and disposal costs, the use of high integrity containers is still at least twice as expensive as incorporating the waste in,

for example, oxidized asphalt. How, or if, this situation will change in the future is difficult to predict.

The various solidification media options have been reviewed in terms of the availability of information, the limitations to use, the sensitivity to changes in the process or waste stream characteristics, the ability to retain radionuclides, the availability of models describing the radionuclide release processes, the ease and safety of use, and the approximate relative costs. In keeping with the task directive, no attempt was made to perform a detailed technical evaluation of the various waste forms and degradation mechanisms but such factors may be critical in a final analysis. Choosing the most appropriate solidification system (or systems) for processing LLW is not a simple problem and consideration must be given to many factors. Cost estimation alone is a particularly complicated area with many uncertainties regarding future commodity prices and transportation and disposal rates. On the technical side, the vast majority of the data available have been obtained from short term testing and there is a significant lack of information on the long term stability of all the waste forms. In addition, although models have been developed to predict radionuclide release rates, confirmatory testing of these models is still required. The findings of the review are summarized in the following table.

TABLE ES-1

Summary of Solidification Media Characteristics and Attributes

	Cementation Processes	Thermoplastic Polymers	Thermosetting Polymers	Gypsum
Data available: short-term long-term	Much Some	Much Little	Adequate Some	Adequate Little
Waste stream limitations	Ion exchange resins; oils; organics; borates and boric acid.	Oxidizing agents (e.g. nitrates); organic liquids.	Boric acid; Borates; wastes must be dewatered.	Few
Sensitivity to changes in waste chemistry	Very sensitive	Relatively insensitive	Relatively insensitive	Very insensitive
Radionuclide retention ability	Cs hard to retain; Co, Sr much more tightly bound.	Retention ability much better than cement.	Retention ability much better than cement.	Cs and Co very hard to retain.
Modeling development	Some	Little	Some	Little
Ease and safety of use	Materials safe to handle; process simple but detailed characterizing of wastes needed.	Process simple but potential fire hazard due to high temperatures.	Processes more complex; material may be flammable.	Similar to cementation; process may be simpler; detailed characterizing of wastes not needed.
Relative costs: materials processing transport disposal	Low Low High High	High High Low Low	Very high High Moderate Moderate	Low Low Moderate Moderate

1. INTRODUCTION

Low-level radioactive waste (LLW) is being continuously produced as a result of a variety of operations and processes, including nuclear fuel fabrication, operation of nuclear power plants, and in medical, educational and research facilities. Irrespective of the source of the waste, there exist requirements by the US Nuclear Regulatory Commission (NRC) that LLW with specific radioactivity characteristics be stabilized in some form prior to disposal (see 10 CFR Part 61). The stability thus imposed is intended to ensure that the waste does not degrade structurally and affect the overall stability of the disposal site, ultimately leading to water infiltration. Stabilization is also intended to limit exposure to an inadvertent intruder to the site. Among other benefits, handling, transportation and interim storage of the waste are facilitated if the waste is in a stabilized form, and the potential for migration of radioactive species into the biosphere is minimized greatly. Guidance on the test methods and results acceptable to the NRC for demonstrating waste form stability is contained in the NRC's "Technical Position on Waste Form" [Higginbotham, 1983] and the recent revision of that document [Lohaus, 1991]. In practice, the required stability is often achieved by solidification in an inert and durable medium.

Solidification generally was achieved during the early years of LLW disposal using cement or concrete as binder material [Burns, 1971]. However, other options were subsequently investigated and developed. Some, such as incorporation in bitumen, have enjoyed a degree of success, while others, including encapsulation in urea formaldehyde, have proved to have insurmountable problems. Discussion of the various solidification options can be found in several sources (for example, [IAEA, 1968], [Burns, 1971], [Colombo, 1976], [Aubouin, 1980], [Claes, 1980], [Oyen, 1980], [Fuhrmann, 1981], [USAEWES, 1982], [Akins, 1983], [Davis, 1983], [Tucker, 1983], [IAEA, 1985], [Moghissi, 1986], [Colombo, 1988] and [Conner, 1990]). It is worthwhile noting at this point that no one method appears to offer a panacea for all waste streams and situations. As [Akins, 1983] concluded, *"to select one (solidification agent) as a universal system would be wrong ... each system must be evaluated on its merits in conjunction with all the specific parameters of its intended use."*

The present review summarizes the findings to date relative to the following solidification media options:

- * cementation (using portland cement, lime/flyash, etc.)
- * thermoplastic polymers (primarily bitumen)
- * thermosetting polymers (vinyl-ester styrene, etc.)
- * gypsum

Emphasis has been placed on those options which are available commercially and have been demonstrated to be viable to various degrees. At the same time, it is recognized that other media are being researched as possible future options. Included in these possibilities are polymer-impregnated cement, polyethylene, modified sulfur cement and vitrification. However, though some of these other methods have reached advanced stages of development and demonstration, their viability has yet to be demonstrated on a commercial scale and it is not possible to fully assess their suitability at this stage. It should also be pointed out that problems have been encountered with the solidification of some waste streams, and most waste generators frequently use high integrity containers (HICs) to provide the required stability for Class B and C wastes. These

containers are generally very expensive (approximately \$8000 for a 200 cubic feet model, according to [Silvey, 1988]) but this disadvantage may be offset by simplified processing of the wastes. In particular, utilities prefer HICs for many reasons, including ease of use, lack of on-site solidification capability, etc. However, [Silvey, 1988] points out that, when account is taken of transportation and disposal costs, the use of high integrity containers is still at least twice as expensive as incorporating the waste in oxidized asphalt. How, or if, this situation will change in the future is difficult to predict.

The following sections discuss the various options in terms of the availability of information, the limitations to use, the sensitivity to changes in the process or waste stream characteristics, the ability to retain radionuclides, the availability of models describing the radionuclide release processes, the ease and safety of use, and the approximate relative costs.

2. AVAILABILITY OF INFORMATION

In cases where approval is sought from the NRC for use of a commercial process to solidify LLW, a vendor usually submits a Topical Report describing the process and presenting the results of tests performed to demonstrate that the wastes have been adequately stabilized. Although submittal and approval of a Topical Report is not mandatory, it represents for the vendor a convenient method for demonstrating compliance with 10 CFR 61.56 and with the requirements imposed by the States to which the wastes may be sent for disposal. Some of the information in a Topical Report is often of a proprietary nature and not readily available. However, the reports usually include some basic data on the material and waste form properties, and the anticipated limitations on usage, in non-proprietary sections. Almost invariably, the data presented in the reports are of a short-term nature.

2.1 Cementation Processes

In the current document, the term "cementation" is used in a very loose generic manner. It includes, in addition to solidifications based on plain portland cement, those which are lime-based and those employing various additives such as pozzolana and silicates. In the early days of LLW disposal, solidifications were usually attempted with plain portland cement (generally Types I, II or III) as the binder material. However, as difficulties began to be encountered with specific waste streams, it was found necessary to incorporate one or more additives into the mixtures in order to produce waste forms with the desired stability. The development of these binder mixes (and others based on lime) has been extensively documented and a considerable database exists concerning the performances of the various waste forms thereby produced, both in the US and in other countries. The current status of cement stabilization of LLW in the US is described in detail in [USNRC, 1989].

There are several commercial solidification systems available in the US and elsewhere based on the cementation process, and information from vendors and other sources is readily available. *Most of the information has been obtained using small, laboratory-size samples and with relatively short term (90 day) testing (this statement is also true for all other solidification media).* In the US, these tests derived from the guidance contained in the NRC's Technical Position on Waste Form [Higginbotham, 1983] (recently revised - see [Lohaus, 1991]). Waste form criteria in European countries and elsewhere differ from

those in the US but qualification of a process is still based mainly on the results of short term tests. However, test programs have been in place in some facilities to acquire data on the stability of cement-based waste forms over longer times. These are now beginning to produce results (see, for example, [Lee, 1989]).

2.2 Thermoplastic Polymers

Only one thermoplastic polymer - bitumen (asphalt) - is in use as a binding medium for LLW. Development has taken place over a period of more than 20 years and several processes involving solidification of specific waste streams in bitumen have been commercialized, principally in Europe but also in the US. Considerable information is readily available on the properties and performance of such waste forms (see, for example, [OECD, 1976] and [Snellman, 1985]), but, again, most of it has been obtained from short term studies, including, in the US, those related to meeting the NRC waste form criteria [Higginbotham, 1983]. Few studies of the performance of the waste forms over the long term appear to have been reported. This is a particularly critical deficiency in view of the fact that degradation has been reported following extended exposure to moisture [Snellman, 1985].

2.3 Thermosetting Polymers

The principal thermosetting polymers used in solidifying LLW are vinyl ester-styrene (VES) (often referred to as Dow binder, after the Dow Chemical Co. which developed the process), polyester resins and epoxy resins. Their development has taken place more recently than those of the cementation and bituminization processes but all are in commercial use in the US and elsewhere. Most of the data readily available were obtained from short-term tests but diligent searching can also reveal data on the long-term performances of the different binding media. Urea formaldehyde was also used as a binder for a period of time but problems were encountered which led to its withdrawal from use. Specifically, urea formaldehyde-based waste forms were found to release acidic liquids after solidification was apparently completed and these, in turn, caused accelerated corrosion of the containers.

2.4 Gypsum

The sole gypsum-based binding medium, marketed as ENVIROSTONE, has been used to solidify LLW until very recently. However, although there have been no problems comparable to that which led to the discontinuation of urea formaldehyde as a solidification agent, there are concerns about the softening of gypsum when exposed to moisture and the NRC has withdrawn approval of its use. Information on ENVIROSTONE-stabilized waste forms is readily available but essentially restricted to performance in short-term tests.

3. LIMITATIONS TO USE

It is obvious from the continuing research into the development of solidification media that no one option has been universally accepted for all applications and that there are limitations to use in all cases. A very brief summary of the limitations of some specific solidification agents with respect to waste streams is to be found in [Moghissi, 1986] and is presented here in Table 1. [Colombo, 1988] provides detailed tabulations of DOE wastes for

potential treatment by the various generic groups of solidification agents. However, the report includes the caveat that *"these predictions ... do not imply that these wastes can be satisfactorily solidified,"* and *"... the potential solidification options should be regarded as preliminary."*

The following paragraphs indicate which waste streams, in general, have proved difficult to solidify satisfactorily using the various options. In this context, a waste is considered by the NRC to be "solidified satisfactorily" when the end product meets the criteria specified in the latest version of the NRC's Technical Position on Waste Form [Lohaus, 1991].

3.1 Cementation Processes

There are many variants on the basic cementation procedure and it is claimed by the vendors that, by choosing the appropriate combination of cement and additives, virtually any LLW can be solidified. However, some waste streams (most notably, ion exchange resins) have proven to be less amenable than others, particularly when the NRC's revised criteria [Lohaus, 1991] are applied. Typical of the problems encountered are the failures experienced when full-scale solidifications of Epicor-II resins were attempted following the development of apparently successful procedures in the laboratory [Barletta, 1984]. Other waste streams which have proved difficult to solidify by cementation include borates and boric acid, sulfates, oils and other organic liquids.

3.2 Thermoplastic Polymers

Bitumen is used to solidify many of the same wastes as the cementation systems, sometimes more successfully, as with boric acid concentrates. Problems are likely to be encountered when trying to solidify organic liquids. Also, the process is not recommended for wastes which contain nitrates and other oxidizing agents. These not only lead to accelerated deterioration of solidified waste forms but also greatly increase the fire hazard of the process. However, probably the most significant factor which could limit the use of bitumen is the ability of water to diffuse in the waste form. This is a relatively slow process but, depending on the wastes contained and their loading factor, this could lead to swelling and cracking of the waste form.

3.3 Thermosetting Polymers

Thermosetting polymers in general appear to be as versatile as bitumen in the wastes they can stabilize. VES is compatible with most wastes although problems can be experienced when trying to solidify boric acid wastes if procedures are not adhered to very closely. The polyester processes, while able to incorporate most wastes, require that they be dry or dewatered, thus steps must be included to ensure that this is so. Solidification in epoxies can be achieved without the necessity of dewatering or drying, and there would appear to be few restrictions regarding the type of LLW which can be incorporated.

3.4 Gypsum

The polymer-modified gypsum cement known as ENVIROSTONE has been used to immobilize many types of LLW and appears to be particularly appropriate for acidic wastes and for oils. However, compressive strengths of waste forms are generally quite low; although greater than the 60 psi minimum criterion contained in the NRC's original Technical Position on Waste Form [Higginbotham, 1983], they

are often much less than the 500 psi minimum recommendation provided for cement-based waste forms in Revision I of the Technical Position [Lohaus, 1991].

4. SENSITIVITY TO PROCESS OR WASTE CHEMISTRY CHANGES

4.1 Cementation Processes

The cementation processes involve complex water-cement chemistries and are sensitive to the physical and chemical characteristics of the waste streams. As a consequence, process control programs prescribe very detailed characterization of the waste stream before solidification processing begins. If required, the waste should be pretreated so that its properties fall within the values deemed necessary to produce a successful solidification. It is also of importance that the cement and additive ingredients be in the appropriate proportions and that mixing procedures, such as order of additions, mixing speed and time, etc., should be followed. To assure that the formulations used are producing successful solidifications, it is a requirement that verification and surveillance specimens be prepared for Class B and C wastes, the latter with the intent of ascertaining that the waste forms remain stable with time [Lohaus, 1991].

4.2 Thermoplastic Polymers

Bitumen solidifications are relatively insensitive to variations in waste stream chemistry due to the fact that hardening depends only on cooling, not on chemical reaction. The main concern is that the waste stream have a pH value of around 7 or higher, a requirement which may necessitate pretreatment of acidic wastes such as boric acid. The process system contains fewer operating parameters than a cement-based system but such process variables as the evaporative capacity of the extruder and the extruder temperature profile are critical if a satisfactory solidification is to be accomplished.

4.3 Thermosetting Polymers

Although all the thermosetting polymer methods are generally thought to be fairly insensitive to variations in waste chemistry, the processes themselves, which may involve up to four components, are chemically more complex than bituminization. This means that the processes have to be closely controlled. Also, with regard to the waste streams, attention must be given to pH values, which, if necessary, should be adjusted to ensure that satisfactory solidification can take place.

4.4 Gypsum

The hardening process is less chemically complex than that of the portland cement-based mixes and thus subject to fewer variables. However, waste stream pH values must be closely monitored and, if necessary, adjusted. If not, solidification may be significantly retarded.

5. RADIONUCLIDE RETENTION ABILITY

There exists a fairly extensive data base on the ability of the various solidification media to retain radionuclides. Most data, however, are restricted to just three elements - cesium, strontium and cobalt. Data on other elements such as iodine, technetium, uranium and plutonium, are very sparse.

5.1 Cementation Processes

[Sullivan, 1989] contains a comprehensive summary of all the data available in the literature on diffusion coefficients and leachability indices (the leachability index, LI, is the negative of the logarithm of the diffusion coefficient) of various nuclides in cement, from which can be deduced the ability of cement-based solidifications to retain these nuclides. The wide variability in the diffusion coefficient data, which can be seen in Table 2, reflects the dependence on nuclide, on waste stream and on cement mixture. The LI information to be found in [McIsaac, 1988] show slightly wider ranges of values for cesium and cobalt but a similar one for strontium. In general, the cement-based waste forms seem most capable in retaining carbon-14, and, to a lesser extent, cobalt. Strontium and tritium are somewhat more strongly retained than cesium, which appears the most susceptible to leaching. However, this latter tendency can be reduced by the use of pozzolanic-type admixtures. There are also data available on the diffusion and sorption of iodine in cement but the processes involved appear quite complex [Atkinson, 1988]. Leach data on LLW containing transuranic elements can be found in [Welch, 1983].

In a related area, there is some information available on the leaching of organic decontamination agents from ion exchange resin beds solidified in cement. According to [Soo, 1988], both EDTA and LOMI reagents have LI values generally in the range 9 to 11. However, [McIsaac, 1988] reports that the LI for EDTA is much lower than this, in the range 5.8 to 9.0. [McIsaac, 1988] also provides data on other agents such as citric acid (6.5 to 11.0) and oxalic acid (7.2 to 10.7).

5.2 Thermoplastic Polymers

Leach test studies on bitumen indicate that such waste forms have, in general, better nuclide retention properties than cement-based waste forms. Both [Mattus, 1987] and [Simpson, 1989] report the LI of cesium to be in excess of 8.0 (values as low as 6.0 have been noted with some cement-based waste forms). Cobalt and strontium have higher values, typically 9.0 or greater. [IAEA, 1985] and [Dougherty, 1986] indicate that it is not unusual for cesium release rates from bitumen to be more than two orders of magnitude less than those from cement (this is equivalent to a four order of magnitude increase in LI) while cobalt appears to be retained slightly more strongly by cement than bitumen. Retention of strontium by bitumen is slightly better than by cement (LI calculated to be about an order of magnitude higher). Carbon-14 release from bitumen is of the same order of magnitude as it is from cement. As with the portland cement-based waste forms, there is some dependence of the values on waste stream but the data spread is not as wide.

5.3 Thermosetting Polymers

The thermosetting polymers appear to have similar nuclide retention properties to bitumen in many cases, though there are exceptions [IAEA, 1985].

[Aubouin, 1980] includes diffusion coefficient data on cesium in polyester or epoxy resin which indicate leachability indices ranging from 8.1 to 12.0. There is also dependence on waste stream characteristics with cesium being more strongly retained than cobalt in some instances but vice versa in others. [Tucker, 1983] reports diffusion data on a polyester product from Toshiba that indicate a leachability index of around 10 (no nuclides defined). [Dougherty, 1986] provides data which show that cesium release from VES is at least two orders of magnitude less than that from cement and similar to that from bitumen. However, there is no significant difference between the release rates from VES of cesium, strontium and cobalt. On the negative side, the ability to retain carbon-14 is much less for polyester than for either cement or bitumen [IAEA, 1985].

As with the cement-based solidifications, there are also data available on the leaching from VES of organic decontamination agents [Soo, 1988]. Again, the leachability indices of both EDTA and LOMI reagents were generally in the range 9 to 11.

5.4 Gypsum

The database on leaching of nuclides from ENVIROSTONE is more restricted than that on the cement-based waste forms. Based on information in [Neilson, 1982] and [USG, 1984], gypsum appears to be less capable of retaining nuclides than portland cement. The most significant difference between the two types is in the diffusion coefficients for cobalt, which are at least three orders of magnitude larger in the gypsum-based waste forms and similar to those of cesium.

6. MODELING OF RADIONUCLIDE RELEASE PROCESSES

Knowledge of the processes controlling radionuclide release is critical to the development of source term models such as FEMWASTE and BLT [Sullivan, 1989]. The acquisition of the leach data described above has been accompanied by numerous efforts to model these release processes. There is a general acceptance that, for short-term tests such as the 90-day leach test defined in [ANS, 1986], the release from a solidified waste form can be adequately described by a diffusion-controlled model. However, it is recognized that this is only an approximation which may not be appropriate for describing release over long time periods and which is probably not applicable to all solidification agents and radionuclides. A survey of the various proposed leaching mechanisms can be found in [Dougherty, 1985] and a program to develop an accelerated leach test to determine the long-term leaching behavior of several waste forms is in place [Fuhrmann, 1989]. Interpretation of the data produced by the accelerated leach test program, however, is still based on assumption of a diffusion-controlled process. Most of the model development has been concentrated on cement-based waste forms and on VES. There has been some work in Europe on bitumen waste forms but little work on other solidification media.

7. EASE AND SAFETY OF USE

7.1 Cementation Processes

Solidifications based on portland cement are well established and involve relatively simple operations carried out at room temperature. The level of

worker exposure to radioactive waste is dependent on the amount of clean up needed after the solidification process. This, in turn, is affected by such factors as whether or not the cement/waste mixing operation is performed in the disposal container. In addition, detailed characterization of the waste stream, essential to assure successful solidification, increases the human exposure factor.

7.2 Thermoplastic Polymers

The bituminization process has been developed over many years and early operating problems have been resolved. Though the process is straightforward, the bitumen must be maintained at relatively high temperature during operations in order to maintain flow of the bitumen and the bitumen/waste mixture. There is a fire hazard associated with the use of hot bitumen but the processing temperatures are significantly below the flash point. The solidified waste form does not pose a fire hazard. Equipment clean up after operations may increase human exposure to radioactivity. However, the relative insensitivity of bituminization to waste stream chemistry means that waste characterization need not be as detailed as with the portland cement-based processes and hence there will be much reduced human exposure.

7.3 Thermosetting Polymers

Solidification using thermosetting polymers does not require high temperature operations and is thus inherently easier to accomplish and safer than bituminization. On the other hand, thermosetting processes usually involve more ingredients (for example, catalysts and promoters in addition to the main binder material) than the thermoplastic process, thereby adding a level of complexity. At the same time, the thermosetting polymers share with the bitumen a relative insensitivity to the waste stream chemistry, thus reducing the need for detailed chemical characterization of the waste and enabling worker exposure to be kept to a minimum in this phase.

The Dow process (using VES) is probably the easiest to use as the mixing of the waste and the solidification agent (and the subsequent blending of catalyst and promoter) are all accomplished in the disposal container, thus minimizing worker exposure to radioactivity during clean up operations. The vinyl ester resin in the unsolidified state, is classed as a flammable liquid and requires appropriate precautions to be taken during storage and use. However, the waste form itself is not a fire hazard.

Polyester resin processes require more complex systems as the waste must be dried or dewatered before mixing with the binder. The processes also include premixing before placement in the disposal container, thus presumably increasing worker exposure to radioactivity during clean up operations. Epoxy-based systems involve either premixing (for dry wastes) or in-container mixing (for liquid and wet wastes). Thus, in terms of ease of operation and of safety, the process can be considered similar to the polyester resin systems.

7.4 Gypsum

Processing waste using ENVIROSTONE is generally thought to be somewhat simpler and safer than using portland cement. All operations are performed at room temperature, and gypsum and the additives require no special handling. ENVIROSTONE is less sensitive to waste stream chemistry than the cement-based

mixtures so the necessity for detailed waste characterization (and associated worker exposure to radioactivity) is much reduced. The equipment used in ENVIROSTONE solidification is similar to that used for cement mixtures but the post-solidification cleaning process is reputedly easier.

8. APPROXIMATE RELATIVE COSTS

Cost evaluation of solidification methods is, of course, a complex process which in practice is often handled on an individual case-by-case basis. Economic considerations must take into account not only material and equipment costs, but also those associated with such factors as training of personnel, worker radiation exposure limits, maintenance of equipment, waste volume reduction, and subsequent handling, storage, transportation and disposal of the waste form. On top of these must be imposed a time-based factor which takes into account the susceptibility of costs to change over the years. Perhaps not surprisingly, evaluations and comparisons which have appeared in the literature fail to provide a coherent picture concerning the relative costs of the different processes. Some of these studies are briefly discussed in the following paragraphs.

A fairly detailed account of costs during the 1960s can be found in [IAEA, 1968]. For simplicity, discussion on these early cost figures is limited here to those in [Burns, 1971] relative to the comparative costs for cementation processing versus bituminization for the immobilization of 4.55 m^3 of sludge. Although the figures presented have little meaning in terms of today's currencies and apply only to costs in the UK at that time, they do provide an insight into the relative costs of the two processes. Some of the figures are shown in Table 3. The materials costs given for both processes are very similar which may seem a little odd in view of the fact that bitumen is normally much more expensive than cement. However, if the bitumen could sustain much higher loading efficiencies, then the amount of bitumen needed to process a defined amount of sludge would be much smaller than that needed if cement was used, and total material costs might be very similar. Overall, however, the processing cost remains lower for the cementation because of increased costs associated with the more extensive and complex support facilities required with bituminization. After this point, the bitumen products recover some of the cost differential due to significantly lower shipping and disposal costs.

A more recent comparison of costs between cementation and bituminization is provided in [Doyle, 1986] relative to processing spent resin from a two-unit BWR. The results in terms of $\$/\text{m}^3$ are shown in Table 4. These data are similar to those presented in [Burns, 1971], in that they reflect the much lower cost of shipping and disposal of bituminized waste, but indicate that solidification processing costs are the same for either process. No details are provided on the breakdown of solidification costs so it is difficult to assess the validity of apparent equality in costs in this area.

[Doyle, 1986] credits the volume reduction feature of bituminization with the lowering of costs compared with cementation processes. In a similar vein, the cost analysis performed in [Oyen, 1980] indicates that volume reduction, per se, can lead to savings of over 50% in annual disposal costs compared with conventional cementation processing. In this particular case, the analysis assumes the volume of waste is reduced by drying and incineration, then the resultant ashes are solidified in cement. The report also discusses other methods of volume reduction/solidification, including bituminization, but does

not perform a cost analysis on these other methods. However, it can be inferred that the authors would expect lower overall costs, irrespective of the mode employed.

Another comparison of costs, this of a more general nature and aimed more at the solidification and disposal of hazardous wastes, was compiled in [USAEWES, 1982]. Some of the findings are summarized in Table 5. Though these data are not necessarily completely relevant to processing LLW, they do serve to indicate some of the general cost trends in the solidification phase. These are that cement-based solidifications should involve lower costs than the other processes except gypsum, and that polyester-based solidification is the most costly. However, the bases used in constructing these costs are not completely defined. In particular, the types of waste being solidified are not discussed and this is an important factor in processing LLW.

The concluding paragraphs in this section attempt to summarize the current positions with regard to the individual solidification systems.

8.1 Cementation Processes

The materials used in cement-based solidifications are comparatively cheap and the prices relatively stable. The equipment needed has been developed and tested over the years, is fairly basic in structure and should represent only a modest cost, both in acquisition and maintenance. Negative cost factors, compared to the other processes, include the need for detailed waste characterization and apparently lower waste loading potential for some waste streams. The latter lead to increased costs in subsequent areas such as transportation, storage and disposal.

8.2 Thermoplastic Polymers

The bituminization equipment needs are more complex than those for cement-based solidification, resulting in increased capital, operating and maintenance costs. The basic binder material, bitumen, is a petroleum-derived product and not only much more expensive than the cementation materials but also subject to price instability. On the positive side, higher waste loading and volume reduction factors may be available which result in cost savings in subsequent waste handling and disposal steps. There are also potential savings in that there may be less of a requirement for detailed characterization of the waste before solidification.

8.3 Thermosetting Polymers

Compared with bituminization, equipment requirements in general are simpler, and should lead to lower capital, operating and maintenance costs. Against this must be set significantly higher material costs which are also dependent on the vicissitudes of the oil market. Volume reduction factors are probably similar to those of cement and gypsum (that is, inferior to those of bitumen) but higher waste loading factors might be achievable. Also, because of the relative insensitivity of the binder materials to waste chemistry, savings could be realized in the reduced need for detailed waste characterization.

8.4 Gypsum

Equipment needs and material costs would be similar to those for cement-based solidification and apparently simpler processing controls could lead to slightly lower costs in this area. Cost savings may also be realized from a reduced need for detailed waste characterization and possibly higher waste loading factors.

9. SUMMARY

Table 6 is an attempt to summarize the findings and to simplify comparisons by highlighting the advantages and disadvantages of each process in the context of the present report. No attempt has been made to perform a detailed technical evaluation of the various waste forms and degradation mechanisms. Such factors as the potential effects of water ingress on the stability of bitumen-based waste forms may be critical in the final analysis. Table 7, taken from [IAEA, 1985], compares the properties of immobilized waste (specifically, ion-exchange resins) from a slightly different perspective. Comparison tables can also be found in other sources. However, as will have become readily apparent, choosing the most appropriate solidification system (or systems) for processing LLW is a not a simple task and consideration must be given to many factors. Cost estimation alone is a particularly complicated area with many uncertainties regarding future commodity prices, and transportation and disposal rates. On the technical side, the vast majority of the data available have been obtained from short term testing and there is a significant lack of information on the long term stability of all the waste forms. In addition, although models have been developed to predict radionuclide release rates, confirmatory testing of these models is still required.

10. REFERENCES

[Akins, 1983]

M.J. Akins, G. Costomiris, P. Delete and R.B. Wilson, "The Options of Solidifying Low Level Waste," Nuclear Engineering International, March 1983, pp 42-46.

[ANS, 1986]

American Nuclear Society, "Measurement of the Leachability of Solidified Low-Level Radioactive Wastes by a Short-Term Test Procedure," ANSI/ANS-16.1, April, 1986.

[Atkinson, 1988]

A. Atkinson and A.K. Nickerson, "Diffusion and Sorption of Cs, Sr and I in Water-Saturated Cement," Nuclear Technology 81:100-113 (1988).

[Aubouin, 1980]

G. Aubouin, P. Hallier and J.P. Bruand, "Experience with the Incorporation of Low and Medium-Level Wastes in Thermosetting Resins," in "Radioactive Waste Management and Disposal" (edited by R. Simon and S. Orlowski), Harwood Academic Publishers, New York, 1980, pp. 261-278.

[Barletta, 1984]

R.E. Barletta and R.E. Davis, "Review of a Test Program for Qualifying the Solidification of Epicor-II Resins with Cement," NUREG/CR-3496, BNL-NUREG-51712, January, 1984.

[Burns, 1971]

R.H. Burns, "Solidification of Low- and Intermediate-Level Wastes," Atomic Energy Review 9:547-599, 1971.

[Claes, 1980]

J. Claes and K. Brodersen, "Overview of Management of Medium Level Wastes," in "Radioactive Waste Management and Disposal" (edited by R. Simon and S. Orłowski), Harwood Academic Publishers, New York, 1980, pp. 279-301.

[Colombo, 1976]

P. Colombo and R.M. Neilson, Jr., "Critical Review of the Properties of Solidified Radioactive Waste Packages Generated at Nuclear Power Reactors," BNL-NUREG-50591, December, 1976.

[Colombo, 1988]

P. Colombo, "Encapsulation Development Phase 1: Detailed Project Planning and Concept Development Project," BNL-41460 (DOE/HWP-54), 1988.

[Conner, 1990]

J.R. Conner, "Chemical Fixation and Solidification of Hazardous Wastes," Van Nostrand Reinhold, New York, 1990.

[Davis, 1983]

M.S. Davis, "The Impact of LWR Decontaminations on Solidification, Waste Disposal and Associated Occupational Exposure Annual Report," NUREG/CR-3444, BNL-Nureg-51699, Vol. 1, August, 1983.

[Dougherty, 1985]

D.R. Dougherty and P. Colombo, "Leaching Mechanisms of Solidified Low-Level Waste, The Literature Survey," BNL-51899, 1985.

[Dougherty, 1986]

D.R. Dougherty, R.F. Pietrzak, M. Fuhrmann and P. Colombo, "Accelerated Leach Test(s) Program Annual Report," BNL-52042, 1986.

[Doyle, 1986]

R.D. Doyle and S.B. Rastberger, "Operating a Transportable Volume Reduction and Solidification System," Trans. ANS 53:126-127 (1986).

[Fuhrmann, 1981]

M. Fuhrmann, R.M. Neilson, Jr., and P. Colombo, "A Survey of Agents and Techniques Applicable to the Solidification of Low-Level Radioactive Wastes," BNL-51521, December, 1981.

[Fuhrmann, 1989]

M. Fuhrmann, R.F. Pietrzak, E.M. Franz, J.M. Heiser III and P. Colombo, "Optimization of the Factors that Accelerate Leaching," BNL-52204, March, 1989.

[Higginbotham, 1983]

L.R. Higginbotham, "Final Waste Classification and Waste Form Technical Position Papers," United States Nuclear Regulatory Commission, May 11, 1983.

[IAEA, 1968]

"Treatment of Low- and Intermediate-Level Radioactive Waste Concentrates," Technical Report Series No. 82, International Atomic Energy Agency, Vienna, 1968.

[IAEA, 1985]

"Treatment of Spent Ion-Exchange Resins for Storage and Disposal," Technical Report Series No. 254, International Atomic Energy Agency, Vienna, 1985.

[Lee, 1989]

D.J. Lee and C.R. Wilding, "Cement Wasteform Properties," Waste Management '89 (R.G. Post, ed.), Arizona Board of Regents, Tucson, AZ, 1989, Vol. 2, pp 319-325.

[Lohaus, 1991]

P.H. Lohaus, "Waste Form Technical Position, Revision 1," United States Nuclear Regulatory Commission, January 24, 1991.

[Mattus, 1987]

A.J. Mattus and M.M. Kaczmarzsky, "Laboratory Performance Testing of an Extruded Bitumen Containing a Surrogate, Sodium Nitrate-Based, Low-Level Aqueous Waste," Waste Management '87 (R.G. Post, ed.), Arizona Board of Regents, Tucson, AZ, 1987, Vol. 3, pp 517-523.

[Moghissi, 1986]

"Radioactive Waste Technology" (edited by A.A. Moghissi, H.W. Godbee and S.A. Hobart) The American Society of Mechanical Engineers, New York, 1986.

[Neilson, 1982]

R.M. Neilson, Jr., and P. Colombo, "Solidification of Ion Exchange Resin Wastes," BNL-51615, August, 1982.

[OECD, 1976]

"The Bituminization of Low and Medium Level Radioactive Wastes," (Proceedings of a Seminar at Antwerp, May 1976) Organization for Economic Co-operation and Development, Paris, July, 1976.

[Oyen, 1980]

L.C. Oyen and R.F. Tucker, Jr., "Advanced Low-Level Radwaste Treatment Systems," EPRI NP-1600, October, 1980.

[Silvey, 1988]

L.M. Silvey and M.M. Kaczmarzsky, "Initial Operating Experience of the Solid Radwaste System at the Hope Creek Generating Station," Waste Management '88 (R.G. Post, ed.), Arizona Board of Regents, Tucson, AZ, 1988, Vol. 1, pp 301-306.

[Simpson, 1989]

S. Simpson, "Waste Form Testing Results for DOE and Commercial Power Reactor Wastes," Waste Management '89 (R.G. Post, ed.), Arizona Board of Regents, Tucson, AZ, 1989, Vol. 2, pp 301-304.

[Soo, 1988]

P. Soo, L.W. Milian and P.L. Piciulo, "The Leachability and Mechanical Integrity of Simulated Decontamination Wastes Solidified in Cement and Vinyl Ester-Styrene," NUREG/CR-5153, BNL-NUREG-52149, May, 1988.

[Snellman, 1985]

"Long-Term Properties of Bituminized Waste Products," (M. Snellman and M. Valkiainen, eds.), Nordic Liaison Committee for Atomic Energy, Norstedts Tryckeri, Stockholm, 1985.

[Sullivan, 1989]

T.M. Sullivan and C.J. Suen, "Low-Level Waste Shallow Land Disposal Source Term Model: Data Input Guides," NUREG/CR-5387 (BNL-NUREG-52206), 1989.

[Tucker, 1983]

R.F. Tucker, Jr., R.A. Nelson and C.C. Miller, "Low-Level Radwaste Solidification," EPRI-NP-2900, 1983.

[USAEWES, 1982]

U.S. Army Engineer Waterways Experiment Station, "Guide to the Disposal of Chemically Stabilized and Solidified Waste," EPA-530-SW-82-872, 1982.

[USG, 1984]

United States Gypsum Corporation, "Topical Report - ENVIROSTONE Gypsum Cement 10 CFR 61 Compliance Testing," USG-684-1, May, 1984.

[USNRC, 1989]

"Workshop on Cement Stabilization of Low-Level Radioactive Waste," NUREG/CP-0103, NISTIR 89-4178, October, 1989.

[Welch, 1983]

J.M. Welch, C.W. Sill and J.E. Flinn, "Leach Tests of Simulated Low-Level Transuranic Waste Forms Containing Transuranic Elements," EGG-FM-6153, January, 1983.

TABLE 1
Chemical Tolerance of Solidification Agents

Waste Stream	Portland Cement	Bitumen	Polyesters
Boric acid concentrate	Poor-fair	Good	Good
Sodium sulfate concentrate	Fair-good	Fair	Good
Alkaline waste solution	Good	Good	Good
Detergent waste solution	Poor	Fair	Fair
Organic liquids	Poor	Fair	Poor
Ion exchange resins	Fair	Fair	Good
Sludges	Good	Good	Good
(based on information in Table 4 in Chapter 8 of [Moghissi, 1986])			

TABLE 2
Diffusion Coefficients and Leachability Indices
in Cement-Based Waste Forms

Nuclide	Diffusion Coefficients (cm ² /s)		Leachability Index
	Low value	High value	
Cs-137	2.8×10^{-11}	1×10^{-6}	6.0 - 10.6
Sr-90	2×10^{-11}	9×10^{-8}	7.0 - 10.7
Co-60	1×10^{-13}	2×10^{-10}	9.7 - 13.0
C-14	7×10^{-15}	1.2×10^{-13}	12.9 - 14.2
H-3	1×10^{-9}	4×10^{-8}	7.4 - 9.0
(based on data in Table A8.2 in [Sullivan, 1989])			

TABLE 3

Comparative Costs for Cementation and Bituminization
Processing of Sludge

Item(s)	Cost (in pounds sterling)	
	Cementation	Bituminization
Materials (cement/bitumen, drums, power, etc.)	23.60	20.60
Non-material costs (wages, overheads, depreciation, maintenance, interest, etc.)	59.00	98.80
Processing cost	82.60	119.40
Transport and disposal	17.10	5.00
Total cost (per 4.55 m ³ sludge)	99.80	124.40
(based on data in [Burns, 1971])		

TABLE 4
Comparative Costs for Cementation and Bituminization
Processing of Spent Resins

Item	Cost (in \$/m ³)	
	Cementation	Bituminization
Solidification	2649	2649
Transportation	1843	971
Burial	2889	1353
Total	7381	4973
(based on data in [Doyle, 1986])		

TABLE 5

Approximate Costs Associated with Various Solidification Media

Solidification Medium	Material Costs (a)	Price Trends	Equipment Costs	Energy Needs
Portland cement	3.00	Stable	Low	Low
Bitumen	18.60	Subject to oil price; increases probable	Very high	High
Polyester	27.70	Subject to oil price; increases probable	Very high	High
Gypsum	Negligible	Stable	Moderate	Moderate

(a) cost (\$) to treat 100 lb of raw waste

(taken from data given in Table 3-6 in [USAEWES, 1982])

TABLE 6

Summary of Solidification Media Characteristics and Attributes

	Cementation Processes	Thermoplastic Polymers	Thermosetting Polymers	Gypsum
Data available: short-term long-term	Much Some	Much Little	Adequate Some	Adequate Little
Waste stream limitations	Ion exchange resins; oils; organics; borates and boric acid.	Oxidizing agents (e.g. nitrates); organic liquids.	Boric acid; Borates; wastes must be dewatered.	Few
Sensitivity to changes in waste chemistry	Very sensitive	Relatively insensitive	Relatively insensitive	Very insensitive
Radionuclide retention ability	Cs hard to retain; Co, Sr much more tightly bound.	Retention ability much better than cement.	Retention ability much better than cement.	Cs and Co very hard to retain.
Modeling development	Some	Little	Some	Little
Ease and safety of use	Materials safe to handle; process simple but detailed characterizing of wastes needed.	Process simple but potential fire hazard due to high temperatures.	Processes more complex; material may be flammable.	Similar to cementation; process may be simpler; detailed characterizing of wastes not needed.
Relative costs: materials processing transport disposal	Low Low High High	High High Low Low	Very high High Moderate Moderate	Low Low Moderate Moderate

TABLE 7

Comparison of the Properties of Immobilized Waste Forms

leach resistance	cement	<	polymers	<	bitumen	<	glass
radiation resistance	polymers	<	bitumen	<	cement	<	glass
mechanical stability	bitumen	<	polymers	<	glass	<	cement
fire resistance	bitumen	≤	polymers	<	cement	<	glass
costs	glass	>	polymers	>	bitumen	>	cement

(taken from TABLE XVI in [IAEA, 1985])

END

DATE
FILMED

4 / 01 / 92

I