Progress Report on

MECHANISM OF MECHANICAL FATIGUE OF FUSED SILICA

Grant No. DE-FG02-85ER45217

Rensselaer Project No. 5-23811

January 1, 1991 -- December 31, 1991

Minoru Tomozawa
Materials Engineering Department
Rensselaer Polytechnic Institute
Troy, New York 12181

January 1992

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Research Accomplishments

(A) Effect of Residual Water in Silica Glass on Static Fatigue

Mechanical fatigue characteristics of abraded and water-soaked silica glass were measured after heat-treatment at various temperatures. It was shown that the fatigue resistance increased with heat-treatment temperature. This was attributed to decreasing water content in the glass near the crack tip. (cf. Appendix A).

(B) Strengthening of Abraded Silica Glass by Hydrothermal Treatment

Mechanical strength of abraded SiO_2 glass was measured after hydrothermal treatment. Strengthening exceeded 100 % by the hydrothermal treatment. This strengthening was most likely due to crack tip blunting. (cf. Appendix B).

(C) Fatigue-resistant Coating of SiO_2 Glass

It was found that a silicon monoxide coating on silica glass improved fatigue resistance of the glass substantially. It is likely that silicon monoxide, which can be oxidized by water, works as a water diffusion trap thus reducing the amount of water penetrating into the glass and its strength degradation. (cf. Appendix C)

(D) Water Entry into Silica Glass During Slow Crack Growth

A nuclear resonance technique was used to measure the hydrogen concentration depth profile on the fracture surfaces of silica glass. Fracture surfaces created by slow crack growth in water and by rapid crack in oil were compared. It was found that the hydrogen concentration and penetration depth were greater in the fracture surfaces produced in water thus suggesting that water enters into the

silica glass during fracture. (cf. Appendix D)

List of Publication in 1991

1. W-T Han and M. Tomozawa, "Effect of Residual Water in Silica Glass on Static Fatigue" J. Non-Crystalline Solids, 127, 97-104 (1991). (Appendix A).

2. W.-T. Han and M. Tomozawa, "Strengthening of Abraded Silica Glass by Hydrothermal Treatment" Ceramic Transactions, 20, 183-190 (1991). (Appendix B)

3. M. Tomozawa, W.-T. Han and K. M. Davis, "Fatigue-Resistant Coating of SiO_2 Glass" SPIE, 1590, 160-167 (1991). (Appendix C).

4. M. Tomozawa, W.-T. Han and W.A. Lanford, "Water Entry into Silica Glass During Slow Crack Growth", J. Am. Ceram. Soc., 74, 2573-2576 (1991). (Appendix D).

END

**DATE
FILMED**

3 / 16 / 92