ANL--90/24

DE92 007001

ARGONNE NATIONAL LABORATORY
9700 South Cass Avenue
Argonne, Illinois 60439

ANL-90/24

**WEIGHT LOSSES OF MARBLE AND LIMESTONE BRIQUETTES EXPOSED TO OUTDOOR
ENVIRONMENTS IN THE EASTERN UNITED STATES**

Results of Exposures, 1984-1988

by

K. J. Reimann

Materials and Components Technology Division

"Work completed June 1990"
Published September 1991

Work Sponsored by

U.S. National Park Service, as part of the
National Acid Precipitation Assessment Program

MASTER

END OF THIS DOCUMENT

CONTENTS

ABSTRACT	1
1 INTRODUCTION	1
2 EXPERIMENTAL PROCEDURES.....	2
3 RESULTS	4
4 DISCUSSION AND CONCLUSIONS.....	9
ACKNOWLEDGMENTS.....	18
REFERENCES	19
APPENDIX A: Weight Losses From Individual Briquettes.....	21
APPENDIX B: Mercury Porosity Measurements.....	27
APPENDIX C: Nuclear Magnetic Resonance Results.....	40
APPENDIX D: Sonoscan Report on Optical Measurements of Acoustic Waves on Marble and Limestone	45

FIGURES

1 Cumulative weight loss and surface recession of marble briquettes as a function of cumulative exposure time at the five sites	10
2 Cumulative weight loss and surface recession of limestone briquettes as a function of cumulative exposure time at the five sites	10
3 Cumulative weight loss and surface recession of marble control briquettes as a function of cumulative elapsed time.....	11
4 Cumulative weight loss and surface recession of limestone control briquettes as a function of cumulative elapsed time	12

5	Comparison of stone recession rates at the five field exposure sites.....	14
6	Cumulative weight loss and surface recession of marble briquettes as a function of cumulative rain depth at the five exposure sites	14
7	Cumulative weight loss and surface recession of limestone briquettes as a function of cumulative rain depth at the five exposure sites	15
8	Cumulative rain depth as a function of cumulative exposure time for the five exposure sites.....	16
9	Recession per rain depth as a function of H^+ ion concentration.....	16
C.1	Briquette dimensions and imaged slice in NMR system	41
C.2	NMR image of slice through center of dry briquette.....	42
C.3	NMR image of slice through center of epoxy-sealed briquette	42
C.4	NMR image of slice through center of briquette after wetting with 10 g of water	43
C.5	NMR image of slice through center of water-saturated briquette	43

TABLES

1	Dates of gravimetric specimen installation and removal at field exposure sites	4
2	Incremental weight change and recession of marble briquettes for period 1984–1988	5
3	Incremental weight change and recession of limestone briquettes for period 1984–1988.....	6
4	Cumulative weight changes of marble briquettes for period 1984–1988.....	7
5	Cumulative weight changes of limestone briquettes for period 1984–1988	8

6	Cumulative weight changes of laboratory control briquettes for period 1984-1988	8
7	Average recession rates of exposed briquettes, by exposure site	12
8	Comparison of estimated annual recession rates.....	13
9	Weight loss and recession as function of rain depth	15
10	Average recession and environmental data for the five exposure sites.....	17
A.1	Weight changes observed in exposed briquettes and control briquettes	21
A.2	Drying and weighing conditions for briquettes after exposure periods	25
B.1	Mercury porosity data for marble layer G	27
B.2	Mercury porosity data for marble layer K.....	30
B.3	Mercury porosity data for limestone layer G.....	33
B.4	Mercury porosity data for limestone layer H	36

**WEIGHT LOSSES OF MARBLE AND LIMESTONE BRIQUETTES EXPOSED TO OUTDOOR
ENVIRONMENTS IN THE EASTERN UNITED STATES
Results of Exposures, 1984-1988**

by

K. J. Reimann

ABSTRACT

Gravimetric changes in marble and limestone briquettes exposed to outdoor environment at five sites in the eastern United States have been monitored since 1984. An earlier report describes procedures and results obtained in 1984-1988. This report presents the results of the exposure period 1984-1988 and reviews and summarizes those of prior years. A linear relationship was found between cumulative gravimetric losses and exposure period or rain depth. These losses resulted in an average recession rate of 14 to 24 $\mu\text{m}/\text{yr}$ for marble and twice that for limestone. Variations in recession among the various exposure sites can be ascribed to differences in rain depth and hydrogen ion concentration. The annual recession rates obtained from gravimetry yielded rates that were for marble twice those obtained from runoff experiments, and more than three times those for limestone; this indicates that physical erosion plays an important role. Gravimetric monitoring of exposed briquettes is continuing in a planned 10-yr program.

1 INTRODUCTION

The effects of acid rain and air pollution on the weathering of Shelburne Marble and Salem Limestone samples exposed to the outdoor environments at five test sites in the eastern United States are being investigated under the National Acid Precipitation Program (NAPAP).¹ The studies of the effects on stone and other building materials are conducted by several federal agencies cooperating in NAPAP. Argonne National Laboratory (ANL) participates in the NAPAP effort as a facility of the U.S. Department of Energy, under the sponsorship of the U.S. Department of Interior, National Park Service.

A variety of methods (e.g., gravimetry, color change, interferometry of roughness/recession change, ion chromatography of surface accumulations, petrographic analyses, and runoff chemistry) are applied to measure stone deterioration. Monitoring of limestone and marble weight after exposure to the environments at the test sites is one of several research tasks performed by ANL.

The environmental exposures of the stone samples, including briquettes for gravimetry, were begun in May 1984 at four established NAPAP materials test sites near

Raleigh, NC; Chester, NJ; Newcomb, NY; and in Washington, DC. A site in Steubenville, OH, was established in 1986 to replace the New Jersey site. The sites (designated NC, NJ, NY, DC, and OH, respectively) are instrumented to record a wide range of environmental parameters.

Sets of gravimetric samples installed in exposure racks at each site were assigned to annual or multiyear periods of exposure in a planned 10-yr schedule. Samples are withdrawn annually on or about the anniversary dates of their installation and sent to ANL for drying and weighing. After the laboratory tests, these samples are returned to their respective field sites for further exposure.

In 1987, additional gravimetry briquettes were installed in a movable rack at the Ohio site. The movable rack slides into a shelter as soon as rainfall begins. In the protective shelter, one set of the briquettes is sprayed with deionized water in the same amount as the quantity of rain per surface area (this is known as the sprayed regime), while the other set stays dry (termed the dry regime). At the end of the rainfall, the movable rack leaves the shelter to be exposed to the normal environment.

To study the gravimetric behavior of the briquettes after prolonged exposure, preexposed slabs of limestone and marble were obtained from buildings destined for demolition or renovation. From these slabs, briquettes were fabricated and installed at the various sites in 1988. The limestone slabs had been preexposed for 80 yr, and the marble 20 yr. Two types of briquettes were fabricated: one with the preexposed surface facing skyward, and the other with the preexposed surface facing groundward.

This report details the results obtained by the gravimetric measurements from May 1984 to September 1988. Data from May 1984 to September 1986 were described in a previous report,² but are included here for completeness.

Description of experimental procedures, detailed in the previous report, is summarized in Section 2 of this report. Results are presented in Section 3, and discussed in Section 4. Weight changes of individual briquettes are listed in Appendix A. Results of tests of the wetting and drying of the limestone, which formed the basis for the premeasurement drying protocol, are given in Appendix B.

2 EXPERIMENTAL PROCEDURES

Briquettes of 51-mm thickness were cut from slabs of marble and limestone obtained by the NAPAP Stone Research Group.^{3,4} The briquette design specified rectangular bottom surfaces 75 by 89 mm in size and smaller top surfaces of 75 by 83 mm. Briquettes were made to

these nominal dimensions and were then wet-ground at edges and corners to reduce the probability of any subsequent loss of weight due to damage to sharp edges during handling. The top surfaces of the marble slabs had been given an 80-grit finish by the supplier; this was retained on the tops of the briquettes, and the other surfaces were wet-ground to 80 grit by ANL. Top surfaces of limestone slabs had been given a "smooth, planed finish"; this was retained on the tops of the limestone briquettes, and the other surfaces were wet-ground to 180 grit by ANL. After fabrication, the samples were rinsed under flowing distilled water while surface powder was removed with a soft bristle brush. After drying in a clean laboratory room, the samples were sealed in bags to await further disposition.

To dry the briquettes for weighing, they were removed from their bags and placed in a drying oven at 50°C for nominally one week. The briquettes were then moved expeditiously to a balance room and allowed to equilibrate with air overnight. The samples were thus brought to a predictable level of dryness, rather than to a condition of absolute dryness. The same procedure was applied to the briquettes returned to ANL after exposure and before measurement.

Each briquette was weighed on a Mettler B5 C1000 balance with 0.2-mg resolution. Afterwards, the briquettes were returned to their individual bags, which were then sealed before the samples were taken from the balance room.

Three briquettes of each stone type were assigned to each field site for the annual cycle of exposure. Three additional briquettes of each type were assigned to each site as field controls to be shipped, dried, and weighed with the exposure samples but never exposed out-of-doors; the purpose was to quantify the effects of handling and transport. Three more briquettes of each type were retained at ANL as laboratory controls to be dried and weighed with every batch of gravimetric samples returned from field sites; the purpose here was to test the effects of measurement methods.

The sets of samples were shipped to and from field sites in hard-cased containers lined with soft padding. Each sample was sealed in its bag and wrapped with two layers of plastic bubblewrap. Ground transport was used when previously exposed briquettes were present in the shipment, to eliminate potential effects of pressure changes, etc., associated with air transport.

At the field sites, the briquettes were exposed in lucite racks that held the samples inclined 30° from the horizontal facing the south and allowed rainwater to drain away freely. The handling protocol specified that vinyl gloves be worn by the site operators when briquettes were installed or removed from racks; samples were to be allowed to dry in the racks before removal on or about the date specified and to be kept in sealed bags when not in racks.

Dates of installation and removal of gravimetric samples at their respective field sites are shown in Table 1. After the first year of exposure, the exposed briquettes and field control briquettes were weighed, sent to the National Bureau of Standards (NBS) for color measurements, and subsequently returned to the sites for redeployment. The color test schedule was changed to a biennial cycle after the second yearly gravimetric measurements, and the briquettes were returned directly to the exposure sites for redeployment. In 1987, the briquettes from all sites, including OH, were weighed and (excluding those of the retired site in NJ) color-tested in accordance with the NBS protocol at ANL before being returned to the sites for redeployment.

3 RESULTS

Averages and standard deviation of gravimetric changes by stone type, exposure site, and exposure period are summarized in Tables 2 and 3. Gravimetric changes in field control and ANL laboratory control briquettes for the same period and site are included for comparison. These control briquettes are kept indoors inside plastic bags, except at the DC site, where they are removed from the bag.

Table 1. Dates of gravimetric specimen installation and removal at field exposure sites

Stone and Operation	Period	NC	NJ	NY	DC	OH	
						Static Rack	Movable Rack
Fresh Stone							
Install Remove	1	5-25-84	3-05-84	6-19-84	8-11-84	7-17-86	-
		5-16-85	6-07-85	6-21-85	8-12-85	7-28-87	-
Install Remove	2	9-16-85	9-16-85	11-20-85	11-12-85	9-02-87	8-03-87
		6-04-86	6-18-86	6-26-86	8-14-86	9-16-88	9-16-88
Install Remove	3	12-16-86	12-22-86	1-06-87	1-06-87	10-17-88	10-17-88
		6-09-87	6-16-87	6-25-87	8-11-87		
Install Remove	4	8-20-87	Disc. ^a	8-28-87	9-14-87	-	-
		7-06-88		7-08-88	9-14-88		
Install		8-02-88	Disc. ^a	8-12-88	10-22-88	-	-
Preexposed Stone		-	-	-	-	-	-
		-	-	-	-	-	-
		NC	NY	DC			
Install		6-09-88	6-10-88	6-08-88	-	6-01-88	6-01-88

^aDiscontinued.

Table 2. Incremental weight change and recession of marble briquettes for period 1984-1988

Site	Exposure Time (days)	Exposed Briquettes				Avg. Loss (g)	
		Avg. Loss (g)	Std. Dev. (g)	Recession, Prorated (μm/yr)	Field Control	Lab. Control	
Period 1 1984-1985							
NC	356	0.2733 ±	0.0173	16.5 ± 1.0	-0.0022	-0.0013	
NJ	367	0.4348 ±	0.0218	25.4 ± 1.3	0.0000	0.0018	
NY	367	0.2877 ±	0.0088	16.8 ± 0.5	0.0005	0.0029	
DC	366	0.3111 ±	0.0044	18.2 ± 0.3	0.0009	0.0016	
Period 2 1985-1986							
NC	261	0.1796 ±	0.0102	14.8 ± 0.8	0.0053	0.0044	
NJ	275	0.3483 ±	0.0239	27.2 ± 1.9	0.0007	0.0023	
NY	218	0.1592 ±	0.0097	15.7 ± 1.0	0.0023	0.0015	
DC	275	0.2389 ±	0.0075	18.7 ± 0.6	0.0036	0.0024	
Period 3 1986-1987							
NC	175	0.1279 ±	0.0055	15.7 ± 0.7	-0.0009	-0.0002	
NJ	176	0.1511 ±	0.0104	18.4 ± 1.3	-0.0017	-0.0043	
NY	170	0.0961 ±	0.0096	12.1 ± 0.2	0.0015	0.0015	
DC	217	0.1478 ±	0.0042	14.6 ± 0.4	0.0024	0.0020	
OHS*	376	0.4481 ±	0.0223	25.6 ± 1.3	0.0007	0.0062	
Period 4 1987-1988							
NC	321	0.2093 ±	0.0111	14.0 ± 0.7	0.0026	0.0010	
NY	315	0.1989 ±	0.0027	13.6 ± 0.2	0.0023	0.0010	
DC	366	0.2920 ±	0.0137	17.1 ± 0.8	0.0037	0.0042	
OHSA	380	0.3129 ±	0.0214	17.7 ± 1.2	0.0046	0.0024	
OHMD ^a	410	0.1155	-	6.1 -	-	-	
OHMS ^a	410	0.2474	-	13.0 -	-	-	

^aOHS = Ohio stationary rack; OHMD = Ohio movable rack, dry regime; OHMS = Ohio movable rack, sprayed regime.

The standard deviation was calculated by

$$\sigma = \left[\frac{\sum_{i=1}^N (x_i - \bar{x})^2}{N} \right]^{1/2}$$

Table 3. Incremental weight change and recession of limestone briquettes for period 1984-1988

Site	Exposure Time (days)	Exposed Briquettes				Avg. Loss (g)	
		Avg. Loss (g)	Std. Dev. (g)	Recession, Prorated (μm/yr)	Field Control	Lab. Control	
Period 1 1984-1985							
NC	356	1.5182 ±	0.1239	107.4 ± 8.8	0.0402	0.0453	
NJ	367	1.8050 ±	0.0673	123.9 ± 4.7	0.0315	0.0577	
NY	367	1.6100 ±	0.1054	110.6 ± 7.2	0.0563	0.0878	
DC	366	1.4210 ±	0.1086	97.8 ± 7.5	0.0697	0.0841	
Period 2 1985-1986							
NC	261	0.3252 ±	0.0452	31.4 ± 4.4	0.0555	0.0603	
NJ	275	0.6639 ±	0.0214	60.8 ± 2.0	0.0474	0.0520	
NY	218	0.2333 ±	0.0156	27.0 ± 1.8	0.0218	0.0235	
DC	275	0.3995 ±	0.0109	36.6 ± 1.0	0.0287	0.0322	
Period 3 1986-1987							
NC	175	0.2773 ±	0.0170	39.9 ± 2.5	0.0271	0.0314	
NJ	176	0.2492 ±	0.0096	35.7 ± 1.4	-0.0079	-0.0057	
NY	170	0.1331 ±	0.0041	19.7 ± 0.6	0.0031	0.0056	
DC	217	0.2828 ±	0.0092	32.8 ± 1.1	0.0701	0.0285	
OHS ^a	376	1.5171 ±	0.0606	101.6 ± 4.1	0.0202	0.1318	
Period 4 1987-1988							
NC	321	0.3162 ±	0.0259	24.8 ± 2.0	0.0097	0.0191	
NY	315	0.3047 ±	0.0067	24.4 ± 0.5	0.0261	0.0299	
DC	366	0.7328 ±	0.0131	50.5 ± 0.9	0.0868	0.0971	
OHS ^a	380	0.7424 ±	0.0232	49.2 ± 1.5	0.0674	0.0697	
OHMD ^a	410	0.7526	-	46.2	-	-	
OHMS ^a	410	0.9809	-	60.3	-	-	

^aOHSA = Ohio stationary rack; OHMD = Ohio movable rack, dry regime; OHMS = Ohio movable rack, sprayed regime.

where: x = Gravimetric change of briquette,
 $\bar{x}$ = average gravimetric change,
 N = number of briquettes (generally $N = 3$), and
 σ = standard deviation.

N was chosen as the weighting factor for the standard deviation because it results in a maximum likelihood estimation generally used to describe populations. $(N-1)$ is an unbiased estimator customarily used for sampled data.

The quoted prorated recession for the exposed briquettes was calculated as follows:

$$\text{Prorated recession} = \frac{\text{average gravimetric weight loss}}{(\text{exposure area}) \times (\text{stone density})} \times \frac{365}{(\text{days of exposure})}$$

The exposed area of the skyward surface of each briquette is approximately 63 cm², and the densities used in the calculations were 2.7 g/cm³ for marble and 2.3 g/cm³ for limestone.

Cumulative gravimetric changes over the period 1984-1988 are summarized in Tables 4-6. These average changes and standard deviations were calculated by summing the changes for each briquette over the various time periods, averaging the results for each site, and calculating the standard deviation as described earlier. Gravimetric changes of exposed

Table 4. Cumulative weight changes of marble briquettes for period 1984-1988

Site	Cum. Exposure Time (days)	Exposed Briquettes			Cum. Elapsed Time (days)	Field Controls		
		Avg.	±	Std. Dev.		Avg.	±	Std. Dev.
NC	356	0.2733	±	0.0173	399	-0.0022	±	0.0004
	617	0.4530	±	0.0275	742	0.0030	±	0.0004
	792	0.5808	±	0.0328	1102	0.0021	±	0.0003
	1113	0.7901	±	0.0432	1491	0.0047	±	0.0006
NJ	367	0.4348	±	0.0218	411	0.0000	±	0.0002
	642	0.7831	±	0.0444	775	0.0007	±	0.0009
	818	0.9341	±	0.0548	1115	-0.0010	±	0.0012
NY	367	0.2877	±	0.0088	431	0.0005	±	0.0006
	585	0.4469	±	0.0182	789	0.0028	±	0.0001
	755	0.5430	±	0.0181	1124	0.0043	±	0.0011
	1070	0.7419	±	0.0203	1503	0.0071	±	0.0027
DC	366	0.3111	±	0.0044	441	0.0009	±	0.0003
	641	0.5500	±	0.0117	804	0.0045	±	0.0016
	858	0.6978	±	0.0158	1155	0.0069	±	0.0020
	1224	0.9898	±	0.0295	1574	0.0106	±	0.0019
OHS ^a	376	0.4481	±	0.0223	411	0.0007	±	0.0006
	756	0.7610	±	0.0405	813	0.0052	±	0.0007
OHMD ^a	410	0.1155		-	-	-		-
OHMS ^a	410	0.2474		-	-	-		-

^aOHS = Ohio stationary rack; OHMD = Ohio movable rack, dry regime; OHMS = Ohio movable rack, sprayed regime.

Table 5. Cumulative weight changes of limestone briquettes for period 1984-1988

Site	Cum. Exposure Time (days)	Exposed Briquettes			Cum. Elapsed Time (days)	Field Controls		
		Avg.	±	Std. Dev.		Avg.	±	Std. Dev.
NC	356	1.5182	±	0.1239	399	0.0402	±	0.0074
	617	1.8434	±	0.1578	742	0.0957	±	0.0107
	792	2.1207	±	0.1722	1102	0.1228	±	0.0122
	1113	2.4369	±	0.1977	1491	0.1325	±	0.0130
NJ	367	1.8050	±	0.0673	411	0.0315	±	0.0091
	642	2.4689	±	0.0869	775	0.0789	±	0.0117
	818	2.7182	±	0.0962	1115	0.0633	±	0.0048
NY	367	1.6100	±	0.1054	431	0.0563	±	0.0075
	585	1.8432	±	0.1169	789	0.0781	±	0.0108
	755	1.9764	±	0.1210	1124	0.0883	±	0.0035
	1070	2.2810	±	0.1225	1503	0.1063	±	0.0144
DC	366	1.4210	±	0.1086	441	0.0699	±	0.0024
	641	1.8204	±	0.1194	804	0.0984	±	0.0037
	858	2.1032	±	0.1111	1155	0.1685	±	0.0126
	1224	2.8360	±	0.0934	1574	0.2554	±	0.0128
OHS ^a	376	1.5171	±	0.0606	411	0.0202	±	0.0010
	756	2.2595	±	0.0819	813	0.0876	±	0.0037
OHMD ^a	410	0.7526		-	-	-		-
OHMS ^a	410	0.9809		-	-	-		-

^aOHS = Ohio stationary rack; OHMD = Ohio movable rack, dry regime; OHMS = Ohio movable rack, sprayed regime.

Table 6. Cumulative weight changes of laboratory control briquettes for period 1984-1988

Cumulative Elapsed Time (days)	Avg. ± Std. Dev.					
	Marble			Limestone		
399	-0.0013	±	0.0005	0.0453	±	0.0067
411	0.0018	±	0.0008	0.0577	±	0.0076
431	0.0029	±	0.0007	0.0878	±	0.0068
441	0.0016	±	0.0007	0.0841	±	0.0065
742	0.0031	±	0.0006	0.1056	±	0.0069
775	0.0040	±	0.0007	0.1098	±	0.0067
789	0.0044	±	0.0009	0.1113	±	0.0075
804	0.0040	±	0.0010	0.1163	±	0.0073
1102	0.0029	±	0.0011	0.1370	±	0.0037
1115	0.0031	±	0.0010	0.1040	±	0.0084
1124	0.0059	±	0.0010	0.1170	±	0.0084
1155	0.0060	±	0.0010	0.1448	±	0.0077
1164	0.0058	±	0.0009	0.1351	±	0.0082
1491	0.0040	±	0.0026	0.1560	±	0.0077
1503	0.0070	±	0.0009	0.1468	±	0.0083
1566	0.0082	±	0.0012	0.2048	±	0.0086
1574	0.0102	±	0.0017	0.2419	±	0.0091

briquettes are tabulated respective to cumulative exposure time, while changes in field and ANL control briquettes are tabulated by cumulative elapsed time between subsequent gravimetric measurements.

For the Ohio exposure site, the same control briquettes were used along with briquettes from the stationary and movable exposure rack, because the gravimetric measurements were performed simultaneously.

A discussion of the results is presented in Section 4 below. Gravimetric results for individual briquettes are tabulated in Appendix A.

4 DISCUSSION AND CONCLUSIONS

Comments offered in the discussion section of Ref. 2 pertinent to results obtained after Periods 1 and 2 continue to be appropriate to Periods 3 and 4. In summary, they were: (1) limestone weight losses for any given site and period were greater than marble weight losses; (2) weight losses for both stone types were site-dependent; and (3) disproportionately large weight losses of limestone during the Period 1 can be attributed to rinsing by rain of loose particles remaining after initial surface preparation in pores. The additional gravimetry data for Periods 3 and 4 permit an assessment of the effect of long-term exposure on gravimetric behavior.

Figures 1 and 2 show the gravimetric (and surface recession) changes of marble and limestone, respectively, as functions of exposure time for the five exposure sites. The shown regression lines, calculated with the omission of the initial values at 0 years, can be expressed for marble by the following equations:

Site	Equation	Correlation coefficient
NC	$y = .250x + .032$	$r = .999$
NJ	$y = .410x + .034$	$r = .995$
NY	$y = .233x + .061$	$r = .999$
DC	$y = .286x + .032$	$r = .999$
OH	$y = .301x + .138$	$r = 1.000$

and for limestone:

NC	$y = .448x + 1.096$	$r = .996$
NJ	$y = .752x + 1.076$	$r = .992$
NY	$y = .344x + 1.273$	$r = .999$
DC	$y = .598x + .779$	$r = .995$
OH	$y = .713x + .783$	$r = 1.000$

where:

y = cumulative weight loss in g, and
x = exposure period in yr.

Fig. 1. Cumulative weight loss and surface recession of marble briquettes as a function of cumulative exposure time at the five sites

Fig. 2. Cumulative weight loss and surface recession of limestone briquettes as a function of cumulative exposure time at the five sites

The correlation coefficient indicates that the weight loss for both stone types increases linearly with exposure time. The graphs contain a recession scale, calculated from the weight loss using the formula shown earlier. The slopes of the regression lines indicate the average annual weight loss and/or recession at a given site. These values, however, include any weight losses incurred by handling, transportation, and oven drying. Unexposed control briquettes at each site and the ANL laboratory control briquettes incur weight losses caused only by handling, transportation, and oven drying. Cumulative losses of the control briquettes are plotted in Figs. 3 and 4 as a function of cumulative elapsed time between successive weighings. It is apparent from these graphs that a small weight loss occurs, larger for limestone than for marble. Subtraction of the weight loss rates of the control briquettes from those of the exposed briquettes yields weight-loss rates caused by exposure alone, which can be related to recession rates, as shown in Table 7.

Error bars in Figs. 1 and 2 are one standard deviation on the mean of three determinations. With the exception of the Ohio site, based on two points, the marble recession lines in Fig. 1 have intercepts of only a few tenths of a micrometer for zero time of exposure, while the limestone samples in Fig. 2 have intercepts of 60 to 130 μm . The difference is assumed to be due to initial rapid loss of loosely adherent particles on freshly exposed surfaces of the limestone briquettes, i.e., residues from briquette preparation.

Fig. 3. Cumulative weight loss and surface recession of marble control briquettes as a function of cumulative elapsed time

Fig. 4. Cumulative weight loss and surface recession of limestone control briquettes as a function of cumulative elapsed time

Table 7. Average recession rates of exposed briquettes, by exposure site ($\mu\text{m}/\text{yr}$)

Site	Exposed Briquettes	Control Briquettes	Exposure Alone
Marble			
NC	14.7	0.1	14.6
NJ	24.1	0.0	24.1
NY	13.7	0.1	13.6
DC	16.8	0.2	16.6
OH	17.7	0.3	17.4
Limestone			
NC	30.9	2.1	28.8
NJ	51.9	1.2	50.7
NY	23.7	1.1	22.6
DC	41.3	4.2	37.1
OH	49.2	4.7	44.5

A simple data point is available for briquettes exposed in the movable rack at the Ohio site for 1 yr. The dry-regime briquettes exhibit a lower loss than the sprayed regime briquettes, as could be anticipated, but losses still occur. Any determination of a trend in weight loss for these briquettes awaits additional data.

Recession rates obtained by gravimetry can be compared with recession rates measured by interferometry⁶ and in runoff experiments,⁷ as shown in Table 8 and Fig. 5. The gravimetry and interferometry recession measurements exceed the runoff measurements in all cases. The interferometry results are systematically higher than the gravimetry results for marble, and lower for limestone, with the exception of those for the NY site. Recession rates vary appreciably from site to site because of different environmental conditions. The gravimetry and interferometry recession rates for marble are approximately double the runoff recession rates, while for limestone the difference equals a factor of 3 or more. The apparent higher erosion rates for limestone versus marble indicates the importance of physical erosion, and this is consistent with the lower density, greater porosity, and more likely grain loss in limestone.⁵

Table 8. Comparison of estimated annual recession rates ($\mu\text{m}/\text{yr}$)

Site	Gravimetry	Interferometry	Runoff
Marble			
NC	14.6	21.1	7.3
NJ	24.1	27.0	9.3
NY	13.6	33.6	7.9
DC	16.6	24.4	8.3
OH	17.4	-	-
Limestone			
NC	28.8	28.5	5.7
NJ	50.7	38.9	6.9
NY	22.6	33.7	5.7
DC	37.1	24.0	7.2
OH	44.5	-	-

In the calculation of the recession rates from gravimetric measurements, it was assumed that a uniform weight loss occurs on the skyward surface only, and no consideration was given to weight gain, especially in limestone, at the groundward surface due to sulfate formation. The data for the Ohio site are probably biased because only two measurement points are available and the initial (first period) loss is higher than subsequent losses. Cumulative weight losses or recession can also be plotted as function of cumulative rain depths for the five exposure sites, as shown in Figs. 6 and 7. The data for the rain depths were extrapolated from environmental EPA data gathered at the exposure sites. The calculated regression lines show a linear relationship with a correlation coefficient of .993 or higher for both stone types. The slope of the regression lines yield the weight loss (recession) as function of rain depth, as shown in Table 9.

Fig. 5. Comparison of stone recession rates at the five field exposure sites

Fig. 6. Cumulative weight loss and surface recession of marble briquettes as a function of cumulative rain depth at the five exposure sites

Fig. 7. Cumulative weight loss and surface recession of limestone briquettes as a function of cumulative rain depth at the five exposure sites

Table 9. Weight loss and recession as a function of rain depth

Site	Weight Loss (g/m of rain)		Recession ($\mu\text{m}/\text{m}$ of rain)	
	Marble	Limestone	Marble	Limestone
NC	0.2624	0.4739	15.4	32.7
NJ	0.3441	0.6331	20.2	43.7
NY	0.2680	0.3949	15.8	27.3
DC	0.4456	0.9403	26.2	64.9
OH	0.4859	1.1527	28.6	79.6

Rain depth is plotted as function of exposure time in Fig. 8 to establish the annual rain depth for each of the five exposure sites. The regression lines show a linear relationship with a correlation coefficient of .995 or higher.

The rain depth data were extrapolated from EPA environmental measurements at each exposure site. The slope of the regression lines is a measure of the average annual rainfall at each site. H^+ ion concentration was also extrapolated and averaged from EPA environmental data for the exposure period at each site and is plotted in Fig. 9 versus calculated recession per meter of rain depth for the two stone types. Each point represents one exposure site with a different H^+ ion concentration. The regression lines show a linear relationship between the H^+ ion concentration and recession per meter of rain depth. The larger recession for the more

Fig. 8. Cumulative rain depth as a function of cumulative exposure time for the five exposure sites

Fig. 9. Recession per rain depth as a function of H^+ ion concentration

Table 10. Average recession and environmental data for the five exposure sites

Site	Marble Prorated Recession ^a		Limestone Prorated Recession ^a		Rain depth per yr (m/yr)	H ⁺ ion Concentration (ppb) ($\mu\text{g/L}$)
	Per yr ($\mu\text{m/yr}$)	Per m Rain ($\mu\text{m/m}$)	Per yr ($\mu\text{m/yr}$)	Per m Rain ($\mu\text{m/m}$)		
NC	14.6	15.3	28.8	30.6	0.945	42.50
NJ	24.1	20.2	50.7	42.5	1.193	68.67
NY	13.6	15.7	22.6	26.2	0.869	52.34
DC	16.6	26.0	37.1	60.7	0.635	90.90
OH	17.4	28.3	44.5	74.9	0.617	107.50

^aCorrected for losses due to handling.

porous limestone over that of marble is evident. The correlation coefficient for the regression lines is .978 for limestone and .991 for marble. The slopes of the regression lines in Figs. 1-9, together with the averaged EPA atmospheric data, are summarized in Table 10 for the five NAPAP exposure sites.

Multiplication of annual rain depth by recession per meter of rain yields the prorated recession per year. The relative recession rates correlate with average pollutant concentrations at the exposure sites and annual rainfall. It was assumed in the evaluation of cumulative weight losses/recessions that the losses during each exposure period are additive; this assumption is to be verified when the five-year exposure briquettes are analyzed. No attention was paid to the severity of rainfall during each occurrence (meter of rain/hour), wind velocity and direction, or average temperatures at the exposure sites. For a more complete picture, these environmental variables should be taken into account.

In 1986, mercury porosimetry of samples from marble layers G and K and limestone layers G and H were performed for ANL by Micrometrics Materials Analysis Laboratory in Norcross, GA. The results show a porosity of 1.4% (layer G) and 0.87% (layer K) in marble and a porosity of 17% in limestone in both layers G and H. The marble layers are further apart from each other, and layer G exhibits a larger average pore diameter than does layer K. It appears that layer K, positioned deeper in the slab, was more compacted during formation and has smaller pores and thus less porosity. The measured porosity in limestone is from adjacent layers, and the average pore diameters are equal, yielding the same porosity. Complete data on the mercury porosity measurements are contained in Appendix B.

Nuclear magnetic resonance (NMR) was evaluated for ANL by General Electric Medical Systems Division in New Berlin, WI, during 1983 to determine moisture content of the briquettes. The results indicate that medical NMR equipment cannot resolve moisture contents in briquettes at the needed level of 10 ppm. A more detailed description of this evaluation is contained in Appendix C.

A feasibility study was conducted by the Sonoscan Company in Bensenville, IL, for ANL to utilize optical measurements of acoustical surface waves for determining surface changes on exposed briquettes. The encountered difficulties would, however, require additional effort to establish the effects of surface roughness on acoustical parameters. The report by Sonoscan is incorporated as Appendix D.

ACKNOWLEDGMENTS

It is a pleasure to acknowledge the valuable assistance and cooperation of many people in this investigation. In particular, the author would like to mention Susan I. Sherwood, NPS Project Officer, for her encouragement, support, and advice; field site operators Curtis Moore (NC), Paul Fiechter (NJ), Ray Masters (NY), the NPS personnel (DC), and B. Weber (OH) for their assistance in briquette installation, exchange, and removal; and C. A. Youngdahl for initiating and guiding this program from 1984 through 1987.

REFERENCES

1. National Acid Precipitation Assessment Program Annual Report 1986 to the President and Congress, Washington, DC (1987).
2. C. A. Youngdahl, *Weight Losses of Marble and Limestone Briquettes Exposed to Outdoor Environments in the Eastern United States*, Argonne National Laboratory Report ANL - 87-56 (1988).
3. M. Ross and L. Knab, *Selection, Procurement, and Description of Salem Limestone Sample Used to Study Effects of Acid Rain*: National Bureau of Standards Report NBSIR 84-2905, pp. 1-17 (1984).
4. M. Ross, *Description, Selection, and Procurement of Shelburne Marble Samples Used to Study Effects of Acid Rain*: U.S. Geological Survey Open-File Report 85-594, (1985).
5. M. Ross, E. S. McGee, D. R. Ross, *Chemical and Mineralogical Effects of Acid Deposition on Shelburne Marble and Salem Limestone Test Samples Placed at Four NAPAP Weather-Monitoring Sites*, *American Mineralogist*, Vol. 74, pp. 177-193 (1989).
6. Sciammarella, C. A., Private communication, Illinois Institute of Technology, Chicago (1989).
7. M. M. Reddy, Private communication, U.S. Geological Survey, Water Resources Div., Denver, Colorado (1989).

APPENDIX A:

Weight Losses from Individual Briquettes

Table A.1. Weight changes observed in exposed briquettes and control briquettes

Site	Expos. Time, Days	Slot	Exposed Briquettes		Field Controls		Lab Controls	
			Sample No.	Weight Change	Sample No.	Weight Change	Sample No.	Weight Change
Marble: Period 1								
NC	356	263	H14-17	0.2915	G36-05	-0.0016	H14-18	-0.0019
		207	G36-19	0.2500	H36-21	-0.0026	G36-23	-0.0006
		265	G26-02	0.2785	I14-01	-0.0025	G26-10	-0.0014
NJ	367	263	H14-24	0.4520	I14-02	-0.0002	H14-18	0.0006
		207	G36-10	0.4040	K36-18	0.0000	G36-23	0.0026
		265	G26-12	0.4483	G36-06	-0.0002	G26-10	0.0021
NY	367	263	H14-15	0.2908	I14-03	0.0012	H14-18	0.0021
		207	G36-17	0.2757	K36-20	-0.0002	G36-23	0.0039
		265	G26-22	0.2965	G36-07	0.0004	G26-10	0.0027
DC	366	263	H14-10	0.3172	H36-22	0.0013	H14-18	0.0008
		207	G36-22	0.3091	K36-22	0.0009	G36-23	0.0025
		265	G26-11	0.3070	G36-08	0.0005	G26-10	0.0016
Limestone: Period 1								
NC	356	163	HU5-05	1.5674	HU6-01	0.0323	HU1-15	0.0441
		107	IL4-22	1.3480	GU1-06	0.0501	HU1-20	0.0378
		165	GL7-09	1.6392	HU4-24	0.0383	GL7-03	0.0540
NJ	367	163	HU5-13	1.8482	GU1-07	0.0436	HU1-15	0.0577
		107	IL4-07	1.7099	HU6-04	0.0294	HU1-20	0.0484
		165	GL7-01	1.8569	HU5-04	0.0215	GL7-03	0.0671
NY	367	163	HU5-22	1.5769	GU1-12	0.0651	HU1-15	0.0890
		107	IL4-03	1.5006	HU6-24	0.0463	HU1-20	0.0789
		165	GL7-18	1.7524	HU5-18	0.0571	GL7-03	0.0955
DC	366	163	HU5-10	1.4169	GL7-04	0.0663	HU1-15	0.0853
		107	IL4-19	1.2900	GL7-11	0.0703	HU1-20	0.0757
		165	GL7-15	1.5560	IU4-15	0.0726	GL7-03	0.0914

Table A.1. (Contd.)

Site	Expos. Time, Days	Slot	Exposed Briquettes		Field Controls		Lab Controls	
			Sample No.	Weight Change	Sample No.	Weight Change	Sample No.	Weight Change
Marble: Period 2								
NC	261	263	H14-17	0.1889	G36-05	0.0049	H14-18	0.0042
		207	G36-19	0.1654	H36-21	0.0060	G36-23	0.0044
		265	G26-02	0.1846	I14-01	0.0049	G26-10	0.0047
NJ	275	263	H14-24	0.3779	I14-02	0.0017	H14-18	0.0027
		207	G36-10	0.3194	K36-18	0.0005	G36-23	0.0023
		265	G26-12	0.3476	G36-06	-0.0001	G26-10	0.0018
NY	218	263	H14-15	0.1668	I14-03	0.0017	H14-18	0.0012
		207	G36-17	0.1455	K36-20	0.0030	G36-23	0.0017
		265	G26-22	0.1653	G36-07	0.0022	G26-10	0.0017
DC	275	263	H14-10	0.2493	H36-22	0.0054	H14-18	0.0020
		207	G36-22	0.2319	K36-22	0.0030	G36-23	0.0027
		265	G26-11	0.2355	G36-08	0.0025	G26-10	0.0024
Limestone: Period 2								
NC	261	163	HU5-05	0.3828	HU6-01	0.0546	HU1-15	0.0647
		107	IL4-22	0.2723	GU1-06	0.0606	HU1-20	0.0582
		165	GL7-09	0.3204	HU4-24	0.0512	GL7-03	0.0580
NJ	275	163	HU5-13	0.6636	GU1-07	0.0508	HU1-15	0.0554
		107	IL4-07	0.6379	HU6-04	0.0469	HU1-20	0.0520
		165	GL7-01	0.6903	HU5-04	0.0445	GL7-03	0.0487
NY	218	163	HU5-22	0.2452	GU1-12	0.0250	HU1-15	0.0257
		107	IL4-03	0.2112	HU6-24	0.0171	HU1-20	0.0221
		165	GL7-18	0.2434	HU5-18	0.0232	GL7-03	0.0228
DC	275	163	HU5-10	0.4014	GL7-04	0.0273	HU1-15	0.0349
		107	IL4-19	0.3853	GL7-11	0.0287	HU1-20	0.0343
		165	GL7-15	0.4117	IU4-15	0.0300	GL7-03	0.0313

Table A.1. (Contd.)

Site	Expos. Time, Days	Slot	Exposed Briquettes		Field Controls		Lab Controls	
			Sample No.	Weight Change	Sample No.	Weight Change	Sample No.	Weight Change
Marble: Period 3								
NC	175	263	H14-17	0.1315	G36-05	-0.0011	H14-18	-0.0007
		207	G36-19	0.1201	H36-21	-0.0010	G36-23	0.0005
		265	G26-02	0.1320	I14-01	-0.0007	G26-10	-0.0004
NJ	176	263	H14-24	0.1632	I14-02	-0.0013	H14-18	-0.0014
		207	G36-10	0.1377	K36-18	-0.0020	G36-23	-0.0105
		265	G26-12	0.1523	G36-06	-0.0018	G26-10	-0.0009
NY	170	263	H14-15	0.0940	I14-03	0.0029	H14-18	0.0013
		207	G36-17	0.0966	K36-20	0.0011	G36-23	0.0015
		265	G26-22	0.0977	G36-07	0.0006	G26-10	0.0017
OH**	376	263	G34-21	0.4255	K15-13	0.0000	H14-18	0.0058
		207	K13-08	0.4785	G22-03	0.0006	G36-23	0.0069
		265	G22-17	0.4404	G34-12	0.0014	G26-10	0.0058
DC	217	263	H14-10	0.1536	H36-22	0.0030	H14-18	0.0019
		207	G36-22	0.1438	K36-22	0.0022	G36-23	0.0019
		265	G26-11	0.1460	G36-08	0.0020	G26-10	0.0022
Limestone: Period 3								
NC	175	163	HU5-05	0.2986	HU6-01	0.0260	HU1-15	0.0338
		107	IL4-22	0.2570	GU1-06	0.0292	HU1-20	0.0305
		165	GL7-09	0.2763	HU4-24	0.0260	GL7-03	0.0298
NJ	176	163	HU5-13	0.2574	GU1-07	0.0549*	HU1-15	-0.0042
		107	IL4-07	0.2357	HU6-04	-0.0080	HU1-20	-0.0082
		165	GL7-01	0.2546	HU5-04	-0.0078	GL7-03	-0.0048
NY	170	163	HU5-22	0.1327	GU1-12	0.0017	HU1-15	0.0072
		107	IL4-03	0.1284	HU6-24	0.0338*	HU1-20	0.0042
		165	GL7-18	0.1383	HU5-18	0.0045	GL7-03	0.0055
OH**	376	163	IL8-22	1.4377	HL2-05	0.0199	HU1-15	0.0306
		107	HL2-12	1.5287	IL8-02	0.0191	J11-20	0.0278
		165	GL6-15	1.5848	GL6-09	0.0215	GL7-03	0.0271
DC	217	163	HU5-10	0.2774	GL7-04	0.0798	HU1-15	0.1411
		107	IL4-19	0.2957	GL7-11	0.0819	HU1-20	0.1136
		165	GL7-15	0.2752	IU4-15	0.0487	GL7-03	0.1407

*Chipped stone.

**First year of exposure at OH site.

Table A.1. (Contd.)

Site	Expos. Time, Days	Slot	Exposed Briquettes		Field Controls		Lab Controls	
			Sample No.	Weight Change	Sample No.	Weight Change	Sample No.	Weight Change
Marble: Period 4								
NC	321	263	H14-17	0.2235	G36-05	0.0033	H14-18	-0.0013
		207	G36-19	0.1964	H36-21	0.0021	G36-23	0.0018
		265	G26-02	0.2080	I14-01	0.0023	G26-10	0.0026
NY	315	263	H14-15	0.1978	I14-03	-0.0014	H14-18	0.0013
		207	G36-17	0.1963	K36-20	0.0059	G36-23	0.0010
		265	G26-22	0.2027	G36-07	0.7635*	G26-10	0.0008
DC	366	263	H14-10	0.3113	H36-22	0.0035	H14-18	0.0037
		207	G36-22	0.2810	K36-22	0.0039	G36-23	0.0054
		265	G26-11	0.2837	G36-08	0.0036	G26-10	0.0036
OH	380	263	G34-21	0.2827	K15-13	0.0042	H14-18	0.0021
		207	K13-08	0.3282	G22-03	0.0053	G36-23	0.0028
		265	G22-17	0.3278	G34-12	0.0042	G26-10	0.0024
OHMD**410		353	G24-19	0.1155				
OHMS**410		335	K14-14	0.2474				
Limestone: Period 4								
NC	321	163	HU5-05	0.3407	HU6-01	0.0079	HU1-15	0.0196
		107	IL4-22	0.2804	GU1-06	0.0107	HU1-20	0.0187
		165	GL7-09	0.3276	HU4-24	0.0105	GL7-03	0.0189
NY	315	163	HU5-22	0.2952	GU1-12	0.0292	HU1-15	0.0316
		107	IL4-03	0.3088	HU6-24	0.0228	HU1-20	0.0300
		165	GL7-18	0.3100	HU5-18	0.0263	GL7-03	0.0280
DC	366	163	HU5-10	0.7257	GL7-04	0.0885	HU1-15	0.1018
		107	IL4-19	0.7512	GL7-11	0.0858	HU1-20	0.0964
		165	GL7-15	0.7215	IU4-15	0.0862	GL7-03	0.0931
OH	380	163	IL8-22	0.7211	HL2-05	0.0704	HU1-15	0.0727
		107	HL2-12	0.7315	IL8-02	0.0632	HU1-20	0.0697
		165	GL6-15	0.7747	GL6-09	0.0687	GL7-03	0.0666
OHMD** 410		338	IL8-06	0.7526				
OHMS** 410		320	HL2-19	0.9526				

*Chipped stone.

**OHMD - Ohio site movable rack - dry regime.

**OHMD - Ohio site movable rack - sprayed regime.

Table A.2. Drying and weighing conditions for briquettes after exposure periods

BRIQUETTE GROUP (w/lab controls)	PERIOD IN OVEN		OVEN TEMP °C	WEIGHING CONDITIONS °C/R.H./BAR.P.
	BEGIN	END		
NC	6 10 85 & 6 15 85	6 13 85 7 24 85	45	22.7/34% *
NJ	7 24 85	8 01 85	45	21.8/40%
NY w/o lab controls	8 04 85		45	
Lab controls added	8 05 85	8 13 85	45	22.4/29% *
DC	8 25 85	9 01 85	45	22.2/32% *
NC	6 20 86	6 30 86	45	22.6/30%/29.31"
OH w/o lab controls	7 7 86	7 13 86	45	22.5/31%/29.34"
NJ	7 28 86	8 4 86	45	22.6/30%/29.27"
NY	8 6 86	8 13 86	45	22.5/30%/29.37"
DC	8 22 86	8 31 86	(45)	22.7/29%/29.30"
NC	6 19 87	6 27 87	45	22.6/26%/29.11"
NJ	7 2 87	7 10 87	45	22.7/44%/29.16"
NY	7 12 87	7 19 87	45	22.4/44%/29.42"
OH	8 12 87	8 19 87	45	22.4/32%/29.35"
DC	8 21 87	(8 28 87)	46	22.4/29%/29.38"
NC	7 13 88	7 20 88	51	22.2/28%/29.90"
NY	7 22 88	8 1 88	50	21.9/35%/29.35"
OH(inc. OHMS and OHMS)	9 26 88	10 3 88	51	21.8/16%/29.51"
DC	10 4 88	10 11 88	50	21.6/8%/29.59"

*Barometric data not available.

APPENDIX B:

Mercury Porosity Measurements*

*Obtained by Micrometrics Materials Analysis Laboratory (Norcross, GA) for ANL in 1986.

Table B.1. Mercury porosity data for marble layer G

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 1

SAMPLE NUMBER: 11 OPERATOR: PC
 SAMPLE ID: 9-2365-1-517
 SUBMITTER: ARGONNE LABS

LP 13:04:13 08/27/86
 HP 14:05:45 08/27/86
 REP 18:28:09 08/28/86

PENETROMETER NUMBER: 49	ADVANCING CONTACT ANGLE: 130.0 deg
PENETROMETER CONSTANT: 10.79 $\mu\text{L}/\text{pF}$	RECEDING CONTACT ANGLE: 130.0 deg
PENETROMETER WEIGHT: 68.3007 g	MERCURY SURFACE TENSION: 485.0 dyn/cm
STEM VOLUME: 0.4120 mL	MERCURY DENSITY: 13.5335 g/mL
MAXIMUM HEAD PRESSURE: 4.5800 psia	SAMPLE WEIGHT: 2.9621 g
PENETROMETER VOLUME: 3.5644 mL	SAMPLE+PEN+Hg WEIGHT: 104.5580 g

LOW PRESSURE:

EVACUATION PRESSURE: 50 μmHg
 EVACUATION TIME: 5 min
 MERCURY FILLING PRESSURE: 1.5279 psia
 EQUILIBRATION TIME: 10 sec

HIGH PRESSURE:

EQUILIBRATION TIME: 10 sec

INTRUSION DATA SUMMARY

TOTAL INTRUSION VOLUME =	0.0052 mL/g
TOTAL PORE AREA =	1.593 $\text{sq-m}/\text{g}$
MEDIAN PORE DIAMETER (VOLUME) =	0.0161 μm
MEDIAN PORE DIAMETER (AREA) =	0.0049 μm
AVERAGE PORE DIAMETER (4V/A) =	0.0111 μm
BULK DENSITY =	2.6826 g/mL
APPARENT (SKELETAL) DENSITY =	2.7209 g/mL
STEM VOLUME USED =	4 % ****

Table B.1. (contd.)

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 5220 V1.04

PAGE 2

SAMPLE NUMBER: 11 OPERATOR: PC
 SAMPLE ID: 9---2365-1-517
 SUBMITTER: ARGONNE LAES

LP 13:04:13 08/27/88
 HP 14:05:45 08/27/88
 REP 18:28:09 08/28/88

PRESSURE psia	PORE DIAMETER μ m	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
1.53	118.3772	0.0000	0.0000	0.000	0.000
2.02	89.4886	0.0005	0.0005	0.000	0.000
3.01	60.1271	0.0004	0.0009	0.000	0.000
4.01	45.1390	0.0005	0.0013	0.000	0.000
5.48	32.9750	0.0002	0.0015	0.000	0.000
6.97	25.9453	0.0004	0.0019	0.000	0.000
8.47	21.3537	0.0001	0.0020	0.000	0.000
10.46	17.2902	0.0000	0.0020	0.000	0.000
12.94	13.9743	0.0000	0.0020	0.000	0.000
15.91	11.3645	0.0000	0.0020	0.000	0.000
19.90	9.0876	0.0000	0.0020	0.000	0.000
22.97	7.8730	0.0001	0.0021	0.000	0.000
24.96	7.2373	0.0001	0.0022	0.000	0.000
29.97	6.0352	0.0000	0.0022	0.000	0.000
40.28	4.4899	0.0000	0.0022	0.000	0.000
49.79	3.6323	0.0000	0.0022	0.000	0.000
59.91	3.0127	0.0000	0.0022	0.000	0.000
74.68	2.4218	0.0000	0.0022	0.000	0.000
89.63	2.0173	0.0000	0.0022	0.000	0.000
114.77	1.5759	0.0000	0.0022	0.000	0.000
139.75	1.2942	0.0000	0.0022	0.000	0.000
174.76	1.0349	0.0000	0.0022	0.000	0.000
219.66	0.8234	0.0000	0.0022	0.000	0.000
270.31	0.6691	0.0000	0.0022	0.000	0.000
329.64	0.5487	0.0000	0.0022	0.000	0.000
418.78	0.4319	0.0000	0.0022	0.000	0.000
517.76	0.3492	0.0000	0.0022	0.000	0.000
637.61	0.2927	0.0000	0.0022	0.000	0.000
795.86	0.2273	0.0000	0.0022	0.000	0.000
985.43	0.1835	0.0000	0.0022	0.000	0.000
1205.52	0.1500	0.0000	0.0022	0.000	0.000
1402.17	0.1290	0.0000	0.0022	0.000	0.000
1606.52	0.1126	0.0000	0.0022	0.000	0.000
1834.91	0.0954	0.0000	0.0022	0.000	0.000
2012.14	0.0782	0.0000	0.0022	0.000	0.000
2241.42	0.0635	0.0000	0.0022	0.000	0.000
2530.56	0.0517	0.0000	0.0022	0.000	0.000
2829.37	0.0417	0.0000	0.0022	0.000	0.000
3225.40	0.0343	0.0000	0.0022	0.000	0.000
3630.52	0.0291	0.0000	0.0022	0.000	0.000
4039.19	0.0259	0.0000	0.0022	0.000	0.000
4435.44	0.0230	0.0000	0.0022	0.000	0.000
4829.05	0.0213	0.0002	0.0025	0.003	0.003
5167.31	0.0081	0.0000	0.0025	0.000	0.003
5485.59	0.0131	0.0001	0.0025	0.007	0.010

Table B.1 (contd.)

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 3

SAMPLE NUMBER: 11 OPERATOR: PC
 SAMPLE ID: 9---2365-1-517
 SUBMITTER: ARGONNE LABS

LP 13:04:13 08/27/86
 HP 14:05:45 08/27/86
 REP 18:28:03 08/28/86

PRESSURE psia	PORE DIAMETER μ m	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
10077.52	0.0166	0.0001	0.0027	0.015	0.071
12551.34	0.0144	0.0001	0.0028	0.023	0.094
14422.95	0.0125	0.0003	0.0030	0.079	0.173
16636.53	0.0109	0.0002	0.0033	0.084	0.257
19121.60	0.0095	0.0000	0.0033	0.000	0.257
22094.40	0.0082	0.0000	0.0033	0.020	0.277
25094.20	0.0072	0.0003	0.0036	0.162	0.439
29261.89	0.0061	0.0000	0.0035	0.000	0.439
34505.25	0.0052	0.0005	0.0041	0.332	0.771
39871.49	0.0045	0.0005	0.0046	0.403	1.174
44793.41	0.0040	0.0001	0.0047	0.062	1.236
49784.72	0.0036	0.0003	0.0050	0.348	1.584
54766.41	0.0032	0.0000	0.0050	0.000	1.584
59701.81	0.0030	0.0002	0.0052	0.309	1.893

Table B.2 Mercury porosity data for marble layer K

MICROMERITICS INSTRUMENT CORPORATION

AUTOPURE II 9220 V1.04

PAGE 1

SAMPLE NUMBER: 12 OPERATOR: PC
 SAMPLE ID: (10)---2366-2-517
 SUBMITTER: ARGONNE LABS

LP 13:04:13 08/27/86
 HP 14:05:45 08/27/86
 REP 18:54:44 08/28/86

PENETROMETER NUMBER: 34	ADVANCING CONTACT ANGLE: 130.0 deg
PENETROMETER CONSTANT: 10.79 $\mu\text{L}/\text{pF}$	RECEDING CONTACT ANGLE: 130.0 deg
PENETROMETER WEIGHT: 67.5144 g	MERCURY SURFACE TENSION: 485.0 dyn/cm
STEM VOLUME: 0.4120 mL	MERCURY DENSITY: 13.5335 g/mL
MAXIMUM HEAD PRESSURE: 4.6800 psia	SAMPLE WEIGHT: 2.5794 g
PENETROMETER VOLUME: 3.5813 mL	SAMPLE+PEN+Hg WEIGHT: 105.1980 g

LOW PRESSURE:

EVACUATION PRESSURE: 50 μmHg
 EVACUATION TIME: 5 min
 MERCURY FILLING PRESSURE: 1.5279 psia
 EQUILIBRATION TIME: 10 sec

HIGH PRESSURE:

EQUILIBRATION TIME: 10 sec

INTRUSION DATA SUMMARY

TOTAL INTRUSION VOLUME =	0.0032 mL/g
TOTAL PORE AREA =	0.950 $\text{sq-m}/\text{g}$
MEDIAN PORE DIAMETER (VOLUME) =	0.1042 μm
MEDIAN PORE DIAMETER (AREA) =	0.0047 μm
AVERAGE PORE DIAMETER (4V/A) =	0.0133 μm
BULK DENSITY =	2.6934 g/mL
APPARENT (SKELETAL) DENSITY =	2.7168 g/mL
STEM VOLUME USED =	2 % ****

Table B.2. (contd.)

MICROMERITICS INSTRUMENT CORPORATION.

AUTOPORE II 9220 V1.04

PAGE 2

SAMPLE NUMBER: 12 OPERATOR: PC
 SAMPLE ID: 10--2366-2-517
 SUBMITTER: ARSONNE LABS

LP 13:04:13 08/27/86
 HP 14:05:45 08/27/86
 REP 18:54:44 08/28/86

PRESSURE psia	PORE DIAMETER µm	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
1.53	118.3772	0.0000	0.0000	0.000	0.000
2.02	89.4386	0.0004	0.0004	0.000	0.000
3.01	60.1371	0.0003	0.0008	0.000	0.000
4.01	45.1390	0.0001	0.0009	0.000	0.000
5.48	32.9750	0.0003	0.0012	0.000	0.000
6.97	25.9453	0.0000	0.0012	0.000	0.000
8.47	21.3537	0.0000	0.0012	0.000	0.000
10.46	17.2902	0.0000	0.0012	0.000	0.000
12.54	13.5743	0.0000	0.0012	0.000	0.000
15.91	11.3645	0.0000	0.0013	0.000	0.000
19.90	9.0876	0.0000	0.0013	0.000	0.000
22.97	7.3730	0.0001	0.0015	0.000	0.000
24.99	7.2373	0.0000	0.0015	0.000	0.000
29.96	6.0359	0.0000	0.0015	0.000	0.000
40.28	4.4901	0.0000	0.0015	0.000	0.000
49.78	3.6336	0.0000	0.0015	0.000	0.000
59.91	3.0187	0.0000	0.0015	0.000	0.000
74.79	2.4213	0.0000	0.0015	0.000	0.000
89.63	2.0178	0.0000	0.0015	0.000	0.000
114.74	1.5783	0.0000	0.0015	0.000	0.000
139.75	1.2342	0.0000	0.0015	0.000	0.000
174.76	1.0349	0.0000	0.0015	0.000	0.000
219.66	0.8234	0.0000	0.0015	0.000	0.000
270.34	0.6690	0.0000	0.0015	0.000	0.000
329.66	0.5485	0.0000	0.0015	0.000	0.000
418.77	0.4315	0.0000	0.0015	0.000	0.000
517.78	0.3493	0.0000	0.0015	0.000	0.000
637.61	0.2837	0.0000	0.0015	0.000	0.000
788.85	0.2273	0.0000	0.0015	0.000	0.000
988.27	0.1836	0.0000	0.0015	0.000	0.000
1208.52	0.1500	0.0000	0.0015	0.000	0.000
1402.34	0.1290	0.0000	0.0015	0.000	0.000
1606.37	0.1129	0.0000	0.0015	0.000	0.000
1855.07	0.0954	0.0000	0.0015	0.000	0.000
2312.14	0.0782	0.0002	0.0018	0.002	0.002
2841.33	0.0605	0.0000	0.0018	0.000	0.002
3030.81	0.0597	0.0000	0.0018	0.000	0.002
3485.48	0.0517	0.0000	0.0018	0.000	0.002
4083.55	0.0449	0.0000	0.0018	0.002	0.010
4631.11	0.0391	0.0000	0.0018	0.000	0.010
5079.13	0.0336	0.0001	0.0017	0.003	0.018
5187.37	0.0292	0.0000	0.0017	0.000	0.018
7079.90	0.0255	0.0000	0.0017	0.000	0.018
8171.15	0.0221	0.0001	0.0018	0.012	0.031
9462.13	0.0191	0.0000	0.0018	0.000	0.031

Table B.2. (contd.)

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 3

SAMPLE NUMBER: 12 OPERATOR: PC
 SAMPLE ID: 10---2356-2-517
 SUBMITTER: ARGONNE LABS

LP 13:04:13 08/27/85
 HP 14:05:45 08/27/85
 REP 18:54:44 08/28/85

PRESSURE	PORE	INCREMENTAL	CUMULATIVE	INCREMENTAL	CUMULATIVE
psia	DIAMETER	VOLUME	VOLUME	PORE AREA	PORE AREA
	μm	mL/g	mL/g	sq-m/g	sq-m/g
10881.78	0.0166	0.0000	0.0018	0.000	0.031
12555.19	0.0144	0.0002	0.0020	0.044	0.075
14436.81	0.0125	0.0001	0.0021	0.037	0.112
16538.46	0.0109	0.0000	0.0021	0.017	0.128
19117.74	0.0095	0.0002	0.0023	0.077	0.206
22098.26	0.0082	0.0000	0.0023	0.000	0.206
25092.27	0.0072	0.0001	0.0024	0.051	0.257
29862.81	0.0061	0.0001	0.0026	0.074	0.331
34605.25	0.0052	0.0001	0.0026	0.053	0.383
39869.56	0.0045	0.0001	0.0028	0.121	0.505
44757.26	0.0040	0.0001	0.0029	0.115	0.620
49788.58	0.0036	0.0001	0.0030	0.154	0.773
54764.48	0.0033	0.0000	0.0030	0.000	0.773
59703.74	0.0030	0.0001	0.0032	0.186	0.960

Table B.3. Mercury porosity data for limestone layer G

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 1

SAMPLE NUMBER: 10 OPERATOR: PC
 SAMPLE ID: 8---2354-4-517
 SUBMITTER: ARCONNE LABS

LP 11:42:15 08/27/86
 HP 13:28:09 08/27/86
 REP 18:15:00 08/26/86

PENETROMETER NUMBER: 15	ADVANCING CONTACT ANGLE: 130.0 deg
PENETROMETER CONSTANT: 10.79 $\mu\text{L/pF}$	RECEDING CONTACT ANGLE: 130.0 deg
PENETROMETER WEIGHT: 68.4228 g	MERCURY SURFACE TENSION: 485.0 dyn/cm
STEM VOLUME: 0.4120 mL	MERCURY DENSITY: 13.5335 g/mL
MAXIMUM HEAD PRESSURE: 4.5800 psia	SAMPLE WEIGHT: 2.3391 g
PENETROMETER VOLUME: 3.6320 mL	SAMPLE+PEN+Hg WEIGHT: 105.6150 g

LOW PRESSURE:

EVACUATION PRESSURE: 50 μmHg
 EVACUATION TIME: 5 min
 MERCURY FILLING PRESSURE: 1.5423 psia
 EQUILIBRATION TIME: 10 sec

HIGH PRESSURE:

EQUILIBRATION TIME: 10 sec

INTRUSION DATA SUMMARY

TOTAL INTRUSION VOLUME =	0.0749 mL/g
TOTAL PORE AREA =	2.461 sq-m/g
MEDIAN PORE DIAMETER (VOLUME) =	0.6070 μm
MEDIAN PORE DIAMETER (AREA) =	0.0199 μm
AVERAGE PORE DIAMETER (4V/A) =	0.1218 μm
BULK DENSITY =	2.2128 g/mL
APPARENT (SKELETAL) DENSITY =	2.6528 g/mL
STEM VOLUME USED =	43 %

Table B.3. (contd.)

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 2

SAMPLE NUMBER: 10 OPERATOR: PC
 SAMPLe ID: 8---2364-4-517
 SUBMITTER: ARGONNE LABS

LP 11:42:15 08/27/86
 HP 13:28:09 08/27/86
 REP 18:15:00 08/28/86

PRESSURE psia	PORE DIAMETER μ m	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
1.54	117.2674	0.0000	0.0000	0.000	0.000
2.02	89.3468	0.0005	0.0005	0.000	0.000
3.01	60.0409	0.0010	0.0015	0.000	0.000
4.00	45.2479	0.0007	0.0023	0.000	0.000
5.49	32.9557	0.0011	0.0034	0.000	0.000
6.98	25.9055	0.0013	0.0046	0.000	0.000
8.45	21.4024	0.0012	0.0059	0.000	0.001
10.45	17.3115	0.0009	0.0068	0.000	0.001
12.54	13.9777	0.0015	0.0083	0.000	0.001
15.22	11.3632	0.0015	0.0098	0.000	0.002
19.90	9.0958	0.0017	0.0116	0.001	0.002
22.97	7.8725	0.0024	0.0139	0.001	0.003
24.97	7.2420	0.0014	0.0153	0.001	0.004
31.40	5.7501	0.0015	0.0168	0.001	0.005
41.58	4.3503	0.0028	0.0196	0.002	0.007
52.06	3.4728	0.0015	0.0211	0.001	0.009
51.09	2.9605	0.0010	0.0221	0.001	0.010
76.37	2.3882	0.0012	0.0233	0.002	0.012
91.01	1.9873	0.0007	0.0240	0.001	0.013
114.85	1.5748	0.0012	0.0252	0.003	0.016
140.25	1.2896	0.0010	0.0263	0.003	0.019
175.16	1.0326	0.0017	0.0280	0.006	0.025
219.71	0.8232	0.0029	0.0309	0.012	0.037
269.93	0.6699	0.0043	0.0352	0.023	0.060
332.42	0.5441	0.0051	0.0403	0.034	0.094
416.12	0.4326	0.0054	0.0456	0.044	0.138
519.18	0.3484	0.0044	0.0500	0.045	0.183
639.92	0.2826	0.0028	0.0528	0.036	0.218
796.82	0.2270	0.0025	0.0553	0.039	0.258
985.69	0.1833	0.0023	0.0577	0.046	0.303
1202.04	0.1505	0.0021	0.0597	0.049	0.353
1405.23	0.1287	0.0013	0.0612	0.043	0.395
1607.46	0.1123	0.0014	0.0626	0.047	0.442
1800.45	0.0952	0.0016	0.0642	0.062	0.504
2203.02	0.0785	0.0018	0.0660	0.032	0.536
2633.30	0.0687	0.0010	0.0670	0.035	0.571
3033.50	0.0596	0.0011	0.0681	0.059	0.709
3488.68	0.0515	0.0010	0.0691	0.071	0.780
4017.90	0.0450	0.0008	0.0699	0.163	0.943
4640.92	0.0390	0.0008	0.0707	0.061	0.983
5387.74	0.0336	0.0004	0.0711	0.040	0.954
6197.42	0.0292	0.0006	0.0716	0.072	1.036
7021.95	0.0255	0.0005	0.0722	0.066	1.122
8171.81	0.0221	0.0002	0.0725	0.028	1.150
9430.67	0.0191	0.0003	0.0728	0.066	1.225

Table B.3. (contd.)

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 3

SAMPLE NUMBER: 10 OPERATOR: PC
 SAMPLE ID: B---2364-4-517
 SUBMITTER: ARGONNE LABS

LP 11:42:15 05/27/86
 HP 13:28:09 08/27/86
 REP 18:15:00 08/28/86

PRESSURE psia	PORE DIAMETER µm	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
10854.83	0.0167	0.0003	0.0731	0.057	1.232
12564.85	0.0144	0.0003	0.0733	0.073	1.355
14452.26	0.0125	0.0002	0.0735	0.050	1.405
16657.41	0.0109	0.0001	0.0736	0.029	1.434
19121.62	0.0095	0.0001	0.0737	0.035	1.485
22107.92	0.0082	0.0003	0.0740	0.129	1.617
25072.02	0.0072	0.0001	0.0741	0.029	1.646
29858.05	0.0061	0.0001	0.0742	0.068	1.714
34905.27	0.0052	0.0002	0.0744	0.140	1.855
39659.03	0.0045	0.0001	0.0745	0.093	1.948
44832.01	0.0040	0.0000	0.0745	0.000	1.948
49777.05	0.0035	0.0003	0.0747	0.265	2.212
54772.23	0.0032	0.0000	0.0747	0.000	2.212
59696.07	0.0030	0.0002	0.0749	0.249	2.461

Table B.4. Mercury porosity data for limestone layer H

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 1

SAMPLE NUMBER: 9 OPERATOR: PC
 SAMPLE ID: 7---2363-3-517
 SUBMITTER: ARGONNE LABS

LP 11:42:15 08/27/86
 HP 13:28:09 08/27/86
 REP 07:27:11 08/29/86

PENETROMETER NUMBER: 999	ADVANCING CONTACT ANGLE: 130.0 deg
PENETROMETER CONSTANT: 10.79 $\mu\text{L}/\text{pF}$	RECEDING CONTACT ANGLE: 130.0 deg
PENETROMETER WEIGHT: 69.0811 g	MERCURY SURFACE TENSION: 485.0 dyn/cm
STEM VOLUME: 0.4120 mL	MERCURY DENSITY: 13.5335 g/mL
MAXIMUM HEAD PRESSURE: 4.6800 psia	SAMPLE WEIGHT: 2.3578 g
PENETROMETER VOLUME: 3.5150 mL	SAMPLE+PEN+Hg WEIGHT: 104.5580 g

LOW PRESSURE:

EVACUATION PRESSURE: 50 μmHg
 EVACUATION TIME: 5 min
 MERCURY FILLING PRESSURE: 1.5423 psia
 EQUILIBRATION TIME: 10 sec

HIGH PRESSURE:

EQUILIBRATION TIME: 10 sec

INTRUSION DATA SUMMARY

TOTAL INTRUSION VOLUME =	0.0772 mL/g
TOTAL PORE AREA =	3.348 cm^2/g
MEDIAN PORE DIAMETER (VOLUME) =	0.6062 μm
MEDIAN PORE DIAMETER (AREA) =	0.0082 μm
AVERAGE PORE DIAMETER (4V/A) =	0.0923 μm
BULK DENSITY =	2.2081 g/mL
APPARENT (SKELETAL) DENSITY =	2.6620 g/mL
STEM VOLUME USED =	44 %

Table B.4. (contd.)

MICROMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 2

SAMPLE NUMBER: 9 OPERATOR: PC
 SAMPLE ID: 7---2363-3-517
 SUBMITTER: ARGONNE LABS

LP 11:42:15 08/27/86
 HP 13:26:09 08/27/86
 REP 07:27:11 08/29/86

PRESSURE psia	PORE DIAMETER µm	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
1.54	117.2674	0.0000	0.0000	0.000	0.000
2.02	89.3466	0.0004	0.0004	0.000	0.000
3.01	60.0409	0.0007	0.0011	0.000	0.000
4.00	45.2479	0.0007	0.0017	0.000	0.000
5.45	32.9557	0.0013	0.0030	0.000	0.000
6.55	25.9095	0.0014	0.0044	0.000	0.000
8.45	21.4024	0.0015	0.0059	0.000	0.001
10.45	17.3115	0.0013	0.0072	0.000	0.001
12.94	13.9777	0.0012	0.0084	0.001	0.001
15.92	11.3633	0.0020	0.0113	0.001	0.002
19.30	9.0358	0.0023	0.0142	0.001	0.003
23.97	7.6723	0.0018	0.0160	0.001	0.004
24.97	7.2420	0.0009	0.0170	0.001	0.005
31.40	5.7536	0.0015	0.0185	0.001	0.006
41.53	4.3501	0.0015	0.0201	0.001	0.007
52.06	3.4727	0.0019	0.0220	0.002	0.009
61.03	2.9504	0.0006	0.0226	0.001	0.009
76.36	2.3587	0.0011	0.0237	0.002	0.011
91.01	1.9873	0.0011	0.0249	0.002	0.013
114.63	1.5750	0.0007	0.0256	0.002	0.015
140.23	1.2898	0.0013	0.0269	0.004	0.019
175.17	1.0325	0.0018	0.0287	0.005	0.025
219.69	0.8223	0.0030	0.0317	0.013	0.038
269.95	0.6699	0.0046	0.0363	0.025	0.062
332.42	0.5441	0.0051	0.0413	0.034	0.095
418.13	0.4326	0.0034	0.0468	0.044	0.140
519.18	0.3484	0.0045	0.0512	0.046	0.185
639.76	0.2827	0.0027	0.0539	0.034	0.220
796.66	0.2270	0.0026	0.0565	0.041	0.261
965.69	0.1835	0.0022	0.0587	0.042	0.303
1202.04	0.1505	0.0022	0.0609	0.053	0.356
1405.39	0.1267	0.0015	0.0624	0.044	0.400
1607.46	0.1125	0.0014	0.0638	0.045	0.445
1900.45	0.0952	0.0016	0.0656	0.070	0.515
2303.02	0.0785	0.0016	0.0672	0.073	0.589
2633.30	0.0697	0.0011	0.0684	0.062	0.651
3033.56	0.0596	0.0010	0.0694	0.063	0.714
3488.79	0.0516	0.0003	0.0701	0.054	0.768
4018.01	0.0450	0.0008	0.0709	0.055	0.822
4640.74	0.0390	0.0009	0.0719	0.050	0.873
5337.74	0.0336	0.0004	0.0723	0.046	0.919
6185.49	0.0292	0.0005	0.0728	0.026	1.037
7083.88	0.0255	0.0004	0.0733	0.065	1.102
8167.35	0.0221	0.0002	0.0734	0.033	1.125
9470.60	0.0191	0.0004	0.0739	0.031	1.216

Table B.4. (contd.)

MICKOMERITICS INSTRUMENT CORPORATION

AUTOPORE II 9220 V1.04

PAGE 3

SAMPLE NUMBER: 9 OPERATOR: PC
 SAMPLE ID: 7---2363-3-517
 SUBMITTER: ARGONNE LABS

LP 11:42:15 08/27/85
 HP 13:28:09 08/27/85
 REP 07:27:11 08/29/86

PRESSURE psia	PORE DIAMETER μ m	INCREMENTAL VOLUME mL/g	CUMULATIVE VOLUME mL/g	INCREMENTAL PORE AREA sq-m/g	CUMULATIVE PORE AREA sq-m/g
10858.68	0.0167	0.0001	0.0740	0.031	1.247
12561.01	0.0144	0.0002	0.0742	0.043	1.290
14454.19	0.0125	0.0004	0.0745	0.108	1.398
16665.48	0.0109	0.0004	0.0749	0.124	1.523
19119.69	0.0095	0.0002	0.0751	0.038	1.511
22111.78	0.0082	0.0001	0.0753	0.053	1.674
25073.02	0.0072	0.0004	0.0755	0.129	1.863
29858.06	0.0061	0.0000	0.0758	0.000	1.863
34907.20	0.0052	0.0006	0.0762	0.416	2.291
39256.11	0.0045	0.0002	0.0764	0.161	2.442
44830.08	0.0040	0.0000	0.0764	0.000	2.442
49773.19	0.0036	0.0003	0.0769	0.554	2.995
54774.15	0.0033	0.0000	0.0769	0.000	2.995
59701.85	0.0030	0.0003	0.0772	0.353	3.348

APPENDIX C:

Nuclear Magnetic Resonance Results

APPENDIX C: Nuclear Magnetic Resonance Results

A method of monitoring low levels of moisture in stone was sought in order to verify levels of dryness prior to weighing of briquettes. The open literature suggested a lower limit of moisture detection near 1%, far above the needed level of 10 ppm.

The availability of an advanced NMR imaging system at the General Electric Medical System Division in nearby New Berlin, WI, presented the opportunity to evaluate detection sensitivity of moisture in limestone briquettes. Limestone briquettes were prepared for imaging by C. A. Youngdahl as follows:

Two samples were soaked by placing them in a pan of water until moisture reached the top surfaces of the samples. They were then placed for several hours on a ceramic screen in a desiccator. One of the samples was subsequently sealed with fast-curing epoxy; the other was left in the desiccator. These two samples, together with a dry sample kept in the laboratory environment, were wrapped in aluminum foil and placed in plastic bags before they were taken to the NMR imaging system site. At the site they were placed in the NMR system so that a 10-mm slice through the center of the briquette was imaged as shown in Fig. C.1. The test on the NMR system was performed by C. Tauber of General Electric.

The results are shown in Figs. C.2-C.5. The left column indicates the setting of the gray scale and its range (window). The curved lines in some of the pictures show the local variation of density (gray scale) through the middle of the picture, and the straight line indicates the center of the gray scale.

The results indicate that the dry briquette, the briquette from the desiccator, and the epoxy-encapsulated briquette did not yield NMR contrast due to moisture content (Figs. C.2 and C.3). The desiccator briquette was subsequently placed on aluminum foil, and 10 g of water was added to the top of the briquette. After disappearance of the water, the test was repeated. Figure C.4 shows water penetration into the top and bottom surface of the briquette. After additional soaking of the briquette in a water bath, the NMR image shows water penetration throughout the briquette (Fig. C.5). The short time available on the NMR system did not allow for parameter optimization. While water content in solids can be assessed by NMR, the system must be optimized to engineering specimens rather than to biological specimens in order to improve its sensitivity.

Fig. C.1. Briquette dimensions and imaged slice in NMR system

Fig. C.2. NMR image of slice through center of dry briquette

Fig. C.3. NMR image of slice through center of epoxy-sealed briquette

Fig. C.4. NMR image of slice through center of briquette after wetting with 10 g of water

Fig. C.5. NMR image of slice through center of water-saturated briquette

APPENDIX D:

Sonoscan Report on Optical Measurements of Acoustic Waves on Marble and Limestone

**SONO
SCAN®****APPLICATIONS LABORATORY REPORT**

FEASIBILITY STUDY: OPTICAL MEASUREMENTS
OF ACOUSTIC WAVES ON
MARBLE AND LIMESTONE

Submitted To:

Argonne National Laboratory
9700 South Cass Avenue
Argonne, IL 60439

Attention: Art Youngdahl
(312) 972-5029

Submitted By:

Sonoscan, Inc.
530 East Green Street
Bensenville, IL 60106

Michael G. Oravec
Lawrence W. Kessler
(312) 766-7088

January 4, 1984

Sonoscan Project Numbers 4302 and 4317

Purchase Order #054473 and 055095

NOTE: This is a combined report under the above purchase orders.

FEASIBILITY STUDY: OPTICAL MEASUREMENTS
OF ACOUSTIC WAVES ON MARBLE AND LIMESTONE

OBJECTIVE

This program is a preliminary feasibility study to determine surface acoustic wave velocity and attenuation on rock samples by means of a laser-optical method. Presumably as the samples become exposed to harsh environments, their surfaces will be altered in such a way as to be observed by suitable acoustic wave measurements.

BACKGROUND AND DESCRIPTION OF METHOD

Optical measurement of acoustic waves on surfaces is not new and a number of different techniques have appeared in the literature. Sonoscan has already made laser acoustic wave sensing instruments available commercially as part of its acoustic microscope. The advantages of optical methods is that they are essentially non-contact and are capable of very high resolution. Therefore, variations in coupling can be removed as an error source in the measurements. Ordinarily, the surface carrying the acoustic wave information should be optically reflective (like a mirror) in order to permit efficient collection of light. Figure 1 shows two (2) optical detection methods for acoustic wave measurement.

FIGURE 1.

A. Knife Edge Method for Acoustic Wave Detection.

Surface acoustic waves generated by transducers T and wedge W distort the surface of a sample by creating a dynamic ripple. Laser light incident upon the surface will be reflected at angles corresponding to the acoustically induced surface tilt. The knife edge KE blocks half of the beam and acts as a demodulator which changes angular modulation of the beam to an intensity modulation. The photodetector PD signal corresponds to the acoustic wave amplitude.

B. Interferometer Method for Acoustic Wave Detection.

Laser light is split into two (2) beams by a beamsplitter BS sending one beam to the active surface and the other to the reference mirror RM. Light reflected from the RM and from the active surface are diverted to the photodetector where the beams overlap. Due to the coherent nature of the laser light, the change of path length between O - S and O - RM causes a change in light intensity at PD.

In the case of sample surfaces which are not reflective optically, additional complications arise. First of all, the optical signal at PD is not only a function of surface movement (acoustic), but also of surface reflectivity (optical). These two functions are multiplicative. If the reflectivity variations are reasonable, they can be compensated for or "normalized out" as follows:

FIGURE 2. BLOCK DIAGRAM FOR NORMALIZING ACOUSTIC SIGNAL FOR OPTICAL REFLECTIVITY VARIATIONS

Alternately, the surface may be made optically reflective. Because of the surface roughness, metalization coating will not render the surface reflective. Instead we propose the following method employing a taut metalized mylar membrane.

FIGURE 3. MYLAR DISH TECHNIQUE

The mylar is stretched over a rigid ring forming a dish and placed in contact with the sample surface. The dish is capped with an optical window and filled with water to press the membrane against the sample surface. The laser light passes through the window and water and is reflected off the mylar's reflective surface.

RESULTS

A breadboard system employing the method shown in Figure 1A was setup using a 4mW laser and a standard compressional wave 1 MHz ultrasonic transducer in place of the sample. The transducer surface was optically polished. Therefore, good signal level was detected. The acoustic wave was transmitted through a piece of 1/16" aluminum whose surface finish was dull. This was an "as extruded" surface, which was far smoother than either the limestone or marble samples of interest. The signal level reduced to the level of hardly being detectable above the laser noise. This tremendous reduction in level may make it unreasonable to expect signals from the samples of interest. To investigate this aspect, acoustic wave and optical measurements were made on the samples as follows:

FIGURE 4. Average Optical Reflectivity Test Setup

A 4mW HeNe laser operating at 6328Å wavelength is incident upon the sample surface through a beamsplitter, BS, at normal incidence. The beam diameter is of the order of 1 mm with a Gaussian profile. Reflectivity of the sample is measured relative to the current meter reading (I) of a 99.9% reflective mirror in place of the sample.

TABLE 1: REFLECTIVITY MEASUREMENTS

<u>Sample</u>	<u>Relative Reflectivity</u>
Clean Marble	0.75%
Exposed Marble	0.5 %
Limestone.	0.5 %
Reference Mirror	100 %

Note that the surfaces are highly irregular and these measurements represent an average over a 1 mm diameter spot.

Since the sample surfaces are rough, a focused laser beam was scanned across the surface and the output video levels monitored. This measurement indicates the spatial variation in reflectivity. Figure 5 indicates the test method which is adapted from Sonoscan's Scanning Laser Acoustic Microscope (SLAM).

FIGURE 5. Scanning Laser Optical Technique for Measuring Reflectivity of Surfaces

FIGURE 6. Low Magnification Calibration

Sample: Grid paper 1mm square, Laser spot size 75 micrometers
at surface of sample.

Reflection Image (from CRT)

Line Scan (from oscilloscope
tracing of a single video
line across image).

FIGURE 7. High Magnification Calibration

Sample: Grid paper, 1mm square, laser spot size 20 micrometers
at surface of sample.

Cal 100

Reflection Image (from CRT)

Cal 100

Line Scan (from oscilloscope
tracing of a single video
line across image).

FIGURE 8. Limestone: Note the wide variation on optical reflectivity. From saturated white to black. A dynamic range estimate is about 60db.

Low Magnification: Image

Line Scan

High Magnification: Image

Line Scan

FIGURE 9. Marble: Compared with the limestone the marble sample appears to have a smoother texture at low magnification.

Low Magnification: Optical

Line Scan

High Magnification: Optical

Line Scan

II ACOUSTIC MEASUREMENTS:

Surface acoustic waves can be produced on a sample by the use of a compressional wave transducer in combination with an appropriate interface wedge as shown in Figure 1. The surface roughness precludes high frequency ultrasound such as employed in the SLAM. Therefore 1 MHz pulsed transducers were employed similar to those employed in standard ultrasonic tests. The surface acoustic wave velocity is related to the compressional wave velocity after taking into account the other Lamé constants of the material. The acoustic pulse measurements were conducted as follows:

FIGURE 10. PULSED ACOUSTIC TRANSMISSION TECHNIQUE

Results: Limestone. Note the transducers were placed in dry contact with the sample surfaces. There was a compressible rubber membrane cushion at the interface to facilitate acoustic contact.

FIGURE 11. Two successive pulses of ultrasound within the sample. The time between pulses represents travel through twice the sample thickness.

Velocity of Ultrasound 3810 m/sec

5 μsec/div

FIGURE 12. Pulsed acoustic measurements on Marble.

Note: An attempt to make the echoes as well defined as possible in marble precluded the use of the rubber membrane approach. The transducers were coupled to the sample with a few drops of water at the transducer - sample interface.

The marble was a very diffuse transmitter of ultrasound and it was not possible to clearly identify specific echos on which to make velocity of sound measurements.

10 μ sec/div

Fig. A and B are two trials made a few minutes apart in the same area of the sample. There were no measurements possible.

10 μ sec/div

FIGURE 13. Marble - Pulsed Acoustic Measurements

As a further illustration of the difficulties with the marble sample. The receiving transducer was placed on an orthogonal surface to the transmitter. The resulting waveform is shown here.

Test Setup:

SUMMARY AND CONCLUSIONS

Optical reflectivity and acoustic transmission measurements were made on limestone and marble samples supplied by Argonne National Laboratories. Optical techniques for acoustic wave measurements require either a good optically reflection surface or a scheme involving acoustic wave coupling from the surface (if bad optically) to a mylar membrane mirror. Preliminary setup of the technique indicated validity of the concept, but also showed poor signal to noise ratio. To improve the situation from an optical point of view requires high light levels and, perhaps lock in amplifier techniques to extract signal from noise. The marble samples at low magnification (75 um spot size) showed reasonable optical reflectivity uniformity relative to the limestone. However, from the ultrasonics point of view, the reverse was true. That is, the marble was highly diffuse acoustically, and it was not possible to define clear pulse arrival times. (These are necessary to measure velocity of sound.) Part of the problem here is the small sample size. The ultrasound scatters in all directions and arrives at the receiving transducer from a variety of pathways. Since the arrival time of the pulse is not clear, valid acoustic measurements would be difficult without a much more elaborate setup. The size of the limestone sample did not appear to be a problem.

RECOMMENDATIONS

Given the above data and restrictions on samples, there appears to be reasonable feasibility of performing velocity of sound measurements in limestone and marble. Attenuation measurements could not be performed with the current setup. Further work would be required to establish the instrumentation, however, for routine measurement capability. This work must include:

- 1) Further investigation of acoustic properties to establish sample size, acoustic frequency and wedge angle to obtain well-defined, measurable surface waves.
- 2) Design and construction of scanning optical system and detection electronics to measure surface waves. This requires rough knowledge of surface wavelength obtained in step 1.
- 3) Demonstration of system on samples of various roughnesses to establish how roughness affects acoustic parameters.

Current estimate is about 1 to 1½ man-years of development effort.

Distribution for ANL-90/24Internal

H. Drucker
 N. M. Heeg
 P. Hess
 A. C. Raptis
 C. A. Malefyt (2)

K. J. Reimann (7)
 J. Shannon
 D. Streets
 C. E. Till
 R. A. Valentin

R. W. Weeks
 M. Wesely
 ANL Patent Dept.
 ANL Contract File
 TIS (3)

External

DOE/OSTI (2)
 ANL Libraries
 DOE-CH:

Manager
 D. T. Goldman
 F. Herbaty
 A. L. Taboas

Materials and Components Technology Division Review Committee:

H. Berger, Industrial Quality Inc., Gaithersburg, MA
 M. S. Dressehaus, Massachusetts Institute of Technology, Cambridge, MA
 S. J. Green, Electric Power Research Institute, Palo Alto, CA
 R. A. Greenkorn, Purdue University, West Lafayette, IN
 C.-Y. Li, Cornell University, Ithaca, NY
 P. G. Shewmon, Ohio State University, Columbus
 R. E. Smith, Electric Power Research Institute, Charlotte, NC

National Park Service:

L. Nelson
 J. Rogers
 S. Sherwood (20)

United States Geological Survey:

P. Baedeker
 M. Kingston
 J. Morgan
 V. Mossotti
 R. Pickering
 M. Reddy
 E. Spiker

Colorado School of Mines:

D. Langmuir

**DATE
FILMED
314192**

I