TECHNICAL REPORT

September 1 through November 30, 1991

Project Title: **Characterization of the Surface Properties of
Illinois Basin Coals** DE-FG22-91PC91334

Principal Investigator: **Ilham Demir, ISGS**
Co-investigators : **Richard D. Harvey, ISGS**
Anthony A. Lizzio, ISGS

Project Monitor : **Ken K. Ho, CRSC**

ABSTRACT

The surface properties of coal play a major role in determining the physical-chemical behavior of coal during such processes as coal cleaning (flotation, flocculation, dewatering, carbon-sulfur bond cleavage reactions), combustion (swelling, pyrolysis, ignition) and conversion (gasification, liquefaction). Data on surface properties help coal scientists and engineers in the design of effective coal desulfurization processes, and thereby aid in the marketability of Illinois Basin coals. The surface properties of eight coals in the Illinois Basin Coal Sample Program (IBCSP) will be characterized, and statistical relationships between surface properties and other coal characteristics will be explored. We will determine total surface area, porosity, pore size distribution, surface charge, and the chemical structure of the coal surface in a fresh state and after oxidation at room temperature. During the first quarter we obtained supplies and a set of samples to prepare for the surface property tests.

Eight samples of the IBCSP were obtained in fresh state. The samples were right away sealed in 1-gallon glass bottles purged with argon gas until they were ground to about -400 mesh size. The samples were ground in a stirred-ball mill and subsequently filtered and partially dried in a vacuum oven to minimize oxidation. The filtered cake of each sample was split in half, and one of the halves was further split into four equal parts. Each part was sealed in a glass bottle, purged with argon gas, to be used to determine the surface properties of the samples in a fresh state. The other ground half of each coal is being exposed to air oxidation at room temperature to investigate the effect of oxidation on the surface properties of coal.

Another set of the same samples will be ground to -100 mesh and processed and stored similarly during December, and the surface property tests for all eight IBCSP coals will start in January.

This project is funded by the U. S. Department of Energy (PETC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

The main objective of this project is to generate fundamental information on the surface properties of Illinois Basin Coal Sample Program (IBCSP) coals. Total surface area, porosity, pore size distribution, surface charge, and surface chemical structure (e.g., nature of C-O- and C-H functional groups) will be determined. Currently, little specific data is available on the surface properties of IBCSP coals. These properties control the physical-chemical behavior of particulate coal during all stages of coal cleaning, combustion and conversion processes, wherein C-S bond cleavage reactions, pyrolysis, swelling, flotation, flocculation, adsorption, and dewatering may occur. Most projects funded by the CRSC are concerned with processes that are directly affected by the surface properties of coal; knowledge of these properties for specific size fractions of unoxidized and oxidized IBCSP coals will help coal researchers choose samples suitable for their experiments and/or better interpret their experimental findings. This in turn could lead to the design of more effective desulfurization processes and enhance industrial utilization of Illinois Basin coals.

Six tasks are scheduled to achieve our objective:

- (1) Grind the eight samples currently available in large quantities in the IBCSP to two top sizes, -100 and -400 mesh.
- (2) Determine total (internal and external) surface area, pore size (micro, meso, macro) distribution, total pore, mesopore, and micropore volume, and total porosity of the above ground coal samples in a fresh (essentially unoxidized) state.
- (3) Determine the surface charge of unoxidized -400 mesh samples; coarser particles may not stay in suspension in the electrophoretic cell, which could produce erroneous test results.
- (4) Perform tests to obtain the Diffuse Reflectance Infrared spectroscopy (DRIS) properties of each unoxidized sample.
- (5) Expose identical splits of each unoxidized samples to air oxidation under normal laboratory (ambient air) conditions for two months, and measure the same surface properties again for the oxidized coals.
- (6) Perform multivariate statistical analysis of the newly determined surface properties and other available

characterization data (including chemical and petrographic composition, vitrinite reflectance, free swelling index, ash yield, forms of sulfur).

For the first task, we purchased supplies and obtained a set of IBCSP coals (IBC-101, IBC-102, IBC-103, IBC-105, IBC-106, IBC-107, IBC-108, and IBC-109). Right after their removal from the IBCSP barrels the samples were sealed in 1-gallon glass bottles purged with argon gas until they were ground to about -400 mesh (37 μm) size. The samples were ground in a stirred-ball mill and subsequently filtered and partially dried in a vacuum oven to minimize oxidation. The filtered cake of each sample was divided in half, and one of the halves was further split into four parts. Each part was sealed in a glass bottle, purged with argon gas, to be used investigate the surface properties of the samples in fresh state. The other half of each sample is being exposed to air oxidation at room temperature to later on determine the effect of oxidation (after two months of exposure to air) on the surface properties.

Another set of the same samples will be ground to -100 mesh and processed similarly within the month of December. The surface property tests for the fresh -100 and -400 mesh samples will start in January.

To determine the surface area and porosity of the IBCSP coals, we will interpret N_2 and CO_2 adsorption isotherms obtained at 77 and 298 K, respectively. The analysis of N_2 and CO_2 isotherms, using the Brunaur-Emmett-Teller (BET) and the Dubinin Radushekevich (DR) equations, provides such information as internal and external surface area, pore size distribution, mesopore volume and area, micropore volume and area, and average pore diameter [Gregg and Sing, 1982]. The total porosity of each sample will be determined using conventional methods which involve the measurement of the true (helium) and particle (mercury) density of coal as described by Mahajan and Walker [1978].

To determine the surface charge, coal particles need to be finer than 325 mesh to ensure the reliability of results [Demir and Chou, 1990]; therefore, the oxidized -100 mesh samples will be ground to -325 mesh or finer prior to the surface charge measurements. Only the -400 mesh samples will be tested in both a fresh and oxidized state. The surface charge of a sample will be determined by suspending the fine coal particles in distilled water and measuring the zeta potential (a direct measure of surface charge) of the suspended particles with a zeta-meter as a function of pH. The pH adjustment will be made using diluted NaOH and HCl solutions.

Measurements and analyses to evaluate the sample surfaces by DRIS will be carried out at the Oak Ridge National Laboratory using a computer controlled infrared spectrometer system. These results will indicate the relative proportions of different oxygen- and hydrogen-bonded functional groups that occur at or near the coal surfaces.

Coal samples may experience a significant amount of air oxidation prior to their use in experiments. Therefore, the effect of oxidation on the surface properties of coal is an important consideration. The extent of oxidation can vary from one sample to another depending on temperature, time of exposure, coal composition and rank, particle size, and porosity. The same coal sample, oxidized to varying degrees, can behave differently under the same experimental conditions.

The surface property data obtained for the eight IBCSP coals of two different size fractions will be analyzed and compared. The effect of oxidation on each sample will be evaluated. Multivariate statistical analyses will be used to determine possible correlations among the measured surface properties and other available characterization data, e.g., ash yield, organic sulfur and total sulfur contents, maceral composition, free swelling index, vitrinite reflectance, that have been published by various authors through the CRSC.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

OBJECTIVES

The overall objective of this research project is to provide fundamental data on the physical and chemical surface properties of Illinois coals, specifically those of the Illinois Basin Coal Sample Program (IBCSP). This will help coal researchers achieve an optimal match between Illinois Basin coals and potential coal cleaning and conversion processes (or at least reduce the number of coals suitable for a particular process) and may lead to improved desulfurization and increased utilization of Illinois Basin coals.

The specific tasks scheduled to meet our objective are:

- (1) Physical Characterization: Determine total surface area, porosity, pore size and volume distributions of IBCSP coals crushed to two particle sizes, -100 and -400 mesh (exclusive of IBC-108 which is available only in -400 mesh form), in both an unoxidized and oxidized state.
- (2) Chemical Characterization: Determine the surface charge (electrokinetic mobility) as a function of pH by electrophoresis and analyze the surface chemical structure of the above samples using Diffuse Reflectance Infrared Spectroscopy (DRIS).
- (3) Multivariate Statistical Analyses: Explore possible relationships among the newly determined surface properties and other available characterization data, including chemical and petrographic compositions, vitrinite reflectance, free swelling index, ash yield, sulfur forms, and other relevant properties.

Eight of the nine samples in the IBCSP will be tested. The supply of IBC-104 coal is near depletion and, therefore, not available for this project.

INTRODUCTION AND BACKGROUND

To date, there has been little (if any) information available concerning the surface properties of IBCSP coals, although these samples are now in considerable demand by coal researchers throughout the state of Illinois and nationwide. The majority of CRSC-funded research projects involve the use of IBCSP coals in various surface-dependent physical and chemical coal-cleaning and coal conversion processes. To fully understand the heterogeneous reactions involved in physical, chemical and microbial coal cleaning and in producing fuel and chemicals from coal, a thorough

knowledge of the physical and chemical structure of coal is required. The establishment of a data base for surface properties of both unoxidized and oxidized IBCSP coals would greatly aid coal scientists and engineers in the research and development of improved processes for desulfurization and increased marketability of Illinois Basin Coals.

Surface Area and Porosity

Most proposed structural models describe bituminous coal as a cross-linked, three-dimensional, macromolecular network of aromatic and hydroaromatic ring systems with a variety of functional groups at their periphery and relatively small, soluble hydrocarbon molecules entrapped in the interstices of the network [Mahajan and Walker, 1978; Wender et al., 1981; Given, 1984]. As a result of its molecular structure coal is a highly porous solid and its total surface area is due mainly to the internal surface area. About 90-95% of the total surface area of coal correspond to micropores [Essenhig, 1981]. Pores with diameters less than 2 nm are generally classified as micropores [Dubinin, 1966]. The mesopores (pore diameters between 2-30 nm), which are important for transport and serve as passages for reactant molecules to the micropores, have relatively low surface area; the surface area due to macropores (30-1000 nm) is considered to be negligible [Dubinin, 1966]. All coals are microporous materials; their surface properties have been studied for several decades. Due to the physical and chemical complexity of coal, data on surface area and porosity of coal may be subject to different interpretations. Fuller [1981] suggested that accessibility is probably a better term to use to define the surface area and pore structure of coal. Gregg and Sing [1982] reviewed the use of adsorption methods for the determination of surface area and pore size distribution of porous solids. Marsh [1987] drew attention to the problems and ambiguities associated with interpreting physisorption data of microporous materials. In short, the surface area of a microporous solid like coal is a function of how it is measured and how the adsorption data are interpreted. Problems in accepting adsorption data may arise because the adsorption equation used is not modelling the adsorption process as it actually occurs. The principle theoretical equations used to interpret adsorption isotherms include Langmuir, BET, Dubinin-Radushkevich, and Dubinin-Astakhov equations. The Langmuir and BET equations supposedly predict monolayer coverage by the adsorbate in porosity and on non-porous surfaces, from which a surface area can be calculated. The other two equations essentially predict a micropore volume. Major differences in surface area can arise from using different adsorbates, e.g., N_2 at 77 °K and

CO₂ at 298 °K, for several reasons: (1) activated diffusion effects which excludes entry of adsorbate molecules into the microporosity, (2) molecular sieve effects whereby molecules having effective diameters larger than the pore entrance are not adsorbed, (3) cooperation effects where multilayer adsorption can occur at relative pressures of only 0.1-0.2 (in the range of BET analysis), and (4) the use of different adsorption equations, i.e., the Langmuir and BET describe the adsorption process over the relative pressure range of about 0.05-0.35, the DA and DR equations are used to interpret data obtained at much lower pressures. Carbonaceous materials in general, and coals in particular, can have a porosity which is so complex that it can exhibit simultaneously several of the problems just listed. The researcher in this area needs to be aware of these problems and should not take a measured value of surface area to be absolute. Marsh [1987] stated that the concept of a "real" or "true" physical surface area does not exist for microporous coals and carbons and recommends the use of the "equivalent" surface area, i.e., the value of surface area which the adsorbent is exhibiting under the experimental conditions used. Again, for microporous solids a value of surface area is a function of how the adsorption isotherm is determined and interpreted. If all conditions are specified, the surface area has value and application, especially in comparing the physical-chemical behavior of one coal sample to that of another.

A knowledge of the surface area and porosity of a given coal is of major importance in understanding the mass transport phenomena that govern its physical-chemical behavior. For example, Mahajan and Walker [1978] pointed out that the amount and ease of extraction of coal-bed methane are controlled by the porosity and pore size distribution of the coal. The specific gravity of coal, which is affected by the porosity, is critical in those coal preparation processes that take advantage of density differences between coal and the mineral matter. In coal cleaning or conversion (e.g., gasification), the transport of reactants to the internal coal surface and the escape of product molecules from the pores to permit access of fresh reactants are significantly influenced by the pore structure. Knowledge of the initial pore structure of the coal precursor can be helpful in predicting the type of porosity that may develop, and, hence, in making an assessment of the suitability of the coal for a particular cleaning or conversion process or for the production of solid products from coal (e.g., activated carbons, carbon molecular sieves).

Gumkowski et al. [1988] recently reported the surface areas of the eight samples in the Argonne Premium Coal Sample bank which includes a sample very similar to the IBC-105 coal in

the IBCSP. Machin et al. [1963] and Thomas and Damberger [1976] measured the porosity and internal surface area of some Illinois coals. Their measurements yielded values of internal surface area ranging from 1.8 to 310 m²/g, with hvA bituminous coals having the lowest and hvC bituminous coals the highest values, and most of the surface area being derived from the vitrinite portion of the coal. Unsworth et al. [1989] concluded that both vitrinites and inertinites contain significant microporosity, mesoporosity, and macroporosity and that inertinite fractions contain more macroporosity and less microporosity than their vitrinite counterparts. According to Thomas and Damberger [1976] most pores in Illinois hvA bituminous coals appear to be smaller than 3.5 nm whereas Illinois hvC bituminous coals contain a large number of pores having diameters in the range of 9 to 22 nm. Studies by Machin et al. [1963] and Thomas and Damberger [1976] also suggest that the surface area and porosity can vary significantly within the same rank even if the maceral composition does not vary. The multivariate statistical analysis of the surface area and porosity data along with other characterization data obtained in this study could lead to further advancements in the formulation of useful correlations involving the physical-chemical properties of Illinois Basin coals.

Coal samples oxidize in the laboratory upon exposure to air which can significantly affect their behavior in coal cleaning and conversion processes. Experimental results of Kaji et al. [1985] indicated that low temperature oxidation correlated well with internal surface area and pores with diameters >10 nm for the coals tested. Su and Perlmutter [1985] and Ng et al. [1988] observed that the difference in pore structure of coal-derived chars can significantly affect their gasification reactivity in air. Data on internal surface area and porosity can be especially useful when the removal of organic sulfur from coal is addressed. Organic sulfur occurs in coal as part of both aromatic and aliphatic functional groups [Attar and Dupuis, 1981; Palmer et al., 1991] as well as thioether bridges. Most of the organic sulfur thus appears to be located on or near the surface of the basic molecular units and the walls of micropores, and sulfur-containing bonds, especially aliphatic ones, should be highly reactive. One of the most important limiting factors for removal of organic sulfur may then be the diffusion of reacting agents into and product molecules out of the micropores.

Surface Charge

Electrostatic charge on the coal surface, resulting mainly from the resident oxygen-containing functional groups, affects surface-dependent processes, e.g., flotation,

flocculation, and dewatering. The surface charge of a coal particle can be altered, if necessary, with appropriate reagents [Campbell and Sun, 1970; Gala et al., 1983; Ayub et al., 1985; Demir et al., 1990] to improve the efficiency of surface-dependent processes. Air oxidation has been reported [Wen, 1977; Khan et al., 1984; Demir et al., 1990] to reduce the surface charge of bituminous coals. Surface charge may thus be a good indicator of the degree of oxidation of untreated coal samples, which is known to correlate well with the extent of flotation recovery of coal during physical cleaning [Ayat, 1987].

In this study, the surface charge of each coal will be determined by measuring its electrophoretic mobility [Solar et al., 1990] over a wide pH range. Attempts will also be made to correlate surface charge data with other measured surface properties and already available coal characterization data, e.g., petrographic and chemical composition, vitrinite reflectance, swelling index, ash yield, and sulfur forms.

Surface Chemical Structure by DRIS Methods

Diffuse Reflectance Infrared Spectroscopy (DRIS) is a powerful tool to study the chemistry and structure of coal [Solomon et al., 1982; Painter et al., 1987]. Fuller and Smyrl [1988, 1990] used DRIS to delineate the surface chemical structure of coals of various ranks. They reported the existence of large amounts of O-H--O bonds in all ranks except anthracite, and that there are five distinct types of hydrogen bonding corresponding to the number of electron donor oxygen atoms involved. They also found that the hydrogen bonding strength increases with rank. Clemens et al. [1990] used DRIS to investigate spontaneous combustion of dried New Zealand coals. From monitoring changes in coal surfaces as a result of exposure to oxygen or air at 30 to 180°C, they concluded that the reactivity responsible for self-heating involve exothermic formation of hydroperoxides followed by their composition into carboxylic acid/aldehyde species. Malhotra, et al. [1990] reported results of experiments in which they determined the grazing-, diffuse reflectance-, and transmission-infrared spectroscopy properties of various samples of pyrite. They observed distinctly different properties for different types of pyrite: cubic pyrite (from Arizona), pyrite from an oil shale in Colorado, and coal-derived pyrite. These properties were correlated with the sample's flotability. Dry grinding produced the least number of hydrophilic sulfate sites on surfaces of the coal-derived pyrite, compared to the other samples. The coal-derived pyrite was slow to develop such sites during wet grinding. Application of these special infrared spectroscopy experiments to coal

particles from the IBCSP is feasible and holds promise to yield useful characterization results related to the particular molecular structure, or general category of functional type, that predominates on the surfaces tested.

This project involves a comprehensive study of the physical and chemical surface properties of IBCSP coals and the effect of oxidation on these properties. State-of-the art analytical equipment and software are used to perform experiments under carefully controlled conditions to characterize the surface properties of eight (of nine) IBCSP coals. Multivariate statistical analysis of the newly determined surface properties and other available characterization data could lead to further advancements in the formulation of predictive correlations involving the physical-chemical properties of Illinois Basin coals.

EXPERIMENTAL PROCEDURES

During the first quarter we obtained and prepared the first set of the samples (Task 1). Eight of the nine IBCSP coals (IBC-101, IBC-102, IBC-103, IBC-105, IBC-106, IBC-107, IBC-108, and IBC-109) were obtained in fresh state. One of the IBCSP samples (IBC-104) is near depletion and, therefore, not available for this study.

Right after their removal from the IBCSP barrels the samples were sealed in 1-gallon glass bottles purged with argon gas. Each bottle was flushed with argon gas to replace at least ten times the volume of the bottle prior to sealing. After about a week, each sample was taken out of the bottle and wet-ground (coal/water = 1lb/1L) in a stirred-ball mill for 10 minutes; IBC-108 is already in micronized form and, therefore, did not need to be ground. Right after grinding the coal-water slurry was filtered and partially dried in a vacuum oven to minimize oxidation. The filtered cake of each sample was divided in half, and one of the halves was then split into four parts. Each part was stored in a sealed glass bottle which was purged with argon (again, at least ten times the volume of the bottle was replaced with argon) to prevent oxidation prior to testing. The other half of each sample is being exposed to air oxidation under normal laboratory (ambient air) conditions.

RESULTS AND DISCUSSION

During the first quarter we obtained and ground the IBCSP coals to about -400 mesh size in a stirred-ball mill (Task 1) to prepare them for the surface property tests. The

analysis of the samples with a Microtrac particle size analyzer indicated that the particle size was reduced to about 90% -400 mesh (37 μm) with a mean volume size diameter ranging from 15 to 17 μm (Table 1).

Table 1. The particle size distribution of ball-milled IBCSP coals*.

Sample	Mean size(μm)*		Standard deviation (μm)	Cum. Distribution ($<$, μm)		
	vol.	area		10%	50%	90%
IBC-101	17	7	12	3.1	12.6	36.3
IBC-102	17	7	13	2.6	13.0	39.8
IBC-103	17	7	12	3.1	12.6	35.9
IBC-105	17	7	13	2.8	12.3	36.8
IBC-106	17	7	13	2.8	12.6	37.5
IBC-107	15	6	12	2.4	11.5	32.6
IBC-108	10	5	6	2.1	7.0	20.8
IBC-109	17	8	13	3.3	13.6	38.2

* Wet-ground in a stirred-ball mill for 10 minutes (except IBC-108). The IBC-108 was analyzed as received because it is already provided in finely ground form.

The vol. measure is the mean diameter of the measured volume distribution of the tested sample, biased toward the larger particles. The area measure is the mean diameter of the measured area distribution, biased toward the small particles.

We did not want to reduce the particle size further (to 100% -400 mesh) because longer than 10-minute grinding in a ball mill has been shown [Riley et al., 1990] to alter the coal density and surface area significantly.

Four representative splits of each ground sample were stored in glass bottles purged with argon gas to prevent oxidation. This is necessary to investigate the surface properties of these coals in fresh state. The rest of each sample is being exposed to air oxidation to be used later to determine the effect of oxidation (after two months of exposure to air) on the surface properties of the coals.

CONCLUSIONS AND RECOMMENDATIONS

During the first quarter we purchased supplies and obtained a set of the Illinois Basin Coal Sample Program coals (IBC-101, IBC-102, IBC-103, IBC-105, IBC-106, IBC-107, IBC-108, and IBC-109) for preparation to measure the surface properties of these coals.

Right after their removal from the IBCSP barrels the samples were sealed in 1-gallon glass bottles purged with argon gas until they were ground to about 90% -400 mesh (37 μ m) size in a stirred-ball mill. One half of each ground coal was split into four parts. Each part was then sealed in a glass bottle purged with argon gas to prevent oxidation. These samples will be used for measurement of their surface properties in an unoxidized state. The other half of each coal is being exposed to air oxidation at room temperature to later on determine the effect of oxidation on the surface properties.

Another set of the same samples will be ground to -100 mesh and processed similarly during December. We will start measuring the surface properties of fresh -100 and -400 mesh samples in January.

REFERENCES

- Attar, A., and Dupuis, F., 1981. Data on the distribution of organic sulfur functional groups in coal. In: M. L. Gorbaty and K. Ouchi (eds.), Coal Structure. Advances in Chem. Ser., 192, Amer. Chem. Soc., Washington, D.C.
- Ayat, M. G., 1987, Composition of coal relative to its functionality and processability. Mining Sci. Tech., v. 4, p. 105-112.
- Ayub, L. A., Al Taweel A. M., and Kwak, J. C. T., 1985, Surface properties of coal fines in water. I. Electrokinetics and surfactant adsorption. Coal Preparation, v. 1, p.117-130.
- Campbell, J. A. L., and Sun, S. C., 1970, Bituminous coal electrokinetics. Soc. Min. Eng., AIME Transactions, v. 247., p. 111-114.
- Clemens, A. H., Matheson, T. W., and Rogers, D. E., 1991, Low temperature oxidation studies of dried New Zealand coals. Fuel, v. 70, p. 215-221.
- Demir, I., Chou, C.-L., and Chaven, C., 1990, Abundances and Leachabilities of Sodium and Chlorine in Lithotypes of Illinois Basin Coals. In: L. L. Chyi and C.-L. Chou (eds.), Recent Advances in Coal Geochemistry, Geological Society of America, Special Paper 248, p. 73-85.
- Dubinin, M. M., 1966, Porous structure and adsorption properties of active carbons. In: P. L. Walker, Jr. (ed.), Chemistry and Physics of Carbon, V. II, p. 51-120, Dekker, New York.

Essenhight, R. H., 1981, Fundamentals of coal combustion. In: M. A. Elliot (ed.), Chemistry of Coal Utilization, Second Suppl. Vol., Wiley-Interscience, New York.

Fuller, E. L., 1981, Physical and chemical structure of coals: sorption studies. In: M. L. Gorbaty and K. Ouchi (eds.), Coal Structure, ACS 192, p. 293-309, American Chemical Society, Washington, D.C.

Fuller, E. L., and Smyrl, M. R., 1988, Diffuse Reflectance Infrared Fourier Transform DRIFT Studies of Coal Preparation Techniques (Preliminary Results). Oak Ridge National Laboratory, Oak Ridge, TN.

Fuller, E. L., and Smyrl, M. R., 1990, Chemistry and structure of coals: Hydrogen bonding structures evaluated by Diffuse Reflectance Infrared Spectroscopy. Applied Spectroscopy, v. 44, p. 451-461.

Gala, H. B., Chiang, S. H., and Wen, W.-W., 1983, Effect of surfactant adsorption on the hydrophobicity of fine coal. Proc. Int. Conf. on Coal Sci., 8/15-8/19/1983, Pittsburgh, PA.

Given, P. H., 1984, An essay on the organic geochemistry of coal. In: M. L. Gorbaty, J. W. Larsen and I. Wender (eds.), Coal Science, Vol. 3, Academic Press, New York.

Gregg, S. J. and Sing, K. S. W., 1982. "Adsorption, Surface Area and Porosity." Academic Press, New York, New York.

Gumkowski, M., Liu, Q., and Arnett, E., 1988, Thermochemical comparisons of six Argonne premium coal samples. Energy & Fuels, v. 2, p. 295-300.

Kaji, R., Hishnuma, Y., and Nakamura, Y., 1985, Low temperature oxidation of coals: Effects of pore structure and coal composition. Fuel, v. 64, p. 297-302.

Khan, L. A., Berggren, D. J., and Hughes, R. E., 1984, Effects of weathering on coal and its sulfur constituents in refuse piles. Illinois State Geological Survey, Reprint 1985F, Champaign, IL.

Machin, J. S., Staplin, F., and Deadmore, D. L., 1963, Studies on the Ultra-fine Structure of Some Illinois Coals. Illinois State Geological Survey Circ., 350, Champaign, IL.

Mahajan, O. P. and Walker, P. L., 1978, Porosity of coals and coal products. In: C. Karr (ed.), Analytical Methods for Coal and Coal Products, Academic Press, New York.

Malhotra, V. M., Saporoschenko, M. and Kent, A., 1990, Modification of pyrite surfaces and preparation of ultrafine clean coal. Illinois Coal Development Board Eighth Annual Contractors' Technical Meeting, Abstracts of Papers, July, p.19.

Marsh, H., 1987, Adsorption methods to study microporosity in coals and carbons - a critique. Carbon, v. 25, p. 49-58.

Ng, S. H., Fung, D. P. C., and Kim, S. D., 1988, Study of pore structure and reactivity of Canadian coal-derived chars. Fuel, v. 67, no. 5, p. 700-706.

Painter, P. C., Sobkowiak, M., and Youtcheff, J., 1987, FT-i.r. study of hydrogen bonding in coal. Fuel, v. 66, p. 973-978.

Palmer, S. R., Hippo, E. J., Kruege, M. A., and Crelling, J. C., 1990. Characterization of organic sulfur compounds in coals and coal macerals. In: W. L. Orr and C. M. White (eds.), Geochemistry of Sulfur in Fossil Fuels, ACS Symp. Series 429, ACS, Washington, DC.

Riley, J. T., Lloyd W. G., Kuehn, K. W., Kuehn, D. W., and Withers, D. L., 1990, Coal density changes during stirred-ball mill attritor milling. J. Coal Quality, v. 9, p. 12-17.

Solar, J. M., Leon y Leon, C. A., Osseo-Asare, K. and Radovic, L. R., 1990, On the importance of the electrokinetic properties of carbons for their use as catalyst supports. Carbon, v. 28, p. 369-375.

Solomon, P. R., Hamblen, D. G., and Carengelo, R. M., 1982, Applications of Fourier Transform Infrared Spectroscopy in Fuel Science. In: E. L. Fuller (ed.), Coal and Coal Products: Analytical Characterization Techniques, ACS Symp. Series 205, ACS, Washington, DC.

Su, J.-L., and Perlmutter, D. D., 1985, Effect of pore structure on char oxidation kinetics. AIChE J., v. 31, no. 6, p. 973-981.

Thomas, J., and Damberger, H. H., 1976, Internal Surface Area, Moisture Content, and Porosity of Illinois Coals: Variations with Coal Rank. Illinois State Geological Survey Circ., 493, Champaign, IL.

Unsworth, J. F., Fowler, C. S., and Jones, L. F., 1989, Moisture in coal, 2. Maceral effects on pore structure. Fuel, v. 68, no. 1, p. 18-26.

Wen, W.-W., 1977, Electrokinetic Behavior and Flotation of Oxidized Coal. Ph. D. Thesis, Pennsylvania State University, 326 p.

Wender, I., Heredy, L. A., Neuworth, M. B., and Dryden, I. G. C., 1981, Chemical reactions and constitution of coal. In: M. A. Elliot (ed.), Chemistry of Coal Utilization, Second Suppl. Vol., Wiley-Interscience, New York.

PROJECT MANAGEMENT REPORT
September 1 through November 30, 1991

**Project Title: Characterization of the Surface Properties of
Illinois Basin Coals**

Principal Investigator: İlham Demir, ISGS
Co-investigators : Richard D. Harvey, ISGS
Anthony A. Lizzio, ISGS

Project Monitor : Ken K. Ho, CRSC

COMMENTS

The purchase of some of the supplies was delayed. There was no travel expenditure for the first quarter. The "other direct cost" expenditure was significantly higher than projected due to commitment of all the general services fund at the beginning of the project. Supplemental forms and charts regarding expenditures and project milestones are attached.

This project is funded by the U. S. Department of Energy (PETC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

END

DATE
FILMED

4 / 01 / 92

I