10
1-9-92 JS①

ORNL/Sub/90-SF204/1

**OAK RIDGE
NATIONAL
LABORATORY**

MARTIN MARIETTA

**Corrosiveness of Wet Residential
Building Thermal Insulation—
Mechanisms and Evaluation
of Electrochemical Methods
for Assessing Corrosion
Behavior**

E. E. Stansbury

**MANAGED BY
MARTIN MARIETTA ENERGY SYSTEMS, INC.
FOR THE UNITED STATES
DEPARTMENT OF ENERGY**

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

**CORROSIVENESS OF WET RESIDENTIAL BUILDING THERMAL
INSULATION - MECHANISMS AND EVALUATION OF
ELECTROCHEMICAL METHODS FOR ASSESSING CORROSION BEHAVIOR**

E. E. Stansbury

**Part of
The National Program
for
Building Thermal Envelope Systems and Materials**

Date Published - October 1991

**Report prepared by
E. E. Stansbury
Consultant
5800 Woodburn Drive
Knoxville, Tennessee 37919**

for

**OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6092
managed by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
U.S. DEPARTMENT OF ENERGY
under Contract DE-AC05-84OR21400**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EB

CONTENTS

Chap. 1	Overview -----	1- 1
Chap. 2	Materials, Instrumentation and Procedures ----	2- 1
	Materials -----	2- 1
	Instrumentation -----	2- 1
	Materials Preparation -----	2- 5
	Procedure -----	2- 9
Chap. 3	Results of Electrochemical and Weight-loss ---	3- 1
	Measurements	
	Introduction -----	3- 1
	Properties of Environments -----	3- 2
	Corrosion Rates in Insulation environments ---	3- 5
	Corrosion Rates in Solutions of Cellulosic ---	3-18
	Insulation Additives	
Chap. 4	Electrochemical Polarization Measurements on -	4- 1
	Building Insulation Leachates and	
	Cellulosic Insulation Additives	
	Introduction -----	4- 1
	Polarization Curves for Low Carbon Steel in --	4- 5
	Insulation Leachates	
	Polarization Curves for Low Carbon Steel in --	4-10
	Solutions of Selected Additives to	
	Cellulosic Insulation	
Chap. 5	Conclusions and Recommendations -----	5- 1
References	-----	R- 1
Appendix A	Overview of Basis for Evaluating -----	A- 1
	Corrosion Behavior by Electrochemical	
	with Emphasis on Direct Reading Instruments	

FOREWORD

This is one of a series of reports to be published describing research, development, and demonstration activities in support of the National Program for Building Thermal Envelope Systems and Materials. The National Program involves several federal agencies and many other organizations in the public and private sectors who are addressing the national objective of decreasing energy wastes in the heating and cooling of buildings. Results described in this report are part of the National Program through delegation of management responsibilities for the DOE lead role to the Oak Ridge National Laboratory.

Jeffrey E. Christian
Program Manager
Building Thermal Envelope
Systems and Materials
Oak Ridge National Laboratory

M. P. Scofield
Program Manager
Building Systems and
Materials Division
Office of Buildings Energy Research
Department of Energy

CORROSIVENESS OF WET RESIDENTIAL BUILDING THERMAL INSULATION

-MECHANISMS AND EVALUATION OF ELECTROCHEMICAL METHODS

FOR ASSESSING CORROSION BEHAVIOR

ABSTRACT

An evaluation has been made of the corrosiveness of selected wet residential building thermal insulation materials in contact with low carbon steel. Investigations were conducted both in wet insulations and in filtered leachates from insulations derived from thirteen cellulosic, three mineral fiber and four foam products. Potentiodynamic polarization measurements are reported from which the overall corrosion response was assessed and then the techniques of Tafel and polarization resistance analysis applied to estimate corrosion rates. Corrosion rates were also estimated electrochemically using a direct reading instrument which performs the rate calculation based on the polarization resistance principle. Direct determinations of corrosion rate were based on weight loss measurements.

An objective of the research to develop a short time, quantitative electrochemical method to evaluate the corrosiveness of wet insulations of general applicability to all types was not accomplished. Corrosion in these environments is largely controlled by diffusion of dissolved oxygen through the wet insulation and corrosion products. The corrosion products were shown to vary in adherence and porosity requiring days to weeks to establish steady state corrosion. These factors contributed to poor correlation between rates determined electrochemically and by weight loss which precluded the possibility of developing a short time test.

The corrosion behavior was investigated, both electrochemically and by weight loss, in both leachates and wet insulations under different conditions of aeration. These studies led to a relatively simple but effective evaluation procedure in which 2 in x 2 in x 0.003 in specimens are supported vertically to a depth of 1.5 in in wet insulation for three weeks. Corrosion is enhanced at the metal-air-wet insulation interface where the severity of attack can be evaluated by a survey of change in thickness and in the limit by penetration of the sheet. A specimen in sterile cotton wet with distilled water is used for base comparison. The method shows promise for being applicable as a comparative evaluation of cellulosic, mineral fiber and foam insulations.

Research sponsored by the U.S. Department of Energy, Assistant Secretary for Conservation and Renewable Energy, Office of Buildings Energy Research, Building Systems and Materials Division, under contract DE-AC05-84OR21400 with Martin Marietta Energy Systems, Inc.

CORROSIVENESS OF WET RESIDENTIAL BUILDING THERMAL INSULATIONS
-MECHANISMS AND EVALUATION OF ELECTROCHEMICAL METHODS
FOR ASSESSING CORROSION BEHAVIOR

CHAPTER 1

BACKGROUND

Residential building thermal insulations are broadly classed as cellulosic, mineral fiber or foam types. Cellulosic insulations consist of disintegrated paper products, predominantly newspaper, to which selected additives have been made to meet performance standards. Mineral fiber insulations are largely fiber glass products and the foam insulations are organic polymer based products. These insulations contain materials, widely varying in amount and chemical composition, that are leachable on contact with water. As a consequence, wet insulations have the potential of causing damaging corrosion to contacted metals used in building construction. These include steel, copper and aluminum pipes, wiring, boxes and fasteners. The subject was covered at the Cellulose I Conference (1) in 1978 and an extensive review was reported in an Assessment of the Corrosiveness of Cellulosic Insulation Materials by Weil and Graviano in 1979 (2). The latter covered specifications, test methods, data and properties of cellulosic insulation related to its corrosiveness.

ASTM Standards contain sections relating to the test for the corrosiveness of wet insulations on contact with steel, copper and aluminum. ASTM C665 (3) pertains to Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured housing; ASTM C739 (4) pertains to Cellulosic Fiber (Wood-base) Loose-Fill Thermal Insulation; ASTM C764 (5) pertains to Mineral Fiber Loose-Fill Thermal Insulation. Briefly these ASTM

Standards specify exposure of small thin sheets of steel, copper and aluminum to the insulation under controlled humidity, temperature and time conditions. Severity of attack is judged based on surface appearance under C665 and by penetration of the sheet under C739. C951 (6), a now discontinued standard on Urea Formaldehyde-Based, Foamed in Place Insulation, required reporting a pitting factor based on visual inspection and a corrosion rate based on weight loss.

Questions have been raised concerning both the procedures for conducting the tests and the applicability of the tests. These include interpretation of the pass/fail criteria, maintenance of the test environment, time to conduct the test and limitations of inter-comparing potential corrosiveness of the three types of insulation because of differences in the standards.

These uncertainties led Weil, Sheppard and co-workers (7,8) to initiate development of electrochemical methods for evaluating the corrosiveness of insulations which would be applicable to a wide range of insulations and metallic materials that may be in contact. They point out that the major advantages of the method are ability to make an evaluation in a few hours rather than days to weeks and that information is obtained relating tendency to localized corrosion as well as average corrosion rate. They investigated several electrochemical techniques including alternative interpretations of the observations relative to corrosion behavior.

The initial proposals of Weil and co-workers (7,8) were reviewed by Stansbury in an "Overview of the Applicability of Electrochemical Methods to Evaluation of the Corrosiveness of Residential Building Thermal Insulations With Proposed Cooperative Test Program" (9). This document reviewed the principles of the several electrochemical techniques available for determining

corrosion behavior, discussed the probable variables and mechanisms controlling corrosion in wet insulations and proposed specific procedures to be investigated that would allow evaluation of the corrosiveness of the several types of insulation.

The following report covers an extensive investigation of the evaluation of several electrochemical methods for assessing the corrosiveness of insulations. Thirteen cellulosic, three mineral fiber and four foam insulations were included in the investigations. In addition, parallel investigations were conducted in saturated and partially saturated solutions of both chemically pure and commercially pure grades of several materials that may be present in cellulosic insulations. For base comparison to the electrochemical measurements, corrosion rates determined from weight-loss were calculated and visual observation made of the corrosive attack modes. The investigation was conducted almost exclusively using low carbon steel exposed to leachates from the insulations, exposed to wet insulation with both total and partial immersion of the metal, and exposed to solutions of the cellulosic insulation additives. The studies were made at room temperature, $75 \pm 5^\circ\text{F}$.

CHAPTER 2

MATERIALS, INSTRUMENTATION AND PROCEDURES

Materials

Insulating materials:

Information is included in this report on the following thermal insulating materials provided either directly or indirectly by several manufacturers or by random purchase from building materials suppliers.

Thirteen cellulosic fiber loose-fill thermal insulation

Three Mineral-fiber blanket thermal insulation

Four foam insulations

Additives:

The following materials representative of or related to additives to cellulosic insulation were included in the investigation.

Pure and commercial grades of borax

Pure and commercial grades of ammonium sulfate

Pure and commercial grades of aluminum sulfate

Pure and commercial grades of boric acid

Metals:

All corrosion measurements were performed on low carbon steel rods 0.125 in in diameter or as sheets either 0.021 in or 0.003 in thick.

Instrumentation

Electrochemical Instruments:

An objective of the present investigation has been evaluation of electrochemical instrumentation capable of providing information from which the corrosiveness of residential building thermal insulation could be assessed. A brief review of the processes involved in electrochemical

corrosion and the principles of the measurements methods are given in Appendix A. A more detailed discussion is presented in an earlier publication related to the present project (8). The present investigation has included types of measurements required to assess corrosiveness, ease of performing the measurements, instrument cost and conversion of the electrochemical information to corrosion performance. In the course of the investigation, three instruments have been used extensively.

Two commercial potentiostats were used to determine polarization curves from which the general corrosion behavior of the steel in any environment could be assessed and estimates made of the corrosion rates. The EG&G Model 273 instrument (Mfg. by EG&G Princeton Applied Research) allows operation under manual or computer control. The majority of measurements using the Model 273 were carried out with computer operation using software supplied with the instrument. The following measurements were made using the Model 273:

1. Corrosion potential as a function of time.
2. Potentiodynamic polarization within the range of -800 to +1400 mV relative to the standard hydrogen electrode (SHE) scale from which an estimate of the corrosion potential and corrosion current density could be made and indications of any tendency for transitions between active and passive behavior could be observed.
3. Cyclic polarization measurements to indicate tendency towards pitting corrosion by the presence of anodic loops on down scans.
4. Polarization measurements, usually ± 100 mV relative to the corrosion potential, from which corrosion rates were estimated by Tafel analysis.
5. Polarization measurements, usually ± 10 mV relative to the corrosion

potential from which corrosion rates were estimated by polarization resistance analysis.

The Model 273 allows storage of data from each measurement with subsequent recall to allow plotting of the polarization curves and calculation of the corrosion rates using computer algorithms based on analytical models of the corrosion process.

Another potentiostat, the BAS CV-27 Voltamograph (Mfg. by Bioanalytical Systems, Inc), was used extensively in the investigation. This instrument is basically designed for manual operation by which most of the measurements listed above may be made. A digital display allows setting a range of variables including potential scan limits and scan rates and following the potential and current for any of the modes of operation. Voltages proportional to the several operating variables are available for inputs to digital voltmeters, to plotters and to computer interfaces. In this investigation, polarization curves were recorded using a x-y plotter; data were also recorded, stored and displayed by computer. The software to perform these tasks was developed as part of the present investigation.

The major contribution of the EG&G Model 273 potentiostat was its versatility of operating over a wide range of variables with high precision and the extensive software allowing computer control of measurement techniques, data acquisition and calculations to yield information on corrosion behavior. Since the instrument is relatively expensive, the BAS CV-27 was investigated as an alternative. The two are representative of commercial instruments having their respective capabilities.

Estimation of corrosion rates using potentiostats requires measurement of the polarization curve in the vicinity of the corrosion potential and

subsequent analysis of these data to yield corrosion rates. The only way to satisfactorily accomplish the data conversion is to use computer algorithms either directly associated with software operating the potentiostat or by computer processing the manually acquired data as a subsequent step. These alternatives were briefly referred to above and are discussed in detail in Reference 8. Thus it is only necessary to determine the polarization curves near the corrosion potential in order to estimate the corrosion rate.

Instruments are commercially available which effectively measure the polarization behavior near the corrosion potential, internally convert the measurement to a corrosion current density and subsequently present the results on a digital display as corrosion rate in mils per year (mpy). These are "direct corrosion rate measuring instruments" requiring only the self contained instrument and a probe of the metal whose rate is being determined on insertion into the corrosive environment.

The direct reading instrument used in the present investigation was the Corratel 9030 (Mfg. by Rohrback Cosasco Systems). Corrosion rate ranges are selectable as 0-1, 0-10, 0-100 and 0-1000 mpy(mils per year). Other variables are selectable including the time interval over which the measurement is made and an alternative mode may be selected which indicates tendency toward localized corrosion rather than uniform corrosion which is assumed on displaying a corrosion rate. The value of the digital display is also available as a 0-10 volt signal which can be passed to a recorder or computer to display corrosion rate as a function of time. The probe for the Corratel consists of a pair of "identical" cylindrical specimens or electrodes of the metal of interest inserted into the environment under investigation. In comparison, use of the potentiostat requires a container with the environment

into which a specimen, a reference electrode and a counter electrode must be inserted.

Because of the simplicity of the direct reading instrument, its potential for evaluating corrosiveness of insulations became a significant factor in the latter stages of this investigation. In particular, comparisons of corrosion rates indicated by the several instruments have been made and these rates compared with those determined by weight loss measurements.

Materials Preparation

Preparation of insulations for testing:

A major concern in developing an electrochemical method for evaluating corrosiveness of residential building insulations is establishing environments into which metal test probes can be placed which are reasonably representative of wet insulations in contact with metals in service situations. At points of contact of moist insulation with a metal surface, the water is undoubtedly saturated with respect to soluble species. Away from these points, and depending on the amount of water, the concentration decreases. Particularly high concentrations of soluble species can be expected with cellulosic insulations which may contain 15-25% additives; mineral fibers and foams contain relatively small amounts of leachable material.

Since electrochemical measurements require a continuous path of electrolyte between the three elements of the potentiostat cell or dual specimens of the direct reading instrument, sufficient water must be added to an insulation and contact time maintained to dissolve potentially corrosive species from the insulation and to provide continuity of solution between electrodes. The extent to which reliable measurements can be made directly in the wet insulation or must be made in the leachate obtained by filtering has

been a part of the investigation. In either case, a concern is the concentration of leachable species in the solution; specifically, how representative is it of conditions in wet insulations in service.

Most of the measurements in the present investigations have been conducted in leachates obtained by filtering insulations to which one liter of distilled water has been added per 100 grams of insulation. For cellulosic insulations, about 0.7 L of leachate is recovered indicating a retention of about 0.3 L of water in the cellulose. The retention is much less for mineral fiber and foam insulations. Leaching time has been a variable and concentrations have been increased by evaporation. With cellulosic insulations, evaporation to 10-20% of the initial volume results in separation of appreciable solid material indicating that the resulting solution is saturated with one or more of the additives. It is evident therefore that making corrosion measurements in filtered, but unconcentrated, leachates corresponds to exposure to environments that may be much lower in concentration of corrosive species than exists in wet insulations. Some investigations of the influence of the concentration were made.

Foam leachates were prepared by breaking or cutting the foam into 1-2 cm pieces and disintegrating in a blender mixing 30 grams of foam with 0.3 L of distilled water. The foam/leachate mixture was filtered after three days of contact.

The pH and specific resistivity of all leachates were determined.

Preparation of solutions of additives to cellulosic insulations:

Measurements were conducted in saturated and 5% saturated solutions of pure and commercial grades of selected additives that may be made to cellulosic insulations. All solutions were prepared with distilled water and

the measurements made at $75 \pm 5^\circ\text{F}$. Approximate amounts of each material to result in small undissolved amounts of solid are listed in Table 2-1.

TABLE 2-1
CELLULOSIC INSULATION ADDITIVES INVESTIGATED

MATERIAL	CHEMICAL FORMULA	SOLUBILITY* g/100 mL
CP Borax	$\text{Na}_2\text{B}_4\text{O}_7 \cdot \text{H}_2\text{O}$	10
Comm. Borax		10
CP Ammonium Sulfate	$(\text{NH}_4)_2\text{SO}_4$	80
Comm1. Ammonium Sulfate		80
Comm2. Ammonium Sulfate		80
CP Aluminum Sulfate	$\text{Al}_2(\text{SO}_4)_3$	80
Comm. Aluminum Sulfate		80
CP Boric Acid	H_3BO_3	8
CP Calcium Sulfate	$\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$	0.2

*These amounts produce small excess of undissolved solid

CP = Chemically Pure Grade
Comm. = Commercially Pure Grade

Preparation of metal test specimens:

Potentiostatic polarization measurements were made on 0.125 in diameter low carbon cold rolled steel rod. A nine-inch length of rod was cleaned and several centimeters along one end and the end cross-section polished with 600 grit paper while rotating the rod. An approximately one-inch length of dual-wall heat shrinkable polyolefin tubing is slipped over the end of a six-inch length of 5 mm OD glass tubing and these slipped over the polished steel rod.

Approximately one cm length of the steel rod is exposed beyond the heat shrinkable tubing and the latter adjusted to cover equally the steel rod and tubing. The assembly was placed in an oven at 300 F for about 15 minutes to allow the inner wall of the tubing to melt and the outer wall to shrink making a tight bond to the glass and steel rod. The exposed rod was again polished with 600 grit paper and cleaned briefly with a paper tissue containing acetone just prior to measurement. After each potentiostatic measurement, the sample was carefully examined for the extent of uniform versus localized attack and particularly for crevice attack at the polyolefin/steel interface.

Specimens used with the direct reading corrosion rate instrument, the Corratrater 9030, were standard carbon steel (1010) specimens available from the manufacturer of the instrument. The specimens are 0.213 in in diameter and have an effective length of 1.16 in to provide an area of 5 cm². Just prior to measurement, the specimens were polished with 600 grit paper while rotating and wiped with dry laboratory tissue and then with tissue containing acetone. After cleaning the specimens were handled with polyethylene gloves and attached to a support probe for immersion in the test environment.

Specimens for weight-loss tests were cut from 0.021 in thick low carbon cold rolled sheet as two inch squares. A 0.25 inch hole was drilled near one corner to allow suspension in the environment from glass rod hooks. All burrs were removed from the cut and drilled edges of specimen. The sample was cleaned by abrading with 600 grit paper moistened with 5% hydrochloric acid followed rinsing with hot water. A uniform adherent layer of water on the specimen was taken as an indication of adequate cleaning. The hot specimen was immediately dried with a laboratory paper tissue and weighed to the nearest tenth milligram. The specimen was handled with polyethylene gloves at all

stages following cleaning.

Partial immersion specimens

Because of the frequent influence of dissolved oxygen in controlling the rate of corrosion, a test procedure was developed in which 2 in square specimens were immersed to a depth of 1.5 in in wet insulation, held for three weeks, cleaned and examined for preferential attack along the metal-air-wet insulation interface. These specimens were 0.003 in thick to evaluate complete penetration as a criterion of failure. Specimens that were not penetrated were surveyed for changes in thickness using ball-tipped micrometers.

Procedure

Potentiostatic polarization measurements

Polarization measurements were conducted in a cell consisting of a 400 mL beaker and rubber stopper drilled to allow entry of diametrically opposite graphite counter electrodes, a center hole for the specimen and a hole for the reference electrode. Additional holes provided access for air, a sparging tube for investigating effects of aeration and deaeration and for a thermometer if required.

The computer controlled Model 273 EG&G potentiostat was used for the following types of measurements:

Corrosion potential as a function time. This mode permitted observation of the stability of the corrosion potential. The criterion for stability was a change of less than one mV per minute which was generally observed to exist within one hour.

Single or cyclic polarization scans. In these modes, scans were usually started about 100 mV negative to the corrosion potential and continued to 1200 mV(SHE). Scan rates were usually 0.2 or 0.3 mV/s.

The resulting polarization curves provided information on the overall dissolution behavior of an environment. In particular, the tendency for the environment to passivate the steel specimen and, from cyclic scans, the tendency to form an anodic loop on down-scan as an indication of localized pitting attack. By extrapolating the anodic and cathodic branches of the polarization curves until they cross at the corrosion potential allowed rough estimations of the corrosion current and hence corrosion rate.

Polarization resistance scans. Corrosion rates were estimated using the polarization resistance mode of the EG&G potentiostat by either a separate scan of ± 10 mV through the corrosion potential or by applying the polarization resistance analysis to this potential range of the data obtained from the single or cyclic polarization scans. The limitation of the latter is that the steady state corrosion processes are progressively upset as scans are initiated over larger potential ranges. Hence more reliable values result by restricting the scan to ± 10 mV. The EG&G system includes software to perform the polarization resistance analysis and report a corrosion rate. The method is discussed in Appendix A.

Tafel analysis scans. In this mode, either a separate scan is made of ± 100 -200 mV through the corrosion potential or data over the selected range is taken from the broad potential range scans. The basis for estimating corrosion rates from the polarization curves near the corrosion potential is discussed briefly in Appendix A and in greater detail in Reference (8). Simple analytical models of the

corrosion process show that the shape of the polarization curve, i.e. the potential/current density values, near the corrosion potential is a function of the corrosion potential, corrosion current density and the Tafel slopes of the linear polarization curves of the individual anodic and cathodic reactions. Although the corrosion potential can be determined from the experimental polarization curve, it is generally difficult to determine the slopes for the individual reactions from the curves. The most significant parameter desired is the corrosion current density from which the corrosion rate is calculated. Computer algorithms are used to apply non-linear regression analysis to determine values for the parameters which give best fit of a curve derived from the analysis with the experimental one. The corrosion current density and rate are thereby determined.

Most of the corrosion rates based on Tafel analysis given in this report were determined from data taken from broad potential range potentiostat scans. Since these scans were usually initiated about 100 mV negative to the corrosion potential, the data met the requirements for the method.

The manually operated BAS potentiostat was investigated as an alternative to conducting the procedures described above.

It was used to determine the corrosion potential as function of time, single and cyclic polarization curves over broad ranges of potential and narrow potential scans for Tafel analysis. The procedures described above for the EG&G instrument were generally applicable to the BAS. The data were recorded either manually from

digital displays or by plotting on an analog x-y plotter using the analog voltages supplied by the instrument proportional to the measured quantities. Software programs for a personal computer were written to perform the Tafel analysis to give corrosion rates. Data acquisition programs were also written to interface the BAS to the computer. The latter programs permitted graphical display of the polarization curves and generated data files for use in the Tafel analysis.

In the course of the investigation, the feasibility of using the BAS potentiostat to meet the objectives of the project became questionable. Several observations supported this conclusion.

First, Operation of the BAS is much more demanding of the user with respect to both procedures and analysis of the data. Considerable insight into the functions performed by the instrument and the relationship of the potentiostat to the cell, its components and understanding the electrochemical principles involved in the corrosion process is required. Further, in the absence of computer interfacing, data must be manually transferred to a personal computer to perform the calculations. The availability of a personal computer to perform the calculations is essential.

A second observation early in the investigation indicated that probably none of the environments, solutions of cellulose insulation additives or insulation leachates, would result in anodic loops indicative of classical pitting corrosion due to break down of passive films. Rather, the broad potential potentiostat scans indicated that the corrosion was occurring in the active potential

range and that non-pitting corrosion was occurring locally although unevenly due to irregular contact of insulation with a metal surface. As a consequence, although providing basic insight into the electrochemical interaction between steel and the environments, determination of full potential range scans were not considered essential to developing an electrochemical method for evaluating the corrosiveness of building insulation materials.

A third observation was that the corrosion rates calculated using the polarization resistance method with the EG&G instrument were in closer agreement with initial weight loss corrosion rate determinations. Although the BAS potentiostat produced satisfactory data for polarization resistance and Tafel analysis, estimations of corrosion rates from the data could not be carried out conveniently as indicated above.

Direct reading corrosion rate instruments - the Corrater

As a consequence of the above experience, attention was turned to investigating the applicability of the more simple direct reading corrosion rate instruments based on the polarization resistance method of measuring corrosion rates. The relatively new Corrater 9030 was used for this purpose. Following are brief comments on the operation of this instrument. The relationship between the procedure followed by the Corrater in determining corrosion rates and the conventional polarization resistance method is covered briefly in Appendix A.

The Corrater probe is a polymeric rod approximately 0.75 in in diameter with two threaded studs 0.375 in apart at one end onto which a pair of specimens, prepared as previously described, are screwed tight against "O-

ring" seals. A cable is attached to the other end of the probe and the instrument box. As described in Appendix A, the instrument follows five steps at a preselected cycle rate which includes applying a potential difference (ΔE) of 20 mV between the specimens and measuring the current (ΔI) that is passed. The quantity, $\Delta E/\Delta I$, is referred to as the polarization resistance which, under assumptions relating to the mechanism of corrosion, is directly related to the corrosion rate. This rate is displayed digitally with selectable ranges of 0-1, 0-10, 0-100, 0-1000 mpy (mils per year).

Low carbon steel specimens were prepared as previously described, immediately attached to the probe and inserted in the test environment. The indicated corrosion rates were recorded manually or by a strip-chart recorder responding to a 0-10 V output for any of the full scale ranges. For purposes of the ASTM Round Robin test program, rates were reported for 1, 24, and 48 hours exposure.

Corrosion rates from weight loss measurements

The 2 in x 2 in x 0.021 in low carbon steel specimens cleaned as previously described were suspended in 800 mL of insulation leachate or solutions of the additives representative of those used in cellulosic insulation. Most specimens were immersed for two weeks, cleaned and reweighed. Some weight loss measurements were conducted on specimens in wet insulation. Two other variables studied were time of exposure to determine if there was a decrease in corrosion rate with time due to buildup of corrosion products and the availability of oxygen by varying the degree of aeration during immersion.

Chapter 3

RESULTS OF ELECTROCHEMICAL AND WEIGHT LOSS MEASUREMENTS

Introduction

Corrosion rate measurements are reported for low carbon steel determined at 75 ± 5 F (room temperature). Leachates were prepared from thirteen sources of cellulosic insulation, three mineral fiber insulations and four foam insulations. Environments based on these sources were characterized in terms of pH and specific conductivity. After many of the measurements, the pH and specific conductivity were again determined. The chemically pure (CP) and commercial grades of additives that may be used in the manufacture of cellulosic insulations were listed in Table 2-1. Test solutions of these materials were either saturated solutions or dilutions to 5% saturation.

The results are presented in sections covering:

- (1) The properties of the insulation leachates, and the saturated and 5% saturated solutions of cellulosic insulation additives,
- (2) Corrosion rates of low carbon steel in the leachates as determined
 - (a) from polarization measurements using a potentiostat,
 - (b) from the Corrater corrosion rate instrument and
 - (c) from weight loss measurements,
- (3) Polarization measurements to provide information on the general corrosion behavior of the environments,
- (4) Effects of partial immersion in wet insulation due to localized corrosion at the metal-air-wet insulation interface,
- (5) Supplementary measurements to support explanations of the results.

Properties of Environments

Properties of insulation leachates

The pH and specific resistivities in ohm-cm of all insulation leachates investigated are listed in Table 3-1. Within the thirteen cellulosic insulation leachates, the pH ranged from 4.4 to 8.2 and the specific resistivities from 49.4 to 255 ohm-cm.

The pH of the mineral fiber (fiber glass) insulation leachates was more alkaline than the cellulosic insulations being 9.1, 9.24 and 9.62 for the three sources of insulation investigated. The specific resistivities of the three leachates were 2300, 1672 and 896 ohm-cm.

The pH of the four foam insulations was in the range 5.58 to 7.48 and the specific resistivities varied from 5370 to 13,160 ohm-cm.

Properties of solutions of cellulosic insulation additives

The pH and specific resistivities of saturated and 5% saturated solutions of five chemicals reported as possible additives to cellulosic insulations are listed in Table 3-2. The solubilities are included in the table for partial correlation with the properties. The solubilities of the ammonium sulfate and aluminum sulfate are very high and these salts hydrolyze to give acid environments, aluminum sulfate near pH = 3 and ammonium sulfate near pH = 5. Their degree of ionization however differs significantly in that the specific resistivity of the ammonium sulfate solutions is much lower. The other salts have much lower

solubilities which is a factor in the higher specific resistivity of their solutions. The borax solutions are the only ones with pH > 9.

Comments on properties of environments

In general, the specific chemical additives that had been used in the production of the cellulosic insulations investigated were not known for this study. The additives probably included one or more of the ones investigated in the present project. Materials other than those in Table 3-2 are known to be used, some of which are essentially proprietary. To meet fire retardation and other requirements of the standards, the amount of the additives ranges from 15-25% of the cellulosic insulation. Of significance to the present investigation is the concentration of soluble species from these additives resulting from leaching of wet insulation. The leachate is potentially responsible for increasing the corrosiveness of the wet insulation above that associated with the source of water. Within the wet insulation, the leachate concentration can range from saturation when the amount of water is small to some variable fraction of saturation with larger amounts of water. The leachates for the investigation were prepared, with some exceptions to be noted, by contacting 100 grams of insulation with 1000 mL of distilled water for three days followed by filtering. Consistently, 700 mL of leachate is recovered indicating a holdup of 300 mL of water in the cellulose. Assuming an average of 20% additives in the insulation and that these are dissolved in the 1000 mL of distilled water,

the leachate should contain about 2% additives. Therefore, the corrosiveness studies in the saturated and 5% saturated solutions of individual additives, were conducted in solutions considerably more concentrated than the leachates. This significant difference in concentrations led to investigations of corrosiveness directly in wet insulations and in leachates concentrated by evaporation. Results of the effects of these variables will be discussed subsequently. It should be noted again however that in damp insulation, the liquid in contact with a metal may be essentially saturated with leachable additives.

Most of the cellulosic insulation leachates had pH values in the range of 5.5 to 7.5 and specific resistivities from 50 to 120 ohm-cm. These values are consistent with the presence of additives such as ammonium sulfate and borax which, while individually hydrolyzing to acid and alkaline solutions respectfully, produce solutions generally in the range of pH = 6.5-7.5.

The relatively high specific resistivities of the mineral fiber and foam insulation leachates are consistent with the small concentrations of leachable species in these products. The pH > 9 for the mineral fiber leachates is expected from a glass-based material.

Corrosion Rates in Insulation Leachates

Estimates of corrosion rates were made on low carbon steel in cellulosic, mineral fiber and foam insulation leachates by (1) analysis of polarization data obtained from potential scans using a potentiostat, (2) using a direct reading corrosion rate meter (Corrater 9030 by Rohrbach Cosasco Systems) and (3) determination of weight loss. The procedures for specimen and leachate preparation and for determination of the corrosion rates were presented in Chapter 2. The basis for estimating corrosion rates from electrochemical measurements is reviewed in Appendix A. Particularly relevant to the results presented are the analytical procedures for estimating corrosion rates by Tafel analysis and by polarization resistance analysis of polarization data. The analyses were performed by the Model 342 SOFTCORR Corrosion Measurement Software using polarization measurements obtained with a Model 273 Potentiostat/Galvanostat, both from EG&G Princeton Applied Research.

The results of the corrosion rate measurements on low carbon steel in the insulation leachates are summarized in Table 3-3. Blank entries in the table indicate that the measurement was not made in the indicated environment. Table 3-4 shows results of some of the supplementary measurements that were made to provide information in support of understanding the variables that might be contributing to the corrosion processes. Included are effects of placing the steel specimens directly into wet insulation, effects of aeration, effects of leachate concentration, and

effects of exposure time. Data are also included for exposure to domestic and distilled water. Further modifications of these environmental variables will be discussed in following sections.

Discussion of estimation of corrosion rates in insulation leachates from potentiostat measurements.

Corrosion rates based on potentiostat measurements and subsequently calculated by Tafel analysis are generally larger than those calculated by polarization resistance analysis. Reference to Table 3-3 indicates that the magnitude of the difference is not consistent and in some environments the relative values are reversed. The disagreement is attributed to both the applicability and differences of the models of the corrosion process used in converting the potentiostat data to corrosion rates. It is also attributed to the difference in the potential range about E_{corr} over which the data are taken; for the polarization resistance analysis measurements are made within ± 20 mV of E_{corr} and for the Tafel analysis within ± 100 mV of E_{corr} . Thus an advantage of the polarization resistance analysis is that the corroding interface is disturbed less.

The corrosion mechanism models used in the derivation of the mathematical expressions for both the Tafel and polarization resistance analyses assume that rates of diffusion of species to or from the corroding interface are not controlling the corrosion rate. Rather, the assumption is made that charge transfer (electrons and ions) at the immediate interface controls the corrosion rate. Under these conditions, the polarization curve, E vs $\log i$, is linear. Diffusion control causes deviation from

linearity which, as will be shown subsequently, was observed in the polarization behavior of the systems investigated. When diffusion is a rate controlling factor, calculations of corrosion rates based on the models become poor approximations. In fact, satisfactory algorithms for computation of corrosion rates for corroding systems with partial diffusion control have not been developed. In the course of the present investigation it was demonstrated that diffusion of oxygen (air) is a major variable and therefore quantitatively useful values of the corrosion rates calculated by the algorithms should not be expected. Since in the pH range of the insulation leachates (4.5-9.5) corrosion product layers consisting of oxides and hydroxides form, the rate of diffusion of oxygen through these layers becomes the significant variable. This rate of diffusion further depends on the specific chemical environment since the structure and properties of the film depend on the type and concentrations of other species in solution as the corrosion product films form.

A qualitative investigation of the influence of the environment on corrosion product formation was performed by immersing 2 in x 2 in steel specimens horizontally on supports in 5 cm deep x 10 cm diameter dishes. The specimens were observed during a two-week period. The corrosion products varied from dark, thin and adherent suggesting passive film formation to flocculent deposits varying in color from red to yellow. No attempt was made to identify the corrosion products. They are undoubtedly hydrated iron oxides whose color and physical

characteristics are determined by incorporation of ions from the environment. It is evident that the differences in adherence and porosity of the corrosion products can have a major and variable influence on the rate of diffusion of oxygen to the corroding interface and hence on the corrosion rate.

Discussion of estimations of corrosion rates in insulation leachates using the Corrater.

Corrosion rates determined with the Corrater decreased with time of exposure. Steady values were usually observed within 48 hours but in some cases the rate continued to decrease slowly for as long as 100 hours. Values are reported in Table 3-3 for 1 and 48 hours. With all insulation leachates, the carbon steel dual Corrater specimens developed a corrosion product film which ranged from thin and very adherent to thick, flocculent and non-adherent.

As discussed in Chapter 2 and in Appendix A, The Corrater operates on the principle of making a polarization resistance measurement from which the corrosion rate is calculated and displayed digitally in mils per year (may). The method involves exposing two specimens, prepared as identically as possible, in the test environment and applying a potential difference of +20 mV and then -20 mV between them. The current is averaged for the two applied potential differences and from the current density-potential difference values, the polarization resistance is calculated. The corrosion rate is directly related to the latter. Therefore, the principle of estimating corrosion rates using the Corrater is the same as that of performing the polarization

analysis on data obtained from a potentiostat. As a consequence, the validity of rates displayed by the Corrater are also limited when corrosion is being influenced by corrosion product formation and the associated effect of diffusion of oxygen to the metal surface.

The corrosion rates based on Corrater data taken at one hour exposure and rates calculated by polarization resistance analysis of potentiostat data (also taken at one hour) are in general agreement. Values determined by the two methods are plotted in Figure 3-1. Linear regression analysis gives a slope 0.9. Reasonable agreement should be expected, as noted above, since the principle upon which the Corrater determines the corrosion rate is a variation of the polarization resistance analysis. (See Appendix A)

Comparison of values in Tables 3-1 and 3-3 indicates that corrosion rates estimated by the Corrater show little correlation with the pH of the insulation leachates. The exceptions are for Source 12 and 13 leachates which have the highest pH. The mineral fiber leachates also have low corrosion rates based on the Corrater measurements and these leachates have higher pH.

Investigation of several variables influencing corrosion rates measured with the Corrater.

A number of investigations were conducted to substantiate that the corrosiveness of insulation leachates to steel was dependent on time and was sensitive to availability of dissolved oxygen in the leachate. Several of these investigations using the Corrater are discussed. Effects related to corrosion rates based

on weight loss are discussed subsequently.

A series of measurements was made by immersing the Corrater specimens directly in the leachate created within wet insulation rather than in the filtered leachate. Dual objectives were to observe if the measurement could be made in the presence of insulation and to determine if immersion would restrict the access of air and thereby reduce the rate. Representative results of these measurements are given in Table 3-4. Satisfactory Corrater measurements could be made in wet insulation but were observed to decrease rapidly with time. Reference to Table 3-3 indicates that the Corrater corrosion rate for Source 1 Cellulosic leachate was 6.4 may at one hour and 3.2 in 48 hours. In contrast, with probes inserted directly into the wet insulation, the rate was 2.9 may in one hour and 0.2 may in 48 hours. A similar effect of immersion in the wet insulation is indicated for Source 2 cellulosic insulation. It is also pointed out that the corrosion rate of the wet Source 2 insulation is greater in both environments.

To investigate the effect of amount of water in the insulation, 400 mL rather than 1000 mL of water was added to the 100 grams of insulation. This smaller amount of water was still sufficient to allow a continuous aqueous solution between the Corrater specimens and result in a satisfactory reading. It was essential however to carefully pack the wet insulation as uniformly as possible about the Corrater dual specimens since acceptable operation of this instrument depends on the corrosion

of the two specimens being as identical as possible. The extent to which this condition exists can be established by switching the Corratrater in a mode that indicates the amount of imbalance in the corrosion rate of the dual specimens. In these measurements, this imbalance was acceptably small. The corrosion rates with the smaller amount of water are slightly larger which would be consistent with a more concentrated local leachate. The lower corrosion rate with direct immersion into the wet insulation is attributed largely to restricted access of oxygen to support the corrosion. An additional contributing factor is the confinement of corrosion products and possible local increase in pH associated with the corrosion reactions.

The effect of degree of aeration was further demonstrated by sparging air through the Source 2 cellulosic insulation during the Corratrater measurement. After one hour exposure under air sparging, the indicated rate was 22 mpy; without sparging the rate was 10 mpy. Degree of aeration also had a major effect on the corrosion rate in Source 1 mineral fiber leachate. After 20 hours with a nitrogen sparge, the indicated corrosion rate was 0.6 mpy. On air sparging, the rate increased within a few minutes to 32 mpy and decayed to 25 mpy in 5 hours. Alternate air and nitrogen sparging caused reversals in rate comparable to these values.

The effect of concentration of the leachate on the corrosion rate indicated by the Corratrater was briefly investigated by concentrating the Source 1 cellulosic leachate initially prepared

with 100 g of insulation per 1000 Ml water to 20% of its initial volume by evaporation at room temperature. After evaporation, solids had precipitated which changes the relative concentrations of dissolved additives in solution. Reference to Tables 3-3 and 3-4 shows that the indicated rate in the concentrated leachate was 9.2 mpy after 48 hours exposure; the rate in the unconcentrated leachate was 3.2 mpy. Thus, concentrating the leachate until saturated in some of the additives increased the corrosion rate of the low carbon steel by a factor of three.

For comparative purposes, the corrosion rate in Knoxville, TN, domestic water was determined with the Corratrater (Table 3-4). After 48 hours under stagnant conditions, the rate was 3.4 mpy. When the specimens were packed in wet sterile cotton at a depth of 2 in, the rate was 1.3 mpy at 48 hours but decreased to a steady value of 0.2 mpy by 120 hours. Again, as with packing the Corratrater probe in wet insulation, packing in wet cotton significantly decreased the corrosion rate due to exclusion of air. Also confinement of corrosion products and possible local increase in pH may be an additional factor decreasing the rate. It is noted that the corrosion rates in the domestic water are comparable to those for the insulation leachates and that the effect of confinement in water-soaked cotton is similar to that of confinement in leachate soaked insulation.

Determination of corrosion rates for insulation leachates using weight loss measurements.

Corrosion rates determined by weight loss in leachates from four cellulosic and three mineral fiber leachates are also listed

in Table 3-3. Rates are based on 4-6 samples in an environment except for the Source 1 cellulosic insulation leachate for which a large number of determinations was made.

Considerable difficulty was encountered in obtaining reproducible weight loss data for any specific environment, particularly when the corrosion rates were less than one mpy. Poor reproducibility was finally attributed to the sensitivity of the initiation of the corrosion process to subtle initial conditions of the surface. It was concluded that the initial, carefully cleaned surface was subject to formation of air-formed films that were inconsistent in allowing initiation and spreading of corrosion products. The weight losses for the 2 in x 2 in x 0.021 in steel specimens suspended for two weeks in 700 ml of the test environment were sufficiently large relative to the accuracy of the measurement (± 0.0001 g) to eliminate weighing as a significant variable. Further, it was demonstrated that an error in the corrosion rate attributable to the cleaning in inhibited 5% hydrochloric acid was less than 0.01 mpy. Since availability of oxygen had been demonstrated as a variable in the electrochemical tests, concern that depletion of oxygen in the containers due to corrosion was eliminated by monitoring the oxygen concentration which showed that it did not decrease during exposure.

Results of several supplementary determinations of corrosion rate by weight loss are included in Table 3-4. The rate in the concentrated Source 1 cellulosic insulation leachate was 7.4 mpy

compared with 0.45 mpy in the dilute leachate. To what extent this difference is due only to the change in absolute concentration of additives or due to a relative change in composition caused by preferential precipitation of one or more of the additive from solution was not established.

To further confirm the influence of dissolved oxygen on the corrosion rate, weight loss measurements were made on the low carbon steel in distilled water. Three conditions are shown in Table 3-4; stagnant, air sparged (aerated) and nitrogen sparged (deaerated). The rate is extremely low under highly deaerated conditions and is increased by large factors when oxygen is made available under stagnant and the air-sparged conditions. A small, but probably insignificant, increase in corrosion rate is noted in stagnant domestic as compared to distilled water.

Reference to Tables 3-3, 3-4 and 3-5 indicate no consistent relationship between pH and the corrosion rate. Among the cellulose insulation leachates, those based on Sources 12 and 13 showed significantly lower corrosion rates based on the Corratel measurements after 48 hours. These also had the highest pH. Further, with one exception, the mineral fiber leachates which have pH > 9 exhibited low corrosion rates when measured with the Corratel but not particularly lower by weight loss.

Another observation based on the data in Tables 3-3, 3-4 and 3-5 is that most of the cellulosic insulation leachates exhibit corrosion rates comparable to that for the carbon steel in distilled or domestic water. In a many cases, the rates are lower

in the leachates indicating that one or more leachable additives in the insulation has a mild inhibiting effect on corrosiveness.

Correlation of corrosion rates of insulation leachates determined by weight loss with rates determined electrochemically.

The correlation between the corrosion rates determined by weight loss and by either the Corrater or potentiostat is poor and inconsistent. The latter are larger by a factor of 4 to 12 greater than rates determined by weight loss. There is some indication that the relative values are reversed for the mineral fiber insulations, the weight loss values tending to be larger. Two major reasons for this difference are suggested. First, it has been shown that a major variable controlling the corrosion rate is availability of oxygen to the corroding interface by diffusion. As discussed previously, and in Appendix A, when diffusion is a significant factor in the corrosion mechanism, the model used by the Corrater to calculate the corrosion rate is inadequate resulting in incorrectly high values. Second, corrosion rates based on the Corrater were usually reported for 1, 24, and 48 hours which biased the data toward short time values. In contrast, the weight loss measurements were based on exposure for two weeks and, with the rate decreasing with time, the calculated results were biased toward the longer time values. For example, reference to Tables 3-3 and 3-4 indicates that for Source 1 cellulosic leachate, the weight loss corrosion rate in 48 hours is 1.5 mpy and the Corrater indicated rate is 3.2 mpy at the same time. However, the weight loss value averaged over two weeks is the much smaller value, 0.45 mpy. Thus better agreement

between corrosion rates determined by the Corratel and by weight loss would be expected if the former were extended to the longer time of two weeks.

The above observations force the conclusion that the environments of the cellulosic insulation leachates result in corrosion products that require several weeks to establish a steady state rate. As a consequence, short-time (< 48 hours) electrochemical measurements cannot result in values for corrosion rates representative of rates over extended periods of time. Rather, the estimated rates based on electrochemical measurements will be too high and this is to be expected regardless of the specific environmental conditions, including the degree of aeration.

Partial immersion to investigate enhanced corrosion at metal-air-wet insulation interfaces.

To further show the effects of aeration, 2 in x 2 in x 0.003 in steel specimens were positioned vertically in crystallizing dishes (15 cm dia., 10 cm deep) and wet insulation packed around the specimens such that one-half was immersed. This provided a metal-air-wet insulation interface not unlike that which would be encountered if insulation were to become wet in a structure. The specimens remained in contact for three weeks with small amounts of distilled water added to compensate for evaporation. After exposure, the specimens were cleaned and measurements made of the thickness using ball tipped micrometers. Minimum thickness was always observed within 1/4 in of the metal-air-wet insulation interface. In two cases, the 0.003 in thick

specimen had been penetrated near the interface. These corrosion rates are listed in Table 3-5 along with rates based on total immersion in filtered leachate.

As expected, maximum attack was at the interface and decreased rapidly with depth into the insulation. At the bottom of the vertical specimen (1.5 in immersion), only a slight discoloration had occurred indicating a low corrosion rate. To further confirm that corrosion rates were low with total immersion of the steel specimen within wet insulation, a specimen was placed in wet Source 1 cellulosic insulation near the bottom of a 800 mL beaker and covered with three inches of insulation. On removal after a two week exposure, the sample was slightly discolored and weight loss measurements indicated a corrosion rate of about 0.1 mpy. This corrosion rate is comparable to the value observed for nitrogen sparged distilled water (Table 3-4) and demonstrates that immersion in wet insulation can produce conditions that are very effective in excluding air.

The data in Table 3-5 indicates no systematic correlation between pH and corrosion rate over the pH range other than that complete penetration occurred for the lowest and one of the high pH environments. There is indication that penetration in the high pH environment is associated with the tendency for these environments to passivate the low carbon steel. These passivated surfaces resist corrosion but are susceptible to localized corrosion when the passive film cannot be maintained. The appearance of the surface of the specimen exposed to the wet

Source 3 mineral fiber insulation indicated that these factors contributed to the observed failure by penetration.

Corrosion Rates in Solutions of Cellulosic Insulation Additives

A summary of corrosion rates of low carbon steel in saturated and 5% saturated solutions of selected chemicals used in the production of cellulosic insulation is given in Table 3-6. The corrosion rates were determined by the same methods described previously for estimating corrosion rates for insulation leachates. The potentiostat was used to obtain polarization curves from which corrosion rates were estimated using Tafel and polarization analysis methods. The Corrater also determines rates based on a modification of the polarization resistance method but reports a single value on a digital display. Direct determination of corrosion rates was made by weight loss measurements. The pH and specific resistivity in ohm-cm of the environments were listed in Table 3.2

Discussion of estimation of corrosion rates in cellulosic insulation additives from potentiostat and Corrater measurements.

The low carbon steel was passivated by all four borax environments and, in the passive state, the corrosion rates were less than 0.1 mpy. Borax solutions, both due to the relatively high pH (≈ 9) and the tetraborate ion, are known to be effective inhibitors of the corrosion of steel. The specimens retained their bright as-polished appearance throughout the measurements.

The corrosion rates in the borax environments were very small (<0.1 mpy) when determined by applying both the Tafel and polarization resistance analysis to data obtained with the

potentiostat. The corrosion rates indicated by the Corratel were also small being 0.1-0.2 mpy, the solutions based on commercial grade borax being slightly higher. An exception was an increase in the rate for the low carbon steel in the 5% saturated solution of commercial grade borax. The rate which was 0.2 mpy at one hour exposure had increased to 0.7 mpy at 48 hours and remained at this higher value for about 100 hours. With the exception of the latter, the specimens remained bright with no visible corrosion product formation, an indication that a protective passive film was being maintained. The sample whose rate increased with time developed a slight flocculent red rust corrosion product.

In the ammonium sulfate and aluminum sulfate environments, the corrosion rates calculated by the Tafel analysis were consistently higher than those based on the polarization resistance analysis. These same relative differences were observed with the insulation leachates. However, all rates are very high compared to those for the insulation leachates (Table 3-3). Both of these materials hydrolyze in water to form acid solutions producing the pH values listed in Table 3.2. The pH of the ammonium sulfate environments is significantly higher (approximately pH = 5) than for the aluminum sulfate environments (approximately pH = 3). The pH of the saturated solutions is 0.5-1 units lower (more acid) than the 5% saturated ones. Table 3.2 also shows that the two commercial grades of ammonium sulfate solutions were slightly more acid than the chemically pure grade. However, although the pH values for solutions of the two

commercial grades were comparable, the corrosion rates for solutions based on the commercial source ammonium sulfate, designated Comm1, were consistently higher.

In the pH range of the ammonium sulfate solutions (≈ 5), The major factor causing corrosion is dissolved oxygen from air. Although data are not shown, the rate was observed to be much smaller for nitrogen sparged (deaerated) as compared to air sparged environments. In the pH range of the aluminum sulfate solutions (≈ 3), the acidity is also a significant, if not dominate, cause of the corrosion and high corrosion rates would be expected as observed. The rate of corrosion however is determined by the availability of oxygen and hydrogen ions to the metal/corrosion product interface and this availability is frequently determined by the physical nature of the corrosion product formation. In both the ammonium and aluminum sulfate environments the physical appearance of the corrosion product deposits supported speculation that they were not as protective as deposits formed in higher pH environments.

That pH may not be a controlling factor in the pH range of all the environments investigated is shown by the results for saturated solutions of boric acid and calcium sulfate. The saturated boric acid solution has a pH of about 3 and an indicated corrosion rate of 3.1 mpy using the polarization resistance method. The saturated calcium sulfate pH is about 5.5 and the Corrosion rate determined by the Corrater was 4.5. These corrosion rates are comparable but much smaller than for either

ammonium or aluminum sulfate environments.

Discussion of estimation of corrosion rates in cellulosic insulation additives from weight loss measurements.

Corrosion rates based on weight loss measurements on low carbon steel in solutions of several cellulosic insulation additives are listed in Table 3-6. As was observed for the insulation leachates, the corrosion rates based on weight loss are significantly lower than those obtain from electrochemical measurements.

The weight loss corrosion rate in the borax solutions was very small, ranging from 0.01 to 0.05 mpy. One exception is noted. In the 5% saturated solution of commercial grade borax, one specimen, during the two week exposure, lost the initial clear passivated surface appearance and was progressively covered with a thin flocculent rust deposit. The averaged corrosion rate was 1.5 mpy. It is significant that a similar change in appearance and corrosion rate was observed during the 48 hour Corratel measurement in the same environment. These results indicate that the commercial grade borax at 5% saturation is not able to sustain a passive film on the low carbon steel. Rather the mode of attack changes from passive to active corrosion. At least in saturated solutions, the steel remains passive almost indefinitely. The variables of concentration, time and source of material were not investigated further.

With one exception, the weight-loss corrosion rates in ammonium sulfate environments varied from 2.2 to 5.8 mpy. The

rate was extremely high (61.5 mpy) in the saturated Comm1 commercial ammonium sulfate solution. It is noted that the rates for this environment were also high when measured electrochemically. Comparison of the rates in solutions based on the two sources of commercial ammonium sulfate (Comm1 and Comm2) indicates a strong tendency for much higher rates in the Comm1 environments. Reference to Table 3-2 shows that the pH values are comparable for solutions based on the two sources. Hence, unidentified materials in the two grades of ammonium sulfate have a measurable influence on corrosion rate.

The aluminum sulfate solutions are extremely aggressive to low carbon steel. Also, the weight losses for the two-week exposure period were difficult to duplicate and to interpret when comparing the behavior in solutions based on chemically pure and commercial grades of aluminum sulfate. In the saturated CP solution, the steel specimen disintegrated to the extent that a final weight measurement was meaningless. In 5% saturated solutions of the CP material, of two specimens run simultaneously in separate volumes of 700 mL, one specimen resulted in a rate of 14 mpy and the other 41.8 mpy. Near the end of the two-week exposure, a slight flocculent white precipitate formed in the solution containing the specimen showing the lower corrosion rate. The precipitate is presumed to be aluminum hydroxide formed because of the increase in pH associated with the cathodic corrosion reactions. The specimen however was relatively clear of corrosion product. The solution containing the specimen showing

the very high corrosion rate showed progressive precipitation throughout the two-week period and the specimen became covered with a flocculent red corrosion product ($\text{Fe}(\text{OH})_3$ or Fe_2O_3).

There is little correlation between the weight-loss corrosion rates and those indicated by the electrochemical measurements. The measurements based on use of the potentiostat were conducted within a few hours and those based on the Corrater extended for only two days. The weight loss measurements were based on a two-week exposure. The lack of correlation of the two methods of evaluating the corrosion rate is related to these significant differences in time over which the measurements were made. In particular to the scattered values of corrosion rate obtained by weight loss and to the observations of change in corrosion mode during the two-week exposure.

TABLE 3-1

SUMMARY OF PROPERTIES OF INSULATION LEACHATES INVESTIGATED*

SAMPLE	pH	RESISTIVITY ohm-cm
--------	----	-----------------------

Cellulosic Insulations

1	7.42	84.4
2	7.07	92.3
3	7.58	62.7
4	6.48	68.7
5	6.37	49.4
6	5.98	49.2
7	4.40	73.6
8	6.05	114.0
9	4.75	255.0
10	7.67	131.0
11	4.44	117.0
12	8.20	103.0
13	8.08	95.0

Mineral Fiber Insulations

1	9.1	2300.0
2	9.62	896.0
3	9.24	1672.0

Foam Insulations

1	6.70	7160.0
2	5.58	5370.0
3	5.60	13160.0
4	7.48	10400.0

Knoxville water		4250.0
-----------------	--	--------

*Filtered leachate after 3 days.
100 grams insulation per 1 L distilled water

TABLE 3-2
 PROPERTIES OF SOLUTIONS OF SELECTED CELLULOSIC INSULATION ADDITIVES

MATERIAL	SOLUBILITY* grams 100 mL water	pH		RESISTIVITY ohm-cm	
		Sat.	5% Sat.	Sat.	5% Sat.
CP Borax	10	9.48	9.08	71.0	942.0
Comm. Borax	10	9.38	9.10	71.5	922.0
CP Am. Sulfate	80	4.77	4.86	3.9	25.8
Comm1. Am. Sulfate	80	4.11	5.11	3.8	29.1
Comm2. Am. Sulfate	80	4.98	5.05	4.1	26.5
CP Al. Sulfate	80	2.76	3.35	47.1	119.2
Comm. Al. Sulfate	80	2.57	3.47	32.0	132.0
CP Boric Acid	8	3.06	4.45	7170.0	119400
CP Calcium Sulfate	0.2	5.56	7.10	482	5950

CP = Chemically pure grade
 Comm. = Commercially pure grade
 * These amounts produce a small excess of undissolved solid

Sat. = Saturated solution
 5% Sat. = 19:1 dilution (5% saturation)

TABLE 3-3

SUMMARY OF CORROSION RATES OF CELLULOSIC INSULATION LEACHATES
DETERMINED BY ELECTROCHEMICAL AND WEIGHT LOSS MEASUREMENTS

Low carbon steel at room temperature					Rates in mpy	
ENVIRONMENT	POTENTIOSTAT		CORRATER		WEIGHT LOSS (14 days)	
	Tafel Analysis	Polarization Resistance Analysis	1 Hr	48 Hr		
Insulation leachates						
Cellulosic						
Source 1	2.0	3.2	6.4	3.2	0.45	
Source 2	16.2	6.9	10.	8.0	2.1	
Source 3	11.5	5.0	5.9	3.6	0.28	
Source 4	29.4	9.2	5.8	6.0	1.62	
Source 5	16.5	14.4	18.0	10.0		
Source 6	8.5	14.8	15.0	10.0		
Source 7	27.5	23.6	15.0	7		
Source 8	4.1	2.7	6.5	3.0		
Source 9	23.6	9.8	11.0	5.0		
Source 10	11.0	4.5	1.2	1.9		
Source 11	12.4	18.9	17.0	5.0		
Source 12	10.6	2.1	1.1	0.2		
Source 13	0.1	0.3	1.6	0.4		
Mineral fiber						
Source 1	7.6	2.7	3.0	0.6	2.0	
Source 2	6.2	2.5	1.5	0.1	1.1	
Source 3	26.2	4.9	2.0	2.8	1.4	
Foam						
Source 1			4.2	3.8		
Source 2			3.5	3.5		
Source 3			3.1	3.8		
Source 4			2.7	3.1		

Weight loss results based on 2 weeks exposure to environment.

TABLE 3-4
SUMMARY OF CORROSION RATES IN RELATED ENVIRONMENTS
DETERMINED BY ELECTROCHEMICAL AND WEIGHT LOSS MEASUREMENTS

ENVIRONMENT	Low carbon steel at room temperature		Rates in mpy	
	CORRATER		WEIGHT LOSS	
	1 Hr	48 Hr		
Corrater probe immersed in Source 1 Cellulosic insulation. 100 g/L dist. water.	2.9	0.2		
	(0.2 at > 48 hrs)			
Corrater probe immersed in Source 2 Cellulosic insulation. 100 g/L dist. water.	3.8	0.6		
	(0.2 at > 60 hrs)			
Corrater probe immersed in Source 2 Cellulosic insulation. 100 g/400 mL dist. water.	6.5	0.5		
	(0.3 at > 60 hrs)			
Corrater probe immersed in Source 2 Cellulosic insulation leachate. 100 g/L dist. water.	22			
Air sparged				
Corrater probe immersed in Source 1 Cellulosic insulation concentrated to 20% volume.		9.2		7.4
Corr. rate from weight loss in Source 1 Cellulosic insulation. Exposed two days.				1.5
Corr. rate from weight loss with air sparge in Source 1 Cellulosic insulation.				3.3
Corrosion rate from weight loss in:				
Distilled water				
Stagnant, air access				1.79
Air sparged				9.1
Nitrogen sparged				0.1
Domestic water				
Stagnant, air access	4.2	3.4		2.07
Immersed in sterile cotton	4.5	1.3		
	(0.2 in 120 hrs)			

TABLE 3-5
CORROSION RATES OF LOW CARBON STEEL PARTIALLY
IMMERSED IN WET INSULATIONS*

Insulation	Rates in mpy Low carbon steel		
	pH	Rate based on maximum local penetration at air interface (24 days)	Rate based on total immersion in leachate (14 days)
Source 1 cellulosic	7.42	6.8	0.45
Source 4 cellulosic	6.48	6.1	1.62
Source 11 cellulosic	4.44	>22.8(1 hole)	.n/d
Source 13 cellulosic	8.08	8.7	.n/d
Source 1 mineral fiber	9.10	7.0	2.0
Source 2 mineral fiber	9.62	9.8	1.1
Source 3 mineral fiber	9.24	>22.8(2 holes)	1.4
Sterile cotton	5.22(a)	9.1	1.8

*Specimens were 2 in x 2 in x 0.003 in immersed in the wet insulation for depth of 1.5 in. Containers were 5 cm deep and 10 cm in diameter. Distilled water added to maintain liquid just visible at top of insulation.

Maximum local penetration

(a) pH of liquid at end of exposure.

TABLE 3-6

SUMMARY OF CORROSION RATES IN SOLUTIONS OF CELLULOSIC INSULATION ADDITIVES
DETERMINED BY ELECTROCHEMICAL AND WEIGHT LOSS MEASUREMENTS

ENVIRONMENT	Low carbon steel at room temperature		Rates in MPY	
	POTENTIOSTAT (a) Tafel Polarization Analysis Resistance Analysis	CORRATER 1 Hr 48 Hr	WEIGHT (b) LOSS	
Borax				
CP (Sat)	0.05	<0.1	<0.1	<0.01
CP (5% Sat)		0.1	0.05	<0.03
Comm (Sat)	0.05	0.2	0.06	0.05
Comm (5% Sat)		0.2	0.7	<0.01(c)
Ammonium sulfate				
CP (Sat)	61	22	7	4.8
CP (5% Sat)	59	12	7	3.3
Comm1 (Sat)	150	133	78	61.5
Comm1 (5% Sat)	149	39	20	5.8
Comm2 (Sat)	49	81	58	2.2
Comm2 (5% Sat)	36	102	59	3.9
Aluminum sulfate				
CP (Sat)	91	45	83	(d)
CP (5% Sat)	170	92	70	27.9(e)
Comm (Sat)	211	89	48	55.8
Comm (5% Sat)	150	154	59	13.5
Boric acid				
CP (Sat)	8.9	3.1		3.8
Calcium sulfate				
CP (Sat)		5.5	4.5	

(a) After 1 hr exposure. (b) Based on 2 weeks exposure.
(c) One specimen slightly "rusty", 1.5 mpy. (d) Specimen disintegrated.
(e) Average of 14.0 and 41.8 mpy. See text for discussion.

Figure 3-1. Correlation of corrosion rates determined by Corrater and with rates determined by polarization resistance analysis of potentiostat data.

CHAPTER 4

ELECTROCHEMICAL POLARIZATION MEASUREMENTS ON BUILDING INSULATION LEACHATES AND CELLULOSIC INSULATION ADDITIVES

Introduction

Electrochemical polarization measurements performed over wide ranges of potential provide information useful in interpreting how a metal is interacting, and to a limited extent how it can interact, with an environment. In the present investigation, electrochemical polarization measurements were performed on low carbon steel in all of the environments, both insulation leachates and solutions of the selected cellulosic insulation additives. The specific objectives of these measurements are summarized as follows:

1. From an analysis of the cathodic and anodic polarization behavior near the corrosion potential, information is obtained about the electrochemical processes which establish steady state corrosion. An estimate can be made of the corrosion current density from which corrosion penetration rates are calculated. These rates can then be correlated with those determined by the electrochemical and weight loss methods discussed in Chapter 3.
2. From the shapes of the anodic and cathodic curves near the corrosion potential, the extent to which the polarization follows Tafel behavior (i.e., potential is a linear function of log current density) can be determined. Although the cyclic polarization curves presented in this chapter are not generally sufficient to make this assessment, a number of potential scans were recorded over narrow (± 10 to ± 200 mV) potential ranges to more clearly show the shapes of the curves. The shape is important in assessing the validity of the mathematical procedures used in the Tafel and polarization resistance techniques for estimating corrosion rates from polarization data. The results of using these techniques were reported in Chapter 3.
3. From the positions of the polarization curves near the corrosion potential, effects of environmental variables, particularly pH and degree of aeration, can be predicted and then confirmed by measurement subsequent to changing an environment variable.
4. The value of the corrosion potential and the shape of the polarization curve indicate if a metal in a given environment is in the active or passive condition at steady state corrosion. If the system is initially undergoing active corrosion, the shape of the curve with increasing potential indicates if the environment is capable of supporting a transition to the passive state. If so, predictions can be made relating changes in the environment,

particularly aeration, which could change the corrosion mode from active to passive.

5. Determination of cyclic polarization curves can be useful in determining the susceptibility of a metal/environment system to localized corrosion (pitting and crevice types). A rapid increase in current density at a particular potential usually indicates initiation of localized corrosion. The potential range over which the current density remains higher during the decreasing potential part of the cycle, the greater the susceptibility to localized corrosion. A "positive loop" is present and the larger the loop the greater the susceptibility. In contrast, if the current density during the decreasing potential is lower than on increasing the potential, susceptibility to pitting and crevice corrosion is predicted to be small. It is important to note the value of the corrosion potential relative to any loop obtained at higher potentials during determination of the polarization curve. If the corrosion potential is significantly lower than the potential range of the loop, then the environment will not place the metal in the susceptible potential range and localized attack should not be the observed corrosion mode. Only if some environmental variable is changed that significantly increases the potential would a transition from uniform corrosion be expected.

Reference can be made to Figure 4-1 for a schematic representation of variations in the shapes that polarization curves exhibit and for some of the terminology used in their description. Appendix A and Reference 8 contain additional discussion of both experimental procedure and interpretation of polarization measurements. Figure 4-1a is representative of the anodic polarization curve for a metal and cathodic polarization curves for hydrogen ion reduction and dissolved oxygen reduction. The current density at any potential along the anodic curve is directly proportional to the corrosion rate of the metal when existing at the particular potential. The intersection of the metal and hydrogen reduction curves define the conditions (E_{corr} and I_{corr}) which are spontaneously established at steady state corrosion in a deaerated environment. The intersection of the metal and oxygen reduction curves define the corrosion conditions for an aerated environment. These potentials can be measured experimentally as the potential between the

corroding metal and a reference electrode, the measurement being made with a high impedance voltmeter or electrometer.

If a potentiostat is used to establish the potential of the metal and the associated current between the specimen and auxiliary electrodes measured, the solid curve in Figure 4-1b is obtained for the aerated environment and the solid curve in Figure 4-1c in the deaerated environment. These solid curves, which would result from experimental measurement, are the difference in the current density of the anodic and cathodic curves at each potential. At E_{corr} , there is no difference in the two curves and the solid curve moves to and rapidly returns from small values of current thus identifying the corrosion potential. Extrapolation (shown as dashed lines) of the anodic and cathodic branches of the polarization curve until they intersect in the vicinity of E_{corr} allows a qualitative estimation of the corrosion current density and hence corrosion rate. Below E_{corr} , the potentiostat forces the cathodic reaction to dominate; above E_{corr} the anodic reaction dominates. The dashed sections of these curves show only the positions of the polarization curves for the individual reactions; these sections are not determined in a single potential scan.

Figure 4-1d is representative of an experimentally determined polarization curve for a metal/environment system leading to localized corrosion, either pitting or crevice corrosion. On the upscan, pitting is initiated at E_b and the initiation and propagation of local corrosion results in a large increase in current density. If the potential is reversed, a loop forms and the localized corrosion finally stops propagating at the potential E_p . If the metal/environment system is not conducive to breakdown to localized corrosion, the measured polarization curve continues to increase as shown by

the dashed extension and, on potential reversal, the curve returns at lower values of current density than on the upscan. The practical significance of knowing these characteristics of the potential/current density relationship is estimation of conditions conducive to pitting. If an environment causes the corrosion potential to exist above E_B then failure by pitting corrosion is predicted. If the corrosion potential is below E_p , pitting is not predicted. Figure 4-1d is representative of a deaerated environment and E_{corr} is $\ll E_p$ and localized corrosion will not occur. If aeration (dissolved oxygen) or other strongly cathodic reactants are present to increase E_{corr} into the range above E_p localized corrosion may occur.

In the present investigation, potentials were measured relative to the Ag/AgCl reference electrode and corrected to the standard hydrogen electrode (SHE) scale. The corrosion potential, E_{corr} , is indicated on the polarization curves which follow. Most of the potential scans were started at a potential of about 100 mV negative to E_{corr} , extended to 1200 mV and returned to the starting potential. The scan rate was 1200 mv per hour. Arrows along the curves indicate the direction of the scan.

It is emphasized that in determining the polarization curves which are shown in the following sections, the so-called "IR" correction was not made. The need for this correction results from the location of the reference electrode in the current path between an auxiliary electrode and the metal undergoing polarization. As a consequence, the potential indicated by the reference electrode is displaced from the true interface potential by the IR potential drop between the reference electrode and the metal interface. The correction is significant only at higher current densities and in environments of high specific resistivity. Since the correction is difficult to estimate

and the objective of the cyclic polarization curves was to characterize the general corrosion behavior of the steel/environment combinations, the reported curves are those measured directly without IR correction.

The steep slope of the polarization curves of the carbon steel at higher potentials and current densities in many of the cellulosic insulation leachates indicate a significant IR drop error exists. Corrected curves would fall below those shown. For this reason, only qualitative significance can be given to the curves at the higher current densities. The curves do, however, reflect tendencies for the steel to undergo transitions from active to passive states and provide indications of tendencies for localized corrosion in the form of pitting.

Polarization curves for low carbon steel in insulation leachates

The properties of all of the insulation leachates, pH and specific resistivity, were listed in Table 3-1 and the corrosion rates determined by Tafel and polarization resistance analysis and by weight loss were listed in Table 3-3. In the following discussion, some reference will be made to conversion of corrosion current density to corrosion penetration rate. For steel, this conversion is $\text{Rate}(\text{mpy}) = 0.457i$ (i in $\mu\text{A}/\text{cm}^2$). Reference will also be made to the corrosion potentials, E_{corr} , identified by position on the polarization curves with values included in the discussion with greater precision than can be determined from the graphs. Approximate values for the corrosion current density are identified as a dot in line with E_{corr} . These corrosion potentials for low carbon steel in the cellulosic insulation leachates, taken directly from the experimental data, are listed in Table 4-1. For reference, the corrosion rates based on using the polarization resistance technique and listed in Table 3-3 have been included in Table 4-1.

Cellulosic insulation leachates.

Cyclic polarization curves for the cellulosic insulation leachates are shown in Figures 4.2 - 4.14. Although the forms of most of the curves are similar near E_{corr} , a significant variation is observed at higher potentials and in the position and size of the loop resulting from the down scan.

The cyclic polarization curve for Source 1 cellulosic insulation is shown in Figure 4-2. As the first in the series of polarization curves for low carbon steel in insulation leachates, this curve will be discussed in some detail. All scans started slightly cathodic, in this case at -600 mV. The transition from net cathodic to net anodic occurs at the corrosion potential which was recorded as -479 mV (Table 4-1). The steel shows a slight tendency to passivate near -200 mV but does not develop a protective passive film. On increasing potential, the current density continues to increase until at 1400 mV the scan was reversed. On potential reversal, the current density is lower than during the upscan and no loop is formed indicating that typical localized corrosion (pitting) was not initiated (see Figure 4-1d). A slight instability occurs near 800 mV on the downscan after which the curve approaches that of the upscan finally passing from net anodic to net cathodic near -400 mV. The corrosion current density should be estimated at E_{corr} from the upscan curve as the intersection of extrapolations of the linear segments of the cathodic and anodic branches. This intersection (a dot in line with E_{corr}) is estimated to occur at $9 \mu\text{A}/\text{cm}^2$ which corresponds to a corrosion rate of $0.45 \times 9 = 4.1$ mpy. This compares to a value of 3.2 mpy determined by the polarization resistance analysis applied to data obtained with the potentiostat (Table 3-3). This agreement is somewhat fortuitous since, in general, the curves are not sufficiently linear to allow reasonable extrapolation and therefore a

meaningful value of the corrosion current density based on the intersection.

The cyclic polarization curves in Figures 4-3, 4-4, and 4-5 are qualitatively similar to the curve in Figure 4-2. All show downscan current densities at lower values than for the upscan; the absence of an "anodic loop" indicates absence of localized corrosion. Source 4 and Source 5 cellulosic insulation leachates resulted in slightly different cyclic polarization performance, Figures 4-6 and 4-7. On the upscan, passivation occurs near 1000 mV. On reversing the scan, the passive state is retained down to about 600 mV below which the curve approaches the curve present during upscan. A similar behavior is shown in Figure 4-7. These curves are quite exceptional in that they do not conform to either of the conventional observations illustrated in Figure 4-1d. However there was no evidence of pitting corresponding to local breakdown of a passive film.

The cyclic polarization curves for Source 7, 8, 9 and 11 cellulosic insulations leachates in Figures 4-8 to 4-11 are similar to the curves of Figures 4-3, 4-4 and 4-5. There is no indication of an active-to-passive transition and the current density on downscan is less than on upscan indicating absence of localized corrosion.

The cyclic polarization curve for steel in the leachate from Source 10 cellulosic insulation was significantly different as shown in Figure 4-12. On upscan there is a strong indication of passivation near 0 mV after which the current again increases with increase in potential, On reverse scan, the current density is initially slightly greater but crosses the upscan curve and passes through an anodic-to-cathodic transition at about 300 mV and remains cathodic. Again the curve is unusual and has been tentatively interpreted as indicating that the passive state formed at 0-100 mV is retained although it

is associated with an increasing current density as the potential increases. That the corrosion product deposit has the characteristics of a passive film is supported by the observation that on downscan below about 1000 mV the current density becomes less than on the upscan. The continued decrease in current density is attributed to a further increase in thickness of the passive film. When the anodic current density of the passive film becomes sufficiently small, the net reaction shifts to the cathodic reduction of oxygen. Thus the curve below 500 mV has the form of Figure 4-1b.

The cyclic polarization curves shown in Figures 4-13 and 4-14, for Source 12 and Source 13 cellulosic insulation leachates, are the only cases among the thirteen cellulosic leachates exhibiting an active/passive transition followed by a "positive downscan polarization loop". In Figure 4-13, passivation tends to occur near -400 mV, a short passive state exists over the potential range -200 to 0 mV after which the current density increases. On potential reversal, the current density on downscan is greater than on upscan, forming a "positive loop", characteristic of localized corrosion. The breakdown potential, E_B , and the protection potential are 0 mV and -250 mV, respectively. A similar behavior is exhibited in Figure 4-14 except that the form of the curve indicates that the surface was already passivated when the scan was initiated at -200 mV and immediately underwent localized corrosion with increasing current density during upscan. A positive loop on downscan supports this conclusion. This behavior is consistent with the higher pH of these leachates, 8.20 and 8.08. Higher pH environments are conducive to passive film formation by moving the anodic polarization curve to lower current densities thereby allowing the cathodic polarization curve for dissolved oxygen to cross the anodic polarization curve of the steel in the

passive region as illustrated in Figure 4-1b. Following cyclic polarization in Source 12 and Source 13 cellulosic insulation leachates, the steel specimen was severely pitted with areas between the pits still bright characteristic of a passivated surface.

Mineral fiber insulation leachates.

Figures 4-15, 4-16 and 4-17 show the cyclic polarization curves for the Source 1, 2 and 3 mineral fiber insulations. None of these curves show an active-to-passive state transition. On potential reversal, a positive anodic loop occurs on downscan with current density greater than on the upscan. In each environment, the low carbon steel specimen following the cyclic polarization was pitted with regions either still bright or slightly corroded between the pits. Also each environment resulted in a slight inflection in the upscan curve; reference to Figures 4-15, 4-16 and 4-17 shows that this inflection occurs at about -100, -250 and +100 mV for the respective environments. If the specimen is removed just below this inflection, no pits are observed; removal at a potential just above the inflection shows pitting. Table 3-1 shows that leachates from all three mineral fiber insulations had $\text{pH} > 9$ which is conducive to passive film formation. Since the polarization curves do not exhibit the usually decrease in current density associated with an active-to-passive state transition (see Figure 4-1a), it is concluded that the dissolved oxygen in the leachate is sufficient to passivate the steel. However, rather than observe a passive state (essentially constant current density) range of potential, the current density immediately increases on increasing potential with observable pitting at the inflection in the upscan curve. Although the pH values of the three mineral fiber leachates are similar, there are differences in the leachate compositions that result in

differences in the potential at which the inflection occurs and in the corrosion potential. The species responsible for these differences were not investigated.

Polarization curves for low carbon steel in solutions of selected additives to cellulosic insulations.

Borax environments.

Cyclic polarization curves for saturated CP and commercial grades of borax are shown in Figures 4-18 and 4-19, respectively. Carbon steel readily passivates in these environments due to the relatively high $\text{pH} > 9$ and absence of other species preventing passive film formation. Under normal aerated conditions, the dissolved oxygen is capable of forming a passive film which accounts for the high corrosion potential in Table 4-2. The measured polarization curve is of the form of Figure 4-1b. The curves in Figures 4-18 and 4-19 show that the reverse scan lies at lower current density than the upscan indicating a stable passive film and absence of any tendency for localized corrosion. Extrapolation of linear portions of the lower (cathodic) and upper (anodic) branches of the curve near E_{corr} results in an intersection near $10^{-1} \mu\text{A}/\text{cm}^2$. Since, for iron, the corrosion rate in mpy is given by $\text{mpy} = 0.45 \times i_{\text{corr}}$ (i_{corr} in $\mu\text{A}/\text{cm}^2$), the polarization curves predict a corrosion rate of less than 0.1 mpy which is consistent with the values reported in Table 3-6.

Ammonium sulfate environments.

The cyclic polarization curve for saturated CP grade ammonium sulfate is shown in Figure 4-20. The curve is complex showing two potentials, ≈ -100 and ≈ 400 mV, at which rapid decrease in current density suggests passive film formation. Near the lower potential a dark corrosion product forms and remains until the decrease in current density near 400 mV. As this decrease occurs,

the dark film drops from the specimen leaving a bright surface characteristics of a passive film. A tentative explanation is that a film of iron sulfate forms initially which is finally replaced by a passive oxide film at the higher potential. Since the curve returns at lower current densities than on the upscan, breakdown to localized corrosion (pitting) is not indicated and examination of the specimen confirms that uniform corrosion occurs. The corrosion current density is estimated to be about $40 \mu\text{A}/\text{cm}^2$ corresponding to an estimated corrosion rate of about 20 mpy which is in general agreement with the value of 26 mpy shown in Table 3-6.

The cyclic polarization curve for the 5% saturated CP ammonium sulfate is shown in Figure 4-21. Significant differences exist relative to the behavior of the saturated environment. Again a black deposit formed at lower potentials but disappeared with a transition to bright passive surface near 800 mV. The return scan was again at lower current densities indicating no breakdown to localized corrosion. The corrosion current density is estimated to be about $60 \mu\text{A}/\text{cm}^2$ which is larger than for the saturated solution. This indicates a higher corrosion rate which is consistent with the data of Table 3-6.

Commercial grade ammonium sulfate from two sources was investigated as saturated and 5% saturated solutions. The cyclic polarization curves are shown in Figures 4-22 to 4-25. The curves for the Comm1 source material are generally similar to those for the CP grade of Figures 4-20 and 4-21. However the curves for the Comm2 source ammonium sulfate are measurably different. The saturated solution (Figure 4-24) shows a single active to passive transition near 400 mV. The 5% saturated Comm2 source solution shows a very unusually high active-to-passive transformation of 1200 mV which was confirmed by

repeated determinations.

The filled circle in the vicinity of the transition from net cathodic to net anodic polarization at E_{corr} in Figures 4-20 to 4-25 are the estimated positions of the corrosion current densities. Applying the multiplying factor of 0.45 to the corrosion current density gives the following estimated corrosion rates:

Source of ammonium sulfate	Saturated	5% saturated
CP grade	20 mpy	15 mpy
Comm1 commercial grade	80	45
Comm2 commercial grade	15	10

With one exception, these rates have the same relative values as shown in Table 3-6 under potentiostat polarization resistance analysis. A significant observation is the lower rates in the Comm2 versus Comm1 commercial grades. This difference in the corrosive environments of these two commercial grades is also shown by the lower values of E_{corr} for the Comm2 commercial grade material. (See Table 4-2) Chemical species in the two commercial ammonium sulfates responsible for the difference in polarization behavior was not investigated.

Aluminum sulfate environments.

The cyclic polarization curves for saturated and 5% saturated solutions of CP grade aluminum sulfate are shown in Figures 4-26 and 4-27. In the saturated solution, an active to passive transition occurs near 600 mV and the reverse scan occurs at lower current densities than on upscan. The active state is recovered at essentially the same potential at which passivation occurred on upscan; the current densities on upscan and down scan in the active state are similar and essentially identical below 200 mV.

The cyclic polarization behavior of the 5% saturated CP aluminum sulfate

environment (Figure 4-27) is surprisingly different from that of the saturated solution. There is no active-to-passive type of change at any potential and the upscan and downscan curves are almost identical. The specimen becomes coated with a dark corrosion product and is not pitted after the cycle; severe uniform corrosion has occurred. The form of the curve indicates presence of a high electrochemical cell resistance. However, the precise reproduction of the upscan curve on down scan is not expected.

The cyclic polarization curves for the saturated and 5% saturated commercial grade aluminum sulfate are shown in Figures 4-28 and 4-29. These are qualitatively similar to the respective curves for the CP grade environments. The passivation potential in the saturated commercial grade solution is higher but the potential of return to the active state on down scan is similar. Again there is no positive loop on downscan and the curves are almost independent of scan direction in the active regions.

The cyclic polarization curve for the 5% saturated commercial grade aluminum sulfate is shown in Figure 4-29. The curve is almost identical to that observed for the 5% saturated CP grade (Figure 4-27) and is again very different from the behavior in the saturated solutions.

It is evident that the corrosion current densities of all of the aluminum sulfate solutions are higher than for the ammonium sulfate solutions. Also they are slightly higher for the 5% saturated compared to saturated solutions. These differences are consistent with the values for corrosion rate in Table 3-6 under polarization resistance analysis. A major contribution to the larger corrosion current densities in the aluminum sulfate solutions is the lower pH (Table 3-2) indicating a measurable contribution of hydrogen ion reduction to the cathodic reaction (in addition to dissolved oxygen

reduction). This is consistent with the observed higher corrosion potential as shown in Table 4-2.

Boric acid environment.

The cyclic polarization curve for saturated boric acid, Figure 4-30, shows almost exact reproducibility on upscan and downscan. Again this behavior is characteristic of high cell resistance although the duplication is not. The corrosion current density estimated to be $7 \mu\text{A}/\text{cm}^2$ from Figure 4-30 corresponds to a corrosion rate of 3.1 mpy which agrees with the value in Table 3-6.

TABLE 4-1

CORROSION POTENTIALS OF INSULATION LEACHATES

Low carbon steel

Cellulosic Leachate	E _{corr} mV	Corr. Rate [*] mpy
Source 1	-479	3.2
Source 2	-482	6.9
Source 3	-487	5.0
Source 4	-481	9.2
Source 5	-458	14.4
Source 6	-463	14.8
Source 7	-456	26.6
Source 8	-432	2.7
Source 9	-444	9.8
Source 10	-262	4.5
Source 11	-429	18.9
Source 12	-491	2.1**
Source 13	- 84	0.3**
Mineral fiber Leachate		
Source 1	-361	2.7**
Source 2	-363	2.5**
Source 3	-431	4.9**

* Corrosion rates from polarization resistance analysis of potentiostatic polarization data. See Table 3-3.

** Specimens showed pitting after cyclic polarization. Pitting does not occur while held at the corrosion potential.

TABLE 4-2

CORROSION POTENTIALS OF SOLUTIONS OF SELECTED
ADDITIVES TO CELLULOSIC INSULATION

Low carbon steel

Additive Species	E_{corr} mV	Corr. Rate* mpy
Borax		
CP(sat)	- 12	0.04
Comm(sat)	- 11	0.03
Ammonium sulfate		
CP(sat)	-509	26
CP(5% sat)	-576	53
Comm1(sat)	-434	74
Comm1(5% sat)	-470	41
Comm2(sat)	-527	43
Comm2(5% sat)	-519	15
Aluminum sulfate		
CP(sat)	-349	45
CP(5% sat)	-394	92
Comm(sat)	-372	89
Comm(5% sat)	-377	154
Boric acid		
CP(sat)	-404	

* Corrosion rates from polarization resistance
analysis of potentiostatic polarization data.
See Table 3-5.

CP - chemically pure grade
Comm - commercial grade

Figure 4-1a. Schematic polarization curves for anodic metal corrosion and for cathodic and hydrogen ion reduction.

- E_1 = Corrosion potential - deaerated
- I_1 = Corrosion current density - deaerated
- E_2 = Corrosion potential - aerated
- I_2 = Corrosion current density - aerated

Figure 4-1b. Solid curve represents experimental polarization under aerated conditions.

Figure 4-1c. Solid curve represents experimental polarization under deaerated conditions.

Figure 4-1d. Solid curve represents polarization when pitting starts on an upscan at E_p . Positive anodic loop indicates susceptibility to localized corrosion. E_p is the protection potential. Dashed curve is observed if localized corrosion does not occur.

Figure 4-2. Cyclic polarization curve for low carbon steel in Source 1 cellulosic leachate.

Figure 4-3. Cyclic polarization curve for low carbon steel in Source 2 cellulosic leachate.

Figure 4-4. Cyclic polarization curve for low carbon steel in Source 3 cellulosic leachate.

Figure 4-5. Cyclic polarization curve for low carbon steel in Source 4 cellulosic leachate.

Figure 4-6. Cyclic polarization curve for low carbon steel in
Source 5 cellulosic leachate.

Figure 4-7. Cyclic polarization curve for low carbon steel in Source 6 cellulosic leachate.

Figure 4-8. Cyclic polarization curve for low carbon steel in Source 7 cellulosic leachate.

Figure 4-9. Cyclic polarization curve for low carbon steel in Source 8 cellulosic leachate.

Figure 4-10. Cyclic polarization curve for low carbon steel in Source 9 cellulosic leachate.

Figure 4-11. Cyclic polarization curve for low carbon steel in Source 11 cellulosic leachate.

Figure 4-12. Cyclic polarization curve for low carbon steel in
Source 10 cellulosic leachate.

Figure 4-13. Cyclic polarization curve for low carbon steel in Source 12 cellulosic leachate.

Figure 4-14. Cyclic polarization curve for low carbon steel in Source 13 cellulosic leachate.

Figure 4-15. Cyclic polarization curve for low carbon steel in
Source 1 mineral fiber leachate.

Figure 4-16. Cyclic polarization curve for low carbon steel in
Source 2 mineral fiber leachate.

Figure 4-17. Cyclic polarization curve for low carbon steel in
Source 3 mineral fiber leachate.

Figure 4-18. Cyclic polarization curve for low carbon steel in saturated solution of CP grade borax.

Figure 4-19. Cyclic polarization curve for low carbon steel in saturated solution of commercial grade borax.

Figure 4-20. Cyclic polarization curve for low carbon steel in saturated solution of CP grade ammonium sulfate.

Figure 4-21. Cyclic polarization curve for low carbon steel in 5% saturated solution of CP grade ammonium sulfate.

Figure 4-22. Cyclic polarization curve for low carbon steel in saturated solution of commercial grade ammonium sulfate.

Figure 4-23. Cyclic polarization curve for low carbon steel in 5% saturated solution of ammonium sulfate.

Figure 4-24. Cyclic polarization curve for low carbon steel in saturated solution of Comm2 commercial grade ammonium sulfate.

Figure 4-25. Cyclic polarization curve for low carbon steel in 5% saturated solution of Comm2 commercial grade ammonium sulfate.

Figure 4-26. Cyclic polarization curve for low carbon steel in saturated solution of CP grade aluminum sulfate.

Figure 4-27. Cyclic polarization curve for low carbon steel in 5% saturated solution of CP grade aluminum sulfate.

Figure 4-28. Cyclic polarization curve for low carbon steel in saturated solution of commercial grade aluminum sulfate.

Figure 4-29. Cyclic polarization curve for low carbon steel in 5% saturated solution of commercial grade aluminum sulfate.

Figure 4-30. Cyclic polarization curve for low carbon steel in saturated solution of CP grade boric acid.

CHAPTER 5

CONCLUSIONS AND RECOMMENDATIONS

In this investigation, four electrochemical techniques were used to evaluate their applicability for assessing the corrosiveness of thirteen cellulosic, three mineral fiber and four foam insulations. The environments were filtered leachates from the insulations and well as the direct wet insulations. Corresponding measurements were conducted on saturated and partially saturated solutions of four additives that may be used in the production of cellulosic insulation. The calculated corrosion rates and corrosion modes indicated by the electrochemical methods were compared to direct measurements of corrosion rates based on weight loss and by visual observations of the corrosion modes. All measurements reported are based on exposure of low carbon steel to the several environments at room temperature, $75\pm 5^{\circ}\text{F}$.

The investigation has led to the following conclusions:

1. The development of an electrochemical method for the evaluation of the corrosiveness of residential building thermal insulation of general applicability to cellulosic, mineral fiber, and foam insulations is questionable. The basic reason for this conclusion is that the models of the corrosion process which are used by the electrochemical techniques to calculate corrosion rates do not apply when the corrosion process is under diffusion control as is the case for wet insulations. Development of calculation algorithms of acceptable accuracy that would be applicable is doubtful. These conclusions are based on the following:
 - (1) The environments within the wet insulations vary widely;
 - (2) Over the pH ranges of the environments (4-9), corrosion products form with a range of adherence and porosity;
 - (3) The cause of the corrosion in this pH range is dissolved oxygen and the rate of corrosion is controlled by access of dissolved oxygen by diffusion through the corrosion product to the metal surface;
 - (4) Access of oxygen is also controlled by the packing of the insulation at a metal surface and by the distance of a metal surface from the insulation to the free air interface;
 - (5) The corrosion products build up slowly requiring

- days to weeks to reach steady state. Also during this time the corrosion may be very heterogeneous;
- (6) The above preclude the applicability of the electrochemical method from providing adequate quantitative measurement of the corrosiveness of an insulation;
 - (7) The above also preclude considering the electrochemical technique as a short-time (few hours) method for evaluating corrosiveness of insulations.
2. Electrochemical measurements were made on low carbon steel in the insulation leachates and in solutions of cellulosic insulation additives. Two instruments were used, a computer operated potentiostat and a direct reading corrosion rate meter (Corrater). Although it was concluded that these instruments would not provide adequate quantitative values of corrosion rates of insulations to be useful as a method of evaluating the corrosiveness of wet insulations, the measurements did provide information on the variables and mechanisms associated with the corrosion processes. Observations based on the electrochemical measurements include:
- (1) All insulation leachates with $\text{pH} < 8$ exhibit active corrosion potentials. Although in some leachates there is some indication of a tendency to passivate the steel near -200 mV , the current density continues to increase and on potential reversal near 1200 mV , downscan current density is less than on upscan indicating no tendency for pitting as defined by a "positive" anodic loop. The specimen following cyclic polarization was uniformly corroded.
 - (2) Leachates with $\text{pH} > 8$ cause the steel to undergo "pseudo-passivation" and in some cases this condition exists at steady state corrosion. On reverse scan during cyclic polarization, a positive polarization loop is observed and the specimen is severely pitted, frequently with a bright unattacked surface between pits.
 - (3) Both CP and commercial grades of borax passivate the steel at steady state and no pitting is indicated by cyclic polarization measurements.
 - (4) The polarization curves for steel in the ammonium and aluminum sulfate solutions indicate steady state corrosion in the active potential range. On increasing the potential complex anodic polarization curves result with an active-to-passive transition that reverses on the downscan. Positive anodic loops do not occur and, although extensive corrosion has occurred, pitting is not observed.
 - (5) Corrosion rates were calculated from the potentiostat data using Tafel analysis and polarization resistance analysis. The values were difficult to reproduce quantitatively and the rates based on Tafel analysis were generally much larger than those based on polarization resistance analysis.
 - (6) The Corrater calculates corrosion rates based on the

- polarization resistance analysis. Measurements were followed for 48 hours and in some cases for >100 hours. Progressive decrease in rate was observed as corrosion products formed, frequently requiring >100 hours to become steady.
- (7) Corrosion rates calculated from potentiostat data by polarization resistance analysis are in qualitative agreement with the rates indicated by the Corrater at one hour. Since the potentiostat data were usually taken after about an hour of immersion (reasonably constant E_{corr}), this agreement is reasonable. The comparison to the long time Corrater determined rates is poor and reflects the time dependence to reach steady state.
 - (8) Corrosion rates calculated from both potentiostat and Corrater measurements when environments were sparged with air or with nitrogen confirmed that access of dissolved oxygen to the interface was the controlling variable. Corrosion rates of the order of 2-3 mpy for the steel in a stagnant environment were decreased to 0.1-0.2 mpy on nitrogen sparge and to >20 mpy on air sparge. Corrosion rates indicated by the Corrater were also much lower when the specimens were immersed in wet insulation such that access of air was restricted.
 - (9) Corrosion rates determined by weight loss were consistently lower than those calculated from electrochemical data. This confirms that the algorithms used in both the Tafel analysis and polarization resistance analysis are not appropriate for the corroding systems involving insulation leachates where corrosion product buildup followed by diffusion control occurs. The algorithms are based on corrosion mechanisms that are not diffusion controlled and satisfactory corrections for diffusion are not available.
3. Extensive weight-loss measurements were performed using 2 in x 2 in x 0.021 in specimens exposed for two weeks to provide a direct measurement of the corrosion rate. The major observations from these measurements include:
- (1) The weight loss corrosion rates in the insulation leachates ranged from 0.28 to 2.1 mpy which are all of the order of or less than rates observed for distilled or domestic water. There is therefore an indication that leachable species in some insulation have an inhibiting effect on the corrosion of low carbon steel.
 - (2) The weight loss corrosion rates in the borax environments were very low, <0.1 mpy. With one exception, the rates in the ammonium sulfate environments ranged from 2.2 to 5.8 mpy. These measurements (also data from the Corrater) indicated that the two sources of commercial ammonium sulfate resulted in different corrosion rates. The corrosion rates in the aluminum sulfate environments were significantly larger, from 3.8 to 55.8 mpy with one sample disintegrating.
 - (3) Several weight loss corrosion rates were measured in stagnant, air sparged and nitrogen sparged environments to determine the

magnitude of change in corrosion rate related to available dissolved oxygen. As a base determination, weight loss corrosion rates for the low carbon steel in distilled water were 1.79 mpy stagnant, 9.2 mpy air sparged and 0.1 mpy nitrogen sparged.

- (4) The weight loss corrosion rates were consistently lower, and frequently very much lower, than rates determined electrochemically.
4. The significant, if not controlling, influence of dissolved oxygen on the corrosion rates suggested that partial exposure of steel to wet insulation would provide conditions for maximum corrosion rate at the steel-air wet insulation interface and that the rate should decrease with depth into the insulation. A procedure in which 2 in x 2 in x 0.003 in steel specimens were immersed vertically to a depth of 1.5" in wet insulation established conditions allowing differentiation of the corrosiveness of different wet insulations. Exposure was standardized as three weeks and wet sterile cotton was included with a group of wet insulations as a comparative standard. After exposure, examination was made along the interface for penetration or measurements were made of change in thickness. Representative examples include: an insulation that showed a corrosion rate of 0.45 mpy on immersion in leachate had a rate of 6.8 mpy at the air interface; another insulation leachate having a rate of 1.4 mpy on total immersion showed two holes along the interface on partial immersion. The rates for the sterile cotton were 1.8 mpy on immersion and 9.1 mpy on partial immersion, i.e. greater corrosiveness than for wet insulations.

The following recommendations are made:

1. The procedure in which the corrosiveness of wet insulations is evaluated by partial immersion of a thin (0.003 in) metal specimen for three weeks followed by examination of the extent of attack along the metal-air-wet insulation interface should be investigated as a corrosiveness test method. The procedure is straightforward and the conditions are representative of those that would exist when wet insulation contacts metal surfaces in building situations. Aside from precautions of specimen preparation, variables to be investigated include time of exposure, maintenance of amount of liquid as related to evaporation and specimen thickness. The use of 2 in x 2 in specimens with partial immersion in 5 cm x 10 cm diameter glass crystallizing dishes appears to be satisfactory.
2. Determinations of polarization curves using a potentiostat are useful in the study of the corrosion mechanisms in wet insulations. However, the instrumentation is relatively expensive and personnel with experience in electrochemistry and interpretation of corrosion phenomena in relationship to polarization behavior should be available.
3. The Corratel shows promise as a quality control instrument if a correlation is established between the corrosion rate indicated by the instrument and service performance (or to the partial immersion test proposed above).

REFERENCES

1. Anderson, R. W., Proceedings of the Cellulose I Conference, June 27-28, 1978. ORNL/Sub/81-40447/1, Oak Ridge National Laboratory, Oak Ridge, TN, 1982.
2. Weil, R. and Graviano, A., Assessment of the Corrosiveness of Cellulosic Insulating Materials, Dept. of Materials and Metallurgical Engineering., Stevens Institute of Technology, Hoboken, NJ, Oak Ridge National Laboratory, Oak Ridge, TN, 1979.
3. ASTM C665-86 Standard Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing. In 1988 Annual Book of Standards, Am. Soc. for Testing and Materials, Philadelphia, PA, 1988, Vol. 04.06 Thermal Insulation, pp. 256-261.
4. ASTM C739-86 Standard Specification for Cellulosic Fiber (Wood-base) loose Fill Thermal Insulation. In 1988 Annual Book of Standards, Am. Soc. for Testing and Materials, Philadelphia, PA, 1988, Vol. 04.06 Thermal Insulation, pp. 343-357.
5. ASTM C764-84 Standard Specification for Mineral Fiber Loose-fill Thermal Insulation. In 1988 Annual Book of Standards, Am. Soc. for Testing and Materials, Philadelphia, PA, 1988, Vol. 04.06 Thermal Insulation, pp. 391-395.
6. ASTM C951-83 Standard Specification for Urea-Formaldehyde-Based Insulation. In 1984 Annual Book of Standards, Am. Soc. for Testing and Materials, Philadelphia, PA, 1984, Vol. 04.06 Thermal Insulation, pp. 625-633.
7. Sheppard, K.G. and Weil, R., Aspects of Corrosion Testing of Thermal Insulating Materials. In F.A. Govan, D.M. Greason and J. D. McAllister (eds.), Thermal Insulation Materials and Systems for Energy Conservation in the 80s. ASTM STP 789, Am. Soc. for Testing and Materials, Philadelphia, 1983, pp. 114-132.
8. Sheppard, K. G., Patel, S., Taneja, M. and Weil, R., Comparisons of Several Accelerated Corrosiveness Test Methods for Thermal Insulation Material. In W. I. Pollock and J. M. Barnhart (eds), Corrosion of Metals under Thermal Insulations, ASTM STP 880, Am. Soc. for Testing and Materials, Philadelphia, PA, 1985, pp. 220-230.
9. Stansbury, E. E., Overview of the Applicability of Electrochemical Methods to Evaluation of the Corrosiveness of Residential Building Thermal Insulations with Proposed Test Program, ORNL/SUB/87-B8240/1, Oak Ridge National Laboratory, Oak Ridge, TN, 1989.

APPENDIX A
OVERVIEW OF BASIS FOR EVALUATING CORROSION BEHAVIOR
BY ELECTROCHEMICAL METHODS WITH EMPHASIS ON
DIRECT READING INSTRUMENTS

The corrosion process is shown schematically in Figure 1 in terms of the corrosion of iron with the corrosion supported by hydrogen ions and dissolved oxygen. Iron atoms pass into solution as ions according to the anodic reaction $\text{Fe} \rightarrow \text{Fe}^{m+} + 2e$ resulting in corrosion. The corrosion is sustained by the electrons released by this reaction being consumed at some other position on the surface according to the cathodic reaction $2\text{H}^+ + 2e \rightarrow \text{H}_2$ or $\text{O}_2 + 2\text{H}_2\text{O} + 4e \rightarrow 2\text{OH}^-$. Since both of these reactions involve transport of electrons, their rates can be expressed as an electrical current. For a freely corroding metal these rates must be equal, i.e., electrons released by the corrosion reaction must be consumed by cathodic reactions. With respect to making electrochemical measurements, it is important to point out here that this balance can be upset by passing electrons to or from the corroding region through an external connection. Electrons removed from the region will cause the metal to have an increased potential (more positive), the corrosion reaction is increased and the cathodic reaction is decreased; electrons added to the region will decrease the corrosion potential, increase the cathodic reaction and decrease the corrosion rate. Such shifts in potential are referred to as polarization and can be accomplished by attaching the metal appropriately to a potentiostat which indicates both the potential of the metal and the direction and magnitude of the external current.

The arrangement for making polarization measurements is shown schematically in Figure 2 in which only the hydrogen reaction is shown as the supporting cathodic reaction. Also, in this representation, the iron is being polarized anodically or shifted to a more positive potential than the corrosion potential. This is represented by the larger arrow for iron passing into solution as iron ions than for hydrogen ions (shorter arrow) moving to the metal surface and producing hydrogen gas. This imbalance is accommodated by electrons passing from the iron to the potentiostat. Conventional electric current flows in the opposite direction and is shown as the current, $i_{a,ex}$, to the iron. The potential of the iron is measured relative to a reference

Figure 1

Representation of uniform corrosion of iron in pH range where corrosion product layers form.

electrode such as the calomel half-cell. The potentiostat, when set for a desired potential of the iron relative to the reference electrode, is designed to pass a current which is the difference between the anodic and cathodic currents at the potential. If the desired potential is continuously changed, then a scan of potential-current values is obtained, a plot of which is a polarization curve for the metal/environment system.

A schematic representation of the polarization behavior of a metal capable of corroding in either the active or passive state is shown in Figure 3. The solid curve represents the potential of the metal relative to some reference electrode (here corrected to the standard hydrogen electrode (SHE)) as a function of the current density at the metal surface. The anodic polarization curve of the iron starts at E_m and increases to a maximum current density. Potentials in this region are associated with active corrosion and the corrosion rates may become very large near the maximum. Depending on the pH of the environment, the surface may remain clean (at low pH) or may progressively become coated with black Fe(OH)_2 or Fe_3O_4 for environments of progressively higher pH. Just past the maximum, the current density may decrease with the formation of a protective or passive film (related to Fe_2O_3). With additional increase in potential, the current density

Figure 2

Component arrangement for potentiostatic polarization. Specimen is shown anodically polarized.

remains relatively constant as the metal exists in the passive anodic state. At much higher potentials, the current density increases rapidly with disappearance of the passive film.

The cathodic hydrogen reaction occurs for potentials below E_H . The polarization curve is initially linear but as the potential is decreased, the rate of hydrogen ion consumption increases until a potential is reached at which the hydrogen ion concentration at the interface starts to become depleted. As this occurs, the availability of hydrogen ions becomes progressively controlled by diffusion from the bulk of the solution to the interface. Since the cathodic current is directly related to the interface hydrogen ion concentration, the current density continues to decrease from that given by the linear relationship and the polarization curve progressively curves downward. In fact there is a limiting current density at which the polarization curve becomes vertical and the rate of the cathodic reaction is totally controlled by the rate at which hydrogen ions can reach the surface by diffusion.

The individual anodic and cathodic polarization curves are shown as the linear dashed lines starting at E_M and E_H and then merging into the solid

Figure 3

Schematic polarization curve of a metal showing active and passive behavior. Dashed lines represent individual anodic and cathodic polarization.

experimental curves. The curves cross at E_{corr} where the anodic and cathodic current densities are equal; therefore the current density difference is zero and the experimental current density, on a log coordinate, goes to very small values. Below E_{corr} , the current density of the cathodic reaction is greater than that for the anodic reaction. The experimental current density is therefore net cathodic. Conversely above E_{corr} , the anodic current density is larger and the reaction is net anodic.

The behavior just described, linear extrapolations until the curves cross, provides a method of estimation of corrosion rates from an experimental polarization curve. That is, if an experimental curve is obtained of the form of Figure 3 with linear sections along the anodic and cathodic branches, the extrapolation of these linear section (the dashed lines) give an intersection at E_{corr} and i_{corr} . Faraday's law shows that the corrosion rate is directly proportional to i_{corr} and hence the rate is determined. The slopes of the

linear anodic and cathodic curves are referred to as the Tafel slopes and this procedure to obtain a corrosion rate is frequently referred to as Tafel extrapolation analysis.

Within the linear Tafel region, the current density as a function of the potential imposed by the potentiostat is

$$i = i_{\text{corr}} \left[10^{\frac{E - E_{\text{corr}}}{B_{\text{Fe}}}} - 10^{\frac{E - E_{\text{corr}}}{B_{\text{H}}}} \right] \quad (1)$$

In this equation, the Bs are the Tafel slopes of the iron anodic and hydrogen cathodic linear polarization curves, and E and i are the values of potential and current density along the solid curve near $E_{\text{corr}}, i_{\text{corr}}$. Experimentally, only the solid line is measurable and E_{corr} and i_{corr} are obtained by either the extrapolation method described above or by solving the above equation for these quantities. When distinct linear portions of the experimental curves are not present, mathematical methods are applied to Equation 1 from which values for the Bs, E_{corr} and i_{corr} giving the best fit to the experimental data are obtained. The method is an analytical Tafel analysis.

Polarization Resistance Analysis

If the experimental curve within ± 30 mV of $E_{\text{corr}}, i_{\text{corr}}$ is replotted on linear, rather than semi-log coordinates and with cathodic currents assigned negative values, a curve of the general form shown in Figure 4 is observed. The shape of the curve depends on the values of the Tafel slopes, B_{Fe} and B_{H} , and the slope through the origin is determined by i_{corr} . The following relationship can be derived from Equation 1 when applied to the curve near the origin:

A-6

Figure 4

Plot of current density and electrode potential on linear coordinates for polarization resistance analysis to determine corrosion rate.

$$i_{corr} = \frac{B_{Fe} B_H}{2.3(B_H + B_{Fe})} \quad (\Delta i / \Delta E) = B / R_p \quad (2)$$

where

$$B = \frac{B_{Fe} B_H}{2.3(B_H + B_{Fe})} \quad (3)$$

and

$$R_p = \Delta E / \Delta i \quad (4)$$

A-7

R_p is the slope of the curve as it passes through the origin of the linear coordinates; the dashed line in Figure 4 is representative of the graphical procedure for determining the slope. Since the slope has units of ohms, it is referred to as the polarization resistance.

The measurement for polarization resistance analysis may be made in several ways. With a potentiostat, steady state corrosion is established by monitoring the corrosion potential as a function of time. The potential is then offset a selected amount, usually 10 mV, from the corrosion potential and a scan made to the same amount of offset past the corrosion potential. The slope of the plotted values is then taken graphically or is determined using computer-based curve fitting programs. Since even a 10 mV offset can upset the interface corrosion processes, a slightly different polarization resistance value may result between measurements on increasing as compared to decreasing scans through the corrosion potential. The values are then averaged and used to calculate the corrosion rate.

An alternative to the above procedure is followed by the internal microprocessors incorporated in direct reading corrosion rate measuring instruments such as the Corrater 9030 (Rohrback Cosasco Systems). This instrument consists of a probe to which dual metal specimens, prepared as identically as possible, are attached. A potential of 20 mV is applied potentiostatically and the associated current measured. This moves one specimen 10 mV positive and the other 10 mV negative which, with the measured current, provides information equivalent to that given by the slope of the E,I curve of Figure 4. That is, the polarization resistance is given by 20 mV divided by the measured current. To accomplish this the instrument performs the following five steps, calculates the corrosion rate and displays the value digitally with selectable ranges of 0-1, 0-10, 0-100 and 0-1000 mils per year (mpy).

1. The short-circuit current between the electrodes is measured and value stored. (This is a measure of the imbalance in corrosion behavior of the supposedly identical dual electrodes)

A-8

2. The open circuit potential difference between the electrodes is measured and the value (E_{oc}) stored.
3. A potential of 20 mV is superimposed upon E_{oc} and the value of the resulting current is stored.
4. A potential of -20 mV is superimposed upon E_{oc} and the value of the resulting current is stored.
5. A high frequency voltage of 5 mV amplitude is superimposed and the value of the resulting current amplitude is stored. (the purpose of this step is to be able to measure the IR voltage drop between the electrodes due to the current passing between the electrodes. This part of the voltage difference is not associated with the electrochemical processes at the electrodes and a correction is made.

Comments on some assumptions and limitations in the use of the Corrater

The validity of the polarization resistance method of estimating corrosion rates is based on several assumptions with respect to both the applicability of the theory on which the method is based and the sensitivity of the metal/environment system to the measurement procedure. Brief comments follow on some of these assumptions and limitations:

It is assumed that the corrosion process is represented by Equation 1 and therefore that it and Equation 4 are valid expressions for calculating the corrosion rate. The basis for Equation 1 is that the anodic and cathodic reactions can be expressed as simple single activated processes involving transfer of electrons at the metal interface.

It follows from the above that the current density is controlled by the interface reaction rate and not by diffusion of species to or from the interface, not by interface corrosion products and not by a high solution ohmic resistance of the electrolyte.

It assumes that the anodic and cathodic reaction sites are uniformly distributed over the surface. That is, significant localized corrosion such as pitting is not present.

Direct use of Equation 2 requires that the value of B is known.

Availability of a correct value for B is a limitation of the polarization resistance, and hence Corrater, method. Calculation of B, according to Equation 3, requires values for the anodic and cathodic Tafel slopes which in turn are obtained from experimental polarization curves of the form shown in Figure 2. This requires that polarization curves be measured and that the curves show linear regions from which the slopes may be calculated. These complications frequently make it impractical to determine B. Some tables of B for various metal/environment combinations are available. It can be shown that in general the values vary by a factor of about 2 among many systems. The Corrater internal calculation sets $B = 27.5 \text{ mV}$.

In summary, the more serious concerns limiting the accuracy of corrosion rates determined by the polarization resistance method are uncertainty for the value of B, the effect of corrosion product formation on the surface (its uniformity, porosity and ability to function as a diffusion barrier) and diffusion limiting processes in the environment near the surface. Although these factors may lead to unacceptable agreement of corrosion rates determined with the Corrater with those based on weight-loss, establishment of a correlation between the two measurements for a given range of environments may be acceptable.

Effect of Aeration on Corrosiveness of Insulation Leachates and Additives

Results from both Corrater and potentiostat measurements show that corrosion rates of low carbon steel in insulation leachates and solutions of cellulose insulation additives can be sensitive to the availability of oxygen to the metal/environment interface. The observations are significant with respect both to procedures for conducting and interpreting the electrochemical measurements and to understanding the corrosiveness of insulations in service.

A-10

The following discussion is an interpretation of this behavior.

Two significantly different polarization curves are shown schematically in Figure 5. The curve to the right is representative of nearly saturated

Figure 5

Approximate polarization curves for iron in borax and ammonium sulfate, and for dissolved oxygen.

solutions of ammonium sulfate that have a pH of approximately 5.5. The curve to the left is representative of borax solutions with pH near 9. Curves for leachates from cellulosic insulations usually lie between these limits and may or may not show the active to passive state transition on increasing potential. It should be noted that the current densities in the passive regions and at the maximum in the anodic curve are several orders of magnitude greater for the ammonium sulfate environment. Also the passivating potential (potential of rapid decrease in current density) occurs at much lower potentials in the borax solution.

Included in Figure 5 are schematic polarization curves for the cathodic reduction of dissolved oxygen. At pH > 4, which applies to borax and ammonium sulfate solutions and to leachates from cellulosic insulation, the dominant cathodic reaction supporting corrosion is dissolved oxygen from contact with air (estimated to be 5-7 ppm oxygen in these solutions). Because of the low

hydrogen ion concentration at $\text{pH} > 4$, the reaction, $2\text{H}^+ + 2\text{e} \rightarrow \text{H}_2$ is insignificant. Rather the direct reduction of water ($2\text{H}_2\text{O} + 2\text{e} \rightarrow \text{H}_2 + 2\text{OH}^-$) tends to occur but the rate of this reaction is insignificant compared to the rate of the reaction of dissolved oxygen ($\text{O}_2 + 4\text{H}^+ + 4\text{e} \rightarrow 2\text{H}_2\text{O}$). For these reasons, the polarization curves for dissolved oxygen are the only ones shown in Figure 5. The oxygen polarization curve is initially linear at low current densities but deviates downward from the linear relationship as the current increases. This deviation is due to oxygen consumption at the interface which is progressively controlled by the rate of diffusion of oxygen to the interface. Two curves show this deviation. Curve (a) qualitatively represents the deviation for an aerated environment. Curve (b) represents the effect of deaeration; for example, by sparging the environment with nitrogen to decrease the amount of dissolved oxygen.

The corrosion current density (and therefore the corrosion rate) is determined by the intersection of anodic and cathodic curves applicable to a given metal/environment system. It is evident from the figure that the intersection occurs in the active region of the polarization curve for iron in aerated ammonium sulfate resulting in an i_{corr} near 10 microamperes/cm². If deaerated, i_{corr} would be near 2 microamperes/cm². In contrast, the oxygen curve intersects the iron polarization curve in borax in the passive potential range resulting in an i_{corr} near 0.1 microamperes/cm². The effects of diffusion control and aeration are illustrated in greater detail in Figure 6. The positions of the individual cathodic oxygen curves and the linear region of anodic curve for iron in ammonium sulfate can be related to the previous figure. The curves tending to very low current densities at E_{corr} are representative of experimental polarization curves obtained by scanning the potential from the net cathodic to net anodic potential range (see Figure 3). This expanded scale of plotting emphasizes the effect of aeration on the positions of the experimental polarization curves. Specifically, deaeration reduces both i_{corr} and E_{corr} . It also follows that if the environment is moving (pipe flow, stirring or oxygen sparging), the interface layer through which oxygen diffuses will be decreased allowing greater access of oxygen to the metal surface. The cathodic curves in Figures 5 and 6 move to higher current densities resulting in increased values of i_{corr} and hence higher corrosion rates.

Figure 6

Expanded portions of Figure 5 near the corrosion potentials and current densities for iron in aerated and deaerated ammonium sulfate.

These effects can be observed in some metal/environment systems (e.g. steel in cellulose leachates) using the Corrater. For example, after establishing steady state corrosion under stagnant conditions in contact with air, sparging the system with air will increase the indicated corrosion rate and sparging with nitrogen will decrease the rate.

Since the polarization resistance technique assumes linear polarization curves in the vicinity of the corrosion potential, the curvature introduced by

diffusion control may become a critical factor in limiting the accuracy of this electrochemical method for estimating corrosion rates.

Use of polarization curves to indicate susceptibility to localized corrosion

Polarization curves, particularly for metal/environment combinations capable of producing passive films, are frequently determined as a means of evaluating susceptibility to localized corrosion. The procedure, frequently referred to as a cyclic polarization scan, is to conduct a scan from E_{corr} into the passive potential range and determine if a significant increase in current density occurs at potentials below the transpassive range (see Figure 3 and E_{TP} in Figure 5). Localized corrosion in the form of pitting or crevice attack is associated with local breakdown of the passive film at a specific potential represented by E_{B} in Figure 5. The current density increases rapidly due to the high rate of corrosion within the local region. On reversing the potential, a loop is formed and the current density remains higher at a given potential than exists for the passive state on the initial upscan. The potential at which the current density returns to that observed on the initial upscan is referred to as the protection potential, E_{P} . The simple interpretation is that if an environment never raises the potential above E_{P} , then localized corrosion should not occur for the metal in the environment. Unfortunately neither E_{B} or E_{P} are safely defined values characterizing the metal/environment combination since their values may depend on the scan rate and E_{P} also on the current density at which the potential was reversed. Qualitatively, however, the higher the potentials of E_{B} and E_{P} and the smaller the cyclic loop, the lower the probability that localized corrosion will occur. If there is no breakdown to localized corrosion, the cyclic scan can be carried to E_{TP} and perhaps higher potentials and on reverse the curve will pass to lower current densities than on the upscan showing that the passive film is becoming even more protective. Thus, in summary, if the cyclic polarization measurement to near E_{TP} results in a downscan curve to the left of the upscan curve, susceptibility to localized corrosion is small or nonexistent; otherwise a loop will be observed indicating susceptibility to localized corrosion if the cathodic reactant in the environment is capable of inducing E_{corr} in the potential range of the loop.

INTERNAL DISTRIBUTION

- 1-5. G. L. Burn
6. R. S. Carlsmith
7. J. E. Christian
8. G. E. Courville
9. D. F. Craig
10. A. O. Desjarlais
11. T. G. Kollie
12. M. A. Kuliasha
13. D. L. McElroy
14. R. B. Shelton
- 15-16. Central Research Library
17. Document Reference Section
- 18-19. Laboratory Records Department
20. Laboratory Records (RC)
21. ORNL Patent Section
22. M&C Records Office

EXTERNAL DISTRIBUTION

23. Adamczyk, E., Manville Corp., Denver, CO
24. Alumbaugh, R. L., Naval Civil Engineering Lab, Port Hueneme, CA
25. Andersen, J., Foam Enterprises, Minneapolis, MN
26. Andrews, G., Fiber Products Corp., Colton, CA
27. Applegate, T., Applegate Insulation, Okemos, MI
28. Baker, A. J., Forest Products Laboratory, Madison, WI
29. Bankvall, C., Swedish National Testing & Research Institute, Boras, Sweden
30. Baumgardner, R. L., Stroudsburg, PA
31. Berg, D., National Roofing Contractors Association, Rosemont, IL
32. Bhattacharjee, D., Dow Chemical USA, Freeport, TX
33. Black, A., Bradford Enercon, British Columbia, Canada
34. Bomberg, M., National Research Council of Canada, Ontario, Canada
35. Boulin, J. J., DOE, Washington, DC
36. Boyer, H., National Cellulose Corp., Houston, TX
37. Braun, S., MIMA, Alexandria, VA
38. Bromley, B. W., American Rockwool, Inc., Spring Hope, NC
39. Brower, G., Knauf Fiberglass, Shelbyville, IN
40. Buchsbaum, D., LBJ Corp., Columbia, MD
41. Building Research Association of New Zealand, Inc., Porirua, New Zealand
42. Carlson, T., USG Corp., Libertyville, IL
43. Chrenka, G., Nu-Wool, Jenison, MI
44. Chu, G., Dow Chemical Canada, Inc., Ontario, Canada

45. Clayville, C., Clayville Insulation, Burley, ID
46. Cline, H., Owens-Corning Fiberglas, Granville, OH
46. Colwell, J., Manville Corp., Denver, CO
48. Cusick, E. F., Rock Wool Manufacturing Co., Leeds, AL
49. Davis, R., Mason, MI
50. Dowds, T., CertainTeed Corp, Blue Bell, PA
51. Drummer, W., Electra Manufacturing Corp., Granville, OH
52. DuPuis, R. M., Structural Research, Inc., Middleton, WI
53. Edmunds, W., Owens-Corning Fiberglas, Granville, OH
54. Eggers, W. J., EG&G, Princeton, NJ
55. Ellis, W. P., Standards Consultant, Harleysville, PA
56. Fairey, P., Florida Solar Energy Center, Cape Canaveral, FL
57. Fesler, R. P., Freudenberg Spunweb Co., Durham, NC
58. Gallagher, K. J., CertainTeed Corp., Blue Bell, PA
59. Gaul, D. J., Owens-Corning Technical Center, Granville, OH
60. Gerrish, R., Pittsburgh Corning Corp., Pittsburgh, PA
61. Gilbo, C. F., Journal of Thermal Insulation, Lancaster, PA
62. Goldsmith, J. C., DOE, Washington, DC
63. Goss, W. P., University of Massachusetts, Amherst, MA
64. Grether, T., Owens-Corning Fiberglas, Toledo, OH
65. Grube, R., Armstrong World Industries, Lancaster, PA
66. Harner, M., CertainTeed Corp., Blue Bell, PA
67. Harris, T., BASF Canada, Inc., Ontario, Canada
68. Harshaw, B. D., Central Fiber Corp., Wellsville, KS
69. Hauser, R., Hauser Laboratories, Boulder, CO
70. Hutto, F., PABCO Insulation, Fruita, CO
71. Kaus, J. Jr., E. I. DuPont Engineering Department, Newark, DE
72. Keating, D., Incide Technologies, Inc., Phoenix, AZ
73. Keeler, D., Dow Chemical USA, Granville, OH
74. Kifer, E. W., Thermal Products International, Pittsburgh, PA
75. Kingsbury, R., Underwriters Laboratory, Inc., Northbrook, IL
76. Kochhar, G. S., University of West Indies, Trinidad, West Indies
77. Kosman, R., Incide Technologies, Inc., Phoenix, AZ
78. Kudder, R. J., Rath, Rath, & Johnson, Inc., Willowbrook, IL
79. Lacher, M., CertainTeed Corp, Valley Forge, PA
80. Lane, R., National Borax, Cave In Rock, IL
81. Larsen, R., Manville Service Corp., Denver, CO
82. Leger, G., Leger Designs, New Boston, NH
83. Leuthold, R., Fiber-Chem, Inc., Bucyrus, OH
84. Lichtenberg, F. W., The Society of the Plastics Industry, New York, NY
85. Lohman, D. J., Cincinnati Fiber, Cincinnati, OH
86. Martin, R. F., Roof Maintenance Systems, Farmingdale, NJ
87. Mattigetz, R., Reichhold Chemical, Ltd, Ontario, Canada
88. Mayer, R., Allied-Signal Corp., Hopewell, VA
89. McBride, M. F., Owens-Corning Fiberglas, Granville, OH
90. McClurg, G., National Borax Corp., Cleveland, OH
91. McCrudden, B., Lehigh Testing Labs, Inc., New Castle, DE
92. McGillvary, D. R., Firestone Building Products Company, Carmel, IN
93. McGuire, D., Regal Industries, Inc., Crothersville, IN
94. Meinel, M., Fiber Master Corp., Monroe, LA

95. Mentzer, K. D., MIMA, Alexandria, VA
96. Miller, R. G., Jim Walter Research Corp., St. Petersburg, FL
97. Miller, S., Insulations, Inc., Harahan, LA
98. Mulroy, P., Black Gold, Inc., Topeka, KS
99. Mumaw, J. R., Owens-Corning Fiberglas, Granville, OH
100. Noonan, P., Knauf Fiber Glass, Shelbyville, IN
101. Ober, D. G., Manville Corp., Denver, CO
102. Poppendiek, H. F., Geoscience, Ltd., Solana Beach, CA
103. Portfolio, D. C., Tremco, Inc., Cleveland, OH
104. Radmon, I., Western Fiberglass, Inc., Salt Lake City, UT
105. Ray, R. J., Manville Sales Corp., Denver, CO
106. Remmele, P., Morton Buildings, Inc., Morton, IL
107. Roberts, H. J. Jr., RMAX, Inc., Dallas, TX
108. Rossiter, W., NIST, Gaithersburg, MD
109. Scofield, M. P., DOE, Washington, DC
110. Shen, K., U.S. Borax Research Corp., Anaheim, CA
111. Sheppard, K., Stevens Institute of Technology, Hoboken, NJ
112. Sherman, M., St. Petersburg, FL
113. Shirliffe, C. J., National Research Council of Canada, Ontario, Canada
114. Shu, L. S., W. R. Grace and Co., Cambridge, MA
115. Sievert, G., The Society of the Plastics Industry, Inc., Washington, DC
116. Skinner, A., Roofing Services Associates, Inc., Knoxville, TN
117. Smelser, R. D., Knauf Fiberglass, Shelbyville, IN
118. Smith, D., Comfort insulation, Bend, OR
119. Smith, G. A., Factory Mutual Research Corp., Norwood, MA
120. Smith, I. T., Southern Cellulose, Atlanta, GA
121. Smith, J. A., NAHB, Washington, DC
122. Smith, S. E., Yankee Scientific, Ashland, MA
123. Smith, T. L., NRCA, Rosemont, IL
124. Springer, B., Solarite Insulation, Sabattus, ME
- 125-134. Stansbury, E. E., Knoxville, TN
135. Stern, E., Quebec, Canada
136. Strzepek, B., Dow Chemical USA, Granville, OH
137. Stumpf, F. M., Dalen Corporation, Netcong, NJ
138. Sullivan, R., National Center for Appropriate Technology, Butte, MT
139. Szoke, S. S., National Concrete Masonry Assoc., Herndon, VA
140. Tewes, S., Small Homes Council - Building Research Council, Champaign, IL
141. Tong, T. W., Arizona State University, Tempe, AZ
142. Troyer, R., Manville, Service Corp., Denver, CO
143. Tuluca, A., Steven Winter Associates, Norwalk, CT
144. Tye, R. P., Cohasset, MA
145. Tyler, F., Fiberglas of Canada, Inc., Ontario, Canada
146. Vander Linden, C. R., Vander Linden and Associates, Littleton, CO
147. Waldo, J., Pittsburgh Corning Corp., Pittsburgh, PA
148. Watson, J., USG Industries, Inc., Chicago, IL
149. Weil, R., Stevens Institute of Technology, Hoboken, NJ
150. Whelan, B. J., Sarnafil, Inc., Canton, MA
151. Williams, D., Dow Chemical USA, Freeport, TX
152. Wilson, K. E., Fiberglas Canada, Inc., Ontario, Canada
153. Wojtechko, B., UC Industries, Tallmadge, OH

154. Zenor, G. N., JPS Elastomerics Corp., Northampton, MA
155. U.S. Department of Energy, Oak Ridge Field Office, P.O. Box 2008, Oak Ridge, TN 37831-8600
- 156-165. U.S. Department of Energy, Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831

**DATE
FILMED**

2 / 14 / 92