DOE/ER/45072--46

DE92 007711

**Amplitude Modulation of Charge-Density-Wave Domains
in 1T-TaS₂ at 300 K**

by

R. V. Coleman, W. W. McNairy and C. G. Slough

**Physics Department
University of Virginia
Charlottesville, VA 22901**

Abstract

Measurements of the charge-density-wave (CDW) amplitude modulation in 1T-TaS₂ at room temperature have been made using a scanning tunneling microscope (STM) operating in the constant current mode. The amplitude profiles are in good agreement with the profile predicted by the CDW domain model of Nakanishi and Shiba. Interference effects between the atomic and CDW lattices have been analyzed and do not modify these profiles significantly. They represent the true CDW amplitude variation connected with the CDW domain structure.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

FEB 12 1992

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

The transition metal dichalcogenide¹ TaS₂ can be grown in a number of different phases all of which exhibit the onset of charge-density-waves (CDW's) at some critical temperature. The 1T phase exhibits the strongest CDW with an onset temperature of ~ 600 K. After forming below 600 K the CDW in turn exhibits a number of distinct phases within specific temperature ranges. The initial phase is incommensurate with the lattice with a wave vector aligned along the lattice direction. At 350 K the CDW wave vector rotates to an orientation making an average angle of ~ 11° to the lattice and increases in length. At room temperature the average rotation angle has increased to 11.9°. As the temperature is lowered from 350 K two distinct nearly commensurate (NC) phases have been identified in x-ray² and electron diffraction^{3,4} experiments. Details of these phases as developed from diffraction experiments have been reviewed by Withers and Wilson.⁵

The NC phase designated 1T₂ occurs on cooling between 350 and 280 K and exhibits a threefold symmetry with respect to the wave vector positions. A second NC phase designated as the T phase exists upon warming between 220 and 280 K and exhibits a broken threefold symmetry. At ~150 K the CDW wave vector rotates to 13.9° and the CDW structure remains uniformly commensurate at lower temperatures.

The existence of domain structure in the NC phases of 1T-TaS₂ was first suggested by the presence of satellites in the electron diffraction^{3,4} patterns and by the need for higher harmonics in the analysis of photoemission data.⁵ Nakanishi and Shiba⁶ developed a domain model based on a free energy analysis which predicted a specific amplitude and phase variation for the domain structure in the NC phase that exists near room temperature. The CDW amplitude was predicted to vary by ~ 40% across the domain, while the phase varied more rapidly near the boundaries and more slowly near the center of the domain. This leads to a nearly commensurate region near the center of the domain. The predicted domain structure applicable to the room temperature phase suggested fairly wide boundaries (discommensurations) comprising at least 50% of the domain area.

Real space STM images showing a clear indication of this CDW domain structure were first published by Wu and Lieber.^{7,8} However, no careful amplitude measurements were presented in those

papers and it was suggested that the amplitude showed localized variations in the boundaries. Giambattista et al.⁹ and Slough et al.^{10,11} also studied the amplitude variations and concluded that the amplitude showed a continuous variation with no localized changes.

The real space data cannot be used to obtain accurate phase information so that a complete comparison to the model of Nakanishi and Shiba⁶ cannot be made from real space data alone. Phase information can be obtained by analyzing the position and intensity of satellites in the Fourier transforms of large area scans as reported by Burk et al.¹² However, careful amplitude measurements from STM scans in the constant current mode are completely consistent with the predictions of Nakanishi and Shiba⁶, and we present an experimental analysis of the amplitude data in this report.

The analysis shows that the original amplitude data published by Giambattista et al.⁹ and Slough et al.^{10,11} is a true measure of the CDW amplitude modulation and is consistent with the CDW domain model of Nakanishi and Shiba⁶. The direct real space amplitude data reported in those papers are not modified by interference as suggested by Burk et al.¹² on the basis of an incomplete analysis of the interference effects. This more recent paper by Burk et al.¹² also extracted data on the amplitude variation by analysis of satellites in the Fourier transforms and the previous amplitude data^{9,10} are in agreement with those results.

The real space amplitude measurement⁹ can be complicated by the simultaneous presence of both the CDW amplitude and the amplitude due to the surface S atoms. This produces an interference effect leading to a pseudo domain structure which would be present even if the CDW's were not amplitude modulated.¹² This pseudo domain structure will be out-of-phase with the CDW domain structure and even when the ratio of atomic to CDW amplitude is significant will produce only limited amplitude modification in the interstitial regions of the CDW domain pattern.

We present a brief analysis of this problem and argue that for most STM scans the measured STM amplitude variation is completely dominated by the CDW domains. Furthermore, the observed amplitude variation is in good agreement with that expected from the Nakanishi and Shiba⁶ model. The analysis is based on two conclusions with regard to the STM observations. First, that the surface

S atomic core potentials modulate the conduction electrons and produce the atomic pattern observed in STM scans: Second, in the STM scans that the CDW maxima at the commensurate positions are located over Ta atoms in the layer below. The first conclusion, although theoretically reasonable, has not been experimentally proved for the STM response. However, AFM scans^{10,13} show exactly the same patterns of atoms and CDW maxima for 1T-TaS₂ and 1T-TaSe₂ that are observed in the STM scans. In the AFM scans the surface S or Se atoms clearly dominate the force modulation and therefore the AFM image.

All of the STM and AFM scans show 7 atom groups at CDW maxima with an asymmetric intensity leading to enhanced 3 atom clusters. (See Figs. 6 and 7 in Ref. 9 for STM and Figs. 2 and 4 in Ref. 10 for AFM). In the commensurate state this occurs around every CDW maximum while in the NC state it occurs at the CDW maximum at the center of the domain. (See 3 atom clusters in Fig. 27 in Ref. 10 and Fig. 1(b) in Ref. 8). These patterns are all consistent with a CDW maximum located over a Ta atom at a horizontal distance of $a_0/\sqrt{3}$ from the surface S atoms. This conclusion applies to all of the CDW patterns so far studied by STM using layer structure crystals. Data and information on nine different layer structure CDW systems have been reviewed by Coleman et al.¹⁴

In the case of AFM scans where the CDW and atomic amplitude modulations are comparable, the interference effect can make a more substantial contribution. AFM scans published by Slough et al.¹⁰ and by Garnes et al.¹³ show a modulated structure, but the hexagonal domain structure observed in STM scans is not clearly resolved. The repeat distance of the long range modulation is observed to be ~ 6 CDW wavelengths, but some fluctuations are observed which depend on the direction and position of a given scan profile.

In the majority of STM scans recorded in the constant current mode the atomic modulation amplitude is a small fraction of the CDW modulation. Interference effects will be extremely small in such scans and the dominant structure is that due to the CDW domains. An example of the CDW domain structure is shown in Fig. 1 where the computer look up table (LUT) has been adjusted to emphasize the two-dimensional domain structure produced by the CDW amplitude modulation. Fig. 2

shows profiles of the CDW maxima obtained by averaging the profiles across four separate domains in an original grey scale STM image of 1T-TaS₂. The solid line in Fig. 2(a) represents the variation of the maxima of one CDW component in the model of Nakanishi and Shiba⁶ as calculated by Burk et al.¹² The absolute CDW amplitude in the calculated curve has been scaled to match the experimentally observed maximum CDW amplitude as measured from maximum to minimum at the center of the domain. The experimentally observed profile is extremely close to the profile calculated from the Nakanishi and Shiba⁶ model and indicates a domain width of approximately 6 CDW wavelengths and an amplitude modulation of 0.53. Fig. 2(b) shows a sine wave fit to the same profile as indicated by the solid line. When compared to the sine wave, the experimental profile indicates a depressed CDW amplitude at the minimum of the domain boundary consistent with the presence of higher harmonics, and therefore a better fit to the data occurs for the Nakanishi and Shiba⁶ calculation as shown in Fig. 2(a).

The amplitude profile data are not sufficiently accurate for a quantitative measurement of the higher harmonic content, but the magnitude and shape are clearly consistent with the Nakanishi and Shiba⁶ CDW domain model. The interference domain centers are not aligned with the CDW domain centers and an interference contribution would show a left-right asymmetry in the profile. (see Fig. 3). The individual profiles in the average are recorded in the same direction and are aligned within an atomic spacing. The profile would exhibit left-right asymmetry if strong interference were present. Although the interference pattern repeats at a distance of ~ 6 CDW wavelengths, it creates a pseudo domain pattern out-of-phase with the true CDW domain pattern. The maximum CDW amplitude occurs at the center of the CDW domain when the CDW is in phase with the Ta atom centered in the 13 atom cluster in the middle layer of the three layer sandwich. This location occurs at the minima of the interference pattern since, at this point the CDW maximum is centered between three surface S atoms a distance $a_0/\sqrt{3}$ from each. The maxima of the interference pattern will occur when the CDW maxima are out-of-phase with the Ta atoms and are located at the surface S atom positions. Figure 3 shows a diagram of the relative positions of the CDW maxima and the surface S atoms for

the NC phase with an average relative orientation of 11.9° and with a CDW wavelength of 11.685 Å.

The model presented in Figs. 3 and 4 represents a uniformly incommensurate CDW lattice with an average wavelength and angle corresponding to an 18×5 rotated superstate with a uniform CDW amplitude. The actual CDW superstate is modulated in both phase and amplitude and therefore exhibits local deviations from an average angle and wavelength. It may also deviate from the 18×5 superstate based on initial observations of rotation angles between the CDW domain centers and the CDW lattice. Such wavelength modifications or deviations from the 18×5 superstate (for example the $19\frac{1}{2} \times 2\frac{1}{2}$ superstate with a slightly different wavelength) will not affect the basic conclusions about the phase of the interference domain relative to the CDW domains. The CDWs at the domain centers are always commensurate and this sets the minimum of the interference domain. The present arguments do not require an exact detailed model of the local CDW variations even if reliable local data could be derived from a complex analysis of the available data.

The pseudo domain structure resulting from the interference effect is demonstrated in Fig. 4. The CDW and atomic lattices have been each represented by three sine waves with each set rotated by 11.9° and having an amplitude ratio of 2. This pseudo domain pattern due to interference will be out-of-phase and translated with respect to the true CDW domain structure. Appreciable interference due to an enhanced atomic amplitude will contribute an enhanced seven atom cluster in three of the six interstitial regions of the true CDW domain structure. The amplitude profiles through these regions will begin to show some modification and the overall CDW domain pattern will show a spatial variation. STM scans such as the one analyzed in Figs. 1 and 2 show no evidence of an interference contribution and are completely dominated by the CDW domain structure. In addition, even when the atomic amplitude is enhanced the interference maxima do not fall along directions which are aligned with the CDW superlattice vectors and which connect approximate domain centers (See Fig. 3). Therefore profiles such as those shown in Fig. 2 would not be appreciably affected by interference even in STM scans where the atomic amplitude is significant. A computer generated pattern with the atomic amplitude equal to 50% of the CDW maximum amplitude and with the CDW

amplitude modulated by $\sim 40\%$ is shown in Fig. 5. The dominant hexagonal domain structure is that generated by the modulated CDW amplitude. The maxima of the interference domains occur as seven atom clusters in three of the interstitial regions of the CDW domain structure. These are clearly visible, but contribute a modulation structure of considerably less amplitude than the dominant CDW domain structure. However, the presence of appreciable atomic amplitude does produce apparent phase slips in the CDW pattern when sighting along CDW maxima running through the CDW domain centers. The modulation of the amplitude and phase of the CDW will be accompanied by a local variation of CDW wavelength and orientation. This will modify the interference pattern to some degree but will be a relatively small change from the interference pattern generated by the models using an average angle of 11.9° .

AFM scans^{10,13} of 1T-TaS₂ show a clear amplitude modulation and domain structure. However, the hexagonal domain pattern is not as well defined as in STM scans and the long range modulation length, although close to 6 CDW wavelengths, shows some fluctuation. Domain centers where three equal modulation profiles intersect are not as well defined as in STM scans. Superposition of a strong interference pattern on the CDW modulation domain structure might be expected to produce a similar pattern and further analysis will be required for AFM data.

We conclude that the STM scans in which the CDW amplitude is dominant show an amplitude modulation which scales with the absolute CDW amplitude and fits very well to the modulation predicted by the Nakanishi and Shiba⁶ model. The interference pattern contribution in these scans is not significant. In STM scans where the atomic amplitude is substantial and in AFM scans the interference domains and the amplitude modulation from the true CDW domains are out-of-phase and the superposition can produce a modulated structure which is modified from the true CDW domain structure. However, even in these scans the domain structure generated by the $\sim 50\%$ modulation of the CDW's amplitude would be expected to dominate, and profiles through the center of the CDW domains would not be strongly modified. A complete analysis of such scans would require separation of these two components in the real space image. Calculation of both the amplitude

and phase variation can be made from Fourier transforms of large area scans as carried out by Burk et al.¹² using a constant height STM mode. The direct amplitude measurements obtained in the constant current STM mode as reported here and previously^{9,10,11} give highly accurate local amplitude data. The real space STM images as published^{7,8,9,10,11} show a modulated CDW amplitude structure that reflects the true CDW domain structure. Interference effects have not been significant in those scans and they clearly show the existence of amplitude modulated CDW domains. The amplitude data analyzed here are completely consistent with the Nakanishi and Shiba⁶ model which has been confirmed in detail by the STM results of Burk et al.¹²

Acknowledgements

This work has been supported by the U.S. Department of Energy, Grant No. DE-FG05-84ER45072. Useful discussions have been held with L. M. Falicov, P. K. Hansma, A. Zettl, John Clarke, B. Burk, R. E. Thomson, V. Celli and J. Garnes. We thank A. Zettl for communicating results from the Berkeley research group prior to publication.

References for the Brief Report 6/91

1. J. A. Wilson, F. J. Di Salvo, and S. Majahan, Adv. Phys. **24**, 117 (1975).
2. Akiji Yamamoto, Phys. Rev. B **27**, 7823 (1983).
3. S. Tanda, T. Sambongi, T. Tani, and S. Tanaka, J. Phys. Soc. Jpn. **53**, 476 (1984).
4. J. A. Wilson, J. Phys.: Condes. Matter **2**, 1683 (1990).
5. R. L. Withers and J. A. Wilson, J. Phys. C **20**, 4809 (1986).
6. K. Nakanishi and H. Shiba, J. Phys. Soc. Jpn. **43**, 1839 (1977).
7. Xian-Liang Wu and Charles M. Lieber, Science **243**, 1703 (1989).
8. Xian-Liang Wu and Charles M. Lieber, Phys. Rev. Lett. **64**, 1150 (1990).
9. B. Giambattista, C. G. Slough, W. W. McNairy, and R. V. Coleman, Phys. Rev. B **41**, 10082 (1990).
10. C. G. Slough, W. W. McNairy, R. V. Coleman, J. Garnaes, C. B. Prater, and P. K. Hansma, Phys. Rev. B **42**, 9255 (1990).
11. C. G. Slough, W. W. McNairy, Chen Wang, and R. V. Coleman, J. Vac. Sci. Technol. B **9**, 1036 (1991).
12. B. Burk, R. E. Thomson, A. Zettl, and John Clark, Phys. Rev. Lett. **66**, 3040 (1991).
13. J. Garnaes, S.A.C. Gould, P. K. Hansma, and R. V. Coleman, J. Vac. Sci. Technol. B **9**, 1032 (1991).
14. R. V. Coleman, B. Giambattista, P. K. Hansma, A. Johnson, W. W. McNairy, and C. G. Slough, Adv. Phys. **37**, 559 (1988).

Figure Captions

1. High contrast image of a STM scan of 1T-TaS₂ at 300 K. The computer look up table (LUT) has been adjusted to emphasize the existence of a strong CDW amplitude variation. The hexagon of domains is rotated $\sim 5-6^\circ$ from the CDW superlattice orientation. (From Reference 10).
2. (a) Profile of CDW maxima obtained by averaging profiles across 4 separate domains in the original grey scale image from which Fig. 1 was generated. The solid line represents the amplitude variation of the maxima of one CDW component of the Nakanishi and Shiba⁶ domain model as calculated by Burk et al.¹¹. The calculated solid curve has been scaled to match the experimentally observed maximum CDW amplitude in the center of the domain. The experimentally observed relative amplitude variation is 0.54 and the calculated variation is 0.63.
(b) Experimentally observed profile of the CDW amplitude compared to a sine wave (solid line). At the center of the domain boundary the amplitude is consistently less than that required to match a sine wave.
3. Plot of the relative positions of both the CDW maxima and the surface S atom positions for a relative angle of 11.9° between the atomic lattice and the CDW lattice with a CDW wavelength of 11.685 Å. Large circles are CDW domain centers. Small circles are interference domain centers.
4. Computer modeled image of the pseudo domain structure generated from the interference between the CDW and S atomic lattices for an average relative orientation of 11.9° . Each lattice is represented by 3 sine waves of uniform amplitude and a CDW to atomic amplitude ratio of 2.
5. Computer generated image including both the CDW and atomic lattice with the CDW amplitude modulated by 50% and a ratio of maximum CDW amplitude to atomic amplitude of 2. The dominant domain structure in this model is that formed by the CDW amplitude modulation. The interference domain centers as shown in Fig. 4 appear as 7 atom clusters in 3 of the 6 interstitial regions.

H
1 nm

FIG. 1

FIG. 2(a)

FIG. 2(b)

FIG. 3

1 nm

FIG. 4

10 nm

FIG. 5

END

**DATE
FILMED**

3 / 16 / 92