DOE/PC/88812--T10

**PROCESS AND ANALYTICAL STUDIES OF ENHANCED LOW
SEVERITY CO-PROCESSING USING SELECTIVE COAL
PRETREATMENT**

DOE/PC/88812--T10

DE92 004861

**R.M. Baldwin and R.L. Miller
Chemical Engineering and Petroleum Refining Dept.
Colorado School of Mines
Golden, CO 80401**

**Quarterly Technical Progress Report for the Period
June - August, 1990**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DOE Contract No. DE-AC22-88PC88812

AMF
DEC 30 1991
MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Nov 9 1997

ABSTRACT

This report describes progress on research during the seventh quarter of this contract dealing with applications of coal pretreatment techniques in coal hydroliquefaction. The objectives of the project are to investigate various coal pretreatment techniques and to determine the effect of these pretreatment procedures on the reactivity of the coal. Reactivity enhancement will be evaluated under both direct hydroliquefaction and co-processing conditions. Coal conversion utilizing low rank coals and low severity conditions (reaction temperatures generally less than 350 °C) are the primary focus of the liquefaction experiments, as it is expected that the effect of pretreatment conditions and the attendant reactivity enhancement will be greatest for these coals and at these conditions.

This document summarizes the results of research performed during the past quarter dealing with the effects of solvent swelling as a pretreatment method. Additionally, baseline data on the effect of stage I reaction conditions on the reactivity of coal-derived intermediates was completed during the past quarter. The swelling studies during the past quarter have focused on the effect of reaction severity on reactivity enhancement in terms of conversion of a low rank (Wyodak) coal to both THF and hexane solubles. In general, the effect of solvent swelling on reactivity has been found to be small for coals that have been subsequently liquefied under direct hydrogenation

reaction conditions. The effect of swelling on reactivity has also been found to be a function of drying conditions.

Baseline data on the effect of stage I reaction severity on the reactivity of coal-derived intermediates is now complete for two low rank coals from the Argonne Premium Coal sample bank. The effect of catalyst and processing environment (direct hydroliquefaction and co-processing) has been determined at both low and high severity conditions, and the conversion of coal to THF and hexane solubles determined quantitatively. These pseudo-stage I data will serve as reference points for the subsequent evaluation of stage II reactivity and distillate yield.

SUMMARY OF TECHNICAL PROGRESS

Solvent Swelling

Background: Current models for coal structure depict coal as a macro-polymer with repeating groups consisting of discrete units in the form of condensed aromatic clusters. These units are interconnected by covalent crosslinks. This molecular network is, however, extensively cross-linked by a variety of non-covalent bonds including localized and non-localized polar (electrostatic) interactions caused by the presence of electro-negative heteroatoms such as oxygen, and short range a-polar electrodynamic forces (e.g. van der Waals). It is well known that certain coals will imbibe certain solvents, with a volumetric expansion taking place. This swelling of the coal is thought to be due to disruption of these non-covalent intermolecular forces.

As a portion of this research program, the effect of solvent swelling on the reactivity of coal under both direct hydroliquefaction and coal/oil coprocessing reaction conditions is to be determined. During the past quarter, extensive data on the effect of swelling as a pre-treatment method for reactivity enhancement has been collected for Wyodak subbituminous coal.

Experimental: The effect of solvent swelling on coal reactivity has been extensively investigated over the past quarter for a low rank coal (Wyodak subbituminous) from the Argonne Premium Coal sample bank. Prior to liquefaction, the sample was swollen in THF for 3 hours following the

procedures outlined in the literature by Green et al. (1). THF is an effective swelling solvent for Wyodak coal, and the measured volumetric swelling ratio for this coal/solvent system was 1.5. After swelling for the prescribed time period, the swelling solvent was removed by vacuum rotary evaporation followed by drying in a high vacuum system at 100 °C for 2 hours. Raw Wyodak coal was dried under similar conditions for 24 hours prior to baseline liquefaction. In both cases (raw and swollen coal), the measured "moisture" content of the coals was zero (following ASTM moisture analysis procedures). In some cases, the raw coal was dried prior to swelling in order to determine the effect of water on the swelling process.

Liquefaction of the coals proceeded in tubing bomb microautoclave reactors (Figures 1 and 2). Reaction conditions included temperatures of 350, 375, 400, 425, and 450 °C for reaction times of both 5 and 30 minutes (at temperature). Nominal heat-up time for the 20 cm³ reactors employed in this system is on the order of 90 to 120 seconds. Tetralin (1,2,3,4-tetrahydronaphthalene) was used as the reaction vehicle in all cases in a 1/2 coal to solvent ratio (wt/wt). Coal conversion was measured for THF and hexane solubles by extraction with THF followed by precipitation of asphaltenes and preasphaltenes from the THF soluble solution with hexane in order to determine both total conversion and yield of "distillate". Conversion of

FIGURE 1
REACTION SYSTEM SCHEMATIC

FIGURE 2
TUBING-BOMB MICROAUTOCLAVE

coal to both solvent soluble classifications was calculated by the following expression:

$$\text{conversion (maf)} = \frac{(\text{insols in} - \text{insols out})}{\text{insols in}}$$

where: insols in = measured mass of THF or hexane insolubles into reactor (moisture and ash-free basis);

insols out = measured mass of THF or hexane insolubles after reaction (moisture and ash-free basis).

In both cases, the measured insols have been corrected for intrinsic THF and hexane solubles in the parent and swollen coal samples.

Results: Data for conversion of both raw and swollen Wyodak coal to THF and hexane solubles are shown in Table 1. In general, the data indicate that little if any reactivity change (either positive or negative) is promoted by application of solvent pre-swelling of coal. Conversion of coal to both THF and hexane solubles is essentially identical for both the parent coals and the swollen coal samples at both low and high severity. These data may be somewhat confounded by the drying process utilized in stripping of the swelling solvent, and this possibility will be investigated in more detail during the next quarter.

Reactivity of Coal-Derived Intermediates: The second phase of this research program is concerned with an experimental evaluation of the effect of the severity of stage I coal dissolution conditions on the reactivity of coal-derived intermediates. The concept under investigation

TABLE I
REACTIVITY DATA, WYODAK COAL

		5 MINUTES		30 MINUTES	
		HEX	THF	HEX	THF
350 °C	raw				
	swollen	6.9	16.1	20.4	31.5
	dry/swell	3.9	20.2	14.2	31.1
375 °C	raw	19.6	29.9	35.6	51.5
	swollen	16.9	30.3	36.4	49.3
400 °C	raw	31.2	42.1	44.0	62.9
	swollen	22.6	39.7	42.7	63.5
	dry/swell	32.6	42.3	50.1	64.2
425 °C	raw	51.8	62.8	65.8	82.1
	swollen	47.8	63.9	63.1	82.9
450 °C	raw	58.4	79.4	76.8	91.5
	swollen	61.6	78.0	74.5	92.3

All coals swollen in THF for 3 hours followed by removal of swelling solvent prior to liquefaction. Liquefaction at the stated time and temperature conditions in tetralin vehicle.

is shown schematically in Figure 3. Two-stage coal liquefaction involves dissolution in a stage I reaction vessel followed by catalytic hydroprocessing of the coal-derived intermediates in an ebullated bed reactor (stage II). The major economic problems concerning commercial application of this process are

- 1) excessive hydrocarbon gas make
- 2) high hydrogen consumption
- 3) high catalyst replacement rate (stage II)

In all cases, lowering the severity of reaction (especially temperature) will help to alleviate these problems. Lowering the severity of the stage I coal dissolution step should produce less refractory coal-derived intermediates that can be more readily upgraded at lower severity in the stage II reaction vessel, thus lowering hydrogen consumption and reducing the rate of catalyst deactivation due to coking. Reduced severity of operation in stage I will, however, mandate that some coal pretreatment method be used to maintain acceptable conversion levels. Examination of alternate reactivity enhancement schemes has been the focus of the first phase of this project, and these studies are currently being completed with the solvent swelling run matrix.

Data on the effect of reaction conditions (temperature and catalyst) on the conversion of three coals from the Argonne Premium Coal sample bank to THF and hexane solubles is shown in Table 2. Raw data for these runs is shown in

FIGURE 3

SCHEMATIC REPRESENTATION OF TWO-STAGE LIQUEFACTION

TABLE 2

RESIDUUM REACTIVITY DATA

COAL CONVERSION BASIS >			THF SOLUBLES		HEXANE SOLUBLES	
REACTION GAS >			HYDROGEN	HYDROGEN	HYDROGEN	HYDROGEN
CATALYST TYPE >			NONE	NiMo/Al ₂ O ₃	NONE	NiMo/Al ₂ O ₃
COAL	SOLVENT	TEMP				
WYODAK	1 - MN	350 C	25.1	47.4	21.9	48.2
			26.2	39.9	21.1	38.7
		425 C	68.3	91.9	61.7	91.9
			65.2	96.9	56.3	96.9
	A - 9	350 C	20.6	15.8	-1.7	11.5
			22.9	15.5	5.0	9.1
		425 C	58.3	83.0	17.6	76.3
			62.6	81.9	24.1	79.8
ILLINOIS # 6	1 - MN	350 C	73.4	68.7	15.4	35.8
			73.4	66.5	20.7	38.1
		425 C	88.6	89.2	59.0	89.2
			83.9	85.9	54.9	85.9
	A - 9	350 C	36.5	15.4	-8.2	-10.9
			40.2	14.9	-8.3	-10.4
		425 C	72.6	50.9	11.8	37.5
			69.7	57.6	10.6	41.8
BEULAH ZAP LIGNITE	1 - MN	350 C	13.3	34.2	12.8	33.2
			13.9	29.7	15.5	28.8
		425 C	71.8	92.9	65.6	93.0
			62.6	97.2	54.3	97.2
	A - 9	350 C	23.2	15.5	8.2	6.4
			21.5	13.3	10.4	0.0
		425 C	64.5	72.6	28.2	66.5
			60.1	68.9	21.7	60.8

Appendix A. As shown, information under both direct hydroliquefaction and coal/oil coprocessing reaction conditions is being developed. The purpose for these data will be to serve as baseline information for subsequent studies on the effect of stage I processing conditions and coal pretreatment methods on the reactivity of coal-derived intermediates in simulated stage II catalytic hydroprocessing runs. These data will be useful in determining reactivity of coal-derived intermediates with respect to both total conversion (THF solubles) and upgrading/distillate yield (hexane solubles). Further examination of these data will be carried out during subsequent quarters as comparative information on pre-treated coal samples becomes available.

References Cited

1. Green, T.K.; Kovac, J.; Larsen, J.W.; FUEL (1984), 63, 935

APPENDIX A
RAW DATA FOR REACTIVITY STUDY

COAL	ASH FRACTION (MF basis)	INTRINSIC THF SOLUBILITY (MAF basis)	REACTION CONDITIONS	
-----	-----	-----	RXM TIME:	30 MIN
WYODAK	0.0877	0.0163	CAT/COAL:	1:1
			PURE A-9/COAL:	2:1
ILL #6	0.1548	0.1193	CATALYST:	-200 MESH SULFIDED
N. DAKOTA	0.0972	0.0184		

COAL CONVERSION DATA UNDER LIQUEFACTION CONDITIONS (1-MN)

RUN #	MF COAL IN (g)	FRACTION ASH IN	ASH IN (g)	MAF COAL IN (g)	INTRINSIC THF INSOL OF FEED COAL	THF	CATALYST IN (g)	MF THF INSOL OUT (g)	CATALYST	THF COAL CONV. (%)	MAF HEX INSOL OUT (g)	HEXANE
						ADJUSTED MAF COAL IN (g)			FREE MAF THF INSOL OUT (g)			COAL CONV. (%)
WYODAK COAL												
TEMP = 350 C / NO CAT												
390	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.00	0.38	0.3361	25.1	0.02	21.5
392	0.52	0.0877	0.0456	0.4744	0.9837	0.4667	0.00	0.39	0.3444	26.2	0.03	21.1
TEMP = 350 C / WITH CATALYST												
391	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.50	0.78	0.2362	47.4	0.00	43.2
393	0.51	0.0877	0.0447	0.4653	0.9837	0.4577	0.50	0.82	0.2753	39.9	0.01	33.7
TEMP = 425 C / NO CAT												
386	0.51	0.0877	0.0447	0.4653	0.9837	0.4577	0.00	0.19	0.1453	68.3	0.03	62.3
388	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.00	0.20	0.1561	65.2	0.04	57.0
TEMP = 425 C / WITH CATALYST												
387	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.49	0.57	0.0362	91.9	0.00	92.1
389	0.52	0.0877	0.0456	0.4744	0.9837	0.4667	0.53	0.59	0.0144	96.9	0.00	97.0
416-u	0.53	0.0877	0.0465	0.4835	0.9837	0.4756	0.51	0.59	0.0335	93.0	0.01	91.0
417	0.53	0.0877	0.0465	0.4835	0.9837	0.4756	0.51	0.59	0.0335	93.0	0.00	93.1
ILLINOIS #6 COAL												
TEMP = 350 C / NO CAT												
402	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.00	0.14	0.0626	83.2	0.21	35.5
404	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.00	0.18	0.1011	73.4	0.22	25.5
414	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.00	0.18	0.1011	73.4	0.20	30.2
TEMP = 350 C / WITH CATALYST												
403	0.49	0.1548	0.0759	0.4141	0.8807	0.3647	0.50	0.69	0.1141	68.7	0.12	43.5
405	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.49	0.72	0.1526	59.0	0.14	30.8
415	0.52	0.1548	0.0805	0.4395	0.8807	0.3871	0.51	0.72	0.1295	66.5	0.11	45.5
TEMP = 425 C / NO CAT												
398	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.00	0.12	0.0426	88.6	0.11	63.9
400	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.00	0.14	0.0611	83.9	0.11	60.3
TEMP = 425 C / WITH CATALYST												
399	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.50	0.62	0.0411	89.2	0.00	90.5
401	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.49	0.62	0.0526	85.9	0.00	87.6

COAL CONVERSION DATA UNDER CO-PROCESSING CONDITIONS (A-9)

(8 gr A-9/5 gr 1-MN)

RUN #	MF COAL IN (g)	FRACTION ASH IN -----	ASH IN (g)	MAF COAL IN (g)	INTRINSIC THF INSOL OF FEED COAL -----	THF ADJUSTED		MF THF INSOL OUT (g)	CATALYST IN (g)	CATALYST FREE MAF THF INSOL OUT (g)	THF COAL CONV. (%)	MAF HEX INSOL OUT (g)	HEXANE COAL CONV. (%)
						MAF COAL IN (g)	MAF COAL IN (g)						
WYODAK COAL													
TEMP = 350 C / NO CAT													
394	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.00	0.40	0.3561	20.6	0.10	0.0	
396	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.00	0.39	0.3462	22.9	0.08	6.6	
TEMP = 350 C / WITH CATALYST													
395	0.51	0.0877	0.0447	0.4653	0.9837	0.4577	0.52	0.95	0.3853	15.8	0.02	12.9	
397	0.52	0.0877	0.0456	0.4744	0.9837	0.4667	0.53	0.97	0.3944	15.5	0.03	10.5	
T = 425 / NO CAT													
378	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.00	0.23	0.1862	58.5			59.2
380	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.00	0.22	0.1762	60.7			61.4
382	0.52	0.0877	0.0456	0.4744	0.9837	0.4667	0.00	0.24	0.1944	58.3	0.19		19.0
384	0.52	0.0877	0.0456	0.4744	0.9837	0.4667	0.00	0.22	0.1744	62.6	0.18		25.3
T = 425 / WITH CATALYST													
379	0.51	0.0877	0.0447	0.4653	0.9837	0.4577	0.50	0.60	0.0553	87.9			88.1
381	0.51	0.0877	0.0447	0.4653	0.9837	0.4577	0.50	0.65	0.1053	77.0			77.4
383	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.51	0.63	0.0761	83.0	0.03		76.7
373	0.52	0.0877	0.0456	0.4744	0.9837	0.4667	0.51	0.64	0.0844	81.9	0.01		80.1
385	0.50	0.0877	0.0439	0.4561	0.9837	0.4487	0.52	0.74	0.1762	60.7	0.00		61.4
ILLINOIS #6 COAL													
TEMP = 350 C / NO CAT													
*406	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.00	0.26	0.1826	50.9	0.21		7.1
408	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.00	0.30	0.2226	40.2	0.18		4.7
416	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.00	0.32	0.2411	36.5	0.17		4.6
TEMP = 350 C / WITH CATALYST													
407	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.51	0.91	0.3211	15.4	0.10		2.3
*409	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.50	0.92	0.3426	7.9	0.07		2.4
417	0.52	0.1548	0.0805	0.4395	0.8807	0.3871	0.51	0.92	0.3295	14.9	0.09		4.6
TEMP = 425 C / NO CAT													
410	0.53	0.1548	0.0820	0.4480	0.8807	0.3945	0.00	0.19	0.1080	72.6	0.24		22.3
412	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.00	0.19	0.1126	69.7	0.22		21.3
TEMP = 425 C / WITH CATALYST													
411	0.50	0.1548	0.0774	0.4226	0.8807	0.3722	0.49	0.75	0.1826	50.9	0.05		45.0
413	0.51	0.1548	0.0789	0.4311	0.8807	0.3796	0.50	0.74	0.1611	57.6	0.06		48.7

LIGNITE COAL: LIQUEFACTION & CO-PROCESSING CONDITIONS

RUN #	HF COAL IN (g)	FRACTION ASH IN	ASH IN (g)	HF COAL IN (g)	INTRINSIC THF INSOL OF FEED COAL	THF	CATALYST IN (g)	HF THF INSOL OUT (g)	CATALYST	THF COAL CONV. (%)	HF THF INSOL OUT (g)	HEXANE
						ADJUSTED HF COAL IN (g)			FREE HF THF INSOL OUT (g)			COAL CONV. (%)
CO-PROCESSING: 350 deg C												
NO CAT												
418	0.54	0.0972	0.0525	0.4875	0.9817	0.4786	0.00	0.42	0.3675	23.2	0.08	8.2
420*	0.49	0.0972	0.0476	0.4424	0.9817	0.4343	0.00	0.42	0.3724	14.3	0.10	-6.8
426	0.53	0.0972	0.0515	0.4785	0.9817	0.4697	0.00	0.42	0.3685	21.5	0.06	10.4
WITH CAT												
419	0.52	0.0972	0.0505	0.4695	0.9817	0.4608	0.52	0.96	0.3895	15.5	0.05	6.4
421	0.52	0.0972	0.0505	0.4695	0.9817	0.4608	0.51	0.96	0.3995	13.3	0.07	0.0
427	0.51	0.0972	0.0496	0.4604	0.9817	0.4520	0.52	0.90	0.3304	26.9	0.02	23.9
CO-PROCESSING: 425 deg C												
NO CAT												
422	0.51	0.0972	0.0496	0.4604	0.9817	0.4520	0.00	0.21	0.1604	64.5	0.17	28.2
424	0.51	0.0972	0.0496	0.4604	0.9817	0.4520	0.00	0.23	0.1804	60.1	0.18	21.7
WITH CAT												
423	0.50	0.0972	0.0486	0.4514	0.9817	0.4431	0.48	0.65	0.1214	72.6	0.03	66.5
425	0.51	0.0972	0.0496	0.4604	0.9817	0.4520	0.50	0.69	0.1404	68.9	0.04	60.8
LIQUEFACTION: 350 deg C												
NO CAT												
432	0.52	0.0972	0.0505	0.4695	0.9817	0.4608	0.00	0.45	0.3995	13.3	0.01	12.8
434	0.50	0.0972	0.0486	0.4514	0.9817	0.4431	0.00	0.43	0.3814	13.9	0.00	15.5
WITH CAT												
433	0.50	0.0972	0.0486	0.4514	0.9817	0.4431	0.53	0.87	0.2914	34.2	0.01	33.2
435	0.50	0.0972	0.0486	0.4514	0.9817	0.4431	0.49	0.85	0.3114	29.7	0.01	28.8
LIQUEFACTION: 425 deg C												
NO CAT												
428	0.49	0.0972	0.0476	0.4424	0.9817	0.4343	0.00	0.17	0.1224	71.8	0.03	65.6
430	0.49	0.0972	0.0476	0.4424	0.9817	0.4343	0.00	0.21	0.1624	62.6	0.04	54.3
WITH CAT												
429	0.50	0.0972	0.0486	0.4514	0.9817	0.4431	0.50	0.58	0.0314	92.9	0.00	93.0
431	0.49	0.0972	0.0476	0.4424	0.9817	0.4343	0.50	0.56	0.0124	97.2	0.00	97.2

END

**DATE
FILMED**

2 / 18 / 92