MASTER

MASTER

HYDROGEN EFFECTS ON FLOW LOCALIZATION AND
FRACTURE IN TYPE 304L STAINLESS STEEL

by

G. R. Caskey

Savannah River Laboratory
E. I. du Pont de Nemours and Company
Aiken, SC 29801

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Proposed for presentation at a Poster Session
of the Gordon Research Conference
Andover, NH
July 9-13, 1979

This paper was prepared in connection with work under Contract No. AT(07-2)-1 with the U.S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U.S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

HYDROGEN EFFECTS ON FLOW LOCALIZATION AND FRACTURE IN TYPE 304L STAINLESS STEEL

by

G. R. Caskey

Savannah River Laboratory
E. I. du Pont de Nemours and Company
Aiken, SC 29801

The onset of plastic instability, localization of plastic flow, and fracture in Type 304L austenitic stainless steel are modified by the presence of hydrogen. It is not certain, however, whether the observed changes in behavior are attributable to the direct effect of hydrogen on plastic flow or to the intervention of a hydrogen-induced brittle fracture process. The effects are observed in both smooth bar and single edge notched specimens and are dependent on deformation temperature.

INTERNAL HYDROGEN

Compared to unexposed samples, the initiation of plastic instability in a smooth bar tensile (SBT) specimen occurs at a lower strain if the metal has been saturated with hydrogen prior to deformation (Figure 1) and the extent of flow localization is reduced. The energy of deformation up to maximum load is little affected, but the total energy to fracture is reduced from ~100,000 to 50,000 in-lb/in². With decreased test temperature,

plastic instability is eliminated and fracture takes place during the rising load portion of the test with no apparent flow localization. In this case, the energy to maximum load is reduced from $\sim 35,000$ to $14,000$ in-lb/in² and total energy to fracture from $\sim 80,000$ to $14,000$ in-lb/in².

The J_c value of $80,000$ to $100,000$ in-lbs/in² at maximum load in single edge notch (SEN) tensile specimens is independent of temperature unless the specimens have been saturated with hydrogen, in which case J_c is lower and markedly temperature dependent (Figure 2). The load-deformation behavior during flow localization and fracture is affected by hydrogen in a manner similar to the SBT specimens (Figure 2).

Fractures are dimpled rupture in the absence of hydrogen and a mixed cleavage and dimpled fracture in hydrogen charged specimens (Figure 2). The areal fraction of cleavage increased with decreased test temperature in keeping with the decreased energy absorbed during deformation and fracture. Sectioning of other specimens prior to failure indicates that microcracks are observable before fracture but after 12-14% strain. In hydrogen charged specimens, strain localization takes place between cracks under conditions of constraint and there appear to be fewer large dimples than in the unexposed specimens.

EXTERNAL HYDROGEN

Plastic instability of a SBT specimens occurs with less deformation when the test is in an environment of 69-MPa hydrogen than when tested in 1 atm air (Figure 3). The consequent strain

localization is modified from the normal necking behavior and cup-cone fracture by microvoid coalescence to a "tearing" failure and complex mixed fracture mode. The latter displays variable amounts of microvoid coalescence and secondary cracking parallel to the tensile axis. In some cases, dimpled rupture appears to have been supplanted entirely by the tearing fracture.

Plastic instability in Type 304L stainless steel is believed to be delayed by formation of strain-induced martensite at the site of incipient necking. Therefore, decreased deformation required to flow localization in external hydrogen environments could be attributed to hydrogen suppression of martensite formation. Magnetic measurements on samples tested at 200K confirm suppression of martensite formation by the hydrogen environment. Data for room temperature are inconclusive.

SUMMARY

- Hydrogen either in solution or in the test environment decreases the deformation required for the onset of plastic instability in Type 304L stainless steel, an effect that may be associated with suppression of strain-induced martensite.
- This effect is more pronounced at 200K than at room temperature and occurs in both smooth and singled edge notched specimens.
- The presence of hydrogen also reduced the amount of necking or deformation following the onset of plastic instability.
- It is not certain whether the observed changes should be attributed to a direct effect of hydrogen on plastic deformation or to intervention of a hydrogen induced fracture mode.

$EI_u = 58\%$

$RA = 64\%$

INTERNAL HYDROGEN SOURCE

Smooth Bar Specimen
Gas-phase Charged
Tested in Air

HYDROGEN EFFECTS

- Plastic instability at lower strain
- Necking less extensive

DUCTILE RUPTURE

$El_u = 64\%$

$RA = 85\%$

MIXED FRACTURE

DUCTILE FRACTURE

20 μm

INTERNAL HYDROGEN SOURCE

Single Edge Notch Specimen

Effect of Hydrogen on Temperature Dependence of J'_c

10 μm

500 μm

TEAR FRACTURE

RA = 75%

El_U = 56%

EXTERNAL HYDROGEN SOURCE

Smooth Bar Specimen
Test in High-Pressure
 H_2 Gas

500 μm

20 μm

DIMPLE RUPTURE

RA = 85%

El_u = 78%

HYDROGEN EFFECTS ON FLOW LOCALIZATION AND
FRACTURE IN TYPE 304L STAINLESS STEEL

by

G. R. Caskey

Savannah River Laboratory
E. I. du Pont de Nemours and Company
Aiken, SC 29801

Proposed for presentation at a Poster Session
of the Gordon Research Conference
Andover, NH
July 9-13, 1979

This paper was prepared in connection with work under Contract No. AT(07-2)-1 with the U.S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U.S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.