DE-FG22-91PC91295

A NOVEL, INTEGRATED TREATMENT SYSTEM FOR COAL
WASTEWATERS:

QUARTERLY REPORT:

FOR THE PERIOD September 2, 1991 - December 1, 1991.

DOE/PC/91295--T1

DE92 009085

PIs: Prof. Henry Y. Wang
Department of Chemical Engineering
The University of Michigan
Ann Arbor, MI 48109-2136.

&

Dr. Keeran R. Srinivasan
Assoc. Research Scientist
Department of Chemical Engineering
The University of Michigan
Ann Arbor, MI 48109-2136.

Submitted To:

Pittsburgh Energy Technology Center
U. S. Department of Energy
Pittsburgh, PA.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

(NOTE: US/DOE Patent Clearance is not required prior to the publication of this document).

ABSTRACT:

This is the first quarterly report of the above project. The aims of this study are to develop, characterize and optimize a novel treatment scheme that would be effective simultaneously against the toxic organics and the inorganics present in coal conversion wastewaters. The initial phase of the work has been focused on the development of modified clays for use in the selective removal and recovery of heavy metals such as Cd, Cu, chromate and selenate. The results presented here show that a surfactant-modified clay adsorbs Cd strongly at a pH of 8.5 and poorly at pH 4.0. Further, the adsorption of Cd on modified clay is unaffected by the ionic strength of the medium. In the case of Cu, it has been shown that the metal forms a complex with alkyl diamines in aqueous solutions at a pH of 6.0 and does not bind to these surfactants at a lower pH of 3.0. These findings are a preliminary indication that the surface and solution chemistry of amine surfactants can be gainfully modified to adsorb and desorb cationic heavy metals.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

INTRODUCTION:

It has been pointed out that abundant reserves of coal in the U. S. - an estimated 936 billion net tons in 1988 - will make coal the major source of fossil fuel in the decades to come, especially so in view of the declining reserves of liquid and gaseous hydrocarbons in the U. S. (1,2). However, a coal conversion facility, be it the SRC-I, SRC-II, the H-Coal or the EDS process, generates wastewaters containing relatively high concentrations of phenols, cyanides, ammonia, dissolved solids, and trace levels of priority pollutants such as polycyclic aromatic hydrocarbons (PAHs), polycyclic aromatic amines (PAAs), and nitrogen heterocyclics (NPAHs) (3). Apart from these toxic organics, coal conversion wastewater is also a complex cocktail of heavy metals derived from the inorganic constituents in coal (4). The purpose of the present project is to develop, characterize and optimize a novel treatment scheme that would be effective *simultaneously* against both types of contaminants. Specifically, the goals of this study are to:

- (1) Develop modified clays containing different chemical coatings that would specifically adsorb and desorb metal ions both in cationic and anionic forms under different solution conditions. Examples of metal ions to be tested are Cd^{2+} , Cu^{2+} , chromate and selenate. By a careful manipulation of system parameters such as pH, ionic strength, and temperature and the surface chemistry of the coatings, it is anticipated that selective removal and recovery of heavy metals can be effected.
- (2) Design and develop a continuous treatment system that would integrate metal recovery with biodegradation. Three important issues that need to be addressed are:
 - (A) Putative toxicity of heavy metals and surface coatings to microorganisms
 - (B) Implementation of efficient biodegradation activity towards multi-ring aromatics
 - (C) Development of cost-effective adsorbents that are effective with respect to heavy metals and toxic organics at the same time.
- (3) Design and build microbioreactors (microcapsules) that will be capable of implementing both the unit operations of adsorption and recovery of heavy metals and the biodegradation of PAHs in a single system.

- (4) Carry out spectroscopic and surface-chemical studies to establish structure-function relationships between adsorbents and their reactivity. Further, a mathematical model will be developed to fully describe the integrated wastewater treatment system developed as a part of this study.

This is the first quarterly report of this study of three years duration, and the preliminary results on the adsorption of Cd to modified clays and the complexation of Cu to alkyl diamines in solution are reported.

I. Adsorption of Cd^{2+} onto modified clay:

The modified clay (PC-1) was supplied by Bentec Corporation, Ferndale, MI. This proprietary organo-clay consists of a smectite clay, to which a dialkyl secondary amine is attached "irreversibly" by electrostatic and micellar forces. Previous work in this lab. and elsewhere had shown that this commercial organo-clay strongly adsorbed toxic organics such as chlorinated phenols and heavy metals such as Cd and Cu (5,6). However, the reversibility of the adsorption, especially of heavy metals, has not been studied. It was theorized that, secondary amines, being weakly basic, can be protonated and deprotonated at low and high pH respectively. In the deprotonated form, these amine groups can be expected to complex with heavy metals. The properties of the modified clay used in this study are reported in Table 1.

Table 1: Properties of modified clay (PC-1):

Property Type	Description
Base clay	Wyoming bentonite; CEC 0.7 - 1.0 meq/g; smectite
Surfactant	Secondary amine (2HT); dihydrogenated tallow alkyl amine. The hydrocarbon tails range in length from C_{12} to C_{18} with some degree of unsaturation. Each molecule has two tails. Equivalent weight 510 g/mole.pH dependent cationic surfactant.

The Amount of surfactant
on PC-1

From solid state organic carbon analysis, an organic on carbon content of 28.4% was observed. The amount of adsorbed surfactant was determined to be 34.4% by weight of PC-1. The corresponding surface concentration of NH groups, the active sites for metal adsorption, is 675 $\mu\text{moles/g}$ PC-1.

The Surface Structure of
Adsorbed Surfactant

Based on the CEC of the base clay and the amount of adsorbed surfactant, a partial bilayer structure is likely.

As a weakly basic surfactant, the secondary amine head group was expected to be protonated at low pH (pH 4.0) and deprotonate under mildly alkaline conditions (pH 8.5). Thus, the adsorption of Cd would be greater at the higher pH and much lower at lower pH. Fig. 1 is an ideal representation of the surface structure of the adsorbed surfactant and the possible mode of Cd adsorption to such a surface.

Experimental Details:

Adsorption of Cd onto PC-1 was studied in a batch mode. A preliminary experiment was carried out in deionized water at a pH of 6.0 and the initial Cd concentrations ranged from 5 to 50 mg/L. Subsequently, buffer solutions (sodium acetate/acetic acid; 20 mM; pH = 4.0 and [Tris (hydroxy methyl) amino methane] (TRIS/HCl); 20 mM and pH = 8.5) were used to maintain constant pH and ionic strength during adsorption. TRIS is a cationic buffer with a pK_a of 8.0, and is suitable for pH control in the 8.0 - 9.0 region. The initial Cd concentrations during these buffered runs were 1.0 to 10 mg/L, and it should be noted that these concentrations are two orders of magnitude higher than the MCL for Cd (7). The adsorbent concentration (PC-1 or the unmodified base clay) was 2g/L.

Following 20 hr incubation at room temperature, solid-liquid separation was achieved by centrifugation. Cd in the supernatant was assayed using an atomic adsorption spectrometer with a graphite furnace accessory. Adsorbed Cd was determined by difference. Identical experiments with Cd solutions at the highest initial Cd concentration, but containing NO adsorbent were carried out to account for nonspecific effects. The measured Cd concentrations were interpolated from a linear calibration curve obtained using certified Cd standard solutions. The relative error of the mean of the measurements carried out in duplicate is estimated to be 10%. The results are shown in Figs. 2 - 4.

Fig. 1 Postulated Structure of modified clay and the proposed mechanism of metal interaction (e.g. Cd)

Fig. 1A Proposed scheme for the Complexation of metal ions by alkyl diamines in solution

Fig. 1B Proposed scheme for the Adsorption of metal ions onto clay-alkyl diamine

Type of clay	Ionic Strength	Bound Cd (mg/g)
Unmodified Clay	--	8.0
PC-1	--	2.5

Fig. 4 Adsorption of Cd^{2+} on unmodified clay:
pH effect

Fig. 3 Adsorption of Cd^{2+} on Modified Clay (PC-1):
pH Effect

Fig. 2 Adsorption of Cd on Modified Clay (PC-1)

Unmodified Clay	20 mM NaCl	4.9
PC-1	20 mM NaCl	2.7

The above experiments show that Cd adsorbs to modified clays and that the adsorption is influenced by pH, but unaffected by ionic strength. With unmodified clays, adsorption of Cd appears to be mainly through nonspecific electrostatic interaction related to the CEC of the base clay.

Future Work:

The above results indicate that further research is necessary in the following areas:

- (1) Spectroscopic verification of the model shown in Fig. 1 using FTIR and NMR.
- (2) Dynamics of adsorption and desorption of Cd, and the role of pH on the dynamics.
- (3) The role of other cationic heavy metals such as Cu
- (4) Simultaneous adsorption of PAHs and heavy metals on modified clays

These and other studies will be undertaken as a part of the present project.

II. Complexation of Cu with alkyl diamines in solution:

The postulated structure of PC-1 as shown in Fig. 1 reveals that the same head group of the surfactant, namely the secondary amine, acts to anchor the surfactant to the clay surface and to bind Cd ions from solution. Since the clay surface is negatively-charged, pH close to the surface may be more acidic compared to the bulk solution, and this may explain as to why, at the high bulk pH, one end of the surfactant remains tethered to the surface while the other end, proximal to bulk solution, is deprotonated in response to solution pH.

On the other hand, diamine of the type (R-NH-(CH₂)₃-NH₂) combines secondary amine as an anchor group while the primary amine function will act as a binding site for the metal ion at the solution interface. The alkyl group imparts extra stability to surfactant adsorption to a clay surface in aqueous media through the well-known hydrophobic attraction. With such bifunctional surfactants, the adsorption of metal ions can be a chelate formation in solution (Fig. 1A) or a monodentate binding on a clay surface (Fig. 1B). A second advantage of the

alkyl diamines is that metal adsorption can be carried out at pH around 6.0 (due to the lower basicity of the primary amine) and this property is quite critical while dealing with metals such as Cu which tend to hydrolyze at higher pH. In this report, chelation of Cu to alkyl diamine in solution has been studied.

Duomeen-T (DT) is an aliphatic diamine, and the alkyl group ranges from C₁₂ to C₁₈. The apparent molecular weight based on hydrocarbon assay is 350 g/mole (8). Duomeen-T (DT) is insoluble in water and a 6.45% solution of DT was prepared in isopropanol. This stock solution was diluted 100-fold in deionized water. At this dilution, the surfactant solution was only slightly turbid and had an absorbance of less than 0.03 at 616 nm, the lowest wavelength used in this study. The diluted DT solution was mixed with Cu²⁺ and the absorbance of the resultant complex was monitored in the 800-600 nm region of the visible spectrum at two pH. From this initial spectrum, three wavelengths were chosen for a quantitative measure of the absorbance of Cu-DT complexes in solution. The results from these experiments are detailed in Table 3.

Table 3: Interaction Between Cu²⁺ and Duomeen-T: pH Effect

Cu ²⁺ μmoles	Duomeen-T μmoles	pH	Absorbance		
			795 nm	660 nm	616 nm
7.86	13.4	6.5	0.06	0.12	<u>0.127</u>
15.72	17.9	6.3	0.085	0.160	0.170
31.45	17.9	6.1	0.096	0.153	0.160
78.62	17.5	5.8	0.16	0.175	0.170
157.24	17.0	5.5	0.26	0.200	0.175
7.86	13.4	3.1	0.01	0.01	<u>0.01</u>
15.72	17.9	3.0	0.03	0.02	0.02
31.45	17.9	3.0	0.05	0.03	0.02
78.62	17.5	3.0	0.11	0.04	0.03
157.24	17.0	3.0	0.20	0.07	0.04

7.86	0.0	5.4	0.01	0.01	0.01
31.45	0.0	5.3	0.04	0.02	0.01
157.24	0.0	5.0	0.19	0.06	0.03
31.45	0.0	3.4	0.02	0.01	0.01
157.24	0.0	3.3	0.19	0.06	0.03

In presence of the surfactant, and at the higher pH, Cu appears to bind to the diamine as evidenced by a large blue shift along with an enhancement in the intensity of the optical transition. Comparison of the absorbance values at 616 nm (the underlined data points in Table 3) shows this clearly. At higher Cu concentrations, pH had to be lowered to 6.0 or less minimize hydrolysis. It is interesting that even at these low pH, Cu remained complexed to the diamine in solution. The data points in the bottom part of the table show that pH alone had no effect.

Discussion and Future Work:

The results from Table 3 show that Cu ions interact with diamines in solution, perhaps by forming chelates. The pH effect is dramatic. However, collateral experiments have to be carried out to determine the exact structure of the complex in solution and compare it with the surface structure of a similar complex when the surfactant is anchored to clay surface. At the minimum, the above procedure appears to be a rapid method to screen a number of such surfactants that are commercially available. Further work is in progress.

References:

- (1) R. Datta: Bio-tech Research Digest, Michigan Biotechnology Institute Bioconnection, p 10 (Dec. 1989).
- (2) R. A. Kerr: Science, 245, 1330 (1989).
- (3) K. Benedek, R. Courant et al.: Vol II, Technical Report. DOE/PC/40068-T5-Vol. 2 323 pp (1984).
- (4) R. H. Gray, H. Drucker, and M. J. Massey: "Toxicology of Coal Conversion Processing", Wiley-Interscience Publication p. 362 (1988).
- (5) Keeran R. Srinivasan and H. Scott Fogler: Unpublished Results
- (6) George Alther: Bentec, Inc., Ferndale, MI (Personal Communication).
- (7) Federal Register 55 (14 3) Wednesday, July 25, 1990, p. 30370.
- (8) Akzo Chemie America: Bulletin 85-1, "Specification and Properties of DUOMEEN Diamines and Diamine Salts", An Arnak Chemical Publication, (1985).

END

**DATE
FILMED**

4 / 23 / 92