DOE/PC/89762--T12

DE92 008694

QUARTERLY

TECHNICAL PROGRESS REPORT

Submitted to U. S. Department of Energy

MAK U

GRANT TITLE: NQR-NMR Studies of Higher Alcohol
Synthesis Cu-Co Catalysts

GRANT NO: DE-FG22 89PC89762 (GSU: 5-5374)

STARTING DATE: 09-15-89

ENDING DATE: 09-14-91

PROJECT DIRECTOR: A. N. Murty
Physics Department

INSTITUTION: Grambling State University
Grambling, Louisiana 71245

U.S./DOE Patent Clearance is not required prior to the publication of this document.

A. N. Murty
Project Director

Dec. 17, 1991
Date

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DEC 30 1991

QUARTERLY TECHNICAL PROGRESS REPORT
(Period: June 15 - Sept. 15, 1991)

This report describes the work carried out during the summer session of 1991. Through an equipment enhancement grant from the State and a research training grant from the Office of Naval Research, we have obtained a computer controlled vibration sample magnetometer system from Digital Measurement Systems of Boston Massachusetts to compliment our existing zerofield NMR/NQR spectrometer system. Mrs. Marie A. Seamster, previous research assistant on the project joined us during the summer and, and we have installed the magnetometer and underwent the necessary training for the operation of the system.

EXPERIMENTAL STUDIES:

Our previous studies (1,2) on the zerofield NMR spectra of Cu/Co catalysts revealed that the method of preparation sensitively influences the magnetic character of the Catalyst. Catalytic studies of the earlier investigators also (3) show similar influence on the product selectivity and indicate reproducible performance is critically dependant on the control and rigor of the preparation technique.

To compliment the NMR results, we have made a thorough investigation of the Hysteresis character of the Cu/Co catalysts with the metal ratio varying from 0.2 to 4.0.

RESULTS DISCUSSION:

All the precursors show typical paramagnetic behavior with a susceptibility value of in the range $3 - 30 \times 10^{-6}$ emu/g. Oersted. (Fig. 1) The precursor is likely to be a mixture of the oxides of Cu, (Cu₂O, CuO) and Co (CoO, Co₂O₃, Co₃O₄) which are all paramagnetic.

$$\chi_{\text{CuO}} = 4 \times 10^{-6}, \chi_{\text{CoO}} = 83 \times 10^{-6} \quad \chi_{\text{Co}_2\text{O}_3} = 77$$

$$\chi_{\text{Cu}_2\text{O}} = -0.3 \times 10^{-6} \quad \chi_{\text{Co}_3\text{O}_4} = 125 \times 10^{-6}$$

$$\chi_{\text{Na}} = 0.7 \times 10^6 \quad \chi_{\text{Na}_2\text{CO}_3} = -0.4 \times 10^{-6}$$

$$\chi_{\text{NaNO}_3} = -0.3 \times 10^6.$$

No data available on the nitrates and carbonates of Cu and Co. The method of preparation described elsewhere (2) consists of precipitation of the nitrates of the metals as carbonates, which are calcined at 350°C, leaving oxides of the metals. It seems possible to describe the observed χ values as $\chi_{\text{sample}} = P_1 \chi_{\text{CuO}} + P_2 \chi_{\text{CoO}}$ to a first approximation. ($P_1/P_2 = \text{Cu/Co}$, starting metal nitrate ratio).

After reduction the samples exhibit typical Ferromagnetic behaviors (Fig. 2) indicating that the oxides are reduced to metallic state. The hysteresis character measurements (S_s - Saturation magnetization, S_r - Remanance magnetization and H_c - Coercive field) for all the samples are presented in Tables I, II and III. The data in tables I and II shows the variation in the three parameters S_s , S_r , and H_c as the metal ratio changes from 0.2 to 4, in the samples with and without a support titania. As expected the saturation magnetization S_s gradually decreases as the cobalt content decreases in samples with Cu/Co ratio >1 . No such pattern appears for samples for Cu/Co ≤ 1 . It seems as copper content increases beyond 50% a uniform bond formation might be taking place, while for samples with Cu $< 50\%$ random mixture might be occurring. Neither the H_c values nor S_r values exhibit any systematic pattern corresponding to the decrease in cobalt content. Since both these values are essentially dependant on particle size distribution, we are lead to believe that the calcination and reduction temperatures and duration might be influencing the morphology and size of the particles.

The data for supported samples shown in Table II, on the other hand shows

a uniformly consistent behavior with no appreciable difference as the copper content increases up to 50%. The NMR spectra (1) also indicate that the support has an annealing effect. Table III presents the temperature effect on the hysteresis character for a set of selected samples. Though both H_c and S_r gradually increase as the temperature decreases the change is not appreciable. ΔH_c is only about 250 oersteds as the temperature drops by 175°C from Room temperature to Liquid nitrogen. This indicates that the cobalt particles are in general multidomain-sizes above 150 Å. The appearance of strong NMR lines further substantiates this conclusion. However, we have so far not yet been able to correlate the catalytic results (3) with the magnetic measurements.

Presently, we are undertaking magnetic studies on a series of Cu/Co/Cr trimetallic catalysts.

STUDENT PARTICIPANTS:

Marie Seamster is planning to continue the work to fulfil the Master's thesis requirements of State University of New York, Albany.

PUBLICATIONS AND PRESENTATIONS:

The results are being finalized for presentation at the ensuing LA Academy of Science meeting (Feb. '92) and the joint AAPT, APS meeting (April '92); enclosed abstracts.

References

1. A. N. Murty, U.S. D.O.E. Quarterly Technical Report, 7/15/91.
2. A. N. Murty, Abstracts - P.E.T.C.-UCR HBCU Projects, June 1991.
3. Xu xiaoding, E. B. M., Doesburg and J. J. F. Scholten, Catalysis Today 2, 125 (1987).

$$r = 0.999$$

$$\chi - m = 3.627 \cdot 10^{-6}$$

FIG.I CALCINED SAMPLE : VSM OUTPUT - PARAMAGNETIC SAMPLE
LEAST SQUARE FIT ANALYSIS

Digital Measurement Systems Vibrating Sample Magnetometer

Filename: XCuCo04T

CUCO=0.4 XU12 T102

30 Jul 1991

Start Time: 01:19:06

Temp 20.5

Duration: 00:07:46

SIGMA 1.389E+01

Mass 6.020E-02

Y units EMU/g

X units Oersted

Hmax 1.350E+04

Sa 1.389E+01

Sr 4.679E+00

SQ 3.369E-01

S* 1.827E-01

Hc 5.085E+02

Angle 0.000E+00

dH 1.467E+03

Sfd 2.885E+00

FIG.II HYSTERESIS LOOP: REDUCED SAMPLE

FIG. III TEMPERATURE EFFECT ON THE COERCIVE FIELD OF THE CATALYST SAMPLE

$$H(c) \text{ vs. } T$$
$$Cu/Co = 0.6$$

TABLE I: HYSTERESIS LOOP DATA ANALYSIS

ROOM TEMPERATURE MEASUREMENTS

SAMPLE	CODE	S(s)	S(r)	H(c)
Cu/Co=0.2	XU11A	11.21	4.0	617.0
Cu/Co=0.4	XU12A	49.72	15.23	455.3
Cu/Co=0.6	XU13A	35.64	12.38	549.5
Cu/Co=0.8	XU14A	43.12	14.56	595.7
Cu/Co=1.5	XU16	51.16	20.59	720.1
Cu/Co=2.0	XU17	48.10	18.64	635.3
Cu/Co=2.5	XU18	37.61	14.50	701.9
Cu/Co=3.0	XU19	32.11	93.3	539.7
Cu/Co=3.5	XU20	27.71	81.41	552.8
Cu/Co=4.0	XU21	24.8	10.25	700.7

TABLE II: SUPPORTED CATALYSTS

ROOM TEMPERATURE MEASUREMENTS

(TiO₂ samples)

SAMPLE	CODE	S(s)	S(r)	H(c)
Cu/Co=0.2	XU11	13.71	48.96	612.2
Cu/Co=0.4	XU12	13.89	46.79	508.5
Cu/Co=0.6	XU13	14.52	50.64	566.7
Cu/Co=0.8	XU14	11.38	38.23	549.3

TABLE III TEMPERATURE EFFECT ON THE HYSTERESIS CHARACTER

SAMPLE	CODE	S(s) (EMU/g)	S(r) (EMU/g)	H(c) (OERSTED)	TEMP (C)
Cu/Co=0.4	XU12	49.72	15.23	455.3	25
		49.67	15.42	455.0	0
		49.59	16.11	496.9	-50
		49.97	17.76	615.1	-100
		49.12	18.04	618.4	-150
		49.17	17.94	683.6	-196
Cu/Co=0.6	XU13A	35.64	12.38	549.5	25
		35.34	12.93	556.8	0
		35.10	14.10	631.7	-50
		35.27	15.22	754.9	-100
		35.19	15.89	842.5	-150
		35.56	15.46	829.2	-196
Cu/Co=0.8	XU14A	43.12	14.56	595.7	25
		42.99	14.97	620.9	0
		42.36	16.26	658.4	-50
		42.14	18.42	737.9	-100
		41.88	18.23	848.7	-150
		42.72	17.31	876.5	-196
Cu/Co=1.5	XU16	51.16	20.59	720.1	25
		51.16	20.07	724.1	0
		51.18	20.44	738.0	-50
		51.55	20.96	788.3	-100
		51.96	22.67	903.6	-150
		51.82	23.26	950.2	-196
Cu/Co=2.5	XU18	37.61	14.50	701.9	25
		37.69	14.44	707.3	0
		37.94	14.86	747.1	-50
		38.18	15.30	781.5	-100
		38.22	16.61	868.5	-150
		38.16	16.83	931.8	-196

Abstract of contributed paper to be presented at the annual meeting of the Louisiana Academy of Sciences (Feb. 1992)

NMR Spectra of Cu-Co Bimetallics: Effect of Method of Preparation*

A.N. Murty. Physics Department, Grambling State University, Grambling, LA 71245

M.A. Akundi, Lillian Ebanks, Carlisa Harris. Physics/Engineering Department, Xavier University, New Orleans, LA 70125.

Cobalt and Copper are active metals which have wide variety of applications as catalysts. Study of the Nuclear Magnetic Resonance (NMR) spectra of these Bimetals gives information on the nature of interaction between the metals. The specific nature of activity and selectivity is a function of CO/Cu atomic ratios and the proximity of the CO-Cu sites.

A series of Cobalt-Copper bimetallics with different CO/Cu ratio ranging from 0.2 to 4.0 were prepared by two different methods. In the first method, one molar solutions of copper and cobalt nitrates were precipitate by adding a one molar solution of sodium hydroxide while maintaining a neutral PH. In the second method these nitrates are co-precipitated in a 7PH sodium hydroxide solution. NMR spectra taken on these samples show a significant shift in the observed NMR frequencies of ^{59}Co . Such a shift could occur due to significant modification of the metallic change distribution or due to formation of an alloy of copper cobalt.

*Work supported by grants from Department of Energy and Office of Naval Research.

ABSTRACT OF CONTRIBUTED PAPER TO BE PRESENTED AT THE 1992 JOINT
APS AND AAPT MEETING (APRIL 20-24) WASHINGTON, D.C.

Magnetic Character Studies of Cu/Co/Cr Trimetallic Catalysts*

A.N. Murty⁺, T.L. Hoard, U.A. Donatto and J. Washington,
Physics Department, Grambling State University, Grambling, LA
71245 (318) 274-2258/2289

M.A. Akundi, Physics/Engineering Department, Xavier University,
New Orleans, LA 70125, (504) 483-7643

Transition metals copper and cobalt have been extensively used for the conversion of synthesis gas to methanols, alcohols, and hydrocarbons. The selectivity is found to be sensitive to the method of preparation and the intermetallic ratio. Neither the role of chromium nor the nature of the catalyst system - whether it is a composite, an alloy, a cluster or a solid solution is not clearly understood.

We have investigated the zerofield Nuclear Magnetic Resonance and Hysteresis Character of a series of both Cu/Co bimetallics and Cu/Co/Cr trimetallics to examine the relations between the catalytic and magnetic properties. The results indicate that both the metallic charge distribution and morphology are sensitive to the metal ratios and strong intermetallic interactions do occur producing significant shifts in the NMR lines of cobalt.

*This work is supported by grants from Department of Energy, National Science Foundation and Office of Naval Research.

- 1) Possible session topics: Chemical Physics - 4
 - 2) My \$25 abstract fee has been sent to the executive office.
- + Member AAPT.

**DATE
FILMED**

4 / 07 / 92