TECHNICAL REPORT

1st September 1991 through 30 November 1991

Project Title: INFLUENCE OF SULFUR IN COALS ON CHAR
MORPHOLOGY AND COMBUSTION

~~DE-FQ22-91PC91334~~

Principal Investigator: * Harry Marsh
Department of Mechanical Engineering and
Energy Processes
Southern Illinois University at Carbondale
Carbondale, IL 62901 (618) 453-7381

Co-Investigator John C. Crelling
Department of Geology
Southern Illinois University at Carbondale
Carbondale, IL 62901 (618) 453-7361

Project Monitor Dr. Ken Ho, CRSC

ABSTRACT

During coal carbonization (pyrolysis), as during the combustion process of pulverized coal in a combustor, not all of the sulfur is released. Significant proportions become part of the structure of the resultant coke and char. The combustion process of the char within the flames of the combustor is influenced dominantly by char morphology. This, in turn, controls the accessibility of oxidizing gases to the surfaces of the carbonaceous substance of the char. Mineral matter content, its extent and state of distribution, also exerts an influence on char morphology created during pyrolysis/carbonization. This complexity of coal renders it a very difficult material to study, systematically, to distinguish and separate out the contributing factors which influence combustion characteristics. Therefore, in such circumstances, it is necessary to simplify the systems by making use of model chars/coke/carbons which can be made progressively more complex, but in a controlled way. In this way complicating influences in chars from coals can be eliminated, so enabling specific influences to be studied independently. It is important to note that preliminary work by Marsh and Gryglewicz (1990) indicated that levels of sulfur of about 3 to 5 wt.% can reduce reactivities by 10 to 20%. The overall purpose of the study is to provide meaningful kinetic data to establish, quantitatively, the influence of organically-bound sulfur on the reactivity of carbons, and to ascertain if gasification catalysts are effective in the preferential removal of sulfur from the chars.

MASTER

This project is funded by the U. S. Department of Energy (PETC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Executive Summary

During coal carbonization (pyrolysis), as during the combustion process of pulverized coal in a combustor, not all of the sulfur is released. Significant proportions become part of the structure of the resultant coke and char. The combustion process of the char within the flames of the combustor is influenced dominantly by char morphology. This, in turn, controls the accessibility of oxidizing gases to the surfaces of the carbonaceous substances of the char. Mineral matter content, its extent and state of distribution, also exerts an influence on char morphology created during pyrolysis/carbonization. This complexity of coal renders it a very difficult material to study, systematically, to distinguish and separate out the contributing factors which influence combustion characteristics. Therefore, in such circumstances, it is necessary to simplify the systems by making use of model chars/coke/carbons which can be made progressively more complex, but in a controlled way. In this way complicating influences in chars from coals can be eliminated, so enabling specific influences to be studied independently. It is important to note that preliminary work by Marsh and Gryglewicz (1990) indicates that levels of sulfur of about 3 to 5 wt.% can reduce reactivities by 10 to 20%. The overall purpose of the study is to provide meaningful kinetic data to establish, quantitatively, the influence of organic-bound sulfur on the reactivity of carbons, and to ascertain if gasification catalysts are effective in the preferential removal of sulfur from the chars.

The specific objectives of this study are to:

1. prepare a series of chars from model compounds of known initial purity levels, to give a range of structure and porosity as found in chars from a rank range of coals;
2. introduce sulfur within these model chars by the controlled co-carbonization of the model feedstocks with elemental sulfur and with sulfur-containing model compounds;
3. dope (load) these carbons with known amounts of known inorganic compounds which are established as being catalytic in gasification (oxidation) reactions;
4. measure the reactivities of these carbons to carbon dioxide and oxygen, and from measurements of total and active surface areas, to be able to express reactivity data on a meaningful relative basis; and
5. be able to assess, comparatively, reactivities of chars from Illinois coals of known sulfur contents to assist the deconvolution of the several parameters which control reactivities of chars from coals.

Rates of gasification of chars are controlled dominantly by:

1. The heat treatment temperature (HTT) of the char/carbon.
2. The total surface area (TSA) which is presented to the oxidizing gas. Hence, rates of gasification must be expressed in units of $\text{g m}^{-2} \text{s}^{-1}$ where m^2 is the surface area of the carbon (per gram) presented to the oxidizing gas. Usually, this area is obtained from an adsorption isotherm obtained in the temperature range 273 to 373 K (Marsh 1987).
3. The active surface area (ASA) is a measure of the number of active sites per square meter of carbon surface. For carbons of the same HTT and TSA, it is necessary to assess/correct for the influence of major differences in the structural perfection of the lamellar constituent molecules (LCM). It is thought that the surfaces of chars from lignites have higher densities of active sites in their surfaces than chars from coals of higher rank.
4. The presence of mineral matter distributed within the carbon material and which may possess catalytic properties during gasification. Such catalytic materials operate without regard for extents of total surface area and active surface area. Rates of catalytic gasification are determined by: (1) the composition of the inorganic catalyst material, (2) the amount of the catalyst present within the char/carbon, and (3) the particle size or state of dispersion of the inorganic mineral matter within the char/carbon.
5. The "regime" of control, that is, whether or not the rate controlling processes are chemical in nature, in which case all that is said above applies. If rate controlling processes are partially or totally controlled by diffusion parameters, then chemical kinetics as such, cannot be applied.

To accomplish the objectives of the project the following tasks will be undertaken:

Char/carbon preparation and analysis. A suite of five samples of pure carbons will be prepared initially, HTT 900° C, from pure acenaphthylene, and from the co-carbonization of this material with a phenolic resin, to give a range of structures from totally anisotropic to totally isotropic. These preparations will be repeated by co-carbonizing with, e.g. thiophene or its derivatives to introduce sulfur into these carbons at levels of 3 to 5 wt.%. Next, two additional suites will be prepared, this time using ferrocene (an iron or anometallic compound) with the pure carbons and with the carbons containing sulfur. Ultimate analyses of C, H, N, and S will be carried out on all of these 20 samples.

Optical and scanning electron microscopy. The 20 carbons will be mounted in thermosetting resin. Polished surfaces will be prepared and optical textures will be assessed by point-counting. Surface topography will be assessed before and after gasification. Appropriate photographs will be taken and placed on record.

Surface Area assessments. All samples will have their surface areas measured via the establishment of adsorption isotherms, using as adsorbates nitrogen at 77 K and carbon dioxide at 273 K. Indications will be given of the relative sizes of microporosity within these samples.

Use of differential gravimetric analysis. This equipment is essentially a microbalance and automatically records changes in weights. Thus, the reactivities of the 15 samples will be determined in carbon dioxide at 900°C and in oxygen (10% in 90% nitrogen). The active surface areas can be determined in the same equipment before a reactivity measurement is made, and time permitting, after a reactivity measurement, usually to the same extents of 50 wt. % burn-off.

OBJECTIVES

The overall purpose of the study is to provide meaningful kinetic data to establish, quantitatively, the influence of organic-bound sulfur on the reactivity of carbons, and to ascertain if gasification catalysts are effective in the preferential removal of sulfur from the chars.

The specific objectives of this study are to:-

1. prepare a series of chars from model compounds of known initial purity levels, to give a range of structure and porosity as found in chars from a rank range of coals;
2. introduce sulfur within these model chars by the controlled co-carbonization of the model feedstocks with elemental sulfur and with sulfur-containing model compounds;
3. dope (load) these carbons with known amounts of known inorganic compounds which are established as being catalytic in gasification (oxidation) reactions;
4. measure the reactivities of these carbons to carbon dioxide and oxygen, and, from measurements of total and active surface areas, to be able to express reactivity data on a meaningful relative basis; and
5. be able to assess, comparatively, reactivities of chars of Illinois coals of known sulfur contents to assist the deconvolution of the several parameters which control reactivities of chars from coals.

INTRODUCTION and BACKGROUND

Coals are extremely complex materials. Not only does the organic matter of coal change in chemical composition with increasing rank (generally becoming more aromatic with a decreasing heteroatom content), but organic matter of coals of very similar rank can also vary as coal maceral composition varies. Further, as coals increase in rank, so the physical structure changes. With the lower rank lignites, surfaces of coal material are polar because of the presence of considerable quantities of surface oxygen groupings (Speight 1978). The surface areas of these coals are amongst the highest in the rank range (Mahajan and Walker 1978). With increasing rank, not only does the extent of bonding within the macromolecular networks change from strong covalent cross-linkages with extensive hydrogen-bonding (so preventing-fusion in lignites) to a weaker bonding (perhaps hydrogen-bonding mainly in the bituminous coals), but the surface area decreases appreciably (Mahajan and Walker 1978, Derbyshire 1989). There is also a significant reduction in the sizes of the microporosity in which the surface area is contained (Mahajan and Walker 1978).

As well as organic matter, coals contain mineral matter in sizes from $<1\mu\text{m}$ to cm size. The organic matter of coal is dominantly made up of the elements carbon and hydrogen, but oxygen, sulfur, nitrogen and chlorine (heteroatoms) are also present. Sulfur is found in three forms within coals: (1) as pyritic sulfur, (2) as sulfates (generally in weathered or oxidized coals), and (3) as organic sulfur.

During coal carbonization (pyrolysis), as during the combustion process of pulverized coal in a combustor, not all of the sulfur is released. Significant proportions become part of the structure of the resultant coke and char.

The combustion process of the char within the flames of a combustor is influenced dominantly by char morphology. This, in turn, controls the accessibility of oxidizing gases to the surface of the carbonaceous substance of the char. Mineral matter content, its extent and state of distribution, also exerts an influence on char morphology created during pyrolysis/carbonization.

This complexity of coal renders it a very difficult material to study, systematically, to distinguish and separate out the contributing factors which influence combustion characteristics. Therefore, in such circumstances, it is necessary to simplify the systems by making use of model chars/coke/carbons which can be made progressively more complex, but in a controlled way. In this way complicating influences in chars from coals can be eliminated, so enabling specific influences to be studied independently. (preliminary work of Marsh and Gryglewicz 1990 indicates that levels of sulfur of about 3 to 5 wt. % can reduce reactivities by 10 to 20 %).

The overall purpose of the study is to provide meaningful kinetic data to establish, quantitatively, the influence of organic-bound sulfur on the reactivity of carbons, and to ascertain if gasification catalysts are effective in the preferential removal of sulfur from chars.

Rates of gasification of chars are controlled dominantly (Marsh et al. 1991) by:

1. The heat treatment (HTT) of the char/carbon.
2. The total surface area (TSA) which is presented to the oxidizing gas. Hence, rates of gasification must be expressed in units of $\text{g m}^{-2} \text{s}^{-1}$ where m^2 is the surface area of the carbon (per gram) presented to the oxidizing gas. Usually, this area is obtained from an adsorption isotherm obtained in the temperature range 273 to 373 K (Marsh 1987).
3. The active surface area (ASA) is a measure of the number of active sites per square meter of carbon surface (Laine et al. 1963). For carbons of the same HTT and TSA, it is necessary to assess/correct for the influence of major differences in the structural perfection of the lamellar constituent molecules (LCM). It is thought that the surfaces of chars from lignites have higher densities of active sites in their surfaces than chars from coals of higher rank, of identical HTT.
4. The presence of mineral matter distributed within the carbon material and which may possess catalytic properties during gasification. Such catalytic materials operate without regard for extents of total surface area and active surface area. Rates of catalytic gasification are determined by (1) the composition of the inorganic catalyst material, (2) the amount of the catalyst present within the char/carbon, and (3) the particle size or state of dispersion of the inorganic mineral matter within the char/carbon particle (Marsh et al. 1991).
5. The "regime" of control, that is, whether or not the rate controlling processes are chemical in nature, in which case all that is said above applies. If rate controlling processes are partially or totally controlled by diffusion parameters, then chemical kinetics, as such, cannot be applied.

Char/carbon preparation. Carbons can be prepared by the carbonization of the aromatic hydrocarbon "acenaphthylene", which has anisotropic, graphitizable properties and low surface area, and is approximate to chars from anthracites. When the acenaphthylene is co-carbonized with, for example, progressively increasing weight ratios of phenolic resin materials or compounds which are chemically similar, there is a progressive decrease in the anisotropy of the carbons as measured in terms of the sizes of optical texture as seen in polished surfaces using polarized light optical microscopy. Further, the surface areas of these carbons progressively increase as the carbons progress to structures with smaller sizes of anisotropy, as in chars from bituminous coals, to the

isotropic non-graphitizable materials, as are the chars from lignites (Marsh and Menendez 1989).

Thus, this series of chars/carbons act as base carbons in the sense that they are pure and behave as reference materials for modified carbons.

Sulfur can be incorporated into these carbons either by co-carbonization with elemental sulfur, or by co-carbonization with sulfur-containing polycyclic aromatic compounds with thio-sulfur or in-ring sulfur. The sulfur contents of the prepared carbons can be assessed by conventional sulfur analytical methods. The use of infrared spectroscopy can indicate the chemical nature of this organically bound sulfur.

Thus, there can be prepared several suites of carbon with different extents of anisotropy and surface areas, and containing known amounts of sulfur with identifiable chemical attachments within the carbon lattice.

Further, the use of such a starting material as acenaphthylene enables co-carbonizations with either: (1) organometallic compounds, or (2) salts of cations known to be catalytic, e.g., potassium, iron, sodium, and calcium. This approach enables the introduction of known amounts of known catalytic materials in known states of dispersion. Analysis of cations can be achieved by conventional wet chemistry or by neutron analyses. States of dispersion of the inorganics can be assessed by transmission electron microscopy of thin sections of the carbon, in terms of density contrast.

Thus, the above suites of carbons can have incorporated within them known amounts of catalyst materials in controlled dispersions.

Char/carbon characterization: Optical microscopy.

The optical textures of the prepared carbons can be assessed by examination of polished surfaces, and of carbons set in resins, using polarized light optical microscopy with a retarder plate to produce color contrast of the crystallites of the carbon structure with different orientations within the carbon. The size distribution within the optical texture is measured using image analysis or a point-counting technique. A nomenclature exists which is used to compare/contrast the range of optical textures within the suites of carbons prepared.

Char/carbon characterization: Scanning electron microscopy (SEM). SEM is a technique used to examine surface topography of solids. As such, it is a valuable tool to examine the topographical features of surfaces of chars/carbons. During gasification of these materials, surface ablation never occurs evenly. There is always some form of "etching," or preferential gasification, even with pure carbon. This etching reveals aspects of structure within the carbons. However, the technique is most valuable for surfaces of carbons doped with catalyst because it is a clear indicator of the

size and mobility of the catalyst particle in terms of pitting and channeling phenomena created during gasification. This is relevant to changes in morphology of chars from coals, as used in power stations.

Char/carbon characterization: Total surface area and microporosity. Total surface area of the carbons is best assessed using nitrogen as an adsorbate at 77 K, and carbon dioxide as an adsorbate at 273 K. The former adsorption isotherms (N₂) are best interpreted by the BET equation. The adsorptions of carbon dioxide are best interpreted by the Dubinin-Radushkevich (D-R) equation. Comparisons of calculated parameters are extremely informative in terms of the sizes of the microporosity. Close agreement between the two surface area values indicates that the microporosity of the carbons is in the size range greater than about 0.5 nm diameter. Lower values from the nitrogen isotherm indicate the presence of ultra-microporosity within the carbons of diameter less than 0.5 nm. Gradients from the D-R plots are indicative of pore-size distributions within the microporosity.

Char/carbon characterization: Active surface area. Active surface areas (ASA) are measured as the extents of chemisorption of molecular oxygen on outgassed surfaces of the char at 300°C and 0.1 MPa pressure. It would appear that the oxygen surfaces complexes are formed on the active sites under these conditions without significant extents of gasification. This determination can be made using a differential gravimetric analyzer (DGA) which measures directly the weight increase due to the formation of these oxygen surface complexes. The active surface area (ASA) is calculated by assigning an area of 0.083 nm² to each chemisorbed oxygen atom.

Char/carbon characterization: Reactivity measurements. No standardized regulations exist that are designed to control the measurement of the "reactivities" of a char. As a result, each investigator has to define closely the sets of conditions under which a reactivity measurement is made. In this series of experimentations, reactivities are measured using a DGA system in which carbon dioxide and oxygen (10% in 90% nitrogen) flow over the sample at 900 and 500°C respectively, with a flow rate of 50 cm³ min⁻¹. At reaction temperature, the gradient of the linear plot of weight loss with time gives a measure of "reactivity" (units of grams lost, per second, per gram of char. [i.e., in units of s⁻¹]). These reactivity data are totally comparable with each other as the properties/composition of the char, undergoing gasification, are changed. Thus, the "reactivity" parameters of importance in this study include:

R in units s⁻¹

R' in units of g m⁻² s⁻¹ (Total Surface Area)

R" in units of g m⁻² s⁻¹ (Active Surface Area)

These parameters are then to be used comparatively to assess the influence of sulphur in chars on their gasification kinetics and to monitor any influence of catalytic inorganic additives. The corresponding reactivities of chars from coals, coal macerals, or modified coals can then be assessed in terms of the parameters of the model compounds, so permitting, at worst a semi-quantitative appraisal of char reactivity, being high or medium or whatever. There would then exist a "yard-stick" capable of establishing a "league-table" of reactivities in a meaningful and comparative way.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

EXPERIMENTAL PROCEDURES

EQUIPMENT

Carbonization:

Figure 1 is a description of the furnace set-up commissioned for carbonizations. The components of the furnace set-up were available, but have had to be assembled into a working unit. Further, the furnace had to be constructed in a dedicated fume-hood so that the laboratory is free from odors.

Reactivity:

Figure 2 is a description of the CAHN microbalance commissioned for reactivity and adsorption measurements. The instrument is designed by CAHN primarily for reactivity studies. However, as the furnace which surrounds then hang-down tube can be lowered and swung away, it is possible to immerse the tube in a Dumas flask enabling adsorption measurements to be made. The use of helium/carbon dioxide mixtures precludes the need for vacuum equipment.

MATERIALS

Acenaphthylene, ferrocene and thiophene were obtained from Aldrich Chemical Company, Inc. Milwaukee. Resol, a phenolic resin, was supplied by Borden Chemicals. The following properties for the Resol are available:-

Resol - resin Sc -1008

Softening point	91°C	Sp gravity	1.32 g cm ⁻³
Xylene insolubles	14.5 wt.%	QI	4.5 wt.%,
Ash	0.16 wt.%	Free phenol	11-18 wt.%
Free formaldehyde	0.6-2.0 wt.%	pH	7.9-8.5
Sulphur	0.56 wt.%	Solvent	isopropanol
Coke yield	41.6 wt.%		

Due to the hazardous nature of the chemicals used in the following series of experiments, all substances were stored and handled in a fume-hood, with the exception of Resol, which was stored in a freezer at -15 °C. Gloves and eye protection were used during all weighing and operational procedures.

CARBONIZATION

A standard program was used for all carbonizations consisting of a 5°C min⁻¹ ramp; final heat-treatment temperature - 900°C; soak time - 1 hour; overnight cool down. Carbonizations were performed in a horizontal Carbolite tube furnace (Figure 1.). The furnace was calibrated by inserting a Pt/Pt-Rh thermocouple down the center of the silica tube, positioned just above the boat, as shown in Figure 1. The temperature controller and calibration thermocouple were in close agreement over the temperature range used in the following experiments.

Figure 1. Furnace set-up

Gas bubblers were assembled and attached to both the inlet and outlet tubes to monitor nitrogen gas flow through the silica tube.

Approximately 5 g of sample was used for each carbonization. The chemicals were weighed and mixed together and the resulting paste spread on to the bottom of a small ceramic boat, dimensions 80 x 12 x 10 mm. The boat was never filled to a depth greater than 5 mm, as expansion occurs during carbonization and overfilling can result in the boat sticking to the silica tube. The boat was placed in the central portion of the furnace and heated under flowing nitrogen to 900°C, at a rate of 5 °C min⁻¹, with 1 hour soak time. The furnace was allowed to cool overnight. The sample was removed and weighed. Carbonization yields are given in Table 2.

After four carbonizations the silica tube was cleaned by heating to 800°C in air thereby burning away the deposits. Carbonization details are given in Table 1.

Table 1. Carbonization details**Acenaphthylene****Ac + 20 wt.% Resol**

" 40 "

" 60 "

" 80 "

Acenaphthylene + 5 wt.% thiophene**Ac + 20 wt.% Resol**

" 40 "

" 60 "

" 80 "

Acenaphthylene + 5 wt.% ferrocene**Ac + 20 wt.% Resol**

" 40 "

" 60 "

" 80 "

Acenaphthylene + 5 wt.% thiophene + 5 wt.% ferrocene**Ac + 20 wt.% Resol**

" 40 "

" 60 "

" 80 "

OPTICAL TEXTURE ANALYSIS

After weighing, the carbons were lightly crushed and mounted in acrylic blocks, supplied by Cortec Corp, Minnesota. Sample preparation consisted of drilling a hole in the hardened acrylic mount, then filling the hole with Epofix epoxy resin and carbonized sample. The pellets were left for two days to harden prior to polishing. A series of micrographs will be taken for each sample; point-counting will also be performed to characterize optical texture.

POINT-COUNTING

Point-counting of the anisotropic optical texture of the carbons was performed on each sample pellet using a Swift automatic point-counting stage and recorded. Point-counting involves classifying the isochromatic areas, in terms of shape and size, that are found at the center of the image field.

The classification system is defined below: 500 points were recorded for each sample and reproducibility was ensured by repeating each count at least twice.

Nomenclature used to characterize optical texture:

isotropic	no optical activity
medium mosaic	$> 0.8 < 0.2 \mu\text{m}$ diameter
granular flow	$> 2 \mu\text{m}$ length
	$> 1 \mu\text{m}$ width
lamellar flow	$> 20 \mu\text{m}$ length
	$> 10 \mu\text{m}$ width
Striated flow	$> 20 \mu\text{m}$ length
	$< 10 \mu\text{m}$ width
microbead	spherical morphology

REACTIVITY

Reactivity measurements of carbons to gasifying gases are performed in a TG-171 thermogravimetric analyzer, supplied by CAHN Instruments Inc., Ca. The apparatus consists of a hang-down arrangement, suspended from a thermocouple. The furnace is air-cooled and a series of flow meters control gas flow rate. A diagram of the furnace and hang-down arrangement is given below in Figure 2.

This apparatus can be modified to obtain surface area estimates by carbon dioxide absorption. The hang-down is filled with helium and surrounded by an ice-bath. Carbon dioxide is introduced to displace the helium and the increase in sample weight, caused by the adsorption of carbon dioxide, is monitored to produce an isotherm.

Figure 2.

Details of the thermogravimetric and adsorption systems will be discussed in subsequent reports.

Reactivity measurements will be determined in carbon dioxide at 900 °C and in 10% oxygen/90% nitrogen at 500°C. Burn-off levels will be limited to approximated 50 wt.%.

The rate of reaction, R , in units of s^{-1} , are calculated from the initial, steady rate of weight loss, dW/dt , from the TGA plot. Reactivity, R , is then calculated as

$$R = \frac{-1}{W_o} \times \frac{dW}{dt}$$

W_o initial weight of sample, mg

dW/dt initial gradient of steady weight loss curve, $mg\ s^{-1}$

Carbon dioxide and oxygen reactivities will be determined for each sample (Table 1.).

RESULTS

The following summarizes the progress made in the first three months of the contract:-

1. We took over a laboratory previously used by others and converted it into a place suitable for carbonizations. A fume-hood was adapted.
2. The equipment for carbonization was assembled from several sources and converted into a carbonization furnace/unit. This included the furnace itself, the central ceramic tubes, ceramic boats to contain the sample, sealing bungs, construction of glass bubblers to act as flow meters, mounting of a nitrogen tank, and the wiring in and testing of a temperature programmer and controller.
3. The chemicals for the project have been identified, ordered and delivered.
4. Equipment (CAHN microbalance) to measure the reactivities and surface areas of prepared and reacted carbons has been identified and checked out for functionality. Minor modifications are needed in terms of gas supplies to be piped to the balance. The gases needed include helium, carbon dioxide, 10% oxygen in 90% nitrogen, and mixtures of helium in carbon dioxide (10, 20, 30, 40, 50, 75 % helium in carbon dioxide).
5. The carbonization equipment is up and running and ten carbonizations have been carried out. Details are in Table 3. The carbons so prepared have been mounted in resin and surfaces polished for identification of optical texture.
6. The computer equipment has been ordered, delivered and commissioned and is working well.
7. Staff to work the project have been identified.

Table 3. Carbonization Yields:
HTT 900°C, ramp 5 °C min⁻¹, 1 h soak

Sample	Yield wt.%
Acenaphthylene	22
Ac + 20 wt.% Resol	22
" 40 "	25
" 60 "	29
" 80 "	35
Acenaphthylene + 5 wt.% thiophene	26
Ac + 20 wt.% Resol "	22
" 40 " "	24
" 60 " "	28
" 80 " "	26

DISCUSSION

Yields are lower than expected from the previous work (Dillon and Marsh 1991). This is due to the relatively small quantity of material used (4-5 g per carbonization cf. to 30 g.) in a shallow boat, which allows a larger surface to be exposed; hence, more volatiles are lost.

The addition of thiophene does not appear to alter yield, although it was noted that the resultant carbon was more resistant to crushing.

REFERENCES

- Derbyshire, F. et al. 1989. Fuel 68: 1091-1106.
- Laine, N.R., Vastola, F.J. and Walker, P.L. Jr. 1963. J. Phys. Chem. 67: 2030-2034.
- Mahajan, O.P. and Walker, P.L. Jr. 1978. In Analytical methods of coal and coal products, Ed. C. Karr Jr., Vol 1, pp 125-162. New York: Academic Press.
- Marsh, H. 1987. Carbon 25: 49-58.
- Marsh, H., Diez, M.A. and Kuo, K. 1991. In Fundamental issues in control of coal gasification reactions, Eds. J. Lahaye and P. Ehrburger, pp. 205-220. Dordrecht: Kluwer Academic Publishers.
- Marsh, H. and Gryglewicz, G. 1990. Unpublished results, University of Newcastle upon Tyne.
- Marsh, H. and Menendez, R. 1989. In Introduction to carbon science, Ed. H. Marsh, Chapter 2, pp. 37-73, London: Butterworths.
- Speight, J.G. 1978. In Analytical methods of coal and coal products, Ed. C. Karr, Jr., Vol. II, pp. 75-101. New York: Academic Press.

END

DATE
FILMED

4 102 192

I