2

DOE/PC/89758--T5

SURFACE ELECTROCHEMICAL CONTROL FOR FINE COAL AND PYRITE SEPARATION

DOE Project No. DE-AC22-89PC89758

DOE/PC/89758--T5

DE92 004491

Technical Progress Report
July 1, 1991 - September 30, 1991

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Prepared by

Weibai Hu
Qinping Huang
Jun Li
Andrew Riley
S. B. Turcotte
R. E. Benner
Ximeng Zhu
David M. Bodily
Jun Liang
Tinghe Zhong
Milton E. Wadsworth

Prepared for

U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

2

NOV 04 1991

SURFACE ELECTROCHEMICAL CONTROL FOR FINE COAL AND PYRITE SEPARATION

DOE PROJECT NO. DE-AC22-89PC89758

Technical Progress Report

July 1, 1991 to September 30, 1991

This technical progress report, prepared in accordance with the reporting requirements of DOE Project No. De-AC22-89PC89758, covers the work performed from July 1, 1991 to September 30, 1991. The ongoing work includes the characterization of coal pyrites, the floatability evaluation of three typical U.S. coal samples, the flotation behavior of coal pyrites, the electrochemical measurement of the surface properties of coal pyrites, and the characterization of species produced at pyrite surfaces.

This report covers a study of Raman spectroscopy of species produced electrochemically on pyrite surfaces.

Spectroscopic Studies of Electrochemically Oxidized Pyrite

TABLE OF CONTENTS

1. INTRODUCTION
 - 1.1 Overview
 - 1.2 Surface Raman spectroscopy
2. EXPERIMENTAL
 - 2.1 Outline of Experimental Work
 - 2.2 Equipment and Procedures for Raman Experiments
 - 2.3 Experiments to Obtain Reference Spectra
 - 2.4 Equipment and Procedures for Photocurrent experiments
 - 2.5 Particle Bed Experiments
3. RESULTS OF RAMAN EXPERIMENTS
 - 3.1 Electrochemistry of Pyrite
 - 3.1.1 Acid conditions
 - 3.1.2 Neutral conditions
 - 3.1.3 Basic conditions
 - 3.2 Cathodic Reduction of Sulfur
 - 3.3 Detection of Oxy-Sulfur Compounds
 - 3.4 Electrochemical Oxidation of Galena
 - 3.5 Reference Spectra
 - 3.5.1 Elemental sulfur
 - 3.5.2 Electrodeposited sulfur
 - 3.5.3 Mineral iron sulfides
 - 3.5.4 Precipitated iron hydroxides
 - 3.6 Particle Bed Experiments
 - 3.7 Electrochemical Oxidation of Amyl Xanthate
4. PHOTOCURRENT EXPERIMENTS
 - 4.1 Pyrite in Acid, Neutral and Basic Conditions
 - 4.2 Electrodeposited Sulfur
5. DISCUSSION
6. FUTURE EXPERIMENTS
7. REFERENCES

INTRODUCTION

1.1 Overview

Iron pyrite is a common constituent of coal and its presence during combustion leads to the production of sulfur dioxide and acid rain. Consequently, there is a large research effort dedicated to improving the methods of separating pyrite from coal.

One of the principal methods of separation is froth flotation. Under suitable conditions the sulfide minerals are sufficiently hydrophobic that their floatability is greatly enhanced. The use of a collecting agent is usually necessary to bring about preferential separation and enhance the degree and rate of recovery. Collecting agents, such as xanthates, are expensive and when used in large scale processes are a significant fraction of the cost of the extraction process.

An alternative approach to the use of collecting agents is to utilize the natural hydrophobicity of many sulfide ores. It has been observed that under the correct conditions of pH and electropotential that sulfide minerals are sufficiently hydrophobic that they can be readily floated. Many studies have attributed this to the formation of elemental sulfur on the surface of the sulfide minerals. In some studies, sulfur has been dissolved from the mineral surface using carbon disulfide and the presence of sulfur detected using calorimetric techniques [1]. Electrochemical studies using cyclic voltammetry have suggested that sulfur can be formed by the direct oxidation of pyrite to sulfur:

Alternatively, the floatability of sulfide minerals may be depressed by forming a hydrophilic surface. At high anodic potentials the sulfide surface can be oxidized to sulfates and metal hydroxides (which are hydrophilic in nature) by the following reaction:

ESCA studies have been carried out to directly confirm the presence of sulfur on the surface [2]. However, the results have not been conclusive and point to the existence of a metal deficient sulfide instead of elemental sulphur. The primary disadvantage with ESCA is that it is an ex-situ technique and requires that the sulfide mineral be removed from solution and placed in a vacuum. This loss of electrochemical potential control can severely modify the surface. The use of a cold stage has proven necessary to prevent the sublimation of the elemental sulfur in the vacuum.

The floatability of pyrite has been investigated using micro-floatation cells in which the pyrite can be electrochemically modified [3]. This is the most direct way to investigate whether the electrochemical formation of sulfur films can enhance the hydrophobicity of the surface of sulfide minerals. However, cyclic voltammograms of particulate pyrite are not identical to those obtained from single specimens which have been mounted and polished [4]. The peaks from particulate pyrite are shifted in a way which is suggestive of the presence of resistive potential drops in the particulate bed. The resistance may be attributable to oxidation products on the surface of the pyrite produced during grinding or during electrochemical pre-treatment. It is difficult to interpret these voltammograms and establish whether the pyrite has been conditioned at a potential suitable for the growth of a hydrophobic sulfur layer. Preliminary experiments using micro-floatation cells revealed little or no increase in floatability over a range of preconditioning potentials and pH. The lack of success may be attributable to the inability to polarize the pyrite at the correct potential to develop the desired hydrophobic surface. One of the objects for developing Raman spectro-electrochemistry is to directly observe the electrochemical formation

of sulfur with an in-situ spectroscopic method. The method has been developed using large single specimens of pyrite to characterize the surface and obtain Raman spectra under conditions of no IR drop. Subsequently, the technique has been used to study the surface chemistry in a modified electrochemical micro-floatation cell equipped with an optical window to allow observation of the particulate pyrite.

1.2 Surface Raman Spectroscopy

Recent developments in instrumentation have enabled the possibility of conducting in-situ studies of surface electrochemistry. In particular, there has been much work using infra-red spectroscopy in conjunction with Fourier transform techniques. However, there are some serious disadvantages with in-situ infrared spectroscopy. The aqueous medium used in most hydro-metallurgical studies is highly absorbing in the important region of the infra-red spectrum. This requires the mineral surface to be extremely close to the window to minimize the attenuation. As a consequence, the geometry of the electrochemical cell is highly compromised. There is an uneven current distribution in the vicinity of the specimen and a large ohmic resistance causing a loss of potential control.

Raman spectroscopy offers a solution to some of the problems associated with in-situ IR spectroscopy. The ability to obtain spectra using visible light eliminates the constraints on cell design posed by IR spectroscopy. The experimental arrangement is greatly simplified and electrochemical studies are free from the complications of ohmic potential drop. The relatively small size of the Raman effect has hindered its use in in-situ electrochemical studies. However, the development of lasers and highly sensitive CCD arrays has increased the magnitude of the Raman signal to the point that it can now be successfully used in in-situ spectro-electrochemical

studies [5,6]. Mycroft *et al.* have recently reported preliminary studies on mineral pyrite using Raman spectroscopy [7]. Campion has demonstrated that it is possible to obtain Raman spectra from monolayers of adsorbed material under suitable conditions [8]. Other improvements such as resonant raman and surface enhanced Raman have also increased the sensitivity of Raman spectroscopy to the point that in-situ studies are feasible [9,10]. Raman spectro-electrochemical studies have also recently been performed on metal surfaces in-situ. Of particular interest are studies of the corrosion of iron based alloys [11].

EXPERIMENTAL

2.1 Outline of the Experimental Work

A cell has been designed to study the surface of iron pyrite with Raman spectroscopy during the course of an electrochemical experiment. These preliminary studies have been carried out to test the feasibility of the technique and to provide additional information to aid in the analysis of previously reported cyclic voltammetric experiments.

Initial experiments have used large single pieces of mineral pyrite to characterize the surface during cyclic voltammetric experiments under ideal electrochemical conditions with no resistive potential drops. Raman spectra have been taken at potentials of interest over the potential range covered during the cyclic voltammetry experiments. Three pH values have been investigated, 2.7 (acid), 6.5 (neutral) and 12.5 (alkaline). In each case the electrolyte was 0.5 M NaCl. This solution was selected as the ions gave the least interference with the Raman spectra. Anions such as sulfate (also borate, silicate, carbonate and nitrate) have Raman peaks in potential regions of interest (1000 cm^{-1}).

As an aid to the interpretation of the pyrite electrochemistry, an attempt was made to establish a set of suitable reference spectra. In particular, a study was made of the electro-deposition of sulfur onto platinum from sulfide solutions. It was hoped that sulfur formed by this method would be similar in both character and mode of formation to sulfur films on metal sulfides.

Raman spectra were also taken in air from a wide range of metal sulfides to help identify the products of the electrochemical oxidation and reduction of the pyrite. Some specimens of naturally occurring iron oxides were obtained and characterized. However, most of these minerals are partially hydrated and crystalline and may not be typical of the iron oxides formed in solution on the surface of the pyrite. Ferrous and ferric hydroxides were synthesized by precipitation from saturated solutions of ferrous and ferric chloride by the addition of sodium hydroxide. The precipitates were washed with deionized water and examined between glass microscope slides. It was hoped that these extensively hydrated and non-crystalline materials would be more representative of the products of the aqueous oxidation of pyrite.

The equipment already in place for the Raman experiments also permitted the characterization of the photo-electrochemical behavior of the surface films. This is a well established and powerful method of studying the electronic properties of the films [12-15]. The results presented here are preliminary and demonstrate the potential of the technique. The photocurrents were measured at one incident wavelength during the course of cyclic voltammetry experiments. Future work should establish the spectral dependence of the photocurrent. Differential capacity measurements with the use of Mott-Schottky plots would aid in the interpretation of the photocurrent results.

2.2 Equipment and Procedures for Raman experiments

The spectro-electrochemical cell designed for this study is shown in Fig. 1. The sample is a piece of mineral pyrite (Wards) which has been glued with epoxy resin into the plunger of a ground glass syringe. Electrical contact to the pyrite is made with silver loaded epoxy resin. The barrel of the syringe is connected to the rear of the cell opposite a quartz window. This arrangement enables the distance between the sample and the window to be accurately controlled. A similar electrode was made using a disc of platinum (5 mm diameter) instead of pyrite. Provision is also made for a spiral platinum wire counter electrode and a standard calomel reference electrode. A luggin capillary is placed as close to the window as possible to minimize any IR drop. Prior to the experiments the pyrite surface was polished with 400 grit and 0.3 mm alumina and washed in deionized water.

A schematic diagram of the Raman spectrometer is shown in Fig. 2. The laser line used in this work was from an Argon ion laser (Spectra Physics) at 514.5 nm and the incident power was set at 20 mW. The cell is arranged such that the incident laser light is at a grazing angle of approximately 70 degrees to the sample. The plane of polarization was not determined. The collection lens is placed normal to the sample to minimize the collection of light from the incident laser beam. The distance between the sample and the window is less than 1 mm. The laser beam was focussed to a spot of approximately 150 μm in diameter. In addition there is scattered light from the window which enlarges the probed area to an uncertain extent. The optics of the spectrometer require a narrow focused beam and hence there is a very small area of the specimen that is probed during each spectrum. It is possible to achieve a certain degree of spatial resolution by using a cylindrical lens and the spatial second dimension of the CCD

array. A more useful approach for future work would be to incorporate some method of scanning the surface by either moving the specimen or scanning the beam with mirrors. Alternatively, selected areas could be individually probed in conjunction with an optical microscope.

The spectrometer (Spex Triplemate 1877) consists of a triple monochromator and a 2D CCD array (Photometrics) of 576 by 354 pixels. The binning was set at 24 by 4. In this preliminary work the gratings were 1200 grooves/mm and the final slit width was 100 μ m. All Raman spectra were taken in 100 seconds unless otherwise stated.

In early experiments a fixed amount of charge was passed through the cell with the laser beam not directed onto the specimen. After conditioning the electrode was made open circuit, the laser beam was directed onto the surface and the Raman spectrum immediately measured. However, problems were experienced with this method. The films dissolved or were modified when potential control was lost. In all subsequent experiments the potential was continuously applied and the laser beam was incident on the surface during the entire experiment. Spectra were taken after various intervals of time.

The solutions used contained 0.5 M NaCl as an electrolyte. The acid solution was prepared by the addition of concentrated HCl to attain a pH of 2.5. The alkaline solution (pH 12.5) was prepared in a similar fashion by the addition of concentrated sodium hydroxide.

The position of the Raman peaks were calibrated by a combination of two methods. A reference spectrum of tungsten oxide was taken under identical equipment settings. The peaks of the various tungsten oxides are well characterized and can be used as a standard. In addition there are good fundamental studies available in the literature which provide exact identification for the major peaks in pyrite and elemental sulfur [16,17].

2.3 Experiments to Obtain Reference Spectra

A Raman spectrum in air was made from sublimed elemental sulfur obtained from Aldrich (99.9999%). The sulfur was held between two glass slides. Sulfur was also electro-deposited onto a platinum electrode from a solution of 10^{-3} M sodium sulfide in 0.5 M NaCl.

Reference spectra of ferric and ferrous hydroxide were taken from samples prepared by precipitation from a solution of ferric and ferrous chloride by the addition of sodium hydroxide. The precipitates were washed with deionized water and then placed between glass slides. No attempt was made to dry the precipitates and they were examined immediately after being made.

2.4 Equipment and Procedures for Photocurrent Experiments

Photocurrent spectroscopy is a powerful modern technique for the in-situ examination of surface films. In particular, it provides detailed information concerning the electronic properties and structure of the surface [12-15]. It is simple to carry out photocurrent and Raman spectroscopy simultaneously at a surface as the basic equipment required is identical.

The electrochemical cell is identical to that used in the Raman experiments. A laser beam is directed onto the surface of the working electrode (incident angle is unimportant). It is modulated at a fixed frequency with a mechanical chopper or electroacoustic modulator. The specimen is potentiostated at either a fixed potential or the potential is slowly scanned as in cyclic voltammetry. A voltage signal proportional to the electrochemical current is fed to a lock-in amplifier. This signal is compared to a reference signal produced by the modulator which is synchronous with the light pulses. The lock-in amplifier is programmed to detect current pulses in phase with the reference signal and produces an output signal whose magnitude is proportional to the size of the in-phase photocurrent. The in-phase photocurrent signal is sent to the Y axis

of a chart recorder and is recorded as a function of the applied potential (X axis). In addition, an oscilloscope directly monitors the electrochemical current to record to shape of the photocurrent pulse produced by the chopped laser beam. A schematic diagram of the equipment is shown in Fig.3.

The photocurrent was measured over a wide potential range as used in the cyclic voltammetry experiments. Only one wavelength of light was used (514.5 nm). More information can be obtained by potentiostating at a single potential and scanning the frequency of the incident light. A white light source and monochromator is very applicable for this type of experiment.

2.5 Particle bed experiments

The original objective of this work was to develop an in-situ tool to determine whether electrochemical modification was able to create a sulfur rich, hydrophobic surface on pyrite in a particulate bed electrode. The existence of electrical resistance between the particles and in the solution due to a poor current distribution can greatly affect the electrochemistry by introducing ohmic potential drops. The potential of the pyrite bed may not be at the desired potential to produce sulfur.

Some preliminary experiments were carried out to determine whether sulfur could be detected on an electrochemically modified bed electrode. Mineral pyrite (100-200 mesh) was placed in the spectroelectrochemical cell and electrical contact was made with a piece of platinum mesh. The bed was polarized at several potentials at which sulfur was detected on single piece macro-electrodes. The laser beam was focussed onto the pyrite through the optical window and the Raman spectra measured in an identical manner.

RESULTS OF RAMAN EXPERIMENTS

3.1 Electrochemistry of Pyrite

The Raman spectrum of mineral pyrite at its open circuit potential (+0.3 V vs SCE) in a solution of 0.5 M NaCl of pH 1.6 is shown in Fig. 4. The rising background at lower wave numbers is probably due to solution fluorescence or enhanced collection of Rayleigh elastically scattered light. There are two distinct peaks at 338 and 373 cm^{-1} . This spectra is very similar to those reported in other work. A third peak is occasionally observed at about 420 cm^{-1} but is much weaker than either of the other two. The spectrum of pyrite we observe is similar to that observed by Vogt *et al.* [16] and Ushioda [18]. The two large peaks are quoted to be located at 343 and 379 cm^{-1} respectively and are the E_g and A_g phonon peaks. The smaller feature at approximately 430 cm^{-1} is the T_g phonon peak. The A_g phonon peaks are the stretching vibrations of the S_2 dumb-bells in phase throughout the crystal. The E_g peak are displacements of the S atoms perpendicular to the dumb-bell axis. The T_g mode is a combination of various stretching and librational motions and is therefore weaker than either of the previous fundamental modes.

All the Raman experiments were carried out at potentials selected from the cyclic voltammograms presented alongside the photocurrent-potential experiments.

3 1.1 Acid Conditions

The cyclic voltammogram for pyrite in acid conditions is shown in Fig. 5. Anodic peaks were identified at the following potentials: -0.87, -0.63, +0.06, +0.57, and +1.0 V vs SCE. Raman spectra were taken as a function of time at each of these potentials and are shown in Figs. 6-10. The potential was applied for up to 30 minutes in each case and the charge measured

at various times during the experiment. At potentials of -0.87, -0.63, and +0.58 V there is a noticeable increase in the intensity of the pyrite peaks as a function of time. This is attributed to the reduction of a surface film (possibly an oxide) formed on the pyrite electrode. At +0.06 V the intensity of the pyrite Raman peaks is constant indicating that the pyrite electrode is being maintained close to its rest potential. At the potentials from -0.87 to +0.58 V the Raman peaks characteristic of sulfur do not appear.

At +1.0 V the pyrite peaks are observed together with peaks centered at 150, 215, and approximately 470 cm^{-1} . The peaks at 150 and 215 cm^{-1} are characteristic of elemental sulfur (see Fig. 41) and are attributed to the S-S-S bending mode. The broad peak between 440 and 480 cm^{-1} is not characteristic of elemental sulfur. In Fig. 11 the frequency shift axis has been expanded to show more detail of this peak as a function of time. It is seen that the peak is the sum of a number of separate peaks. These peaks are attributed to the S-S stretching mode of various polysulfide species. The separate peaks change in size relative to each other with time. After 25 minutes a large peak at 455 cm^{-1} appears and then decreases in intensity by 35 minutes. At the end of the experiment it was visually observed that the pyrite electrode surface was slightly blackened.

Because of time limitations it was decided to take spectra more often in the range $100\text{-}700\text{ cm}^{-1}$ where the important sulfur peaks are located. From previous studies we have shown that the prepared pyrite surface does not show any Raman peaks at greater than 700 cm^{-1} . The pyrite surface was first examined in the range $700\text{-}1400\text{ cm}^{-1}$ after 7.5 minutes. This spectrum is shown in Fig. 12. A large broad peak is observed which can be resolved into two equal-sized peaks. Very small peaks are seen at 992 and 1100 cm^{-1} . After 17.5 minutes peak the

peak centered at 850 cm^{-1} has diminished by a factor of 3 while there is a small increase in the size of the peaks at 992 and 1100 cm^{-1} . We can attribute the peaks at 850 cm^{-1} to the overtones of the fundamental sulfur peaks. The peak at 992 cm^{-1} is very close to the Raman shift caused by the breathing motion of the sulfate ion. However, the peak at 1100 cm^{-1} could also be associated with an S-O stretch. There are a large numbers of oxy-sulfur species whose Raman spectra have been characterized [19]. However, to date, we have not been able to identify the presence of any other species other than sulfate.

An estimate of the sensitivity of the technique can be obtained by a measure of the charge passed during the electrochemical oxidation. The spectrum ($100\text{-}700\text{ cm}^{-1}$) taken at 20 seconds in Fig. 10 was after the passage of less than 71 mC of charge (3.6×10^{-7} moles of S assuming 100% efficiency). This amount of charge is equivalent to approximately 10^5 monolayers of sulfur using the method described by Ralston *et al.* [20]. According to this approximation, 5.0×10^{-6} g of sulfur is equivalent to a monolayer on 0.4 m^2 assuming each atom occupies $8.7\text{ \AA}^2$. It should be noted that the area probed by the laser beam ($1.77 \times 10^{-4}\text{ cm}^2$) is much smaller than the area of the electrode (0.125 cm^2). Hence the detected Raman signal is from a much smaller quantity of sulfur (approximately 5×10^{-10} moles). This is a very poor estimate of the sensitivity as no allowance is made for the production of soluble polysulfide or oxy-sulfur complexes. These are known to occur during the oxidation of sulfides to sulfur and the coulombic efficiency may be much less than 100% as assumed in this calculation [21].

3.1.2 Neutral Conditions

The cyclic voltammogram for pyrite in neutral conditions is shown in Fig. 13. Anodic peaks were identified at the following potentials: -0.76 , -0.15 , $+0.62$, and $+1.0\text{ V}$ vs SCE.

Two large photocurrent peaks were observed at -0.40 and +0.42 V as shown in Fig. 67. Raman spectra were taken at potentials coinciding with these photocurrent peaks as well as the four anodic peaks.

The Raman spectra for pyrite held at -0.76 V are shown in Fig. 14. The pyrite peaks were observed to decrease as a function of time. The height of the peak at 379 cm^{-1} fell linearly from 400 to 200 counts per 100 seconds as the charge passed increased from 0 to 40 mC (Fig. 15). The same results were found at a potential of -0.15 V as seen in Fig. 17. At both -0.76 and -0.15 V sulfur was not detected.

At a potential of +0.42 V, the sulfur peaks were observed after 5 minutes and the passage of charge of 3.3 mC (Fig. 18). The peaks were not very strong but are clearly present. The pyrite phonon peaks were also present and were very strong. This gives further indication of the sensitivity of the technique as resolvable sulfur peaks of 100 counts are obtained in 100 seconds for charge of 3.3 mC (10^4 monolayers). No spectral features were observed at higher cm^{-1} at this or any lower potentials.

Sulfur spectra were obtained at potentials +0.62 V (Fig. 19) and +1.0 V (Fig. 20). Fig. 21 shows the growth of the S-S stretching modes at a potential of +1.0 V. The relative intensity of the peak heights does not change with time. This contrasts with the results at the same potential in acidic conditions where non-uniform growth was observed. Other than this difference the spectral features were similar in acidic and neutral conditions.

An analysis of the growth of the sulfur peak at 469 cm^{-1} shows that it grows linearly as a function of charge (Fig. 22). The pyrite peak at 379 cm^{-1} decreases initially but then has a constant intensity.

The sulfur overtone peaks at 800-950 cm^{-1} were only detected at potentials of +0.62 and +1.0 V. The spectrum at +1.0 V after 25 minutes is shown in Fig. 23. The peaks at 992 and 1100 cm^{-1} (attributed to the sulfate ion) were not observed.

3.1.3 Basic Conditions

The cyclic voltammogram for pyrite in basic conditions is shown in Fig. 24. Raman spectra were taken at the following potentials: -0.4, 0.0, +0.35, +0.62 and +1.0 V vs SCE (Figs. 25-29).

There were distinct differences between the spectra taken at this pH and under acid and neutral conditions. Peaks associated with sulfur were detected only at -0.4 V (Fig. 25). They were very weak and only just visible above the background. There was some indication that the magnitude of the peaks decreased during the experiment. The pyrite peaks were clearly present and did not change with time to a significant extent.

At higher oxidation potentials the pyrite peaks decreased in magnitude throughout the course of the oxidation (Figs. 27-29). At +1.0 V they were clearly present after 20 seconds but after 10 minutes and the passage of 828 mC they were no longer visible (Fig. 29).

At 0.0 V, a small broad peak was observed at 680 cm^{-1} (Fig. 26). This peak became slightly more prominent at the higher oxidation potentials in particular at +0.62 V (Fig. 28). Usually, no other features were observed in the range 700-1400 cm^{-1} . In the range 1100-1900 cm^{-1} , a peak at 1345 cm^{-1} is observed and is attributed to the breathing mode of the silicate ion present in the optical window. Occasionally a small broad peak at 1750 cm^{-1} is observed whose origin is unknown.

Occasionally, when trying to reproduce the spectra, some unusual features have been

observed. For example at +0.62 V (Figs. 30 and 31) a very broad feature is observed between 300-500 cm^{-1} . Its presence is accompanied by two small broad peaks centered at 800 and 1100 cm^{-1} . The peak at 800 cm^{-1} is similar to the overtones of elemental sulfur. However, none of the fundamental peaks of sulfur are present. This has also been observed occasionally at other pH and potentials. There is some evidence to suggest that the source of these spectral features is localized at certain regions of the surface. Relocation of the laser beam on the same specimen during the same experiment produced "normal" spectra without the presence of these features.

3.2 Cathodic Reduction of Electrochemically Formed Sulfur

A piece of mineral pyrite was polarized at +0.8 V vs SCE in pH 2 and approximately 0.5 C of charge passed. The Raman spectrum was taken and is shown in Fig. 32a. The sample was then polarized to a negative potential of -1.2 V vs SCE. The object was to reduce the surface films that had formed during the conditioning at +0.8 V vs SCE and return the pyrite to its original state. The spectrum after 1 minute at -1.2 V vs SCE is shown in Fig. 32b. The three sulfur peaks that appeared at +0.8 V have now been greatly diminished and the spectrum is almost identical to that at the beginning of the experiment. This suggests that cathodic polarization reduces the pyrite surface to a state that is spectroscopically identical to the freshly ground condition.

Sulfur produced by electrochemical deposition from sulfides solutions at a platinum electrode can also be reduced. The sulfur was deposited at a potential of +1.0 V vs SCE in a 0.5 M NaCl solution with 2×10^{-3} M Na_2S . The Raman spectrum of the platinum surface after 25 minutes is shown in Fig. 33a. The voltage was then polarized to a potential of -0.93 V. Figs. 33b and 33c were taken 30 seconds and 2 minutes later, respectively. The absence of the sulfur

peaks indicates that the sulfur has been reduced from the surface.

The ability to electrochemically reduce sulfur suggests that it cannot be an electrical insulator as is elemental sulfur. The ability of the material to support a photocurrent (discussed elsewhere) also suggests that the sulfurous film has unusual electronic properties more akin to a semiconductor than an insulator.

3.3 Detection of Oxy-Sulfur Compounds

It has been suggested that oxy-sulfur compounds may be produced during the oxidation of pyrite [22]. However, ring-disc studies of the oxidation of sulfide ion on gold did not provide any evidence for oxy-sulfur species [2]. From thermodynamic considerations they would be expected in greater quantities at higher pH [23].

Sulfate is a known byproduct and has been measured as a function of oxidation potentials [24]. Woods, Constable and Hamilton have also looked for other oxy-sulfur species using a ring-disc electrode at pH 6, 9 and 13 [21]. On the basis of their coulometric analysis they concluded that none were produced and the oxidation products were entirely sulfur and sulfate. We have tried to observe the presence of sulfate ions which are indicated by a peak at approximately 985 cm^{-1} . We have generally been unsuccessful even though large quantities of charge (1 Coulomb) have been passed during the oxidation. On one occasion we have detected a very small peak at 990 cm^{-1} after prolonged oxidation at +1.2 V vs SCE in pH 2 (Fig. 34a). The addition of sodium sulfate to the solution caused a large increase in the size of the peak confirming its identification with the sulfate breathing mode (Fig. 34b). We believe the obstacle to the detection of sulfate is its considerable solubility. The sulfate dissolves immediately upon formation and is transported by diffusion away from the pyrite surface and out of the probe volume. If a porous

film is present on the surface such as ferrous or ferric hydroxide it may hinder the transport of the sulfate and remain in sufficient quantities in the film to be detected.

3.4 Electrochemical Oxidation of Galena-Raman Experiments

Thiosulfate has been implicated in the anodic oxidation of Galena [25]. Some preliminary work has been carried out at pH 6.5 to ascertain the existence of oxy-sulfur species (Figs. 35-40). None have so far been detected. However, strong Raman peaks similar to those observed on pyrite have been observed at potential of +0.13 V vs SCE and above (Figs. 37-40). In particular, the sulfur peak in the range 400-500 cm^{-1} is very broad and suggests that polysulfides are produced in a manner similar to that described for pyrite. This broad peak develops with time (Fig. 37) and eventually becomes indistinguishable from elemental sulfur (Fig. 41). It suggests that the initial products of the oxidation are short chain polysulfides. As more charge passes, more S is produced and the chains become longer. The Raman peaks of these S-S bonds will be shifted due to the different bond lengths. The longer chains will also have a tendency to arrange themselves into rings of different size. The final product is likely to be S_8 rings as it is the thermodynamically stable product at this temperature. Buckley *et al.* and Woods *et al.* have discussed the production of polysulfide chains in the context of their ring-disc electrode studies [2,21].

3.5 Reference Spectra

3.5.1 Elemental sulfur

The spectra of the oxidized pyrite samples can be compared with the Raman spectrum of pure elemental sulfur taken in air (Figs. 41 and 42). The peaks present are in good agreement

with previously published studies. In particular the paper of Harvey and Butler is important as it presents a detailed description of the origin of the peaks in the sulfur spectrum [17]. The fundamental vibrations are very strong. There are two fundamental vibration modes. The S-S stretch which produces a Raman peak at 470 cm^{-1} . Two strong peaks are also produced at 150 and 210 cm^{-1} due to bending of the S-S-S chain. All the other peaks in the range from 600 to 1000 cm^{-1} are overtones and combinations of these various modes and are much weaker.

Sulfur is a very strong Raman scatterer and sufficient counts can be obtained with this equipment to get good spectra in 0.1 second of integration.

3.5.2 Electrodeposited sulfur

As a source of comparison for the oxidization of pyrite, sulfur was electro-deposited on a platinum electrode. The cyclic voltammogram for platinum in a 0.5 M NaCl and $1 \times 10^{-3}\text{ M Na}_2\text{S}$ solution with a pH of 12.5 is shown in Fig. 43. Raman spectra were taken at potentials corresponding to the following anodic peaks: -0.10 , $+0.38$, $+0.80$, and $+1.20\text{ V vs SCE}$. Raman peaks characteristic of sulfur were observed at all of these potentials except at -0.80 V . Significantly more charge was passed as the oxidation potential was made more anodic (Fig. 48).

The Raman spectra closely resembled elemental sulfur. The peak at 470 cm^{-1} was sharp and did not have the broad multipeak observed during the oxidation of pyrite. This suggests that there are fewer species of polysulfide ion involved during the oxidation of sulfide ions to sulfur at a platinum electrode.

The height of the sulfur peak at 210 cm^{-1} was plotted as a function of potential after 20 minutes (Fig. 49). Assuming the alignment of the spectrometer to be approximately the same in each case, the peak height reaches a maximum at about $+0.5\text{ V vs SCE}$ and then decreases.

If the peak height is proportional to the quantity of sulfur produced then the coulombic efficiency of S production also passes through a maximum. If this is compared to the charge passed in the same time (Fig. 48) then we must conclude that another species must be being formed at the platinum disc or that the sulfur is being converted to a solution soluble species. This could be sulfate ion which is known to be an oxidation product of sulfur.

We have observed that the presence of sulfide ions in the solution can attenuate the Raman signal. If sulfur is electrodeposited on the Pt electrode and observed in deionized water a strong spectra is observed. However, the addition of a small amount of sodium sulfide greatly diminished the size of the sulfur peaks. This is probably due to the chemical dissolution of the sulfur by reaction with bisulfide ions to form soluble polysulfide ions as discussed by Buckley *et al.* [2].

3.5.3 Mineral Iron Sulfides

It has been suggested by Hamilton and Woods that one of the products of the oxidation of pyrite may be a non-stoichiometric compound of FeS [24]. The structural and chemical rearrangement of the substrate may lead to the alteration of the pyrite spectrum (peak position) or the creation of new peaks. Hence, samples of various types of mineral iron sulfides were obtained from Wards Scientific. For reference purposes Raman spectra were also taken from samples of Chalcopyrite (CuFeS_2) and Galena (PbS). All spectra were taken in air on a freshly cleaved surface using the 514.5 nm laser line.

The spectra for Pyrrhotite (FeS) and Marcasite (FeS_2) are shown in Figs. 50-53. As there are no S_2 molecules in Chalcopyrite, Galena, and Pyrrhotite, no Raman peaks were expected. This was the case for Pyrrhotite where only florescence was observed.

Marcasite has the same chemical formula as pyrite but has a slightly different crystal structure. It also consists of S_2 dumbbells. In Pyrite the disulfide atoms lie at the center of a cube and the cube edges. The mid-point of the S_2 group occupies the Cl sites of an NaCl structure, the Fe atoms occupy the Na positions. The S_2^{2-} pairs are oriented such that their axes are parallel to 4 non-intersecting body diagonals of the cubic lattice. If the S_2 is replaced by X then the structure can be seen to be made of MX_6 octahedra. In pyrite the MX_6 octahedra share corners while in marcasite they share edges and form chains of linked octahedra. The structure of metal sulfides is discussed in detail by Vaughan and Craig [26].

In Marcasite the ratios of the Ag to the Eg peak is smaller than in pyrite. It is possible that the smaller size of the Ag peak is because the crystal structure of marcasite disrupts the in-phase motion of the S-S stretch.

Three Raman peaks were detected on Galena, at 70, 120 and 980 cm^{-1} (Figs. 54 and 55). The origin of the two peaks at low cm^{-1} is unknown. However, the peak at 980 cm^{-1} is suspected to be due to the air oxidation product of Galena; possibly an oxy-sulfur compound such as thiosulfate.

The spectra of Chalcopyrite was surprising in that it closely resembled that of pyrite (Figs. 56 and 57). The nature of our sample must be verified, but our work suggests that pyrite may be associated with the Chalcopyrite.

3.5.4 Precipitated iron hydroxides

Iron (II) and (III) hydroxides should also be formed on the pyrite surface at high anodic potentials. The Raman spectra from the freshly precipitated iron(III) hydroxides exhibited no Raman peaks (Figs. 58 and 59). However, after several weeks in the laboratory drying slowly

in air, the ferric hydroxide did finally produce some Raman peaks (Figs. 60 and 61). The dehydration probably caused some crystallization of the material leading to a weak Raman spectra.

The hydroxides of iron are known to be weak Raman scatterers and the use of SERS has been necessary to obtain useful spectra [27,28]. There are reference spectra available in the literature. Of particular interest is the broad peak observed at 670 cm^{-1} by Thierry *et al.* which is attributed to hydrated and non-stoichiometric Fe_3O_4 [29]. Dunnwald and Otto present a series of reference spectra of iron hydroxides [11]. They show that $\text{Fe}(\text{OH})_3$ also has a small broad Raman peak centered at 696 cm^{-1} . We have observed similar peaks on pyrite oxidized at high anodic potentials in alkaline solutions.

Detailed studies of the iron hydroxides will require the use of SERS by using silver or gold substrates or by deposition of small islands of silver.

3.6 Particle bed experiments

A solution of pH 6.5 was used in these preliminary experiments. The bed was polarized at $+1.0\text{ V}$ vs SCE where previous experiments have demonstrated that sulfur was readily produced and detectable by Raman spectroscopy. However, after prolonged oxidation no evidence of sulfur was obtained but the pyrite peaks were clearly present (Fig. 62). The potential was increased in stages up to $+2.5\text{ V}$ but with no effect on the spectrum.

It has been suspected that the presence of ohmic potential drops may preclude the formation of sulfur. Poor interparticle contact may prevent electrochemical control. This may explain the lack of any significant increase in the floatation behavior of particulate pyrite over that due to entrainment during micro-floatation experiments.

There may be several solutions to this problem. Thorough cleaning of the pyrite surface by an acid etch prior to electrochemical treatment combined with the use of electrochemical reduction at a sufficiently negative potential.

Fluidization of the bed by agitation with a stirrer bar or gas may lead to enhanced particle contact with the platinum grid and eliminate the effect of ohmic potential drop.

3.7 The Electrochemical Oxidation Of Amyl Xanthate

It has been shown that xanthate collectors have to be oxidized to dixanthiogen to enhance the floatability of metal sulfides. The nature of this process is not fully understood. FTIR has been used to follow this process but this technique has the inherent problems associated with using IR radiation [30]. Some preliminary experiments were carried out to investigate if the oxidation process could be studied in-situ at the surface of metal sulfides using Raman spectroscopy.

A Raman spectra of solid amyl xanthate was taken in air (Fig. 63) as a reference. Raman peaks were detected only in the range 200-800 cm^{-1} .

A solution of 0.5 M NaCl was prepared with a small amount of amyl xanthate and placed in the electrochemical cell. The working electrode consisting of a platinum electrode was potentiostated at +0.2 V vs SCE. Raman spectra were taken at regular intervals.

Initially, no Raman peaks were detected. After 5 minutes some small broad peaks were detected which grew with time. The Raman spectra at 11 minutes is shown in Fig. 64. At this time oily drops were visible on the surface of the solution. After 15 minutes, Raman spectra were taken at higher cm^{-1} . A new peak was detected at 1050 cm^{-1} and 1460 cm^{-1} which were not present in solid amyl xanthate (Figs. 65 and 66).

We have shown that it is possible to follow the oxidation of collectors using Raman spectroscopy and certainly obtain qualitative information of the process. Quantitative studies will be more difficult and the issue of sensitivity to monolayers will become important.

The use of polarized light and variation in the incident angle will help elucidate the orientation of the adsorbed species at the surface.

PHOTOCURRENT EXPERIMENTS

4.1 Pyrite In Acid, Neutral, And Basic Conditions

The photocurrent-potential measurements were made for mineral pyrite in pH 2.5, 6.5 and 12.5. Only a qualitative comparison will be attempted in this preliminary study.

There are considerable differences between the photocurrent behavior at the different pH. No photo-current is detected under acid conditions. In basic solution, a strong photocurrent is observed only at anodic potentials above 0.0 V vs SCE. The photocurrent response in neutral solutions is complex with a large number of features on both anodic and cathodic cycles. The in-phase and out-of-phase components of the photocurrent for the neutral solution are shown in Figs. 67 and 68.

The photocurrent behavior in acid and alkali may be explained by the absence and presence of a ferric hydroxide film. One of the oxidation products of pyrite is ferric hydroxide which is soluble in acid but insoluble under alkali conditions. Photo-electrochemical studies of the corrosion of iron have shown that ferric films can produce a strong photo-current response [31,32]. In acid conditions the ferric hydroxide dissolves leaving no film capable of producing photocurrent. Conversely, the ferric hydroxide is very insoluble in basic conditions and a thick

film exists on the electrode which produces a strong photocurrent response. The size of the photocurrent has been related to the oxidation state of the film *i.e.* the Fe(II)/Fe(III) ratio [15,33].

The complex nature of the photocurrent at neutral pH suggests that many films of different electronic properties are present at different stages during the cyclic voltammogram.

There have been some studies of the photoelectrochemistry of pyrite [34-37]. However, these studies have mainly concentrated on the semiconducting properties of bulk pyrite and little attention was paid to the existence and nature of surface films. In particular, little work has been done to characterize the oxidation products of pyrite. In these studies careful attention must be paid to making good ohmic contacts to the metal sulfides as the metal-semiconductor contact is akin to a schottky barrier and can have appreciable resistance [38].

4.2 Electrodeposited Sulfur

Sulfur was deposited and reduced during a cyclic voltammetry experiment from a solution of 0.1 M Na₂S and 0.5 M NaCl with a pH of 6.5. The photocurrent-potential curve was measured concurrently. No attempt has been made in this study to analyze the photo-current spectra in detail. However, the film of electrodeposited sulfur is capable of producing a measurable photocurrent during both oxidation and reduction cycles. There is clearly a relationship between peaks on the cyclic voltammogram and photocurrent.

DISCUSSION

Raman spectroscopy has been able to characterize a pyrite surface in-situ during an electrochemical experiment. Strong spectra were observed in relatively short times providing the

possibility of being able to follow surface chemistry in real time without long integration periods to accumulate sufficient counts.

Elemental sulfur has a similar Raman spectrum to electrodeposited sulfur. Mycroft *et al.* have also reported similar spectra after prolonged periods of oxidation of up to 23 hours [7]. The features observed in our experiments on elemental sulfur are identical to those reported by Harvey and Butler who have characterized orthorhombic sulfur at 40 K [17]. The major and minor Raman peaks centered at 125.5 and 190 cm^{-1} were attributed to an S-S-S bending motion. The major and minor peaks centered at 474 cm^{-1} were attributed to S-S stretching. All the features at greater than 600 cm^{-1} were associated with various overtones and combinations of the previous stretching motions.

The sulfur formed by electrodeposition and oxidation of pyrite has sufficient interatomic bonding with other sulfur atoms to be able to generate the simplest forms of vibrations, namely the S-S stretch and S-S-S bend. However, the peak associated with the S-S stretch is very broad and is composed of many individual peaks. These peaks develop with time indicating that the relative distribution of polysulfide species is changing. It is known that the Raman shift is a strong function of the S-S bond length. Comparison with other work on inorganic polysulfides is in agreement with this interpretation [39,40]. Janz *et al.* have measured the Raman spectra of various potassium polysulfides and show that the S-S stretch for the polysulfide species S_3 , S_4 , S_5 and S_6 are at 466, 434 and 484, 432, and 373 cm^{-1} respectively [41]. Some work by Lenain *et al.* on the Raman spectra of sulfur vapor will also be useful in identifying the sulfur species [42]. At high temperatures, the sulfur S_8 ring breaks up into chains and rings of different length.

However, the ability to be able to reduce the sulfur formed by the oxidation of pyrite, indicates that the sulfur species must possess some degree of electrical conductivity. This indicates that sulfur formed electrochemically is not similar to orthorhombic sulfur which is an electrical insulator. The existence of a photocurrent from electrodeposited sulfur gives further evidence for its semiconducting nature.

Few oxy-sulfur species have been detected except for the occasional small peak attributed to sulfate. This is not surprising in view of the good solubility of these species, its detection depending upon it being trapped within the surface films on the pyrite.

The spectrum of the ferric hydroxide does not contain many distinct features and is very weak Raman spectra compared to pyrite and sulfur. There is a broad peak centered at 670 cm^{-1} . In other studies, strong spectra have been obtained for iron hydroxides using surface enhanced Raman scattering after the deposition of silver onto the surface. However, the ferric hydroxide films give strong photocurrent response and can be best examined with this technique.

FUTURE EXPERIMENTS

The long term objective of this study is to elucidate the character of the films formed on the surface of pyrite during electrochemical oxidation. Studies on other metal sulfides *e.g.*: Galena will help elucidate the mechanism of sulfur formation.

The electrochemistry of particle beds should be investigated further with modifications to ensure good electrical contact with the working electrode and better current distribution within the bed.

Photocurrent spectroscopy is a powerful tool and could provide useful information

concerning the electronic structure and properties of semiconducting sulfur films. It should be done in conjunction with differential capacity measurements to provide more information about the band bending in the material using Mott-Schottky plots. This will be a useful tool to study iron hydroxide films (and other metal hydroxide films *e.g.* lead) which are poor Raman scatterers.

The charge involved during the previously reported cyclic voltammetry experiments was equivalent to many monolayers. However, this estimate is complicated by an inaccurate assessment of the amount of sulfur on the surface using coulometric measurements. Combined ring-disc and Raman studies may help to solve this issue. Future experiments should concentrate on establishing the lower limit of detection of in-situ Raman spectra, in particular that of sulfur.

Spatial resolution should be obtained by using a cylindrical lens to project a line on the specimen instead of a spot. Alternatively, an optical microscope stage could be used to pinpoint regions of interest which could be subsequently analyzed by Raman using a focussed spot.

REFERENCES

- [1] S. A. Allison and N. P. Finkelstein, "A method for the determination of elemental sulfur on the surface of sulfide minerals," *NIM report No 1495*, Johannesburg, South Africa (1972).
- [2] A. N. Buckley, I. C. Hamilton and R. Woods, "An investigation of the sulfur (-II)/sulfur(0) system on gold electrodes," *J. Electroanal. Chem.* 216 213 (1987).
- [3] J. R. Gardner and R. Woods, "The use of a particulate bed electrode for the electrochemical investigation of metal and sulfide floatation," *Aust. J. Chem.* 26 1635-1644 (1973).

- [4] D. M. Bodily and M. E. Wadsworth, "Surface Electrochemical control for the fine coal and pyrite separation," Jan. 1 to Mar. 31 Technical Progress Report, DOE Project No. DE-AC22-89PC89758.
- [5] C. A. Murray and S. B. Dierker, "Use of an unintensified charge coupled detector for low light raman spectroscopy," *J. Opt. Soc. Am. A* 3 2151 (1986).
- [6] P. M. Epperson, J. V. Sweedler, R. B. Bilhom, G. R. Sims and M. Bonner-Denton, "Applications of charge transfer devices in spectroscopy," *Anal. Chem.* 60 327 (1988).
- [7] J. R. Mycroft, G. M. Bancroft, N. S. McIntyre, J. W. Lorimer and I. R. Hill, "Detection of sulfur and polysulfides on electrochemically oxidised pyrite surfaces by X-ray photoelectron spectroscopy and Raman spectroscopy," *J. Electroanal. Chem.* 292 139 (1990).
- [8] A. Campion, "Raman Spectroscopy" in *Vibrational spectroscopy of molecules on surfaces*, eds. J. T. Yates and T. E. Madey, Pub. Plenum N.Y. (1987).
- [9] R. L. Garrell, "Surface enhanced raman spectroscopy," *Anal. Chem.* 61 401A (1989).
- [10] R. L. McCreery and R. T. Packard, "Raman monitoring of dynamic electrochemical events," *Anal. Chem.* 61 775A (1989).
- [11] J. Dunnwald and A. Otto, "An investigation of phase transitions in rust layers using raman spectroscopy," *Corr. Sci.* 29 1167-1176 (1989).
- [12] H. Gerischer, "Models for the discussion of the photo-electrochemical response of oxide layers on metals," *Corr. Sci.* 29 257 (1989).
- [13] H. Gerischer, "The impact of semiconductors on the concepts of electrochemistry," *Elect. Acta.* 35 1677 (1990).
- [14] U. Stimming, "Photoelectrochemical studies of passive films," *Elect. Acta.* 31 415-429 (1986).
- [15] U. Stimming and J. W. Schultze, *Elect. Acta.* 24 859 (1979).
- [16] H. Vogt, T. Chattopadhyay and H. J. Stolz, "Complete first order raman spectra of the pyrite structure compounds FeS_2 , MnS_2 and SiP_3 ," *J. Phys. Chem. Solids*, 44 869 (1983).
- [17] P. D. Harvey and I. S. Butler, "Raman Spectra of Orthorhombic sulfur," *J. of Raman Spectroscopy*, 17 329 (1986).

- [18] S. Ushioda, "Raman scattering from phonons in iron pyrite (FeS_2)," *Solid Comm.* **10** 307 (1972).
- [19] S. Sato, S. Higuichi and S. Tanaka, "Identification and determination of oxygen containing inorganosulfur compounds by laser raman spectrometry," *Appl. Spect.* **39** 822 (1985).
- [20] J. Ralston, P. Alabaster and T. W. Healy "Activation of zinc sulfide with Cu(II) , Cd(II) and Pb(II) . The mass spectroscopic determination of elemental sulfur." *Int. J. Min. Proc.* **7** 279 (1981).
- [21] R. Woods, D. C. Constable and I. C. Hamilton, "A rotating ring disc electrode study of the oxidation of sulfur (-II) species on gold and sulfide minerals," *Int. J. Min. Proc.* **27** 309 (1989).
- [22] I. C. Hamilton and R. Woods, "*Proc. Int. Symp. Electrochemistry in mineral and metal Processing*", eds. Richardson P. E., Srinivasan S. and Woods R., Electrochemical Society N.J., pp. 259-285 (1984).
- [23] S. I. Zhdanov "Sulfur," *Encyclopedia of the electrochemistry of the elements* Volume 4, pg. 273.
- [24] I. C. Hamilton and R. Woods, "An investigation of surface oxidation of pyrite and pyrrhotite by linear sweep voltammetry," *J. Electroanal. Chem.* **118** 327 (1981).
- [25] R. L. Paul, M. J. Nicol, J. W. Diggle and A. P. Saunders, "The electrochemical behaviour of galena(lead sulfide)- 1 anodic dissolution," *Elect. Acta.* **23** 625-633 (1978).
- [26] D. J. Vaughan and J. R. Craig, "Mineral Chemistry of Metal Sulfides," Cambridge University Press (1978).
- [27] J. C. Rubim, "In-situ spectroelectrochemical study of the passivation of iron in alkaline solutions" *J. Chem. Soc. Farad. Trans. 1* **85(12)** 4247 (1989).
- [28] J. C. Rubim and J. Dunnwald, "Enhanced raman scattering from passive films on silver coated iron electrodes," *J. Electroanal. Chem.* **258** 327 (1989).
- [29] D. Thierry, D. Perrson, C. Leygraf, N. Boucherit and A. Hugot-Le Goff "Raman spectroscopy and XPS investigations of anodic corrosion films formed on Fe-Mo alloys in alkaline solutions," *Corr. Sci.* **32** 273 (1991).

- [30] J. O. Leppinen, C. I. Basilio and R. H. Yoon, "In-situ FTIR study of ethyl xanthate adsorption on sulfide minerals under conditions of controlled potential," *Int. J. Min. Proc.* **26** 259 (1989).
- [31] E. Ahlberg, K. S. E. Forssberg and X. Wang, "The surface oxidation of pyrite in alkaline solution," *J. Appl. Electrochem.* **20** 1033 (1990).
- [32] C. Suseri, S. Piazza, A. DiPaola and F. Di Quarto, "A photocurrent spectroscopic investigation of passive films on ferritic stainless steels," *J. Electrochem. Soc.* **134** 2410 (1987).
- [33] M. P. Dare-Edwards, J. B. Goodenough, A. Hamnett and P. Trevellick, *J. Chem. Soc. Farad. Trans. 1* **79** 2027 (1983).
- [34] A. Ennaoui, S. Fiechter, W. Jaegermann and H. Tributsch, "Photoelectrochemistry of highly quantum efficient single crystalline n-FeS₂ (pyrite)," *J. Electrochemical Society* **133** 97 (1986).
- [35] K. K. Mishra and Asseo-Asare "Photo-dissolution of coal pyrite," *Fuel* **66** 1161 (1987).
- [36] K. K. Mishra and Asseo-Asare, "Aspects of the interfacial electrochemistry of semiconductor pyrite (FeS₂)," *J. Electrochemical Society* **135** 2502 (1988).
- [37] T. Biegler, "Oxygen reduction on sulfide minerals," *J. Electroanal. Chem.* **70** 265 (1976).
- [38] A. L. Echarri and C. Sanchez "N type semiconductivity in natural single crystals of FeS₂ (pyrite)" *Solid State Comm.* **15** 827 (1974).
- [39] W. Giggenbach, "Optical spectra and equilibrium distribution of polysulfide ions in aqueous solution at 20 °C," *Inorg. Chem.* **11** 1201 (1972).
- [40] R. Steudel, "Homocyclic sulfur molecules," in *Inorganic ring systems* ed. T. Chivers *et al.*, Springer Verlag (1982).
- [41] G. J. Janz, J. W. Coutts, J. R. Downey and E. Roduner, "Raman studies of sulfur containing anions in inorganic polysulfides. Potassium polysulfides," *Inorg. Chem.* **15** 1755 (1976).
- [42] P. Lenain, E. Picquenard, J. Corset, D. Jensen and R. Steudel, "Raman spectrometric studies of the composition of sulfur vapor at temperature up to 700 °C", *Ber. Bunsenges. Phys. Chem.* **92** 859 (1988).

Figure 16 has been deleted

Fig. 1. Electrochemical cell used for Raman spectroscopy and photocurrent spectroscopy.

Fig. 2. Schematic diagram of apparatus used for Raman spectroscopy. L1-L4 are lenses, M1 is a mirror, and PF is a plasma line filter.

Fig. 3. Apparatus used for photocurrent spectroscopy.

Fig. 4. Raman spectrum of mineral pyrite.

Fig. 5. Cyclic voltammogram for pyrite in a 0.5 M NaCl solution with a pH of 2.7.
The scan rate is 50 mV/sec.

Fig. 6. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7.
The applied potential is -0.87 V.

Fig. 7. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7.
The applied potential is -0.63 V.

Fig. 8. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7. The applied potential is +0.06 V.

Fig. 9. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7.
The applied potential is +0.57 V.

Fig. 10. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7. The applied potential is +1.0 V.

Fig. 11. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7
The applied potential is +1.0 V.

Fig. 12. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.7. The applied potential is +1.0 V.

Fig. 13. Cyclic voltammogram for pyrite in a 0.5 M NaCl solution with a pH of 6.5.
The scan rate is 50 mV/sec.

Fig. 14. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is -0.76 V.

Fig. 15. Plot of Raman intensity as a function of charge for the Pyrite peak at 379 1/cm . The solution pH is 6.5 with an applied potential of -0.76 V.

Fig. 17. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is -0.15 V.

Fig. 18. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is +0.42 V.

Fig. 19. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is +0.62 V.

Fig. 20. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is +1.0 V.

Fig. 21. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is +1.0 V.

Fig. 22. Plot of Raman intensity as a function of charge for the Pyrite peak at 379 1/cm and the sulfur peak at 470 1/cm. The solution pH is 6.5 with an applied potential of +1.0 V.

Fig. 23. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 6.5. The applied potential is +1.0 V.

Fig. 24. Cyclic votammogram for pyrite in a 0.5 M NaCl solution with a pH of 12.5.
The scan rate is 50 mV/sec.

Fig. 25. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential is -0.40 V.

Fig. 26. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential is 0.0 V.

Fig. 27. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential is +0.35 V.

Fig. 28. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential is +0.62 V.

Fig. 29. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential is +1.0 V.

Fig. 30. Raman spectrum of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential of +0.62 V was applied for 15 minutes.

Fig. 31. Raman spectrum of oxidized pyrite in 0.5 M NaCl with a pH of 12.5. The applied potential of +0.62 V was applied for 17.5 minutes.

Fig. 32. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.0.
a) The applied potential is +0.80 V. b) The applied potential is -1.2 V.

Fig. 33. Raman spectra of electro-deposited sulfur on platinum. a) After applying a potential of +1.0 V for 25 minutes. b) 30 seconds after changing the potential to -0.93 V. c) 2 minutes at -0.93 V.

Fig. 34. Raman spectra of oxidized pyrite in 0.5 M NaCl with a pH of 2.0.
a) After oxidation at +1.2 V for 20 minutes. b) After addition of sodium sulfate to the solution.

Fig. 35. Cyclic voltammogram for Galena in a 0.5 M NaCl solution with a pH of 6.5.
The scan rate is 50 mV/sec.

Fig. 36. Raman spectra of oxidized Galena in 0.5 M NaCl with a pH of 6.5. The applied potential is -0.32 V.

Fig. 37. Raman spectra of oxidized Galena in 0.5 M NaCl with a pH of 6.5. The applied potential is +0.13 V.

Fig. 38. Raman spectra of oxidized Galena in 0.5 M NaCl with a pH of 6.5. The applied potential is +0.32 V.

Fig. 39. Raman spectra of oxidized Galena in 0.5 M NaCl with a pH of 6.5. The applied potential is +0.57 V.

Fig. 40. Raman spectra of oxidized Galena in 0.5 M NaCl with a pH of 6.5. The applied potential is +1.0 V.

Fig. 41. Raman spectrum of elemental sulfur taken in air showing the stretching and bending vibrational modes.

Fig. 42. Raman spectrum of elemental sulfur showing the overtones and combinations of the fundamental modes.

Fig. 43. Cyclic voltammogram for platinum in a 0.5 M NaCl and .001 M Na₂S solution with a pH of 12.5. The scan rate is 50 mV/sec.

Fig. 44. Raman spectra of electro-deposited sulfur on platinum with a solution pH of 12.5. The applied potential is -0.10 V.

Fig. 45. Raman spectra of electro-deposited sulfur on platinum with a solution pH of 12.5. The applied potential is +0.38 V.

Fig. 46. Raman spectra of electro-deposited sulfur on platinum with a solution pH of 12.5. The applied potential is +0.80 V.

Fig. 47. Raman spectra of electro-deposited sulfur on platinum with a solution pH of 12.5. The applied potential is +1.2 V.

Fig. 48. Amount of charge deposited on the platinum electrode in 20 minutes as a function of potential.

Fig. 49. Height of sulfur peak at 210 $1/\text{cm}$ plotted as a function of potential after 20 minutes.

Fig. 50. Raman spectrum of Pyrrhotite.

Fig. 51. Raman spectrum of Pyrrhotite.

Fig. 52. Raman spectrum of Marcasite.

Fig. 53. Raman spectrum of Marcasite.

Fig. 54. Raman spectrum of Galena.

Fig. 55. Raman spectrum of Galena.

Fig. 56. Raman spectrum of Chalcopyrite.

Fig. 57. Raman spectrum of Chalcopyrite.

Fig. 58. Raman spectrum of precipitated ferric hydroxide.

Fig 59. Raman spectrum of precipitated ferric hydroxide.

Fig. 60. Raman spectrum of precipitated ferric hydroxide left in air for two weeks.

Fig. 61. Raman spectrum of precipitated ferric hydroxide left in air for two weeks.

Fig. 62. Raman spectrum of pyrite particles in 0.5 M NaCl with a pH of 6.5. The bed was polarized at +1.0 V for 10 minutes.

Fig. 63. Raman spectrum of solid amyl xanthate taken in air.

Fig. 64. Raman spectrum of a platinum electrode in a 0.5 M NaCl solution with amyl xanthate. The electrode was polarized at +0.2 V for 11 minutes.

Fig. 65. Raman spectrum of a platinum electrode in a 0.5 M NaCl solution with amyl xanthate. The electrode was polarized at +0.2 V for 15 minutes.

Fig. 66. Raman spectrum of a platinum electrode in a 0.5 M NaCl solution with amyl xanthate. The electrode was polarized at +0.2 V for 18 minutes.

Fig. 67. Photocurrent -potential curve for pyrite in a 0.5 M NaCl solution with a pH of 6.5.
In-phase component.

Fig. 68. Photocurrent -potential curve for pyrite in a 0.5 M NaCl solution with a pH of 6.5.
Out of phase component.

END

**DATE
FILMED**

2 / 18 / 92